SUPPORT EFFECTS STUDIED ON MODEL SUPPORTED CATALYSTS

Progress Report

for Period April 1, 1991 — March 31, 1992

R. G. Gorte

University of Pennsylvania
Philadelphia, PA 19104

November 1991

Received by OSTI
APR 13 1992

Prepared for

THE U.S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG02-85ER13350

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EP

Results for 1990/91:

We are studying model catalysts in which the active phase is deposited onto flat oxide substrates in order to understand how a catalyst is affected by its support. Particular emphasis is being placed on metals catalysis for application to automotive emissions control and to acidity in supported oxides.

The first of our results from the last year was actually aimed at finishing our studies of titania support effects in order to resolve a question about the migration of titania in group VIII metals. We examined the growth and stability of titania overlayers which had been vapor deposited onto a Rh foil. Titania was found to grow layer by layer, with approximately 1×10^{15} TiO_x species/ cm^2 in the first layer. Submonolayer coverages of titania were unaffected by heating the sample to temperatures as high as 1320K. However, heating multilayer coverages to 1320K resulted in one monolayer remaining on the surface, with the rest migrating into the Rh. The migrating titania could be brought back to the surface by removing the top monolayer and heating the sample above 900K in vacuum. Saturation coverages of CO were found to decrease linearly with surface titania coverage, independent of sample treatment; however, annealing to high temperatures appears to remove defects in the titania overlayer.

We next examined the growth of Pt films on $\text{ZnO}(0001)\text{Zn}$ and $\text{ZnO}(0001)\text{O}$ and compared the results to those obtained for Pt on $\alpha\text{-Al}_2\text{O}_3(0001)$. Samples were prepared by vapor deposition of Pt onto flat substrates in ultra high vacuum, and metal coverages were measured using a quartz-crystal, film thickness monitor. On both ZnO surfaces, Auger electron spectroscopy (AES) and transmission electron microscopy (TEM) indicated that Pt grows as a 2-D film at 300K, in contrast to results for Pt on $\alpha\text{-Al}_2\text{O}_3(0001)$ where 3-D particles are formed under these conditions. Furthermore, transmission electron diffraction (TED) showed that the Pt grew as an ordered overlayer on the ZnO crystals. Heating the Pt/ZnO surfaces resulted in the formation of Pt particles starting at ~650K, but the Pt particles were still oriented with the ZnO. On both ZnO surfaces, temperature programmed desorption (TPD) curves for CO from high Pt coverages (> one monolayer) and from Pt particles formed by heating thinner films were identical to TPD curves for CO from Pt on $\alpha\text{-Al}_2\text{O}_3(0001)$. The main desorption features were observed at 400 and 510K and are interpreted as being due to different site geometries on the Pt by comparison to results from Pt single crystals. However, for Pt at submonolayer coverages prior to particle formation, the TPD curves for CO from Pt on $\text{ZnO}(0001)\text{Zn}$ were shifted down in temperature by ~60K compared to results for Pt on $\text{ZnO}(0001)\text{O}$. These results are interpreted as indicating a chemical interaction between Pt and the Zn^{+2} ions which are in direct contact.

We next examined the structure and CO adsorption properties of Pt films vapor deposited onto a $\text{ZrO}_2(100)$ crystal. AES indicated that the growth of the film was almost two-dimensional at 300K; however, TEM showed that the films formed particles upon exposure to air or mild heating above 350K. TED indicated that these islands were oriented with respect to the underlying ZrO_2 lattice, even for particles formed by heating to 850K which were larger than 50Å for deposition of

$2 \times 10^{15} \text{ Pt/cm}^2$. TPD of CO from relatively high Pt coverages ($> 1 \times 10^{15} \text{ Pt/cm}^2$) and from Pt following particle formation showed desorption features at 400 and 510K, similar to features found on Pt single crystals. For submonolayer quantities of Pt prior to annealing, a single CO desorption feature was observed at ~460K, which is ~50K lower than the peak temperature found for low Pt coverages on noninteracting supports. This shift appears to be due to interactions between Pt and the metal cations which are present on the $\text{ZrO}_2(100)$ surfaces.

To determine whether the conclusions reached for Pt on ZrO_2 could be extended to other supported metals, we studied the deposition of Rh on a $\text{ZrO}_2(100)$ crystal. As with Pt, film growth is close to two dimensional for Rh at 300K and metal particles are formed by heating above ~500K. TED again indicated that the Rh particles are preferentially oriented with respect to the substrate which implies that interactions exist between the support and the Rh. TPD curves for CO were essentially independent of particle size and similar to curves obtained on bulk Rh crystals. However, TPD curves for NO were strongly affected by particle size and film annealing. For particles between 3 and 10 nm formed by annealing, more than 98% of the NO dissociated during TPD from a saturation exposure. For the 10-nm particles, the TPD were similar to curves on bulk metals in that N_2 left the surface from two separate features: a sharp peak at 440K due to $\text{NO}_{\text{ad}} + \text{N}_{\text{ad}} = \text{N}_2 + \text{O}_{\text{ad}}$ and a broad feature between 450 and 700K due to N_{ad} recombination. For smaller particles, only the recombination feature was observed at approximately the same temperature.

The adsorption of NO on Pt particles supported on CeO_2 , $\alpha\text{-Al}_2\text{O}_3(0001)$, and the Zn- and O-polar surfaces of $\text{ZnO}(0001)$ was also studied. Both support composition and particle size influenced the TPD results. For CeO_2 and $\alpha\text{-Al}_2\text{O}_3(0001)$, the TPD curves were essentially identical, and observed changes appear to be due to particle size only. An upward shift from 460 to ~550K was observed in the N_2 peak temperature when the particle size decreased below ~2.5 nm. Changes in the TPD curves for NO from Pt on the ZnO surfaces were more dramatic. Significant amounts of N_2O were observed in TPD for small particles and a N_2 desorption peak was observed at ~650K.

In addition to our work with supported metals, we have also begun to investigate supported oxides in order to understand the acidic properties that have been reported for monolayer oxides. Our first studies were of amorphous, silica-alumina catalysts, in a collaborative study with David Chapman of WR Grace. We were able to show that the TPD-TGA techniques which we developed with zeolites work well for characterizing acidity of amorphous catalysts. For desorption of isopropylamine, we observe a well defined feature in TPD corresponding to the reaction of the amine to form propene and ammonia. Reaction occurs between 575 and 650K, the same temperature at which reaction occurs at Brønsted sites in high-silica zeolites. This feature is not observed on pure silica or alumina, suggesting that we are able to distinguish the unique sites which are present on the mixed oxides.

Finally, we have also begun to prepare model supported oxides in order to be able to use spectroscopic methods to characterize the sites formed on these materials. Our first studies were of niobia deposition on oxidized Al films and on an α - $\text{Al}_2\text{O}_3(0001)$ crystal. Vapor deposition of niobia resulted in amorphous, two-dimensional films which were stable upon heating up to at least 900K in vacuum. The presence of niobia had no measureable effect on the acidity of the samples. TPD of 2-propanol and isopropylamine occurred from sharp desorption features at 185K and 140K respectively on all surfaces examined, indicating that no acid sites were present on any of samples. An alternate approach to deposition of niobia using $\text{Nb}(\text{C}_2\text{H}_5\text{O})_5$ resulted in significant carbon contamination. While our initial efforts were not successful in preparing models with similar properties to those obtained on high-surface-area catalysts, we are continuing our efforts to prepare adequate models.

Publications Citing DOE Support for 1990-91:

1. "A Study of the Migration and Stability of Titania on a Model Rh Catalyst", S. Roberts and R.J. Gorte, *Journal of Catalysis*, 124 (1990) 553.
2. "A Comparison of Pt Overlayers on α - $\text{Al}_2\text{O}_3(0001)$, $\text{ZnO}(0001)$, and $\text{ZnO}(000\bar{1})$ ", S. Roberts and R.J. Gorte, *Journal of Chemical Physics*, 93 (1990) 5337.
3. "A Study of Pt Films on $\text{ZrO}_2(100)$ ", S.I. Roberts and R.J. Gorte, *Journal of Physical Chemistry*, 95 (1991) 5600.
4. "Adsorption of CO and NO on $\text{Rh}/\text{ZrO}_2(100)$ ", G. Zafiris and R.J. Gorte, *Journal of Catalysis*, 132 (1991) 000.
5. "A Study of Niobia Deposition on α - $\text{Al}_2\text{O}_3(0001)$ and Oxidized Al", S.I. Roberts and R.J. Gorte, *Applied Surface Science*, accepted.
6. "A Study of NO Adsorption on Model Pt and Rh Catalysts", G. Zafiris, S. Roberts and R.J. Gorte, submitted for publication.
7. "A Characterization of the Acid Sites in Amorphous Silica-Aluminas", J. Tittensor, R.J. Gorte, and D. Chapman, in preparation.
8. "Characterization of Model Pt/CeO_2 Catalysts", G. Zafiris and R.J. Gorte, in preparation.

Plans for 1991/92:

First, we are beginning to carry out reaction kinetics (CO oxidation and NO reduction by CO) on the model, supported metals which have already been

characterized by TPD and TEM. These measurements are being carried out in a high-pressure cell on samples which have been examined in vacuum with AES. Our initial results have demonstrated that CO oxidation on Pt is structure sensitive, as should be expected based on the variations in the TPD curves observed as a function of particle size. We are attempting to determine whether the support can also modify the reaction properties.

Second, we are continuing our studies ceria support effects by depositing Pt and Rh onto flat ceria supports. While our initial results with Pt suggest that support effects with ceria are not strong compared with zirconia or ZnO, we plan examine these systems more closely with TEM and to measure reaction kinetics in order to determine the extent of support effects with ceria.

Third, we have recently acquired the capabilities to low energy ion scattering in collaboration with Dr. Tom Buck, recently retired from Bell Labs. The system for carrying out these measurements uses a time-of-flight detector and can actually determine the positions of the top layer of atoms in relation to the substrate for ordered systems. We plan to apply this technique to Pt on ZnO(0001), for which our earlier results have shown that the metal forms ordered, monolayer coverages for deposition at room temperature. It is our hope that LEIS will be able to show how the Pt is bonded to the substrate, which will in turn show how the support can affect the metal properties.

While our initial results obtained with model supported oxides were not successful, our work with high-surface-area materials has demonstrated TPD is capable of monitoring the unique sites formed at mixed-oxide surfaces. Therefore, we plan to continue to look for methods of preparing model systems with similar sites to those present on high-surface-area samples. Our next attempts will involve preparing flat materials using methods similar to that for real catalysts and studying them in UHV in order to show that our methods of studying these catalysts is appropriate.

END

**DATE
FILMED**

5 / 14 / 92