RECEIVED
JUN 10 1993
OSTI

DOE/CE/23810-11

**MATERIALS COMPATIBILITY AND LUBRICANTS RESEARCH
ON CFC-REFRIGERANT SUBSTITUTES**

**Quarterly MCLR Program
Technical Progress Report**

1 January 1993 - 31 March 1993

David S. Godwin
Glenn C. Hourahan
Steven R. Szymurski

**Air-Conditioning and Refrigeration
Technology Institute, Inc.**
4301 North Fairfax Drive, Suite 425
Arlington, Virginia 22203

April 1993

Prepared for

The U.S. DEPARTMENT OF ENERGY
Grant Number DE-FG02-91CE23810

This program is supported, in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this program constitutes of \$4,143,000 or 93.67% of allowable costs. Funding from non-government sources supporting this program consists of direct cost sharing totaling \$280,000 or 6.33% of allowable costs, and significant in-kind contributions from the air-conditioning and refrigeration industry.

MASTER
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED *db*

DISCLAIMER

The U.S. Department of Energy's and the air-conditioning industry's support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared on account of work sponsored by the United States Government. Neither the United States Government, nor the Department of Energy, nor the Air-Conditioning and Refrigeration Technology Institute, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE

By acceptance of this article the publisher and/or recipient acknowledges the rights of the U.S. Government and the Air-Conditioning and Refrigeration Technology Institute, Inc. (ARTI) to retain a nonexclusive, royalty-free license in and to any copyright covering this paper.

TABLE OF CONTENTS

<u>ABSTRACT</u>	1
<u>SCOPE</u>	1
<u>SIGNIFICANT RESULTS</u>	2
ON-GOING PROJECTS	
Thermophysical Properties	2
Miscibility of Lubricants with Refrigerants	8
Compatibility of Refrigerants and Lubricants with Motor Materials	10
Compatibility of Refrigerants and Lubricants with Elastomers	15
Compatibility of Refrigerants and Lubricants with Engineering Plastics	19
Measurement of Viscosity, Density, and Gas Solubility of Refrigerant Azeotropes and Blends in Selected Refrigerant Lubricants	22
Viscosity, Solubility, and Density Measurements of Refrigerant -Lubricant Mixtures	23
Electrohydrodynamic (EHD) Enhancement of Pool and In-Tube Boiling of Alternative Refrigerants	33
Accelerated Screening Methods for Predicting Lubricant Performance in Refrigerant Compressors	34
Accelerated Test Methods for Predicting the Life of Motor Materials Exposed to Refrigerant-Lubricant Mixtures	36
Accelerated Screening Methods for Determining Chemical and Thermal Stability of Refrigerant-Lubricant Mixtures	36
Refrigerant Database	37
COMPLETED PROJECTS	
Theoretical Evaluations of R-22 Alternative Fluids	39
Chemical and Thermal Stability of Refrigerant-Lubricant Mixtures with Metals	40
COMPLIANCE WITH AGREEMENT	41
PRINCIPAL INVESTIGATOR'S EFFORT	41

MATERIALS COMPATIBILITY AND LUBRICANT RESEARCH ON CFC-REFRIGERANT SUBSTITUTES

ABSTRACT

The Materials Compatibility and Lubricants Research (MCLR) program supports critical research to accelerate the introduction of CFC-refrigerant substitutes. The MCLR program addresses refrigerant and lubricant properties and materials compatibility. The primary elements of the work include data collection and dissemination, materials compatibility testing, and methods development. The work is guided by an Advisory Committee consisting of technical experts from the refrigeration and air-conditioning industry and government agencies. Under the current MCLR program the Air-Conditioning and Refrigeration Technology Institute, Inc., (ARTI) is contracting and managing multiple research projects and a data collection and dissemination effort. Detailed results from these projects are reported in technical reports prepared by each researcher.

SCOPE

The Materials Compatibility and Lubricant Research (MCLR) program is a 36 month research grant administered by the Air-Conditioning and Refrigeration Technology Institute (ARTI), a not-for-profit organization for scientific research in the public interest. The program was implemented on 30 September 1991 and, as currently funded, will run through 30 September 1994. The MCLR program currently consists of a number of research projects grouped in phases. Phase I encompasses seven research projects and a data collection and dissemination project. Phase I projects began in January 1992 and were scheduled for completion in March 1993. However, several of these projects have been extended due to schedule delays or added work. Phase II currently consists of eight research projects and a data collection and dissemination project. Phase II projects began in October 1992 and will run through September 1994. This report summarizes the research conducted during the 1st quarter of calendar year 1993.

SIGNIFICANT RESULTS

ON-GOING PROJECTS

THERMOPHYSICAL PROPERTIES

Objective:

To provide highly accurate, selected thermophysical properties data for refrigerants HFC-32, HCFC-123, HCFC-124, HFC-125, HFC-143a and HFC-152a; and to fit these data to simple, theoretically-based equations of state, as well as complex equations of state and detailed transport property models. The new data will fill the gaps in existing data sets and resolve the problems and uncertainties that exist in and between the data sets. Thermodynamic properties measurements and determinations will include vapor pressure-volume-temperature behavior, liquid pressure-volume-temperature behavior, saturation and critical points, vapor sound speed and ideal gas heat capacity, isochoric heat capacity, Carnahan-Starling-DeSantis (CSD) and the modified Benedict-Webb-Rubin (MBWR) equations of state. Transport properties measurements and correlations will include thermal conductivity and viscosity measurements.

Results:

The Thermophysics Division of the National Institute of Standards and Technology (NIST) has completed the initial portion of this research which included measurements on four alternative refrigerants. Measurements and correlations of HFC-143a and HFC-152a were added to the project in January 1993. This will extend the project through 31 March 1994. A detailed report on results for HFC-32, HCFC-123, HCFC-124 and HFC-125 is presented in DOE report number DOE/CE/23810-16, *Thermophysical Properties*, Final Report, April 1993, by Dr. Richard F. Kayser. This report is still undergoing final review and will be available upon approval by ARTI. Key results are summarized below:

HFC-32:

NIST has developed a 32-term MBWR equation of state (Table 1) for HFC-32. The equation is reported to be valid at temperatures from the triple point at 137 K (-213°F) to 400 K (260°F), and it may be reasonably extrapolated up to 500 K (440°F). The maximum pressure for the equation is 40 MPa (6000 psi), and it may be reasonably extrapolated up to 100 MPa (15000 psi). NIST fitted the equation using a multi-parameter linear least squares routine on the measured data.

HCFC-123:

NIST has revised and the existing MBWR equation of state for HCFC-123. This work was prompted by an evaluation of equations of state for HFC-134a and HCFC-123 carried out by Annex 10 of the International Energy Agency. Weaknesses revealed during the evaluation included the derived properties for speed of sound and heat capacity. The revised equation (Table 2) is reported to be valid at temperatures from just above the triple point at to 550 K (530°F) and at pressures to 40 MPa (6000 psi).

HCFC-124:

NIST has developed a 32-term MBWR equation of state (Table 3) for HCFC-124. The equation is reported to be valid at temperatures from 210 K (-82°F) to 450 K (350°F), and it may be reasonably extrapolated up to 500 K (440°F). The maximum pressure for the equation is 20 MPa (3000 psi).

HFC-125:

NIST has developed a 32-term MBWR equation of state (Table 4) for HFC-125. The equation is reported to be valid at temperatures from 200 K to 400 K (-100°F to 260°F). It may be reasonably extrapolated up to 500 K (440°F). The maximum pressure for the equation is 20 MPa (3000 psi).

TABLE 1. Coefficients to the MBWR equation of state for HFC-32
(units are K, bar, L, mol)

$$p = \sum_{n=1}^9 a_n \rho^n + \exp(-\rho^2/\rho_c^2) \sum_{n=10}^{15} a_n \rho^{2n-17}$$

$$\rho_c = 8.1245 \text{ mol/L} \quad R = 8.314471 \text{ J/K-mol (gas constant)}$$

$$\begin{aligned} a_1 &= RT \\ a_2 &= b_1 T + b_2 T^{0.5} + b_3 + b_4/T + b_5/T^2 \\ a_3 &= b_6 T + b_7 + b_8/T + b_9/T^2 \\ a_4 &= b_{10} T + b_{11} + b_{12}/T \\ a_5 &= b_{13} \\ a_6 &= b_{14}/T + b_{15}/T^2 \\ a_7 &= b_{16}/T \\ a_8 &= b_{17}/T + b_{18}/T^2 \\ a_9 &= b_{19}/T^2 \\ a_{10} &= b_{20}/T^2 + b_{21}/T^3 \\ a_{11} &= b_{22}/T^2 + b_{23}/T^4 \\ a_{12} &= b_{24}/T^2 + b_{25}/T^3 \\ a_{13} &= b_{26}/T^2 + b_{27}/T^4 \\ a_{14} &= b_{28}/T^2 + b_{29}/T^3 \\ a_{15} &= b_{30}/T^2 + b_{31}/T^3 + b_{32}/T^4 \end{aligned}$$

i	b _i		
1	-0.184799147712E-01	17	-0.399464119357E-04
2	0.199258716261E+01	18	0.653548292730E-01
3	-0.450818142855E+02	19	-0.119312200130E-02
4	0.517320130169E+04	20	-0.896057555372E+05
5	-0.770847082500E+06	21	-0.218872108921E+08
6	-0.170184611963E-03	22	-0.189705435851E+04
7	-0.143023459131E+01	23	0.310718784685E+08
8	0.606314008455E+03	24	-0.126638710844E+02
9	0.192559574847E+06	25	0.246519270465E+04
10	-0.596044051707E-04	26	-0.231516734828E-01
11	0.297147086969E+00	27	-0.438977929243E+04
12	-0.104964078480E+03	28	-0.315318636002E-03
13	-0.775008265186E-02	29	0.139459067806E+00
14	0.222564856042E+00	30	0.163298486259E-06
15	-0.330783818273E+02	31	-0.326147254524E-03
16	-0.313533565119E-02	32	0.342233333783E-01

TABLE 2. Coefficients to the MBWR equation of state for HCFC-123
(units are K, bar, L, mol)

$$p = \sum_{n=1}^9 a_n \rho^n + \exp(-\rho^2/\rho_c^2) \sum_{n=10}^{15} a_n \rho^{2n-17}$$

$$\rho_c = 3.596417 \text{ mol/L} \quad R = 8.314471 \text{ J/K-mol (gas constant)}$$

$$\begin{aligned} a_1 &= RT \\ a_2 &= b_1 T + b_2 T^{0.5} + b_3 + b_4/T + b_5/T^2 \\ a_3 &= b_6 T + b_7 + b_8/T + b_9/T^2 \\ a_4 &= b_{10} T + b_{11} + b_{12}/T \\ a_5 &= b_{13} \\ a_6 &= b_{14}/T + b_{15}/T^2 \\ a_7 &= b_{16}/T \\ a_8 &= b_{17}/T + b_{18}/T^2 \\ a_9 &= b_{19}/T^2 \\ a_{10} &= b_{20}/T^2 + b_{21}/T^3 \\ a_{11} &= b_{22}/T^2 + b_{23}/T^4 \\ a_{12} &= b_{24}/T^2 + b_{25}/T^3 \\ a_{13} &= b_{26}/T^2 + b_{27}/T^4 \\ a_{14} &= b_{28}/T^2 + b_{29}/T^3 \\ a_{15} &= b_{30}/T^2 + b_{31}/T^3 + b_{32}/T^4 \end{aligned}$$

i b_i

1	-0.193042434973E-01	17	0.106201732381E+00
2	-0.263410206086E+00	18	-0.401991529370E+02
3	0.266439262928E+02	19	0.156703568146E+01
4	-0.102447174272E+05	20	0.395804226685E+07
5	-0.714962376060E+06	21	-0.490428403406E+09
6	0.179594735089E-01	22	0.171175389582E+06
7	-0.106601466621E+02	23	0.376067424212E+10
8	-0.106973465680E+04	24	0.719667521763E+04
9	-0.150556666672E+07	25	-0.110348184730E+07
10	-0.126504809410E-02	26	0.571211837951E+02
11	-0.123264787943E+00	27	0.642498617888E+07
12	0.293238981229E+03	28	0.227383595657E+01
13	0.134389339775E+00	29	-0.670239087161E+03
14	0.745030119681E+01	30	-0.162446239669E-01
15	0.413916532768E+04	31	0.190850894641E+02
16	-0.212267981526E+01	32	-0.267293932199E+04

TABLE 3. Coefficients to the MBWR equation of state for HCFC-124
(units are K, bar, L, mol)

$$p = \sum_{n=1}^9 a_n \rho^n + \exp(-\rho^2/\rho_c^2) \sum_{n=10}^{15} a_n \rho^{2n-17}$$

$$\rho_c = 4.10153 \text{ mol/L} \quad R = 8.314471 \text{ J/K-mol (gas constant)}$$

$$\begin{aligned} a_1 &= RT \\ a_2 &= b_1 T + b_2 T^{0.5} + b_3 + b_4/T + b_5/T^2 \\ a_3 &= b_6 T + b_7 + b_8/T + b_9/T^2 \\ a_4 &= b_{10} T + b_{11} + b_{12}/T \\ a_5 &= b_{13} \\ a_6 &= b_{14}/T + b_{15}/T^2 \\ a_7 &= b_{16}/T \\ a_8 &= b_{17}/T + b_{18}/T^2 \\ a_9 &= b_{19}/T^2 \\ a_{10} &= b_{20}/T^2 + b_{21}/T^3 \\ a_{11} &= b_{22}/T^2 + b_{23}/T^4 \\ a_{12} &= b_{24}/T^2 + b_{25}/T^3 \\ a_{13} &= b_{26}/T^2 + b_{27}/T^4 \\ a_{14} &= b_{28}/T^2 + b_{29}/T^3 \\ a_{15} &= b_{30}/T^2 + b_{31}/T^3 + b_{32}/T^4 \end{aligned}$$

i	b _i		
1	-0.204576807203E+00	17	-0.688566863825E-01
2	0.183289763904E+02	18	-0.132391812938E+02
3	-0.436304129852E+03	19	0.667600131841E+00
4	0.784900629507E+05	20	-0.271799858829E+07
5	-0.882621240790E+07	21	-0.111422740208E+09
6	-0.214052457908E-02	22	-0.175854504297E+06
7	-0.421490706906E+01	23	0.566801130630E+10
8	0.379367628599E+04	24	-0.214018815397E+04
9	0.257319006570E+07	25	-0.327561948065E+06
10	-0.128703560721E-02	26	-0.546930696467E+02
11	0.318383860178E+01	27	0.931832376640E+06
12	-0.126323679904E+04	28	0.193654970621E-02
13	-0.359253621024E-01	29	-0.110844683745E+03
14	-0.201822160275E+02	30	-0.452370482664E-02
15	0.239512195711E+03	31	0.163031126242E+01
16	0.249923391219E+01	32	-0.681395650661E+03

TABLE 4. Coefficients to the MBWR equation of state for HFC-125
(units are K, bar, L, mol)

$$p = \sum_{n=1}^9 a_n \rho^n + \exp(-\rho^2/\rho_c^2) \sum_{n=10}^{15} a_n \rho^{2n-17}$$

$$\rho_c = 4.7650 \text{ mol/L} \quad R = 8.314471 \text{ J/K-mol (gas constant)}$$

$$\begin{aligned} a_1 &= RT \\ a_2 &= b_1 T + b_2 T^{0.5} + b_3 + b_4/T + b_5/T^2 \\ a_3 &= b_6 T + b_7 + b_8/T + b_9/T^2 \\ a_4 &= b_{10} T + b_{11} + b_{12}/T \\ a_5 &= b_{13} \\ a_6 &= b_{14}/T + b_{15}/T^2 \\ a_7 &= b_{16}/T \\ a_8 &= b_{17}/T + b_{18}/T^2 \\ a_9 &= b_{19}/T^2 \\ a_{10} &= b_{20}/T^2 + b_{21}/T^3 \\ a_{11} &= b_{22}/T^2 + b_{23}/T^4 \\ a_{12} &= b_{24}/T^2 + b_{25}/T^3 \\ a_{13} &= b_{26}/T^2 + b_{27}/T^4 \\ a_{14} &= b_{28}/T^2 + b_{29}/T^3 \\ a_{15} &= b_{30}/T^2 + b_{31}/T^3 + b_{32}/T^4 \end{aligned}$$

i	b _i		
1	0.695150135527E-01	17	-0.637258406198E-01
2	-0.109596263920E+02	18	0.291220108725E+02
3	0.289171467191E+03	19	-0.102197580663E+01
4	-0.510408655996E+05	20	-0.560938443772E+07
5	0.366753946576E+07	21	0.770104599552E+08
6	0.385350808228E-01	22	-0.224544749331E+06
7	-0.370988373715E+02	23	0.183452398750E+10
8	0.134556555861E+05	24	-0.292476384933E+04
9	0.371143622964E+07	25	-0.388467529252E+05
10	-0.123685768773E-02	26	-0.339743229627E+02
11	0.130495983411E+01	27	-0.544169038319E+06
12	-0.468463056623E+03	28	-0.168305711698E+00
13	0.511361375061E-01	29	0.115387298598E+02
14	-0.204695459886E+02	30	-0.734893856572E-03
15	-0.414622181605E+04	31	-0.329200834300E+00
16	0.219744136091E+01	32	-0.403885226023E+01

MISCIBILITY OF LUBRICANTS WITH REFRIGERANTS

Objective:

To provide information on the miscibility of both current and new lubricants with potential substitutes for CFC refrigerants.

Results:

Iowa State University of Science and Technology is performing this research under contract with ARTI. Part 1 of the project, preliminary miscibility screening, has been completed. These studies examined mixtures at three refrigerant-lubricant concentrations (10, 50, and 95% refrigerant by weight) and a single viscosity for each lubricant. A detailed report on the results of this research is presented in DOE report number DOE/CE/23810-6, *Miscibility of Lubricants with Refrigerants (Phase 1)*, Final Report, October 1992, by Dr. Michael B. Pate, Mr. Steven C. Zoz, and Mr. Lyle J. Berkenbosch. Table 5 summarizes the results of the Phase 1 miscibility studies.

Iowa State University is continuing with Phase 2 of the project which encompasses more detailed miscibility plots with five additional refrigerant-lubricant concentrations (20, 35, 65, 80 and 90% refrigerant by weight) and two viscosity grades for each lubricant.

TABLE 5. Miscibility Results

HCFC-22			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	M	M	M
modified polyglycol	I	M	M
naphthenic mineral oil	M	< -20 deg C	< -30 deg C
pentaerythritol ester mixed acid #1	M	M	M
pentaerythritol ester mixed acid #2	M	M	M
polypropylene glycol butyl monoether	M	M	M
polypropylene glycol diol	M	M	M

HFC-32			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	< 20 deg C		
modified polyglycol	< -20 deg C	< 10 deg C	M
naphthenic mineral oil	< 30 deg C	I	I
pentaerythritol ester mixed acid #1	M	< -40 deg C	< -50 deg C
pentaerythritol ester mixed acid #2	M	< -20 deg C	< -30 deg C
polypropylene glycol butyl monoether	M	> 50 deg C	> 40 deg C
polypropylene glycol diol	M	< -30 deg C	< -20 deg C

HCFC-123			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	M	M	M
modified polyglycol	M	I	I
naphthenic mineral oil	M	M	M
pentaerythritol ester mixed acid #1	M	M	M
pentaerythritol ester mixed acid #2	M	M	M
polypropylene glycol butyl monoether	M	M	M
polypropylene glycol diol	M	M	M

HFC-125			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	< 0 deg C		
modified polyglycol	M	< 0 deg C	> 40 deg C
naphthenic mineral oil	< 30 deg C	I	I
pentaerythritol ester mixed acid #1	M	M	< -30 deg C
pentaerythritol ester mixed acid #2	M	M	< 40 deg C
polypropylene glycol butyl monoether	M	M	> 50 deg C
polypropylene glycol diol	M	M	< -40 deg C

HCFC-124			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	M	M	M
modified polyglycol	M	M	M
naphthenic mineral oil	M	< 0 deg C	< -30 deg C
pentaerythritol ester mixed acid #1	M	M	M
pentaerythritol ester mixed acid #2	M	M	M
polypropylene glycol butyl monoether	M	M	M
polypropylene glycol diol	M	M	M

HFC-143a			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	< 0 deg C		
modified polyglycol	< -40 deg C	> 20 deg C	> 20 deg C
naphthenic mineral oil	< 40 deg C	< -10 deg C	< -40 deg C
pentaerythritol ester mixed acid #1	M	I	M
pentaerythritol ester mixed acid #2	M	I	I
polypropylene glycol butyl monoether	M	I	I
polypropylene glycol diol	M	I	I

HCFC-142b			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	M	M	M
modified polyglycol	M	M	M
naphthenic mineral oil	M	< -50 deg C	M
pentaerythritol ester mixed acid #1	M	M	M
pentaerythritol ester mixed acid #2	M	M	M
polypropylene glycol butyl monoether	M	M	M
polypropylene glycol diol	M	M	M

HFC-152a			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	< -40 deg C	< 40 deg C	< -10 deg C
modified polyglycol	M	M	M
naphthenic mineral oil	< 10 deg C	I	< 50 deg C
pentaerythritol ester mixed acid #1	M	M	M
pentaerythritol ester mixed acid #2	M	M	M
polypropylene glycol butyl monoether	M	M	M
polypropylene glycol diol	M	M	M

HFC-134			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	< -10 deg C		
modified polyglycol	M	< 0 deg C	M
naphthenic mineral oil	I	I	I
pentaerythritol ester mixed acid #1	M	M	M
pentaerythritol ester mixed acid #2	M	M	M
polypropylene glycol butyl monoether	M	M	< -50 deg C
polypropylene glycol diol	M	M	M

HFC-134a			
Temperature Range: -50 to +50 degrees C			
Lubricant	Nominal 10% Refrigerant	Nominal 50% Refrigerant	Nominal 95% Refrigerant
alkylbenzene	< 0 deg C		
modified polyglycol	M	< 0 deg C	< 0 deg C
naphthenic mineral oil	< 20 deg C	I	I
pentaerythritol ester mixed acid #1	M	< 10 deg C	M
pentaerythritol ester mixed acid #2	M	M	< -40 deg C
polypropylene glycol butyl monoether	M	M	> 50 deg C
polypropylene glycol diol	M	M	< -10 deg C

M -- miscible over the complete test temperature range
 I -- immiscible over the complete test temperature range
 deg C -- the mixture became immiscible below or above this temperature, as indicated

COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS WITH MOTOR MATERIALS

Objective:

To provide information on the compatibility of motor materials with potential substitutes for CFC refrigerants and with suitable lubricants.

Results:

The Trane Company has recently completed this research under contract with ARTI and is preparing the final report of their progress is contained in DOE report number DOE/CE/23810-13, *Compatibility of Refrigerants and Lubricants with Motor Materials*, Final Report, May 1993, by Dr. Robert Doerr, Mr. Stephen Kujak, and Mr. Todd Waite. This report is still under review and will be available upon ARTI approval.

This project investigated the compatibility of 24 samples of commercially available motor materials with ten pure refrigerants and 17 refrigerant-lubricant mixtures. The sample motor materials were exposed to refrigerant or refrigerant-lubricant mixtures for 500 hours at temperatures specified for each refrigerant. The effect of heat alone was determined by exposing the samples in nitrogen gas at the same temperatures as the refrigerants exposures.

<u>HCFC Refrigerants</u>		<u>HFC Refrigerants</u>		<u>Baseline Exposures</u>
HCFC-22	@ 90°C*	HFC-152a	@ 90°C	Nitrogen @ 60°C
HCFC-123	@ 90°C	HFC-134a	@ 90°C	Nitrogen @ 90°C
HCFC-124	@ 90°C	HFC-134	@ 90°C	
HCFC-142b	@ 90°C	HFC-125	@ 60°C**	*90°C = 194°F
		HFC-32	@ 60°C	**60°C = 140°F
		HFC-143a	@ 60°C	

The various evaluations listed below were made on the motor materials immediately after the 500 hour exposure, and also after the 500 hour exposure with an additional 24 hour air bake at 150°C (302°F) to out-gas the absorbed refrigerant. The test samples included six different varnishes, three different magnet wires, six different sheet insulation materials, one tie cord, three different spiral wrapped sleeving insulating materials, and three different tapes. For the magnet wire/varnish samples, the three types of magnet wire were overcoated with one of each of the six varnishes, producing eighteen different magnet wire/varnish combinations.

Motor Materials EvaluationsVarnish

weight change

Lead Wire

weight change

dielectric strength

Tie Cord

weight change

break load strength

Magnet Wire/Varnish

bond strength

burnout resistance

dielectric strength

Spiral Wrapped Sleeving

weight change

break load strength

Sheet Insulation

weight change

tensile strength

elongation

dielectric strength

Tapes

weight change

Preliminary observations of the data indicate that the refrigerant-lubricant mixtures affected the motor materials less than the pure refrigerants. Two issues of concern were the delamination of sheet insulation materials when exposed to mixtures with polyalkylene glycol - diol, and the decrease strength of tie tapes. Mineral oil extracted polyester materials. However, the synthetic lubricants did not. The synthetic oils tested present few compatibility problems with current motor materials. Preliminary materials compatibility concerns have been summarized for pure refrigerants (Table 6) and refrigerant-lubricant mixtures (Tables 7 and 8).

TABLE 6. Compatibility Concerns of Motor Materials with Refrigerants.

	Refrigerant Exposure										
	HFC-22	HFC-123	HCFC-124	HCFC-142b	HFC-134a	HFC-125	HFC-143a	HFC-32	HFC-152a	HFC-13a	HFC-245a
Magnet Wires											
-Modified polyester overcoated with polyimide imide	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
-Modified polyester overcoated with polyimide imide & epoxy saturated glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
-Polyester imide overcoated with polyimide imide	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Varnishes											
U-475EH	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Y-380PG	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
ER-810	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Y-833	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
No. 823	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Epoxyl 800	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Sheet Insulations											
Nomex/Mylar/Nomex	C2	C2	C2	C2	Y	Y	Y	Y	Y	C2	Y C7
Dacron/Mylar/Dacron	C3	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Mylar	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex Mica	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Melhex	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Sleeving Insulation											
Nomex	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Mylar	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex/Mylar	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Tapes											
Heat Cleaned Glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Heat Shrinkable Glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Glass/Acrylic	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Lead Wire Insulation											
Dacron/Mylar/Dacron	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Dacron/Mylar/Teflon/Dacron	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Tie Cord											
Polyester	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y

LEGEND

Y Compatible
 C Caution
 N Not compatible

Material may be compatible under field conditions similar or less stringent than test conditions. However, observations or test results suggest that caution or further testing should be done before using these materials.

TABLE 7. Compatibility Concerns of Motor Materials with Refrigerant-Lubricant Mixtures.

	Refrigerant-Lubricant Exposure									
	HFC-22/ Mineral	HFC-124/ Allylbenzene	HFC-134a/ Allylbenzene	HFC-134a/ Allylbenzene	HFC-134a/ Allylbenzene	HFC-134a/ Allylbenzene	HFC-134a/ Allylbenzene	HFC-134a/ Allylbenzene	HFC-134a/ Allylbenzene	HFC-134a/ Allylbenzene
Magnet Wires										
-Modified polyester overcoated with polyamide imide	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
-Modified polyester overcoated with polyamide imide & epoxy saturated glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
-Polyester imide overcoated with polyamide imide	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Varnishes										
U-475EH	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Y-300PG	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
ER-810	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Y-833	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
No. 923	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Epoxy 800	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Sheet Insulations										
Nomex/Mylar/Nomex	C8	C10	C10	C10	C10	C10	C10	C10	C10	C2
Darcon/Mylar/Darcon	C8	C10	C10	C10	C10	C10	C10	C10	C10	C2
Mylar	C8	C10	C10	C10	C10	C10	C10	C10	C10	C2
Nomex	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex/Mica	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Melinex	C8	C10	C10	C10	C10	C10	C10	C10	C10	C2
Slivering Insulation										
Nomex	C8	Y	Y	Y	Y	Y	Y	Y	Y	Y
Mylar	C8	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex/Mylar	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Tapes										
Heat Cleared Glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Heat Shrinkable Glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Glass/Acrylic	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Lead Wire Insulation										
Darcon/Mylar/Darcon	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Darcon/Mylar/Teflon/Darcon	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Tie Cord										
Polyester	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y

LEGEND

Y Compatible

C Caution

N Not compatible

Material may be compatible under field conditions similar or less stringent than test conditions. However, observations or test results suggest that caution or further testing should be done before using these materials.

TABLE 8. Compatibility Concerns of Motor Materials with Refrigerant-Lubricant Mixtures.

	Refrigerant-Lubricant Exposure									
	HFC-143a/ Ester-B	HFC-245ca/ Ester-B	HFC-134a/ PAG-1	HFC-32/ PAG-1	HFC-125/ PAG-1	HFC-134a/ PAG-2	HFC-125/ PAG-2	HFC-134a/ PAG-2	HFC-125/ PAG-3	HFC-134a/ PAG-3
Magnet Wires										
- Modified polyester overcoated with polyimide inks	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
- Modified polyester overcoated with polyimide inks & epoxy saturated glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
- Polyester inks overcoated with polyimide inks	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Varnishes										
U-475EH	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Y-380FG	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
ER-810	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Y-833	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
No. 823	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
epoxy 800	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Sheet Insulations										
Nomex/Mylar/Nomex	C2	Y	C12	C12	C2	C2	C2	C2	N15	N15
Darcon/Mylar/Darcon	Y	Y	C14	Y	Y	Y	Y	Y	Y	Y
Mylar	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex Mica	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Melinex	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Sleeving Insulation										
Nomex	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Mylar	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Nomex/Mylar	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Tapes										
Heat Cleaned Glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Heat Shrinkable Glass	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Glass/Acrylic	C13	Y	C13	C13	C13	Y	C13	Y	C13	Y
Lead Wire Insulation										
Darcon/Mylar/Darcon	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Darcon/Mylar/Teflon/Darcon	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y
Tie Cord										
Polyester	Y	Y	Y	Y	Y	Y	Y	Y	Y	Y

LEGEND
 Y Compatible
 C Caution
 N Not compatible

Material may be compatible under field conditions similar or less stringent than test conditions. However, observations or test results suggest that caution or further testing should be done before using these materials.

COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS WITH ELASTOMERS

Objectives:

- To provide compatibility information for elastomers with potential substitutes for CFC refrigerants and with suitable lubricants.
- To obtain data on changes in the physical and mechanical properties of selected elastomers after thermal aging in refrigerant-lubricant mixtures.

Results:

The University of Akron is performing this research under contract with ARTI. A draft final report is expected ny mid-June 1993 and will be released after peer review by the project monitoring subcommittee. Upon acceptance, the final report will be released under DOE report number DOE/CE/23810-14, *Compatibility of Refrigerants and Lubricants with Elastomers*.

This research project examines the compatibility of ten refrigerant and seven lubricants with 95 elastomeric materials:

Refrigerants

HCFC-22
HCFC-123
HCFC-124
HCFC-142b
HFC-32
HFC-125
HFC-134
HFC-134a
HFC-143a
HFC-152a

Lubricants

naphthenic mineral oil
alkylbenzene
polypropylene glycol butyl monoether
polypropylene glycol diol
modified polyglycol
pentaerythritol ester, mixed-acid
pentaerythritol ester, branched-acid

Elastomer Families

butyl polypropylene TPE (1 type)	nitrile rubbers (10 types)
butyl rubbers (7 types)	polychloroprenes (2 types)
chlorinated polyethylenes (3 types)	polyisoprenes (3 types)
chlorosulfonated polyethylenes (5 types)	polysulfide rubbers (4 types)
epichlorohydrin based rubbers (6 types)	polyurethanes (7 types)
ethylene acrylic elastomers (2 types)	silicones (5 types)
ethylene propylene rubbers (3 types)	styrene butadiene rubbers (3 types)
ethylene propylene diene rubbers (5 types)	thermoplastic elastomers, TPEs
fluorinated rubbers (7 types)	(11 types)

plus, ten industry-supplied gaskets of various compositions

Swell behavior of elastomer samples were determined by comparing pre-exposure sample measurements for weight, thickness and diameter with their measurements after exposure. As indicated above, these elastomeric formulations include general purpose and specialty thermoset and thermoplastic elastomers.

Lubricant Immersion Studies: Elastomer samples were completely immersed in the test lubricant, sealed in a glass vessel and then heated at 60°C (140 °F) for 14 days. Sample diameters were measured in situ after 24 hours of exposure. The elastomer samples were also measured for weight, thickness and diameter immediately after the 14 day exposure and then again 24 hours after removal.

Several of the elastomeric compositions, including some of the industry-supplied gaskets, were resistant to swelling in all of the lubricants. These included rubbers from the epichlorohydrin, nitrile, polysulfide rubber, and thermoplastic elastomer families. Refer to Table 9 for a relative comparison of the in situ swelling results.

Refrigerant Immersion Studies: Elastomer samples were completely immersed in the test refrigerant, sealed in a pressure vessel and maintained at room temperature (ambient) for 14 days. In situ diameter changes were determined using a traveling microscope after 24 hour, 72 hour and 14 day exposures. Following the 14 day exposures, the samples were remeasured 2 hours and 24 hours after they were removed from the pressure vessels.

In reviewing the results, the following general statements can be made concerning in situ swelling measurements after the 14 day exposures:

- samples exposed to HCFC-123 had the largest swell
- samples exposed to HCFC-22, HCFC-124, HCFC-142b had moderate swell
- samples exposed to HFC-134, HFC-134a, HFC-125, HFC-143a, and HFC-152a had the least swell

Refer to Table 9 for a relative comparison of in situ swelling results.

Refrigerant-Lubricant Thermal Aging Tests: Based on the results of the separate lubricant and refrigerant studies, 25 elastomeric samples were identified for inclusion in the refrigerant-lubricant thermal aging tests. These 25 elastomers will be fully immersed in 17 individual refrigerant-lubricant mixtures for 14 days at 100 °C (212 °F). Depending on the refrigerant-lubricant combination, the refrigerant weight percent will vary from 32% to 65% concentration to maintain a pressure of 275-300 psia. After the 14 day exposures, the tensile properties of the elastomers will be measured and compared to those of non-aged specimens.

Results from the refrigerant-lubricant thermal aging tests will be presented in the final report.

TABLE 9. Relative Elastomer Swelling

RELATIVE ELASTOMER SWELLING: REFRIGERANTS

	22	32	123	124	125	124	124a	142b	142a	152a
butyl polypropylene TPE	-	*	S	-	S	S	S	-	S	-
butyl rubbers	S	S	-	S	S	S	S	S	S	S
chlorinated polyethylenes	S	*	-	S	S	S	S	S	S	S
chlorosulfonated polyethylenes	-	*	-	S	S	S	S	S	S	S
epichlorohydrin based rubbers	L	S	L	L	S	-	S	S	S	S
EPM rubbers	S	*	-	S	S	S	S	S	S	S
ethylene acrole elastomers	L	*	L	L	L	-	-	L	S	-
ethylene propylene diene rubbers	S	*	-	S	S	S	S	S	S	S
fluorinated rubbers	L	-	L	L	-	L	L	L	-	L
nitrile rubbers	L	-	L	L	S	-	S	-	S	-
polychloroprenes	S	S	-	S	S	S	S	S	S	S
polyisoprenes	-	S	L	S	S	S	S	-	S	S
polyurethane rubbers	S	*	L	S	S	S	S	S	S	S
polyurethanes	L	*	L	L	-	-	S	-	S	-
silicones	L	-	L	L	-	-	-	L	-	L
styrene butadiene rubbers	-	S	L	S	S	S	S	S	S	S
thermoplastic elastomers (TPE)	-	*	-	-	S	S	S	S	S	S

RELATIVE ELASTOMER SWELLING: LUBRICANTS

	AB	MO	PEBA	PEMA	PPGSM	PPGD	MPG
butyl polypropylene TPE	-	-	S	S	S	S	S
butyl rubbers	L	L	S	S	S	S	S
chlorinated polyethylenes	S	-	-	-	S	S	S
chlorosulfonated polyethylenes	-	-	-	-	S	S	S
epichlorohydrin based rubbers	S	S	-	-	S	-	S
EPM rubbers	L	L	S	S	S	S	S
ethylene acrole elastomers	-	-	L	L	L	L	L
ethylene propylene diene rubbers	L	L	S	S	S	S	S
fluorinated rubbers	S	S	L	-	S	S	S
nitrile rubbers	S	S	-	-	S	S	S
polychloroprenes	-	-	-	L	-	S	S
polyisoprenes	L	L	-	-	S	S	S
polyurethane rubbers	S	S	S	S	S	S	S
polyurethanes	-	S	S	-	S	-	-
silicones	-	-	-	S	S	S	S
styrene butadiene rubbers	L	L	-	-	-	S	S
thermoplastic elastomers (TPE)	S	-	S	S	S	S	S

Legend:	
S	- small linear swell; less than 8 %
L	- large linear swell; greater than 35 %
-	- mixed swell values and/or 8% < swell < 35%
*	- test data not yet available
AB	- alkylbenzene
MO	- mineral oil
PEBA	- Pentaerythritol ester branched acid
PEMA	- pentaerythritol ester mixed acid
PPGSM	- polypropylene glycol butyl monosether
PPGD	- polypropylene glycol diol
MPG	- modified polyglycol

COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS WITH ENGINEERING PLASTICS

Objectives:

- To provide compatibility information for engineering plastics with potential substitutes for CFC refrigerants and with suitable lubricants.
- To obtain data on changes in the mechanical properties of selected plastics after thermal aging in refrigerant-lubricant mixtures.

Results:

Imagination Resources, Inc., is performing this research under contract with ARTI. A draft final report has been received and will be released upon peer review by the project monitoring subcommittee. Upon acceptance, the final report will be released under DOE report number DOE/CE/23810-15, *Compatibility of Refrigerants and Lubricants with Engineering Plastics*.

This research project examines the compatibility of ten refrigerants and seven lubricants with 23 engineering plastics:

Refrigerants

HCFC-22
HCFC-123
HCFC-124
HCFC-142b
HFC-32
HFC-125
HFC-134
HFC-134a
HFC-143a
HFC-152a

Lubricants

naphthenic mineral oil
alkylbenzene
polypropylene glycol butyl monoether
polypropylene glycol diol
modified polyglycol
pentaerythritol ester, mixed-acid
pentaerythritol ester, branched-acid

Engineering Plastics Tested

acetal	polyamide-imide (2 types)
polyethylene terephthalate (PET)	acrylonitrile-butadiene-styrene (ABS)
polyaryletheretherketone (PEEK)	polyamide thermoset (2 types)
liquid crystal polymer (LCP)	polyaryletherketone (PEK)
polyphenylene sulfide (PPS)	modified polyetherimide
polyaryl sulfone	polyphthalamide
modified polyphenylene oxide	polybutylene terephthalate (PBT)
polypropylene	nylon 6/6
polycarbonate	polytetrafluoroethylene (PTFE)
phenolic	polyetherimide
polyvinylidene fluoride	

Lubricant Immersion Studies: The plastic specimens were evaluated after 14 day exposures in pure lubricants at 60°C (140°F) and 100°C (212°F). Each plastic was affected to some extent by the lubricants. In general, weight and dimensional changes were in the plus or minus 1-2% range. However, the ABS specimens exhibited relatively larger changes in all the lubricants (in the 5-15% range).

Refrigerant Immersion Studies: The plastics were evaluated at room temperature (ambient) and 60°C (140°F) in pure refrigerant for 14 days at the saturation pressure of the refrigerant. All refrigerants had some effect on the plastics; generally, weight increase and some softening of the plastics. HFCs seem to have the least effect. The ABS plastic failed (e.g., dissolved or deformed) in HCFC-22, HFC-32, HCFC-123, HCFC-124, HFC-134, and HFC-152a. The polycarbonate and the modified polyphenylene oxide plastics failed in HCFC-123.

Stress Crack-Creep Rupture Tests: Linear creep was measured for plastic test bars submerged in a 32 ISO VG branched acid polyolester lubricant with 40% refrigerant concentrations (by weight) at 20°C (68°F) for 14 days. Each plastic was weight loaded at 25% of its ultimate tensile capability to stress the gage area of specimen test bars. The resultant deformation under load information provided the creep modulus arising from the exposure effects of synthetic lubricant with the differing refrigerants.

Plastic creep appeared to be nearly the same for all refrigerants. However, plastics exposed to HCFC-22 exhibited slightly lower creep rates than when exposed to the other nine refrigerants. Two plastics that routinely failed (e.g., broke within one hour) were ABS and modified polyphenylene oxide. HCFC-123, as expected, induced a pronounced increase in plastic creep, but did not promote rupture of the plastic test specimens.

Refrigerant-Lubricant Thermal Aging Tests: Thermal aging tests on the 23 plastic specimens in 17 refrigerant-lubricant combinations were completed. These tests were performed at 150°C (300°F) for 14 days at a 275-300 psia refrigerant pressure exposure. Due to its higher reactivity, HCFC-123 aging tests were performed at 125°C (260°F) and at 105°C (220°F). Physical changes were observed, dimensional changes measured, and specimen tensile properties were compared to the original, unexposed specimens.

After aging, the plastics exhibited minimal dimensional and weight changes (i.e., generally within plus or minus 2%). However, the phenolic, polyvinylidene fluoride, and polypropylene plastic specimens exhibited the largest dimensional and weight changes (generally 5-20%). As compared to the tensile tests performed on non-aged plastic test bars, the aged specimens exhibited large reductions in tensile capabilities (i.e., changes in tensile strengths ranged from a 30% gain to a 50% loss, changes in elongation ranged from a 10% increase to a 85% loss). Hence, as a result of environmental embrittlement, many plastics broke after a much smaller elongation under a much lower tensile load; as compared to the non-aged specimens.

MEASUREMENT OF VISCOSITY, DENSITY, AND GAS SOLUBILITY OF REFRIGERANT AZEOTROPES AND BLENDS IN SELECTED REFRIGERANT LUBRICANTS

Objective:

To measure the viscosity, density, and solubility of four refrigerant mixtures that may potentially replace HCFC-22 or R-502.

Results:

Imagination Resources, Inc., is performing this research under contract with ARTI. A detailed report of their progress is contained in DOE report DOE/CE/23810-11B, *Measurement of Viscosity, Density, and Gas Solubility of Refrigerant Blends*, Quarterly Report, 1 January 1993 - 31 March 1993, by Dr. Richard C. Cavestri and Mr. Jens Munk.

Viscosity and solubility data on HCFC-22 and Suniso 3GS mineral oil was reported from -20 to 120 °C at 10 - 250 psia. Initial work with R-502 and Suniso 3GS mineral oil was also reported. The purpose of these preliminary tests was to permit determinations of the repeatability and acceptability of results generated by Imagination Resources' proprietary oscillating-bob viscometer.

Also presented in the quarterly report is miscibility screening results of six refrigerant blends with five lubricants. This screening information permitted the selection of four refrigerant blends to be evaluated in the balance of the research project:

Possible HCFC-22 Alternatives

HFC-32/HFC-125 (60/40%)

HFC-32/HFC-134a (30/70%)

HFC-32/HFC-125/HFC-134a (30/10/60%)

Possible R-502 Alternative

HFC-125/HFC-143a/HFC-134a (44/52/4%)

Final viscosity and solubility data on the R-502 and mineral oil mixture, with a comparative discussion of the measured R-22 and R-502 values, will be presented in the next quarterly report. Additionally, it is anticipated that the next report will include complete viscosity/solubility/density data on one of the four refrigerant blends.

VISCOSITY, SOLUBILITY AND DENSITY MEASUREMENTS OF REFRIGERANT-LUBRICANT MIXTURES

Objective:

To measure the viscosity, solubility, and density of alternative refrigerant-lubricant mixtures

Results:

Spauschus Associates, Inc. is performing this research under contract with ARTI. This research involves complete viscosity, solubility, and density measurements of the following 38 refrigerant-lubricant mixtures at 7 different concentrations (0, 10, 20, 30, 80, 90, and 100% refrigerant by weight).

Baseline Fluids

- CFC-12/mineral oil (ISO 32)
- CFC-12/mineral oil (ISO 100)
- HCFC-22/mineral oil (ISO 32)

Test Mixtures:

- HFC-134a/polypropylene glycol butyl monoether (ISO 68)
- HFC-134a/pentaerythritol ester - mixed acid (ISO 22)
- HFC-134a/pentaerythritol ester - mixed acid (ISO 32)
- HFC-134a/pentaerythritol ester - mixed acid (ISO 68)
- HFC-134a/pentaerythritol ester - mixed acid (ISO 100)
- HFC-134a/pentaerythritol ester - branched acid (ISO 22)
- HFC-134a/pentaerythritol ester - branched acid (ISO 32)
- HFC-134a/pentaerythritol ester - branched acid (ISO 68)
- HFC-134a/pentaerythritol ester - branched acid (ISO 100)

- HCFC-123/mineral oil (ISO 32)
- HCFC-123/mineral oil (ISO 100)
- HCFC-123/alkylbenzene (ISO 32)
- HCFC-123/alkylbenzene (ISO 68)

- HFC-32/pentaerythritol ester - mixed acid (ISO 22)
- HFC-32/pentaerythritol ester - mixed acid (ISO 68)
- HFC-32/pentaerythritol ester - branched acid (ISO 100)

- HFC-125/pentaerythritol ester - mixed acid (ISO 22)
- HFC-125/pentaerythritol ester - mixed acid (ISO 68)

HFC-125/pentaerythritol ester - branched acid (ISO 32)
 HFC-125/pentaerythritol ester - branched acid (ISO 100)

HFC-152a/alkylbenzene (ISO 32)
 HFC-152a/alkylbenzene (ISO 68)
 HFC-152a/pentaerythritol ester - mixed acid (ISO 22)
 HFC-152a/pentaerythritol ester - mixed acid (ISO 68)

HFC-143a/pentaerythritol ester - mixed acid (ISO 22)
 HFC-134a/pentaerythritol ester - mixed acid (ISO 68)
 HFC-143a/pentaerythritol ester - branched acid (ISO 32)
 HFC-143a/pentaerythritol ester - branched acid (ISO 100)

HCFC-124/alkylbenzene (ISO 32)
 HCFC-124/alkylbenzene (ISO 68)

HCFC-142b/alkylbenzene (ISO 32)

Spauschus Associates, Inc., has completed high lubricant concentration (70, 80, 90, and 100% lubricant by weight) for twelve of the 38 mixtures and has correlated the measurements to the following mathematical relationships for viscosity, pressure, and density.

Dynamic Viscosity (Walter equation):

$$\log\{\log(\mu + 0.7)\} = A + B \log(T)$$

Pressure:

$$P = a + bT + cT^2$$

Density:

$$\rho = \alpha + \beta T$$

Kinematic Viscosity:

Kinematic viscosities were derived by dividing density measurements into dynamic viscosity measurements at the same temperatures. These derived data points were then fitted to the equation

$$\log\{\log(\nu + 0.7)\} = A_1 + B_1 \log(T)$$

Legend

$\log$	= logarithm to the base 10
μ	= dynamic viscosity in centipoise
T	= temperature in Kelvin
P	= pressure in kPa
ρ	= density in g/cc
ν	= kinematic viscosity in centistokes
A, B	= constants found by least squares regression
a, b, c	= constants found by least squares regression
α, β	= constants found by least squares regression
A_1, B_1	= constants found by least squares regression

Tables 10 through 21 provide listings of the constants for each equation and each refrigerant-lubricant concentration, along with the correlation of coefficients (σ) for each fit.

Spauschus Associates also presented the data in the charts depicting density and Daniel¹ charts for each mixture measured. Figures 2-1 and 2-2 depict graphical density, viscosity and solubility charts for HFC-134a and pentaerythritol ester lubricant (ISO 22).

¹ G. Daniel, M. J. Anderson, W. Schmid and M. Tokumitsu, "Performance of Selected Synthetic Lubricants in Heat Pumps", Heat Recovery Systems, Vol. 2, No. 4, 1982, pp. 359-368.

TABLE 10. Solubility, Viscosity and Density Coefficients for CFC-12/Naphthenic Mineral Oil (ISO 32).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.999
	A	9.47597	10.19943	10.89065	11.38118
	B	-3.86349	-4.10609	-4.33684	-4.49652
Pressure (eq. 2)					
	σ	0.999	0.999	0.999	
	a	4374.051	2062.376	1305.893	
	b	-37.503	-20.012	-12.199	
	c	0.081	0.048	0.028	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.273	1.198	1.140	1.092
	β	-0.00087	-0.00076	-0.00068	-0.00063
Kinematic Viscosity (eq. 4)					
	A ₁	9.22713	9.83313	10.42120	10.80355
	B ₁	-3.76388	-3.95592	-4.14356	-4.25893

TABLE 11. Solubility, Viscosity and Density Coefficients for CFC-12/Naphthenic Mineral Oil (ISO 100).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.999
	A	10.19283	10.60454	10.75274	11.41539
	B	-4.10345	-4.21914	-4.23426	-4.45554
Pressure (eq. 2)					
	σ	0.999	0.997	0.989	
	a	7167.797	200.889	-2074.689	
	b	-56.843	-9.640	8.938	
	c	0.115	0.034	-0.004	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.267	1.198	1.145	1.095
	β	-0.00083	-0.00073	-0.00067	-0.00062
Kinematic Viscosity (eq. 4)					
	A ₁	9.97378	10.27182	10.33680	10.90908
	B ₁	-4.01603	-4.08345	-4.06394	-4.24882

TABLE 12. Solubility, Viscosity and Density Coefficients for
HCFC-22/Naphthenic Mineral Oil (ISO 32).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.999
	A	9.25145	9.85591	10.69663	11.38118
	B	-3.79682	-3.99205	-4.27658	-4.49652
Pressure (eq. 2)					
	σ	0.999	0.999	0.944	
	a	5612.729	814.275	-867.667	
	b	-53.612	-17.142	-0.760	
	c	0.126	0.056	0.017	
Density (eq. 3)					
	σ	0.999	0.998	0.999	0.999
	α	1.253	1.204	1.144	1.092
	β	-0.00089	-0.00082	-0.00072	-0.00063
Kinematic Viscosity (eq. 4)					
	A ₁	8.91780	9.42202	10.19665	10.80355
	B ₁	-3.66083	-3.81331	-4.07022	-4.25893

TABLE 13. Solubility, Viscosity and Density Coefficients for
HFC-134a/Pentaerythritol Ester Mixed Acid (ISO 22).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.999
	A	8.66303	8.69946	9.26892	9.47542
	B	-3.53213	-3.50566	-3.69637	-3.74463
Pressure (eq. 2)					
	σ	0.999	0.999	0.999	
	a	8555.920	4036.226	1075.969	
	b	-69.408	-36.286	-12.344	
	c	0.142	0.081	0.032	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.359	1.302	1.256	1.210
	β	-0.00102	-0.00091	-0.00082	-0.00074
Kinematic Viscosity (eq. 4)					
	A ₁	8.47992	8.45970	8.98226	9.17649
	B ₁	-3.46230	-3.41065	-3.58092	-3.62316

TABLE 14. Solubility, Viscosity and Density Coefficients for
HFC-134a/Pentaerythritol Ester Mixed Acid #1 (ISO 32).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)	σ	0.999	0.999	0.999	0.999
	A	8.91339	9.16047	9.30513	9.73910
	B	-3.63169	-3.68527	-3.70202	-3.83538
Pressure (eq. 2)	σ	0.999	0.999	0.999	
	a	8501.689	5138.981	1415.953	
	b	-68.163	-43.015	-14.669	
	c	0.138	0.091	0.036	
Density (eq. 3)	σ	0.997	0.892	0.999	0.999
	α	1.350	1.290	1.253	1.209
	β	-0.00098	-0.00086	-0.00081	-0.00075
Kinematic Viscosity (eq. 4)	A_1	8.76733	8.94779	9.02865	9.44023
	B_1	-3.57715	-3.60129	-3.59078	-3.71402

TABLE 15. Solubility, Viscosity and Density Coefficients for
HFC-134a/Pentaerythritol Ester Mixed Acid #2 (ISO 32).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)	σ	0.999	0.999	0.999	0.999
	A	8.61674	9.22623	9.30455	9.46370
	B	-3.50608	-3.70102	-3.69200	-3.72377
Pressure (eq. 2)	σ	0.999	0.995	0.998	
	a	7298.391	184.671	376.180	
	b	-61.329	-10.367	-7.802	
	c	0.129	0.036	0.024	
Density (eq. 3)	σ	0.872	0.999	0.999	0.999
	α	1.358	1.313	1.266	1.218
	β	-0.00099	-0.00092	-0.00083	-0.00075
Kinematic Viscosity (eq. 4)	A_1	8.46171	9.00929	9.03635	9.19483
	B_1	-3.44807	-3.61558	-3.58433	-3.61474

TABLE 16. Solubility, Viscosity and Density Coefficients for
HFC-134a/Pentaerythritol Ester Mixed Acid (ISO 68).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.999
	A	8.80740	9.34660	9.77783	10.44210
	B	-3.55951	-3.73780	-3.86217	-4.07926
Pressure (eq. 2)					
	σ	0.999	0.999	0.997	
	a	8491.430	5967.728	643.548	
	b	-68.782	-48.594	-10.370	
	c	0.141	0.100	0.030	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.320	1.264	1.216	1.172
	β	-0.00094	-0.00084	-0.00076	-0.00070
Kinematic Viscosity (eq. 4)					
	A ₁	8.59080	9.06684	9.47712	10.09354
	B ₁	-3.47458	-3.62526	-3.74003	-3.93750

TABLE 17. Solubility, Viscosity and Density Coefficients for
HFC-134a/Pentaerythritol Ester Mixed Acid (ISO 100).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.999
	A	9.51442	9.44837	9.28163	9.60676
	B	-3.83543	-3.76003	-3.64718	-3.72997
Pressure (eq. 2)					
	σ	0.999	0.999	0.998	
	a	8938.146	4492.305	1761.664	
	b	-71.830	-39.226	-16.893	
	c	0.146	0.085	0.039	
Density (eq. 3)					
	σ	0.998	0.999	0.999	0.999
	α	1.329	1.274	1.226	1.175
	β	-0.00096	-0.00086	-0.00078	-0.00069
Kinematic Viscosity (eq. 4)					
	A ₁	9.30558	9.17156	9.00600	9.30143
	B ₁	-3.75360	-3.64886	-3.53540	-3.60602

**TABLE 18. Solubility, Viscosity and Density Coefficients for
HCFC-123/Naphthenic Mineral Oil (ISO 32).**

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.999
	A	10.65570	10.67383	11.20571	11.38118
	B	-4.30217	-4.27624	-4.45489	-4.49652
Pressure (eq. 2)					
	σ	0.999	0.999	0.999	
	a	2760.394	2191.630	1165.102	
	b	-19.987	-15.561	-8.391	
	c	0.037	0.028	0.015	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.285	1.221	1.153	1.092
	β	-0.00086	-0.00079	-0.00070	-0.00063
Kinematic Viscosity (eq. 4)					
	A ₁	10.45903	10.33653	10.86300	10.80355
	B ₁	-4.22439	-4.13881	-4.31313	-4.25893

**TABLE 19. Solubility, Viscosity and Density Coefficients for
HCFC-123/Naphthenic Mineral Oil (ISO 100).**

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.999	0.999	0.998
	A	10.00582	10.61860	10.87689	11.41539
	B	-3.99599	-4.20568	-4.27593	-4.45554
Pressure (eq. 2)					
	σ	0.999	0.999	0.999	
	a	3202.688	2272.644	1018.503	
	b	-22.898	-16.403	-7.758	
	c	0.042	0.030	0.015	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.283	1.216	1.151	1.095
	β	-0.00085	-0.00077	-0.00069	-0.00062
Kinematic Viscosity (eq. 4)					
	A ₁	9.77456	10.26906	10.45355	10.90908
	B ₁	-3.90392	-4.06382	-4.10295	-4.24882

TABLE 20. Solubility, Viscosity and Density Coefficients for HCFC-123/Alkylbenzene (ISO 32).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.997	0.999	0.999
	A	11.46558	11.37300	11.41055	11.44333
	B	-4.63799	-4.56942	-4.54302	-4.52918
Pressure (eq. 2)					
	σ	0.999	0.999	0.999	
	a	2364.792	1702.791	832.516	
	b	-17.311	-12.453	-6.154	
	c	0.032	0.023	0.012	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.247	1.181	1.113	1.060
	β	-0.00087	-0.00079	-0.00071	-0.00065
Kinematic Viscosity (eq. 4)					
	A ₁	11.12973	10.89197	10.80978	10.70913
	B ₁	-4.50110	-4.37115	-4.29479	-4.22616

TABLE 21. Solubility, Viscosity and Density Coefficients for HCFC-123/Alkylbenzene (ISO 68).

		70% Oil	80% Oil	90% Oil	100% Oil
Dynamic Viscosity (eq. 1)					
	σ	0.999	0.998	0.999	0.999
	A	11.54181	11.46732	11.66957	12.05281
	B	-4.64742	-4.57749	-4.62395	-4.74176
Pressure (eq. 2)					
	σ	0.999	0.999	0.999	
	a	2529.820	1640.973	928.530	
	b	-18.421	-12.130	-6.837	
	c	0.034	0.023	0.013	
Density (eq. 3)					
	σ	0.999	0.999	0.999	0.999
	α	1.253	1.177	1.112	1.056
	β	-0.00088	-0.00078	-0.00071	-0.00064
Kinematic Viscosity (eq. 4)					
	A ₁	11.20939	10.97909	11.05285	11.31162
	B ₁	-4.51214	-4.37677	-4.37002	-4.43757

FIGURE 2-1. Density of HFC-134a/Pentaerythritol Ester Lubricant (ISO 22). **Figure 2-2. Viscosity and Solubility of HFC-134a/Pentaerythritol Ester Lubricant (ISO 22).**

**ELECTROHYDRODYNAMIC (EHD) ENHANCEMENT
OF POOL AND IN-TUBE BOILING
OF ALTERNATIVE REFRIGERANTS**

Objectives:

- To construct a test rig that can measure improvements with in-tube boiling and in-tube condensation heat transfer performance when utilizing EHD enhancement technology.
- To ascertain the heat transfer benefits on pool boiling with HCFC-123/lubricant on single and multiple enhanced tubes when utilizing EHD techniques.

Results:

The University of Maryland is performing this research under contract with ARTI. A final report detailing the pool boiling test results and the fabrication and qualification of the in-tube apparatus is expected in June 1993. After peer review and acceptance by the project monitoring subcommittee, the final report will be released under DOE report number DOE/CE/23810-17, *EHD Enhancement of Pool and In-Tube Boiling of Alternative Refrigerants*.

ACCELERATED SCREENING METHODS FOR PREDICTING LUBRICANT PERFORMANCE IN REFRIGERANT COMPRESSORS

Objective:

To propose/devise a bench type device that simulates lubricant performance in refrigeration and air-conditioning compressors.

Results:

The University of Illinois at Urbana-Champaign is performing this research under contract with ARTI. The literature search and manufacturer visits have been completed. The testing portion of the project is just getting underway and will include the following fluids:

CFC-12 and mineral oil	---	as a CFC baseline
HCFC-22 and mineral oil	---	as a HCFC baseline
HFC-134a and pentaerythritol ester lubricants	---	HFC evaluation
HFC-32 blend and ester lubricants	---	blend evaluation

To compare results from the University of Illinois' proprietary high pressure tribometer (HPT) with data obtained from Falex^(R) tests, it is expected that four of the following contact pairs will be evaluated:

- 380 die cast aluminum with case hardened low carbon steel
- 356 die cast aluminum with case hardened low carbon steel
- 333 permanent mold cast aluminum with gray cast iron
- hardened gray cast iron with case hardened low carbon steel
- hardened steel with hardened steel

To compare results from the HPT with those obtained from equipment manufacturer's compressor tests, it is expected that four material contact pairs will be evaluated:

380 die cast aluminum with case hardened carbon steel, in a conformal contact
(to simulate the wrist pin-bearing contact of reciprocating compressors)

mild steel with itself, and with ductile cast iron, in a line contact
(to simulate the male-female rotor interface of screw compressors)

sintered ferrous metal with itself, in a line contact
(to simulate the vane-roller contact in rotary compressors)

mild steel or aluminum with Norplex™, in an area contact
(to simulate the thrust bearing-Oldham coupling in scroll compressors)

**ACCELERATED TEST METHODS
FOR PREDICTING THE LIFE OF MOTOR MATERIALS
EXPOSED TO REFRIGERANT-LUBRICANT MIXTURES**

Objectives:

- To develop test methods and procedures to predict the life of motor insulating materials and varnishes used in hermetic motors
- To validate test method and procedures

Results:

The Radian Corporation is performing this research under contract with ARTI. Radian Corporation is currently conducting a literature search and analysis of current procedures and motor failure mechanisms.

**ACCELERATED SCREENING METHODS
FOR DETERMINING CHEMICAL AND THERMAL STABILITY
OF REFRIGERANT-LUBRICANT MIXTURES**

Objectives:

- To develop screening method(s) and procedure(s) to assess the chemical and thermal stability of refrigerants and lubricants, as well as additives, metals, surface treatments, and polymers, used in hermetic systems.
- To validate screening method(s) and procedure(s).

Results:

This research is being performed by the University of Dayton Research Institute under contract to ARTI.

REFRIGERANT DATABASE

Objectives:

- To develop a database for materials compatibility and lubricant research (MCLR) information on substitutes for chlorofluorocarbon (CFC) and hydrochlorofluorocarbon (HCFC) refrigerants for air-conditioners, heat pumps, refrigeration equipment, and automotive and applied refrigeration cycles.
- To assemble physical properties, materials compatibility, lubricant, and related test data for these refrigerants, along with comparative data for currently-used refrigerants.
- To make the data readily accessible for rapid screening and identification of pertinent source documents based on user-defined search criteria.

Results:

James M. Calm, Consulting Engineer, is performing this research project under contract to ARTI. The database is available on a subscription basis (for a nominal charge to recover distribution costs) in either a computerized or printed format.

The core of the database consists of bibliographic citations and extended abstracts for publications that may be useful in research and design of air-conditioning and refrigeration equipment. The bibliographic citations provide information to facilitate ordering of source documents from the author or the publisher. Approximately 40% of the documents are available from the database contractor. Many of the entries have a detailed abstract that describe the data, tests, evaluations, and the materials noted in the documents. These detailed abstracts permit searching of information by refrigerant or refrigerant-lubricant combination, topic, author, material (by generic or commercial name), specific refrigerant property, or just about any other search criteria or combinations of criteria.

As a relatively new enhancement, the computerized version of the database includes summaries for 90 refrigerants, both single-component and blends. Fluids are identified by ASHRAE Standard 34 designations, chemical names and formulae, common names, refrigerant groups, blend compositions, and familiar chemical abstract numbers. Summary property data (with dimensional quantities in dual IP and SI units) are provided for molecular mass, atmospheric boiling point, melting or freezing point, and critical-point parameters (temperature, pressure, specific volume, and density). The lower and upper flammability limits (LFL and UFL), ASHRAE Standard 34 safety classification, ozone depletion potential (ODP), global warming potential (GWP), halocarbon global warming potential (HGWP), and common uses are indicated if known. Specific sources

are referenced for the data to enable verification, obtaining further information, and examining underlying limitations.

The May 1993 release of the ARTI Refrigerant Database will contain in excess of 700 entries related to:

- refrigerant properties
- materials compatibility
- environmental and safety data
- performance with new refrigerants
- lubricants for new refrigerants
- related research programs

COMPLETED PROJECTS

THEORETICAL EVALUATIONS OF R-22 ALTERNATIVE FLUIDS:

Objective:

To provide information regarding the Coefficients of Performance (COP), capacities, compressor discharge temperatures, compressor discharge pressures, and compressor discharge pressure ratios of the following nine alternative fluids, relative to HCFC-22 and three alternative fluids relative to R-502:

Alternative Refrigerants/Blends (% Weight)

HCFC-22 Alternatives

HFC-32/HFC-123 (60/40)
HFC-32/HFC-134a (30/70)
HFC-125/HFC-134a (45/55)
HFC-32/HFC-125/HFC-134a (10/70/20)
HFC-32/HFC-125/HFC-134a (30/10/60)
HFC-134a
HFC-125/HFC-143a/HFC-134a (40/45/15)
R-290 (Propane)
HFC-32/HFC-125/HFC-134a/R-290 (20/55/20/5)

R-502 Alternatives

HFC-32/HFC-125/HFC-143a (10/45/45)
HFC-125/HFC-143a/HFC-134a (44/52/4)
HFC-125/HFC-143a (45/55)

Results:

The Building Environment Division of the National Institute of Standards and Technology (NIST) completed this research under contract with ARTI. Detailed results of this study are reported in DOE report number DOE/CE/23810-7, *Theoretical Evaluations of R-22 Alternative Fluids*, Final Report, by Dr. Piotr A. Domanski and David A. Didion, January 1993.

CHEMICAL AND THERMAL STABILITY OF REFRIGERANT-LUBRICANT MIXTURES WITH METALS

Objective:

To provide information on the stability of potential substitutes for CFC refrigerants and appropriate lubricants.

Results:

Spauschus Associates, Inc., has completed this research under contract with ARTI. A detailed report of results is presented in DOE report number DOE/CE/23810-5, *Chemical and Thermal Stability of Refrigerant-Lubricant Mixtures with Metals*, Final Report, by Dr. Dietrich F. Huttenlocher. Key results are summarized below:

Alternative Refrigerant-Lubricant Combinations

CFC-11 (baseline) with:	HFC-134 with:
naphthenic mineral oil ISO 32	pentaerythritol ester, branched acid
naphthenic mineral oil ISO 46	HFC-134a with:
CFC-12 (baseline) with:	pentaerythritol ester, mixed acid
naphthenic mineral oil ISO 32	pentaerythritol ester, branched acid
alkylbenzene	pentaerythritol ester, 100 cSt
HCFC-22 with:	polypropylene glycol butyl monoether
naphthenic mineral oil ISO 32	polypropylene glycol diol
HFC-32 with:	modified polyglycol
pentaerythritol ester, branched acid	HCFC-142b with:
polypropylene glycol butyl monoether	alkylbenzene
HCFC-123 with:	HFC-143a with:
naphthenic mineral oil ISO 32	pentaerythritol ester, branched acid
naphthenic mineral oil ISO 46	HFC-152a with:
HCFC-124 with:	alkylbenzene
alkylbenzene	
HFC-125 with:	
pentaerythritol ester, branched acid	
polypropylene glycol butyl monoether	
modified polyglycol	

Based on the results of his research, Dr. Huttenlocher made the following conclusions:

- All HFCs tested, along with HCFC-22, were very stable and did not undergo any measurable chemical reactions or thermal decompositions at temperatures up to 200°C (392°F).
- HCFC-124 and HCFC-142b were less stable than the HFCs tested but more stable than CFC-12; a long time industry standard.
- While HCFC-123 was the least stable of the "new" refrigerants tested, it was still ten fold more stable than CFC-11; the refrigerant it is intended to replace in low pressure chiller applications.
- The pentaerythritol esters included in the project exhibited acid number increases after aging at 200°C (392°F). The high viscosity (100 cSt) pentaerythritol ester exhibited additional evidence of molecular changes during aging at 200°C. The formation of CO₂ indicated decarboxylation of the high viscosity pentaerythritol ester lubrication at that temperature.
- All of the polyalkylene glycol lubricants indicated signs of molecular change after aging.

COMPLIANCE WITH AGREEMENT

ARTI has complied with all terms of the grant agreement during the reported period.

PRINCIPAL INVESTIGATOR'S EFFORT

Mr. Mark Menzer is the ARTI principal investigator for the MCLR program. During the first quarter of calendar year 1993, Mr. Menzer devoted a total of 245.5 hours (54.8% of his available work hours) on the MCLR program.

END

DATE
FILMED

6 / 30 / 93