DE-FG02-91ER14185

DOE/ER/14185--2

DE93 009049

ULTRAFAST OPTICAL STUDIES OF SURFACE REACTION PROCESSES AT SEMICONDUCTOR INTERFACES

Progress Report

for Period June 1, 1992 to May 31, 1993

P.I.: R. J. Dwayne Miller

Department of Chemistry and Institute of Optics
University of Rochester
Rochester, NY 14627

March 1993

RECEIVED
MAR 16 1993
OSTI

Prepared for

THE U. S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG02-82ER01834

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

Abstract

The rectifying properties of semiconductor liquid junctions make these systems one of the simplest and most efficient systems for converting and storing optical energy in the form of interfacial charge separation. However, the primary events of interfacial electron or hole carrier transfer and competing non-radiative (energy loss) channels are not well understood at surfaces. This research has explored the use of three novel optical techniques, Surface Space Charge Electro-optic Sampling, Surface Restricted Transient Grating Spectroscopy, and Femtosecond Optical Kerr Spectroscopy (OKE) to obtain the time evolution of the surface spatial distribution of photogenerated charge carriers, the photocarrier population dynamics at semiconductor interfaces, and the solvent modes responsible for charge localization and separation, respectively. These studies have shown that carriers arrive at GaAs(100) surfaces on the hundred femtosecond time scale. Improvements in time resolution, using surface grating spectroscopy, have shown interfacial hole transfer is occurring on the picosecond time scale. The OKE approach to solvent dynamics has determined the response of water to a field is multiexponential with a major relaxation component of 100 femtoseconds. The observed interfacial hole transfer to Se^{2-} acceptors is occurring on this same time scale. This observation illustrates charge transfer processes can occur in the strong electronic coupling limit and can be competitive with carrier thermalization. These results demonstrate that it is possible to specifically engineer interfaces to maximize energy conversion efficiencies by minimizing energy loss through carrier thermalization.

Progress Report

One of the most important processes in surface mediated chemical reactions is the primary interfacial electron transfer step. Principally, there are two models developed for this process at semiconductor surfaces that differ on the energetic state of the electron as it crosses the surface barrier, i.e., thermalized vs. hot carrier injection models. The predicted dynamics for the two models differ by two orders of magnitude and are differentiable based on the observed time scale for interfacial electron transfer. Previous studies of interfacial transfer processes have been conducted on time scales which were not sufficient to follow the initial electron transfer dynamics. By taking advantage of the high quantum yields for electron transfer at semiconductor liquid junctions, we have been able to study the electron transfer process directly at working single crystal semiconductor surfaces using picosecond electro-optic sampling and transient grating techniques.

The transient grating method, in particular, has proven to be an extremely sensitive probe of semiconductor electron-hole carrier processes. The temporal evolution of the transient grating diffraction efficiency gives direct information on the minority carrier lifetime within the depletion layer which effectively measures interfacial electron or hole transfer processes along with the competing processes of surface state trapping. The temporal resolution is laser pulse width limited (10^{-12} - 10^{-13} seconds). This method has turned out to be much more sensitive than originally proposed. We have demonstrated detection limits that correspond to 10^{-5} of a monolayer of reactive electron flux across the interface. This makes this method one of the most sensitive, if not the most sensitive, optical method developed to date for the study of surface processes. In addition, this new surface spectroscopy has introduced the concept of surface space charge field focusing to eliminate transport problems on the temporal resolution. The surface fields act to take the original spatial distribution of photocarriers and selectively drive the minority carrier to within tunneling distances of the interfacial acceptors on a 100 femtosecond time scale. This new effect provides surface selectivity and conserves the hundred femtosecond time resolution needed to follow all the carrier photophysical processes in the surface region. Our earlier results on GaAs have demonstrated the field dependence on the carrier depletion dynamics at the surface and explicitly illustrated the space charge field focusing effect. This work was able to unambiguously follow the interfacial hole carrier depletion dynamics and found that the hole carrier interfacial charge transfer dynamics to Se^{-2} acceptors was less than 30 picoseconds.

The above studies were limited in time resolution by the infrared probe pulse duration and not by intrinsic limitations in the method. It is only in the last two years that methods have been developed that enable the production of femtosecond infrared pulses. To this end, we have explored the combined use of frequency upconversion of the diffracted infrared signal pulse with a

sub-picosecond visible pulse. The summing process is analogous to a sub-picosecond optical gate or boxcar that only measures the diffracted infrared intensity during the time interval of the summing pulse. In this manner, the time resolution has been improved to the 100 femtosecond regime. This approach has the advantage of not having to tackle problems of pulse broadening in the infrared and producing a signal in the visible part of the spectrum which is much easier to detect. It has the disadvantage of turning a normal three pulse grating experiment into a five pulse experiment which is technically more demanding. Our first results with this new technology are shown in Figure 1. A fast 1-2 picosecond decay component is observed. This component is only observed in the presence of 1 M K_2Se . This finding is in line with our previous findings. However, in the present study, we have been able to fully resolve the minority hole carrier dynamics. The charge transfer dynamics determined in our grating studies are competitive with the time scales normally associated with carrier thermalization. These findings support Nozik's hypothesis that energy can be stored, in principle, through charge separation at a semiconductor liquid junction faster than the carriers can lose energy through non-radiative relaxation.

The most important finding in this work is that the interfacial hole transfer is occurring on a time scale that is almost identical to the maximum theoretical rate for an aqueous liquid half space. Normally, electron transfer processes are considered to be limited ultimately by the relaxation of bath modes to the reaction field that develops during electron exchange. For an aqueous system, continuum dielectric theories and experimental studies would suggest upper limits for electron transfer of 500 femtoseconds. This time scale is very similar to the observed dynamics. It is for this reason that the statement that the hole transfer is occurring within adiabatic limits. However, one would like to understand the microscopic modes of the transient water structure that are responsible for the field response. Further, it is not clear at the present time whether previous studies have been done with sufficient time resolution. In the last year, the femtosecond optical Kerr effect has been used to determine the response function of water to a field (in this case a laser field). These results are shown in Figure 2. It is clear from this study that water is capable of responding on sub-100 femtosecond time scales. The question then reduces to the energy relaxation of the field coupled modes and the magnitude of the coupling coefficient to the field. Our preliminary results show a 100 femtosecond decay time obtained via three pulse correlation techniques. This work illustrates that an aqueous solvent cavity should very effectively trap charge (via interfacial charge transfer) relative to carrier thermalization within the solid state half space of the reaction coordinate.

The combined use of surface grating spectroscopy (carrier depletion dynamics), surface space charge electro-optic sampling (minority carrier transit time to surface reaction boundary) and femtosecond optical Kerr effect studies of solvent dynamics spectroscopies have been able to map out the interfacial carrier transfer dynamics. These studies have progressed to the point that

quantitative numbers have been put on these variables. This is the main information needed to characterize the fundamental electronic coupling between molecular states at the surface and the extended electronic states of the solid state. The work described above has now demonstrated that interfacial charge transfer processes can occur within the strong coupling limit - on time scales competitive with carrier thermalization (heat loss). These observations represent an important departure from conventional views of interfacial processes at electrodes and should form a new conceptual basis for controlling surface photochemistry.

Publications

1. L. A. Gomez-Jahn and R. J. D. Miller, "Picosecond Studies of Carrier Reaction Dynamics at n-GaAs(100) Interfaces," *J. Chem. Phys.* **1992**, 3982 (initial work).
2. J. Lanzafame and R. J. D. Miller, "Surface Electron Transfer Dynamics" in Understanding Chemical Reactivity, J. R. Simon (ed.), Academic Press, **1993** (in press - copy included).
3. R. J. D. Miller, L. A. Gomez-Jahn, J. Lanzafame, and S. Palese, "Ultrafast Non-Linear Optical Studies of Surface Reaction Processes," *S.P.I.E. Proceedings* **1993**, (in press - copy included).
4. R. J. D. Miller, G. McLendon, A. Nozik, W. Schmickler, and F. Willig, Surface Electron Transfer Processes, (Verlag, contracted for 1993 publication).
5. S. Palese, L. Schilling, W. Lotshaw, and R. J. D. Miller, "Femtosecond Optical Kerr and Three Pulse Correlation Studies of Water," *J. Phys. Chem.* (submitted).
6. R. J. D. Miller and J. Lanzafame, "Ultrafast Surface Reaction Dynamics. Surface Chemistry from the Electron's Point of View," *J. Phys. Chem.*, invited article (to be submitted).

Works in Progress

7. D. Wang, C. Bonner, J. Buontempo, and R. J. D. Miller, "Subpicosecond Surface Grating Studies of Interfacial Hole Transfer Dynamics at n-GaAs(100) Interfaces."
8. D. Wang and R. J. D. Miller, "Femtosecond Electro-optic Sampling Studies of Surface Field Dynamics."

2 preprints reviewed,
ds

END

DATE
FILMED
5/12/93