001261

1 OF 1

**Development of an Advanced Continuous Mild Gasification
Process for the Production of Coproducts
Task 4
Mild Gasification Tests**

Topical Report

**N.W. Merriam
C.Y. Cha
T.W. Kang
M.B. Vaillancourt**

December 1990

Work Performed Under Contract No.: DE-AC21-87MC24268

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia

By
Western Research Institute
Laramie, Wyoming

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**Development of an Advanced Continuous Mild Gasification
Process for the Production of Coproducts
Task 4
Mild Gasification Tests**

Topical Report

**N.W. Merriam
C.Y. Cha
T.W. Kang
M.B. Vaillancourt**

Work Performed Under Contract No.: DE-AC21-87MC24268

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Western Research institute
P.O. Box 3395
University Station
Laramie, Wyoming 82071-3395**

December 1990

ABSTRACT

A continuous mild-gasification process research unit (PRU) was operated at Western Research Institute (WRI) using inclined fluidized-bed reactors to dry and gasify coal under mild conditions.

Results of drying and mild-gasification tests in inclined fluidized-bed (IFB) reactors at coal feed rates from 93 to 149 lb/hr are presented in this report. Minus 8-mesh Wyodak coal from the AMAX Eagle Butte Mine is readily dried to zero moisture content and partially decarboxylated using recycle gas to fluidize coal in an inclined fluidized-bed dryer. During the 3-minute residence time in the dryer, the coal is heated to a maximum temperature of 300 to 550°F (149 to 288°C) by fluidizing gas entering the dryer at 540 to 815°F (282 to 435°C). The plug-flow characteristic of the IFB reactors permits the temperature of the dried coal leaving the dryer to be about 200°F (110°C) higher than the effluent gas temperature, providing a high thermal efficiency. The drying operation produces 29 to 31 wt % of the raw coal as water, 5 to 7 wt % as fines, 1 to 2 wt % as carbon dioxide gas, and 60 to 65 wt % as dried coal.

The dried coal flows into a mild-gasification reactor where the coal is fluidized by contact with recycle gas heated to 1240 to 1450°F (671 to 788°C). The coal is heated to 950 to 1150°F (510 to 621°C) producing 38 to 42 wt % of the raw coal as char, 2 to 6 wt % as fines, 4 to 10 wt % as gas, and 10 to 14 wt % as liquids. Dry coal liquid yields vary from 12 to 15 wt % of the moisture- and ash-free (MAF) feed to the mild-gasification reactor.

The char produced in the process research unit (PRU) typically contains 15 to 21 wt % volatiles, has hydrogen-to-oxygen mass ratios of 0.21 to 0.33, and is highly reactive in both hydrogen and air.

The liquid produced is a tarry substance, with 55 to 60 wt % boiling above 700°F (371°C), having hydrogen-to-carbon atomic ratios of 1.15 to 1.25. The gas produced has gross heating values varying from 550 to 600 Btu/scf and contains increasing concentrations of hydrogen, methane, and carbon monoxide at higher reaction temperatures.

Results of tests conducted in the PRU using coal feed rates of 93 to 149 lb/hr agree very well with results of tests conducted using feed rates of 10-lb/hr in the bench-scale equipment.

ACKNOWLEDGEMENT

We wish to thank the United States Department of Energy's Morgantown Energy Technology Center for funding this work under contract number DE-AC21-87MC24268. We wish to express our gratitude to Riley Research and Development for designing and constructing the equipment, to AMAX Coal Company for their interest in the work and for supplying the coal for testing, and to AMAX Research and Development Center for their close cooperation in the work.

Thanks also to Ron Beckett, Jim Binder, Godwin Biezugbe, Nelson Brower, Bob Cummings, Jim Dean, Les Gitke, Bruce King, Dan Olson, Blake Rickard, Steve Roach, Bob Shaw, Al Sullivan, Bob Tweed, and Ed Walker who assembled the equipment, installed the instruments, prepared the coal, and conducted the tests. Thanks to Jan O'Dell for typing the manuscript. Special thanks to Ken Thomas and Dan Hunter for preparing the liquid samples and coordinating the analyses, to John Boysen who summarized and correlated much of the data, and to Dr. H. Fred Bauer for his able guidance and assistance with interpretation of the data.

EXECUTIVE SUMMARY

Western Research Institute (WRI) teamed with the AMAX Research and Development Center and Riley Stoker Corporation on Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts under contract DE-AC21-87MC24268 with the Morgantown Energy Technology Center of the U.S. Department of Energy. The strategy for this project is to produce electrode binder pitch and diesel fuel blending stock by mild gasification of Wyodak coal. The char is upgraded to produce anode-grade carbon, carbon black, and activated carbon. This report describes results of mild-gasification tests conducted by WRI. Char upgrading tests conducted by AMAX will be described in a separate report.

A series of 24-hour and 5-day tests was conducted using the PRU designed by Riley Stoker for a feed rate of 100 lb/hr of minus 8-mesh coal. The effects of maximum bed temperatures of 950 to 1150°F (510 to 621°C) and coal (char) residence times of 5 to 9 minutes upon the distribution and properties of products were determined.

Results of the tests using the PRU show the yield of coal liquids increases from about 10 wt % of the moisture- and ash-free (MAF) coal feed to the mild gasification reactor when using a maximum bed temperature of 950°F (510°C) to about 15 wt % at 1150°F (621°C). We were not able to test bed temperatures above 1150°F (621°C) because of the limited heater capacity in the PRU.

The coal liquids produced are heavy, viscous substances with 55 to 60 wt % having boiling points of 700+°F (371+°C) needed for anode-binder pitch. Typical hydrogen-to-carbon (H:C) atomic ratios vary from 1.15 to 1.25. The liquids are sufficiently low in ash content to meet specifications for binder pitch. However, they contain too much hydrogen and oxygen, and the specific gravity is low. Heat treatment of the liquid has been shown to reduce the hydrogen and oxygen content while increasing the specific gravity as well as the content of quinoline insolubles.

The yield of char produced varies from about 42 wt % of the raw coal at a bed temperature of 950°F (510°C) to about 38 wt % at 1150°F (621°C). The char contains 15 to 21 wt % volatiles and is highly reactive in both hydrogen (for methanation) and air (for combustion). Results of tests conducted at Oak Ridge National Laboratories (Daw et al. 1990) indicate that the char appears to be sufficiently reactive for firing in a wide variety of combustors, possibly including those burning pulverized coal.

The hydrogen and oxygen content of the char can be controlled by the degree of devolatilization used in the mild-gasification reactor. Increased devolatilization, using higher bed temperature and/or longer residence time, results in reduction of the hydrogen and oxygen contents of the char at different rates. The rate of oxygen removal from the char is higher than the rate of

hydrogen removal at temperatures up to about 1100°F (593°C). Above about 1150°F (621°C), the rate of hydrogen removal greatly exceeds the rate of oxygen removal. Thus, a maximum hydrogen-to-oxygen (H:O) ratio in the char is determined when using bed temperatures of 1100 to 1150°F (593 to 621°C). The sulfur content of the char remains essentially constant at different volatiles contents, whereas the nitrogen content decreases with further removal of volatiles.

Gas produced by mild gasification of Wyodak coal using the WRI PRU varies from 4 to 10 wt % of the raw coal with the quantity of gas produced increasing at higher temperatures. Heating value of the gas varies from 550 to 600 Btu/scf with the highest heat content gas produced at higher temperatures. The concentrations of methane, carbon monoxide, and hydrogen in the gas produced increase from about 22 to 34 vol %, 16 to 20 vol %, and 4 to 13 vol %, respectively, as reactor bed temperature is increased from 950 to 1150°F (510 to 621°C).

Closures of coal balances for the ten 24-hour and 5-day tests using the PRU are excellent; only one closure falls outside the range of 98.0 to 103.7 %. Elemental balances show that most of the carbon from the raw coal remains in the char, whereas hydrogen is concentrated in the gas, coal liquids, and pyrolysis water. Nitrogen remains mostly in the char, whereas sulfur is distributed roughly in proportion to the weight of the products. Over one-half of the oxygen in the MAF feed coal is converted to gas and water during pyrolysis.

Results of tests with the PRU using raw coal feed rates of 93 to 149 lb/hr agree well with results from tests using the bench-scale system at a feed rate of 10 lb/hr.

The most notable operating problems with the PRU were caused by occasional plugging in the coal feed line to the dryer and high pressure drop across the air-cooled and water-cooled condensers in the mild-gasification liquid recovery system, also caused by partial plugging. We recommend use of heated outer surfaces on the coal feed hopper and feed screw in addition to the dry-gas purge and vibrator we already use at the feed lockhopper. The warm outer surface will prevent condensation of moisture on the walls of the feed hopper and feed system.

We also recommend the use of two stages of wet-scrubbing for the coal liquid recovery system. The first-stage will operate above the dew point of water in the recovery system and also above the pour point of the pitch. The pitch will be recovered from the first stage. The second-stage scrubber will operate in the 40 to 100°F (4 to 38°C) range, depending upon economic tradeoffs and avoidance of formation of hydrates.

TABLE OF CONTENTS

	<u>Page</u>
LIST OF TABLES.....	viii
LIST OF FIGURES.....	x
1.0 INTRODUCTION.....	1
2.0 BACKGROUND.....	2
3.0 TEST EQUIPMENT AND PROCEDURES.....	8
3.1 Description of Equipment.....	8
3.2 Coal Preparation.....	13
3.3 Coal Drying.....	14
3.4 Mild-Gasification Tests.....	16
3.5 Collection of Coal Liquids.....	17
4.0 RESULTS AND DISCUSSION.....	18
4.1 Shakedown Tests.....	18
4.2 Coal-Drying Tests.....	28
4.3 Mild-Gasification Tests.....	38
4.4 Discussion of Test Results.....	75
5.0 CONCLUSIONS AND RECOMMENDATIONS.....	81
6.0 REFERENCES.....	83

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1. Typical Composition and Characteristics of Feed Coals for the Mild-Gasification Project.....	4
2. Summary of Design Conditions for the Mild-Gasification PRU.....	11
3. Location of Bed Thermocouples and Solids Sample Ports in the IFB Dryer and Mild-Gasification Reactor.....	12
4. Design Parameters for Condensers in the Mild-Gasification PRU.....	13
5. Feed-Coal Size.....	14
6. Coal Residence Time in Dryer.....	19
7. Summary of Drying Conditions.....	29
8. Conditions Used for Drying Coal During Mild-Gasification Tests.....	33
9. Coal Balances for Drying Tests.....	34
10. Composition of Gas in the Drying System During Test 114.....	35
11. Proximate Analyses of Fines and Dust from Test 114.....	36
12. Screen Analysis of Fines from Cyclone Produced During Test 114.....	36
13. Composition of Water Produced by Drying Coal.....	37
14. Conditions Used for Mild-Gasification Tests.....	41
15. Product Distribution from Mild-Gasification Tests, lb of material.....	45
16. Product Distribution from Mild-Gasification Tests, wt % of raw coal.....	46
17. Summary of Liquids Produced by Mild Gasification.....	47
18. Carbon Balances from Selected Mild-Gasification Tests.....	52
19. Hydrogen Balances from Selected Mild-Gasification Tests.....	56

LIST OF TABLES (continued)

<u>Table</u>	<u>Page</u>
20. Nitrogen Balances from Selected Mild-Gasification Tests.....	56
21. Sulfur Balances from Selected Mild-Gasification Tests.....	57
22. Oxygen Balances from Selected Mild-Gasification Tests.....	57
23. Comparison of Carbon Balances from 10-lb/hr and 100-lb/hr Tests.....	58
24. Properties of Dry-Coal Liquids Produced by Mild Gasification.....	59
25. Ash Content of Liquids from Successive Collection Points.....	59
26. Toluene Insolubles and Quinoline Insolubles from Successive Collection Points.....	60
27. Composition of Water from the Chilled Condenser.....	60
28. Boiling Range of Dry-Coal Liquid from Test 118.....	61
29. Boiling Range of Dry-Coal Liquid from Test 119.....	62
30. Composition of Distilled Liquids from Test 122.....	62
31. Effect of Caustic Wash Upon IBP-700°F Distillate from Test 112.....	63
32. Hydrocarbon-Group-Type Analysis of Distillate from Test 112.....	64
33. Composition of Gas Produced by Mild Gasification.....	65
34. Ratios of Components in Gas from Mild Gasification.....	67
35. Composition of Char Produced by Mild Gasification.....	68
36. Size Distribution of Char Produced.....	73
37. Proximate Analyses of Fines from the Mild-Gasification Reactor.....	74
38. Dried Coal and Char Residence Times.....	75

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1. Process Flow Diagram for Mild-Gasification PRU.....	9
2. Solid and Gas Flow in Inclined Fluidized-Bed Reactor.....	10
3. Dryer Temperatures During Shakedown Test 111.....	20
4. Dryer Bed Temperatures During Shakedown Test 111.....	21
5. Removal of Moisture in the Inclined Fluidized-Bed Dryer.....	22
6. Mild-Gasification Temperatures During Shakedown Test 111.....	24
7. Mild-Gasification Bed Temperatures During Shakedown Test 111.....	25
8. Volatiles Removal from Wyodak Coal in the Mild- Gasification Reactor.....	26
9. Composition of Recycle Gas from Test 111.....	27
10. Coal Moisture Content and Dryer Bed Temperature During Test 113.....	30
11. Coal Moisture Content and Bed Temperature During Test 114.....	31
12. Coal Moisture Content and Bed Temperature During Test 117.....	32
13. Moisture Content of Wyodak Coal Versus Dryer Bed Temperature.....	39
14. Loss of Volatiles from Coal in the Dryer Versus Bed Temperature at Zone 3.....	40
15. Distribution of Products from Mild Gasification at Various Maximum Bed Temperatures.....	49
16. Distribution of Gas, Water, and Char at Various Bed Temperatures.....	50
17. Distribution of Coal Liquids and Char Produced at Various Bed Temperatures.....	51

LIST OF FIGURES (continued)

<u>Figure</u>	<u>Page</u>
18. Yield of Dry Coal Liquid Products at Various Bed Temperatures.....	53
19. Yield of Coal Liquids from PRU Tests at Various Temperatures.....	54
20. Yield of Coal Liquids Produced at Various Bed Temperatures in Zone 1 of the Mild Gasification Reactor.....	55
21. Major Components of the Gas Produced at Various Temperatures.....	66
22. Fixed Carbon Content of Dried Coal and Char at Increasing Temperatures.....	69
23. The Effect of Changing Reactor Slope Upon the Volatiles Content of the Chars Produced.....	70
24. Oxygen and Hydrogen Content of Chars Having Different Volatiles Contents.....	71
25. Ratios of Nitrogen- and Sulfur-to-Ash in Chars Having Different Volatiles Contents.....	72

1.0 INTRODUCTION

The U.S. Department of Energy (DOE) is developing processes to convert coal to usable gaseous and liquid forms. Successful development of the processes will increase the use of coal, the largest domestic fossil energy resource. However, these processes typically require high temperatures and pressures and have been slow in receiving commercial acceptance because they require high capital and operating costs.

To overcome this problem, Morgantown Energy Technology Center (METC), the lead technical center in gasification technology, developed a concept called Mild Gasification. In this concept, devolatilization of coal under nonoxidizing and relatively mild temperature and pressure conditions can yield three marketable products: (1) a high-heating-value gas, (2) a high-aromatic coal liquid, and (3) a high-carbon char.

METC awarded a contract (DE-AC21-87MC24268), Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, to Western Research Institute (WRI) in Laramie, Wyoming, with AMAX R&D and Riley Stoker as subcontractors to further enhance the technology and the economics of mild gasification.

The objective of this program is to develop an advanced, continuous, mild-gasification process to produce products that will make the concept economically and environmentally viable.

The program consists of four tasks:

- Task 1--Literature Survey and Market Assessment
- Task 2--Bench-Scale Mild-Gasification Study
- Task 3--Bench-Scale Char Upgrading Study
- Task 4--System Integration Studies

The work in task 1 has been completed and reported by Cha et al. (1988). The work in tasks 2 and 3 has been completed and reported by Merriam and Cha (1989) and Jha and McCormick (1989), respectively. This report contains descriptions of mild-gasification tests conducted using a 100-lb/hr PRU along with summaries of the results. This report is submitted to fulfill the contractual requirement for a final topical report describing mild-gasification work performed as task 4. Results of char upgrading tests conducted by AMAX R&D using a 50-lb/hr process research unit (also task 4) will be reported in a separate topical report.

2.0 BACKGROUND

The major goal for developing and demonstrating mild gasification of high-volatile coal is to stimulate commercial production of fuels and feedstocks from coal in the United States. The achievement of this goal will reduce the dependence of the American economy on petroleum from foreign sources and will also stimulate production of coal from vast domestic resources.

Much work has been done in the United States during the last several decades to produce fuels and feedstocks from coal. However, nearly all of the development focused on severe conditions to produce maximum yields of liquid or gas products. Although some of the processes have been shown to be technically feasible, the high temperatures ($>1292^{\circ}\text{F}$ [$>700^{\circ}\text{C}$]) and high pressure (>50 psig) used in those processes have resulted in high-cost processes that do not appear to be economically feasible for commercial implementation in the foreseeable future.

One approach to developing low-cost processes is to use mild conditions (i.e., lower temperatures and pressures) to reduce the cost of producing fuels and feedstocks from coal. The use of mild conditions may produce less than maximum yields of gas and liquid products; however, it is likely that low-cost processes can produce a slate of marketable products with economically acceptable yields. The focus of mild gasification is, therefore, upon developing and demonstrating processes that can be built and operated with relatively low cost on the commercial scale and that will give a satisfactory return on the investment.

Cost estimates for plants using severe processing conditions show that investments of billions of dollars are needed to construct a single plant. Few organizations in the United States have the capital needed for such an undertaking and are willing to accept the enormous risk. Thus, one goal of the mild-gasification work is to prove that processes can be built for a small fraction of the investment needed for severe processes, thus, significantly lowering the financial risk of constructing a mild-gasification plant. Mild-gasification processes must also have low operating costs to be economically feasible.

Versions of mild gasification of coal, commonly called devolatilization, are presently practiced in England, India, and South Africa and have been used commercially in many countries in the past. The development of new mild-gasification processes will be based on experience with older technology combined with recent technological improvements and a systems approach to optimizing the overall value of the products.

There are four factors to be considered for successful operation of a mild-gasification plant: (1) properties of the coal source, (2) gasification conditions, (3) product upgrading, and (4) the locations and sizes of markets for products. All these factors are requisite for the mild-gasification process to be successful.

The most important factor is markets for the products because the operator has less control over the markets than over other factors.

Market assessment studies were performed by AMAX Coal Company and JDS Group Inc., as part of task 1 (Cha et al. 1988). The studies showed that revenue from a commercial plant could be significantly improved if char is converted to carbon black, electrode-grade carbon, activated carbon, or metallurgical coke. The fact that Alumax, a division of AMAX, consumes over 250,000 tons of anode-grade carbon per year at delivered prices of about \$200 per ton resulted in a decision to develop a process to produce anode-grade carbon from char.

We decided to produce four liquid products: (1) dirty pitch, (2) clean pitch, (3) heavy oil, and (4) light oil. The dirty pitch will be used to coat dried coal before shipment. It will displace a petroleum product purchased for \$100 per ton. Clean pitch will be used as electrode binder pitch by Alumax, displacing pitch imported for \$200 to \$250 per ton. Heavy oil will be blended with diesel fuel to operate equipment at the mine or sold to a refinery for about \$100 per ton. Light oil will be sold as an octane enhancer for \$100 per ton or as crude cresylic acid.

It is presently not economically attractive to convert the gas produced to pipeline gas, although it is technically feasible. The best economic use for this process gas is to burn the gas to supply heat for the mild-gasification process.

Only one of the selected products, the light oil, will not be consumed within AMAX. All other products will be used at the mine or within divisions of AMAX. The internal use will help gain market acceptance for the products.

A preliminary economic evaluation of the process performed by Stearns-Roger showed that the process may be commercially attractive. This evaluation also reaffirmed our perception that we must develop a low-cost process if we are to achieve commercial success.

Coals from three AMAX mines are candidate feed coals for the mild-gasification process (Table 1). Wyodak, a subbituminous coal, has the advantages of low sulfur and ash content and the disadvantages of high moisture and oxygen content. AMAX Coal Company is drying Wyodak coal for shipment so that the cost of the proposed plant may be lowered by using some of the coal handling and drying facilities as part of the mild-gasification plant. Therefore, METC approved a primary emphasis on testing Wyodak coal with a secondary emphasis on testing bituminous coals, Illinois No. 6 and Indiana No. 3, which are very similar in composition. Wyodak is noncaking coal, whereas Illinois No. 6 and Indiana No. 3 are mildly caking coals. Wyodak coal is also much less expensive than the midwestern coals.

The mild-gasification testing was conducted to maximize production of clean pitch, the most valuable liquid product, and to produce highly reactive

char having a hydrogen-to-oxygen mass ratio higher than 0.125 so that no hydrogen from external sources is needed to react with oxygen during char upgrading. We also wanted to completely dry the coal and drive out as much oxygen as possible by partial decarboxylation during drying while producing clean water from the drying operation.

Table 1. Typical Composition/Characteristics of Feed Coals for Mild-Gasification Project

Coal Seam	Wyodak	Illinois No. 6	Indiana No. 3
Coal Rank	Subbituminous	Bituminous	Bituminous
Mine Name	Belle Ayr/ Eagle Butte	Delta	Chinook
Nearest City, State	Gillette, WY	Marion, IL	Brazil, IN
Proximate Analysis, % as received			
Moisture	30.68	9.00	13.50
Ash	4.93	10.84	10.46
Volatile Matter	33.66	32.58	35.98
Fixed Carbon	30.73	47.58	40.06
Sulfur	0.35	2.85	4.20
Forms of Sulfur			
Pyritic	0.05	1.31	2.25
Organic	0.28	1.51	0.81
Sulfate	0.02	0.03	0.14
Ultimate Analysis, % dry basis			
Carbon	68.96	70.84	67.99
Hydrogen	5.29	4.84	5.16
Ash	7.11	11.91	12.09
Sulfur	0.50	3.13	4.86
Nitrogen	0.94	1.38	1.32
Chlorine	0.01	0.13	0.05
Oxygen	11.91	7.07	7.39
Btu/lb, as received	8,300	11,600	10,982
Btu/lb, dry	11,975	12,747	12,696

Table 1. Typical Composition/Characteristics of Feed Coals for Mild-Gasification Project (continued)

Coal Seam	Wyodak	Illinois No. 6	Indiana No. 3
Mineral Analysis of Dry Ash, %			
Al ₂ O ₃	13.02	18.79	22.01
SiO ₂	29.87	49.83	42.88
Fe ₂ O ₃	5.45	18.23	25.32
TiO ₂	1.30	1.12	0.81
CaO	23.66	4.10	3.70
MgO	7.15	1.18	0.71
K ₂ O	0.25	2.55	1.59
Na ₂ O	1.66	0.37	0.30
SO ₃	16.27	3.40	2.41
P ₂ O ₅	0.80	0.44	0.43
Ash Fusion Temp., °F			
Reducing			
Initiation	2,125	2,067	2,014
Fluid	2,224	2,307	2,386
Oxidizing			
Initiation	2,178	2,315	2,399
Fluid	2,302	2,471	2,578

Complete drying and partial decarboxylation is achieved by drying below the temperature at which volatile organics are released to avoid producing dirty water. Maximum pitch production requires high heating rates, high sweep-gas flow rates, and use of a relatively small average particle size. The hydrogen-to-oxygen mass ratio in the char can be maintained above 0.125 by avoiding temperatures above about 1200°F (649°C).

Results of the bench-scale mild-gasification tests (by WRI) and char-upgrading tests (by AMAX) are briefly summarized for the convenience of the reader (Merriam and Cha 1989).

WRI conducted 23 successful coal-drying tests and 14 successful mild-gasification tests using inclined fluidized-bed reactors. The tests in the 10-lb/hr reactors ran for four to sixteen hours with most tests maintaining steady-state conditions for eight hours. The effects of bed temperature, particle size, and drying-gas water content on the drying rates and residual moisture content of the dried coal were determined. Coal was readily dried to zero moisture, and

about 1 wt % of the raw coal was driven off as carbon dioxide by partial decarboxylation at a maximum bed temperature of 575°F (302°C) using a solids residence time of five minutes. The drying rate was slightly slower using 0.050 lb of water per lb of dry carbon dioxide than when 0.030 and 0.015 lb per lb were used. Differences in particle size from 0.004 to 0.020 inch did not measurably affect the drying rate or residual moisture content of the coal.

The effects of bed temperature, heating rate, coal particle size, solids residence time, and fluidizing-gas composition on the yield of liquid products and the composition of char and gas produced were determined from the mild-gasification tests. The char contained 11 to 19 wt % volatiles, had hydrogen-to-oxygen mass ratios of 0.18 to 0.30, and had heating values of 12,333 to 12,905 Btu/lb. The volatiles content and the hydrogen-to-oxygen ratio of the char were reduced by increasing the maximum bed temperature in the mild-gasification reactor from 1100 to 1200°F (593 to 649°C). The hydrogen-to-oxygen mass ratios were greater than the 0.125 value needed to supply hydrogen for formation of water during char upgrading, avoiding any need for makeup hydrogen.

Liquid products collected varied from 8.3 to 18.1 wt % of the MAF coal with most of the coal liquids boiling above 700°F (371°C), a characteristic needed for electrode-binder pitch. The median hydrogen-to-carbon atomic ratio of the condensates was 1.23. Maximum liquid yield occurred at a maximum bed temperature of about 1150°F (621°C). The yield of coal liquids increased with higher heating rates in the inlet portion of the mild-gasification bed. We were not able to determine any effect of particle size on yield from 0.004- to 0.020-inch average particle size.

Gas produced had typical heating values of about 675 Btu/scf and contained 30 to 50% by volume carbon monoxide and about 3600 ppm hydrogen sulfide. A test using steam as the fluidizing gas resulted in production of gas containing about 40% hydrogen.

Evaluation of the chars produced from bench-scale tests showed that the volatile matter content correlated with average mild-gasification bed temperature, residence time, and starting coal particle size for most samples (Jha and McCormick 1989). Higher average bed temperatures lead to lower hydrogen content and lower H:O ratios in the chars. These data are consistent with the higher hydrogen content of the mild-gasification liquids relative to the starting coal. The amount of sulfur in the final char is not affected by mild-gasification conditions. The amount of nitrogen is lower for chars with a lower volatile matter content (chars processed at higher temperatures). The use of steam in mild gasification produces a low-volatile, relatively low-oxygen char. Brunauer, Emmett, and Teller (BET) surface areas for the chars also correlated with average bed temperature and inversely with volatile matter content. All of the chars exhibited a very open pore structure with most of the surface area in relatively large macropores.

Bench-scale char gasification studies show that up to 70 % conversion to methane can be obtained in less than two hours at relatively moderate conditions of temperature and pressure. Temperatures in the range of 1300 to 1550°F (704 to 843°C) and pressures of about 200 to 400 psig are adequate.

The use of gasification catalysts for char upgrading appears to offer no advantage in runs conducted in the bench-scale system, in contrast to results obtained in the micro-fixed bed. Catalysts did not increase the gasification rate; however, they did increase the final conversion obtainable with a given char.

The results of a char reactivity test show some significant differences in the chars produced by mild gasification at different conditions. These differences in reactivity can not be conclusively correlated with char properties or with mild-gasification conditions. However, chars with a low volatile matter content appear to be less reactive.

The use of steam for char upgrading does not have a beneficial effect on the methane formation rate and can result in gasification of a large portion of the carbon to form carbon oxides.

The results of bench-scale tests also show that carbons similar to both thermal blacks and furnace blacks can be produced by decomposition of methane in an indirectly heated system. The type of carbon produced depends upon the conditions selected for the reactor. The physical properties of the carbon product can be controlled by varying residence time, temperature, and methane partial pressure. Also, the carbon and hydrogen content can be controlled by varying conditions. If sulfur is present in the feed gas as H₂S, very little will become incorporated into the carbon. Although this will be important in fuel and anode applications, the presence of low levels of sulfur does not significantly affect the performance of carbon black in elastomers.

Results of bench-scale char upgrading tests showed:

- The mild-gasification chars have a very open pore structure, relatively low volatile matter content, and maintain their reactivity when stored in an inert atmosphere.
- Sulfur in the mild-gasification chars is present in a very refractory form, so it is not gasified. The sulfur remains with the spent char or ash.
- A fluidized-bed reactor is the most appropriate choice of reactor design for the char methanation reactor.
- The production of carbon from methane in indirectly heated, tubular reactors was proven to be feasible.

- The carbon produced in this type of reactor has properties that depend on the temperature, gas composition, and residence time employed.
- Carbon samples exhibited particle size distributions, surface areas, and structure similar to those of commercial-grade thermal and furnace blacks.
- The overall process of conversion of char to high-purity carbon is technically feasible.

3.0 TEST EQUIPMENT AND PROCEDURES

The 100-lb/hr mild-gasification process research unit (PRU) is described in this section. Procedures used for coal preparation, conduct of the tests, collection of samples, process measurements, and collection of products are also described in this section.

3.1 Description of Equipment

The mild-gasification PRU (Figure 1) consists of a coal feed system and drying system (left-half of Figure 1) and a mild-gasification system (right-half). The PRU was designed and equipment procured by Riley Stoker Corporation. After assembly of the drying and mild-gasification systems at Riley Research Center, the equipment was partially disassembled and shipped to WRI. WRI reassembled the system, added utilities systems, and conducted shakedown tests to locate and fix problems with the equipment.

We replaced the solids pump (Figure 1) used to feed coal to the dryer with a lockhopper before test 115. The PRU also has a lockhopper between the drying reactor and the mild-gasification reactor that is not shown in Figure 1. The equipment (Table 2) has all wetted parts made of 304 stainless steel.

The IFB reactors used for drying and mild gasification feature plug-flow of solids along shallow beds fluidized by cross-flow of gas (Figure 2). The plug-flow of solids permits nonisothermal control of bed temperatures and allows small and large particles to have the same residence times. The cross-flow of gas through the shallow beds rapidly sweeps volatiles out of the beds and causes a high concentration gradient between volatiles in the particles and in the bulk gas flow. The plug-flow also permits solids to flow from the beds at temperatures above the temperature of the effluent gas, indicating higher thermal efficiency than conventional fluidized beds. Plug-flow also permits us to collect solids samples with the distance along the bed proportional to residence time.

Figure 2. Solid and Gas Flow in Inclined Fluidized-Bed Reactor

Table 2. Summary of Design Conditions for the Mild Gasification PRU

Coal Feed Rate	100 lb/hr
Coal Size	minus 8-mesh
Drying System	
Recycle Gas Flow	72 scfm
Heater Capacity	40 kW
Reactor	0.35 x 6.75 ft IFB
Condensers (3)	70,000 Btu/hr
Condensers (2)	18,000 Btu/hr
Design Operating Pressure	3 psig
Mild-Gasification System	
Recycle Gas Flow	76 scfm
Heater 1	16 kW
Heater 2	65 kW
Reactor	0.35 x 10.8 ft IFB
Air-Cooled Condensers	85,900 Btu/hr
Water/Glycol-Cooled Condensers (3)	76,330 Btu/hr
Electrostatic Precip. Loading	4.2 gr/scf
Chilled Condenser	17,500 Btu/hr
Design Operating Pressure	4 psig

The drying reactor consists of a lower, rectangular section 4.25 inches wide by 81 inches long and 4 inches high. The bottom of the first 72 inches of the lower section is a flat-plate gas distributor. A recycle-gas inlet plenum having three equally spaced gas inlets is attached below the gas-distribution plate. A disengaging space above the lower section has a width increasing from 4.25 inches to 13.375 inches over the 16-inch height of the disengaging section. Three gas outlets are equally spaced along the top of the disengaging section. The coal inlet is located on the top of the disengaging section 2.75 inches from the front of the reactor. The dried coal outlet is in the bottom of the lower section 2.75 inches from the end of the reactor.

The drying reactor is welded construction except for the bottom of the recycle-gas inlet plenum and two access doors in the side of the disengaging space, which are attached by bolts. The reactor has three thermocouples (Table 3) centered in the width of the lower section 2 inches above the gas distributor as well as three in the gas inlets, three in the gas outlets, one in the coal outlet, and two on the outside to control adiabatic heaters.

The mild gasification reactor has a cross section that is identical to the dryer but is 130 inches long. It has four gas inlets, four gas outlets, four bed thermocouples, and a corresponding number of gas inlet and gas outlet thermocouples and bed sample ports.

Table 3. Location of Bed Thermocouples and Solids Sample Ports in the IFB Dryer and Mild-Gasification Reactor

	Thermocouples		Sample Ports	
	Distance from Inlet, Inches	Fraction	Distance from Inlet, Inches	Fraction
Dryer				
Zone 1	12.00	0.1574	21.00	0.2754
Zone 2	36.25	0.4754	45.25	0.5934
Zone 3	60.50	0.7934	69.50	0.9115
Outlet	76.25	1.0000	76.25	1.0000
Mild-Gasification Reactor				
Zone 1	15.00	0.1242	27.00	0.2236
Zone 2	45.25	0.3747	57.25	0.4741
Zone 3	75.50	0.6253	87.50	0.7246
Zone 4	105.75	0.8758	117.75	0.9752
Outlet	120.75	1.0000	120.75	1.0000

The two sets of condensers in the drying system and the water-cooled condensers in the mild-gasification system (Table 4) are cooled by recycling an ethylene glycol-water solution from an air-cooled heat exchanger. The fourth and fifth tubes from the air-cooled condenser were removed to reduce pressure drop across that condenser. A water-cooled coil was installed on the outside of the first tube in the air-cooled condenser to rapidly quench the effluent from the reactor.

Gases are analyzed once each hour using gas chromatographs. The chromatographs use thermoconductivity detectors for general gases, such as CO₂; photometric detectors for hydrocarbon gases; and flame ionization detectors for sulfur species.

Coal feed rate is controlled using a variable-speed screw feeder. Recycle gas flows are controlled by differential pressure controllers across the blowers. The flow rates are measured using turbine meters with temperature and pressure compensators. Temperature of recycle gas in both the drying and mild-gasification loops is controlled by electronic controllers, which vary the power load to the heaters to maintain a set outlet gas temperature. Both the dryer and mild-gasification reactor are equipped with adiabatic heaters that are automatically controlled. Pressure is maintained in both loops by vent valves, which are operated by pressure controllers.

Table 4. Design Parameters for Condensers in the Mild-Gasification PRU

Condensers	Process			Coolant			Overall U ^a	Area
	Flow, lb/hr	In. °F	Out. °F	Flow, gpm	In. °F	Out. °F	Btu/ft ² ·hr·°F	ft ²
Dryer								
First 3	542	400	90	4.7	70	100	4.09	165
Last 2	514	90	70	2.8	25	39	3.18	118
Mild Gasification								
Air-Cooled ^b	406	950	500				2.56	55
Water-Cooled	406	500	100	1.4	70	180	3.24	193
Chilled ^c	383	110	15				2.78	87

^a Heat transfer coefficient

^b Air at 80°F

^c Liquid CO₂ at 215 psig

The water-cooled condensers in the mild-gasification system develop a high pressure drop when the gas outlet temperature falls below 70°F (21°C) so we control the gas outlet at 70 to 80°F (21 to 27°C). Apparently, heavy tars build up in the tubes at low temperature. The pressure drop across the chilled condenser increases rapidly when the gas outlet temperature is below 75°F (24°C) so we control the gas outlet temperature at 75 to 85°F (24 to 29°C) to avoid the formation of hydrates in the tubes (HYSIM 1990).

Pressures, temperatures, flow rates, and differential pressures are read by a computer and displayed on a screen that is updated every 30 seconds. Key parameters are displayed graphically to assist in controlling conditions during tests. All of the data are stored on discs, and a hard copy is printed with data shown at 5-minute intervals. All of the liquid and solid materials are weighed. Gas flow from the dryer is measured using a dry-gas meter. Gas produced in the mild-gasification reactor is computed from gas analyses using a metered flow of 0.1 scfm of argon as a tracer.

3.2 Coal Preparation

Wyodak coal from the sampling system at the AMAX Eagle Butte mine is shipped in sealed steel drums to the PRU. The coal is screened to remove the plus 8-mesh particles, which typically are about 20 wt % of the coal. The minus 8-mesh fraction (Table 5) is stored for use in the PRU.

The moisture from the coal, typically 30 wt %, migrates to the outer and lower portions of the drums when the coal is stored out of doors in warm weather. When the coal contains about 33 wt % or more moisture, it is sticky and plugs the discharge from the feed screw. The coal will flow freely when it contains about 25 wt % moisture or less. The screened coal is stored indoors to avoid temperature cycles and is spread on the concrete floor to predry the coal overnight. This procedure results in coal containing about 28-29 wt % moisture that will flow through the feed system and plug the discharge from the feed screw less frequently.

Table 5. Feed Coal Size

Screen, mesh ^a	Sample, wt % Retained			
	A	B	C	D
6	0	0	1.1	1.2
8	0.6	5.0	6.0	5.7
20	42.5	33.0	48.1	48.1
40	29.6	25.3	24.3	23.7
70	16.8	19.3	11.2	10.9
100	4.6	5.6	2.8	2.9
140	2.3	4.5	2.0	2.1
200	1.0	1.8	0.8	1.0
Pan	2.6	5.5	3.6	4.2

^a U.S. Standard

The minus 8-mesh, floor-dried coal sticks to the sides of the coal feed hopper when the outside temperature is well below freezing. Apparently, the coal freezes to the sides of the feed hopper. We have observed that small sizes of undried Wyodak coal from the AMAX Eagle Butte mine freeze into solid blocks.

3.3 Coal Drying

The operating procedure for the drying tests is to purge air out of the system using CO₂, turn on the recycle gas blower, start the coolant flow to the condensers, and heat the fluidizing gas to 400°F (204°C). The coal feed is started to the dryer when the reactor temperature is below 450°F (232°C) to avoid heating the Nomex™ bags in the dust filter to over 450°F. When the flow of coal enters the drying reactor, the effluent gas temperature falls. We then increase the temperature of the fluidizing gas to the temperature for the test. If

the flow of coal is interrupted, it is necessary to reduce the temperature of the fluidizing gas to avoid damage to the filter bags.

A flow of about 10 scfh of CO₂ into the dryer feed lockhopper prevents moisture in gas from the dryer from being condensed on coal in the feed system. About one-half of the purge gas flows into the dryer, and the other one-half is vented through the feed screw. The drying system has a leak rate of 21 scfh at 3.0 psig and ambient temperature. Thus, during tests when the rate of gas production is less than 15 scfh, it is necessary to add CO₂ into the drying system to maintain a positive pressure on the system to prevent air from leaking into the system. We typically operate the drying system with 0.5 psig at the recycle blower suction and 2.0 psig at the blower discharge.

A pulse of high-pressure CO₂ is used to backflush the filter bags whenever the pressure drop across the bags exceeds 6 inches of water column. The backflush is used irregularly at intervals varying from 1 to 8 hours. The fines, dust, and dried coal receivers are purged with CO₂ whenever an empty receiver is put into service.

It is necessary to operate the dryer without the mild-gasification system to measure the residence time of coal in the dryer. The residence time of coal is determined by simultaneously stopping the coal feeder and switching dried coal receivers. The weight of coal from the bed is divided by the dry-coal feed rate to determine the residence time. When a drying test is conducted as part of a mild-gasification test, the dried coal flows into a lockhopper between the reactors, and no dried coal receiver is used.

Coal samples are taken from the various sample ports (Table 3) using a double-valve arrangement to prevent the escape of a large volume of gas and to cool the samples before the coal is permitted to contact air. Following this procedure, the sample ports are emptied, the inlet valves are opened, and the time of sampling is noted. The inlet valves are then closed, and 10 minutes are allowed to pass so the coal in the uninsulated pipe between the valves can cool. The samples are then drained into small jars, which are filled with coal and immediately sealed to minimize the exposure of dried coal to air. A similar procedure is used to collect samples of char from the mild-gasification reactor.

Condensed water from the drying operation flows into a small collection tank and is pumped to a collection drum each hour. Fines from the dryer cyclone flow into a collection drum, which fills after about 20 hours and is then replaced. The new drum is purged with CO₂ before the valve between the drum and cyclone is opened. Dust is drained from the bag filter into a sealed pail every four hours.

3.4 Mild-Gasification Tests

The procedure for operating the mild-gasification system is to purge the system using CO₂ until no oxygen is detected in the loop, establish the flow rate and then turn on the heaters and cooling system. When the bed temperatures reach 900°F (482°C), we turn on the electrostatic precipitator (ESP), the lockhoppers, and the coal feed. The temperatures and flow rate of recycle gas are then adjusted to the values specified for the test. The selected steady-state temperatures are typically reached in about 2 hours. When production of gas is detected, we light the flare used to burn the gas produced. The recycle gas composition reaches steady state in 3 to 5 hours. We typically operate the mild-gasification system with 0.5 psig at the suction of the recycle-gas blower and 7 psig at the discharge.

Fines from the cyclone and char from the reactor flow continuously into collection drums. Liquid products are drained from the system each half hour into sealed collection pails and drums. Liquid drain lines from the air-cooled condensers are held at 400°F (204°C), whereas drain lines from the water-cooled condensers and ESP are heated to 250°F (121°C). The drain line from the chilled condenser is not heated.

The temperature of the gas from the reactor is typically about 850°F (454°C), falling to about 350°F (177°C, skin temperature) at the outlet of the third tube in the air-cooled condenser and to about 325°F (163°C, skin temperature) at the outlet of the last tube. We control the temperature of the water-glycol coolant to hold the temperature of the gas from the water-cooled condensers in the range of 70 to 80°F (21 to 27°C). We hold the temperature of the gas from the chilled condenser at 75 to 85°F (24 to 29°C) by controlling the flow of liquid CO₂ to the chilled condenser. We collect large amounts of light liquids and water from the chilled condenser in spite of the apparently higher temperature from that unit.

The pressure profile in the mild-gas PRU at typical operating conditions is blower discharge, 7.0 psig; reactor, 6.0 psig; outlet from air-cooled condensers, 2.7 psig; outlet from water-cooled condensers, 1.7 psig; outlet from ESP, 1.5 psig; outlet from chilled condenser, 0.5 psig; and the blower suction pressure, 0.5 psig.

Temperature at zone 1 of the mild-gasification reactor bed fluctuates from 30 to 50°F (17 to 28°C) in 30 seconds. The fluctuations result from the steep temperature gradient in zone 1 and from the proximity of the zone 1 thermocouple to the coal inlet. (The lockhopper feeding the reactor operates on a 15-second cycle.) The temperature fluctuations become less pronounced as the char moves along the bed until almost no fluctuation is observed at zones 3 and 4.

We use the bed temperature at zone 4, which is usually the maximum bed temperature, to specify conditions for the tests. The temperature at zone 4 is readily controlled up to the maximum capacity the recycle gas heaters permit.

Heating rate in the first part of the reactor is an important determinant of liquid yield from mild gasification; therefore, we attempted to increase the heating rate. We conducted tests 115, 117, and 118 with all four valves in the recycle gas inlet lines to the reactor fully open. For tests 119 and after, we used differential pressure readings to partially close the valves to zones 2, 3, and 4. This reduced the flow to each of these zones by 10%, while increasing the gas flow to zone 1 by 30%. We expected this alteration to increase the heating rate by about one-third. Instead, the heating rate was increased only slightly, probably because the difference in differential pressure across the distributor plate in each zone with the valve fully open and then closed was only about 1 inch of water. The change in differential pressure was too small to accurately adjust the gas flow.

3.5 Collection of Coal Liquids

Collection of the liquid products from these tests is difficult because of the properties of the liquids. Some of the heavier liquids have pour points above 150°F (66°C), whereas light liquids have relatively high vapor pressures at 150°F. Much of the liquid enters the collection system in the form of mist. Dust from the reactor, which is not separated in the cyclone, collects in the liquids, as does water.

Liquids from air-cooled condenser tubes 1-3 were initially collected in the first receiving pail. This liquid has a very high pour point because of the high molecular weight and the 2 to 5 wt % ash present suggesting the presence of large amounts of dust. The 1-inch drain lines from the 3-inch condenser tubes frequently plug even though the lines are kept at 350 to 400°F (177 to 204°C) during the tests. Fortunately, we collect only a small amount of this material, which is a hard, black, shiny substance at ambient temperature. After test 120, we attached collection pots directly to the bottoms of the tubes because the drain lines plugged so often.

The condensate from tube 6 of the air-cooled condenser and water-cooled condenser 1 commonly contains only about 0.2 wt % ash, and now and then we find a water phase in this receiver. This material flows from the condensers more readily; although, it is necessary to keep the drain lines at about 300°F (149°C) to prevent plugging, which can occur now and then.

The condensate from water-cooled condensers 2 and 3 represents a large fraction of the total condensate and nearly always has a layer of water in the receiver along with the heavy tar. The tar is a semisolid at room temperature. The condenser drain lines are heated to about 300°F (149°C) and rarely plug.

The condensate from the ESP typically represents about 2 wt % of the raw coal and is a fairly small fraction of the total condensate. The condensate is a tacky paste at ambient temperature and contains about 2 to 4 wt % water within the tar phase. We maintain the shell of the ESP at 125°F (52°C) and rarely see a water phase in this receiver. The drain line is heated to about 250°F (121°C) and rarely plugs. The condensate from the chilled condenser is water that is contaminated with organics and flows readily through an unheated 1-inch drain.

After test 120, we combined the drains from ACC 6 and WCC 1 with those from WCC 2 and WCC 3 to reduce the number of containers being handled.

We separated the water from the liquids produced during test 115 by distillation in a batch still. We had planned to keep the steam-heated coils in the pot at a low temperature but the heat transfer was so poor that it was necessary to use 700°F (371°C) steam in the coil. The distillate was readily decanted to separate the water and light-oil phases.

Condensates from tests 117 through 120 were dewatered by blending the water containing portions in a small tank while mixing at 140°F (60°C). After setting for 2 hours, most of the water was separated from the liquid by decanting. The liquid from test 122 was distilled into IBP to 420°F, 420 to 720, and 720+°F (IBP to 216, 216 to 382, and 382+°C) boiling fractions.

4.0 RESULTS AND DISCUSSION

This section describes the results of shakedown, drying, and mild gasification tests.

4.1 Shakedown Tests

Shakedown tests were run to verify that the individual equipment items were operable, to determine the operating characteristics of the PRU, and to gain experience with the system.

We reduced the rate of leakage from the drying system (at 3.0 psig using CO₂ and ambient temperature) to 21 scfh, which is approximately equal to the rate of gas production in the dryer. However, we could not justify spending more time locating and repairing leaks in the drying system. The leakage rate of gas from the mild-gasification system was reduced to 8 scfh at 3.0 psig and ambient temperature, which was well below the 60 to 150 scfh estimated gas production. The leakage rate was low enough to maintain a safe carbon monoxide level in the building.

The first successful tests with the drying system were conducted to determine the coal residence time in the dryer (Table 6) by shutting off the coal feed, collecting and weighing the coal from the dryer bed, and dividing the

weight of the bed by the dry-coal flow rate. All subsequent tests at a feed rate of 100 lb/hr were conducted using a coal residence time of approximately 3 minutes in the dryer.

Table 6. Coal Residence Time in Dryer

Gas Flow, scfm	Slope, degrees	Residence Time, minutes
83	0	7.8
79	3.3	3.2

Shakedown tests also demonstrated the superior thermal efficiency of the IFB reactor over conventional fluidized beds (Figure 3). The gas leaves the IFB dryer much below the maximum bed temperature. The temperature of the gas from a conventional fluidized bed leaves the reactor at or slightly above the temperature of the fluidized bed. The reduction in effluent gas temperature from IFB reactors is possible because of the nonisothermal, plug-flow characteristics of IFB reactors. By contacting the coal at successively increasing temperature along the coal bed, the average temperature of the gas mixture leaving the reactor is much below the maximum bed temperature.

The superior thermal efficiency of IFB reactors has important economic ramifications. First, less heat is required to drive the process. Second, the equipment in the gas effluent stream (i.e., cyclone, dust filters, condensers) can be smaller because the lower temperature reduces the volume of gas to be handled.

Bed temperatures in the dryer (Figure 4) remain almost constant near the inlet end of the bed (zone 1) where the water on the coal acts as a heat sink. (The upsets between 2 and 4 hours were caused by interruptions in the flow of coal to the dryer.) As the coal moves farther into the dryer and the water is removed (zones 2 and 3), the bed temperature is sensitive to variations in water content of the coal and fluctuates.

A graph of coal moisture content and dryer bed temperature as functions of distance along the dryer (Figure 5) shows that the moisture is rapidly removed from the coal at a bed temperature of about 150°F (66°C). Drying is nearly complete at a distance one-half way along the bed. After the moisture is removed from the coal, the temperature of the coal increases rapidly. The portion of the bed operating at elevated temperature removes volatiles from the coal. The graph also shows that the inclined fluidized-bed dryer has the capacity to dry and partially decarboxylate much more than 100 lb/hr of Wyodak coal.

Figure 3. Dryer Temperatures During Shakedown Test 111

Figure 4. Dryer Bed Temperatures During Shakedown Test 111

Figure 5. Removal of Moisture in the Inclined Fluidized-Bed Dryer

Figure 6 shows the temperatures of the fluidizing gas flowing into the mild-gasification reactor, the last part of the mild-gasification bed (zone 4), and the gas flowing from the reactor to the air-cooled condensers. Again, the superior thermal efficiency of the inclined fluidized-bed mild-gasification reactor over a conventional fluidized bed is shown by the gas outlet temperature below the temperature in zone 4.

Temperatures of the coal bed from the inlet (zone 1) of the mild-gasification reactor to the last zone (4) are shown in Figure 7. Interruptions in the coal flow cause the temperature upsets between 2 and 4 hours. These data show rapid increases in the temperature in zones 1 and 2 with smaller temperature increases in zones 3 and 4. The test was conducted using a maximum bed temperature of 1050°F (566°C).

The rate of volatiles removal from the coal is shown as a function of distance along the mild-gasification reactor in Figure 8. Essentially, all of the volatiles removal occurs in the first one-third of the reactor where the temperature increases rapidly. The heating rate of 330°F/min (166°C/min) from the coal inlet to zone 1 is approximately twice the heating rate we were able to achieve using the 10-lb/hr unit. Data from the 10-lb/hr tests show that heating rates in zones 1 and 2 are strong determinants of liquid yield. The data in Figure 8 also show that a residence time of much less than 9 minutes is adequate to achieve devolatilization and that the reactor is capable of much higher coal throughput.

Steady-state composition of the recycle gas is achieved in the mild-gasification system in 5 hours using a maximum bed temperature of 1050°F (566°C, Figure 9). The time to achieve steady-state composition of the recycle gas was the determining factor in our decision to conduct 24-hour tests. We were particularly concerned about the CO₂ concentration because the CO₂-char reaction affects the bed temperature.

After test 112, the following modifications were made to the PRU to improve the quality of the test data.

- The solids pump was removed and replaced with a lock hopper to make the coal feed flow less susceptible to interruptions.
- The valves on the lock hopper between the dryer and mild-gasification reactor were replaced to reduce leakage and provide reliable flow of coal.
- A cooling coil was placed on the first air-cooled condenser to rapidly quench the vapors flowing from the reactor. Air-cooled condensers 4 and 5 were removed to reduce pressure drop.
- A drip pot was installed in the suction pipe to the recycle gas blower in the mild-gasification system to collect liquids that were not removed in the chilled condenser.

Figure 6. Mild-Gasification Temperatures During Shakedown Test 111

Figure 7. Mild-Gasification Bed Temperatures During Shakedown Test 111

Figure 8. Volatiles Removal from Wyodak Coal in the Mild-Gasification Reactor

Figure 9. Composition of Recycle Gas from Test 111

Tests 115 through 120 were conducted as 24-hour tests. Following test 120, we made additional modifications to increase the capacity of the PRU and to facilitate the conduct of 5-day tests:

- The capacity of the coal feed screw was increased to 200 lb/hr.
- The capacities of both the coal-feed lockhopper and the lockhopper between the reactors were increased correspondingly.
- The piping around the mild-gasification heaters was revised to reduce heat losses and increase heat input to the mild-gasification reactor.
- Thermocouples were installed in all gas inlets and outlets immediately adjacent to the drying and mild-gasification reactors.
- A larger capacity pump was installed to increase the flow of cooling water through tubing attached to the outside of the first section of the air-cooled condenser.
- Larger liquid collection pots were installed to reduce the number of containers of liquid collected from each test.

Tests 122 thru 125 were conducted for long periods (~100 hr, Table 8) to produce sufficient quantities of char for upgrading tests.

4.2 Coal Drying Tests

Tests 107, 111, 113, and 114 were conducted as separate drying tests (Table 7). Drying tests were also conducted as part of mild-gasification tests for tests 115 and later (Table 8). Material balance results for drying tests 115 and later are reported as part of mild-gasification tests in the next section of this report.

Coal drying tests 113, 114, and 115 were conducted to determine the effects of drying temperature upon the rate of drying, the quantity and characteristics of the water produced, and the quantity and composition of gas produced. Flow rates and temperatures in Table 7 are averages from the entire length of the tests.

For test 113, we controlled the temperature of the coal bed in the dryer at the zone 3 thermocouple located 0.8 of the distance through the bed at a position where the temperature is increasing rapidly. Thus, slight shifts of the drying curve (Figure 10) caused fluctuations of the temperature. Beginning with test 114, we controlled the temperature of the fluidizing gas at a constant value, thereby, reducing the fluctuations of temperature at zone 3.

Drying curves from tests 113, 114, and 117 (Figures 10, 11, and 12) show that nearly all the moisture is removed from the coal in the first half of the bed where bed temperatures reach 150 to 200°F (66 to 93°C). The bed temperatures increase rapidly in the last half of the bed where the coal is partially decarboxylated, producing gas from the coal.

Table 7. Summary of Drying Conditions

Test:	107	111	113	114
Fluidizing Gas				
Flow, scfm	80	79	82	92
Temp, °F	804	721	661	580
Coal Feed Rate, lb/hr	-	102	93	103
Bed Temp, °F				
Zone 1 (0.16)	155	145	136	135
Zone 2 (0.48)	338	167	207	178
Zone 3 (0.79)	554	486	440	348
Water in Coal, wt %				
Zone 1 (0.28)	10.8	6.9	2.5	3.8
Zone 2 (0.59)	0.1	0.6	0.6	0.9
Zone 3 (0.91)	0.0	0.0	0.4	0.4

Numbers in parentheses () show fraction of bed length

A sample of raw coal and samples from the dryer heated to 310 and 550°F (154 and 288°C), respectively, were analyzed using infrared spectroscopy to verify that decarboxylation does occur in the dryer. The three coal samples were investigated using Fourier transform infrared spectroscopy (FT-IR). The method of analysis included diffuse reflectance Fourier transform (DRIFT) spectroscopy and photoacoustic spectroscopy (PAS). The PAS experiment was conducted on the coal, whereas the DRIFT experiment was conducted on a portion of the coal mixed with potassium bromide. After comparing the data and determining the limitations of the DRIFT method, we chose the PAS data to assess the results of the experiments. The results from these methods are not quantitative, but definite trends can be identified.

Figure 10. Coal Moisture Content and Dryer Bed Temperature During Test 113

Figure 11. Coal Moisture Content and Bed Temperature During Test 114

Figure 12. Coal Moisture Content and Bed Temperature During Test 117

Table 8. Conditions Used for Drying Coal During Mild-Gasification Tests

Test:	115	117	118	119	120	122	123	124	125	126
Fluidizing Gas										
Flow, scfm	93	92	84	86	83	81	82	80	87	81
Temp, °F	540	540	620	540	699	710	817	754	578	709
Coal Feed Rate, lb/hr	104	119	94	93	107	96	149	138	149	93
Bed Temp, °F										
Zone 1 (0.16)	130	128	129	128	136	142	169	178	159	145
Zone 2 (0.48)	162	151	163	150	230	267	224	254	181	287
Zone 3 (0.79)	296	284	420	347	531	549	430	466	277	547
Water in Coal, wt %										
Zone 1 (0.28)	18.4	5.8	0.6	-	5.5	1.5	1.2	-	9.6	16.2
Zone 2 (0.59)	2.0	0.8	0.1	-	0.4	1.3	0.0	-	0.5	2.3
Zone 3 (0.91)	0.0	0.0	0.0	-	0.0	0.3	0.4	-	0.0	0.0
Test Duration, hr	24	24	25	25	25	103	102	64	98	24

All tests were conducted using minus 8-mesh Wyodak coal and a coal residence time of approximately three minutes.

Numbers in parentheses () show fraction of bed length

The spectra from the dried coal samples are very similar suggesting that the structures are similar. The intensity of absorption in the 3400 to 2200 cm^{-1} region, characteristic of hydrogen-bonded hydroxyl groups, shows definite decreases in the dried coal samples relative to the raw coal. The infrared analysis detects the loss of water from the samples of dried coal. We also observe a definite decrease in the intensity of absorption in the carboxyl region (1800 to 1650 cm^{-1}) for the dried coals relative to the raw coal. This suggests that the drying process has caused a loss of C=O type functional groups from the structure of the dried coals. Poor resolution of the peaks, a characteristic of the samples, does not allow definitive identification of individual functional groups (e.g., carboxylic acids, ketones). However, at the low temperatures prevailing in the dryer, decarboxylation of carboxylic acids to produce carbon dioxide is a reasonable conclusion.

Coal balances for tests 113 and 114 show that we produced only 0.3 to 0.4 wt % of the raw coal as gas (Table 9). The high water production from test 113 (33.5 wt %) was caused by loading coal into the feed hopper while rain was falling.

Gas produced from the coal in the dryer is calculated from volatiles content because we are presently unable to measure the gas production rate directly. Direct measurement of gas production in the dryer is not presently possible because:

1. The drying system has a leak rate of 21 scfh at 3.0 psig. We will only make about 15 scfh of gas if 1 wt % of volatiles is driven from the coal.
2. It is necessary to add gas to the dryer to maintain a positive pressure and avoid air leaking into the dryer.
3. A purge of about 5 scfh of carbon dioxide enters the dryer from the coal feed lockhopper. The purge is used to prevent moisture from the dryer from condensing on coal in the feed system.
4. A small amount of air enters the dryer with the coal feed.
5. A small amount of gas from the mild-gasification system leaks into the dryer when the mild-gasification system is operated as part of the test.

Table 9. Coal Balances for Drying Tests

Test:	113		114	
	wt, lb	%	wt, lb	%
Coal Fed	648.0	100.0	762.9	100.0
Water Produced	217.0	33.5	227.1	29.8
Fines	43.7	6.7	51.9	6.8
Dust from Filter	0.4	0.1	0.8	0.1
Gas	2.3 ^a	0.4	2.2 ^a	0.3
Dried Coal	398.2	61.5	494.5	64.8
Total Out	661.5	102.1	776.5	101.8

^a Calculated from loss of volatiles

Before test 114, we changed the inert gas purges on the dried coal and fines receivers from nitrogen to carbon dioxide to eliminate any possibility of nitrogen entering the drying system. The gas analyses from the drying system from test 114 (Table 10) show that the concentration of nitrogen increases throughout the test. This leads us to conclude that air enters the dryer with the coal feed. The composition of the recycle gas did not reach a steady-state composition during the 8-hour test, as evidenced by the increasing nitrogen concentration.

Table 10. Composition of Gas in the Drying System During Test 114

Time, hours	Composition, vol %					
	N ₂	O ₂	CO	CO ₂	CH ₄	C ₂ H ₆
1	0.707	0.124	0.020	99.135	0.013	ND
2	0.642	0.118	0.217	98.885	0.112	0.027
3	0.974	0.128	0.457	98.402	0.032	0.006
4	1.709	0.134	0.624	97.487	0.035	0.007
5	1.935	0.105	0.780	97.126	0.046	0.009
6	2.675	0.117	0.887	96.262	0.050	0.010
7	3.588	0.129	0.825	95.401	0.047	0.010
8	3.789	0.113	0.881	95.152	0.054	0.011

ND indicates that the component is not detectable.

Clearly, some carbon monoxide, methane, and ethane are produced in the dryer at the conditions used for test 114. However, the effluent gas from the dryer can be readily incinerated in the commercial process we propose by injecting the gas into the fluidized-bed combustor used to produce heat for the process.

The data in Table 10 are of concern because it is well known that when mild oxidation of coal is used to prevent agglomeration of caking coals, it causes a substantially lower yield of liquid products. We may be, unintentionally, oxidizing coal in the drying system. Oxygen from the air is being consumed to produce products other than carbon monoxide.

The proximate analyses of fines from the cyclone and dust from the bag filter are listed in Table 11. Screen analysis of the fines is listed in Table 12. The dust is too finely divided to permit measurement of size distribution using dry sieve analysis.

Table 11. Proximate Analyses of Fines and Dust from Test 114, wt %

Material Source	Fines Cyclone	Dust Filter
Moisture	6.2	3.4
Volatiles	42.2	40.4
Ash	7.8	6.6
Fixed Carbon	43.9	49.7

Table 12. Screen Analysis of Fines from Cyclone Produced in Test 114

Screen Size, mesh ^a	wt % Retained
6	0
8	0
20	0
40	0
70	0
100	0
140	11.0
200	20.0
Pan	69.0

^a U.S. Standard Testing Sieves

Water condensed in the drying system during tests 113, 114, and 115 was analyzed to determine the quality of water produced at various drying bed temperatures. The water was preserved and analyzed using U.S. EPA approved protocols. Results of the water analyses (Table 13) show that the condensed water is relatively clean, containing little solids and inorganics. The total organic carbon (TOC) will require further characterization if condensing and using the water remains part of the process being considered for commercial development. Clearly, organic compounds other than phenols are present in the water. The water probably contains benzene, toluene, xylene and substituted derivatives of those compounds.

If the compounds represented as TOC are biologically degradable, the water can be made suitable for use in irrigation, livestock consumption, or reinjection by treating it in a carbon bed containing active bacteria. If the TOC is resistant to biological destruction, air stripping is more suitable. Both of these treatments are low-cost operations.

Table 13. Composition^a of Water Produced by Drying Coal

Test:	115	114	113
Fluidizing Gas Temp, °F	540	579	640
Zone 3 Bed Temp, °F	316	365	434
pH	4.4	4.6	4.6
Total Organic Carbon	75	66	146
Total Dissolved Solids	20	23	330
Total Suspended Solids	<10 ^b	<10	150
Phenols as Phenol	1.5	6.6	6.1
Ammonia as N	2.5	2.0	3.3
Sulfide	<1	1	<1
Sulfate	<5	<5	<5
Alkalinity as CaCO ₃	<10	<10	<10
Carbonate as CaCO ₃	<1	<1	<1
Bicarbonate as CaCO ₃	<10	<10	<10
Cyanide	<0.020	<0.020	<0.020
Aluminum	<0.045	0.069	0.059
Arsenic	<0.100	<0.100	<0.100
Barium	0.020	0.049	0.028
Beryllium	<0.002	<0.002	<0.002
Boron	<0.020	<0.020	<0.020
Calcium	0.193	0.500	0.622
Cadmium	<0.010	<0.010	<0.010
Chromium	0.009	0.014	0.013
Iron	3.00	4.35	4.78
Phosphorous	<1.00	<1.00	<1.00
Potassium	<5.00	<5.00	<5.00
Magnesium	0.041	0.101	0.106
Selenium	<0.100	<0.100	<0.100
Silver	<0.007	<0.007	<0.007
Sodium	0.116	0.192	0.205
Silicon	<0.100	<0.100	<0.100
Lead	<0.050	<0.050	<0.050
Thorium	<0.050	<0.050	<0.050

^a All units are mg/L except temperature and pH.

^b The less than symbol(<) indicates none detected above the respective detectable limit.

A graph of moisture content of the coal versus dryer bed temperature (Figure 13) shows that the coal is completely dry when the bed temperature reaches 350°F (177°C). These data also show considerable variation in water content of the coal in the range of 120 to 150°F (49 to 66°C), typical bed temperatures at zone 1 (0.15 of the dryer length).

The loss of volatiles from coal in the dryer compared with the temperature at zone 3 (0.8 of the bed length, Figure 14) shows a gradual increase in the loss of volatiles up to about 500°F (260°C) and then a rapid loss of volatiles as the temperature increases above 500°F. A major concern is the quantity of volatiles that can be removed from the coal as gas before condensable volatiles (tars) are removed from the coal. We want to remove as much gas as possible from the coal in the dryer without removing any tars. We have had numerous excursions of the zone 3 bed temperature in the dryer to 580°F (304°C) with no detectable emission of tars. During test 122, we experienced an upset during which the bed temperature at zone 3 climbed to 609°F (321°C). The pressure drop across the bag filter began immediately to increase and continued to increase for 15 hours, reaching 47 inches of water. After test 122, the bag filter was coated with tar. This suggests that the emission of tars begins between 580 and 609°F (304 and 321°C) and is rather rapid at 609°F with the heating rate used in the dryer.

4.3 Mild-Gasification Tests

The first five mild-gasification tests were conducted to determine the effects of maximum bed temperature and heating rate upon the yield of liquid products. For tests 115, 117, and 118, we attempted to use maximum bed temperatures (zone 4 in Table 14) of 950, 1050, and 1150°F (510, 566, and 621°C). We were not able to achieve an average temperature of 1150°F (621°C) during test 118. However, we did maintain an average of 1129°F (609°C), which is significantly higher than the maximum temperature attained during the previous test.

For tests 119 and 120, we attempted to achieve heating rates of 400 and 500°F/min (222 and 278°C) while maintaining the maximum temperatures used during tests 117 and 118. We calculate heating rate as the difference between bed temperature at zone 1 and the temperature of coal entering the reactor divided by the time required for coal to flow from the reactor inlet to the zone 1 thermocouple. Thus, low coal inlet temperatures result in high heating rates and vice versa.

Figure 13. Moisture Content of Wyodak Coal Versus Dryer Bed Temperature

Figure 14. Loss of Volatiles from Coal in the Dryer Versus Bed Temperature at Zone 3

We used differential pressures across the reactor as indicators while adjusting valves at each of the four gas inlets to increase the flow of gas into zone 1, and while reducing the flow of gas into zones 2, 3, and 4 for test 119. This effort resulted in producing a heating rate only slightly higher than that used for test 117. The attempt to achieve a heating rate of 400°F/min (222°C) was not successful because the flow adjustments could not be made with sufficient accuracy using the differential pressure measurements available from the existing equipment.

For test 120, we increased the temperature of the coal flowing into the reactor to achieve a higher temperature in zone 1 than we had achieved during test 118. This attempt resulted in only a slightly higher temperature in zone 1 for test 120 than that used for test 118. Our attempts to separate the effects of heating rates from temperature were not successful. The heating rates achieved in the tests with the PRU are roughly twice as high as heating rates used in bench-scale tests.

Table 14. Conditions Used for Mild Gasification Tests

Test	Bed Temperature, °F				Heating Rate, °F/min	
	Zone 1 (0.1242)	Zone 2 (0.3747)	Zone 3 (0.6253)	Zone 4 (0.8758)	Zone 1	Zone 2
115	659	869	914	950	325	93
117	669	916	987	1043	344	110
118	777	1010	1068	1129	319	103
119	721	952	995	1050	335	102
120	794	1023	1071	1131	235	102
122	880	1061	1124	1113	381	83
123	822	1030	1040	1051	574	95
124	941	1020	1080	1079	695	36
125	722	907	974	993	651	84
126	827	1036	1133	1146	322	95

Numbers in parentheses () show fraction of bed length

All mild gasification tests were conducted using recycle gas (fluidizing gas) flow rates of approximately 80 scfm. The char residence times were approximately 9 minutes for tests 115 through 120, 7 minutes for tests 122 and 126, and 5.5 minutes for tests 123 through 125. Char residence times are defined as the weight of char in the bed divided by the average char production rate.

For test 122, we adjusted the slope of the mild-gasification reactor from the 3 degrees used for tests through 120 to 5 degrees to reduce the residence time of char in the reactor. During test 122, we fed coal to the dryer for 103 hours. Late in the test, we experienced problems with a high pressure drop across the bag filter in the drying loop, numerous fuses being blown in the power supply to the 65 kW recycle-gas heater in the mild-gasification loop, high pressure drop across the air-cooled condensers, and the recycle-gas blower in the mild-gasification loop tripping off three times because of electrical overload. During the test, we operated the air-cooled condensers with the gas outlet temperature at 500 to 550°F (260 to 288°C) instead of the typical 350°F (177°C). This was done to permit the tar and dust mixture in the condensers to flow to reduce the pressure drop. We also operated the gas outlet from the chilled condenser at about 85°F (10 degrees above normal) to soften the tar accumulating in the recycle gas blower. These temperature changes resulted in less liquid being collected from the water-cooled condensers and chilled condenser and more liquid being collected from the electrostatic precipitator than when operating at normal temperatures. In spite of these problems, test 122 was continued to the planned shutdown time.

The 65 kW heater in the mild-gasification loop was opened, and we found large deposits of carbonaceous material and numerous broken and melted heating elements. Both recycle gas heaters in the mild-gas loop were rebuilt before test 123. Also, the insulation on the pipes between the heaters and the mild gasification reactor was repaired.

Test 123 was conducted at an average feed rate over 149 lb/hr for 102 hours. After we experienced an abnormally high incidence of plugging of the coal feed to the dryer, we found that the float in the rotameter that supplies CO₂ to the coal feed lockhopper was stuck, and no CO₂ was flowing. After correcting this problem, the incidence of plugging in the coal feed system was greatly reduced.

The higher coal feed rate (150 versus 100 lb/hr) makes the dryer much more susceptible to temperature excursions because we use a higher fluidizing-gas temperature than we use at the lower feed rate. Dryer bed temperatures above 600°F (316°C) cause the ΔP across the bag filter to increase because the deposition of tar reduces the recycle gas flow rate.

The mild-gasification reactor operates well at a maximum bed temperature of 1050°F (566°C) using a feed rate of 150 lb/hr with clean recycle gas heaters. The outlet temperatures from the 65 and 18 kW heaters were 1140 and 1305°F (616 and 707°C), respectively, well below the operating limits. We also observed a temperature profile in the reactor in which the bed temperature reached 1050°F (566°C) at zone 2 and remained constant to the outlet of the reactor. The changed temperature profile is probably a result of better insulation on the four fluidizing gas inlet pipes.

The pressure drop across the air-cooled condensers did not increase as much as during the previous 5-day test.

Test 124 was conducted with the objective of using a feed rate of 150 lb/hr and a maximum bed temperature in the mild-gas reactor of 1100°F (593°C). We continued to experience a high pressure drop across the dust filter caused by tar deposits resulting from upsets and temperature excursions in the dryer. On the third day of the test, the recycle-gas flow in the drying loop became very erratic, the temperature of the gas to the dryer fell below 500°F (260°C), and it could not be increased. (This was later diagnosed as being caused by slugs of water passing through the blower and heater and entering the pneumatic recycle flow controller. The water entered the gas stream because the drain from one of the condensers was plugged.) The pressure drop across the water-cooled condensers (WCCs) in the mild-gas loop also increased to unacceptably high levels (84 inches of water) causing the recycle gas blower to trip off from high discharge temperatures. Test 124 was terminated after feeding coal at an average rate of 138 lb/hr for 64 hours.

Following test 124, we opened the process side of the water-cooled condensers and cleaned out the heads and tubes. This is the first time the WCCs were cleaned after 428 hours of operation feeding dried coal to the mild-gasification system. About 164 of the hours were at feed rates of approximately 150 lb/hr. It was necessary to drill the tar out of the tubes in WCC 1. WCC 2 and WCC 3 were rodded out. The tar would not flow when the shell was heated to about 240°F (116°C). (We routinely clean the air-cooled condensers after each test). We also put clean bags in the dust filter in the drying loop after test 124.

During test 125, we avoided putting tar on the bags in the dust filter by controlling the temperature of the gas to the dryer at 600°F (316°C). This strategy worked, as evidenced by the low pressure drop across the bag filter (8 to 11 inches of water) throughout the test.

During the first day of test 125, the test was stopped for 6 hours because of slugs of water in the dryer recycle system. After we diagnosed and corrected the problem (a plugged condenser drain line), flow control and temperature control were good for the remainder of the test. During the last day of test 125, the pressure drop across the air-cooled condensers suddenly increased to 77 inches of water, and the recycle gas flow was too low to sustain operation in the mild-gasification loop. We were not able to reduce the ΔP by increasing the temperature in the condensers, and we terminated the test 7 hours sooner than we had planned.

We conducted test 126 for 24 hours using a feed rate of 100 lb/hr, while attempting to maintain a maximum bed temperature of 1200°F (649°C) in the mild-gas reactor. We were not able to maintain 1200°F (649°C) and stay within the design temperature limits of the recycle gas heaters in the mild-gas loop. The bed averaged a disappointing 1146°F (619°C), only 17°F (9°C) hotter

than the previous maximum temperature. Test 126 was conducted with no significant upsets or problems except for our inability to achieve our temperature objective.

Temperatures and heating rates listed in Table 14, particularly the zone 1 temperatures, are dependent upon factors outside of the immediate flows and temperatures controlled within the mild-gasification reactor. First, the temperature of the coal leaving the dryer (Table 7, zone 3 bed temperatures) affects the temperature of char in the mild-gasification reactor, particularly at zone 1. Second, heating rates are calculated values that depend upon the accuracy of the estimated residence times. Third, changing the slope of the mild-gasification reactor and revising the piping at the mild-gasification loop recycle-gas heaters after test 120 caused the temperature-devolatilization response of tests before and including 120 to differ from that of tests after and including 122. Test 121 failed, and no data were collected.

Coal balances for the tests are listed as weight of components (Table 15) and as wt % of the raw coal feed (Table 16). Following test 120, we revised the liquid receivers to increase the capacity of the containers and reduce plugging in drain lines. This was done by combining the drains from air-cooled condenser 6 and water-cooled condenser 1 with drains from water-cooled condensers 2 and 3. All weights were determined by placing materials on a scale except the weight of gas produced. Gas produced in the dryer was determined from volatile balances. Gas produced in the mild-gasification loop was determined by argon tracer balance for all tests except 122. After test 122, we found that the meter used to measure the argon flow had gradually failed during the test. Gas produced during test 122 was determined by forcing closure on the coal balance.

In the later series of tests (122-126), production of fines from the mild-gasification loop increased (Table 16), the quantity of char decreased slightly, and the amount of gas produced from the mild-gasification loop decreased. Fines from drying are collected using a cyclone, whereas dust is collected using a bag filter. Water collected from drying during test 120 is low because the coal was floor-dried longer than normal.

The weights of condensed liquids in Tables 15 and 16 are crude liquids that contain water. The water content of the liquids is listed in Table 17. Condensates from air-cooled condensers 1-3 contain no water. We determined the water content of samples of condensates from air-cooled condenser 6, the water-cooled condensers, and the electrostatic precipitator using azeotropic distillation with toluene for samples blended in proportion to the weight of condensate collected from the respective receivers. We used total organic carbon analyses to determine the oil content of water from the chilled condenser.

Table 15. Product Distribution from Mild-Gasification (MG) Tests, lb of material

Test:	115	117	118	119	120	122	123	124	125	126
Raw Coal Feed	3444.0	2892.6	2341.8	2391.3	2637.9	9834.0	15128.9	8855.8	14574.3	2201.7
Fines from Dryer	177.0	156.0	136.5	159.8	182.6	464.7	724.4	488.8	734.7	180.1
Dust from Dryer	0.8	1.9	20.9	8.4	5.3	6.9	1.0	1.5	22.0	0.0
Water from Dryer	995.3	862.4	677.0	702.4	697.0	3014.0	4560.5	2721.1	4270.9	672.0
Gas from Dryer	26.4	25.4	16.3	19.1	26.4	228.2	305.3	206.4	244.0	24.6
Fines from MG	66.7	73.6	58.8	51.9	120.1	607.0	944.7	604.2	958.0	136.7
Char	1475.4	1157.4	915.3	966.3	1072.3	3566.9	5770.4	3292.7	5891.9	874.9
Gas from MG	119.3	257.9	230.3	203.7	246.9	698.7	754.7	644.4	604.2	137.2
Liquids from MG										
ACC 1-3	6.2	6.2	6.3	4.7	4.5	33.8	33.1	3.3	59.1	11.9
ACC 6, WCC 1	108.8	180.8	76.4	78.5	90.7	707.6	1093.7	646.2	677.0	135.4
WCC 2, WCC 3	138.1	151.6	116.0	114.8	139.7					
ESP	56.2	65.2	71.9	59.1	62.1	356.6	354.1	261.9	492.5	52.4
Chilled Cond.	36.3	19.1	44.0	43.5	36.4	78.7	391.3	235.3	322.4	57.4
Total Out	3206.5	2957.5	2375.0	2412.2	2683.7	9763.1	14933.1	9105.7	14276.5	2282.5

Liquid products collected from ACC 6 and WCC 1 were combined with liquids drained from WCC 2 and WCC 3 for all tests after 120.

Table 16. Product Distribution from Mild-Gasification (MG) Tests, wt % of raw coal

Test:	115	117	118	119	120	122	123	124	125	126
Raw Coal Feed	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0
Fines from Dryer	5.2	5.5	5.8	6.7	6.9	4.7	4.8	5.5	5.0	8.2
Dust from Dryer	0.0	0.0	0.9	0.3	0.2	0.1	0.0	0.0	0.2	0.0
Water from Dryer	28.9	29.8	28.9	29.4	26.4	30.7	30.1	30.8	29.3	30.5
Gas from Dryer	0.8	0.9	0.7	0.8	1.0	2.3	2.0	2.3	1.7	1.1
Fines from MG	1.9	2.5	2.5	2.2	4.6	6.2	6.2	6.8	6.6	6.2
Char	42.8	40.0	39.1	40.4	40.7	36.4	38.1	37.2	40.4	39.7
Gas from MG	3.5	8.9	9.8	8.5	9.4	7.1	5.0	7.3	4.2	6.2
Liquids from MG										
ACC 1-3	0.2	0.2	0.3	0.2	0.2	0.3	0.2	0.0	0.4	0.5
ACC 6, WCC 1	3.2	6.3	3.3	3.3	3.4	7.6	7.2	7.3	4.6	6.2
WCC 2, WCC 3	4.0	5.2	5.0	4.8	5.3					
ESP	1.6	2.3	3.1	2.5	2.4	3.6	2.3	3.0	3.4	2.4
Chilled Cond.	1.1	0.7	1.9	1.8	1.4	1.1	2.6	2.7	2.2	2.6
Total Out	93.2	102.3	101.5	100.5	101.7	100.2	98.7	102.9	98.0	103.7

Liquid products collected from ACC 6 and WCC 1 were combined with liquids drained from WCC 2 and WCC 3 for all tests after 120.

Table 17. Summary of Liquids Produced by Mild Gasification (MG)

Test:	115	117	118	119	120	122	123	124	125	126
Water, lb	139.3	207.3	94.8	93.2	113.7	417.5	641.7	379.9	460.1	81.1
Water, wt % of raw coal	4.0	7.2	4.8	3.9	4.3	4.2	4.2	4.3	3.2	3.7
Hydrocarbons, lb	202.6	211.7	232.6	207.2	219.6	759.2	1230.5	766.8	1090.9	176.0
Hydrocarbons, wt % of raw coal	5.9	7.3	9.9	8.7	8.3	7.7	8.1	8.7	7.5	8.0
Yield based on MAF raw coal feed, %	9.1	11.4	15.4	13.5	12.9	12.0	12.5	13.5	11.4	12.4
Yield based on MAF coal feed to MG reactor, %	9.8	12.3	17.0	14.9	14.3	12.8	13.4	14.6	12.2	13.9

The yields of dry liquids based upon the moisture- and ash-free (MAF) coal feed to the mild-gasification reactor range from 9.8 to 17.0% (Table 17). Yields from the 10-lb/hr tests range from 8.3 to 18.1% (Merriam 1989). The maximum yield from the 10-lb/hr tests occurred at about 1100 to 1150°F (593 to 621°C). Data from the 100-lb/hr PRU tests show yields increasing with temperatures to about 1100 to 1150°F (Figure 15). However, we were not able to conduct tests in the PRU above the 1100 to 1150°F range to verify a decrease in yields at higher temperatures determined in the 10-lb/hr tests.

The distribution of products from mild-gasification tests (Figures 15, 16, and 17) is based upon the exclusion of fines from both the dryer and mild-gasification system. The gases produced in the dryer and mild-gasification systems, char, dry coal liquids, and water from pyrolysis (produced in the mild-gasification system) are normalized to make the sum of the products equal to 100%. These adjustments have the effect of removing fines production and losses (or gains) as variations in the data. We then focus on the effect that temperature has on the distribution of the products.

Figure 15 shows that the distribution of char and volatile products from both the 10-lb/hr (bench-scale) and 100-lb/hr (PRU) tests follows the same trends with maximum bed temperatures. Char production is at a minimum at 1050 to 1150°F (566 to 621°C), whereas production of volatiles shows a maximum in that same temperature range.

In Figure 16, we have included the water collected from pyrolysis in the mild-gasification section of the PRU because we think the recycle gas system causes water to form from gaseous products. Gaseous products from the bench-scale reactor had little chance to react in the carbon dioxide flowing once through the reactor. Thus, we think gas produced in the PRU is more directly comparable to gas produced in the bench-scale unit if pyrolysis water is included. The adjusted data show good agreement between the bench-scale and PRU units.

Dry coal liquid production from both the bench-scale and PRU units (Figure 18) increases with bed temperature up to about 1150°F (621°C). The yields of dry coal liquids from the bench-scale and PRU tests show good agreement over the temperature range that we tested. As we expected, there is more scatter in the yield data from the bench-scale unit. Tests using the bench-scale reactor were mostly in the higher end of the temperature range, whereas tests using the PRU were conducted at temperatures below 1150°F (621°C). Dry coal liquid production from the PRU shows a trend of increasing yield from maximum bed temperatures of 950 to 1150°F (510 to 621°C, Figure 19). The yield of coal liquids also increases with higher bed temperatures in zone 1 of the reactor from 650 to about 775°F (343 to about 413°C). Above 775°F in zone 1, the yield either levels off or decreases (Figure 20).

Figure 15. Distribution of Products from Mild Gasification at Various Maximum Bed Temperatures

Figure 16. Distribution of Gas, Water, and Char at Various Bed Temperatures

Figure 17. Distribution of Coal Liquids and Char Produced at Various Bed Temperatures

Carbon balances from selected tests for which the liquids were analyzed show that most of the carbon in the raw coal remains in the char (Table 18). Hydrogen from the MAF feed coal is concentrated in gas, liquid, and water produced by mild gasification, whereas the char has a lower concentration of hydrogen than the feed coal (Table 19). Nitrogen remains mostly in the char (Table 20). Sulfur is distributed in the products from mild gasification about in proportion to the weight of the respective products (Table 21). Over one-half of the oxygen in the MAF feed coal is in the gas and the water formed during pyrolysis (Table 22).

We removed fines from the carbon balances and renormalized the results to bring the balances back to the closures that existed before fines were removed. These adjusted carbon balances are on a comparable basis with carbon balances from the earlier 10-lb/hr tests (Table 23). Comparison of these balances shows that less carbon went to gas and more to liquid in the 100-lb/hr tests than in the 10-lb/hr tests. We think the shift in carbon-containing products reflects better measurement of gas produced and better recovery of liquid products using the recycle gas in the 100-lb/hr system than with the once-through carbon dioxide used with the 10-lb/hr system. Also, the use of recycle gas in the PRU tests reduced the carbon dioxide-char reaction because of the lower carbon dioxide concentration in the fluidizing gas.

Table 18. Carbon Balances from Selected Mild-Gasification (MG) Tests, wt % of C in feed on a MAF basis

Test:	118	119	122
Feed Coal	100.0	100.0	100.0
Dryer: Fines	7.6	8.7	6.3
Dust	1.2	0.5	0.1
Gas	0.4	0.5	1.4
MG: Fines	3.5	3.0	8.9
Gas	7.1	7.8	6.9
Liquids	17.0	14.8	13.9
Pyrolysis Water	0.2	0.2	0.3
Char	64.1	61.7	58.3
Closure	101.2	97.3	96.0

Figure 18. Yield of Dry Coal Liquid Products at Various Bed Temperatures

Figure 19. Yield of Coal Liquids from PRU Tests at Various Temperatures

Figure 20. Yield of Coal Liquids Produced at Various Bed Temperatures in Zone 1 of the Mild Gasification Reactor

Table 19. Hydrogen Balances from Selected Mild-Gasification (MG) Tests, wt % of H in feed on a MAF basis

Test:	118	119	122
Feed Coal	100.0	100.0	100.0
Dryer: Fines	7.6	8.7	6.3
Dust	1.2	0.5	0.1
Gas	0	0	0
MG: Fines	3.5	3.1	8.9
Gas	16.0	16.3	15.0
Liquids	22.6	19.3	18.3
Water	12.2	13.4	16.5
Char	23.9	25.8	37.3
Closure	87.1	86.9	102.4

Table 20. Nitrogen Balances from Selected Mild-Gasification (MG) Tests, wt % of N in feed on a MAF basis

Test:	118	119	122
Feed Coal	100.0	100.0	100.0
Dryer: Fines	7.6	8.7	6.3
Dust	1.2	0.5	0.1
Gas	0	0	0
MG: Fines	3.6	3.0	8.9
Gas	0	0	0
Liquids	14.2	11.1	10.1
Water	5.5	4.8	5.8
Char	68.0	76.5	58.5
Closure	100.1	104.6	89.7

Table 21. Sulfur Balances from Selected Mild-Gasification (MG) Tests, wt % of S in feed on a MAF basis

Test:	118	119	122
Feed Coal	100.0	100.0	100.0
Dryer: Fines	7.6	8.7	6.3
Dust	1.2	0.5	0.1
Gas	0	0	0
MG: Fines	3.5	3.1	8.9
Gas	4.6	4.5	18.9
Liquids	14.3	8.4	12.5
Water	0.7	0.4	0.5
Char	46.0	47.7	52.7
Closure	77.9	73.3	99.9

Table 22. Oxygen Balances from Selected Mild-Gasification (MG) Tests, wt % of O in feed on a MAF basis

Test:	118	119	122
Feed Coal	100.0	100.0	100.0
Dryer: Fines	7.6	8.7	6.3
Dust	1.2	0.5	0.1
Gas	3.7	4.2	12.6
MG: Fines	3.5	3.1	8.9
Gas	25.5	30.4	24.4
Liquids	6.1	5.7	5.0
Water	25.2	23.9	29.5
Char	24.9	43.6	28.3
Closure	97.7	120.1	115.1

Table 23. Comparison of Carbon Balances from 10-lb/hr and 100-lb/hr Tests, wt % of C in feed on a MAF basis

Test:	7	8	9	118	119	122
Feed Rate, lb/hr	10	10	10	100	100	100
Feed	100.0	100.0	100.0	100.0	100.0	100.0
Dryer Gas	0.6	0.6	0.6	0.5	0.5	1.6
MG Gas	11.0	12.3	11.4	8.2	8.9	8.2
MG Liquid	15.2	12.3	8.5	19.5	16.9	16.5
Char	68.5	68.4	70.9	73.3	70.4	69.1
Closure	95.3	93.6	91.4	101.5	96.7	95.4

Compositions of liquids produced during mild gasification tests (Table 24) are very similar. The elemental analyses do not total 100%. This is because the oxygen analyses are difficult, and the results may be low. The boiling range of liquids produced during test 117 shows more low-boiling liquids than liquids from other tests. However, temperatures used for test 119 were very close to those used for 117, and the liquid from test 119 does not exhibit the shift in boiling range.

Ash content of the liquids decreases at successive collection points away from the reactor (Table 25). Significantly, the ash content of the composite samples is well below the 0.35 wt % maximum ash content for electrode-binder pitch. The low ash content of the liquids may make it unnecessary to produce dirty pitch. If the material from air-cooled condensers 1, 2, and 3 can be used in clean pitch, the high quinoline-insolubles content (Table 26) will improve the quality of the binder pitch.

Water collected from the chilled condenser contains organic compounds (Table 27), which are mostly tar acids (phenolics). The analyses also show high concentrations of nitrogen-containing compounds, such as ammonia, amines, nitriles, or cyanide.

Table 24. Properties of Dry-Coal Liquids Produced by Mild Gasification, wt %

Test:	117	118	119	120
Elemental				
Carbon	80.1	80.1	80.1	79.5
Hydrogen	8.4	7.8	7.7	7.7
Nitrogen	0.8	0.7	0.7	1.1
Sulfur	0.4	0.5	0.5	0.4
Oxygen	8.6	8.8	8.8	9.2
H:C (atomic)	1.25	1.16	1.15	1.15
Boiling Range				
IBP-700°F	55.4	38.0	45.0	45.6
701-1000°F	27.8	22.9	24.5	21.8
Residue	16.8	39.1	30.5	32.6
Ash	0.20	0.16	0.13	0.04
Specific Gravity, 60°F		1.064	1.064	

Table 25. Ash Content of Liquids from Successive Collection Points, wt %

Test:	117	118	119
ACC 1-3	1.2	0.98	2.57
ACC 6, WCC 1	0.2	0.10	0.19
WCC 2, WCC 3	0.0	0.03	0.03
ESP	0.0	0.12	0.11
Composite	0.20	0.16	0.13

Table 26. Toluene Insolubles and Quinoline Insolubles from Successive Collection Points, wt %

Test:	118	119
Toluene Insolubles		
ACC 1-3	30.3	66.1
ACC 6, WCC 1	4.4	5.5
WCC 2, WCC 3	4.6	3.9
ESP	3.7	1.9
Composite	6.6	4.3
Quinoline Insolubles		
ACC 1-3	5.1	16.8
ACC 6, WCC 1	-	-
WCC 2, WCC 3	-	-
ESP	-	-
Composite	1.8	0.9

Table 27. Composition of Water from the Chilled Condenser, mg/L

Test:	118	119	122
Nitrite as N	42	46	7.5
Nitrate as N	5.4	23	4.4
Oil and Grease	350	320	280
Total Kjeldahl Nitrogen	8,650	7,630	7,920
Total Organic Carbon	26,000	27,000	20,000
Trace Sulfur	720	480	140

The liquid recovery train used in the PRU has a very low separation efficiency resulting in no sharp separation between low- and high-boiling materials in the series of condensers. However, a slight trend toward early condensation of high-boilers and later condensation of low-boilers is discernible (Tables 28 and 29). The presence of a mist that passes through some condensers to be separated by the ESP also complicates the recovery requirements.

Liquids from test 122, which were separated into fractions by distillation, show trends to high carbon and nitrogen contents and lower sulfur content (Table 30) in the high-boiling fraction. In the mid-range boiling fraction, hydrogen concentration is the highest, whereas oxygen concentration is lowest. This is equivalent to the boiling range for diesel fuel.

Distillate from liquid produced during shakedown test 112 was washed by thoroughly mixing the distillate with a 30 wt % solution of sodium hydroxide. The caustic wash removed much of the oxygen-containing and asphaltene compounds (pentane insolubles) from the distillate (Table 31).

Table 28. Boiling Range of Dry-Coal Liquid from Test 118, ASTM D 2887, wt %

Source, °F	ACC 1-3	ACC 6, WCC 1	WCC 2, WCC 3	ESP	Composite
101-200	-	-	-	-	-
201-300	-	-	-	-	0.8
301-400	-	3.9	9.0	4.4	4.4
401-500	-	13.3	13.7	12.2	10.2
501-600	-	12.2	15.1	14.0	12.3
601-700	-	0.4	12.6	14.4	10.0
701-800	0.4	10.1	11.8	14.2	10.5
801-900	0.6	7.8	8.7	10.9	8.3
901-1000	0.6	3.9	3.8	4.9	3.5
Residue	98.5	42.4	25.2	25.0	39.8
Condensation Conditions					
Temperature, °F					
In	850	334		79	850
Out	350		79	79	76
Pressure, psia					
In	15.7				15.7
Out		13.3	12.3	12.2	12.0

Table 29. Boiling Range of Dry-Coal Liquid from Test 119, ASTM D 2887, wt %

Source, °F	ACC 1-3	ACC 6, WCC 1	WCC 2, WCC 3	ESP	Composite
101-200	-	-	-	-	-
201-300	-	-	-	1.3	0.3
301-400	-	6.0	9.0	3.7	8.3
401-500	-	13.4	16.0	10.2	13.2
501-600	-	12.9	13.8	13.6	12.4
601-700	-	10.8	12.7	14.2	11.4
701-800	0.1	10.7	11.9	13.6	11.2
801-900	0.2	8.6	8.6	10.1	9.1
901-1000	0.4	3.9	4.0	4.3	4.4
Residue	99.3	33.7	24.0	30.4	29.8
Condensation Conditions					
Temperature, °F					
In	820	348		79	820
Out	363		79.	79	77
Pressure, psia					
In	16.1				
Out		13.4	12.3	12.0	11.7

Table 30. Composition of Distilled Liquids from Test 122, wt %

Boiling Range	IBP-419°F	420-720°F	720+°F
Portion of Liquid	15.76	20.87	63.37
Carbon	78.1	81.1	82.2
Hydrogen	8.5	9.2	7.6
Nitrogen	0.3	0.9	0.9
Sulfur	0.9	0.7	0.6
Oxygen	9.4	7.9	8.2
Specific Gravity, 60°F	0.985	1.017	1.160

Table 31. Effect of Caustic Wash Upon IBP-700°F Distillate from Test 112, wt %

	Distillate	Washed Distillate
Carbon	78.1	85.8
Hydrogen	8.4	10.1
Nitrogen	0.6	0.5
Sulfur	0.3	0.6
Oxygen	10.0	2.0
H:C (atomic)	1.28	1.40
Specific Gravity, 60°F	1.015	0.930
Pentane Insolubles	10.2	0.4
Amount, g	100	38.3

Hydrocarbon-group-type analysis of distillate from coal liquids produced during shakedown test 112 (Table 32) shows the IBP-350°F (177°C) fraction is almost 90 wt % aromatic hydrocarbons. The gas chromatographic/mass spectrometric analysis shows the 350 to 700°F (177 to 371°C) fraction is 76.7 wt % saturated hydrocarbons, whereas the 700+°F (371+°C) fraction is 97.9 wt % saturated hydrocarbons.

The composition of the gas produced by mild gasification (Table 33) using different test conditions (Table 14) shows that the concentrations of hydrogen, carbon monoxide, methane, and ethylene increase with increasing temperature (Figure 21). Concentrations of carbon dioxide, ethane and propane decrease with increasing temperature. The gross heating value of the gas ranges from 547 to 604 Btu/scf, and the gas burns readily with a clean blue flame.

The gas composition is the product of several simultaneous reactions: gas formed during pyrolysis, reaction of carbon dioxide with char, reaction of hydrogen with carbon dioxide (reverse water-gas shift), and cracking or coking of products formed during mild gasification.

Table 32. Hydrocarbon-Group-Type Analysis of Distillate from Test 112, wt %

Z Series	Compound	IBP-350°F	350-700°F	700+°F
+2	Alkanes	2.2	32.4	65.3
0	Monocyclic	6.8	0.1	0.0
0	Alkenes	1.9	33.7	32.6
-2	Dicyclic	0.0	0.8	0.0
-4	Tricyclic	0.0	9.7	0.0
Total Saturated Hydrocarbons		10.9	76.7	97.9
-6	Alkylbenzenes	66.1	3.5	0.0
-8	Indanes/Tetralins	23.0	13.8	0.0
-12	Naphthalenes	0.0	2.1	0.0
-16	Fluorenes	0.0	2.6	0.0
-18	Anthracenes/Phenanthrenes	0.0	1.4	1.8
-22	Pyrenes/Flouranthenes	0.0	0.0	0.2
Total Aromatic Hydrocarbons		89.1	23.3	2.1
Weight Percentage in Sample		2.1	73.7	24.2

The ratio of hydrogen to C₆ (benzene) (Table 34) does not suggest a strong trend with temperature. The production of hydrogen shows a definite increase with increasing temperatures (Figure 21). The benzene concentration shows a possible trend of increasing with temperature. We think that hydrogen production occurs mostly in the hottest part of the bed, zones 3 and 4, whereas benzene is produced in zones 1 and 2 where essentially all of the devolatilization occurs.

The ethane-to-ethylene ratio shows a definite decrease with increasing bed temperature. We attribute this lower ratio to increased thermal cracking caused by beta scission of long-chain alkanes. Thus, there is strong evidence of cracking, but we are not able to attribute production of hydrogen to cracking of coal liquids. It seems most likely that hydrogen production results from high-temperature pyrolysis, mostly in zones 3 and 4 of the reactor. Some hydrogen is also produced by reaction of water vapor with carbon monoxide in the recycle gas.

Char produced during tests in the PRU typically contains 16 to 21 wt % volatiles (Table 35). All of the chars produced exceed the minimum requirement of 0.125 lb of hydrogen per lb of oxygen so that no makeup hydrogen is needed for the char upgrading system.

Table 33. Composition of Gas Production by Mild Gasification, vol %

Test:	115	117	118	119	120	122	123	124	125	126
H ₂	4.41	10.12	14.19	10.93	12.76	13.65	11.56	11.29	7.26	13.40
N ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
O ₂	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Ar	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
CO	18.14	19.13	22.41	21.24	23.15	19.09	17.83	19.35	16.77	20.93
CO ₂	42.30	33.93	25.11	30.44	24.48	26.80	30.44	31.36	40.17	28.03
CH ₄	22.61	28.19	33.58	31.68	34.46	32.55	29.69	28.98	23.64	31.90
C ₂ H ₆	5.03	2.81	0.68	2.24	1.14	1.10	3.18	1.43	4.06	1.05
C ₂ H ₄	1.58	2.81	2.79	1.91	2.63	4.51	3.83	4.96	3.28	2.90
C ₃ H ₈	1.28	0.17	0.03	0.16	0.16	0.38	1.37	0.54	1.84	0.08
C ₃ H ₆	1.74	0.79	0.14	0.45	0.20	0.09	0.12	0.28	0.31	0.16
C ₄	1.03	1.18	0.05	0.15	0.09	0.13	0.30	0.13	0.54	0.14
C ₅	0.29	0.00	0.00	0.03	0.02	0.01	0.03	0.00	0.11	0.01
C ₆	0.23	0.24	0.72	0.46	0.59	0.71	0.48	0.59	0.39	0.80
C ₇	0.02	0.00	0.00	0.00	0.01	0.00	0.00	0.00	0.00	0.00
C ₈	0.17	0.02	0.08	0.13	0.09	0.12	0.18	0.13	0.19	0.13
C ₉	0.03	0.00	0.01	0.01	0.01	0.04	0.03	0.02	0.04	0.03
C ₁₀	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
H ₂ S	0.00	0.52	0.14	0.17	0.18	0.66	0.86	0.82	1.28	0.37
COS	(682)	(492)	(198)	(119)	(134)	(473)	(570)	(618)	(606)	(328)
CH ₃ SH	(592)	(113)	(65)	(13)	(39)	(107)	(218)	(160)	(341)	(41)
C ₂ H ₅ SH	(46)	(10)	(59)	(0)	(0)	(21)	(0)	(0)	(0)	(0)
CS ₂	(0)	(0)	(10)	(0)	(7)	(302)	(30)	(46)	(16)	(48)
Thiophene	(220)	(170)	(299)	(80)	(191)	(613)	(241)	(350)	(212)	(255)
Gross Heating Value, Btu/scf	567	553	561	547	576	592	604	565	560	560
Molecular Weight	32.33	28.18	24.89	26.83	25.05	25.65	27.27	27.38	30.89	25.94
Specific Gravity	1.12	0.97	0.86	0.93	0.86	0.89	0.94	0.95	1.07	0.90

Numbers in parentheses are in parts per million

Figure 21. Major Components of the Gas Produced at Various Temperatures

Table 34. Ratios of Components in Gas from Mild Gasification

Test	Maximum Bed Temperature, °F	Hydrogen to C ₆	Ethane to Ethylene
115	950	19.2	3.2
125	993	18.7	1.2
117	1043	42.2	1.0
119	1050	23.8	1.2
123	1051	24.1	0.83
124	1080	19.1	0.29
122	1124	19.2	0.24
118	1129	19.7	0.24
120	1131	21.6	0.43
126	1146	16.8	0.36

The fixed-carbon content of the coal increases rapidly as water is removed (Figure 22) in the first part of the dryer. The fixed-carbon content then changes very little in the remainder of the dryer as small amounts of gaseous volatiles are removed. The fixed-carbon content of the char increases as devolatilization takes place, mostly in the first part of the mild-gasification reactor.

The volatiles content of the char is strongly influenced by the temperature in zone 1 of the mild-gasification reactor (Figure 23). The temperature in zone 1 is an important determinant of devolatilization because most of the volatiles are removed from the char in zone 1 (Figure 8). Also, the slope of the reactor is the primary control of the residence time of char in the reactor. The slope of the mild-gasification reactor and the temperature in zone 1 of the reactor control the volatiles content of the char regardless of large variations in temperature of coal from the dryer and dried-coal feed rate.

Figure 24 shows that oxygen is removed from the char by further devolatilization in the range of 950 to 1150°F (510 to 621°C). Hydrogen content of the char changes little with removal of volatiles in that temperature range. However, Merriam and Cha (1989) show in the bench-scale work that at temperatures above about 1125 (607°C) the rate of hydrogen loss from the char greatly exceeds the rate of loss of oxygen. The oxygen content of the char affects the economics of the char-to-carbon system because formation of carbon monoxide reduces the capacity of the system.

The sulfur-to-ash ratio of the char (Figure 25) is essentially constant for chars with different volatiles content produced using both the 10-lb/hr bench-scale reactor and the 100-lb/hr PRU. The constant sulfur-to-ash ratios suggest that the sulfur in the char is a refractory-like component in the ash and is not part of the volatiles (such as organic sulfur in heteroatoms).

Table 35. Composition of Char Produced by Mild Gasification, wt %

Test:	115	117	118	119	120	122	123	124	125	126
<u>Proximate</u>										
Volatiles	20.5	17.4	15.9	17.6	16.1	18.6	20.2	19.5	26.3	20.9
Fixed Carbon	71.9	74.0	74.9	74.0	74.8	72.2	70.0	70.7	65.9	70.2
Ash	7.5	8.7	9.2	8.8	8.9	8.7	9.5	9.8	7.8	8.8
<u>Ultimate</u>										
Carbon	76.7	78.7	78.3	76.2	78.5	70.8	73.1	77.5	72.8	74.6
Hydrogen	2.5	2.6	2.2	2.4	2.2	3.4	2.8	2.7	2.9	3.3
Nitrogen	1.2	1.1	1.1	1.3	1.3	0.9	1.1	1.1	1.2	1.3
Sulfur	0.4	0.6	0.5	0.5	0.6	0.6	0.7	0.7	0.5	0.5
Oxygen (direct)	11.7	8.3	8.7	10.8	8.5	15.6	12.8	8.2	14.8	11.5
H:O (direct)	0.21	0.31	0.25	0.22	0.26	0.22	0.22	0.33	0.20	0.29
<u>Gross Heating Value, Btu/lb</u>										
Measured		13,230	13,332	13,315						
Calculated (Bole Eq.)	12,320	12,881	12,579	12,273	12,599	11,711	11,903	12,737	11,796	12,424

Figure 22. Fixed Carbon Content of Dried Coal and Char at Increasing Temperatures

Figure 23. The Effect of Changing Reactor Slope Upon the Volatiles Content of the Chars Produced

Figure 24. Oxygen and Hydrogen Content of Chars Having Different Volatiles Contents

Figure 25. Ratios of Nitrogen- and Sulfur-to Ash in Chars Having Different Volatiles Contents

However, there is a step-like increase in the sulfur-to-ash ratio between the 10-lb/hr and the 100-lb/hr chars. The increased ratio in the char from the PRU may be caused by use of coal from a different part of the mine or it may be caused by the use of larger particle-size coal feed.

The nitrogen-to-ash ratio of the char from the bench-scale tests decreases as the volatiles content of the char decreases. This suggests that the nitrogen compounds are organic heteroatoms in the volatiles. Seven of the chars from the PRU follow the trend of chars from the bench-scale unit, whereas three of the PRU chars only increase the scatter in the nitrogen-to-ash ratio data.

Screen analyses of char (by AMAX) produced during tests 117, 118, and 119 (Table 36) show that the char from test 117 has approximately the same size distribution as the feed coal (Table 5), except the char contains less fines. Char from tests 118 and 119 is smaller than the average distribution of the four samples of feed coal listed in Table 5.

Proximate analyses of fines from the mild-gasification reactor (Table 37) show that the fines have lost almost none of the volatiles content. (The dried coal typically contains about 41 wt % volatiles.) The failure of fines to be devolatilized suggests that the fines are elutriated from the fluidized bed near the inlet of the mild-gasification reactor. Thus, fines from the mild-gasification reactor are most likely the result of fines in the dried coal being removed by slightly different fluidization in the mild-gasification reactor or from formation of fines in the lockhopper between the dryer and mild-gasification reactors. We can conclude that fines are not formed in the mild-gasification reactor.

Table 36. Size Distribution of Char Produced, wt % retained

Test:	117	118	119
Screen, mesh ^a			
8	0	0	0
14	2.9	1.4	1.4
16	18.7	11.2	8.5
20	24.6	20.3	13.7
30	18.3	17.5	14.8
40	14.1	15.4	15.6
50	9.7	12.9	15.6
70	6.0	9.6	13.0
100	3.6	7.8	10.9
140	1.6	3.3	5.8
200	0.4	0.5	0.9
Pan	0.1	0.1	0.1

^a U.S. Standard Testing Sieves

Table 37. Proximate Analyses of Fines from the Mild-Gasification Reactor, wt %

Test:	117	120
Volatiles	41.4	39.1
Ash	6.8	6.8
Fixed Carbon	51.9	54.1

We measure the residence time of dried coal and char by collecting material from the bed and dividing the weight of the dried coal (char) bed by the dried coal (char) production rate. This technique requires that the flow of solids into the bed be stopped and the flow of solids from the bed be simultaneously diverted to a separate receiver. Thus, the technique causes upsets in bed temperatures because the feed to the reactor is suddenly stopped. Consequently, measurements of bed weights near the ends of the tests minimizes the disruption during tests. Also, accurate measurements of bed weights and dried coal (char) production rates are needed for accurate measurements of residence time.

Results of the residence time determinations (Table 38) are generally in the range we expected, but there are inconsistencies in the results. The drying reactor is designed to achieve a dried coal residence time of 5 minutes, and it does. This implies that test 123 should have the lowest dried coal residence time; however, it does not. The mild-gasification reactor is designed to provide a 10-minute residence time for char, which is possible using a slope of 0 degrees. We expected about 40% reduction in char residence time from test 111 to test 123, but our measurements do not show this reduction.

The inconsistencies in the residence time determinations are probably caused by our inability to accurately measure the bed weight. Clearly, there is a significant difference between the reaction conditions used for tests 115 through 120 and those used for 122 through 126 (Figure 23). The shorter residence times that we expected using the 5-degree slope (about 5 minutes) should produce chars that contain more volatiles than chars produced at longer residence times. The estimates of residence times used to support Tables 8 and 14 are consistent with the overall range of results listed in Table 38. All of the test results are not used because some are of doubtful accuracy. Test 107 is our best estimate of residence time in the dryer.

Table 38. Dried Coal and Char Residence Times

Test	Slope, degrees	Raw Coal Feed Rate, lb/hr	Fluidizing Gas		Residence Time, min
			Flow, scfm	Temp., °F	
<u>Dryer: Based on Dried Coal Out</u>					
105	0	100	83	639	7.8
107	3.3	100	79	804	3.2
123	3.3	149	82	817	5.4
<u>Mild Gasification: Based on Char Out</u>					
111	3	100	75		9.0
123	5	149	79		8.8

We think that the 9-minute residence time for the mild-gasification reactor in test 111 is likely. We expect a 20% reduction in residence time by increasing the slope of the reactor from 3 to 5 degrees and an additional 20% reduction by increasing the feed rate from 100 to 150 lb/hr. Thus, the use of 9.0, 7.0, and 5.5 minutes are our best estimates of residence time for char in the mild-gasification reactor.

4.4 Discussion of Test Results

The PRU proved to be an effective system for collection of data using tests lasting from 1 to 5 days. However, improvements are needed for the system to become the basis for a reliable commercial process.

The coal-drying portion of the PRU worked very well with the exception of numerous instances of plugging in the coal-feed pipe between the outlet of the 3-inch-diameter feed screw and the top of the upper 3-inch ball valve used as part of the feed lockhopper. We installed a vibrator on the feed lockhopper that is activated when the lower valve is open. This seemed to reduce the frequency of plugging. We also injected a flow of about 0.25 scfm of CO₂ into the feed lockhopper, which definitely reduced the frequency of plugging. The plugging of the coal-feed line commonly occurred at night, when the air around the feed screw was cool, and near the end of tests, when we were emptying the feed hopper. Apparently, collection of moisture along the walls of the feed hopper and screw was the cause of a large portion of the plugging. Use of heated outer surfaces in the coal feed system should eliminate condensation of water vapor at the surfaces.

Loss of coal feed to the dryer causes much larger variations in temperature when operating with a coal feed rate of 150 lb/hr than with 100 lb/hr. The higher feed rate requires that the gas flow into the dryer be at a higher temperature to dry the coal. We found numerous instances of dryer bed temperatures reaching 580°F (304°C) during upsets, and no apparent problems resulted. When bed temperatures got above 600°F (316°C), the pressure drop across the bag filter increased, sometimes rapidly. After the test, we found that the filter bags were coated with tar. During test 125, we operated with the temperature of the gas to the dryer at 600°F (316°C) to avoid release of tar during upsets. In spite of the flow of feed coal stopping numerous times, the pressure drop across the bag filter did not increase during test 125.

Drying and devolatilization curves (Figures 5 and 8) show that both the drying and mild-gasification reactors in the PRU are greatly oversized for use at raw-coal feed rates of 100 lb/hr. Results of tests using a cold-flow model of the reactors show that both reactors have capacities of about 300 lb/hr. However, the capacity to carry heat into the reactors limited our testing to feed rates of 150 lb/hr.

The mild-gasification loop has limitations that affected our tests and that will have negative impact upon a long-term operation. We were not able to conduct tests using bed temperatures in the mild-gasification reactor over 1150°F (621°C) because of limited capacity to carry heat into the reactor. We often experienced unacceptably high pressure drops across the air-cooled condensers and sometimes had high pressure drops across the water-cooled condensers. We were not able to cool the gas flowing from the chilled condenser below 70°F (21°C) because the formation of hydrates caused excessive pressure drops at lower temperatures. Carry-over of condensable liquids from the chilled condenser caused build-up of tars in the recycle gas blower. Also, carbon that formed in the recycle gas heaters reduced the output from the heaters.

We wanted to conduct at least one mild-gasification test at 1200°F (649°C) or higher to confirm bench-scale results that show the maximum yield of liquid products occurs at about 1150°F (621°C). A test at a temperature well above 1150°F is needed to verify a liquid yield below the maximum. In spite of burning some of the carbon out of the recycle gas heaters for 48 hours before test 126, we were not able to achieve a bed temperature of 1200°F (649°C).

High pressure drops across the 3-inch-i.d., air-cooled condensers was the cause of shutting down at least two of the tests. Before test 115, we removed two of the six sections of condensers to reduce the pressure drop. We later cut out the impact separators from the two down-flow condensers to eliminate the small openings that sometimes plugged. The increased pressure drop across the modified system during tests was caused by formation of a thick, carbonaceous, dust-bearing scale that formed on the walls of the tubes. Increasing the temperature at the outlet of the air-cooled condensers from the

typical 350°F (177°C) to over 500°F (260°C) reduced the pressure drop early in the tests, but had no effect after several days of operation. It was difficult to keep the pressure drop from reaching 70 to 80 inches of water after 4 or 5 days of operation.

The air-cooled condensers were readily cleaned, when cooled to ambient temperature, because the deposits were so brittle that the hard, black, shiny substance fell off when a tube was struck with a hammer. The material, which contained 0.7 to 2.5 wt % ash, had a high quinoline-insolubles content, making it a desirable component for binder pitch.

The water-cooled condensers were operated for about 470 hours (over numerous tests) before the pressure drop made it necessary to clean them. The tar in the tubes would not flow out when the tubes were heated with 250°F (121°C) steam from the shell side. The material in the first condenser in the process stream (highest temperature) was drilled out, whereas the tubes in the other condensers could be cleaned by pushing a rod through the tubes.

Clearly a new design is needed to replace the design of air- and water-cooled condensers used in the PRU. We have proposed a hot, wet scrubber followed by a cold, wet scrubber for this service (Cha et al. 1988), but we chose not to use it in the PRU to reduce costs.

The chilled condenser, cooled by boiling carbon dioxide liquid in the shell, is designed to cool the outlet gas to 40°F (4°C) to condense high vapor-pressure liquids from the recycle gas stream. We determined that when the temperature of the gas flowing from the condenser falls below 70°F (21°C), the amount of the pressure drop across the condenser increases rapidly. Conditions at the condenser outlet are suitable for formation of hydrates from methane and water in the recycle gas.

We determined that the recycle gas blower in the mild-gasification loop would freeze up after being shut down following each test. It became our standard procedure to wash out the blower using a solvent after each test. During the 5-day tests, the blower would sometimes shut down because of electrical overload late in the tests. A deposition of tar (or heavy oil) caused friction in the close clearances of the positive displacement blower.

After test 122, we removed the recycle gas heaters from the mild-gasification loop and inspected them. The heaters were full of carbonaceous material. The deposits in the heaters probably originated from carryover of liquids that coked or from reactions of gases at 1400 to 1500°F (760 to 816°C) in the heaters.

The design of the next system will need to deal with the problem of liquids passing through the chilled condenser into the blower and the recycle gas heaters. Also, some of the carbon deposits in the recycle gas heaters may be formed by the reaction of gases.

We experienced several small fires from combustion of gas leaking from equipment between the recycle gas heaters and the mild-gasification reactor. The problem was solved by welding all joints in the areas where the gas is hotter than 900°F (482°C).

High thermal efficiency of IFB reactors, indicated by the temperature of the solids from the bed being well above the temperature of the effluent gas, is an important benefit of using the plug-flow design. We have seen evidence that the thermal efficiency of an IFB reactor, used to dry coal, started to decline at coal residence times of 1.5 minutes and lower (Merriam 1990).

We were able to dry coal to zero moisture content using fluidizing gas temperatures of 540 to 817°F (282 to 436°C) with gas-to-raw coal flow ratios of 33 to 55 scf of recycle gas per lb of raw coal feed. Our objective in the drying process is to remove all of the moisture from the coal and as much of the oxygen-containing gas as we can without releasing any of the oil or tars in the drying system. This is because the presence of oxygen in the coal reduces the yield of coal liquids from the mild-gasification step. The results of the water analyses from drying tests 113, 114, and 115 (Table 13) show that the water produced from the dryer, when using fluidizing-gas temperatures of 540 to 640°F (282 to 338°C), is relatively clean water.

Our data do not suggest that severe drying conditions are needed to produce high yield of coal liquids. Some of the highest liquid yields are from tests in which moderate drying temperatures are used (tests 118, 119, and 124). Also, the tests where we used the highest dryer-bed temperatures (120, 122, and 126) resulted in near-average liquid yields. Drying conditions may have a relatively small effect upon liquid yields compared with the effects of temperature and heating rate in the mild-gasification reactor.

While we were not able to accurately determine the composition of gas produced in the dryer, for the reasons discussed earlier, we did get an approximate composition. During test 122, after about 40 hours of operation, we measured the composition of recycle gas in the dryer loop. After subtracting the gases that were obviously leaking into the dryer from the mild-gasification system, we determined that the gas produced in the dryer is essentially carbon dioxide with several percent methane and carbon monoxide. We detected no oxygen and several percent nitrogen.

The higher coal feed rates (tests 123, 124, and 125) alter the characteristic temperature profiles of both the dryer (Table 8) and mild-gasification (Table 14) reactors. The high feed rates cause the temperature profiles to increase more rapidly near the inlet and to flatten out near the reactor outlet. The high feed rates also cause the apparent heating rates in zone 1 to increase, but the yield of liquid products from tests using high feed rates are near the average.

Increased fines production from the mild-gasification reactor (Table 16) should have been noticed starting with test 119. Before test 119, we increased the flow of gas in the first part of the reactor. Volatiles content of fines from both the dryer and the mild-gasification reactor suggests that fines are quickly elutriated from the beds near the inlet of the reactors. We modified the lockhopper that feeds the mild-gasification reactor and increased the slope of the reactor from 3 to 5 degrees after test 120.

The agreement in product distribution of PRU results and the 10-lb/hr tests (Figures 16 and 17) suggests that the effect of particle size upon product distribution is negligible over the size range of particles that we tested.

The hydrogen in the raw coal is concentrated in the gas, coal liquids, and pyrolysis water produced by mild gasification (Table 19). Oxygen from the raw coal is concentrated in the gas and water (Table 22), as indicated by those components comprising larger shares of the oxygen balances than of the coal balances.

The coal liquids from the PRU tests are very similar to the liquids produced during the 10-lb/hr tests (Merriam and Cha 1989). Liquids from both series of tests have about 60 wt % of the dry liquid boiling above 700°F (371°C), and both have H:C ratios of 1.15 to 1.20. The liquids from the PRU contain more light ends because we were not able to collect low-boiling liquids with the once-through gas flow used for the 10-lb/hr tests. The heavy liquid and high hydrogen content are caused by the shallow bed in the IFB mild-gasification reactor, which is designed to minimize cracking, coking, and polymerization of liquid products.

The ash contents of composite samples of liquids (Table 25) are all well below the 0.35 wt % maximum ash content specified for electrode-binder pitch. The low ash content of the liquids shows that it may be possible to put all of the 700+°F (371°C) boiling point liquids into feedstock for binder pitch and not produce any dirty pitch. (Oil used to spray dried coal has less value than binder pitch.) Also, the material from ACC 1-3, has a significant quinoline-insolubles content, which is needed in electrode-binder pitch.

All of the crude liquids recovered from test 122, except material from ACC 1, 2, 3 and the chilled condenser, were composited and distilled. The water was first removed by batch distillation, and the dry liquid was distilled into three cuts using continuous vacuum distillation (Table 30). Samples of the IBP-419°F (IBP-215°C) and 420-720°F (216-382°C) distillates were tested as blends with diesel fuel and cosolvents using ignition delay to determine cetane ratings (Daw et al. 1990). The blends tested were 40% coal distillate with 40% diesel fuel and 20% cosolvent and 40% distillate with 60% diesel fuel. The cosolvent improved the storage stability of the blends but did not improve the cetane ratings. Daw et al. (1990) conclude that the blends are, at best, marginally suited for heavy power generation diesels but probably inadequate for use in transport or passenger diesels without cetane enhancement. We

have, however, shown that even a simple alkaline wash dramatically lowers the oxygen and asphaltene content of the distillates (Table 31). More work needs to be done to evaluate low-cost methods of cetane enhancement and sulfur removal.

Work is underway to evaluate methods for converting crude pitch into electrode-binder pitch. The crude pitch has too high oxygen and hydrogen content and too low carbon, quinoline insolubles, and specific gravity. Traditionally heat treating and air-blowing have been used to improve the properties mentioned above. A test using heat treating (Jha et al. 1990a) did reduce the oxygen and hydrogen contents and increase the carbon and toluene insolubles of the 700+°F (371°C) residue from test 122 liquids. However, their tests were limited by use of an open reactor that prevented them from using temperatures above the atmospheric boiling point of the liquid. More work is needed to find low-cost methods to convert the 700°F (371°C) boiling residue to material which meets specifications for electrode-binder pitch.

The major control over the composition of the char is the degree of devolatilization. The oxygen and the hydrogen content of the char can be reduced significantly by reducing the volatiles content from 20 to about 15 wt %. Also, the rate of oxygen loss exceeds the rate of hydrogen loss from the char at temperatures up to about 1100°F (593°C, Figure 24). Above 1100°F, the rate of loss of hydrogen accelerates (Merriam and Cha 1989).

The char is highly reactive in both hydrogen (Jha and McCormick 1989) and air (Daw et al. 1990). Daw et al. (1990) concluded that the char evaluated at Oak Ridge National Laboratory appears to be sufficiently reactive for firing in a wide variety of combustors, possibly including those burning pulverized fuel.

5.0 CONCLUSIONS AND RECOMMENDATIONS

The conclusions drawn from the results of PRU tests and recommendations for future work are presented in this section.

We were able to conduct successful 24-hour and 5-day tests using the PRU at raw coal feed rates of 100 to 150 lb/hr using mild-gasification temperatures of 950 to 1150°F (510 to 621°C).

Results of tests using the PRU agree well with test results from the 10-lb/hr unit. One slight difference is that carbon balances show slightly more liquid and less gas is produced by the PRU than by the 10-lb/hr system.

We are not able to detect any effects of particle size upon product distribution when comparing results of tests using minus 8-mesh Wyodak coal in the PRU with the smaller sizes tested using the 10-lb/hr system.

We are able to dry minus-8-mesh Wyodak coal to zero moisture content and remove about 1 to 2 wt % of the volatiles as gas using conditions shown in Tables 7 and 8.

The drying system is much more susceptible to temperature excursions in the bed when operated at feed rates of 150 lb/hr than when using 100 lb/hr because of the higher fluidizing gas temperature used at the higher feed rates. We have not observed release of tars from the coal at bed temperatures up to 580°F (304°C) but observed an accumulation of tar on the bag filters when bed temperatures were greater than 600°F (316°C).

The distribution of products as wt % of the raw coal varies from 950 to 1150°F (510 to 621°C) as char, 43 to 40; gas, 4 to 9; and liquids, 10 to 13.

The yield of coal liquids is typically 12 to 15 wt % of the MAF feed to the mild-gasification reactor. Our data show that the yield increases with increasing maximum bed temperature from 950 to 1100°F (510 to 621°C). The liquid produced is heavy (about 60 wt % boiling above 700°F/371°C) and has H:C ratios of about 1.15.

The char contains 16 to 21 wt % volatiles and is highly reactive. The oxygen content of the char varies proportionately with the volatiles content. Thus, the oxygen content of the char can be reduced to less than 8 wt % by devolatilizing the char to about 15 wt % volatiles content.

The quantity of gas produced increases with temperature over the range of temperatures tested, and the hydrogen, carbon monoxide, methane, and ethylene contents of the gas increase at higher temperatures. The gross heating value of the gas varies from 550 to 600 Btu/scf.

We recommend the following:

- Revise the design of the coal feed system from the outlet of the feed screw to the top lockhopper valve to eliminate plugging. Also, consider heating the outer surfaces of the coal feed hopper, feed screw, and lockhopper.
- Study the possibility of limiting the temperature of the fluidizing gas flow to the dryer to 600°F (316°C) to avoid release of coal tar during upsets. This condition is not needed if plugging in the coal feed system can be avoided.
- Revise the design of the liquid recovery system in the mild- gasification loop to avoid plugging and to separate liquid products having different boiling ranges. We recommend a hot, wet scrubber, followed by a cold, wet scrubber be used to replace the condensers and electrostatic precipitator that were used in the PRU.
- We may need to conduct some tests specifically designed to get better measurement of bed weights to determine residence times of dried coal and char more precisely.

6.0 REFERENCES

- Cha, C.Y., N.W. Merriam, M.C. Jha, and R.W. Breault, 1988, Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products, Topical Report for Task 1, Literature Survey and Market Assessment. Western Research Institute, Laramie, WY, WRI-91-R017.
- Daw, C.S., R.L. Graves, R.P. Krishnan, B.H. West, A.L. Compere, and W.L. Griffith, 1990, Mild-Gasification Product Characterization--1990 Results, Proceedings of Tenth Annual Gasification and Gas Stream Cleanup Systems Contractor Review Meeting, METC, Morgantown, WV, in press.
- HYSIM Process Simulator, 1990, version C1.0, Hyprotech, Calgary, Alberta, Canada.
- Jha, M.C., and R.L. McCormick, 1989, Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, Topical Report for Task 3, Bench-Scale Char Upgrading and Utilization Study, Western Research Institute, Laramie, WY, WRI-89-R048.
- Jha, M.C., R.L. McCormick, R.F. Hogsett, and R.M. Rowe, 1990, Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, July-September 1990 Technical Progress Report, Western Research Institute, Laramie, WY, WRI-90-R058.
- Merriam, N.W., 1990, Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, January-March 1990 Technical Progress Report, Mild-Gasification Tests, Western Research Institute, Laramie, WY, WRI-91-R020.
- Merriam, N.W., 1989, Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, October-December 1989 Technical Progress Report, Mild Gasification Tests, Western Research Institute, Laramie, WY, WRI-91-R019.
- Merriam, N.W., and C.Y. Cha, 1989, Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, Task 2 Topical Report, Mild Gasification Tests, Western Research Institute, Laramie, WY, WRI-91-R018.

END

DATE
FILMED
6/16/92