DOE/PC/91288--T1

DE92 012505

DOE/PC/91288--T1

Quarterly Progress Report:
High Temperature Electrochemical Separation
Of H₂S from Coal Gasification
Process Streams

Grant DE-^{FG}~~PS~~22-91PC91282⁸

October 1, 1991 - December 31, 1991

by

Received OSTI
APR 20 1992

Professor Jack Winnick
Georgia Institute of Technology
School of Chemical Engineering
Atlanta, Georgia 30332-0100

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED.

Purpose and Goals of Research

An advanced process for the separation of hydrogen sulfide from coal gasification product streams through an electrochemical membrane is being developed using the funds from this grant. H_2S is removed from the syn-gas stream, split into hydrogen, which enriches the syn-gas, and sulfur, which can be condensed from an inert gas sweep stream. The process allows removal of H_2S without cooling the gas stream and with negligible pressure loss through the separator. The process is economically attractive by the lack of adsorbents and the lack of a Claus process for sulfur recovery.

Research conducted during the present quarter is here highlighted, with an emphasis on progress towards the goal of an economically viable H_2S removal technology for use in coal gasification facilities providing polished fuel for co-generation coal fired electrical power facilities and Molten Carbonate Fuel Cell electrical power facilities.

Introduction

The process under development is presented schematically in Figure 1. The process gas, cleaned of particulates, is passed by the cathode. Here, the most easily reduced species will be electronated; under these conditions, it is H_2S :

The sulfide ions are maintained, with alkali-metal cations, as a fused electrolyte in a ceramic membrane. The sulfide is transported across to the anode, where it is oxidized to elemental sulfur. An inert gas such as N_2 is used at the anode to carry away the vaporous sulfur, S_2 , to be condensed for recovery downstream.

Figure 1.
Schematic of H_2S Removal Cell.

Feasibility Calculations

The following is a comparison of electrochemical cell stack sizes of an Electrochemical Membrane Separator (EMS) with a Molten Carbonate Fuel Cell (MCFC). The facilities each process 10MM SCFD of coal synthesis gas with the following composition presented in Table 1.

Table 1.
Coal Synthesis Gas Composition

CH ₄ :	0.3 vol%
H ₂ :	29.8 vol%
CO:	41.0 vol%
CO ₂ :	10.2 vol%
H ₂ S:	100 ppmv
COS:	in equilibrium
N ₂ :	0.7 vol%
H ₂ O:	17.1 vol%

The gases are supplied to the EMS and the MCFC facilities at 650°C and 1 atm.

In order to be an economically viable process, the EMS must be substantially smaller in size than the MCFC and consume only a fraction of the produced power.

EMS Calculations

The calculations for the EMS are based on a volumetric flow rate of 10MM SCFD or 3.3×10^6 cm³/sec. This flow is equally divided into each cell in the EMS stack and then sub-divided into parallel gas flow channels above the cathode with dimensions of 0.3 cm by 0.3 cm. With this, the equivalent channel diameter is calculated by equation (3).

$$D_{eq} = 4 * r_H = 4 * \left[\frac{\text{cross sectional area}}{\text{wetted perimeter}} \right] = 0.3 \text{ cm} \quad (3)$$

Initially, laminar flow is assumed in each channel. Thus, from Incropera and DeWitt⁽¹⁾,

$$N_{Sh} = k_m * \frac{D_{eq}}{D_{AB}} = 2.98 \quad (4)$$

From Reid, Prausnitz, and Poling⁽²⁾:

$$D_{AB} = \left[\frac{0.0018583 * T^{3/2}}{P * \sigma_{AB}^2 * \Omega_{D,AB}} \right] * \left[\frac{1}{M_A} + \frac{1}{M_B} \right]^{1/2} \quad (5)$$

with A = CO and B = H₂S. If P = 1 atm, T = 923 K, $\sigma_{AB} = 3.657$, $\Omega_{D,AB} = 0.82$, $M_A = 28$, and $M_B = 34$ then $D_{AB} = 1.2 \text{ cm}^2/\text{sec}$. Thus, by applying equation (4), the mass transfer coefficient for the gas phase diffusion can be found to be $k_m = 12.0 \text{ cm/sec}$.

The gas-phase limiting current density is the maximum current density which the cell can support as dictated by the maximum rate of diffusion of reagent to the sites of the electrochemical reaction. In this case, this reagent is H₂S by the reaction:

The flux of material to the electrode/electrolyte interface (neglecting pore diffusion, which has been shown to be negligible) is defined as:

$$N_{H_2S} = k_m \rho \frac{(y_{feed} - y_{out})}{\ln\left(\frac{y_{feed}}{y_{out}}\right)} \quad (7)$$

where ρ is the molar density of the gas phase (at 650°C and 1 atm this is 1.32×10^{-5} gmole/cm³). The current density supported by this diffusion is thus,

$$i_{d,H_2S} = nFN_{H_2S} \quad (7)$$

By combining equations (6) and (7), the current density can be calculated as follows:

$$i_{d,H_2S} = nFk_m \rho \left(\frac{y_{feed} - y_{out}}{\ln \frac{y_{feed}}{y_{out}}} \right) \quad (8)$$

With $n = 2$ faradays/equivalent and $F = 96500$ coulombs/equivalent, the limiting current density for the 1st stack which removes H₂S from 100 ppmv to 10 ppmv is 1.2 mA/cm².

There is a direct relationship between the amount of H₂S removed and the total current applied to the cell. This is defined by equation (9):

$$I = nFm(y_{\text{feed}} - y_{\text{out}}) \quad (9)$$

where m is the total molar flowrate of the gas to the removal cell. At 10MM SCFD, $m = 134$ gmole/sec. Thus, for the 1st stack of removal cells (100ppmv to 10 ppmv), the total current required is 2.33×10^3 Amps. If the driving potential to maintain this current is around 1 volt, this translates to 2.33 kWatts.

The active membrane surface area can be found by dividing the total required current by the maximum gas phase limiting current density:

$$A = \frac{I}{i_{d,H_2S}} \quad (10)$$

With $I = 2.33 \times 10^3$ Amps and $i_{d,H_2S} = 1.2 \times 10^{-3}$ Amps/cm², the total stack surface area is 1.96×10^6 cm² (or 2099 ft²). MCFC membranes are commonly available as 4 ft by 4 ft squares. If the same technology for the manufacture of these membranes is applied to the EMS membranes, then the total number of 4 ft by 4 ft electrochemical cells in the first stack is 131.

Since there are 131 individual cells in the first stack, the total molar flowrate is divided evenly into each cell in the stack. Therefore, the molar flowrate to each individual cell is 1.02 gmole/sec. Since the cell is 4 ft wide, there will be 406 individual parallel flow channels above the surface of each cathode and anode. The molar flowrate in each channel is thus 2.5×10^{-3} gmole/sec. This corresponds to a volumetric flowrate of 1.89×10^2 cm³/sec through each channel. The gas velocity is

found by dividing the volumetric flow through the channel by the channel cross sectional area. For a 0.3 cm by 0.3 cm square channel, this corresponds to a velocity of 21 meters/sec. The Reynolds Number for this flow is found to be 573, which verifies the original assumption of laminar flow. The cell residence time is thus found to be 0.058 seconds.

The calculations for the second EMS stack (10 ppmv to 1 ppmv) are identical to the calculations for the first. The results of this analysis show the limiting current density to be 0.12 mA/cm². The total applied current is 2.33×10^2 Amps (0.23 kWatts) and the required surface area is identical to the first stack, 2099 ft (131 individual membranes).

As a check of the mass transfer and cell residence time calculations, total molar transport through the membrane over the period of the cell residence time was calculated based on the mass flux estimation of current density and compared to a material balance around the cathode side of the cell. Multiplying the mass flux through the membrane by the membrane area and the cell residence time gives 6.97×10^{-4} gmoles of material transported (100 ppmv to 10 ppmv cell). Multiplying the molar flowrate by cell residence time and concentration change gives 6.94×10^{-4} gmoles of material transported. This confirms the residence time estimation to within 0.3%.

A summary of the EMS design calculations follows in Table 2.

Table 2.
Summary of EMS Design Calculations.

<u>Gas Phase Mass Transfer Coefficient, k_m:</u>	<u>12.0 cm/sec</u>
<u>Current Density in 1st Stack:</u>	<u>1.2 mA/cm²</u>
<u>Total Current to 1st Stack:</u>	<u>2330 Amps</u>
<u>Area of 1st Stack:</u>	<u>2099 ft²</u>
<u>Individual 4 ft x 4 ft Cells in 1st Stack:</u>	<u>131</u>
<u>Current Density in 2nd Stack:</u>	<u>0.120 mA/cm²</u>
<u>Total Current to 2nd Stack:</u>	<u>233.0 Amps</u>
<u>Area of 2nd Stack:</u>	<u>2099 ft²</u>
<u>Individual 4 ft x 4 ft Cells in 2nd Stack:</u>	<u>131</u>
<u>Total EMS Area:</u>	<u>4198 ft²</u>
<u>Gas Velocity in Each Channel:</u>	<u>21 m/sec</u>
<u>Total Cell Residence Time:</u>	<u>0.116 sec</u>
<u>Reynold's Number:</u>	<u>574</u>
<u>Total EMS Power Requirements:</u>	<u>2.56 kWatts</u>
* <u>0.058 seconds in each stack</u>	

MCFC Calculations

The MCFC calculations for stack size are outlined in the following manner. A current density of 160 mA/cm² was assumed. Processing of a synthesis gas stream which is 29.8 vol% H₂, 41.0 vol% CO, and 17.1 vol% H₂O at an 80% fuel utilization gives 76 gmole/sec of fuel oxidized. With two faradays of electricity produced for each mole of fuel utilized, this translates to 1.47×10^7 Amps of electricity produced. With a current density of 0.160 Amps/cm², the total area of the MCFC stack is 9.181×10^7 cm² (or 9.884×10^4 ft²). At a cross cell potential of around 1 volt, this translates to a power production of 14700 kWatts. Thus, the EMS is only 4.2% the size of the MCFC for a 10MM SCFD treating facility and consumes only 0.02% of the power produced. If the individual cells in the stack are 4 ft wide and 6 ft long, there are 4118 individual cells in the stack.

If the fuel flow is divided evenly between each cell in the stack, the molar flowrate to each cell is only 4.915×10^{-2} gmole/sec. There are assumed to be 0.3 cm by 0.15 cm parallel flow channels across the surface of the electrodes. Thus, with the flow to each cell evenly divided into each flow channel, the molar flowrate through each channel is only 8.015×10^{-5} gmole/sec. This translates to a volumetric flow of $6.07 \text{ cm}^3/\text{sec}$. The gas velocity in each channel is therefore 1.35 meters/sec. This gives a residence time in the stack of 1.38 seconds and a Reynold's Number of 24.

A summary of the MCFC design calculations results follows in Table 3.

Table 3.
Summary of MCFC Design Calculations

<u>Current Density:</u>	<u>160 mA/cm²</u>
<u>Total Current in Stack:</u>	<u>1.47×10^7 Amps</u>
<u>Total Stack Area:</u>	<u>$9.88 \times 10^4 \text{ ft}^2$</u>
<u>Individual 4 ft by 6 ft Cells in Stack:</u>	<u>4118</u>
<u>Gas Velocity in Each Flow Channel:</u>	<u>1.35 m/sec</u>
<u>Cell Residence Time:</u>	<u>1.36 seconds</u>
<u>Reynold's Number:</u>	<u>24</u>
<u>MCFC Power Production:</u>	<u>14700 kWatts</u>

Experimental Results

To date, five experimental runs of the laboratory scale EMS unit here at Georgia Tech have attempted to verify the polishing applications of this technology with simulated coal gasification product streams. The gas used in these experiments had an initial composition of approximately 18.0% CO₂, 38.0% H₂, 44.0% CO, and 100 ppm H₂S.

The cell housings were either made from 316 stainless steel or MACOR machinable ceramic blocks. The housings were 3" diameter, 1" thick cylinders with gas flow channels machined into the large surface faces. Gas flow tubes were connected to supply process and sweep gases to the cell (see Figure 2). Once the electrode and membrane materials were ready for testing, the electrodes were either set onto platinum current collectors if the MACOR housings were used, or directly onto the steel flow channels if the 316 SS housings were used (the SS housings acted as their own current collectors). The electrodes contacted the gas stream on one side and the electrolyte membrane on the other (see Figure 2). The full cell was then assembled by placing the membrane between the housing blocks and connecting the gas supply lines to the assembly.

Figure 2.
Experimental Cell Configuration.

When current is applied to the electrochemical cell, H_2S is reduced at the cathode:

However, carbon dioxide and water vapor compete in the reduction reaction by:

If hydrogen is present at the anode, then the following oxidation reactions occur after transport of the ionic species through the membrane:

By summing the half-cell reactions for sulfide transport (1) and (12) and the half-cell reaction for carbonate transport (11) and (13) one can see that if H_2 is present at the anode there is no net cell reaction and species are concentrated on the anode side of the membrane. The ionic flux through the membrane in this case depends on the relative mobilities of carbonate and sulfide as well as the concentrations of H_2S and CO_2 (and H_2O) in the process gas. Since CO_2 and H_2O are present in orders of magnitude higher concentrations than H_2S , they are preferentially transported.

If no hydrogen is present at the anode, the following oxidation reactions take place:

and

The direct oxidation of carbonate by reaction (14) takes place at a standard potential some 700 mV more positive than that for sulfide. When summed, the half-cell reactions for the transport of sulfide (1) and (2) at 900 K gives:

When the half-cell reactions for the transport of carbonate (11) and (14) are summed, the resulting cell reaction and standard potential are:

This gives an electrochemical 'window of operation'. If no H_2 is present at the anode and if the cell potential is maintained below -0.239 V yet above -1.030 V, the net

effect is the continuous removal of H_2S from the process gas accompanied by enrichment of the process gas with H_2 and direct generation of elemental sulfur. This mode of operation is preferable for commercial application, with one-step removal of H_2S and direct production of elemental sulfur as a by-product. Actual experimental results are as follows:

Run 44

This was our first attempt at the application of this technology to coal synthesis gas H_2S separation. The membrane used in this experimental run was three of MgO tape casts layered together with the acrylic binder burned out in-situ under an O_2 atmosphere. Eutectic composition Li/K carbonate (62% Li, 38% K) was then wicked into the membrane in-situ. Both the anode and cathode were lithiated NiO.

The coal synthesis gas fed to the cell after binder burn-out and electrolyte impregnation had an initial composition of 18.0% CO_2 , 38.0% H_2 , 44.0% CO, and 100 ppm H_2S . After allowing for the water-gas shift reaction:

$$K_a = \frac{(P_{CO_2} * P_{H_2})}{(P_{CO} * P_{H_2O})} \quad (18)$$

which has a K_a of 1.865 at 650° C, the composition of the gas in the cell was 13.2% CO_2 , 33.2% H_2 , 48.8% CO , 4.8% H_2O , and 100 ppm H_2S (assuming that the gas has gone to its equilibrium composition).

Using these gas compositions, the electrolyte equilibrium reaction:

$$K_a = \frac{(a_{\text{M}_2\text{S}} * P_{\text{CO}_2} * P_{\text{H}_2\text{O}})}{(a_{\text{M}_2\text{CO}_3} * P_{\text{H}_2\text{S}})} \quad (20)$$

was analyzed. K_a was found to be 3.57 at 650°C. This corresponded to an electrolyte equilibrium composition of 99.6% carbonate and 0.4% sulfide.

The run was terminated before any removal data was collected. Several factors contributed to the decision to terminate the experiment. First of all, the control relay on the furnace froze shut, causing the temperature to overshoot the acrylic burnout temperature of 350°C by over 300°. This damaged the membrane before the electrolyte was added and allowed process gas to cross over and mix with the sweep gas. The gas chromatograph results also became highly variable. It was found that a piece of the injection port septum broken off and fallen into the injection chamber, interfering with carrier gas flow. The GC was repaired and the run terminated due to gas cross-over through the damaged membrane.

The cell was shut down after 14.8 hrs of operation.

Run 45

This was the second attempt at polishing H_2S from coal gas, and the first using 316 stainless steel cell housings. The housings themselves acted as the current collectors with the galvanostat hooked directly onto the gas flow tubes. Aluminum foil gaskets were used to try to protect the stainless steel housings and improve gas seals by forming a protective layer of $LiAlO_2$ in-situ. The membrane was three MgO tapes layered together with the acrylic binders burned out in-situ and subsequently wetted with Li/K eutectic carbonate electrolyte. Both cathode and anode were lithiated NiO.

Initially, seals were excellent with both process gas and sweep gas pushing over 5 inches of H_2O back-pressure with no decrease in exit flow-rate. These seals were damaged, however, when the housings were adjusted in an effort to correct a current short between the cell housings.

No removal data was collected as the cell was shut down due to the current short across the cell. A post mortem examination of the cell showed a bead of what appeared to be molten aluminum shorting between the cathode housing and the anode housing. This is surprising considering the 'bead' was outside the cell housings and exposed to furnace air at $650^\circ C$. One would have expected such a 'bead' to oxidize to non-conductive Al_2O_3 . However, if the bead was formed over an area of the cell where reducing fuel gas was leaking into the furnace, it may have been protected from oxidation.

The cell was shut down after 8.15 hrs of operation.

Run 46

This experimental run was the third attempt at polishing H_2S from coal gas. The cell used three MgO tapes layered together within the stainless steel housings. No aluminum gaskets were used. Both the cathode and the anode were NiO and the electrolyte was eutectic composition Li/K carbonate. No useful removal data was collected from the cell. The extremely low cross-cell potentials together with the fact that the cathodic to reference potential was positive suggests that cross-over was present even though none was observed directly. Very low cross-over flow will carry enough hydrogen to transport carbonate with essentially no cross-cell potential.

The cell was shut down after 24.1 hrs of operation.

Run 47

This was the fourth attempt at polishing H_2S from coal gas. The cell used two layers of MgO tape with a mat of zirconia woven cloth from Zircar, Inc. for strength. The stainless steel cell housings were used with smaller aluminum foil gaskets around the wet seal area. These smaller gaskets had an outer diameter of only two inches and an inner diameter of 1.5 inches. This put the inner and outer edge of the gasket well away from either the edge of the electrode or the outer edge of the membrane. This was done to prevent a current short from forming as in run 45. The electrolyte was eutectic Li/K carbonate and the electrodes were both lithiated NiO.

The cell survived an initial temperature overshoot during the acrylic burn-out stage when the furnace control relay froze shut and ran the cell temperature up to

750°C. The zirconia mat gave enough re-enforcement to the membrane to allow it to survive this shock. The electrolyte was added after the cell had cooled back down to the run temperature of 650°C.

A small effect of current was observed after 18.8 hours with 3mA (0.37 mA/cm²) applied to the cell. This current level should have been sufficient for 155% removal of H₂S from the process gas stream assuming that all the current was carried by the sulfide ion. Only 26.4% removal was observed (exit H₂S concentration dropping from 31.3 ppm to 23.1 ppm at 150 cc/min total gas flowrate). An alternative, parallel current path was suspected. This seemed to be verified by the fact that the cell could still conduct current even after it had cooled to below the melting temperature of the electrolyte (R = approx. 4 MΩ). At run temperatures, this alternative current path could act in parallel with ion transport, cutting down the cell's current efficiency.

The cell was shut down after 152.7 hrs of operation.

Run 48

This experimental run was the fourth run using coal gas and, like the previous run, used two tapes of MgO and one mat of zirconia cloth as the membrane matrix material. The electrodes were both lithiated NiO. The acrylic binders were burned out under an O₂ atmosphere and the Li/K eutectic composition electrolyte was added with the cell at run temperature. MACOR machinable ceramic housings were used instead of the stainless steel housings and the inlet gas stream was hydrated to a level of 3.3% H₂O by passing the simulated coal gas through a bubbler since the cell did

not have a shift reactor in the gas line before the cell to allow the CO_2 and H_2 to go to an equilibrium H_2O and CO levels through the water-gas shift reaction.

CO_2 removal from the process gas as a function of applied current was recorded and is presented in Table 4. Examination of this data shows that the removal of CO_2 from the cathode side of the cell and production of CO_2 at the anode side of the cell is stoichiometric across the range of applied currents examined.

Cell seals were initially excellent on both sides of the cell, but flow out the anode side of the cell eventually stopped. Shortly after the anode flow stopped, cell cross-flow was observed and the cell run was terminated.

The cell run was terminated after 6.75 hours.

Table 4.
Run 48 Recorded Data.

<u>Applied Current (mA)</u>	<u>Actual Cathode CO_2 Out</u>	<u>Calc. Cathode CO_2 Out</u>	<u>Actual Anode CO_2 Out</u>	<u>Calc. Anode CO_2 Out</u>
0	19.0 %	19.0 %	0.0 %	0.0 %
100	18.4 %	18.6 %	0.6 %	0.8 %
200	18.2 %	18.1 %	1.2 %	1.5 %
300	18.2 %	17.7 %	2.0 %	2.3 %
400	17.2 %	17.2 %	2.7 %	3.1 %
500	16.8 %	16.8 %	3.7 %	3.8 %
600	15.6 %	16.3 %	4.2 %	4.6 %

Summary

Marginal success with the application of this removal cell to the polishing of H_2S from simulated coal gasification process streams has been shown. Some success has also been shown on the use of 316 stainless steel as a cell housing material for the coal gasification process gas polishing application. The CO_3^{2-} transport reactions were studied in coal gas and CO_2 removal was shown to be stoichiometric.

Planned Work for Next Quarter

Work will continue on the application of this technology to the polishing of coal gasification process streams. Use of Molten Carbonate Fuel Cell Materials (stainless steel housings, Ni/NiO electrodes, and eutectic Li/K carbonate electrolyte membranes) will be the main goal.

References

- 1) Incropera, F.P., and DeWitt D.P., Fundamentals of Heat and Mass Transfer, John Wiley & Sons, New York, 1985.
- 2) Reid, R.C., Prausnitz, J.M., and Poling, B.E., The Properties of Gases and Liquids, 4th ed., McGraw-Hill, New York, 1987.

END

**DATE
FILMED**

6 / 11 / 92