ESTIMATED STEADY-STATE COMPOSITIONS OF SUPERNATANT LIQUID DURING SLUDGE WASHING (U)

by D. T. Hobbs

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

Other Authors:

RECEIVED
FEB 04 1993
OSTI

This paper was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U. S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U. S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

de
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P. O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

WESTINGHOUSE SAVANNAH RIVER COMPANY
SAVANNAH RIVER LABORATORY

381263
WSRC-RP-91-1138

Keywords: Nitrate, pH,
Hydroxide,
Carbon dioxide
Bicarbonate,
Carbonate,
Absorption,
HLW

November 12, 1991

To: D. L. Fish, 773-A

DTJ
From: D. T. Hobbs, 773-A

SRL
RECORD COPY

**Estimated Steady-State Compositions of Supernatant Liquid
During Sludge Washing (U)**

SUMMARY

Steady-state hydroxide, pH, carbonate and bicarbonate levels have been estimated for supernatant liquids during sludge washing and storage. These compositions were needed in order to prepare synthetic solutions for determining inhibitor requirements. The steady-state pH was plotted versus the nitrate concentration and fitted to a logarithmic expression of the form,

$$\text{pH} = 10.23 \times [\text{NO}_3^-]^{0.0178}$$

where $[\text{NO}_3^-]$ is the concentration of nitrate in moles/liter. Similar expressions were also developed for calculating the concentrations of carbonate and bicarbonate as a function of the nitrate concentration.

INTRODUCTION

During sludge washing and storage, the hydroxide concentration in the supernatant liquid of the sludge can decrease by up to five orders of magnitude due to a combination of dilution and absorption of atmospheric carbon dioxide. Previous corrosion testing has shown that the supernatant liquid is much more corrosive at the lower hydroxide concentrations (lower pH).¹ Nitrite has been found to be an effective corrosion inhibitor at low hydroxide concentrations.² The steady-state concentrations of hydroxide (pH), bicarbonate and carbonate were estimated so that synthetic solutions could be prepared and tested to determine the inhibitor requirements during sludge washing and storage.

DISCUSSION

During sludge washing, the soluble salt concentration in the supernatant liquid will be diluted by a factor of about seventy.³ It was assumed that fourteen separate washing steps will be required to reduce the soluble salt concentration to meet the vitrification feed specification. Thus, the soluble salt concentration is diluted by a factor of 1.36 at each washing step.

Air is continuously pulled through the processing tanks to prevent the accumulation of a flammable mixture of hydrogen. Because of the high alkalinity, atmospheric carbon dioxide is absorbed into the supernatant liquid. The absorbed carbon dioxide reacts with hydroxide producing bicarbonate and carbonate species, and reducing the hydroxide concentration and pH.

Carbon dioxide is absorbed until a steady-state condition is reached. Steady-state is reached when the partial pressure of carbon dioxide in equilibrium with the solution containing hydroxide, bicarbonate and carbonate equals the partial pressure of carbon dioxide in the air entering the tank. The steady-state condition depends on the initial hydroxide and the initial carbonate concentration and the atmospheric concentration of carbon dioxide.

Steady-state concentrations of hydroxide, pH and total carbonate were calculated for each washing step using the previously reported waste tank absorption model.⁴ The composition of the supernatant liquid at the beginning of washing was set at 70.2 times the concentration of that reported for washed sludge.⁵ For these calculations, the atmospheric carbon dioxide concentration was assumed to be a constant 360 ppm, which is the average concentration measured over a one year period in 1986 and 1987.⁶ Bicarbonate and carbonate concentrations were calculated using the reported equilibrium values.⁷

The estimated steady-state compositions are given in Table I. The steady-state pH ranges from 9.51 to 10.28. During the first half of washing, carbonate is the predominant carbonate species. During the latter half of washing and during storage, bicarbonate is the predominant carbonate species.

Plots of the steady-state pH and bicarbonate and carbonate concentrations versus the nitrate concentration are given in Figures 1 and 2. Each set of data was fit to a logarithmic expression. The expressions for pH, carbonate and bicarbonate are given below.

$$\text{pH} = 10.23 \times [\text{NO}_3^-]^{0.0178}$$

$$[\text{CO}_3^{2-}] = 0.577 \times [\text{NO}_3^-]^{1.22}$$

$$[\text{HCO}_3^-] = 0.329 \times [\text{NO}_3^-]^{0.690}$$

**Table I. Estimated Steady-State Compositions of
Supernatant Liquid During Sludge Washing**

Wash Step	[Nitrate] (molar)	[Hydroxide] (molar)	pH	[HCO ₃ ⁻] (molar)	[CO ₃ ²⁻] (molar)
0	1.44E+0	4.05E-4	10.28	4.09E-1	8.31E-1
1	1.03E+0	3.46E-4	10.22	3.32E-1	5.75E-1
2	7.46E-1	2.96E-4	10.17	2.68E-1	3.98E-1
3	5.38E-1	2.52E-4	10.12	2.16E-1	2.72E-1
4	3.88E-1	2.15E-4	10.06	1.73E-1	1.87E-1
5	2.80E-1	1.82E-4	10.01	1.39E-1	1.27E-1
6	2.02E-1	1.55E-4	9.96	1.11E-1	8.65E-2
7	1.46E-1	1.31E-4	9.91	8.88E-2	5.82E-2
8	1.05E-1	1.11E-4	9.85	7.07E-2	3.93E-2
9	7.58E-2	9.31E-5	9.79	5.64E-2	2.63E-2
10	5.46E-2	7.73E-5	9.73	4.46E-2	1.73E-2
11	3.94E-2	6.36E-5	9.66	3.53E-2	1.12E-2
12	2.84E-2	5.20E-5	9.59	2.78E-2	7.25E-3
13	2.05E-2	4.18E-5	9.51	2.17E-2	4.55E-3

Figure 1. Estimated Steady-State pH of the Supernatant Liquid During Sludge Washing

Figure 2. Estimated Steady-State Bicarbonate and Carbonate Concentrations in the Supernatant Liquid During Sludge Washing

REFERENCES

1. A. F. Riechman, "In-Tank Processing: Corrosion Phenomena Due to Storage of Dilute Waste Solutions", DPST-86-236, January 20, 1986.
2. J. W. Congdon and J. S. Lozier, "Inhibition of Washed Sludge with Sodium Nitrite", DPST-87-379, April 7, 1987.
3. T. Motyka, "Technical Data Summary for In-Tank Sludge Processing", DPSTD-84-100, April, 1984.
4. D. T. Hobbs and R. M. Wallace, "Hydroxide Depletion in Waste Storage Tanks By Reaction With Carbon Dioxide", DPST-85-846, October 14, 1985.
5. "Basic Data Report - Defense Waste Processing Facility - Sludge Plant", DPSP-80-1033, Appendix G, Rev. 90, October 30, 1984.
6. D. T. Hobbs, "Absorption of Carbon Dioxide in Waste Tanks", DPST-87-596, September 3, 1987.
7. "Lange's Handbook of Chemistry", J. A. Dean, editor, McGraw-Hill, New York, 13th edition, 1985.

END

DATE
FILMED

5 / 10 / 93