NOTICE

**CERTAIN DATA
CONTAINED IN THIS
DOCUMENT MAY BE
DIFFICULT TO READ
IN MICROFICHE
PRODUCTS.**

DOE/MC/25168--3290

DE93 013361

**Advanced Alternate Planar Geometry
Solid Oxide Fuel Cells**

Interim Quarterly Technical Progress Report
November 1, 1988 to January 31, 1989

By

**Dave Prouse, S. Elangovan and A. Khandkar
Ceramatec, Inc.**

and

**Rich Donelson and Len Marianowski
Institute of Gas Technology**

Work Performed under
DoE Contract No: DE-AC 21-88MC25168

For

**Department of Energy
Morgantown Energy Technology Center
Morgantown, WV 26505**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

By

**Ceramatec, Inc.
2425 South, 900 West
Salt Lake City, Utah, 84119.**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

RECEIVED

MAY 20 1993

OSTI

This quarterly report documents the progress made during November 1988 through January 1989. During this quarter progress was made at Ceramated in seal development and conductivity measurements of YIG compositions, a creep test was completed on the porous/dense/porous trilayer IGT. IGT also provided a discussion on possible interconnect materials to Ceramated. Below is detailed the progress at Ceramated and IGT during this quarter.

PROGRESS SUMMARY

During this reporting period, work was carried out on the following tasks:

- Task 1: Cell Design Analysis
- Task 2: Program Liaison and Test Facility Preparation
- Task 3: Electrolyte Development and Fabrication
- Task 4: Edge Seal Development and Fabrication
- Task 5: Electrode Development and Fabrication:
- Task 6: Interconnect Development and Fabrication
- Task 7: Out-of-cell Tests

Tasks 8, 9 and 10 were not active during this period and are not scheduled to be active until later in the project.

Task 1: Cell Design Analysis

At this point, Task 1 is essentially complete and the pressure drop for a given cell design can now be calculated. A summary of the results is given in the August-October 1988 Quarterly Report. When new information on the design of the planar-ribbed SOFC is obtained, the program may be used.

Task 2: Program Liaison and Test Facility Preparation

The first part of Task 2, namely, set up of a high temperature creep rig, is complete. This rig will allow testing of the materials developed by Ceramated under Tasks 3-6 for their suitability in the solid oxide fuel cell

Work will now begin on the design of test rigs for cell seal evaluation and in-cell testing.

(3) Tasks 3-6: Cell Component Fabrication Development

Efforts were concentrated on edge seal development and conductivity measurements of doped YIG compositions. Electrode matrix-electrolyte blanks were sent to IGT for creep testing under Task 7.0. At IGT, a report on alternate metal and ceramic materials for interconnect was prepared. The thermal expansion coefficient of the seal sample was measured.

Task 7: Out-of-cell Tests

Samples of trilayer electrolyte components were sent to IGT. One creep test has already been run under Task 7. Additional tests will be run as soon as seal and electrode impregnation studies are completed.

Progress at Ceramatec

During the latter part of November Ceramatec moved its R&D labs to a new location. This has caused some inadvertent delay associated with set-up of laboratory facilities in the new location. Ceramatec will make every effort to complete the move and bring all equipment up and in working order.

Task 3.0 Electrolyte Development and Fabrication:

The electrode matrix-electrolyte samples sintered earlier were inspected for flatness and uniformity of shrinkage as well as the presence of any delamination during the sintering process. No delamination was found. These samples were then delivered to IGT for creep testing. The samples had uniform thickness and area of approximately 0.25 in.². The creep test details are included under Task 7.0. The average creep was found to be negligible, about 0.31%. This is very encouraging and hence it was decided to make more composite electrode matrix-electrolyte tape. This activity was planned for this report period but could not be carried out due to delay associated with the move.

Task 4.0 Edge Seal Development and Fabrication

During the previous reporting period the seal characteristics of a melt quenched glass was reported. The components of the glass were melted in a platinum crucible, held at 1250°C for 16 hours to possibly eliminate any volatile species and then homogenized at 1300°C. When the resulting glass was used to seal two zirconia membranes, one with a porous layer, the bonding was very good in spite of the fact that the optical microscopy suggested that the seal temperature of 1150°C was low. When the seal was subjected to reducing atmosphere (H_2) at 1000°C for one hour the seal showed some discoloration. This has been observed in earlier studies of this seal material at Ceramtec. This discoloration is believed to occur due to the PbO component in the glass that reduces to Pb in H_2 . However, the discoloration did not appear to affect effectiveness of the sealing and the same composition of glass was used successfully to seal zirconia electrolytes for more than 200 hours of continuous operation under fuel cell operating conditions. Efforts are underway, however, to identify and replace the Pb containing component of the glass without compromising other characteristics.

During the processing of glass components to form the glass a sample was drawn for thermal expansion studies as follows. The platinum crucible containing the molten glass at 1300°C was pulled out of the furnace. A stainless steel rod (1/4" dia) was dipped into the molten glass and pulled slowly at a relatively constant speed such that a glass rod of uniform cross section solidifies. The rod thus formed was about 2" long and had a diameter of about 1/8". The edges of the rod were polished to give parallel flat surfaces. The glass rod was sent for coefficient of thermal expansion (CTE) measurement using a dilatometer. The dilatometric trace is given in Figure 1. The trace displays the differential change in dimension of the glass rod on heating and cooling. The glass was quenched in air from about 1300°C in the process of drawing the rod. It is highly likely that the glass rod had residual internal stresses. This fact is evidenced from the anomalous behavior of the dilatometric trace in the 550 to 600°C range during the heating cycle where negligible or negative change in expansion is observed. It appears that in the 550 to 600°C range stress relaxation occurs due to annealing causing an increase in glass density. This results in a decrease in specimen dimensions. The second similar anomalous behavior occurs at about 690°C. At this

TYPE THERMOCOUPLE

SAMPLE: IN/0017

SIZE: 1/4" x 1/4"

REMARKS:

Y AXIS SCALE: 0.25 mV

RATE: 2°C/min

ATM: 1.1

MODE:

DATE: 1/2/86

Coefficient of Thermal Expansion CTE
(50 - 550°C) = $6.8 \times 10^{-6}/^{\circ}\text{C}$

Coefficient of Thermal Contraction CTC
(700 - 650°C) = $9.0 \times 10^{-6}/^{\circ}\text{C}$

FIGURE 1

temperature the glass rod softens sufficiently to the point that the force from the push rod of the dilatometer causes the sample to bend. This bend was observed in the sample after removal from the dilatometer. Upon cooling the thermal contraction behavior is as expected. Since the internal stress of the glass rod were completely removed during heating the cooling trace reveals the expected ideal thermal expansion (or contraction) behavior characteristic of a glass.

There are several useful data that can be derived from this experiment. The glass transition temperature, T_g , of this glass is about 630° C (from the cooling trace). The temperature at which the rod begins to bend during thermal expansion measurement known as dilatometric deformation temperature, T_d , is about 690° C. The glass transition temperature establishes the annealing temperature after effecting the seal at about 600° C. Since 690° C is the temperature at which the glass begins to deform under load, it is conceivable that at the operating temperature (1000° C) the seal will be still more compliant. However the glass will still be confined to the joint area due to the operating temperature being 200-250°C below its working point.

Another important factor to consider in characterizing a seal material is its coefficient of thermal expansion (CTE). Below T_g the calculated value of CTE is $6.8 \times 10^{-6} / ^\circ\text{C}$ and above T_g it is $9.0 \times 10^{-6} / ^\circ\text{C}$ (from the cooling curve). The CTE for the zirconia electrolyte material is $10.5 \times 10^{-6} / ^\circ\text{C}$. Ideally a good CTE match is desired above T_g , such that residual stresses are not created when the components are cooled after the seal is effected. However, it should be remembered that glasses can withstand very high compressive stresses but fracture under low tensile stress levels. Hence a glass that has a lower CTE than zirconia may still function as an effective seal material. Work will be continued to increase the CTE of the glass closer to that of zirconia and still maintaining the other characteristics. Options to reduce or eliminate components that reduce in the fuel atmosphere are also being investigated.

Two aspects of the seal development work were carried out during the latter part of this report period. Firstly, a wide range of lead-free commercial glasses were considered as possible seal candidate. Earlier it was reported that the current glass seal material (KW0847) has performed adequately in hermetic sealing of zirconia membranes to zirconia tubes. The arrangement was tested under fuel cell operating conditions. It was observed that on the anode side of the seal the glass had blackened presumably due to reduction of lead oxide present in the glass. The long term effects of

such reduction is presently unknown. A parallel effort was thus initiated to identify lead-free glasses that will provide adequate sealing, in combination with the other components of the current seal material or by itself. Two candidate glass materials have been chosen for further evaluation. These lead-free glasses are expected to form a good seal in conjunction with the major components of KW0347. The new lead-free glasses chosen are expected to increase CTC of the baseline glass in addition to providing a non-reducing seal. Discussions with a commercial vendor is currently underway to procure the desired glasses.

Infiltration of the glass into the porous zirconia layer was the other aspect that was investigated during this report period. An initial trial was done with a slurry of glass in an organic binder. The slurry was placed on the porous surface of the porous-dense bilayer and fired at 1250° C for 30 minutes. Optical microscopy of the sample revealed that the glass has not penetrated appreciably into the pores. This conclusion was arrived at due to the fact that the glass slurry had not flowed appreciably on the surface. Even though the firing temperature of 1250° C may be adequate for sealing of two dense membranes, as evidenced from the hermeticity experiment, it may be too low for infiltration. Two approaches are being planned for the next report period. In the first one a thinner slurry will be vacuum infiltrated and fired at 1250° C and a second trial of vacuum infiltrated glass will be fired at a higher temperature. Options to use screen printing technique will also be investigated.

5.0 Electrode Development and Fabrication:

(a) Electronically Conducting ZrO_2 Based Electrode Materials

The materials for the 40/10/50 mol% composition in the three phase In_2O_3 - $PrO_{1.8}$ - ZrO_2 system were received. Synthesis of the electrode will soon begin and the material will be evaluated for conductivity and thermal expansion characteristics.

(b) Doped "p" type perovskites

No work was done on this sub-task during this report period.

(c) $\text{Y}_3\text{Fe}_5\text{O}_{12}$ (YIG) compounds

Conductivity trials on doped $\text{Y}_3\text{Fe}_5\text{O}_{12}$ continue at Ceramtec. Figure 2 shows the conductivity of a series of Mg-doped YIG compositions. The conductivity shows a small activation energy of 0.024 eV indicating relatively small variation with temperature. Measurements at temperatures of 1000°C will also be carried out. However based on these results the conductivity is not expected to change significantly.

A series of Cr-doped YIG compositions were synthesized and tested for conductivity. Figure 3 shows the conductivity of a series of the Cr-doped YIG compositions. The conductivity shows an activation energy of 0.56 eV. Comparison of conductivities of the Mg doped and the Cr doped series of YIG materials shows that the Mg-doped series exhibit a greater conductivity (2.6×10^{-2} S/cm) at 700°C than the Cr-doped series (8×10^{-3} - 2.5×10^{-2} S/cm). However the Mg doped YIG materials exhibit far less temperature dependence as shown in the previous report. Extrapolation of the conductivity behavior of Cr-doped (see Figure 4) suggests that these may have higher conductivity (4.5×10^{-2} - 2×10^{-1} S/cm) compared to the Mg-doped YIG electrodes. Platinum lead wires have been ordered and a couple of Cr and Mg doped samples will be tested at 1000°C as soon as they are received.

6.0 Interconnector Development and Fabrication:

Interconnect Development and Fabrication, is being carried out by Ceramtec. However, fabrication of thin, flat ceramic structures with flow-field ribs poses very challenging problems. In order to expedite cell testing using advanced cell design and component geometry concepts, Ceramtec asked IGT to supply a discussion of possible materials which could be used for an interconnect. IGT had carried out an in-depth survey on high temperature metal alloys for use in MCFCs. Ceramtec wanted to explore the possibility of using a stamped metal interconnect-electrode structure incorporating ribs or dimples to allow gas flow. Ceramtec also requested recommendations on alternative interconnect materials. This request was based on prior discussions at IGT where Mark Lawson of IGT suggested the possible use of Fe_2O_3 as a potential interconnect material. Discussions of these two areas are given below.

FIGURE 1

Conductivity of Mg doped Ca(0.4)-YIG

FIGURE 2
Conductivity of Cr doped Ca(0.4)-YIG

FIGURE 3

Projected Conductivity Behavior of Cr-doped YIG @ 1000C

Figure 4. TERNARY DIAGRAM FOR NICKEL-IRON-CHROMIUM SYSTEM
PHASES FORMED AT 1200°F

From "High Temperature Alloy Hot Performance Guide," Huntington Alloys, Inc.,
Huntington, WV, 25720.

CREEP STRENGTH
(1% Min. Creep Rate/10,000 Hrs.)

Figure 5. CREEP DATA FOR NICKEL-IRON-CHROMIUM ALLOYS OVER
A RANGE OF TEMPERATURES

From "High Temperature Alloy Hot Performance Guide," Huntington Alloys, Inc.,
Huntington, WV, 25720.

Thermal expansion (between room temperature and temperature shown) of heat-resistant alloys based on the percent nickel.

Figure 6. DIAGRAM SHOWING THERMAL EXPANSION COEFFICIENTS OF NICKEL-IRON-CHROMIUM ALLOYS

From "High Temperature Alloy Hot Performance Guide," Huntington Alloys, Inc., Huntington, WV, 25720.

Stamped Metal Interconnect-Electrode Materials

In order for such a ribbed electrode plate to be effective in an SOFC stack, it must have dimensional stability and resist oxidation at 1000°C. The ribbed electrode plate must act as a current collector, as well as provide flow paths for fuel and oxidant gases, so that the material must remain electronically conductive. Also it is desirable to have a ribbed electrode plate material with a coefficient of thermal expansion similar to that of the zirconia electrolyte.

A metallic ribbed electrode plate has the advantage that it can be drawn and formed into a complex geometry that will act as a rigid spacer to yield the height needed to get sufficient cross sectional area for fuel and oxidant gas flows, and will not be prone to cracking and catastrophic failure that could occur if a brittle material were utilized. The only moderately priced commercial alloys which have slow enough growing scales to be sufficiently passivating at 1000°C are silica-, alumina-, and chromia-formers. Of these three, chromia-formers have the best chance of providing sufficiently high electronic conductivity to function effectively as a current collector. A chromia-former with a sufficient nickel content is desired to provide the high temperature strength and creep resistance necessary so that the separator plate will maintain its shape satisfactorily in an operating cell.

Figure 5 shows the composition of some readily available and reasonably affordable (under \$15/lb) alloys in the nickel-iron-chromium system. Table 1 lists the compositions of these alloys.

Figure 6 shows the creep strength at elevated temperatures for some of the alloys listed in Table 1. Figure 7 shows that the magnitude of the thermal coefficient of expansion of these alloys is dependent on the nickel content.

The tetragonal phase yttria-stabilized zirconia electrolyte has a thermal coefficient of expansion of approximately $6 \times 10^{-6}/^{\circ}\text{F}$ (or $3.33 \times 10^{-6}/^{\circ}\text{C}$). Therefore, those alloys with greater than 60% nickel are more like the zirconia electrolyte than those alloys with intermediate nickel contents (approximately 30%, see Figure 7). An examination of Figure 6 reveals that these higher nickel alloys also possess better resistance to creep at high temperature.

Cobalt alloys also show promise for use as a ribbed electrode structure. They have lower coefficients of thermal expansion and exhibit very good creep resistance but are very expensive. Alloy 617 is a nickel-chromium-cobalt alloy with superior creep resistance as shown in Figure 6.

Table 1

ALLOY COMPOSITIONS (WEIGHTPERCENT)

	Ni	Cr	Fe	Si	Mn	Other
Incoloy 800 ¹	32.5	21.0	46.0	0.5	0.8	0.5 each; Cu, Al, Ti
330 Stainless	26.0	19.0	42.0	1.25	2.0	
310 Stainless	20.0	25.0	52.0	1.50	2.0	
309 Stainless	14.0	23.0	60.0	1.0	2.0	
Inconel 600 ¹	76.0	15.5	8.0	0.2	0.5	0.2 Cu
Inconel 601 ¹	60.5	23.0	14.1	0.2	0.5	0.5 Cu, 1.4 Al
Inconel 625 ¹	61.0	21.5	2.5	0.2	0.2	
Inconel 617 ¹	54.0	22.0				12.5Co, 9 Mo, 1.0Al

¹ Huntington Alloys, West Virginia

Of the readily available, reasonably affordable alloys considered, Inconel 600¹ is the most likely candidate for use as a metallic separator plate material with solid oxide fuel cells. The available oxidation data is available for a wide variety of exposure conditions indicating that the depth of oxidation should be a few mils per year of exposure. Depending on the actual rate of oxidation during long term exposure and the projected operating life of a cell, the separator plate may have to be between 20 and 30 thousandths of an inch thick.

¹ Huntington Alloys, West Virginia

FIGURE 7.

OXIDATION MECHANISMS OF IRON TO FORM A THREE-LAYERED SCALE OF FeO, Fe₃O₄ AND Fe₂O₃ ABOVE 570°C SHOWING DIFFUSION STEPS AND INTERFACIAL REACTIONS

FIGURE 8.
TEMPERATURE DEPENDENCE OF THE ELECTRICAL CONDUCTIVITY OF
SEVERAL ELECTRONICALLY CONDUCTING OXIDES
(Courtesy D. Adler)

Alternative Interconnect Materials

Iron oxide is a readily obtained, low-cost substance which may be suitable for use as an interconnect material. Figure 8 shows the three-layered scale which is likely to form in the oxygen potential gradient across the interconnect. The thickness of these layers depend on the magnitude of the partial pressure of oxygen present in the fuel gas. Figure 9 shows that both FeO and Fe_3O_4 are highly conductive at the operating temperature (1000°C) of the SOFC. Therefore the magnitude of the electrical resistivity of the interconnect would be determined primarily by the Fe_2O_3 layer where the interconnect is in contact with the oxidant gas. This layer may only be a fraction of the the total interconnect surface, depending on the rate of transfer of oxygen from the cathode gas through the interconnect.

Thus Fe_2O_3 is the electrically insulating layer in the multi-layer iron oxide scale. In the oxidizing environment of the cathode gas, the electrical conductivity of the Fe_2O_3 lattice could be enhanced by doping the cationic sub-lattice of the oxide with a lower valent cation. The results of some work which examined the electrical resistivity of iron oxide doped with Cu, Co, or Mn indicates that replacing a fraction of the iron with a lower valent cation should result in sufficient electrical conductivity to run a series of solid oxide cells at temperature (1000°C). The electrical conductivity and thermal expansion of an interconnect fabricated from such a material must be compared to those of the electrolyte matrix and electrodes which compose the remainder of the cell package.

Samples of FeO_x will be fabricated and the CTE will be measured. Based on the CTE compatibility, a decision will be made as to whether or not to pursue the alternate FeO_x based concept. Ceramtec has already obtained a sample of corrugated stainless steel (SS 304) for trials as the interconnect. Literature on Inconel alloys is being evaluated and material will be ordered.

IGT PROGRESS

Task 1. Cell Design Analysis

Background

The proposed planar design will incorporate a seal between the manifold and the electrolyte material which will undergo a clamping stress in order to obtain a pressure-tight seal. The magnitude of this pressure depends on the pressure drop across the cell. That is, as the pressure differential is increased a higher holding force must be applied. The purpose of Task 1 is to calculate the pressure drop across the cell for a given cell configuration.

Creep tests and cell seal evaluation, which are to be carried out under Task 7, will yield information about how strong and gas-tight the seals are. These two pieces of information will then be utilized as cell design criteria.

Activities

No activities in this area at this time. A summary of results was given in the Quarterly Report covering August 15 through October 31, 1988.

Task 2. Program Liaison and Test Facility Preparation

Background

This task involves the design and construction of test equipment which are to be used to test SOFC components in Tasks 7, 6, and 9. There are three types of tests to be carried out under this contract: these are:

- Creep testing of single or multiple SOFC components
- Cell sealing efficiency
- Complete cell tests.

The creep rig design requires a 0.5" diameter test sample which is placed in compression and held at 1000°C for 200 hours. The dimensional change is then measured and predictions will be made as to the suitability of the component for use in the SOFC.

Activities

Some minor redesign of the creep rig was carried out during this period. These changes included specifying higher temperature thermocouples and implementation of a dial indicator in conjunction with the kaman meter.

Work has begun on the design of the cell seal or cell testing equipment. Design criteria for the cell seal evaluation rig were recently discussed during a visit of IGT staff to Ceramtec.

Task 7. Out-of-cell Tests

Activities

A creep test was carried out on the trilayer (porous/electrolyte/porous) during this reporting period. This test ran for 74 hours before thermocouple failure shut down the test, then restarted and run for an additional 126 hours. A complete discussion of the creep test is included below. Creep under compression was measured at 1000°C with a loaded area of approximately 0.25 square inch. A compressive load of 50 psi was used.

The result indicates that the primary creep was on the order of 0.31% and occurred within the first 5 hours of testing. The creep rate after this point appeared to be 0 within the limits of resolution of our equipment.

Objective

Measure the creep rate under compression of the solid oxide fuel cell components, in this case the trilayer structure

Introduction

The trilayer consists of three layers of stabilized zirconia which are to form the middle section of the solid oxide fuel cell. It consists of a layer of fully dense zirconia sandwiched between layers of porous zirconia.

Since this component will be placed under compression, the deformation under load at operating temperature becomes an important parameter. Therefore creep tests are being carried out under conditions similar to those expected in the solid oxide fuel cells, namely, at 1000°C under a 50 psi compressive load.

Experimental Procedure

The samples were received as non-equilateral hexagonal pieces, from Ceramtec Lot PC3645CFT. Because of the irregular shape, the area was measured by tracing the shape onto a paper and cutting out. This was then compared to the weight piece of the same paper with a known area.

Thickness was measured in seven places and averaged (see Table 2). Five samples were placed on top of each other and glued together. The stacking was required to obtain sufficient thickness to be within the resolution of the test rig. This yielded a total sample thickness of around 150 mils.

This sample stack was then placed between two alumina cylinders and held with under a low load. The furnace was brought up to 1000°C at about 4°C/min and allowed to stabilize. A compressive load of 50 psi was then applied and held for 74 hours, then restarted and run out 126 more hours. Changes in the thickness of the sample stack were measured in the creep rig and recorded. After testing, the samples were removed and the thickness of each test piece was then measured in seven places as was done prior to testing.

Results

For this type of material, very little creep is expected. However, this test gave an opportunity to test our apparatus and verify that this is the case. The results of thickness measurements before and after the 74 hours test showed that there was

on average 0.31% change in thickness over the test period. It is expected that all, or nearly all, of the creep took place in the first 5 hours of testing. This type of creep is referred to as primary creep.

The plot of change in thickness versus time shown in Figure 10 indicates that the steady state creep rate, which occurred after the first 5 hours is essentially 0, within the limit of our resolution. Thus, the trilayer material will most likely not cause any problem during use in terms of deforming under load if an initial "setting in" of less than 0.5% is accommodated.

The creep rate from 74 to 200 hours appeared to be zero, within the limits of resolution of our equipment. This was also indicated by the pre- and post-test thickness measurements shown in Table 2 where the change in thickness from 74 to 200 hours was essentially zero.

Table 2
RESULTS OF CREEP TESTING OF ELECTROLYTE TRILAYER MATERIAL
PC3848CFT

(Samples were measured before and after testing for 74 hours and then tested out to 200 hours at 1000°C under 50 psi compressive load.)

Hours No.	Pre-Test (Mils)	@ 74 Hours (Mils)	Change 0-74 Hours (Mils)	@ 200 Hours (Mils)	Change 74-200 (Mils)
1	31.9	31.7	0.2	31.6	0.1
2	32.2	32.1	0.1	32.1	0.0
3	31.1	31.0	0.1	31.0	0.0
4	31.8	31.8	0.0	31.8	0.0
5	32.6	32.4	0.1	32.4	0.0

CREEP TEST OF SAMPLE CT111588-1

FIGURE 9.
THICKNESS CHANGE VERSUS TIME FOR ELECTROLYTE TRILAYER MATERIAL PC3848CFT
(Tested at 1000°C under 50 psi compressive load)

(MR65079Nov/RPE:rd)

Tasks 8-11

These tasks were not active during this reporting period.

APPENDIX: SIX MONTH PLAN FOR SOFC DEVELOPMENT

The following is a list of items to be delivered by Ceramtec and IGT during the period of February 1989 to August 1989 in order to accomplish the goals of the SOFC program.

FEBRUARY

Ceramtec

- Schematic of proposed cell design to IGT
- Creep Sample CRP-2 to IGT; bilayer + glass seal material.

IGT

- Design of the Cell Seal Evaluation (CSE) rig using schematic referred to above.

MARCH

Ceramtec

- Creep Samples CRP-3 and CRP-4 to IGT; trilayer + anode, trilayer + cathode

IGT

- Order parts for CSE rig
- Run creep test on Sample CRP-2, data to Ceramtec

APRIL

Ceramatec

- CSE Sample CSE-1 to IGT.

IGT

- Build CSE rig
- Run creep test on Sample CRP-3 and CRP-4, data to Ceramatec.

MAY

Ceramatec

- Creep Sample CRP-5 to IGT; interconnect sample.

IGT

- Run CSE test on Sample CSE-1.

JUNE

Ceramatec

- CSE Sample CSE-2 to IGT.

IGT

- Run creep test on CRP-5, data to Ceramatec.

JULY

Ceramatec

IGT

- Run CSE-2. data to Ceramtec.

AUGUST

Ceramtec-IGT

- Meeting to discuss test results and final cell design of SOFC test cell.

END

**DATE
FILMED**

6 / 10 / 93