011751

1 OF 1

DOE/ER/45419--2

DE92 011751

ROLE OF STRUCTURE IN ION MOVEMENT OF GLASSES

Progress Report

for Period January 14, 1991 to January 15, 1992

Himanshu Jain

Lehigh University
Bethlehem, Pennsylvania 18015

January 15, 1992

Prepared for

THE U. S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG02-90ER45419

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ROLE OF STRUCTURE IN ION MOVEMENT IN GLASSES

(Grant DE-FG02-90-ER45419)

Summary of Progress for the Period

January 16, 1991 - January 15, 1992

Can the structure of a melt much above the glass transition temperature (T_g) determine the structure and (transport) properties of glass? In other words, are there extremely long lasting configurations in a melt which would affect ion transport in the glassy state? A major effort during the past year has been to address these very fundamental questions. An important consideration here is to separate the effect of the variable melt structure from that of a variable cooling rate in the glass transformation range. For this reason our experiment consists of preparing 0.3 Na_2O - 0.7 B_2O_3 glasses from the melt which is first equilibrated at 1400 C and then annealed at 850 C for 0 to 180 minutes. From 850 C variously annealed melts are quenched to the glassy state by following identical procedure. If the structure (as reflected in ion transport) of 1400 C melt relaxes to that of 850 C in $\sim$ minutes, we may expect to observe variations in the conductivity time in the ns range.

Because the composition and cooling rate are the same for all samples, one expects rather small, if any, difference among the samples and high accuracy of the measurements is critical. To avoid errors from sample geometry measurements, we have chosen to compare the activation energy of conductivity (E) of various samples. The results show E to vary within 0.017 eV which is more than the reproducibility limit of our measurements

on glasses prepared from the same batch. Further, statistically from two sets of experiments E appears to decrease with increasing annealing time (t). Assuming that the melt at 1400 C has more open structure than at 850 C, one expects E to increase with t, if at all. Surprisingly, our present data indicate an opposite trend. This work has been presented at two technical meetings. Because we are relying on very small variations of E, we plan to once again repeat our experiments for more reliable statistics before publishing important consequences of the observations so far.

Concerning the development of EXAFS at Brookhaven for determining local structure around Na and Si, we are continuing collaboration with the group at AT&T. The appropriate detection capability for low energy X-rays has not become operational yet. In the interim, however, we have successfully obtained EXAFS on both the network modifier and former cations in four $x\text{Rb}_2\text{O} - (1-x)\text{GeO}_2$ ($x=0.01-0.20$) glasses. Preliminary analysis indicates that Ge-O first shell bond length increases with x, but for Rb-O it increases slightly from $x=0.01$ to 0.05, remains unchanged to $x=0.10$ and then decreases for $x=0.20$. The disorder, both in Rb-O and Ge-O bonds, increases monotonically with x. Bond lengths and coordination numbers around the two cations are yet to be analyzed.

The quartz experiments for determining the importance of amorphousness on ion transport is progressing well. We have obtained a low impurity crystal and determined its electrical conductivity in the c-direction (E-1.78 eV). Further, a test sample has been subjected to neutron irradiation at the Brookhaven reactor, and from the level of radioactivity we foresee no radiation hazard in working at Lehigh with the irradiated samples.

Finally, we have successfully collaborated with Professor Nowick to investigate bulk electrical relaxation processes in silicate glasses (see the enclosed preprint). Our experiments show that the only bulk relaxation process is due to the "universal" power law dependence of conductivity; our results fail to show the bulk relaxation peak which is often quoted in the literature. We have also collaborated with Professor Kanert in investigating how the ion movement in heavy metal fluoride glasses compares with that in oxide glasses (see the enclosed preprint). There are indications of a new localized motion involving F atoms. Ion movement in these glasses is particularly sensitive to the structural relaxation below T_g and hence they are particularly suitable for our program.

PUBLICATIONS:

1. Ion Movement Relaxation in Inorganic Glass - Salient Features
J. Non-crystalline Solids 131, 961 (1991)
2. Measurement of Electrical Conductivity of Glasses
Trans. Am. Ceram. Soc. To be published.
3. On the Nature of Electrical Relaxation in Silicate Glasses
Proc. VII Int. Conf. Physics of Non-cryst. Solids. To be published.
4. Nuclear Spin Relaxation in Fluorozirconate Glass
Proc. VII Int. Conf. Physics of Non-cryst. Solids. To be published.

PUBLICATIONS: ABSTRACTS ONLY

1. Correlation between Structure and Ion Movement in Oxide Glasses
Diffusion and Defects in Materials - 1991, Moscow, USSR, July 1991
To be sent when available.
2. Effect of Glass Preparation Method on Ionic Conduction in Sodium-Borate Glass
93rd Annual Meeting of the American Ceramic Society
(Glass & Optical Materials Division) - April 28 - May 2, 1991
Cincinnati, OHIO, U.S.A.

*Abstract reviewed,
to*

EFFECT OF GLASS PREPARATION METHOD ON IONIC CONDUCTION IN
SODIUM-BORATE GLASS⁺, W. C. Huang* and H. Jain, Dept. of Materials Sci. &
Eng., Lehigh University, Bethlehem, PA 18015-3195

It has been reported that the structure of a B_2O_3 glass depends on the temperature at which its melt is equilibrated before quenching [1]. In the present work we investigate the effect of structural differences arising from different preparation methods on ion transport. The ionic conduction and electrical relaxation of 0.3 Na_2O -0.7 B_2O_3 glass prepared by quenching the melt from different temperatures and at different cooling rates are studied. The relationship of the various preparation parameters to the structure and electrical properties will be discussed.

1. Kamitsos, E. I. & Karakassides, M. A., *Physics
Chem. Glasses* **30**(6), 235-236 (1989)

+. Work supported by U.S. Department of Energy (Grant
No. DE-FG02-90ER45419)

-- 93rd Annual Meeting of the American Ceramic Society (Glass & Optical
Materials Division), April 28-May 2, 1991, Cincinnati, OHIO

END

DATE
FILMED

6/10/92