FE-MIT-89773-8

Coal Plasticity at High Heating Rates and Temperatures

Eighth Technical Progress Report

Sarakorn Gerjarusak, William A. Peters, and Jack B. Howard

Energy Laboratory and Department of Chemical Engineering
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government, nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Submitted to the United States Department of Energy
Pittsburgh Energy Technology Center
Attention: Dr. Philip M. Goldberg

PREPARED FOR THE UNITED STATES DEPARTMENT OF ENERGY

Under Contract No. DE-FG22-89PC-89773

Date Submitted: May 1992

"US/DOE Patent Clearance is not required prior to the publication of this document."

MASTER

JUN 1 1992

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED *sp*

Abstract

The potential influence of gas bubbles on the viscosity of molten coal at elevated temperatures was estimated by calculations, using literature models for the viscosity of two and three phase suspensions. In one approach, gas bubbles in molten coal were approximated as the dispersed phase of deformable liquid globules in G. I. Taylor's model of emulsion viscosity. This model was incorporated into different models for the viscosity of solid-in-liquid suspensions, in which the dispersed solids are approximated as rigid spheres. Calculations show that in the presence of gas bubbles, the apparent viscosity of molten coal increases roughly in proportion to the volume fraction of gas with respect to the liquid continuum phase. It is experimentally and mathematically difficult to accurately determine gas volume fractions throughout the softening stage of coal pyrolysis. Our current plan is therefore to assume that the apparent viscosity of molten coal can be reasonably modeled in terms of a single liquid continuum phase and one dispersed phase consisting only of solids, using for example the two phase suspension viscosity model of Hatschek or of Frankel and Acrivos. In this approximation, gas bubble effects would force the model to underestimate metaplast concentrations and to overpredict the contribution of the dispersed solids to increase the viscosity of the liquid continuum.

Introduction

A high temperature plastometer with a new cone-shaped shearing disk is being used to measure the apparent viscosity of molten coals as affected by temperature, time, and coal type. It is generally accepted that the apparent viscosity of molten coal is related to the coal's liquid or "metaplast" inventory. In the past, the concentrated suspension of solid spheres model of Frankel and Acrivos (1967) was used to express this relationship quantitatively. Fong (1986) reasoned, in light of the works on coal carbonization by Kirov and Stephens (1967) and Szladow and Ignasiak (1976), that the coal melt is well described as a concentrated suspension of solids. However, there is a need to determine the influence on viscosity of gas bubbles generated at elevated temperature in the coal melt during pyrolysis of the coal. The reasons are to gain further insight on the mechanisms of coal plasticity at elevated temperature and if gas bubbles are important, to be sure that the mathematical expressions used to relate the viscosity of molten coal to its metaplast inventory properly reflect contributions from gas bubbles.

Models for the Viscosity of Suspensions Developed by Einstein and by Hatschek

Einstein's viscosity model for a dilute suspension of solid in liquid is:

$$\eta_{\text{rel}} = \frac{\eta}{\eta_0} = 1 + K\phi \quad (1)$$

where η_0 is the viscosity of the solid-free liquid, ϕ is the volume fraction of solid in the suspension, and the constant K depends on the shape and rigidity of the particles (e.g. $K = 2.5$ for rigid spheres) (Hauser, 1939). The Einstein model is valid when ϕ is less than 0.05. (Frankel and Acrivos, 1967, Sherman, 1968, and Van Krevelen, 1990)

For a concentrated suspension of rigid spheres in a liquid, Hatschek's viscosity model is:

$$\eta_{\text{rel}} = \frac{\eta}{\eta_0} = \frac{1}{(1 - \sqrt[3]{\phi})} \quad (2)$$

where η_0 and ϕ have the same meaning as defined above. This model is generally valid when ϕ is greater than 0.5. (Hauser, 1939 and Sherman, 1968)

These equations are the early works on which many later models are based.

The Concentrated Suspension Model of Frankel and Acrivos

Frankel and Acrivos (1967) used an asymptotic mathematical analysis of governing equations of change to derive a suspension

viscosity model similar to that of Hatschek. According to the model by Frankel and Acrivos, the effective Newtonian viscosity of a suspension of uniform solid spheres is:

$$\mu_{\text{rel}} = \frac{\mu}{\mu_0} = \frac{9}{8} \frac{\sqrt[3]{\phi/\phi_m}}{1 - \sqrt[3]{\phi/\phi_m}} \quad (3)$$

where μ_0 is the viscosity of the solid-free liquid, ϕ is the volume fraction of solids in the suspension, and ϕ_m is the maximum solid volume fraction. The most important assumption of this model is that the suspension exhibits Newtonian behavior. Based upon comparisons with experimental data, Frankel and Acrivos found that equation 3 is valid for ϕ/ϕ_m greater than 0.5 (where for randomly packed rigid spheres, ϕ_m is 0.64).

The Foam Model

One approach to assessing the role of gas bubbles in molten coal viscosity is to consider whether or not they impart foam-like behavior to the coal melt. Foams by definition are "agglomerations of gas bubbles separated from each other by thin liquid films" (Bikerman, 1973). However, to classify a suspension of gas bubbles in liquid as foams usually requires a gas volume fraction exceeding

0.75 (Heller and Kuntamukkula, 1987 and Walstra, 1989). Bikerman (1973) even suggests a gas volume fraction of 0.9 or higher to qualify gas in liquid suspensions as foams. In addition, numerous experimental observations have found that the bubble diameter of foams is typically between 0.1 mm to 3 mm (Walstra, 1989).

Experiments by Griffin (1989) suggest that the number density and size distribution of bubbles in molten coal do not match those of bubbles in typical foams. His methodology was optical microscopy of chars quenched from molten coal and the assumption that the size and number of cavities in those chars were representative of the size and number of bubbles in the molten coal just prior to quenching. His findings indicate that: 1) when bubble number density is large enough to be considered foam-like, the volume fraction gas is below 75%; and 2) if the gas volume fraction exceeds 75%, the bubble diameter is comparable to the particle diameter, but there are too few bubbles to produce a foam.

Taylor's Emulsion Model

Taylor (1932) extended Einstein's hydrodynamic treatment for dilute liquid suspensions of rigid spheres to dilute liquid suspensions of deformable globules, i.e. liquids in a liquid (Sherman, 1968):

$$\eta_{rel} = \frac{\eta}{\eta_o} = 1 + K \frac{\eta' + (2/5)\eta_o}{\eta' + \eta_o} \phi \quad (4)$$

where η_o is the viscosity of the solid-free liquid, η' is the viscosity of the fluid inside the globule, ϕ is the globule volume fraction, and the constant K depends on the shape of the particles ($K = 2.5$ for rigid spheres, $K < 2.5$ when the globule is deformable). The equation is generally valid when ϕ is less than 0.2. (Meyer, 1950 and Sherman, 1968)

Viscosity of an Emulsion with Two Dispersed Phases.

From past studies of suspensions and emulsions, one can write a general model describing the effective viscosity of a suspension or an emulsion as:

$$\eta_{o+i} = \eta_c [1 + \text{factor}(\phi_i)] \quad (5)$$

where $\text{factor}(\phi_i)$ means a factor that is a function of the quantity ϕ_i . η_{o+i} is the effective viscosity of the suspension or emulsion, η_o is the viscosity of the continuous phase free of the dispersed phase, and ϕ_i is the volume fraction of the dispersed phase i . From studies of hydrocolloids and pigment in different emulsions, the viscosity of an

emulsion with two dispersed phases (a and b) can be described based on series or parallel interactions of the constituents. In the series model, one of the dispersed phases and the continuous phase forms a new continuous phase. The new continuous phase then interacts with the remaining dispersed phase. The effective viscosity can be modeled as (Sherman, 1968):

$$\begin{aligned}\eta_{o+a+b} &= \eta_{o+a}[1 + \text{factor}(\phi_b)] \\ &= \eta_o[1 + \text{factor}(\phi_a)] \cdot [1 + \text{factor}(\phi_b)]\end{aligned}\quad (6)$$

In the parallel model, η_o remains the viscosity of the continuous phase, but that phase is considered to interact simultaneously with both dispersed phases. The effective viscosity of the suspension is modeled as (Sherman, 1968):

$$\eta_{o+a+b} = \eta_o[1 + \text{factor}(\phi_a) + \text{factor}(\phi_b)] \quad (7)$$

The difference in the two models is the extra factor of $[\text{factor}(\phi_a) \cdot \text{factor}(\phi_b)]$ in the series model which accounts for the fact that the second suspended component (here b) interacts with the first suspended component (here a) as well as the continuous phase. In general, the series model seems plausible in a suspension or emulsion which is not highly concentrated. When the continuous phase is present at very high concentration, it interacts with one of

the dispersed phases (the more dilute one) first to form a new continuous phase. The new continuous phase then interacts with the other, more concentrated, dispersed phase. The parallel model is more appropriate for a concentrated suspension or emulsion in which a continuous phase, present at lower concentration, is likely to interact with both dispersed phases simultaneously. An illustration of an emulsion/suspension with two dispersed phases is shown in Figure 1.

Whether the suspended phases are dilute or concentrated, equations 6 and 7 are best applied when the volume fraction of the continuous phase is high i.e. $\phi_0 > 0.5$. In molten coal, however, the volume fraction of the continuous phase (liquid metaplast) is generally expected to be ≤ 0.5 . It is therefore necessary to modify equations 6 and 7 before they can be confidently applied to the molten coal system.

The first step is to define the concept of relative volume fraction. When the continuous phase is not present at high concentration, its interactions with *each* of the dispersed phases are important and depend on the amount of each dispersed phase relative to the amount of the continuous phase. Thus for a suspension of two dispersants in one continuous phase it proves convenient to define a

Figure 1: An illustration of an emulsion/suspension with two dispersed phases (1 and 2). When applied to molten coal, the two dispersed phases are gas bubbles and unsoftened solids, and the continuous phase is the liquid metaplast.

volume (V) of one of the dispersed phases, i, relative to volume expressed by the continuous phase and the dispersed phase i as:

$$\phi_{io} = \frac{V_i}{V_i + V_o} = \frac{\phi_i}{\phi_i + \phi_o} \quad (8)$$

When there is only one dispersed phase $\phi_{io} = \phi_i$ because $\phi_i + \phi_o = 1$.

When the continuous phase is present at very high concentration, $\phi_o \gg \phi_i$, and ϕ_{io} is well approximated by ϕ_i .

In the series model, when the continuous phase interacts with one of the dispersed phases to form a new continuous phase, the effective viscosity of the new continuous phase depends on the volume fraction of the dispersed phase relative to the volume fraction of the original continuous phase. This is significant when the volume fractions of the two dispersed phases are vastly different. Thus for suspensions with lower concentrations of continuous phase, the volume fraction ϕ_a in equation 6 should be replaced by the volume fraction of dispersed phase a relative to the original solids free continuous phase, ϕ_{ao} :

$$\begin{aligned} \eta_{o+a+b} &= \eta_{o+a} [1 + \text{factor}(\phi_b)] \\ &= \eta_o [1 + \text{factor}(\phi_{ao})] \cdot [1 + \text{factor}(\phi_b)] \end{aligned} \quad (9)$$

The volume fraction of the second dispersed phase ϕ_b is unchanged since it already is the volume fraction of phase b relative to the new continuous phase.

In the parallel model, the continuous phase interacts simultaneously with both dispersed phases. The effective viscosity of the suspension/emulsion therefore depends on the relative volume fraction of each dispersed phase with respect to the continuous phase. Consequently, the relative volume fractions replace the corresponding volume fractions in equation 7 which becomes:

$$\eta_{o+a+b} = \eta_o[1 + \text{factor}(\phi_{ao}) + \text{factor}(\phi_{bo})] \quad (10)$$

Incorporating the Taylor Model into the Concentrated Suspension Model

In light of all the different models described, the next task is to determine which model is best suited for the coal melt during pyrolysis. The Taylor model (Meyer, 1950 and Sherman, 1968) is a potentially good choice for describing the effect of gas bubbles on the coal melt, since it can treat two different fluids -the suspending liquid and the suspended globule. Here as the first approximation, we associate the globules with the gas bubbles and assume then to

be spherical and retain their form throughout the course of the experiment ($K=2.5$).

Models for concentrated suspensions of rigid spheres such as those of Frankel and Acrivos (1967) or Hatschek (Hauser, 1939 and Sherman, 1968) can be used to describe the interaction between the liquid metaplast and the solid coal particles. The viscosity of the coal melt has been shown to be Newtonian when the shear rate is varied from 2 to 10 s^{-1} (Gerjarusak et al., 1992). Thus from the perspective of Newtonian vs. non-Newtonian behavior, the Newtonian model by Frankel and Acrivos is applicable in this range of shear rates. The difference in the relative viscosity calculated by the two models is less than 10% when the solid volume fraction (ϕ_s) is greater than 0.5 (assuming the maximum solid concentration (ϕ_{sm}) is 1.0). Since either model seems suitable, both models will be used in this report for illustrative purposes.

The next step is to determine whether the series or parallel model for a suspension/emulsion with two dispersed phases is suitable for describing the effective viscosity of the coal melt. In incorporating the Taylor model to Hatschek's or Frankel and Acrivos' concentrated suspension model:

$$\text{factor}(\phi_i) = K \frac{\eta' + 2/5\eta_o}{\eta' + \eta_o} \phi_i \quad (\text{Taylor Model, } K = 2.5) \quad (11a)$$

and since $\eta_o \gg \eta'$:

$$\text{factor}(\phi_i) = \phi_i \quad (\text{Taylor's Model, low gas concentration}) \quad (11b)$$

$$\text{factor}(\phi_i) = \frac{\sqrt[3]{\phi_i}}{(1 - \sqrt[3]{\phi_i})} \quad (\text{Hatschek Model}) \quad (12)$$

$$\text{factor}(\phi_i) = 1/8 + 9/8 \frac{2\sqrt[3]{\phi_i} - 1}{(1 - \sqrt[3]{\phi_i})} \quad (\text{Frankel and Acrivos}) \quad (13)$$

These factors are substituted into equations 6 and 7 to determine the relative viscosity of the coal melt. In the series model, the new continuous phase can be either a gas-liquid emulsion (series model I) or a solid-liquid suspension (series model II). Letting the subscript "g" denote the gas phase and the subscript "s" denote the solid phase :

$$\eta_{\text{rel}} = [1 + \text{factor}(\phi_{go})] \cdot [1 + \text{factor}(\phi_s)] \quad (\text{series model I}) \quad (14)$$

$$\eta_{rel} = [1 + \text{factor}(\phi_{so})] \cdot [1 + \text{factor}(\phi_g)] \quad (\text{series model II}) \quad (15)$$

$$\eta_{rel} = [1 + \text{factor}(\phi_{go}) + \text{factor}(\phi_{so})] \quad (\text{parallel model}) \quad (16)$$

A summary of the various viscosity models described above is in Table 1. The apparent relative viscosities for suspensions and emulsions calculated from various models are shown in Figures 2 and 3 for relative gas volume fractions of 0.05 and 0.20. Figure 4 shows the apparent viscosities calculated by the Frankel-Acrivos and Taylor parallel model as a function of solid volume fraction (ϕ_s) and relative gas volume fraction (ϕ_{go}).

Discussion of Results

In general, the models which incorporate Hatchek's concentrated suspension model give slightly lower relative viscosity values than those which incorporate the model of Frankel and Acrivos. The difference is, however, less than about 10%.

The two series models and the parallel model which incorporate the same concentrated suspension model give essentially the same results. Since the exact mechanism by which different phases interact is difficult to determine, each of these three models would seem to be of comparable value for correlating the relative viscosity of a coal melt. The viscosity determined by a concentrated

Table 1: Summary of Viscosity Models for Suspension/Emulsion

<u>Model</u>	<u>Type of System</u>	<u>Range of Predictability</u>
Einstein	Rigid spheres in liquid	ϕ of dispersed phase < 0.05
Frankel & Acrivos	Rigid spheres in liquid	ϕ/ϕ_m of dispersed phase > 0.5 , Newtonian suspensions only
Hatschek	Rigid globules in liquid	ϕ of dispersed phase > 0.5
Taylor	Deformable spheres in liquid	ϕ of dispersed phase < 0.2
Frankel- Acrivos/Taylor	Rigid spheres and deformable spheres in liquid	ϕ of rigid spheres relative to the ϕ 's of liquid and rigid spheres > 0.5 , ϕ of deformable spheres relative to ϕ 's of liquid and deformable spheres < 0.2 , Newtonian suspensions only.
Hatschek/Taylor	Rigid spheres and deformable spheres in liquid	ϕ of rigid spheres relative to the ϕ 's of liquid and rigid spheres > 0.5 , ϕ of deformable spheres relative to ϕ 's of liquid and deformable spheres < 0.2

Figure 2: Relative Viscosity vs. Solid Volume Fraction
Relative Gas Volume Fraction = 0.20

Figure 3: Relative Viscosity vs. Solid Volume Fraction
Relative Gas Volume Fraction = .05

Figure 4: Relative Viscosity vs. Solid Volume Fraction for Frankel-Acrivos and Taylor Parallel Model

suspension model alone is approximately 20 % lower than that which is determined by a model which considers two dispersed phases (with the relative gas volume fraction of 0.2, Figure 1). At a lower relative gas volume fraction (e.g. 0.05), the difference is about 5%. The Taylor models assumes that the surface tension is large enough that the fluid bubbles retain their spherical shape throughout the experiment. These spherical bubbles create "extra" resistance in the suspending liquid and thus increases the effective viscosity of the suspension or emulsion. They act similarly to rigid spheres, but their contribution to the "extra" resistance is less since they are deformable.

The above models correlate suspension viscosity with the volume fraction of a continuous phase with the volume fraction(s) of one or more dispersed phases. For molten coal one approach is to consider the dispersed phase to consist only of solids, and to estimate the volume fraction of these solids from the volume fraction of the liquid continuum (metaplast) by a material balance. Metaplast concentration must then be known or predictable for the pyrolysis conditions of interest. Direct measurements of metaplast concentrations as affected by pyrolysis conditions are not a prime focus of the present study. Kinetics parameters for predicting metaplast inventories during softening will be determined from data on apparent viscosity of molten coal as affected by temperature and

time. Metaplast kinetics models, e.g. the multiple independent parallel reaction (MIPR) model (Anthony et al., 1975), will be inputted to viscosity models and parameterized by best fitting predicted viscosities to those determined experimentally.

To account explicitly for effects of suspended solids and of gas bubbles, suspension viscosity models for molten coal require that the relative volume fraction of gas be known throughout the softening period of pyrolysis. In principle this quantity could be determined experimentally or predicted theoretically. Pertinent experiments by Griffin (1989) are noted above, and Oh (1985; et al., 1989) developed a mathematical model that predicts gas volume fractions and bubble size distributions in molten coal. However, neither approach is easy to implement. Our current plan is therefore to assume that the apparent viscosity of molten coal can be reasonably modeled in terms of a single liquid continuum phase and one dispersed phase consisting only of solids. In this approximation, gas bubble effects would force the model to underestimate metaplast concentration and overpredict the contribution of the dispersed solids to increase the viscosity of the liquid continuum.

Future Work

More experiments will be performed to determine the effect of temperature-time history on coal plasticity. The viscosity-time data will be used to determine the different parameters needed for the MIPR model of metaplast kinetics. The difference in plastic behavior of coals of different ranks will also be investigated. The goal is to obtain correlations relating the plasticity of a coal to characteristics of that coal that are relatively easy to measure or infer, e.g. fraction of labile bridges and elemental composition (Ko, 1988).

Literature Reference

Anthony, D. B., Howard, J. B., Hottel, H. C., and Meissner, H. P., "Rapid Devolatilization of Pulverized Coal," Fifteenth Symposium (International) on Combustion, pp. 1303-1317, The Combustion Institute, Pittsburgh, (1975).

Bikerman, J.J., Foams, Springer-Verlag, 1973.

Fong, W. S., "Plasticity and Agglomeration in Coal Pyrolysis, " Sc.D. Thesis, Department of Chemical Engineering, MIT, Cambridge, MA, 1986.

Frankel , N. A. and A. Acrivos, "On the viscosity of A Concentrated Suspension of Solid Spheres," Chemical Engineering Science, 22, pp. 847-853, 1967.

Gerjarusak, S., Peters, W. A., and Howard, J. B. , "Coal Plasticity at High Heating Rates and Temperatures: Seventh Technical Report to the U.S. Department of Energy," US DOE Pittsburgh Energy Technology Center, Contract No. DE-FG22-89PC-89733 (February 1992).

Griffin, T. P., "Intraparticle Secondary Reactions of Tar During Bituminous Coal Pyrolysis," Ph.D. Thesis, Dept. of Chemical Engineering, MIT, Cambridge, MA ,1989.

Hauser, E. A., Colloidal Phenomena, McGraw-Hill Book Company, 1939.

Heller J. P. and Kuntamukkula M. S., "Critical Review of the Foam Rheology Literature," Industrial Engineering and Chemical Research, 26, pp.318-324, 1987.

Kirov N. Y. and Stephens J. N., Physical Aspects of Coal Carbonisation, National Coal Research Advisory Committee, Australia, 1967.

- Ko, G. H., "Pyrolysis of Different Coal Types," Ph.D Thesis, Department of Chemical Engineering, MIT, Cambridge, MA, 1988.
- Meyer, K. H., Natural and Synthetic High Polymers, Interscience Publisher, Inc., 1950.
- Nazem, F. F., "Rheology of Carbonaceous Mesophase Pitch," Fuel, 59, pp. 851-858 1990.
- Oh, M. S., "Softening Coal Pyrolysis, " Sc.D. Thesis, Dept. of Chemical Engineering, MIT, Cambridge, MA, 1985.
- Oh, M. S., Peters, W. A., and Howard, J. B., "An Experimental and Modeling Study of Softening Coal Pyrolysis," AIChE Journal 35, 775-792, 1989.
- Sherman, P., Emulsion Science, Academic Press, 1968.
- Szladow, J. A. and Ignasiak, B. S., "Geisler Fluidities and Contents of Reactive Oxygen Groups in Caking Coals," Fuel, 55, p. 253, 1976.
- Taylor, G. I., "The Viscosity of a Fluid Containing Small Drops of Another Fluid," Proc. Roy. Soc. (London), A138, pp.41-48, 1932.
- Van Krevelen, D. W., Properties of Polymers, Third Edition, Elsevier Scientific Publishing Company, 1990.
- Walstra, P., "Principles of Foam Formation and Stability," Foams: Physics, Chemistry and Structure, A. J. Wilson, editor, Springer-Verlag, Chapter 1, 1989.

**DATE
FILMED**
8/12/92