DOE/ER/45280--T3

X-RAY SCATTERING STUDIES OF NON-EQUILIBRIUM
ORDERING PROCESSES

DOE/ER/45280--T3

Progress Report

DE92 010311

November 1, 1990 - October 31, 1991

S. E. Nagler

Department of Physics, University of Florida

Gainesville, FL 32611

Prepared for the U. S. Department of Energy

Under Grant Number DE-FG05-90ER45280

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

MAR 24 1992

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Abstract

We report on the progress of the project entitled "X-ray Scattering Studies of Non-Equilibrium Ordering Processes." The past year has seen continued progress in the study of kinetic effects in metallic binary alloys and polymers. In addition, work has begun on a low dimensional CDW system: blue bronze. A sample chamber has been constructed to perform small angle neutron scattering measurements on a model quantum system with phase separation: solid He3/He4. Work is continuing on magnetic systems. Planned future experiments include an investigation of crystallization in Rubidium.

X-ray Scattering Studies of Non-equilibrium Ordering Processes

- I. Introduction.
- II. Research Activities.
- III. Invited Lectures.
- IV. Conference Presentations.
- V. Publications.
- VI. Travel.
- VII. Personnel.
- VIII. External Support. (*Removed*)
- IX. References.
- X. Figures.
- XI. Appendices. (*Removed*)

I. Introduction

The theme of our work is the study of ordering, especially kinetics, in a variety of systems generally undergoing first order phase transitions. The irreversibility and kinetic phenomena associated with first order phase transition are nearly ubiquitous¹ and occur in such diverse systems as ceramic high-T_c superconductors, polymers, alloys, and even the large-scale structure of the universe. The related scientific questions are at the forefront of modern statistical physics, and are also important for applied areas such as processing technology. Our approach is to investigate model systems chosen for their scientific interest. These are generally studied with x-ray scattering.

II. Research Activities

Over the past year work has continued on several problems:

(1.) Block Copolymers

Our previous experiments on diblock copolymers revealed unusual universal behavior of the ordered volume fraction of ordered "mesophase" as a function of time.² The system examined is polystyrene-polybutadiene (PS-PB) in the solvent n-tetradecane, which selectively dissolves the PB only. At high temperatures the mixture is homogeneous, as the temperature is lowered the system forms "micelles", which are PS rich spheres approximately 100 angstroms in diameter. The spheres order onto a BCC lattice (lattice constant approximately 400 angstroms). The large scale ordered structure gives materials such as these special mechanical properties, and they can be a better alternative than galvanized rubber for many applications. Even though the apparent structure is complicated, our work has shown that very simple models can account for some of the major features of the ordering kinetics.

After constructing a special in-situ quenching sample cell in-house and synchrotron (NSLS) based small angle scattering measurements were made of the crystalline volume fraction as a function of time after a rapid temperature quench. Our previous results led us

data extremely well. (See figure I.) The physics is now correct, and the phenomenological growth law should apply generally not just to Block copolymers, but to any system quenched into a coexistence region. A preprint (which will be published in the issue of Physica honoring M. Fisher) is included as an appendix.

The oscillatory behavior observed in shallow quenches appears to be genuine. Experiments are planned at NSLS in the fall of 91 to explore these phenomena further.

Note that this work resulted in an invitation for Marsha Singh (former post-doc working on this project to speak at the APS 1991 Cincinnati March Meeting. The abstract of her talk is included as an appendix, along with a draft of a full paper to be submitted to Physical Review.

(2.) Cu_3Au

The binary alloy Cu_3Au is the prototypical order-disorder alloy with a first order phase transition. Our previous work has examined ordering, coarsening, and non-equilibrium scaling in this system. It is worth noting that some of the interesting phenomena discovered in these investigations has been seen in other systems too, for example the change in superlattice peak lineshape signaling the onset of coarsening is also seen in structural transitions of some organic conductors.⁴

Part of our ongoing effort has been to examine early time data (see figure 2) especially for critical slowing down effects. R.F. Shannon Jr. presented some of this work at the 1991 March Meeting (abstract enclosed in the appendices). Analysis of data taken at NSLS is under completion. The appendix contains a draft of a full paper to be submitted to Phys. Rev. B. Two others are also in preparation.

An exciting new area that is now unfolding is the application of coherent x-ray beams to the study of these problems. The first experiments examined Cu_3Au and confirmed that using a synchrotron source (beamline X-25 at NSLS in the first run) collimated by tiny (ie roughly micron-sized) pinholes one can observe "speckle" in diffraction patterns from superlattice peaks. The results have been submitted to the

to develop a picture of an intermediate state consisting of a micellar liquid (although the terminology was not used directly) and to view the formation of the ordered state as a relatively simple crystallization process occurring on a timescale very amenable to experimental measurement.

This year our understanding of the experiments has advanced a great deal. In addition to model fitting of the scattering data "Reverse Monte-Carlo" methods³ have been applied to obtain structural information in a less model dependent manner. This analysis has confirmed the basic structural picture. The previously noted universal behavior in the ordering kinetics had some rather puzzling features that are now explained. Experimental measurements of volume fractions as a function of time are usually analyzed by an "Avrami Law", where the ordered volume fraction, is given as: $X(t) = X_0(1 - e^{-kt^n})$ where t is the time after quenching, and the exponent n is characteristic of the ordering mechanism. For example, a three dimensional system with a constant nucleation rate and linearly growing domains shows $n=4$. Measurements of volume fraction can almost always be characterized by a single value of n if it is treated as an adjustable parameter. For the PS-PB system our measurements showed that this is not the case. Empirically, our data could be fitted by assuming that nucleation of the ordered regions occurred selectively on a two-dimensional defect (for example, a grain boundary surface). The problem is that the "micellar liquid" does not seem capable of sustaining such a defect.

The resolution of the problem is the fact that our quenches are into a coexistence region, and are effectively performed at constant volume. This is very unlike the usual metallurgical situation where a sample may be quenched by, say, dropping it into a bucket of ice water, a process that clearly does not have a fixed specimen volume. This may be why the correct derivation of volume fraction for a quench into a coexistence region does not seem to have appeared in the literature before. In collaboration with E. Domany the equivalent of the Avrami law was derived for this case, and seen to describe our polymer

there should be a measurable change in the superlattice peak position as the sample is cycled or anneals. We are undertaking a combined study of the defect dependence of the transport and structural properties of this process.

(4.) Solid Helium

Phase separation and spinodal decomposition have been studied in great depth in metal alloys and liquids. One aspect of the problem that has not been explored in detail is quantum effects. An interesting system from this point of view is solid helium with a mixture of ^3He and ^4He . This undergoes phase separation at low temperatures (in the vicinity of 0.1K depending on the pressure). The process has been examined using wide-angle x-ray scattering,⁶ and the kinetics have been studied by pressure measurements.⁷ We are undertaking a small angle neutron scattering study of the system in collaboration with E.D. Adams of UF and R.M. Nicklow of Oak Ridge National Laboratories (ORNL). Prof. Adams is an expert on ultra-low temperature physics and in particular solid Helium. To perform the experiments it has been necessary to build a special cell which will fit in the ORNL neutron scattering dilution refrigerator. The cell has been built at UF (see figure 4). It incorporates a gas handling system to create the He mixture, and allows for "quenches" by applying pressure (typically 20–30 atmospheres are required). At the present time the ORNL dilution refrigerator is out of commission, but it is expected that it will be operational by the fall and we hope to carry out measurements in the coming year.

(5.) Magnetic X-ray Scattering

Last year we began magnetic x-ray scattering measurements at NSLS. The f-electron system UPd_3 was chosen to see if magnetic x-ray scattering could resolve the paradox of the systems's low temperature phase transition. The experiment did not detect magnetic scattering, and at the present time the reasons for this are unknown. The problem is still under investigation. In the meantime we have determined that materials with 5d magnetic electrons would be favorable for study by this still developing technique,

journal "Nature" (preprint appended). This opens up the possibility of studying critical dynamics in a completely new manner analogous to that used in dynamic light scattering: measuring the time auto correlation function of the scattering in the peak. This may turn out to be an important area of research at future state of the art synchrotron sources, such as the Advanced Photon Source, and, among other applications, allow for the study of mutiscaling fluctuations in ordering kinetics.

(3.) $K_{0.3}MnO_3$ (Blue Bronze)

Blue Bronze is a typical quasi-one dimensional charge-density wave (CDW) system, with a Peierls transition to the CDW state at $T=180K$ in the absence of an electric field. The CDW is signaled in a scattering experiment by the presence of superlattice peaks at incommensurate positions. There is not much understood about the kinetics of incommensurate systems in general and CDW systems are an obvious choice for studying non-equilibrium behavior. At low temperatures the application of an electric field leads to well known nonlinear effects and irreversibility in measured quantities such as resistivity. At the same time the superlattice peaks broaden and shift. The time scales for the structural response are of the order of seconds, allowing for the study of kinetics in this incommensurate system using time-resolved x-ray scattering techniques. Figure 3 shows an example of some preliminary "in-house" data obtained with a blue-bronze single crystal. The work is being carried out with S.E. Brown at UF who synthesized the materials and is an expert in transport measurements, which are made in-situ simultaneously with the X-ray measurements.

Blue bronze can be doped with known concentrations of impurities via irradiation with electrons, and the resulting samples have a remarkable hysteresis in the resistivity-temperature curve.⁵ The temperature in the center of the loop (typically 100K) as well as the amount of irreversibility depend on the defect concentration. Annealing in the center of the loop for several hours leads to a reversible equilibrium state. A simple model of the system suggests that the CDW wavevector and resistivity are coupled, and

and ultimately we would hope to look at these materials in a time resolved fashion. The principal advantages over neutron scattering are the greatly improved Q resolution (necessary for determining domain sized), the ability to use relatively small crystals, and the possibility of separating not only the "charge" and "magnetic" scattering cleanly by polarization techniques (with the x-rays), but also the "spin" and "orbital" components of the magnetic scattering. The first system we have chosen to study is K_2ReCl_6 , which has a transition to an anti ferromagnetic state around 8K. A crystal has been acquired and time requested at NSLS for the experiment.

(6.) Crystallization in Rubidium

The crystallization process is of fundamental importance in understanding the micro structures of materials. Our work on block copolymers has been a study of crystallization in an unusual context. Metals such as Rubidium come to mind as simple systems in which to study these phenomena. In collaboration with R. McGreevy of Oxford University, who has a longstanding program studying the equilibrium structure of Rb and related materials with neutron diffraction, a time-resolved x-ray experiment is being planned. The Rb can be easily melted by running a current through a ribbon shaped sample (enclosed in Nb foil), and quenched rapidly by shutting off the current. Most of the measurements should be obtainable with the UF rotating anode facility.

(7.) Other Related Activities

A brief synopsis of other activities that may relate to, but have not been supported by this project:

I Advanced Photon Source (APS)

I have headed the Florida effort to develop a portion of APS sector as part of a collaborating access team (CAT). After submitting a letter of intent which was received favorably, the Florida group united with researchers at Northwestern University (P. Dutta), Notre Dame (B. Bunker), Illinois Institute of Technology (T. Morrisson) and Amoco Research (J. Faber) to form a group called MRCAT. A proposal to develop the

sector was submitted in March of 1991 and is pending.

II Neutron Scattering on Low-dimensional Magnetic Systems

For much of the past academic year I was a visitor with R.A. Cowley at the Clarendon Labs, Oxford University. During this time I began a study of excitations in quantum magnetic chains using pulsed neutron scattering at the Rutherford Appleton Laboratories in the UK. The results have shown that pulsed neutrons and chopper spectrometers are excellent for measuring excitations in low dimensional systems. I hope to follow up on this work in the future, possibly using the new chopper spectrometer under construction at LANSCE. (A preprint of an article submitted to Phys. Rev. B. is enclosed for informational purposes.)

III. Invited Lectures

Since the last reporting period several invited lectures have been given on the work supported by this award:

By S.E. Nagler:

Clarendon Labs, Oxford University

James Franck Institute, University of Chicago

Department of Physics, Keele University

By M.A. Singh:

Invited talk at APS 1991 March Meeting, several other colloquia.

IV. Conference Presentations:

APS 1991 March Meeting in Cincinnati had an invited presentation by M.A. Singh and a contributed talk by R.F. Shannon, Jr.

V. Publications:

E. Domany and S.E. Nagler "Nucleation and Growth in the Co-existence Region"
Accepted in Physica.

M. Sutton, S.G.J. Mochrie, T. Greytak, S.E. Nagler, L.E. Berman, G.A. Held and
G.B. Stephenson "The Observation of Speckle by Diffraction with Coherent X-Rays"
submitted to Nature.

Published Abstracts:

Bull. American Physical Society 36, 379 (1991).

Bull. American Physical Society 36, 428 (1991)

See also the enclosed preprints, which are about to be submitted to Physical
Review.

VI. Travel:

One person travelled to the March Meeting. There are also travel costs to BNL,
and expected to ORNL.

VI. Personnel:

Personnel supported by this program during the past year include:

S.E. Nagler, PI

J. Zhang, graduate student

R.F. Shannon Jr., postdoctoral fellow

C.R. Harkless and R.F. Shannon, Jr. both received the Ph.D. degree at the end of
1990. Harkless now works for Xontech Corporation in Van Nuys, CA. Shannon remained
at UF for this year as a postdoc and is taking a position next year at Queen's University as
a Visiting Assistant Professor.

V. Lane, who is supported by a minority fellowship, also worked on the project. It
is expected that another graduate student will join in the autumn.

IX. References:

1. J.G. Gunton, M.S. Miguel and P.S. Sahni in "Phase Transitions and critical Phenomena" ed. by C. Domp and J. Lebonitz (Academic, NY, 1983) Vol. 8, Pg. 267.
2. C.R. Harkless et.al. Phys. Rev. Lett. 64, 2285 (1990).
3. R.L. McGreevy, M.A. Howe, D.A. Keen and K.N. Clausen, Clarendon Laboratory Preprint #OUCL 90/03 (1990).
4. J.P. Pouget et.al. J. Phys. Soc. Japan 59, 2036 (1990).
5. H. Mutka et.al. J. Physique 48, 425 (1987).
6. S.N. Erlich, Ph.D. Thesis, Univ. of Illinois, 1986.
7. P.N. Henriksen, M.F. Punczyk and E.D. Adams, Sol. State Comm. 8,735.(1970).

X. Figures:

Figure 1 Block Co-polymer scattering intensity vs. time. The intensity is proportional to the crystalline volume fraction. The Avrami curve is the best fit to conventional theoretical models of nucleation and growth. The co-existence curve is a fit to the new theory we have derived.

Figure 2 Log-Log plot of the superlattice peak width in Cu_3Au vs. time after quenching. The different regions are characteristic of the nucleation, ordering, and coarsening processes.

Figure 3 Superlattice peak in Blue Bronze at different times following the application of an electric field.

Figure 4 Pressure quenching sample cell for small angle neutron scattering study of solid $^3\text{He}/^4\text{He}$. The cell has been built at UF and will be installed in a dilution refrigerator at ORNL.

Figure 1

Figure 2

5th.dat

Figure 3

Figure 4

suddenly changed. Here we present results for three types of quenches: re-equilibration of short-range order within the disordered (B2) phase; re-equilibration of short- and long-range order within the ordered (DO₃) phase; and evolution of short-range order into long-range order following a quench from the disordered to the ordered phase. The short-range order is characterized by the diffuse peak intensity I_{DIFFUSE} and correlation length ξ ; the long-range order is characterized by the Bragg intensity I_{Bragg} . For quenches within the disordered phase, I_{DIFFUSE} and ξ both relax exponentially at the same rate. The temperature dependence of the relaxation rate shows critical slowing-down close to the critical temperature. For quenches within the ordered phase, I_{DIFFUSE} and ξ do not show simple exponential relaxation. Instead, coarsening of short-range order into long-range order is seen, as in quenches from the disordered phase into the ordered phase.

9:00

A354 Intermediate Stage Kinetics of an Order-Disorder Transition. R. F. Shannon, Jr, C. R. Harkless, S. E. Nagler, University of Florida; G. B. Stephenson, J. L. Jordan-Sweet, IBM T.J. Watson Research Ctr. Kinetics of the order-disorder transition in Cu₃Au have been studied using time-resolved synchrotron x-ray scattering, with a time resolution of one second. The growth of an ordered domain is found to obey a power law. For quenches within 20K of T_c the main ordered peak at [0,1,0] is surrounded by satellites approximately at [0,0.9,0] and [0,1.1,0]. These satellites exist only during the growth stage, first growing in intensity as the main peak rapidly develops, but as the intensity of the main peak saturates the satellites decay.

*Supported by U.S. DOE under Award No. DE-FG05-89ER45280.

9:12

A355 ²⁷Al NMR Study of the Martensitic Transformation in Ni-Al Alloys. F. BORSA J. ZIOLO and D.R. TORGESON, Ames Laboratory* and Iowa State U. -- ²⁷Al NMR line shape, Knight Shift, spin-lattice, T_1 , and spin-spin, T_2 , relaxation rates, have been measured as functions of T for two Ni-Al alloys undergoing martensitic phase transition (MPT) from bcc to monoclinic phase. Several specimens of each of the compositions Ni₄₂Al₅₈ and Ni₄₂Al₅₈ having different particle sizes and heat treatments have been studied. ²⁷Al spectrum is composed of a symmetrical 22 kHz central line superimposed on a wide distribution of satellite transitions 120 kHz wide. The MPT produces a smooth continuous change of the ²⁷Al Knight shift of 0.067% at M_s to 0.058% at M_f . No change of width or shape was detected in the temp range M_s to M_f . T_1 depends linearly on T with a small slope change above M_s and below M_f as expected, but no anomaly is present between M_s and M_f . Temp M_s was sensitive to particle size, shifting from 320 to 260K for Ni₄₂Al₅₈ for particle sizes 1 μm to 10⁻³ μm respectively.

*Operated for the USDOE by Iowa State University under contract No. W-7405-Eng-82.

9:24

A356 Discussion

9:36

A357 Kinetics of quenched systems with long-range repulsive interactions CHRISTOPHER ROLAND, RASHMI DESAI, University of Toronto -- The kinetics of a quenched system with a nonconserved order parameter having both an attractive and a long-range repulsive interaction (specifically for a uniaxial ferromagnetic film) is studied. The presence of the repulsive interaction leads to the formation of periodically modulated structures. For various physical situations, the kinetics is studied through numerical integration of the appropriate Langevin equation. For the case of a system in zero external field and at zero temperatures, we have constructed a dynamical theory based on a singular perturbation expansion. The theory compares well with the results of the numerical integration.

9:48

A358 Phase Separation During Vapor Deposition of Al-Ge Films. C. D. ADAMS, M. ATZMON, Y.-T. CHENG* and D. J. SROLOVITZ, University of Michigan. The microstructure and surface morphology of phase separated vapor deposited Al-Ge films have been studied as a function of deposition temperature. The experimental results are modeled and analyzed in terms of surface diffusion as the mechanism of phase separation, and an activation energy for surface interdiffusion of 0.36 eV/atom is obtained. When the film thickness is varied, a transition from lateral to transverse phase separation is observed, and shown to be driven by the competition between surface and interfacial energies.

* Supported by NSF Grant DMR-8820285.

** General Motors Research Laboratories.

10:00

A359 Growth and Structure Characterization of a Pb Overlayer on Cu(100). WEI LI^a, J.S. LIN^a, M.KARIMI^b, G. VIDALI^a, a: Syracuse University; b: Alabama A&M University. -- Atom beam scattering (ABS), LEED and Auger Electron Spectroscopy (AES) have been used to study the growth and the structure of a Pb overlayer on Cu(100) with substrate temperatures between 140K and 450K. At 150K adsorption temperature, we observed that Pb grows in a Simultaneous Multilayer mode after completion of the first layer, while Stranski-Krastanov growth is obtained for adsorption at room temperature or higher. The first layer adsorbed at 150K is an ordered partially commensurate phase. Our structural model for this phase shows that it has a $(5 \times 5)R_{45}^{-1}(\frac{1}{2})$ symmetry with superstructure buckling¹. We characterize Pb growth by measuring the ABS specular intensity vs Pb coverage, and we analyze these results using the kinematic approximation for the scattering from adsorbates. Ongoing phase transition studies will also be presented.

1. Wei Li, J.S.Lin, M.Karimi, C.Moses and G.Vidali, Appl. Surf. Sci., in press.

*Supported by NSF grant DMR 8802512

10:12

A3510 Discussion

XI. Appendices:

(preprints sent to Smith only)

END

**DATE
FILMED
5/05/92**