2

**TECHNICAL PROGRESS REPORT
TO THE DEPARTMENT OF ENERGY**

Title: Measurements of Crystal Growth Kinetics at Extreme Deviations from Equilibrium

Award #: DE-FG02-89ER45401

Period of Award: 1 September 1992 - 31 August 1993

Grantee: President & Fellows of Harvard College
Office for Sponsored Research
Holyoke Center, Room 440
1350 Massachusetts Avenue
Cambridge MA 02138

P.I.: Michael J. Aziz
Professor of Materials Science
Division of Applied Sciences
Harvard University
29 Oxford St.
Cambridge MA 02138
(617) 495-9884

RECEIVED
JUN 07 1993
OSTI

Date: May 7, 1993

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED
yes

ABSTRACT

We have measured solute trapping of Sn in Al over a wide enough range of velocities to make a quantitative test of theory. The Continuous Growth Model of Aziz is the only one-parameter model that fits the data. We have also measured the diffusive speed - the growth rate at which interfacial partitioning is in mid-transition between equilibrium partitioning and complete solute trapping - for several solutes in Al. We have found an inverse correlation between the equilibrium partition coefficient and the diffusive speed. Taken together, these results give us heretofore unprecedented predictive capability in modeling rapid solidification processing. We have also examined theoretically short-range diffusion-limited growth, characteristic of incomplete solute trapping, and interface-limited growth, characteristic of complete solute trapping, in alloy solidification and have shown that the two regimes fall naturally out of a single unified theory of solidification.

RESEARCH PROGRESS FOR 1992-93

We have made the world's first measurements of solute trapping in metallic systems. This is much more difficult than our experiments in silicon because the resistance change on melting is so much smaller in metals. But it is quite important to get data in metals. In contrast to silicon, where the change in structure from a covalent solid to a metallic melt is a theorist's nightmare, in metals we are getting to the point where first-principles calculations of the structure and properties of the crystal-melt interface are possible. Such calculations can already be done in fcc and hcp metals with the embedded-atom method (though it is not first-principles, it is less phenomenological than the simple "continuous growth model"). Additionally, the main technological applications of rapid

solidification are in metallic alloys. Solute trapping is responsible for many of the improvements in properties of RSP alloys. Until now, however, how fast one must solidify in order to trap solute, how rapidly solute trapping "turns on" with increasing growth rate, and whether solute trapping could be understood in the same way as in silicon, have been unknown. Whenever a composition change has been made, the inclusion of a new alloying element has been considered, or a change in the RSP process has been contemplated, the metallurgical community has been making assumptions about how solute trapping will behave guided solely by our measurements in silicon.

We have measured the velocity-dependence of solute trapping of Sn in Al over the range 1-5 m/s. Sn is the best solute in Al for this purpose because the largest disagreement between the various models is in the low partition coefficient regime and Al(Sn) has a low equilibrium partition coefficient. Originally, we varied the regrowth velocity by preheating with a CO₂ laser for a few seconds prior to pulsed laser melting. However, the relatively long period spent at high temperatures during post-solidification cooling (seconds, as opposed to microseconds which is typical of non-preheated samples) promoted solid-phase diffusion, which obscured the post-solidification composition depth profile. Consequently, we varied the solidification velocity by varying the thickness of the SiO₂ insulator layer that lay underneath the sample, from 66 nm to 1 μ m. This layer controls the rate of heat flow out of the solidifying alloy layer. With modest amounts of CO₂ heating in addition to the layer thickness variation, a sufficient velocity range could be covered to make an experimental test of the various solute trapping theories.

As shown in Fig. 1, the Continuous Growth Model (CGM) of Aziz is the only one-parameter model that fits the data. The three-level Baker/Cahn model, which postulates an energy level for solute atoms adsorbed at the interface (its binding energy becomes a second free parameter in addition to the diffusive speed, which is a free parameter in all models), can also fit the data. The Aperiodic Stepwise Growth Model (ASGM) of Goldman and Aziz, another two-parameter model (not shown), also fits the velocity-dependence data. Its predicted velocity-dependence is virtually indistinguishable from the CGM; an orientation-dependence experiment would permit us to

distinguish between CGM and ASGM. Because in all models the partition coefficient is a function of the dimensionless ratio v/v_D (v : interface speed; v_D : diffusive speed), the effect of varying the free parameter v_D , when the velocity is plotted on a log scale as in Fig. 1, is a rigid shift of the curve to the left or right with no change in slope. Hence the Stepwise Growth Model (SGM) of Aziz and the two level Baker/Cahn model rise too steeply with velocity to fit the data. Sufficient differences exist between the CGM and the three-level Baker/Cahn model at low speeds that a measurement should be able to distinguish between them.

Figure 1. Dependence of the partition coefficient on solidification velocity for 0.2 at/o Sn in Al. The Continuous Growth Model of Aziz is the only one-parameter model that fits the data.

By making a single measurement of the nonequilibrium partition coefficient at intermediate velocity for several alloying elements in Al, we have been able to look for correlations between the inferred diffusive velocity and a series of more readily measured physical properties of the alloy system. This is important because there are very few alloy systems in which a measurement of the diffusive speed will ever be possible, and for most commercially important alloys a measurement will not be possible. Hence, the development of a way to make predictions (or, more realistically, to make "educated guesses") of the diffusive speed has been one of the main goals of our work. Solute trapping has been measured for Sn, Ge, Cu, and In in Al. We looked for correlations between the diffusive speed in these systems and (1) the equilibrium partition coefficient k_e , (2) the solute diffusivity D_L in the bulk liquid, (3) the solute diffusivity D_S in the solid at the melting

point, (4) the maximum equilibrium solubility limit of solute in Al, and (5) the geometric mean of D_L and D_S . The only positive correlation that we found was an inverse one with k_e , as shown in Table I.

System	k_e	v_D (m/s)
Al-Sn	0.0047	36
Al-In	0.0096	38
Al-Ge	0.055	6.1
Al-Cu	0.15	6.7

Evidently, the more the alloying element "wants" to remain in the liquid (lower k_e), the faster you must go in order to trap it into the solid (higher v_D). While this makes sense intuitively, it is not consistent with currently accepted theories. The theories will have to be reexamined in light of this new information.

In a theoretical development, we have demonstrated that both short-range diffusion-limited growth (sluggish crystal/melt interface) and collision-limited growth (highly mobile crystal/melt interface) are natural consequences of a single theory of solidification. It has been known for some time that many pure metallic elements exhibit collision-limited growth: a vanishingly small activation barrier to interface motion and a correspondingly high interface mobility that is proportional to the speed of sound v_s . And for the growth of ordered intermetallic compounds, or disordered alloys solidifying slowly enough that substantial partitioning of solute was occurring, growth was short-range diffusion-limited: a barrier to interface motion similar to the barrier to interdiffusion, and a much more sluggish interface whose mobility is proportional to the diffusive speed, v_D . Because v_D is typically a few meters per second and v_s is typically a few kilometers per second, three orders of magnitude in mobility separate these growth regimes. It has been presumed that alloys solidifying so rapidly that virtually complete solute trapping was occurring would also exhibit collision-limited growth. How pure does the alloy have to be, or how much

solute trapping or disorder trapping (for intermetallic compounds) must occur, in order to exhibit collision-limited growth? Bill Boettinger (NIST) and I derived the answer by starting with the collision-limited growth equation for all cases, and considering the interface mobility while taking proper account of the reduced free energy of the supersaturated solid being formed during rapid solidification. When this is done, v_D enters through the solute trapping or disorder trapping function and automatically replaces v_s in the resulting interface mobility. En route to this discovery, we developed simple analytical expressions for the velocity-undercooling function of the crystal/melt interface during dilute alloy solidification for the CGM both with and without solute drag. These simple expressions will be used frequently by the solidification community in dealing with rapid solidification of dilute alloys when the thermodynamic functions of the supersaturated solid and liquid phases are unavailable.

2. PUBLICATIONS SUPPORTED BY GRANT

Patrick M. Smith and Michael J. Aziz, "Solute Trapping in Metals", to be published in Materials Research Society Symposia Proceedings **279**, in press (1993).

W.J. Boettinger and M.J. Aziz, "On the Transition from Short-Range Diffusion-Limited to Collision-Limited Growth in Alloy Solidification", submitted to Acta Metall. Mater.

3. PERSONNEL SUPPORTED BY GRANT

Michael J. Aziz, professor (part-time summer salary).

Patrick M. Smith, Ph.D. student; graduated summer 1992. Remained here as post-doc through fall 1992. Currently a postdoc at Lawrence Livermore National Laboratory.

David E. Hoglund, fourth year Ph.D. student; expected graduation summer 1994.

We anticipate taking on a new student this year to replace Smith.

END

DATE
FILMED
7/9/93