ENHANCEMENT OF SURFACE PROPERTIES FOR COAL BENEFICIATION

Final Report

By
S. Chander
F. F. Aplan

January 30, 1992

Work Performed Under Contract No. FG22-88PC88934

For
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania

By
The Pennsylvania State University
University Park, Pennsylvania

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

DOE/PC/88934--T11

DE92 011276

ENHANCEMENT OF SURFACE PROPERTIES FOR COAL BENEFICIATION

Final Report for
DOE Grant No. DE-FG22-88PC88934

Submitted to

The U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10904
Pittsburgh, PA 15236

by

S. Chander and F. F. Aplan

The Pennsylvania State University
115 Mineral Sciences Building
University Park, PA 16802

January 30, 1992

TABLE OF CONTENTS

	<u>Page</u>
COVER SHEET	i
TABLE OF CONTENTS	ii
LIST OF FIGURES	vi
LIST OF TABLES	xiii
ACKNOWLEDGEMENTS	xv
EXECUTIVE SUMMARY	xvi
 PART I. COLLECTORLESS FLOTATION OF PYRITE	 1
ABSTRACT	1
INTRODUCTION	1
EXPERIMENTAL MATERIALS AND METHODS	6
EXPERIMENTAL RESULTS AND DISCUSSION	6
Cyclic Voltammetry	6
Galvanostatic Polarization	16
Solution Analysis	26
Contact Angles	26
Impedance Spectroscopy	32
Flotation Tests	38
SUMMARY	38
REFERENCES	43
 PART II. MODULATION OF PYRITE AND COAL HYDROPHOBICITY	 45
 PART II-A. A COMPARATIVE FLOTATION OF COAL-SOURCE AND ORE SOURCE PYRITES	 45
ABSTRACT	45

TABLE OF CONTENTS

(Cont'd.)

	<u>Page</u>
INTRODUCTION	45
EXPERIMENTAL MATERIALS AND METHODS	47
Pyrite Samples	47
Reagents	47
Flotation Procedure	50
EXPERIMENTAL RESULTS AND DISCUSSION	50
Ore-Source Pyrite	50
Comparative flotation of ore-source pyrites	56
Coal-Source Pyrite	58
Comparative flotation of coal-source pyrites	66
Comparison of Figure II-6 (ore-source pyrites) with Figure II-12 (coal-source pyrites)	66
Effect of pH	67
Other Collectors	67
The Effect of Oil on Pyrite Flotation	67
The Influence of Oxidation on the Natural Floatability of Pyrite ..	70
SUMMARY	72
REFERENCES	75
 PART II-B. REACTION PRODUCTS FROM COAL-SOURCE PYRITE	
OXIDATION	77
ABSTRACT	77
INTRODUCTION	77
EXPERIMENTAL MATERIALS AND METHODS	79
EXPERIMENTAL RESULTS AND DISCUSSION	81
Development of a Rapid Pyrite Oxidation Procedure	81
Identification of Reaction Products	81

TABLE OF CONTENTS

(Cont'd.)

	<u>Page</u>
SUMMARY	92
ACKNOWLEDGEMENTS	92
REFERENCES	93
 PART II-C. ADSORPTION OF POLYSACCHARIDES AND SIMILAR COMPOUNDS ONTO PYRITE AND COAL	 94
ABSTRACT	94
INTRODUCTION	94
EXPERIMENTAL MATERIALS AND METHODS	95
EXPERIMENTAL RESULTS AND DISCUSSION	97
Effect of Polymer Structure	104
SUMMARY	111
REFERENCES	113
 PART III. EMULSION PROCESSES AND PRINCIPLES	 114
ABSTRACT	114
INTRODUCTION	114
EXPERIMENTAL MATERIALS AND METHODS	117
Material Description and Sample Preparation	117
Apparatus	117
Liquid-Liquid Separation	117
Emulsification in the Presence of Fine Particles	118
Procedure	118
Liquid-Liquid Separation Method	118
Emulsification in the Presence of Fine Particles	121
Analysis	122

TABLE OF CONTENTS

(Cont'd.)

	<u>Page</u>
Emulsion Type	122
EXPERIMENTAL RESULTS AND DISCUSSION	122
Liquid-Liquid Separation	122
Kinetics of Emulsification in Multi-Phase System	132
SUMMARY	136
REFERENCES	141
 PART IV. EVALUATION OF COAL HYDROPHOBICITY	 142
ABSTRACT	142
INTRODUCTION	142
EXPERIMENTAL MATERIALS AND METHODS	143
EXPERIMENTAL RESULTS AND DISCUSSION	146
SUMMARY	157
REFERENCES	158
LIST OF PAPERS AND PUBLICATIONS	160

LIST OF FIGURES

		<u>Page</u>
Figure I-1.	The conditional Eh-pH diagram of pyrite-EDTA-H ₂ O system. Various concentrations were $[\text{Fe}]_T = [\text{S}]_T = 10^{-3} \text{ M}$ and $[\text{EDTA}]_T = 2 \times 10^{-3} \text{ M}$	
Figure I-2.	The voltammograms of pyrite in various solutions. The scan, at a rate of 20 mV/sec. was started from 0.24 V, and went to the cathodic direction initially	7
Figure I-3.	The voltammograms of pyrite in air saturated 0.1 M sodium tetraborate + 0.1 M EDTA solution. (a) At various oxidation switching potentials; (b) At various reduction switching potentials	8
Figure I-4.	The pH versus concentration of EDTA in 0.1 M air saturated sodium tetraborate solution	10
Figure I-5.	The voltammograms in nitrogen saturated 0.1 M sodium borate + 0.1 M EDTA solution. (a) platinum electrode, (b) platinum and pyrite electrodes in the solution with 0.001 M ferrous ammonium sulfate addition	11
Figure I-6.	The voltammograms of pyrite in 0.1 M sodium tetraborate + 0.1 M EDTA solution saturated with nitrogen or air	12
Figure I-7.	The voltammogram of pyrite in the nitrogen saturated 0.1 M sodium borate, 0.1 M EDTA, and 1.0 mM ferrous ammonium sulfate solution. The solution was stirred during the measurement	14
Figure I-8.	The voltammograms of pyrite in air saturated 0.1 M sodium borate solution with different reagent additions	15
Figure I-9.	The voltammograms of pyrite in nitrogen saturated 0.1 M sodium borate + 0.1 M EDTA solution with various amounts of $\text{Fe}(\text{NH}_4)\text{SO}_4$ additions	17
Figure I-10.	Dependence of the peak current and peak potential, respectively, on the scan rate for pyrite electrode in air saturated 0.1 M sodium borate + 0.1 M EDTA solution	18
Figure I-11.	The galvanostatic polarization curves for a pyrite electrode in various solutions at pH 9.3. The anodic current was kept as a constant of $4 \mu\text{A}/\text{cm}^2$ and the solutions were nitrogen saturated	19

LIST OF FIGURES

(Cont'd.)

	<u>Page</u>
Figure I-12. The galvanostatic curves of pyrite in the nitrogen saturated 0.1 M sodium borate + 0.1 mM EDTA (solid line), or 0.1 M EDTA (dotted line) solution. The anodic current was $4 \mu\text{A}/\text{cm}^2$. The dashed line represents the contact angles of pyrite measured during the galvanostatic treatment in 0.1 mM EDTA solution	20
Figure I-13. The galvanostatic polarization curves for pyrite in air saturated solutions with different EDTA concentrations. The anodic current was $4 \mu\text{A}/\text{cm}^2$	23
Figure I-14. The galvanostatic polarization curves for pyrite in the air saturated solutions with different pH values. The anodic current was $4 \mu\text{A}/\text{cm}^2$	24
Figure I-15. The dependence of open circuit potential of pyrite electrode on EDTA concentration. The electrode was pre-treated by passing $40 \text{ mC}/\text{cm}^2$ of galvanostatic anodic charge	25
Figure I-16. The voltammograms of pyrite after different extent of galvanostatic treatments. The solution was nitrogen saturated 0.1 M sodium borate +0.1 M EDTA	27
Figure I-17. The UV spectrum of the 0.1 M sodium borate +0.1 M EDTA solution treated with pyrite. The conditioning period was 17 hours	28
Figure I-18. The contact angles of pyrite measured in the various solutions under the potentiostatic mode. The data were taken after the potential was applied for 2 minutes	30
Figure I-19. The contact angles of pyrite versus the EDTA concentration. They were measured after $2.16 \text{ mC}/\text{cm}^2$ anodic charge passed through the electrode	31
Figure I-20. The impedance spectra of the pyrite electrode in the solutions with various amounts of EDTA. The solution was nitrogen saturated. The discrete symbols are the experimental data whereas the lines are the calculated spectra	35
Figure I-21. An equivalent circuit model for pyrite/solution interface. Z_w is Warburg impedance and σ is the coefficient of Warburg impedance. Other quantities are defined in the table given above	36

LIST OF FIGURES

(Cont'd.)

	<u>Page</u>
Figure I-22. The flotation recovery of pyrite as a function of pH of conditioning. The 1 gram of 65x100 mesh pyrite powder was preconditioned with -200 mesh quartz at a certain pH. After 30 minutes, the quartz was washed out with distilled water. The flotation was carried out in a Hallimond tube with a 130 mL distilled water and 1 gram pyrite sample; the gas flow rate was 55 mL/min.	39
Figure I-23. The flotation recovery of pyrite as a function of pH of conditioning in 0.01 M EDTA. A 1 gram sample of 65x100 mesh pyrite was preconditioned with 5 grams of -200 mesh quartz at the desired pH. After 30 minutes, the quartz was washed with the distilled water. The flotation was carried out in a Hallimond tube with a 130 mL water and 55 mL/min gas flow	40
Figure I-24. The flotation recovery of pyrite as a function of the amount of quartz. The solution contained various amount of EDTA. The 1 gram of 65x100 mesh pyrite powder was preconditioned with certain amount of -200 mesh quartz at pH 4.6. After 30 minutes, the quartz was washed out with the distilled water. The flotation was carried out in a Hallimond tube with a 130 mL water and 55 mL/min gas flow . . .	41

LIST OF FIGURES

(Cont'd.)

	<u>Page</u>
Figure II-1. Flotation of Peru ore pyrite (P-8) with various xanthates	51
Figure II-2. Flotation of Manora, Que. Ore pyrite (P-22) with various xanthates	52
Figure II-3. Flotation of Mexico oil pyrite (P-24) with various xanthates	53
Figure II-4. Flotation of Rico, CO ore pyrite (P-23) with various xanthates . . .	54
Figure II-5. Flotation of Black Hills, SD ore pyrite (P-25) with various xanthates	55
Figure II-6. Effect of xanthate alkyl chain length on the flotation of various ore-source pyrites	57
Figure II-7. Flotation of anthracite wall (P-1) and seam (P-2) coal pyrite with various xanthates	59
Figure II-8. Flotation of Pittsburgh seam coal pyrite, (P-5) (Osage, WV) with various xanthates	60
Figure II-9. Flotation of Pittsburgh seam coal pyrite (P-11) (Greene Co., PA) with various xanthates	61
Figure II-10. Flotation of KY #1 coal pyrite (P-7) with various xanthates	62
Figure II-11. Flotation of Lower Kittanning coal pyrite, (P-10) (Clarion, Co.) with various xanthates	63
Figure II-12. Effect of xanthate alkyl chain length on the flotation of various coal-source pyrites	64
Figure II-13. Effect of pH on the flotation of Pittsburgh seam coal pyrite (P-5) with various xanthates	68
Figure II-14. Effect of pH on the flotation of several ore-source pyrites with amyl xanthate (2×10^{-6} M)	69
Figure II-15. Effect of No. 2 fuel oil on the flotation of several coal- and ore-source pyrites	71
Figure II-16. Effect of oxidation on the natural floatability of several coal- and ore-source pyrites	73

LIST OF FIGURES (Cont'd.)

	<u>Page</u>
Figure II-17. Metavoltine on Pocahontas No. 3 raw coal (X25)	85
Figure II-18. Halotricnite on Pocahontas No. 3 raw coal	85
Figure II-19. Colorless fibers of Rozenite on Pittsburgh (P-11) pyrite (X25)	86
Figure II-20. White form of Rozenite with a few colorless fibers in the upper left of the photo. Same pyrite as in Figure II-19 above (X25)	86
Figure II-21. Rozenite (amorphous to the naked eye) on Pittsburgh (P-11) pyrite (X25)	87
Figure II-22. Szomolnokite and gypsum crystallized from washings of Lower/Middle Kittanning (P-4) pyrite (X230)	87
Figure II-23. Gypsum growths on Pittsburgh seam (P-5) pyrite (X373)	88
Figure II-24. Gypsum growths promoted by immersing P-5 pyrite in 0.1 M CaCl ₂ prior to oxidation (X373)	88
Figure II-25. Gypsum crystal formed on refuse from Doverspike Preparation Plant. Iron sulfate growth on top of gypsum crystal (X800)	89
A. SEM micrograph	B. Ca Map
C. Fe Map	D. S Map
Figure II-26. Growth on KY No. 11 pyrite (P-7) (X800)	90
A. SEM micrograph	B. Ca Map
C. Fe Map	D. S Map
Figure II-27. Same sample and location as in Figure II-15 (X800)	91
A. SEM micrograph	B. Si Map
C. Mg Map	
Figure II-28. Hydroxyl group configurations in polysaccharides	100
Figure II-29. Structures of natural and modified starches	101
Figure II-30. Structures of some other polysaccharides	102

LIST OF FIGURES

(Cont'd.)

	<u>Page</u>
Figure II-31. Adsorption of starches on coal and pyrite at pH 7	109
○ - pyrite	
● - coal	
□ - average	
Figure II-32. Adsorption of guar gums on coal and pyrite at pH 7	110
○ - pyrite	
● - coal	
□ - average	
Figure III-1. A schematic representation of various stages in liquid-liquid separation process	115
Figure III-2. A schematic representation of fluid flow in an agitated tank	119
Figure III-3. Experimental setup used in the emulsification studies	120
Figure III-4. Effect of hydrocarbons on separation performance	124
Figure III-5. Dependence of relative interfacial area on equivalent carbon number	126
Figure III-6. Dependence of recoveries on equivalent carbon number	127
Figure III-7. Dependence of recoveries on relative interfacial area	129
Figure III-8. Emulsification of dodecane as a function of dodecane concentration	133
Figure III-9. Emulsification of dodecane as a function of stirrer speed	134
Figure III-10. Emulsification of dodecane in the presence of a sub-bituminous A coal	135
Figure III-11. Emulsification of dodecane in the presence of a high volatile A coal	137
Figure III-12. High speed motion analyzer photographs of oil/water emulsion in the presence of 3.5 μm particles of sub-bituminous A coal	138
Figure III-13. High speed motion analyzer photographs of oil/water emulsion in the presence of 3.5 μm particles of high volatile A coal particles . . .	139

LIST OF FIGURES (Cont'd.)

	<u>Page</u>
Figure IV-1. Schematic representation of the partitioning of a particle at the liquid/gas interface for determination of contact angle	147
Figure IV-2. Effect of particle size on the contact angle measurements	148
Figure IV-3. Effect of particle shape on the contact angle measurement	149
Figure IV-4. Effect of time of contact of a particle with water on the contact angle measurement	151
Figure IV-5. Distribution of contact angles for different materials	152
Figure IV-6. Relationship between the contact angles and the density of particles	154
Figure IV-7. Differences of the contact angles between "dry" and "prewetted" particles	156

LIST OF TABLES

	<u>Page</u>
Table I-1. Time constants for various sub-processes associated with pyrite oxidation in nitrogen saturated EDTA solution	22
Table I-2. The effect of the EDTA Concentration on the contact angle of pyrite electrode after various electrochemical treatments. The solution was saturated with purified nitrogen in this series of tests	33
Table I-3. The equivalent circuit parameters and their importance for pyrite/solution interface. The solution was nitrogen saturated 0.1 M sodium borate with various concentration of EDTA	37
Table II-1. Pyrite samples	48
Table II-2. Flotation reagents used	49
Table II-3. Effectiveness of various collectors for coal-source pyrites at pH 7 .	70
Table II-4. Sources of raw coal pyrite and refuse samples showing pyrite oxidation products	79
Table II-5. Species identified on pyrite and raw coal and from chrystallized washings from oxidized pyrite	82
Table II-6. Variation of pyrite reaction products depending on coal source and conditions	83
Table II-7. Pyrite and coal samples studied	96
Table II-8. Specific surface areas of pyrite and coal samples	98
Table II-9. Organic polymers used	99
Table II-10. Adsorption densities for various polymers onto pyrite and coal, pH 7	103
Table II-11. Relative adsorption densities of various polymers onto pyrite and coal at pH 7	105
Table II-12. Comparative adsorption densities of various polymers onto pyrite and coal from similar sources (pH 7)	106
Table II-13. Comparative average adsorption densities (mg/m ²) of polymers onto pyrite and coal based on structure, hydroxyl group configuration and ionic charge	107

LIST OF TABLES
(Cont'd.)

	<u>Page</u>
Table III-1. The effect of ionic strength on clean coal yield and product ash and sulfur for a Pittsburgh seam coal (-8mm)	130
Table III-2. Effect of agitator speed, time, pH and salt type on clean coal yield and product ash and sulfur for a Pittsburgh seam coal	131
Table IV-1. Material specifications for various samples used in this investigation	144
Table IV-2. Analysis of various coals	145
Table IV-3. A comparison of different techniques for determining contact angle	155

ACKNOWLEDGEMENTS

Several investigators contributed to the research studies presented in this report. These investigators were: Part I - J. Pang; Part II - Y. H. Chen, V. E. Lundberg and C. E. Esposito; Part III - T. C. Hsu and M. Polat; and Part IV - D. Wei and Professor R. Hogg. Their contributions are gratefully acknowledged. This work could not have been performed without financial support from the Department of Energy through its Grant No. DE-FG22-88PC88934.

EXECUTIVE SUMMARY

One of the more pressing problems facing the nation is the acid rain problem. As coal is the major source of electric power generation, the SO_x component of acid rain may often be most economically reduced by pre-combustion strategies. This report will focus on means of pyrite removal from coal using surface-based coal cleaning technologies.

The major subjects being addressed in this study are the natural and modulated surface properties of coal and pyrite and how they may best be utilized to facilitate their separation using advanced surface-based coal cleaning technology. Emphasis is based on modified flotation and oil agglomerative processes and the basic principles involved. The four areas being addressed are:

- Collectorless flotation of pyrite
- Modulation of pyrite and coal hydrophobicity
- Emulsion processes and principles
- Evaluation of coal hydrophobicity

Since the experimental methods, materials and type of results vary a great deal for each of the four sub-sets enumerated above, we have discussed them in separate parts, as a convenience to the reader.

Collectorless flotation of pyrite is discussed in Part I. It depends upon the formation of a layer of elemental sulfur on the surface of pyrite. Low pH and moderate oxidation potentials favor the conditions for formation of this layer. Ordinarily, the surface layer is covered with a layer of iron compounds such as hydroxides and oxy-sulfides. Surface coverage by the iron compounds is altered in the presence of iron chelating reagents and other methods of controlling the quantity of ferrous/ferric ions. Under these conditions, the sulfur layer is exposed and the surface of pyrite becomes hydrophobic. In this part of the project the effect of a model iron chelating reagent, namely, ethylene diamine tetracetic acid (EDTA), on the oxidation of pyrite was investigated in detail. Various electrochemical methods such as cyclic voltammetry, polarization and impedance spectroscopy were used to determine interfacial properties. Wettability was determined by contact angle measurements on the pyrite electrode and by flotation in a laboratory cell.

Modulation of pyrite and coal hydrophobicity is discussed in Part II-A of this report. Coal-source pyrite has proven to be much more refractory to xanthate flotation than is ore-source pyrite. Using a series of purified samples from both coal

and ore sources, and a variety of xanthate collectors (from ethyl to dodecyl), coal-source pyrite has been found to require one to three orders of magnitude more xanthate than does ore pyrite, even under the most favorable conditions.

Furthermore, there is a great variation in the amount of collector required to float coal-source pyrite depending on its source and genesis. A variety of other collectors have also been evaluated though none were found to be particularly superior to the xanthates. Fuel oil, frequently used as a collector for coal, was also found to float pyrite at relatively low concentrations.

Reaction products of oxidation of coal-source pyrite are discussed in Part II-B of the report. Coal-source pyrite is known to oxidize much more readily than does ore-source pyrite. While ore-source pyrite may remain bright for decades, coal-source pyrite is known to react with humid air in a few hours. A laboratory procedure for the rapid oxidation of coal-source pyrite has been developed. The reaction products formed on the surface of coal-source pyrite on exposure to the atmosphere for a few hours or a few months, have been evaluated by optical and scanning electron microscopy, by microprobe analysis and by X-ray diffraction. Seven different iron sulfates and Gypsum have been identified. Of these, Gypsum ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) and Rozenite ($\text{FeSO}_4 \cdot 4\text{H}_2\text{O}$) appear to occur the most frequently in our studies. The quantity and type of the pyrite reaction products appear to be highly variable based on the source of the pyrite or raw coal.

Modulating the surface hydrophobicity of both pyrite and coal by adsorption of organic polymers is discussed in Part II-C. A series of 13 natural starches, gums, cellulose products and their modifications were evaluated as to their adsorption onto both coal and coal-source pyrite. It was found that there is a great variation in the adsorption of various polymers onto a given pyrite and there is also a great variation in the adsorption of the same polymer onto pyrites from different sources. This observation probably explains why a given polymer may be a good depressant for the pyrite found in one coal and a poorer depressant for the pyrite from another coal source. Polymer structural considerations and charge were also found to play an important role in the adsorption of polysaccharides onto pyrite and onto coal.

Emulsion processes and underlying principles are discussed in Part III. Partitioning of coal and ash-forming minerals between oil and aqueous phases was studied to determine the role of oil in selective agglomeration separation processes for cleaning of ultra-fine coal. The effect of organic phase type and aqueous phase

composition was determined. Kinetics of emulsification of oil was studied in the absence and presence of coal particles of various rank to demonstrate that many sub-processes occur. These include dispersion of oil, capture of hydrophobic particles by oil droplets, particle-aided coalescence of oil droplets, and aggregation of oil droplets by particle bridges. These processes play an important role in the grade and recovery of coal whenever oil is used.

A new technique to determine the hydrophobicity of coal particles is discussed in Part IV. The contact angle for a coal particle was estimated from the equilibrium partitioning of a particle at the water/air interface. From the contact angle values, the distribution of the wettability of coals of different rank was determined. Using this technique, contact angles were determined for a large number of particles from a given sample and a frequency distribution of contact angle was obtained. The contact angle distribution was broad for all the coals tested which included an anthracite, a hvA bituminous and a sub-bituminous coal. In comparison, spherical particles of polymethylmethacrylate gave a much narrower distribution. The distribution for irregular polyethylene particles was somewhat broader than that for the polymethylmethacrylate spheres but broader than that for the polymethylmethacrylate spheres but considerably narrower than that for coal. The broader wetting distribution for coal was attributed to differences in surface chemical properties.

PART I. COLLECTORLESS FLOTATION OF PYRITE

ABSTRACT

Collectorless flotation of pyrite depends upon the formation of a layer of elemental sulfur on the surface. Low pH and moderate oxidation potentials favor the conditions for formation of this layer. Ordinarily, the surface layer is covered with a layer of iron compounds such as hydroxides and oxy-sulfides. Surface coverage by the iron compounds is altered in the presence of iron chelating reagents and other sinks for ferrous/ferric ions. Under these conditions sulfur layer is exposed and the surface of pyrite becomes hydrophobic. In this part of the project the effect of a model iron chelating reagent, namely, ethylene diamine tetraacetic acid (EDTA), on the oxidation of pyrite was investigated in detail. Various electrochemical methods such as cyclic voltammetry, polarization and impedance spectroscopy were used to determine interfacial properties. Wettability was determined by contact angle measurements on the pyrite electrode and by flotation in a laboratory cell.

INTRODUCTION

Previous studies of electrochemical properties of coal- and ore-source pyrites show that significant differences occur between the nature of surface films that form when pyrite oxidizes. A fresh surface of pyrite oxidizes to release ferrous ions into solution leaving a reacted S-rich layer (Chander and Briceno, 1987). In the present study, it has been demonstrated that the formation of such a layer is a necessary but not a sufficient condition for collectorless flotation of pyrite. Using XPS spectroscopy, such a layer was postulated as a metal-deficient layer by Buckley and Woods (1984). The released ferrous ions oxidize to ferric ions under oxidizing conditions and precipitate as a hydroxide or some other iron compound depending upon the conditions prevalent in solution. This layer was referred to as the product layer by Chander and Briceno (1987). In addition, upon continued reaction, oxidation of the sulfur layer occurs giving rise to various oxysulfide ions in the product layer. When the sulfur-rich hydrophobic layer oxidizes completely, pyrite becomes hydrophilic. These results will be discussed in a paper to be presented at the forthcoming Annual Meeting of the society of Mining Engineers in Phoenix, AZ,

February 24-27 (Chander et al., 1992). Precipitation of iron sulfate and gypsum has been observed in some of our studies discussed in Part II of this report.

In previous studies conducted in our laboratories, surface films were grown on pyrites under galvanostatic and potentiostatic control and their in-situ properties were determined by impedance spectroscopy and contact angle measurements. It was necessary to use in-situ techniques because aging of hydroxides and oxides of iron is well known. Impedance spectra of pyrite/solution interface were analyzed by Chander et al. (1988) and Pang et al. (1990), to determine properties of the surface layers as a function of the extent of reaction. As the extent of oxidation increases, thickness and properties of the surface layers change altering the rate determining step. Our previous studies have shown that characteristics of the surface layers change with conditions of oxidation and the pyrite source. On the basis of the analysis of impedance spectra four stages in oxidation of pyrite were postulated. In the first stage, the reactions are controlled by charge transfer processes. As the oxidation proceeds a S-rich layer forms which may be covered with a layer of hydroxides and oxides of iron. For the ore pyrites, the S-rich layer is passivating and the rate determining step is diffusion through this layer. Studies show that the passivity of the sulfur layer is greater for the n-type pyrites than the p-type pyrites. In contrast, the high porosity of most coal-source pyrites give rise to a rough surface. The high roughness of coal source pyrites is one of the reasons which gives rise to its greater reactivity. This is the dominant contributing factor for the oxidation behavior of coal pyrites when the extent of reaction is small.

The second stage of pyrite oxidation occurs when the processes occurring in both the S-rich and Fe-rich layers determine the overall rate. In this stage, oxidation of sulfur species is considered to be minimal. The charge transfer resistance increases with the extent of reaction and potential of oxidation. A high value of the Warburg diffusion term was interpreted to suggest that the diffusion of ferrous ions through the sulfur layer is rate limiting. Compared to an ore pyrite the charge transfer resistance for a coal pyrite is much smaller due to high porosity of the surface film on coal pyrite. The higher porosity of the surface film on coal pyrite also gives rise to a smaller value of the pore resistance and the coating capacitance.

In the third stage of oxidation the surface of pyrite is covered with S- and Fe-rich layers. Partial oxidation of sulfur species occurs which gives rise to an increase in the charge transfer resistance for the ore pyrite. Since the S-layer on coal pyrite is non-passivating the behavior of ore and coal pyrite is somewhat different in this stage. The decrease in Warburg impedance observed for the ore pyrite is not observed for the coal pyrite because the sulfur layer on coal pyrite is porous to begin with. The Warburg impedance for coal pyrite is an order of magnitude smaller than that for an ore pyrite. The relatively porous layer on coal pyrite also gives rise to a smaller charge transfer resistance.

The fourth stage of oxidation is characterized by the presence of a relatively thick layer of oxidation products of iron and sulfur on the surface of pyrite. In this stage, the S-rich layer is virtually absent and the rate of oxidation is determined by diffusion of reactant and products through the product layer. For the coal pyrite, this stage was not observed under the conditions of experimentation.

To understand the mechanism of collectorless flotation of pyrite and its modulation by chelating agents, electrochemical and wetting studies were carried out in the pyrite - EDTA system. Various compounds containing carboxylic and hydroxyl functional groups are known to form as oxidation products of coal. A knowledge of the role of these groups in pyrite oxidation is important for understanding the behavior of pyrite in surface-based coal cleaning separation processes. Specifically, studies were conducted to delineate the role of iron oxidation products on the surface properties of pyrite. Collectorless flotation of pyrite was observed by previous investigators when iron oxidation products were removed by certain reagents such as EDTA (disodium ethylenediamine tetraacetate, $\text{Na}_2\text{C}_{10}\text{H}_{14}\text{O}_8\text{N}_2 \cdot 2\text{H}_2\text{O}$) by Guy and Trahar (1985), Shannon and Trahar (1986), and Wang (1989). However, the reasons for its flotation remain to be established.

EDTA was chosen as a model reagent because it is a well-known chelating reagent for iron. As a consequence, the surface and the interfacial characteristics can be significantly altered. In a reactive system containing a solid and a chelating reagent in solution, two major effects were suggested by Chander et al. (1979). First, when a reagent is added to the solution it may adsorb thereby decreasing the rate of

oxidation. Second, the reagent may enhance the dissolution by forming a compound in bulk solution. Both these effects, which are strongly dependent on pH and reagent concentration, are likely to influence the flotation of pyrite also. Previous studies have shown that the adsorption of the EDTA ligand in some cases may enhance, while in other cases inhibit dissolution of iron compounds. For example, Rubio and Matijevic (1979) found that the solubility of β -FeOOH can be altered with different concentrations of EDTA and pH. A higher concentration of EDTA resulted in an increase in iron released from the solid in the pH range of 8 to 11. When metal oxides are dispersed in EDTA solutions, Blesa et al. (1984) considered that many competing reactions involving chelating agents may occur. These include complexation, oxidation/ reduction, dissolution, precipitation, and adsorption/desorption.

It is known that both ferrous EDTA complexes (such as FeEDTA^{2-}) and ferric EDTA complexes (such as FeEDTA^{-1} and FeOHEDTA^{-2}) are formed as soluble species. The stability domains for these species were calculated using the SOLGASWATER computer program developed by Eriksson (1979) and are shown in Figure I-1. With increase in the potential, the ferric EDTA complexes become predominant at moderate pH's. With the increase in pH, the ferric EDTA complex may convert to the ferric-hydroxy EDTA complex, however. At pH's above 12, ferric hydroxide becomes predominant. The oxidation reactions of pyrite may be written as:

Depending upon the state of oxidation of pyrite and the concentration of EDTA, various type of species may be adsorbed on pyrite. The adsorbed ferrous EDTA complexes may oxidize to ferric EDTA or ferric-hydroxy EDTA complexes, by reactions of the type:

Figure I-1. The conditional Eh-pH diagram of pyrite-EDTA-H₂O system. Various concentrations were $[\text{Fe}]_T = [\text{S}]_T = 10^{-3} \text{ M}$ and $[\text{EDTA}]_T = 2 \times 10^{-3} \text{ M}$.

The surface potential, pH and EDTA concentration will determine the extent of reactions given above.

If the iron hydroxide coating, which is ordinarily present on pyrite, can be removed, a hydrophobic surface due to the presence of a sulfur-rich layer would be exposed making collectorless flotation of pyrite possible. Various techniques were used in this investigation to determine the growth characteristics and properties of surface coatings on pyrite.

EXPERIMENTAL MATERIALS AND METHODS

Standard methods were used for electrochemical and wetting measurements. Details were given in a previous DOE report under Grant No. DE-85PC-FG22-80523.

EXPERIMENTAL RESULTS AND DISCUSSION

Cyclic Voltammetry

The nature of oxidation/reduction reactions of pyrite in EDTA was studied by cyclic voltammetry. The voltammogram of pyrite in the nitrogen saturated 0.1 M sodium borate solution containing 0.1 M EDTA is shown in Figure I-2 as a dashed line. The voltammogram is different from that in a solution without EDTA (solid line). The results for other electrolytes are included for comparison. In the oxidation cycle, two peaks at -0.17 V and +0.09 V, respectively, were observed. In the reduction cycle, three current peaks at +0.03 V, -0.11 V and -0.39 V respectively, were observed. To elucidate the reactions associated with these peaks, the anodic and cathodic switching potentials were changed and voltammograms are shown in Figure I-3a and b. The peaks, namely A_I , A_{II} , C_I and C_{II} , are marked in Figure I-3a. The difference between A_I and C_I is about 0.22 V, and between A_{II} and C_{II} it was 0.06 V. The peaks, A_I and A_{II} are not influenced by changing the anodic switching potential. In contrast the current density decreased with a shift in cathodic switching potential to less negative values as shown in Figure I-3b. The peak potentials did not change, however.

Figure I-2. The voltammograms of pyrite in various solutions. The scan, at a rate of 20 mV/sec . was started from 0.24 V, and went to the cathodic direction initially.

Figure I-3. The voltammograms of pyrite in air saturated 0.1 M sodium tetraborate + 0.1 M EDTA solution. (a) At various oxidation switching potentials; (b) At various reduction switching potentials.

Before discussing the phenomena associated with the electrode processes, it should be noted that the pH of the 0.1 M sodium borate solution containing 0.1 M EDTA was 8.25. Since EDTA is an acidic reagent, the solutions were not adequately buffered when EDTA concentrations were high. The pH as a function of EDTA concentration is given in Figure I-4. To understand the behavior of pyrite in EDTA solutions, one needs to interpret the reactions associated with the two pairs of peaks, (A_I , C_I) and (A_{II} , C_{II}). To determine redox behavior of EDTA, the voltammetric behavior of a platinum electrode in such a solution was determined and the results are shown in Figure I-5. In the absence of ferrous ions, no redox reaction peaks were observed in the range of potentials investigated. In the presence of 2×10^{-3} M ferrous ions, an oxidation peak was observed at 0.14 V, and the corresponding cathodic peak at -0.01 V. Based on the conditional Eh-pH diagram in Figure I-1, the redox reaction might be the oxidation of ferrous EDTA complex to ferric. The adsorbed EDTA molecules on the electrode surface build up a barrier for the diffusion of iron EDTA complexes, so that the oxidation of ferrous EDTA complexes to ferric complexes requires a higher potential. Not only the reaction potential is higher than that expected from the Nernst relation, but also the difference between the oxidation and reduction peak potentials is 0.15 V rather than the 0.06 V expected for a one electron charge transfer process. This means that the charge transfer rate is slow, or the reaction is irreversible.

When similar measurements were made on a pyrite electrode, results shown in Figure I-5b, the oxidation peak potential was 0.09 V, which is about the same as the potential for peak A_{II} in Figure I-3. The corresponding reduction peak potential was 0.03 V which is same as the peak C_{II} in Figure I-3. In the case of pyrite, ferrous ions might also be released from the pyrite lattice, in addition to the ferrous ions added into the solution, so that the total concentration of ferrous EDTA complexes on the pyrite surface might be greater than that on the platinum. Therefore the oxidation peak was shifted to lower potentials with a higher peak current. The 60 mV difference between oxidation and reduction peaks is indicative of a one electron transfer process.

Figure I-6 shows the effect of oxygen on the voltammogram of pyrite in EDTA

Figure I-4. The pH versus concentration of EDTA in 0.1 M air saturated sodium tetraborate solution.

Figure I-5. The voltammograms in nitrogen saturated 0.1 M sodium borate + 0.1 M EDTA solution. (a) platinum electrode, (b) platinum and pyrite electrodes in the solution with 0.001 M ferrous ammonium sulfate addition.

Figure I-6. The voltammograms of pyrite in 0.1 M sodium tetraborate + 0.1 M EDTA solution saturated with nitrogen or air.

solutions. It can be seen that the voltammetric behavior of pyrite in the air saturated 0.1 M sodium borate and 0.1 M EDTA solution was not very different from that of pyrite in the nitrogen saturated solution. This observation, however, should not be interpreted to mean that the effect of oxygen can be ignored as will be discussed in a later section of this report. The increase in cathodic current was due to reduction of molecular oxygen.

Figure I-7 shows that the anodic current peak A_I disappears when the solution is stirred indicating that the oxidation reactions corresponding to A_I are strongly dependent upon diffusion. The diffusing species are probably the iron EDTA complexes. When the solution was stirred, the surface species are removed from the surface with a decrease in the current. To determine the role of sulfur species in the reaction, sodium sulfide (Na_2S) was added into the EDTA solution. Currents for both the peaks A_I and A_{II} increased but the peak potentials did not change, as can be seen in Figure I-8. At the same time, the current for reduction peak at $E = -0.19 \text{ V}$ significantly increased possibly due to the accelerated decomposition of pyrite by adsorbed HS^- ions:

The above reaction might increase the concentration of ferrous EDTA complexes on the surface, and contribute to the increase in current peak A_I . Under these conditions, iron hydroxide layer does not form. The electrochemical processes in the sulfur-rich layer became rate controlling. The oxidized sulfur species released from this layer may undergo reduction reactions, increasing the current of reduction peak at $E = -0.19 \text{ V}$. The added sulfide ions may undergo oxidation reactions also, to form elemental sulfur and sulfate ions and contribute to the increase in current of oxidation peak A_{II} .

When $1 \times 10^{-3} \text{ M}$ ferrous ammonium sulfate was added to the 0.05 M EDTA solution (air saturated), the currents of peaks A_I , A_{II} and C_{II} increased, but the reduction peak at $E = -0.19 \text{ V}$ disappeared (see Figure I-8). The increase in current

Figure I-7. The voltammogram of pyrite in the nitrogen saturated 0.1 M sodium borate, 0.1 M EDTA, and 1.0 mM ferrous ammonium sulfate solution. The solution was stirred during the measurement.

Figure I-8. The voltammograms of pyrite in air saturated 0.1 M sodium borate solution with different reagent additions.

for peak A_I was due to the contribution of ammonium iron complexes which facilitated the decomposition of pyrite (Kho, 1989). The increase in current peaks A_{II} and C_{II} was attributed to the redox process associated with ferrous/ferric EDTA complexes. Further evidence is presented in Figure I-9, where both the peaks A_{II} and C_{II} increased with the addition of ferrous ammonium sulfate. The current density of the two oxidation peaks, A_I and A_{II} , are dependent upon the scan rate as shown in Figure I-10. The peak currents are proportional to the scan rate, and peak potentials are independent of the scan rate. These results imply that the reactions corresponding to the two peaks are quasi-reversible. In other words, the rate of charge transfer is slower than or equal to the rate of diffusion.

Galvanostatic Polarization

Chronopotentiogram for the pyrite electrode in nitrogen saturated 0.1 M sodium borate + 0.1 M EDTA solution is given in Figure I-11 (the dashed curve for the pyrite in the carbonate solution is given for comparison). Three time constants which are marked as τ_E , τ_F and τ_O in the figure can be identified. The chronopotentiogram at low charge densities is presented in Figure I-12 for a lower concentration of EDTA. The processes associated with the time constants marked as τ_B , τ_C and τ_D in Figure 12, were observed only at low EDTA concentrations. At these concentrations, with a gradual increase in the anodic charge passed, the EDTA molecules reacted with iron species released during the electrode preparation to form iron EDTA complexes. This step is associated with time constant τ_A . The reactions are written as:

Solubilization of iron compounds might promote the further reaction of pyrite with EDTA solution. This process corresponds to the time constant τ_H . Since only a limited amount of EDTA was available, there is competition between the precipitation and dissolution reactions involving of iron species. The process

Figure I-9. The voltammograms of pyrite in nitrogen saturated 0.1 M sodium borate + 0.1 M EDTA solution with various amounts of $\text{Fe}(\text{NH}_4)\text{SC}_4$ additions.

Figure I-10. Dependence of the peak current and peak potential, respectively, on the scan rate for pyrite electrode in air saturated 0.1 M sodium borate + 0.1 M EDTA solution.

Figure I-11. The galvanostatic polarization curves for a pyrite electrode in various solutions at pH 9.3. The anodic current was kept as a constant of $4 \mu\text{A}/\text{cm}^2$ and the solutions were nitrogen saturated.

Figure I-12. The galvanostatic curves of pyrite in the nitrogen saturated 0.1 M sodium borate + 0.1 mM EDTA (solid line), or 0.1 M EDTA (dotted line) solution. The anodic current was $4 \mu\text{A}/\text{cm}^2$. The dashed line represents the contact angles of pyrite measured during the galvanostatic treatment in 0.1 mM EDTA solution.

corresponding to the time constant, τ_C , was considered to involve oxidation of ferrous to ferric species. Because the iron EDTA complexes diffused into the solution, leaving a porous iron hydroxide coating, oxidation of sulfur-rich layer occurred as the potential increased. This process was identified by time constant τ_D . At higher EDTA concentrations, the iron species were readily dissolved exposing the pyrite surface to EDTA and the potential increased to higher values as can be seen from the dotted curve in Figure I-12. At higher charge densities, the time constant τ_E (see Figure I-11) was observed and is associated with the oxidation of sulfur. At a high EDTA concentrations, the excess EDTA molecules adsorbed on the pyrite surface to build up a diffusion barrier of iron EDTA complexes. The accumulated species inhibited the continued decomposition of pyrite. This might be a transition process corresponding to the time constant τ_F . Continued oxidation promoted reactions in the iron hydroxide layer. This process corresponded to τ_G . The various processes corresponding to different time constants are tabulated in Table I-1.

Figure I-13 shows the effect of EDTA concentration on galvanostatic polarization. The increase in potential at higher concentrations was postulated to occur due to two reasons: 1) the pH in 0.1 M EDTA solution was lower and 2) a greater contribution to the overall current from the oxidation of sulfur. To verify the first premise, the effect of pH on the galvanostatic behavior was determined and the results are given in Figure I-14. The results are consistent with thermodynamic calculations.

In a separate experiment, it was observed that the open circuit potential of the pyrite electrode was a complex function of the amount of galvanostatic charge. Removal of oxidized iron species decreased the surface potential. Whereas conditions which favored oxidation of sulfur gave higher potentials. The effect of EDTA concentration on the open circuit potential is given in Figure I-15. The measurements were made after passing an anodic charge of 40 mC/cm^2 at a current of $4 \text{ } \mu\text{A/cm}^2$. At the EDTA concentration below $2 \times 10^{-5} \text{ M}$, the open circuit potential was constant. In the range from 5×10^{-5} to $8 \times 10^{-5} \text{ M}$ of EDTA concentration, the open circuit potential first increased and then decreased. As the concentration was gradually raised, excess EDTA adsorbed on the surface to build a diffusion barrier. When the

Table I-1. Time constants for various sub-processes associated with pyrite oxidation in nitrogen saturated EDTA solution.

PROCESS	TIME CONSTANT	APPROXIMATE RANGE Q, mC/cm ²	PROCESS DESCRIPTION
A	τ_A	0 - 2	Surface iron species complexed by EDTA.
B	τ_B	2 - 8	Dissolution of pyrite & formation of ferrous EDTA complexes.
C	τ_C	8 - 12	Oxidation of ferrous EDTA to form ferric-hydroxy EDTA & precipitation of iron hydroxides.
D	τ_D	12 - 25	Oxidation of sulfur species in the sulfur-rich layer.
E	τ_E	25 - 120	Dissolution of pyrite by EDTA complexation & oxidation of sulfur-rich layer.
F	τ_F	120 - 200	Iron EDTA complexes accumulate on pyrite surface.
G	τ_G	200 -	Oxidation of adsorbed ferrous EDTA complexes in the coating layer.

Figure I-13. The galvanostatic polarization curves for pyrite in air saturated solutions with different EDTA concentrations. The anodic current was $4 \mu\text{A}/\text{cm}^2$.

Figure I-14. The galvanostatic polarization curves for pyrite in the air saturated solutions with different pH values. The anodic current was $4 \mu\text{A}/\text{cm}^2$.

Figure I-15. The dependence of open circuit potential of pyrite electrode on EDTA concentration. The electrode was pre-treated by passing 40 mC/cm² of galvanostatic anodic charge.

EDTA concentration was greater than 2×10^{-4} M, the solubilization of iron layer was high and the corresponding increase in the rate of oxidation decreased the open circuit potential.

In a series of experiments to determine the type of surface species, cathodic polarization curves were obtained after anodic oxidation of pyrite. The various amounts of galvanostatic charge (at $4 \mu\text{A}/\text{cm}^2$, anodic) passed through the electrode is given in Figure I-16. A linear potential sweep of $20 \text{ mV}/\text{sec}$ was used starting from 0.24 V . The pyrite undergoes processes B and C, which tabulated in Table I-1 after passing about $10 \text{ mC}/\text{cm}^2$ anodic charge. The cathodic peak potential became less negative, because only a portion of the iron hydroxides at the surface was dissolved by EDTA. After a mild oxidation in the EDTA solution ($60 < Q < 200 \text{ mC}/\text{cm}^2$), reduction of sulfur species occurred and a new current peak was observed at -0.22 V . This indicates that the reactions in the sulfur-rich layer became predominant. After a heavy oxidation ($Q > 200 \text{ mC}/\text{cm}^2$), the thickness of the intermediate sulfur layer was small as can be seen in a decrease in the peak current.

Solution Analysis

To identify the species present in EDTA solution equilibrated with pyrite, UV spectroscopy was performed. Figure I-17a shows the UV spectrum of the filtrate solution after conditioning pyrite in an air saturated 0.1 M sodium borate + 0.1 M EDTA solution for 17 hours. An absorbance peak at $\lambda = 266 \text{ nm}$ with $I = 1.7$ was observed. Based on a comparison of the UV spectrum for ferrous ions in the alkaline EDTA solutions (Figure I-17b), this peak is considered to be due to ferrous EDTA complexes. This result provided further evidence that EDTA removed iron species from the pyrite surface. The iron content of the solution was determined to be 174 ppm by atomic adsorption spectrophotometry. Using the same procedure, when the pyrite sample was conditioned without EDTA, only 3 ppm of iron was found in the filtrate solution.

Contact Angles

To determine the wettability of pyrite, contact angles were measured on pyrite

Figure I-16. The voltammograms of pyrite after different extent of galvanostatic treatments. The solution was nitrogen saturated 0.1 M sodium borate +0.1 M EDTA.

Figure I-17. The UV spectrum of the 0.1 M sodium borate +0.1 M EDTA solution treated with pyrite. The conditioning period was 17 hours.

electrodes during the galvanostatic treatment and the results were shown in Figure I-12. Based on the various electrode processes given in Table I-1, it is proposed that iron species were removed by EDTA complexation during the process B, exposing a sulfur-rich layer to the solution. This layer being hydrophobic, gave contact angles of 40 to 50 degrees. During process C, the competition between the precipitation of iron hydroxides and complexation of iron EDTA caused a decrease in the hydrophobicity, i.e., the magnitude of the contact angle decreased. On continued oxidation, process D occurred in which the sulfur-rich layer oxidized and contact angles became zero. Under the open circuit conditions, a contact angle of between 40 to 45 degrees was observed.

When the EDTA solution was air saturated, a non zero contact angle was observed only in a narrow potential range compared to the nitrogen saturated solution (as shown in Figure I-18). This is probably due to that oxygen was reduced to hydroxide ions, which facilitated the formation of iron hydroxide and adsorbed hydrolyzed complexes. Near the open circuit potentials, the extent of oxidation was small and the pyrite electrode surface should not be altered. The measured contact angles were about the same as those observed in the nitrogen saturated solution. Similarly, in the air saturated EDTA solution (0.1 M sodium borate + 0.1 mM EDTA), under the open circuit conditions, the contact angle was about 40 degrees. At potentials above the open circuit potential, the decomposition of pyrite by EDTA occurred simultaneously with the oxygen reduction. The overall reaction may be written as:

The stability of the sulfur-rich layer depends on the local concentration of hydrogen ions. A higher oxygen content increased the local concentration of hydroxyl ions, so that the stability of the sulfur-rich layer was poor and the probability of iron precipitation was higher. Therefore, the contact angle was zero.

Figure I-19 shows the effect of EDTA concentration on the contact angle of

Figure I-18. The contact angles of pyrite measured in the various solutions under the potentiostatic mode. The data were taken after the potential was applied for 2 minutes.

Figure I-19. The contact angles of pyrite versus the EDTA concentration. They were measured after $2.16 \text{ mC}/\text{cm}^2$ anodic charge passed through the electrode.

galvanostatically oxidized pyrite. At a very low EDTA concentration such as 3×10^{-6} M, the iron hydroxides, which were produced during the wet-polishing of the electrode, were dissolved. A sulfur-rich sulfide layer was exposed to the solution giving rise to a contact angles of 35° . When the concentration of EDTA increased, more iron EDTA complexes were formed. Some of these complexes may adsorb on the surface, rendering the surface hydrophilic as reflected by zero contact angles. The rest potentials given in Figure I-15 did not correlate with contact angles. When the concentration of EDTA was in the range of 3×10^{-5} to 2×10^{-4} M, the rate of complexation of iron was significantly increased. Continued oxidation of pyrite with simultaneous solubilization of iron resulted in formation of a sulfur-rich layer exposed to the solution. This layer was responsible for the second peak of observed contact angles in Figure I-19. When the EDTA concentration was very high ($> 2 \times 10^{-4}$ M), excess EDTA molecules adsorbed on the electrode surface and made the surface hydrophilic. The contact angle became zero. A similar observation in a flotation experiment was made by Wang (1989) who suggested that excess EDTA will continue to leach the bulk pyrite and cause the flotation recovery to decrease. In our opinion, the excess EDTA cannot continue to leach bulk pyrite due to the protective barrier of the sulfur-rich layer at moderate potentials. High oxidation potentials are needed to oxidize the sulfur-rich layer which would result in continued dissolution of pyrite.

The contact angles measured under the potentiostatic mode are given in Table I-2. The pyrite electrode was in the 0.1 M sodium borate solution with various amounts of EDTA. The solution was nitrogen saturated. This series of tests shows the effect of EDTA concentration on the surface hydrophobicity of pyrite without electrochemical treatment. The contact angles gradually increased with increase in EDTA concentration. These results further confirm the hypothesis that dissolution of surface iron species by EDTA exposes the sulfur-rich layer rendering the surface hydrophobic.

Impedance Spectroscopy

The effect of EDTA concentration on the properties of the pyrite/solution interface was studied by analysis of the impedance spectra. The spectra were

Table I-2. The effect of EDTA concentration on the contact angle of a pyrite electrode after various electrochemical treatments. The solution was saturated with purified nitrogen in this series of tests.

Treatment Potential, V	EDTA Concentration, Mole/liter					
	01	0^{-6}	5×10^{-6}	10^{-5}	5×10^{-5}	10^{-4}
-0.4	0	0	0	0	0	0
-0.3	0	0	0	0	0	41
-0.2	0	22	34	32	39	39
-0.1	0	0	33	30	34	45
0.0	0	32	41	40	41	45
0.1	32	0	35	42	35	44
0.2	0	50	36	45	40	41
0.3	42	39	0	33	0	40
0.4	0	0	43	45	0	40

measured in the nitrogen saturated 0.1 M sodium borate solutions containing various amounts of EDTA. The electrode was anodically charged with 40 mC/cm² at a current of 4 μ A/cm² before the impedance measurement and the results are given in Figure I-20. The measured spectra are represented as discrete symbols and the spectra calculated with equivalent circuit model, TLMWLC, are represented by lines. The equivalent circuit model is given in Figure I-21 and the parameters are listed in Table I-3. The open circuit potential of the pyrite electrode after 40 mC/cm² anodic charging varied with EDTA concentration and the effect of concentration was quite complex. At a concentration of 5×10^{-5} M, the open circuit potential was measured as -4 mV. The corresponding Nyquist plot considerably differs from the corresponding plot for other concentrations as can be seen in Figure I-20a. The results cannot be interpreted in terms of the open circuit potential alone, however. It may be noted that the impedance spectrum was quite different at a concentration of 7.5×10^{-5} M, even though the OCP was -8 mV. At very low EDTA concentrations ($\sim 3 \times 10^{-6}$ M), the amount of adsorbed EDTA molecules on the pyrite surface was expected to be small. A part of the ferrous ions released was complexed by EDTA ligands which diffused into the solution, and the remainder precipitated as an iron hydroxide layer. Since the amount of iron EDTA complexes was small at low concentrations of EDTA, the dissolution of pyrite was slow. Therefore, both the iron hydroxide layer and the sulfur-rich layers were thin. The rate of charge transfer through the sulfur-rich layer was relatively fast as shown by the small charge transfer resistance, R_t (0.29 Kohms/cm²). These observations are consistent with our previous findings that the charge transfer resistance is proportional to the thickness of the sulfur layer. The charge transfer resistance of the iron hydroxide layer was relatively high as can be seen from the value of the coating resistance term, R_c , which was 8,097 kohms/cm². At high EDTA concentrations ($\sim 1 \times 10^{-4}$ M), the ferrous ions were readily complexed by EDTA as soon as they were released from the lattice. This facilitated the decomposition of pyrite. Therefore the rate of charge transfer was fast, which is seen from the small value of R_t (1.96 kohms/cm²). Under these conditions, the coating layer resistance was high ($R_c = 22,134$ kohms/cm²), which is attributed to the higher stability of the sulfur-rich layer. This situation will give rise

Figure I-20. The impedance spectra of the pyrite electrode in the solutions with various amounts of EDTA. The solution was nitrogen saturated. The discrete symbols are the experimental data whereas the lines are the calculated spectra.

PARAMETERS OF THE EQUIVALENT CIRCUIT

R_t : Charge transfer resistance at reacted layer

R_p : Pore resistance

σ : Coefficient of Warburg impedance (inversely proportional to rate of diffusion)

R_c : Reaction resistance of the coating layer

L : Self inductance of the coating layer

C_c : Capacitance of the coating layer

C_d : Diffusion layer capacitance

Figure I-21. An equivalent circuit model for pyrite/solution interface. Z_w is Warburg impedance and σ is the coefficient of Warburg impedance. Other quantities are defined in the table given above .

Table I-3. The equivalent circuit parameters and their importance for pyrite/solution interface. The solution was nitrogen saturated 0.1 M sodium borate with various concentration of EDTA.

[EDTA], mM	0.003	0.017	0.050	0.060	0.075	0.085	0.100
OCP*, mV	-90	-96	-4	-61	-8	-29	-94
E _{DC} **, mV	-90	-96	-4	-61	-8	-29	-94
CIRCUIT MODEL	TLMWLC	TLMWLC	TLMWLC	TLMWLC	TLMWLC	TLMWLC	TLMWLC
R _o , Ω/cm^2	41	26	39	42	39	39	41
R _p , $\text{K}\Omega/\text{cm}^2$	2.18	2.05	1.53	2.26	1.96	2.04	2.22
R _t , $\text{K}\Omega/\text{cm}^2$	0.29	8.33	11.08	13.12	12.27	6.91	1.96
R _c , $\text{K}\Omega/\text{cm}^2$	8,097	15,673	288	3,699	672	822	22,134
σ , $10^3/\text{cm}^2$	39	34	33	43	37	43	33
C _c , $\mu\text{F}/\text{cm}^2$	95	112	130	98	114	108	118
C _d , $\mu\text{F}/\text{cm}^2$	46	59	53	52	52	51	54
L, mH/cm^2	77	59	20	134	(0)	38	32
Sav ***	0.162	0.167	0.122	0.164	0.127	0.164	0.169
IMPORTANCE ORDER							
1	C _c	C _c	C _c	C _c	C _c	C _c	C _c
2	R _o	R _o	R _o	R _o	C _d	R _o	R _o
3	C _d	C _d	C _d	C _d	R _o	C _d	R _o , C _c
4	R _o , C _c	σ	R _o , C _c	R _o , C _c	σ	R _o , C _c	C _d
5	σ	R _o , C _c	σ	σ	R _o , C _c	σ	σ

* OCP: Open Circuit Potential. This potential was measured 3 hours after the pyrite was placed in the solution. Impedance measurements were commenced immediately after this period.

** E_{DC}: The DC potential which was applied during the impedance measurement.

*** Sav: Averaged standard deviation.

to a slow rate of the charge transfer through the interface. Since the Warburg coefficient, σ_r , for all of the EDTA concentrations was essentially constant (33,000 - 43,000/cm²), the rate of diffusion can be expected to be a constant. The EDTA concentration influenced the adsorption of iron EDTA complexes, which affected the self-inductance term, L , however.

Flotation Tests

The Hallimond tube flotation recovery of 65x100 mesh pyrite as a function of pH is given in Figure I-22. The pyrite sample was preconditioned with quartz to remove iron hydroxide from the surface. Although the recoveries were low, their values increased with increase in the amount of quartz. When the pyrite was preconditioned with 0.01 M EDTA, in the presence of quartz, the flotation recovery increased significantly at pH's below 6, as shown in Figure I-23. At higher pH's (> 7), the effect of EDTA was not significant. This is probably because of the lower stability of the sulfur-rich layer at higher pH's. Figure I-24 shows the effect of EDTA concentration and the amount of quartz on the flotation pyrite at pH 4.6. With the increase in EDTA concentration, the recoveries gradually increased.

SUMMARY

In alkaline solutions, the iron species can be dissolved by complexation with EDTA, thereby exposing the sulfur-rich layer. Based on the results presented in this report, a stage-wise oxidation model of pyrite in EDTA solutions is proposed, which is similar to the model for pyrite oxidation in the absence of EDTA. In the initial stages of oxidation, the iron hydroxides and oxides produced during the sample preparation are dissolved by EDTA. With continued oxidation, the ferrous ions are released from lattice to form ferrous EDTA complexes. These complexes can either diffuse into solution or react at the surface to form ferric-hydroxy EDTA complexes. Meanwhile, the sulfur-rich layer formed by preferential release of iron may undergo oxidation reactions. The conditions which favor slow oxidation of the sulfur-rich layer and high dissolution of the iron species give rise to a hydrophobic surface making pyrite floatable without collector. The decomposition of the sulfur-rich layer results

Figure I-22. The flotation recovery of pyrite as a function of pH of conditioning. The 1 gram of 65x100 mesh pyrite powder was preconditioned with -200 mesh quartz at a certain pH. After 30 minutes, the quartz was washed out with distilled water. The flotation was carried out in a Hallimond tube with a 130 mL distilled water and 1 gram pyrite sample; the gas flow rate was 55 mL/min.

Figure I-23. The flotation recovery of pyrite as a function of pH of conditioning in 0.01 M EDTA. A 1 gram sample of 65x100 mesh pyrite was preconditioned with 5 grams of -200 mesh quartz at the desired pH. After 30 minutes, the quartz was washed with the distilled water. The flotation was carried out in a Hallimond tube with a 130 mL water and 55 mL/min gas flow.

Figure I-24. The flotation recovery of pyrite as a function of the amount of quartz. The solution contained various amount of EDTA. The 1 gram of 65x100 mesh pyrite powder was preconditioned with certain amount of -200 mesh quartz at pH 4.6. After 30 minutes, the quartz was washed out with the distilled water. The flotation was carried out in a Hallimond tube with a 130 mL water and 55 mL/min gas flow.

in poor hydrophobicity and floatability.

Under similar conditions, the extent of pyrite oxidation depended on the concentration of EDTA. At low concentrations, the rate of formation of iron EDTA complexes was comparable to the rate of formation of iron hydroxides and hydrolyzed complexes. Under these conditions, the surface was patchy with some portion being hydrophobic and others hydrophilic. With an increase in the concentration of EDTA, the contact angle gradually increased, and became more uniform over the entire surface. At an extremely high concentration of EDTA, because of the adsorption and accumulation of iron EDTA complexes and free EDTA ions at the surface of oxidized pyrite, the contact angle was zero.

REFERENCES

Blesa, M. A., Borghi, E. B., Maroto, J. G., and Regazzoni, A. E., "Adsorption of EDTA and Iron-EDTA Complexes on Magnetite and the Mechanism of Dissolution of Magnetite by EDTA", *J. Colloid and Interface Science*, 98:295-305, 1984.

Buckley, A., and Woods, R., "An X-ray Photoelectron Spectroscopic Investigation of the Surface Oxidation of Sulfide Minerals", *Proceedings of the International Symposium on Electrochemistry and Mineral Processing*, The Electrochemical Society, 286-302, 1984.

Chander, S., "Electrochemistry of Sulfide Flotation: Growth Characteristics of Surface Coatings and Their Properties, with special reference to chalcopyrite and pyrite", *International J. Mineral Processing*, 33:121-134, 1991.

Chander, S., "Floatability of Pyrite in the Absence of Conventional Collectors", paper presented at the Spring Information Transfer Session", Cooperative Program in Coal Research, The Pennsylvania State University, University Park, PA, May 17-18, 1990. (This paper was also presented at DOE's VCR/HBCU Contractor's Review Meeting in Pittsburgh, PA, July 16-19, 1990).

Chander, S., and Briceno, A., "Kinetics of Pyrite Oxidation", *Minerals and Metallurgical Processing*, 171, 1987.

Chander, S., Briceno, A. and Pang, J., "On the Mechanism of Sulfur Oxidation in Pyrite", paper to be presented at the SME Annual Meeting, Phoenix, AZ, February 24-27, 1992.

Chander, S., Pang, J. and Briceno, A. "Some Equivalent Circuit Models for AC Impedance Analysis of Pyrite/Solution Interface", *Electrochemistry in Mineral and Metal Processing-II*, Eds., P. E. Richardson and R. Woods, The Electrochemical Society, 88-21:247-263, 1988.

Chander, S., Pang, J., and Zhou, R., "Effect of Anodic Oxidation on Collectorless Flotation of Pyrite", paper presented at the 1991 SME Annual Meeting, Denver, CO, February 25-28, 1991.

Chander, S., Kar, G., and Fuerstenau, D. W., "Corrosion and Wetting Behavior of Copper in the Presence of Some Thiol Reagents", *Corrosion Science*, 19:405-416, 1979.

Eriksson, G., "An Algorithm for the Computation of Aqueous Multicomponent, Multiphase Equilibria", *Analytica Chimica Acta*, 112:375-383, 1979.

Guy, P. J., and Trahar, W. J., "The Effects of Oxidation and Mineral Interaction on Sulphide Flotation", Flotation of Sulphide Minerals, Ed., K. S. Eric Fossberg, New York: Elsevier, 91-110, 1985.

Kho, Y. T., Anodic Behavior of Iron in Aqueous Ammoniacal Solution. Ph. D. Thesis in Metals Science and Engineering, The Pennsylvania State University, 1989.

Pang, J., Briceno, A., and Chander, S., "A Study of Pyrite/Solution Interface by Impedance Spectroscopy", J. Electrochemical Society, 137:3447-3455, 1990.

Rubio, J., and Matijevic, E., "Interactions of Metal Hydrous Oxides With Chelating Agents, I. β -FeOOH-EDTA", J. Colloid and Interface Science, 68:408-421, 1979.

Shannon, L. K., and Trahar, W. J., "The Role of Collector in Sulfide Ore Flotation", Advance in Mineral Processing, AIME, 408-425, 1986.

Wang, X., The Chemistry of Flotation, Activation and Depression of Iron-Containing Sulfide Minerals, Ph.D. Thesis in Mineral Processing, The Lulea University of Technology, Sweden, 1989.

Part II. MODULATION OF PYRITE AND COAL HYDROPHOBICITY

Part II-A. A COMPARATIVE FLOTATION OF COAL-SOURCE AND ORE-SOURCE PYRITES

ABSTRACT

Coal-source pyrite has proven to be much more refractory to xanthate flotation than is ore-source pyrite. Using a series of purified samples from both coal and ore sources, and a variety of xanthate collectors (from ethyl to dodecyl), coal-source pyrite has been found to require one to three orders of magnitude more xanthate than does ore pyrite, even under the most favorable conditions. Furthermore, there is a great variation in the amount of collector required to float coal-source pyrite depending on its source and genesis. A variety of other collectors have also been evaluated though none were found to be particularly superior to the xanthates. Fuel oil, frequently used as a collector for coal, was also found to float pyrite at relatively low concentrations.

INTRODUCTION

Flotation is a major method of coal preparation for the rejection of pyrite and the ash-forming minerals from fine (-0.5 mm) coal. There are, however, several major problems in using the process to effectively reject pyritic sulfur, and principal among these is improving the selectivity between coal and pyrite during flotation (Aplan, 1989). The problem is exacerbated by the presence of oil (Olson and Aplan, 1985, 1987) commonly used as a coal collector in the flotation of most coals. The following means are available to separate pyrite from coal using flotation and similar surface-based processes (Aplan, 1989):

1. Depress the pyrite during coal flotation
2. Depress the coal and float the pyrite.
3. Improved flotation circuitry (cleaners, scavengers, split feed, etc.)
4. Froth sprinkling
5. Improved machines and processes (e.g., modified mechanical cells, bubble columns, bubble size control, etc.)
6. Alternative machines and processes (e.g., bubble techniques, agglomerative techniques, etc.)

This report is specifically directed toward Method 2 (which also uses circuitry modifications). This method is typified by the two-stage, reverse process developed by K. J. Miller (Miller and Baker, 1972; Miller, 1975; Miller, 1989) first at the U.S. Bureau of Mines and later at the U.S. Department of Energy. In this process, the coal is floated from the bulk of the pyrite and ash-forming minerals in a conventional rougher flotation circuit. The partially cleaned coal is then sent to a second stage of flotation where the coal is depressed and the pyrite is floated. Unfortunately, the process uses relatively large amounts of reagents (roughly ten times as much xanthate to float the pyrite as is used in sulfide ore flotation), and the process works well for some coals but not for others. The authors believe that many of the complications with this process can be attributed to the differing nature of pyrite from source to source. Determining how various pyrites from both coal and ore sources respond to flotation using thiol and oily collectors is the major thrust of this present study.

In an extensive study on the characterization of coal-source pyrites, Esposito, Chander and Aplan (1987) compared the properties of several coal-source and one ore-source pyrite in terms of chemical and mineralogical analyses, morphology, apparent specific gravity, surface area, semi-conductor type, optical anisotropy, inherent floatability, dissolution and oxidation rate. They found differences in nearly all of these characteristics with the greatest differences between pyrites from various sources due to a wide variation in their morphologies, BET surface areas and oxidation rates. There was a major difference between coal-source pyrites and the ore-source pyrite used for comparison as well as great differences among the coal-source pyrites. Only pyrite from anthracite sources had many characteristics similar to those from ore sources.

The differing nature of pyrite from source to source has long been known. Smith (1942) found a variation in the properties of ore-source pyrite due to its genesis and Carrucio (1970) and Smith, Svanks and Shumate (1968) found a variation in the oxidizability of various coal-source pyrites. In coal flotation, Hirt and Aplan (1991) found that three different coal-source pyrites floated 2.3 to 5.7 times faster than did an ore-source pyrite during the flotation of coal using MIBC frother as the only reagent. Chernowsky and Lyon (1972) showed that coal-source pyrite adsorbed much

more xanthate than did ore-source pyrite and it required more xanthate for its flotation.

It is the goal of this research to evaluate the flotation of a broad variety of pyrites from both coal and ores sources with several different collectors of both the xanthate and other types.

EXPERIMENTAL MATERIALS AND METHODS

Pyrite Samples

The nine coal-source and six ore-source pyrite samples used in this study are listed in Table II-1. Typically the coal-source samples were from sulfur balls or from some sulfur-rich fraction from the preparation plant. The feed material was crushed and sized, and the separate size fractions treated by hindered settling classification and repeated treatment on a shaking table. The final concentrate was hand vanned and further treated several times in an ultrasonic bath to remove any adhering coal, clay or other fine particulates. The material was quickly dried and stored in a vacuum desiccator until used. Samples P-1 to P-8 are the same as those characterized by Esposito, Chander and Aplan (1987). The ore pyrites were obtained from Wards Natural Science Establishment, Rochester, NY, except for the Black Hills sample which was collected by one of us (FFA) from the Deadwood, SD district. Hand specimens were crushed, hand vanned if necessary, and given the ultrasonic treatment to remove any adhering fines.

Reagents

The flotation reagents used in this study are given in Table II-2. The ethyl, amyl, octyl and dodecyl xanthates were made from their respective alcohols, CS_2 and KOH using the method of Foster (1928). The xanthate was precipitated from an acetone solution with petroleum ether, filtered and then recrystallized twice more, dried and stored in a desiccator (Ackerman, 1986). The thionocarbamates and the xanthogen formate were synthesized by G. H. Harris (then of Dow Chemical) and P. K. Ackerman of Penn State (Ackerman, 1986).

Table II-1. Pyrite Samples

Number	Description and Location	Rank of Parent Seam
Coal-Source Pyrites		
P-1	Anthracite wall pyrite, Tamaqua prep plant, Schuylkill, Co., PA	an
P-2	Anthracite seam pyrite, as above	an
P-4	Lower/Middle Kittanning seam, Cambria Co., PA	lvb
P-5	Pittsburgh seam, Osage Co., WV	hvAb
P-6	Upper Freeport seam, Indiana Co., PA	m vb
P-7	KY No. 11 seam, Union Co., KY	hvBb
P-9	Lower Clarion seam, Clarion Co., PA	hvAb
P-10	Lower Kittanning seam, Clarion Co., PA	hvAb
P-11	Pittsburgh seam, Greene Co., PA	hvAb
Ore-Source Pyrites		
P-8	Huanzala, Peru	
P-22	Manora, Que, Canada	
P-23	Rico, CO	
P-24	Mexico	
P-25	Black Hills, SD	
P-26	Superior, AZ	

Table II-2. Flotation Reagents Used

Abbreviation	Name	Source
KEtX	Potassium ethyl xanthate	synthesized
KAmX	Potassium amyl xanthate	synthesized
KOcX	Potassium octyl xanthate	synthesized
KDDX	Potassium dodecyl xanthate	synthesized
sBbIpTC	Sec-Butyl bis-Isopropyl Thionocarbamate	see text
Nph-OH TC	N-2-Phenyl-thio-ethyl-O Hexyl Thiobocarbamate	see text
Nph-SH DTC	N-2-Phenyl-thio-ethyl-S-Hexyl Dithiocarbamate Ester	see text
IpxPhF	Isopropyl Xanthogen Phenyl Formate	see text
Imidazoline	1-Hydroxy-ethyl-2-Heptadecenyl	Union Carbide
MIBC	4-methyl-2-pentanol (Frother)	Shell
#2 fuel oil	Hydrocarbon oils (Collector)	Exxon

Flotation Procedure

The flotation tests were done in a micro-flotation cell made from a 150 ml coarse, porous frit funnel as described by Fuerstenau (1964). The effective cell volume was 125 ml and the pH value was set with HCl and NaOH. Approximately, 0.5 g of 48+65 mesh pyrite (freshly ground and sized just before use) and 10 μ l of MIBC were added to the 125 ml of collector solution in the cell. The pulp was then conditioned for one minute using overhead stirring to minimize pyrite attrition. A nitrogen flowrate of 40 ml/min and magnetic stirring was used during flotation and the froth was collected at 40 and 120 sec. The pH and Eh were monitored continuously. After flotation the two concentrates were dried and weighed. The 40 sec. concentrate was used for rate calculations and most of the reported recovery data were the values at 120 sec.

EXPERIMENTAL RESULTS AND DISCUSSION

The flotation of pyrite was evaluated largely at pH 7 since most coal flotation is done at neutral pH, though in a few cases flotation at other pH values was also evaluated.

Ore-Source Pyrite

The data for the two-minute flotation of 48x65 mesh ore-source pyrite are given in Figures II-1 to 5. For the flotation of the P-8 Peru pyrite, given in Figure II-1, the order of flotation with the from xanthate is:

All but the ethyl xanthate float this pyrite at a concentration of $\sim 10^{-6}$ M. Note that $\sim 20\%$ of this pyrite floats at 10^{-7} M for any of the xanthates tested. This is believed to be due to the natural floatability of this pyrite (see subsequent data). Ackerman (1983) has noted a similar natural floatability with this pyrite.

The Manora, Que pyrite (P-22) and the Superior, AZ pyrite, (P-26) (this latter sample gave similar results that are not shown here) show a similar pattern to that

Figure II-1. Flotation of Peru ore pyrite (P-8) with various xanthates.

Figure II-2. Flotation of Manora, Que. Ore pyrite (P-22) with various xanthates.

Figure II-3. Flotation of Mexico ore pyrite (P-24) with various xanthates.

Figure II-4. Flotation of Rico, CO ore pyrite (P-23) with various xanthates.

Figure II-5. Flotation of Black Hills, SD ore pyrite (P-25) with various xanthates.

noted for the P-8 pyrite except that the KDDX is somewhat superior to KOcX and KEtX is a very poor collector at any reasonable concentration. Excellent flotation of this pyrite with the two xanthates having the longest hydrocarbon chain takes place at $\sim 10^{-6}$ M. No evidence of natural floatability of the Manora pyrite was seen, through some could be inferred for the Superior, AZ pyrite.

The Mexican pyrite, P-24 (Figure II-3) again shows the KEtX to be a relatively poor collector with the others performing well at a collector concentration of 10^{-6} M. However, it will be noted that the shorter chain KAmX (C-5) is superior to the longer chain KOcX (C-8) or KDDx (C-12).

Pyrite from Rico, CO, P-23 (Figure II-4) shows yet another pattern with the order of flotation being:

$$\text{KAmX} \geq \text{KEtX} > \text{KOcX} > \text{KDDX}$$

at $\sim 10^{-6}$ M, though at 10^{-5} M, the KDDX also performs well. The drastic change in the relative position of KEtX, as compared to the pattern previously established, is especially noteworthy.

The Black Hills, SD pyrite, P-25 shows a somewhat different pattern to that seen previously in that the three longest chain xanthates show 50-60% flotation at 10^{-7} M (Figure II-5). Though the KEtX shows a different pattern from the other three xanthates, it is a good collector for this pyrite at 10^{-6} M.

Comparative flotation of ore-source pyrites. This may best be seen in Figure II-6. In this type of plot, advocated by Ackerman et al., (1987), the collector chain length is plotted against the log of collector concentration for 50% flotation. In this way the problems of natural hydrophobicity and the problem of slow approach to complete flotation above $\sim 75\%$ recovery are obviated. All of the ore pyrites generally float in a similar manner except for these differences:

- (1) The great variation in floatability with ethyl xanthate
- (2) The slightly different response to the various pyrites with dodecyl xanthate
- (3) The superior ease of flotation of the Black Hills, SD pyrite

Figure II-6. Effect of xanthate alkyl chain length on the flotation of various ore-source pyrites.

Optimum flotation occurs using a hydrocarbon chain length of C-5 to C-12 except for the Rico, CO pyrite where the C-2 xanthate is equally effective.

Note from Figure II-6 that the effectiveness of ethyl (C-2) xanthate varies by three orders of magnitude. It is not a very effective pyrite collector except for the Rico, CO pyrite and for those from Peru and the Black Hills, SD. Note from Figures II-1, II-4 and II-5 that these three pyrites are those that show the greatest natural floatability, this indicates that the xanthate effectiveness is being given a "boost" by the natural floatability.

Figure II-6 also shows that generally the C-12 xanthate floats pyrite in a manner similar to the C-5 and C-8 xanthates. The Rico, CO sample is an exception. A review of Figures II-1 to 5 confirms this generalization at other all xanthate concentrations. While the position of amyl (C-5) xanthate is similar to that of octyl (C-8) using the 50% recovery criterion, Figures II-1 to 5 show that for ~90% recovery the C-5 is inferior to C-8 or C-12 except for the Mexican (Figure II-3) and Rico, CO pyrites (Figure II-4).

The general shape of these curves is similar to that noted by Ackerman, et al. (1987) for the flotation of pyrite, chalcopyrite, bornite, chalcocite and covellite at pH 10.5. These authors found optimum flotation of these sulfides to occur with C-5 to C-8 xanthates. The ethyl xanthate was inferior to these two xanthates and the effectiveness of the C-12 xanthate was variable. For pyrite and chalcopyrite, the effectiveness of C-12 xanthate was similar to or slightly better than the C-5 and C-8 xanthates. However, for bornite, chalcocite and covellite, the C-12 xanthate was substantially inferior to the C-5 and C-8 forms.

Coal-Source Pyrite

Similar tests were run with nine different coal-source pyrites from anthracite and from low and medium volatile and high volatile A and B bituminous coal seams (Table II-1). The primary flotation data are shown in Figures II-7 to 11 and the concentration for 50% recovery as a function of xanthate chain length and concentration is given in Figure II-12.

Anthracite wall pyrite (P-1), that was highly metamorphosed during coalification,

Figure II-7. Flotation of anthracite wall (P-1) and seam (P-2) coal pyrite with various xanthates.

Figure II-8. Flotation of Pittsburgh seam coal pyrite, (P-5) (Osage, WV) with various xanthates.

Figure II-9. Flotation of Pittsburgh seam coal pyrite (P-11) (Greene Co., PA) with various xanthates.

Figure II-10. Flotation of KY #11 coal pyrite (P-7) with various xanthates.

Figure II-11. Flotation of Lower Kittanning coal pyrite, (P-10)
(Clarion, Co.) with various xanthates.

Figure II-12. Effect of xanthate alkyl chain length on the flotation of various coal-source pyrites.

is the one that responds to flotation most nearly like ore pyrite (Figure II-7).

Flotation with C-5, C-8 and C-12 xanthates requires about the same collector concentration as does ore pyrite ($\sim 10^{-6}$ M). The effectiveness of these three xanthates is similar, though recovery increases slightly as the hydrocarbon chain becomes longer. Ethyl (C-2) xanthate is a relatively poor collector even at 10^{-4} - 10^{-5} M as is shown in Figure II-7. Flotation recovery decreases slightly above 5×10^{-5} M with the KEtX.

The pyrite taken from in or near the anthracite seam (P-2) is decidedly less floatable than the P-1 anthracite wall samples. It requires about 5×10^{-5} M, for its recovery with the C-8 and C-12 xanthates, somewhat more for the C-5 xanthate and the C-2 xanthate is again an ineffective collector. This difference is not unexpected in view of the differences between these pyrites reported by Esposito et al. (1987) with regard to morphology (more porous grains in P-2) and the lower density and higher surface area of the P-2 sample as compared to the P-1 sample.

For the two Pittsburgh seam samples P-5 and P-11 (Figures II-8 and II-9), a new pattern emerges in that the C-12 xanthate is not an effective collector even at a concentration of $\sim 10^{-3}$ to 5×10^{-3} M. The C-12 form is generally inferior even to the C-2 xanthate. For the P-5 sample, the C-5 xanthate is superior to C-8 while for P-11 the reverse is generally true. The P-5 Pittsburgh seam sample takes slightly more xanthate for its flotation than does the P-11 sample. These two samples of pyrite from the Pittsburgh seam require $\sim 5 \times 10^{-4}$ M of the most favorable xanthate for $> 90\%$ recovery, among the highest quantities of collector for the flotation of any of the bituminous coal-source pyrite tested. Note also for both pyrites, that too much collector ($> \sim 10^{-4}$ M) may be disadvantageous for pyrite collection.

The KY #11 pyrite, P-7 shows a still different pattern (Figure II-10) with collector effectiveness following the pattern:

while for the Lower Kittanning, P-10 sample the order of the KDDX and KAmX are reversed (Figure II-11). Also for the P-10 sample, ethyl xanthate appears somewhat effective but only at very high collector levels ($\sim 10^{-2}$ M).

Comparative flotation of coal-source pyrites. These data are consolidated in Figure II-12 for ease of comparison. The most notable feature is that even with the most favorable xanthate (Octyl, C-8), the variation in collector concentration for 50% recovery varies by more than two orders of magnitude for the most favorable (P-1) and least favorable situation (P-5). For flotation with dodecyl (C-12) xanthate, the variation exceeds 100,000-fold. In no case was ethyl (C-2) xanthate found to be a very effective collector for these coal-source pyrites, whereas for ore-source pyrites a collector concentration of 10^{-5} M for even this relatively poor pyrite collector floated four of the six samples tested (compare with Figure II-6).

For the bulk of these coal-source pyrites, the C-5 and C-8 xanthates were generally the best collectors. With the P-5 and P-11 (Pittsburgh seam) samples, the C-12 xanthate was massively inferior to the C-5 and C-8 forms, while for the P-1, 2, 4, 6 and 7 samples the three xanthates with the longest hydrocarbon chains were roughly equivalent.

Comparison of Figure II-6 (ore-source pyrites) with Figure II-12 (coal-source pyrites)

The comparison shows these features:

- There is a greater variability in the amount of collector required for the flotation of coal-source than for ore-source pyrite.
- Under the most favorable conditions, it takes more collector to float coal-source than ore-source pyrite, ranging from 10- to 1000-fold more depending on the pyrites being compared. It averages about 30-fold more: $\sim 10^{-6}$ M for ore-source pyrite and $\sim 3 \times 10^{-5}$ M for coal-source pyrite.
- For most of the ore- and coal-source pyrites, the amyl, octyl and dodecylxanthates show roughly equivalent effectiveness for a given pyrite, though for a few coal-source pyrites the dodecyl form is less effective than is amyl or octyl.
- The effectiveness of dodecyl (C-12) xanthate is variable. For ore-source pyrite, it is generally about as good as the C-5 and C-8 forms whereas for coal-source pyrite its effectiveness ranges from equivalent to C-5 or C-8 xanthate to infinity worse.

- Only in the case of one pyrite (ore-source, Rico, CO) could ethyl xanthate be considered as effective a pyrite collector as were xanthates of greater hydrocarbon chain length.

Effect of pH

To evaluate the effect of pH on pyrite flotation, the Pittsburgh seam sample, P-5 was tested in a series 2×10^{-4} M xanthate solutions (Figure II-13). The selection of this collector concentration was based on the results at pH 7 given in Figure II-12. KAmX and KOcX are shown in Figure II-13 to be the best collectors under these conditions while neither KEtX or KDDX are very effective at any pH value in the range pH 4-10.5.

Shown in Figure II-14 is the flotation of Manora, Mexico and Peru ore pyrites, as a function of pH, in a 2×10^{-6} M solution of KAmX. This collector concentration was chosen based on the average data of Figure II-6. The sample from Mexico floated the best over the entire range of pH 4 to 10. The flotation of Manora and Mexico samples with KDDX was found to be nearly identical to that with KAmX. It is obvious that pyrites from different sources respond differently to xanthate flotation.

Other Collectors

Five other collectors, given in Table II-2 were evaluated for their effectiveness in floating three coal-source pyrites: Anthracite wall (P-1), Pittsburgh seam (P-5), and Kentucky #11 (P-7). These collectors were chosen because Ackerman (1980) found them to be good collectors for an ore-source pyrite. It will be noted from Table II-3 that none of the collectors are effective at a collector concentration of 10^{-5} M except for the two phenyl thiocarbamates when floating the anthracite wall pyrite, P-1. Tests at higher reagent concentrations of 5×10^{-5} M, and, in some cases, 10^{-4} M, give evidence of Pittsburgh P-5 pyrite floatability with NPh-OH TC, Imidazoline and IpxPhF, and the KY No. 11 Seam, P-7 pyrite with the latter compound only.

The Effect of Oil on Pyrite Flotation

Figure II-15 shows the influence of No. 2 fuel oil on the floatability of several pyrites. This reagent was tested since it is the most popular coal flotation collector

Figure II-13. Effect of pH on the flotation of Pittsburgh seam coal pyrite (P-5) with various xanthates.

Figure II-14. Effect of pH on the flotation of several ore-source pyrites with amyl xanthate (2×10^{-6} M).

Table II-3. Effectiveness of Various Collectors for Coal-Source Pyrites at pH 7.

% Recovery @ 10^{-5} M			
	P-1	P-5	P-7
Collector*	Anth (Wall)	Pitts. Seam	KY #11
sBbIp TC	13	43	5
NPh-OH TC	75	23	8
NPh-SH DTC	87**	33	3
Ip XPh F	17	31	15
Imidazoline	3	27	14

* See Table II-2 for Collector descriptions

** Extrapolated value

(Aplan and Arnold, 1991). At the $10\ \mu\text{l}$ level all of the pyrites are seen to float, though the anthracite wall pyrite floats less than will the Pittsburgh seam, P-5 pyrite or the Peru, Mexico or Black Hills ore pyrites. As a frame of reference, if it is assumed that the molecular weight of No. 2 fuel oil is similar to that of dodecane, then the $10\ \mu\text{l}$ addition corresponds to a solution concentration of $\sim 5 \times 10^{-5}$ M. Clearly, the use of oil can promote the accidental flotation of pyrite.

The Influence of Oxidation on the Natural Floatability of Pyrite

The fundamental reasons for the natural floatability of pyrite have been given in Part I of this study. The following study was designed to evaluate the natural floatability of pyrite on a comparable basis to the flotation tests reported in Figures II-1 to 5 and 7 to 11. Attention has previously been called to the apparent natural floatability of $\approx 20\%$ for several of the ore and coal pyrites previously studied. For these tests, pyrite was quickly ground and sized (~ 30 sec.) and the 48x65 Mesh material exposed to air for various time periods. The sample was then transferred to the porous frit flotation cell containing double distilled water. Ten μl MIBC frother was then added and the sample conditioned for one minute. The froth was collected

Figure II-15. Effect of No. 2 fuel oil on the flotation of several coal- and ore-source pyrites.

for 40 and 120 sec., though only the 120 sec. flotation data are reported in Figure II-16. The data indicates that coal-source pyrite appears to be much less naturally floatable than is ore-source pyrite. With one notable exception, prolonged oxidation has little effect on most of the pyrite samples except perhaps a slight diminution in natural floatability. The major exception is the ore-source sample from Peru, P-8 where natural floatability reaches a maximum of ~ 80 % in about 10 hours and then decreases to zero at the end of 24 hours.

SUMMARY

1. Coal-source pyrites float much more poorly with xanthate collectors than do ore-source pyrites
 - There is a variation between these classes of pyrite.
 - There is a variation among the members of each class.
2. Anthracite wall pyrite is the only coal pyrite that floats similarly to ore-source pyrite.
3. For the flotation of coal-source pyrites
 - amyl (C-5) and octyl (C-8) xanthate are usually the best
 - ethyl (C-2) xanthate is nearly always a poor collector
 - dodecyl (C-12) xanthate varies from useless to excellent
 - xanthate required varies by 100-fold or more for the different pyrites
 - average minimum concentration for C-5 and C-8 xanthate is $\sim 3 \times 10^{-5}$ M
4. For the flotation of ore-source pyrites
 - ethyl (C-2) xanthate poorest
 - amyl (C-5), octyl (C-8) and dodecyl (C-12) are the best collectors for each pyrite and they act similarly
 - xanthate required varies by 30-fold (but 5 of 6 samples only 4-fold) for the different pyrites using amyl, octyl or dodecyl xanthate
 - average minimum concentration for amyl, octyl and dodecyl xanthate is $\sim 10^{-6}$ M
5. Greater than ~ 60 mg/l of No. 2 fuel oil causes substantial flotation of both coal- and ore-source pyrites.

Figure II-16. Effect of oxidation on the natural floatability of several coal- and ore-source pyrites.

6. Only one pyrite sample (from an ore source) showed any major amount of natural floatability due to oxidation and in the absence of collector, though several pyrites show some evidence of a small amount of natural floatability (ore-more so than coal-source pyrite).

REFERENCES

- Ackerman, P. K., "Evaluation of Flotation Collectors for Copper Sulfides and Pyrite Using Rate and Recovery Criteria", M. S. Thesis, The Pennsylvania State University, University Park, PA, 1983.
- Ackerman, P. K., "A Study of Sulfide Mineral Collectors", Ph.D. Thesis, The Pennsylvania State University, University Park, PA 1986.
- Ackerman, P. K., Harris, G. H., Klimpel, R. R., and Aplan, F. F., "Evaluation of Flotation Collectors for Copper Sulfides and Pyrite. III. Effect of Xanthate Chain Length and Branching", Int. Jol. Min. Proc., 21:141-156, 1987.
- Aplan, F. F., "Coal Flotation -- The Promise and the Problems" in Advances in Coal and Mineral Processing Using Flotation, Eds., S. Chander and R. R. Klimpel, SME, Littleton, CO, 95-104, 1989.
- Aplan, F. F., Arnold, B. J., "Flotation" in Coal Preparation, 5th Edition, Eds., J. W. Leonard and B. C. Hardinge, SME, Littleton, CO, 450-485, 1991.
- Carrucio, F. T., "The Quantification of Reactive Pyrite by Grain Size", in Third Symposium on Coal Mine Drainage Research, Mellon Institute, Pittsburgh, PA, 123-131, 1970.
- Chernowsky, F. J. and Lyon, M., "Comparison of the Flotation and Adsorption Characteristics of Ore and Coal-Pyrite with Ethyl Xanthate", Trans. AIME, 252:11-14, 1972.
- Esposito, M. C., Chander, S. and Aplan, F. F., "Characterization of Pyrite from Coal Sources", in Process Mineralogy, VII, Eds., A. H. Vassiliou, D. M. Hausen and D. J. T. Carson, TMS, Warrendale, PA, 475-493, 1987.
- Foster, L. S., "Flotation Fundamentals, Part II", University of Utah, Tech. Paper No. 2, Salt Lake City, UT, 1928.
- Fuerstenau, M. C., "An Improved Micro-Flotation Technique", Eng. Mng. Jol. No. 11, 165:109-109, 1964.
- Hirt, W. C., and Aplan, F. F., "The Influence of Operating Factors on Coal Recovery and Pyritic Sulfur Rejection During Coal Flotation", Proc. and Util. of High Sulfur Coals, IV, Eds., P. R. Dugan, D. R. Quigley and Y. A. Attia, Elsevier, Amsterdam, 339-356, 1991.
- Miller, K. J., "Coal Pyrite Flotation", Trans. AIME, 258:30-33, 1975.

Miller, K. J., "Evaluation of Reverse Coal-Pyrite FLOTation for a Prepared Ohio Advanced Coal-Cleaning Test Facility", DOE/PETC/TR89/8 (DE 89016405), 1989.

Miller, K. J. and Baker, A. F., "Flotation of Pyrite from Coal", USBM TPR-51, 1972.

Olson, T. J. and Aplan, F. F., "The Floatability of Locked Particles in a Coal Flotation System", in Applied Mineralogy, Proceedings 2nd ICAM, Eds. W. C. Park, D. M. Hausen and R. D. Hagni, TMS, Warrendale, PA, 367-393, 1985.

Olson, T. J., and Aplan, F. F., "The Effect of Frothing and Collecting Agents on the Flotation of Coal, Pyrite and Locked Particles in a Coal Flotation System", in Proc. and Util. of High Sulfur Coals. II, Eds., Y. P. Chugh and R. D. Caudle, Elsevier, Amsterdam, 71-82, 1987.

Smith, F. G., "Variation in the Properties of Pyrite", Am. Mineralogist, 27:1-19, 1942.

Smith, E. E., Svanks, K. and Shumate, K., "Sulfide to Sulfate Reaction Studies", in 2nd Symp. on Coal Mine Drainage Research, Bituminous Coal Research, Inc., Monroeville, PA, 12-34, 1968.

PART II. MODULATION OF PYRITE AND COAL HYDROPHOBICITY

PART II-B. REACTION PRODUCTS FROM COAL-SOURCE PYRITE OXIDATION

ABSTRACT

Coal-source pyrite is known to oxidize much more readily than does ore-source pyrite. While ore-source pyrite may remain bright for decades, coal-source pyrite is known to react with humid air in a few hours. A laboratory procedure for the rapid oxidation of coal-source pyrite has been developed.

The reaction products formed on the surface of coal-source pyrite on exposure to the atmosphere for a few hours or a few months, have been evaluated by optical and scanning electron microscopy, by microprobe analysis and by X-ray diffraction. Seven different iron sulfates and gypsum have been identified. Of these, Gypsum ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) and Rozenite ($\text{FeSO}_4 \cdot 4\text{H}_2\text{O}$) appear to occur the most frequently in our studies. The quantity and type of the pyrite reaction products appear to be highly variable based on the source of the pyrite or raw coal.

INTRODUCTION

Pyrite from coal sources is known to be substantially different from the pyrite found in ore sources (Chernowsky and Lyon, 1972; Esposito, Chander and Aplan, 1987). As a consequence, it is not just a simple matter of transferring the vast amount of technical information on ore-source pyrite to the problems related to the removal of pyrite from coal during the coal preparation process. The major differences between coal-source and ore-source pyrite are related to differences in morphology of the different pyrites and to their oxidation rates (Esposito, Chander and Aplan, 1987). The differences in the oxidation rates of various pyrites appear to be related to the average crystallite size and to their surface area (Smith, Svanks and Shumate, 1968; Carrucio, 1970; Esposito, Chander and Aplan, 1987), and both of these, in turn, are represented by morphological differences. Ore-source pyrites have smooth surfaces and small surface areas whereas coal-source pyrites show some combination of porous grains, granular masses, framboids, and cell fillings and imprints.

The BET surface areas of coal-source pyrites range from 2 to 5 times greater than the area of ore pyrite for anthracite-source material, and from 8 to 30 times greater for bituminous source pyrites (Esposito, Chander and Aplan, 1987).

Accurate quantification of the oxidation rates of coal-source pyrites has been difficult (Esposito, Chander and Aplan, 1987), and the values recorded for the oxidation rate of coal-source pyrites are probably much too low.

On an anecdotal basis, the reaction rates for coal-source pyrites are probably best expressed in reciprocal hours while for ore-source pyrites they might best be given in reciprocal decades. Ore-source pyrite when exposed to air will often remain bright for decades while coal-source is known to oxidize overnight on a humid day, forming the well-known "sulfur bloom" and a plethora of iron sulfates. To illustrate the contrasting nature of ore-source pyrite, one of the authors (FFA) a decade ago collected a piece of pyrite from a mine dump in Leadville, CO which was likely mined well over 50 years ago. The specimen remains bright to this day.

This section of the study will focus on the reaction products of coal-source pyrite. This area has been studied but little; through the Ames Laboratory report by Junk et al. (1986) is a notable exception. They studied the composition of the reaction products on pieces of coal and refuse and on the leachates from coal refuse and plant waters. On the coal and refuse samples, they identified shale, illite, kaolinite, gypsum, quartz, calcite, siderite and pyrite. From the residues of leachates and plant process waters from IL and WV bituminous sources, they identified Bassinite ($\text{CaSO}_4 \cdot 0.5\text{H}_2\text{O}$), Gypsum ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$), Szomolnokite ($\text{FeSO}_4 \cdot \text{H}_2\text{O}$), Rhomboclase ($\text{FeH}(\text{SO}_4)_2 \cdot 4\text{H}_2\text{O}$), Coquimbite ($\text{Fe}_2(\text{SO}_4)_3 \cdot 9\text{H}_2\text{O}$) and from the IL plant, Thenardite (Na_2SO_4) and Halite (NaCl).

The oxidation of coal-source pyrite leads to:

- acid mine drainage
- acid drainage from stockpile and refuse piles
- acid waters in preparation plants leading to
 - corrosion of plant equipment and piping
 - need to neutralize with, e.g., lime
 - plant scale
- erratic response to flotation

EXPERIMENTAL MATERIALS AND METHODS

The basic samples studied were:

- (1) Scrapings from coal, pyrite and refuse samples taken from raw coal sources and preparation plants. These were hand picked or selected under the microscope.
- (2) Growths from purified coal-source pyrite samples (many of these are the same purified pyrite samples as used in Part II-A). The growths were hand picked under the microscope.
- (3) Bulk and segregated precipitates from supersaturated solutions of washings from various purified pyrite samples.

The first category of samples were from the sources given in Table II-4.

Table II-4. Sources of raw coal, pyrite and refuse samples showing pyrite oxidation products.

Pittsburgh seam, Cumberland Mine, Greene Co., PA
Upper Kittanning, C-prime seam, Slope 33 Mine, Cambria Co., PA
Pocohontas No. 3 seam, Pinnacle Prep Plant, Wyoming Co., WV
Upper Freeport seam, Helen Mine, Indiana Co., PA - sample taken from a flotation launder at CQ, Inc., pilot plant, Homer City, PA
Lower Clarion/Lower Kittanning seams (probably), refuse sample from Doverspike Bros. Prep Plant, Punxsutawney, PA. Exact seam source unknown.
Lower Kittanning seam, sulfur balls from C&K Coal Co., Clarion Co., PA
KY No. 11 seam, sulfur balls from Camp No. 2 Mine, Peabody Coal Co., Union Co., KY
IL No. 5 seam, from raw coal surface, Hamilton Co., IL

The pyrites for the latter two categories were those of the purified coal-source pyrite samples listed in Table II-1, and most of them (P-1 to P-7) have been characterized by Esposito, Chander and Aplan (1987).

To obtain precipitated reaction products from leachates from the pyrite samples, the individual purified samples were contacted with water. The pyrites were then allowed to dry and stand exposed to the atmosphere for several days, and the process repeated. The

washings were combined and the water evaporated by gently heating (40° C) in a water bath under vacuum. The evaporation of the last amount of fluid water was accomplished open to the atmosphere and at room temperature.

For those samples where it was desired to grow reaction coatings on pyrite, the growth was typically accomplished in a natural setting. That is, the samples were allowed to stand exposed to the room air for days, weeks and in a few cases months. This growth was facilitated by the hot, humid days that accompanied the summer time when most of this work was done. Toward the end of the study, a technique for over-night growth of crystals was developed. This will be described in the results and discussion section.

Reaction products were given a preliminary identification by visual and microscopic examination and by evaluation of their water solubility (most of the products, except gypsum, are water soluble. All results were, however, checked by X-Ray diffraction analysis. A Rigaku Geigerflex X-Ray diffractometer using $\text{CuK}\alpha$ radiation was used to determine the crystal structure. Two sample preparation techniques were used: (1) the crystalline material was ground in ethanol in an agate mortar and pestle and a few drops of the ground suspension were then placed on a glass slide and allowed to evaporate; (2) the material was ground in the mortar and pestle and screened at 400 mesh over a glass slide coated with a thin layer of vacuum grease. Method 2 worked the best when there was more than one mineral present. Relatively simple patterns were evaluated by the Johnson/Vand Search Match Technique and the Johnson/Smith PSU/XRD Search and Identification procedure for the JCPDS data analysis. More complicated patterns resulting from the presence of several different species were done by hand. A crude quantification was achieved by evaluating the height of the prominent diffraction lines and assigning the system: M = major, S = small, T = trace.

Toward the end of the study when overnight generation of reaction products had been achieved, monocrystalline material was hand packed with a needle under the microscope and mounted with collodian in a Gandolfi modified Debrye-Scherrer film camera manufactured by Huber, Instruments, Germany. Data analysis was by the Johnson/Vand Search Match Program of the JCPDS file.

EXPERIMENTAL RESULTS AND DISCUSSION

Development of a Rapid Pyrite Oxidation Procedure

Initial pyrite oxidation was accomplished *au naturel*, i.e., exposure to the atmosphere, for days or weeks and waiting for something to happen. Only in a few instances was this achieved over-night and it could not be regularly repeated. Innumerable attempts to repeat nature using a desiccator with controlled humidity, or a controlled humidity - temperature tent structure with heater and vaporizer proved fruitless over a period of several months. Reflection on how nature was able to do something, simply, that we could not readily duplicate, lead to a consideration of the humidity-temperature-time profile. The sample was placed in a plastic tent and at a high humidity ($\sim 97\%$) generated with a household humidifier. The temperature used was $30\text{--}35^\circ\text{C}$., though this is not especially critical. The tent containing the sample was then placed outdoors overnight where the temperature might drop to $\sim 20^\circ\text{C}$. This process condensed water on the pyrite surface and initiated a reaction. In the morning, a surface growth on the pyrite was visible. In some cases, where the overnight temperature drop was great, a film of liquid was seen on the pyrite surface in the morning. Crystal growth was promoted by drying for a few minutes in air. The critical aspects of this process are to expose the pyrite to a relatively high humidity in a confined space and then condense water on the surface by dropping the ambient temperature.

Identification of Reaction Products

The species identified on raw coal and on pyrite and in crystallized washings from purified coal-source pyrite samples is given in Table II-5. There are seven different iron sulfates, two forms of gypsum and a clay (the latter identified only on scrapings from a raw coal sample from IL No. 5 seam). The specific clay was not identified but it was likely an illite or kaolinite. Of the seven iron sulfates, five are ferrous sulfates, the iron in one is in the ferric form (Rhomboclase) and both ferrous and ferric iron are present in Metavoltine.

The various reaction products identified in this study are given in Table II-6. Note the great variety of products produced on the sulfur balls, refuse and raw coal samples under normal exposure to the atmosphere. Note also the substantial variation in the kind and amount of the reaction product produced on each specimen tested. It is obvious that a great

Table II-5. Species identified on pyrite and raw coal and from chrystallized washings from oxidized pyrite*

CODE	NAME	TEXTBOOK FORMULA	TEXTBOOK DESCRIPTION	JCPDS NO.
SZ	Szomolnokite	$\text{FeSO}_4 \cdot \text{H}_2\text{O}$	Yellow monoclinic	21-925
RD	Rozenite	$\text{FeSO}_4 \cdot 4\text{H}_2\text{O}$	White, monoclinic	19-632
SI	Siderotil	$\text{FeSO}_4 \cdot 5\text{H}_2\text{O}$	Pale green, triclinic	22-357
ME	Melanterite	$\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$	Pale blue-green monoclinic	22-633
RH	Rhomboclase	$\text{FeH}(\text{SO}_4)_2 \cdot 4\text{H}_2\text{O}$	Colorless, White-gray, Yellow, Orthorhombic	27-245
HA	Halotrichite	$\text{FeAl}_2(\text{SO}_4)_4 \cdot 18\text{H}_2\text{O}$	Colorless monoclinic	39-1387
MV	Metavoltine	$\text{Na}_6\text{K}_2\text{Fe}_7(\text{SO}_4)_{12} \cdot 22\text{H}_2\text{O}$	Yellow, orange-brown	29-1043
GY	Gypsum	$\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$	white, monoclinic	21-816
CL	Clay	-	-	-

* Data from JCPDS file (Joint Committee on Powder Diffraction Studies).

Table II-6. Variation of pyrite reaction products depending on coal source and conditions

Pyrite or Coal Source	Description	Composition		
		Major	Small	Trace
Scrapings from sulfur balls, refuse and raw coal				
IL #5		RO	-	RH,ME,SI,Clay
KY #11 (P-7)		RO,SI	-	GY
L. Clarion (P-9)		SZ	-	-
L. Clarion/ L. Kittanning	yellow-white	GY	-	SZ
U. Kittanning	red-brown	SI	-	-
U. Kittanning		SZ,MV	RO	RH
Pitts. (P-11)		RH	SI	SZ,ME
U. Fpt.	Yellow ¹	SI	-	SZ,GY
U. Fpt.		SZ	SI	GY
Growths on pyrite-hand picked under microscope				
Pocoh. #3	yellow	MV	-	-
Pocoh. #3		HA	-	-
Pitts. (P-11)	clear fibers	RO	-	-
Pitts. (P-11)	white rods	RO	-	-
Pitts. (P-11)	white, amor- phous to the eye	RO	-	-
Precipitated from supersaturated solution of washings				
Anth (Wall) (P-1)		GY	-	-
Anth (Seam) (P-2)		GY	RO	-
L. Kittanning (P-3)		GY,SZ	RO	-
L/M Kittanning (P-4)		SZ	GY	-
Pitts. (WV) (P-5)		RH	MV	SZ
Ditto + NaOH		GY	RO	-
Pitts. (WV) (P-5)		SI	GY	-
U. Fpt. (P-6)		GY	RO	-

¹ from flotation launder

deal of work will have to be done before the reaction product can be predicted and controlled.

The growths on Pocahontas No. 3 seam and Pittsburgh seam pyrites were grown overnight by the procedure outline in the previous section. Usually no more than two or three species were noted, and often only one. A single species was handpicked under the microscope for X-ray identification with the Debye-Scherrer camera. Figure II-17 shows yellow metavoltine on a raw coal sample from Pocahontas No. 3 seam and Figure II-18 shows halotrichite on a sample from the same source.

Figure II-19 shows the colorless crystalline and Figure II-20 the white crystalline form of Rozenite, while Figure II-21 shows a more amorphous (to the naked eye) form of Rozenite, all on Pittsburgh P-11 pyrite. Figure II-22 shows a precipitate from the P-4 (Lower/Middle Kittanning) pyrite washings. From Table II-6, it is seen to contain Szmolnokite and gypsum.

Optical microscopic studies of several of the specimens were made under conditions of higher magnification. A typical gypsum growth on Pittsburgh seam (P-5) pyrite is shown in Figure II-23 and this growth can be greatly facilitated by immersing the specimen in CaCl_2 solution and then removing it to stand exposed to the atmosphere for several days (Figure II-24). Scanning Electron Microscope (SEM) and microprobe studies were then made on several specimens. In Figure II-25 the growth of gypsum and an iron sulfate on a piece of refuse taken from the Doverspike preparation plant is seen. This specimen was first gold coated to improved conductivity. The presence of Calcium and sulfur by microprobe analysis indicates that the large growth is a gypsum crystal though on the upper portion, the presence of iron and sulfur indicates that an iron sulfate is also present. Bulk scrapings from this sample, have indicated the presence of Gypsum and Szomolnokite (see Table II-6).

Another SEM/microprobe of reaction product on KY No. 11 (P-7) pyrite is given in Figures II-26 and II-27. The conductivity on this specimen was adequate so that a gold coating was not required. The microprobe maps for calcium and sulfur and the absence of iron indicates the crystal in the lower center is gypsum (Figure II-25). An iron sulfate is also present and by inference from Table II-6 (which gives the analysis of the bulk scrapings from which this sample was taken) this is probably a mixture of Rhomboclase and Siderotil. In Figure II-27B, the silicon just above the gypsum crystal is probably due to quartz. No

Figure II-17. Metavoltine on Pocahontas No. 3 raw coal (X25).

Figure II-18. Halotrichite on Pocahontas No. 3 raw coal.

Figure II-19. Colorless fibers of Rozenite on Pittsburgh (P-11) pyrite (X25).

Figure II-20. White form of Rozenite with a few colorless fibers in the upper left of the photo. Same pyrite as in Figure II-19 above (X25).

Figure II-21. Rozenite (amorphous to the naked eye) on Pittsburgh (P-11) pyrite (X25).

Figure II-22. Szomolnokite and gypsum crystallized from washings of Lower/Middle Kittanning (P-4) pyrite (X230).

Figure II-23. Gypsum growths on Pittsburgh seam (P-5) pyrite (X373).

Figure II-24. Gypsum growths promoted by immersing P-5 pyrite in 0.1 M CaCl_2 prior to oxidation (X373).

Figure II-25. Gypsum crystal formed on refuse from Doverspike Preparation Plant.
Iron sulfate growth on top of gypsum crystal (X800).
A. SEM micrograph
B. Ca Map
C. Fe Map
D. S Map

A **B** **C** **D**

Figure II-26. Growth on KY No. 11 pyrite (P-7)

A. SEM micrograph

C. Fe Map

B. Ca Map

D. S Map

A

B

C

Figure II-27. Same sample and location as in Figure II-15 (X800)

A. SEM micrograph

B. Si Map

C. Mg Map

aluminum was found in this spot which tends to rule out a clay. The microprobe analysis also indicated 1-2% Mg but the magnesium map of Figure II-27C shows the Mg generally dispersed throughout.

A review of the data indicates that Gypsum and Rozenite appear to occur most frequently. No sulfur was identified on the surface of any of the samples studied. The ready formation of Gypsum on the purified pyrite specimens was unexpected as spectroscopic analysis (Esposito, Chander and Aplan, 1987) shows only a minor amount of calcium in these purified pyrite samples.

SUMMARY

1. Seven different iron sulfates and gypsum growths have been identified on the surface of oxidized pyrites and in the crystallized washings from oxidized pyrite.
2. Rhomboclase, $\text{FeH}(\text{SO}_4)_2 \cdot 4\text{H}_2\text{O}$ and Gypsum, $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$ would appear to occur somewhat more frequently than do the other compounds identified in this study.
3. The reaction products show a wide range in composition and morphology.
4. Under proper conditions, coal-source pyrite may be made to react overnight with the atmosphere to form a variety of oxidation products. Accurate prediction and control of the reaction product formed must await further research.
5. The most common color of the reaction products is white.
6. The well-known 'sulfur bloom' isn't sulfur. Some of it has been identified as Metavoltine (which contains both Fe^{+2} and Fe^{+3}). Other possibilities would be Szomolnokite, Rhomboclase, Melanterite, Jarosite or attributable to the oxidation of some of the Fe^{+2} to Fe^{+3} .
7. The large observed differences in the reactivity between coal- and ore-source pyrite must be due either to their differing nature (morphology, surface area, crystallite size), or to a passivation which favors the ore-source pyrite. This might be analogous to the oxidation of aluminum metal which forms an alumina coating on its surface that effectively inhibits further oxidation of the bare metal.

ACKNOWLEDGEMENTS

The authors owe a special debt of gratitude to Dr. Deane K. Smith, Professor of Geochemistry and Mineralogy, The Pennsylvania State University, who provided invaluable assistance in the X-Ray procedures and in deciphering multiple component X-ray patterns.

REFERENCES

Carrucio, F. T., "The Quantification of Reactive Pyrite by Grain Size", in Third Symposium on Coal Mine Drainage Research, Mellon Institute, Pittsburgh, PA, 123-131, 1970.

Chernowsky, F. J. and Lyon, M., "Comparison of the Flotation and Adsorption Characteristics of Ore and Coal-Pyrite with Ethyl Xanthate", Trans. AIME, 252:11-14, 1972.

Esposito, M. C., Chander, S. and Aplan, F. F., "Characterization of Pyrite from Coal Sources", in Process Mineralogy, VII, Eds., A. H. Vassiliou, D. M. Hausen and D. J. T. Carson, TMS, Warrendale, PA, 475-493, 1987.

Junk, G. A., Richard, J. J., Avery, M. J., Conzemius, R. J., Benson, J. E., and Chriswell, C. D., "Physical Coal Cleaning: Characterization of Constituents in Waste and Process Streams", Final Report DOE/NBM-7001097 (DE-877001097) US DOE/METC by Ames Laboratory, Iowa State University, Ames, IA.

Smith, E. E., Svanks, K. and Shumate, K., "Sulfide to Sulfate Reaction Studies", in 2nd Symp. on Coal Mine Drainage Research, Bituminous Coal Research, Inc., Monroeville, PA, 12-34, 1968.

PART II. MODULATION OF PYRITE AND COAL HYDROPHOBICITY

PART II-C. ADSORPTION OF POLYSACCHARIDES AND SIMILAR COMPOUNDS ONTO PYRITE AND COAL.

ABSTRACT

A series of 13 natural starches, gums, cellulose products and their modifications were evaluated as to their adsorption onto both coal and coal-source pyrite. It was found that there is a great variation in the adsorption of various polymers onto a given pyrite and there is also a great variation in the adsorption of the same polymer onto pyrites from different sources. This observation probably explains why a given polymer may be a good depressant for the pyrite found in one coal and a poorer depressant for the pyrite from another coal source. Polymer structural considerations and charge were also found to play an important role in the adsorption of polysaccharides onto pyrite and onto coal.

INTRODUCTION

The concept of using high, molecular weight organic compounds to depress sulfide minerals is an old one, going back to the work of Bartsch (1924) who used gelatin and saponin as depressants. Taggart (1945) cited the use of a variety of organic colloids such as tannins, licorice, quebracho, dextrans and starches. More recently, the use of starches, gums and similar polymeric materials have been evaluated for the depression of pyrite during coal flotation (Perry and Aplan, 1985, 1988; Arnold and Aplan, 1990; Raleigh and Aplan, 1991; Choudhry and Aplan, 1991). Care must be used because these same compounds are also coal depressants (Im and Aplan, 1981; Perry and Aplan, 1988). Coal depression usually occurs at a higher depressant concentration than does pyrite depression, so a "window of opportunity" is present to allow the pyrite to be depressed without seriously affecting the flotation of the coal (Perry and Aplan, 1988).

While both Perry and Aplan (1985, 1988) and Choudhry and Aplan (1991) have studied the effectiveness of a variety of polysaccharides and similar compounds, all of their work was done using Pittsburgh seam pyrite. Other data (Arnold and Aplan, 1990; Raleigh and Aplan, 1991), infer that pyrite from other sources may act differently. In fact, differences

should likely be expected in view of the variation in the properties of coal-source pyrite from source to source (Esposito, Chander and Aplan, 1987).

The goal of this study was to evaluate the adsorption of polysaccharides and related compounds onto a broad variety of pyrites and coals.

EXPERIMENTAL MATERIALS AND METHODS

The eight highly purified pyrite and 10 coal samples used are shown in Table II-7. The pyrites are the same as those used in Part II-A and their chemical and physical properties have been described in detail in the literature (Esposito, Chander and Aplan, 1987). The coals were selected to cover the same or similar seams, as well as a broad range of coal ranks from sub-bituminous to anthracite. The coals used were all the 1.4 float fraction except for anthracite where the 1.55 float fraction was used. Gravity fractionation was done in a magnetite media to avoid contamination from halogenated hydrocarbons or heavy metal salts. The adhering magnetite was washed from the coal surface by a vigorous spraying with water.

The samples were prepared for adsorption testing and for surface area determination as follows:

Coal - This was hand ground in a ceramic mortar and pestle and sieved at 100x400 mesh. The fraction was then wet screened on a 400 mesh stainless steel screen with double distilled water. The particles were quickly dried (70° C) and stored in a vacuum dissicator over Drierite until used.

Pyrite - This was hand ground in an alumina mortar and pestle and sieved at 100x400 mesh. The particles were then placed in double distilled water and given a repeated ultrasonic treatment until all clays and other fine particles were removed. It was quickly dried at 70° C, re-sieved and stored in a vacuum dissicator over Drierite before use. If there was any evidence of oxidation (the most sensitive test was a sulfurous odor), the ultrasonic treatment was repeated.

The adsorption method was to contact the 100x400 mesh material with a dilute (150 ppm) solution of the polymer and agitate on a Burrell wrist action shaker for 5 minutes at pH 7. The material was filtered over a 3-inch stainless steel 400 mesh sieve and the polymer concentration in the solution that passed through the sieve was determined by the phenol-sulfuric acid method of Dubois et al., (1956) using an ultra violet spectrophotometer at 486

Table II-7. Pyrite and coal samples studied

Pyrites and Location	Coal seams, rank and location
P-1 Anthracite (wall), PA	C-1 Anthracite (an), PA
P-2 Anthracite (seam), PA	
P-3 Lower Kittanning, PA	C-2 Lower Kittanning, (lvb), PA
P-4 L/M Kittanning, PA	
P-5 Pittsburgh, WV	C-5 Pittsburgh (hvAb), PA
P-6 Upper Freeport, PA	C-3 Upper Freeport (mvb), PA
P-7 KY #11, KY	C-6 KY #11 (hvBb), KY
P-8 Ore pyrite, Huanzala, Peru	
	C-7 IN #6 (hvBb), IN
	C-8 IL #5 (hvBb), IL
	C-9 Bed 53, WY (Sub A), WY
	C-10 Dietz #3, WY (Sub B), WY

nm. Further details may be found elsewhere (Perry and Aplan, 1985, 1988)

The surface areas of the samples used for the study are given in Table II-8. To calculate the adsorption density only the Blaine surface areas were used. This is because the nitrogen used in the BET surface areas can get into the many micro pores found in coals which a bulky polymer could not reach. The authors feel that the Blaine area is probably a more realistic surface area to use.

The polymers used and their composition are given in Table II-9 and their structural aspects are given in Figures II-28 to II-30.

EXPERIMENTAL RESULTS AND DISCUSSION

The various polysaccharide and similar organic polymers used in this study were selected because of differences in their structural configurations. The basic adsorption data are given in Table II-10. It will be immediately noted from these data that there is a great variation in the adsorption density on pyrite depending not only on the pyrite source but upon the particular organic polymer used. The same holds true for the adsorption of these polymers onto the various coals. For pyrite, the adsorption density varies from 1.6 mg/m² for Gum Ethylex 3095 onto P-1 pyrite to 30.3, mg/m² for the adsorption of Guartec SJM onto P-7 --- a 19-fold difference. The variation of polymer adsorption onto coal is even greater as it varies from 0.2 mg/m² for CMC 7H adsorption onto C-7 and C-8 coal to 11.2 mg/m² for the attachment of Cato-2 starch onto C-10 coal. This represents a 56-fold variation. The mean adsorption of these polymers onto pyrite is more than twice that for the coal.

While there is a variation in the adsorption onto the various pyrites, it should be noted that, on average, the cationic starch, Cato-2, the hydroxyethyl cellulose, Natrosol 150 GXR and the three guar gums Jaguar C-13 (cationic) and Guartec SJM and Jaguar HP-11 (both unmodified guar) show the greatest attachment to pyrite. For coal, the best adsorbed compounds are the high amylopectin (branched chain) starch (Amioco), the cationic starch, Cato-2 and the unmodified guar, Guartec SJM. Two of these were also among the best adsorbed onto pyrite. This indicates that they should be used in judicious quantities so as not to run the risk of depressing the coal while attempting to depress the pyrite.

In order to facilitate rapid assimilation of this large amount of data, the simplified

Table II-8. Specific surface areas of pyrite and coal samples*

Sample	Blaine Permeability (m ² /g)	N ₂ (m ² /g) ⁺
Pyrite Samples		
P1	0.0260	0.101
P2	0.0272	0.266
P3	0.0323	0.362
P4	0.0243	0.854
P5	0.0339	1.502
P6	0.0310	0.951
P7	0.0308	0.597
P8	0.0295	0.045
Coal Samples		
C1	0.1004	0.9082
C2	0.1185	0.3829
C3	0.1334	0.3649
C4	0.1348	0.2460
C5	0.1299	0.3537
C6	0.1456	5.8470
C7	0.1513	20.3460
C8	0.1776	52.2300
C9	0.1261	0.2550
C10	0.1225	0.2430

* 100 x 400 mesh, deslimed prior to measurement

+ Nitrogen used for B.E.T. measurement

Table H-9. Organic polymers used.

<u>Class</u>	<u>Trade Name</u>	<u>Composition*</u>	<u>Manufacturer</u>
STARCH α /trans OH configuration	Hylon VII	Corn, high amylose nonionic, (o)	National Starch and Chemical Corp.
	Amioca	Corn, high amylopectin, nonionic (o)	National Starch and Chemical Corp.
	Cato-2	Corn, high amylopectin, cationic (+)	National Starch and Chemical Corp.
	Hamaco 196	Potato, high amylopectin, anionic (-)	AE Staley Co.
	Gum Ethylex 3095	Corn derivative, hydroxy ethyl ether (o)	AE Staley Co.
	CPC 8071 Dextrin	Corn Dextrin (o)	CPC Inter- national, Inc.
CELLULOSE β /trans OH configura- tion	CMC 7H	Carboxy methyl cellulose (-)	Hercules Inc.
	Natrosol 150 GXR	Hydroxy ethyl cellulose (o)	Hercules Inc.
GUMS β -cis OH configuration w/ α /trans Branches	Jaguar HP-11	Modified guar gum (o)	Celanese
	Guartec SJM	Unmodified guar gum (o)	Henkel
	Jaguar C-13	Cationic guar gum (+)	Celanese
	Gendrix 307	Anionic guar gum (-)	Henkel
CARRAGEENAN β -trans OH configuration	Chondrus Carrageenan	Powdered seaweed, κ -carrageenan	Hercules, Inc.

*Charge given in parentheses.

(a) Starch molecule showing reactive hydroxyl sites.

(b) α - configuration

(c) β - configuration

(d) Cis configuration

(e) Trans configuration

Figure II-28. Hydroxyl group configurations in polysaccharides.

(a) Starch (amylose)

(b) Starch (amylopectin)

(c) Hydroxyethyl Starch

(d) Dextrin

Figure II-29. Structures of natural and modified starches.

(a) Guar Gum

(b) Kappa (κ) Carrageenan

(c) Hydroxyethyl Cellulose (HEC)

(d) Carboxymethyl Cellulose (CMC)

Figure II-30. Structures of some other polysaccharides.

Table II-10. Adsorption densities for various polymers onto pyrite and coal, pH 7.

	Adsorption Density, mg/m ²															Coals										B
	Pyrites							A								C					C10 Mean					
	P1	P2	P3	P4	P5	P6	P7	P8	Mean	C1	C2	C3	C4	C5	C6	C7	C8	C9								
Rylon VII	6.7	4.7	7.8	9.1	12.3	7.2	20.5	3.9	9.0	2.5	4.0	4.3	2.4	2.7	5.0	10.1	6.2	3.6	6.1	4.7						
Amloca	7.5	6.4	17.2	20.1	7.1	8.7	5.8	5.1	9.7	7.5	7.0	5.4	5.8	5.6	6.7	5.0	6.3	6.2	6.3	6.2						
Cato-2	13.8	12.7	18.2	12.4	17.4	8.5	10.3	6.3	12.5	6.0	5.1	6.9	5.8	5.8	5.8	10.1	9.6	8.9	11.2	7.5						
Hamaco 196	4.8	2.4	11.1	10.5	15.3	7.1	10.9	5.0	8.3	3.0	6.3	4.1	3.5	0.8	6.0	5.9	6.1	5.8	4.9	5.2						
Gum Ethylex 3095	1.6	5.0	8.6	8.0	15.2	5.1	9.9	9.6	7.9	-	-	-	-	-	-	-	-	-	-	-						
CPC 8071	2.4	3.8	14.0	4.6	15.6	3.0	20.1	8.5	9.0	3.2	2.5	0.8	2.4	1.4	3.8	6.8	6.9	2.8	3.3	3.4						
CMC 7H	7.4	2.8	6.2	14.7	2.9	2.7	6.6	3.4	5.8	1.0	3.0	0.4	0.4	1.4	1.9	0.2	0.2	2.2	1.6	1.2						
Nattosol 150 GXR	6.7	9.1	9.0	11.1	13.8	15.6	19.2	10.1	11.8	2.5	2.1	3.9	3.0	2.3	2.2	2.6	2.4	2.6	3.3	2.7						
Jaguar C-13	12.6	17.0	12.0	16.5	6.3	13.2	15.3	8.0	12.6	5.0	5.1	5.1	6.1	1.4	1.6	5.8	3.8	5.4	3.7	4.2						
Gendriv 307	7.6	7.9	6.4	10.0	5.5	7.7	15.9	3.9	8.1	6.2	4.0	4.3	5.4	6.0	2.6	2.2	1.8	2.4	2.5	3.7						
Guartec SJM	15.3	20.2	18.4	29.9	25.0	28.4	30.3	15.7	22.9	7.2	6.5	8.8	7.8	7.9	8.8	6.8	7.5	7.5	10.8	8.0						
Jaguar HP-11	5.5	16.7	16.2	21.3	10.3	15.3	17.7	12.5	14.4	2.7	5.1	3.9	5.9	4.2	2.6	-	5.1	3.2	4.3	4.1						
Chondrus	7.6	8.8	3.6	2.4	1.5	4.9	5.4	2.5	4.6	2.0	1.1	1.5	2.6	1.7	2.4	-	-	3.8	4.1	2.4						
Carrageenan																										
Mean	8.3	9.0	11.4	13.1	11.4	9.8	14.4	7.3	10.5	4.1	4.3	4.1	4.3	3.4	4.1	5.7	5.1	4.5	5.2	4.4						

format of Table II-11 is given. For this presentation, arbitrary bounds were set for poor, intermediate and good adsorption as follows:

<u>Symbol</u>	<u>Ranking</u>	<u>Adsorption Density, mg/m²</u>
O	poor	< 6
◐	intermediate	6 - 12
●	good	> 12

It may at once be seen that the adsorption density, as defined here, is much greater onto pyrite than onto coal. The superior pyrite and coal depressants defined above are clearly seen. Further, polymer adsorption onto the ore and anthracite-source pyrites is generally less than onto the bituminous-source pyrites. Greatest adsorption is onto the Pittsburgh seam pyrite (P-5) with those from the KY No. 11 seam (P-7) and the other bituminous sources also showing fairly strong polymer adsorption. The poorest adsorbing polymer is the Irish moss (Chondrus Carrageenan) with the carboxymethyl cellulose, CMC 7H and the corn starch dextrine, CPC 8071 not much better.

For coals, adsorption into the intermediate and lower ranks seems to be greater than onto the higher ranks since the least adsorption is on the hvb (C-2) and mvb (C-3) bituminous coals and the greatest onto a hvBb (C-8) coal. The superior adsorption of Amioca, Cato-2 and Guartec SJM has previously been noted. The anionic potato starch, Hamaco 196 is also seen to be a rather strongly adsorbed onto most coals.

Another way of comparing these data is shown in Table II-12 where the data for pyrite-coal pairs from the same or similar sources are given. Also given in this tabulation, is the percentage decrease in adsorption from pyrite to coal. This difference varies from no change (NC) to 94%, but adsorption densities onto coal averaged 56% lower than on to the comparable pyrite.

Effect of Polymer Structure

From the basic adsorption data of Table II-10 and the structure of the polymers given in Figures II-28 to II-30 and in Table II-9, the influence of structural configuration, hydroxyl group configuration and ionic charge are compared for pyrites and for coals in Table II-13.

For pyrites the branched chain starch (Amioca) is slightly superior to the straight chain

Table II-11. Relative adsorption densities of various polymers onto pyrite and coal at pH 7.

Sample Reagent		Pyrite								Coal										
		P1	P2	P3	P4	P5	P6	P7	P8	C1	C2	C3	C4	C5	C6	C7	C8	C9	C10	
Hylon VII		○	○	○	○	●	○	●	○	○	○	○	○	○	○	○	○	○	○	○
Amioca		○	○	●	●	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Cato-2		●	●	●	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Hamaco 196		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Gum Ethylex 3095		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
CPC 8071		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
CMC 7H		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Natrosol 150 GXR		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Jaguar C-13		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Gendriv 307		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Guartec SJM		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Jaguar HP-11		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Chondrus		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
Carrageenan		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○

Adsorption Density, mg/m^2

○ < 6 ○ 6 - 12 ● > 12

Table II-12. Comparative adsorption densities of various polymers onto pyrite and coal from similar sources (pH 7).

		Adsorption Density, mg/m ²															
		○ < 6				◐ 6 - 12				● > 12							
Sample	Reagent	Anthracite				Lower Kittanning				Upper Freeport				Pittsburgh Seam			
		P1	P2	C1	% Dec	P3	C2	% Dec	P6	C3	% Dec	P5	C5	% Dec	P7	C6	% Dec
	Hylon VII	◐	○	○	50	◐	○	50	◐	○	43	●	○	75	◐	○	75
	Amioca	◐	◐	◐	* NC	●	◐	59	◐	○	17	◐	◐	14	◐	◐	* NC
	Cato-2	●	●	◐	56	●	○	72	◐	◐	13	●	◐	65	◐	◐	40
	Hamaco 196	○	○	○	14	◐	◐	45	◐	○	43	●	○	93	◐	◐	45
	CPC 8071	○	○	○	* NC	●	○	79	○	○	67	●	○	94	●	○	81
	CMC 7H	◐	○	○	80	◐	○	50	○	○	67	○	○	67	◐	○	71
	Natrosol 150 GXR	◐	◐	○	47	◐	○	78	●	○	75	●	○	86	●	○	89
	Jaguar C-13	●	●	○	67	◐	○	58	●	○	62	◐	○	83	●	○	87
	Gendriv 307	◐	◐	◐	25	◐	○	33	◐	○	50	◐	◐	* NC	●	○	81
	Guartec SJM	●	●	◐	60	●	◐	61	●	◐	68	●	◐	68	●	◐	70
	Jaguar HP-11	◐	●	○	74	●	○	69	●	○	73	◐	○	60	●	○	83
	Chondrus Carrageenan	◐	◐	○	76	○	○	75	○	○	60	○	○	* NC	○	○	60

* NC indicates no change.

Table II-13. Comparative average adsorption densities (mg/m²) of polymers onto pyrite and coal based on structure, hydroxyl group configuration and ionic charge.

Comparison Basis Sample	Structure Branched Chain (Amioca)	Straight Chain (Hylon VII)	Hydroxyl Group			Ionic Charge		
			β /cis	β /trans	α /trans	Starch (0) (+)	(-) (-)	Guar Gum (0) (+) (-)
Pyrites			Guartec SJM	Natrosol CXR	Hylon VII	Amioca Cato-2	Hamaco 196	SJM C-13 307
	General Trend: 9.7 Branched > Straight Special Cases (P5, P7): 6.5 Branched < Straight	9.0	General Trend: 22.9 β /cis > β /trans	11.8 9.0 α /trans	9.0 α /trans	General Trend: 9.7 12.5 8.3 Always: (+) > (-)	General Trend: 22.9 12.6 8.1 Always: (0) > (+) > (-)	
Coals								
	General Trend: 6.2 Branched > Straight Special Cases: (C7): 5.0 Branched < Straight (C8, C10): 6.2 Branched = Straight	4.7 Straight	General Trend: 8.0 β /cis > β /trans Special Cases: (C7): 4.1 β /cis > β /trans	2.7 2.6 β /trans < α /trans	4.7 10.1 α /trans	General Trend: 6.2 7.5 5.2 (+) > (-) Special Cases: (C2, C6): (+) < (-)	General Trend: 8.0 4.2 3.7 (0) > (+) or (-)	

(Hylon VII), though for the pyrites from two important seams (Pittsburgh and KY #11), the reverse is true. In both of these exceptions to the general rule, the preference for the straight chain starch over the branched form is massive. Working with Pittsburgh seam pyrite, Perry and Aplan, (1985) found a preference of the straight chain form over the branched form for pyrite adsorption and for pyrite depression during flotation. For most of the coal samples, the branched chain form of corn starch is a little better than the straight chain form, but not for several of the lower rank coals (C-7, C-8 and C-10).

With regard to the hydroxyl group configuration, the general trend for adsorption onto pyrite is

$$\beta/\text{cis} > \beta/\text{trans} > \alpha/\text{trans}$$

Perry and Aplan (1985), noted this same trend for Pittsburgh seam pyrite. The same trend of preferred hydroxyl group configuration is generally the same for all of the coals with the exception of the C-7 coal where the α/trans form adsorbed more strongly than did the β/trans form. Note for both the pyrites and the coals, the superiority of the β/cis form. This form is typical of the guar gum which has two β/cis groupings in the main chain and one α/trans in the side chain. By contrast, starches exist in the α/trans form and cellulose in the β/trans form.

With respect to ionic charge, it will be seen that the cationic starch is more strongly adsorbed onto pyrite than is either the neutral or the anionic starch used here. By way of comparison to the guar gums, a different trend emerges with the neutral form being more strongly adsorbed than either of the two charged forms.

The charge data for starches may best be seen in Figure II-31 and for guar gums in Figure II-32. For the starches (II-31) a great variation in adsorption density from pyrite to pyrite may be seen, with a lesser derivation from average for the eight coal samples tested. For the average data, however, the adsorption of starches onto both pyrite and coal follows the pattern:

$$\text{cationic} > \text{neutral} > \text{anionic}$$

For the guar gums a substantial variation in the data is also seen, but this is lesser for coal than for pyrite. For either the pyrite or the coal samples, on average the form is

$$\text{neutral} > \text{cationic} = \sim \text{anionic}$$

Perry and Aplan (1985, 1988) noted a strong influence of pH on the adsorption of

Figure II-31. Adsorption of starches on coal and pyrite at pH 7.

○ - pyrite

● - coal

□ - average

Figure II-32. Adsorption of guar gums on coal and pyrite at pH 7.

○ - pyrite

● - coal

□ - average

Pittsburgh seam pyrite and coal and found strong evidence that electrostatic adsorption play a substantial role.

These data clearly indicate that the source of the pyrite and of the coal exert a substantial influence on the adsorption of polymers onto them. It also serves to explain why a polymer may be a good depressant for the pyrite formed on one raw coal and not nearly as effective in depressing the pyrite in another coal.

Though it will not be discussed further here, these data in part substantiate the mechanisms as summarized by Perry and Aplan (1985) for the adsorption of polymers such as polysaccharides onto pyrite:

1. Electrostatic attraction of charged polymers
2. Specific adsorption as through the formation of an iron - polysaccharide complex (or a polysaccharide xanthate).
3. Hydrogen bonding through hydroxyl groups
4. Entropy change from the polymer adsorption replacing water molecules at the pyrite surface.

In like manner, Im and Aplan (1981, see also Perry and Aplan, 1988) discussed the following mechanisms for the adsorption of polymers onto coal:

1. Electrostatic attraction
2. Hydrogen bonding
3. Ester formation at the surface
4. A 'squeezing out' effect due to the lower potential energy of the polymer molecule at the surface than in solution
5. Hydrophobic bonding with the polymeric depressant displacing water molecules at the coal surface.
6. Specific adsorption through selected active groups.

SUMMARY

1. There is a great variability in the adsorption of various polymers onto a given pyrite sample and there also is a great variation in the adsorption of the same polymer onto a variety of pyrites from different sources.
2. This observation probably explains why a given polymer may be a good depressant for a pyrite from one-source and a poor depressant for the pyrite from another source.
3. Based on an adsorption density criterion of mg/m² and Blaine surface area, polymer adsorption onto pyrite is generally greater than onto coal.

4. For the adsorption of polysaccharides onto pyrite, the following general trends were noted:

- structure: branched > straight chain starches (with important exceptions)
- hydroxyl configuration: $\beta/\text{cis} > \beta/\text{trans} > \alpha/\text{trans}$
- charge: Cationic > neutral $\geq$ anionic (starches)
 neutral > cationic > anionic (guars)

5. For the adsorption of polysaccharides onto coal, the following general trends were noted:

- structure: branched > straight chain starches (with a few exceptions)
- hydroxyl configuration: $\beta/\text{cis} > \beta/\text{trans} > \alpha/\text{trans}$ (one exception where
 $\alpha/\text{trans} > \beta/\text{cis}$)
- charge: Cationic > neutral $\geq$ anionic (starches)
 neutral > cationic > anionic (quars)

REFERENCES

- Arnold, B. J., and Aplan, F. F., "The use of pyrite depressants to reduce the sulfur content of upper freeport seam coal" in Proc. and Util. High Sulfur Coals, III, Eds. R. Markuszewski and T. D. Wheelock, Elsevier, Amsterdam, 171-185, 1990.
- Bartsch, O., Kolloidchem. Beihefte, 20:1, 1924, (as cited by K. L. Sutherland and I. W. Wark, Principles of Flotation, Aus. IMM, Melbourne, 1955).
- Choudhry, V. and Aplan, F. F., "Pyrite depressions during coal flotation, Part II organic polymers, their xanthated forms and related compounds", submitted to Minerals and Metallurgical Processing, 1991.
- Dubois, M., Gilles, K. A., Hamilton, P. A., Rebes, P. A. and Smith, F., "Colorimetric method for determination of sugars and related substances", Analytical Chemistry, 28:350, 1956.
- Esposito, M. C., Chander, S. and Aplan, F. F., "Characterization of pyrite from coal sources" in Process Mineralogy, III, Eds. A. H. Vassiliou and D. M. Hausen and D. J. T. Carson, TMS, Warrendale, PA, 475-493, 1987.
- Im, C. J. and Aplan, F. F. "Depression of coal and starches and starch derivatives", in Proc. First Aust. Coal Prep. Conf., Ed. A. R. Swanson, Coal Preparation Societies of New South Wales and Queensland, Newcastle, NSW, 183-204, 1981.
- Perry, R. W. and Aplan, F. F., "Polysaccharides and xanthated polysaccharides as pyrite depressants during coal flotation", in Proc. and Util. High Sulfur Coals, I, Ed., Y. A. Attia, Elsevier, Amsterdam, 215-238, 1985.
- Perry, R. W. and Aplan, F. F., "Adsorption of polysaccharides and related compounds onto coal and their effect on the flotation of coal and pyrite", Sep. Sci. & Tech., 23:2097-2112, 1988.
- Raleigh, C. E. and Aplan, F. F., "Effect of feed particle size and reagents on coal-mineral matter selectivity during the flotation of bituminous coals", Minerals and Metallurgical Processing, 8:82-90 and Trans. AIME, Vol. 290, 1991.
- Taggart, A. F., Handbook of Mineral Dressing, John Wiley, New York, Section 12, 1945.

PART III. EMULSION PROCESSES AND PRINCIPLES

ABSTRACT

Partitioning of coal and ash-forming minerals between oil and aqueous phases was studied to determine the role of oil in selective agglomeration separation processes for cleaning of ultra-fine coal. The effect of organic phase type and aqueous phase composition was determined. Kinetics of emulsification of oil was studied in the absence and presence of coal particles of various rank to demonstrate that many sub-processes occur. These include dispersion of oil, capture of hydrophobic particles by oil droplets, particle-aided coalescence of oil droplets, and aggregation of oil droplets by particle bridges. These processes play an important role in the grade and recovery of coal whenever oil is used.

INTRODUCTION

This part of the investigation is divided into the following:

- Cleaning of coal by liquid-liquid extraction
- Emulsification of oil in the presence of fine particles

In this part of the project, the role of oil in selective coalescence processes was investigated. Such processes have been thoroughly reviewed by Mehotra et al., (1983) and Capes and Darcovich (1984). Multiphase interactions involving at least two solids (coal and ash-forming mineral) and two immiscible liquids (water and heptane) occur whenever oil is present as a separate phase. In previous studies (Hsu and Chander, 1988), we established that partitioning of coal, pyrite and ash-forming minerals between oil and water occurs in three stages which are schematically represented in Figure III-1. In Stage I, emulsification of oil occurred to form droplets of oil in water making oil-in-water (O/W) emulsions. These droplets capture hydrophobic particles. Recoveries of both the ash and combustible matter increased monotonically with time in this stage. The increase in concentration of hydrophobic coal particles at the oil/water interface destabilized the O/W emulsion and an

Figure III-1. A schematic representation of various stages in liquid-liquid separation process .

inversion of emulsion occurred. The combustible matter recovery was about 90% at the condition of incipient phase inversion. With continued agitation, a slow transitional period emerged in which O/W and W/O emulsions coexisted, this is referred to as Stage II. The conditions for inversion of emulsion favor rejection of ash-forming minerals from the clean coal. Intense and continued agitation results in formation of complex or bridged emulsions in which particles act as bridges between the dispersed phase. Once formed such emulsions are difficult to disperse. This stage was referred to as Stage III in which significant lowering of the grade of clean coal was observed possibly due to entrapment of the mineral matter. These studies were continued to determine the effect of organic phase and solution conditions.

An analysis of the kinetic curve for the liquid-liquid separation process showed that the performance depends strongly on hydrodynamics, or more specifically, the stirrer speed and time. Since several stages are involved and the transition from one stage to the other depended upon several variables, it was desirable to obtain a normalized kinetic curve. This approach was important because appropriate stage of the system must be recognized before comparing the effect of other variables, such as type of organic phase, solution concentration, etc., on the process performance. Assuming that the recovery depends on the droplet size or the available interfacial area, a hydrodynamic parameter, A_i , might be defined as follows:

$$A_i = N^{m-t}, (m = 0.72 \text{ to } 3.5, n < 0.5)$$

where N is the stirrer speed and t is the extraction time. Other hydrodynamic variables, such as geometry of the mixing tank and the stirrer, the position of the stirrer, and the method of oil addition were assumed to remain unchanged.

Based on the above discussion, liquid-liquid separation performance, that is partitioning of coal between oil and aqueous phases will depend on the emulsion size and/or emulsion type, both of which might change with organic phase, salt concentration, etc. For example, emulsion droplet size, D_p , will increase with increasing oil viscosity under given hydrodynamic and solution conditions. Calderbank (1958) suggested a semi-empirical equation to calculate the surface

volume mean diameter of liquid-liquid dispersion under non-coalescence condition:

$$D_p = 0.224 \sigma^{0.6} \cdot (P/V)^{-0.4} \cdot d_c^{-0.2} \cdot H^{0.5} (\mu_d/\mu_c)^{0.25}$$

Where, D_p = droplet diameter, cm
 σ = interfacial tension, dynes/cm²
 P = power input, ergs/sec
 V = total volume, cm³
 d = density, g/cm³
 $H = V_d/V_c$ = volumetric hold-up, and $V = V_d + V_c$
 μ = viscosity, cp

Subscripts d and c represent the dispersed and continuous phase respectively.

EXPERIMENTAL MATERIALS AND METHODS

Material Description and Sample Preparation

The hvA coal sample used in this set of experiments was from Robena mine, Pittsburgh seam, PA. Raw coal with a top size of 1/4 inch analyzed 14.0% ash, 2.7% total sulfur and less than 1% moisture. The raw coal sample was ground to 80% passing 400 mesh in a laboratory coffee grinder followed by a particle pulverizer (Bleuler Rotary mill). The -400 mesh screen fraction was then classified in a Donaldson Acucut air classifier at cut sizes of 2, 8 or 10 and 16 μ m. To study the effect of coal hydrophobicity on the kinetics of emulsification, a sub-bituminous A coal from Colorado Q Seam in Moffat County-Craig Township, Co was also used. The particle size distribution of the coal sample was determined by a Microtrac particle size analyzer, model SPA.

The hydrocarbons used in this investigation, heptane (99%), pentane, hexane, cyclohexane, isooctane, dodecane and xylene were obtained from the Aldrich Chemical Company. All other chemical reagents were of the ACS grade and distilled water was used throughout the experiments.

Apparatus

Liquid-Liquid Separation. A schematic of the agitation tank used for the

liquid-liquid separation tests is shown in Figure III-2. A standard geometry of the agitation tank, given by Holland and Chapman (1966), was used. A cell of capacity 420 ml was used in this part of the work. For a tank of diameter T , the dimensions of the six-blade turbine impeller in a fully baffled tank are as given below:

$$\begin{aligned} \text{impeller diameter, } D_i &= T/3 \\ \text{impeller width, } w &= D_i/5 = T/15 \\ \text{impeller height, } h &= D_i = T/3 \\ \text{liquid height, } L &= T \\ \text{baffle width} &= T/10 \end{aligned}$$

Emulsification in the Presence of Fine Particles. A one liter cell of standard geometry with four baffles was used in the emulsification studies. This cell was also equipped with a six blade, turbine type stirrer, speed of which was maintained constant to within 1% of the nominal value with a feedback controller. A schematic of the experimental set up is given in Figure III-3. The mixing cell was connected to the measurement chamber of a size analysis device using 1/8" masterflex tubing. The cell was tapered at the bottom where it had an outlet equipped with a three way valve to direct a portion of the suspension for size distribution measurements. Sampling from the mixing cell to the size measurement chamber was achieved by hydrostatic pressure difference to ensure undisturbed flow of the suspension and droplets. A known amount of oil was added to the cell and the time of addition was set as the zero time of emulsification. The location of oil addition in the cell was kept constant throughout all the experiments. Size distributions were taken at preselected time intervals of 1, 2, 4, 8, 16, and 32 minutes using a light scattering size measurement device, Malvern 2600c Series Particle Size Analyzer.

Procedure

Liquid-Liquid Separation Method. The following procedure was used in a typical liquid-liquid separation test. A predetermined amount of coal sample was added to the aqueous solution of the desired ionic strength and pH value. Unless otherwise specified, a slurry concentration of 1% solids (by weight per unit volume of liquid) was maintained throughout this investigation. The volume of oil used was 15% of the total liquid volume. The slurry was first conditioned for 30 minutes at

Figure III-2. A schematic representation of fluid flow in an agitated tank.

Figure III-3. Experimental setup used in the emulsification studies.

- C: Cell of standard geometry
- V: 3-Way valve
- P₁: Peristaltic pump for suspension circulation
- P₂: Peristaltic pump for dilution water
- S: Stirrer, 6 blade, turbine-type
- W: Window of the size measurement chamber

2000 rpm (with the 2.7 cm diameter turbine impeller in tank B) to ensure dispersion and chemical equilibrium. No variation in separation performance was observed for a conditioning time of up to 120 minutes. The impeller speed and stirring time in the conditioning stage were kept constant for each set of experiments.

After the conditioning period, the stirrer was adjusted to the appropriate speed and oil was added within a period of 5 seconds through a funnel. After the preset time for separation, the stirrer was stopped and the phases were allowed to settle for 5 minutes (longer time was found unnecessary). The aqueous phase containing the ash-forming minerals was drained from the bottom of the vessel. The solids in the aqueous and phases were filtered, dried and analyzed for ash and sulfur.

Emulsification in the Presence of Fine Particles. The fluid in the cell was circulated continuously using a peristaltic pump during emulsification and was directed to the size distribution device for only a few seconds using a three way valve. During the measurement the emulsion entered the flow-through chamber with two windows on the sides to permit the travel of the laser beam through the solution. At the inlet point of the measurement chamber, dilution water was added to the emulsion to prevent coalescence of the oil droplets and their adhesion to windows. The solution passing the size distribution measurement chamber was discarded. As soon as the size measurement was completed the three way valve was turned to its original position to circulate the emulsion back into the cell.

To study the emulsification in the presence of fine coal, particles were added to the system in the form of a slurry. The slurry was prepared by dispersing the particles in an ultrasonic bath for ten minutes and it was transferred to the mixing cell prior to the oil addition.

The standard cell described in the previous paragraphs was also employed for observing the emulsion droplets with a High Speed Motion Analysis System, Spin Physics Model SP2000. The chamber used in the size distribution measurements was placed in front of the lens of a high speed video camera and the images of the emulsion was recorded during its passage from the measurement chamber. A long focal length microscope was used to obtain the magnifications necessary to observe the droplets. A fiber-optic light source was employed for illuminating the droplets.

Size of the droplets could be measured to an accuracy of a few microns with such a set up.

Analysis

The ash tests were performed in a commercial ashing oven. The coal samples were pre-dried at 110°C for one hour and then heated slowly to 750°C and remained at this temperature for at least two hours, the ash content was then calculated from the weight loss.

The total sulfur content was analyzed by a Leco Sulfur analyzer. Analysis for the sulfur forms was carried out for selected samples by the Warner Laboratories, PA.

Emulsion Type

Identification for the emulsion types were carried out by the dispersion method and/or microscopic examination. Addition of dye or conductivity measurement were found to be ineffective. A small amount of sample to be identified was taken from the emulsion phase immediately after the separation in the stirred cell. The sample was divided and placed in two watch glasses. Water or oil was then carefully added to each sample. The emulsion was checked to determine its stability in the added fluid. If the emulsion dispersed by the added water but not oil, water was designated as the continuous phase. Similarly, if the emulsion dispersed in oil it was considered to be a water-in-oil emulsion. If the emulsion could neither be dispersed by the addition of oil nor by water, it was designated as the bridged-emulsion. Each of the dispersed sample was also examined under the microscope to estimate the size of droplets.

EXPERIMENTAL RESULTS AND DISCUSSIONS

Liquid-Liquid Separation (Cleaning of Ultrafine Coal by Partitioning at Oil-Water Interface).

Several hydrocarbons were tested to determine their influence on the liquid-liquid separation process. Results of combustible matter and ash recovery are plotted

in Figure III-4, for several organic liquids. Dashed lines represent the iso-selectivity lines with selection efficiency values, E_s , marked on the figure. These results show that:

a) Both R_o and R_a decreased with increasing chain length of hydrocarbons at short extraction times (≈ 10 and 30 minutes).

b) The selectivity was higher for shorter chain length hydrocarbons after sufficient long extraction times, but no difference was observed in selectivity among the hydrocarbons tested at short times (≈ 3 minutes).

c) The selectivity increased with time for the agitation speed range tested. Within the test time frame (< 30 minutes), a decrease in selectivity at long times was observed only for longer chain length hydrocarbons.

Based on the above observations and previous discussion on the kinetic behavior of liquid-liquid separation process, it seems that the separation system remains in Stage I for all the tests carried out at (1800 rpm, 3 minutes) irrespective of the organic phase used. The system was under dispersion-control with formation of predominantly O/W emulsions. The clean coal product could be diluted by adding water but not oil confirming the presence of O/W emulsion. Low recovery and non-selectivity were found for all the oils tested under these conditions.

The high recovery (greater than 90%) and high selectivity at (2000 rpm, 30 minutes) are attributed to the process being in Stage II (near t_{min} in a kinetic curve) for pentane, hexane, heptane, and probably also for isooctane. Other longer chain hydrocarbons showed the characteristics of Stage III, which would be controlled mainly by the behavior of W/O/W complex emulsions or bridged emulsions.

Tests performed at (1800 rpm, 10 min.) show features of late Stage I, i.e., after the transition time in Stage I and in the vicinity of t_{max} . The characteristic phase expected under these conditions is a combination of O/W and W/O/W emulsions. The system is under particle-capture control, and recoveries increase rapidly. However, xylene may be one exception found for its extreme high recovery and low selectivity.

At (1800 rpm, 3 min.), which corresponds to Stage I, combustible recovery can be considered primarily a function of the available interfacial area if particle-

Figure III-4. Effect of hydrocarbons on separation performance.

droplet collision is assumed to be the primary recovery determining mechanism. The "ultimate" or steady state Interfacial area of a non-coalescence dispersion system can be estimated from the equation proposed by Calderbank (1958). The interfacial area and droplet diameter are related as follows:

$$A = 6H/D_p$$

Where A is the interfacial area per unit volume of mixed phases, H is the fractional volumetric hold-up of the dispersed phase and D_p is the Sauter or surface mean diameter of the dispersed phase. In addition, O/W dispersion is assumed for (1800,3) and W/O type is assumed for all other cases.

The relative interfacial areas for each hydrocarbon are shown in Figure III-5. For convenience, cyclohexane and xylene were each assigned an "equivalent carbon number" of 10 and 13, respectively. The interfacial area was calculated and normalized to a relative scale of 0 to 100. Some of the assumptions in constructing the curves are: a) the existence of "compensation condition", where the size distribution from a continuous droplet breakage is independent of time, b) the existence of a linear relationship between logarithm of the mean drop diameter and time. That is, the drop size or the interfacial area of the dispersion system should be only a fraction of the calculated ultimate droplets size, or, the droplets size is given by:

$$D_p(t) = t^n(D_p)_\infty \quad (-1 < n < 0)$$

Where $(D_p)_\infty$ is defined as the mean droplets size at long time (steady state or ultimate size). One-sixth power of time, $n = 1/6$, was chosen and the agitation time needed to reach the "ultimate" droplet size $(D_p)_\infty$ was assumed to be 30 minutes.

Experimental data are replotted in a form similar to Figure III-5 and shown in Figure III-6 which shows a direct correspondence between the interfacial area and recovery. These results support the hypothesis that there is no specific effect of short chain hydrocarbons on the separation performance. The major difference is the size

Figure III-5. Dependence of relative interfacial area on equivalent carbon number.

Figure III-6. Dependence of recoveries on equivalent carbon number.

of emulsion droplets, which is influenced mainly by the variation in viscosities of different hydrocarbons.

Deviation from the above hypothesis was observed for xylene, however. The large recovery could not be explained solely by the droplet size effect. In addition to the effect of viscosity, some other parameters might have affected the droplet size. From a review of the factors affecting liquid-liquid dispersion, density of oils, which increases with the assigned equivalent carbon number, may also have some effect on the droplets size or interfacial area. This effect was not considered in estimating the interfacial area. Furthermore, the effect of colloidal interactions on emulsion droplet size was not considered.

The effect of hydrocarbons on the liquid-liquid separation process can be summarized in the form of a kinetic curve in Figure III-7. The calculated relative interfacial areas (x-axis) were obtained from Figure III-5 and the recoveries are the corresponding values from Figure III-6. At (1800 rpm, 3 min.), the system is in Stage I for various hydrocarbons (excluding xylene). A relative interfacial area of about 15 can be regarded as the transition in Stage I, at which the system changes from dispersion-control to particle-capture control. At (1800 rpm, 10 min.), these hydrocarbon systems are in Stage II and at (2000 rpm, 30 min.) systems are in Stage III. All the recovery data of different oils lie on the same R_c or R_a versus relative interfacial area curve except some insignificant deviation near the transition time in Stage I. One may conclude that the emulsion size and type determine the combustible matter and ash recovery.

The effect of agitator speed, time of separation and ionic strength on clean coal yield and product quality, % ash and % sulfur, is shown in Table III-1. A complex interaction between hydrodynamic and solution variables can be seen. High speed of agitation gave large yields but the grade was poor. This set of experiments was done at natural pH of 4.8. The ash-mineral rejection was better at an ionic strength of 0.05 M but a further increase in ionic strength significantly increased the ash. Improvement in the separation could be achieved by changing pH and by adding dispersants. The results are shown in Table III-2. These results were explained on the basis of the model discussed in previous section which recognized the three stages

Figure III-7. Dependence of recoveries on relative interfacial area.

Table III-1. The effect of ionic strength on clean coal yield and product ash and sulfur for a Pittsburgh seam coal (-8mm).

NaCl Conc. Mole/liter	Clean Coal Yield, %	Ash. %	Total Sulfur, %
A. 2000 RPM, 0.5 min			
0.0003	69	6.34	-
0.0008	50	6.55	-
0.005	52	6.26	-
0.05	57	6.20	-
B. 2000 RPM, 30 min			
0.001	97	7.28	-
C. 1500 RPM, 20 min			
0.005	94	6.26	1.65
D. 1400 RPM, 30 min			
0.0002	62	6.16	1.61
0.001	70	6.40	1.55
0.005	65	6.36	1.59
0.05	91	5.87	1.58
0.5	91	8.72	(1.40)

Table III-2. Effect of agitator speed, time, pH and salt type on clean coal yield and product ash and sulfur for a Pittsburgh seam coal.

Agitator Speed RPM	Agitation Time, Min	pH	Salt	Clean Coal Yield, %	Ash %	Total Sulfur %
1400	40	2.8	NaCl	82	6.04	ND
1600	30	2.8	H ₂ SO ₄	93	6.54	ND
1400	40	3.8	NaCl	93	6.33	1.60
1400	40	3.8	Na ₂ Cr ₂ O ₃	77	4.69	1.74
1400	40	5.8	NaCl	92	6.04	ND
1400	40	5.8	NaCl	91	5.66	1.63
1400	40	5.8	NaCl	94	6.58	1.58
1400	60	5.8	Na ₂ SiO ₃	90	6.16	1.69
1400	30	5.8	Na ₂ SiO ₃	77	5.70	ND
1400	40	9.8	NaCl	63	4.62	1.53
1400	40	9.8	Al(NO ₃) ₃	74	4.36	1.66
1600	30	9.8	Al(NO ₃) ₃	88	4.50	1.62

ND: Not Determined

that occur when oil and an aqueous slurry of coal are mixed in an agitated vessel.

Kinetics of Emulsification in Multi-Phase System

Kinetic studies of emulsification were carried out using n-dodecane as the dispersed phase. In the initial experiments the amount of oil in the system was varied and its effect on the emulsification was examined. Oil concentrations of 0.1%, 0.25%, 0.5%, 1.0%, 2.0% and 5.0% by volume were used in these experiments. The stirrer speed was kept constant at 1400 rpm in this set of experiments. It was observed that at a given oil concentration, the mean size of the emulsion droplets displayed an initial decrease due to breakage as expected. The rate of breakage decreased with increasing agitation time and at some point an equilibrium was reached between the breakage and coalescence and no further reduction in the size of oil droplets was observed (Figure III-8). At low oil additions such as 0.1% and 0.25%, the mean size of the droplets after 32 minutes of agitation was about 60 μm . As the concentration of oil increased, the mean size of the droplets became coarser and the system reached equilibrium at shorter times, suggesting increased coalescence due to increasing number of oil droplets. At an oil concentration of 5.0%, the breakage was balanced by the coalescence within the first minute of the dispersion process and no decrease in the size of the droplets was observed. The mean size of the droplets was about 130 μm in this case.

Another set of experiments was carried out at different stirrer speeds by keeping the amount of oil constant at 1.0% by volume. It was observed that the increasing the intensity of agitation decreased the final droplet size considerably (Figure III-9). At a stirrer speed of 2000 rpm, the equilibrium was reached within the first minute at about a mean droplet size of 60 μm .

Similar experiments were conducted in the presence of fine particles of two different coals with mean volume sizes of about 3.5 μm . The amount of oil and the stirrer speed was kept constant in these experiments at 1.0% and 1400 rpm, respectively. The amount of particles added was 2, 5, 10, 20 and 50 mg/L for each coal. It was observed that the presence of fine particles of the sub-bituminous A coal increased the observed droplet size (Figure III-10). As the amount of the particles of

Figure III-8. Emulsification of dodecane as a function of dodecane concentration.

Figure III-9. Emulsification of dodecane as a function of stirrer speed.

Figure III-10. Emulsification of dodecane in the presence of a sub-bituminous A coal.

this coal in the emulsion was increased, the droplet size began to increase at longer agitation times. For coal addition of 50 mg/L, the mean droplet size after 32 minutes reached a value of about 200 μm . The increase in the droplet size due to presence of hydrophobic particles was much more dramatic in the case of high volatile A coal. The droplet size showed a rapid increase in the presence of this coal sample at even very low concentrations (Figure III-11). When the amount of coal added was 50 mg/L, the mean droplet size reached a value of 240 μm in the first 16 minutes of agitation and remained constant thereafter. It was also observed that the shape of the curves obtained in Figures III-10 and III-11 for the two coals were quite different.

In order to explain the difference in the coalescence characteristics of oil droplets in the presence of different coal particles, high speed recordings of the emulsions were carried out. The amount of oil and the stirrer speed were kept constant at 1.0% and 1400 rpm, respectively. Amount of coal added to the system was 50 mg/L. The microphotograph of the emulsion droplets taken by the High Speed Motion Analyzer showed aggregation of droplets to form a floc structure. Obviously fine hydrophobic particles promote formation of the aggregates. For less hydrophobic particles, as was the case for sub-bituminous A coal, the number of droplets in the flocs increased with increasing agitation time as can be seen in Figure III-12. However, no change in the structure of the flocs was observed, except that some flocs coalesced to form larger droplets with particles still positioned at the oil-water interface. For strongly hydrophobic particles of the hvA coal, a different floc structure was observed as shown in Figure III-13. Through emulsion identification tests, this stage was identified as a water/oil/water emulsion. Further coalescence of small individual droplets did not cause a significant change in the size of the emulsion droplets, explaining the shape of the curves in Figure III-11.

SUMMARY

The following conclusions were made of the basis of this study:

- a) Several sub-processes occur when coal particles are mixed with water and oil. These include: dispersion of oil, capture of particles, particle aided coalescence and aggregation and phase inversion. In general, no specific effect of hydrocarbons was found. Results obtained using

Figure III-11. Emulsification of dodecane in the presence of a high volatile A coal.

Figure III-12. High speed motion analyzer photographs of oil/water emulsion in the presence of $3.5 \mu\text{m}$ particles of sub-bituminous A coal.

Figure III-13. High speed motion analyzer photographs of oil/water emulsion in the presence of 3.5 μm particles of high volatile A coal particles.

different organic phases can be described by the same set of kinetic curves based on available interfacial area for collection of particles.

- b) For a coal of certain hydrophobicity, a change in hydrocarbons changed the emulsion droplet size if hydrodynamic conditions were the same. That is, similar results can be obtained for different hydrocarbons by appropriately modifying the hydrodynamic conditions. The effect is much more complex if the coal is changed because of differences in the extent of sub-processes listed in (a) above.
- c) The effect of salt type and concentration was complex and requires further studies.
- d) Type of emulsion and kinetics of emulsification are strongly dependent on the hydrophobicity of coal particles. High rank particles which are strongly hydrophobic, promote coalescence of oil droplets and phase inversion. In contrast, low rank coal particles, which are less hydrophobic, promote aggregation of oil droplets into large flocs. As a result, differences in grade and recovery can be expected depending upon the type of emulsion present.

REFERENCES

Calderbank, P. H., "Physical Rate Processes in Industrial Fermentation: I. The interfacial area in G-L contacting with mechanical agitation", *Trans. Instn. Chem. Engrs.*, 36:443-463, 1958.

Capes, C. E., and Darcovich, K., "A Survey of Oil Agglomeration in Wet Fine Coal Processing", *Powder Technology*, 40:43-52, 1984.

Hsu, T. C., and Chander, "Interfacial and Colloidal Effects in Liquid-liquid Separation of Ultrafine Coal", *Interfacial phenomena in biotechnology and materials processing*, Eds., Y. A. Attia and B. M. Moudgil, Elsevier, 399-411, 1988.

Mehrotra, V. P., Sastry, K. V. S., and Morey, B. W., "Review of Oil Agglomeration Techniques for Processing of Fine Coal", *International Journal of Mineral Processing*, No. 3, 11:175-201, 1983.

PART IV. EVALUATION OF COAL HYDROPHOBICITY

ABSTRACT

The distribution of the wettability of coals of different rank was determined by measurements of contact angles for individual particles. The contact angle was estimated from the equilibrium partitioning of a particle at the water/air interface. Using this technique contact angles were determined for a larger number of particles from a given sample and a frequency distribution of contact angle was obtained. The contact angle distribution was broad for all the coals tested with included an anthracite, a hvA bituminous and a sub-bituminous coal. In comparison, spherical particles of polymethylmethacrylate gave a much narrower distribution. The distribution for irregular polyethylene particles was somewhat broader than that for the polymethylmethacrylate spheres but broader than that for the polymethylmethacrylate spheres but considerably narrower than that for coal. The broader wetting distribution for coal was attributed to differences in surface chemical properties.

INTRODUCTION

A knowledge of the wetting properties of coals is very useful in coal cleaning by flotation and other processes in which separations are based on differential surface properties. The various methods available for measuring wetting characteristics include: contact angle (Taggart et al., 1930) and Sutherland and Wark, 1955), immersion/sink time (Draves and Clarkson, 1931), bubble attachment (Hannis and Rutter, 1989), film flotation (Williams and Fuerstenau, 1987), displacement pressure (Bartell and Osterhof, 1927; Crowl and Wooldridge, 1967), penetration rate (Peek and Mclean, 1934; Kaya and Koishi, 1988), bubble pick-up (Finch and Smith, 1975), induction time (Glembotsky et al., 1953), imbibition time (Mohal and Chander, 1986), and calorimetry (Zettlemoyer, 1986; Healy and Fuerstenau, 1965). Of all these methods, however, the measurement of contact angle by the sessile drop and captive bubble techniques have been most widely used. (Brady and Gauger, 1940), demonstrated through the use of the contact angle method that the natural

hydrophobicity of coal varied greatly from sample to sample. Subsequent experiments showed that this difference correlated well with rank, the larger contact angles generally being associated with the higher rank coals (Horsley and Smith, 1951; Brown, 1962). More recent studies by Aplan and co-workers (Parekh 1978; Gutierrez et al., 1984; Gutierrez and Aplan, 1984; Arnold and Aplan, 1989; Aplan, 1989) show that the wettability of various ranks of coals as determined by sessile drop and captive bubble methods is a more complex function of rank. The hydrophobicity of coal usually increases with rank up to about 80% fixed carbon (dmmf) and then decreases.

Coal is an extremely heterogeneous material with a great deal of variation in its physical and chemical properties. This variation occurs not only from rank to rank and seam to seam but also from location to location (Aplan, 1989). Hence, in a given sample of coal, various particles may have different wettabilities and contact angles. The objective of this article is to describe a method to determine contact angles for individual particles. The measured values can be used to represent a frequency distribution which is characteristic of the wetting behavior of a given coal sample.

EXPERIMENTAL MATERIALS AND METHODS

The various coals, which included an anthracite, a hvA bituminous and a sub-bituminous coal, were obtained from Penn State Coal Data Bank. These coals were crushed by hand and screened to obtain the necessary size fractions prior to the contact angle measurement. The polymer samples of polymethylmethacrylate and polyethylene were obtained from Aldrich Chemical Company, Inc. The material specifications are given in Table IV-1 and the analysis of various coals are given in Table IV-2. In addition, a sample with particles ranging from 0.2 mm to 1.20 mm, was prepared for a special series of tests which was designed to determine the effects of size on the contact angle measurement.

The contact angle for the individual particles was measured, using the interface partitioning method (Wei et al., 1990). The principle of this technique is that when a particle is placed at the water/air interface it will be partitioned between the two phases with a part of the surface in air and the remainder in water. The position of

Table IV-1. Material specifications for various samples used in this investigation.

	Size, mm	Aspect Ratio*	Source
Anthracite coal	0.54-0.81	0.61-0.84	Schuykill, PA
HvA bituminous coal	0.60-0.86	0.63-0.86	Lawrence, PA
Sub-bituminous coal	0.58-0.82	0.63-0.85	Moffat, CO
Polymethylmethacrylate	0.32-0.68	0.97-1.0	Aldrich Chem.
Polyethylene	0.53-0.85	0.63-0.83	Aldrich Chem.

*Aspect ratio is defined as the ratio between the minimum and the maximum Feret's diameter of the particle and was taken as a measure of shape in this study.

Table IV-2. Analysis of various coals.

Rank	Anthracite	hVa bituminous	Sub bituminous
PSU ID#	PSOC-867	PSOC-1361p	PSOC-1382p
Moisture, %	3.15	3.20	13.03
Proximate analysis (Dry basis %)			
Ash	11.36	8.47	5.65
VM	5.23	38.16	34.20
FC	81.05	53.37	47.12
Ultimate analysis (DAF basis %)			
C	94.3	81.94	75.19
H	1.55	5.70	5.04
N	0.69	1.54	2.01
S	0.46	2.12	0.40
O	2.19	8.70	17.37

the particle at the interface depends on the wettability of the solid as schematically illustrated in Figure IV-1. For a small spherical particle, neglecting gravity, the partitioning can be described by:

$$R = 1 - 1/\pi(\theta - \cos \theta \sin \theta)$$

where R is the ratio of the cross-sectional area of the particle in liquid to its total area of cross-section, and θ is the contact angle in radians. For irregular particles, the above relation defines an effective contact angle. The procedure involves placing a particle at the water/air interface. The value of R is determined from the projected image with the aid of the image analyzer which the contact angle was calculated. The particle size and shape, in terms of aspect ratio, can also be determined by the image analyzer at the same time. For each data set contact angles of at least 30 particles were measured from which the means and standard deviations were calculated.

EXPERIMENTAL RESULTS AND DISCUSSIONS

Prior to measurements of the distribution of contact angles for different ranks of coal particles, some studies were made to determine the influence of particle size, shape and time of contact of a particle with the liquid in order to determine the effects of these variables on the measurements.

The effect of particle size on the contact angle measurement is shown in Figure IV-2. The results show that the effect of gravity can be neglected if the particle size is small. That is, the value of contact angle measured by this technique might be somewhat smaller than the actual value when the particle size is too large. For the coal tested, the contact angle was independent of size in the range of 0.2 to 1.0 mm. The standard deviation of the measured contact angles was constant, independent of size.

The effect of particle shape is shown in Figure IV-3, in which the mean value and standard deviation of contact angles were plotted as a function of the aspect ratio. The mean of the contact angle was constant but the standard deviation increased with a decrease in the aspect ratio, that is when the particles are more elongated.

- a) Small Sphere (gravity negligible)
Partitioning Ratios, R

$$= \frac{A_2}{A_1 + A_2}$$

$$= 1 - (\theta - \sin\theta\cos\theta)/\pi$$

$$\phi = \theta$$

- b) Large Sphere
(gravity significant)

$$\phi \neq \theta$$

- c) Irregular (small) Particle

θ and ϕ are not uniquely measurable, but measured R can be used to calculate an effective angle ϕ - should provide a reasonable estimate of contact angle ϕ .

Figure IV-1. Schematic representation of the partitioning of a particle at the liquid/gas interface for determination of contact angle.

Figure IV-2. Effect of particle size on the contact angle measurements.

Figure IV-3. Effect of particle shape on the contact angle measurement.

To determine the effect of time of contact of a particle with the liquid, the contact angles of three single particles were determined as a function of time and the results are shown in Figure IV-4. Within the error of measurement the angle did not change with time. There was one exception, however for particle 1, where the first measured value was much larger than the others. This is because the particle changed its orientation after the first measurement. Therefore, it is necessary to wait for a minute or so after placing the particle at the interface to ensure that the particle is in a stable orientation before measurements are made.

The distributions of contact angles for the five solids listed in Table IV-1 are shown in Figure IV-5. A narrow size fraction for each material was used in order to eliminate the effect of particle size on the contact angle measurement. Fortunately, the natural shapes of particles were similar for the three coals as can be seen from the aspect ratios given in Table IV-1. The representative sample taken from each material consisted of more than one hundred particles. The particles of polymethylmethacrylate gave a much narrower range of contact angles. This material can be considered to be relatively homogeneous in chemical properties and the particles were spherical in shape. The mean contact angle was 66° with a standard deviation of only 3° . The range of contact angles for polyethylene particles was somewhat greater than that for the polymethylmethacrylate spheres, with a mean of 93° and a standard deviation of 6° . The polyethylene was also chemically homogeneous but the particles were irregular in shape with a mean aspect ratio of 0.73. All of the coal samples gave a much wider range of contact angles than the polymers. The broad distribution for coals was considered to arise from the heterogeneous properties of coal particles as well as their irregular shape. It can also be seen that the different coals gave different distributions. The average contact angle for lower rank coal is smaller than that for higher rank. The mean contact angles were 83° , 79° and 73° for anthracite, hvA bituminous and sub-bituminous coal respectively. The corresponding standard deviations were 14° , 13° and 13° indicating that coals have a wide range of wettabilities even for a given rank.

To determine the reasons for the wide variation of contact angles for coal the density of individual particles was determined by floating the particle after measuring

Figure IV-4. Effect of time of contact of a particle with water on the contact angle measurement.

Figure IV-5. Distribution of contact angles for different materials.

the contact angle in liquids of successively increasing densities. The results are shown in Figure IV-6. The particles with contact angles less than 50° had densities greater than 1.8. Obviously, these particles contain significant amounts of ash-forming mineral. More important, however, was the result that a large variation was obtained for different particles of the same density. These differences are considered to arise from differences in the wetting behavior of coal. Such variation may occur due to differences in maceral type, degree of surface oxidation and the presence hydrophilic surface regions resulting from the associated mineral matter.

The technique for determining contact angle reported here can also be used in evaluating advancing and receding angles. To determine the advancing angle, the 'dry' particles should be placed on the water/air interface. In this case, it is the liquid that replaces the air on the particle surface when the particle contacts the liquid. All of the values shown above are advancing angles. To determine receding angle, however, the particle was immersed in water for a certain time, which was about 5 minutes for the results discussed in this paper. The 'prewetted' particle was then placed at the water/air interface with a clean pair of tweezers. In this case, it is the air that replaces the liquid on the particle surface. Some values of advancing and receding angles obtained by different methods are compared in Table IV-3. The mean contact angle for 'dry' particles of anthracite obtained using the interface partitioning method was 83° , similar to the advancing angle of 81° measured by the sessile drop method. The value for 'prewetted' particles was 45° , which is in agreement with the receding angle of 43° measured by the sessile drop method. Considering the high variability of contact angles on coal, the agreement between different methods is fairly good.

The wetting distributions for 'dry' and 'prewetted' particles are shown in Figure IV-7 for the three coals. A greater difference between the wetting distributions for the different coals is seen for the 'prewetted' particles, i.e. for the receding angle. A complete explanation for differences in the advancing and receding angles is beyond the scope of this paper. It was observed, however, that the high contact angle of 'prewetted' sample was restored when the sample was dried at room temperature. These results suggested that the decrease in contact angle on prewetting is through a

Figure IV-6. Relationship between the contact angles and the density of particles.

Table IV-3. A comparison of different techniques for determining contact angle.

	Contact angle, degrees			
	Sessile Drop	Captive Bubble	Interface Partitioning	Remarks
Advancing				
Anthracite	81 ± 3	75 ± 7	83 ± 14	Dry
HvAbituminous	75 ± 5	61 ± 12	79 ± 13	Dry
Receding				
Anthracite	43 ± 6	47 ± 9	45 ± 13	Prewetted
HvAbituminous	27 ± 3	27 ± 10	33 ± 12	Prewetted

Figure IV-7. Differences of the contact angles between "dry" and "prewetted" particles.

reversible phenomena and not due to oxidation which for coal is usually irreversible.

SUMMARY

A novel method to determine the contact angle of individual particles is described. In this method the area of cross-section of a particle partitioned at an interface between two immiscible fluids is measured from which the contact angle can be estimated. In a separate study, the method was validated using materials of known contact angle (Wei, Hogg and Chander, 1990). In this investigation, it was used to determine wetting distributions for selected polymers and coal. For a coal, the particle size was found not to affect the contact angle provided the size was less than 1 mm. The lower size limit is determined by the resolution of the optical system. For the system used here, the limit was about 0.2 mm. Below this size resolution of the particle at the interface was poor. The particle shape seems to have a significant effect on standard deviation although the mean contact angle remained essentially constant. The standard deviation increased with decrease in the aspect ratio.

The distributions of contact angle for different materials showed that homogeneous polymer particles gave a narrow range of contact angles. It was most narrow for the polymer particles with a spherical shape. Heterogeneous particles of coal gave a much wider distribution even within the same rank. The particles from different ranks of coal gave different distributions of wettabilities. Polyethylene particles, which had the same size fraction and the aspect ratio as coal particles gave a narrower distribution than those for coals. The broader wetting distribution for coal was attributed to differences in chemical properties. The exact nature of such properties could not be established due to difficulties associated with analysis of small amounts of sample collected after contact angle measurements.

Using interface partitioning methods, both advancing and receding angles can be estimated by measuring the contact angles for 'dry' or 'prewetted' particles. A greater difference between the wetting distributions was observed when measurements were made using 'prewetted' particle which gave receding angles.

REFERENCES

Arnold, B. J., and Aplan, F. F., "The Hydrophobicity of Coal Macerals", *Fuel*, 68:651-658, 1989.

Aplan, F. F., "Coal Flotation- the Promise and Problems", *Advances in Coal and Mineral Processing Using Flotation*, S. Chander and R. R. Klimpel, Eds., SEM, Littleton, CO., 95-104, 1989.

Bartell, F. E., and Osterhof, H. J., "Determination of the Wettability of a Solid by a Liquid", *Ind. Eng. Chem.*, 19(11):1277-1280, 1927.

Brady, G. A., and Gauger, A. W., "Properties of Coal Surfaces", *Ind. and Engrg. Chem.*, 32:1599-1604, 1940.

Brown, D. J., "Coal Flotation", *Flotation-50th Anniversary Volume*, S. W. Fuerstenau, ed., AIME, New York, NY, 518-538, 1962.

Crowl, V. T., and Wooldridge, W. D., "A Method for the Measurement of Adhesion Tension of Liquid in Contact with Powders", *SCI Monograph*, Vol. 25, Society of Chemical Industry, London, 200-212, 1967.

Draves, C. Z., and Clarkson, R. G., "A New Method for the Evaluation of Wetting Agents", *Am. Dyest. Rep.*, 20:109-116, 1931.

Finch, J. F., and Smith, G. W., "Bubble-Solid Attachment as a Function of Bubble Surface Tension", *Can. Metall. Q.*, 14(1):47-51, 1975.

Glanville, F. O., and Wightman, J. P., "Actions of Wetting Agents on Coal Dust", *Fuel*, 58:819-822, 1979.

Glembotsky, V. A., *Izv. Akad. Nauk USSR Otd. Tekh. Nauk*, 1524-1531, (in Russian), 1953.

Gutierrez, J. A., Purcell, R. L., and Aplan, F. F., "Estimating Hydrophobicity of Coal", *Colloids and Surfaces*, 12:1-25, 1984.

Gutierrez, J. A., and Aplan, F. F., "The Effect of Oxygen on the Hydrophobicity and Floatability of Coal", *Colloids and Surfaces*, 12:27-51, 1984.

Hannins, R. N., and Rutter, P. R., "A Simple Method for Determining Contact Angles on Particles and Their Relevance to Flotation", *Int. J. Miner. Process.*, 27:133-146, 1989.

- Healy, T. W., and Fuerstenau, D. W., "The Oxide-Water Interface-Interrelation of the Zero Point of Charge and the Heat of Immersion", *J. Colloid Sci.*, 20:376-386, 1965.
- Horsley, R. M., and Smith, H. G., "Principles of Coal Flotation", *Fuel*, 30:54-63, 1951.
- Kaya, N., and Koishi, M., "The Wetting Properties of Powders and Devices for Measuring Them", *KONA*, No. 6:86-91, 1988.
- Mohal, B. R., and Chander, S., "A New Technique to Determine Wettability of Powders-Imbibition Time Measurements", *Colloids and Surfaces*, 21:193-203, 1986.
- Parekh, B. K., and Aplan, F. F., "The Critical Surface Tension of Wetting of Coal", *Recent Developments in Separation Science*, N. N. Li., ed., CRC Press, Inc., 4:107-113, 1978.
- Peek, R. L., and Mclean, D. A., "Capillary Penetration of Fibrous Materials", *Ind. Eng. Chem., Anal. Ed.*, 6(2):85-90, 1934.
- Sutherland, K. L., and Wark, I. W., "Principles of Flotation", Australasian Institute of Mining and Metallurgy, Melbourne, 1955.
- Taggart, A. F., Taylor, T. C., and Ince, R. C., "Experiments with Flotation Reagents", *Trans. Am. Inst. Min. Metall. Pet. Eng.*, 87:285-357, 1930.
- Walker, Jr., P. L., Peterson, E. E., and Wright, C. C., "Surface Active Agent Phenomena in Dust Abatement", *Ind. Eng. Chem.*, 44(10):2389-2392, 1952.
- Wei, D., Chander, S., and Hogg, R., "Distribution of wettability of coal", *Coal Preparation*, in press.
- Wei, D., Hogg, R., and Chander, S., "Contact Angle Determination from Partitioning of Particles at Fluid-Fluid Interfaces", Paper presented at Fall Information Transfer Session, Cooperative Program in Coal Research, The Pennsylvania State University, November 19-20, 1990.
- Williams, M. C., and Fuerstenau, D. W., "A Simple Flotation Method for Rapidly Assessing the Hydrophobicity of Coal Particles", *Int. J. Miner. Process.*, 20:153-157, 1987.
- Zettlemoyer, A. C., "Hydrophobic Surfaces", *J. Colloid Sci.*, 28:343-369, 1968.

LIST OF PAPERS AND PUBLICATIONS

T. Onlin and F.F. Aplan, "Surface Properties of Coal as Influenced by Collectors," Proc. Annual Tech. Conf. on Filtration and Separation, 37-44, 1989.

T. Onlin and F.F. Aplan, "Use of Amines and Other Nitrogenous Compounds as Collector for the Flotation of Coals of Various Ranks," paper presented at the Annual SME Meeting, Las Vegas, NV, Mar. 2, 1989. Abstract booklet, p. 152 (manuscript in preparation).

J. Pang, A. Briceno, and S. Chander, "A Study of Pyrite/Solution Interface by Impedance Spectroscopy," J. Electrochemical Soc., 137:3447-3455, 1990.

T.C. Hsu and S. Chander, "Effect of Salts on Partitioning of Coal and Ash Minerals at Hydrocarbon Oil/Water Interface," paper presented at Annual SME Meeting, Salt Lake City, UT, February 26-March 1, 1990. Abstract booklet, p. 172 (manuscript in preparation).

J. Pang and S. Chander, "Effect of Anodic Oxidation on Floatability of Pyrite," paper presented at the Annual SME Meeting, Denver, CO, February 25-28, 1991. Abstract booklet, p. 168 (manuscript in preparation).

Y.H. Chen and F.F. Aplan, "Comparative Flotation of Coal-Source and Ore-Source Pyrite, paper presented at the Annual Meeting, Denver, CO, Feb. 25-28, 1991, abstract booklet, p. 175 (manuscript in preparation).

M.C. Esposito and F.F. Aplan, "Use of Ordinary and Xanthated Polysaccharides as Pyrite Depressants During Coal Flotation, paper presented at the Annual SME Meeting, Denver, CO, Feb., 1991, abstract booklet, p. 169, (manuscript in preparation).

C.E. Raleigh, Jr. and F.F. Aplan, "The Effect of Feed Particle Size and Reagents on Coal-Mineral Matter Selectivity During the Flotation of Bituminous Coals," Minerals and Metallurgical Processing, 8:82-90, 1991.

S. Chander, "Electrochemistry of Sulfide Flotation: Growth Characteristics of Surface Coatings and Their Properties, with special reference to chalcopyrite and pyrite," International J. Mineral Processing, Vol. 33, pp. 121-134, 1991. (This paper was also published in the Proceedings of the 2nd Workshop on Flotation of Sulfide Minerals, Lulea, Sweden, June 18-19, 117-137, 1990.

S. Chander, A. Briceno and J. Pang, "On the Mechanism of Sulfur Oxidation in Pyrite," paper to be presented at the Annual SME Meeting, Phoenix, AZ, February 24-27, 1992.

T. Onlin and F.F. Aplan, "The Effect of Collectors on the Contact Angle and Flotation of Coals of Various Ranks", paper to be presented at the Annual SME Meeting, Phoenix, AZ, February 24-27, 1992.

LIST OF PAPERS AND PUBLICATIONS

(Continued)

M. Polat and S. Chander, "Kinetics of Emulsification in the Presence of Fine Particles", paper to be presented at the Engineering Foundation Conference on Dispersion and Aggregation: Fundamentals and Applications, to be held at Palm Coast, FL, March 15-20, 1992.

J. Pang and S. Chander, "The Effect of EDTA on collectorless Flotation of Pyrite," paper to be presented at The Symposium on Electrochemistry in Mineral and Metal Processing III, the Electrochemical Society, St. Louis, Missouri, May 17-22, 1992.

END

**DATE
FILMED**

6 / 16 / 92