PENNSTATE

DOE/PC/92122--T1

DE93 009706

Novel Bimetallic Dispersed Catalysts for Temperature-Programmed Coal Liquefaction

**Technical Progress Report
October - December 1992**

Chunshan Song and Harold H. Schobert

**Fuel Science Program
Department of Materials Science and Engineering,
The Pennsylvania State University
University Park, Pennsylvania, PA 16802**

February 1993

**Prepared for the U.S. Department of Energy
under Contract No.
DE-AC22-92PC92122**

US/DOE Patent Clearance is not required
prior to the publication of this document.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

gpc

DE-AC22-92PC92122-TPR-1

Novel Bimetallic Dispersed Catalysts for Temperature-Programmed Coal Liquefaction

**Technical Progress Report
October - December 1992**

Chunshan Song and Harold H. Schobert

**Fuel Science Program
Department of Materials Science and Engineering,
209 Academic Projects Bldg., The Pennsylvania State University
University Park, Pennsylvania, PA 16802**

February 1993

**Prepared for the U.S. Department of Energy
under Contract No.
DE-AC22-92PC92122**

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process or service by trade name, mark manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ACKNOWLEDGEMENTS

This on-going project is supported by the U.S. Department of Energy, Pittsburgh Energy Technology Center, in Advanced Coal Research Program. Dr. Udaya Rao is the DOE/PETC Project Manager. Drs. H.H. Schobert and C. Song are the Co-Principal Investigators at Penn State. The authors wish to express their appreciation to Dr. Udaya Rao of DOE/PETC for his support of this effort. The authors would also like to thank Mr. D. Glick and Dr. A. Davis for providing the samples and analytical data of the Department of Energy Coal Samples (DECS) from DOE/Penn State Coal Sample Bank, and Mr. R.M. Copenhaver for the fabrication of tubing bomb reactors.

TABLE OF CONTENTS

ABSTRACT	1
INTRODUCTION	2
PROJECT OBJECTIVES	4
TECHNICAL PROGRESS	7
1. LITERATURE SURVEY	7
Mechanisms of Coal Liquefaction and Catalysis.....	7
Bimetallic Dispersed Catalysts	9
Temperature-Programmed Liquefaction	10
2. STATEMENT OF WORK	12
Task 1. Selection and Characterization of Feedstocks	13
Task 2. Preparation and Characterization of Catalysts	16
Task 3. Activity and Selectivity Tests by Model Reaction	17
Task 4. Temperature-Programmed Catalytic Liquefaction	19
Task 5. Effects of Catalysts on Product Quality	20
LITERATURE CITED	21
APPENDIX - ANALYTICAL DATA FOR COALS SELECTED	29

ABSTRACT

Development of new catalysts is a promising approach to more efficient coal liquefaction. It has been recognized that dispersed catalysts are superior to supported catalysts for primary liquefaction of coals, because the control of initial coal dissolution or depolymerization requires intimate contact between the catalyst and coal. This research is a fundamental and exploratory study on catalytic coal liquefaction, with the emphasis on the development of novel bimetallic dispersed catalysts for temperature-programmed liquefaction.

The ultimate goal of the present research is to develop novel catalytic hydroliquefaction process using highly active dispersed catalysts. The primary objective of this research is to develop novel bimetallic dispersed catalysts from organometallic molecular precursors, that can be used in low concentrations (<1%) but exhibit high activity for efficient hydroliquefaction of coals under temperature-programmed conditions. The major technical approaches are, first, to prepare the desired heteronuclear organometallic molecules as catalyst precursors that contain covalently bound, two different metal atoms and sulfur in a single molecule. Such precursors will generate finely dispersed bimetallic catalysts such as Fe-Mo, Co-Mo and Ni-Mo binary sulfides upon thermal decomposition. The second major technical approach is to perform the liquefaction of coals impregnated with the organometallic precursors under temperature-programmed conditions, where the programmed heat-up serves as a step for both catalyst activation and coal pretreatment or preconversion. Two to three different complexes for each of the Fe-Mo, Co-Mo, and Ni-Mo combinations will be prepared. Initial catalyst screening tests will be conducted using a subbituminous coal and a bituminous coal. Effects of coal rank and solvents will be examined with the selected bimetallic catalysts which showed much higher activity than the dispersed catalysts from conventional precursors.

Concordant with the goal of developing an efficient catalytic liquefaction process, we seek to understand the functions of the new catalysts and their effects on product quality by characterizing the liquefaction products and performing the tests using model reactions of aromatic and polar compounds that are relevant to coal liquefaction. This research will provide a novel approach to the design of catalysts for coal liquefaction, in that the methodology will enable the dispersed catalyst to be tailored to display high activity at low loading level.

INTRODUCTION

Currently, coal accounts for about 23% of the U.S.'s total energy generation, and in 1990, coal production reached 1 billion tons for the first time in history (Lepkowski, 1991). Electric utilities consume nearly 800 million tons of coal per year in the U.S., and about 55% of all the electricity generated in the U.S. is produced from coal (Ruth, 1991). The coal reserves are more than double the world's known petroleum reserves (Ruth, 1991). On the other hand, the average daily consumption of petroleum products in the U.S. is as high as 17 million barrels per day, and almost half of the petroleum crude is now imported; about two-thirds of the total petroleum consumed is used for transportation fuels (Farcasiu, 1991). The U.S. chemical industry uses the equivalent of almost 1.2 million barrels of crude oil daily as feedstock, plus another 2.6 million-bbl equivalent for total needs (Lepkowski, 1991). The importance of secure supply of liquid hydrocarbon sources and direct coal liquefaction to produce liquid transportation fuels has been well documented (Lumpkin, 1988; DOE COLIRN, 1989; Moroni, 1991; Farcasiu, 1991). Liquefaction is also one of the important routes for producing useful aromatic chemicals and advanced materials from coals (Song and Schobert, 1992a, 1993a; Schobert and Song, 1992).

Direct coal liquefaction is the process for producing liquid fuel from coal and involves the reactions of coal with reducing gas (H_2) in a solvent vehicle at high temperature and high pressure. On the microscopic level, the coal conversion into liquids is an extremely complex process and involves both chemical and physical transformations. Despite enormous strides in coal liquefaction research, and great effort at Wilsonville Advanced Two-Stage Liquefaction Facility to reduce the cost of coal-derived distillates, coal-derived liquids are still not competitive with petroleum crudes. Further improvements are required and the most promising approach would be the development of improved catalytic process. It is known that direct coal liquefaction proceeds through two loosely defined stages, coal dissolution into solvent-soluble materials, followed by upgrading of the solubilized products. The distribution and quality of primary liquefaction (coal dissolution) products depend on the coal, catalyst, solvent and process conditions used in the first stage. The upgrading of primary liquefaction products into transportation fuels requires two conversion steps: an overall upgrading of heavy materials to distillate materials, followed by the upgrading of different distillate fractions to liquid products with the necessary properties for use as transportation fuels including gasoline, jet fuels, and diesel fuels.

Numerous studies have been conducted of the application or improvement of conventional catalysts and of the development of new catalysts for hydroliquefaction of coals. As indicated recently by Derbyshire (1988, 1990), research on catalytic liquefaction has been retarded by the persistent and misguided belief that catalysts cannot influence the reactions whereby the solid coal feed is converted to soluble products. It is relatively easy for conventional supported catalysts to

promote the reactions after the primary liquids are formed. However, by this time the most critical reactions may have taken place and distributions of products may have already been determined (DOE COLIRN Panel, 1989). In this respect, dispersed catalysts are superior because they may be able to affect the coal dissolution due to their more intimate contact with coal. Monitoring the change of system pressure for catalytic reactions has clearly demonstrated that some dispersed Ni and Mo catalysts can promote the hydrogenation reactions of coals at fairly low temperatures, as revealed by the considerable H₂ uptake at 300-350 °C (Bockrath et al., 1990; Song et al., 1991a). Some novel Lewis acidic Ni and Mo catalysts also enhance the coal pyrolysis at temperatures as low as 300°C, even under N₂ atmosphere (Song et al., 1986a, 1987a, 1991a).

Extensive research at Pittsburgh Energy Technology Center, PETC (Bockrath et al., 1984, 1986, 1991; Utz et al., 1989; Cugini et al., 1991a, 1991b) and Penn State (Davis et al., 1986, 1989; Derbyshire et al., 1986a, 1986b, 1989; Stansberry et al., 1987; Burgess and Schobert, 1990; Burgess et al., 1991; Artok et al., 1991) has demonstrated the potential of using dispersed molybdenum or iron catalyst. The work at Penn State has demonstrated that the combination of low-temperature catalytic reaction followed by the high temperature catalytic reaction using dispersed molybdenum significantly enhanced coal conversion and oil production. More recent work in this laboratory has shown that temperature-programmed liquefaction is more effective for converting low rank coals (Song et al., 1991b; Song and Schobert, 1992b; Huang et al., 1992). We have found that low-temperature catalytic reactions using dispersed Mo catalyst lead to some desirable changes in coal structure, and the temperature-programmed catalytic liquefaction affords considerably higher conversion than the conventional non-programmed or the temperature-staged liquefaction (Song et al., 1992b; Huang et al., 1992). All these results point to the beneficial effects of dispersed catalysts for lower-severity liquefaction, and clearly indicate that dispersed catalysts could significantly affect the chemistry of initial coal dissolution (primary liquefaction) and reduce undesirable reactions. It should be noted that almost all of the previous work used precursors of single transition metal sulfides, and little has been reported about bimetallic dispersed catalysts.

Development of new catalysts is a promising approach to more efficient coal liquefaction. Coal conversion catalysis is a comparatively immature field. Perhaps the most promising approach to the development of novel catalysts lies in research into multi-component systems, which, compared to the work with single metal catalysts, are essentially unexplored (Derbyshire, 1990). Several reports have demonstrated on the synergistic effects for multi-component Lewis acidic Zn-, Ni-, and Mo-based catalysts for coal liquefaction or model reactions (Mobley and Bell, 1980; Song et al., 1986a, 1988a, 1991a). Synergism has been reported for Fe-Mo catalysts by Garg and Givens (1984). Even under high-severity conditions (440°C, 2000 psi H₂), significant benefits were observed by using Fe and Mo together; simultaneous impregnation of coal with Fe and Mo significantly increased coal, preasphaltene and asphaltene conversion as compared to individual metals for liquefaction of a

Kentucky bituminous coal in the presence of SRC-II heavy distillate. There are clear evidences of the synergism for two or multi-component supported catalysts in the field of heterogeneous catalysis, especially hydrotreating catalysts such as Co-Mo and Ni-Mo. We can anticipate that synergistic effects of multicomponent dispersed catalysts could lead to significantly improved catalytic processes for direct conversion of coal to transportation fuels. 4

Emphasis for developing novel catalytic process should be directed at promoting the direct transformation of coal to distillates that have low aromaticity and low heteroatom content. This is primarily because the 1990 Clean Air Act Amendments and the increased worldwide concern about global warming will require the production of liquid transportation fuels from coals be based on new strategy away from the formation of aromatic products and more toward formation of hydrogen-rich aliphatic hydrocarbons. Equally important, novel catalysts should promote coal conversion into low-molecular-weight products and their hydrogenation at lower-severity conditions. The present research is a fundamental and exploratory study on catalytic coal liquefaction, with the emphasis on the development of novel bimetallic dispersed catalysts for temperature-programmed liquefaction.

PROJECT OBJECTIVES

The ultimate goal of the present research is to develop highly active dispersed catalysts and novel catalytic hydroliquefaction process. The primary objective of this research is to develop novel bimetallic dispersed catalysts from organometallic molecular precursors, that can be used in low concentrations (<1%) but exhibit high activity for efficient hydroliquefaction of coals under temperature-programmed conditions. The major technical approaches are, first, to prepare the desired heteronuclear organometallic molecules as catalyst precursors that contain covalently bound (two different) metal atoms and sulfur. Such precursors will generate finely dispersed bimetallic catalysts such as Fe-Mo, Co-Mo and Ni-Mo binary sulfides upon thermal decomposition. The second major technical approach is to perform the liquefaction of coals impregnated with the organometallic precursors under temperature-programmed conditions, where the programmed heat-up serves as a step for both catalyst activation and coal pretreatment or preconversion. Concordant with the goal of developing an efficient catalytic liquefaction process, we seek to understand the functions of the new catalysts and their effects on product quality by characterizing the liquefaction products and performing the tests using model reactions of aromatic and polar compounds that are relevant to coal liquefaction.

Figure 1 illustrates the technical approach and experimental efforts of the present research. We seek to explore novel bimetallic dispersed catalysts with desired catalytic activity for conversion of coal to hydrogen-rich distillates under appropriate conditions. A number of organometallic precursors will be prepared and dispersed onto coal by impregnation methods. Model compound

tests will be performed to gain some insight into the catalytic functions - activity and selectivity - of the new catalysts. Temperature-programmed coal liquefaction will be carried out to assess the potential of the new bimetallic catalysts. The information feedback from liquefaction and model reactions will be used to guide further work on the preparation of novel catalysts. 5

There are three features of the proposed novel process: 1) organometallic precursor that contain sulfur and two different transition metals in a single cluster, 2) high dispersion of the binary metal sulfide catalysts on coal surface, and 3) temperature-programmed liquefaction. The idea behind our approach to developing novel catalysts is that binary metal sulfide catalysts containing two different active metals and sulfur within the molecular dimension would be much more effective in promoting simultaneously a variety of chemical reactions including hydrogenation, hydrodeoxygenation, hydrodesulfurization and hydrodenitrogenation, which are all desirable for converting coal to hydrogen-rich distillates with low heteroatom content in high yields. By dispersing the solvent-soluble precursors on the coal surface via impregnation from an appropriate solvent system, it is expected that higher conversions and oil yields can be obtained with lower metal loading ($< 1\%$). Our preliminary data have shown that Mo-Co binary sulfides, prepared from a single thiocubane type cluster, offer some unique advantages over the well-known dispersed Mo catalyst from inorganic metal salts. These catalysts will be compared to conventional dispersed catalysts and their combinations.

The use of temperature-programming in the proposed catalytic process is motivated by our recent finding that temperature-programmed liquefaction is much more effective for converting coals, especially low-rank coals, as compared to conventional processes at a single temperature as well as temperature-staged liquefaction. When catalyst precursors are dispersed on coals, the programmed heat-up serves as a dual-aimed step: on the one hand it facilitates transforming the precursor to catalytically active phase; on the other hand it provides a time period for beneficial coal pretreatment which is desirable low-temperature preconversion. Much of the relevant chemistry and details of technical issues will be described in the following section of literature review. This research will provide valuable and needed information on the key factors for developing highly effective catalysts, and the design of improved catalytic process. Many of the metal clusters can be synthesized by using relatively simple procedures which can be scaled-up readily; the programmed heat-up can be incorporated into the industrial plant operations without major problems. Therefore, the proposed approach, if successful, could contribute greatly to the development of novel processes for direct coal liquefaction.

Figure 1. Experimental approach of the proposed research

TECHNICAL PROGRESS

LITERATURE SURVEY

Mechanisms of Coal Liquefaction and Catalysis

Mechanisms of Coal Liquefaction. The coal organic matrix is thought to consist of relatively smaller structural units that are connected together by a number of weak and strong bonds to form a three-dimensional macromolecular network (Larsen et al., 1985). The initial step in primary coal liquefaction is thermally initiated fragmentation. The coal-derived reactive fragments (radicals) must be stabilized via hydrogen-donation by hydrogens in donor solvent, gas-phase H_2 and coal itself to form preasphaltene, asphaltene and oil. Otherwise, the reactive fragments promptly recombine or crosslink to form insoluble materials which can be more refractory than the original coal (Song et al., 1989). Such retrograde reactions could also make the solubilized products less amenable to subsequent upgrading. Balancing the fragmentation rate to the rate of stabilization is a critical factor, especially for low-rank coals (Song et al., 1987b, 1989). Stenberg et al. (1989) and Janikowski and Stenberg (1989) suggested that high liquefaction conversion can be achieved at relatively lower temperatures by matching the rate of radical production with the ability of a solvent/gas system to cap the radicals.

With respect to the chemistry of thermal fragmentation, of great importance is that recent research has revealed that coals, especially low-rank coals, are more reactive than previously thought, as described later, and in conventional high-severity processes there is an imbalance between thermal fragmentation and stabilization, resulting in extensive retrograde reactions (DOE COLIRN Panel, 1989). In a two-stage liquefaction process, the single most significant requirement for the first stage is to control the primary liquefaction (dissolution) of coal. The outcome of this process determines the nature of problems to be encountered in subsequent catalytic upgrading stage (Derbyshire, 1988). The goal of improving coal reactivity and reducing retrograde reactions in the dissolution stage can be achieved by controlling the reaction conditions and by using a catalyst.

Catalysis. The catalytic aspects for coal liquefaction are different from those for upgrading of coal liquids. Numerous studies have been conducted on catalytic hydroliquefaction using supported and unsupported catalysts. It is relatively easy for conventional supported catalysts to promote the reactions after the primary liquids are formed. However, by this time the most critical reactions may have taken place and distributions of products may have already been determined (DOE COLIRN Panel, 1989). The fact that there exists diffusional limitations even in upgrading of coal liquids over supported catalysts (Song et al., 1991c, 1991d, 1992c) also points to the

conclusion that the restricted access of coal to the surface of supported catalysts makes them unable to affect the initial reactions of solid coal. In this respect, dispersed catalysts are superior because they may be able to affect the coal dissolution due to their more intimate contact with coal.

8

A brief review of previous work using dispersed catalysts for coal liquefaction is given below, since the present research project involves the development of novel dispersed catalysts. Sulfided molybdenum is a typical hydrogenation catalyst. Extensive research at Pittsburgh Energy Technology Center (Bockrath et al., 1984, 1986, 1991; Utz et al., 1989) and Penn State (Davis et al., 1986, 1989; Derbyshire et al., 1986a, 1986b, 1989; Stansberry et al., 1987; Burgess and Schobert, 1990; Burgess et al., 1991) has demonstrated the potential of dispersed molybdenum catalyst. In most cases, the catalyst was impregnated on coal as a precursor salt such as sulfided ammonium molybdate or ammonium tetrathiomolybdate, which decomposes upon heating to higher temperatures to form MoS_2 (Naumann et al., 1982) and thus disperses MoS_2 on coal (Stansberry et al., 1987; Utz et al., 1989). These previous investigations have demonstrated that low-temperature catalytic reaction using dispersed molybdenum catalyst can improve coal reactivity. In the temperature-staged liquefaction, conducting the reaction using sulfided molybdenum at low-temperature leads to higher oil yield upon reaction at high temperature, without remarkable increase of hydrocarbon gas. The low-temperature stage is apparently more than a simple slow-down of thermal fragmentation of coal. Previous work in this laboratory has revealed that the reactions using dispersed molybdenum catalysts remarkably enhanced hydrodesulfurization of high-sulfur lignites at the temperatures as low as about 300°C (Garcia and Schobert, 1988, 1989a, 1989b, 1990, 1991).

Another type of dispersed catalyst is Lewis acidic metal halide. ZnCl_2 is a typical Lewis acid catalyst. Since the work of Zielke et al. (1966a, 1966b), this molten salt catalyst has been widely studied both in liquefaction of coal and in the reaction of model compounds, as reviewed by Derbyshire (1988). While the insufficient recovery and corrosive nature of this acid catalyst hindered its practical application, the catalyst chemistry is sufficiently attractive (Derbyshire, 1988). Recently, it has been found that two multi-component Lewis acids, NiCl_2 - and MoCl_3 - LiCl - KCl , are effective dispersed catalysts; these catalysts can significantly promote oil production in liquefaction at 400°C , especially for subbituminous coals, and they can also substantially enhance coal conversion in low temperature pyrolysis (300 - 400°C) in N_2 (Song et al., 1986a, 1986b, 1987a, 1988a, 1988b). The catalytic features of, and the synergistic effects between, different components of these ternary catalysts have been reviewed recently (Song et al., 1991a). The use of other water-soluble catalyst precursors such as nickel acetate (Takemura and Okada, 1988), ferrous sulfate (Garg and Givens, 1984; Artok et al., 1992), nickel nitrate and cobalt nitrate (Garg and Givens, 1984), and nickel sulfate (Garcia and Schobert, 1991) has also been reported. Recently, the preparation and application of fine particles of iron carbides (Bi et al., 1991) and metal colloid materials (Klavetter et al., 1991) as dispersed catalyst for coal liquefaction have also been reported.

Bimetallic Dispersed Catalyst from Organometallic Precursors

Two-component or multi-component dispersed catalysts are essentially unexplored, although the pioneering work on liquefaction using dispersed catalysts was reported early in 1950s (Weller and Pelipetz, 1950, 1951; Hawk and Hiteshu, 1965). Related to the background of this work is that besides the water-soluble catalysts like those mentioned above, Hawk and Hiteshu (1965) and more recent reports (Wantanabe et al., 1984; Suzuki et al., 1985, 1991; Herrick et al., 1990; Artok et al., 1992a, 1992b) also showed that other types of dispersed catalysts, oil-soluble organometallic compounds such as $\text{Fe}(\text{CO})_5$, $\text{Mo}(\text{CO})_6$, Mo naphthenate, and $\text{Ru}_3(\text{CO})_{12}$ are effective catalysts or precursors for high-severity liquefactions. The use of oil-soluble catalyst precursors such as molybdenum naphthenate in coal/resid co-processing and in model reactions has also been reported to be successful (Curtis et al., 1987; Curtis and Pellegrino, 1989;). Hirschon and Wilson (1991) also reported that some organometallic precursors are more active than the inorganic salts. However, very few studies have been reported on the catalytic activity of binary sulfides or multi-component inorganic or organometallic precursors (Garg and Givens, 1984; Hirschon and Wilson, 1991; Song et al., 1991a).

There are some unique advantages of organometallic compounds as candidates of catalyst precursors. First, most organometallic compounds are soluble in hydrocarbon solvents and may be used as oil-soluble precursors. It is well known that increasing dispersion of catalysts increases their effectiveness. In the case of dispersed catalyst for coal conversion, the general method of increasing dispersion is to introduce the catalyst as a soluble precursor. Second, organometallic compounds can be easily decomposed to metal sulfides or oxides at low temperatures. This means they can form activated catalysts at lower temperatures, and this is apparently an advantage when compared to inorganic salt precursors such as ATTM which decomposes at relatively higher temperatures. It is believed that the high activity coupled with high dispersion can allow catalyst concentrations of substantially less than 1 wt% be used.

The most novel approach of the proposed work is the preparation of bimetallic dispersed sulfide catalysts from organometallic compounds or metal clusters that contain sulfur and two metals in a single molecule. These organometallic precursors are distinctly different from those mentioned above. The advantage of using two metals in a single catalyst has been demonstrated in many cases in the field of heterogeneous catalysis. It is well known that the addition of a second transition metal such as Co or Ni to MoS_2 or WS_2 can give rise to a significant increase in hydrogenation and hydrodesulfurization (HDS) activity (Satterfield, 1991). Five-fold to ten-fold increases of HDS activity of the unpromoted sulfide upon addition of second transition metal sulfide are not uncommon for hydrotreating catalysts (Bond, 1987). Our interest in the organometallic compounds

was stimulated by the recent book on metal clusters published by Mingos and Wales (1990). Although this book contains no information on catalytic aspects, it seemed to us that highly active catalysts might be obtained from some of the clusters containing metal-metal bonds, especially heteronuclear clusters containing two metals such as Fe or Co and Mo in a single molecule. While the proposed technical approach is of exploratory nature, this approach seems to be promising from our preliminary data on coal liquefaction and the data of Chianelli et al. (1990) on HDS.

In their work on the fundamental study of active sites in supported transition metal sulfides and role of Co as a promotor in Co-Mo/Al₂O₃, Chianelli et al. (1990) et al. prepared several unsupported Co-Mo catalysts from [Co(ethylenediamine)₃]²⁺[MoS₄]²⁻, trianion Co(MoS₄)₂³⁻, and Co₂Mo₂S₄ (S₂CNEt₂)₂(CH₃CN)₂(CO)₂ thiocubane prepared by using the procedure of Halbert et al. (1985). After thermal decomposition, these complexes led to the formation of Co/Mo/S amorphous materials. Table 1 shows the activity of unsupported Co-Mo catalysts derived from molecular precursors for HDS of dibenzothiophene (DBT). It is clear from Table 1 that the two Co/Mo/S cluster precursors exhibit improved catalytic activity. From these data, Chianelli et al. (1990) concluded that the covalent bonding of Co, Mo, and S apparently facilitates formation of an active Co promoted Mo/S phase.

Table 1. Activity of Unsupported Catalysts for HDS of DBT*

Molecular Precursor	HDS Activity**
(NH ₄) ₂ MoS ₄	40
Co(en) ₃ MoS ₄	149
Co(MoS ₄) ₂ ³⁻	245
CoMo Cubane	374

* Chianelli et al. (1990); ** 10¹⁶ molecules/sec/(g eq metal sulfide)

Temperature-Programmed Liquefaction Using Dispersed Catalysts

The conventional concept for high-severity conversion of coal is that coal must be heated to high temperatures (400-450°C) causing thermal cleavage of bonds in organic matrix of coal to yield free radicals, which are capped by hydrogen to form low-molecular-weight products. However, recent fundamental research in coal liquefaction and pyrolysis has revealed that coal is more reactive than had been thought previously. The thermally initiated reactions of coal can take place very rapidly (Whitehurst et al., 1980a, 1980b) and, especially for low-rank coals, can occur at lower

temperatures (Neavel, 1982; Suuberg et al., 1985, 1987; DOE COLIRN, 1989; Song et al., 1991a). 1 1
It is now recognized that low-rank coals are more reactive than had been thought previously, and their conversion in high-severity processes is accompanied by significant retrogressive reactions (DOE COLIRN Panel, 1989; Song et al., 1989).

Due to the presence of various C-O and C-C bonds in coals, there may be a relatively broader distribution of dissociation energies of bonds connecting the structural units in low-rank coals, as can be visualized from the dissociation energies of various C-O, C-C and C-H bonds that are believed to be relevant to coal and coal conversion processes (Song et al., 1991a). The concept of bond energy distribution for coals is also supported by the results of temperature-programmed pyrolysis (TPP) of coals ranging from brown to bituminous coals (Song et al., 1986a, 1987a, 1991a). TPP data show that more bonds in low-rank coals are thermally broken at lower temperatures as compared to bituminous coals. The question that arises for liquefying low-rank coals is how to balance the rates of bond cleavage with the rates of hydrogen transfer to the radicals. Of some importance to the temperature-programmed liquefaction work are several recent reports showing that using relatively slow heating rates is effective for liquefying low-rank coals (Song et al., 1987b, 1989; Masuyama and Kageyama, 1989). In catalytic liquefaction, temperature-staged conditions have been shown to improve coal conversion and oil yields (Derbyshire et al., 1986; 1990; Burgess and Schobert, 1990; Burgess et al., 1991), even in the aqueous liquefaction system (Stenberg et al., 1989).

For a given reaction system, controlling the conditions is important for maximizing the yield and quality of products and minimizing retrogressive reactions. The retrogressive reactions may include the crosslinking of thermally generated radicals and condensation of thermally sensitive compounds (Song et al., 1991b). The temperature-programmed liquefaction (TPL) seeks to efficiently liquefy low-rank coals by controlling the rate of pyrolytic cleavage of weak bonds while minimizing the retrogressive crosslinking of radicals and thermally sensitive groups. Recently we have demonstrated that temperature-programmed liquefaction is a promising approach to more efficient liquefaction of coals, especially low rank-coals (Song et al., 1991b, 1992a, 1992b; Song and Schobert, 1992b; Huang et al., 1992). Given below is a brief description of the rationale and advantages of the temperature-programmed liquefaction (TPL) as compared to non-programmed liquefaction (N-PL).

We tested two subbituminous coals using several solvents including middle distillates (WI-MD) produced from Run 259 in Wilsonville coal liquefaction plant, tetralin, naphthalene, and 1-methylnaphthalene. The selected temperature program consisted of a low-temperature soak at 200 °C for 15 min, programmed heating to a final temperature at about 7°C/min, followed by a 30 minute hold at the final temperature (300, 350, 375, 400, 425, and 450 °C). We expect few chemical reactions to occur at 200°C. The rationale for selecting such a low temperature for soaking is to allow

the solvent molecules to penetrate into the interior of coal particle (diffusion and swelling), before they are needed as hydrogen donors for stabilizing the radicals and thermally labile compounds in the subsequent heat-up period and high temperature stage. In the catalytic runs, we used ammonium tetrathiomolybdate (ATTM) as precursor of dispersed MoS₂ catalyst. Detailed results may be found elsewhere (Song and Schobert, 1992b; Huang et al., 1992; Song et al., 1992b). Briefly, the temperature-programmed liquefaction in tetralin and WI-MD afforded considerably higher conversion and at higher final temperatures, higher oil yields, than the non-programmed liquefaction. Table 2 shows some of our recent results on temperature-programmed (TPL), temperature-staged (TSL, 200°C/400°C) and conventional, non-programmed (N-PL) catalytic liquefaction of a Montana subbituminous coal using ATTM as catalyst and WI-MD as solvent (Huang et al., 1992).

Table 2. Effects of Temperature-Programming in Liquefaction of Coal Using Dispersed Mo Catalyst**

Catalyst	Solvent	Feature	Final Temp °C	THF-Conv dmmf wt %	Toluene-Conv dmmf wt %	Oil + Gas dmmf wt %
ATTM	WI-MD	TPL	400	91.0	75.4	51.5
ATTM	WI-MD	TSL	400	89.5	71.6	44.0
ATTM	WI-MD	N-PL	400	84.4	71.6	42.7
None	WI-MD	N-PL	400	52.2	42.6	30.2
None	WI-MD	TPL	400	58.6	47.5	30.3

** Reported by Huang, L.; Song, C.; Schobert, H.H., Am. Chem. Soc. Div. Fuel Chem. Prepr., 1992, 37 (1), 223-227.

STATEMENT OF WORK

This research project will focus on the novel bimetallic dispersed catalysts for temperature-programmed catalytic coal liquefaction. The experimental work can be divided into five Tasks.

Task 1. Selection and Characterization of Feedstocks

Task 2. Preparation and Characterization of Catalysts

Task 3. Activity and Selectivity Tests by Model Reactions

Task 4. Temperature-Programmed Catalytic Liquefaction

Task 5. Effects of Catalysts on Product Quality

Task 1. Selection and Characterization of Feedstocks

The objectives of this Task are to select the coals and solvents and to characterize their structural and compositional features. The most important part of the proposed work is the development of the novel catalysts for temperature-programmed liquefaction of well-characterized coals, and of fundamental chemistry of key catalytic aspects for conversion of coal to transportation fuels. However, in order to support DOE's mission in coal liquefaction process development, we realize that it is also important to select the coals that have been used in pilot plant tests supported by DOE, to test the novel catalysts under process conditions with process solvents from such pilot plant, and to make cross comparison experiments using the dispersed catalyst that has been tested recently at Wilsonville plant. Therefore, Task 1 can be divided into three activities, selection of 1) coal samples and 2) solvent samples and 3) analytical characterization of these samples. The final selection of coals and solvents will be made in consultation with DOE project managers.

Selection of Coals. One lignite, two subbituminous and two bituminous coals shall be selected from the DOE/Penn State Coal Sample Bank, preferably from the Department of Energy Coal Sample series (DECS). The advantages of using the DECS samples are that these samples were collected recently and stored under inert atmosphere, and complete information on the elemental and maceral composition of these samples will be available to the proposed work at no cost. For direct comparison of results, one lignite, one subbituminous and one bituminous coals that are being used in on-going DOE projects at Penn State (Schobert, Song, Hatcher, DE-AC22-91PC91042; Davis and Schobert, DE-AC22-89PC89877) are to be used. Examples of such coals are Texas Big Brown lignite, Dietz and Wyodak subbituminous coals, and Pittsburgh #8 and Blind Canyon bituminous coals. In order to provide immediately comparable results to DOE for the novel catalysts to be developed, two other coals, preferably one subbituminous coal and one bituminous coal that have been used extensively at the Advanced Two-Stage Coal Liquefaction Plant at Wilsonville or other plant will be solicited from DOE. Examples of such coals are Black Thunder subbituminous and Illinois No.6 bituminous coals.

Table 2 is a list of the tentatively selected coals. In order to provide the detailed information on the characteristics of available coals to the DOE/PETC project managers, we also included the detailed analytical data for the relevant coal samples of the DECS-series in Appendix 1. As shown in Appendix 1, there is also an Illinois #6 coal in the DOE/Penn State sample bank (DECS-2), but this sample and the Illinois #6 coal tested in DOE-supported pilot plant were from different mines (There are several coal mines over 15 miles in the area where the so-called ILL#6 coals are mined by Peabody Coal company). The final selection will be made in consultation with the DOE Project Manager.

Table 3. Coal Samples Tentatively Selected for This Project

State	Number	Name/Rank	C%, daf	From
Main Selection				
TX	DECS-1	Texas (Bottom) Lignite	(74.3%C)	DECS*
MT	DECS-9	Montana (Diez) Subbituminous	(76.1%C)	DECS
PA	DECS-12	Pittsburgh #8 Bituminous	(84.8%C)	DECS
WY	BT	Black Thunder Subbituminous	* *	From DOE
IL	ILL#6	Illinois #6 Bituminous	* *	From DOE
Other Coal Samples for Cross-Comparison				
WY	DECS-8	Wyodak Subbituminous	(75.8%C)	DECS
UT	DECS-6	Blind Canyon Bituminous	(81.3%C)	DECS

* DECS series coal samples from DOE/Penn State Coal Sample Bank.

Selection of Solvents. In order to develop better catalysts, the initial catalyst screening tests will be conducted in the presence of a non-donor solvent such as methylnaphthalene. For the novel bimetallic dispersed catalysts (to be developed in Tasks 3 and 4) that showed high activity, their potential for practical application will be evaluated using several solvents. The solvent effects in the catalytic liquefaction using the selected catalysts will be examined using a H-donor (such as tetralin), a non-donor (such as methylnaphthalene), two process solvents such as the middle distillates and heavy distillates from Wilsonville coal liquefaction plant, and a petroleum resid. The preferable liquid distillates as process solvents are those from the appropriate runs conducted recently at Wilsonville plant with Black Thunder and/or Illinois No.6 coal. Based on the foregoing, the influence of solvents in liquefaction using the selected, novel bimetallic dispersed catalysts will be examined using the following hydrocarbon solvents and process solvents.

A brief review of the relevant chemistry of solvent effects is given as follows. The use of solvent is important in catalytic reactions from both physical (dilution, heat and mass transfer) and chemical (H-donation, synergistic effects) viewpoints, although in general the nature of catalysts (activity, selectivity) is more important than the nature of the solvent. Using H-donor solvent can help stabilization of fragments through H-transfer. The use of ammonium molybdate (Bockrath et al., 1986) and NiCl_2 - and MoCl_3 -LiCl-KCl catalyst (Song et al., 1987a, 1988b) and dispersed MoS_2 (Hirschon and Wilson, 1991) in liquefaction of bituminous and subbituminous coals has been found to reduce the demands placed on the H-donor solvent. However, an interesting effect of decreasing the total hydrogen consumption (sum of hydrogen consumed from H_2 and tetralin) without decreasing hydrogen content of products was observed with the co-presence of tetralin solvent and NiCl_2 -LiCl-KCl catalyst, as compared to the solvent-free catalytic liquefaction (Song et

al., 1987a, 1988b). The use of LiCl-KCl (without NiCl₂), at various loading levels (from 0.1:1 to 1:1 1 5 weight ratios) on a subbituminous coal (which showed little catalytic effect on oil production and conversion) in the presence of tetralin, dramatically eliminated the consumption of gas phase H₂-- below the detectable level (Song et al., 1988b).

Extensive reviews of hydrogen transfer by Stock (1985) and H-donor solvents by Bockrath (1983) have been published. The concept of hydrogen transfer by hydrogen shuttling by polyaromatic compounds is also well known (Raaen and Roark, 1978; Derbyshire and Whitehurst, 1981). McMillen and Malhotra and their co-workers (McMillen et al., 1985a, 1987, 1991; Malhotra and McMillen, 1990) proposed a mechanism of radical hydrogen transfer (RHT) which can account for solvent-mediated hydrogenolysis. While the H-donor solvent plays an important role, it should be noted that in conventional high severity liquefaction processes, extensive retrograde reactions may already begin in the heat-up period, where the H-donating ability of the system is relatively low, as suggested by comparative examination of short-contact-time pyrolytic liquefaction (SCT-PL) results (Song et al., 1989) and temperature-programmed liquefaction (TPL) results for low-rank coals (Song and Schobert, 1992).

These results suggest that some catalyst and solvent can act in concert to enhance oil production with reduced, unnecessary H₂ consumption. It has yet to be established what is the synergistic mechanism behind such a desirable effect. Garg et al. (1985) also observed a synergistic effect between dispersed Mo catalyst and high-boiling solvents in improving liquefaction of a bituminous coal at 440°C. N-containing solvents may also be beneficial to catalytic pretreatments, although they are widely considered to be poisons and deactivators for supported Ni-Mo catalysts in hydrotreating. Recent work in this laboratory has revealed that the addition of a small amount of THQ to coal/naphthalene system using sulfided ammonium molybdate or incorporating THQ into precursor salt improved conversion and oil yield in temperature-staged liquefaction of a subbituminous coal, although adding THQ had little apparent effect for the low temperature (350°C) stage (Burgess and Schobert, 1990).

Based on the foregoing, the influence of solvents in liquefaction using the selected, novel bimetallic dispersed catalysts will be examined in this work using several typical pure hydrocarbons and process solvents. Table 4 gives a list of the candidate solvents. The final selection will be made in consultation with the DOE Project Manager.

Table 4. Solvents To Be Tested in This Project

Solvent	Compound Class	Chemical Functions
1-Methylnaphthalene	Aromatics	Non-donor
Tetrahydronaphthalene	Hydroaromatics	Hydrogen-donor
Decahydronaphthalene	Cycloalkanes	Weak H-donor
Wilsonville Middle Distillates	Aromatic Mixture	Process Recycle
Hondo Resid	Aliphatic Mixture	Co-Processing

Characterization of Feedstocks. The objectives of Activity 3 are to characterize the structure and thermal reactivity of coals and process solvents. Coal samples will be characterized by using a combination of modern spectroscopic and thermochemical analytical techniques including cross-polarization (CP), and dipolar-dephasing (DD) magic angle spinning (CPMAS and DDMAS) solid state ^{13}C NMR, flash pyrolysis-gas chromatograph-mass spectrometer (Py-GC-MS), FT-IR, and TGA-DTA. CPMAS and DDMAS NMR will be used to determine distributions of aliphatic and aromatic carbons and their degree of protonation. Py-GC-MS will be conducted to characterize the molecular components or structural units of coals. FT-IR will be used to determine chemical functionality in addition to CPMAS ^{13}C NMR. Swelling tests will be performed to characterize the coals in terms of crosslink density. The process solvents will be characterized by GC-MS, GC, and ^1H and ^{13}C NMR. Their compositional features and their major components, especially the components that can serve as H-donors or H-shuttlers will be identified.

Task 2. Preparation and Characterization of Catalysts

The main objective of this Task is to synthesize the organometallic compounds that contain two different transition metals and sulfur in a single cluster. The candidates are Fe-Mo, Co-Mo, and Ni-Mo bimetallic complexes. In general, the synthesis will be carried out using the published procedures, and the preferable procedures will be selected based on the metal species of interest, simplicity, and ease to scale up in the future. Two to three different complexes for each of the Fe-Mo, Co-Mo, and Ni-Mo combinations will be prepared. The information feedback from liquefaction (Task 4) and model reactions (Task 3) will be used to guide further work on the preparation of novel catalysts.

There are several types of complexes containing the same metal species (for example, Co-Mo). The first method to be used is the procedure for synthesis of thiocubane cluster, which was originally developed by Brunner and Watcher (1982). The reaction for preparing Mo-Co

thiocubane, $(C_5H_5)_2Mo_2Co_2S_4(CO)_2$ (**II**), is shown in equation 1. Compound **II** can be prepared 17
by adding **IB** to the brown solution of **IA** in toluene.

Another general method is the procedure developed by Muller et al. (1971). Bimetallic transition metal thioanions with d^0 -configuration of the central atom form complexes with ions of first transition series. As shown in equation 2, MoS_4^{2-} ion (**IIIA**) forms complexes with transition metals (**IIIB**), which can be isolated in the form of the tetraphenylphosphonium salts (**IV**). The synthesis shown in equation 2 is simple and can be applied for preparing Fe-Mo, Co-Mo, Ni-Mo, and Zn-Mo bimetallic complexes.

There are several other methods for synthesizing bimetallic complexes (Brunner et al., 1983; Halbert et al., 1985; Dias et al., 1985). Appropriate methods will be finally selected based on the initial screening tests to be performed in Tasks 3 and 4.

Task 3. Activity and Selectivity Tests by Model Reactions

The primary rationale for this task is to study the activity and selectivity of the bimetallic catalysts prepared in Task 2 in well-defined reaction systems. The catalyst screening is also a part of this task. We will select a series of model compounds which are relevant to coal liquefaction. This will cover at least one or two of the polyaromatics, hydroaromatics, cycloalkanes, nitrogen-, oxygen-, and sulfur-containing compounds. Possible candidates include phenanthrene, pyrene, methylnaphthalene, tetralin, decalin, dinaphthyl ether, naphthol, quinoline, dibenzofuran, and dibenzothiophene. The selection of binary and ternary mixtures of model compounds is also planned for this task. For the catalysts that exhibited excellent activity for single model compounds and liquefaction reactions, our attention in model reactions will then be focused on the tests using binary

and/or ternary mixtures of model compounds to examine the catalyst activity and selectivity for hydrogenation and hydrocracking of polyaromatics in the presence of nitrogen, oxygen, and sulfur compounds. The final selection of the model compounds will be made in consultation with DOE project managers.

1 8

Because of the complexity of coal structures and catalytic coal liquefaction reaction systems, hydrogenation and cracking reactions of polycyclic aromatic hydrocarbons have been taken as model test reactions for clarifying the effects of various catalysts. The model reactions are also very important for understanding the hydrodesulfurization (HDS), hydrodenitrogenation (HDN), and hydrodeoxygenation (HDO) reactions that can be promoted by the new catalysts. There are a number of reports on the tests of dispersed catalysts by model reactions using anthracene and phenanthrene (Song et al., 1988a, 1989b, 1991a, 1991e; Curtis and Pellegrino, 1989), pyrene and dinaphthylether (Schobert et al., 1992a, 1992b), acridine, carbazole, and 1-naphthol (Curtis and Pellegrino, 1989), and dibenzyl, benzylphenyl ether, and dibenzyl ether (Song et al., 1991a). Recently, Farcasiu et al. (1991a, 1991b) and Farcasiu and Smith (1991) have used an interesting model compound, 4-(1-naphthylmethyl)bibenzyl, in their model compound studies of catalysis of various iron compounds as well as carbon catalysts. Farcasiu et al. (1991a) also indicated that it is possible to distinguish among the radical, ion radical, and ionic reactions of this model compound. The above-mentioned studies have demonstrated that the use of model reactions in conjugation with liquefaction of coals provides a better understanding of the catalytic functions - activity and selectivity - of different catalysts for various reactions involved in coal liquefaction.

In the present work, the model reactions will be conducted in 25 ml stainless steel microautoclaves at 350-425°C for 1 hour with an initial H₂ pressure of 6.9-9.8 MPa. To achieve a good mass balance, both the overall conversion of the initial materials and the yields of individual products will be determined by using chromatographic and spectroscopic techniques. The gaseous products will be analyzed by GC using packed column. The liquid products will be identified by using high resolution capillary GC-MS and quantified by capillary GC (Song et al., 1991a, 1991e; Schobert et al., 1992a, 1992b). The used catalysts will be washed by toluene, and dried at 120°C in vacuum oven. For selected runs, the dried catalyst will be analyzed for its carbon and hydrogen content. The activity and selectivity of the prepared catalysts will be evaluated based on the conversion and product distribution. Their effectiveness will be evaluated by comparing with the results of control experiments using the known dispersed catalysts such as ATTM and Molyvan-L. This Task can start when the catalyst precursors have been synthesized, and the information from this Task as well as Task 4 will be used in Task 2 for further progress of catalyst preparation.

The objective of this task is to test the liquefaction catalysis of the bimetallic catalysts to be generated in-situ from organometallic precursors impregnated on coals. It should be noted that the second major technical approach of the proposed work is to perform the conversion of coals impregnated with the organometallic precursors under temperature-programmed liquefaction (TPL) conditions, where the programmed heat-up serves as a step for both catalyst activation and coal pretreatment or preconversion. Two to three different complexes for each of the Fe-Mo, Co-Mo, and Ni-Mo combinations will be prepared in Task 2 and impregnated onto coal. Initial catalyst screening tests will be conducted using a subbituminous coal and a bituminous coal. Control experiments using the conventional precursors such as ATTM and Molyvan will also be carried out. Effects of coal rank and solvents will be examined with the selected bimetallic catalysts which showed much higher activity than the dispersed catalysts from conventional precursors. We have demonstrated the effectiveness of TPL runs (Song et al., 1991b, 1992b; Song and Schobert, 1992b; Huang et al., 1992), and the advantages of temperature-programming have been discussed in the section of literature survey.

The precursors will be loaded onto coal by using impregnation method with the solution of the organometallic precursors in organic solvent system. The liquefaction will be conducted in a mode of temperature-controlled heating and holding in a microautoclave using fluidized sand bath. The coal-catalyst-solvent-H₂ will be heated up rapidly to a low temperature (200-300°C) and held there for 15 minutes, followed by controlled heating at a given heating rate to a high (final) temperature (350-450°C) and held at final temperature for a short period (5-30 min). The reaction conditions (initial temperature of the fluidized sand bath, the heating rate, final temperature and holding time) are also important parameters and will be selected based on coal reactivity and pyrolysis data collected from Task 1. The products from TPL will be separated carefully by Soxhlet extraction into gas, oils (hexane solubles), asphaltene (hexane-insoluble toluene-solubles), preasphaltene (toluene-insoluble THF-solubles) and residue (Song and Schobert, 1992b). To achieve a good mass balance, both the overall coal conversion and the yields of products will be determined.

The low temperature (200-300°C) soak and the programmed heat-up can be considered as a pretreatment stage. This stage allows the complete thermal decomposition of the organometallic precursors, and the penetration of solvent molecules into the interior of the pores inside coal particles, and catalytic pretreatment (low temperature catalytic reactions). Control of heating rate from initial to final temperature could control the rate of pyrolytic cleavage of weak bonds in coals, especially low-rank coals, which are highly sensitive to temperature, and high conversions could be achieved by temperature-controlled reactions of coals in catalyst/H₂/solvent systems. Control of the

initial coal dissolution is best implemented by reaction at sub-pyrolysis temperatures (below 400°C). 20

Overall, the control of temperature and heating rates aims at matching the rate or ability of hydrogen donation (by the catalyst/solvent/gas system to the reactive radical fragments) with the rate of thermal fragmentation, which would lead to high coal conversion by suppressing the retrogressive reactions to form insoluble materials. For comparison, some experiments will be conducted under conventional (not programmed) conditions. In addition, the role of molecular H₂ in TPL runs will be evaluated by conducting the selected runs under inert N₂ atmosphere.

Task 5. Effects of Catalysts on Product Quality

The objective of this Task is to evaluate the effects of the catalysts on the quality and composition of liquefaction products. The products from Task 4 will be kept in glass vials in dark place under nitrogen atmosphere. A set of liquefaction products from a number of representative experiments in Task 4 shall be analyzed. Emphasis on product quality shall be placed on oil products. The analysis of asphaltene, preasphaltene and residue shall be directed to the structural correlation with the original coals. All the products from selected experiments will be subjected to elemental analysis. The oil products shall be analyzed by capillary GC-MS and capillary GC for product identification, liquid chromatography for product distribution in terms of functionality (LC or HPLC) and molecular weight (GPC), and liquid ¹H and ¹³C NMR. Most coals and the catalyst precursors contain sulfur. Some catalysts such as Molyvan, which has been tested at Wilsonville plant and will be used in control experiments in this work, also contain phosphorus. Selected oil products will also be subjected to sulfur-selective and phosphorus-selective GC analysis using both FPD and FID detectors (see below). The asphaltene, preasphaltene, and the residue from a number of typical experiments will be characterized by solid state CPMAS & DDMAS ¹³C NMR, and Py-GC-MS.

In developing coal liquefaction processes, attention has always been focused on maximizing the conversion to soluble products and the yields of distillates. However, it is also important to characterize the composition of the distillate as well as the heavy products, and their dependence on the chemical constitution of the starting coals and solvents and the characteristics of the catalysts and process conditions. The information from this Task will be used to evaluate the effects of catalysts on product quality, and to correlate the coal conversion in catalytic runs to their structural and compositional characteristics.

Most of the characterization methods involved in Tasks 1, 3 and 5 are state-of-the-art

analytical techniques including CPMAS and DDMA¹³C NMR, FT-IR, Py-GC-MS, and TGA-DTA. Many papers have described the use of CPMAS ¹³C NMR (Maciel et al., 1979; Earl et al., 1980; Wilson et al., 1984; Hatcher et al., 1989a; Song et al., 1992); DDMA¹³C NMR (Alemany et al., 1983; Hatcher et al., 1987, 1988a); FT-IR (Painter et al., 1983; Senftler et al., 1984; Fraser and Griffiths, 1990); Py-GC-MS (Saiz and Leeuw, 1984; Hatcher et al., 1988b, 1989b; Song et al., 1992b) which is a combination of pyrolysis-GC and MS (Gallegos, 1979; Meuzelaar et al., 1983); GC-MS (Mudamburi and Given, 1985; Song and Hatcher, 1992); TGA-DTA (Song et al., 1986a, 1987a, 1989); and solvent-swelling (Liotta et al., 1983; Green et al., 1982, 1984; Artok, et al., 1991). In addition, capillary GC with flame photometric detector (FPD) can be used for selective detection of sulfur and phosphorus compounds. The switching between the sulfur mode and phosphorus mode is made by switching a filter. It should be noted that the methods for applications of most of the above-mentioned techniques have been established in this laboratory, as described in a recent report to DOE (Song et al., 1992b).

LITERATURE CITED

- Alemany, L.B., Grant, D.M., Alger, T.D. and Pugmire, R.J., *J. Am. Chem. Soc.*, 1983, 105, 6697.
- Anderson, R.R.; Bockrath, B.C., "Effect of Sulfur on Coal liquefaction in the Presence of Dispersed Iron or Molybdenum Catalysts", *Fuel*, 1984, 63, 329-333.
- Artok, L.; Davis, A.; Mitchell, G.D.; Schobert, H.H., "Catalyst Dispersion and Activity under Conditions of Temperature-Staged Liquefaction", *Proceedings of DOE Liquefaction Contractors' Review meeting*, Sept.3-5, 1991, Pittsburgh, pp.422-444.
- Artok, L.; Schobert, H.H.; Davis, A., "Temperature-Staged Liquefaction of Coals Impregnated with Ferrous Sulfate", *Fuel Processing Technol.*, 1992, 32, 87-100.
- Artok, L.; Davis, A.; Mitchell, G.D.; Schobert, H.H., "Swelling Pretreatment of Coals for Improved Catalytic Liquefaction", *Fuel*, 1992, 71, 981-991.
- Artok, L.; Davis, A.; Mitchell, G.D.; Schobert, H.H., "Swelling Pretreatment of Coals for Improved Temperature-Staged Catalytic Liquefaction", *Energy & Fuels*, 1993, 7, 67-77.
- Levent, A.; Erbatur, Schobert, H.H., "Comparative Reduction and Cleavage Reactions of Dinaphthyl Ether at Liquefaction Conditions", 1993, in preparation.
- Baldwin, R.M., Nganpraesert, O, Kennar, D.R. and Miller, R.L., *ACS Fuel Chem. Prepr.*, 1990, 35, 70.
- Baldwin, R.M.; Kennar, D.R.; Nganpraesert, O; Miller, R.L., *Proceedings of DOE Liquefaction Contractors' Review meeting*, Sept.3-5, 1991, Pittsburgh, pp.616-624.
- Beinkowski, P.R., Narayan, R., Greenkorn, R.A. and Chao, K-C., *Ind. Eng. Chem. Res.*, 1987, 26, 202.

- Bi, X.-X.; Derbyshire, F.J.; Eklund, P.C.; Hager, G.T.; Stencel, J.M., "Coal dissolution promoted by ultrafine iron-based catalysts", Proceedings of 1991 International Conference on Coal Science, Newcastle upon Tyne, UK, pp.683-686. 2 2
- Bockrath, B.C., in "Coal Science", Vol. 2, Academic Press, New York, 1982, 65.
- Bockrath, B.C., Finseth, D.H. and Illig, E.G., Fuel Proc. Technol., 1986, 12, 175.
- Bockrath, B.C.; Illig, E.G.; Hough, M., "Physical Organic Chemistry of Coal Liquefaction", ACS Fuel Chem. Prepr., 1990, 35 (1), 232-240.
- Bockrath, B.C., Illig, E.G., Keller, M.J., III, Solar, J.G., Bittner, E.W., and Finseth, D.H., "Low Temperature Liquefaction Catalysis", Proceedings of DOE Liquefaction Contractors Review Meeting, September 3-5, 1991, Pittsburgh, pp.387-397.
- Bond, G.C., "Heterogeneous Catalysis", Oxford Science Publications, Clarendon Press: Oxford, 1987, Chapter 8, pp. 85-103..
- Brunner, H.; Watcher, J., J. Orgnomet. Chem., 1982, 240, C41-C44.
- Brunner, H.; Kauermann, H.; Watcher, J., Angew. Chem. Int. Ed. Engl., 1983, 22, 549-550.
- Burgess, C. and Schobert H.H., ACS Fuel Chem. Prepr., 1990, 35, 31.
- Burgess, C. and Schobert H.H., Fuel, 1991, 70, 32.
- Burgess, C.; Artok, L.; Schobert H.H., ACS Fuel Chem. Prepr., 1991, 36 (2), 462-469.
- Chamberlin, P.L. and Schobert, H.H., Fuel Proc. Technol. 1991, 28, 67-76.
- Chianelli, R.R.; Daage, M., "Structure-Function Relations in Transition Metal Sulfide Catalysts", in "Advances in Hydrotreating Catalysts", M.L. Occelli and R.G. Anthony Eds., Elsevier: Amsterdam, 1989, pp.1-19.
- Chianelli, R.R.; Daage, M., Halbert, T.R.; Ho, T.C.; Stiefel, E.I., Am. Chem. Soc. Div. Petrol. prepr., 1990, 35 (2), 227-231.
- Comolli, A.G., Ganguli, P., Harris E., MacArthur, J.B., McLean, J.B. and Smith, T.P., "New Technology Concept for Two-Stage Liquefaction", DOE-PC-60017-Ta, New Jersey, Hydrocarbon Research Inc., 1985, 413 pp.
- Cugini, A.V.; Utz, B.R.; Hickey, R.F.; Lett, R.G.; Krastman, D.; Balsone, V.D., "Effects of Activation Conditions on Dispersed Iron Catalysts in Coal Liquefaction", Am. Chem. Soc. Div. Fuel Chem. Prepr., 1991a, 36 (1), 91-102.
- Cugini, A.V.; Krastman, D.; Hickey, R.F.; Lett, R.G., "Recent Progress in the Use of Disposable Catalysts for Coal Liquefaction", Proceedings of DOE Liquefaction Contractors' Review Meeting, Sept. 3-5, 1991b, Pittsburgh, p.590-597.
- Curtis, C.W., Tsai, K-J. and Guin, J.A., Ind. Eng. Chem. Res., 1987, 26, 12.
- Curtis, C. W.; Pellegrino, J. L.; Energy & Fuels, 1989, 3, 160-168.
- Davidson, R.M., "Molecular Structure of Coal", ICTIS-TR-08, London, UK., IEA Coal Research, 1980, 86p.
- Davis, A., Derbyshire, F.J., Finseth, D.H., Lin, R., Stansberry, P.G. and Terrer, M-T., Fuel,

- Davis, A., Derbyshire, F.J., Mitchell, G.D. and Schobert, H.H., "Enhanced Coal Liquefaction by Low-Severity Catalytic Reactions", U.S. Department of Energy, Final Report DOE-PC-90910-F1, July, 1989, 175 p.
- Davis, A., Schobert, H.H., Mitchell, G.D. and Artok, L., "Catalyst Dispersion and Activity under Conditions of Temperature-Staged Liquefaction", Progress Report DOE-AC-22-89PC89877, January, 1990.
- Davis, A.; Glick, D.C.; Mitchell, G.D., Proceedings of DOE Liquefaction Contractors' Review Meeting, Sept. 3-5, 1991, Pittsburgh, p.398-410.
- Derbyshire, F.J. and Whitehurst, D.D., Fuel, 1981, 60, 655.
- Derbyshire, F.J., Davis, A., Epstein, M. and Stansberry, P., Fuel, 1986a, 65, 1233.
- Derbyshire, F.J., Davis, A., Lin, R., Stansberry, P. and Terrer M-T., Fuel Proc. Technol., 1986b, 12, 127.
- Derbyshire, F.J. and Stansberry, P., Fuel, 1987, 66a, 1741.
- Derbyshire, F.J., Catalysis in Coal Liquefaction: New Directions for Research, IEA Report, IEACR/08, June, 1988, 69p.
- Derbyshire, F.J., Energy & Fuels, 1989, 3, 273.
- Derbyshire, F.J., Davis, A. and Lin, R., Energy & Fuels, 1989, 3, 431.
- Derbyshire, F.J.; Davis, A.; Schobert, H.; Stansberry, P.G. Am. Chem. Soc. Div. Fuel Chem. Prepr. 1990, 35, 51.
- Deshpande, G.V., Solomon, P.R. and Serio, M.A., ACS Fuel Chem. Prepr., 1988, 33, 310.
- Deurbrouck, A.W. and Hucho, R.E., "Coal Preparation in "Chemistry of Coal Utilization, Supp. Vol. 2", M. Elliot Ed., Wiley and Sons, New York, 1982, 571-607.
- Dias, A.R.; Green, M.L.H., J. Chem. Soc. (A), 1971, 2807-2809.
- DOE COLIRN Panel, "COAL LIQUEFACTIONS - A Research and Development Needs Assessments", DOE DE-AC01,87ER30110, Final Report, Vol. 1 and Vol. 2, 1989.
- Dutta, R.; Schobert, H.H.; "Hydrogenation of Quadricyclic Aromatic Hydrocarbons in the Presence of Ammonium Tetrathiomolybdate", 1993, in preparation.
- Earl, W.L. and VanderHart, D.L., J. Am. Chem. Soc., 1980, 102, 3251.
- Ettinger, M., Nardin, R., Mahasay, S.R. and Stock, L.M. J. Org. Chem., 1986, 51, 2840.
- Farcasiu, M., PETC Review, 1991, Issue 3, pp. 4-14.
- Farcasiu, M.; Smith, C.; Pradhan, V.R.; Wender, I., "Iron Compounds and Iron Catalyst: Activities in Reactions Relevant to Direct Coal Liquefaction", Fuel Processing Technol., 1991a, 29, 199-208.
- Farcasiu, M.; Smith, C.; Ladner, E.P.; "Carbon Materials - Activity and Selectivity in Hydrocracking Reactions", Am. Chem. Soc. Div. Fuel Chem. Prepr., 1991b, 36 (4), pp. 1869-1877.

- Farcasiu, M.; Smith, C.; *Energy & Fuels*, 1991, 5, 83.
- Fraser, D.J. and Griffiths, P.R., *Appl. Spectrosc.*, 1990, 193, 44.
- Gallegos, E.J., in "Chromatography in Petroleum Analysis", K.H. Altgelt and T.H. Gouw Eds., Marcel Dekker, New York, 1979, pp. 162-184.
- Garcia, A.B. and Schobert, H.H., *ACS Fuel Chem. Prepr.*, 1988.
- Garcia, A.B. and Schobert, H.H., *Coal Preparation*, 1989, 7, 47.
- Garcia, A.B. and Schobert, H.H., *Fuel*, 1989, 68, 1613.
- Garcia, A.B. and Schobert, H.H., *Fuel Processing Technol.*, 1990, 24, 179.
- Garcia, A.B. and Schobert, H.H., "Liquefaction Behavior of High-Sulfur Lignites", in "Coal Science II", H.H. Schobert, K.D. Bartle, and L. Lynch Eds., ACS Sym Ser. 461, 1991, 213-224.
- Garcia, A.B. and Schobert, H.H., "Hydrodesulfurization of a High Organic Sulfur Spanish Lignite with Impregnated Nickel Sulfate", *Coal preparation*, 1991, 9, 185-197.
- Garg, D., Miller, R.M., Hoover, D.S., Givens, E.N., Schweighardt, F.K., Tarrer, A.R., Guin, J.A., Curtis, C.W. and Luckie, P., "Evaluation of the Effect of Solvent Modification and Coal Pretreatment and Beneficiation on Liquefaction", DOE/TIC-50003-28, Air Products and Chemicals, Inc., PA.
- Given, P.H., Marzec, A., Barton, W.A., Lynch, L.J. and Gerstein, B.C., *Fuel*, 1986, 65, 155.
- Gould, K.A., Gorbaty, M.L. and Miller, J.D., *Fuel*, 1978, 57, 510.
- Green, T.K. Kovac, J. and Larsen, J.W., in "Coal Structure", R.A. Meyers Ed., Academic Press, New York, 1982, p. 199.
- Green, T.K., Kovac, J. and Larsen, J.W., *Fuel*, 1984, 63, 935.
- Halbert, T.R.; Cohen, S.A.; Stiefel, E.I., *Organometallics*, 1985, 4, 1689-1690.
- Hatcher, P.G., *Org. Geochem.*, 1987, 11, 31.
- Hatcher, P.G., *Energy & Fuels*, 1988a, 2, 48.
- Hatcher, P.G., Lerch, H.E., Kotra, R.K. and Verheyen, T.V., *Fuel*, 1988b, 67, 1069.
- Hatcher, P.G., Lerch, H.E., Bates, A.L. and Verheyen, T.V., *Org. Geochem.*, 1989a, 14, 145.
- Hatcher, P.G., Lerch, H.E. and Verheyen, T.V., *Int. J. Coal Geol.*, 1989b, 13, 65.
- Hawk, C.O. and Hiteshue, R.A., Bulletin 622, Bureau of Mines, US Department of Interior, 1965, 42 pp.
- Hengel, T.D. and Walker, P.L., *Fuel*, 1984, 63, 1214.
- Huang, L.; Song, C.; Schobert, H.H., "Temperature-Programmed Catalytic Liquefaction of Low-Rank Coal Using Dispersed Mo Catalyst", *Am. Chem. Soc. Div. Fuel Chem. Pre r.* 1992, 37, in press.
- Janikowski, S.K. and Stenberg, V.I., *Fuel*, 1989, 68, 95.
- Joseph, J.T., *Fuel*, 1991, 70, 139.
- Klavetter, E.; Sylwester, A.; Wilcoxon, J.; Nigrey, P.; Snape, C.; Lafferty, C.; Mitchell, S.,

- "Novel Dispersed Catalysts for Fixed-Bed Hydropyrolysis", Proceedings of 1991 International Conference on Coal Science, Newcastle upon Tyne, UK, pp.699-702.
- Larsen, J.W., Sams, T.L. and Rogers, B.R., *Fuel*, 1980, 59, 666.
- Larsen, J.W., Green, T.K. and Kovac, J., *J. Org. Chem.*, 1985, 50, 4729.
- Lepkowski, W., *Chem. Eng. News*, June 17, 1991, pp.20-31.
- Liotta, R., Rose, K. and Hippo, E.J., *J. Org. Chem.*, 1981, 46, 277.
- Liotta, R., Brons, G. and Issacs, J., *Fuel*, 1983, 63, 781.
- Lumpkin, R.E., *Science*, 1988, 239, 873.
- Lynch, L.J.; Sakurovs *Proc. 1991 Int. Conf. Coal Sci.*, Newcastle upon Tyne, 1991, 592.
- Maciel, G.E., Bartuska, V.J. and Mikinis, F.P., *Fuel*, 1979, 58, 391.
- Mahajan, O.P.; "Porosity of Coals and Coal Products", in *Analytical Methods for Coal and Coal Products*, Vol.1, C. Karr, Ed., Academic Press, New York, 1978, p.125-162.
- Malhotra, R. and McMillen, D.F., "A Mechanistic Numerical Model for Coal Liquefaction Involving Hydrogenolysis of Strong Bonds. Rationalization of Interactive Effects of Solvent Aromaticity and Hydrogen Pressure", *Energy & Fuels*, 1990, 4, 184-193.
- Masunaga, T and Kageyama Y. *Proc. 1989 Int. Conf. Coal Sci.*, Tokyo, 1989, 819.
- McLean, J.B., Comolli, A.G. and Smith, T.O., *ACS Fuel Chem. Prepr.*, 1986, 31, 268.
- McMillen, D.F., Malhotra, R., Hum, G.P., Chang, S-J. and Nigenda, S.E., *Proc. Inter. Conf. Coal Sci.*, Sydney, Australia, 1985a, p. 91.
- McMillen, D.F., Chang, S-J., Nigenda, S.E. and Malhotra, R., *ACS Fuel Chem. Prepr.*, 1985b, 30, 414.
- McMillen, D.F.; Chang, S.; Nigenda, S.E.; Malhotra, R. *Proc. 1985 Int. Conf. Coal Sci.*, Sydney, 1985, 153.
- McMillen, D.F., Malhotra, R., Hum, G.P. and Chang, S-J., *Energy & Fuels*, 1987, 1, 193.
- McMillen, D.F., Malhotra, R., Tse, D.S., "Interactive Effects between Solvent Components: Possible Chemical Origin of Synergy in Liquefaction and Coprocessing", *Energy & Fuels*, 1991, 5, 179-187.
- Meuzelaar, H.L.C., Haverkamp, J. and Hileman, F.D., "Pyrolysis Mass Spectrometry of Recent and Fossil Biomaterials", Elsevier, Amsterdam, 1982, 286 pp.
- Miller, R.L., Armstrong, M.E. and Baldwin, R.M., *ACS Fuel Chem. Prepr.*, 1989, 34, 873.
- Mingos, D.M.P.; Wales, D.J., "Introduction to Cluster Chemistry", Prentice Hall: Englewood Cliffs, New Jersey, 1990, 318 pp.
- Mobley, D.P.; Bell, A.T., *J. Catal.*, 1980, 64, 494-496.
- Moroni, E.C., *ACS Fuel Chem. Prepr.*, 1986, 31, 340.
- Moroni, E.C., *ACS Fuel Chem. Prepr.*, 1991, 36 (2), 433-437.
- Mudamburi, Z. and Given, P.H., *Org. Geochem.*, 1985, 8, 441.
- Muller, V.A.; Ahlborn, E.; Heinsen, H.-H., *Z. anorg. Allg. Chem.*, 1971, 386, 102-106.

- Naumann, A.W., Behan, A.S. and Thorsteinson, E.M., Proc. 4th Int. Conf. Chem. & Uses of Molybdenum (H.E. Barry and C.N. Mitchell Eds.), 1982, p. 313.
- Neavel, R.C., in "Coal Sciencae", Vol. 1, Academic Press, New York, 1982, pp. 1-19.
- Narain, N.K., Appell, H.R. and Utz, B.R., ACS Fuel Chem. Prepr., 1983, 28, 161.
- Neuworth, M.B. and Moroni, E.C., Fuel Proc. Technol., 1984, 8, 231.
- O'Brian, R.J., Gibbins, J.R. and Kandiyoti, R., Fuel Proc. Technol., 1987, 15, 71.
- Painter, P.C., in "Coal and Coal Products: Analytical Characterization", E.L. Fuller Ed., Am. Chem. Soc. Sym. Ser., 1982, 205, 47.
- Painter, P.C., Starsinic, M., Squires, E. and Davis, A., Fuel, 1983, 62, 742.
- Piasecki, C.A.; Gatsis, J.G.; Fullerton, H.E., "UOP Slurry-Catalyzed Co-Processing", Proceedings of DOE Liquefaction Contractors' Review Meeting, Sept. 3-5, 1991, Pittsburgh, p.598-616.
- Raaen, V.F. and Roark, W.H, Fuel, 1978, 57, 650.
- Rincon, K.M. and Cruz, S., Fuel, 1988, 67, 1162.
- Ross, D.S. and Hirschon, A., ACS Fuel Chem. Prepr, 1990, 35, 37.
- Saiz-Jimenez, C. and De Leeuw, J.W., Org. Geochem., 1984, 6, 417.
- Serio, M.A., Solomon, P.R., Kroo, E., Bassilakis, R., Malhotra, R. and McMillen, D., ACS Fuel Chem. Prepr., 1990, 35, 61.
- Schlosberg, R.H.; Neavel, R.C.; Maa, P.S.; Gorbaty, M.L., Fuel, 1980, 59, 45.
- Schobert, H.H., Tomic, J., Moyer, D. and McConnie, J., "Inhibition of Retrograde Reactions in Coal/Petroleum Co-Processing", Technical Progress Report, DOE DE-FG22-88PC888935, June, 1990.
- Schobert, H.H., Resources, Conservation and Recycling 1990, 3, 111.
- Schobert, H.H.; Song, C., "Moving Coal into the 21st Century", Earth & Mineral Sciences, The Pennsylvania State University, 1992, 61 (3), 51-55.
- Shabtai, J., Oblad, H.B., Katayama, Y. and Saito, Y., ACS Fuel Chem. Prepr., 1985a, 30, 495.
- Shabtai, J.,Skulthai, T. and Saito, Y., ACS Fuel Chem. Prepr., 1986, 31, 15.
- Snape, C.E., Derbyshire, F.J., Stephens, H.P., Kottenstette, R.J. and Smith, N.W., Fuel Proc. Technol., 1990, 24, 119.
- Solomon, P.R., Hamblen, D.G., Carangelo, R.M., Serio, M.A. and Deshpande, G.V., Energy & Fuels, 1988, 2, 405.
- Solomon, P.R.; Serio, M.A.; Deshpande, G.V.; Kroo, E. Energy & Fuels 1990, 4, 42.
- Sondreal, E.A., "A Review of U.S. Low-Rank Coal: Policy, Resource and technology", Paper presented at the Information Transfer Session, Cooperative Program in Coal Research, The Pennsylvania State University, Nov. 18-19, 1991.
- Song, C. and Nomura, M., Fuel, 1986a, 65, 922.
- Song, C. and Nomura, M., Bull. Chem. Soc. Japan, 1986b, 59, 3643.

- Song, C. and Nomura, M., *Fuel*, 1987a, 66, 1225.
- Song, C., Nomura, M. and Hanaoka, K., *Coal Sci. Technol.*, 1987b, 11, 239.
- Song, C., Ono, T. and Nomura, M., *Bull. Chem. Soc. Japan*, 1988a.
- Song, C., Hanaoka, K. and Nomura, M., *Energy & Fuels*, 1988b, 2, 639.
- Song, C., Hanaoka, K. and Nomura, M., *Fuel*, 1989, 68, 287.
- Song, C.; Ono, T.; Nomura, M., *Bull. Chem. Soc. Japan*, 1989b, 62, 630-632.
- Song, C.; Nomura, M.; Ono, T., "Catalysis of Multi-Component Lewis Acids for Coal Hydroliquefaction and Model Reactions", *Am. Chem. Soc. Div. Fuel Chem. Prepr.*, 1991a, 36 (2), 586-596.
- Song, C.; Schobert, H., H.H.; Hatcher, P.G., *Proc. 1991 Int. Conf. Coal Sci.*, University of Newcastle upon Tyne, UK, 1991b, pp. 664-667.
- Song, C., T. Nihonmatsu, and M. Nomura, Effect of Pore Structure of Ni-Mo/Al₂O₃ Catalysts in Hydrocracking of Coal-Derived and Oil Sand Derived Asphaltenes. *Industrial & Engineering Chemistry Research*, 1991c, Vol. 30, No.8, pp.1726-1734.
- Song, C., T. Nihonmatsu, K. Hanaoka and M. Nomura, Effect of Pore Structure of Unimodal Catalysts on Hydrocracking of Asphaltene and Preasphaltene and Heteroatom Removal, *Am. Chem. Soc. Div. Fuel Chem. Prepr.*, 1991d, 36 (2), pp.542-550.
- Song, C.; Schobert, H.H.; Matsui, H., "Catalysis of Metal-Ion Exchanged Y-Zeolites and Modified Ni-Mo/Al₂O₃ for Hydrocracking of Phenanthrene and Coal-derived Distillates", *Am. Chem. Soc. Div. Fuel Chem. Prepr.*, 1991e, 36 (3), 1892-1899.
- Song, C.; Schobert, H.H., "Specialty Chemicals and Advanced Materials from Coals: Research Needs and Opportunities", *Am. Chem. Soc. Div. Fuel Chem. Prepr.*, 1992a, 37 (2), 524-532.
- Song, C.; Schobert, H.H., "Temperature-Programmed Liquefaction of Low-Rank Coals in H-donor and Non-donor Solvents", *Am. Chem. Soc. Div. Fuel Chem. Prepr.*, 1992b, 37 (2), 976-983.
- Song, C.; Schobert, H.H., "Opportunities for Developing Specialty Chemicals and Advanced Materials from Coals", *Fuel Process. Technol.*, 1993a, in press.
- Song, C.; Hatcher, P.G.; "Compositional Differences between Coal-derived and Petroleum-derived jet Fuels", *Am. Chem. Soc. Div. Petrol. Chem. Prepr.*, 1992, 37 (2), 529-539.
- Song, C.; Schobert, H., H.H.; Hatcher, P.G., "Temperature-Programmed Liquefaction of a Low Rank Coal", *Energy & Fuels*, 1992a, 6, 326-328.
- Song, C., A. Saini, L. Huang, K. Wenzel, P.G. Hatcher, H.H. Schobert, "Effects of Low-Temperature Catalytic Pretreatments on Coal Structure and Reactivity in Liquefaction", *Technical Progress Report for the Period October 1991 - December 1991*, U.S. DOE / PETC, 91PC91042-TPR-1, January, 1992b, 90 pp.
- Song, C.; Hanaoka, K.; Nomura, M., "Effects of Pore Structure and Support Type of Catalysts in

- Hydroprocessing of Heavy Coal Liquids", Am. Chem. Soc. Div. Fuel Chem. Prepr., 1992c, 28 37 (1), 215-222.
- Song, C.; Schobert, H.H.; Hatcher, P.G., "Solid State ^{13}C NMR and Pyrolysis-GC-MS Studies of Coal Structure and Liquefaction Reactions", Am. Chem. Soc. Div. Fuel Chem. Prepr., 1992d, 37 (2), 638-645.
- Spears, D.R.; Sady, W.; Kispert, L.D., Am. Chem. Soc. Div. Fuel Chem. Prepr. 1991, 36 (2), 1277.
- Stansberry, P.G., Lin, R., Terrer, M-T., Lee, C.W., Davis, A. and Derbyshire, F., Energy & Fuels, 1987, 1, 89.
- Stenberg, V.I., Gutenkunst, V. and Sweeny, P.G., Fuel, 1989, 68, 95.
- Stenberg, V.I., Gutenkurt, V., Nowok, J. and Sweeny P.G. Fuel 1989, 68, 133.
- Stock, L.M., in "Chemistry of Coal Conversion", H. Schlosberg Ed., Plenum, New York, 1985, pp. 253-316.
- Suuberg, E.M., Lee, D. and Larsen, J.W., Fuel, 1985, 64, 1668.
- Suuberg, E.M.; Unger, P.E.; Larsen, J.W. Energy & Fuels 1987, 1, 305.
- Suzuki, T., Yamada, O., Then, J.H., Ando, T. and Watanabe, Y, Proc. 1985 Inter. Conf. Coal Sci., Sydney, Australia, 1985, p. 205.
- Takemura, Y.; Okada, K., Fuel, 1988, 67, 1548-1553.
- Utz, B.R., Cugini, A.V. and Frommell, E.A., "Dispersed-Phase Catalysis in Coal Liquefaction", in "Novel Materials in Heterogeneous Catalysis", ACS Sym. Ser. No. 437, 1989, 289-299.
- Watanabe, Y., Yamada, O., Fujita, K., Takegami, Y. and Suzuki, T., Fuel, 1984, 63, 752.
- Weber, W. and Steward, N., EPRI Journal, 1987, 12, 40.
- Weller, S., Pelipetz, M.G., Friedman, S. and Storch, H.H., Ind. Eng. Chem. Chem, 1950, 42, 330.
- Weller, S. and Pelipetz, M.G, "Coal Hydrogenation Catalysts Studies of Catalyst Distribution", Ind. Eng. Chem. Chem., 1951, 43, 1243-1246.
- Whitehurst, D.D., "Coal Liquefaction Fundamentals", Am. Chem. Soc. Sym. Ser. 1980, 139, 132.
- Whitehurst, D.D., Mitchell, T.O. and Farcasiu, M., "Coal Liquefaction", Academic Press, New York, 1980.
- Wilson, M.A., Aleman;y, L.B., Woolfenden, W.R., Pugmire, R.J., Given, P.H., Grant, J.D.M. and Karas, J., Anal. Chem., 1984, 56, 933.
- Zielke, C.W., Struck, R.T., Evans, J.M., Costanza, C.P. and Gorin, E., Ind. Eng. Chem. Process Des. Dev., 1966a, 5, 151.
- Zielke, C.W., Struck, R.T., Evans, J.M., Costanza, C.P. and Gorin, E., Ind. Eng. Chem. Process Des. Dev., 1966b, 5, 158.

Appendix

Complete Data Sheets for Some Coals of DECS-series in DOE/Penn State Sample Bank

DECS-1	Texas (Bottom) Lignite/Subbituminous	(74.3%C)
DECS-8	Wyodak (Smith-Roland) Subbituminous	(75.3%C)
DECS-9	Montana (Diez) Subbituminous	(76.1%C)
DECS-6	Blind Canyon Bituminous	(81.3%C)
DECS-12	Pittsburgh #8 Bituminous	(84.8%C)
DECS-2	Illinois #6 Bituminous	(81.0%C)
DECS-5	Hiawatha Bituminous	(79.5%C)
DECS-7	Wyoming (Adaville) Subbituminous/Bituminous	(77.1%C)
DECS-11	North Dakota (Beulah) Lignite	(74.2%C)

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> TEXAS
 COUNTY -> FREESTONE
 TOWNSHIP ->
 CITY -> FAIRFIELD
 COAL PROVINCE-> GULF
 REGION ->

MAP REFERENCE: LATITUDE -> 31 D 51 M 10 S
 LONGITUDE -> 96 D 3 M 59 S
 QUADRANGLE-> YOUNG

LIFE EXPECTANCY -> 25 YEARS
 MINING METHOD -> STRIP

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-1
 SEAM NAME -> BOTTOM
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> SUBBIT C

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 12/11/89 ; PSU

SAMPLE TYPE -> CHANNEL-WHOLE SEAM

ADDITIONAL INFORMATION ->

MINE INFORMATION:

RESERVES ->
 ANNUAL PRODUCTION -> 5500 THOUSAND TONS

SEAM INFORMATION:

AGE OF SEAM -> EOCENE
 GROUP -> Upper Wilcox
 FORMATION -> Upper Calvert Bluff
 SEAM THICKNESS -> 9 FT. 6 IN.

SAMPLE IDENTIFICATION:-----
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:-----
COUNTRY
STATE

DECS-1
-> BOTTOM
->
-> SUBBIT C

DECS-1
DECS-1
02/04/93
PAGE 2

** PENN STATE COAL DATA BASE **

***** C H E M I C A L D A T A * * * * *

PROXIMATE ANALYSIS AS REC'D DRY DAF DMMF(PARR)
% MOISTURE 30.00
% ASH 11.07 15.81
% VOLATILE 33.18 47.40 55.52
% FIXED CARBON 25.75 36.79 44.48
% EQUILIBRIUM MOISTURE = 31.47
MM-FREE = 35.89

ULTIMATE ANALYSIS AS REC'D DRY DAF DMMF(PARR) ELEMENTAL ANALYSIS DRY DMMF(MOD.P) DMMF(DIR.)
% ASH 11.07 15.81 (17.62%MM)
% CARBON 43.77 62.53 74.27 62.45 76.13
% HYDROGEN 3.32 (*) 4.75 5.64 4.55 5.54
% NITROGEN 0.86 1.23 1.46 1.23 1.50
% TOTAL SULFUR 0.69 0.99 1.18 0.86 1.05
% OXYGEN(DIFF) 10.28 (*) 14.69 17.45 12.94 15.78
% MINERAL MATTER (INCL. 0.21% FES2) 17.97
(*)-EXCLUDES MOISTURE

SULFUR FORMS % PYRITIC % SULFATIC % ORGANIC % TOTAL
DRY 0.11 0.02 0.86 0.99
DAF 0.13 0.02 1.02 1.18
DRY % CHLORINE = 0.11 DRY % CO2 = 0.29
MOTT-SPOONER DIFFERENCE = -115.

CALORIFIC VALUE (GROSS, BTU/LB) DRY AS REC'D EQUIL. MOIST.
MM-CONTAINING 10956. 7669. 7508.
MM-FREE (PARR) 13239. 8709. 8501.
MM-FREE (MOD. P) 13349. 8768. 8558.
NET CV, DMMF BTU/LB 12812.

ATOM RATIOS (DMMF) PARR MOD. PARR DIRECT
ATOMIC H/C 0.9124 0.8744
ATOMIC O/C 0.1665 0.1556

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK
--> DECS-1
--> BOTTOM
-->
--> SUBBIT C
SAMPLE LOCATION:
COUNTRY
STATE
--> USA
--> TEXAS
** PENN STATE COAL DATA BASE **
** DECS-1
**
** 02/04/93
** PAGE 3

***** RANK CALCULATIONS *****
APPARENT RANK (AS REC'D MOIST.)
--> SUBBIT C
INTERNATIONAL RANK :
AS REC'D MOIST. -->
ASTM RANK (EQUIL. MOIST.)
--> SUBBIT C
EQUIL. MOIST. -->
REFLECTANCE RANK CATEGORY
-->
REPORTED RANK : -->

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT AND FLUORESCENCE ANALYSIS)

Table with 10 columns: TEXT-INITE, ULM-INITE, HUMO-DETRINITE, GEL-INITE, CORPO-HUMINITE, SPOR-INITE, CUT-INITE, RES-INITE, ALG-INITE, FUS-INITE, SEMI-FUSINITE, MAC-RINITE, SCLERO-TINITE. Rows include DMF VOL. %, DRY WT. %, and DMF VOL % HUMINITE = 78.4.

ULMINITE REFLECTANCE DATA:
HIGH: 0.51 LOW: 0.20 MEAN-MAX: 0.35

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:
INIT. SOFTENING TEMP
TEMP. MAX. FLUIDITY
SOLIDIFICATION TEMP.
FLUID TEMP. RANGE
GRAY-KING COKE TYPE
HARDGROVE GRINDABILITY
FREE SWELLING INDEX
VICKERS HARDNESS NUMBER
MAXIMUM FLUIDITY
WASHABILITY DATA AVAILABLE? NO

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-1
-> BOTTOM
->
-> SUBBIT C

SAMPLE LOCATION:

COUNTRY
STATE

-> USA
-> TEXAS

** PENN STATE COAL DATA BASE **
**
** DECS-1
**
** 02/04/93
** PAGE 4
**

MAJOR ELEMENT ANALYSIS

% HTA = 17.14

	SI02	AL203	T102	FE203	MG0	CA0	NA20	K20	P205	S03
OXIDE % OF HTA	45.6	17.0	1.26	4.18	2.68	5.50	0.42	0.60	0.23	12.7
ELEMENT % OF TOTAL DRY COAL	SI	AL	TI	FE	MG	CA	NA	K	P	S
	3.7	1.5	0.13	0.50	0.28	0.67	0.05	0.09	0.02	1.0

TRACE ELEMENT ANALYSIS

% HTA = 17.14

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES -----	PPM TOTAL COAL
AG							AS	
B							BR	
BA	1344.	230.					CD	
BE	5.0	0.9	1239.	212.			CL	1100.
BI							F	
CE							HG	
CO			< 25.	< 4.			SB	
CR	95.	16.			50.	9.	SE	
CU	130.	22.	30.	5.	270.	46.		
GA								

** PENN STATE COAL DATA BASE **
**
** DECS-1 **
** **
** 02/04/93 **
** PAGE 5 **

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> TEXAS

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-1
SEAM NAME -> BOTTOM
ALTERNATE SEAM NAME ->
APPARENT RANK -> SUBBIT C

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)	
---	-----
INITIAL DEFORMATION	1840.
SOFTENING	2000.
HEMISPHERICAL	2060.
FLUID	2100.

REDUCING	OXIDIZING
2120.	2220.
2280.	2330.

SAMPLE IDENTIFICATION:-----
PSU NUMBER -> DECS-2
SEAM NAME -> ILLINOIS #6
ALTERNATE SEAM NAME -> HERRIN
APPARENT RANK -> HVC
SAMPLE HISTORY:-----
SAMPLING DATE & AGENCY -> 12/13/89 ; PSU
SAMPLE TYPE -> CHANNEL-WHOLE SEAM
ADDITIONAL INFORMATION ->
MINE INFORMATION:-----
RESERVES ->
ANNUAL PRODUCTION ->
SEAM INFORMATION:-----
AGE OF SEAM -> PENNSYL.
GROUP -> Kewanee
FORMATION -> Carbondale
SEAM THICKNESS -> 6 FT. 3 IN.

SAMPLE LOCATION:-----
COUNTRY -> USA
STATE -> ILLINOIS
COUNTY -> RANDOLPH
TOWNSHIP ->
CITY -> SPARTA
COAL PROVINCE-> INTERIOR
REGION -> EASTERN
MAP REFERENCE: LATITUDE -> 38 D 9 M 27 S
LONGITUDE -> 89 D 43 M 19 S
QUADRANGLE-> Tilden (7.5')

** PENN STATE COAL DATA BASE **
**
** DECS-2
**
** 02/04/93
** PAGE 1
**

LIFE EXPECTANCY ->
MINING METHOD -> STRIP

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:
COUNTRY
STATE

DECS-2
ILLINOIS #6
HERRIN
HVC

PENN STATE COAL DATA BASE
DECS-2
02/04/93
PAGE 2

C H E M I C A L D A T A

Table with 4 columns: ANALYSIS, AS REC'D, DRY, DAF. Rows include % MOISTURE, % ASH, % VOLATILE, % FIXED CARBON, and summary statistics like EQUILIBRIUM MOISTURE and MM-FREE.

Table with 6 columns: ANALYSIS, AS REC'D, DRY, DMMF(PARR), ELEMENTAL ANALYSIS, DRY, DMMF(MOD.P), DMMF(DIR.). Rows include % ASH, % CARBON, % HYDROGEN, % NITROGEN, % TOTAL SULFUR, % OXYGEN(DIFF), and % MINERAL MATTER.

Table with 4 columns: SULFUR FORMS, % PYRITIC, % SULFATIC, % TOTAL. Rows include DRY and DAF.

Table with 4 columns: ANALYSIS, AS REC'D, DRY, EQUIL. MOIST. Rows include CALORIFIC VALUE, MM-CONTAINING, MM-FREE (PARR), MM-FREE (MOD. P), and NET CV.

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK
--> DECS-2
--> ILLINOIS #6
--> HERRIN
--> HVC
SAMPLE LOCATION:
COUNTRY -> USA
STATE -> ILLINOIS
** PENN STATE COAL DATA BASE **
** DECS-2
**
** 02/04/93
** PAGE 3

***** RANK CALCULATIONS *****
APPARENT RANK (AS REC'D MOIST.) -> HVC
ASTM RANK (EQUIL. MOIST.) -> HVC
REFLECTANCE RANK CATEGORY -> HVC
INTERNATIONAL RANK:
AS REC'D MOIST. ->
EQUIL. MOIST. ->
REPORTED RANK: ->

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT AND FLUORESCENCE ANALYSIS)

Table with 10 columns: DMF VOL. %, DRY VOL. %, DRY WT. %, PSEUDO-VITRINITE, FUSINITE, SEMI-FUSINITE, MACRINITE, MICRINITE, SCLERO-TINITE, SPORINITE, RESINITE, ALGINITE, CUTINITE. Rows show data for DMF, DRY, and REFLECTANCE.

REFLECTANCE DATA
VITRINITE : HIGH: 0.65 LOW: 0.42 MEAN-MAX: 0.52

VITRINITE TYPES V 4 V 5 V 6
PERCENT 33.0 62.0 5.0

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:
INIT. SOFTENING TEMP 385
TEMP. MAX. FLUIDITY 411
SOLIDIFICATION TEMP. 432
FLUID TEMP. RANGE 47
GRAY-KING COKE TYPE
HARDGROVE GRINDABILITY 57.8
FREE SWELLING INDEX 3.5
VICKERS HARDNESS NUMBER
MAXIMUM FLUIDITY 8
WASHABILITY DATA AVAILABLE? NO

SAMPLE IDENTIFICATION:-----
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-2
-> ILLINOIS #6
-> HERRIN
-> HVC
SAMPLE LOCATION:-----
COUNTRY -> USA
STATE -> ILLINOIS

** PENN STATE COAL DATA BASE **
**
** DECS-2
**
** 02/04/93
** PAGE 4
**

MAJOR ELEMENT ANALYSIS

% HTA = 15.97
S102 AL2O3 T102 FE2O3 MGO CAO NA2O K2O P2O5 S03
OXIDE % OF HTA 49.2 19.1 0.89 20.4 5.18 0.71 1.87 0.17 1.60
SI AL TI FE MG CA NA K P S
ELEMENT % OF 3.7 1.6 0.09 2.3 0.08 0.59 0.08 0.01 4.52
TOTAL DRY COAL

TRACE ELEMENT ANALYSIS

% HTA = 15.97
PPM PPM PPM PPM PPM PPM PPM PPM PPM PPM
HTA HTA HTA HTA HTA HTA HTA HTA HTA HTA
TOTAL COAL TOTAL COAL TOTAL COAL TOTAL COAL TOTAL COAL TOTAL COAL TOTAL COAL TOTAL COAL
AG GE SN SR TH U V Y YB ZN ZR
B LA
BA 269. 43.
BE 8.0 1.3 62. 387. 85. 14. 97. 26.
BI MO NB NI PB RB SC
CE
CO 130. 21. 610. 160.
CU 60. 10. 14. 160.
GA

** PENN STATE COAL DATA BASE **
 **
 ** DECS-2
 **
 ** 02/04/93
 ** PAGE 5

SAMPLE LOCATION:

 COUNTRY
 STATE
 -> USA
 -> ILLINOIS

SAMPLE IDENTIFICATION:

 PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK
 -> DECS-2
 -> ILLINOIS #6
 -> HERRIN
 -> HVC

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)			

	REDUCING	OXIDIZING	
INITIAL DEFORMATION	1900.	2240.	
SOFTENING	2035.	2340.	
HEMISPHERICAL	2100.	2400.	
FLUID	2180.	2450.	

SAMPLE IDENTIFICATION:-----
PSU NUMBER -> DECS-5
SEAM NAME -> HIAWATHA
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVC

SAMPLE HISTORY:-----
SAMPLING DATE & AGENCY -> 6/ 6/90 ; PSU

SAMPLE TYPE -> CHANNEL-WORKING SECTION
ADDITIONAL INFORMATION ->

MINE INFORMATION:-----
RESERVES ->
ANNUAL PRODUCTION ->

SAMPLE LOCATION:-----

COUNTRY -> USA
STATE -> UTAH
COUNTY -> SEVIER
TOWNSHIP ->
CITY -> EMERY
COAL PROVINCE-> ROCKY MOUNTAIN
REGION -> UINTA

MAP REFERENCE: LATITUDE -> 38 D 57 M 55 S
LONGITUDE -> 111 D 23 M 15 S
QUADRANGLE-> ACORD LAKES

LIFE EXPECTANCY ->

MINING METHOD -> UNDERGROUND

SEAM INFORMATION:-----

AGE OF SEAM -> CRET.
GROUP -> MESAVERDE
FORMATION -> BLACKHAWK
SEAM THICKNESS ->

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-5
-> HIAWATHA
->
-> HVC

SAMPLE LOCATION:

COUNTRY
STATE

-> USA
-> UTAH

** PENN STATE COAL DATA BASE **
**
** DECS-5
**
** 02/04/93
** PAGE 2
**

***** C H E M I C A L D A T A * * * * *

PROXIMATE ANALYSIS AS REC'D DAF DMMF(PARR)

% MOISTURE 7.54
% ASH 7.90
% VOLATILE 37.29 44.10 43.58
% FIXED CARBON 47.27 51.13 55.90 56.42

% EQUILIBRIUM MOISTURE = 7.88
MM-FREE = 8.66

ULTIMATE ANALYSIS

AS REC'D DRY DAF DMMF(PARR) ELEMENTAL ANALYSIS DRY DMMF(MOD.P) DMMF(DIR.)
(9.53%MM) (9.80%MM) (%MM)

% ASH 7.90 8.54
% CARBON 67.22 72.70 79.49 80.36 % CARBON 72.40 80.27
% HYDROGEN 4.58 (*) 4.95 5.41 5.47 % HYDROGEN 4.84 5.37
% NITROGEN 1.05 1.14 1.25 1.26 % NITROGEN 1.14 1.26
% TOTAL SULFUR 0.52 0.56 0.61 % ORGANIC SULFUR 0.28 0.31
% OXYGEN(DIFF) 11.20 (*) 12.11 13.24 12.91 % OXYGEN(DIFF) 11.53 12.78

(*)-EXCLUDES MOISTURE

% MINERAL MATTER
(INCL. 0.51% FES2)

9.80

SULFUR FORMS

% PYRITIC % SULFATIC % ORGANIC % TOTAL
0.27 0.01 0.28 0.56
0.30 0.01 0.31 0.61
DRY DRY % CHLORINE = 0.05 DRY % CO2 = 1.09
DAF MOTT-SPOONER DIFFERENCE = 40.

CALORIFIC VALUE
(GROSS, BTU/LB)

MM-CONTAINING 12760. 11798. 11755.
MM-FREE (PARR) 14073. 12910. 12858.
MM-FREE (MOD. P) 14131. 12959. 12906.
NET CV, DMF BTU/LB 13622.

ATOM RATIOS (DMMF)

DIRECT

ATOMIC H/C 0.8178 0.8036
ATOMIC O/C 0.1206 0.1196

MOD.PARR

PARR

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:
COUNTRY
STATE

DECS-5
HIAWATHA
HVC
USA
UTAH

INTERNATIONAL RANK :
AS REC'D MOIST.
EQUIL. MOIST.
REPORTED RANK :

PETROGRAPHIC DATA

MACERAL COMPOSITION (WHITE LIGHT AND FLUORESCENCE ANALYSIS)

	VITRINITE	PSEUDO-VITRINITE	FUSINITE	SEMI-FUSINITE	MACRINITE	MICRINITE	SCLERO-TINITE	SPOR-INITE	RESINITE	ALGINITE	CUTINITE
DMMF VOL. %	65.5	0.0	3.7	9.7	5.6	0.8	0.0	10.9	2.2	0.3	0.5
DRY VOL. %	62.3	0.0	3.5	9.2	5.3	0.8	0.0	10.4	2.1	0.3	0.5
DRY WT. %	60.0	0.0	3.8	9.5	5.5	0.8	0.0	8.5	1.7	0.2	0.4

MEAN-MAX: 0.59

VITRINITE :

LOW: 0.48

HIGH: 0.68

REFLECTANCE DATA

VITRINITE TYPES V 4 V 5 V 6
PERCENT 2.0 56.0 42.0

CAKING AND MECHANICAL PROPERTIES

GIESELER COAL PLASTOMETER:

INIT. SOFTENING TEMP
TEMP. MAX. FLUIDITY
SOLIDIFICATION TEMP.
FLUID TEMP. RANGE
GRAY-KING COKE TYPE
HARDGROVE GRINDABILITY
FREE SWELLING INDEX
VICKERS HARDNESS NUMBER

MAXIMUM FLUIDITY
WASHABILITY DATA AVAILABLE? NO

** PENN STATE COAL DATA BASE **
**
** DECS-5 **
** **
** 02/04/93 **
** PAGE 5 **

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> UTAH

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-5
SEAM NAME -> HIAWATHA
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVC

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)			

	REDUCING	OXIDIZING	
INITIAL DEFORMATION	1920.	2150.	
SOFTENING	2045.	2205.	
HEMISPHERICAL	2100.	2245.	
FLUID	2170.	2300.	

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-6
-> Blind Canyon
->
-> HVA

SAMPLE HISTORY:

SAMPLING DATE & AGENCY

-> 6/ 7/90 ; PSU

SAMPLE TYPE

-> CHANNEL-WORKING SECTION

ADDITIONAL INFORMATION

-> TOP 8' OF 8' 6" SEAM

MINE INFORMATION:

RESERVES

->

ANNUAL PRODUCTION

->

SAMPLE LOCATION:

COUNTRY

-> USA

STATE

-> UTAH

COUNTY

-> Emery

TOWNSHIP

->

CITY

-> Huntington

COAL PROVINCE-> ROCKY MOUNTAIN

REGION -> UINTA

MAP REFERENCE:

LATITUDE -> 39 D 21 M 44 S

LONGITUDE -> 111 D 10 M 4 S

QUADRANGLE-> Mahogany Point

LIFE EXPECTANCY

->

MINING METHOD

-> UNDERGROUND

SEAM INFORMATION:

AGE OF SEAM

-> U. CRET.

GROUP

-> Mesaverde

FORMATION

-> Blackhawk

SEAM THICKNESS

-> 8 FT. 6 IN.

** PENN STATE COAL DATA BASE **
**
** DECS-6 **
**
** 02/04/93 **
** PAGE 1 **

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

DECS-6
Blind Canyon
HVA

COUNTRY
STATE

USA
UTAH

DECS-6
02/04/93
PAGE 2

PENN STATE COAL DATA BASE

SAMPLE IDENTIFICATION:

SAMPLE LOCATION:

***** C H E M I C A L D A T A *****

PROXIMATE ANALYSIS		AS REC'D	DRY	DAF	DMMF(PARR)
% MOISTURE		4.73			
% ASH		5.56	5.84		
% VOLATILE		42.40	44.50	47.26	46.94
% FIXED CARBON		47.31	49.66	52.74	53.06

% EQUILIBRIUM MOISTURE = 4.85
MM-FREE = 5.18

ULTIMATE ANALYSIS		AS REC'D	DRY	DAF	DMMF(PARR)	ELEMENTAL ANALYSIS		DRY	DMMF(MOD. P)	DMMF(DIR.)
% ASH		5.56	5.84			(6.53%MM)			(6.67%MM)	(%MM)
% CARBON		72.91	76.53	81.28	81.87		% CARBON	76.27	81.72	
% HYDROGEN		5.60 (*)	5.88	6.24	6.29		% HYDROGEN	5.80	6.22	
% NITROGEN		1.39	1.46	1.55	1.56		% NITROGEN	1.46	1.56	
% TOTAL SULFUR		0.38	0.40	0.42			% ORGANIC SULFUR	0.37	0.40	
% OXYGEN(DIFF)		9.42 (*)	9.89	10.50	10.27		% OXYGEN(DIFF)	9.43	10.10	

(*)-EXCLUDES MOISTURE

SULFUR FORMS	% PYRITIC	% SULFATIC	% ORGANIC	% TOTAL	DRY % CHLORINE =	DRY % CO2 =
DRY	0.02	0.01	0.37	0.40	0.12	0.96
DAF	0.02	0.01	0.39	0.42	MOTT-SPOONER DIFFERENCE = -72.	

CALORIFIC VALUE (GROSS, BTU/LB)		DRY	AS REC'D MOIST.	EQUIL. MOIST.	ATOM RATIOS (DMMF)	PARR	MOD. PARR	DIRECT
MM-CONTAINING		13923.	13264.	13248.	ATOMIC H/C	0.9228	C.9141	
MM-FREE (PARR)		14874.	14124.	14105.	ATOMIC O/C	0.0942	0.0928	
MM-FREE (MOD. P)		14917.	14163.	14144.				
NET CV, DMF BTU/LB		14333.						

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK
COUNTRY
STATE
REPORTED RANK :
HVA
HVB
HVA
HVB
DECS-6
Blind Canyon
HVA
HVB
PENN STATE COAL DATA BASE
DECS-6
02/04/93
PAGE 3

APPARENT RANK (AS REC'D MOIST.)
ASTM RANK (EQUIL. MOIST.)
REFLECTANCE RANK CATEGORY
INTERNATIONAL RANK :
AS REC'D MOIST.
EQUIL. MOIST.
REPORTED RANK :

PETROGRAPHIC DATA

MACERAL COMPOSITION (WHITE LIGHT AND FLUORESCENCE ANALYSIS)

Table with 10 columns: DMF VOL. %, DRY VOL. %, DRY WT. %, VITRINITE, PSEUDO-VITRINITE, FUSINITE, SEMI-FUSINITE, MACRINITE, MICRINITE, SCLERO-TINITE, SPORINITE, RESINITE, ALGINITE, CUTINITE. Includes rows for DMF, DRY, and VITRINITE percentages.

REFLECTANCE DATA
VITRINITE : HIGH: 0.82 LOW: 0.58 MEAN-MAX: 0.66

VITRINITE TYPES
PERCENT
V 5 V 6 V 7 V 8
3.0 77.0 19.0 1.0

COAL PLASTOMETER: GIESELER

Table with 2 columns: PROPERTY, VALUE. Rows include INIT. SOFTENING TEMP (400), TEMP. MAX. FLUIDITY (419), SOLIDIFICATION TEMP. (438), FLUID TEMP. RANGE (38), MAXIMUM FLUIDITY (3), WASHABILITY DATA AVAILABLE? (NO).

SAMPLE IDENTIFICATION:-----
PSU NUMBER--> DECS-6
SEAM NAME--> Blind Canyon
ALTERNATE SEAM NAME--> HVA
APPARENT RANK--> HVA
SAMPLE LOCATION:-----
COUNTRY--> USA
STATE--> UTAH

** PENN STATE COAL DATA BASE **
** DECS-6
**
** 02/04/93
** PAGE 4
**

MAJOR ELEMENT ANALYSIS

% HTA = 6.26

SI02	AL203	T102	FE203	MGO	CAO	NA2O	K2O	P2O5	S03
OXIDE % OF HTA	50.3	15.3	0.96	1.26	12.0	6.91	0.59	0.38	4.80
SI	AL	T1	FE	MG	CA	NA	K	P	S
ELEMENT % OF TOTAL DRY COAL	1.5	0.5	0.04	0.05	0.5	0.32	0.03	0.01	0.40

TRACE ELEMENT ANALYSIS

% HTA = 6.26

PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG	GE	SN	AS				
B	LA	SR	BR				
BA	LI	TH	CD				
BE	MN	U	CL				1200.
BI	MO	V	F				
CE	NB	Y	HG				
CO	NI	YB	SB				
CR	PB	ZN	SE				
CU	RB	ZR					
GA	SC						

** PENN STATE COAL DATA BASE **
**
** DECS-6
**
** 02/04/93
** PAGE 5

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> UTAH

SAMPLE IDENTIFICATION:

FSJ NUMBER -> DECS-6
SEAM NAME -> Blind Canyon
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVA

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	1900.	2250.
SOFTENING	2020.	2345.
HEMISPHERICAL	2090.	2400.
FLUID	2240.	2440.

SAMPLE IDENTIFICATION:-----
PSU NUMBER -> DECS-7
SEAM NAME -> ADAVILLE #1
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVC
SAMPLE HISTORY:-----
SAMPLING DATE & AGENCY -> 6/ 8/90 ; PSU
SAMPLE TYPE -> CHANNEL-WHOLE SEAM
ADDITIONAL INFORMATION ->
MINE INFORMATION:-----
RESERVES ->
ANNUAL PRODUCTION ->
SEAM INFORMATION:-----
AGE OF SEAM -> U. CRET.
GROUP ->
FORMATION -> ADAVILLE
SEAM THICKNESS -> 120 FT. 0 IN.

SAMPLE LOCATION:-----

COUNTRY -> USA
STATE -> WYOMING
COUNTY -> LINCOLN
TOWNSHIP ->
CITY -> KEMMERER
COAL PROVINCE-> ROCKY MOUNTAIN
REGION -> HAMS FORK
MAP REFERENCE: LATITUDE -> 41 D 47 M 23 S
LONGITUDE -> 110 D 36 M 32 S
QUADRANGLE-> KEMMERER

** PENN STATE COAL DATA BASE **
** DECS-7 **
** 02/04/93 **
** PAGE 1 **

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:

COUNTRY
STATE

DECS-7
-> ADAVILLE #1
->
-> HVC

DECS-7
DECS-7
02/04/93
PAGE 2

***** CHEMICAL DATA *****

PROXIMATE ANALYSIS AS REC'D DRY DAF DMF(PARR)
% MOISTURE 17.34
% ASH 3.45 4.17
% VOLATILE 38.11 46.10 48.11 47.78
% FIXED CARBON 41.11 49.73 51.89 52.22
% EQUILIBRIUM MOISTURE = 18.40
MM-FREE = 19.15

ULTIMATE ANALYSIS AS REC'D DRY DAF DMF(PARR) ELEMENTAL ANALYSIS DRY DMF(MOD.P) DMF(DIR.)
(5.04%MM) (4.79%MM) (%MM)
% ASH 3.45 4.17 77.12 77.82 % CARBON 73.74 77.45
% CARBON 61.09 73.90 5.53 5.58 % HYDROGEN 5.25 5.51
% HYDROGEN 4.38 (*) 5.30 1.03 1.04 % NITROGEN 0.99 1.04
% NITROGEN 0.82 0.99 1.02 15.55 % ORGANIC SULFUR 0.87 0.91
% TOTAL SULFUR 0.81 0.98 15.30 % OXYGEN(DIFF) 14.37 15.09
% OXYGEN(DIFF) 12.12 (*) 14.66
(*)-EXCLUDES MOISTURE
% MINERAL MATTER (INCL. 0.19% FES2) 4.79

SULFUR FORMS % PYRITIC % SULFATIC % TOTAL
% ORGANIC
% CHLORINE = 0.06 DRY % CO2 = 0.60
MOTT-SPOONER DIFFERENCE = 52.

CALORIFIC VALUE (GROSS, BTU/LB) AS REC'D DRY EQUIL. MOIST.
MM-CONTAINING 13068. 10802. 10663.
MM-FREE (PARR) 13710. 11230. 11079.
MM-FREE (MOD. P) 13720. 11243. 11093.
NET CV, DMF BTU/LB 13204.

ATOM RATIOS (DMF) PARR MOD. PARR DIRECT
ATOMIC H/C 0.8614 0.8548
ATOMIC O/C 0.1500 0.1463

SAMPLE IDENTIFICATION: -----
PSU NUMBER -> DECS-7
SEAM NAME -> ADAVILLE #1
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVC
SAMPLE LOCATION: -----
COUNTRY -> USA
STATE -> WYOMING
** PENN ** STATE COAL DATA BASE **
** DECS-7 **
** **
** 02/04/93 **
** PAGE 3 **

***** RANK CALCULATIONS *****
APPARENT RANK (AS REC'D MOIST.) -> HVC
INTERNATIONAL RANK :
AS REC'D MOIST. ->
EQUIL. MOIST. ->
ASTM RANK (EQUIL. MOIST.) -> HVC
REFLECTANCE RANK CATEGORY -> REPORTED RANK : ->

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT AND FLUORESCENCE ANALYSIS)

TEXT- INITE	ULM- INITE	HUMO- DET	GEL- INITE	CORPO- HUMINITE	SPOR- INITE	CUT- INITE	RES- INITE	ALG- INITE	FUS- INITE	SEMI- FUSINITE	MAC- RINITE	SCLERO- TINITE
DMHF VOL. %	0.0	32.5	52.9	1.3	7.9	3.1	0.0	0.1	0.0	0.3	0.5	0.5
DRY WT. %	0.0	30.9	50.2	1.2	7.5	2.9	0.0	0.1	0.0	0.3	0.5	0.5
DMHF VOL % HUMINITE =	94.6											
5.0 % MM.												

ULMINITE REFLECTANCE DATA: -----
HIGH: 0.56 LOW: 0.27 MEAN-MAX: 0.45

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:
INIT. SOFTENING TEMP
TEMP. MAX. FLUIDITY
SOLIDIFICATION TEMP.
FLUID TEMP. RANGE
GRAY-KING COKE TYPE
HARDGROVE GRINDABILITY 49.3
FREE SWELLING INDEX 1.0
VICKERS HARDNESS NUMBER

MAXIMUM FLUIDITY
WASHABILITY DATA AVAILABLE? NO

SAMPLE IDENTIFICATION:-----
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-7
-> ADAVILLE #1
->
-> HVC

SAMPLE LOCATION:-----
COUNTRY -> USA
STATE -> WYOMING

** PENN STATE COAL DATA BASE **
** DECS-7 **
** 02/04/93 **
** PAGE 4 **

MAJOR ELEMENT ANALYSIS

% HTA = 4.43

SI02	AL203	TI02	FE203	MG0	CA0	NA20	K20	P205	S03
OXIDE % OF HTA	50.2	18.7	4.49	3.41	8.87	0.38	0.41	0.18	10.5
ELEMENT % OF	SI	AL	FE	MG	CA	NA	K	P	S
TOTAL DRY COAL	1.0	0.4	0.14	0.09	0.28	0.01	0.02	0.003	1.0

TRACE ELEMENT ANALYSIS

% HTA = 4.43

PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG		GE		SN		AS	
B		LA		SR	1945.	BR	
BA	2060.	LI		TH		CD	
BE	< 3.0	MN	465.	U		CL	600.
BI		MO		V	< 10.	F	
CE		NB		Y		HG	
CO		NI	< 25.	YB		SB	
CR	85.	PB		ZN	95.	SE	
CU	85.	RB	20.	ZR	380.		
GA		SC			17.		

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-7
-> ADAVILLE #1
->
-> HVC

SAMPLE LOCATION:

COUNTRY
STATE

-> USA
-> WYOMING

** PENN STATE COAL DATA BASE **

**
** DECS-7
**
** 02/04/93
** PAGE 5
**

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2120.	2200.
SOFTENING	2200.	2300.
HEMISPHERICAL	2260.	2345.
FLUID	2330.	2390.

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> WYOMING
 COUNTY -> CAMPBELL
 TOWNSHIP ->
 CITY -> GILLETTE

COAL PROVINCE-> NORTHERN GREAT PLAINS
 REGION -> FORT UNION

MAP REFERENCE: LATITUDE -> 44 D 16 M 40 S
 LONGITUDE -> 105 D 23 M 36 S
 QUADRANGLE-> GILLETTE EAST

LIFE EXPECTANCY ->
 MINING METHOD -> STRIP

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-8
 SEAM NAME -> SMITH-ROLAND
 ALTERNATE SEAM NAME -> WYODAK
 APPARENT RANK -> SUBBIT C

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 6/11/90 ; PSU

SAMPLE TYPE

-> RUN OF MINE

ADDITIONAL INFORMATION -> COLLECTED FROM AUTOMATIC SAMPLER

MINE INFORMATION:

RESERVES ->
 ANNUAL PRODUCTION ->

SEAM INFORMATION:

AGE OF SEAM -> PALEO.
 GROUP ->
 FORMATION -> FORT UNION
 SEAM THICKNESS ->

** PENN STATE COAL DATA BASE **
 **
 ** DECS-8
 **
 ** 02/04/93
 ** PAGE 2
 **

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> WYOMING

--> DECS-8
 --> SMITH-ROLAND
 --> WYODAK
 --> SUBBIT C

SAMPLE IDENTIFICATION:

 PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK

* * * * * C H E M I C A L D A T A * * * * *

PROXIMATE ANALYSIS AS REC'D DRY DAF DMF(PARR)
 % MOISTURE 28.42
 % ASH 9.90 13.83
 % VOLATILE 32.38 45.23 51.77
 % FIXED CARBON 29.30 40.94 48.23
 % EQUILIBRIUM MOISTURE = 28.41
 MM-FREE = 32.03

ULTIMATE ANALYSIS AS REC'D DRY DAF DAF DMF(PARR) ELEMENTAL ANALYSIS DRY DMF(MOD.P) DMF(DIR.)
 (15.78%MM) (15.34%MM) (15.78%MM) (%MM)
 % ASH 9.90 13.83
 % CARBON 45.91 64.14 74.43 75.76 63.87 75.84
 % HYDROGEN 3.23 (*) 4.51 5.23 5.33 4.34 5.15
 % NITROGEN 0.62 0.86 1.00 1.02 0.86 1.02
 % TOTAL SULFUR 0.52 0.73 0.85 17.90 0.43 0.51
 % OXYGEN(DIFF) 11.40 (*) 15.93 18.49 17.48
 % MINERAL MATTER 15.78
 (INCL. 0.52% FES2)

Sulfur Forms % Pyritic % Sulfatic % Total
 DRY 0.28 0.02 0.73
 DAF 0.32 0.02 0.85
 DRY % Chlorine = 0.05 DRY % CO2 = 0.98
 Mott-Spooner Difference = 178.

CALORIFIC VALUE (GROSS, BTU/LB) AS REC'D MOIST. EQUIL. MOIST. ATOM RATIOS (DMF) PARR MOD.PARR DIRECT
 MM-CONTAINING 11168. 7994. 7995. ATOMIC H/C 0.8446 0.8153
 MM-FREE (PARR) 13148. 8951. 8952. ATOMIC O/C 0.1773 0.1730
 MM-FREE (MOD. P) 13243. 9000. 9002.
 NET CV, DMF BTU/LB 12747.

** PENN STATE COAL DATA BASE **
 **
 ** DECS-8
 **
 ** 02/04/93
 ** PAGE 3

SAMPLE IDENTIFICATION:

 PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK

 -> DECS-8
 -> SMITH-ROLAND
 -> WYODAK
 -> SUBBIT C

 SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> WYOMING

***** RANK CALCULATIONS *****

APPARENT RANK (AS REC'D MOIST.) -> SUBBIT C INTERNATIONAL RANK :
 AS REC'D MOIST. ->
 EQUIL. MOIST. ->
 ASTM RANK (EQUIL. MOIST.) -> SUBBIT C
 REFLECTANCE RANK CATEGORY -> SUBBIT C REPORTED RANK : -> SUBBIT C

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT AND FLUORESCENCE ANALYSIS)

	TEXT- INITE	ULM- INITE	HUMO- DETRINITE	GEL- INITE	CORPO- HUMINITE	SPOR- INITE	CUT- INITE	RES- INITE	ALG- INITE	FUS- INITE	SEMI- FUSINITE	MAC- RINITE	SCLERO- TINITE
DMMF VOL. %	0.0	32.6	34.3	8.0	4.0	11.3	0.1	0.3	0.1	2.6	3.6	3.0	0.1
													15.3 % MM.

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:
 GRAY-KING COKE TYPE
 INIT. SOFTENING TEMP
 HARDGROVE GRINDABILITY 55.3
 TEMP. MAX. FLUIDITY
 FREE SWELLING INDEX 0.0
 SOLIDIFICATION TEMP.
 VICKERS HARDNESS NUMBER
 FLUID TEMP. RANGE

MAXIMUM FLUIDITY
 WASHABILITY DATA AVAILABLE? NO

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:
COUNTRY
STATE

DECS-8
SMITH-ROLAND
WYODAK
SUBBIT C

PENN STATE COAL DATA BASE
DECS-8
02/94/93
PAGE 4

% HTA = 13.19

MAJOR ELEMENT ANALYSIS

Table with 10 columns: Element, SI02, AL203, TIO2, FE203, MG0, CAO, NA20, K20, P205, S03. Rows include OXIDE % OF HTA and ELEMENT % OF TOTAL DRY COAL.

% HTA = 13.19

TRACE ELEMENT ANALYSIS

Table with 10 columns: Element, PPM HTA, PPM TOTAL COAL, PPM HTA, PPM TOTAL COAL, Volatiles, PPM TOTAL COAL. Rows include AG, B, BA, BE, BI, CE, CO, CR, CU, GA.

** PENN STATE COAL DATA BASE **
**
** DECS-8
**
** 02/04/93
** PAGE 5

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> WYOMING

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-8
SEAM NAME -> SMITH-ROLAND
ALTERNATE SEAM NAME -> WYODAK
APPARENT RANK -> SUBBIT C

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2000.	2200.
SOFTENING	2100.	2260.
HEMISPHERICAL	2145.	2300.
FLUID	2210.	2345.

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> MONTANA
 COUNTY -> BIGHORN
 TOWNSHIP ->
 CITY -> DECKER
 COAL PROVINCE-> NORTHERN GREAT PLAINS
 REGION -> FORT UNION

MAP REFERENCE: LATITUDE -> 45 D 6 M 41 S
 LONGITUDE -> 106 D 53 M 53 S
 QUADRANGLE->

LIFE EXPECTANCY ->

MINING METHOD -> STRIP

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-9
 SEAM NAME -> DIETZ
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> SUBBIT B

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 6/12/90 ; PSU

SAMPLE TYPE ->

ADDITIONAL INFORMATION -> AIR ROTARY DRILL CUTTINGS

MINE INFORMATION:

RESERVES ->

ANNUAL PRODUCTION ->

SEAM INFORMATION:

AGE OF SEAM -> PALEO.

GROUP ->

FORMATION -> FORT UNION

SEAM THICKNESS -> 830 FT. 80 IN.

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:
COUNTRY
STATE

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

DECS-9
DIETZ
SUBBIT B

DECS-9
DIETZ
SUBBIT B

US
MONTANA

DECS-9
DIETZ
SUBBIT B

DECS-9
DIETZ
SUBBIT B

Table with 4 columns: AS REC'D, DRY, DAF, DMMF(PARR). Rows include % MOISTURE, % ASH, % VOLATILE, % FIXED CARBON.

% EQUILIBRIUM MOISTURE = 24.57
MM-FREE = 26.00

Table with 4 columns: AS REC'D, DRY, DAF, DMMF(PARR). Rows include % ASH, % CARBON, % HYDROGEN, % NITROGEN, % TOTAL SULFUR, % OXYGEN(DIFF).

% ELEMENTAL ANALYSIS
% CARBON
% HYDROGEN
% NITROGEN
% ORGANIC SULFUR
% OXYGEN(DIFF)
% MINERAL MATTER (INCL. 0.15% FES2)

(*)-EXCLUDES MOISTURE

Table with 4 columns: % PYRITIC, % SULFATIC, % TOTAL, % ORGANIC. Rows include DRY, DAF.

DRY % CHLORINE = 0.09
MOTT-SPOONER DIFFERENCE = 201.

Table with 4 columns: DRY, DAF, AS REC'D MOIST., EQUIV. MOIST. Rows include CALORIFIC VALUE, MM-CONTAINING, MM-FREE (PARR), MM-FREE (MOD. P).

NET CV, DMMF BTU/LB 12809.

NET CV, DMMF BTU/LB 12809.

** PENN STATE COAL DATA BASE **
 ** DECS-9 **
 ** 02/04/93 **
 ** PAGE 3 **

SAMPLE IDENTIFICATION:

PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK

COUNTRY
 STATE

***** RANK CALCULATIONS *****

APPARENT RANK (AS REC'D MOIST.)
 ASTM RANK (EQUIL. MOIST.)
 REFLECTANCE RANK CATEGORY

***** PETROGRAPHIC DATA *****

***** NO PETROGRAPHIC DATA THIS SAMPLE *****

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:
 INIT. SOFTENING TEMP.
 TEMP. MAX. FLUIDITY
 SOLIDIFICATION TEMP.
 FLUID TEMP. RANGE
 MAXIMUM FLUIDITY
 WASHABILITY DATA AVAILABLE? NO

GRAY-KING COKE TYPE
 HARDGROVE GRINDABILITY
 FREE SWELLING INDEX
 VICKERS HARDNESS NUMBER

** PENN STATE COAL DATA BASE **
 **
 ** DECS-9
 **
 ** 02/04/93
 ** PAGE 4
 **

SAMPLE IDENTIFICATION:

PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK

-> DECS-9
 -> DIETZ
 ->
 -> SUBBIT B

COUNTRY
 STATE

-> USA
 -> MONTANA

% HTA = 5.96

MAJOR ELEMENT ANALYSIS

OXIDE % OF HTA	SI02	AL2O3	TI02	FE2O3	MG0	CA0	NA2O	K2O	P2O5	SO3
36.2	18.1	1.20	4.90	4.52	13.5	5.55	1.01	0.36	13.4	
SI	AL	TI	FE	MG	CA	NA	K	P	S	
1.0	0.6	0.04	0.20	0.16	0.6	0.25	0.05	0.01	0.4	

ELEMENT % OF
 TOTAL DRY COAL

% HTA = 5.96

TRACE ELEMENT ANALYSIS

PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG		GE		SN		AS	
B		LA		SR	5835.	BR	
BA	11644.	LI		TH		CD	
BE	4.0	MN	310.	U		CL	900.
BI		MO		V	250.	F	
CE		NB		Y		HG	
CO		NI	< 25.	YB		SB	
CR	85.	PB		ZN	130.	SE	
CU	210.	RB	40.	ZR	370.		
GA		SC					

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK
--> DECS-9
--> DIETZ
-->
--> SUBBIT B

SAMPLE LOCATION:
COUNTRY
STATE
--> USA
--> MONTANA

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)
REDUCING OXIDIZING
INITIAL DEFORMATION 1910. 2050.
SOFTENING 1990. 2145.
HEMISPHERICAL 2040. 2210.
FLUID 2090. 2240.

** PENN STATE COAL DATA BASE **
** DECS-9 **
** 02/04/93 **
** PAGE 5 **

** PENN STATE COAL DATA BASE **
 **
 ** DECS-11
 **
 ** 02/04/93
 ** PAGE 1
 **

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> NORTH DAKOTA
 COUNTY -> MERCER
 TOWNSHIP ->
 CITY -> BEULAH
 COAL PROVINCE-> NORTHERN GREAT PLAINS
 REGION -> FORT UNION
 MAP REFERENCE: LATITUDE -> 47 D 23 M 29 S
 LONGITUDE -> 101 D 47 M 59 S
 QUADRANGLE-> BEULAH NE

LIFE EXPECTANCY -> 50 YEARS
 MINING METHOD -> STRIP

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-11
 SEAM NAME -> BEULAH
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> LIGNITE

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 6/15/90 ; PSU

SAMPLE TYPE

-> CHANNEL-WHOLE SEAM

ADDITIONAL INFORMATION

->

MINE INFORMATION:

RESERVES

->

ANNUAL PRODUCTION

-> 9999 THOUSAND TONS

SEAM INFORMATION:

AGE OF SEAM

-> PALEO.

GROUP

->

FORMATION

-> FORT UNION

SEAM THICKNESS

-> 17 FT. 0 IN.

** PENN STATE COAL DATA BASE **
 **
 ** DECS-1*
 **
 ** 02/04/93
 ** PAGE 2
 **

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> NORTH DAKOTA

SAMPLE IDENTIFICATION:

 PSU NUMBER -> DECS-11
 SEAM NAME -> BEULAH
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> LIGNITE

* * * * * C H E M I C A L D A T A * * * * *

PROXIMATE ANALYSIS				DAF	DMMF(PARR)
AS REC'D	DRY				
% MOISTURE	33.38	% EQUILIBRIUM MOISTURE = 35.22			
% ASH	6.37	9.56	MM-FREE = 37.92		
% VOLATILE	37.36	56.08	61.63		
% FIXED CARBON	22.89	34.36	38.37		

ULTIMATE ANALYSIS				DAF	DMMF(PARR)	DRY	ELEMENTAL ANALYSIS	DMMF(MOD.P)	DMMF(DIR.)
AS REC'D	DRY				(10.73%MM)			(10.99%MM)	(%MM)
% ASH	6.37	9.56	73.14	74.10	66.05	% CARBON	74.20		
% CARBON	44.07	66.15	4.46	4.51	3.91	% HYDROGEN	4.39		
% HYDROGEN	2.68 (*)	4.03	1.00	1.01	0.90	% NITROGEN	1.01		
% NITROGEN	0.60	0.90	0.82	20.59	17.76	% ORGANIC SULFUR	0.44		
% TOTAL SULFUR	0.49	0.74	18.62		10.99	% OXYGEN(DIFF)	19.96		
% OXYGEN(DIFF)	12.40 (*)					% MINERAL MATTER (INCL. 0.58% FES2)			

(*)-EXCLUDES MOISTURE

SULFUR FORMS	% PYRITIC	% SULFATIC	% ORGANIC	% TOTAL	DRY % CHLORINE = 0.08	DRY % CO2 = 0.38
DRY	0.31	0.03	0.39	0.74	MOTT-SPOONER DIFFERENCE = 179.	
DAF	0.34	0.03	0.43	0.82		

<u>CALORIFIC VALUE</u> (GROSS, BTU/LB)	<u>DRY</u>	<u>AS REC'D</u> <u>MOIST.</u>	<u>EQUIL.</u> <u>MOIST.</u>	<u>ATOM RATIOS (DMMF)</u>	<u>PARR</u>	<u>MOD. PARR</u>	<u>DIRECT</u>
MM-CONTAINING	11062.	7370.	7166.	ATOMIC H/C	0.7317	0.7114	
MM-FREE (PARR)	12350.	7910.	7676.	ATOMIC O/C	0.2064	0.2019	
MM-FREE (MOD. P)	12409.	7940.	7703.				
NET CV, DMMF BTU/LB	11989.						

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK
COUNTRY
STATE
REPORTED RANK

SAMPLE LOCATION:

DECS-11
BEULAH
LIGNITE

USA
NORTH DAKOTA

RANK CALCULATIONS

APPARENT RANK (AS REC'D MOIST.)
ASTM RANK (EQUIL. MOIST.)
REFLECTANCE RANK CATEGORY

PETROGRAPHIC DATA

MACERAL COMPOSITION (WHITE LIGHT AND FLUORESCENCE ANALYSIS)

DMMF VOL. %
DRY WT. %
DMMF VOL % HUMINITE =
ULMINITE REFLECTANCE DATA:
HIGH: 0.47
LOW: 0.25
MEAN-MAX: 0.35

CASTING AND MECHANICAL PROPERTIES

GIESELER COAL PLASTOMETER:

INIT. SOFTENING TEMP
TEMP. MAX. FLUIDITY
SOLIDIFICATION TEMP.
FLUID TEMP. RANGE
HARDGROVE GRINDABILITY
FREE SWELLING INDEX
VICKERS HARDNESS NUMBER

MAXIMUM FLUIDITY
WASHABILITY DATA AVAILABLE?

PENN STATE COAL DATA BASE
DECS-11
02/04/93
PAGE 3

** PENN STATE COAL DATA BASE **
 **
 ** DECS-11
 **
 ** 02/04/93
 ** PAGE 4

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> NORTH DAKOTA

SAMPLE IDENTIFICATION:

 PSU NUMBER -> DECS-11
 SEAM NAME -> BEULAH
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> LIGNITE

% HTA = 9.41

MAJOR ELEMENT ANALYSIS

	SI02	AL203	TI02	FE203	MGO	CAO	NA2O	K2O	P2O5	S03
OXIDE % OF HTA	11.5	11.1	0.57	9.29	9.94	27.4	9.39	0.59	0.49	18.2
ELEMENT % OF TOTAL DRY COAL	SI	AL	TI	FE	MG	CA	NA	K	P	S
	0.5	0.6	0.03	0.61	0.56	1.8	0.66	0.05	0.02	0.7

% HTA = 9.41

TRACE ELEMENT ANALYSIS

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES PPM
							----- TOTAL COAL
AG					SN		AS
B					SR	8202.	BR
BA	9225.	868.			TH		CD
BE	7.0	0.7	620.	58.	U		CL
BI					V	145.	F
CE					Y		HG
CO			< 25.	< 2.	YB		SB
CR	55.	5.			ZN	120.	SE
CU	95.	9.	25.	2.	ZR	160.	
GA							

** PENN STATE COAL DATA BASE **
 **
 ** DECS-11
 **
 ** 02/04/93
 ** PAGE 5

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> NORTH DAKOTA

SAMPLE IDENTIFICATION:

 PSU NUMBER -> DECS-11
 SEAM NAME -> BEULAH
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> LIGNITE

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2000.	2200.
SOFTENING	2070.	2270.
HEMISPHERICAL	2100.	2330.
FLUID	2140.	2380.

** PENN STATE COAL DATA **
 **
 ** DECS-12
 **
 ** 02/04/93
 ** PAGE 1
 **

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> PENNSYLVANIA
 COUNTY -> GREENE
 TOWNSHIP ->
 CITY -> GRAYSVILLE
 COAL PROVINCE -> EASTERN
 REGION -> APPALACHIAN
 MAP REFERENCE: LATITUDE -> 39 D 55 M 58 S
 LONGITUDE -> 80 D 23 M 59 S
 QUADRANGLE -> WIND RIDGE (7.5')

LIFE EXPECTANCY ->
 MINING METHOD -> UNDERGROUND

SAMPLE IDENTIFICATION:

PSU NUMBER -> DECS-12
 SEAM NAME -> PITTSBURGH
 ALTERNATE SEAM NAME -> #8
 APPARENT RANK -> HVA

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 7/25/90 ; PSU

SAMPLE TYPE -> CHANNEL-WHOLE SEAM
 ADDITIONAL INFORMATION ->

MINE INFORMATION:

RESERVES ->
 ANNUAL PRODUCTION ->

SEAM INFORMATION:

AGE OF SEAM -> PENNSYL.
 GROUP -> MONONGAHELA
 FORMATION ->
 SEAM THICKNESS -> 6 FT. 7 IN.

SAMPLE IDENTIFICATION:-----
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:-----
COUNTRY
STATE

-> DECS-12
-> PITTSBURGH
-> #8
-> HVA

-> USA

-> PENNSYLVANIA

** PENN STATE COAL DATA BASE **
** DECS-12
** 02/04/93
** PAGE 2

***** C H E M I C A L D A T A * * * * *

PROXIMATE ANALYSIS

	AS REC'D	DRY	DAF	DMMF(PARR)
% MOISTURE	2.40			
% ASH	10.00	10.25		
% VOLATILE	35.16	36.02	40.13	39.35
% FIXED CARBON	52.44	53.73	59.87	60.65

% EQUILIBRIUM MOISTURE = 2.88
MM-FREE = 3.26

ULTIMATE ANALYSIS

	AS REC'D	DRY	DAF	DMMF(PARR)	ELEMENTAL ANALYSIS	DRY	DMMF(MOD.P)	DMMF(DIR.)
% ASH	10.00	10.25			(11.69%MM)		(11.88%MM)	(%MM)
% CARBON	72.99	74.78	83.32	84.68	% CARBON	74.69	84.75	
% HYDROGEN	4.99 (*)	5.11	5.69	5.79	% HYDROGEN	4.98	5.66	
% NITROGEN	1.20	1.23	1.37	1.39	% NITROGEN	1.23	1.40	
% TOTAL SULFUR	1.09	1.12	1.25		% ORGANIC SULFUR	0.73	0.83	
% OXYGEN(DIFF)	7.33 (*)	7.51	8.37	8.15	% OXYGEN(DIFF)	6.49	7.37	

(*)-EXCLUDES MOISTURE
% MINERAL MATTER 11.88
(INCL. 0.71% FES2)

SULFUR FORMS

	% PYRITIC	% SULFATIC	% TOTAL
DRY	0.38	0.01	1.12
DAF	0.42	0.01	1.25

DRY % CHLORINE = 0.23 DRY % CO2 = 0.34
MOTT-SPOONER DIFFERENCE = 61.

CALORIFIC VALUE
(GROSS, BTU/LB)

	DRY	AS REC'D MOIST.	EQUIL. MOIST.	ATOM RATIOS (DMMF)	PARR	MOD.PARR	DIRECT
MM-CONTAINING	13532.	13207.	13142.	ATOMIC H/C	0.8208	0.8016	
MM-FREE (PARR)	15259.	14846.	14763.	ATOMIC O/C	0.0722	0.0653	
MM-FREE (MOD. P)	15332.	14916.	14833.				
NET CV, DMMF BTU/LB	14795.						

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-12
-> PITTSBURGH
-> #8
-> HVA

COUNTRY -> USA

STATE -> PENNSYLVANIA

** DECS-12
**
** 02/04/93
** PAGE 3

***** RANK CALCULATIONS *****

APPARENT RANK (AS REC'D MOIST.) -> HVA INTERNATIONAL RANK :
AS REC'D MOIST. ->
ASTM RANK (EQUIL. MOIST.) -> HVA EQUIL. MOIST. ->
REFLECTANCE RANK CATEGORY -> HVA REPORTED RANK : -> HVA

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT ANALYSIS)

	PSEUDO-		SEMI-		SCLERO-		SPOR-		
	VITRINITE	VITRINITE	FUSINITE	FUSINITE	MACRINITE	MICRINITE	TINITE	INITE	
DMMF VOL. %	83.0	0.0	2.7	4.0	1.4	0.8	0.0	5.5	0.0
DRY VOL. %	78.0	0.0	2.5	3.8	1.3	0.8	0.0	5.2	0.0
DRY WT. %	73.0	0.0	2.7	3.8	1.3	0.8	0.0	4.5	0.0
RESINITE									0.0
ALGINITE									0.0
CUTINITE									0.0

REFLECTANCE DATA VITRINITE : HIGH: 0.99 LOW: 0.68 MEAN-MAX: 0.87

VITRINITE TYPES V 6 V 7 V 8 V 9
PERCENT 1.0 6.0 60.0 33.0

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:

INIT. SOFTENING TEMP 387
TEMP. MAX. FLUIDITY 440
SOLIDIFICATION TEMP. 477
FLUID TEMP. RANGE 90
GRAY-KING COKE TYPE
HARDGROVE GRINDABILITY 56.4
FREE SWELLING INDEX 7.5
VICKERS HARDNESS NUMBER

MAXIMUM FLUIDITY 20002
WASHABILITY DATA AVAILABLE? NO

** PENN STATE COAL DATA **
 **
 ** DECS-12
 **
 ** 02/04/93
 ** PAGE 4
 **

SAMPLE LOCATION:

 COUNTRY
 STATE

-> USA
 -> PENNSYLVANIA

SAMPLE IDENTIFICATION:

PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK

-> DECS-12
 -> PITTSBURGH
 -> #8
 -> HVA

MAJOR ELEMENT ANALYSIS

% HTA = 11.89

	SI02	Al2O3	TI02	FE2O3	MGO	CAO	NA2O	K2O	P2O5	S03
OXIDE % OF HTA	55.8	25.8	1.21	6.37	0.91	3.20	0.49	2.19	0.56	2.10
	SI	AL	TI	FE	MG	CA	NA	K	P	S
ELEMENT % OF TOTAL DRY COAL	3.1	1.6	0.09	0.53	0.07	0.27	0.04	0.22	0.03	1.12

TRACE ELEMENT ANALYSIS

% HTA = 11.89

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG					SN		AS	
B					SR	111.	BR	
BA	717.	85.			TH		CD	
BE	8.0	1.0	155.	18.	U		CL	2300.
BI					V	60.	F	
CE					Y		HG	
CO			95.	11.	YB		SB	
CR	180.	21.			ZN	130.	SE	
CU	75.	9.	100.	12.	ZR	200.		
GA								

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> DECS-12
-> PITTSBURGH
-> #8
-> HVA

SAMPLE LOCATION:

COUNTRY
STATE

-> USA
-> PENNSYLVANIA

** PENN STATE COAL DATA BASE **
**
** DECS-12
**
** 02/04/93
** PAGE 5
**

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2225.	2420.
SOFTENING	2330.	2510.
HEMISPHERICAL	2390.	2565.
FLUID	2445.	2600.

END

DATE
FILMED

4 / 7 / 93