Approximate Techniques for Predicting Size Effects on Cleavage Fracture Toughness (J_c)

Manuscript Completed: February 1993
Date Published: July 1993

Prepared by
M. T. Kirk, R. H. Dodds, Jr., University of Illinois

University of Illinois at Urbana-Champaign
Department of Civil Engineering, MC-250
205 North Mathews Avenue
Urbana, IL 61801-2352

Under Contract to:
Naval Surface Warfare Center
Annapolis Detachment, Carderock Division
Code 2814
Annapolis, MD 21402-5067

Prepared for
Division of Engineering
Office of Nuclear Regulatory Research
U.S. Nuclear Regulatory Commission
Washington, DC 20555-0001
NRC FIN B6290

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

for

ABSTRACT

This investigation examines the ability of an elastic T -stress analysis coupled with a modified boundary layer (MBL) solution to predict stresses ahead of a crack tip in a variety of planar geometries. The approximate stresses are used as input to estimate the effective driving force for cleavage fracture (J_o) using the micromechanically based approach introduced by Dodds and Anderson. Finite element analyses for a wide variety of planar cracked geometries are conducted which have elastic biaxiality parameters (β) ranging from -0.99 (very low constraint) to $+2.96$ (very high constraint). The magnitude and sign of β indicate the rate at which crack-tip constraint changes with increasing applied load. All results pertain to a moderately strain hardening material (strain hardening exponent(n) of 10). These analyses suggest that β is an effective indicator of both the accuracy of T - MBL estimates of J_o and of applicability limits on evolving fracture analysis methodologies (i.e. T - MBL , J - Q , and J/J_o). Specifically, when $|\beta| > 0.4$ these analyses show that the T - MBL approximation of J_o is accurate to within 20% of a detailed finite-element analysis. As "structural type" configurations, i.e. shallow cracks in tension, generally have $|\beta| > 0.4$, it appears that only an elastic analysis may be needed to determine reasonably accurate J_o values for structural conditions.

Keywords: Elastic-plastic fracture mechanics, size effects, finite element analysis, modified boundary layer, T -stress, J_{SSY} , J_o , Q , structural integrity assessment.

Contents

Section No.	Page
Abstract	iii
List of Figures	vii
List of Tables	ix
1. INTRODUCTION	1
1.1 Crack–Tip Stress Fields	1
1.2 T and Q as Constraint Parameters	4
1.3 Micromechanical Models for Cleavage Fracture	4
2. T-MBL APPROXIMATION	6
2.1 The Elastic T–Stress	6
2.2 Modified Boundary Layer Model	6
2.3 Approximation of Opening Mode Stresses	6
3. MICROMECHANICS PREDICTIONS OF SIZE EFFECTS ON J_c	8
4. NUMERICAL PROCEDURES	12
4.1 Constitutive Model	12
4.2 Finite Elements and Crack–Tip Modelling	13
4.3 Modified Boundary Layer (MBL) Model	13
4.4 Models of Finite Geometries	15
4.5 Post Processing to Obtain J , CTOD, J_o , and β	15
5. RESULTS AND DISCUSSION	17
5.1 Modified Boundary Layer Solutions	17
5.2 Opening Mode Stresses in Finite Bodies	17
5.3 J_o Estimation Deformation Limits on the Applicability of these Fracture Analysis Methodologies	18
5.4 Deformation Limits on the Applicability of these Fracture Analysis Methodologies	23

6.	SUMMARY AND CONCLUSIONS	26
7.	REFERENCES	27

List of Figures

Figure No.	Page
1 Small scale yield (SSY) model	2
2 Effect of infinite body reference solution on radial independence of Q for an $a/W=0.15$ SE(B) specimen having a Ramberg–Osgood strain hardening exponent (n) of 10	4
3 Schematic illustration of fracture toughness locus constructed in mid–transition using various planar specimen geometries to obtain J_{crit} over a range of constraint conditions	5
4 Relationship between opening mode stress and elastic T –stress quantified by a modified boundary layer model. Similar curves can be constructed at any constant normalized distance, $\mathfrak{R}$, ahead of the crack tip from finite element results	7
5 Conceptual variation of J_o with J for two finite bodies. Horizontal lines (J_o =constant) denote equivalent driving force for cleavage fracture (equivalent stressed volumes) in both bodies	9
6 Effect of applied load on opening mode stresses ahead of a crack in a finite body, after [Kirk and Dodds, 1992]	10
7 Opening mode stresses on the crack plane in SSY for Ramberg–Osgood materials [Kirk and Dodds, 1992]	11
8 Effect of stress errors in estimated opening mode stress on predicted toughness values. These results depend on σ_f^* , however the relative effect of strain hardening (n) is independent of σ_f^*	11
9 Uniaxial stress–strain curve defined by eqn. (10)	14
10 Finite element mesh for double cantilever beam specimen	14
11 Opening mode stresses on the crack plane from modified boundary layer analysis	16
12 Variation of opening mode stress on the crack plane with applied T –stress and distance ahead of the crack tip determined by modified boundary layer analysis	18
13 Comparison of modified boundary layer approximation with opening mode stresses in various planar cracked geometries for an $n=10$, $\sigma_o/E=0.002$ material	19
14 Comparison of modified boundary layer approximation with opening mode stresses in various planar cracked geometries grouped by $ \beta $ values for an $n=10$, $\sigma_o/E=0.002$ material	20
15 Comparison of constraint correction curves for cleavage fracture determined by elastic–plastic finite element analysis with those determined by the T –MBL approximation for an $n=10$, $\sigma_o/E=0.002$ material	21

16	Effect of modified boundary layer stress estimation accuracy on J_o estimation accuracy for an $n=10$, $\sigma_o/E=0.002$ material	22
17	Postulated effect of material strain hardening on the range of biaxiality parameter (β) over which T - MBL J_o estimates have acceptable accuracy	23
18	Deformation limits on the T - MBL approximation for J_o (top graph) and on elastic-plastic finite element calculation of J_o (bottom graph) for an $n=10$, $\sigma_o/E=0.002$ material. Symbols representing specimens of same type are connected by lines. Symbols on top graph marked with asterisks denote deformation when $T/\sigma_o=0.8$. At this deformation the T - MBL approximation has the error given in parenthesis	25

List of Tables

Table No.	Page
1. β values for planar cracked geometries modelled	8

Approximate Techniques for Predicting Size Effects on Cleavage Fracture Toughness (J_c)

1. INTRODUCTION

Numerous experimental studies report an increase of the cleavage fracture toughness, J_c , for steels (e.g. A36, A515, HY-80, A533B) as the crack depth is reduced in SE(B) specimens [Sorem, et al., 1991; Kirk, et al., 1991; Sumpter and Forbes, 1992; Theiss and Bryson, 1991]. Cleavage fracture toughness also increases with the transition from bending to tensile load [Keeney-Walker, et al., 1992]. These increases of J_c develop when the in-plane plastic flow produced by gross deformation of the specimen impinges on the local crack-tip fields. This relaxes the kinematic constraint against further plastic flow. Once the global and local plastic fields interact, the crack-tip stresses and strains no longer increase in proportion to one another with amplitude governed by J alone. At these high deformation levels, equivalence of J (or CTOD) between different cracked geometries does not insure identical crack-tip stress and strain fields. Because the micro-mechanisms of fracture require attainment of critical conditions described in terms of stress and/or strain, different values of applied J may be required to cause fracture in different structures. These interrelated effects of geometry and loading mode on near-tip stresses, near-tip strains, and fracture toughness are referred to collectively as “size effects.” The routinely observed size effects on J_c are actually a size effect on the relation between macroscopic fracture parameters (e.g. J) and micro-scale crack driving force (e.g. opening mode stress). These size effects can be quantified for cleavage fracture by coupling a description of the stress field surrounding the crack tip with appropriate micromechanical failure models. The following sections discuss recent developments in these areas.

1.1 Crack-Tip Stress Fields

Small scale yielding (SSY) conditions exist when the crack-tip plastic zone is infinitesimally small compared to all other characteristic lengths and is embedded within a linear-elastic field. Elastic-plastic crack-tip fields in SSY are generated by applying displacements consistent with the first two terms of the linear elastic crack-tip fields to a circular region containing an edge crack (Figure 1):

$$\begin{aligned} u(r, \theta) &= K_I \frac{1-\nu}{E} \sqrt{\frac{r}{2\pi}} \cos\left(\frac{\theta}{2}\right) (3 - 4\nu - \cos\theta) + T \frac{1-\nu^2}{E} r \cos\theta \\ v(r, \theta) &= K_I \frac{1-\nu}{E} \sqrt{\frac{r}{2\pi}} \sin\left(\frac{\theta}{2}\right) (3 - 4\nu - \cos\theta) - T \frac{\nu(1+\nu)}{E} r \sin\theta \end{aligned} \quad (1)$$

K_I and T are the leading coefficients of an asymptotic expansion for stresses surrounding the crack tip in a two dimensional linear-elastic body:

$$\begin{aligned} \sigma_x &= \frac{K_I}{\sqrt{2\pi r}} f_x(\theta) + T + O(\sqrt{r}) \\ \sigma_y &= \frac{K_I}{\sqrt{2\pi r}} f_y(\theta) + O(\sqrt{r}) \\ \tau_{xy} &= \frac{K_I}{\sqrt{2\pi r}} f_{xy}(\theta) + O(\sqrt{r}) \end{aligned} \quad (2)$$

Figure 1: Small scale yield (SSY) model.

Here r is the radial distance from the crack tip, K_I is the stress intensity factor, and T is the stress parallel to the crack over vanishingly small r . All remaining terms are defined in Figure 1. The truncated terms in eqn. (2) are of order $\sqrt{r}$ or higher and consequently approach zero as $r \rightarrow 0$. Thus, K and T alone control the stress state in the near vicinity of the crack tip under SSY conditions.

Rice and Tracy [1968] and McMeeking [1977] originally proposed the model depicted in Figure 1, with $T=0$, as a boundary layer solution of the infinite body, single-ended crack problem. For this special case, the single parameter J both sets the size scale over which large deformations develop *and* describes the magnitude of stresses near the crack tip but outside of the finite deformation zone. The HRR field equations quantify the relation between J and crack-tip stresses and strains in an infinite body made of incompressible, fully plastic power-law hardening material [Hutchinson, 1968; Rice and Rosengren, 1968].

Larsson and Carlsson [1973] *modified* the boundary layer (*MBL*) solution by applying non-zero T stresses to approximate the effects of finite size on crack-tip region deformation and plastic flow. The $T=0$ (infinite body) solution is one of a family of SSY solutions generated by changing the magnitude of the T -stress applied to the *MBL* model. Larsson and Carlsson found a marked influence of the the sign and magnitude of the T -stress on the size and shape of the crack-tip plastic zone. More recent investigations by both Hancock and Parks (and co-workers) [Al-Ani and Hancock, 1991; Bertegon and Hancock, 1991; Sumpter and Hancock, 1991; Parks, 1991; Du and Hancock, 1991; Wang, 1991(a); Wang, 1991(b)] demonstrate a strong influence of T -stress on opening mode stresses near the crack tip. Positive T stresses slightly elevate the opening mode stresses relative to the $T=0$ condition while negative T -stresses reduce significantly the opening mode stress. Despite this influence on near-tip stresses, the T -stress has no effect on J because T is non-singular. These findings demonstrate the inadequacy of J as the sole descriptor of deformation near a crack tip in finite geometries, which generally have non-zero T .

O'Dowd and Shih [1991, 1992] propose a two-parameter theory which describes crack-tip fields in finite geometries ($T \neq 0$). They describe stresses surrounding a crack tip in terms of J plus an additional parameter Q :

$$\frac{\sigma_{ij}}{\sigma_o} = \left(\frac{J}{\alpha \varepsilon_o \sigma_o J_n r} \right)^{\frac{1}{n+1}} \tilde{\sigma}_{ij}(\theta; n) + Q \left(\frac{r}{J/\sigma_o} \right)^q \hat{\sigma}_{ij}(\theta; n) \quad (3)$$

Here, J sets the size scale over which large deformations develop while Q quantifies the opening stress magnitude. O'Dowd and Shih found by analysis of the *MBL* model that (1) the power on the radial coefficient in the second term (q) is approximately zero for $n \geq 4$, (2) for $|\theta| \leq 90^\circ$ the second-order normal stresses ($\hat{\sigma}_{rr}$ and $\hat{\sigma}_{\theta\theta}$) are approximately equal, and (3) the second-order shear stress ($\hat{\sigma}_{r\theta}$) is approximately zero. Thus, Q is the amplitude of a hydrostatic, or tri-axiality term. Based on these observations, eqn. (3) simplifies to:

$$\frac{\sigma_{ij}}{\sigma_o} = \left(\frac{J}{\alpha \varepsilon_o \sigma_o J_n r} \right)^{\frac{1}{n+1}} \tilde{\sigma}_{ij}(\theta; n) + Q \delta_{ij} \quad \text{for } |\theta| \leq 90^\circ \quad (4)$$

Equation (4) expresses normal stresses in finite bodies as the infinite body HRR solution [Hutchinson, 1968; Rice and Rosengren, 1968] plus an additive constant (Q) which is independent of radial distance from the crack tip. Numerical studies reveal that this model is adequate for deformation up to some geometry dependent limit, beyond which Q becomes radially dependent. Dependence of Q on distance from the crack tip introduces ambiguity into the selection of a Q value to parameterize constraint effects on fracture toughness. Selection of an arbitrary location at which to calculate Q implies knowledge of the critical distance for cleavage fracture which a pure mechanics approach, such as the J - Q theory, seeks to avoid. However, use of an alternative infinite body reference solution improves the radial independence of Q and, thereby, the robustness of the J - Q theory. Figure 2 shows that Q values referenced to a full-field infinite body solution (i.e. $SSY T=0$) remain radially independent to much larger deformations than those referenced to an infinite body solution which includes only the singular term (i.e. HRR). Equation (4) is altered to reflect this change of reference solution:

$$\sigma_{ij} = \sigma_{ij}|_{SSY, T=0} + Q \sigma_o \delta_{ij} \quad (5)$$

Under *SSY* conditions, T relates uniquely to Q . Analysis of cracks in finite bodies [O'Dowd and Shih, 1992] reveals that eqn. (5) accurately describes the departure of stresses near the crack tip from the *SSY* family of solutions well into large scale yielding (*LSY*). Thus, Q remains a descriptor of crack-tip stresses at deformation levels beyond those for which T can be defined. However, Figure 2 demonstrates that the crack-tip fields in finite bodies lose self-similarity with the *SSY* $T=0$ reference solution at high load levels. Once self-similarity with the infinite body reference solution is lost, the conditions for fracture in a finite body depend on characteristics unique to that body. These conditions cannot be parameterized currently within the context of any two-parameter theory.

Figure 2: Effect of infinite body reference solution on radial independence of Q for an $a/W=0.15$ SE(B) specimen having a Ramberg–Osgood strain hardening exponent (n) of 10.

1.2 T and Q as Constraint Parameters

The linkage of T (in SSY) and of Q (in SSY and LSY) with crack-tip stress state motivates the use of Q and T to parameterize constraint effects on fracture toughness data. Several investigators have generated fracture toughness loci [Sumpter and Hancock, 1991; Kirk, et al., 1991; Sumpter and Forbes, 1992], J_{crit} vs. Q or J_{crit} vs. T , as depicted schematically in Figure 3. However, this approach greatly complicates the determination of fracture toughness; it necessitates conducting difficult experiments with low constraint geometries (e.g. shallow cracks in bending, cracks in tension) to fully define the fracture toughness locus.

Considerable debate surrounds the application of T as a constraint parameter under LSY conditions rather than Q . The T approach has the advantage of simplicity relative to Q , requiring only a linear-elastic analysis rather than an elastic-plastic analysis of the cracked structure. Under moderate to large scale yielding, the relations between T and the opening mode stresses become geometry dependent. At these deformation levels, opening mode stresses predicted by T only approximate the full elastic-plastic solution quantified by Q . However, several numerical studies show that the T -MBL approximation predicts stresses to within 10% of finite body calculations even for very large deformations.

1.3 Micromechanical Models for Cleavage Fracture

Dodds and Anderson [Dodds, et al., 1991; Anderson and Dodds, 1991, Kirk and Dodds, 1992] combine the computation of stresses near the crack tip with the micromechanical conditions for cleavage fracture (achievement of a critical stress over a critical volume [Ritchie, et al., 1973]) to predict the conditions for cleavage fracture in one geometry based on toughness data

Figure 3: Schematic illustration of fracture toughness locus constructed in mid-transition using various planar specimen geometries to obtain J_{crit} over a range of constraint conditions.

from another. Experimental data for several steels including mild steel, A36, and A515 in low to mid transition demonstrate the validity of this approach [Sorem, et al., 1991; Kirk, et al., 1991; Sumpter and Forbes, 1992]. For stress controlled cleavage fracture, this micromechanical approach greatly reduces the experimentation needed to define the toughness locus; a considerable simplification over parameterizing constraint effects by either Q or T . The micromechanical approach requires detailed resolution of crack-tip fields which, until now, have been obtained by very detailed elastic-plastic finite element analysis. The determination of Q requires computations of equivalent detail. This complication makes such approaches unattractive for routine application to structural fracture safety analysis at this time. In this investigation, the possibility of using the elastic T -stress approximations of crack-tip stress distributions as input to the micromechanics analysis is investigated to determine if predictions of size effects having engineering accuracy can be obtained without a detailed elastic-plastic analysis of each configuration considered.

2. T-MBL APPROXIMATION

Two analyses are needed to couple remotely applied load to opening mode stresses near the crack tip:

1. An elastic analysis of the cracked structure that relates applied load to T -stress.
2. An elastic-plastic analysis of the MBL model that relates T -stress to opening mode stresses near the crack tip.

The synthesis of these two analyses to approximate opening mode stresses in finite bodies is referred to as the T - MBL approximation.

2.1 The Elastic T -Stress

The T -stress (eqn. (2)) is the non-singular elastic stress acting parallel to the crack over vanishingly small r . T -stress values for various geometries are frequently reported in the literature, usually as a non-dimensional ratio with K :

$$\beta = \frac{T\sqrt{\pi a}}{K} \quad (6)$$

where β is referred to as a *biaxiality* parameter which is a constant for a given geometry and loading mode. The various techniques used to compute T , and thereby β , include boundary collocation, second order weight functions, and domain interaction integrals [Leevers and Radon, 1982; Kfoury, 1986; Sham, 1991; Nakamura and Parks, 1992].

2.2 Modified Boundary Layer Model

Details of the MBL model were presented in Section 1.1. Displacements are applied to the MBL model consistent with the first two terms (i.e. K and T) of the linear solution. Elastic-plastic finite element analysis of the model provides a family of full field SSY solutions parametric in T/σ_o . Conditions are achieved wherein stresses and strains at all angles scale with $r/(J/(\sigma_o \epsilon_o a))$, as do the HRR fields. The fields remain self-similar until the plastic zone size becomes a significant portion of the modelled domain radius, $\approx 10\%$, at which point it senses the finite boundary. Figure 4 schematically depicts the results of such an analysis. The C_i coefficients are determined by curve fitting the finite element results at various normalized distances ahead of the crack tip.

2.3 Approximation of Opening Mode Stresses

The effect of finite size on opening mode stress near the crack tip is computed by combining the information discussed in the preceding sections. First, an elastic analysis of the cracked geometry is performed to determine K , T , and β . The variation of T with load is determined from eqn. (6) as follows:

$$\frac{T}{\sigma_o} = \frac{\beta K}{\sigma_o \sqrt{\pi a}} \quad (7)$$

These elastic T -stress and K values are inserted into the MBL solution (Figure 4) to determine the variation of opening mode stress near the crack tip with applied loading:

$$\frac{\sigma_{yy}}{\sigma_o} = \sum_{i=0}^n C_i \left(\frac{\beta K}{\sigma_o \sqrt{\pi a}} \right)^i \quad (8)$$

Equation (8) couples the far-field elastic solution with near-tip stresses. The applied load enters this approximation through K while β characterizes geometry. Moreover, β controls the direction and rate at which increasing load causes deviation of near-tip stresses from the $T=0$ limit. Three examples indicate potential limitations on the applicability of this approximation.

1. $\beta > 0$ (high constraint): Equation (8) predicts a continuous increase of normalized opening mode stress with increasing load. This can lead to unrealistic predictions – consider the rectangular double cantilever beam specimen ($a/W=0.5$, $H/W=2.5$, $\beta=2.96$ [Leevers and Radon, 1982]). At some load the arms of this specimen must form plastic hinges which reduce opening mode stress significantly below the T -MBL prediction.
2. $\beta = 0$ ($T \equiv 0$): Equation (8) predicts that normalized opening mode stresses remain constant independent of the applied load, i.e. the constraint remains constant at the $T=0$ level. Consider a SE(B) with $a/W=0.39$ which has $\beta=0$ [Leevers and Radon, 1982]. A plastic hinge must form at some load. After hinge formation, plastic flow is no longer contained and opening mode stresses must fall as a consequence.
3. $\beta < 0$ (low constraint): Equation (8) predicts the continuous decrease of normalized opening mode stress with increasing load. This behavior is observed in analyses of finite bodies. Two-dimensional cracked geometries having $\beta < 0$ include tension loaded central cracks, tension loaded edge cracks ($a/W < 0.60$), edge cracks loaded in bending ($a/W < 0.39$), and double edge cracks. This class of problems also includes the particularly important case of semi-elliptical surface cracks loaded in tension.

Figure 4: Relationship between opening mode stress and elastic T -stress quantified by a modified boundary layer model. Similar curves can be constructed at any constant normalized distance, $\mathcal{R}$, ahead of the crack tip from finite element results.

3. MICROMECHANICS PREDICTIONS OF SIZE EFFECTS ON J_c

For steels operating at temperatures where cleavage occurs after significant plastic deformation but before the initiation of ductile growth (lower to mid-transition), attainment of a critical stress over a microstructurally relevant volume is an appropriate micro-mechanical failure criteria [Ritchie, et al., 1973]. Important classes of engineering structures can fail by this mechanism, including high strength rails, offshore oil platforms, ships, pipelines storage tanks, and nuclear pressure vessels after years of neutron irradiation embrittlement. Dodds and Anderson [Dodds, et al., 1991; Anderson and Dodds, 1991, Kirk and Dodds, 1992] show that, by quantifying the effects of finite size on micro-scale / macro-scale crack driving force relations, the apparent effect of size on fracture toughness can be rigorously predicted without resort to empirical arguments. These size effects become steadily more pronounced as load increases due to the deviation of crack-tip region deformations from the $SSY (T=0)$ conditions essential for SPFM to apply. Once SPFM becomes invalid, a micro-mechanics failure criteria is required to establish the geometry invariant conditions at fracture. Finite element analysis provides a means to quantify the geometry dependent relations between these conditions and macro-scale crack driving force. This permits (in principle) prediction of fracture in any body from toughness values measured using standard specimens.

Although cleavage is driven by stress and stressed volume, the difficulty of measuring critical values of these parameters dictates that fracture driving force, and thereby critical fracture conditions, be expressed in terms of more easily measured macroscopic parameters (e.g. J). Thus, an effective macroscopic driving force for cleavage fracture (J_o) can be defined as follows:

J_o is the J to which the infinite body ($T=0$, MBL model) must be loaded to achieve the same stressed volume, and thereby the same driving force for cleavage fracture, as in a finite body.

Early papers on this topic employed the notation J_{SSY} instead of J_o . The notation is changed here to emphasize that the infinite body reference configuration is $T=0$.

The variation of J_o with J is depicted schematically for two finite bodies in Figure 5. Upon initial loading of a finite body, crack-tip plasticity is well contained within a surrounding elastic field. Crack-tip conditions are well approximated by $T=0$ and, up to some geometry dependent deformation level, $J_o \approx J_{Finite Body}$. Subsequent interaction of plasticity at the crack tip with plasticity resulting from overall deformation of the structure relaxes the kinematic constraint against plastic flow at the crack tip, thus reducing the stresses in the crack-tip region below what they are for $T=0$ at the same J . This reduces the micro-scale driving force for cleavage. Consequently, the finite body requires more applied- J to achieve the same conditions for cleavage (same stressed volume) as in the infinite body. This finite size effect on crack-tip stress fields differs for different geometries constructed from the same material; it is indicated by deviation from the 1:1 slope in Figure 5. Information of this type is useful for both analysis of fracture test data and for assessing the defect integrity of structures. Path A-B-C on Figure 5 illustrates the procedure to remove geometric dependencies from experimental cleavage fracture toughness (J_c) data by determining the geometry independent cleavage fracture toughness (J_o) corresponding to a measured J_c value. Alternatively, Figure 5 permits determination of the effective driving force for cleavage fracture produced by structural loading to a certain $J_{Applied}$ value (path E-D-C).

Figure 5: Conceptual variation of J_o with J for two finite bodies. Horizontal lines ($J_o = \text{constant}$) denote equivalent driving force for cleavage fracture (equivalent stressed volumes) in both bodies.

J_o is estimated from opening mode stresses acting on the plane directly ahead of the crack tip [Dodds, et al., 1991]. The variation of these stresses with distance from the crack tip is illustrated schematically in Figure 6. Here, finite body stresses are normalized by the stress that occurs in the $T=0$, *MBL* solution at the same normalized distance ahead of the crack tip (same $r/(J/(\alpha\sigma_o\epsilon_o))$) when loaded to the same J as the finite body, i.e. $J_o \equiv J$. Previous studies show that finite body stresses remain self-similar to the $T=0$ *MBL* solution, as indicated by the radial independence of the normalized stresses in Figure 6, to deformation levels greatly exceeding those at which SPFM breaks down [Dodds, et al., 1991]. J_o is calculated for each line on this graph as the J value required in the $T=0$ *MBL* solution to achieve the same opening mode stress as in the finite body. In practice, equivalence of stresses is forced at a single location ahead of the crack tip. This corresponds to selecting the critical microstructural distance (l_o^*) in the Ritchie–Knott–Rice model [Ritchie, et al., 1973]. However, self-similarity between the *SSY* and finite body stress distributions makes the specific location selected unimportant over a wide range of deformation. J_o values are independent of the critical distance selected over a range of distances that encompasses fractographically determined l_o^* values [Herrens and Read, 1988; Miglin, et al., 1990]. This ability to determine J_o irrespective of the actual l_o^* value relies on self-similar stress distributions around the crack in finite and infinite bodies.

Previous investigations [Dodds, et al., 1991; Anderson and Dodds, 1991, Kirk and Dodds, 1992] employed very detailed elastic–plastic finite element analysis to quantify the effects of finite geometry and load level on opening mode stresses. The cost and time required to implement this approach make it unattractive for routine application. Conversely, opening mode stresses determined by the T -*MBL* approximation require only an elastic analysis of the cracked structure. However, this approximation is not exact for *LSY*. Previous investigators report differences of $\approx 10\%$ between the T -*MBL* approximation and opening mode stresses from full finite body calculations. These small errors are misleading due to the considerable

influence they exert on J_o . The effect of stress errors on J_o is quantified by assuming that the stress distribution ahead of the crack tip in a finite body is self-similar to that characteristic of $T=0$ over some range of loading, an assumption justified by reference [Dodds, et al., 1991]. Kirk and Dodds [1992] report $T=0$ solutions for a wide range of strain hardening coefficients, some of which are reproduced in Figure 7. The effect of errors in the opening mode stress at cleavage fracture on J_o can be calculated from these results using the following equation:

$$\frac{J_o|_{T-MBL}}{J_o} = \frac{\bar{r} \left(\frac{\sigma_f^*}{\sigma_o}, n \right)}{\bar{r}_{T-MBL} \left(\frac{\sigma_f^*}{\sigma_o} (1 - \xi), n \right)} \quad (9)$$

where

$\bar{r}$ $r/(J/(\sigma_o \epsilon_o \alpha))$

σ_f^* cleavage fracture stress

ξ percentage by which opening mode stress estimated by eqn. (8) and actual opening mode stress differ

Figure 8 shows that small errors in the estimated opening mode stress have proportionately greater effects on J_o , particularly for materials that do not strain harden appreciably. This example demonstrates that the seemingly small stress errors typically attributed to T - MBL approximations produce unacceptably large variations in J_o . As toughness, not stress, is the quantity used when assessing structural fracture integrity, the ability of the T - MBL approximation to correctly predict the effect of constraint on the effective driving force for cleavage fracture (J_o) is quantified in this study.

Figure 6: Effect of applied load on opening mode stresses ahead of a crack in a finite body, after [Kirk and Dodds, 1992].

Figure 7: Opening mode stresses on the crack plane in SSY for Ramberg–Osgood materials [Kirk and Dodds, 1992].

Figure 8: Effect of stress errors in estimated opening mode stress on predicted toughness values. These results depend on σ_f^* , however the relative effect of strain hardening (n) is independent of σ_f^* .

4. NUMERICAL PROCEDURES

Two-dimensional, plane-strain finite element analyses of the *MBL* model and of numerous finite cracked geometries are performed to obtain detailed resolution of stresses in the crack-tip region and to determine how they change with loading. Table 1 lists the planar geometries studied along with their β values, which range from -0.99 (very low constraint) to $+2.96$ (very high constraint). These analyses permit assessment of the range of conditions over which the *T-MBL* approximation provides J_o estimates of acceptable accuracy. Conventional small strain theory is employed throughout. These analyses are conducted using the POLO-FINITE analysis software [Dodds and Lopez, 1985] on an engineering workstation.

4.1 Constitutive Model

Uniaxial stress-strain behavior is described using a linear / power law model (see Figure 9) proposed by Wang [1991(a), 1991(b)]:

$$\begin{aligned}
 \text{Linear Region:} \quad & \frac{\varepsilon}{\varepsilon_o} = \frac{\sigma}{\sigma_o} && \text{for } \frac{\sigma}{\sigma_o} < L_1 \\
 \text{Transition Region:} \quad & \frac{\varepsilon}{\varepsilon_o} = \varepsilon_{Nc} - \sqrt{r_{Nc}^2 - \left(\frac{\sigma}{\sigma_o} - \sigma_{Nc}\right)^2} && \text{for } L_1 \leq \frac{\sigma}{\sigma_o} \leq L_2 \\
 \text{Power-Law Region:} \quad & \frac{\varepsilon}{\varepsilon_o} = \left(\frac{\sigma}{\sigma_o}\right)^n && \text{for } \frac{\sigma}{\sigma_o} > L_2
 \end{aligned} \tag{10}$$

where σ_o is the reference stress (0.2% offset yield), $\varepsilon_o = \sigma_o/E$ is the reference strain, and n is the strain hardening coefficient for the power-law region. The remaining parameters are defined in Figure 9. Values representing a moderately strain hardening material are used: $n = 10$, $\sigma_o = 60$ ksi, $E = 30000$ ksi, $\varepsilon_o = 0.002$, and $L_1 = 0.95$. This constitutive model is adopted rather than the conventional Ramberg-Osgood description to ensure that *SSY* conditions are maintained in the *MBL* model even for applied *T*-stresses near the yield stress. A transition region consisting of a circular arc between the linear and power-law regions makes the tangent modulus a smooth, continuous function of equivalent strain.

J_2 deformation plasticity theory (i.e. nonlinear elasticity) describes the multi-axial material behavior. By using an effective stress defined from the von Mises yield function and an effective strain defined from the Prandtl-Reuss relations, the total stress components are expressed in terms of total strain components:

$$\frac{\sigma_{ij}}{\sigma_o} = \frac{1}{3(1-2\nu)} \frac{\varepsilon_{kk}}{\varepsilon_o} \delta_{ij} + \frac{2}{3} \frac{\sigma_e/\sigma_o}{e_e/\varepsilon_o} \frac{e_{ij}}{\varepsilon_o} \tag{11}$$

where ε_{kk} is the trace of the stress tensor, δ_{ij} is the Kronecker delta, and the effective stress and strain are defined by

$$\sigma_e^2 = \frac{1}{2}[(\sigma_{11} - \sigma_{22})^2 + (\sigma_{22} - \sigma_{33})^2 + (\sigma_{33} - \sigma_{11})^2 + 6(\sigma_{12}^2 + \sigma_{23}^2 + \sigma_{13}^2)] \quad (12)$$

$$e_e^2 = \frac{2}{9}[(\varepsilon_{11} - \varepsilon_{22})^2 + (\varepsilon_{22} - \varepsilon_{33})^2 + (\varepsilon_{33} - \varepsilon_{11})^2 + \frac{3}{2}(\gamma_{12}^2 + \gamma_{23}^2 + \gamma_{13}^2)] \quad (13)$$

Table 1: β values for planar cracked geometries modelled.									
	a/W	H/W	Loaded by	β		a/W	H/W	Loaded by	β
SE(B)	0.05	N/A	Traction	-0.415	DB(T)	0.25	0.40	Traction	+1.578
	0.15			-0.296		0.50	0.40		+2.956
	0.25			-0.178		0.50	1.00		+0.899
	0.391			-0.006	SE(T)	0.025	2.50	Displ.	-0.460
	0.50			+0.137		0.20	5.00	Displ.	-0.415
	0.70			+0.410		0.391	2.25	Traction	-0.283
	0.90			+1.180		0.50	2.25	Traction	-0.148
DE(T)	0.70	2.25	Traction	-0.423	M(T)	0.70	2.25	Traction	+0.218
	0.90	2.25		-0.273		0.025	2.50	Displ.	-0.994
β calculation by collocation							0.20		5.00

4.2 Finite Elements and Crack-Tip Modelling

Eight noded, plane-strain isoparametric quadrilateral elements are used throughout. Reduced (2 x 2) Gaussian integration eliminates locking of the elements under incompressible plastic deformation. The crack-tip elements are collapsed into wedges with the initially coincident nodes left unconstrained to permit development of crack-tip blunting deformations. The side nodes of these elements are retained at the mid-point position. This modelling technique produces a $1/r$ strain singularity, appropriate in the limit of perfect plasticity.

4.3 Modified Boundary Layer (MBL) Model

A circular domain of outer radius R that contains a sharp crack tip at $r=0$ is modelled using finite elements (see Figure 1). Symmetrical boundary conditions are enforced on the crack plane. The mesh contains 3109 nodes and 986 elements divided into seventeen equally sized wedges of elements in the θ direction. Each wedge contains 58 elements whose radial dimension decreases geometrically with decreasing distance to the crack tip. Elements incident on the crack tip have a side length of $R/530000$. Displacement increments of the 2-term elastic field, eqn. (14), are imposed on the outer circular boundary:

$$\begin{aligned} \Delta u(r, \theta) &= \Delta K_I \frac{1-\nu}{E} \sqrt{\frac{r}{2\pi}} \cos\left(\frac{\theta}{2}\right) (3 - 4\nu - \cos \theta) + T \frac{1-\nu^2}{E} r \cos \theta \\ \Delta v(r, \theta) &= \Delta K_I \frac{1-\nu}{E} \sqrt{\frac{r}{2\pi}} \sin\left(\frac{\theta}{2}\right) (3 - 4\nu - \cos \theta) - T \frac{\nu(1+\nu)}{E} r \sin \theta \end{aligned} \quad (14)$$

Displacements generating the full magnitude of the T -stress are applied first. Thereafter, loading occurs by displacements corresponding to increments of applied- K until the plastic

zone radius is 10% of R . At this point, J calculated by the domain integral technique over rings embedded within the plastic zone differ from the applied $J(=K^2(1-\nu^2)/E)$ by less than 0.1%, indicating that SSY conditions prevail. The deformation plasticity constitutive model ensures that load sequence does not influence the computed results. Application of the full T -stress first followed by K leads to more rapid convergence of the nonlinear solution and enables verification of the self-similarity of the stresses at all K levels.

Figure 9: Uniaxial stress-strain curve defined by eqn. (10).

Figure 10: Finite element mesh for double cantilever beam specimen.

4.4 Models of Finite Geometries

Finite element models are constructed for each cracked geometry listed in Table 1. A semi-circular core of elements surrounds the crack tip in all models. This core consists of eight equally sized wedges of elements in the θ direction. Each wedge contains 30 quadrilateral elements whose radial dimension decreases geometrically with decreasing distance to the crack tip. Crack-tip element size ranges from 0.003% to 0.22% of the crack depth depending on the crack depth modelled. All models exploit symmetry conditions where possible. Model size ranges from 343 elements / 1150 nodes for the 0.5 a/W DB(T) to 1735 elements / 5482 nodes for the 0.2 a/W SE(T) and M(T). Figure 10 illustrates a typical model.

Tension geometries are loaded by either uniform tractions or by uniform displacements applied normal to the crack plane on the remote end of the specimen. Loading by applied displacements maintains better control of the solution near the limit state for shallow cracks. SE(B) specimens are loaded by distributing uniform tractions over two small elements at the center of the compression face to eliminate the local singularity effects caused by a concentrated nodal load. DB(T) specimens are loaded by a uniform shear force applied normal to the crack plane along the centerline of the pin location in a mechanical test specimen.

4.5 Post Processing to Obtain J , CTOD, J_o , and β

The J -integral is computed at each load step using a domain integral method [Li, et al., 1985; Shih, et al., 1986]. J values calculated over domains adjacent to and remote from the crack tip are within 0.003% of each other, as expected for deformation plasticity combined with these detailed meshes. CTOD is defined by the blunted shape of the crack flanks using the $\pm 45^\circ$ intercept procedure. J_o is estimated by iteratively solving the following equation using a non-linear root finder [Johnson and Riess, 1982]:

$$\log \left[\frac{\sigma_{yy}|_{FB}}{\sigma_o} \right] = G_0 + G_1 R + G_2 R^2 + G_3 R^3 + G_4 R^4 \text{ for } 0.00085 < R < 0.1073 \quad (15)$$

where,

$\sigma_{yy}|_{FB}$ finite body stress at $r = 2J_{Applied}/\sigma_o$

R $\log[r_{crit}/(J_o/(\sigma_o \epsilon_o))]$

r_{crit} $2J_{Applied}/\sigma_o$

$J_{Applied}$ J applied to the finite body as computed by the domain integral technique

G_0 -1.03137 G_3 -0.33021

G_1 -2.14688 G_4 -0.03401

G_2 -1.21929

This functional form is adopted solely for convenience, i.e. a simple closed-form fit to the $T=0$ MBL solution. The fit applies to a linear power law material, eqn. (10), with a strain hardening coefficient of 10.

The biaxiality parameter β is determined by using nodal displacements from a linear analysis of each model as input to a least-squares solution for the first twelve terms of a Westergaard series expansion. Barker employed the least-squares procedure to extract the stress

intensity factor from experimental Moré or speckle interferometry data [Barker, et al., 1983]. For computation of β , nodal displacements are extracted from an annular region surrounding (but excluding) the crack tip having an outer radius $\leq 0.9a$. β is calculated by eqn. (6) as the normalized ratio of the first two series coefficients (K and T). Generally estimates of β stabilize once the number of nodal displacement conditions exceeds 40 times the number of terms in the series. β values calculated by this technique compare favorably with those reported elsewhere [Leevers and Radon, 1982, Kfoury, 1986; Sham, 1991]. All β values reported in Table 1 are calculated in this manner.

Figure 11: Opening mode stresses on the crack plane from modified boundary layer analysis

5. RESULTS AND DISCUSSION

5.1 Modified Boundary Layer Solutions

Figure 11 shows the variation of opening mode stress in the *MBL* solution with distance ahead of the crack tip for different applied *T*-stresses. Negative *T* values decrease significantly the opening mode stresses below those for *T*=0 while positive *T* values elevate slightly opening mode stresses. Approximations for crack plane stresses in finite bodies are constructed from these stress distributions by taking vertical cuts at different $r/(J/\sigma_o)$ values to obtain a relation between elastic *T*-stress and opening mode stress (Figure 12). The curve fit to these results for $r/(J/\sigma_o) = 2$ facilitates comparison of this *T-MBL* approximation to finite body stresses. Comparison at other normalized distances produces similar conclusions.

5.2 Opening Mode Stresses in Finite Bodies

Figure 13 compares opening mode stresses in various finite bodies to those predicted by the *T-MBL* approximation at $r/(J/\sigma_o) = 2$. On these figures, the zero-load condition for all finite body results occurs at $T=0$, $\sigma_{yy}/\sigma_o=3.43$ (i.e. the infinite body result). As the applied load increases, the symbols representing each finite geometry depart from this initial point. Mesh refinement limits the ability to accurately resolve near-tip stresses below a certain load, thus some geometries have no results near this initial point. The *T-MBL* approximation accounts for only those finite geometry effects contained in the second term (*T*) of the series expansion for stresses near the crack tip in a linear elastic body. Under *SSY* this is the only geometry effect so the *T-MBL* approximation is always accurate over some initial loading range. As load increases, plastic-flow breaks to a free surface in some geometries. Un-contained yielding, not accounted for by the *T-MBL* approximation, relieves stresses at the crack tip causing them to drop below the *MBL* solution. On Figure 13, finite body results are plotted until the applied deformation becomes so extensive that the stress distribution loses self-similarity with the reference $T=0$ distribution. This loss of self-similarity causes ambiguity in computed J_o values, indicating that toughness values can no longer be scaled between geometries without regard of the location of cleavage fracture initiation. An operational definition for the breakdown of self-similarity is made as the deformation beyond which J_o values calculated at $r/(J/\sigma_o) = 1.5$ and at $r/(J/\sigma_o) = 4$ differ by more than $\pm 10\%$ of their average value.

The results in Figure 13 show that the *T-MBL* approximation generally differs by less than 10% from the results of a full elastic-plastic analysis of the finite body. However, in certain geometries differences between the *T-MBL* approximation and finite body results due to *LSY* do not appear significant until near or after self-similarity breaks down. The *T-MBL* approximation for these specimens is much more accurate than it is for the totality of cases considered. Figure 14 re-groups the data presented in Figure 13 by β value rather than by specimen type. Three categories emerge:

1. $|\beta| > 0.9$ *T-MBL* stress approximation within 1.5% of finite body results
2. $|\beta| > 0.4$ *T-MBL* stress approximation within 3.0% of finite body results
3. $|\beta| < 0.4$ *T-MBL* stress approximation within 17.5% of finite body results

Errors associated with very deep cracks ($a/W > 0.7$) are ignored in establishing these limits. These cases are unimportant in engineering practice. While Category 3 errors do not seem un-

Figure 12: Variation of opening mode stress on the crack plane with applied T -stress and distance ahead of the crack tip determined by modified boundary layer analysis.

reasonably large, the effects of small stress errors become magnified when calculating J_o . It is encouraging that “structural type” configurations, i.e. shallow cracks in tension, fall mostly in Category 1 and 2. This suggests the possibility of estimating, with acceptable accuracy, the effective driving force for cleavage fracture, J_o , based only on elastic analysis. However, “test specimen” configurations fall mostly in Category 3 where the T -MBL approximation displays limited accuracy. Fortunately, many detailed analyses of test specimen geometries have been reported in the literature, making the availability of accurate approximate techniques less important.

5.3 J_o Estimation

Figure 15 shows the variation of J_o with J estimated by the T -MBL approximation for one geometry in each Category established in Section 5.2. The reference curves shown on each figure are determined by elastic-plastic finite element analysis. Because J is proportional to crack plane stresses raised to a power, the T -MBL estimates are quite accurate if stress errors are small ($|\beta| > 0.9$). However, the stress errors for $|\beta| < 0.4$ produce large errors in the predicted J_o . These effects are illustrated in Figure 16. Use of T -MBL estimates of stress to calculate J_o by eqn. (15) magnifies stress errors by seven to twelve fold. These results permit development of limits that must be imposed on T -MBL errors in stress to keep estimates of J_o sufficiently accurate. For example, stress errors must be below 1.5% to insure J_o values accurate to within $\pm 10\%$. Only geometries having $|\beta| > 0.9$ satisfy this requirement. Alternatively, stress errors below 3% (i.e. specimens with $|\beta| > 0.4$) produce J_o estimates accurate to within $\pm 20\%$. These error limits on J_o are defined here only to illustrate that the T -MBL approximation is much more accurate for certain geometries (high $|\beta|$) than for others (low $|\beta|$). Acceptable limits on J_o error need to take account of the relation between J_o and J for the particular

Figure 13: Comparison of modified boundary layer approximation with opening mode stresses in various planar cracked geometries for an $n=10$, $\sigma_0/E=0.002$ material.

Figure 14: Comparison of modified boundary layer approximation with opening mode stresses in various planar cracked geometries grouped by $|\beta|$ values for an $n=10$, $\sigma_o/E=0.002$ material.

Figure 15: Comparison of constraint correction curves for cleavage fracture determined by elastic-plastic finite element analysis with those determined by the T -MBL approximation for an $n=10$, $\sigma_o/E=0.002$ material.

Figure 16: Effect of modified boundary layer stress estimation accuracy on J_0 estimation accuracy for an $n=10$, $\sigma_o/E=0.002$ material.

Figure 17: Postulated effect of material strain hardening on the range of biaxiality parameter (β) over which T - MBL J_0 estimates have acceptable accuracy.

structure being assessed. As the J_0 vs. J curve (Figure 15) becomes flat, small errors in J_0 produce much larger errors in J and, consequently, in load at fracture. In this situation, tighter limits on J_0 error may be required.

These results suggest that a diagram of the type illustrated in Figure 17 can be constructed. This investigation quantifies only the point for one strain hardening exponent, $n=10$. The trend shown is conjectural based on information presented in earlier studies which suggests that increased material strain hardening (i.e. $n < 10$) reduces the sensitivity to stress errors of the J_0 values predicted using T - MBL . While further analysis is needed to quantify the actual variation, it is encouraging that the low to moderate strength steels (yield stress below 580 MPa, or 84 ksi) used extensively in civil and offshore construction typically have strain hardening exponents below 10 [Barsom and Rolfe, 1987]. Thus, for a broad class of engineering structures, the T - MBL approximation should produce acceptably accurate estimates of J_0 for a wider range of cracked geometries than reported here for $n=10$.

5.4 Deformation Limits on the Applicability of these Fracture Analysis Methodologies

The applicability limits of single parameter fracture mechanics (SPFM) are typically expressed as a maximum permissible deformation level relative to specimen size. So long as deformation of the structure remains below this level, the crack-tip fields in the finite body are accurately described by J alone and critical J values are geometry independent:

$$D_{max.} = \frac{c}{J_{crit}/\sigma_{flow}} \quad (16)$$

Here J_{crit} represents the value of J at some critical event (J_c for cleavage fracture initiation, J_{lc} for ductile fracture initiation) and c is the smallest characteristic structural dimension

(crack length, ligament length, or thickness). The smallest characteristic dimension (c) must be large compared to the CTOD (proportional to J_{crit} / σ_{flow}) for J alone to characterize crack-tip deformations. Previous investigators have used different criteria to quantify D_{max} . Shih and German [1981] establish D_{max} based on excessive deviation ($\geq 10\%$) of crack plane stresses in finite bodies from the HRR solution. This criteria was established without regard to the fracture mechanism, although the intent was to set limits on J_{Ic} (ductile fracture) validity. Conversely, Dodds, et al. [1991] establish D_{max} for cleavage fracture as the deformation level above which $J_c / J_o > 1.1$. This criteria requires assumption of a failure mode to establish the geometry independent conditions at fracture. While deformation limits constructed on a purely mechanical basis (e.g. deviation from HRR) are more simply determined, they are of less practical utility than micromechanically based limits, for these establish the maximum error in the quantity used to assess structural fracture integrity: toughness.

The evolving methodologies for fracture analysis discussed here extend significantly, relative to SPFM, the range of deformation over which the crack-tip stress state can be accurately described. However, these techniques also have deformation limits beyond which the crack-tip fields are not uniquely and completely characterized by the parameters used. Use of any methodology beyond its applicability limit will produce apparent size dependencies in fracture toughness data. Criteria which define these limits are established as follows:

- a. Limit on the T -MBL Approximation for J_o : J_o cannot be estimated accurately using opening mode stresses from the T -MBL approximation when J/J_o calculated by the T -MBL approximation at $r/(J/\sigma_o) = 2$ differs by more than 10% from J/J_o determined by elastic-plastic finite element analysis of the finite geometry.
- b. Limit on J_o from Elastic-Plastic Finite element Analysis: The effective driving force for cleavage fracture, J_o , cannot be unambiguously calculated when J_o values calculated at $r=1.5J/\sigma_o$ and at $r=1.5J/\sigma_o$ differ by more than 10% of their average value.

As shown in Figure 18, it appears that β parameterizes these deformation limits, effectively accounting for the combined effects of geometry and loading mode. While this relationship lacks a rigorous basis, it is not completely unforeseen that β should account for geometry and loading mode effects as β depends on both. However, as β is only an elastic quantity, the effect of material strain hardening remains unquantified.

Figure 18: Deformation limits on the T -MBL approximation for J_0 (top graph) and on elastic-plastic finite element calculation of J_0 (bottom graph) for an $n=10$, $\sigma_o/E=0.002$ material. Symbols representing specimens of same type are connected by lines. Symbols on top graph marked with asterisks denote deformation when $T/\sigma_o=0.8$. At this deformation the T -MBL approximation has the error given in parenthesis.

6. SUMMARY AND CONCLUSIONS

This investigation examines the ability of an elastic T -stress analysis coupled with a modified boundary layer (MBL) solution to predict stresses ahead of a crack tip in a variety of planar geometries. The approximate stresses are used as input to estimate the effective driving force for cleavage fracture (J_o) using the micromechanically based approach introduced by Dodds and Anderson. Finite element analyses for a wide variety of planar cracked geometries are conducted which have elastic biaxiality parameters (β) ranging from -0.99 (very low constraint) to $+2.96$ (very high constraint). The magnitude and sign of β indicate the rate at which crack-tip constraint changes with increasing applied load. All results pertain to a moderately strain hardening material (strain hardening exponent (n) of 10). The following specific conclusions may be drawn from these analyses:

1. The accuracy of the T - MBL approximation for opening mode stresses strongly correlates with the elastic biaxiality parameter β for planar geometries. The following limits are established by comparing T - MBL estimates to finite body calculations:

$|\beta| > 0.9$ T - MBL stress approximation within 1% of finite body results

$0.4 < |\beta| < 0.9$ T - MBL stress approximation within 2.5% of finite body results

$|\beta| < 0.4$ T - MBL stress approximation within 17.5% of finite body results

2. These errors in the estimated stress become magnified by a factor of 7 to 12 when used to calculate the effective driving force for cleavage fracture (J_o) because J scales with stress raised to a power. However, for a restricted range of geometries, reasonable accuracy is available:

$|\beta| > 0.9$ T - MBL approximation of J_{SSY} within 10% of finite body results

$0.4 < |\beta| < 0.9$ T - MBL approximation of J_o within 25% of finite body results

As "structural type" configurations, i.e. shallow cracks in tension, generally have $|\beta| > 0.4$, it appears that only an elastic analysis is needed to determine reasonably accurate J_o values for structural conditions.

3. β parameterizes deformation limits on the applicability of evolving fracture methodologies (i.e. T - MBL , J - Q , and J/J_o), effectively accounting for the combined effects of geometry and loading mode.

Available evidence suggests that increased material strain hardening (i.e. $n < 10$) will increase the range of cracked geometries for which the T - MBL approximation is sufficiently accurate. The low to moderate strength steels (yield stress below 580 MPa, or 84 ksi) used extensively in civil and offshore construction typically have strain hardening exponents below 10. Thus, for a broad class of engineering structures, the T - MBL approximation should produce acceptably accurate estimates of J_o for a wider range of cracked geometries than reported here for $n=10$.

7. REFERENCES

- Al-Ani, A.M., and Hancock, J.W., "J-Dominance of Short Cracks in Tension and Bending," *Journal of Mechanics and Physics of Solids*, Vol. 39, pp. 23-43, 1991.
- Anderson, T.L., and Dodds, R.H., "Specimen Size Requirements for Fracture Toughness Testing in the Ductile-Brittle Transition Region," *Journal of Testing and Evaluation*, Vol. 19, pp. 123-134, 1991.
- Barker, D.B., Sanford, R.J., and Chona, R., "Determining K and Related Stress Field Parameters from Displacement Fields," *Proceedings, Society for Experimental Stress Analysis*, Bethel, Pennsylvania, 1983.
- Barsom, J.M., and Rolfe, S.T., *Fracture and Fatigue Control in Structures - Applications of Fracture Mechanics*, Prentice Hall, Inc., Englewood Cliffs, New Jersey, p. 265, 1987.
- Bertegon, C., and Hancock, J.W., "Two-Parameter Characterization of Elastic-Plastic Crack Tip Fields," *Journal of Applied Mechanics*, Vol. 58, pp. 104-113, March 1991.
- Dodds, R.H., and Lopez, L.A., "Software Virtual Machines for Development of Finite-Element Systems," *International Journal for Engineering with Computers*, Vol. 13, pp. 18-26, 1985.
- Dodds, R.H., Anderson, T.L., and Kirk, M.T., "A Framework to Correlate a/W Ratio Effects on Elastic-Plastic Fracture Toughness (J_c)," *International Journal of Fracture*, Vol. 48, pp. 1-22, 1991.
- Du, Z.Z., and Hancock, J.W., "The Effect of Non-Singular Stresses on Crack Tip Constraint," *Journal of the Mechanics and Physics of Solids*, Vol. 39, pp. 555-567, 1991.
- Herrens, J., and Read, D.T., "Fracture Behavior of a Pressure Vessel Steel in the Ductile-to-Brittle Transition Region," NISTIR 88-3099, National Institute for Standards and Technology, Boulder, Colorado, December, 1988.
- Hutchinson, J.W., "Singular Behavior at the End of a Tensile Crack in a Hardening Material," *Journal of Mechanics and Physics of Solids*, Vol. 16, pp. 13-31, 1968.
- Johnson, L.W., and Riess, R.D., *Numerical Analysis*, Addison-Wesley Publishing Co., Reading, Massachusetts, p.145, 1982.
- Keeney-Walker, J., Bass, B.R., and Landes, J.D., "An Investigation of Crack Tip Stress-Field Criteria for Predicting Cleavage Crack Initiation," to appear in ASTM STP 1131, 1993.
- Kfoury, A.P., "Some Evaluations of the Elastic T -term using Eshelby's Method," *International Journal of Fracture*, Vol. 30, pp. 301-315, 1986.
- Kirk, M.T., and Dodds, R.H., "An Analytical and Experimental Comparison of J_i Values for Shallow Through and Part Through Surface Cracks," *Engineering Fracture Mechanics*, Vol. 39, No. 3, pp. 535-551, 1991.
- Kirk, M.T., and Dodds, R.H., "The Influence of Weld Strength Mismatch on Crack-Tip Constraint in Single Edge Notch Bend Specimens," to appear in the *International Journal of Fracture*, 1993.
- Larsson, S.G., and Carlsson, A.J., "Influence of Non-Singular Stress Terms and Specimen Geometry on Small-Scale Yielding at Crack Tips in Elastic-Plastic Materials," *Journal of the Mechanics and Physics of Solids*, Vol. 21, pp. 263-277, 1973.
- Leevers, P.C. and Radon, J.C., "Inherent Stress Biaxiality in Various Specimen Geometries," *International Journal of Fracture*, Vol. 19, pp. 311-325, 1982.
- Li, F.Z., Shih, C.F., and Needleman, A., "A Comparison of Methods for Calculating Energy Release Rates," *Engineering Fracture Mechanics*, Vol. 21, pp. 405-421, 1985.
- McMeeking, R.M., "Finite Deformation Analysis of Crack-Tip Opening in Elastic-Plastic Materials and Implications for Fracture," *Journal of the Mechanics and Physics of Solids*, Vol. 25, pp. 357-381, 1977.
- Miglin, M.T., Wade, C.S., and Van Der Sluys, W.A., "Analysis of Fracture Toughness Data for Modified SA508 C12 in the Ductile-to-Brittle Transition Region," *Fracture Mechanics: Twenty-First Symposium, ASTM STP 1074*, J.P. Gudas, J.A. Joyce, and E.M. Hackett, Eds., American Society for Testing and Materials, Philadelphia, Pennsylvania, pp. 238-263, 1990.

- Moran, B., and Shih, C.F., "Crack Tip and Associated Domain Integrals from Momentum and Energy Balance," *Engineering Fracture Mechanics*, Vol. 27, pp. 615–642, 1987.
- Nakamura, T., and Parks, D., "Determination of Elastic T -Stress Along 3-D Crack Fronts Using an Elastic Interaction Integral," submitted for publication in the *International Journal of Fracture*, 1992.
- O'Dowd, N.P., and Shih, C.F., "Family of Crack-Tip Fields Characterized by a Triaxiality Parameter: Part I – Structure of Fields," *Journal of the Mechanics and Physics of Solids*, Vol. 39., No. 8, pp. 989–1015, 1991.
- O'Dowd, N.P., and Shih, C.F., "Family of Crack-Tip Fields Characterized by a Triaxiality Parameter: Part II – Fracture Applications," *Journal of the Mechanics and Physics of Solids*, Vol. 40, pp. 939–963, 1992.
- Parks, D.M., "Engineering Methodologies for Assessing Crack Front Constraint," *Proceedings*, Spring Meeting of the Society for Experimental Mechanics, Milwaukee, Wisconsin, 1991.
- Rice, J.R., and Rosengren, G.F., "Plane Strain Deformation Near a Crack Tip in a Power-Law Hardening Material," *Journal of Mechanics and Physics of Solids*, Vol. 16, pp. 1–12, 1968.
- Rice, J.R., and Tracey, D.M., in *Numerical and Computer Methods in Structural Mechanics*, S.J. Fenves et al. (eds.), Academic Press, New York, pp. 585–623, 1968.
- Ritchie, R.O., Knott, J.F., and Rice, J.R., "On the Relationship Between Critical Tensile Stress and Fracture Toughness in Mild Steel," *Journal of the Mechanics and Physics of Solids*, Vol. 21, pp. 395–410, 1973.
- Sham, T.L., "The Determination of the Elastic T -term using Higher Order Weight Functions," *International Journal of Fracture*, Vol. 48, pp. 81–102, 1991.
- Shih, C.F. and German, M.D., "Requirements for a One Parameter Characterization of Crack Tip Fields by the HRR Singularity," *International Journal of Fracture*, Vol. 17, No. 1, pp. 27–43, 1981.
- Shih, C.F., Moran, B., and Nakamura, T., "Energy Release Rate Along a Three-Dimensional Crack Front in a Thermally Stressed Body," *International Journal of Fracture*, Vol. 30, pp. 79–102, 1986.
- Sorem, W.A., Dodds, R.H., and Rolfe, S.T., "Effects of Crack Depth on Elastic Plastic Fracture Toughness," *International Journal of Fracture*, Vol. 47, pp. 105–126, 1991.
- Sumpter, J.D.G., and Hancock, J.W., "Shallow Crack Toughness of HY-80 Welds: An Analysis Based on T Stresses," *International Journal of Pressure Vessels and Piping*, Vol. 45, pp. 207–221, 1991.
- Sumpter, J.D.G., and Forbes, A.T., "Constraint Based Analysis of Shallow Cracks in Mild Steel," *Proceedings of the International Conference on Shallow Crack Fracture Mechanics Tests and Applications*, TWI, Cambridge, England, September 1992.
- Theiss, T.J., and Bryson, J.R., "Influence of Crack Depth on Fracture Toughness of Reactor Pressure Vessel Steel," *Constraint Effects in Fracture*, ASTM STP 1171, E.M. Hackett, K.-H. Schwalbe, and R. H. Dodds, Eds., American Society for Testing and Materials, Philadelphia, Pennsylvania, pp. 104–119, 1993.
- Wang, Y.Y., "On the Two-Parameter Characterization of Elastic-Plastic Crack-Front Fields in Surface-Cracked Plates," *Constraint Effects in Fracture*, ASTM STP 1171, E.M. Hackett, K.-H. Schwalbe, and R. H. Dodds, Eds., American Society for Testing and Materials, Philadelphia, Pennsylvania, pp. 120–138, 1993.
- Wang, Y.Y., "A Two-Parameter Characterization of Elastic-Plastic Crack Tip Fields and Applications to Cleavage Fracture, Ph.D. Dissertation, MIT, 1991(b).

BIBLIOGRAPHIC DATA SHEET

(See instructions on the reverse)

1. REPORT NUMBER
(Assigned by NRC. Add Vol., Supp., Rev.,
and Addendum Numbers, if any.)

NUREG/CR-5970
UILU-ENG-92-2016
CDNSWC/SME-CR-18-92

2. TITLE AND SUBTITLE

Approximate Techniques for Predicting Size Effects on Cleavage
Fracture Toughness (J_c)

3. DATE REPORT PUBLISHED

MONTH YEAR
July 1993

4. FIN OR GRANT NUMBER

B6290

6. TYPE OF REPORT

Technical

7. PERIOD COVERED (Inclusive Dates)

10-1-91 : 9-30-92

5. AUTHOR(S)

Mark T. Kirk, University of Illinois
Robert H. Dodds, Jr., University of Illinois

8. PERFORMING ORGANIZATION -- NAME AND ADDRESS (If NRC, provide Division, Office or Region, U.S. Nuclear Regulatory Commission, and mailing address; if contractor, provide name and mailing address.)

University of Illinois at Urbana-Champaign
Department of Civil Engineering, MC-250
205 North Mathews Avenue
Urbana, IL 61801-2352

Under Contract to:
Naval Surface Warfare Center
Annapolis Detachment, Carderock Division
Code 2814
Annapolis, MD 21402-5067

9. SPONSORING ORGANIZATION -- NAME AND ADDRESS (If NRC, type "Same as above"; if contractor, provide NRC Division, Office or Region, U.S. Nuclear Regulatory Commission, and mailing address.)

Division of Engineering
Office of Nuclear Regulatory Research
U.S. Nuclear Regulatory Commission
Washington, DC 20555

10. SUPPLEMENTARY NOTES

11. ABSTRACT (200 words or less)

This investigation examines the ability of an elastic T-stress analysis coupled with a modified boundary layer (MBL) solution to predict stresses ahead of a crack tip in a variety of planar geometries. The approximate stresses are used as input to estimate the effective driving force for cleavage fracture (J_0) using the micromechanically based approach introduced by Dodds and Anderson. Finite element analyses for a wide variety of planar cracked geometries are conducted which have elastic biaxiality parameters (β) ranging from -0.99 (very low constraint) to +2.96 (very high constraint). The magnitude and sign of β indicate the rate at which crack-tip constraint changes with increasing applied load. All results pertain to a moderately strain hardening material (strain hardening exponent (n) of 10). These analyses suggest that β is an effective indicator of both the accuracy of T-MBL estimates of J_0 and of applicability limits on evolving fracture analysis methodologies (i.e. T-MBL, J-Q, and J/ J_0). Specifically, when $|\beta| > 0.4$ these analyses show that the T-MBL approximation of J_0 is accurate to within 20% of a detailed finite-element analysis. As "structural type" configurations, i.e. shallow cracks in tension, generally have $|\beta| > 0.4$, it appears that only an elastic analysis may be needed to determine reasonably accurate J_0 values for structural conditions.

12. KEY WORDS/DESCRIPTORS (List words or phrases that will assist researchers in locating the report.)

Elastic-plastic fracture mechanics, size effects, finite element analysis, modified boundary layer, T-stress, JSSY, J_0 , Q, structural assessment.

13. AVAILABILITY STATEMENT

Unlimited

14. SECURITY CLASSIFICATION

(This Page)

Unclassified

(This Report)

Unclassified

15. NUMBER OF PAGES

16. PRICE

END

**DATE
FILMED**

9/17/93