DE- DOE/PC/89757--7
DE92 040017

THERMODYNAMICS AND SURFACE STRUCTURE OF COALS

Quarterly Report for the Period
April 1, 1991 to June 31, 1991

Amy S. Glass, John W. Larsen, Deanna M. Quay, James E. Roberts,
and
Patrick C. Wernett

Department of Chemistry
Lehigh University
Bethlehem, PA 18015

PREPARED FOR THE UNITED STATES DEPARTMENT OF ENERGY
Under Contract DE-AC22-89PC89757
DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Thermodynamics and Surface Structure of Argonne Coals

SCOPE AND OBJECTIVES OF WORK

Scope. An understanding of the surface structure and chemistry of coals is necessary for a true understanding and optimization of coal cleaning and other surface interactions. In all chemical reactions of solid coal, the reagent first encounters the coal surface. The extent of surface which is available to a molecule and the interactions which occur during the molecule/surface encounter are critical parameters to understanding the chemistry of the interaction of coals with various solvents. The present studies have been undertaken with the objective of understanding these complex interactions.

Objectives. The present work involves investigations of the surface structure and thermodynamics of coals and treated coals in order to develop a detailed understanding of the coal surface and its transformations and interactions as a result of various chemical treatments. To this end we are using several types of experimental probes:

- 1.) NMR relaxation agents are deposited on coals and the resulting spectra provide information about the structure and chemistry of the atoms at the coal surface.
- 2.) ^{129}Xe NMR is being used as a probe of pore distributions and surface polarity of coals.
- 3.) Classical calorimetric studies and inverse gas chromatography are being used to determine the strengths of interaction between various probe molecules and coals.

Gas-Solid Chromatography Studies

Introduction

Review of previous use of Gas-Solid Chromatography (GSC) to determine thermodynamics of coal adsorption revealed several problems with data acquisition, as discussed previously (quarterly report 6, January 1, 1991 to March 31, 1991).

In addition, in previous studies, the effect of diffusion of the adsorbate into the coal was not correctly taken into account. The goal of the present work is to obtain a more complete characterization and understanding of the adsorbate/coal interaction from both a physical and chemical viewpoint.

These studies should contribute much to the fundamental understanding of the interaction of technologically important molecules with the complex structure that is coal. In addition, this work has profound implications for modelling of various industrial processes, including: extraction of fuel from coal and from carbonaceous/inorganic matter in general, reaction of solvents with coal during production of clean coal and during production of organic chemicals from coal, effects of solvent swelling on coal structure and chemistry, and characterization of coal thermodynamics for efficient burning of coal.

Experimental

As a result of the above considerations, it was decided to construct an apparatus to allow investigation of coal adsorption

thermodynamics and kinetics. Small amounts of gas are introduced via a gas sampling valve connected to the GC column. We are monitoring diffusion by acquiring Van Deemter plots of a given adsorbate/coal pair. From these the effective diffusion coefficient, D_{eff} , is extracted. Adsorption isotherms are determined from chromatograms by methods described previously.

In addition to GC and sample introduction apparatus, data acquisition has been computerized so that the chromatogram corresponding to an adsorbate at a given flow rate and temperature for a given coal may be stored on an AT computer, manipulated, and finally stored on a floppy disk. All data manipulation software including computation of the isotherm from the chromatogram, plotting of the Van Deemter equation, and extraction of the diffusion coefficients has been programmed in BASIC.

Results and Discussion

Preliminary results indicate that it should be possible to obtain adsorption and diffusion data for several probe molecules such as methane, ethane, and hydrogen on different coals. Diffusion coefficients from Van Deemter plots of methane and ethane on Illinois #6 coal were obtained and are about 2×10^{-4} and 4×10^{-5} cm^2/sec , respectively. These values agree fairly well with diffusion constants for methane determined by static methods¹. Studies are presently underway to relate methane adsorption and diffusion data to changes in coal structure.

Determination of the Surface Structure of Coals By the Deposition of NMR Relaxation Agents

Present Work:

Our work this quarter has been directed at looking at the effect of depositing dysprosium(III) ions on the surface of coal. We have also been examining the effect of this relaxation agent on our new model system, a carboxylic acid silica gel.

Background:

To the best of our knowledge, NMR has not previously been applied to surface studies of coal. In contrast, solid state NMR has been applied extensively to coal and related systems. It is a powerful technique because line positions and intensities are indicative of geometry, bonding hybridization and population of distinct functionalities as well as local environment effects. The NMR spectrum can be influenced by many factors including dipolar through-space coupling between an unpaired electron spin and the spin of the carbon atom. The unpaired electron can act as a relaxation sink, significantly shortening the spin-lattice relaxation time (T_1) of the coupled carbon-13 atom. This shortening of the T_1 can theoretically broaden the signal to the point where it disappears. The effective range of interaction is proportional to the inverse sixth power of the separation of two spins (r^{-6})². In this system the effective range is a relatively

short distance on the order of approximately one nanometer. Assuming that the paramagnetic centers are deposited on the surface of our sample, an effective range of approximately one nanometer would limit the paramagnetic effects to surface functionalities.

We are depositing NMR relaxation and shift reagents on the surface of coals. The dipolar coupling of the unpaired electron spin of the relaxation agent and the carbon atom should significantly shorten the carbon T_1 which should broaden it away. We propose to take the NMR spectrum of a coal before and after deposition and subtract the spectra. The difference spectra will represent the functionalities within approximately one nanometer of the surface and should represent the surface composition of the coal.

Experimental:

In order to observe the effect of paramagnetics on coal, we deposited a known excess of dysprosium nitrate on a sample of Beulah Zap lignite³. We chose Beulah Zap lignite primarily because it is low rank and it has a high concentration of oxygen functional groups. We expect the oxygen and carboxylate groups to bind the dysprosium ions. We chose dysprosium because it appears that dysprosium may be a better relaxation agent than copper(II). Work with copper(II) was described in Quarterly Report DEAC22-89C89PC89757-4⁴. When compared to the other lanthanides, dysprosium exhibits the largest downfield shifting behavior⁵. We chose a downfield shifting lanthanide so that the shifted carbonyl

would not move into the highly congested aromatic region.

We also deposited known concentrations of dysprosium onto carboxylic acid and aryl sulfonate ion exchange resins. Samples containing 0.5, 1, 2, 4, 8, and 16% dysprosium on a charge equivalence basis were made with the carboxylic acid resin. A 3% dysprosium sample was made using the aryl sulfonate. (Charge equivalence means that we determine the number of dysprosiums with a +3 charge needed to balance the carboxylates with a -1 charge. A 1% coverage means that we calculate the amount of dysprosium needed for complete coverage and then apply 1% of that to the gel.)

The coal used is Beulah Zap lignite of the Argonne Premium Coal Sample Program³. All NMR spectra were obtained using a General Electric GN-300 NMR spectrometer operating at 75.4 MHz for ^{13}C and utilizing a Doty 7mm probe. The samples were examined under Magic Angle Sample Spinning (MASS) conditions⁶. The model compounds used were aryl sulfonate and carboxylic acid ion exchange resins produced by J.T. Baker, Inc.

The Beulah Zap was treated by mixing with a sodium bicarbonate buffer for one week. It was then dialyzed for 24 hours against deionized water three times. The sample was split, one half was mixed with a dysprosium nitrate solution for one week. Samples containing 2X and 20X excess dysprosium per carboxylic acid functionality were prepared based on 7 carboxylic acid functionalities per 100 carbon atoms⁷. The other half, our control, was kept in water for one week. The solvent was evaporated from both samples which were then dried in a 110°C oven

under vacuum. All manipulations of coal samples were done in a nitrogen environment to minimize oxidation.

The silica gel was prepared by titrating a known quantity of aqueous dysprosium nitrate solution into a slurry of the gel with gentle stirring. The solvent was then evaporated and the samples dried under vacuum at 50°C.

NMR spin-lattice relaxation (T_1) studies were then conducted in order to compare treated and untreated sample T_1 times.

Discussion:

The spin-lattice relaxation time (T_1) studies employed cross-polarization conditions. Cross polarization is a technique commonly employed in solid state NMR involving the transfer of magnetization from the protons to the carbons⁶. Cross polarization is used to improve carbon sensitivity. The technique has been described in an earlier Quarterly Report DE-AC22-89PC89757-4¹. The pulse sequences employed for the relaxation studies referred to in our laboratory as T1CP1H (proton T_1) and T1NOE (carbon-13 T_1) have also been described in Quarterly Report DE-AC22-89PC89757-4¹.

We observed no signal with the coal and carboxylic acid samples using either cross polarization⁶ or Bloch decay experiments⁸. We attempted to observe the sodium treated carboxylic acid and we observed no signal. The quantity of COOH functionalities on the surface was reported as 0.4 meq/g compared to the aryl sulfonate which has 1 meq/g of functionalities on the surface.⁹ We believe the problem to be one of sensitivity. There

was not enough material to obtain an NMR signal. Another possible explanation for the lack of signal is the spin dynamics of the carboxylic acid system. We also measured the lossiness of each of these samples and it was comparable to samples from which we observed signal. We think the loss of signal with the coal samples is the result of too much dysprosium. Cross polarization is often not effective when there are a large number of unpaired electrons present. The first experiments completed used cross polarization. A spectrum from one of these experiments is found in Figure 1. No signal was observed. We therefore completed a Bloch Decay experiment. A Bloch Decay is not dependent on cross polarization. If our signal was lost due to ineffective cross polarization, we should be able to observe a signal using the Bloch decay. This experiment also produced essentially no signal. Bloch Decay spectra of Beuhlah Zap treated with sodium and dysprosium are presented in Figure 2. The dysprosium is a much better relaxation agent than copper(II), so it is possible that it may be relaxing the carbons so fast that no signal is observable. There also may be a problem with magnetic susceptibility since dysprosium has five unpaired electrons compared to copper(II)'s one.

The 3% dysprosium on aryl sulfonate resin did yield a signal and we were able to determine T_1 times as described above. The proton and carbon T_1 's are presented in Table 1 for both the sodium and dysprosium treated samples. As can be seen from these numbers dysprosium shortens the relaxation times as predicted.

Future Work:

Next quarter, we plan to do relaxation studies on a series of samples in which we will vary the amount of dysprosium on a aryl sulfonate silica gel resin. We plan to switch back to this resin because there are enough functionalities present to give a NMR signal. We also plan to apply smaller quantities of dysprosium to a Beulah Zap sample. We hope that we can selectively broaden away the surface functionalities of the Beulah Zap and leave the bulk signal.

References

1. D. W. Van Krevelen, "Coal," Elsevier, New York, 1961, pp. 2.
2. Sternlicht, H. J. Chem. Phys. 1965, 42, 2250.
3. Vorres, K. S. Energy and Fuels, 1990, 4, 420-426.
4. Larsen, J. W.; Quay, D. M.; Roberts, J. E.; Wernett, P. C. Thermodynamics and Surface Structures of Coals, Quarterly Report, DE-AC22-89PC89757-4, July 1, 1990- September 30, 1990.
5. Horrocks, W. D. Jr.; Sipe, J. P. III J. Am. Chem. Soc. 1971, 93, 6800-6804.
6. Fyfe, C. A. in Solid State NMR for Chemists; C. F. C. Press: Ontario, (1984).
7. Solum, M. S.; Pugmire, R. J.; Grant, D. M. Energy and Fuels, 1989, 3, 187-193.
8. Bloch, F. Phys. Rev. 1946, 70, 460.
9. Personal Communication with William Leister, J.T. Baker, Inc. November 9, 1990

List of Figures

Figure 1. Carbon-13 NMR spectrum of Beulah Zap Sample treated with 2X excess dysprosium using cross polarization.

Figure 2. Comparison of the Bloch Decay spectra of sodium and dysprosium treated samples. Notice there is essentially no signal in the dysprosium spectrum.

DQ011 101 DMQ
DQ011 P5L213 5.6KHZ DY

Figure 1

^{13}C NMR OF COAL

Figure 2

Table 1
Relaxation Time, T1 (Seconds) for Aryl Sulfonate
Resin Unbound and with 3% Dysprosium(III)

	Unbound	3% Dysprosium
C-13 10 ppm	1.5(0.2)	0.6(0.3)
C-13 26 ppm	2.9(0.3)	0.9(0.2)
C-13 125 ppm	0.86(0.08)	0.78(0.01)
C-13 178 ppm	1.9(0.3)	0.58(0.05)
H 10 ppm	0.26(0.01)	0.051(0.003)
H 27 ppm	0.24(0.01)	0.062(0.003)
H 125 ppm	0.26(0.01)	0.061(0.002)
H 178 ppm	0.26(0.01)	0.08(0.01)

END

DATE
FILMED

10 / 21 / 92