DOE/PC/89778--T8

DOE/PC/89778--T8

Technical Progress Report

DE92 018317

to

**United States Department of Energy
Pittsburgh Energy Technology Center**

**Attention: Mr. James D. Hickerson, Program Officer
David Hunter, Contract Specialist
Richard Rogus, Contract Officer**

MOLTEN IRON OXYSULFIDE AS A SUPERIOR SULFUR SORBENT

DOE/DE-FG22-89PC89778

by

**Malcolm T. Hepworth
Principal Investigator**

**Period Covered:
Third Quarter
March 1, 1990 - June 1, 1990**

2nd 1990

**MINERAL RESOURCES RESEARCH CENTER
DEPARTMENT OF CIVIL AND MINERAL ENGINEERING**

UNIVERSITY OF MINNESOTA

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

JMg

ABSTRACT*

Slagging combustors with injected lime or limestone are being considered as replacements for conventional coal burners. They have advantages in that they can be staged to reduce NO_x and SO_x emissions. Iron oxide, as an alternative to lime or limestone may be effective not only as a desulfurizing agent, but, under the right conditions of oxygen potential, it can act as a flux to produce a glassy slag. This glassy slag should be dense and environmentally inert. In this reporting period, the thermodynamic conditions are determined for the operation of the first stage of a combustor which would have as its feed six types of coals. The calculations are made for the four phase equilibrium: $\text{FeO}(\text{wustite})/\text{Fe}/\text{Liquid}/\text{Gas}$ over the temperature range 950° to 1300°C . The minimum dosage of iron oxide required at equilibrium and the calculated maximum percent sulfur removal are reported. Also given are the expected pounds of SO_2 per million Btu of heat evolution calculated for complete combustion.

These preliminary results indicate in the Fe-O-S system that higher temperatures give better results approaching 96 percent sulfur removal from a coal containing (on a dry basis) 3.29% by weight sulfur. In the prior reporting period, a comparison is made between iron oxide and lime as a desulfurizing agent. With lime, the thermodynamic conditions were chosen: a set of conditions where the compound calcium sulfide is the product and a set of conditions where calcium sulfate is the product. The temperature limits of the sulfate forming and sulfide forming reactions were defined.

- Underlined text are key words.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCUSSION

In the first two quarters of this project an interactive computer program was developed which allows the operator to input a given coal composition, temperature and air input in order to achieve a particular set of operating conditions. The condition chosen initially was the four-phase equilibrium: FeO(wustite)/Fe/Liquid/Gas. The temperature range chosen was from 950° to 1300°C. A comparison was made between the desulfurizing power of lime to form either calcium sulfide or calcium sulfate, and with iron to form an iron oxysulfide liquid. The composition of this liquid was determined by the phase equilibria with an initial limitation that the liquid be in contact with wustite and iron. This limitation was made for ease of calculation and because the thermodynamic data are readily available. In this third reporting period, the calculations have been extended to include five representative coals of from southern Indiana and southern Illinois. Equipment for testing the validity of the thermodynamic calculations is being constructed, and test data in the form of gas compositions in equilibrium with the four phases described above will be determined by experiment to verify the calculations.

Background Information on Coal Types and Compositions

The previously reported calculations were made on an Illinois Basin Coal (IBC), 102, Colchester from an Illinois Number 2 seam. In this present report calculations are made on IBC coals from an Illinois Number 6 seam. Information in this section was provided by the Illinois State Geological Survey¹. Table 1 is a description of the coals which were used as a basis for the calculation made in the present quarterly report. All except for IBC 102 sample are Illinois Number six coal, Herrin except for IBC 108 which is a blend of Herrin and Springfield coals.

Table 1. Description of Coals

Sample	Seam	Location	Unique Characteristics
IBC			
102	Colchester (IL #2)	Western IL	Low organic, high pyritic S
104	Herrin (run-of-mine)	Southwestern IL	2/3 of S pyritic
105	Herrin (channel)	Southwestern IL	Part of ANL premium sample program
107	Herrin (special)	Central IL	Unusual ratio of S isotopes
108	80% Herrin; 20% Springfield	Southern IL	High moisture content, Filter cake: micronized coal
109	Herrin	Southern IL	Low ash; low S; High Cl

These coals are characterized by the chemical analyses given in Table 2.

Table 2. Analyses of Coals

	Analyses of samples from IBC lots (Moisture Free Values)					
	IBC-102	IBC-104	IBC-105	IBC-107	IBC-108	IBC-109
Moisture	14.2	15.0	9.4	9.3	45.*	9.2
Carbon	73.9	46.78	63.6	68.11	76.20	74.95
Hydrogen	5.29	3.41	4.58	5.00	5.41	4.95
Nitrogen	1.52	0.88	1.19	1.20	1.56	1.76
Oxygen	9.02	8.25	7.55	10.56	10.39	8.93
Total Sulfur	3.29	4.17	4.52	3.67	2.63	1.14
BTU/lb	13582	8522	11540	12224	13700	13301

Coal IBC-108 has an anomalously high moisture content since it is a micronized coal in the form of a filter cake. IBC-104 has both a low carbon and hydrogen content, and IBC-109 is a coal of low sulfur content for an Illinois coal.

Interactive Computer Program for Combustion Conditions

As discussed in the prior report, an interactive computer program was developed which enables coal assays to be entered as well as combustion conditions. These conditions include temperature, total pressure, coal composition, moisture content, and volume of air. Two interactive programs have been written. The first program, presented in Appendix A, is for coal combustion products in equilibrium in the Ca-S-O system. The second program, presented in Appendix B is for coal combustion products in equilibrium in the Fe-O-S system. In the former program there are two cases: Case A, where the condensed phases are CaO and CaS, and Case B, where the condensed phases are CaO, CaSO₄. In second program the calculations are presently limited to gas phase equilibria in contact with the condensed phases: wustite, iron, and liquid iron oxysulfide. This restriction will be removed as data are determined and entered into the program for the two-phase equilibria between gas and liquid oxysulfide phase (without the additional restriction of the presence of iron and wustite). Data for input into these two programs were taken from Kubaschewski and Alcock² for the thermodynamics of the gas phase interactions and for the stabilities of the calcium compounds. The iron oxygen-sulfur systems incorporates data from Darken and Gurry³, Bog and Rosenqvist⁴, Rosenqvist and Hartvig⁵, and Burgmann et al.⁶ as reported by Turkdogan and Kor.⁷

First Program, Ca-S-O Gas Equilibrium:

Case A: Gas, condensed phase equilibria in the presence of calcium sulfide.

As was reported in the prior quarterly report, under equilibrium conditions, calcium sulfate decomposes at temperatures above 1150°C. This can be seen in Figure 1, which is a predominance diagram for the system Ca-S-O. In this figure the equilibrium phase regions are designated on a logarithmic plot of partial pressures of sulfur (taking the dimmer as the predominant elemental sulfur species) on the ordinate and log oxygen partial pressure as a measure of the chemical potential of oxygen on the abscissa. The solid lines represent conditions at 1000°C. and the dashed lines at 1300°C., respectively. As is expected, calcium sulfide is oxidized upon increasing the oxygen potential to the sulfate form and can only be maintained under the reducing conditions shown. As temperature is increased (dashed lines) the transition from sulfide to sulfate occurs under more oxidizing conditions. Also, as temperature is increased, the equilibrium between sulfide and oxide occurs at lower sulfur pressures in the equilibrium between CaS and CaO; however, the sulfur pressures for the equilibrium between CaO and CaSO₄ phases occur for higher sulfur pressures as temperature is raised.

In the prior quarterly report, calculations were made of the Colchester coal (IBC-102) for desulfurization of coal combustion products in the presence of calcium sulfide. Using the interactive program and the coal composition given above, the calculations in Figure 2 for the condensed phases, CaO/CaS, yield the anticipated equilibrium sulfur concentration. These concentrations are reported as pounds of SO₂ per million BTU plotted against temperature. Figures 2, 3, 5, 6, 7, 8, 9, 10, 11, and 12 refer to Colchester coal (IBC-102). For the other coals of the Illinois Number 6 seam, the figures are referenced to the particular coal type. For the plot shown in Figure 2, the partial pressure of oxygen was arbitrarily taken at 10⁻¹² atmospheres with a total gas pressure of 1 atmosphere. The thermodynamic conditions would be those which would obtain in the reducing stage of a two-stage combustor; however, the calculations for the sulfur dioxide emissions (ordinate) are based upon stoichiometric conditions existing in the second stage of the combustor. Figure 2 substantiates the conditions borne out in Figure 1; that is, high temperatures for the calcium sulfide system yield better desulfurization. These calculations could readily be extended for the other coals from having the compositions listed in Table 1.

Case B: Gas, condensed phase equilibria in the presence of calcium sulfate.

When lime as a sorbent is utilized under oxidizing conditions, that is, with calcium sulfate as the product of reaction, the converse temperature dependence is noted. The Colchester coal (IBC-102) was again used as the basis for calculations in determining desulfurization for coal combustion products in the presence of calcium sulfate. Figure 3 shows that for temperatures much above 1150°C, the sulfur pressure rises rapidly. The conditions chosen were for an oxygen pressure of 0.05 atmospheres, or a slight excess of

oxygen over stoichiometric requirements. In Figures 2 and 3, the theoretical dosage of lime is also plotted. As the lime reacts with sulfur, the dosage of lime required, of course, increases (Figure 2); whereas, the converse is true for Figure 3 where lime becomes less effective as a desulfurizer.

Second Program, Fe-O-S Gas Equilibrium:

The second program, as contained in Appendix B, is the primary thrust of this study. As was mentioned earlier, the calculations at present are restricted to the set of conditions in which the liquid iron oxysulfide phase is in equilibrium with iron and wustite. This restriction was chosen because the data are readily available from the literature and serve as a check on the experimental work which is about to be undertaken. For example, by use of iron crucibles to hold the liquid charge and by setting the oxygen potential (by use of the ratio of CO_2/CO) in inflowing gas stream, the solid phases, iron and wustite, can be stabilized. Later in this study, the calculations will be extended to the two-phase equilibrium, liquid oxysulfide and gas.

Figures 4 through 8 are taken from the previously reported calculations (Appendix A of the second quarterly report). Figure 4 is a ternary projection of the liquidus surfaces in the Fe-O-S system showing the phase pyrrhotite (FeS) at the lower right hand corner. The liquid phase is seen to be in the thermal "trough" with a ternary eutectic of 920°C . From this ternary eutectic the labeled isotherms diverge outward to form the steep walls of this valley. The region in this paper for which calculations were made is the heavy diagonal line toward the left-hand wall of this trough which marks the boundary between the regions of iron/wustite/and liquid.

Calculations Based upon As-Received Colchester No. 2 Coal.

Figures 5 through 8 are calculated for the coal sample IBC-102 (Colchester No. 2). Figure 5 is a plot of the conditions of oxygen and sulfur potential as a function of temperature to maintain this four phase equilibrium (three condensed phases plus gas). This plot is not for a system of constant composition but for the composition along the solid line shown in the previous figure. As temperature rises, the oxygen partial pressure is shown to rise, but interestingly, the sulfur partial pressure shown on a log scale drops sharply. Part of this drop can be attributed toward the increasing solubility limit of the liquid phase (closer to lower sulfur concentrations); nevertheless, the rapid drop in sulfur partial pressure is steeper than would be predicted merely by a shift in composition to lower sulfur contents. Even at 1300°C the chemical potential of sulfur, as measured by the parameter, $-RT\ln P_{\text{S}_2}$, is about 45,000 calories per gram mole corresponding to a partial pressure of sulfur of 5.58×10^{-7} atm. This is a fortuitous aspect of the iron-oxygen-sulfur system; i e., the thermodynamic calculations on desulfurization show improvement with higher temperatures. Figure 6 is a plot for the Fe-O-S system similar to those for the lime-based systems in which

this improved degree of desulfurization with increasing temperature is shown. The increased dosage of iron is also shown. For example, at 1300°C an iron dosage for the coal composition for these calculations would be 15 grams per 100 grams of coal.

One of the objectives of this study is to develop an interactive computer program such that an operator of a slagging combustor can enter coal compositions and combustions conditions and determine the optimum process conditions required. Figure 7 shows the air requirements for 100 grams of dry coal and the theoretical percent sulfur removal which can be achieved.

Figure 8 shows the calculated concentrations of all of the major gas species as a function of temperature for the equilibrium between Fe/FeO/Liquid/Gas. The predominant species for these reducing conditions (corresponding to a combustion stoichiometry of approximately 55 % of the required air for complete combustion) are N₂ and CO followed by CO₂, H₂, and H₂O, in that order. The total sulfur pressure is the sum of all the sulfur-bearing species with H₂S being the predominant sulfur carrier. Lower rank coals with higher hydrogen water vapor contents would be expected to carry more sulfur into the gas phase. Since the pressure of the sulfur species, S₂, is fixed by the Fe-O-S equilibria, the actual amount of sulfur in the gas phase is determined principally by the equilibrium:

This equilibrium has an equilibrium constant somewhat greater than unity. Also the pressure of H₂S is proportional only to the square root of the sulfur pressure but varies linearly with hydrogen pressure. It follows, then, that iron oxysulfide would perform best on dry, high-rank coals.

Calculations Based upon Colchester No. 2 Coal with Variation in Moisture Content.

Figure 9 shows the effect of water at 1200°C on the three major sulfur species in the gas phase for the equilibrium between FeO/Fe/Liquid/Gas. Under these reducing conditions, as shown on the logarithmic scale, hydrogen sulfide predominates over sulfur dioxide. The partial pressure of hydrogen sulfide is somewhat increased with increasing moisture content of the coal as shown on a logarithmic scale.

In Figure 10, the results of Figure 9 are now recalculated for conditions of combustion after stoichiometric air has been introduced. Note that the introduction of up to 20 percent moisture has increased the effluent sulfur dioxide content from 0.29 to 0.395 pounds per million Btu of energy release.

In Figure 11, the effect of coal moisture on air and iron dosage requirements is shown. The oxygen in the water replaces oxygen from added air via the water-gas shift

reaction. The dosage of iron is slightly reduced because of less effective capture of sulfur resulting in lower iron requirement for the equilibrium liquid.

In Figure 12, the effect of total pressure on the terminal sulfur dioxide concentrations for the burned coal are shown as absolute pressure in atmospheres.. Increasing the pressure beyond one atmosphere has little effect on the result.

Calculations on Illinois No. 6 Coals.

In Figure 13, the five coals of the Illinois No. 6 type are compared. Reference is made to Table 2 with respect to the moisture and hydrogen content of the coals, which is the primary factor determining the theoretical limit on the possible degree of desulfurization. The coal IBC-109 has the highest calculated sulfur dioxide content because of its extremely high moisture content (45%). Grouped below this coal are, in the order of decreasing sulfur content: the IBC series 104, 107, 105, and 109. Except for the latter, this decrease is a function of a decrease in the combined hydrogen plus water content. For the sample IBC-109, the low value of the SO_2 content is in major part a result of the low sulfur content of the coal.

Figures 14 through 18 are plots of the three major gas species as a function of temperature for each coal sample. The species shown are the predominant ones under the reducing conditions of equilibrium with Fe/FeO/Liquid/Gas phases.

CONCLUSIONS

The following can be concluded from this analysis:

- Lime added under oxidizing conditions to form sulfate as a reaction product is not theoretically feasible at sorbent temperatures above 1175°C.
- In the Fe-O-S system for the four-phase contact, Fe/FeO/Liquid/Gas, higher temperatures result in greater degrees of desulfurization for the range of temperatures studied.
- Increasing the hydrogen content of the coal via its intrinsic hydrogen and/or moisture has a significant detrimental effect on the degree of desulfurization in the Fe-O-S system.

ACKNOWLEDGEMENT

The assistance of Mr. Shaolin Zhong is acknowledged in preparing the computer programs. This report constitutes part of his research program for his PhD Thesis.

REFERENCES

1. Harvey, Richard D.: Illinois Geological Survey, Letter of 9/8/89 to M. T. Hepworth.
2. Kubaschewski, O and Alcock, C. B.: Metallurgical Thermochemistry, Pergamon Press, 1979.
3. Darken, L. S. and Gurry, R. W., J. Am. Chem. Soc., 1945, Vol 67. pps. 1398-1412; 1946, vol 68, pps. 798-816.
4. Bog, S. and Rosenqvist: The Physical Chemistry of Metallic Solutions and Intermetallic Compounds, Paper 6B, NPL Symposium No 9, Vol II, 1959.
5. Rosenqvist, T. and Hartvig, T.: Roy. Norweg. Concil Sci. and Ind. Res., Rep. No 12, Part II, 1958.
6. Burgmann, W., Urbain, G., and Froberg, M. G.: IRSID Saint Germain-en-Laye, France, January 1968.
7. Turkdogan, E. T. and Kor, G. J. W.: "Sulfides and Oxides in Fe-Mn Alloys: Part I, Phase Relations in the Fe-Mn-S-O System", Metallurgical Transactions, Vol 2, June 1971 pps 1561-1578.
8. Hilty, D.C. and Crafts, W.: Trans. AIME, 1952, 194, 1307.

Figure 1. Predominance Diagram
Ca-S-O System
Solid Line - 1000°C
Dashed Line - 1300°C.

Figure 2. CaO/CaS/Gas System
SO₂ Concentration at Stoichiometric Combustion & Lime Dosage g/100g Dry
Coal vs. Temperature.

Figure 3. Ca/CaSO₄/Gas System
SO₂ Concentration at Stoichiometric Combustion & Line Dosage g/100g Dry Coal vs. Temperature; O₂ Pressure : 0.05 Atmospheres.

Figure 4. Projection of the Miscibility Gap Boundary and the Liquidus Isotherms on the Combustion Diagram for the System Fe-S-O.

After: Bog and Rosenqvist⁴ and Hilty and Crafts⁵.

**Figure 5. Fe/FeO/Liquid/Gas System
Chemical Potentials S, O.**

Figure 6. Fe/FeO/Liquid/Gas System
SO₂ Concentration at Stoichiometric Combustion & Iron Dosage g/100g Dry
Coal vs. Temperature.

**Figure 7. Fe/FeO/Liquid/Gas System
Sulfur Removal vs. Temperature.**

Figure 8. Calculated Partial Pressure (atm) vs. Temperature for Coal Combustion Products in Equilibrium with Fe/FeO/Liquid.

Figure 9. Fe/FeO/Liquid/Gas
Partial Pressure Major S Constituents vs. Moisture g/100g Dry Coal at
 $1200^\circ C$.

Figure 10. Fe/FeO/Liquid/Gas System
SO₂ Concentration at Stoichiometric Combustion vs. Moisture g/100g Dry
Coal at 1200°C.

Figure 11. Fe/FeO/Liquid/Gas System
Air & Iron Dosage vs. Moisture g/100g Dry Coal at 1200°C.

**Figure 12. Fe/FeO/Liquid/Gas System
Effect of Pressure Upon Desulfurization.**

Figure 13. Comparative Effect of Temperature Upon Desulfurization.

Figure 14. IBC-104.

Figure 15. IBC-105.

Figure 16. IBC-107.

Figure 17. IBC-108.

Figure 18. IBC-109.

APPENDIX A

COMPUTER PROGRAM FOR COAL COMBUSTION PRODUCTS AT EQUILIBRIUM IN THE CA-O-S SYSTEM

Interactive Computer Program
for Coal Combustion Products
in Equilibrium with Ca-S-O System

```
1000 DIM G(25),K(25)
1050 DIM X(100),Y(100),Z(100)
1200 PRINT "CaO As Sulfur Sorbent"
1250 PRINT "The Composition of Coal Based On 100 g Dry Coal"
1300 INPUT "C%=";C:INPUT "S%=";S:INPUT "O%=";O:INPUT "H%=";H
1310 INPUT "N%=";N:INPUT "Moisture(g)=";M
1325 GOSUB 4000
1350 PRINT "The Partial Pressure of Oxygen"
1400 INPUT "PO2=";PO2
1500 INPUT "Temperature (c)=";T:T=T+273.15
1550 INPUT "The pressure=";P
1650 GOSUB 6000
1800 GOSUB 8000
1900 PRINT
1950 PRINT "Analysis of The Result"
1980 PRINT "The Amount of Air Under SPT=";A
2000 PST=PS2+PH2S+PSO2+PCOS+PSO+PSO3
2050 PRINT "The Total Pressure (atm) of Sulfur Species=";PST
2100 NST=NN*(2*PS2+PH2S+PSO+PSO2+PSO3+PCOS)/2/PN2
2120 PSST=2*NST*PN2/NN*1000000
2130 NOOT=NN*(PCO+2*PCO2+PH2O+2*PSO2+PCOS+PSO+2*PO2+3*PSO3)/2/PN2
2150 PRINT "The Total Sulfur (Moles) Evolved in The Gas=";NST
2170 PRINT "The Total Pressure of Equivalent SO2 (ppm)=";PSST
2200 PRINT "The Percent of Sulfur Removal="; (NS-NST)/NS*100;"%"
2300 NCV=(145.8*C+612*(H-O/8)+39.6*S-10.52*(9*H+M))/1000000
2355 SSS=(NST/NS)*(S/100)*(64.06/32.06)
2400 PRINT "SO2 Emission Rate (LB SO2/MM BTU)="; SSS/NCV
2500 PRINT "Present EPA Maximum=1.2"
2550 PRINT "Oxygen Amount (atom moles) into System=";NO-NOOT
2600 PRINT "Sulfur Amount (atom moles) into System=";NS-NST
```

```

2650 WCaO=(NS-NST)*56.08
2700 PRINT "The Dosage of CaO=";WCaO
2800 PRINT :PRINT
2850 INPUT "If calculating again, please type 1";CAL
2900 IF CAL=1 THEN 1000
2950 END
4000 NCC=C/12.01:NSC=S/32.06:NOC=O/16+M/18.016
4050 NHC=H/1.008+M/9.008:NNC=N/14.01
4070 RCH=NCC/NHC
4100 RETURN
6000 G(1)=-67500+20.75*T
6050 G(2)=-58900+13.1*T
6100 G(3)=-21580+11.805*T
6150 G(4)=-86620+17.31*T
6200 G(5)=-22860+18.7*T
6250 G(6)=-15400-1.4*T
6300 G(7)=-26700-20.95*T
6350 G(8)=-94200-.2*T
6400 G(9)=40800-41.7*T
6450 G(10)=-109220+38.67*T
6500 IF (T-273.15)<1195 THEN 6600
6510 G(13)=-216800+73.92*T
6550 G(11)=-194800+72.79*T:GOTO 6650
6600 G(11)=-196810+74.19*T
6610 G(13)=-218810+75.32*T
6650 G(12)=22000-1.13*T
7550 FOR I=1 TO 25
7600 K(I)=EXP(-G(I)/1.987/T)
7650 NEXT I
7700 RETURN
8000 K=1:PCO=1E-5:PH2=1E-5
8001 IF PO2<(1/K(13))^.5 THEN 8400
8005 PS2=1/(K(11))^2/(PO2)^3
8010 PCO2=K(1)*PCO*(PO2)^.5
8015 PH2O=K(2)*PH2*(PO2)^.5

```

```

8020 PH2S=K(3)*PH2*(PS2)^.5
8025 PSO2=K(4)*PO2*(PS2)^.5
8030 PCOS=K(5)*PCO*(PS2)^.5
8035 PSO=K(6)*(PS2*PO2)^.5
8040 PSO3=K(10)*(PS2)^.5*(PO2)^1.5
8045 NST=NCC*(2*PS2+PH2S+PSO+PSO2+PSO3+PCOS)/(PCO+PCO2+PCOS)
8050 NOOT=NCC*(PCO+2*PCO2+PH2O+2*PSO2+PCOS+PSO+2*PO2+3*PSO3)/(PCO+PCO2+PCOS)
8055 NOA=NOOT+3*(NSC-NST)-NOC:NNA=NOA*.79/.21
8060 NO=NOA+NOC:NN=NNA+NNC:NH=NHC:NS=NSC:NC=NCC
8065 RNH=NN/NH:RNC=NN/NC:RSN=NS/NN
8070 PN2=RNC*(PCO+PCO2+PCOS)/2
8075 PT=PCO+PH2+PO2+PS2+PCO2+PH2O+PH2S+PSO2+PCOS+PSO+PN2+PSO3
8080 RCHC=.5*(PCO+PCO2+PCOS)/(PH2O+PH2S+PH2)
8100 ZZA=ABS((PT-P)/P):ZZB=ABS((RCHC-RCH)/RCH)
8110 IF (ZZA<=1E-5) AND (ZZB<=1E-5) THEN 8700
8120 PCO=PCO*(P/PT)*(RCH/RCHC)^.5
8130 PH2=PH2*(P/PT)*(RCHC/RCH)^.5
8140 K=K+1
8150 GOTO 8005
8400 PRINT "CaO-CaS System"
8410 K=1:PCO=1E-5:PH2=1E-5
8420 PS2=PO2/K(12)^2
8430 PCO2=K(1)*PCO*(PO2)^.5
8440 PH2O=K(2)*PH2*(PO2)^.5
8450 PH2S=K(3)*PH2*(PS2)^.5
8460 PSO2=K(4)*PO2*(PS2)^.5
8470 PCOS=K(5)*PCO*(PS2)^.5
8480 PSO=K(6)*(PS2*PO2)^.5
8490 PSO3=K(10)*(PS2)^.5*(PO2)^1.5
8500 NST=NCC*(2*PS2+PH2S+PSO+PSO2+PSO3+PCOS)/(PCO+PCO2+PCOS)
8510 NOOT=NCC*(PCO+2*PCO2+PH2O+2*PSO2+PCOS+PSO+2*PO2+3*PSO3)/(PCO+PCO2+PCOS)
8520 NOA=NOOT-(NSC-NST)-NOC:NNA=NOA*.79/.21
8530 NO=NOA+NOC:NN=NNA+NNC:NH=NHC:NS=NSC:NC=NCC
8540 RNH=NN/NH:RNC=NN/NC:RSN=NS/NN
8550 PN2=RNC*(PCO+PCO2+PCOS)/2

```

```

8560 PT=PCO+PH2+PO2+PS2+PCO2+PH2O+PH2S+PSO2+PCOS+PSO+PN2+PSO3
8570 RCHC=.5*(PCO+PCO2+PCOS)/(PH2O+PH2S+PH2)
8580 ZZA=ABS((PT-P)/P):ZZB=ABS((RCH-RCHC)/RCH)
8590 IF(ZZA<=1E-5) AND (ZZB<=1E-5) THEN 8720
8620 PCO=PCO*(P/PT)*(RCH/RCHC)^.5
8630 PH2=PH2*(P/PT)*(RCHC/RCH)^.5
8640 K=K+1
8650 GOTO 8420
8700 PRINT "CaO-CaSO4 System"
8720 A=NOA*22.415/.21/2
8730 IF PCO^2/PCO2>K(9) THEN 8950
8840 PRINT "The result of calculation"
8850 PRINT "PCO=";PCO;" PH2=";PH2
8860 PRINT "PCO2=";PCO2;"PH2O=";PH2O
8870 PRINT "PN2=";PN2;" PO2=";PO2
8880 PRINT "PH2S=";PH2S;"PSO2=";PSO2
8890 PRINT "PCOS=";PCOS;"PSO=";PSO
8900 PRINT "PS2=";PS2;" PSO3=";PSO3
8910 RETURN
8950 PRINT "There is excess carbon in system."
8960 END

```


APPENDIX E

COMPUTER PROGRAM FOR COAL COMBUSTION PRODUCTS AT EQUILIBRIUM IN THE FE-O-S SYSTEM

Interactive Computer Program
for Coal Combustion Products
in Equilibrium with Fe-S-O System

```
500 DIM X(100),Y(100),Z(100)
800 DIM G(15),K(15)
1000 PRINT
1020 PRINT "Fe-FeO-Liquid System (1)"
1040 PRINT "FeO-Fe3O4-Liquid System (2)"
1060 PRINT "Fe-Liquid System (3)"
1080 PRINT "FeO-Liquid System (4)"
1100 PRINT "Fe3O4-Liquid System (5)"
1120 PRINT "Liquid (Fe-S-O) System (6)"
1140 INPUT "Number of System=";SYS
1180 ON SYS GOSUB 3000, 3150, 3300, 3450, 3600,3750
1250 PRINT "The Composition of Coal Based On 100 g Dry Coal"
1300 INPUT "C%=";C:INPUT "S%=";S:INPUT "O%=";O:INPUT "H%=";H
1310 INPUT "N%=";N:INPUT "Moisture(g)=";M
1325 GOSUB 4990
1550 INPUT "The pressure=";P
1650 GOSUB 6000
1750 PCO=1:PH2=1
1800 GOSUB 8000
1900 PRINT
1950 PRINT "Analysis of The Result"
1952 PRINT "The Amount of Air Under SPT=";A
1955 PRINT "PCO2/PCO Ratio=";PCO2/PCO
1960 PST=PS2+PH2S+PSO2+PCOS+PSO+PSO3
1965 PRINT "H2/CO Ratio=";.5*NH/NC
1970 PRINT "The Total Pressure (atm) of Sulfur Species=";PST
1980 NST=NN*(2*PS2+PH2S+PSO+PSO2+PSO3+PCOS)/2/PN2
1990 PSST=2*NST*PN2/NN*1E6
2000 NOOT=NN*(PCO+2*PCO2+PH2O+2*PSO2+PCOS+PSO+2*PO2+3*PSO3)/2/PN2
2010 PRINT "The Total Sulfur (Moles) Evolved in The Gas=";NST
2020 PRINT "The Total Pressure of Equivalent SO2 (ppm)=";PSST
```

```

2030 PRINT "The Percent of Sulfur Removal="; (NS-NST)/NS*100;"%"
2040 NCV=(145.8*C+612*(H-O/8)+39.6*S-10.52*(9*H+M))/1E6
2050 SSS=(NST/NS)*(S/100)*(64.06/32.06)
2060 PRINT "SO2 Emission Rate (LB SO2/MM BTU)="; SSS/NCV
2070 PRINT "Present EPA Maximum=1.2"
2080 PRINT "Oxygen Amount (atom moles) into System=";NO-NOOT
2090 PRINT "Sulfur Amount (atom moles) into System=";NS-NST
2100 LFe=100-LS-LO:WFe1=(LFe/LS)*(NS-NST)*32.06
2110 NOO=(LO/LS)*(NS-NST)*32.06/16.00
2120 IF (NO-NOOT-NOO)<0 THEN 2950
2130 WFe2=(NO-NOOT-NOO)*55.89
2140 PRINT "The Dosage of Iron (g)=";WFe1+WFe2:GOTO 2960
2950 PRINT "The amount of air is less, please try again":GOTO 1000
2960 PRINT :PRINT
2970 INPUT "If calculating again, please type 1";CAL
2980 IF CAL=1 THEN 1000
2990 END
3000 PRINT "Now Selecting Fe-FeO-Liquid As Sulfur Sorbent"
3005 PRINT "The Data From Turkdogan And Kor"
3010 PRINT "The Temperature (c): 950(1),1000(2),1050(3),1100(4),"
3015 PRINT "1150(5),1200(6),1250(7),1300(8)"
3020 INPUT "Number of Temperature";NUM
3025 ON NUM GOTO 3030,3040,3050,3060,3070,3080,3090,3100
3030 PRINT "The Temperature = 950 c":T=1223.15
3035 LS=22.5:LO=9.6:PS2=5E-08:PO2=1.49E-16:GOTO 3140
3040 PRINT "The Temperature =1000 c":T=1273.15
3045 LS=20.67:LO=11:PS2=1.09E-07:PO2=1.16E-15:GOTO 3140
3050 PRINT "The Temperature =1050 c":T=1323.15
3055 LS=19.42:LO=11.6:PS2=2.26E-07:PO2=7.78E-15:GOTO 3140
3060 PRINT "The Temperature =1100 c":T=1373.15
3065 LS=18.75:LO=12.4:PS2=3.5E-07:PO2=4.53E-14:GOTO 3140
3070 PRINT "The Temperature =1150 c":T=1423.15
3075 LS=17.31:LO=13.2:PS2=5.35E-07:PO2=2.34E-13:GOTO 3140
3080 PRINT "The Temperature =1200 c":T=1473.15
3085 LS=15.96:LO=14:PS2=7.23E-07:PO2=1.08E-12:GOTO 3140

```

```

3090 PRINT "The Temperature =1250 c":T=1523.15
3095 LS=15.19:LO=14.6:PS2=7.96E-07:PO2=4.49E-12:GOTO 3140
3100 PRINT "The Temperature =1300 c":T=1573.15
3105 LS=13.85:LO=15.4:PS2=7.98E-07:PO2=1.71E-11:GOTO 3140
3140 RETURN
3150 PRINT "Now Selecting FeO-Fe3O4-Liquid As Sulfur Sorbent"
3155 PRINT "The Data From Turkdogan And Kor"
3160 PRINT "The Temperature (c): 950(1),1000(2),1050(3),1100(4),"
3165 PRINT "1150(5),1200(6),1250(7),1300(8)"
3170 INPUT "Number of Temperature";NUM
3175 ON NUM GOTO 3180,3190,3200,3210,3220,3230,3240,3250
3180 PRINT "The Temperature = 950 c":T=1223.15
3185 LS=22.88:LO=9.8:PS2=6.43E-06:PO2=1.01E-14:GOTO 3290
3190 PRINT "The Temperature =1000 c":T=1273.15
3195 LS=20.87:LO=11.3:PS2=1.53E-5:PO2=1.33E-13:GOTO 3290
3200 PRINT "The Temperature =1050 c":T=1323.15
3205 LS=20:LO=11.9:PS2=2.58E-5:PO2=1.45E-12:GOTO 3290
3210 PRINT "The Temperature =1100 c":T=1373.15
3215 LS=19.04:LO=12.4:PS2=4.2E-5:PO2=1.33E-11:GOTO 3290
3220 PRINT "The Temperature =1150 c":T=1423.15
3225 LS=17.79:LO=13.3:PS2=5.63E-5:PO2=1.04E-10:GOTO 3290
3230 PRINT "The Temperature =1200 c":T=1473.15
3235 LS=16.25:LO=14.5:PS2=6.88E-5:PO2=7.09E-10:GOTO 3290
3240 PRINT "The Temperature =1250 c":T=1523.15
3245 LS=15.38:LO=15.2:PS2=5.43E-5:PO2=4E-09:GOTO 3290
3250 PRINT "The Temperature =1300 c":T=1573.15
3255 LS=14.13:LO=15.9:PS2=2.79E-5:PO2=2.2E-08:GOTO 3290
3290 RETURN
3300 PRINT "Now Selecting Fe-Liquid As Sulfur Sorbent"
3305 PRINT "Sorry, we have no data available to calculate now.":END
3310 INPUT "The Temperature (c)=";T:T=T+273.15
3440 RETURN
3450 PRINT "Now Selecting FeO-Liquid As Sulfur Sorbent"
3455 PRINT "Sorry, we have no data available to calculate now.":END
3460 INPUT "The Temperature (c)=";T:T=T+273.15

```

```

3590 RETURN
3600 PRINT "Now Selecting Fe3O4-Liquid As Sulfur Sorbent"
3605 PRINT "Sorry, we have no data available to calculate now.":END
3610 INPUT "The Temperature (c)=";T:T=T+273.15
3740 RETURN
3750 PRINT "Now Selecting Liquid (Fe-S-O) As Sulfur Sorbent"
3752 PRINT "The Temperature (c): 1600(1),1120(2),1200(3),1450(4)"
3754 INPUT "Number of Temperature=";NUM
3756 ON NUM GOTO 3758,3772,3850,3950
3758 PRINT "The Data From Calculation And Extrapolation of Interation"
3760 PRINT "Coefficients in Ternary Iron Based Alloy Melts at 1600 c"
3761 PRINT "The Temperature=1600(c)"
3762 PRINT "The Composition of Liquid (Fe-S-O)"
3764 INPUT "O%=";LO:INPUT "S%=";LS:T=1873.15
3766 ZZZ=LS*EXP((-0.27*LO-0.028*LS)*2.303)
3768 AO=LO*EXP((-0.2*LO-0.133*LS)*2.303)
3770 PS2=(ZZZ/309.42)^2:PO2=(AO/2618.7)^2:GOTO 4980
3772 PRINT "The Data From Bog And Rosenqvist"
3774 PRINT "The Temperature=1120(c)"
3776 PRINT "The Composition of Liquid (Fe-S-O) (At. pct.):"
3778 PRINT "S=34.28,O=14.23(1);S=36.14,O=12.56(2);S=39.86,O=8.74(3)"
3780 PRINT "S=40.42,O=06.67(4);S=41.44,O=05.17(5);S=42.93,O=2.23(6)"
3782 PRINT "S=43.17,O=04.37(7);S=43.49,O=05.58(8);S=43.58,O=0.93(9)"
3784 PRINT "S=43.58,O=2.05(10);S=44.29,O=0.88(11);S=44.7,O=1.95(12)"
3786 PRINT "S=45.35,O=0.83(13);S=45.53,O=3.07(14);S=46.15,O=1.86(15)"
3788 PRINT "S=46.78,O=0.78(16)"
3790 INPUT "Number of Composition of Liquid=";NUM:T=1393.15
3792 ON NUM GOTO 3794,3796,3798,3800,3802,3804,3806,3808,3810,
      3812,3814,3816,3818,3820,3822,3824
3794 PO2=5.358E-14:PS2=2.752E-06:LS=34.28:LO=14.23:GOTO 3830
3796 PO2=5.358E-14:PS2=4.597E-06:LS=36.14:LO=12.56:GOTO 3830
3798 PO2=5.358E-14:PS2=1.019E-05:LS=39.86:LO=8.74:GOTO 3830
3800 PO2=1.099E-14:PS2=2.752E-06:LS=40.42:LO=6.67:GOTO 3830
3802 PO2=1.099E-14:PS2=4.597E-06:LS=41.44:LO=5.17:GOTO 3830
3804 PO2=3.646E-15:PS2=2.752E-06:LS=42.93:LO=2.23:GOTO 3830

```

```

3806 PO2=1.099E-14:PS2=1.019E-05:LS=43.17:LO=4.37:GOTO 3830
3808 PO2=5.358E-14:PS2=4.038E-06:LS=43.49:LO=5.58:GOTO 3830
3810 PO2=1.125E-15:PS2=2.752E-06:LS=43.58:LO=.93:GOTO 3830
3812 PO2=3.646E-15:PS2=4.597E-06:LS=43.58:LO=2.05:GOTO 3830
3814 PO2=1.125E-15:PS2=4.597E-06:LS=44.29:LO=.88:GOTO 3830
3816 PO2=3.646E-15:PS2=1.019E-05:LS=44.7:LO=1.95:GOTO 3830
3818 PO2=1.125E-15:PS2=1.019E-05:LS=45.35:LO=.83:GOTO 3830
3820 PO2=1.099E-14:PS2=4.038E-05:LS=45.53:LO=3.07:GOTO 3830
3822 PO2=3.646E-15:PS2=4.038E-05:LS=46.15:LO=1.86:GOTO 3830
3824 PO2=1.125E-15:PS2=4.038E-05:LS=46.78:LO=.78:GOTO 3830
3830 LFe=100-LS-LO:LLL=LFe*55.89+LO*16+LS*32.06
3840 LS=LS*32.06/LLL*100:LO=LO*16/LLL*100:GOTO 4980
3850 PRINT "The Data From Shima and Naldrett"
3852 PRINT "The Temperature=1200(c)"
3854 PRINT "The Composition of Liquid (Fe-S-O) (wt-%):"
3856 PRINT "S=26.22,O=8.659(1);S=27.85,O=7.317(2);S=25.12,O=8.780(3)"
3858 PRINT "S=26.59,O=7.317(4);S=23.90,O=7.195(5);S=27.68,O=1.829(6)"
3860 PRINT "S=28.48,O=.4878(7);S=29.76,O=1.707(8);S=30.61,O=.5488(9)"
3862 PRINT "S=30.37,O=3.415(10);S=33.35,O=.4878(11);S=32.87,O=1.098(12)"
3864 PRINT "S=29.76,O=4.756(13);S=33.41,O=2.073(14);S=35.00,O=1.463(15)"
3866 PRINT "S=32.32,O=3.780(16)"
3868 INPUT "Number of Composition of Liquid=";NUM:T=1473.15
3870 ON NUM GOTO 3872,3874,3876,3878,3880,3882,3884,3886,3888,
      3890,3892,3894,3896,3898,3900,3902
3872 PO2=1E-08:PS2=1:LS=26.22:LO=8.659:GOTO 4980
3874 PO2=1E-09:PS2=1:LS=27.85:LO=7.317:GOTO 4980
3876 PO2=1E-09:PS2=.1:LS=25.12:LO=8.78:GOTO 4980
3878 PO2=1E-10:PS2=.01:LS=26.59:LO=7.317:GOTO 4980
3880 PO2=1E-12:PS2=1E-5:LS=23.9:LO=7.195:GOTO 4980
3882 PO2=1E-13:PS2=3.1E-6:LS=27.68:LO=1.829:GOTO 4980
3884 PO2=3.2E-14:PS2=3.1E-6:LS=28.48:LO=.4878:GOTO 4980
3886 PO2=1E-13:PS2=1E-5:LS=29.76:LO=1.707:GOTO 4980
3888 PO2=3.2E-14:PS2=1E-5:LS=30.61:LO=.5488:GOTO 4980
3890 PO2=1E-12:PS2=1E-4:LS=30.37:LO=3.415:GOTO 4980
3892 PO2=3.2E-14:PS2=1E-4:LS=33.35:LO=.4878:GOTO 4980

```

```

3894 PO2=1E-13:PS2=1E-4:LS=32.87:LO=1.098:GOTO 4980
3896 PO2=1E-11:PS2=.001:LS=29.76:LO=4.756:GOTO 4980
3898 PO2=1E-12:PS2=.001:LS=33.41:LO=2.073:GOTO 4980
3900 PO2=1E-12:PS2=.01:LS=35:LO=1.463:GOTO 4980
3902 PO2=1E-11:PS2=.01:LS=32.32:LO=3.78:GOTO 4980
3950 PRINT "The Data From Shima and Naldrett"
3952 PRINT "The Temperature=1450(c)"
3954 PRINT "The Composition of Liquid (Fe-S-O) (wt-%):"
3956 PRINT "S=22.01,O=8.719(1);S=24.51,O=6.098(2);S=26.95,O=3.537(3)"
3958 PRINT "S=28.17,O=1.463(4);S=27.07,O=4.634(5);S=29.27,O=2.439(6)"
3960 PRINT "S=30.24,O=1.159(7);S=26.46,O=5.732(8);S=29.45,O=3.354(9)"
3962 PRINT "S=31.28,O=.9756(10);S=31.95,O=.8537(11);S=23.66,O=8.415(12)"
3964 PRINT "S=31.34,O=3.232(13);S=32.80,O=2.073(14);S=33.72,O=1.098(15)"
3966 PRINT "S=33.96,O=.7317(16)"
3968 INPUT "Number of Composition of Liquid=";NUM:T=1723.15
3970 ON NUM GOTO 3972,3974,3976,3978,3980,3982,3984,3986,3988,
      3990,3992,3994,3996,3998,4000,4002
3972 PO2=1E-09:PS2=1E-4:LS=22.01:LO=8.719:GOTO 4980
3974 PO2=3.2E-10:PS2=1E-4:LS=24.51:LO=6.098:GOTO 4980
3976 PO2=1E-10:PS2=1E-4:LS=26.95:LO=3.537:GOTO 4980
3978 PO2=3.2E-11:PS2=1E-4:LS=28.17:LO=1.463:GOTO 4980
3980 PO2=3.2E-10:PS2=3.2E-4:LS=27.07:LO=4.634:GOTO 4980
3982 PO2=1E-10:PS2=3.2E-4:LS=29.27:LO=2.439:GOTO 4980
3984 PO2=3.2E-11:PS2=3.2E-4:LS=30.24:LO=1.159:GOTO 4980
3986 PO2=1E-09:PS2=.001:LS=26.46:LO=5.732:GOTO 4980
3988 PO2=3.2E-10:PS2=.001:LS=29.45:LO=3.354:GOTO 4980
3990 PO2=1E-10:PS2=.001:LS=31.28:LO=.9756:GOTO 4980
3992 PO2=3.2E-11:PS2=.001:LS=31.95:LO=.8537:GOTO 4980
3994 PO2=1E-08:PS2=.01:LS=23.66:LO=8.415:GOTO 4980
3996 PO2=1E-09:PS2=.01:LS=31.34:LO=3.232:GOTO 4980
3998 PO2=3.2E-10:PS2=.01:LS=32.8:LO=2.074:GOTO 4980
4000 PO2=1E-10:PS2=.01:LS=33.72:LO=1.098:GOTO 4980
4002 PO2=3.2E-11:PS2=.01:LS=33.96:LO=.7317:GOTO 4980
4980 RETURN
4990 NCC=C/12.01:NSC=S/32.06:NOC=O/16+M/18.016

```

```

4995 NHC=H/1.008+M/9.008:NCC=N/14.01
4997 RCH=NCC/NHC
4999 RETURN
6000 G(1)=-67500+20.75*T
6050 G(2)=-58900+13.1*T
6100 G(3)=-21580+11.805*T
6150 G(4)=-86620+17.31*T
6200 G(5)=-22860+18.7*T
6250 G(6)=-15400-1.4*T
6300 G(7)=-26700-20.95*T
6350 G(8)=-94200-.2*T
6400 G(9)=40800-41.7*T
6450 G(10)=-109220+38.67*T
6550 FOR I=1 TO 15
6600 K(I)=EXP(-G(I)/1.987/T)
6650 NEXT I
6700 RETURN
8000 K=1
8050 PCO2=K(1)*PCO*(PO2)^.5
8100 PH2O=K(2)*PH2*(PO2)^.5
8150 PH2S=K(3)*PH2*(PS2)^.5
8200 PSO2=K(4)*PO2*(PS2)^.5
8250 PCOS=K(5)*PCO*(PS2)^.5
8300 PSO=K(6)*(PS2*PO2)^.5
8310 PSO3=K(10)*(PS2)^.5*(PO2)^1.5
8315 NST=NCC*(2*PS2+PH2S+PSO+PSO2+PSO3+PCOS)/(PCO+PCO2+PCOS)
8320 NOOT=NCC*(PCO+2*PCO2+PH2O+2*PSO2+PCOS+PSO+2*PO2+3*PSO3)/(PCO+PCO2+PCOS)
8325 NOO=(LO/LS)*(NSC-NST)*32.06/16.00
8330 NOA=NOOT+NOO-NOC:NNA=NOA*.79/.21
8335 NO=NOA+NOC:NN=NNA+NNC:NH=NHC:NS=NSC:NC=NCC
8340 RNH=NN/NH:RNC=NN/NC:RSN=NS/NN
8350 PN2=RNC*(PCO+PCO2+PCOS)/2
8400 PT=PCO+PH2+PO2+PS2+PCO2+PH2O+PH2S+PSO2+PCOS+PSO+PN2+PSO3
8450 RCHC=.5*(PCO+PCO2+PCOS)/(PH2O+PH2S+PH2)
8500 IF((ABS(PT-P)/P)<=1E-6) AND ((ABS(RCHC-RCH)/RCH)<=1E-6) THEN 8750

```



```

8550 PCO=PCO*(P/PT)*(RCH/RCHC)^.5
8600 PH2=PH2*(P/PT)*(RCHC/RCH)^.5
8650 K=K+1
8700 GOTO 8050
8750 IF(PCO^2/PCO2<K(9)) THEN 9550
8800 PRINT "There is excess carbon in system."
8850 K=1
8900 PCO=K(7)*(PO2)^.5
8950 PCO2=K(8)*PO2
9000 PH2O=K(2)*PH2*(PO2)^.5
9050 PH2S=K(3)*PH2*(PS2)^.5
9100 PSO2=K(4)*PO2*(PS2)^.5
9150 PCOS=K(5)*PCO*(PS2)^.5
9200 PSO=K(6)*(PS2*PO2)^.5
9220 PSO3=K(10)*(PS2)^.5*(PO2)^1.5
9250 PN2=RNH*(PH2+PH2O+PH2S)
9300 PT=PCO+PH2+PO2+PS2+PCO2+PH2O+PH2S+PSO2+PCOS+PSO+PN2+PSO3
9350 IF ((ABS(PT-P)/P)<=1E-6) THEN 9550
9400 PH2=PH2*(P/PT)
9450 K=K+1
9500 GOTO 8900
9550 PRINT
9580 PRINT "The result of calculation"
9600 PRINT "PCO=";PCO;"PH2=";PH2
9610 PRINT "PCO2=";PCO2;"PH2O=";PH2O
9620 PRINT "PN2=";PN2;"PO2=";PO2
9650 PRINT "PH2S=";PH2S;"PSO2=";PSO2
9700 PRINT "PCOS=";PCOS;"PSO=";PSO
9750 PRINT "PS2=";PS2;"PSO3=";PSO3
9800 A=NOA*22.415/21/2
9850 RETURN

```

END

**DATE
FILMED
9 / 24 / 92**