RECEIVED

JUN 10 1993

DOE/CE/23810-6

OSTI

MISCIBILITY OF LUBRICANTS WITH REFRIGERANTS (PHASE I)

Phase 1 Final Report

6 February 1992 - 15 October 1992

**Michael B. Pate
Steven C. Zoz
Lyle J. Berkenbosch**

**Iowa State University of Science and Technology
Department of Mechanical Engineering
2028 Black Engineering Bldg.
Ames, Iowa 50011**

October 1992

**Prepared for
The Air-Conditioning and Refrigeration Technology Institute
under
ARTI MCLR Project Number 650-50300**

This research project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.67% of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.33% of allowable costs, and in-kind contributions from the air-conditioning and refrigeration industry.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED.

ym

DISCLAIMER

The U.S. Department of Energy's and the air-conditioning industry's support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared on account of work sponsored by the United States Government. Neither the United States Government, nor the Department of Energy, nor the Air-Conditioning and Refrigeration Technology Institute, nor any of their employees, nor of any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE **(for journal publication submissions)**

By acceptance of this article, the publisher and/or recipient acknowledges the right of the U.S. Government and the Air-Conditioning and Refrigeration Technology Institutes, Inc. (ARTI) to retain a non-exclusive, royalty-free license in and to any copyrights covering this paper.

TABLE OF CONTENTS

Disclaimer.....	i
Notice.....	i
Copyright Notice.....	i
Table of Contents	ii
Abstract.....	1
Scope.....	2
Test Facility and Experimental Procedures.....	3
Significant Results	6
Refrigerant and Lubricant Purity	20
Conclusions	20
Compliance with Agreement	21
Appendix A - Tabulation of Experimental Data.....	22
Appendix B - Actual Test Lubricants	58

MISCIBILITY OF LUBRICANTS WITH REFRIGERANTS

ABSTRACT

Miscibility data have been obtained for a variety of non-CFC refrigerants and their potential lubricants. Ten (10) different refrigerants and seven (7) different lubricants were investigated. Experiments are being performed in two phases: Phase I, reported herein, focuses on performing screening tests for miscibility and Phase II consists of developing miscibility plots. The miscibility tests are being performed in a test facility consisting of a series of miniature test cells submerged in a constant temperature bath. The bath temperature can be precisely controlled over a temperature range of -50°C to 90°C (-58°F to 194°F). The test cells are constructed to allow for complete visibility of lubricant-refrigerant mixtures under all test conditions.

SCOPE

Phase I - Preliminary Screening

Miscibility tests were performed on refrigerant-lubricant mixture for refrigerant concentrations of 95%, 50% and 10% by weight. These tests were performed by keeping the liquid phase visible at all times, by controlling temperatures to $\pm 1^\circ\text{C}$, and by providing agitation of the test cells.

The following refrigerants were tested for miscibility in 10°C (18°F) increments over the temperature ranges indicated below:

• R-22: $-50 - +60^\circ\text{C}$ ($-58 - +140^\circ\text{F}$)	• R-134: $-50 - +60^\circ\text{C}$ ($-58 - +140^\circ\text{F}$)
• R-32: $-50 - +60^\circ\text{C}$ ($-58 - +140^\circ\text{F}$)	• R-134a: $-50 - +90^\circ\text{C}$ ($-58 - +194^\circ\text{F}$)
• R-123: $-50 - +60^\circ\text{C}$ ($-58 - +140^\circ\text{F}$)	• R-142b: $-50 - +90^\circ\text{C}$ ($-58 - +194^\circ\text{F}$)
• R-124: $-50 - +90^\circ\text{C}$ ($-58 - +194^\circ\text{F}$)	• R-143a: $-50 - +60^\circ\text{C}$ ($-58 - +140^\circ\text{F}$)
• R-125: $-50 - +60^\circ\text{C}$ ($-58 - +140^\circ\text{F}$)	• R-152a: $-50 - +90^\circ\text{C}$ ($-58 - +194^\circ\text{F}$)

Each of the above refrigerants was tested for miscibility with the lubricants listed below. The viscosity for the penta erythritol ester mixed acid was ISO 22, while all other lubricants had a viscosity of ISO 32.

- mineral oils (<30 ppm moisture, acid number <0.01)
naphthenic mineral oil
- alkylbenzenes (<30 ppm moisture, acid number <0.01)
- polyglycols (<50 ppm moisture, acid number <0.05)
polypropylene glycol butyl monoether
polypropylene glycol diol
modified polyglycol
- polyclesters (<50 ppm moisture, acid number <0.05)
penta erythritol ester mixed-acid
mixed-acid polyol ester

During the above miscibility tests, the contents of each test cell were observed for signs of cloudiness, floc or precipitate formation, and liquid layer formation. These observations were made at each required temperature after equilibrium (i.e., steady state) conditions had been reached. Applicable miscibility data consists of the refrigerant/lubricant concentration, the temperature at equilibrium, and the observations of the test cell contents for evidence of immiscibility.

Phase II - Derivations Of Miscibility Plots

Phase II will consist of additional tests made up of an expanded concentration range. In addition to Phase I lubricant concentrations (i.e., 5%, 50%, 90%), lubricant concentrations by weight of 10, 20, 35, 65 and 80% will be tested for miscibility. Miscibility plots consisting of critical solution temperatures will be developed.

The basis for selecting lubricant-refrigerant combinations to be tested in Phase II will be that the combination must have demonstrated single-phase miscibility in at least one of the three test points obtained in Phase I. Assuming that these criteria are met, each of the refrigerants will be tested for miscibility with the lubricants listed below. The lubricant viscosities to be used in the tests are also noted.

- mineral oils (30 ppm moisture, acid number <0.01)
naphthenic mineral oil, ISO 32 and 68
- alkylbenzenes (<30 ppm moisture, acid number <0.01), ISO 32 and 68
- polyglycols (<50 ppm moisture, acid number <0.05)
polypropylene glycol butyl monoether, ISO 32 and 68
polypropylene glycol diol, ISO 32 and 100
modified polyglycol, ISO 32 and 68
- polyolesters (<50 ppm moisture, acid number <0.05)
penta erythritol ester mixed-acid, ISO 22 and 46
mixed-acid polyol ester, ISO 32 and 100

TEST FACILITY AND EXPERIMENTAL PROCEDURES

The test facility used in this project was designed for the purpose of measuring the miscibility of refrigerant-lubricant mixtures. Test cells with glass viewports are submerged in one of two constant temperature baths, and then the miscibility of the mixture is observed and recorded.

Test Cells

The test cells are constructed to allow for complete visibility of the lubricant/refrigerant mixture at all test conditions. Each test cell consists of a double-port seal-cap type liquid indicator, which is essentially a 1.25 inch pipe cross with sight windows screwed into opposing ports. Valves for charging the refrigerant into the cell are screwed into the other two ports. A temperature sensor can be inserted in each cell or in an adjoining reference cell exposed to the same heating or cooling conditions.

The overall volume of each test cell varies slightly; however, all were measured to have volumes around 65 ml. During charging, each cell can be filled so that the vapor space is less than 15% of the total volume. In addition, if temperature and pressure data are available, changes in the liquid concentration due to vapor space refrigerant can be calculated.

Four charged cells can be placed in a Plexiglas holder, and three such holders can be placed in a constant temperature bath to permit the testing of 12 test cells at one time.

Constant Temperature Baths

The temperature of the cells is fixed by placing them in one of two constant temperature baths. The hot bath is used to maintain temperatures from 10°C to 90°C(50°F to 194°F), while the cold bath is used for temperatures in the range of 10°C to -50°C(50°F to -58°F).

The baths are constructed of glass which allows complete visibility of the test cells and, therefore, the lubricant/refrigerant mixtures throughout the test. Figure 1 is a photograph showing an array of twelve test cells in the bath. Movable fluorescent lights are mounted behind a bath to help increase visibility.

Figure 1 Photograph of test facility.

Cold Bath

The cold bath fluid is composed of 65% pure ethylene glycol and 35% water. Pure ethylene glycol is used so that the bath fluid will be transparent. The bath is cooled with the use of an R-502 refrigeration system. A temperature controller and a heater are installed to regulate the bath temperature.

The bath is insulated on all sides to ensure a uniform temperature. The insulation on the front and back of the bath consists of a double-paned Plexiglass window mounted on the glass bath. Condensation is prevented by using a nitrogen purge of the dead air spaces. Insulation on the other sides is provided by 2 inches of styrofoam.

Hot Bath

The hot bath fluid is water with rust inhibitor added. Two inch styrofoam provides the insulation on the ends of the bath, while the insulation on the front and back of the bath is provided by a single Plexiglass window mounted on the glass leaving a half-inch air space.

Instrumentation

The precise temperature of the bath fluid is measured by two internal resistance temperature detectors (RTD). These primary temperature probes consist of a platinum RTD connected to a signal conditioner/current transmitter that provide a linear response over the temperature range -51°C (-60°F) to 149°C (300°F). A microcomputer and data acquisition hardware under the direction of a data acquisition program monitors and records signals from all instruments. Table 1 gives a summary of the range and precision of the measurements.

Table 1 Summary of measurements, ranges, and precision.

Instrument	Range	Precision
Platinum RTD & Signal Conditioner	-50°C to 150°C	$\pm 0.1^{\circ}\text{C}$
Type T Thermocouple	-50°C to 100°C	$\pm 0.5^{\circ}\text{C}$
Concentration Measurements	0% to 100%	$\pm 0.5\%$

One cell in each bath is assembled with an internal thermocouple to determine equilibrium (i.e., steady state) conditions. The cell is charged with pure lubricant to provide a "worst case" heat transfer situation. The temperature difference between the internal thermocouple and another mounted on the outside of the cell indicates when thermal equilibrium between the cell and the bath has been achieved. Steady state conditions are typically achieved about thirty minutes after a change (e.g., 5° - 10°C) in the circulating bath temperature.

Experimental Procedure

Experimental procedures have been developed for measuring refrigerant-lubricant miscibility by using the test facility described previously. The cells start out with the front and back windows removed for cleaning. After cleaning, the back window is installed and tightened. The prescribed amount of lubricant is injected with a syringe through the front window space. The front window is then replaced and tightened. A vacuum pump is hooked up to one of the valves and a vacuum is pulled to remove any dissolved moisture or air. Fittings are retightened if a failure to hold either a vacuum or a set pressure indicates that this is necessary.

Refrigerant is then injected into the cell from the refrigerant canister by using a manifold that allows for the evacuation of the connecting lines. The cells are weighed on a scale before and after the injection of the lubricant and the refrigerant. The scale has an uncertainty of ± 0.01 gram. The concentration of the liquid in each cell is calculated from the masses of refrigerant and lubricant injected. It is important to note that since the refrigerant vapor density changes as the temperature and pressure change, then the refrigerant vapor mass also varies. As a result, the liquid concentration varies slightly as the temperature and pressure change. For the experimental approach presented here, the vapor volumes are kept small; less than 15% of the total space is vapor. Therefore, the overall variation in refrigerant concentration as temperature and pressure are changed during any particular test are small. Once the desired amounts of lubricant and refrigerant have been injected into the cell, it is ready for testing.

The cells are then placed in the bath and heated or cooled to the desired temperature. The desired temperatures are 10°C increments from either 90°C to -50°C or 60°C to -50°C, depending on the refrigerant being tested. Steady state conditions are assumed when two conditions are met: first, the bath temperature is within $\pm 0.5^\circ\text{C}$ of the setpoint temperature and second, the difference between the instrumented cell and the bath temperature is within 0.5°C. At this point the characteristics of the fluid in each cell are noted.

After testing the cells through the temperature range, the cells are removed from the bath. The refrigerant/lubricant mixture is drained through one of the valves, and the cell is rinsed three times with R-113. The final cleaning of the cell is accomplished by removing the front and back window and rinsing with R-113 to remove traces of lubricant. The windows and seals are then cleaned and visually examined for defects.

SIGNIFICANT RESULTS

Test Results

Miscibility preliminary screening tests are complete for R-22, R-32, R-123, R-124, R-125, R-134, R-134a, R-142b, R-143a, and R-152a, and the following lubricants:

- polypropylene glycol butyl monoether
- mixed-acid polyol ester
- polypropylene glycol diol
- penta erythritol ester mixed-acid
- naphthenic mineral oil
- alkylbenzene
- modified polyglycol

These tests were performed at refrigerant concentrations of approximately 10%, 50%, and 95% over a temperature range of -50°C to 90°C (tests are concluded at 60°C for the higher pressure refrigerants as specified in the Work Statement). According to the Work Statement,

when cloudiness, precipitate formation, or formation of a second liquid phase is noticed, the mixture is considered immiscible. However, in the following discussion, when cloudiness or precipitate formation was observed, it will be noted as such, but when the mixture separated into two liquid phases, it will be noted as immiscible. The observations for each refrigerant/lubricant pair are provided below. These data are summarized and also presented in tables, with each table containing the data for a specific refrigerant with all of the lubricants. Appendix A contains tables of data for each refrigerant and lubricant pair.

Refrigerant Concentration

The refrigerant concentrations given in Tables 2 through 11 are nominal values for each lubricant-refrigerant test condition. The measured (actual) concentration may vary from the nominal concentration by $\pm 4\%$ (0.04). Measured concentrations are calculated as previously described and are included in the tables in Appendix A. The measured concentration represents the concentration that exists in the cell when the cell is at its lowest temperature. At this temperature, essentially all of the refrigerant in the cell is in the liquid phase. As the temperature is raised in each cell, the density of the vapor phase increases which results in the transport of refrigerant from the liquid phase to the vapor phase and, hence, an increase in lubricant concentration. However, the volume of the vapor phase decreases due to thermal expansion which diminishes some of the impact of this lubricant concentration increase.

These changes in the liquid composition with temperature are small since the vapor volume in each cell is minimized during charging. However, in order to cover the whole temperature range, a 10 to 15% vapor space is required due to thermal expansion and contraction. For this required vapor space, changes in liquid composition are noticeable for refrigerant concentrations lower than 30%. For example, for a 10% R-134a mixture with a 15% vapor volume, the liquid concentration could decrease up to 2.5% from its initial value.

R-22

Penta Erythritol Ester Mixed-Acid All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Butyl Monoether All three concentrations were miscible throughout the test temperature range.

Naphthenic Mineral Oil The 12% refrigerant mixture was miscible throughout the test temperature range. The 50% and 95% refrigerant mixtures were immiscible at temperatures below -19.6°C and -30.1°C, respectively.

Alkylbenzene All three concentrations were miscible throughout the test temperature range.

Modified Polyglycol The 49% and 95% refrigerant mixtures were miscible throughout the test temperature range. The 9% refrigerant mixture contained a highly dispersed second phase throughout the entire test temperature range.

Table 2 provides a summary of the test data for each lubricant and R-22 pair.

Table 2 Summary of miscibility data for R-22 and seven lubricants.

R-22			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	M
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	M	M
polypropylene glycol butyl monoether	M	M	M
naphthenic mineral oil	M	-20°C	-30°C
alkylbenzene	M	M	M
modified polyglycol	I	M	M

Notes: M -- miscible over the complete test temperature range
 I -- immiscible over the complete test temperature range
 --°C -- the mixture became immiscible below this temperature

R-32

Penta Erythritol Ester Mixed-Acid The 14% refrigerant mixture was miscible throughout the temperature range. Both the 49% and 95% refrigerant mixtures were immiscible below -19.6°C and -30.4°C, respectively.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester The 11% refrigerant mixture was miscible throughout the test temperature range. Slight haziness was observed for the 95% refrigerant mixture at -19.6°C. Also, both the 48% and 95% refrigerant mixtures were immiscible at temperatures below -40.4°C and -19.6°C, respectively.

Polypropylene Glycol Butyl Monoether The 14% refrigerant mixture was miscible over the entire temperature range. The 53% refrigerant mixture was immiscible at temperatures above 55.4°C and also at temperatures below -30.4°C. The 94% refrigerant mixture was immiscible at temperatures above 38.7°C and also at temperatures below -19.6°C.

Naphthenic Mineral Oil Both the 53% and 94% refrigerant mixtures were immiscible throughout the test temperature range. The 9% refrigerant mixture was immiscible below 29.7°C.

Alkylbenzene Both the 49% and 94% refrigerant mixtures were immiscible throughout the test temperature range. The 13% refrigerant mixture was immiscible below 19.8°C.

Modified Polyglycol The 48% and 12% refrigerant mixtures were slightly hazy at temperatures below 10.4°C and -19.8°C, respectively. The 94% refrigerant was miscible throughout the test temperature range.

Table 3 provides a summary of the test data for each lubricant and R-32 pair.

Table 3 Summary of miscibility data for R-32 and seven lubricants.

R-32			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	-20°C	-30°C
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	-40°C	-20°C
polypropylene glycol butyl monoether	M	60°C* -30°C	40°C* -20°C
naphthenic mineral oil	30°C	I	I
alkylbenzene	20°C	I	I
modified polyglycol	-20°C	10°C	M

Notes: M -- miscible over the complete test temperature range
I -- immiscible over the complete test temperature range
--°C -- the mixture became immiscible below this temperature
* -- the mixture became immiscible above this temperature

R-123

Penta Erythritol Ester Mixed-Acid All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Butyl Monoether All three concentrations were miscible throughout the test temperature range.

Naphthenic Mineral Oil All three concentrations were miscible throughout the test temperature range.

Alkylbenzene All three concentrations were miscible throughout the test temperature range.

Modified Polyglycol The 13% concentration was miscible throughout the test temperature range. The 46% and the 94% concentrations contained a highly dispersed second phase throughout the entire temperature range.

Table 4 provides a summary of the test data for each lubricant and R-123 pair.

Table 4 Summary of miscibility data for R-123 and seven lubricants.

R-123			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	M
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	M	M
polypropylene glycol butyl monoether	M	M	M
naphthenic mineral oil	M	M	M
alkylbenzene	M	M	M
modified polyglycol	M	I	I

Notes: M -- miscible over the complete test temperature range
I -- immiscible over the complete test temperature range
--°C -- the mixture became immiscible below this temperature

R-124

Penta Erythritol Ester Mixed-Acid All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Butyl Monoether All three concentrations were miscible throughout the test temperature range.

Naphthenic Mineral Oil The 11% refrigerant mixture was miscible throughout the test temperature range. The 52% and 96% refrigerant mixtures were immiscible at temperatures below -0.1°C and -30.0°C, respectively.

Alkylbenzene All three concentrations were miscible throughout the test temperature range.

Modified Polyglycol All three concentrations were miscible throughout the test temperature range.

Table 5 provides a summary of the test data for each lubricant and R-124 pair.

Table 5 Summary of miscibility data for R-124 and seven lubricants.

lubricant	R-124		
	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	M
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	M	M
polypropylene glycol butyl monoether	M	M	M
naphthenic mineral oil	M	0°C	-30°C
alkylbenzene	M	M	M
modified polyglycol	M	M	M

Notes: M -- miscible over the complete test temperature range
 I -- immiscible over the complete test temperature range
 --°C -- the mixture became immiscible below this temperature

R-125

Penta Erythritol Ester Mixed-Acid The 10% and 48% refrigerant mixtures were miscible throughout the test temperature range. The 96% refrigerant mixture was hazy at temperatures below 40.1°C.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester The 8% and 50% refrigerant mixtures were miscible throughout the test temperature range. The 94% refrigerant mixture was hazy at temperatures below -30.5°C.

Polypropylene Glycol Butyl Monoether The 12% and 52% refrigerant mixtures were miscible throughout the test temperature range. The 96% refrigerant mixture was hazy at temperatures below -39.8°C, and also was immiscible at temperatures above 50.1°C.

Naphthenic Mineral Oil Both the 52% and 95% refrigerant mixtures were immiscible throughout the test temperature range. The 11% refrigerant mixture was immiscible below 30.1°C.

Alkylbenzene Both the 53% and 95% refrigerant mixtures were immiscible throughout the test temperature range. The 13% refrigerant mixture was immiscible at temperatures below -0.6°C.

Modified Polyglycol The 11% refrigerant mixture were miscible throughout the entire test temperature range. The 49% refrigerant mixture was hazy at temperatures below -0.4°C. The 95% refrigerant mixture was immiscible at temperatures above 40.5°C.

Table 6 provides a summary of the test data for each lubricant and R-125 pair.

Table 6 Summary of miscibility data for R-125 and seven lubricants.

R-125			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	40°C
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	M	-30°C
polypropylene glycol butyl monoether	M	M	50°C* -40°C
naphthenic mineral oil	30°C	I	I
alkylbenzene	0°C	I	I
modified polyglycol	M	0°C	40°C*

Notes: M -- miscible over the complete test temperature range
 I -- immiscible over the complete test temperature range
 --°C -- the mixture became immiscible below this temperature
 * -- the mixture became immiscible above this temperature

R-134

Penta Erythritol Ester Mixed-Acid All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Butyl Monoether The 12% and 50% refrigerant mixtures were miscible over the entire test temperature range. The 95% refrigerant mixture was hazy at temperatures below -20.8°C.

Naphthenic Mineral Oil All three concentrations were immiscible throughout the entire test temperature range.

Alkylbenzene Both the 49% and 95% refrigerant mixtures were immiscible throughout the test temperature range. The 11% refrigerant mixture was immiscible at temperatures below -9.3°C.

Modified Polyglycol Both the 9% and 95% refrigerant mixtures were miscible throughout the test temperature range. The 48% refrigerant mixture was hazy at temperatures below -0.4°C.

Table 7 provides a summary of the test data for each lubricant and R-134 pair.

Table 7 Summary of miscibility data for R-134 and seven lubricants.

R-134			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	M
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	M	M
polypropylene glycol butyl monoether	M	M	-20°C
naphthenic mineral oil	I	I	I
alkylbenzene	-10°C	I	I
modified polyglycol	M	0°C	M

Notes: M -- miscible over the complete test temperature range
I -- immiscible over the complete test temperature range
--°C -- the mixture became immiscible below this temperature

R-134a

Penta Erythritol Ester Mixed-Acid A highly dispersed second phase was observed for the 95% refrigerant mixture at temperatures below -40.1°C. The 12% and 51% refrigerant mixtures were miscible throughout the temperature range.

Polypropylene Glycol Diol Haziness was observed for the 95% refrigerant mixture at temperatures below -10.1°C. Both the 53% and 9% refrigerant mixtures were miscible throughout the temperature range.

Mixed-Acid Polyol Ester A highly dispersed second phase was observed for the 52% refrigerant mixture at temperatures below 10.5°C. The 10% or the 95% refrigerant mixtures were miscible over the entire temperature range.

Polypropylene Glycol Butyl Monoether Both the 9% and 51% refrigerant mixtures were miscible over the entire temperature range. The 95% refrigerant mixture was immiscible at temperatures greater than 80°C.

Naphthenic Mineral Oil Both the 49% and the 95% refrigerant mixtures were immiscible throughout the temperature range. The 10% refrigerant mixture was immiscible at temperatures below 19.9°C.

Alkylbenzene Both the 52% and the 95% refrigerant mixtures were immiscible throughout the test temperature range. The 13% refrigerant mixture was immiscible at temperatures below -0.2°C.

Modified Polyglycol Both the 52% and the 95% refrigerant mixtures were hazy at temperatures below 0.1°C. The 10% refrigerant mixture was miscible throughout the test temperature range.

Table 8 provides a summary of the test data for each lubricant and R-134a pair.

Table 8 Summary of miscibility data for R-134a and seven lubricants.

R-134a			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	-40°C
polypropylene glycol diol	M	M	-10°C
mixed-acid polyol ester	M	10°C	M
polypropylene glycol butyl monoether	M	M	80°C*
naphthenic mineral oil	20°C	I	I
alkylbenzene	0°C	I	I
modified polyglycol	M	0°C	0°C

Notes: M -- miscible over the complete test temperature range
I -- immiscible over the complete test temperature range
--°C -- the mixture became immiscible below this temperature
* -- the mixture became immiscible above this temperature

R-142b

Penta Erythritol Ester Mixed-Acid All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Butyl Monoether All three concentrations were miscible throughout the test temperature range.

Naphthenic Mineral Oil The 9% and the 95% refrigerant concentrations were miscible throughout the test temperature range. The 50% mixture was immiscible at a temperature of -48.3°C.

Alkylbenzene All three concentrations were miscible over the entire temperature range.

Modified Polyglycol All three concentrations were miscible over the entire temperature range.

Table 9 provides a summary of the test data for each lubricant and R-142b pair.

Table 9 Summary of miscibility data for R-142b and seven lubricants.

R-142b			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	M
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	M	M
polypropylene glycol butyl monoether	M	M	M
naphthenic mineral oil	M	-50°C	M
alkylbenzene	M	M	M
modified polyglycol	M	M	M

Notes: M -- miscible over the complete test temperature range
 I -- immiscible over the complete test temperature range
 --°C -- the mixture became immiscible below this temperature

R-143a

Penta Erythritol Ester Mixed-Acid The 8% refrigerant mixture was miscible over the entire temperature range. The 50% and 95% refrigerant mixtures were immiscible over the entire temperature range.

Polypropylene Glycol Diol The 13% refrigerant mixture was miscible over the entire temperature range. The 51% and 95% refrigerant mixtures were immiscible over the entire temperature range.

Mixed-Acid Polyol Ester The 14% and 96% refrigerant mixtures were miscible over the entire temperature range. The 49% refrigerant mixture were immiscible over the entire temperature range.

Polypropylene Glycol Butyl Monoether The 12% refrigerant mixture was miscible over the entire temperature range. The 47% and 95% refrigerant mixtures were immiscible over the entire temperature range.

Naphthenic Mineral Oil The 14% refrigerant mixture was immiscible at temperatures below 40.2°C. The 54% and 95% refrigerant mixtures were immiscible over the entire temperature range.

Alkylbenzene The 14% refrigerant mixture was immiscible at temperatures below -0.2°C. The 52% and 95% refrigerant mixtures were immiscible over the entire temperature range.

Modified Polyglycol The 13% refrigerant mixture was hazy at temperatures below -39.6°C. The 49% refrigerant mixture was immiscible at temperatures above 19.6°C, and at -49.6°C. The 49% refrigerant mixture was also hazy at temperatures below -10.0°C. The 95% refrigerant mixture was immiscible at temperatures above 19.6°C and below -39.6°C.

Table 10 provides a summary of the test data for each lubricant and R-143a pair.

Table 10 Summary of miscibility data for R-143a and seven lubricants.

R-143a			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	I	I
polypropylene glycol diol	M	I	I
mixed-acid polyol ester	M	I	M
polypropylene glycol butyl monoether	M	I	I
naphthenic mineral oil	40°C	I	I
alkylbenzene	0°C	I	I
modified polyglycol	-40°C	20°C* -10°C	20°C* -40°C

Notes: M -- miscible over the complete test temperature range
 I -- immiscible over the complete test temperature range
 --°C -- the mixture became immiscible below this temperature
 * -- the mixture became immiscible above this temperature

R-152a

Penta Erythritol Ester Mixed-Acid All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Diol All three concentrations were miscible throughout the test temperature range.

Mixed-Acid Polyol Ester All three concentrations were miscible throughout the test temperature range.

Polypropylene Glycol Butyl Monoether All three concentrations were miscible throughout the test temperature range.

Naphthenic Mineral Oil The 52% refrigerant mixture was immiscible throughout the temperature range. The 13% and 95% refrigerant mixtures were immiscible at temperatures below 10.3°C and 50.0°C, respectively.

Alkylbenzene The 12%, 47%, and 96% refrigerant mixtures were immiscible at temperatures below -40.2°C, 40.5°C, and -9.7°C, respectively.

Modified Polyglycol All three concentrations were miscible throughout the test temperature range.

Table 11 provides a summary of the test data for each lubricant and R-152a pair.

Table 11 Summary of miscibility data for R-152a and seven lubricants.

R-152a			
lubricant	nominal 10% refrigerant	nominal 50% refrigerant	nominal 95% refrigerant
penta erythritol ester mixed-acid	M	M	M
polypropylene glycol diol	M	M	M
mixed-acid polyol ester	M	M	M
polypropylene glycol butyl monoether	M	M	M
naphthenic mineral oil	10°C	I	50°C
alkylbenzene	-40°C	40°C	-10°C
modified polyglycol	M	M	M

Notes: M -- miscible over the complete test temperature range
I -- immiscible over the complete test temperature range
--°C -- the mixture became immiscible below this temperature

REFRIGERANT AND LUBRICANT PURITY

The lubricants used in this testing were to meet certain moisture content, acid number, iron content, and copper content requirements. These tests were conducted according to the standards recommended in the Work Statement, and the results are shown in Table 12. Prior to testing, each lubricant was heated and evacuated to remove dissolved air or water. This technique was also used prior to all miscibility testing. The refrigerants were used as delivered from the manufacturer.

Table 12 Characteristics of the test lubricants.

Lubricant	Moisture (ppm)	Iron Content (microgram/gram)	Copper Content (microgram/gram)	Acid Number
penta erythritol ester mixed-acid	33	< 1	< 1	0.018
polypropylene glycol diol	68	< 1	< 1	0.007
mixed-acid polyol ester	59	< 1	< 1	0.229
polypropylene glycol butyl monoether	62	< 1	< 1	0.002
naphthenic mineral oil	31	< 1	< 1	0.004
alkylbenzene	28	< 1	< 1	0.006
modified polyglycol	67	< 1	< 1	0.015

CONCLUSIONS

Phase I of the Miscibility of Lubricants With Refrigerants project is complete. Miscibility data have been obtained for a variety of non-CFC refrigerants and their potential lubricants. Ten (10) different refrigerants and seven (7) different lubricants were investigated. A test facility has been described and experimental procedures have been documented. The data have been summarized as well as presented in detail in the appendices. The data presented herein will be used to help determine the scope of Phase II of this project. Phase II will consist of testing five additional concentrations (20, 35, 65, 80, and 90% refrigerant) of each refrigerant/lubricant combination previously tested as well as eight concentrations (10, 20, 35, 50, 65, 80, 90, 95% refrigerant) of the same refrigerants with higher viscosity lubricants of the same base stocks. However, the R-134/naphthenic mineral oil combination will not be tested further. Additionally, from the results of Phase I, it appears that each of the refrigerants tested are miscible with at least one of the lubricants, with the exception of R-143a and R-134a, which exhibit partial miscibility with at least one of the refrigerants.

COMPLIANCE WITH AGREEMENT

The work statement designated temperatures ranging from 90°C to -50°C in ten degree increments. The exact temperatures (e.g., 90, 80, ..., -50) are not necessarily being achieved. However, steady state temperatures near these temperatures at approximately 10°C increments are being achieved and recorded. Any immiscibility that occurs will certainly be observable by using this approach. The work statement also specified refrigerant concentrations of 95, 50, and 10% refrigerant. For the data presented herein, the refrigerant concentrations are within $\pm 4\%$ from the above stated values. Exact refrigerant concentrations for each test are given, along with other data, in Appendix A. Also, the work statement stated that the lubricants meet certain purity requirements as previously discussed. In particular, it was stated that the moisture content of the ester and glycol based lubricants were not to exceed 50 ppm. These lubricants were found to contain slightly higher moisture levels as shown in Table 12. Also, the mixed-acid polyol ester was tested to have an acid number of 0.229, whereas the required acid number was to be less than 0.05.

Appendix A - Tabulation of Experimental Data

Tables A.1 through A.70 provide a summary of the test data for each lubricant and refrigerant pair.

Table A.1 Observations for R-22/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.49	0.94
60.4	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.3	clear	clear	clear
20.2	clear	clear	clear
10.3	clear	clear	clear
-0.3	clear	clear	clear
-9.9	clear	clear	clear
-20.0	clear	clear	clear
-30.4	clear	clear	clear
-40.3	clear	clear	clear
-49.6	clear	clear	clear

Table A.2 Observations for R-22/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.53	0.95
60.4	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.3	clear	clear	clear
20.2	clear	clear	clear
10.3	clear	clear	clear
-0.3	clear	clear	clear
-9.9	clear	clear	clear
-20.0	clear	clear	clear
-30.4	clear	clear	clear
-40.3	clear	clear	clear
-49.6	clear	clear	clear

Table A.3 Observations for R-22/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.48	0.95
60.4	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.3	clear	clear	clear
20.2	clear	clear	clear
10.3	clear	clear	clear
-0.3	clear	clear	clear
-9.9	clear	clear	clear
-20.0	clear	clear	clear
-30.4	clear	clear	clear
-40.3	clear	clear	clear
-49.6	clear	clear	clear

Table A.4 Observations for R-22/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.52	0.95
60.4	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.3	clear	clear	clear
20.2	clear	clear	clear
10.3	clear	clear	clear
-0.3	clear	clear	clear
-9.9	clear	clear	clear
-20.0	clear	clear	clear
-30.4	clear	clear	clear
-40.3	clear	clear	clear
-49.6	clear	clear	clear

Table A.5 Observations for R-22/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.50	0.95
60.2	clear	clear	clear
49.6	clear	clear	clear
39.6	clear	clear	clear
30.4	clear	clear	clear
20.1	clear	clear	clear
10.2	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-19.6	clear	two phase	clear
-30.1	clear	two phase	two phase
-40.1	clear	two phase	two phase
-49.4	clear	two phase	two phase

Table A.6 Observations for R-22/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.51	0.95
60.2	clear	clear	clear
49.6	clear	clear	clear
39.6	clear	clear	clear
30.4	clear	clear	clear
20.1	clear	clear	clear
10.2	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-19.6	clear	clear	clear
-30.1	clear	clear	clear
-40.1	clear	clear	clear
-49.4	clear	clear	clear

Table A.7 Observations for R-22/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.49	0.95
59.9	highly dispersed second phase	clear	clear
50.2	highly dispersed second phase	clear	clear
39.8	highly dispersed second phase	clear	clear
29.8	highly dispersed second phase	clear	clear
19.6	highly dispersed second phase	clear	clear
10.4	highly dispersed second phase	clear	clear
0.0	highly dispersed second phase	clear	clear
-10.0	highly dispersed second phase	clear	clear
-19.8	highly dispersed second phase	clear	clear
-29.8	highly dispersed second phase	clear	clear
-39.6	highly dispersed second phase	clear	clear
-49.6	highly dispersed second phase	clear	clear

Table A.8 Observations for R-32/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.14	0.49	0.95
55.4	clear	clear	clear
49.9	clear	clear	clear
38.7	clear	clear	clear
30.2	clear	clear	clear
20.3	clear	clear	clear
11.3	clear	clear	clear
-0.3	clear	clear	clear
-9.6	clear	clear	clear
-19.6	clear	two phase	clear
-30.4	clear	two phase	two phase
-40.4	clear	two phase	two phase
-48.3	clear	two phase	two phase

Table A.9 Observations for R-32/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.14	0.50	0.95
55.4	clear	clear	clear
49.9	clear	clear	clear
38.7	clear	clear	clear
30.2	clear	clear	clear
20.3	clear	clear	clear
11.3	clear	clear	clear
-0.3	clear	clear	clear
-9.6	clear	clear	clear
-19.6	clear	clear	clear
-30.4	clear	clear	clear
-40.4	clear	clear	clear
-48.3	clear	clear	clear

Table A.10 Observations for R-32/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.48	0.95
55.4	clear	clear	clear
49.9	clear	clear	clear
38.7	clear	clear	clear
30.2	clear	clear	clear
20.3	clear	clear	clear
11.3	clear	clear	clear
-0.3	clear	clear	clear
-9.6	clear	clear	clear
-19.6	clear	clear	slightly hazy
-30.4	clear	clear	hazy
-40.4	clear	hazy	two phase
-48.3	clear	two phase	two phase

Table A.11 Observations for R-32/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.14	0.53	0.94
55.4	clear	two phase	two phase
49.9	clear	clear	two phase
38.7	clear	clear	two phase
30.2	clear	clear	clear
20.3	clear	clear	clear
11.3	clear	clear	clear
-0.3	clear	clear	clear
-9.6	clear	clear	clear
-19.6	clear	clear	two phase
-30.4	clear	two phase	two phase
-40.4	clear	two phase	two phase
-48.3	clear	two phase	two phase

Table A.12 Observations for R-32/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.53	0.94
57.0	clear	two phase	two phase
50.0	clear	two phase	two phase
40.2	clear	two phase	two phase
29.7	slightly hazy	two phase	two phase
19.8	very hazy	two phase	two phase
11.0	very hazy	two phase	two phase
-0.2	very hazy	two phase	two phase
-9.8	two phase	two phase	two phase
-19.6	two phase	two phase	two phase
-30.3	two phase	two phase	two phase
-40.4	two phase	two phase	two phase
-48.0	two phase	two phase	two phase

Table A.13 Observations for R-32/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.49	0.94
57.0	clear	two phase	two phase
50.0	clear	two phase	two phase
40.2	clear	two phase	two phase
29.7	clear	two phase	two phase
19.8	hazy	two phase	two phase
11.0	hazy	two phase	two phase
-0.2	hazy	two phase	two phase
-9.8	two phase	two phase	two phase
-19.6	two phase	two phase	two phase
-30.3	two phase	two phase	two phase
-40.4	two phase	two phase	two phase
-48.0	two phase	two phase	two phase

Table A.14 Observations for R-32/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.48	0.94
59.9	clear	clear	clear
50.2	clear	clear	clear
39.8	clear	clear	clear
29.8	clear	clear	clear
19.6	clear	clear	clear
10.4	clear	slightly hazy	clear
0.0	clear	slightly hazy	clear
-10.0	clear	slightly hazy	clear
-19.8	slightly hazy	slightly hazy	clear
-29.8	slightly hazy	hazy	clear
-39.6	slightly hazy	hazy	clear
-49.6	slightly hazy	hazy	clear

Table A.15 Observations for R-123/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.52	0.95
60.8	clear	clear	clear
50.7	clear	clear	clear
40.7	clear	clear	clear
30.2	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.4	clear	clear	clear
-9.6	clear	clear	clear
-19.7	clear	clear	clear
-30.5	clear	clear	clear
-40.3	clear	clear	clear
-49.0	clear	clear	clear

Table A.16 Observations for R-123/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.50	0.95
60.8	clear	clear	clear
50.7	clear	clear	clear
40.7	clear	clear	clear
30.2	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.4	clear	clear	clear
-9.6	clear	clear	clear
-19.7	clear	clear	clear
-30.5	clear	clear	clear
-40.3	clear	clear	clear
-49.0	clear	clear	clear

Table A.17 Observations for R-123/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.51	0.94
60.8	clear	clear	clear
50.7	clear	clear	clear
40.7	clear	clear	clear
30.2	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.4	clear	clear	clear
-9.6	clear	clear	clear
-19.7	clear	clear	clear
-30.5	clear	clear	clear
-40.3	clear	clear	clear
-49.0	clear	clear	clear

Table A.18 Observations for R-123/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.48	0.95
60.8	clear	clear	clear
50.7	clear	clear	clear
40.7	clear	clear	clear
30.2	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.4	clear	clear	clear
-9.6	clear	clear	clear
-19.7	clear	clear	clear
-30.5	clear	clear	clear
-40.3	clear	clear	clear
-49.0	clear	clear	clear

Table A.19 Observations for R-123/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.53	0.94
60.2	clear	clear	clear
49.6	clear	clear	clear
39.6	clear	clear	clear
30.4	clear	clear	clear
20.1	clear	clear	clear
10.2	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-19.6	clear	clear	clear
-30.1	clear	clear	clear
-40.1	clear	clear	clear
-49.4	clear	clear	clear

Table A.20 Observations for R-123/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.50	0.95
60.2	clear	clear	clear
49.6	clear	clear	clear
39.6	clear	clear	clear
30.4	clear	clear	clear
20.1	clear	clear	clear
10.2	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-19.6	clear	clear	clear
-30.1	clear	clear	clear
-40.1	clear	clear	clear
-49.4	clear	clear	clear

Table A.21 Observations for R-123/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.46	0.94
59.9	clear	small particles throughout	highly dispersed second phase
50.2	clear	highly dispersed second phase	highly dispersed second phase
39.8	clear	highly dispersed second phase	highly dispersed second phase
29.8	clear	highly dispersed second phase	highly dispersed second phase
19.6	clear	highly dispersed second phase	highly dispersed second phase
10.4	clear	highly dispersed second phase	highly dispersed second phase
0.0	clear	highly dispersed second phase	highly dispersed second phase
-10.0	clear	highly dispersed second phase	highly dispersed second phase
-19.8	clear	highly dispersed second phase	highly dispersed second phase
-29.8	clear	highly dispersed second phase	highly dispersed second phase
-39.6	clear	highly dispersed second phase	highly dispersed second phase
-49.6	clear	highly dispersed second phase	highly dispersed second phase

Table A.22 Observations for R-124/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.14	0.54	0.95
89.7	clear	clear	clear
79.6	clear	clear	clear
69.8	clear	clear	clear
60.0	clear	clear	clear
50.3	clear	clear	clear
40.2	clear	clear	clear
30.1	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-20.4	clear	clear	clear
-30.0	clear	clear	clear
-40.5	clear	clear	clear
-49.7	clear	clear	clear

Table A.23 Observations for R-124/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.52	0.96
89.7	clear	clear	clear
79.6	clear	clear	clear
69.8	clear	clear	clear
60.0	clear	clear	clear
50.3	clear	clear	clear
40.2	clear	clear	clear
30.1	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-20.4	clear	clear	clear
-30.0	clear	clear	clear
-40.5	clear	clear	clear
-49.7	clear	clear	clear

Table A.24 Observations for R-124/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.46	0.94
89.7	clear	clear	clear
79.6	clear	clear	clear
69.8	clear	clear	clear
60.0	clear	clear	clear
50.3	clear	clear	clear
40.2	clear	clear	clear
30.1	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-20.4	clear	clear	clear
-30.0	clear	clear	clear
-40.5	clear	clear	clear
-49.7	clear	clear	clear

Table A.25 Observations for R-124/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.51	0.96
89.7	clear	clear	clear
79.6	clear	clear	clear
69.8	clear	clear	clear
60.0	clear	clear	clear
50.3	clear	clear	clear
40.2	clear	clear	clear
30.1	clear	clear	clear
19.9	clear	clear	clear
10.1	clear	clear	clear
-0.3	clear	clear	clear
-9.5	clear	clear	clear
-20.4	clear	clear	clear
-30.0	clear	clear	clear
-40.5	clear	clear	clear
-49.7	clear	clear	clear

Table A.26 Observations for R-124/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.52	0.96
88.5	clear	clear	clear
80.1	clear	clear	clear
70.1	clear	clear	clear
60.2	clear	clear	clear
50.0	clear	clear	clear
40.5	clear	clear	clear
30.4	clear	clear	clear
20.1	clear	clear	clear
10.3	clear	clear	clear
-0.1	clear	two phase	clear
-9.7	clear	two phase	clear
-19.8	clear	two phase	clear
-30.0	clear	two phase	two phase
-40.2	clear	two phase	two phase
-49.5	clear	two phase	two phase

Table A.27 Observations for R-124/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.51	0.96
88.5	clear	clear	clear
80.1	clear	clear	clear
70.1	clear	clear	clear
60.2	clear	clear	clear
50.0	clear	clear	clear
40.5	clear	clear	clear
30.4	clear	clear	clear
20.1	clear	clear	clear
10.3	clear	clear	clear
-0.1	clear	clear	clear
-9.7	clear	clear	clear
-19.8	clear	clear	clear
-30.0	clear	clear	clear
-40.2	clear	clear	clear
-49.5	clear	clear	clear

Table A.28 Observations for R-124/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.50	0.94
87.6	clear	clear	clear
79.6	clear	clear	clear
69.7	clear	clear	clear
59.6	clear	clear	clear
49.8	clear	clear	clear
39.6	clear	clear	clear
29.6	clear	clear	clear
19.8	clear	clear	clear
9.5	clear	clear	clear
0.1	clear	clear	clear
-9.7	clear	clear	clear
-20.3	clear	clear	clear
-30.2	clear	clear	clear
-40.3	clear	clear	clear
-50.0	clear	clear	clear

Table A.29 Observations for R-125/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.10	0.48	0.96
60.5	clear	clear	clear
50.1	clear	clear	clear
40.1	clear	clear	hazy
30.3	clear	clear	hazy
20.1	clear	clear	slightly hazy
10.7	clear	clear	slightly hazy
-0.1	clear	clear	slightly hazy
-9.7	clear	clear	slightly hazy
-20.2	clear	clear	slightly hazy
-30.5	clear	clear	slightly hazy
-39.8	clear	clear	slightly hazy
-47.8	clear	clear	slightly hazy

Table A.30 Observations for R-125/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.48	0.96
60.5	clear	clear	clear
50.1	clear	clear	clear
40.1	clear	clear	clear
30.3	clear	clear	clear
20.1	clear	clear	clear
10.7	clear	clear	clear
-0.1	clear	clear	clear
-9.7	clear	clear	clear
-20.2	clear	clear	clear
-30.5	clear	clear	clear
-39.8	clear	clear	clear
-47.8	clear	clear	clear

Table A.31 Observations for R-125/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.08	0.50	0.94
60.5	clear	clear	clear
50.1	clear	clear	clear
40.1	clear	clear	clear
30.3	clear	clear	clear
20.1	clear	clear	clear
10.7	clear	clear	clear
-0.1	clear	clear	clear
-9.7	clear	clear	clear
-20.2	clear	clear	clear
-30.5	clear	clear	slightly hazy
-39.8	clear	clear	hazy
-47.8	clear	clear	hazy

Table A.32 Observations for R-125/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.52	0.96
60.5	clear	clear	two phase
50.1	clear	clear	two phase
40.1	clear	clear	clear
30.3	clear	clear	clear
20.1	clear	clear	clear
10.7	clear	clear	clear
-0.1	clear	clear	clear
-9.7	clear	clear	clear
-20.2	clear	clear	clear
-30.5	clear	clear	clear
-39.8	clear	clear	slightly hazy
-47.8	clear	clear	hazy

Table A.33 Observations for R-125/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.52	0.95
59.8	clear	two phase	two phase
49.2	clear	two phase	two phase
40.0	clear	two phase	two phase
30.1	two phase	two phase	two phase
20.1	two phase	two phase	two phase
10.5	two phase	two phase	two phase
-0.6	two phase	two phase	two phase
-9.3	two phase	two phase	two phase
-19.7	two phase	two phase	two phase
-30.2	two phase	two phase	two phase
-39.8	two phase	two phase	two phase
-47.3	two phase	two phase	two phase

Table A.34 Observations for R-125/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.53	0.95
59.8	clear	two phase	two phase
49.2	clear	two phase	two phase
40.0	clear	two phase	two phase
30.1	clear	two phase	two phase
20.1	clear	two phase	two phase
10.5	clear	two phase	two phase
-0.6	two phase	two phase	two phase
-9.3	two phase	two phase	two phase
-19.7	two phase	two phase	two phase
-30.2	two phase	two phase	two phase
-39.8	two phase	two phase	two phase
-47.3	two phase	two phase	two phase

Table A.35 Observations for R-125/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.49	0.95
59.9	clear	clear	two phase
50.2	clear	clear	two phase
40.5	clear	clear	two phase
30.1	clear	clear	clear
19.7	clear	clear	clear
10.3	clear	clear	clear
-0.4	clear	hazy	clear
-9.7	clear	hazy	clear
-19.6	clear	hazy	clear
-30.1	clear	hazy	clear
-40.5	clear	hazy	clear
-49.6	clear	hazy	clear

Table A.36 Observations for R-134/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.48	0.95
59.6	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.1	clear	clear	clear
10.9	clear	clear	clear
-3.0	clear	clear	clear
-10.1	clear	clear	clear
-20.8	clear	clear	clear
-29.7	clear	clear	clear
-39.7	clear	clear	clear
-47.6	clear	clear	clear

Table A.37 Observations for R-134/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.49	0.94
59.6	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.1	clear	clear	clear
10.9	clear	clear	clear
-3.0	clear	clear	clear
-10.1	clear	clear	clear
-20.8	clear	clear	clear
-29.7	clear	clear	clear
-39.7	clear	clear	clear
-47.6	clear	clear	clear

Table A.38 Observations for R-134/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.10	0.47	0.95
59.6	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.1	clear	clear	clear
10.9	clear	clear	clear
-3.0	clear	clear	clear
-10.1	clear	clear	clear
-20.8	clear	clear	clear
-29.7	clear	clear	clear
-39.7	clear	clear	clear
-47.6	clear	clear	clear

Table A.39 Observations for R-134/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.50	0.95
59.6	clear	clear	clear
50.3	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.1	clear	clear	clear
10.9	clear	clear	clear
-3.0	clear	clear	clear
-10.1	clear	clear	clear
-20.8	clear	clear	slightly hazy
-29.7	clear	clear	slightly hazy
-39.7	clear	clear	slightly hazy
-47.6	clear	clear	slightly hazy

Table A.40 Observations for R-134/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.48	0.95
59.8	two phase	two phase	two phase
49.2	two phase	two phase	two phase
40.0	two phase	two phase	two phase
30.1	two phase	two phase	two phase
20.1	two phase	two phase	two phase
10.5	two phase	two phase	two phase
-0.6	two phase	two phase	two phase
-9.3	two phase	two phase	two phase
-19.7	two phase	two phase	two phase
-30.2	two phase	two phase	two phase
-39.8	two phase	two phase	two phase
-47.3	two phase	two phase	two phase

Table A.41 Observations for R-134/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.49	0.95
59.8	clear	two phase	two phase
49.2	clear	two phase	two phase
40.0	clear	two phase	two phase
30.1	clear	two phase	two phase
20.1	clear	two phase	two phase
10.5	clear	two phase	two phase
-0.6	clear	two phase	two phase
-9.3	two phase	two phase	two phase
-19.7	two phase	two phase	two phase
-30.2	two phase	two phase	two phase
-39.8	two phase	two phase	two phase
-47.3	two phase	two phase	two phase

Table A.42 Observations for R-134/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.48	0.95
59.9	clear	clear	clear
50.2	clear	clear	clear
40.5	clear	clear	clear
30.1	clear	clear	clear
19.7	clear	clear	clear
10.3	clear	clear	clear
-0.4	clear	hazy	clear
-9.7	clear	hazy	clear
-19.6	clear	hazy	clear
-30.1	clear	hazy	clear
-40.5	clear	hazy	clear
-49.6	clear	hazy	clear

Table A.43 Observations for R-134a/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.51	0.95
87.4	clear	clear	clear
80.0	clear	clear	clear
69.9	clear	clear	clear
60.4	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.3	clear	clear	clear
10.5	clear	clear	clear
0.1	clear	clear	clear
-10.1	clear	clear	clear
-20.2	clear	clear	clear
-30.1	clear	clear	clear
-40.1	clear	clear	highly dispersed second phase
-49.4	clear	clear	highly dispersed second phase

Table A.44 Observations for R-134a/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.53	0.95
87.4	clear	clear	clear
80.0	clear	clear	clear
69.9	clear	clear	clear
60.4	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.3	clear	clear	clear
10.5	clear	clear	clear
0.1	clear	clear	clear
-10.1	clear	clear	slightly hazy
-20.2	clear	clear	hazy
-30.1	clear	clear	very hazy
-40.1	clear	clear	very hazy
-49.4	clear	clear	very hazy

Table A.45 Observations for R-134a/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.10	0.52	0.95
87.4	clear	clear	clear
80.0	clear	clear	clear
69.9	clear	clear	clear
60.4	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.3	clear	clear	clear
10.5	clear	highly dispersed second phase	clear
0.1	clear	highly dispersed second phase	clear
-10.1	clear	highly dispersed second phase	clear
-20.2	clear	highly dispersed second phase	clear
-30.1	clear	highly dispersed second phase	clear
-40.1	clear	highly dispersed second phase	clear
-49.4	clear	highly dispersed second phase	clear

Table A.46 Observations for R-134a/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.51	0.95
87.4	clear	clear	two phase
80.0	clear	clear	two phase
69.9	clear	clear	clear
60.4	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.3	clear	clear	clear
10.5	clear	clear	clear
0.1	clear	clear	clear
-10.1	clear	clear	clear
-20.2	clear	clear	clear
-30.1	clear	clear	clear
-40.1	clear	clear	clear
-49.4	clear	clear	clear

Table A.47 Observations for R-134a/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.10	0.49	0.95
89.4	clear	two phase	two phase
80.3	clear	two phase	two phase
70.2	clear	two phase	two phase
60.2	clear	two phase	two phase
50.4	clear	two phase	two phase
40.2	clear	two phase	two phase
30.4	clear	two phase	two phase
19.9	two phase	two phase	two phase
10.2	two phase	two phase	two phase
-0.2	two phase	two phase	two phase
-10.0	two phase	two phase	two phase
-20.5	two phase	two phase	two phase
-30.2	two phase	two phase	two phase
-40.2	two phase	two phase	two phase
-48.3	two phase	two phase	two phase

Table A.48 Observations for R-134a/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.52	0.95
89.4	clear	two phase	two phase
80.3	clear	two phase	two phase
70.2	clear	two phase	two phase
60.2	clear	two phase	two phase
50.4	clear	two phase	two phase
40.2	clear	two phase	two phase
30.4	clear	two phase	two phase
19.9	clear	two phase	two phase
10.2	clear	two phase	two phase
-0.2	two phase	two phase	two phase
-10.0	two phase	two phase	two phase
-20.5	two phase	two phase	two phase
-30.2	two phase	two phase	two phase
-40.2	two phase	two phase	two phase
-48.3	two phase	two phase	two phase

Table A.49 Observations for R-134a/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.10	0.52	0.95
87.6	clear	clear	clear
79.6	clear	clear	clear
69.7	clear	clear	clear
59.6	clear	clear	clear
49.8	clear	clear	clear
39.6	clear	clear	clear
29.6	clear	clear	clear
19.8	clear	clear	clear
9.5	clear	clear	clear
0.1	clear	slightly hazy	slightly hazy
-9.7	clear	hazy	hazy
-20.3	clear	hazy	hazy
-30.2	clear	hazy	hazy
-40.3	clear	hazy	hazy
-50.0	clear	hazy	hazy

Table A.50 Observations for R-142b/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.49	0.95
86.9	clear	clear	clear
80.6	clear	clear	clear
69.8	clear	clear	clear
60.6	clear	clear	clear
50.7	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.5	clear	clear	clear
9.7	clear	clear	clear
-1.4	clear	clear	clear
-9.8	clear	clear	clear
-19.1	clear	clear	clear
-31.5	clear	clear	clear
-40.5	clear	clear	clear
-48.7	clear	clear	clear

Table A.51 Observations for R-142b/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.47	0.95
86.9	clear	clear	clear
80.6	clear	clear	clear
69.8	clear	clear	clear
60.6	clear	clear	clear
50.7	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.5	clear	clear	clear
9.7	clear	clear	clear
-1.4	clear	clear	clear
-9.8	clear	clear	clear
-19.1	clear	clear	clear
-31.5	clear	clear	clear
-40.5	clear	clear	clear
-48.7	clear	clear	clear

Table A.52 Observations for R-142b/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.46	0.95
86.9	clear	clear	clear
80.6	clear	clear	clear
69.8	clear	clear	clear
60.6	clear	clear	clear
50.7	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.5	clear	clear	clear
9.7	clear	clear	clear
-1.4	clear	clear	clear
-9.8	clear	clear	clear
-19.1	clear	clear	clear
-31.5	clear	clear	clear
-40.5	clear	clear	clear
-48.7	clear	clear	clear

Table A.53 Observations for R-142b/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.47	0.95
86.9	clear	clear	clear
80.6	clear	clear	clear
69.8	clear	clear	clear
60.6	clear	clear	clear
50.7	clear	clear	clear
40.3	clear	clear	clear
30.0	clear	clear	clear
20.5	clear	clear	clear
9.7	clear	clear	clear
-1.4	clear	clear	clear
-9.8	clear	clear	clear
-19.1	clear	clear	clear
-31.5	clear	clear	clear
-40.5	clear	clear	clear
-48.7	clear	clear	clear

Table A.54 Observations for R-142b/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.50	0.95
89.4	clear	clear	clear
80.3	clear	clear	clear
70.2	clear	clear	clear
60.2	clear	clear	clear
50.4	clear	clear	clear
40.2	clear	clear	clear
30.4	clear	clear	clear
19.9	clear	clear	clear
10.2	clear	clear	clear
-0.2	clear	clear	clear
-10.0	clear	clear	clear
-20.5	clear	clear	clear
-30.2	clear	clear	clear
-40.2	clear	clear	clear
-48.3	clear	two phase	clear

Table A.55 Observations for R-142b/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.10	0.53	0.95
89.4	clear	clear	clear
80.3	clear	clear	clear
70.2	clear	clear	clear
60.2	clear	clear	clear
50.4	clear	clear	clear
40.2	clear	clear	clear
30.4	clear	clear	clear
19.9	clear	clear	clear
10.2	clear	clear	clear
-0.2	clear	clear	clear
-10.0	clear	clear	clear
-20.5	clear	clear	clear
-30.2	clear	clear	clear
-40.2	clear	clear	clear
-48.3	clear	clear	clear

Table A.56 Observations for R-142b/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.09	0.53	0.95
87.6	clear	clear	clear
79.6	clear	clear	clear
69.7	clear	clear	clear
59.6	clear	clear	clear
49.8	clear	clear	clear
39.6	clear	clear	clear
29.6	clear	clear	clear
19.8	clear	clear	clear
9.5	clear	clear	clear
0.1	clear	clear	clear
-9.7	clear	clear	clear
-20.3	clear	clear	clear
-30.2	clear	clear	clear
-40.3	clear	clear	clear
-50.0	clear	clear	clear

Table A.57 Observations for R-143a/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.08	0.50	0.95
60.6	clear	two phase	two phase
50.1	clear	two phase	two phase
40.1	clear	two phase	two phase
30.6	clear	two phase	two phase
20.9	clear	two phase	two phase
11.0	clear	two phase	two phase
0.2	clear	two phase	two phase
-9.5	clear	two phase	two phase
-19.3	clear	two phase	two phase
-31.0	clear	two phase	two phase
-40.3	clear	two phase	two phase
-48.0	clear	two phase	two phase

Table A.58 Observations for R-143a/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.51	0.95
60.6	clear	two phase	two phase
50.1	clear	two phase	two phase
40.1	clear	two phase	two phase
30.6	clear	two phase	two phase
20.9	clear	two phase	two phase
11.0	clear	two phase	two phase
0.2	clear	two phase	two phase
-9.5	clear	two phase	two phase
-19.3	clear	two phase	two phase
-31.0	clear	two phase	two phase
-40.3	clear	two phase	two phase
-48.0	clear	two phase	two phase

Table A.59 Observations for R-143a/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.14	0.49	0.96
60.6	clear	two phase	clear
50.1	clear	two phase	clear
40.1	clear	two phase	clear
30.6	clear	two phase	clear
20.9	clear	two phase	clear
11.0	clear	two phase	clear
0.2	clear	two phase	clear
-9.5	clear	two phase	clear
-19.3	clear	two phase	clear
-31.0	clear	two phase	clear
-40.3	clear	two phase	clear
-48.0	clear	two phase	clear

Table A.60 Observations for R-143a/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.47	0.95
60.6	clear	two phase	two phase
50.1	clear	two phase	two phase
40.1	clear	two phase	two phase
30.6	clear	two phase	two phase
20.9	clear	two phase	two phase
11.0	clear	two phase	two phase
0.2	clear	two phase	two phase
-9.5	clear	two phase	two phase
-19.3	clear	two phase	two phase
-31.0	clear	two phase	two phase
-40.3	clear	two phase	two phase
-48.0	clear	two phase	two phase

Table A.61 Observations for R-143a/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.14	0.54	0.95
57.0	clear	two phase	two phase
50.0	clear	two phase	two phase
40.2	two phase	two phase	two phase
29.7	two phase	two phase	two phase
19.8	two phase	two phase	two phase
11.0	two phase	two phase	two phase
-0.2	two phase	two phase	two phase
-9.8	two phase	two phase	two phase
-19.6	two phase	two phase	two phase
-30.3	two phase	two phase	two phase
-40.4	two phase	two phase	two phase
-48.0	two phase	two phase	two phase

Table A.62 Observations for R-143a/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.14	0.52	0.95
57.0	clear	two phase	two phase
50.0	clear	two phase	two phase
40.2	clear	two phase	two phase
29.7	clear	two phase	two phase
19.8	clear	two phase	two phase
11.0	clear	two phase	two phase
-0.2	two phase	two phase	two phase
-9.8	two phase	two phase	two phase
-19.6	two phase	two phase	two phase
-30.3	two phase	two phase	two phase
-40.4	two phase	two phase	two phase
-48.0	two phase	two phase	two phase

Table A.63 Observations for R-143a/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.49	0.95
59.9	clear	two phase	two phase
50.2	clear	two phase	two phase
39.5	clear	two phase	two phase
29.8	clear	two phase	two phase
19.6	clear	two phase	two phase
10.4	clear	clear	clear
0.0	clear	clear	clear
-10.0	clear	slightly hazy	clear
-19.8	clear	hazy	clear
-29.8	clear	hazy	clear
-39.6	slightly hazy	hazy	two phase
-49.6	slightly hazy	two phase	two phase

Table A.64 Observations for R-152a/penta erythritol ester mixed-acid mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.53	0.95
89.9	clear	clear	clear
79.9	clear	clear	clear
70.0	clear	clear	clear
59.6	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.0	clear	clear	clear
9.7	clear	clear	clear
-0.5	clear	clear	clear
-10.0	clear	clear	clear
-20.1	clear	clear	clear
-30.1	clear	clear	clear
-40.2	clear	clear	clear
-49.7	clear	clear	clear

Table A.65 Observations for R-152a/polypropylene glycol diol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.51	0.96
89.9	clear	clear	clear
79.9	clear	clear	clear
70.0	clear	clear	clear
59.6	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.0	clear	clear	clear
9.7	clear	clear	clear
-0.5	clear	clear	clear
-10.0	clear	clear	clear
-20.1	clear	clear	clear
-30.1	clear	clear	clear
-40.2	clear	clear	clear
-49.7	clear	clear	clear

Table A.66 Observations for R-152a/mixed-acid polyol ester mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.11	0.49	0.95
89.9	clear	clear	clear
79.9	clear	clear	clear
70.0	clear	clear	clear
59.6	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.0	clear	clear	clear
9.7	clear	clear	clear
-0.5	clear	clear	clear
-10.0	clear	clear	clear
-20.1	clear	clear	clear
-30.1	clear	clear	clear
-40.2	clear	clear	clear
-49.7	clear	clear	clear

Table A.67 Observations for R-152a/polypropylene glycol butyl monoether mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.52	0.96
89.9	clear	clear	clear
79.9	clear	clear	clear
70.0	clear	clear	clear
59.6	clear	clear	clear
50.2	clear	clear	clear
40.2	clear	clear	clear
30.3	clear	clear	clear
20.0	clear	clear	clear
9.7	clear	clear	clear
-0.5	clear	clear	clear
-10.0	clear	clear	clear
-20.1	clear	clear	clear
-30.1	clear	clear	clear
-40.2	clear	clear	clear
-49.7	clear	clear	clear

Table A.68 Observations for R-152a/naphthenic mineral oil mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.13	0.52	0.95
88.5	clear	two phase	clear
80.1	clear	two phase	clear
70.1	clear	two phase	clear
60.2	clear	two phase	clear
50.0	clear	two phase	two phase
40.5	clear	two phase	two phase
30.4	clear	two phase	two phase
20.1	clear	two phase	two phase
10.3	two phase	two phase	two phase
-0.1	two phase	two phase	two phase
-9.7	two phase	two phase	two phase
-19.8	two phase	two phase	two phase
-30.0	two phase	two phase	two phase
-40.2	two phase	two phase	two phase
-49.5	two phase	two phase	two phase

Table A.69 Observations for R-152a/alkylbenzene mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.12	0.47	0.96
88.5	clear	clear	clear
80.1	clear	clear	clear
70.1	clear	clear	clear
60.2	clear	clear	clear
50.0	clear	clear	clear
40.5	clear	two phase	clear
30.4	clear	two phase	clear
20.1	clear	two phase	clear
10.3	clear	two phase	clear
-0.1	clear	two phase	clear
-9.7	clear	two phase	two phase
-19.8	clear	two phase	two phase
-30.0	clear	two phase	two phase
-40.2	two phase	two phase	two phase
-49.5	two phase	two phase	two phase

Table A.70 Observations for R-152a/modified polyglycol mixtures.

Temperature °C	Refrigerant Concentration (mass fraction refrigerant)		
	0.10	0.48	0.95
87.6	clear	clear	clear
79.6	clear	clear	clear
69.7	clear	clear	clear
59.6	clear	clear	clear
49.8	clear	clear	clear
39.6	clear	clear	clear
29.6	clear	clear	clear
19.8	clear	clear	clear
9.5	clear	clear	clear
0.1	clear	clear	clear
-9.7	clear	clear	clear
-20.3	clear	clear	clear
-30.2	clear	clear	clear
-40.3	clear	clear	clear
-50.0	clear	clear	clear

Appendix B - Actual Test Lubricants

The actual lubricants tested are commercially available and are listed as follows:

- naphthenic mineral oil (ISO 32): Witco Suniso® 3GS
- alkylbenzene (ISO 32): Shrieve Zerol® 150
- polypropylene glycol butyl monoether (ISO 32): ICI Emkarox™ VG32
- polypropylene glycol diol (ISO 32): Dow P425
- modified polyglycol (ISO 32): Allied-Signal BRL-150
- penta erythritol ester mixed-acid (ISO 22): ICI Emkarate™ RL244
- mixed-acid polyol ester (ISO 32): Castrol Icematic™ SW32

**DATE
FILMED**

7 / 19 / 93

1