AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 6

**Cover Sheet for a Hanford
Historical Document
Released for Public Availability**

Released 1994

**Prepared for the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830**

**Pacific Northwest Laboratory
Operated for the U.S. Department of Energy
by Battelle Memorial Institute**

DISCLAIMER

This is a **historical document** that is being released for public availability. This was made from the best available copy. Neither the United States Government nor any agency thereof, nor Battelle Memorial Institute, nor any of their employees, makes any **warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights.** The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

CIRCULATING COPY
RECEIVED 300 AREA

SEP 12 1956

RETURN TO

TECHNICAL INFORMATION FILES

DECLASSIFIED

HW-40000

This document consists
of 557 pages. Copy No. 20
of 125 copies. Series 20

FUEL ELEMENT TECHNICAL MANUAL

Compiled by members of the
Engineering and Manufacturing Department

H. H. Burley, Editor

CLASSIFICATION CANCELLED AND CHANGED TO
CONFIDENTIAL

BY AUTHORITY OF CG-PR-2 (PR-24)

DS Lewis 9-15-92

BY J. E. Savely 10-23-92

VERIFIED BY PM Eick 4-12-94

August 1, 1956

Classification Cancelled (C)

CONFIDENTIAL

By Authority Printout

14-94

L. Pope 2-1-75

HANFORD ATOMIC PRODUCTS OPERATION
RICHLAND, WASHINGTON

Work performed under Contract No. W-31-109-Eng-52 between
the Atomic Energy Commission and General Electric Company

RESTRICTED DATA

This document contains Restricted Data as defined in the Atomic
Energy Act of 1954. Transmittal or the disclosure of such
data in any form to an unauthorized person is prohibited.

Route To:	P. R. No.	Location	Files Route Date	Signature and Date
<u>E. A. Bennett</u>	<u>857</u>	<u>713</u>	<u>9/12/56</u>	
<u>JP McNece</u>	<u>37851</u>	<u>Sig 3</u>	<u>JUL 26 1988</u>	

MASTER ed

DECLASSIFIED

DECLASSIFIED

-2-

HW-40000

DISTRIBUTION

1	A. E. C., Hanford Operations	42	J. E. Faulkner
	Office - Attn: A. T. Gifford	43	E. J. Filip
2	A. E. C., Washington	44	J. M. Fouts
	Attn: W. N. Munster	45	R. M. Fryar
3	BMI, Attn: H. R. Nelson -	46	G. C. Fullmer
	J. R. Keeler	47	P. F. Gast
4	duPont, Wilm., Attn: J. C. Woodhouse	48	L. L. German
5	ISC, Attn: F. H. Spedding	49	S. M. Gill
6	ISC, Attn: H. A. Wilhelm	50	S. Goldsmith
7	KAPL, Attn: T. M. Snyder	51	O. H. Greager
8	KAPL, Attn: F. E. Crewer -	52	A. B. Greninger
	D. H. White	53	C. Groot
9	MCW, Attn: Norton Berry	54	L. L. Hagie
10	NLO, Attn: F. L. Cuthbert	55	G. B. Hansen
11	TIS	56	H. Harty
12	TIS	57	W. M. Harty
13	TIS	58	H. W. Heacock
14	F. W. Albaugh	59	J. M. Heffner
15	J. M. Atwood	60	E. Hollister
16	R. C. Aungst	61	E. J. Hubbard
17	J. A. Ayres	62	H. H. Hubble
18	J. T. Baker	63	R. E. Hueschen
19	R. S. Bell	64	I. L. Huffman
20	C. A. Bennett	65	G. F. Jacky
21	J. A. Berberet	66	J. L. Jaech
22	H. E. Berg	67	W. T. Kattner
23	W. A. Blanton	68	R. S. Kemper
24	A. G. Blasewitz	69	W. K. Kratzer
25	C. W. Botsford	70	L. E. Kusler
26	L. P. Bupp	71	T. V. Lane
27	S. H. Bush	72	L. W. Lang
28	J. J. Cadwell	73	C. G. Lewis
29	P. A. Carlson	74	D. S. Lewis
30	A. B. Carson	75	W. R. Lewis
31	E. D. Clayton	76	G. L. Locke
32	R. G. Clough	77	W. K. MacCready
33	V. R. Cooper	78	A. R. Maguire
34	R. F. Corlett	79	W. M. Mathis
35	G. L. Davis	80	L. H. McEwen
36	D. R. deHalas	81	J. S. McMahon
37	R. L. Dickeman	82	H. C. Money
38	R. L. Dillon	83	J. F. Music
39	E. A. Eschbach	84	J. W. Nageley
40	E. A. Evans	85	S. L. Nelson
41	T. W. Evans	86	E. W. O'Rorke

DISTRIBUTION

87 W. J. Ozeroff
88 H. M. Parker
89 R. S. Paul
90 O. H. Pilkey
91 W. W. Porter
92 C. A. Priode
93 O. W. Rathbun
94 E. L. Reed
95 P. H. Reinker
96 R. B. Richards
97 J. W. Riches
98 W. C. Riley
99 O. C. Schroeder
100 W. Seeburger
101 K. V. Stave
102 J. T. Stringer
103 G. W. Stuart
104 J. W. Talbott
105 F. E. Tippets
106 J. R. Triplett
107 L. D. Turner
108 F. W. VanWormer
109 W. P. Wallace
110 L. G. Waters
111 H. T. Wells
112 W. W. Windsheimer
113 N. G. Wittenbrock
114 F. W. Woodfield
115 W. K. Wright
116 H. F. Zuhr
117 300 Files
118 Record Center
119 - 125 Extra

DECLASSIFIED

DECLASSIFIED

DECLASSIFIED

HW-40000

-4-

<u>CONTENTS</u>		<u>Page</u>
PART I: INTRODUCTION		101
Chapter I. Introduction		101
PART II: TECHNICAL BASES		201
Chapter II. Physics		201
Chapter III. Engineering		301
Chapter IV. Operating Experience		401
Chapter V. Metallurgy (Unirradiated Materials)		501
Chapter VI. Metallurgy (Irradiated Materials)		601
PART III: PROCESS		701
Chapter VII. Components		701
Chapter VIII. Assembly Processes		801
Chapter IX. Auxiliary Processes		901
PART IV: PLANT AND EQUIPMENT		1001
Chapter X. Description of the Manufacturing Plant		1001
Chapter XI. Process Equipment		1101
Chapter XII. Auxiliary Equipment		1201
PART V: PROCESS CONTROL AND IMPROVEMENT		1301
Chapter XIII. Instrumentation		1301
Chapter XIV. Quality and Standards		1401
Chapter XV. Identification, Data Processing and Storage		1501
Chapter XVI. Auxiliary Facilities		1601
PART VI: SAFETY		1701
Chapter XVII. Radiation Protection and Critical Mass Control		1701
Chapter XVIII. Safety and Fire Prevention		1801
INDEX		1901

DECLASSIFIED

DECLASSIFIED

-101-

HW-40000

PART I: INTRODUCTION
CHAPTER I: INTRODUCTION

<u>CONTENTS</u>	<u>Page No.</u>
A. PURPOSE, SCOPE AND ARRANGEMENT OF THE MANUAL	102
1. Purpose and Scope	102
2. Arrangement of the Manual	102
B. DESIGN CRITERIA	103
1. General	103
1.1 Description of a fuel element	103
1.2 Functions of fuel and target elements	104
1.2.1 Isotope production	104
1.2.2 Power production	105
1.2.3 Neutron sources for experimental purposes	106
1.3 Required properties of fuel elements	106
1.3.1 Nuclear properties	108
1.3.2 Mechanical properties	108
1.3.3 Physical properties	108
1.3.4 Chemical properties	108
1.4 Operating conditions	109
1.4.1 Coolant conditions	109
1.4.2 Stress environment	109
1.4.3 Radiation environment	110
1.4.4 Cyclic reactor operation	111
1.4.5 Exposure period	111
C. THE PROCESS	112
1. Feed Materials	112
1.1 Aluminum canning components	112
1.2 The uranium core	113
1.3 Processing materials	114
2. Assembly Processes	114
2.1 Lead dip canning	115
2.2 Hot press canning	116
2.3 Unbonded canning	116

DECLASSIFIED

DECLASSIFIED

HW 40800

A. PURPOSE, SCOPE, AND ARRANGEMENT OF THE MANUAL

1. Purpose and Scope

It is the purpose of the Fuel Element Technical Manual to provide a single document describing the fabrication processes used in the manufacture of the fuel element as well as the technical bases for these processes. The manual will be instrumental in the indoctrination of personnel new to the field and will provide a single data reference for all personnel involved in the design or manufacture of the fuel element. The material contained in this manual was assembled by members of the Engineering Department and the Manufacturing Department at the Hanford Atomic Products Operation between the dates October, 1955 and June, 1956.

2. Arrangement of the Manual

The manual is divided into six parts:

<u>Part</u>	<u>Title</u>
I	Introduction
II	Technical Bases
III	Process
IV	Plant and Equipment
V	Process Control and Improvement
VI	Safety

Part I contains the description of the manual, a general discussion of the design criteria, and a synopsis of the process.

Part II discusses the individual phases of the technical bases for fuel element design. It covers physics, engineering, operating experience, and metallurgy (both of irradiated and unirradiated material) .

Part III describes the processes involved in the fabrication of fuel elements.

Part IV is a description of the plant and equipment used in the manufacture of fuel elements. This part of the discussion is limited to the plant at HAPO which is located in the 300 Area.

DECLASSIFIED

DECLASSIFIED

Part V describes the methods of process control and improvement, and includes discussions on instrumentation, quality and standards, identification, data processing and storage, and auxiliary facilities.

Part VI describes the process hazards and the methods used to safeguard against them.

A total of eighteen chapters are included in the six parts. Pages are numbered to designate the chapter number (i. e., Chapter I page numbers begin with 101, Chapter II with 201, etc.). Figures and tables are located at the end of each chapter and are numbered in separate series for each chapter (e. g., Table I-1, Table I-2., Figure I-1, Figure I-2, etc.). References to documents containing more detailed information are listed at the end of each chapter, just before the figures and tables.

A table of contents is listed on the first page of each chapter. A subject index, arranged alphabetically, is included in the back of the manual for quick reference to specific points.

B. DESIGN CRITERIA

1. General

1.1 Description of the fuel element

One of the major problems in the development of efficient and economical nuclear reactors for power and isotope production is the design and fabrication of reliable, economical fuel elements. A brief discussion follows, concerning the general characteristics and the function of fuel elements.

The fuel material may be any of the three fissionable isotopes (U-233, U-235, or Pu-239) in the form of pure metal, alloy, ceramic, or cermet. In addition, there may be present fertile material (isotopes which are not fissionable but may be converted to fissionable species by neutron absorption, such as U-238 and Th-232), or target material (isotopes which can be converted to other isotopes by neutron reactions, such as Li-6, from which

DECLASSIFIED

H-3 (tritium) is made, and Bi-209 which is used to make Po-210).

The cladding is present to confine the fission products and to prevent corrosion of the fuel material by the coolant. The essential requisites of the cladding are a high resistance to corrosion and a low neutron absorption cross-section. Typical materials now in use are aluminum, aluminum alloy, zirconium, zirconium alloy, and stainless steel.

Fuel elements have been designed and fabricated in a variety of geometries. Some of the more common fuel element geometries are cylinders, tubes, and flat plates.

1.2 Functions of fuel and target elements

The nature of a fuel or target element is determined to a large extent by the function it is to perform, as well as by the function of the reactor in which it is to be used. The intended use of an element is a major factor governing the selection of materials, geometry, and fabrication procedures.

The primary function of a reactor may be to produce isotopes, to produce power, or to provide a neutron source for experimental purposes. A reactor may also be designed to perform a combination of these functions.

1.2.1 Isotope production

A wide variety of isotopes are produced in the United States for defense, scientific and medical purposes. Although many isotopes for other purposes are produced in the Hanford and Savannah River reactors, the primary purpose of these reactors is the production of weapon-grade plutonium for the defense effort. The reactors were designed to use natural uranium as the combined fuel-target material. The Hanford element is a cylinder approximately 1-1/2 inch in diameter by 8 inches long; the Savannah River element is a cylinder approximately 1 inch in diameter by 8 inches long.

The air cooled X-10 reactor at Oak Ridge is used primarily for the production of a variety of radiochemicals for scientific and medical purposes. The fuel elements used are almost identical to those used at

DECLASSIFIED

Hanford except they are four inches long.

1.2.2 Power production

In general, fuel elements for power generation must operate satisfactorily under conditions of higher coolant temperatures and must withstand operation to considerably higher levels of burnup of the fissionable atoms than is the case for isotope producing reactors.

Two naval propulsion reactors, the Submarine Thermal Reactor (STR) and the Submarine Intermediate Reactor (SIR), have been developed in the United States; in addition, an aircraft propulsion reactor and a number of stationary power reactors are being developed.

There is an important difference in philosophy between the military propulsion reactors and the commercial power reactors. In the former, the military advantage resulting from possession of submarine and aircraft engines that require very infrequent refueling is so great that the use of expensive materials, large safety factors (in cladding thickness for example), very strict specifications, and materials with somewhat higher neutron cross-sections to insure reliable, safe operation can be justified. In commercial power reactors, however, where existing steam and hydroelectric plants offer stiff economic competition, the problems are much greater. These power reactors must operate as reliably as the military reactors and the fuel elements are subjected to similar temperature and burnup conditions. Thus, to be competitive as power producers the fuel element for commercial power reactors must be of the same sound design and high integrity as are needed in military reactors but in addition they must be produced at a minimum cost. A further incentive to the search for a cheap but reliable fuel element arises from the fact that once a reactor is built and operating, one of the few ways to reduce costs will be in the fuel element because it is a large volume, expensive replacement item.

The fuel materials used or being considered for power reactors are usually dilute uranium alloys of high corrosion resistance, or uranium oxide.

DECLASSIFIED

DECLASSIFIED

-106-

HW 40000

Zirconium, zirconium alloys, and stainless steel are being used as the cladding materials. The geometries usually used are flat plates or small cylinders because the high surface-to-volume ratio permits high specific power operation while maintaining reasonable fuel temperatures.

1.2.3 Neutron sources for experimental purposes

Less critical perhaps, but necessary for the continued progress of reactor technology, are the experimental testing reactors. Fuel elements for this class of reactor, in general, have been conservatively designed to provide a trouble-free neutron source for research and development studies. In the Materials Testing Reactor (MTR) at Idaho Falls, Idaho, the fuel material is an enriched uranium-aluminum alloy of a flat plate geometry with aluminum cladding.

In the Brookhaven National Laboratory reactor, which is graphite moderated, and in the NRX reactor at Chalk River, Canada, which is heavy water moderated, natural uranium rods of cylindrical geometry with aluminum cladding (unbonded) are used.

1.3 Required Properties of Fuel Elements

The properties required in fuel materials and fuel elements are combinations of the nuclear, mechanical, physical and chemical properties which are fixed by the reactor design and the operating requirements of the reactor. As in all industrial situations where there are materials problems, no one fuel material or fuel element has been found which has all of the right combination of properties. A considerable effort has been and is being made to improve the properties of fuel materials and elements now in use. Efforts are also being made to minimize the effects of fuel deficiencies by reactor design.

1.3.1 Nuclear properties

In the design of a reactor, a very important consideration is the neutron balance, which is a summary of the manner in which the neutrons are used.

DECLASSIFIED

In a typical isotope producing reactor, for example, fast neutrons (which travel out to the moderator) are moderated and then diffuse back to the fuel. Some of the neutrons cause further fission in the fuel to keep the chain reaction going and some are absorbed to form the new isotopes. A certain percentage of the neutrons are captured in the moderator, the coolant, the cladding of the elements, and in impurity atoms in all components. The efficiency of the process depends directly on how many neutrons are lost by this type of capture.

In power reactors there will frequently be fertile material present (thorium and U-238 in thermal reactors and U-238 in fast neutron reactors) and these extraneous neutron losses reduce the breeding ratio of the reactor. In military propulsion reactors, where there is usually no fertile material present, these losses are less important.

The neutron absorption cross section of the fuel element components must be kept to a minimum to conserve or to use efficiently the neutrons produced by fission. It is not enough that the cross section of a material itself be low; the purity level must be high so neutrons are not absorbed by impurities with high neutron absorption cross sections.

The nuclear requirements seriously restrict the choice and concentration of alloying elements for uranium, plutonium, or thorium and for the cladding components. The elements that have been used or considered most frequently as cladding materials are aluminum and zirconium. Possible alloying elements include aluminum, zirconium, magnesium, molybdenum, niobium, beryllium, chromium, and silicon. In fast neutron (unmoderated) reactors the cross sections are somewhat less critical; hence, stainless steel has been used in the few fast reactors that have been built. The alloying elements may improve other properties of the fuel material or fuel element but they may affect the nuclear properties adversely. The cost of the extra enrichment needed to compensate for neutron absorbing elements must be carefully considered when new fuel material compositions or fuel element components are

DECLASSIFIED

being proposed.

1.3.2 Mechanical properties

The mechanical properties (strength, ductility, creep rate, etc.) of the fuel material and other components must be sufficient to withstand the thermal stresses imposed on the assembly by virtue of the temperature gradients which exist in a fuel element. In most reactors the fuel components must also withstand the effects of cyclic operation of the reactor. The mechanical properties which are drastically changed as a result of irradiation must be adequate initially and they must remain adequate throughout the service life of the element.

1.3.3 Physical properties

The important physical properties that a fuel material should possess are good thermal conductivity, dimensional stability during irradiation and under cyclic operating conditions, and high melting point. Dimensional stability is very important because reactors usually must be built with close tolerances in the fuel and coolant channels. Dimensional changes in the fuel disturb the flow of coolant and can seriously shorten the life of the fuel. In extreme cases structural damage to the reactor can result or, at least, there will be operational complications arising from the necessity to forcibly remove fuel elements which have become stuck in the reactor. In fuel materials with low thermal conductivity and/or a low melting point, the power density (heat generation per unit volume) at which the fuel can operate may be limited.

1.3.4 Chemical properties

Although fuel materials are clad with a corrosion resistant material to keep fission products out of the coolant and to prevent corrosion of the fuel by the coolant, it is still desirable for the fuel material itself to be corrosion resistant. Experience has shown that it is difficult to eliminate completely the possibility of fuel element failures. The formation of corrosion products in a natural uranium fuel element results in a large increase in

DECLASSIFIED

DECLASSIFIED

volume and can lead to structural damage to the reactor. In power reactors corrosion resistance is critical because of the higher coolant temperatures (and therefore higher corrosion rate) and because of the length of time it takes to cool the reactor before a failed fuel element can be removed. The fuel material must be chemically reactive enough that it can be dissolved without undue trouble or expense so that the unused fissionable material may be recovered for re-use.

1.4 Operating Conditions

1.4.1 Coolant conditions

The majority of reactors in this country are cooled by water and thus the fuel element must be resistant to corrosion by water for periods as long as one to two years. The water temperatures vary widely from one reactor to another. In the Materials Testing Reactor (MTR), for instance, the maximum water temperature is only about 50 C while, at Hanford, temperatures slightly in excess of 100 C are encountered. It is in power reactors that more serious corrosion conditions are encountered for the fuel elements are subjected to water or steam at high temperatures. In some applications high temperature liquid metals are used as the cooling fluid in the primary loop of the reactor. Some representative liquid metal coolants are sodium at 600 C in the Sodium-Graphite Reactor (SGR) and sodium-potassium alloy (eutectic NaK) at 550 C in the first Experimental Breeder Reactor (EBR-I). Gas cooling (other than by steam) has not been used extensively in this country except in very low power reactors.

1.4.2 Stress environment

Thermal stresses arise in fuel elements because heat is generated throughout the fuel material and must flow through the fuel element and the cladding to the coolant. The portion of the fuel farthest from the coolant is hottest and undergoes thermal expansion to a greater extent than the cladding and the portion of the fuel nearest the coolant. The compressibility of metals is so slight that the cooler portions of the fuel must yield elastically or even

DECLASSIFIED

DECLASSIFIED
HY 40000

[REDACTED]

plastically if the stress is great enough. For each fuel element geometry -- externally cooled cylinder, internally and externally cooled tube, flat plates, etc. -- the stresses will be different in degree and/or kind. Whether a stress failure problem exists in a given fuel element depends upon geometry, specific power, exposure, temperature range, and the properties of the fuel and cladding material at the given conditions.

1.4.3 Radiation environment

In a reactor, the fuel elements and the materials of construction may be subjected to bombardment by a variety of particles and by gamma radiation. Neutrons are released at high velocities from the fuel atoms as a result of fission. Collisions between the fast neutrons and the atoms of the fuel element have a disruptive effect on the orderly arrangement of atoms in the fuel elements. The fuel and cladding are subjected to intense bombardment by beta particles and gamma radiation from the fission products and from the fission event itself. In addition, the fuel is subjected to an internal bombardment by the heavier fission products, for the tremendous release of energy in the fission process appears mainly as the kinetic energy of the fission products as they recoil from the site of fission.

The disruption of the structure resulting from collisions between fuel atoms and fission products and the presence of the fission products as alloying additions both have an effect upon the properties of the fuel material. This alloying effect is usually regarded as a form of radiation damage and is considered along with the particle bombardment effects.

The effect of gamma radiation on metals is negligible. The effect of beta particle bombardment is very slight in fuel elements. Fast neutrons may exert a considerable effect on the non-fuel components of a reactor. In metals the principal effect is to increase the ultimate strength and decrease the ductility in a manner similar but not identical to work-hardening. In the fuel, the fission product recoils are probably far more productive of structural damage than is bombardment by sub-nuclear particles.

[REDACTED]

DECLASSIFIED

[REDACTED]

DECLASSIFIED

HW-40090

1.4.4 Cyclic reactor operation

Stresses arise when operation of the fuel element begins and, because the element then spends an appreciable time at elevated temperatures during operation, stress relief by plastic deformation and creep may be expected to occur. When the reactor is shut down, there is a reversal of the stresses, the extent of which is dependent upon how much plastic deformation and creep took place initially. If the stress level becomes high enough on shutdown, the fuel piece may fail by fracture. Successive cycles of this nature along with the deterioration of mechanical properties known to occur in uranium upon irradiation constitutes a formidable stress situation.

The amount of cycling that may occur during the life of a fuel element may vary over an extremely wide range -- from the single cycle per element of the Savannah River reactors to the several thousand that a submarine reactor fuel element may experience. At Hanford, the fuel elements may be cycled as many as a hundred times in extreme cases. A power reactor fuel element, on the other hand, should experience very few cycles.

1.4.5 Exposure period

The exposure period of a fuel element will depend upon the purpose of the element and of the reactor in which it is used. Exposure is usually expressed in units which are a measure of how many fissions have occurred per unit volume. Units commonly used are megawatt days per ton (MWD/T); i. e., the fission energy generated per unit mass, and also the per cent burnup of fissionable atoms.

Target elements for plutonium production are normally irradiated in the range 200-1,000 MWD/T (or approximately 0.1% burnup of the uranium atoms). Exposures much over about 1000 MWD/T result in an effectively lower yield of product because the Pu-239 fissions to an increasing extent as the concentration increases. Also, a poorer product results because of increasing contamination by Pu-240, which is formed from Pu-239, by neutron absorption. An appreciable quantity of plutonium has been produced from

DECLASSIFIED

DECLASSIFIED
E.O. 14176

fuel elements irradiated to only 200 MWD/T. This latter material is more expensive to produce but, because of its low Pu-240 content, is useful in certain weapons applications.

In power reactors, the exposure levels should be much greater because of the economic advantage of replacing the fuel only infrequently. The exposure levels of power reactor fuel elements range up to 10,000 to 20,000 MWD/T or 1 to 2 per cent burnup of the fuel atoms.

C. THE PROCESS

The processing from raw materials to the finished fuel element varies depending upon the reactor for which the fuel element is fabricated; however, in the United States the preparation of the uranium for all natural uranium elements is much the same until the final forming stages.

Since it is the Hanford element with which this manual is concerned, the discussion of the process will be limited to those fuel elements which are designed and fabricated for the Hanford reactors. It should be borne in mind, however, that some parts of the process may apply to the fabrication of elements for other reactors as well.

1. Feed Materials

1.1 Aluminum canning components

The jacket components used at Hanford are essentially the same for all the processes. The "can" is a hollow thin wall right cylinder with one end closed. For the lead dip process (see Chapter VIII) the can has a wall thickness of about 45 mils, a can base thickness of about 0.2 inch, and an overall length of about 9-1/2 inches. The cap is the shape of a small disc of aluminum with a boss on top (for handling with the canning tongs). The finished jacket components are obtained from the Aluminum Company of America under a 2S alloy designation of M-329-F or M-261-F. The 2S ingots are extruded into rod from which extrusion blanks are machined. The blanks are then impact extruded into cans and caps.

DECLASSIFIED

DECLASSIFIED

1.2 The uranium core

Figure I-1 shows a flowsheet which carries the uranium from the uranium ore to the finished slug. The processes are described as follows:

- (1) Ore concentration; both at Mallinckrodt Chemical Works (MCW) and National Lead of Ohio (NLO) by either a carbonate or a sulphuric acid process. Ores with a high calcium content require the carbonate process to break down the minerals.
- (2) Extraction and purification; MCW uses ether extraction process, NLO uses a tributyl phosphate process. The Weldon Spring Plant of MCW is being designed for a two stage process using both ether extraction and tributyl phosphate. The end product of this process is uranyl nitrate.
- (3) Denitration: the uranyl nitrate is converted (by both plants) into orange salt (UO_3) by denitration.
- (4) Reduction: the orange salt (UO_3) is converted to the brown or black salt (UO_2) in a reactor at 1200 F with cracked ammonia.
- (5) Hydrofluorination; the UO_2 is converted to uranium tetrafluoride (UF_4) by reaction with a stoichiometric excess of anhydrous hydrogen fluoride (HF).
- (6) Reduction: the uranium tetrafluoride is reduced to uranium by the reaction $\text{UF}_4 + 2\text{Mg} \rightarrow \text{U} + 2\text{MgF}_2 + 82 \text{ kilocalories/mole uranium}$. The product from the reduction bomb is either the derby (produced at both NLO and MCW) or the dingot* (produced at MCW).
- (7) Remelt: when derbies are the end product of the reduction step (6), they are remelted and cast into ingots.
- (8) Press forge: when dingots are the end product of the reduction step (6), they are press forged into a size suitable for rolling.
- (9) Rolling: all ingots and press forged dingots are then shipped to Fernald

* A contraction of the words direct-cast ingot

DECLASSIFIED

DECLASSIFIED

HW 40009

- (NLO, sometimes referred to as FMPC) for rolling into rods.
- (10) Heat treating: the rods are beta heat treated in a molten eutectic mixture of lithium carbonate (Li_2CO_3) and potassium carbonate (K_2CO_3) at 720 ± 10 C for 12 minutes then quenched in circulating water. (Rods for SRO fuel elements are not heat-treated).
- (11) Machining: the rods are cut to slug size and finish machined on Acme-Gridley lathes at FMPC.

The finished slugs are then shipped to HAPO (or Savannah River) for assembling into the finished slug.

1.3 Processing Materials

All of the processing materials such as bath metals, cleaning agents, and inert gases are purchased from commercial sources.

2. Assembly Processes

Fuel elements are assembled at HAPO by dip canning, unbonded canning, and hot press canning methods. On a production basis the processes are designated as follows:

"A" Process - Triple Dip Canning*

"B" Process - Unbonded Canning

"C" Process - Unbonded Canning

"F" Process - Lead Dip Canning

"HPA" Process - Hot Press Canning

Natural uranium fuel cores are canned by the "F" Process and, because of the relative number canned, are considered the standard HAPO fuel element. Cores of uranium-aluminum alloy, lithium-aluminum alloy, bismuth, lead-cadmium alloy, and thorium are canned by the "B", "C", and "HPA" processes. Production test quantities of the above mentioned materials, plus enriched uranium and several alloys of uranium, have been canned by all of the standard processes (or variations

* Replaced by "F" Process in March, 1954, (See Chapter VIII)

DECLASSIFIED

DECLASSIFIED W-40000

thereof) for evaluation purposes. The remainder of this chapter is devoted to a very brief description of the assembly processes. For a more detailed account see Chapters VIII and XI.

2.1 Lead dip canning ("F" process)

The slug cores are received at HAPO in final form. They are prepared for canning by (1) dimensional and quality inspections, (2) vapor degrease, (3) nitric acid pickle, (4) water rinse, (5) forced frying, and (6) pickled slug inspection.

The caps and cans are prepared for canning by (1) dimensional inspection, (2) vapor and detergent degreasing, (3) deoxidation, (4) water rinse, (5) methanol dehydration, (6) forced drying, and (7) surface inspection (cans only).

An integral part of the process is the canning sleeve which supports and contains the can during preheat and assembly. The sleeve is prepared for canning by (1) inspection, (2) caustic cleaning, (3) water rinse, (4) soap dip, and (5) drying.

The core is immersed in the Duplex Bath (an Al-Si layer over a lead layer) and agitated within the lead layer until the uranium reaches the canning temperature (ca. 590 C). The agitation is continued as the slug is raised into and then out of the Al-Si layer. It is then immediately transported to the Al-Si canning bath where the can in the canning sleeve has been pre-heated (in the canning bath) and awaits assembly. The core is lightly agitated in the canning bath, then inserted into the submerged can. The cap is also inserted while the can is submerged. The assembled slug (and canning sleeve) is then removed from the bath and water quenched. After quenching, post-assembly operations include (1) removal from canning sleeve, (2) facing, (3) welding, (4) weld inspection, (5) bond test, (6) Al-Si penetration test, (7) canned slug etch, (8) closure radiography, (9) autoclaving, (10) final inspection, and (11) storage until shipment to piles.

DECLASSIFIED

DECLASSIFIED

HW 40000

2.2 Hot press canning

The hot press canning process, originally developed for uranium slug cores, was adapted for the canning of U-Al alloy slug cores in aluminum jacketing components in 1954. The basic canning steps are; (1) inspection and surface preparation of the slug core and the jacketing components, (2) assembly of the components, (3) sizing of slug assembly, (4) preparation for pressing the sized assembly, (5) pressing, (6) finishing of the pressed assembly, (7) bond testing, and (8) final inspection.

The hot pressing operation bonds the can, wafer cap, and core into one integral assembly. The sized slug assembly is pressed in a heated die assembly consisting of a die housing, a solid insert which forms a cylinder for holding the slug during pressing, and the cylindrical end punches. The exterior surface of the insert is coated with Aqua-Dag to prevent the insert from sticking in the die housing. The insert, punch, and plug are pre-heated to 600-625 C in an auxiliary die housing prior to the hot pressing operation. The heated insert is seated in the die housing with about 12 tons total force. After a delay of about 45 seconds the end punches and slug assembly are inserted and eleven tons total force is applied for 10 to 13 minutes. The temperature of the die assembly during hot pressing is maintained at 600 to 625 C. After pressing, the insert, punch, plug, and slug assembly are removed from the die housing and quenched in hot water.

2.3 Unbonded canning

Two canning processes have been used at HAPO for jacketing slug cores with aluminum without effecting a bond between the jacketing component and the core. The two processes, the "B" Process and the "C" Process, are similar except for the sizing of the slug assembly and the manner of welding and inspecting the slug closure. Basically, the "C" process canning steps are; (1) preparation and inspection of the slug core, (2) preparation and inspection of the jacketing components, (3) component

[REDACTED]

DECLASSIFIED

[REDACTED]

DECLASSIFIED HW-40000

assembly, (4) sizing of the slug assembly, (5) finishing of the slug assembly, and (6) inspection of the canned assembly.

The sizing operation ensures adequate heat transfer between the jacket and the slug core by minimizing the air gap. The slug assembly is prepared for sizing by applying a thin coat of water-soluble drawing wax. The lubricated assembly is then sized to reduce the can-core gap to less than 0.0001 inch. About 2000 pounds of axial pressure is applied prior to and throughout the sizing operation. After sizing, the lubricant is removed by hot water or steam. The sized assembly is then faced to remove the excess can wall and to square the end of the assembly. The closure between the wafer cap and can wall is made by an inert arc fusion weld with high purity 2S aluminum filler wire added to the weld bead (GE "Fillerweld")

DECLASSIFIED

[REDACTED]

DECLASSIFIED

HW-40000

NATIONAL LEAD OF OHIO
(FMPC & NLO)

MALLINCKRODT CHEMICAL WORKS
(MCW)

FIGURE I-1

FLOW SHEET FOR PRODUCING URANIUM CORES

DECLASSIFIED

DECLASSIFIED

PART II: TECHNICAL BASES
CHAPTER II: PHYSICS

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION.	202
B. LATTICE PHYSICS	202
1. Fission Process	202
2. Reactivity	203
2.1 Exponential pile	207
2.2 Test pile	207
2.3 Physical constants test reactor	207
2.4 Pile startup experiments	208
C. REACTOR PHYSICS :	212
D. REFERENCES	215
E. LIST OF TABLES AND FIGURES	216

DECLASSIFIED

DECLASSIFIED

-202-

HV 40000

A. INTRODUCTION

Since the basis for reactor operation is the behavior of the atom and its component parts and since the fuel element is an integral part of any reactor design, this chapter on physics has been included to provide the background information necessary in the design of the fuel element. Basic concepts of the fission process, reactivity, and related subjects are discussed along with more specific references to fuel element variables and the effect of these variables on reactor operation.

B. LATTICE PHYSICS

1. Fission Process

The fission process is the basic feature of a chain reacting pile. In this process the nucleus of a heavy element splits into two smaller nuclei after being placed in an excited state by the capture of a neutron. This process is accompanied by the release of considerable energy which is carried off by the several particles that are emitted.

The particles emitted and their average energies are:

2	fission product nuclei	168 ± 5.0 mev.
2.5	fast neutrons	5 ± 0.5 mev.
	fission gammas	4.6 ± 1.0 mev.
	(delayed)	
	fission product betas	7 mev.
	fission product gammas	<u>6 mev.</u>
		191 mev.
	neutrinos (not available as heat)	
		<u>11 mev.</u>
		202 mev.

Perfectly symmetrical fission is an unlikely event. By plotting the fractional yield as a function of the mass number of nucleus, one obtains a curve with two maxima, the most common isotopes having masses of

DECLASSIFIED

DECLASSIFIED

about 95 and 139 (See Figure II-1). The fission product nuclei travel only a short distance within the fuel element, but owing to their high energy are capable of considerable damage to crystal lattices.

The fast neutrons emitted provide the means for continuing the reaction. In a thermal reactor like the Hanford type the fast neutrons lose their energy by diffusion in the moderator until they are nearly in thermal equilibrium with the carbon atoms. At thermal energies, the neutrons have a high probability of reacting with fissionable isotopes in the fuel to cause fission.

The beta and gamma radiations are primarily observed as sources of heat. The beta radiation is essentially contained within the fuel element while a certain fraction of the gamma escapes and contributes to heating the graphite. The fraction that escapes is determined by the self shielding of the element and, for example, is greater in uranium-aluminum alloy than in solid uranium.

2. Reactivity

To operate a chain reacting assembly, a delicate balance must be established between neutron production and absorption. Neutrons are gained through the fission process where several neutrons are produced for each neutron causing a fission. Neutrons are lost by various absorptive processes, some of which produce plutonium while others are parasitic.

For calculation purposes, it is convenient to consider a flow sheet that describes the various processes in a chain reaction. Since it is a closed circle of events, one may start at any point in the process. Calculations of the various events in the cycle are expressed in terms of the number of neutrons existing after some point per neutron existing before. Fission processes in general lead to probabilities greater than one while absorptive processes lead to probabilities less than one. The probabilities are a function of the energy and position of the neutron. Three energy ranges are of interest: (1) the fast, in which the neutrons are born, (2) the

DECLASSIFIED

DECLASSIFIED

-204-

HW 1000

intermediate, especially the energy of the uranium absorption resonances, and (3) the thermal.

Hanford piles consist of rods of fuel in a square lattice. For the purpose of calculation, a single cell is considered, consisting of one rod and its associated fraction of the lattice. Within this cell it is desired to calculate how many neutrons there will be after one cycle or generation in the chain reactor for each neutron entering it. This number is called the multiplication or k . If k is exactly equal to one there will be the same number of neutrons in each subsequent generation and the flux or power will stay constant. Similarly, if k is greater or less than one, the power level will go up or down at a rate related to $(k - 1)$ and the time necessary for a neutron generation to be completed. A pile is designed to possess a k greater than one after which sufficient control rod is inserted to absorb the balance of the neutrons.

The calculation of the k of a lattice involves evaluating the four terms in the product.

$$k = \eta \epsilon p f$$

η (eta) is the number of fast neutrons produced in fission per capture of a thermal neutron in the fuel. This number is usually dependent only upon the fuel used. For natural uranium, it is of the order of 1.34. ϵ (epsilon) is the so-called fast effect. While only U-235 is fissionable to thermal neutrons, U-238 is slightly fissionable at the energies of the neutrons formed in fission and contributes to the process. ϵ can be defined as the increase in the number of fast neutrons due to fast fission.

After the neutrons leave the fuel element they lose energy by elastic collisions with the carbon nuclei in the moderator. At energies in the so-called intermediate region, uranium has a series of very sharp absorption resonances. If a neutron of the correct energy interacts with the fuel, its capture is almost certain. This amounts to a rather significant effect. The probability of escaping capture in the resonance region is called the

DECLASSIFIED

DECLASSIFIED

resonance escape probability, p . Resonance capture leads to plutonium formation and hence is not without virtue.

As the neutrons lose more energy, they arrive at a point at which they are in thermal equilibrium with the atoms of the moderator. At these energies (about 0.025 electron volts for a moderator at room temperature) the probability of being absorbed is quite high. Some neutrons will be captured in the graphite, the coolant, the process tubes, and other materials, but most are captured in the fuel. The thermal utilization, f , is defined as the fraction of the neutrons arriving at thermal energies that are captured in the fuel.

The capture of a thermal neutron was the initial event in the chain that was under consideration so the cycle has been completed. Since each term is expressed as a sort of independent probability, the product of the four terms represents the probability of the complete cycle. The separate terms can be calculated with knowledge of the materials in the lattice, the quantities thereof, their nuclear cross sections and similar constants, and the relative neutron flux distribution. The first two are normally specified by the problem, the third is available from tables and the fourth may be measured if the lattice can be built or it may be calculated by any of several methods. The calculation of the relative flux distribution is usually the greatest source of error. The most simple method, referred to as the diffusion theory approximation, yields results that are seriously in error within strongly absorbing media such as uranium fuel rods. The most exact expressions are not integrable in closed form and other methods are used to evaluate the solutions. A high degree of accuracy must be maintained in these calculations, for one percent in k corresponds to 383 inhours (ih) - the inhour being that amount of reactivity which can cause the pile power level to increase by a factor of e (2.718) in one hour. Thus far we have treated cases where a neutron is removed from the pile by some form of capture. In all piles of finite size there will be a loss

DECLASSIFIED

DECLASSIFIED

-206-

HW-40006

of neutrons through leakage out of the lattice. One of the boundary conditions is that the neutron flux go to zero at the extrapolated boundaries of the pile. This requirement, together with the dimensions of the pile and a parameter (called the migration area) which is related to the average distance the neutron travels between birth and capture, determine the fraction of neutrons that will be lost through leakage.

We can thus define two values of k , the pile multiplication: k infinite (k_{∞}) is the multiplication of an infinitely large pile that has no leakage; k effective (k_{eff}) is the multiplication with the leakage term included.

$$K_{\text{eff}} = \frac{k_{\infty}}{1 + M^2 B}$$

where M^2 is the migration area mentioned above and B is the geometric buckling which is a measure of the size of the pile. For a rectangular pile of dimensions a , b , and c .

$$B = \frac{\pi^2}{a^2} + \frac{\pi^2}{b^2} + \frac{\pi^2}{c^2}$$

Increasing the size of the pile decreases B and hence reduces the leakage loss.

From this point the concept of criticality can be discussed. A given lattice arrangement will have a value of k_{∞} associated with it which we will assume for the example has been designed to be greater than one. For the pile with this lattice to be just critical, the effective k need be equal only to one. Substituting these values for k_{∞} and k_{eff} and using a calculated value for M^2 , one can determine B , the buckling for the pile to be just critical. Since this number is a function of the material used, it is called the material buckling or the critical buckling. Given the shape of the pile, the dimensions of the just-critical assembly can then be calculated since at critical the material and geometric bucklings are equal.

DECLASSIFIED

DECLASSIFIED

HW-1980

The units of B , if the pile dimensions are in centimeters, are in reciprocal centimeters squared. It is more convenient to use a unit of 10^{-6} cm^{-2} , which is commonly called the microbuck (μB). The migration area can be determined in the loading of a critical assembly such as at the initial startup of a new pile. The change in reactivity with increasing geometric buckling is noted as the pile is loaded just beyond critical. A value of 24.6 inhours per microbuck for the 8-3/8" lattice and 22.2 ih per μB for the 7-1/2" lattice has been measured.

The cumulative errors in the calculation of the four factors, η , ϵ , p and f are normally too large to be used for pile design. Experiments that yield the value of the material buckling are more desirable from the standpoint of accuracy. Several tools for measurements are discussed below.

2.1 Exponential Pile: The exponential pile is a fundamental method for the study of lattices. A small portion of a critical pile is assembled and driven with an external neutron source. The neutron flux distribution through the pile is measured and fitted to theoretical expressions to determine the material buckling.

2.2 Test Pile: The Hanford Test Pile (see Chapter XVI, Section C) is a zero power mockup of a production lattice. As such, one can substitute a small amount of material contemplated for use in a production pile in the Test Pile lattice and, by means of extremely accurate measurements, predict the gross pile reactivity effect of this material. To keep errors in theoretical interpretation as small as possible, it is necessary to confine the work to materials that represent relatively small changes from standard fuel elements. The Test Pile is the fundamental tool for metal testing and evaluation at present.

2.3 Physical Constants Test Reactor: The Physical Constants Test Reactor (PCTR) is a hybrid between the exponential pile and the Test Pile. It is a small critical pile with a removable 3 ft. by 3 ft. core in which small portions of various lattices may be substituted. By appropriate

DECLASSIFIED

DECLASSIFIED

-208-

HW-40000

calibration of the pile, one can determine the essential characteristics of the lattice under test.

2.4 Pile Startup Experiments: The most useful measurements are obtained in the experiments conducted at the initial startup of a new pile. All parameters of the lattice are measured together with studies on special slugs and loadings. Good accuracy is achieved on the former, but some accuracy is lost on the latter because of the small fraction of the pile that is used in the test. The measurements normally made on natural uranium include the critical bucklings for the pile with and without cooling water, the migration area, and measurements relative to special loadings. The conversion efficiency (conversion ratio) of a production reactor is an item of importance. This is the ratio of product atoms formed per fuel atom consumed. Plutonium is formed by two processes, resonance capture and thermal capture in uranium-238. The value is related to the lattice constants by

$$C. E. = \frac{f_{28}}{f_{25}} + \eta_{25} \epsilon (1-p)$$

The first term is the ratio of the thermal capture in U-238 to U-235 and the second term is the ratio of resonance capture in U-238 to thermal capture in U-235. The use of natural uranium fixes the first term, but the second term is increased by a decrease in the resonance escape probability.

Conversion efficiency is most commonly determined by a chemical analysis of the irradiated fuel; however, by combining certain data from flux distribution measurement, using methods developed in HW-38738, (7) it is possible to arrive at initial conversion efficiencies for fuel elements without chemical data.

Let us consider the optimization of a lattice. In a Hanford reactor the use of natural uranium fixes the value of η and the choice of a slug diameter determines ϵ . If one increases the ratio of uranium to graphite (by

DECLASSIFIED

DECLASSIFIED

HW-33088

decreasing the lattice spacing, for example) the thermal utilization will increase and the resonance escape probability will decrease. The multiplication will pass through a maximum at the point of optimum design for reactivity. Lattices on the high uranium side of this have greater conversion efficiency.

The lattice constants for Hanford reactors have been studied by various means. Early theoretical work used diffusion theory approximations. More recent work is based on experimental measurements which eliminate most of the uncertainties in these numbers. The major errors remaining are in the nuclear cross sections used and in temperature effects.

Quantity	Pile Lattice Spacing	
	8-3/8 in.	7-1/2 in.
η	1.341	1.341
ϵ	1.034	1.034
p	0.87	0.846
f	0.87	0.878
Conversion Efficiency	0.835	0.886

Variations of the fuel element dimensions from their nominal values will, in general, cause reactivity changes in the pile. The diameter may be changed at the expense of the can wall or the water annulus and the length may be varied at the expense of the end cap and base or the total length of the column. The calculations on this subject are described in HW-33088⁽⁵⁾ with the exception of the change in water annulus case.

Over the region of small changes in diameter of the uranium at the expense of the can wall, one will observe an increase of 3.9 inhours per mil of uranium diameter increase for the piles with 8-3/8 in. lattice spacing (B, C, D, DR, F, H). The piles with 7-1/2 in. lattice spacing (KW and KE) show essentially no reactivity change with uranium diameter in this manner. If the length of each slug core is increased at the expense of the end cap or base a total pile reactivity gain of 0.314 inhours per mil of uranium will be experienced.

The presence of absorbing impurities in the fuel is undesirable from the reactivity loss standpoint. The effect of such impurities is to change the

DECLASSIFIED

DECLASSIFIED HW-40009

values of η and f in the formula for pile multiplication. If only small amounts of impurity are considered, the reactivity loss is $7.8 \cdot 10^4 \cdot \sum_a$ inhours where $\sum_a$ is the macroscopic cross section of the poisoning constituents. $\sum_a$ is equal to the product of the number of poison atoms per cubic centimeter times their cross section in square centimeters. See Table II-1 for determining this effect.

The neutron multiplication of a Hanford pile is very sensitive to the isotopic content of U-235 in the uranium. A relationship has been derived in HW-33919 ⁽⁶⁾ as follows:

$$\Delta k \text{ (inhours)} = 20,400 \cdot \frac{\Delta F}{F}$$

where F is the fraction of U-235 in normal uranium and ΔF is the deviation from normal. The sensitivity of this concentration has led to rather close tolerances on the isotopic abundance.

The uranium density has a small effect on reactivity. An increase of one tenth gram per cubic centimeter in the density would cause a loss of about six inhours in the pile.

Effects that produce changes in reactivity in general will produce changes in the conversion ratio. The conversion ratio effects are tabulated below:

- Diameter effect: + 0.041% per mil increase in diameter.
- Isotopic ratio: - 0.685% per percent increase in isotopic ratio.
- Density effect: + 0.15% per 0.1 g/cc increase in density.

As the fuel in a Hanford reactor is irradiated, changes in concentration occur that are large enough to produce significant changes in the rates of product formation and U-235 burnout. The equations for the 8-3/8 in. lattices have been solved in HW-31285. ⁽⁴⁾ The equations are as follows:

$$\begin{aligned} \text{Grams Plutonium/Ton} &= 0.974 \text{ Me}^{-2.15} M \cdot 10^{-4} \\ \text{Grams U-235 Consumed/Ton} &= \text{Me}^{-1.72} M \cdot 10^{-4} \\ \% \text{ Pu-240 in product} &= 0.00908 \text{ Me}^{-2.68} \cdot 10^{-4} \end{aligned}$$

where M is the column exposure in MWD/ton. Calculations are being extended to other lattices, U-235 enrichments, and fuel configurations.

DECLASSIFIED

DECLASSIFIED

Other isotopes than plutonium may be produced by pile irradiation. This is accomplished by loading the target material for isotope production together with fuel sufficiently enriched in fissionable isotopes to maintain the chain reaction.

The fuel elements that have been considered are a uranium-235 - aluminum alloy slug and a slightly enriched (up to about 2%) uranium slug. The target slugs that have received study have been the thorium slug for U-233 production and the lithium aluminum alloy slug for tritium production. While some special slug designs have been proposed, this discussion will be limited to a loading consisting of alternating slugs of fuel and target material in the column.

The following nomenclature has been used:

- J Slug: U-235 - Al alloy containing 38.5 g U-235 (called "NP" by some sites)
- E Slug: Enriched uranium slug (concentration should be specified.)
- N Slug: Lithium-aluminum alloy - 3.5 w/o lithium (Z slug - obsolete term).
- Q Slug: Thorium slug.

The loadings are thus designated J-N, E-N, J-Q, and E-Q. The variables that enter in from a nuclear physics standpoint are the composition of each of the elements and their relative volumes. These quantities are adjusted to provide a pile loading with approximately the same neutron multiplication as natural uranium. In the case of the E slug fuel element, it is possible to balance the relative conversion to isotope production against plutonium production. Heat transfer and metallurgical considerations put certain limitations on the range of these variables.

J-N Loadings:

The standard J-N loading consists of an 8.3 in. J slug and a 3.8 in. N slug (core dimensions are used here). The conversion ratio is about 0.67 atoms of tritium formed per atom of U-235 consumed.

DECLASSIFIED

DECLASSIFIED HW-40900

E-N Loadings:

The E-N loading has an additional variable in the isotopic concentration of the E metal. A case of great interest is that of a 0.94% E slug with standard N slugs. Calculations indicate that six 7.592 in., 0.94% E slugs with one N slug would give a conversion ratio of 0.12 to tritium and 0.70 to plutonium. These calculations are preliminary and are subject to experimental confirmation. It will be noted that the total conversion ratio (to Pu+ T) is much more attractive than the J-N conversion Ratio.

J-Q Loadings:

The J-Q loading consists of 8.3 inch J slugs paired with 6 inch Q slugs. The conversion ratio of this loading is about 0.607 atoms of U-233 per atom of U-235.

E-Q Loadings:

The E-Q Loading as studied consists of one eight inch and one four inch E slug (1.75 w/o U-235) with one six inch Q slug. The conversion ratio of this loading is approximately 0.28 to U-233 and 0.48 to Pu.

Figures II-2 through II-6 present data on the radial distribution of neutron flux through fuel elements and target elements. The data are for unexposed elements at room temperatures and have been taken from work by W. E. Niemuth ⁽⁸⁾.

C. REACTOR PHYSICS

There are many effects that assume importance when a production pile is operated at significant power levels. The neutron cross sections are dependent on the energy of the neutrons which are, in turn, a function of the moderator temperature. The resonance absorption of neutrons is a function of the temperature of the metal through Doppler broadening. As the pile is operated, high cross section fission products accumulate, the best known of which is xenon-135 which has a 3,000,000 barn cross section. The net change due to these various effects is a loss in reactivity as one

DECLASSIFIED

DECLASSIFIED

HW-2000

goes to power from the shutdown condition. Figure II-7 shows the reactivity necessary to operate at various power levels for a typical pile. There are many variables associated with this and the curve given only indicates the order of magnitude of the reactivity required. It will be noted that at high power levels some of the effects saturate so there is a tendency to gain reactivity with increasing power beyond a certain point.

If a pile is limited by the power generation in a tube, the maximum power will be generated by having as many tubes operating at this power as possible. However, this situation is not easily accomplished as the unperturbed flux distribution in a rectangular pile follows a cosine function, falling off in all directions from center. If the pile is built sufficiently larger than is necessary for criticality, it is possible to place neutron absorbing materials (called poison columns) into the pile in such positions as are suitable for reducing the rate of reaction and bringing the power generation rates nearer to the same value. The idea is to flatten the power generation distribution, and hence the term flattening is used. Figure II-8 shows in a qualitative manner the flux distribution before and after flattening.

The effectiveness of flattening can be measured in terms of the number of effective tubes. As was mentioned above, with a tube power limit, the more tubes that can be operated at this power the higher the total power will be. Hence, we can define the number of effective tubes as that number which, if operated at the limiting power, would be able to develop the total pile power. For an unflattened pile, it would take only 1084 effective tubes of a 2004 tube pile to develop the full power. Figure II-9 shows the number of effective tubes that can be achieved in a 2004 tube pile with varying amounts of flattening. This is a theoretical curve and in practice only about 90% of this number of effective tubes can be achieved because of operating inflexibilities.

The next step in increasing the capacity of the pile is to improve the flattening by adding enriched uranium just outside of the region that was flattened with poison columns. These increase the rate of reaction and extend the flattened

DECLASSIFIED

DECLASSIFIED

HW-19000

region further out. In an experiment at H pile, ⁽²⁾ the following numbers of effective tubes were obtainable with enrichment:

<u>Enrichment Tubes</u>	<u>Theoretical Effective Tubes</u>
0	1540
20	1630
35	1675
42	1725
45	1730

As a result of these operations one would expect to have a pile in which the flux distribution was constant over a region from side to side and top to bottom, falling off outside this region, and fitting a half cycle of a cosine function about the center from front to rear. There are several limitations which prevent obtaining this in practice but most of the modifications are of the nature of small variations superimposed upon the overall picture. Since the poison columns are charged in a discrete manner, a truly flat condition cannot be achieved but only approached asymptotically. Similarly, metal of higher exposure gains reactivity and will tend to run hotter than new (green) metal. From front to rear the horizontal control rods create significant dips in the theoretical cosine flux in the distribution. Accurate data on local power generation are best obtained from temperature and water flow information together with some form of flux traverse from front to rear.

DECLASSIFIED

DECLASSIFIED

-216-

HW-40,000

E. LIST OF TABLES AND FIGURES

TABLE II-1	Effect of Small Impurity Content in Uranium on Pile Reactivity
FIGURE II-1	Fission Yield for Slow Neutron Fission
FIGURE II-2	Distribution of Fissions in Natural Uranium
FIGURE II-3	Distribution of Fissions in 1.75% E Slug
FIGURE II-4	Distribution of Fission in J Slug
FIGURE II-5	Distribution of Captures in Lithium-Aluminum Slug
FIGURE II-6	Distribution of Capture Events in Thorium Slug
FIGURE II-7	Required Reactivity for Operation
FIGURE II-8	Flattened and Unflattened Power Distributions with the Same Limiting Specific Power
FIGURE II-9	Number of Effective Tubes as a Function of Flattening

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE II-1
EFFECT OF SMALL IMPURITY CONTENT IN
URANIUM ON PILE REACTIVITY (3)

<u>Element</u>	<u>(ih)₁₀₅*</u> <u>(inhours)</u>	<u>Element</u>	<u>(ih)₁₀₅*</u> <u>(inhours)</u>
Li	10	Ru	0.026
Be	0.0011	Rh	1.6
B	73	Pd	0.080
C	0.00031	Ag	0.59
N	0.14	Cd	29
O	< 0.000013	In	1.8
F	< 0.00066	Sn	0.0059
Ne	< 0.15	Sb	0.056
Na	0.023	Te	0.036
Mg	0.0026	I	0.056
Al	0.0088	Cs	0.23
Si	0.0050	Ba	0.0089
P	0.0067	La	0.069
S	0.016	Ce	0.0053
Cl	0.96	Pr	0.086
A	0.017	Nd	0.32
K	0.053	Sm	69
Ca	0.011	Eu	31
Sc	0.31	Gd	298
Ti	0.13	Tb	0.29
V	0.10	Dy	7.2
Cr	0.059	Ho	0.40
Mn	0.24	Er	1.1
Fe	0.046	Tm	0.73
Co	0.63	Yb	0.22
Ni	0.082	Lu	0.65
Cu	0.059	Hf	0.69
Zn	0.017	Ta	0.13
Ga	0.040	W	0.12
Ge	0.033	Re	0.46
As	0.059	Os	0.084
Se	0.16	Ir	2.4
Br	0.086	Pt	0.042
Kr	0.37	Au	0.50
Rb	0.0086	Hg	2.0
Sr	0.014	Tl	0.017
Y	0.017	Pb	0.00088
Zr	0.0021	Bi	0.00016
Cb	0.013	Th	0.032
Mo	0.027		

*Effect of one PPM dispersed throughout total 105 loading

DECLASSIFIED

DECLASSIFIED

UNCLASSIFIED

HW-40000

FISSION YIELDS FOR SLOW-NEUTRON
FISSION
Taken from AECD3645 (1)

UNCLASSIFIED

DECLASSIFIED

DECLASSIFIED

HW-40000

Radius (cm)
FIGURE II-2

DISTRIBUTION OF FISSIONS IN NATURAL URANIUM

DECLASSIFIED

DECLASSIFIED

DISTRIBUTION OF FISSIONS IN 1.75 % E SLUG

FIGURE II-3

HW-40000

DECLASSIFIED

DECLASSIFIED HW-40000

Radius (cm)
FIGURE II-4
DISTRIBUTION OF FISSIONS IN J SLUG

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE II-5
DISTRIBUTION OF CAPTURES IN LITHIUM-ALUMINUM SLUG

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE II-6

DISTRIBUTION OF CAPTURE EVENTS IN THORIUM SLUG

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE II-7

DECLASSIFIED

UNCLASSIFIED

DECLASSIFIED

HW-40000

FIGURE II-8

FLATTENED AND UNFLATTENED POWER DISTRIBUTIONS
WITH THE SAME LIMITING SPECIFIC POWER

DECLASSIFIED

UNCLASSIFIED

DECLASSIFIED

HW-40000

FIGURE II-9

NUMBER OF EFFECTIVE TUBES AS A FUNCTION OF
FLATTENING

DECLASSIFIED

DECLASSIFIED

-301-

HW-40000

PART II: TECHNICAL BASES (Cont.)

CHAPTER III: ENGINEERING

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION	302
B. FLUID FLOW	302
C. HEAT TRANSFER	304
1. General Considerations	304
2. Discussion of Temperature Drops	305
3. Results of Typical Calculations	309
4. The Slug Burnout Problem	310
D. THERMAL STRESSES	310
1. General Considerations	310
2. Application of Stress Analysis to Hanford Type Fuel Elements	311
E. CORROSION	313
1. Bare Uranium	313
2. Interdiffusion of Uranium and Aluminum	313
3. Corrosion of 2S Aluminum Cans	314
4. Other Can Materials	318
F. NOMENCLATURE	319
G. REFERENCES	321
H. LIST OF TABLES AND FIGURES	325

DECLASSIFIED

DECLASSIFIED HW-40000

A. INTRODUCTION

The trend at Hanford through the years has been toward higher and higher specific power generation in the uranium fuel material. This trend increases the severity of the demands made on the fuel elements while exposed to the reactor environment. In this chapter the engineering considerations important in the design of fuel elements for use in the Hanford piles will be discussed. Some of the proposed means of meeting the ever more severe demands on fuel element performance will be discussed briefly as examples of designs differing from the conventional solid cylindrical uranium slug.

Since reactor environmental conditions inevitably enter the discussion, some attention is devoted to pile problems. However, no attempt has been made to be comprehensive in this regard. Many problems of importance in pile operation are not even mentioned here, being considered beyond the scope of a manual devoted to fuel element technology.

Costs are not discussed explicitly in this chapter. However, sound engineering analysis always involves economic as well as purely technical considerations. In what follows, an economic balance among opposing technological factors is always implied.

B. FLUID FLOW

The designer of fuel elements for the existing Hanford piles is faced with a limitation on the size of fuel elements which may be placed in the reactors. This limitation is imposed by the size of the process tube which contains the fuel elements and the pile coolant (such measures as boring out the graphite channels to receive larger diameter process tubes are not considered in this discussion). The conventional cylindrical fuel element is centered in the process tube by means of ribs, integral with the tubes, forming an annular channel through which the cooling water flows. There are three process tube sizes in use at Hanford with dimensions as given below:

DECLASSIFIED

DECLASSIFIED

HYD-10000

<u>Reactor</u>	<u>Process Tube O.D., Inches</u>	<u>Approximate Annulus Thickness With 1.44 in. Slug, Inches</u>	<u>Inlet Nozzle Bore Diameter, Inches</u>
B, D, F, DR, H	1.729	0.085	1.500 ± .005
C	1.764	0.102	1.500 ± .005
K	1.806	0.120	1.500 ± .005

As a consequence of the extrusion process used in fabricating the aluminum process tube, the wall thickness is not uniform leading to an elliptical rather than circular inside cross section.

Water flows through the annular passage at rather high velocities. For example, a tube flow rate of 40 gpm in the C Pile annulus leads to an average linear velocity of about 30 feet per second. At high velocities, unbalanced fluid forces may give rise to slug "chattering" (where the slugs rattle around in the tube) with consequent damage to slug or tube or both. This problem is of importance primarily with the low density aluminum-uranium alloy slugs used for enrichment of the piles (C-slugs and J-slugs; see Chapter VII). Consideration is being given to welding C-slugs together in pairs to minimize the chattering problem.

For steady, single-phase flow of incompressible fluids in horizontal channels of constant cross section, the pressure drop due to fluid friction may be expressed as

$$(1) \quad \Delta p = f \frac{1}{D_e} \frac{\rho V^2}{2g} \quad (\text{See nomenclature at end of chapter})$$

Strictly, the above equation applies to isothermal flow. However, it is often used for heated fluids by evaluating the fluid properties (density and viscosity) at a mean temperature and utilizing these in equation (1). The friction factor (f) may be estimated from the Reynolds number (N_{Re}) by means of the empirical relation

DECLASSIFIED

DECLASSIFIED

-304-

HW-40000

(2) $f = \frac{a}{N_{Re}^e}$ where a and e are constants and $N_{Re} = \frac{D_e V \rho}{\mu}$.

For constant flow passage dimensions, we may combine (1) and (2) with the flow continuity condition to obtain

$\Delta P = CF^{1.8}$ where F is the volume flow rate and C is a proportionality constant. Now since the pumping power (P) required to maintain a given flow rate is proportional to the product of the pressure drop and the flow rate we have

$$P = CF^{2.8}$$

It is evident that the required pumping power, which represents a pile operating cost, rises rapidly with increasing flow for a constant flow passage size. Increasing the flow passage size reduces the pressure drop for a given flow or, alternatively, increases the flow rate attainable for a given pressure drop. From the fluid flow standpoint alone then, it would be desirable to have a large annulus size in the piles. However, this consideration must be balanced against opposing factors such as providing space for enough uranium to give satisfactory reactivity, and the fact that water is a nuclear poison.

C. HEAT TRANSFER

1. General Considerations

In any nuclear reactor provision must be made for removing the heat generated in the fission reaction, in order to maintain reasonable temperatures in the pile structure. In practice, maximum temperature limitations may be placed on any or all of the material components of the reactor. As an example from the fuel element standpoint, a classical limitation at Hanford has been that the uranium should not undergo an alpha-beta phase transformation during pile operation. This means that the maximum uranium temperature must be kept below about 660 C. A limitation has also been placed on the slug surface temperature in order to keep

DECLASSIFIED

DECLASSIFIED

-305-

HW-10000

corrosion of the aluminum slug jacket (or can) within reasonable bounds.

In the Hanford reactors, pressurized liquid water is used as the coolant. The water (treated Columbia River water) enters the reactors at an average temperature of about 12 C (varying somewhat with the season). The combination of high specific heat and good heat transfer rates obtainable with liquid water make it a highly satisfactory coolant. The specific heat varies from 1.0 to 1.2 Btu/lb^oF over the temperature range from 32 to 500 F. With reasonably high velocities, such as prevail in the Hanford cooling annuli, heat transfer coefficients up to about 10,000 Btu/hr ft² are obtained.

2. Discussion of Temperature Drops

Heat transfer computations may be most clearly described by considering several temperature drops separately. These are the drops (a) across the water film next to the slug jacket, (b) across scale or corrosion film on the outside of slug jacket, (c) across the jacket proper, (d) across the bonding layer between jacket and uranium core, and (e) across the uranium core. Figure III-1 shows a qualitative sketch of these temperature drops.

2.1 Temperature drop across water film. The first problem is the estimation of the heat transfer coefficient of the water film. The most widely used equation for estimation of the water film heat transfer coefficient is the correlation of Seider and Tate:

$$\frac{h_1 D_e}{k} = 0.023 \left(\frac{D_e V \rho}{\mu} \right)^{0.8} \left(\frac{C_p \mu}{k} \right)^{0.4} \left(\frac{\mu}{\mu_s} \right)^{0.14}$$

This equation is considered adequate to calculate heat transfer coefficients for turbulent flow with Reynolds Numbers up to 200,000⁽¹⁸⁾. A common modification to this equation is the omission of the last term expressing the viscosity ratio of the water at the bulk water temperature to that at the slug surface temperature⁽¹⁸⁾. When this modification is made the physical properties of the water (evaluated at the bulk water temperature) may be combined into one factor to give

DECLASSIFIED

DECLASSIFIED

$$h_1 = K_t \frac{V^{0.8}}{D_e^{0.2}}$$

Figure III-2 shows a plot of K_t for water versus the bulk water temperature. With the heat transfer coefficient determined, the temperature drop across the water film may be calculated from the usual equation for convection:

$$\Delta t_1 = \frac{q}{h_1 A_1}$$

Inserting the surface area for a standard size Hanford slug (1.440 inch canned diameter) and converting to specific power in kw / ft and temperature in $^{\circ}\text{C}$, the temperature drop may be expressed as ⁽²⁴⁾

$$\Delta t_1 (^{\circ}\text{C}) = \frac{5029 Q}{h_1}$$

2.2 Temperature drop across corrosion film. Buildup of a corrosion film or scale on the slug surface during pile operation effectively decreases the equivalent diameter of the flow channel and may manifest itself as an increased pressure drop for a given flow. Scale pressure drops of 10, 20, and 40 psi have calculated scale temperature drops of 17, 34, and 68 C respectively, at a specific power of about 30 kw / ft⁽⁹⁾. In an early pile test, film buildup was observed to affect the operating temperature of the slug by less than 3 C⁽⁷⁾. Periodic purging of the tubes may be used to keep the film thickness (and thus pressure drop and temperature effect) at a reasonable value. A method for determination of the rate of film formation has been described in the literature ⁽¹⁴⁾.

2.3 Temperature drop across slug can. This temperature drop may be expressed as

$$\Delta t_3 = \frac{q m}{k_1 A_2}$$

Again, with the standard slug OD, we have

$$\Delta t_3 (^{\circ}\text{C}) = 301.8 \frac{Q}{k_1} \ln \left(\frac{1.440}{1.440 - 2m} \right)$$

DECLASSIFIED

Now for an aluminum can, for which the thermal conductivity is about 120 Btu/hr ft °F and for a can wall thickness of 40 mils, we have finally,

$$\Delta t_3 (^{\circ}\text{C}) = 0.144Q$$

2.4 Temperature drop across bond. This temperature drop may be expressed as

$$\Delta t_4 = \frac{q}{h_3 A_3}$$

if we have available an effective heat transfer coefficient for the thin bonding layer. Such coefficients have been determined experimentally for various types of bonds⁽²¹⁾. Table III-1 summarizes the data available on various types of bonds. The tests were performed at heat fluxes of 10-30 kw/ft with average bond temperatures of 125-325 C. Within the accuracy of the tests the heat transfer coefficients were found to be independent of heat flux and average bond temperature⁽²¹⁾. For the standard slug diameter,

$$\Delta t_4 (^{\circ}\text{C}) = \frac{7243 Q}{h_3(1.440-2m)}$$

For an Al-Si lead dip bond and a 40 mil aluminum can, we have finally,

$$\Delta t_4 (^{\circ}\text{C}) = 0.178 Q$$

2.5 Temperature drop across uranium core. There are several methods in current use for calculating this temperature drop. The simplest method involves the assumption of constant uranium thermal conductivity and uniform volumetric heat generation across the uranium core. With these assumptions the temperature drop across a solid cylindrical uranium slug is given by

$$\Delta t_5 = \frac{W b^2}{4k_2}$$

where W is the uniform volumetric heat generation rate. Expressing specific power as kw/ft, temperature as °C, and using $k_2 = 18 \text{ Btu/hr ft } ^{\circ}\text{F}$, the above equation becomes

$$\Delta t_5 (^{\circ}\text{C}) = 8.38 Q$$

It will be noted that when specific power is expressed as kw/ft, the temperature drop across the solid uranium core is independent of core diameter. Figure III-3 has been constructed on the basis of the above equation. In drawing the curves a correction factor was applied because the simplified equation overestimates the uranium temperature drop. For a cored slug with similar simplifying assumptions we obtain

$$\Delta t_5 = 8.38 Q \frac{2c^2 \ln \frac{c}{b}}{b^2 - c^2} + 1$$

This equation has been plotted as Figure III-4 for the case of the standard Hanford O.D. (1.336 inches) with various hole sizes.

The thermal conductivity of unirradiated uranium is known to vary with temperature. Attempts have been made to determine the effect of irradiation (See Chapter VI) but the situation is not clear at present⁽²³⁾. Usually the Kuniansky data⁽²⁶⁾ for unirradiated uranium are used. The conductivity is expressed as a linear function of temperature as follows:

$$k_2 = (k_2)_0 + \left(\frac{1}{\alpha} \right) t$$

For k_2 in Btu/hr ft °F and t in °C, the equation becomes

$$k_2 = 14.3 + 0.012 t$$

The assumption of uniform power generation is in error because of the blocking effect of the outer layers of uranium which causes the flux (and thus the power generation) to decrease toward the center of the uranium core. A first order correction to the uniform power generation assumption is provided by the use of simple diffusion theory to account for the change in flux across the slug core. According to this theory the radial power generation is described by means of a modified Bessel function.

Making use of the diffusion theory approximation and linearly temperature dependent uranium thermal conductivity the temperature drop across

DECLASSIFIED

DECLASSIFIED

the solid uranium core may be computed from reference (24):

$$\frac{t_6^2 - t_5^2}{2 \alpha} + (k_2)_o (t_6 - t_5) = \frac{1896 Q}{2 \pi D b} \frac{I_0 (H b) - 1}{I_1 (H b)}$$

Here, t_6 is the maximum uranium core temperature and t_5 is the uranium surface temperature. Inserting the standard slug diameter and the constants from the thermal conductivity equation yields

$$t_6^2 - t_5^2 + 2384 (t_6 - t_5) = 22,700 Q$$

For a cored, externally cooled slug, the general expression is more complex, involving K_0 's and K_1 's (modified Bessel functions of the second kind) as well as the I_0 's and I_1 's (first kind). For a 3/8 inch diameter core, standard slug diameter, the expression reduces to: (24)

$$t_6^2 - t_5^2 + 2384 (t_6 - t_5) = 18,480 Q$$

Extensive derivations and applications of these equations, as well as treatment of end effects (eg., boiling at the slug and caps), are available in the Hanford literature. (8), (11), (12), (16), (17)

The analysis of the internally-externally cooled fuel element is more complex than the analyses discussed above, involving as it does a geometry dependent distribution of coolant flow and heat flow to the two coolant channels. A non-iterative method of solution has been derived and is completely described in reference (19).

3. Results of Typical Calculations

As an example of the application of the principles discussed previously, the results of typical calculations for solid, cored, and internally-externally cooled slugs are presented in Table III-2⁽²⁰⁾. The case considered was the Hanford C-Pile with a tube power of 1000 KW, an inlet water temperature of 15 C and an outlet temperature of 105 C. It was assumed

DECLASSIFIED

DECLASSIFIED

HW-40000

that 94 per cent of the power was generated in the uranium (balance in the graphite) and that the longitudinal power distribution across the tube was sinusoidal.

4. The Slug Burnout Problem

If the water flow in a process tube is permitted to decrease below a specific allowable minimum value, slugs will become surrounded by an insulating blanket of steam. If the steam film persists, slug temperature will rise with continued operation resulting in melted slug jackets and tubes. This phenomenon is known as burnout. It is obviously important to assure that such conditions do not arise under any reasonable conditions of pile operation. A detailed discussion of this effect and the measures taken to guard against it is considered beyond the scope of this manual. The interested reader will find several excellent discussions in the literature. (5), (6), (10), (13), (15), (22)

D. THERMAL STRESSES

1. General Considerations

Whenever a solid body is subjected to temperature gradients, incompatible thermal expansions occur which cause thermal stresses. These stresses may become very large and may cause failure of the material. Fuel elements under irradiation are subjected to temperature gradients both under steady state operating conditions and during transients (eg., pile startup and shutdown or changes in local power generation due to movement of control rods) which cause thermal cycling of the material.

Calculated values of stresses are highly dependent on the assumed relation between stress and strain⁽³²⁾, eg., elastic or plastic behavior.

DECLASSIFIED

As indicated in the sketch of the familiar stress-strain curve, elastic behavior is characterized by a linear relationship between stress and strain. In the case of a plastic material less stress is required to produce a given strain than for elastic strains.

2. Application of Stress Analysis to Hanford Type Fuel Elements

It is generally agreed that a change in fuel element from the present solid cylinder to a less highly stressed element is necessary to prevent excessive failure rates at projected future power densities. Two avenues of approach to this problem have been considered for development. One method seeks more effective cooling of a cylinder to provide lower temperature drops, and thus lower thermal stresses, while the other method permits part or all of the uranium to operate at higher temperatures (in the beta or gamma phase) to obtain stress relief by plastic yielding. These two methods will now be discussed separately.

The internally-externally cooled (I and E) slug provides a more effectively cooled cylindrical fuel element. In this slug, a central hole lined with can material (aluminum at present) provides a path for coolant in addition to the annular passage around the outside of the slug. As an intermediate case between the conventional solid slug and the I and E slug, the cored slug containing a central hole but cooled externally only, has been developed.

A comparative stress analysis has been made for these three types of slugs⁽³⁰⁾. The mathematical details of the method of analysis have been treated in another paper⁽²⁸⁾. Figure III -5 and III-6 are based on this analysis and show qualitatively the effects to be expected for the three types of fuel elements. Table III-3 gives calculated results for the case of fuel elements operating at a specific power of 50 kw / ft.

The lack of proportionality between temperature drops and maximum tensile stress can be partially explained by the difference in operating temperature for the three slug types⁽³⁰⁾. At higher temperatures an

DECLASSIFIED

DECLASSIFIED
HW 140000

increased fraction of the strains arising from the incompatible thermal expansions are due to plastic slip; hence relatively lower thermal stresses are developed. Also, as the method of cooling becomes more effective, as in cored over solid slugs and I and E over cored slugs, the ratio of thermal gradient to maximum temperature drop increases near the outer surfaces. Since temperature gradients are a measure of the incompatibilities of thermal expansion which cause thermal stresses, the ratio of circumferential thermal tensile stress to temperature drop may be expected to increase as the cooling method becomes more effective.

Because the mechanism of a split type rupture is related to a crack formation process which depends on the amount of plastic flow, a strain criterion should be a more direct indication of failure probability than a stress criterion.^{(29), (30)} Experiments with unirradiated uranium and stainless steel^{(35), (36)} have indicated that for given temperature limits the product of the plastic strain per cycle and the number of thermal cycles can be used to predict when failure will occur. It is evident from Table III-3 that the use of the plastic shear strain instead of the maximum circumferential stress as an indication of failure probability considerably enhances the merits of the I and E type fuel element.

In order to limit crack propagation and thus reduce the split type failure rate as well as to make the consequences of a failure less severe, several types of fuel elements containing pre-fractured uranium have been suggested. The wafer type slug and the uranium shot-magnesium matrix slug are examples of this type of approach to the stress relief problem.

To take advantage of the plastic behavior of uranium at elevated temperatures, several designs have been considered. The insulated slug contains a layer of thermal insulating material (eg., aluminum oxide) between the uranium surface and the can wall. This heat transfer barrier causes the uranium to operate at high temperatures and thus permits stress relief by plastic deformation.

DECLASSIFIED

The coaxial fuel element, (33), (34) consisting of two separate concentric uranium cylinders separated by a gap for thermal insulation, represents another design concept to permit plastic behavior of the uranium. The outer uranium cylinder operating at relatively low temperature may be looked on as a high strength container for the inner cylinder operating at high temperature.

As mentioned previously the numerical results of stress calculations are strongly dependent on the type of material behavior model which is assumed. The problem is quite complex as may be realized by considering the fact that varying operating temperatures, thermal cycling during pile startup and shutdowns, and irradiation effects all cause alterations in the properties of uranium. The general result is that the material model changes with time as irradiation progresses. This discussion has been limited to qualitative considerations and some specific examples in order to avoid lengthy mathematical discussions. The interested reader may examine the literature cited at the end of the chapter for the mathematical developments and detailed consideration of the underlying assumptions.

E. CORROSION

1. Bare Uranium

Water at elevated temperatures rapidly attacks bare uranium forming the dioxide, UO_2 . Figure III-7 shows the corrosion rate of unirradiated uranium in water as a function of temperature. Exposure of bare uranium in the Hanford piles would result in washing of the corrosion products, containing highly radioactive fission products, into the pile effluent water. This would produce an intolerable level of contamination in the water discharged to the plant environs. For this reason it is important that the uranium slugs be canned in a corrosion resistant container prior to irradiation in the reactors. The material currently in use for this purpose is 2S aluminum.

2. Interdiffusion of Uranium and Aluminum

If uranium is canned so that the uranium and aluminum surfaces are in direct contact an interdiffusion of the two metals can take place. The

DECLASSIFIED

DECLASSIFIED

CONFIDENTIAL

conditions of surface contact and temperature determine the extent and rate of diffusion. This diffusion produces brittle compounds such as UAl_3 which may cause cracking of the can permitting water entry and subsequent rapid undercutting of the exposed uranium surface. Some of the reactions which may take place are as follows:⁽⁵³⁾

The presence of the can may serve to prevent the removal of the hydrogen formed in the first reaction thus increasing the corrosion rate through the intermediate hydride formation reaction. The large volume increases which occurs with the formation of these corrosion products may cause swelling of the canned assembly with consequent reduction or stoppage of coolant flow. In an operating reactor such a situation must be quickly detected and acted upon (the reactor shut down) to prevent disastrous overheating of pile components.

In the present uranium fuel elements a layer of a eutectic alloy of aluminum and silicon (Al-Si) is used as a diffusion barrier between the slug and the aluminum can. This bonding layer also acts as a high conductivity path for heat flow from the uranium slug through the can to the pile cooling water. The methods of preparation and testing of such uranium - AlSi - aluminum can assemblies are discussed in detail in Chapter VIII of this manual.

3. Corrosion of Aluminum (2S) Cans

Several types of corrosion which might occur are thermogalvanic corrosion, pitting attack, intergranular attack, and generalized corrosion. By thermogalvanic corrosion is meant the increase in corrosion of a hot aluminum surface due to the presence of a colder aluminum surface electrically connected to the hot surface. In-pile experiments have demonstrated

DECLASSIFIED

-315-**DECLASSIFIED**

HW-40000

that under present conditions of process water quality this type of corrosion does not constitute a problem in the reactors⁽⁴⁶⁾. If other materials were used in cans and/or process tubes a re-evaluation of the effect would of course be necessary.

Localized pitting attack appears to be important in water at low pH⁽⁴⁵⁾. Surface inclusions in the aluminum cans may also lead to this type of attack,⁽⁵⁵⁾ and for this reason considerable effort is devoted to minimizing the occurrence of such inclusions during the canning process. Increasing coolant flow rate and pH will decrease pitting.⁽⁴⁵⁾ It has also been shown by experience that a small amount of sodium dichromate added to the pile process water inhibits this type of attack. Observations made on slugs exposed in the reactors and cooled with pH 7.6 process water containing 2 ppm dichromate have shown that in general both the frequency and average depth of pitting increases with increasing slug surface temperatures.⁽⁴⁸⁾ However, the point at which pitting becomes a serious limit on fuel element performance is not known at present.⁽⁴⁸⁾

Another type of localized corrosion, known as intergranular attack, occurs at high temperatures. At 230 C and above, 2S aluminum suffers rapid intergranular attack and is of little value as a corrosion barrier.⁽⁵⁵⁾ A change of slope in the plot of log corrosion rate versus reciprocal temperature occurs in the vicinity of 230 C. The actual temperature at which this change in corrosion mechanism occurs varies with the composition, degree of cold work, and other properties of the alloy.⁽⁵⁵⁾

Intergranular attack has been noted in "hot spots" on several slugs which have ruptured in the piles.⁽⁵²⁾ The corrosion film in these areas of the slugs had the appearance of boiler scale, which is indicative of excessively high water temperatures. The water temperatures required for boiler scale formation in pH 7.6 and 7.3 process water are about 135 C and 145 C respectively.⁽⁵²⁾ Under present pile outlet water temperature conditions (approximately 100 C) it appears that local elevation of the water temperature can cause fuel element failures through the mechanism of intergranular

DECLASSIFIED

Using these corrosion rates, slug corrosion limits (usually specified as maximum allowable tube outlet water temperatures) have been derived for various pile conditions of power, flow rate, and exposure concentration of the uranium.⁽⁵⁰⁾

The preceding discussion has emphasized the corrosion aspects of the fuel element cladding (can). Similar considerations apply to the process tubes which are currently made of 2S aluminum, clad on the inside with 72S aluminum. Data currently available show no significant difference between the corrosion rates of these two alloys.⁽⁵⁴⁾

4. Other Can Materials

Very pure aluminum (99.99+%) is inferior to 2S aluminum from the standpoint of intergranular corrosion, suffering this type of attack at temperatures as low as 100 C.⁽⁵⁵⁾ Some alloys have been found, however, which are vastly superior to 2S aluminum in this respect. One of the most promising of these alloys is M-388 (2S aluminum containing 1% nickel). This alloy does not appear to corrode intergranularly even at temperatures up to 350 C.⁽⁵⁵⁾ The M-388 alloy thus offers some promise as a corrosion resistant material for a temperature range up to 350 C.

Zirconium has long been considered a possible substitute for aluminum because of its good corrosion resistance, negligible interdiffusion with uranium, and very low neutron absorption cross section.⁽⁴³⁾ Some of the disadvantages of zirconium as a slug can material are hydrogen embrittlement on reaction with water⁽⁴⁴⁾, fabrication difficulties, and its high cost relative to aluminum.

DECLASSIFIED

DECLASSIFIED

-319-

HW-40000

F. NOMENCLATURE

<u>Notation</u>	<u>Definition</u>	<u>Common Engineering Units</u>
A	Cross sectional area for flow	ft ²
A ₁	Surface area of canned slug per unit length	ft ² /ft
A ₂	Log mean surface area of slug jacket	ft ² /ft
A ₃	Bond surface area	ft ² /ft
a	Constant in friction factor equation $\cong 0.17$	dimensionless
b	External radius of slug core	ft
C	General proportionality constant	-
C _p	Specific heat at constant pressure	Btu/lb _m F
c	Internal radius of cored slug	ft
De	Equivalent diameter = $\frac{4 \times \text{cross sectional area}}{\text{wetted perimeter}}$	ft
e	Constant in friction factor equation $\cong 0.2$	dimensionless
F	Volumetric flow rate	ft ³ /sec
f	Darcy-Weisbach friction factor (=4 X Fanning friction factor)	dimensionless
g	Gravitational conversion factor = 32.2	$\frac{\text{lbm ft}}{\text{lb}_f \text{ sec}^2}$
h ₁	Heat transfer coefficient of the water film	Btu/hr ft ² °F
h ₂	Heat transfer coefficient of the corrosion film	Btu/hr ft ² °F
h ₃	Heat transfer coefficient of the bonding layer	Btu/hr ft ² °F
I ₀ , I ₁	Modified Bessel functions of the first kind and orders zero and one	-
K ₀ , K ₁	Modified Bessel functions of the second kind orders zero and one	-
k	Thermal conductivity of water	Btu/hr ft °F
k ₁	Thermal conductivity of can material	Btu/hr ft °F
k ₂	Thermal conductivity of uranium core	Btu/hr ft °F
l	Length of flow channel	ft
m	Slug jacket thickness	inches
N _{Re}	Reynolds number = $\frac{D_e V \rho}{\mu}$	dimensionless

DECLASSIFIED

DECLASSIFIED HW-70009

corrosion. Local hot spots may be due to misalignment of slugs in the process tubes caused perhaps by excessive pressure on the slug column during charging.

In addition to the types of localized corrosion which have been discussed above, generalized or uniform corrosion must be considered. This type of corrosion depends on water quality, pH, temperature, and water velocity in addition to the properties of the material being exposed. Figure III-8 shows corrosion rate as a function of temperature for exposure in static process water. The single curve has been found to apply to a large number of aluminum alloys, including 2S.⁽⁵¹⁾ The curve shows that the corrosion rate for 2S aluminum is approximately 13 mils per year for a process water temperature of 105 C and that the rate approximately doubles for each 18 C rise in temperature. In deionized water the corrosion rate is much lower, about 0.2 mils per year for a temperature of 105 C.⁽³⁹⁾

The method of fabrication of cans and their treatment during the canning process may be very important because corrosion rates and tendency toward intergranular corrosion may depend on the hardness of the aluminum, which in turn depends on the amount of cold work and annealing.^{(52), (55)} When testing a new fuel element concept it is thus very important that the materials to be used are corrosion tested in the fabricated conditions; i. e., as completed fuel element assemblies.

The effect of high water flow rates has been estimated to approximately triple the corrosion rate of test coupons.⁽⁴⁰⁾ Here again, in testing fuel elements this variable should be evaluated on actual fuel element jackets at flow rates and temperatures similar to those to be expected in reactor service.

The effect of irradiation on corrosion of aluminum is difficult to distinguish from thermal effects.⁽⁵⁵⁾ The concentrations of certain transient species in water such as HO_2 , H_2O_2 , etc. are greatly increased in a radiation field. These substances could affect the corrosion rate of

DECLASSIFIED

aluminum. Irradiation can also produce changes in the structure of the metal as is shown by the increase in hardness which aluminum undergoes during irradiation.⁽⁵⁶⁾ These changes could also affect corrosion rates. On the other hand, there are no data on in-pile aluminum corrosion which cannot be accounted for by making certain reasonable assumptions concerning the temperature at the corroding surface. Additional experimental work is needed to resolve this question.

When canned slugs are autoclaved at 170 C, a thin film (approximately 0.05 mils thick) of aluminum oxide monohydrate ($\text{Al}_2\text{O}_3 \cdot \text{H}_2\text{O}$) is deposited on the surface of the aluminum can. This film acts as a corrosion barrier. A thicker layer of oxide may be deposited on the surface of fuel elements by means of an anodizing process. Anodic oxidation of aluminum in sulfuric or oxalic acid solution produces a hard, adherent but porous layer of aluminum oxide.⁽⁴⁹⁾ The pores which remain after this treatment can be sealed by hydration of the oxide in a water autoclave at 170 C. It is estimated that the combination of abrasion and corrosion resistance achieved by anodizing may increase the effective aluminum can thickness for corrosion by as much as 5 mils.⁽⁴⁹⁾ Pile tests have shown that abrasion damage to aluminum cans, primarily due to sliding friction between the slug and the ribs of the process tube, does take place during charging.⁽⁴²⁾ In one extreme case gouging to a depth of 12 1/2 mils was noted.⁽⁴²⁾

It should be remembered that in considering corrosion the temperature of interest is that of the corroding surface and not that of the cooling water. In the pile the aluminum slug jacket is heated from the inside by the fissioning uranium and cooled on the outside by flowing water. The aluminum surface temperature will be higher than the coolant temperature and will depend on the power generation in the slug and the properties of the water film and corrosion product film which separate the aluminum surface from the bulk coolant. Empirical correlations of in-pile corrosion data have been developed and used to predict corrosion rate as a function of slug surface temperature, specific power generation, and exposure time.⁽⁴⁷⁾

DECLASSIFIED

DECLASSIFIED

HW-40000

P	Pumping power	ft lb _f /sec
Δp	Pressure drop	lb _f /ft ²
Q	Specific power	kw/ft of length
q	Specific power	Btu/hr ft
t_1, t_2	Temperatures as indicated in Figure III-1	°C
t_3, t_4		
t_5, t_6		
Δt_1		°C
Δt_2	Temperature drop across corrosion film	°C
Δt_3	Temperature drop across can	°C
Δt_4	Temperature drop across bonding layer	°C
Δt_5	Temperature drop across uranium core	°C
V	Linear velocity	ft/sec
W	Volumetric heat generation rate	Btu/hr ft ³
κ	Inverse diffusion length in uranium	ft ⁻¹
ρ	Density	lb _m /ft ³
μ	Dynamic viscosity	lb _m /ft sec

DECLASSIFIED

DECLASSIFIED

G. REFERENCES

General References

- (1) ANL-5311, Reactor Engineering Lectures, Parts I, II, and III, S. McLain, Sept. 54.
- (2) RH-2, Reactor Handbook, Vol. 2, Engineering, U.S.A.E.C., Sept. 53.
- (3) RH-3, Reactor Handbook, Vol. 3, Materials, U.S.A.E.C., Sept. 53.

Fluid Flow and Heat Transfer References

- (4) W. H. McAdams, Heat Transmission, 1942.
- (5) DuH-10169, Boiling in the Pile, W. K. Woods and H. Worthington, 4-1-43.
- (6) DuH-7-2562, Allowable Temperature Rise in Tubes of the Piles, W. K. Woods, 9-27-45.
- (7) HW-10558, Final Report on Production Test 105-80-P, Measurement of Slug Temperature, W. K. Woods and S. S. Jones, 7-27-48.
- (8) HW-24791, Temperature Distribution in a Slug, D. E. Amos, 6-24-52.
- (9) HW-26565, Some Heat Transfer Aspects for New Fuel Element Development, H. H. Greenfield and T. W. Ambrose, 12-15-52.
- (10) HW-26770, Technical Note on Excess Header Pressure, L. H. McEwen and R. J. Shields, 1-9-53.
- (11) HW-27416, Temperatures of Zirconium Jacketed Slugs, D. E. Amos, 3-16-53.
- (12) HW-27918, Maximum Temperatures in a Hollow Externally Cooled Slug, D. E. Amos, 5-1-53.
- (13) HW-28083, Pile Safety as Affected by Boiling Considerations, W. K. Woods, 5-18-53.
- (14) HW-28304, A Method for Precise Measurement of Pile Film Formation, N. R. Miller and W. C. A. Woods, 11-19-53.
- (15) HW-28563, Technical Note on Protection Against Boiling Damage, L. H. McEwen, 7-1-53.

DECLASSIFIED

Fluid Flow and Heat Transfer References (Cont.)

- (16) HW-30226, Steady State Temperature Distributions in Solid Slugs, P. M. Anselone, D. O. Banks, and R. Y. Dean, 12-10-53.
- (17) HW-30853, Temperature Distribution in a Slug with Insulated End Caps, D. E. Amos and C. R. McNutt, 2-15-54.
- (18) HW-32500, Adequacy of the Formulas Used to Calculate Heat Transfer Coefficients Between Slug Surfaces and Coolant at High Reynolds Numbers and Temperatures, H. H. Greenfield, 7-30-54.
- (19) HW-33434, Heat Transfer Analysis of Internally-Externally Cooled Cylindrical Fuel Elements for Nuclear Reactors, REV. F. E. Tippetts, 10-15-54.
- (20) HW-33451, Calculated Temperature for Solid, Cored, and Internal-External Cooled Slugs in C Pile, F. E. Tippetts, 10-18-54.
- (21) HW-33741, Thermal Conductance Tests on Hanford Fuel Element Bonds, R. Neidner, 3-21-55.
- (22) HW-37437, Tube Power Limits - Past, Present, and Future, M. W. Carbon and W. D. Gilbert, 5-31-55.
- (23) HW-38080, Reactor Fuel Temperatures and Apparent Thermal Conductivities, S. S. Jones, 7-25-55.
- (24) HW-38929, Heat Transfer Equations and Graphs for the MTR Testing Facility, W. F. Ekern, 9-7-55.
- (25) M-4476, An Up-to-Date Review of the Principles of Heat Transfer, with Particular Application to Nuclear Power, C. F. Bonilla, 1949.
- (26) TNX-5 Compendium of W-Pile Data, S. Kuniansky, 10-12-43.

Thermal Stress References

- (27) HW-31681, A Plastic Stress Analysis for Solid and Cored Fuel Elements, Part II, K. R. Merckx, 5-12-54.
- (28) HW-32032, A Variational Method for Calculating the Plastic Thermal Stresses in a Finite Cylinder, K. R. Merckx, 6-3-54.
- (29) HW-32562, Time Relations for the Thermal Stresses in an Infinite Cylinder, K. R. Merckx, 7-30-54.

DECLASSIFIED

DECLASSIFIED

-323-

HW-40000

Thermal Stress References (Cont.)

- (30) HW-34911, Comparative Stress Analysis for Solid, Cored, and Internally-Externally Cooled Fuel Elements, K. R. Merckx, 2-7-55.
- (31) HW-36723-RD, Thermal Stresses and Thermal Stress Relations in Hanford Type Fuel Elements, K. R. Merckx, undated.
- (32) HW-36863, General Concepts of Mechanics and Their Relation to Thermal Stresses, K. R. Merckx, 5-24-55.
- (33) HW-38794, Stress Distribution in Coaxial Fuel Elements, K. R. Merckx, 8-16-55.
- (34) HW-39036, A Coaxial Fuel Element Design, T. W. Evans, 9-15-55.
- (35) KAPL-953, A Study of the Effect of Cyclic Thermal Stresses on a Ductile Metal, L. F. Coffin Jr., June 1953.
- (36) KAPL-1020, A Cyclic Thermal Stress Mechanism for Hanford Fuel Slug Rupture, L. F. Coffin Jr., December 1953.
- (37) KAPL-1304, Plastic Analysis of Hollow Cylinders with Uniform Power Generation, L. F. Coffin, Jr. and M. M. Pfleger, 3-1-55.

Corrosion Reference

- (38) ANL-JRH-41, Corrosion Rates of 2S Aluminum-Preliminary Literature Survey, L. E. Link, 10-17-50.
- (39) ANL-5001, Aqueous Corrosion of 2S Aluminum at Elevated Temperatures, J. E. Draley and W. E. Ruther, 2-1-53.
- (40) ANL-5430, Corrosion Resistant Aluminum Above 200 C, J. E. Draley and W. E. Ruther, 7-15-55.
- (41) BMI-998, Apparatus for Visual Study of Corrosion by Hot Water, D. R. Grieser and E. M. Simons, 5-4-55.
- (42) HW-23543, Final Report on Production Test 105-468-P, Mechanical Damage to Slug Cans During Charging, C. H. Goldthorpe, 3-10-52.
- (43) HW-30024, Feasibility Survey of Zirconium and Alternate Reactor Structural Materials for High Temperature Operation, S. H. Bush and R. S. Kemper, 11-18-53.

DECLASSIFIED

DECLASSIFIED HW-40000

Corrosion Reference (Cont.)

- (44) HW-30254, Trip Report Covering Visits to ANL, KAPL, ASM Metals Show, and University of Michigan for Period October 12 to 23, 1953, to Discuss In-Pile Structural Materials, S. H. Bush and M. J. Sanderson, 12-11-53.
- (45) HW-33881, The Galvanic Corrosion of Aluminum, C. Groot, 1-6-55.
- (46) HW-33882, Thermogalvanic Corrosion of Slugs - Final Report on PT 105-29-M, C. Groot, 2-3-55.
- (47) HW-34196, The Corrosion of Hanford Fuel Elements - Method for Treatment and Analyses of In-Pile Corrosion Data, D. R. deHalas, 12-21-54.
- (48) HW-34430, Summary of Slug Pitting Data, D. R. deHalas, 1-12-55.
- (49) HW-35740, Production Cost for Anodizing Present Production Fuel Elements, R. G. Post and W. B. Kerr, 3-17-55.
- (50) HW-36191, A Revised Basis for Slug Corrosion Limits, D. R. deHalas, 4-12-55.
- (51) HW-36692, The Corrosion of Aluminum and Its Alloys, C. Groot and R. M. Peekema, 5-13-55.
- (52) HW-38314, Preliminary Report - Intergranular Corrosion of Aluminum, D. R. deHalas, 7-26-55.
- (53) HW-38379, Second Interim Report on Fuel Element Rupture Tests in High Temperature, High Pressure Recirculating Water Systems, J. M. Skarpelos and K. D. Hayden, 10-5-55.
- (54) HW-38708, Process Tube Corrosion and Replacement Rates, S. Goldsmith and D. R. deHalas, 8-17-55.
- (55) HW-39144, Corrosion Resistant Aluminum Alloys, J. A. Ayres and R. L. Dillon, 10-10-55.
- (56) MIT-1067, The Effect of Radiation on Hanford 2S Aluminum Water Cooling Tubes, J. L. Kline, 2-7-49.

DECLASSIFIED

DECLASSIFIED

H. LIST OF TABLES AND FIGURES

TABLE III-1	Thermal Conductances of Various Fuel Element Bonds
TABLE III-2	Temperature Comparison - Solid, Cored, and I and E Slugs
TABLE III-3	Comparative Values of Maximum Stress, Temperature Drop, and Plastic Shear Strain
FIGURE III-1	Qualitative Sketch of Temperature Drops for a Solid Slug
FIGURE III-2	K_t Vs. Bulk Water Temperature
FIGURE III-3	Relationship Between Specific Power and Uranium Temperature Drop for Solid Cylinders
FIGURE III-4	Uranium Temperature Drop Vs. Specific Power
FIGURE III-5	Comparative Temperature Distribution
FIGURE III-6	Comparative Circumferential Stress Distribution
FIGURE III-7	Corrosion of Bare Uranium in Water
FIGURE III-8	Corrosion of Aluminum

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE III-1

THERMAL CONDUCTANCES OF VARIOUS FUEL ELEMENT BONDS

Data from References (21), (24)

<u>Type of Bond</u>	<u>Nominal Heat Transfer Coefficient, Btu/hr ft² F</u>
Al-Si, lead dip	30,000
Al-Si, hot pressed	10,000
Nickel plated, hot pressed	40,000
Cold pressed	25,000
No bond	6,000
1 mil aluminum oxide	4,800
4 mils aluminum oxide	1,200

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE III-2
TEMPERATURE COMPARISON, SOLID, CORED, AND I AND E SLUGS
 Data from Reference (20)

<u>Quantity</u>	<u>Solid Slug^(a)</u>	<u>Cored Slug^(b)</u>	<u>I and E Slug^(c)</u>	
			<u>Hole</u>	<u>Annulus</u>
Maximum uranium temperature, °C	546	502	263	
Radius of max. U temperature, inches	0	0.220	0.431	
Temperature rise of water across tube, °C	90	90	79	94.3
Maximum Jacket surface temperature, °C	116.4	113.9	105.5	116.9
Heat flow distribution to hole and annulus	-	-	30.6%	69.4%
Water flow distribution to hole and annulus	-	-	32.8%	67.2%

(a) Standard solid slug, 1.44 in. canned diameter, 0.041 in. jacket thickness.

(b) Cored slug, 1.474 in. canned diameter, 0.032 in. jacket thickness, 0.440 in. core diameter.

(c) I and E slug, 1.474 in. canned OD, 0.37 in. canned ID, 0.032 outer jacket thickness, 0.035 in. inner jacket thickness.

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE III-3
COMPARATIVE VALUES OF MAXIMUM CIRCUMFERENTIAL STRESS,
TEMPERATURE DROP, AND PLASTIC SHEAR STRAIN FOR
SOLID, CORED, AND I AND E SLUGS

Specific power = 50 KW/ft
Data from Reference (30)

<u>Slug Type</u>	<u>O. D. (in.)</u>	<u>I. D. (in.)</u>	<u>Maximum Circumferential Stress (psi)</u>	<u>Temperature Drop (°C)</u>	<u>Maximum Plastic Shear Strain(in/in)</u>
Solid	1.36	0	32,200	350	0.00542
Cored	1.36	0.5	28,200	240	0.00173
I and E	1.36	0.5	24,900	100	0.00078

DECLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE III-1

QUALITATIVE SKETCH OF TEMPERATURE
DROPS FOR SOLID SLUG

UNCLASSIFIED

FIGURE III-2

 K_t vs BULK WATER TEMPERATURE

FIGURE III-3

RELATIONSHIP BETWEEN SPECIFIC POWER
AND URANIUM TEMPERATURE DROP FOR SOLID CYLINDERS

FIGURE III-4

URANIUM TEMPERATURE DROP vs SPECIFIC POWER

UNCLASSIFIED

FIGURE III-5

COMPARATIVE TEMPERATURE DISTRIBUTION
All Slugs Operating at Same Specific Power (kw/ft)
Reference(30)

UNCLASSIFIED

HW-40000

FIGURE III-6

COMPARATIVE CIRCUMFERENTIAL STRESS DISTRIBUTION
Reference(30)

UNCLASSIFIED

HW-40000

FIGURE III-7

CORROSION OF BARE URANIUM IN WATER

UNCLASSIFIED

FIGURE III-8

CORROSION OF ALUMINUM (UNHEATED COUPONS IN STATIC PROCESS WATER)
Data from Reference (51)

DECLASSIFIED

-401-

HW-40000

PART II: TECHNICAL BASES (Cont.)
CHAPTER IV: OPERATING EXPERIENCE

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION.	402
B. HANFORD REACTORS.	402
1. Power and Exposure History	403
2. Failure History	404
2.1 Chronological history	404
2.2 Types of failure	405
3. Dimensional Stability.	409
C. SUBMARINE THERMAL REACTOR	410
D. MATERIALS TESTING REACTOR.	411
E. LIST OF TABLES AND FIGURES	412

DECLASSIFIED

DECLASSIFIED
NW-10000

A. INTRODUCTION

Operating experience has been acquired in the United States with many reactor types -- isotope producers, research reactors and power reactors. Intensive efforts are being made throughout the AEC (and in foreign countries as well) to find fuel materials for these reactor types that are stable and can resist the damaging influence of the radiation environment. Our understanding of the phenomena occurring during irradiation is far from complete but progress has been and is continuing to be made.

The occasional failure of a fuel element poses a threat to the reactor. The failure must be detected and the faulty element found and removed from the reactor as rapidly as possible before corrosion product formation can cause damage to the reactor and before a large volume of contaminated water is accumulated. At HAPO, valuable production time is lost with each failure because the reactor must be shut down completely to remove the faulty element.* Likewise, elements which have become lodged in the process tube cause excessive down-time for removal and, sometimes, tube replacement.

In this chapter a description will be given of the difficulties which have been encountered in three of the United States reactors which have had extensive operating experience. As would be expected the section on Hanford Reactors is in more detail than are the sections on the other reactors.

B. HANFORD REACTORS

The eight Hanford reactors are essentially identical. From time to time basic differences appear to exist between the reactors but the effects can always be traced back to differences in the mode of operation. A vigorous attempt has been and is being made to increase the production rate of the reactors. Principally, this has been accomplished by increasing the

*An automatic charge-discharge mechanism is now under study. This may eliminate much of the production time loss since it can function during pile operation.

DECLASSIFIED
DECLASSIFIED

DECLASSIFIED

1990

power levels. Accompanying the power increases, the demands on the fuel element have become more and more severe.

1. Power and Exposure History

The Hanford reactors operated at their designed power of 250 megawatts until 1948 when the program for increasing power levels was initiated. Since that time there has been a steady increase in power except insofar as the seasonal variation of the river water temperature affects the permissible power levels.

It is difficult to describe the increases in power quantitatively because of the wide variation in specific fuel power throughout the volume of the reactor. If a Hanford reactor were charged only with normal fuel elements, the variation in the specific power along any of the cartesian axes could be described by one peak of the sine function. However, a number of fringe tubes (near the edges of the reactors) are routinely charged with enriched fuel elements. The effect of this special loading is to raise the specific power in the fringe tubes so the tube power is quite uniform throughout a large central zone of the reactor. However, from front-to-rear in each tube, the sinusoidal variation still exists (see Chapter II). It is customary to speak of the specific power (in kilowatts per foot of uranium) at or near the center of a tube in the central zone as the power at which fuel elements are being operated in the reactor. In these terms, then, Hanford fuel elements operated at about 10 kw/ft in the beginning. By mid 1956, in the five older reactors, the power level was approximately 45 kw/ft while in the newer C reactor the power was nearly 60 kw/ft. At full power operation, the specific power in the fuel elements of the K reactors ranged up to about 65 kw/ft.

For the first few years of operation of the Hanford reactors, the average tube exposure was 200 MWD/T, or about 0.02% burnup (by fission) of the total atoms. By mid 1956, the tube exposures were approximately 800 MWD/T. This exposure level amounts to nearly 0.1% burnup of the total atoms. The

DECLASSIFIED

DECLASSIFIED

central fuel element in an 800 MWD/T tube operates at 1.4 times the average tube power and thus its exposure is approximately 1100 MWD/T.

2. Failure History

Whenever the fuel element cladding can no longer keep the coolant away from the fuel material, the element is said to have failed. Fission product activity is detected in the effluent water or there is a marked change in water pressure and the reactor is shut down. If an element has failed, it is discharged as soon as possible.

2.1 Chronological history

The Hanford reactors operated without a known fuel element failure until May, 1950. Since that time several hundred failures have been detected and discharged from the reactors. The loss per failure has ranged from about 30 minutes downtime and no damage to the reactor in the best case to several weeks downtime, a punctured tube, extensive damage to the surrounding area, and several hundred gallons of water in the graphite in the worst case. The failure history of the Hanford reactors is shown in Figure IV-1 where the number of failures detected per month is plotted against time. In a general way, this curve can be explained by relating the ups and downs to process or operating changes. Starting in the late forties, the power levels and exposure levels were gradually increased until by 1951 the power level was about 25 kw/ft and the exposure level had reached nearly 600 MWD/T. It is generally believed that the increase in failures in 1951 was simply a matter of the power levels outstripping the quality of the fuel elements. When the failure rate began to increase rapidly, the control and inspection procedures in the metal fabrication and canning processes were tightened. After the elements which were processed under the more rigid controls reached the appropriate exposures, the failure rate declined steadily to a low level which prevailed through 1953.

In the meantime, the new C reactor was finished and began operation in December of 1953. Up to this point no difference had been noted in failure

DECLASSIFIED

DECLASSIFIED

-405-

HW-12109

rates in the different reactors (except for a corrosion problem in F-pile which was traceable to a change in the water treatment process). C-pile, however, was designed for and operated at a substantially higher specific power than the older reactors. The large hump in the failure curve in the first half of 1954 was due to a high incidence of failures in C-pile. The C-pile failure problem was "solved" by using C-reactor for the production of low exposure (200 MWD/T) plutonium. The failure rate again dropped to a low level. Except for an outbreak of seventeen failures at H-pile* in October, 1954, the failure rate remained at a low level until early in 1955. The increased number of failures that occurred during 1955 and into 1956 were principally of a different type both in appearance and exposure reached. Prior to this period, elements rarely failed before about 400 MWD/T tube exposure while almost half of the failures during 1955 occurred below 400 MWD/T.

2.2 Types of failures

The failures which have been observed at Hanford can be placed in one of three major categories; jacket, core, and cap. Occasionally, a fuel element is stuck so firmly in the process tube that it becomes damaged during its forcible ejection from the reactor. In this case it is frequently impossible to determine the type of failure and thus there is also a "miscellaneous" or "fragmented" classification. A description of typical specimens of each class and possible causes of failure are given below.

2.2.1 Jacket failures

One type of jacket failure is characterized by a crater-like eruption of the can wall of the fuel element with a large hole in the can and with the can wall around the hole somewhat raised (See Figure IV-2). Frequently, bulging of the can some distance away from the hole is observed. Because of this bulging, the side failure is dangerous or potentially dangerous because the

*The unusual incident at H-pile apparently resulted from a "hot spot" that developed in the reactor during a startup in October and all seventeen failures occurred in a very small region of the reactor.

DECLASSIFIED

element may stick in the tube or may even puncture the tube. Usually a corrosion crater is found in the uranium directly under the hole in the can. The appearance of the failure suggests that the primary event was the entry of water through very small holes in the can and braze layer, followed by corrosion of the uranium. The jacket ultimately bursts as a result of the ever-increasing amount of corrosion product being formed under it.

The low exposure or hot spot jacket failure (see Figure IV-3) usually has a tear-drop shaped scale pattern on the can wall with a portion of the can seriously corroded. In addition many of these failures occur below 400 MWD/T, whereas very few failures of the preceding type have been observed at such low exposures. On microscopic examination the aluminum in the failure region is found to have corroded intergranularly. Inasmuch as this type of corrosion occurs in 2S aluminum only at elevated temperatures, localized overheating has been advanced as the explanation for this type of failure.

2.2.2 Core failures

The cleavage core failure (see Figure IV-4) is characterized by a split in the can wall and a split in the uranium core coinciding with it. In contrast to the cap and jacket failures, usually very little corrosion of the uranium is observed. Presumably, this is because the fracture is abrupt and fission products appear in the water almost immediately. Occasionally the so-called "incipient" split failures are found. These elements have a wavy indentation in the surface of the can where the aluminum has plastically yielded over a split in the uranium core but the can has not yet fractured. The fracture surface may be either transverse to the cylindrical axis or parallel to this axis. The feature that relates these variations is the primary splitting or cracking of the uranium with failure of the can appearing to be secondary.

DECLASSIFIED

DECLASSIFIED

-407-

REF ID: A64000

The cleavage type of failure is usually not difficult to discharge but has occasionally led to extended outages because of sticking in the tube. During the period 1951-52, the bulk of the failures were cap failures, with cleavage failures accounting for about 25 per cent of the total. During the latter part of 1953 and the first half of 1954 when the C reactor began operating and was producing high exposure plutonium, fifty per cent of the failures were of the split type and the majority of them occurred in the new reactor. During this time the quality of the uranium was steadily being improved and in late 1954 and early 1955 (when C-pile production was converted to low exposure plutonium) even though the powers and exposures were being increased at the older piles, the cleavage failure became of minor importance to Hanford operation.

Some facts have been revealed about the cleavage type of failure: (1) little or no corrosion is observed to have occurred, suggesting that the uranium is not in contact with the water very long; (2) statistical studies of the failures and the conditions associated with them reveal that split failures occur more frequently when the specific power is high, and (3) the majority of cleavage failures are found within two days after startup of the reactor, and furthermore, more cleavage failures occur after a startup preceded by a rapid shutdown than when the shutdown was made at the normal rate.

It is clear from the facts stated above that the cleavage failure is associated with stresses in the uranium. Thermal stresses arise in the uranium because of the anisotropy in its expansion characteristics and because heat is generated throughout the metal but is removed only through the surface. The temperature distribution across the diameter of the uranium is approximately parabolic, rising from about 100 C at the surface to 300-600C (depending on the specific power) at the axis. The hot interior of the metal undergoes thermal expansion to a greater degree than the cooler surface. The result is that on startup, the surface must yield plastically as well as elastically and is under tension while the central region of an element is loaded in compression. Because uranium rapidly loses its ductility under

DECLASSIFIED

DECLASSIFIED

HW 12000

irradiation, the ability of the metal to yield under the imposed stresses during cyclic reactor operation is steadily and drastically reduced. Other phenomena which affect the behavior of the elements are plastic strain and creep and reduction of ultimate strength caused by irradiation. With the time, temperature and stress levels that exist, plastic strain and creep very likely occur, although quantitative information is not available at present. There is evidence that fracture is initiated at the center of the element during shutdown which is an indication that tensile stresses have developed in the center. Reduction of the stresses that arise initially by plastic strain and creep would account for the development of reverse stresses on shutdown. This is analogous to the stress situation that causes shrinkage cracks in castings.

2.2.3 Cap Failures

The cap failure is characterized by a circumferential tear in the can between the cap and the uranium core. The tear may or may not completely encircle the fuel element and thus the cap may or may not be separated from the rest of the element. The central region of the exposed end of the uranium usually contains a large crater or hole. In some cap failures a wedge-shaped piece of uranium is also split away from the end of the slug (this type of failure has also been referred to as a "compound cap failure"). A typical cap failure is shown in Figure IV-5.

During 1951-52, a major portion of the failures observed were cap failures. At this time a more strict control over welding inspection was initiated (along with a change from four-inch to eight-inch elements). The cap failure then became almost non-existent until mid-1954 at which time the canning process was being changed from triple-dip canning to lead-dip canning (see Chapter VIII).

Several theories for cap failures have been advanced. Among these are (1) poor weld integrity, (2) an unsound Al-Si braze layer under the central portion of the cap which would negate the last line of corrosion defense once water has gained an entry through the jacket, cap, or weld,

DECLASSIFIED

DECLASSIFIED

HW-40000

and (3) uneven thermal expansion of the core (lengthwise) which would exert a cyclic strain on the jacket at the core-cap junction (particularly if the Al-Si bonding layer between the core and cap were defective). Once water entry is gained, the poor aqueous corrosion resistance of uranium, the large volume expansion that results from the conversion of uranium to uranium dioxide or hydride (about a factor of two), and the fact that the temperature across the end of the uranium slug is highest on the cylindrical axis of the slug could account for additional pressure on the cap and the resultant crater-like hole in the uranium.

3. Dimensional Stability

In the Hanford reactors, as in the majority of reactors, the fuel elements are made to close tolerances and are held in the reactor in tubes of a size such that only a narrow annulus (0.08 to 0.10 in.) exists between the fuel element and the tube. It is important that fuel elements be dimensionally stable because adequate cooling of the fuel elements must be maintained and it must be possible to remove the elements from the reactor without undue difficulty.

Dimensional instability has been experienced with Hanford fuel elements in a variety of ways. For many years a fraction of the fuel elements developed a bumpy surface as a result of irradiation (see Figure IV-6). On such specimens the uranium had become bumpy and the can developed bumps matching those of the uranium. The fuel elements whose cores had been fabricated by the gamma extrusion method were those which exhibited the most bumping. This bumping essentially disappeared when the fabrication method was changed to alpha rolling, beta heat treating (in rod form) and lead dip canning and, since that time, no operation difficulties have arisen from this condition.

The fuel elements exhibit an overall dimensional instability in addition to the localized deformation referred to above. That is, after irradiation, some elements have increased in length with a corresponding decrease in diameter. Except for a brief period in 1948 during the change over from

DECLASSIFIED

AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

2 of 6

extrusion to rolling as the fabrication method for uranium, this overall dimensional instability has not constituted an operational difficulty of any magnitude.

A form of dimensional instability that has caused and is causing operational difficulties is warp. A slug warp of 0.080 inch is sufficient to cause a slug to stick in an old pile process tube. Analysis of slug warp data has shown that the per cent of slugs which will warp more than 0.080 inch increases roughly ten times with each increase of 200 MWD/T in exposure and triples when the tube power is doubled. At 900 MWD/T and 600 KW/tube about one slug per 1000 will warp greater than 0.080 inch. Lowering coolant temperatures also appears to increase warp. Evidence for this statement is (1) slugs showing maximum warp are invariably located upstream with the greater tendency to warp in the fifth to eighth slugs from the upstream end of the tube, and (2) after startup of K piles, there was a greater tendency to warp in the K pile where the outlet temperatures were 20 to 30 C lower than the temperatures in the older piles.

C. SUBMARINE THERMAL REACTOR (STR)

The first model of the STR was constructed as a prototype for land based testing under simulated service conditions at the National Reactor Testing Station near Idaho Falls. It had already operated for several thousand hours when the "Nautilus" was launched and testing under actual service conditions was begun. As mentioned in Chapter I, the STR fuel element consists of flat plates of 4% U-235 in zirconium alloy fuel material, clad in zirconium. The water temperatures are 225 C inlet and 245 C outlet. The specific power (2000 w/cm³ of fuel maximum, 1000 w/cm³ average)* is such that the maximum fuel temperature is about 335 C. As of March, 1956, no operating difficulties of any sort were traced to the fuel elements of this reactor. They were stable dimensionally; the jacket provided more than adequate corrosion resistance; and no failures had occurred. The elements operated to exposures of about 10% burnup. As mentioned earlier, the fuel element is considerably overdesigned and the economics *50 kw/ft in HAPO elements corresponds to a power density of 200 w/cm³ of maximum.

DECLASSIFIED

DECLASSIFIED

permit this because of the great military value of a submarine propulsion unit which requires infrequent refueling and whose engine does not require air for operation.

D. MATERIALS TESTING REACTOR (MTR)

The MTR has operated since April, 1952, at the National Reactor Testing Station near Idaho Falls, Idaho, as a facility for testing materials under simulated reactor service conditions. The fuel elements consist of a 15% U-235 - aluminum alloy fuel material (flat plate geometry: 0.060 in. thick by 3 X 24 5/8 in.) clad with aluminum (0.020 in. thick). The fuel elements operate at an average specific power of approximately 4500 w/cm³ of fuel to exposures as high as about 30% burnup of the fissionable atoms. Except for one period of time, there had been no operational difficulties traceable to the fuel elements as of June, 1956. During the fall of 1954 several fuel elements failed and many more had extensive corrosion of the aluminum cladding. The nature of the attack suggested that inadequate cooling was the primary cause of the corrosive attack and of the failures. The trouble was traced back to a change in the design of the fuel element which reduced the water flow and pressure inside the fuel elements. The plates were not designed to withstand more than a few pounds per square inch of pressure against the sides and in operation they were buckling. When adjacent plates touched, the water flow was restricted, overheating occurred, and accelerated intergranular corrosion of the cladding material resulted. When the elements were redesigned to permit an even water flow, the fuel element problems diminished although some tendency toward corrosive attack is still noticed. The fuel elements are inspected visually every three weeks and any that show signs of attack are replaced.

DECLASSIFIED

DECLASSIFIED

E. LIST OF TABLES AND FIGURES

FIGURE IV-1	Hanford Failure History
FIGURE IV-2	A Typical Jacket (Side) Failure
FIGURE IV-3	A Typical Jacket (Low Exposure) Failure
FIGURE IV-4	A Typical Cleavage (Core) Failure
FIGURE IV-5	A Typical Cap Failure
FIGURE IV-6	Element with Bumpy Surface

DECLASSIFIED

DECLASSIFIED

FIGURE IV-1

HANFORD FAILURE HISTORY

HW-40000

DECLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE IV-2

A TYPICAL JACKET (SIDE) FAILURE

UNCLASSIFIED

UNCLASSIFIED

FIGURE IV-3

A TYPICAL JACKET ("LOW EXPOSURE") FAILURE

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE IV-4

A TYPICAL CLEAVAGE (CORE) FAILURE

HW-40000

UNCLASSIFIED

FIGURE IV-5

A TYPICAL CAP FAILURE. (THE CAP IS NOT SHOWN.)

FIGURE IV-6
ELEMENT WITH BUMPY SURFACE

DECLASSIFIED

-501-

HW-40000

PART II: TECHNICAL BASES, (Cont'd.)
CHAPTER V: METALLURGY (Unirradiated Materials)

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION	502
B. METALLURGY OF URANIUM	502
1. Crystal Structure and Allotropic Transformations .	502
2. Properties of Uranium	503
3. Deformation of Uranium	503
4. Fabrication of Uranium	503
5. Heat Treatment of Uranium	504
6. Uranium Alloys	505
C. METALLURGY OF JACKET AND TUBE MATERIALS . .	506
1. Aluminum	506
2. Zirconium	507
D. METALLURGY OF TARGET ALLOYS	508
1. Aluminum-Lithium Alloys	508
2. Thorium	508
E. NEUTRON SOURCE MATERIALS	509
F. REFERENCES	510
G. LIST OF TABLES AND FIGURES	511

DECLASSIFIED

DECLASSIFIED

-502-

A. INTRODUCTION

The basic metallurgical properties of unirradiated component materials are presented in this chapter. Since radiation has a marked effect on these properties, Chapter VI, on the metallurgy of irradiated materials, should be considered as a companion chapter treating what happens to the materials when they are exposed to the reactor environment. Corrosion of component materials, which might be regarded as within the scope of these chapters, is covered in Chapter III.

B. METALLURGY OF URANIUM

1. Crystal Structure and Allotropic Transformations

Uranium exhibits three crystalline forms, Figure V-1. The alpha phase, stable up to 660°C , is orthorhombic with unit cell dimensions of: $a_0 = 2.854 \text{ \AA}$, $b_0 = 5.869 \text{ \AA}$ and $c_0 = 4.956 \text{ \AA}$. There are four atoms per unit cell located as shown in Figure V-1. The theoretical density of alpha uranium at 25°C is 19.01 g/cc and at 650°C is 18.45 g/cc .

The beta phase is stable from 660°C to 760°C . The crystal structure of the beta phase is tetragonal with unit cell dimensions of: $a_0 = b_0 = 10.759$ and $c_0 = 5.656$. There are 30 atoms in each unit cell. The density of uranium decreases during the transformation from alpha to beta from 18.45 g/cc to 18.13 g/cc .

The gamma phase is stable from 760°C to the melting point (1133°C). It has a body centered cubic structure with unit cell dimensions of: $a_0 = b_0 = c_0 = 3.474 \text{ \AA}$. There are two atoms per unit cell. Transformation from the beta to gamma phase results in a decrease in density from 18.07 g/cc to 17.94 g/cc . The density of the gamma phase at 1000°C is 17.64 g/cc . Little is known about the mechanism of transformations from alpha to beta or from beta to gamma. Because of its importance in current production processes, the alpha to beta and beta to alpha transformations are being studied intensively. Studies at KAPL⁽⁹⁾ on uranium-chromium alloys showed that the beta to alpha transformation in these alloys was martensitic (a rearrangement of atoms to a new crystal structure without nucleation and growth). Extrapolation of these data leads to the conclusion that the transformation in pure uranium is probably martensitic also.

DECLASSIFIED

DECLASSIFIED

-503-

HW-40000

The cooling rate from the gamma or beta phase has a marked effect on the temperature of the transformations. In Figure V-2 the transformation temperature is plotted vs. the cooling rate⁽¹⁰⁾. At a cooling rate of 2000 C/sec. the gamma to beta transformation temperature is depressed by 110 degrees and the beta to alpha transformation temperature is depressed by 160 degrees to 500 C.

2. Physical and Mechanical Properties of Uranium

These properties of uranium can best be depicted by the series of graphs appearing at the end of the chapter (Figures V-10 through V-14). These include thermal expansion, electrical resistivity, thermal conductivity, hardness, and impact strength.

3. Deformation of Uranium

Uranium deforms by both slip and twinning. At temperatures below 350 C, uranium deforms by slip on the (010) plane in the [100] direction and by {130} twinning. At 25 C the critical shear stress for slip on the (010) - [100] system is 0.34 Kg per mm² (483 psi).⁽³⁾ The (001) plane is approximately parallel to the rod axis under all conditions of working. At temperatures below 350 C a mixed texture is produced consisting predominantly of (010) planes perpendicular to the rod axis and a minor population of (110) planes perpendicular to the rod axis.

Above 350 C, deformation occurs primarily by slip on the (010) plane in the [100] direction. As the temperature of working increases the population of (010) planes perpendicular to the rod axis decreases until at 640 C it essentially disappears. The population of (110) planes perpendicular to the rod axis increases up to about 600 C and then decreases from 600 C to 640 C. Above 600 C, the presence of (200) planes perpendicular to the rod axis has been noted.

4. Fabrication of Uranium

Uranium has been successfully fabricated at temperatures from 25 C to 1000 C. The extrusion constant, defined as $K = \frac{\text{Pressure of Extrusion}}{\ln(\text{reduction ratio})}$,

markedly with temperature as shown in Figure V-3.⁽²⁾⁽⁷⁾ The pressure

DECLASSIFIED

DECLASSIFIED

-504-

REF ID: A40000

required for extrusion at 900 C is about one tenth that required at 650 C. Rolling of uranium is possible in either the alpha or beta phase but the metal is too soft to be rolled in the gamma phase. Near either transformation temperature the metal becomes very hard and brittle because of the extreme hardness of the beta phase relative to the alpha phase at 650 C or to the gamma phase.

Fabrication in the low alpha range, 25 C to 500 C, results in a cold worked structure and a high degree of preferred orientation. Working in the high alpha range, 600 C to 650 C, produces a recrystallized fine grained structure with a low degree of preferred orientation determined by the type of fabrication process.

Uranium rolled in the beta phase temperature range exhibits an alpha grain structure about 6 times larger than alpha worked metal and a random orientation.

Working in the gamma temperature range produces an alpha structure that is randomly oriented with a grain size 20-30 times that produced by alpha phase fabrication.

5. Heat Treatment of Uranium

The alpha-beta-alpha transformation, usually referred to as beta transformation, reduces or eliminates preferred orientation produced in uranium during alpha phase fabrication. This transformation is accompanied by an increase in grain size of about 6 to 1 over the alpha worked, recrystallized grain size.

Beyond these two statements the knowledge of the effect of transformation is sketchy and limited in application. Recent unpublished work at the Savannah River Laboratory indicates that at temperatures between 660 C and 700 C randomization does not occur until after a definite holding period in the beta phase. Several investigators at HAPO have shown that the degree of randomization obtained is dependent upon the cooling rate from the beta phase. Under certain conditions, cycling through the transformation actually increases the preferred orientation of the

DECLASSIFIED

DECLASSIFIED

-505-

REF ID: A60009

(200) planes.

The alpha grain size produced by the transformation is independent of the prior alpha grain size for grain sizes up to about 0.40 mm.* Larger prior alpha grain sizes as produced in gamma phase working are reduced by the transformation; two to three cycles are sufficient to reduce the grain size to about 0.40 mm.

The cooling rate from the beta phase affects the alpha grain structure as shown in Figure V-4a. The bar shown was quenched from 730 C by a stream of water striking the bottom of the bar. Reheating such a sample to 640 C for 20 minutes produces an equiaxed grain structure shown in Figure V-4b for that portion of the bar having a cooling rate in excess of about 5 C/sec. The recrystallization of the beta-quenched grain structure follows the laws of recrystallization of cold worked metals. The rate of recrystallization is related to the temperature by the equation $R = Ae^{-\frac{Q}{RT}}$. The activation

energy is 61,000 cal/mol for uranium in the state of stress produced at the center of a rod when quenched from the beta phase.

Uranium oxides can be retained in solution by rapid quenching from the gamma phase. The size and distribution of uranium hydride particles in uranium are determined by the cooling rate from temperatures above about 500 C. High cooling rates disperse the hydride in a continuous network of fine particles in the grain and sub-grain boundaries. Slow cooling rates cause the hydrides to form large lance-like particles usually located in the grain boundaries.

6. Uranium Alloys

Alloys of uranium have been considered from the standpoints of increased corrosion resistance, improved mechanical properties and refined grain size. Alloys containing large additions of zirconium, niobium, molybdenum or silicon exhibit improved corrosion resistance in water up to 300 C. Special

*The grain sizes for uranium reported in this section were determined using the macro-technique developed by Gardner. (8)

DECLASSIFIED

DECLASSIFIED

The physical properties of both the 1100 (2S) and 6063 (63S) aluminum alloys are very similar to those of pure aluminum except for their

Thermal Conductivity, cal/(sec)(cm)(°C)	
20 - 100 C	23.8 x 10 ⁻⁶
20 - 200 C	24.7 x 10 ⁻⁶
20 - 400 C	26.7 x 10 ⁻⁶
20 - 600 C	28.7 x 10 ⁻⁶
25 C	0.503
100 C	0.503
200 C	0.530
400 C	0.546

Coefficient of linear expansion, per °C

Melting Point, °C 660.2

Density, g/cc 2.694

Thermal Neutron absorption cross-section, barns/atom 0.215 ± .008

1.1 Physical Properties of Aluminum

1. Aluminum

Other physical properties of importance to both uses are thermal conductivity and coefficient of thermal expansion. Aluminum and zirconium are the leading choices for jacket and tube materials.

The principal requirements of jacketing metals are corrosion resistance, low neutron absorption cross-section, formability and freedom from defects that might lead to penetration by water. Process tube metals must possess one more attribute--that of resistance to creep at operating temperatures.

C. METALLURGY OF JACKET AND TUBE METALS

Small additions of chromium, silicon or zirconium refine the grain size of uranium and increase strength with some loss in ductility. Figure V-5 illustrates the change in mechanical properties caused by alloying. heat treatments are required for each alloy to obtain maximum improvement in corrosion resistance.

HW-40000

DECLASSIFIED

-506-

DECLASSIFIED

-507-

HW-20000

melting temperatures which are 643 C and 610 C respectively.

1.2 Formability

The aluminum alloys considered for in-pile use are readily formed into cans or process tubes.

1.3 Mechanical Properties

The tensile strength and creep strength of aluminum decrease rapidly with an increase in temperature. Figure V-6 illustrates the change in tensile strength of both alloys 1100 and 6063 with temperature. The creep properties of aluminum at various strain rates are presented in Figure V-7.

2. Zirconium

2.1 Physical and Chemical Constants of Zirconium

Pure Zirconium

Thermal Neutron absorption cross-section, barns/atom

$0.18 \pm .02$

Density, g/cc

Alpha phase

25 C

6.50

863 C (estimated)

6.36

Beta phase

Above 863 C

6.40

Melting Point, °C

1845°

Coefficient of Linear Expansion, per °C at 25 C

a - axis

5.69×10^{-6}

c - axis

6.15×10^{-6}

2.2 Mechanical Properties

The creep rates of zircaloy-2 in several conditions are tabulated in Table V-1. The effect of temperature on the yield and ultimate strengths of several possible process tube materials is shown in Figures V-8 and V-9. (5)

DECLASSIFIED

DECLASSIFIED

-508-

HW-40000

Cold work markedly increases the yield and ultimate strength of zircaloy-2; however, extended use at elevated temperatures results in softening. Both hydrogen and oxygen dissolved in zircaloy-2 decreases its ductility by factors as high as three.

D. METALLURGY OF TARGET ALLOYS

1. Aluminum-Lithium Alloys

Aluminum-lithium alloys used for the production of tritium are prepared by induction melting at a pressure of less than 300 microns. The low pressure removes the hydrogen normally present in lithium, thus preventing dilution of the tritium. Under equilibrium conditions the alloy consists of two phases, the solid solution of Lithium-Aluminum and the compound Al-Li concentrated in the grain boundaries. Corrosion of this alloy in water occurs primarily by intergranular attack of the compound. Solution heat treatment of alloys containing less than 3.5 per cent lithium at 1020° F for 20 minutes and water quenching converts the alloy to a single phase supersaturated solid solution. Alloys containing more than 3.5 per cent lithium cannot be converted to a single phase and are subject to quench cracking. The corrosion resistance of the unprotected alloy in reactor process water is enhanced by the solution heat treatment. ⁽¹¹⁾

2. Thorium

2.1 Physical and Chemical Constants of Thorium

Density, g/cc	(theoretical)	11.71
Melting point, °C		1690
Coefficient of linear expansion, per °C		
30 to 100 C	11.5 x 10 ⁻⁶	
30 to 500 C	11.9 x 10 ⁻⁶	
30 to 1000C	12.5 x 10 ⁻⁶	

DECLASSIFIED

DECLASSIFIED

-509-

HW-40000

Thermal conductivity, cal/(sec)(cm)(°C)

100 C 0.090

650 C 0.180

Crystal Structure

Face Centered Cubic

2.2 Mechanical Properties

The mechanical properties of thorium are extremely sensitive to small quantities of impurities, especially the carbon content. Pure thorium is very ductile exhibiting elongations of 50 per cent and reduction of area of 70 per cent. The yield strength of annealed thorium is about 25,000 psi and the ultimate strength is about 35,000 psi.

2.3 Fabrication of Thorium

Thorium is readily hot worked by forging, rolling or extrusion. The arc-melted sponge prepared by the Bureau of Mines in Albany, Oregon had much improved fabrication characteristics. Cold worked thorium exhibits a major texture of [111] and a minor [100] texture. Recrystallization produces a single [114] texture. ⁽¹¹⁾

E. NEUTRON SOURCE MATERIALS

Neutron-producing fuel elements are used at HAPO for enrichment and to provide control of flux patterns. Aluminum is nearly ideal as matrix material to carry the U^{235} neutron source. It combines good corrosion resistance below 200 C, ease of fabrication and low neutron cross-section. For alloys containing up to 20 weight per cent uranium, much of the experience on aluminum and its conventional alloys is directly applicable. ⁽⁶⁾ Published phase diagrams ⁽⁴⁾ show a eutectic reaction between aluminum and UAl_4 at 13 weight per cent uranium. At lower uranium concentrations the alloy structure consists of primary grains of aluminum surrounded by eutectic mixture, while above 13 per cent uranium the structure consists of primary grains of UAl_4 surrounded by eutectic. In the latter case the U^{235} will be more uniformly dispersed throughout the matrix and should lead to

DECLASSIFIED

DECLASSIFIED

-510-

more severe irradiation damage than in the proeutectic structure.

Tensile and thermal properties of these alloys are listed in Tables V-2 and V-3.

F. REFERENCES

- (1) O. D. Sherby and J. E. Dorn, University of California Institute of Engineering Research, Sept. 1950 (Effect of Annealing on the Creep Properties of 2S-0 (1100) Alloy.
- (2) AERE-M/R-1048, The Extrusion of Uranium Rod and Tube Direct from Powder, H. Lloyd, 10-28-52.
- (3) ANL-5367, Deformation Mechanisms of Alpha Uranium Single Crystals, H. H. Chiswick and L. T. Lloyd.
- (4) DPST-54-233, The Aluminum-Uranium Alloy System, B. W. Dunnington, 3-30-54.
- (5) HW-33248-RD, Properties of Zirconium and Zircaloy-2 and Alternate Reactor Structural Materials for the DPR, S. H. Bush, 9-30-54.
- (6) HW-34868-C14, Nuclear Metallurgy Lectures, J. E. Minor, 4-22-55.
- (7) HW-37040, Quarterly Report of the Working Committee on Uranium Quality and Fabrication, 6-3-55.
- (8) HW-41343, A Macro Grain Size Technique for Uranium, H. R. Gardner, 2-9-56.
- (9) KAPL-831, The Isothermal Transformation of Metastable Beta Uranium Single Crystals, A. N. Holden, 11-19-52.
- (10) NAA-SP-169, The Effect of the Rate of Cooling on the Allotropic Transformation Temperature of Uranium, Pol Duwez, 2-18-52.
- (11) RH-3, The Reactor Handbook (First Edition) Volume 3, April, 1953.

DECLASSIFIED

DECLASSIFIED

-511-

G. LIST OF TABLES AND FIGURES

TABLE V-1	The Creep Properties of Zirconium and Zircaloy -2
TABLE V-2	Tensile Properties of Forged Aluminum - Uranium Alloys
TABLE V-3	Thermal Conductivity Data for Forged Al-U Alloys
FIGURE V-1	Allotropic Transformations in Uranium
FIGURE V-2	The Depression of Allotropic Transformation Temperatures of Uranium by Increasing the Cooling Rate
FIGURE V-3	The Effect of Extrusion Temperature on the Extrusion Constant for Uranium
FIGURE V-4	The Effect of Cooling Rate from the Beta Phase on Alpha Grain Size and Alpha Annealed Grain Size
FIGURE V-5	The Effect of Alloying Elements on the Tensile Properties of Uranium as a Function of Temperature
FIGURE V-6	The Effect of Temperature on the Tensile Properties of Aluminum Alloys, 1100 and 6063
FIGURE V-7	The Effect of Temperature on the Stress Required to Produce a Creep Rate of 1×10^{-5} in/hr in Annealed Aluminum Alloy 1100
FIGURE V-8	Yield Strength vs. Temperature of Process Tube Materials
FIGURE V-9	Elevated Temperature Tensile Strength of Process Tube Materials
FIGURE V-10	The Range of Expansion vs Temperature Obtained for Beta Heat-treated Uranium
FIGURE V-11	Electrical Resistivity of Uranium versus Temperature as Determined by Bennett
FIGURE V-12	Thermal Conductivity of Uranium
FIGURE V-13	Hardness of Uranium at Various Temperatures
FIGURE V-14	Charpy Impact Strength of Uranium with Temperature

DECLASSIFIED

DECLASSIFIED

HW-40000

DECLASSIFIED

TABLE V-1

THE CREEP PROPERTIES OF ZIRCONIUM
AND ZIRCALOY-2(5)

Material	Secondary Creep Rate in/in/hr	Temperature C	Stress
Zircaloy 2	3 x 10 ⁻⁶	345	19,000
Hot Rolled	1 x 10 ⁻⁵	345	21,000
Cold Rolled	1.8 x 10 ⁻⁵	345	24,000
750 C Anneal	27 x 10 ⁻⁵	345	24,500
Zirconium Sheet	1 x 10 ⁻⁶	360	17,000
	1 x 10 ⁻⁶	370	15,000
	1 x 10 ⁻⁶	380	13,000
	1 x 10 ⁻⁶	400	8,500

DECLASSIFIED

HW-40000

TABLE V-2

TENSILE PROPERTIES OF FORGED ALUMINUM-URANIUM ALLOYS⁽⁶⁾

Composition Wt. % U	Ave. Modulus of Elasticity 10^6 lb/sq in.	Tensile Strength 10^3 lb/sq. in.	Yield Strength (0.2% offset) 10^3 lb/sq. in.	% Elongation
0	10.0	13.0	5.0	45
12.5	10.4	22.5	10.8	20
22.7	10.9	18.6	11.6	4
30.5	11.3	26.1	14.9	10.5

TABLE V-3

THERMAL CONDUCTIVITY DATA FOR FORGED AL-U ALLOYS⁽⁶⁾

Temperature C	Conductivity in cal/(sec)(cm)(°C)		
	12.5% U	22.7% U	30.5% U
200	0.44	0.40	0.36
300	0.43	0.39	0.36
400	0.43	0.38	0.35

DECLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE V-1

ALLOTROPIC TRANSFORMATIONS IN URANIUM

UNCLASSIFIED

DECLASSIFIED

HW-40000

FIGURE V - 2
THE DEPRESSION OF THE ALLOTROPIC TRANSFORMATION
TEMPERATURES OF URANIUM BY INCREASING THE COOLING RATE

DECLASSIFIED

FIGURE V - 3

THE EFFECT OF EXTRUSION TEMPERATURE ON THE
EXTRUSION CONSTANT FOR URANIUM

HW-40000

DECLASSIFIED

(a) As-quenched from 730 C

(b) Same as (a) plus 20 minutes
at 640 C

FIGURE V-4

THE EFFECT OF COOLING RATE FROM THE
BETA PHASE ON THE ALPHA GRAIN SIZE AND
ON THE ALPHA ANNEALED GRAIN SIZE. END
QUENCH SPECIMENS QUENCHED FROM BOTTOM.

DECLASSIFIED

HW-40000

FIGURE V-5

THE EFFECT OF ALLOYING ELEMENTS ON THE TENSILE PROPERTIES OF URANIUM AS A FUNCTION OF TEMPERATURE

DECLASSIFIED

FIGURE V-6

THE EFFECT OF TEMPERATURE ON THE TENSILE PROPERTIES OF
ALUMINUM ALLOYS, 1100 AND 6063

FIGURE V-7

THE EFFECT OF TEMPERATURE ON THE STRESS
REQUIRED TO PRODUCE A CREEP RATE OF 1×10^{-5} in/in/hr
IN FULLY ANNEALED ALUMINUM ALLOY
1100(1)

FIGURE V-8

YIELD STRENGTH vs TEMPERATURE OF PROCESS TUBE MATERIALS

UNCLASSIFIED

FIGURE V-9

ELEVATED TEMPERATURE TENSILE STRENGTH OF PROCESS TUBE MATERIALS

UNCLASSIFIED

DECLASSIFIED

HW-40000

FIGURE V - 10

THE RANGE OF EXPANSION VERSUS TEMPERATURE OBTAINED
FOR BETA HEAT-TREATED URANIUM

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE V - 11

ELECTRICAL RESISTIVITY OF URANIUM VERSUS
TEMPERATURE AS DETERMINED BY BENNETT

DECLASSIFIED

DECLASSIFIED

FIGURE V - 12

THERMAL CONDUCTIVITY OF URANIUM AS DETERMINED BY
DANIELSON AND AS PREDICTED FROM THE WIEDEMAN-FRANZ LAW
USING BENNETT'S ELECTRICAL RESISTIVITY DATA

HW-40000

DECLASSIFIED

DECLASSIFIED

FIGURE V-13

HARDNESS OF URANIUM AT VARIOUS TEMPERATURES

HW-40000

DECLASSIFIED

HW-40000

FIGURE V - 14

CHARPY IMPACT STRENGTH OF URANIUM WITH TEMPERATURE

DECLASSIFIED

DECLASSIFIED

PART II: TECHNICAL BASES (Contd.)
CHAPTER VI: METALLURGY (Irradiated Materials)

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION	602
B. EFFECT OF IRRADIATION ON URANIUM.	602
1. Mechanical Properties	603
2. Physical Properties	604
3. Metallography	606
4. Reactions in the Solid State	609
5. Deformation Mechanisms	610
6. Structural Properties	611
7. Irradiation Damage Hypotheses	612
C. EFFECT OF IRRADIATION ON OTHER COMPONENT MATERIALS	618
1. Mechanical Properties	618
2. Physical Properties.	620
3. Metallography	621
4. Reactions in the Solid State	621
5. Structural Properties	622
6. Chemical Metallurgy	622
D. REFERENCES	624
E. LIST OF TABLES AND FIGURES	631

DECLASSIFIED

DECLASSIFIED

A. INTRODUCTION

A number of special problems arise in connection with fuel elements during their service life in a reactor. In general, these problems were discussed in Chapter IV, Operating Experience. One approach to a solution is to accept some of the deficiencies in the fuel element as being inevitable and endeavor to design around them. An alternative approach is to attempt to understand the underlying mechanisms of the several phenomena. It is the latter approach with which this chapter deals.

B. EFFECT OF IRRADIATION ON URANIUM

The majority of the data available on irradiation damage to fissionable materials is qualitative, consisting of visual observation, or, at most, of measurements of changes in dimensions. The quantitative data available in the fields of mechanical and physical properties, metallography, x-ray diffraction and corrosion are very limited compared to similar data on the unirradiated metals. When one considers the difficulties connected with obtaining one piece of data such as a single elevated temperature tensile test, it is understandable why there is so little information available. For example, a reasonable estimate of the cost of the single elevated temperature test is one hundred thousand dollars; the time from initiation to completion of the test, including irradiation, is about four years; and total expended man hours for design, fabrication, and testing probably exceeds 3000 hours.

The effects of irradiation on the properties of unalloyed uranium are presented here together with the theories advanced to explain these effects, and the implications of radiation damage in fuel elements. Another significant factor discussed is the effect of fission product diffusion and buildup. Radiation damage and fission product buildup are interrelated, but there are significant side effects such as mobility of the inert gases which influence reactor and fuel element design. Also included is a third effect unique to uranium under irradiation, its phenomenal growth when

DECLASSIFIED

DECLASSIFIED

preferredly oriented.

1. Mechanical Properties

1.1 Tensile Properties

Tensile data permit a quantitative evaluation of irradiation damage in uranium. Unfortunately, due to difficulties in handling and testing, only a few tests have been performed. The test results show a drastic decrease in ductility, an increase in yield strength, and a decrease in ultimate tensile strength. (59), (66), (70) The data are presented in Table VI-1. Tensile data reported by Konobeevsky ⁽⁷⁾ of Russia showed that all specimens, regardless of previous history, gave zero elongation values and suffered marked losses in tensile strength after irradiation. Properties of these specimens appear in Table VI-2.

An evaluation of these limited results indicates the profound changes occurring in elongation, tensile strength and yield strength after relatively short exposures. Unless some method yet unknown can be found to minimize such damage, the only answer will be to minimize such effects in the design of the fuel element.

1.2 Hardness

Hardness values are not very useful in interpreting the extent of damage in irradiated uranium. It is safe to say that there will be an increase in hardness with fission product buildup, but a quantitative prediction of the change in other mechanical properties cannot be made on the basis of present data. Typical hardness values are given in Table VI-3. No attempt has been made to convert to one hardness scale due to the dubious validity of such conversions.

Cold worked uranium irradiated in a flux of 10^{11} nv softens under exposures of 10^{15} to 5×10^{17} nvt whereas annealed uranium hardens. ⁽²¹⁾ Annealing experiments show that the hardness induced by these low irradiations (10^{15} to 10^{17} nvt) is stable at 150 C (300 F) but can be removed at 220 C

DECLASSIFIED

DECLASSIFIED

-604-

HW-40000

(428 F). These results for low exposures are consistent with the view that the hardness changes are the net effect of competing processes; hardening due to thermal spiking and vacancy-interstitial generation resulting in removal of atoms from normal sites, and thermal recovery.

The effects of irradiation temperature on hardness were evaluated after irradiation testing of straight and tapered normal uranium pins at exposures to 2×10^{18} nvt.⁽⁶⁶⁾ The hardness of the irradiated pin increased as the calculated temperature of the pin decreased from 900 C to 50 C (1652 to 122 F). The hardness data in Table VI-3 relating to specimens exposed longer than 10^{19} nvt illustrates the definite increases in hardness resulting from more extended irradiations where the substantial burnup and fission product generation is occurring.

1.3 Impact Strength

Work reported by Konobeevsky, et al., of Russia⁽⁷⁾ on specimens cut from cylindrical rods after an exposure of 10^{19} nvt shows that the impact strength of: 1) cast uranium decreased by a factor of 3 to 4 depending on carbon content; 2) heat-treated uranium decreased by a factor of three, and 3) hot rolled uranium decreased by a factor of four. The irradiation temperature of the rods and the type of impact test were not reported.

2. Physical Properties

2.1 Thermal Conductivity

Data on the post-irradiation thermal conductivity of normal irradiated uranium are very limited. This property is an important one because decreases in thermal conductivity on irradiation might increase uranium core temperatures to an unsafe level. The thermal conductivity of uranium fuel elements, measured during irradiation, was reduced 15 per cent at 1×10^{19} nvt after which some recovery of conductivity occurred up to an exposure of 1.4×10^{20} nvt.⁽⁵⁰⁾ Similar results based on post-irradiation measurements were reported by Siegel and Billington.⁽²⁾

DECLASSIFIED

Subsequent investigations on fuel elements showed a decrease in thermal conductivity of about 15 per cent at 7.5×10^{19} nvt, after which no further decrease was observed out to an exposure of 1.7×10^{20} nvt. (68)

The limited data indicate a decrease in thermal conductivity of about 10 to 15 per cent. Since the methods used to obtain these data are probably accurate to within ± 20 per cent at best, the validity of the results in an absolute sense is dubious. Qualitatively, however, the results are quite valuable in that they show no gross change in thermal conductivity of uranium after irradiation.

2.2 Electrical Resistivity

Electrical resistivity measurements are valuable not so much for reactor application as for interpreting the fundamental mechanism of radiation damage, or for predicting thermal conductivities by applying the Wiedemann-Franz ratio. A few typical values are given below.

A four per cent increase in electrical resistivity at 20 C (70 F) was noted for a section cut from a beta heat-treated uranium slug after an exposure to 4.5×10^{19} nvt. (57) The temperature coefficient of resistance was found to be slightly lower for the irradiated material.

Samples of uranium wire exposed in the CP-3 reactor for approximately 4.5×10^{17} nvt at 25 C (77 F) increased one per cent in electrical resistivity. (42) This exposure resulted in the production of 4.2×10^{-4} atomic per cent fission product impurities. The only fabrication history known is that the sample was annealed at 400 C (752 F) for one hour prior to irradiation.

The electrical resistivity of irradiated rolled uranium foil exposed to an average flux of 2.5×10^{19} nvt was determined. (7) The rolled uranium foil increased in resistivity from 30.3 to 30.5×10^{-6} ohm cm for a per cent increase of 0.7. A foil annealed at 600 C (1112 F), then irradiated, increased in resistivity from 28.8 to 29.9×10^{-6} ohm cm or 3.7 per cent after the exposure. Tests conducted during irradiation revealed an increase in

electrical resistivity of only four per cent. ⁽⁷⁾

2.3 Density

Density determinations made at Argonne National Laboratory^(35, 37) are given in Tables VI-4 and VI-5. No data are available on the temperature of irradiation in the case of Table VI-4. The uranium used in obtaining data in Table VI-5 was evidently alpha rolled material.

2.4 Thermal Expansion

Work by the Russians⁽⁷⁾ on rolled uranium foil irradiated to 2.5×10^{19} nvt gives thermal expansion values over the range 100-300 C (212-572 F) of $8.05 \times 10^{-6}/^{\circ}\text{C}$ before and $7.5 \times 10^{-6}/^{\circ}\text{C}$ after the irradiation when measured in the rolling direction, and values in the transverse direction of $16.6 \times 10^{-6}/^{\circ}\text{C}$ before and $15.5 \times 10^{-6}/^{\circ}\text{C}$ after irradiation.

2.5 Modulus of Elasticity

An apparent increase in the modulus of elasticity has been observed after irradiating to 1.8×10^{20} nvt at 150 C (300 F). This was an increase of 10 to 15 per cent, based on tensile test data.⁽⁵⁹⁾

3. Metallography

Metallography is one of the most valuable tools for investigating radiation damage in fissionable materials. Metallographic studies are necessary to determine the fracture modes, grain boundary states, and grain damage. A combination of optical and electron microscopy together with x-ray diffraction should yield much data required for a realistic hypothesis of the radiation damage mechanism.

3.1 Optical Microscopy

The macro study of uranium, excluding bulk geometry measurements, customarily requires etching to reveal the grain structure on the specimen surface. Considerable effort has been expended in an attempt to develop a satisfactory method for macroetching irradiated uranium.

DECLASSIFIED

Cathodic vacuum etching is most satisfactory because a surface cathodically vacuum etched after polishing suffices for both macro and micro examination and does not deteriorate as rapidly as a chemically etched surface. The relationship of cracks, voids, and grain disposition with respect to the bulk geometry can be studied by low power examination (see Figure VI-1). The two photographs illustrate the dependence of contrast among the various grains on the type of illumination used. Many grains appear to be as large as 1 mm in diameter, an erroneous value due to the lack of selectivity and resolution afforded by macro techniques. The apparent macro grain structure, however, frequently reveals zone and orientation effects not discernible by micro examination methods.

Figure VI-2 illustrates the microstructure of uranium irradiated to various exposure levels. In general, as the irradiation exposure increases, the complexity in the microstructure also increases. An interpretation of the microstructure of irradiated uranium, if valid, must be consistent with known facts and observed property changes. As already indicated, many interacting variables influence the microstructure of unirradiated uranium. Superposition of only a few reactor variables, for example thermal and flux gradients, cyclic changes in flux and temperature, and fission, further complicates the problem of interpreting microstructure.

It is conceivable that an accurate evaluation of the microstructure of irradiated uranium will be possible as more and more data are collected and correlated, and that the derived information will also permit predictions of the behavior and performance of uranium for various irradiation conditions. Basically, irradiation introduces thermal and stress effects which initially are relieved by atomic and microstructural changes, primarily slip and twinning. The ability to withstand and overcome these stress conditions apparently decreases with increasing reactor exposure, and must be attributed to the cumulative effect of interstitials and vacancies formed by the neutron bombardment and fission events. Migration and diffusion of these foreign atoms to locations which reduce the ability of irradiated uranium to withstand continued damage

DECLASSIFIED

DECLASSIFIED

HW-10000

is a possibility, and may account for the brittle behavior, the formation of voids and microcracks, and the eventual failure or fracture of uranium due to irradiation.

3.2 Electron Microscopy

The possibility that minute structural detail, such as the presence of fission products or the formation of microcracks at grain boundaries may be discernible with the electron microscope, has warranted development of etching and replication techniques suitable for use on irradiated uranium. Micro-structural detail, unresolvable by optical methods, is shown in the electron micrographs of Figure VI-3. This phase of the metallography of irradiated uranium has just recently begun.

3.3 Etching and Replica Techniques

The etching and replication, as developed for electron microscopy, offers distinct advantages to optical methods of study. Cathodically vacuum etched surfaces can be examined directly on the remotized metallograph with the use of bright field illumination, as opposed to uranium surfaces polished electrolytically, which show structure only with the use of polarized light illumination. Photographic exposure times have been reduced by as much as a factor of 100, since the intensity of bright illumination is so much greater than polarized light illumination.

Replicas of cathodically vacuum etched surfaces of irradiated uranium accurately describe the surface topography, and since they are essentially nonradioactive, they can be examined and photographed on conventional microscopic equipment. Additional advantages of such replicas are: they do not deteriorate with time; they serve as a permanent easily stored record of the specimen; and they can be examined and studied with either bright field or polarized light techniques. Figure VI-4 illustrates the optical appearance of a typical, aluminized Faxfilm replica of irradiated uranium.

DECLASSIFIED

DECLASSIFIED

-609-

DECLASSIFIED

Recent improvements in facilities and techniques have improved the quality of metallographic work on irradiated uranium. Metallographic studies strive to establish the nature and extent of radiation induced damage to uranium, and to evaluate measures which may counteract this damage.

4. Reactions in the Solid State

Certain reactions occurring in fuel elements can profoundly influence the methods of fabrication and cladding. For example, the rate of diffusion of fuel into jacket or recrystallization of the core material may serve as limiting factors in the life of the element. When the fuel diffuses through the jacket and reacts with the coolant, the element has exceeded its life expectancy. Of concern, therefore, is the effect of radiation when superposed on the usual diffusion and recrystallization variables of temperature and time.

4.1 Diffusion

There are very limited data available on the effect of irradiation on diffusion rates. Uranium-stainless steel has been investigated at fluxes of 4×10^{11} to 3×10^{12} nv and temperatures of 500 to 700 C (930-1290 F) over a period of sixteen days.⁽³⁸⁾ The lowest temperature at which diffusion was observed was 380 C (720 F) after 16 days. A marked difference was observed in activation energy, but the apparent effect of fluxes to 3×10^{12} nv was negligible on the diffusion of uranium and stainless steel.

A greater change has been observed in the case of uranium-zirconium and uranium-titanium. Measurements in pin type, pre-bonded couples^(75, 76, 51) are included in Table VI-6

One other type of diffusion is important. This is the diffusion of fission products, particularly the noble gases krypton and xenon through the uranium. Post-irradiation studies by Reynolds⁽¹⁰⁵⁾ on uranium wires indicate a steplike release of the gases. There is an initial period where no gas is released followed by a burst of gas. The amount of gas released is a function of temperature. There is some indication that a limited

DECLASSIFIED

DECLASSIFIED

-610-

HW-40090

quantity of such gaseous fission products is released during irradiation. The diffusion coefficient for xenon in irradiated uranium is quoted as $1.5 \times 10^{-13} \text{ cm}^2/\text{sec}$ at 600 C (1112 F) or about 100 times faster than non-gaseous fission products. (92)

4.2 Recrystallization

No quantitative experiments are known in which the effect of irradiation on recrystallization rate has been studied. A change in grain structure has been observed in uranium which is attributed to heating into the beta region. (66) This effect, however, is probably due to temperature result-in from the flux rather than the flux per se.

5. Deformation Mechanisms

Several studies have been made of the various deformation mechanisms in unirradiated uranium. Slip, twinning, and kink band formation are known to be the means of deformation, with the relative order of deformation by the various mechanisms and the slip or twin planes a function of the test temperature. Unfortunately, there is little or no information correlating the deformation mechanisms in irradiated uranium with those in unirradiated uranium. Since fissioning results in an alloy differing markedly from the pure uranium, it is difficult to select an appropriate basis of comparison between the unirradiated and irradiated metal.

When considering macroscopic plasticity, existent tensile data on irradiated uranium indicate that there is a gross decrease in plastic flow. Whether this is due to a shift in tensile transition temperature, alloying due to fissioning, generation of micro cracks, gross irradiation damage, or a combination of all these factors is unknown. It is probably safest to attribute the change to fission product concentration.

There is no evidence of slip occurring in irradiated uranium. This lack of evidence is understandable since the slip must occur on polished surfaces to be identified metallographically. Extensive twinning has been

DECLASSIFIED

DECLASSIFIED

-611-

HW-4000

observed in uranium irradiated to 6.8×10^{19} nvt. This twinning was accompanied by slight grain growth.^(53, 55) Metallographic examination generally discloses twinning accompanied by a microstructure which can best be described as smudged. Annealing helps to define the microstructure,

An interpretation of the modes of fracture of irradiated uranium needs to be correlated with information on the diffusion of fission products. An intergranular fracture coupled with evidence of intergranular diffusion would indicate quite conclusively the influence of fission products on the mode of fracture. To date, it has not been possible to identify tensile fractures as intergranular or transgranular in nature.

One interesting fracture was observed in a tensile specimen irradiated to 1.8×10^{20} nvt and annealed at 700 C (1290 F), in the beta phase. The fracture consisted of pronounced silvery facets, typical of a cleavage failure.⁽⁷³⁾ Here, too, there are insufficient data to interpret fracture modes.

The best way to summarize the state of knowledge on deformation mechanisms in irradiated uranium is to say there are no quantitative data. A great deal of work must be done in this field.

6. Structural Properties

Potentially, x-ray diffraction is an invaluable tool in recording and assisting in the interpretation of irradiation damage and recovery mechanisms in uranium. Due to the radioactivity of the test specimens, there is a special problem in equipment design. A double crystal x-ray spectrometer is required to separate beta and gamma emission from the specimen from the diffracted x-ray beam. Problems with beam intensity and sensitivity make the instrument not so precise as a standard x-ray diffraction unit.

With all the limitations of a double crystal unit, it has still been possible to detect line broadening, line shift, and asymmetry in irradiated uranium compared to unirradiated uranium. The evidence of damage is available,

DECLASSIFIED

DECLASSIFIED

-612-

HW-40000

but it is not possible to interpret the information quantitatively due to lack of theoretical knowledge in the field of anisotropic materials.

Some evidence of recovery has been observed in uranium exposed to a limited number of spike cycles. Specimens irradiated for two weeks in a poison column facility were found on examination to have a diffraction pattern characterized by asymmetry and slight line shift. ⁽⁶⁴⁾ Subsequent examination yielded the diffraction pattern observed with unirradiated uranium. Current experiments to reproduce these results have not proved successful. Additional work must be done before it can be definitely concluded that recovery occurs at or near room temperature in irradiated uranium.

Uranium single crystals irradiated to low total exposures (7.3×10^{19} nvt), then subjected to x-ray diffraction revealed diffuse Laue spots corresponding to (020) and (021) planes; there were also a few high index planes present on the Laue photogram. Such results indicate substantial fragmentation; there was little or no rotation of the lattice typical in a growth deformation. ⁽⁸⁴⁾

Studies of uranium foils irradiated to 1.9×10^{17} nvt at 175 C (345 F) indicated that line broadening occurred, which could be ascribed to microstresses; annealing at 250 and 500 C (480 and 930 F) was insufficient to cause recovery, but after 16 hours at 600 C (1110 F) the observed diffraction line shape was essentially the same as that in the unirradiated state. ⁽⁷⁷⁾

7. Irradiation Damage Hypotheses

The most significant effects of integrated neutron flux on natural uranium are the pronounced loss of ductility, the disintegration of the metal at nominal burnups, the increased volume, and the growth of preferred oriented specimens. The latter two items will be dealt with under dimensional instability.

DECLASSIFIED

DECLASSIFIED

-613-

HW-40090

The changes in tensile properties are much too great to be attributed to vacancy-interstitial or thermal spike effects. The decrease in room temperature ductility from about twenty to less than 0.5 per cent after irradiation, and the limited effects of 400 and 700 C (750 and 1290 F) anneals, indicate that either a critical dispersion of fission products⁽⁵⁹⁾ or extensive internal cracking⁽²⁵⁾ or both are responsible for the loss in properties.

It is quite probable that the noble gases, xenon and krypton, have a pronounced effect on the mechanical properties, and they are believed to be primarily responsible for the disintegration of alpha uranium after relatively short burnups. Varley⁽²³⁾ and Seitz⁽¹⁰³⁾ believe these gases may result in cracking or fracture of the uranium by a buildup either interstitially,⁽²³⁾ or at voids or cracks.⁽¹⁰³⁾ Unalloyed enriched uranium disintegrates after relatively low burnups and resembles coke, suggesting that the formation and expansion of gas bubbles may play a part in the disintegration.

A suggested mechanism for minimizing irradiation damage due to gaseous fission products has been advanced.⁽²⁴⁾ The introduction of a second phase as small discrete particles should result in the diffusion of the gases to these sites and their being anchored as mono- or multi-atomic layers. Limited work with uranium two phase alloys does indicate that the alloys can be exposed to longer burnups before disintegrating.

7.1 Implications of Irradiation Damage

The significance of the damage occurring in uranium on exposure to neutron flux is readily apparent when the records of fuel element failures are studied. (See Chapter IV) Many such failures were by cleavage, indicative of extensive embrittlement. A study of such factors as metal quality, flux, exposure, and temperature distribution indicates that poor metal quality will increase failures, but the most significant factor is integrated flux. The number of failures increases with increased integrated neutron flux, and after a limiting value the failure rate will increase markedly with increased exposure.

DECLASSIFIED

DECLASSIFIED

HW-40000

The loss in mechanical properties can be minimized by changing the fuel element geometry, by encasing in a strong ductile jacket, by distributing the uranium in a matrix, or possibly, by alloying.

7.2 Fission Product Effects

Aside from the obvious changes in physical and mechanical properties attributable to fission product buildup, there are also problems of reactor contamination due to the diffusion and release of the more mobile atoms, such as the noble gases krypton and xenon. Relatively low concentrations of such gases pose a definite radioactive contamination problem if they escape into the pile coolant. Generally, the release of such products indicates a fuel element failure, but it is conceivable that diffusion rates will be sufficiently high in power reactors to result in a continuous release of gases into the coolant.

The fission event can be summarized as the capture of fast or slow neutrons by the uranium followed by a splitting of the nucleus into two new nuclei. The per cent distribution of the elements formed by such fissioning is a function of several factors.

The fission event is accompanied by the release of approximately 200 Mev of energy, most of which is retained by the two fission products. These ionized particles smash through the uranium lattice, dislodging uranium atoms, generating vacancies and interstitials, probably causing localized melting of the lattice due to the energy release, and finally lodging as foreign atoms in the lattice. Obviously changes of this magnitude cannot be duplicated in alloys of comparable composition compounded by melting and casting or powder metallurgy techniques.

The damage caused by fissioning and the fission products may be annealed to some extent, but elevated temperatures cause other effects. At sufficiently high temperatures, the gaseous fission products, krypton and xenon, diffuse and agglomerate causing macro void generation, gross

DECLASSIFIED

DECLASSIFIED

-615-

REF ID: A665

decreases in uranium density, and possibly pronounced swelling. Porosity has been observed in the outer 600 microns of an irradiated fuel element.⁽¹¹⁵⁾ This was attributed to the flow of radiation-produced vacancies from the periphery toward the center, and their agglomeration at regions of maximum vacancy concentration. This vacancy diffusion is attributed to the presence of large fission product atoms in the uranium lattice. Such diffusion to the sites of these large atoms should relieve the stresses to the point where surface tension of the void in the lattice should balance the presence of single gas atoms. A somewhat similar phenomenon has been observed in a cored fuel element.⁽⁷³⁾ An aluminum clad uranium rod containing a 3/8-inch hole and insulated at the uranium-aluminum interface with an anodized layer to increase the uranium temperature during irradiation was exposed at the Materials Testing Reactor. No dimensional changes were observed in the case of the canned element after irradiation, but on examination of the sectioned element it was found that the hole had disappeared due to flow of uranium, and a gross change in density had occurred. It is quite possible that this phenomenon is similar to that observed by the British, and was caused by movement of vacancies and interstitials and the agglomeration of the diffusing gaseous fission atoms, resulting in extensive internal porosity. This is in agreement with one hypothesis⁽²³⁾ which predicts that irradiated uranium will suffer a large increase in volume due to internal gas pressure, if the creep of the metal is sufficient to avoid fracture. According to this hypothesis, a solid, massive fuel element of uranium is not practical at high temperatures due to formation of gas bubbles.

Post-irradiation tests on the diffusion of krypton and xenon in uranium indicate that thermal cycling or holding at elevated temperatures causes pronounced swelling accompanied by escape of the gas from the fuel elements.⁽¹⁴⁾ These results are essentially the same as observed by Pugh,⁽²⁵⁾ who considered the possibility of either bubble formation or intergranular fracture by the agglomerating gases.

DECLASSIFIED

DECLASSIFIED

-616-

REF-40000

Fission products result in a loss of mechanical properties, and a decrease in density often accompanied by swelling, cracking, and eventual disintegration of the uranium. Because of fission product radioactivity, gross contamination of the reactor or even the reactor site may occur if they are released into the coolant.

7.3 Dimensional Instability

Unalloyed uranium is used as a reactor fuel in the HAPO reactors since it is possible to obtain the maximum conversion ratio with this fuel rather than with an alloy. This means a greater yield of plutonium per gram of uranium. Unfortunately uranium is anisotropic, and exhibits pronounced dimensional instability when preferentially oriented. Fuel element stability is one of the most important factors in a heterogeneous reactor since dimensional changes may result in restriction or plugging of the coolant annulus. This in turn would cause overheating, failure of the element, and contamination of the coolant.

Gross changes in fuel element dimensions were first observed in alpha rolled rod. This growth resulted in a marked upsurge in fuel element failures. Two solutions were found to this problem. The first consisted of controlled rolling over a narrow range of temperature thereby developing a duplex structure which was stable when irradiated. Owing difficulties in controlling the rolling conditions, this method was abandoned in favor of a beta heat treatment which randomized the grain orientation.

The phenomenon of dimensional instability of uranium has been studied by the Americans, British, and Russians. Substantial agreement exists as to some factors favoring growth, whereas there is some disagreement on other parts of the problem. Some of these factors are listed in Table VI-7.

7.4 Thermal Cycling

Present data show no correlation between dimensional instability produced by thermal cycling and that occurring during irradiation. No growth

DECLASSIFIED

DECLASSIFIED

1955-10-00

occurs in single crystals during thermal cycling but they do grow under irradiation. ^(81, 26)

Growth is dependent upon the texture, but there is no correlation of growth as a function of texture when the growth occurs by irradiation and by thermal cycling. A comparison of growth rates in uranium having different textures is given in Table VI-8. ⁽¹⁰⁶⁾

There is still disagreement on the effect of grain size on growth. The only valid application of thermal cycling as an explanation of growth under irradiation appears to be that such a phenomenon might supplement growth due to a grain boundary effect. This has been advanced to explain the different rates of growth under irradiation. ⁽⁸¹⁾ An oriented polycrystal grew more than a pseudo single crystal, which grew more than a true single crystal, in the ratio 6:3:2. British ⁽²⁶⁾ results contradict these data; single crystals and polycrystalline material similarly oriented were reported to grow at the same rate. Differences in metal purity may account for some of these discrepancies.

A comparison of growth due to thermal cycling and irradiation as a function of orientation is given in Table VI-9. ⁽⁸¹⁾

Figure VI-5 illustrates the degree of growth of uranium as a function of orientation. ⁽⁶⁴⁾ In this instance polycrystalline material was oriented by controlling the rolling temperature. Orientations were determined by comparing to a randomly oriented specimen.

7.5 Mechanisms of Growth

Excellent surveys of the early growth mechanisms proposed to explain dimensional instability have been made. ^(106, 12)

Any mechanism proposed must explain the effects of the following factors:

- (1) growth in polycrystalline and single crystal uranium, (2) integrated flux,
- (3) metal purity, (4) the pronounced influence of specimen temperature during irradiation, and (5) the preferred orientation.

DECLASSIFIED

DECLASSIFIED

HW 49000

The two mechanisms best explaining the observed effects are the diffusion mechanism originally proposed by Siegel⁽¹⁰¹⁾ and later revised,⁽¹³⁾ and the modified twinning mechanism.⁽¹³⁾

C. EFFECT OF IRRADIATION ON OTHER COMPONENT MATERIALS

A considerable amount of work has been done to determine the effects of irradiation on materials employed for reactor components. Most of these investigations have been isolated tests on specific materials under widely varying conditions so that comparisons are difficult. For this reason alone, it is apparent that much more work must be performed before the subject is completely understood. A number of excellent review articles have been written in which theories and models have been proposed to explain the observed irradiation effects in solids.^(1, 3, 4, 5, 17, 18, 19, 74, 79, 88, 101)

In this section the general effects on aluminum, zirconium, some of their alloys, and stainless steels are presented. Much of the data could not be included due to space limitations. A more complete discussion of specific investigations may be found in the indicated references.

1. Mechanical Properties

Neutron bombardment produces changes in mechanical properties of non-fissionable metals similar to those produced by plastic deformation. It also increases the yield and tensile strengths, decreases ductility, and increases penetration hardness. The magnitude of the changes depends upon the crystal structure of the material, its recrystallization temperature, the initial state of the material, the temperature of exposure, and the type and length of exposure.

The tensile properties and hardness of 2S aluminum determined by Klein⁽⁸⁹⁾ on sections of a process tube exposed to a maximum fast neutron flux of about 4×10^{20} nvt (0.5 Mev and greater) at 15-60 C are given in Figures VI-6 and VI-7. Additional data for 2S aluminum and some aluminum alloys determined by Steele and Wallace⁽⁸⁷⁾ are given in Table

DECLASSIFIED

DECLASSIFIED

-619-

HW-48400

VI-10. The generally observed greater change in initially annealed material is indicated in Table VI-10. Wright⁽⁵²⁾ and O'Keefe⁽⁶²⁾ determined tensile properties and hardness of the precipitation hardenable alloy, 63-S, in several temper designations after irradiation. These data are shown in Tables VI-11 and VI-12. The property changes produced in high purity aluminum and 2S aluminum are given in Table VI-13⁽⁹⁾. The influence of exposure temperature is indicated by the data of Konobeevsky⁽⁸⁾ in which little or no change in tensile properties or hardness of annealed aluminum resulted from exposure to approximately 1×10^{20} nvt at 250-300 C.

The radiation induced changes in zirconium are similar to those produced in aluminum, but are greater for the same exposure conditions due to the higher recrystallization temperature and different crystal structure. The hardness of irradiated crystal bar zirconium,⁽¹¹³⁾ a 2.5 per cent tin-crystal bar zirconium alloy,⁽¹¹²⁾ and Bureau of Mines zirconium⁽⁶⁷⁾ are given in Table VI-14 and Figures VI-8 and VI-9. The tensile properties of irradiated crystal bar zirconium⁽¹¹³⁾ and Bureau of Mines zirconium⁽⁶⁷⁾ are given in Table VI-15 and Figure VI-10. Additional hardness and tensile property data for crystal bar zirconium alloys were determined at ANL.⁽³³⁾

The data given in Table VI-15 and the results of post-irradiation annealing shown in Figure VI-10 indicate that the changes in tensile properties are slight for zirconium irradiated at temperatures near 250 C.

A number of irradiation experiments have been reported for a variety of stainless steels. The mechanical properties of these materials often depend upon retention of a metallurgically unstable phase or a precipitation reaction. The material is then often metallurgically unstable with respect to temperature and this instability may be aggravated by neutron bombardment. The data that are presented must be viewed with caution and with the realization that more work is required to understand completely the behavior of these materials under certain conditions. The effect of

DECLASSIFIED

DECLASSIFIED

HW-40000

neutron irradiation on the hardness of several stainless steels is given in Table VI-14 and Table VI-16. The influence of prior cold work and subsequent irradiation is given in Table VI-17. The tensile properties of irradiated stainless steels are given in Tables VI-14, VI-18, VI-19, and VI-20.

The effect of irradiation on the impact strength has not been determined for aluminum or the stainless steels. The data of Wheeler⁽⁷¹⁾ and of Bleiberg and Castleman⁽¹¹²⁾ for zirconium are shown in Figures VI-11 and VI-12. The results shown in Figure VI-11 indicate a definite increase in embrittlement of irradiated Zircaloy-2 specimens containing hydrogen.

The possible acceleration of creep in structural materials under neutron bombardment led to a number of in-pile creep experiments.^(20, 22, 45, 46, 110) This property is difficult to measure under laboratory conditions, so it is not surprising that the results of the in-pile tests are not always consistent. The conclusions drawn from these tests are that neutron or cyclotron irradiation has little or no effect on the creep rate of aluminum, the creep rate of zirconium at 260 C is decreased markedly in a fast neutron flux (>0.5 Mev) of approximately 3×10^{12} n/cm²/sec, and that the effect of fast neutron irradiation of Type 347 stainless steel may be to produce a slight increase in the rate above 760 C and a decrease in the rate below this temperature. Other investigators⁽⁴⁵⁾ found no significant effect on the creep rate of 347 stainless steel at 600 C.

2. Physical Properties

The temperature of irradiation markedly influences the changes occurring in some physical properties of metals such as electrical resistivity. Increases of 15-20 per cent in the resistivity of aluminum were found by McReynolds⁽¹¹⁾ after exposure to 1.3×10^{19} nvt at -150 C to -195 C. These changes have been shown to begin annealing at temperatures as low as -80 C and to be completely annealed at room temperature.⁽¹⁰⁾ Klein⁽⁸⁹⁾ found a decrease in electrical resistivity of 2S aluminum

DECLASSIFIED

DECLASSIFIED

REF ID: A6690

process tubing exposed to fast neutron flux of approximately 4×10^{20} nvt at 15-60 C. Since the material was initially cold worked, this decrease was attributed to the same effect noted at high levels of cold work.⁽¹⁶⁾ The effects of neutron bombardment at slightly above room temperature on the electrical resistivity of crystal bar zirconium and a 2.5 per cent tin-zirconium alloy are shown in Figures VI-13 and VI-14. Electrical resistivity increases of 5 per cent were reported for types 304, 309, and 347 stainless steel after an exposure of 5×10^{20} nvt (thermal) and 4×10^{19} nvt (fast) at 540 F.⁽³³⁾ No data have been reported for the thermal conductivity of these materials after irradiation; however, only slight changes would be expected to result from exposure at room temperature or above based on the results of electrical resistivity measurements.

Negligible or slight changes in density, thermal expansion, or dimensions due to irradiation have been found for aluminum,⁽⁴⁸⁾ zirconium,^(33, 58) and stainless steel.^(33, 100) Thermal expansion data for aluminum, aluminum alloys, and Type 347 stainless steel are given in Table VI-21.

3. Metallography

Observation of the microstructure of aluminum⁽⁶⁵⁾ and zirconium⁽⁶⁷⁾ after neutron irradiation has not revealed any changes due to the exposure. This is, of course, dependent upon the exposure temperature. At higher temperatures, recrystallization of cold worked metal and phase changes in alloy systems would be observed. Changes in the microstructure of zirconium due to irradiation have been reported by Russian investigators.⁽⁹⁾ The appearance of deformation twins and evidence of recrystallization during irradiation at temperatures near 250 C were attributed to the neutron bombardment.

4. Reactions in the Solid State

All results to date indicate that irradiation has no influence on the macroscopic diffusion rate of metals.⁽⁶⁾ Other solid state reactions such as order-

DECLASSIFIED

DECLASSIFIED

-622-

REF ID: A66000

disorder processes, phase transitions, precipitation reactions, and recovery processes in non-fissionable metals are found to be influenced by neutron irradiation.⁽²⁷⁾ Increases in magnetic susceptibility of austenitic stainless steels have been observed^(15, 33) indicating some transition from austenite to ferrite. The effect appears to be due to the enhanced growth of existing ferrite nuclei in the presence of radiation. In alloys that develop super-lattice structure, radiation has been shown to have two effects:⁽²⁷⁾ an initially ordered material becomes disordered, and initially disordered specimens tend toward the ordered state. Nucleation of precipitating phases in precipitation hardening alloys has been observed due to neutron irradiation.⁽¹⁾ In addition to these reactions, some amount of recovery or annealing of radiation damage occurs even below room temperatures, and the net effect of reactor exposure at room temperature and above is a balance of the production and annealing of the damage.

5. Structural Properties

Examination of irradiated aluminum by x-ray techniques has shown that additional lattice distortion is produced in initially cold worked 2S aluminum exposed to a total fast neutron flux of 4×10^{20} nvt at 15-60 C.^(90, 91) Lattice expansion was observed in samples of aluminum exposed to 2.5×10^{18} nvt at liquid nitrogen temperature.⁽⁸³⁾ Annealing at room temperature removed the major portion of this damage. Other investigators have not observed structural damage in aluminum.^(93, 95, 97, 98, 107)

Increases in lattice parameter have been observed in irradiated zirconium.^(80, 95, 96, 98)

No studies have been reported for stainless steel.

6. Chemical Metallurgy

Severe corrosion of aluminum samples exposed in a Hanford test hole in water vapor and air was observed in the form of a white deposit and weight gain.⁽⁴⁹⁾ Other investigators have reported noticeable corrosion

DECLASSIFIED

DECLASSIFIED

-623-

HW-40000

at low temperatures in air. ⁽³²⁾ Exposures of zirconium to pile atmosphere were made at temperatures near 580 C. ⁽⁶⁰⁾ Preferential oxidation at welds was observed where oxidation had already been initiated, but the initially sound metal appeared to be unattacked. Short exposures of stainless steel in air at 250-300 C indicated no significant effect of the irradiation. ⁽³²⁾

Experiments at HAP₂O ^(54, 69, 72) have shown that accelerated corrosion of 2S aluminum by flowing water results from pile irradiation. Corrosion rate was increased by a factor of five in a region of thermal neutron flux of 2×10^{13} n/cm²/sec. ⁽⁵⁴⁾ Somewhat limited experiments indicate an increase in corrosion rate on both fuel element jackets and on dummy 2S aluminum elements. Under comparable conditions, with flux as the variable, out-of-pile rates were 0.6 mils/year in high purity water at 180 C (360 F) and pH of 5.2, while in-pile rates were 30 mil/year. ⁽⁶⁹⁾ A tentative corrosion factor has been established for fuel elements which indicates an apparent rise in aluminum surface temperature of 1.8 C for each kilowatt of heat generated in an eight-inch slug. ⁽⁷²⁾ Experience in the Canadian pile indicates that direct irradiation increases the corrosion rate of aluminum, but that the corrosion rate is lower in irradiated water than in un-irradiated water. ⁽³⁹⁾ Deuteron bombardment of 2S aluminum in water at 90 C is shown to have no effect on the corrosion. ⁽⁴¹⁾ The aqueous corrosion of zirconium and zirconium alloys appears to be similar in the irradiated and unirradiated condition. ^(28, 29, 30, 31, 34, 61, 104, 109) The same conclusion is indicated to be true for the stainless steels. ^(28, 29, 34, 36, 40, 41, 82) Although irradiation causes some transformation of austenite to ferrite, the amount transformed is not sufficient to cause an appreciable increase in corrosion susceptibility of the common stainless steel types. ⁽⁴⁷⁾

Neutron, deuteron, and proton bombardment does not appear to aggravate the corrosion of stainless steel in NaK, sodium, or lithium. ^(85, 94, 99)

DECLASSIFIED

DECLASSIFIED**D. REFERENCES**

- (1) D. S. Billington and S. Siegel, Metal Progress, 58, 847, (1950).
- (2) D. S. Billington, "Radiation Damage in Reactor Materials," Geneva Conference Paper A/Conf/8/P-744.
- (3) J. A. Brinkman, "On the Nature of Radiation Damage in Metals," Journal of Applied Physics, 25, No. 8(August, 1954).
- (4) G. J. Dienes, "Effects of Nuclear Radiations on Mechanical Properties of Solids," Journal of Applied Physics, 24, No. 6 (June, 1953).
- (5) G. J. Dienes, "Radiation Effects in Solids," Annual Review of Nuclear Science, Vol. II (1953).
- (6) F. E. Faris, "The Effects of Irradiation on Structural Materials," International Conference on the Peaceful Uses of Atomic Energy, USA Paper No. 747 (June, 1955).
- (7) S. T. Konobeevsky, et al., "Effect of Irradiation on the Structure and Properties of Fissionable Materials," Geneva Conference Paper A/Conf/8/P/681 (July, 1955).
- (8) S. T. Konobeevsky, et al., "The Effect of Irradiation on the Structure and Properties of the Structural Materials," International Conference on the Peaceful Uses of Atomic Energy, USSR Paper 680 (July, 1955).
- (9) NARF-54-1, T, Vol. 1, Radiation Effects Handbook for Aircraft Designers, A. M. Liebschutz, November, 1954.
- (10) A. B. Martin, et al., "The Effects of Cyclotron Bombardment on the Physical Properties of Metals," Bulletin of American Physical Society, 25, 6, 21 (1950). Physical Review, 81, 664 (1951).
- (11) A. W. McReynolds, et al., "Neutron Irradiation Effects at Low Temperature - Cu and Al," Bulletin of American Physical Society, 29, 3, 19 (1954).
- (12) S. H. Paine and Kittel, "Irradiation Effects in Uranium and Its Alloys," Preprint 94, AICHE, Nuclear Engineering and Science Congress
- (13) S. F. Pugh, "Damage Occurring in Uranium During Burnup," Geneva Conference Paper A/Conf/8/P/443, (June 20, 1955).
- (14) M. B. Reynolds, "The Diffusion of Fission Gases in Metallic Uranium," Preprint 92, AICHE. Nuclear Engineering and Science Congress.
- (15) M. B. Reynolds, J. R. Low, and L. O. Sullivan, "Study of the Radiation Stability of Austenitic Type 347 Stainless Steel," Journal of Metals, 7, 555 (1955).

DECLASSIFIED

DECLASSIFIED

- (16) Rutter and Reekie, Physical Review, 78, 70 (L) (1950).
- (17) F. Seitz, Disc. Faraday Soc., No. 5, 271 (1949).
- (18) J. C. Slater, Journal of Applied Physics, 22, Pt. 1 (1951).
- (19) AEC-500, Survey of Effects of Radiation, B. L. Averbach, et al, Undated.
- (20) AECD-3631, Effect of Cyclotron Irradiation on the Creep of Aluminum - Final Report, M. R. Jeppson, et al., February 12, 1953.
- (21) AERE-M/R-741, Effects of Irradiation on the Hardness of Alpha Uranium, P. E. Madsen, July, 1951.
- (22) AERE-M/R-795, Creep of Aluminum in the N.R.X Pile, E. R. W. Jones, et al., October 4, 1951.
- (23) AERE-M/R-1380, A Possible Interpretation of the Irradiation Disintegration of Uranium, J. H. O. Varley, February 17, 1954.
- (24) AERE-M/R-1446, A Possible Method of Minimizing the Damage by Gaseous Fission Products in Uranium Fuels, P. C. L. Pfeil and J. D. Browne, May 31, 1954.
- (25) AERE-M/R-1489, The Growth, Wrinkling, and Fission Product Damage of Uranium and Its Alloys During Irradiation, S. F. Pugh, August 4, 1954.
- (26) AERE-M/R-1518, Some Experimental Irradiation Tests on Natural Uranium, O. S. Plail and L. M. Wyatt, September 20, 1954.
- (27) AERE-M-TN-27, A Survey of Radiation Effects in Metals, J. W. Glen, July 15, 1954, (UNCLASSIFIED).
- (28) ANL-4504, Naval Reactor Division Quarterly Report, June 1, 1950 - August 31, 1950, C. R. Breden, et al., September, 1950.
- (29) ANL-4537, Naval Reactor Division Quarterly Report, September - November, 1950, C. R. Breden, et al., December, 1950.
- (30) ANL-4634, Interim Evaluation of Irradiation of Naval Reactor Fuel Element Prototype Sub Assemblies in Chalk River Reactor, D. C. Layman and S. Naymark, May 1, 1951.
- (31) ANL-4641, Naval Reactor Division Quarterly Report, March - May, 1951, C. R. Breden, et al., June, 1951.
- (32) ANL-4763, Some Radiation Chemistry Aspects of the Corrosion of Metals on Irradiation, W. L. Primak and L. H. Fuchs, April 21, 1952.
- (33) ANL-4792, The Effect of Irradiation on the Mechanical and Physical Properties of Structural Materials With Particular Reference to the Mark I Naval Reactor, D. O. Leeser, November, 1953.

DECLASSIFIED

DECLASSIFIED

-626-

HW-40000

- (34) ANL-4795, Naval Reactor Division Quarterly Report, December, 1951 - February, 1952, C. R. Breden, et al., March, 1952.
- (35) ANL-5036, Quarterly Progress Report - January, February, March, 1953, F. G. Foote, March 31, 1953.
- (36) ANL-5059, Naval Reactor Program Quarterly Report, March 1, 1953 - May 31, 1953, J. E. Kemme and A. H. Roebuck.
- (37) ANL-5338, Quarterly Progress Report - April, May, June, 1954, F. G. Foote, June 30, 1954.
- (38) ANL-5346, Effect of Irradiation Upon Interdiffusion of Stainless Steel and Uranium, R. Well and S. H. Paine, July 15, 1953.
- (39) ANL-FF-459, Visit of J. E. Draley, ANL, and Milton Lewis, HAPO, to Chalk River, Canada, March, 1954.
- (40) ANL-HE-1478, Factors Which Affect Formation and Deposition of Transport Corrosion Products in High Temperature Recirculating Water Loops, C. Wohlberg and F. W. Kleimola, June 6, 1952.
- (41) CC-1677, The Effect of Radiation on the Corrosion of Metals by Water, A. O. Allen, et al., July, 1944.
- (42) CC-2319, The Effects of Neutron Bombardment on the Electrical Resistance of Aluminum, Beryllium, and Tuballoy I, J. Royal, November 2, 1944.
- (43) CC-3165, Further Work on Embrittlement of Tuballoy by Irradiation, J. S. Koehler, July 25, 1945.
- (44) CF-53-3-276, Part I, "Metallography and Hardness Studies of Irradiated Uranium," Radiation Damage Conference, 1953. D. P. O'Keefe.
- (45) CF-53-3-276 Part II, "Radiation Effects on Creep of Stainless Steel," Radiation Damage Conference, 1953, L. F. Coffin, Jr., p. 258.
- (46) CF-53-3-276, Part II, "Creep of Inconel and Stainless Steel Under Irradiation," Radiation Damage Conference 1953, J. C. Wilson, J. C. Zukas, and W. W. Davis, p. 268.
- (47) CF-53-3-276, Radiation Damage Conference, Part II, March, 1953.
- (48) CR-MET-471, The Effect of Irradiation on the Thermal Expansion and Linear Dimensions of Certain Pile Construction Materials, T. B. Weston, February 23, 1951.
- (49) HW-7-5215, H. A. Fowler, October 8, 1946.
- (50) HW-10558, Measurement of Slug Temperatures - Final Report, W. K. Woods and S. S. Jones, July 27, 1948.

DECLASSIFIED

-62 **DECLASSIFIED**

HW-40000

- (51) HW-25330, Behavior of SIR Fuels Irradiated in Sodium (Final Report - PT-105-108-P) (Special Request KAPL-79, The Beta Experiment), J. B. Lambert, August, 1952.
- (52) HW-25412, Irradiation of 53-S Aluminum Samples, P. D. Wright, September 21, 1952.
- (53) HW-26173, Technical Activities Report - Metallurgy - Applied Research Sub-Section, October, 1952, R. Ward, November 3, 1952.
- (54) HW-27531, Interim Report, PT-105-510-E, Determination of Pile Irradiation Effects on Corrosion of 2S Aluminum, S. Goldsmith, June 1, 1953.
- (55) HW-27585, -RD, Metallographic and Hardness Studies of Irradiated Uranium, D. P. O'Keefe, March, 1953.
- (56) HW-30024, Feasibility Survey of Zirconium and Alternate Structural Materials for High Temperature Operation, S. H. Bush and R. S. Kemper, November 18, 1953.
- (57) HW-28309, Electrical Resistivity Measurements of Irradiated Uranium Samples, R. S. Kemper and C. L. Boyd, June 8, 1953.
- (58) HW-31121, In-Pile Exposure of Zirconium to Pile Gas, R. G. Wheeler, March 12, 1954.
- (59) HW-31823, Effects of Irradiation on the Mechanical Properties of Uranium, R. E. Hueschen and R. S. Kemper, August 13, 1954.
- (60) HW-32582, Exposure of Zirconium to Pile Atmosphere and Radiations at Elevated Temperatures, D. B. Lovett, July 29, 1954.
- (61) HW-33248, Properties of Zirconium and Zircaloy-2 and Alternate Structural Materials for DPR, S. H. Bush, September 30, 1954.
- (62) HW-33516, Tensile Tests of Irradiated 63-S Aluminum From PT-105-501-M, D. P. O'Keefe, October 23, 1954.
- (63) HW-33602, Metallurgy Progress Report, July, August, September, 1954, J. J. Cadwell, October 29, 1954.
- (64) HW-34455, Metallurgy Progress Report, October, November, December, 1954, J. J. Cadwell, February 1, 1955.
- (65) HW-37049, Surface Structure of Pile Irradiated 2S Aluminum, R. Borasky and B. Mastel, August 1, 1955.
- (66) HW-37979, Metallurgy Progress Report, April, May, June, 1955, J. J. Cadwell, August 15, 1955.
- (67) HW-38079, The Effect of Irradiation on the Mechanical Properties of Arc-Melted Bureau of Mines Zirconium With Various Degrees of Cold Work, R. S. Kemper and W. S. Kelly, July 29, 1955
(UNCLASSIFIED)

DECLASSIFIED

-628- **DECLASSIFIED**

HW-40000

- (68) HW-38080, Reactor Fuel Temperatures and Apparent Thermal Conductivity, S. S. Jones, July 25, 1955.
- (69) HW-38766, Interim Report No. 5, PT-105-506-E, Recirculation of Pile Cooling Water, R. J. Lobsinger, November 15, 1955.
- (70) HW-39495, Metallurgy Progress Report, July, August, September, 1955, J. J. Cadwell, November 1, 1955.
- (71) HW-39805, Irradiation of Zircaloy-2 Impact Specimens Containing Hydrogen, R. G. Wheeler and W. S. Kelly, November 2, 1955, (UNCLASSIFIED).
- (72) HW-39941, Corrosion of Aluminum in High Temperature Water, N. R. Miller, November 22, 1955 .
- (73) HW-40858, Metallurgy Progress Report - October, November, December, 1955, J. J. Cadwell, February 1, 1956.
- (74) KAPL-360, H. Brooks.
- (75) KAPL-395, Reactor Materials, Section III; Progress Report No. 49, August, 1950, September 20, 1950, pp. 23-24.
- (76) KAPL-415, Reactor Materials, Section III; Progress Report No. 50, September, 1950, October, 27, 1950.
- (77) KAPL-749, An X-ray Study of the Effect of Fission Events on the Structure of Solids, C. W. Tucker, Jr. and P. Senio, April 30, 1952.
- (78) KAPL-807, The Report of the Metallurgy Section, June, July, August, 1952, J. R. Low, et al., August, 1952.
- (79) KAPL-929, A Model for Radiation Damaged Ductile Metals, A. N. Holden and F. W. Kunz, June 10, 1953, (UNCLASSIFIED).
- (80) KAPL-1039, X-ray Diffraction Studies of Radiation Damage, C. W. Tucker and P. Senio, p. 63.
- (81) KAPL-1044, The Dimensional Stability of Uranium Single Crystals and Polycrystals During Irradiation and Thermal Cycling, A. M. Turkalo, February 8, 1954.
- (82) KAPL-1094, SIR Program Progress Report, Vol. I, Mark A, February and March, 1954, G. E. Calomion.
- (83) KAPL-1196, Interstitial Content of Irradiated Metals, C. W. Tucker and P. Senio, June, July, August, 1954, p. 66.
- (84) KAPL-1305, Metallurgy Report of the Technical Section, December, 1954, January, February, 1955, p. 30.
- (85) KAPL-1338, A Sodium In-Pile Loop Test For Activity Transport Measurements, F. G. Haag and W. W. Kendall, May 16, 1955.

DECLASSIFIED

DECLASSIFIED

-629-

- (86) LRL-143, Uranium-Zirconium Diffusion Studies, D. R. Mash, and D. F. Disselhorst, June, 1954.
- (87) LRL-145, The Effect of Neutron Flux on the Mechanical Properties of Aluminum Alloys, R. V. Steele and W. P. Wallace, May, 1954, (UNCLASSIFIED).
- (88) M-3990, Irradiation Physics, A. O. Allen and F. Seitz, Undated.
- (89) MIT-1067, Effects of Irradiation on a Hanford 2S Aluminum Water Cooling Tube, J. L. Klein, May 7, 1951.
- (90) MIT-1085, Effect of Irradiation on the X-ray Line Shape of 2S Aluminum From a Hanford Water Cooling Tube, J. L. Klein and W. B. Nowak, May, 1952.
- (91) MIT-1091, Radiation Damage in 99.0 Per Cent Aluminum, J. L. Klein and W. B. Nowak.
- (92) MUC-NS-3067, The Thermal Diffusion of Fission Products From Uranium and Uranium Oxide, F. H. Spedding, et al.
- (93) N-1483 (MUC FF 127) Properties and Structure of Irradiated Aluminum Tubing, F. Foote, July, 1944.
- (94) NAA-SR-74, Cyclotron Irradiation of Type 347 Stainless Steel Welds in NaK at Elevated Temperatures, A. A. Epp, R. D. Mueller, and H. Pearlman, March 13, 1953.
- (95) NAA-SR-75, The Effect of Cyclotron Irradiation on the Physical Properties of Metals, A. B. Martin, M. Tarpinian, and R. R. Eggleston, January, 1951.
- (96) NAA-SR-241 Vol. 2, Report of Private Communication, E. K. Halteman to F. E. Farris.
- (97) NNES-IV, Vol. 10-B, Preliminary Experiments on Fast Neutron Effects in Beryllium and Aluminum, J. Royal.
- (98) NYO-3732, X-Ray Study of Radiation Damage, B. E. Warren, December 1952.
- (99) ORNL-1170, Aircraft Nuclear Propulsion Quarterly Progress Report for Period Ending December 10, 1951, O. Sisman, et al., March 6, 1952.
- (100) ORNL-1915, Investigation of Materials For a Water Cooled and Moderated Reactor, Louis Scheib, August, 1955.
- (101) SEP-160, Mechanism of Dimensional Instability, L. L. Siegel and A. J. Opinsky, August 2, 1954, (DECLASSIFIED).
- (102) TID-65, Radiation Damage in Solids, F. Seitz.
- (103) TID-65:1, "The Influence of Pile Radiation on Solid Materials," Journal of Metallurgy and Ceramics, F. Seitz, July, 1948.

DECLASSIFIED

- (104) TID-275, "Metallurgy and Radiation Damage," Reports for Session IX, General Information Meeting, October, 1949.
- (105) TID-2010, "A Preliminary Note on the Effect of Neutron Irradiation Upon Specimens of Natural Uranium Wire," Reactor Science Technology; 3, No. 3 (Sept. 1953), M. B. Reynolds, pp. 104-7.
- (106) TID-2015, "Further Considerations on the Dimensional Instability of Uranium," Reactor Science and Technology, No. 4 (December 1954), J. E. Burke and A. M. Turkalo.
- (107) TID-5021 (ANL-FF-252) C. O. Henry and S. S. Sidher.
- (108) TID-5185, The Effects of Irradiation on the Mechanical Properties of Natural Uranium, Part II, M. B. Reynolds.
- (109) WAPD-52, The Effect of Deuteron Bombardment on the Hot Water Corrosion of Zirconium Metal, H. L. Glick and F. C. Brooks, April, 1952.
- (110) WAPD-63, The Effect of Neutron Bombardment on the Creep Strength of Zirconium, R. H. Fillnow, L. A. Cook, and W. E. Johnson, May, 1953.
- (111) WAPD-77, Correlation of Zirconium Electrical Resistivity With Fast Flux, M. L. Bleiberg and R. L. Ely, Jr., May 20, 1953, (DECLASSIFIED).
- (112) WAPD-78, Effects of Irradiation Upon the Properties of Zirconium and a Zirconium-Tin Alloy, M. S. Bleiberg and L. S. Castleman, March 17, 1953.
- (113) WAPD-90, Tensile Properties of Irradiated Zirconium and Stainless Steel, J. D. Eichenberg and L. S. Castleman, November 5, 1953.
- (114) WAPD-107, Recovery of Irradiated Crystal Bar Zirconium, M. L. Bleiberg and L. S. Castleman, April 23, 1954.
- (115) WASH-577, Report of Visit to British Atomic Energy Research Establishment, Harwell, England on July 28-29, 1955, Under The Technical Cooperation Program, J. P. Howe, September 12, 1955.

DECLASSIFIED

DECLASSIFIED

-631-

FORM 10000

E. LIST OF TABLES AND FIGURES

TABLE VI-1	Tensile Properties of Irradiated Uranium
TABLE VI-2	Tensile Properties of Irradiated Uranium
TABLE VI-3	Typical Hardness Values of Uranium Before and After Irradiation
TABLE VI-4	Density Changes in Irradiated Uranium
TABLE VI-5	Density Changes in Irradiated Uranium
TABLE VI-6	Diffusion in U-Zr and U-Ti Couples
TABLE VI-7	Dimensional Instability In Uranium
TABLE VI-8	Growth Rates of Uranium Having Different Textures
TABLE VI-9	Growth of Uranium by Thermal Cycling and Irradiation
TABLE VI-10	Effect of Neutron Flux on the Mechanical Properties of Aluminum Alloys
TABLE VI-11	Mechanical Properties of 63S Al Before and After Irradiation
TABLE VI-12	Tensile Properties of Irradiated 63S Al
TABLE VI-13	Radiation Effects on Aluminum
TABLE VI-14	Hardness of Irradiated Zirconium and Stainless Steel
TABLE VI-15	Tensile Properties of Irradiated Zirconium and Stainless Steel
TABLE VI-16	Effect of Irradiation on Hardness of Selected Stainless Steel
TABLE VI-17	Effect of Irradiation on Brinell Hardness of Sheet SS-347 for Various Degrees of Cold Work
TABLE VI-18	Tensile Data on Stainless Steel Irradiated in Flowing Water in Argonne Water Loop at Oak Ridge
TABLE VI-19	Tensile Properties of Irradiated Stainless Steels
TABLE VI-20	Irradiation Effects on the Tensile Properties of 347 Stainless Steel
TABLE VI-21	Effect of Irradiation on the Thermal Expansion and Linear Dimensions of Certain Pile Construction Materials
FIGURE VI-1	Optical Macrographs of Irradiated Uranium
FIGURE VI-2	Photomicrographs Illustrating Effect of Irradiation on Microstructure of Uranium
FIGURE VI-3	Electron Micrographs of Irradiated Uranium

DECLASSIFIED

DECLASSIFIED

- FIGURE VI-4 Optical Micrographs of Aluminized Faxfilm Replicas of Irradiated Uranium
- FIGURE VI-5 Effects of Preferred Orientation on the Dimensional Stability of Uranium During Irradiation
- FIGURE VI-6 Effects of Irradiation on Tensile and Yield Strengths of 2S Aluminum Tubing
- FIGURE VI-7 Effect of Irradiation on Hardness of 2S Aluminum Tubing
- FIGURE VI-8 Hardness of Crystal Bar Zirconium and a 2.5 Per cent Tin-crystal Bar Zirconium Alloy vs. Exposure
- FIGURE VI-9 Effect of Irradiation on the Hardness of Arc-Melted Bureau of Mines Zirconium
- FIGURE VI-10 Effect of Irradiation and Post-Irradiation Annealing on the Yield Strength of Arc-Melted Bureau of Mines Zirconium
- FIGURE VI-11 Impact Energy to Fracture vs. Temperature for Zircaloy-2 Irradiated in Circulating Pressurized Water
- FIGURE VI-12 Impact Energy to Fracture at -78 C vs. Exposure
- FIGURE VI-13 Per Cent Change of Electrical Resistivity vs. Exposure
- FIGURE VI-14 Increase in Electrical Resistivity Due to Neutron Bombardment in Crystal Bar Zirconium (Annealed and 96 Per Cent Cold Worked)

DECLASSIFIED

TABLE VI-1

Tensile Properties of Irradiated Uranium^(59, 66, 70)

Specimen History	Ult. T. S. 10 ³ psi	% Change	Y. S. 10 ³ psi	% Change	% Elong. in 1"	% Change
Control HAPO Irradiation	104		31		17 ± 1	
As irradiated to 1.8 x 10 ²⁰ nvt at HAPO. Exposure Temp. 150 C.	76	-27	71.5	+ 117	0.36	-97.5
Irradiated to 1.8 x 10 ²⁰ nvt-annealed at 400 C for 15 hours.	65	-38	52	+ 58	0.5	-96.8
Irradiated to 1.8 x 10 ²⁰ nvt-annealed at 700 C for 15 hours.	65	-39	49.5	+ 60	1.8	-90
Irradiated to 1.8 x 10 ²⁰ nvt-tested at 285 C.	71	-32	70	+ 112	0.7	-96
Control-MTR Irradiation	97		32.4		19 ± 1	
Irradiated to 1.3 x 10 ²⁰ nvt in MTR. Exposure Temp. 150 C.	93.5	- 4	59	+ 85	0.6	- 97
Irradiated to 1.8 x 10 ²⁰ nvt Calculated exposure. Temp. 300-400 C.	78.1	-19.3	45	+ 40	0.4	- 98

DECLASSIFIED

DECLASSIFIED

HW-40000

DECLASSIFIED

HW-40000

TABLE VI-2

Tensile Properties of Irradiated Uranium⁽⁷⁾

Specimen History	Tensile Strength 10 ³ psi	% Change	Elongation
Cast (with increased carbon content)			All irradiated specimens had zero elongation
Before Irradiation	78	-61	
After Irradiation	30		
Cast			
Before Irradiation	64	-70	
After Irradiation	19		
Heat Treated			
Before Irradiation	79		
After Irradiation	40	-49	
Hot Rolled			
Before Irradiation	58		
After Irradiation	38	-35	

TABLE VI-3

Typical Hardness Values of Uranium Before and After Irradiation

Specimen History	Integrated Neutron Flux	Hardness		Comments
		Pre- Irradiation	Post- Irradiation	
Cold worked uranium	5×10^{17}			
Annealed at 635 C	5×10^{17}			
Beta Heat Treated	2×10^{18}	82 R _G	88 - 90 R _G	Temp. range 50 - 900 C
HAPO Fuel Element	7.2×10^{19}	71 - 78 R _G	84 - 89 R _G	Center softer than edge
	1.7×10^{20}	71 - 78 R _G	89 - 94 R _G	At center
	1.7×10^{20}	71 - 78 R _G	98 - 103 R _G	Near edge
Uranium specimen	3.3×10^{19}	214 + 12 DPH	275 + 10 DPH	
	3.3×10^{20}	214 + 12 DPH	315 + 20 DPH	
Cast Uranium	$10^{19} - 10^{20}$	330 DPH	415 DPH	
Heat Treated Uranium	$10^{19} - 10^{20}$	368 DPH	440 DPH	
Hot-rolled Uranium	$10^{19} - 10^{20}$	351 DPH	417 DPH	

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE VI-4Density Changes in Irradiated Uranium⁽³⁵⁾

Total Atom Burnup Per Cent	Per Cent Density Decrease	
	<u>300 C Rolled</u>	<u>Beta Heat Treated</u>
0.05	0.4	0.2
0.10	0.9	0.4
0.15	1.5	0.7

TABLE VI-5Density Changes in Irradiated Uranium⁽³⁷⁾

Total Atom Burnup Per Cent	Irradiation Temperature		Density Decrease Per Cent
	<u>°C</u>	<u>°F</u>	
1.26	190	375	3.3
1.46	220	430	2.8
1.63	240	465	2.7
1.75	250	480	2.6

TABLE VI-6

Diffusion in U-Zr and U-Ti Couples

Couple	Nominal Temp. °C	Time in-pile days	Burnup Per Cent	Average Flux nv	Penetration of the Couple by the Uranium inches
U-Zr	415	96	2.5	7×10^{12}	0.002
U-Ti	415	96	2.5	8×10^{12}	0.003
U-Zr	415	(4 yrs.)	---	---	0.001

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE VI-7

Dimensional Instability In Uranium

Results on which there is substantial agreement:

- (1) An [010] direction orientation results in maximum growth
- (2) An [100] direction orientation results in maximum shrinkage
- (3) An [001] direction orientation results in little or no change in dimension
- (4) Duplex orientations may promote or prevent growth or shrinkage, depending on type and degree of orientation.
- (5) Single crystals deform under irradiation, but not under thermal cycling.
- (6) A random orientation is stable when irradiated or thermally cycled.
- (7) High (400 C) or low (-100 C) temperature operation during irradiation minimizes dimensional instability.
- (8) There appears to be no limit on the degree of dimensional change under irradiation.
- (9) Growth appears to be a direct function of integrated flux.

Results on which there is inadequate information or lack of agreement:

- (1) Increased metal purity may increase the rate of irradiation growth
- (2) Growth rate appears greatest for oriented polycrystalline uranium, decreases as metal approaches or becomes a single crystal (definite disagreement on this.)
- (3) Dimensional instability produced by irradiation and thermal cycling are qualitatively similar (definite disagreement).

DECLASSIFIED

DECLASSIFIED

Growth Rates of Uranium Having Different Textures

TABLE VI-8

Texture	Predominant Component	Approximate Elongation (%) in 100 MWD/T	Approximate Elongation (%) in 100 Thermal Cycles
(100) + (110)	(100)	- 0.8	+ 1.49
(010) + (110)	(010)	+ 1.0	+ 4.9
(110) + (010)	(110)	0.0	+ 3.3
(010) + (110)	(010)	+ 0.9	+ 4.4

DECLASSIFIED

TABLE VI-9

Growth of Uranium by Thermal Cycling and Irradiation

Texture and Orientation Data	Thermal Cycling Data ⁽²⁾		Irradiation Data			Comments
	No. of Cycles	G ⁽¹⁾ x 10 ⁻⁶	Reactor	NVT x 10 ⁻¹⁹	Elongation	
Textured Polycrystalline Wire						
(010) fiber texture predominant	174	442	Hanford	11.8	59.8 ⁽³⁾	Restrained in containers because of excessive growth
	174	442	Hanford	21.4	103.5 ⁽³⁾	
	174	442	MTR	21.6 ⁽⁴⁾	56.9 ⁽³⁾	
	174	442	MTR	21.6 ⁽⁴⁾	54.5 ⁽³⁾	Held in additional mild steel split tube during irradiation
	174	442	MTR	39.3 ⁽⁴⁾	110.1 ⁽³⁾	
	174	442	MTR	39.3 ⁽⁴⁾	139.0 ⁽³⁾	
	174	442	MTR	39.3 ⁽⁴⁾	142.3 ⁽³⁾	
β-treated Polycrystalline Wire						
Nearly random	1091	45	Hanford	11.8	2.6	
	1091	45	Hanford	21.4	2.4	
	1091	45	MTR	21.6 ⁽⁴⁾	4.2	
	1091	45	MTR	39.3 ⁽⁴⁾	4.9	
Transformation Single Crystal						
(001) pole within 10° of wire axis	362	0	Hanford	11.8	1.1	Cross section became elliptical major axis roughly 15% longer than original diameter.
Unknown	769	0	Hanford	21.4	104.7 ⁽³⁾	Sample flattened in cross section.
(010) pole within 10° of wire axis	1075	0	MTR	21.6 ⁽⁴⁾	30.0	Became elliptical in cross section.
	--	--	MTR	39.3 ⁽⁴⁾	59.8 ⁽³⁾	Became elliptical in cross section.

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE VI-9 (Contd.)

Texture and Orientation Data	Thermal Cycling Data ⁽²⁾		Irradiation Data			Comments
	No. of Cycles	G ⁽¹⁾ x 10 ⁻⁶	Reactor	NVT x 10 ⁻¹⁹	Elongation	
Recrystallization Single Crystal						
(010) pole within 15° of wire axis	?	0 ⁽⁵⁾	MTR	21.6 ⁽⁴⁾	19.4	Became elliptical in cross section. Minor axis near [100] - direction of shortening. Major axis near [001] - little or no change.

- (1) $G = 1/N \ln L/L_0$, where N = No. of cycles; and L_0 , the original length.
- (2) Thermal cycling range: 100 C to 500 C.
- (3) Approximate minimum values - specimens twisted.
- (4) Values may be too high by a factor of 2.
- (5) Argonne reports no change for their true single crystals after thermal cycling.

DECLASSIFIED

DECLASSIFIED

HW-40000

DECLASSIFIED

DECLASSIFIED

TABLE VI-10

The Effect of Neutron Flux on the Mechanical Properties of Aluminum Alloys*

		No. of Tests	Yield Strength	Tensile Strength	Elongation
2SO	ASM Metals Handbook		5,000 psi	13,000 psi	35%
	Control Specimens	8	6,800 + 180	13,600 + 320	38.2 + 3.2
	Irradiated Specimens	25	17,100 + 890	26,000 + 2000	21.2 + 1.2
2SH14	ASM Metals Handbook		16,000 psi	17,500 psi	9%
	Control Specimens	8	16,600 + 250	17,300 + 460	6.0 + 0.6
	Irradiated Specimens	22	24,000 + 450	26,000 + 380	5.5 + 1.2
52SO	ASM Metals Handbook		12,000 psi	27,000 psi	25%
	Control Specimens	7	14,700 + 670	29,200 + 450	34.0 + 3.4
	Irradiated Specimens	22	22,900 + 540	37,400 + 490	30.6 + 4.2
52SH34	ASM Metals Handbook		31,000 psi	37,000 psi	10%
	Control Specimens	7	29,500 + 800	36,000 + 700	11.2 + 2.3
	Irradiated Specimens	21	36,400 + 1000	44,700 + 1200	14.0 + 1.1
61SO	ASM Metals Handbook		8,000 psi	18,000 psi	22%
	Control Specimens	8	9,460 + 200	18,050 + 240	28.8 + 2.8
	Irradiated Specimens	25	25,600 + 460	37,300 + 400	22.4 + 0.8
61ST6	ASM Metals Handbook		40,000 psi	45,000 psi	12%
	Control Specimens	8	38,500 + 740	45,000 + 320	17.5 + 1.0
	Irradiated Specimens	23	44,400 + 670	50,600 + 540	16.2 + 0.7
A54S	Control Specimens	8	47,800 + 450 psi	54,700 + 500 psi	8.8 + 1.1%
	Irradiated Specimens	17	50,800 + 460 psi	57,800 + 510 psi	12.5 + 0.6%

* 1.26×10^{21} nvt exposure at 65 C (150 F). (87)

HW-40000

DECLASSIFIED

DECLASSIFIED

TABLE VI-11

Mechanical Properties of 63S Al Before and After Irradiation*

Sample	Unirradiated				Sample	Irradiated			
	Ultimate Strength psi	Yield Strength psi	Elong. % in 1 inch	Hardness** R-15T		Ultimate Strength psi	Yield Strength psi	Elong. % in 1 inch	Hardness** R-15T
1A	25,900	11,900	32.8	--	1A	33,900	20,400***	34.4	70.0
1B	23,200	10,000	28.1	59.0	1B	31,600	19,200	28.1	--
2A	32,700	28,200	23.4	77.0	2A	35,500	29,000	21.9	75.0
2B	33,700	28,400	23.4		2B	32,600	27,200	18.8	
3A	35,000	34,300	15.6	74.0	3A	35,700	33,400	12.5	75.0
3B	34,100	32,500	17.2		3B	36,000	34,200	15.6	

* 3 months exposure in water cooled "B" test hole. (52)

** Hardness values obtained on metallographic specimens.

*** Due to faulty loading of specimens, these values of yield strength are not reliable.

Key: (1) Solution heat-treated only.
 (2) Solution heat-treated and precipitation hardened.
 (3) Solution heat-treated, precipitation hardened, and overaged 100 hours at 180 C (350 F).

DECLASSIFIED

HW-40000

DECLASSIFIED

HW-40000

TABLE VI-12

Tensile Properties of Irradiated 63-S Aluminum⁽⁶²⁾

Sample No.	Heat Treatment	Diameter (in)	Ultimate Strength (psi)	Per Cent Elongation in 1" gage length
1	T4	0.251	36,700	28
2	T4	0.251	33,500	34
3	T4	0.252	36,800	34
4	T4	0.250	36,700	31
Avg.			35,900	
10	T6	0.251	31,000	19
11	T6	0.252	29,600	25
12	T6	0.250	33,900	16
13	T6	0.249	29,800	19
Avg.			31,100	
16	T6 + 100	0.251	31,800	14
17	T6 + 100	0.251	30,600	16
19	T6 + 100	0.251	30,200	16
20	T6 + 100	0.251	29,800	19
Avg.			30,600	
Unirradiated 63-S Samples				
5	T4	0.250	28,000	37
6	T4	0.251	26,300	36
7	T4	0.250	26,700	32
8	T4	0.250	27,100	31
Avg.			27,000	
14	T6	0.250	29,000	20
15	T6	0.250	28,600	
Avg.			28,800	
21	T6 + 100	0.251	30,000	20
22	T6 + 100	0.250	28,400	20
Avg.			29,200	

DECLASSIFIED

TABLE VI-13

Radiation Effects on Aluminum⁽⁹⁾

Material	Condition	Total Flux		Irradiation Temp. °C	Property Change, % *				Modulus of Elasticity
		10 ¹⁸ nvt Slow	Fast		Hardness	Yield Strength	Ultimate Strength	Elongation	
High purity aluminum	Annealed	Hanford Re- actor for five months		20-60		Almost 100	60	-67	
	Half hard			20-60		10	6	0	
	Extra hard			20-60		0	0	0	
	Annealed	Hanford Re- actor for ten months		20-60		>100	70	-67	
	Half hard			20-60		10	6	0	
	Extra hard			20-60		0	0	0	
2S	3/4 to full hard	ND	400	20-60	10.7	22.8	17.7	5.6	1.2
	Annealed	1.7	ND	50	0				
		0.15 alphas		-150	0				
	Slightly cold worked	1.7	ND	50	2.1				
		50	ND	20-60	16.3				

* - Unless otherwise stated, all values are positive

ND- Not determined

DECLASSIFIED

DECLASSIFIED

HW-40000

DECLASSIFIED

TABLE VI-14

Hardness of Irradiated Zirconium and Stainless Steel⁽¹¹³⁾

<u>Specimen Numbers</u>	<u>Temp. °F</u>	<u>Fast Flux (Est.) (nv)</u>	<u>Exposure (Est.) (nvt)</u>	<u>Pre-Irrad. (DPH)</u>	<u>Post-Irrad. (DPH)</u>
<u>Crystal Bar Zirconium</u>					
Z ₁ , Z ₂ , Z ₃	490-510	2.5 x 10 ¹³	25 x 10 ¹⁹	99 ± 2.5*	109 ± 3.0*
Z ₄ , Z ₅ , Z ₆	490-510	8 x 10 ¹²	8 x 10 ¹⁹	100 ± 2.5	108 ± 3.0
Z ₇ , Z ₈	485-515	Not Irradiated		98 ± 2.5	96 ± 3.0
<u>Type 347 Stainless Steel</u>					
A ₁ , A ₂	490-510	2.5 x 10 ¹³	25 x 10 ¹⁹	251 ± 4.5	265 ± 7.0
A ₃ , A ₄	490-510	8 x 10 ¹²	8 x 10 ¹⁹	249 ± 2.0	254 ± 6.0
A ₅ , A ₆	485-515	Not Irradiated		250 ± 3.0	231 ± 6.0
<u>Type 322 W Stainless Steel</u>					
W ₁ , W ₂	490-510	2.5 x 10 ¹³	25 x 10 ¹⁹	443 ± 4	459 ± 10
W ₃ , W ₄	490-510	8 x 10 ¹²	8 x 10 ¹⁹	448 ± 3	451 ± 10
W ₅ , W ₆	485-515	Not Irradiated		446 ± 3	450 ± 6

* Standard deviations

DECLASSIFIED

HW-40000

DECLASSIFIED

TABLE VI-15

Tensile Properties of Irradiated Zirconium and Stainless Steel (113)

Specimen Numbers	Temp. (°F)	Fast Flux (nv)	Exposure (nvt)	0.2% Yield Strength (10 ³ psi)	Tensile Strength (10 ³ psi)	Red. in Area %	Elongation in 2" %
Zirconium							
Z ₁ , Z ₂ , Z ₃	490-510	2.5 x 10 ¹³	25 x 10 ¹⁹	23.5 ± 1.6*	39.8 ± 1.4*	52.4 ± 2.0*	24.7 ± 0.9*
Z ₄ , Z ₅ , Z ₆	490-510	8 x 10 ¹²	8 x 10 ¹⁹	22.0 ± 1.2	40.6 ± 2.8	49.6 ± 1.3	29.3 ± 2.6
Z ₇ , Z ₈	485-515	Not Irradiated		17.1 ± 2.8	39.5 ± 2.0	48.3 ± 0.2	29.0 ± 3.9
Type 347 Stainless Steel							
A ₁ , A ₂	490-510	2.5 x 10 ¹³	25 x 10 ¹⁹	68.2 ± 0.4	99.7 ± 0.1	---	36.7 ± 0.1
A ₃ , A ₄	490-510	8 x 10 ¹²	8 x 10 ¹⁹	65.2 ± 0.5	98.2 ± 0.4	---	38.4 ± 1.0
A ₅ , A ₆	485-515	Not Irradiated		59.9 ± 0.7	95.3 ± 0.5	---	45.0 ± 0.1
A ₇ , A ₈	R. T.	Not Irradiated		59.7 ± 0.4	95.8 ± 0.0	---	44.8 ± 0.9
A ₉ , A ₁₀							
Type 322 W Stainless Steel							
W ₁ , W ₂	490-510	2.5 x 10 ¹³	25 x 10 ¹⁹	207.5 ± 1.5	210 ± 1.0	---	5.5 ± 0.3
W ₃ , W ₄	490-510	8 x 10 ¹²	8 x 10 ¹⁹	197 ± 0.5	199 ± 0.0	---	6.5 ± 0.1
W ₅ , W ₆	485-515	Not Irradiated		192 ± 1.0	195 ± 0.5	---	5.9 ± 0.1
W ₇ , W ₈	R. T.	Not Irradiated		189 ± 0.8	192.5 ± 0.8	---	6.1 ± 0.2
W ₉ , W ₁₀							

* Standard Deviations

HW-40000

DECLASSIFIED

HW-40000

TABLE VI-16

Effect of Irradiation on the Hardness of Selected Stainless Steels⁽³³⁾

Material, Type, and Treatment	Exper. No. (App. B)	Hardness			Converted BHN
		Scale	Before	After	
Type 304, Annealed ⁽¹⁾	1-S	B	72-76	72-76	131
Type 304, Malcomized (2)	2-S	15N	89-91	93-95	654 to 810
Type 309, Annealed (1)	3-S	B	81-83	81-85	152 to 158
Type 316, Annealed (2)	5-S	B	82-83	98	154 to 228
Type 316, Annealed (1)	4-S	B	78-80	75-79	143
Type 316, Cold Worked (2)	5-S	C	25-27	28-32	262 to 285
Type 329, Annealed (3)	6-S	A	50-53	50-54	158
Type 347, Annealed (3)	8-S	B	89-90	81-90	183
Type 347, Malcomized (4)	10-S	15N	89-92	87-91	656
Type 347, Annealed (1)	7-S	B	81-83	81-83	152
Type 347, Cb-Ta, Annealed (3)	8-S	A	50	54-55	153 to 175
Type 347, Cb-Ta, Shot Peened (3)	8-S	A	49-51	52-54	153 to 168
Type 410, Malcomized (2)	12-S	15N	90-91	90-94	656 to 740
Type 410, Malcomized (4)	12-S	A	81-83	82-83	688
Type 410, Malcomized (5)	13-S	15N	91-92	92	739
Type 431, Annealed (3)	14-S	A	64-65	68	277 to 331
Type 431, Hardened (3)	14-S	A	70-71	72	371 to 400
Type 440C, Hardened (5)	15-S	A	75	77-79	461-534
Type 440C, Hardened (2)	16-S	C	54-55	53-55	545
Type 440C, Hardened (5)	15-S	C	56-57	58-59	588 to 635
Type 440C, Malcomized (4)	17-S	15N	88-89	85-96	577 to 800
Type 442, Annealed (3)	18-S	A	53-57	59-61	185 to 223
Type 446, Hardened (3)	19-S	A	57	61-63	200 to 250
U.S.S. Stainless "W," Hardened(2)	20-S	C	48-49	47-49	461
U.S.S. Stainless "W," Hardened(3)	21-S	A	73	74	415 to 440
Armco 17-4 PH, Annealed (6)	22-S	C	33-35	48-52	315 to 477
Armco 17-4 PH, Hardened (3)	22-S	A	73	74	415 to 440
Armco 17-4 PH, Hardened (6)	22-S	C	43-44	44-48	403 to 432
Armco 17-7 PH, Hardened (3)	23-S	A	73	75	415 to 460
Armco 17-7 PH, Hardened (6)	23-S	C	50-51	45-50	477
Armco 17-7 PH, Malcomized (3)	23-S	15N	92	95	740 to 820

- (1) 4-1/2 month exposure in flowing water with calculated nvt of 1×10^{19} slow in the Argonne Water Loop (Run I) at Oak Ridge. For the 3200-hour irradiation the channel was active at 500 F for 2000 hr. at 400-500 F for 900 hr. and below 400 F for 300 Hr.
- (2) 3000-hour exposure with measured (foils) nvt of 3.7×10^{20} slow and 5.1×10^{20} fast at 70-80 F in the Argonne STR test at Chalk River.
- (3) 2065-hour exposure in flowing water at 540 F with calculated nvt of 3×10^{19} slow in the Argonne Water Loop at Hanford (HIR-ANL-140-X2; Cartridge 10).

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE VI-16 (Contd.)

- (4) 4-month dry exposure with calculated nvt of 10^{19} slow in the Argonne Water Loop (Run II) at Oak Ridge. For 75 hr. the channel was active at 500 F, 1450 hr at 450 to 495 F, and 470 hr below 450 F.
- (5) 2-1/2 month exposure with calculated nvt of 5×10^{19} fast and 4×10^{19} slow in Hanford process-tube receptacle slugs (HIR-ANL-178).
- (6) 4-month exposure with calculated nvt of 4×10^{19} slow in 540 F flowing water in Argonne Water Loop at Hanford (HIR-ANL-140-X1; Cartridge 6).

TABLE VI-17

Effect of Irradiation Upon Brinell Hardness of
Sheet SS-347 for Various Degrees of Cold Work⁽⁵⁶⁾

Reduction in Thickness Per Cent	Initial Hardness	Hardness after Indicated Thermal nvt		
		6.3×10^{19}	1.5×10^{20}	2.3×10^{20}
0	143	216	223	227
10	223	259	273	290
19.8	265	291	298	300
32.5	302	327	339	343
38.8	319	343	348	352
50.2	328	356	359	369

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE VI-18

Tensile Data on Stainless Steel Irradiated
In Flowing Water in Argonne Water Loop at Oak Ridge^{(33)*}

Material** Type and Specimen No.	Exper. No. (App. B)	Condition	Ultimate Tensile Strength psi	Yield Strength (0.2% Offset), psi	Elongation % in 2 In.
304-1	1-S	Irradiated	92,000	43,500	58.5
304-2	1-S	Irradiated	95,500	48,500	41.0
304-3	1-S	Unirradiated	92,500	44,000	70.8
309-1	3-S	Irradiated	99,000	43,500	51.0
309-3	3-S	Unirradiated	95,000	38,500	54.0
316-1	4-S	Irradiated	89,500	36,500	66.5
316-2	4-S	Unirradiated	90,000	35,000	70.0
347-1	7-S	Irradiated	103,000	42,500	54.5
347-3	7-S	Unirradiated	99,000	37,500	56.6

* Flat tensile specimens 7.3 in. long by 0.07 and 0.15 in. thick with 0.5 in. gage width.

Calculated nvt of 1×10^{19} slow.

For the 3200 hr. irradiation the channel was active at 500 F for 2000 hr., at 400-500 F for 900 hr. and below 400 F for 300 hr. (Run I).

** Type 304 specimens quench-annealed from 1900 F. Type 309, 316, and 347 specimens quench-annealed from 2000 F.

DECLASSIFIED

TABLE VI-19

Tensile Properties of Irradiated Stainless Steels (33)

Material Type and Treatment	Exper. No. (App. B)	Ultimate Tensile Strength psi		Yield Strength, 0.2% Offset psi	
		Unirradiated	Irradiated	Unirradiated	Irradiated
316, Annealed ⁽¹⁾	5-S	79,500	151,000	----	----
U.S.S. Stainless "W" ⁽¹⁾	20-S	113,000	134,500	----	----
410, Malcomized ⁽²⁾	13-S	69,000	70,000	47,000	62,000
410, Malcomized ⁽²⁾	13-S	70,000	75,000	44,000	61,000
440C, Hardened ⁽²⁾	15-S	199,000	240,000	185,000	205,000
440C, Hardened ⁽²⁾	15-S	211,000	240,000	185,000	200,000

(1) Specimen Figure 15-1. 3000 hour exposure with measured (foils) nvt of 3.7×10^{20} slow and 5.1×10^{20} fast at 70-80 F in the Argonne STR test at Chalk River.

(2) Specimen Figure 11-b. 2-1/2-month exposure with calculated nvt of 4×10^{19} slow and 5×10^{19} fast in Hanford process-tube receptacle slugs (HIR-ANL-178).

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE VI-20
Irradiation Effects on the Tensile Properties of 347 Stainless Steel (56)

Condition	Specimen Gauge inches	Total Flux 10 ¹⁹ nvt		0.2% Yield Strength 1000 psi		Ultimate Strength 1000 psi		Elongation Per cent	
		slow	fast	control	irradiated	control	irradiated	control	irradiated
Annealed	1/32 x 1-1/2	2	0.7 [†]	-	-	82.0	112.5	16	16
Sheet	0.075 x 0.075 x 1	22	30 ^I	32.5	76.9	85.6	102.8	55	34
Sheet	0.075 x 0.075 x 1	36	50 ^I	32.5	86.3	85.6	107.0	55	29
Sheet	0.020 x 0.25 x 1	22	30 ^I	32.9	81.5	86.3	105.8	62	37
Sheet	0.020 x 0.25 x 1	36	50 ^I	32.9	74.5	86.3	103.7	62	37
			25*	59.7	68.2	95.7	99.7		

† Hanford test hole

I Hanford hollow uranium slugs

* Chalk River at 500 F

Condition	0.2% Yield Strength psi	Ultimate Strength psi	Uniform Elongation Per Cent	Elongation to Fracture 4 x diam. gauge Per cent
Unirradiated	47,500	98,100	41.6	54.1
	51,600	95,400	45.4	54.1
Irradiated*	78,200	104,500	35.9	46.0
	76,500	104,100	36.3	--

* Hanford Reactor, 6-8 x 10¹⁹ nvt (thermal) at >50 C

DECLASSIFIED.

DECLASSIFIED

HW-40000

TABLE VI-21

Effect of Irradiation on the Thermal Expansion and Linear Dimensions
Of Certain Pile Construction Materials (48)

Substance	Group	Condition	Coeff. of Expansion			Length at 25 C		
			$\times 10^{-6}$		$^{\circ}\text{C}^{-1}$	Inches		
			Before	After	Change	Before	After	Change
Super-pure Al	1	as fabricated	21.1	20.1	- 5%	4.3333	4.3344	+ 0.0011
	3	annealed	20.3	19.6	- 3-1/2%	4.3550	4.3555	+ 0.0005
Al Alloy 2S-0	1	as machined	20.7	20.8	+ 1/2%	4.3276	4.3272	- 0.0004
	3	annealed	20.4	20.0	- 2%	4.3283	4.3285	+ 0.0002
Al Alloy 2S-F	2	as fabricated	20.8	20.5	- 1-1/2%	4.3000	4.3002	+ 0.0002
Al Alloy 55S-T	2	as machined	20.8	20.2	- 3%	4.3354	4.3352	- 0.0002
Al Alloy 57S-F	2	as fabricated	20.6	21.0	+ 2%	4.3047	4.3046	- 0.0001
Al Alloy 17S-T	1	as machined	20.5	19.7	- 4%	4.3121	4.3131	+ 0.0010
	3	heat-treated	20.1	20.3	+ 1%	4.2666	4.2667	+ 0.0001
Nickel	1	as machined	11.0	11.1	+ 1%	4.2765	4.2771	+ 0.0006
	3	annealed	11.0	10.9	- 1%	4.3443	4.3449	+ 0.0006
Stainless Steel 347	1	as machined	13.8	14.0	+ 1-1/2%	4.2645	4.2655	+ 0.0010
	3	annealed	13.8	13.8	0	4.3395	4.3401	+ 0.0006
	3	sensitized	13.8	13.8	0	4.3485	4.3491	+ 0.0006
	3	stabilized	13.4	13.2	- 1-1/2%	4.3493	4.3501	+ 0.0008

UNCLASSIFIED

DECLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE VI-1

OPTICAL MACROGRAPHS OF URANIUM IRRADIATED TO
 7×10^{19} NVT. NOTE THE EFFECT OF ILLUMINATION ON
THE APPEARANCE OF THE MACROSTRUCTURE.
MAGNIFICATION: 2.5X

FIGURE VI-2

PHOTOMICROGRAPHS ILLUSTRATING THE EFFECT OF
IRRADIATION ON THE MICROSTRUCTURE OF URANIUM.
BRIGHT FIELD ILLUMINATION. (a) 0 NVT. (b) 5×10^{19}
NVT.

UNCLASSIFIED

HW-40000

FIGURE VI-3

ELECTRON MICROGRAPHS OF URANIUM IRRADIATED
TO 1.5×10^{20} NVT.

REPLICA: PALLADIUM SHADOWED CARBON REPLICA
PREPARED FROM FAXFILM.

MAGNIFICATION: 2000X

UNCLASSIFIED

250 X

500 X

FIGURE VI-4

OPTICAL MICROGRAPHS OF ALUMINUMIZED FAXFILM
REPLICAS OF URANIUM IRRADIATED TO 1.5×10^{20} NVT.
BRIGHT FIELD ILLUMINATION.

UNCLASSIFIED

UNIT CELL OF URANIUM WITH PERTINENT PLANES INDICATED

PREDOMINANT PLANES	(RANDOM)	(RANDOM)	(110)(020)	(110)(200)	(020)
RHO VALUES			44 26	23 26	71

PREDOMINANT PLANES	(110)(020)	(110)(020)	(020)(110)	(020)(110)	(110)(020)
RHO VALUES	46 21	53 51	11 26	152 34	91 24 29

FIGURE VI-5

EFFECTS OF PREFERRED ORIENTATION ON THE DIMENSIONAL STABILITY OF URANIUM DURING IRRADIATION. EXPOSURE 10^{20} - 3×10^{20} NVT, TEMPERATURE 100-150 C.

UNCLASSIFIED

HW-40000

DECLASSIFIED

FIGURE VI-6

EFFECT OF IRRADIATION ON TENSILE AND YIELD STRENGTH OF
2S ALUMINUM TUBING (89)

DECLASSIFIED

HW-40000

DECLASSIFIED

FIGURE VI-7

EFFECT OF IRRADIATION ON HARDNESS OF 2S ALUMINUM TUBING (39)

DECLASSIFIED

HW - 40000

DECLASSIFIED

HARDNESS OF CRYSTAL BAR ZIRCONIUM AND A 2.5 PER CENT TIN-CRYSTAL BAR ZIRCONIUM ALLOY VS EXPOSURE ⁽¹¹²⁾

AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

3 of 6

FIGURE VI-9

EFFECT OF IRRADIATION ON THE HARDNESS OF ARC-MELTED
BUREAU OF MINES ZIRCONIUM ⁽⁶⁷⁾

FIGURE VI-10

EFFECT OF IRRADIATION AND POST-IRRADIATION ANNEALING
ON THE YIELD STRENGTH OF ARC-MELTED BUREAU OF MINES ZIRCONIUM (67

FIGURE VI-11

IMPACT ENERGY TO FRACTURE VS TEMPERATURE FOR ZIRCALOY-2
IRRADIATED TO 100 PPM IN CIRCULATING PRESSURIZED WATER (71)

DECLASSIFIED

FIGURE VI-12

IMPACT ENERGY TO FRACTURE AT -78C vs EXPOSURE⁽¹¹²⁾

DECLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE VI-13

PER CENT CHANGE OF ELECTRICAL RESISTIVITY VS EXPOSURE (111)

UNCLASSIFIED

HW-40000

DECLASSIFIED

HW-40000

FIGURE VI-14

INCREASE IN ELECTRICAL RESISTIVITY DUE TO NEUTRON BOMBARDMENT FOR ANNEALED AND 96 PER CENT COLD WORKED CRYSTAL BAR ZIRCONIUM (114)

DECLASSIFIED

DECLASSIFIED

-701-

HW-40000

PART III: PROCESS
CHAPTER VII: COMPONENTS

	<u>Table of Contents</u>	<u>Page No.</u>
A.	ALUMINUM CANNING COMPONENTS	702
	1. Introduction	702
	2. Description of Components	703
	3. Fabrication Methods	703
B.	URANIUM	705
	1. General Flow of Uranium in HAPO Production Stream	705
	2. Sources of Uranium	706
	3. Ore Concentration	707
	4. Extraction-Purification Process	707
	5. Denitration	709
	6. Hydrofluorination	709
	7. Reduction to Uranium Metal	710
	8. Melting and Recasting of Ingots	713
	9. Fabrication into Rods	715
	10. Heat Treating	719
	12. Development Program	721
C.	ENRICHED URANIUM-ALUMINUM SLUG FABRICATION	722
D.	LITHIUM-ALUMINUM SLUG FABRICATION	725
E.	REFERENCES	728
F.	LIST OF TABLES AND FIGURES	729

DECLASSIFIED

DECLASSIFIED

HW-40000

A. ALUMINUM CANNING COMPONENTS

1. Introduction

The need for a jacket material surrounding the uranium core became apparent in the fall of 1942 when corrosion studies showed that water would react with uranium at operating temperatures (~ 80 C). Because it is impossible to employ within a chain reacting pile a jacket material that absorbs any considerable proportion of the fission neutrons, few suitable jacketing materials other than aluminum, zirconium, and beryllium have sufficiently low neutron absorption cross sections when used in the thicknesses necessary to protect the uranium. Because of neutron absorption characteristics, coating thicknesses of elements such as gold, silver, zinc, nickel, chromium, copper, and other readily available elements would have to be limited to a few thousandths of an inch. The mechanical problem of getting impervious coatings of such dimensions ruled out their use. The scarcity of zirconium and beryllium and the abundance of aluminum determined the choice between these metals for the jacketing and tubing material.

In addition to meeting the requirement of low neutron absorption, coating materials must resist corrosion by the pile coolant for a sufficient length of time to protect the uranium during its exposure. The jacket material should be readily fabricated, have suitable properties of strength, heat transfer, thermal stress and strain, and be compatible with the chemical process for plutonium extraction. Two other jacket materials zirconium and stainless steel, are being used in operating reactors or will be used in reactors under construction. Zirconium has a neutron cross section about half that of aluminum but is much more expensive. Stainless steel requires enriched uranium (in thermal neutron piles) to overcome its high neutron cross section - about ten times that of aluminum.

DECLASSIFIED

DECLASSIFIED

HW-40000

2. Description of Components

The jacket components (Figure VII - 1) used at Hanford are essentially the same for all the processes ("F", "C" "HPA", See Chapter VIII). The "can" is a hollow thin wall right cylinder with one end closed. When the core material is inserted in the can, the cap is placed on top of the core and the cap-can interface closed by fusion welding, producing a jacketed fuel element. The can used for the "F" process (lead dip) has a wall thickness of about 45 mils, a can base thickness of about 0.2 inch, and an overall length of about 9-1/2 inches. The rings near the open end of the can prevent Al-Si from leaking between the can and the canning sleeve during the canning operation.

The cap pictured in Figure VII - 1 is used in the "F" process. The boss on top of the cap is gripped by the canning tongs during the canning operation. Subsequently, it is machined off to give the finished fuel element pictured. The overall height of the cap is held to close tolerance (+0.005 inch) to provide a reference surface for the trimming operation prior to welding. On a nominal eight inch fuel element the finished cap thickness is 0.340 ± 0.010 inch. For standard dimensions of various fuel elements, see Table VII - 1.

3. Fabrication Methods

The present jacket components are obtained from the Aluminum Company of America under a 2S alloy designation of M 329 F or M 261 F. The 2S ingots cast by Alcoa are sampled for purity, and those meeting HAPO specifications (Table VII - 2) are extruded into rod from which the impact extrusion blanks are machined. The impact extrusion process for the cans is illustrated in Fig. VII - 2. As can be seen in the figure, the extrusion punch must be held some distance from its striking end, magnifying the tendency for the extrusion punch to drift laterally in the die. This lateral drift causes variations in the wall thickness of the can, though it is minimized by incorporating a small "center point" in the punch. The as-extruded can has full hard properties (Rockwell "H" of about 70-75). The highly cold worked

DECLASSIFIED

DECLASSIFIED

-704-

HW-40000

aluminum structure is shown in Figure VII - 3. The aluminum grain structure after the canning operation is shown in Figure VII - 4. The R_H hardness after canning is about 30-35.

Some effort has been directed toward evaluating drawn cans as a possible can fabrication technique. Initial batches of drawn cans obtained from both Scoville and Victor were unsatisfactory because of inclusions and poor aluminum composition. It was established, however, that the cost of impact extruded cans was about one-third less than drawn cans so the evaluation was discontinued.

Can processing at Alcoa includes a trimming operation, a detergent wash, and dimensional inspection. The stringent specifications on mechanical defects (such as scratches, dents, and mars) call for special handling of the components. The cans are shipped in corrugated cardboard boxes which are divided into cardboard lined compartments to separate each can individually. Prior to use in the canning process the cans are stored in a non-corrosive atmosphere free of water and mercury. ⁽⁶⁾

4.1 Reactivity Considerations

Two reactivity considerations are composition and dimensional tolerances. Of the sixteen elements specified in the composition specification, only four (silicon, magnesium, lead and bismuth) have thermal neutron absorption cross sections less than aluminum. In general however, the composition limits for most of the materials are set by the composition of special grades of 2S aluminum (99.3 to 99.8% aluminum) which are commercially available. Exceptions to this are boron and cadmium which have very high cross sections, and bismuth and lithium which form undesirable by-products during irradiation. With the exception of iron and silicon, none of the impurities exceeds 0.05%.

Dimensionally the aluminum components are held to within five mils on the can wall and ten mils on the base and cap.

DECLASSIFIED

DECLASSIFIED

-705-

HW-48909

4.2 Corrosion Considerations⁽¹⁵⁾

Corrosion considerations include composition and structural defects. As pointed out previously, pile reactivity consideration led to the use of aluminum as the jacket and process tube material. Then corrosion experiments indicated that a 2S composition aluminum (with high cross section materials held to a minimum) had adequate corrosion resistance. As technology increased, purer grades of 2S aluminum (alloys M 261 and M 329) were obtained. Out-of-pile and in-pile tests indicated that these purer alloys were more satisfactory from the corrosion standpoint also.

The aluminum components should be free of visual cracks, seams, porosity, laminations, and imbedded foreign material which might lead to corrosive attack. In general, surface scratches and mars should not exceed three mils in depth. The acceptability of a metallographic structure is based primarily on the corrosion resistance of that structure. Certain obvious defects include a greatly enlarged grain structure, precipitation at the grain boundaries, and segregated impurities. A more detailed discussion of corrosion of the aluminum jacket can be found in Chapter III.

B. URANIUM

1. General Flow of Uranium in HAPO Production Stream

The general flow of uranium for Hanford production is shown in Figure VII-5. Ore concentrates are received at the feed material production centers* from the Belgian Congo, the Rand in South Africa, the Colorado plateau, and other sources. These concentrates are processed following the production stream shown in Figure VII-5, and the resultant metal eventually is irradiated in the piles at Hanford. During the irradiation to produce plutonium there is a depletion of the U_{235} content of the uranium. To build this up to the normal U_{235} content (0.7115 per cent), the orange oxide (UO_3) from the HAPO separation plant is sent to Paducah, Kentuck, where it is converted to uranium

* The feed material production centers are operated by the Mallinckrodt Chemical Works (MCW) and the National Lead Company of Ohio (NLO).

DECLASSIFIED

DECLASSIFIED

-706-

HW-40000

hexafluoride (UF_6) and processed through the gaseous diffusion cascades. This diffusion process produces an enriched uranium hexafluoride and a by-product uranium hexafluoride with a U_{235} content less than that which was present in the irradiated uranium. The uranium hexafluoride which has been brought up to normal U_{235} content is drawn off and shipped to Fernald. There the UF_6 is reduced to uranium tetrafluoride (UF_4), which in turn is reintroduced into the feed material stream and reduced to metal along with refined material from the ore concentrates. Each of the steps in the process of converting the ore concentrates to uranium slugs for use at Hanford will be discussed in turn in this portion of Chapter VII.

2. Sources of Uranium

Only four parts per million of the earth's crust is uranium. However, uranium is more abundant than some of the more commonly known elements; e.g., cadmium, bismuth, mercury, and silver. It is nearly always found in complex combinations with other metal oxides and is considerably more abundant in weathered igneous rocks than in sedimentary or metamorphic formations. Some of the more commercially important ores, carnotite, pitchblende, and torbenite, are found in the Belgian Congo, the Colorado plateau, and Canada. The uranium oxide (U_3O_8) content of these ores may range from 7.0 to 70 per cent.

There are other ores which are not so well known. The tailings from the gold mines in Rand, South Africa are scheduled to become the third principal source of uranium for the United States in the immediate future. In addition, the Atomic Energy Commission is developing new sources. One example is the extraction of uranium as a by-product from Florida phosphate rock (leached zone material) which is treated in the course of making fertilizer. In general, the break-even point in handling domestic ores is 0.2% uranium. If the uranium content is much lower than this, the handling costs make it prohibitive to remove the uranium unless there

DECLASSIFIED

DECLASSIFIED

-707-

HY 100-100

are other materials which may be extracted at the same time or unless the tailings may be inexpensively handled. This is important in processing the phosphate rock in Florida, for example, where the uranium is purely a by-product.

3. Ore Concentration

There are two general processes employed for the concentration of uranium ores. The carbonate process is used where the calcium content of the ores is extremely high. For these ores it is necessary to use a 10% sodium carbonate solution to break down the minerals. Usually the sulphuric acid process is suitable. A typical sulphuric acid process is shown in the flow sheet, Fig VII - 6. Diagrams of the flow of materials in both the carbonate and acid leach processes are shown in references 1 and 17. These references also present discussions of both processes. The sulphuric acid process is employed in conjunction with the ion exchange column, Fig. VII - 7. This process is important in working tailings and picked-over ore residues. In the ion exchange, strong base anionic resins adsorb the uranyl sulphate. The concentrate produced by this process compares favorably with the best of the hand picked pitchblends such as were shipped from the Belgian Congo early in Manhattan District history. The resin-in-pulp process,⁽¹²⁾ is used to concentrate low value Colorado plateau ores. The crushed ore is leached in an acid. Baskets containing a strong base ion exchange resin are passed through the unfiltered pulp. In passing the resin through the pulp, the uranium is extracted. The uranium is washed from the resin with nitric acid and is precipitated as sodium diuranate. There are about a dozen ore concentrating plants on the Colorado plateau operated by different companies for the purpose of producing uranium for the Atomic Energy Commission. Flow sheets of some of these processes are presented in reference 12 which also provides further references to sources of information in the classified literature.

4. Extraction - Purification Processes

The other extraction process was developed early in the Manhattan Engineering

DECLASSIFIED

DECLASSIFIED

-708-

HW-40000

District history by J. I. Hoffman of the National Bureau of Standards. This method of extracting and purifying uranium was developed to a high state of efficiency by the Mallinckrodt Chemical Works at St. Louis, and this general process is still employed. The current Mallinckrodt process⁽¹⁸⁾ is outlined in Figure VII - 8. The ore solution, after precipitation of the sulphate ion as barium sulphate, generally contains about 4000 parts per million of molybdenum oxide, about 2000 parts per million of P_2O_5 , 350 parts per million of silica and 5000 parts per million of iron along with smaller amounts of other impurities. Among these are rare earths with large neutron cross sections; these elements must be removed before uranium may be used in the piles. The Mallinckrodt practice is a two-stage extraction process, the second stage being particularly important in the removal of iron and boron from the NOK (not okay) liquor. Both calcium nitrate and sodium nitrate have been used as salting-out agents to increase the partition coefficient in the columns. A high concentration of nitrate ion is maintained to drive the uranium into the ether. The Feed Materials Production Center at Cincinnati, Ohio, operated by the National Lead Company of Ohio, extracts and purifies uranium with a TBP (tributyl phosphate) process.⁽¹⁸⁾ In general, the TBP process permits use of a stronger concentration of acid than does the ether process and the distribution coefficient is higher, particularly at the bottom of the column. The ether extraction recovers about 99.7 per cent of the uranium, and TBP extraction recovers about 95 per cent. TBP approaches saturation sharply, but it has a lower uranium carrying capacity than the ether by a factor of 3. Consequently, a higher capital investment for the TBP plant is required than for an ether plant. Ether is less efficient for removal of boron; however, it is more favorable than TBP for removal of thorium. The scrub step, which consists of sprinkling a small amount of water through the OK extract liquor, efficiently removes iron and boron, thus making the one-cycle TBP extraction at Fernald competitive with the two-stage ether

DECLASSIFIED

DECLASSIFIED

-709-

HW-40000

extraction at Mallinckrodt Chemical Works. Mallinckrodt is currently engaged in the design and construction of a new plant at Weldon Spring near St. Louis. For this plant, it is planned to use one stage of TBP followed by a second stage of ether. This process is expected to combine the advantages of the TBP and ether processes. A disadvantage, however, is the extreme care required to prevent mixing of the extractants.

The product of the extraction-purification process is a uranyl nitrate solution relatively free of contaminating materials. Some contamination (Ni, Cr, Mg) is picked up in subsequent processing. On the other hand, some volatile contaminants, such as rare earths, that may remain in the purified UO_3 are volatilized in the bomb reduction and recasting operation.

5. Denitration

At both Mallinckrodt and National Lead the purified uranyl nitrate solution is converted to orange oxide (UO_3) in gas fired stainless steel pots about 3 ft. in diameter by 2-1/2 ft deep. During the evolution of nitric acid during the boil-down and drying operation, some pot corrosion occurs; consequently, the purified UO_3 contains small amounts of iron, nickel, and chromium. For this reason, the pot denitrification is not an entirely satisfactory process. At present HAPO uses electrically heated pots for denitrification of the uranyl nitrate obtained during the separation of plutonium from the uranium after irradiation. A continuous stationary calciner with an internal rotating shaft with attached propulsion blades is being constructed at Hanford. The use of the calciner will greatly increase the capacity for production of UO_3 and at the same time decrease the corrosion contamination.

6. Hydrofluorination

Figure VII - 9 shows a schematic drawing of the hydrofluorination process in which UO_3 is converted to UF_4 . The following discussion is based upon the current operating practice in the Mallinckrodt Plant Number 6 and is typical of the process at Fernald. The production rate of UF_4 at Mallinckrodt

DECLASSIFIED

DECLASSIFIED

-710-

HW-10000

is about 300 to 350 lbs. of UF_4 per hour. The uranium compounds are carried through the reactors by hydraulically driven ribbon screws. The conversion from UO_3 to UO_2 is conducted in a reactor at 1200 F with about a 50% excess of the stoichiometric requirements of cracked ammonia. The reaction in this part of the conversion process is $UO_3 + H_2 \rightarrow UO_2 + H_2O$. Following this the UO_2 is converted to uranium tetrafluoride by reaction with a stoichiometric excess of anhydrous hydrogen fluoride: $UO_2 + 4HF \rightarrow UF_4 + 2H_2O$. In the first zone of this reaction the temperature is 650 F, which is gradually increased to 1100 F as the reaction proceeds. Some impurities or contaminants are picked up in the course of these reactions; nickel, chromium and iron are the principal ones. There is a constant corrosion problem involving the flights of the screws and the welds holding the flights to the central shaft. Some of the alloys which have been used for this purpose are Illium R (no longer obtainable); Inconel; and Hastelloy B.

7. Reduction to Uranium Metal

The thermal reduction which is employed both at Mallinkrodt and National Lead is based upon a process developed by Dr. F. H. Spedding and his associates at Iowa State College early in Manhattan Engineering District history. This reduction is performed in bombs made from pipe with a flange for bolting on a lid (Figure VII - 10). The reduction reactions which may be used are: $UF_4 + 2Mg \rightarrow U + 2MgF_2 + 82$ kilocalories per mole uranium at 298 C, and $UF_4 + 2Ca \rightarrow 2CaF_2 + 134$ kilocalories per mole U at 298 C. As can be seen from these reactions, the use of calcium gives considerably more heat to aid in the separation of the calcium fluoride slag than is available for the separation of the magnesium fluoride slag when magnesium is used. However, since calcium costs more than magnesium and since a satisfactory removal of the MgF_2 is possible, calcium is not used in the production of uranium metal for Hanford. To protect the steel pipe used in the bomb from the

DECLASSIFIED

DECLASSIFIED

-711-

HW 40000

alloying attack of the uranium metal, a liner of electrically fused dolomite is used by National Lead; Mallinckrodt employs a ground magnesium fluoride slag liner. However, the National Lead Company is studying the desirability of converting from dolomite to a slag liner. The metallic product of the bomb reduction of the UF_4 is familiarly known as a derby, because the small reduction buttons produced early in the project history weighed about 125 pounds and were shaped very much like a derby hat without the brim. The derby currently produced at Mallinckrodt and National Lead weighs about 300 pounds and no longer bears this resemblance (Figure VII - 11). The bomb charge is composed of UF_4 with magnesium metal in a 2 to 4% excess of that stoichiometrically required. The average yield of solid metal is 97%. The techniques for the change in 1954 to the large diameter and greater weight derby were developed in studies to improve the quality of the uranium produced. A further important gain was made in production rate. Calculations made at Mallinckrodt indicate that with the eight-inch diameter bomb producing a 125 pound derby, about $1/3$ pound of metal was produced per minute, while about $2/3$ pounds of metal is produced per minute in the 300 pound derby process. These calculations include all the operations from the initial placing of the liner in the bomb to the derby break-out and bomb cleaning.

A further step is being taken at Mallinckrodt in the production of large size reduction derbies. These large size reductions are called dingots, a contraction of direct ingot. In the production of dingots, a stoichiometric excess of about one per cent magnesium is sufficient, and pieces of uranium weighing 3300 pounds are produced (Figure VII - 12). The purpose of the production of dingots is to obtain high-purity metal with a minimum of inclusions. The dingot makes this possible since it consists of a larger mass of molten metal which cools more slowly, thus providing an opportunity for the frozen slag particles to rise to the surface before the uranium solidifies. Mallinckrodt is investigating two avenues for handling the dingot material. One is the conventional method for the melting and recasting of the metal produced,

DECLASSIFIED

DECLASSIFIED

-712.

HW-40000

like the method currently employed with the ingot uranium from the smaller derbies. The other approach is the fabrication of the dingot directly without intermediate recasting. Initial working of the scalped (surface machined to sound metal) dingot is forging (Figure VII - 13), followed by rolling or extrusion.

Chemical analysis and metallographic appearance of the derby prove that the dingot metal is quite clean. The carbon content may be about 35 ppm, nitrogen about 35 ppm, and magnesium 25 ppm. Hydrogen may range from 4 1/2 to 6 1/2 parts per million. The density is generally from 19.00 to 19.04 grams per cc throughout the scalped derby or dingot. In recasting however, the composition of the uranium metal changes. Reaction with the graphite in the crucible increases the carbon content to about 300 to 400 parts per million. The nitrogen content increases slightly to approximately 40 parts per million, due to reaction with the nitrogen in the atmosphere which was not exhausted from the vacuum melting and casting furnace. The hydrogen, however, is partially lost, and the resultant hydrogen content in the recast ingot is about 2 parts per million. The magnesium content also is reduced from about 20 to between 5 and 10 parts per million. Thus it can be seen that if the hydrogen content can be controlled, the purity of the dingot uranium will be superior to that of recast ingot uranium.

In preparing a bomb for firing, the thoroughly blended mixture of uranium tetrafluoride and magnesium is tamped into the bomb liner. A layer of the liner material is then placed above the charge and the lid is bolted in place. The loaded bomb is placed in an electrically heated furnace at about 1200 F. As the bomb is heated the charge may fire at internal temperatures between 900 and 1200 F. This firing temperature apparently is determined by the strength of the oxide film on the magnesium particles. The maximum temperature within the reacting mass is estimated to be around 3500 F.

DECLASSIFIED

DECLASSIFIED

-713-

HW-40000

After the thermite reaction within the bomb has gone to completion, the bomb is removed from the furnace and placed in an open pit where it is allowed to cool. When the bomb approaches room temperature, it is placed in a tank filled with water where cooling is completed. After cooling, the lid is removed from the bomb and the slag and the uranium derby are broken out. The uranium metal is cleaned mechanically and moved to the storage area at Fernald; however, at Mallinckrodt, in addition to mechanical cleaning, the uranium derby is pickled in nitric acid.

8. Melting and Recasting of Ingots

The process for melting and recasting of ingots is essentially the same at both Mallinckrodt and National Lead. But the composition of the charge varies at the two plants. National Lead also fabricates ingots to rods and machines slugs. Mallinckrodt, on the other hand, ships the ingots to National Lead for rolling and machining. As a consequence, the Mallinckrodt charges for recasting consists largely of derbies plus small amounts of uranium cropped from ingots. National Lead, on the other hand, in addition to recasting derbies includes in its charges solid scrap cropped from the top of the ingots, rejected solid slugs, and briquetted turnings. This charge is known as a blended or composite charge. The resultant ingot has a lower magnesium content than the unblended Mallinckrodt ingot because a large amount of the charge has previously been through the casting operation. During the casting, the magnesium metal has had an opportunity to boil off and the magnesium fluoride has had an opportunity to rise to the top of the melt. The size of the charges at the two plants is about 1200 pounds regardless of the make-up. The charge is carefully placed in a graphite crucible which is then placed in a vacuum induction melting and casting furnace (Figure VII - 14). The metal is melted by electrical induction, the power being supplied by motor generator sets at a frequency of 3000 cycles per second. The vacuum during the melting and recasting operation is usually 200 microns or less. At both sites the metal is poured by breaking a

DECLASSIFIED

DECLASSIFIED

-714-

HW-40000

graphite plug in the bottom of the crucible. After the plug is broken, no control can be exercised over the way the metal flows into the graphite mold, held in the vacuum chamber below the crucible. Process studies at Mallinckrodt indicate that it takes about five hours to melt and recast either a five-inch diameter ingot (600 pound charge) or a seven-inch diameter ingot (1200 pound charge). This includes melting, attaining pour temperature, casting, cooling, final stripping of the ingot from the mold, and breakdown of the furnace for the new charge. In general, the pouring temperature is selected as a compromise between a lower temperature resulting in low carbon and nitrogen concentrations and a higher temperature which results in good surface quality. As the temperature rises above 2650 F there is less piping, especially with hot top molds, and better directional cooling. The seven-inch diameter molds permit lower pouring temperatures (around 2400 F) but the solidification pattern is not favorable for the elimination of secondary pipe; consequently, both Mallinckrodt and National Lead pour from temperatures above 2500 F.

A mold wash is often used to assure good ingot surfaces. A mixture of magnesium oxide and magnesium sulphate or magnesium chloride in water, when baked in the graphite mold, protects the graphite from the attack of the stream of uranium during its flow into the mold during casting. This has only a slight effect in reducing the carbon content of the uranium, since most of the carbon is picked up during the melting cycle in the crucible itself. After the ingot has been cast it is given an opportunity to cool before the vacuum is broken, otherwise considerable oxidation of the hot uranium occurs. The ingot in the graphite mold is removed from the vacuum furnace and the mold is stripped from the ingot. The fin, which may result from uranium flowing between the two parts of the split graphite mold is removed by grinding in an enclosed hood. Any other surface irregularities which may be troublesome in subsequent fabrication are also removed by grinding. The unsound metal at the top of the ingot is cropped by a circular saw. Beneath this crop, a small

DECLASSIFIED

DECLASSIFIED

-715-

HW-40009

slab of metal is removed for a density determination. After sufficient crops have been made to reach the desired density specification, this sample is analyzed to ensure that the ingot meets chemical specifications. The principal changes in chemical composition with remelting and casting are discussed in part 7 above. In general, cropping is repeated until sound metal is reached and there is no evidence of secondary piping.

A projection is cast on every fifth or sixth ingot and at the sawing station the projection (or egg) is removed and identified prior to machining and shipping to Hanford for reactivity (TDS) testing in the 305 Building (Chapter XVI). Shortly after completion of the TDS test, the results are transmitted to the casting site by teletype. The accepted ingots are then shipped to the rolling plant at Fernald.

9. Fabrication into Rods

The seven-inch diameter by 40-inch long ingots are fabricated into rods by rolling in the alpha phase. Previous practice for the manufacture of uranium rods has included gamma extrusion (above 770 C) and alpha extrusion (below 660 C). Gamma extrusion is no longer practiced because of the large grains produced. Alpha extrusion is not practiced because there appears to be no economic justification for it. The current practice at Fernald is to preheat the 1000-pound cropped ingot in a 54-46% molten mixture of potassium and lithium carbonate salts to between 1180 and 1200 F (Figure VII - 15), this being 20 F below the alpha-to-beta transformation region. This temperature is selected because it is in the portion of the alpha region where uranium is most easily deformed without damage, and less power is required for rolling. In addition the nominal 1.435-inch diameter uranium rod produced is almost random with regard to grain orientation after fabrication at this temperature. A temperature slightly less than the alpha-to-beta transformation temperature is selected so there will be a minimum of danger that the metal will transform to the beta phase during rolling.

The rolling mill at Fernald may be considered in two parts; the first portion of the mill is a two-high reversing-blooming mill with rolls 22 inches in

DECLASSIFIED

DECLASSIFIED

-718-

HW-40000

diameter and mechanical handling equipment for manipulating the ingot as it moves back and forth through the rolls (Figure VII - 16). The operator sits in the pulpit, over the mill, where he can watch the mechanical manipulators which he controls. The salt used in the preheat bath provides a protective blanket so the air cannot reach the uranium billet, thus preventing oxidation of the metal and subsequent contamination of the area. Salt is added to the ingot from time to time during the blooming operation.

In addition to the mechanical manipulators for rotating and moving the ingot back and forth as required by the blooming schedule, there is equipment for moving the bloomed billet to the intermediate heating furnace. This furnace contains a eutectic lithium-potassium carbonate bath of the same composition and temperature as that in the ingot preheat furnace. When the bloomed billets are too long to be accommodated in the intermediate furnace, they are sheared to a more convenient length. The residence time in the intermediate furnace is about 12 minutes minimum compared with the 70 minutes minimum required in the ingot preheat furnace, to ensure that the 7-inch diameter ingot is uniformly heated throughout.

The second portion of the rolling mill (Figure VII - 17) consists of a six-stand continuous finishing mill. The rod being rolled passes through guide rolls and the entire continuous mill without interruption. The pass schedule is oval-round with the oval rolls rotating in the vertical plane whereas the round rolls, which alternate with the vertical rolls, rotate horizontally. Approximately fifteen per cent reduction in cross-sectional area is made in each pass, and the mill delivers the rod at a speed of 250 to 350 feet per minute.

Following the rolling portion of the mill, there is a flying shear which can be set to cut the finished rod to the desired lengths. Temperatures are controlled in the rolling process by thermocouples in the salt baths for heating the ingots and the billets. From time to time, the uranium oxide sludge build-up is great enough that the rods are partially beneath the

DECLASSIFIED

DECLASSIFIED

-717-

HW-40000

surface of the sludge. In these instances, particularly in the intermediate furnace, portions of the rods are actually rolled in the beta phase. National Lead now carefully removes the sludges from these baths to assure more uniform heat distribution. Also, both of the furnaces are now electrically heated rather than gas heated as formerly. In addition to the thermocouples for control of the bath, Radiamatic heads are provided on the first and sixth stands in the finishing mill to give an indication of the temperature of the rod as it passes these particular points. Although the Radiamatic heads do not give an accurate temperature reading (probably correct to within ± 50 F), they indicate whether or not rod temperatures are as expected.

After the rods have been rolled in accordance with the established process, the resulting structure consists of completely recrystallized alpha phase uranium grains with a diameter of .020 to .069 millimeters (determined at 100 diameters magnification). In addition to being completely recrystallized, the grains are almost randomly oriented. The principal orientation that exists is that of the (200) plane parallel to the rolling direction. If the rod is rolled at lower temperatures, a (110) - (010) orientation replaces the (200).⁽⁹⁾ From time to time, a banded structure has been observed in the as-rolled material from Fernald.⁽¹³⁾ The bands consist of alternate grains of large diameter and grains of small diameter. Less frequently, uranium billets have been over-heated in the sludge in the intermediate furnace with a resultant structure representing rolling in the alpha and the beta phase simultaneously within a rod. Usually, this is easily detected by a visual examination of the ends of the machined uranium slug. The grain diameter of the as-rolled uranium is determined by conventional metallographic techniques. The preferred orientation may be checked either by x-ray diffraction or by using the sonic vibration technique developed at Hanford.^(7, 11)

10. Heat Treating

Current processing of HAPO fuel elements at Fernald includes beta heat-treating the rolled rod prior to straightening and machining. The heat-treating

DECLASSIFIED

DECLASSIFIED

-718-

HW 40000

step is necessary to reduce the amount of preferred grain alignment produced by the rolling operation.

At the present time, all heat-treating of virgin HAPO production metal is done at FMPC. The bath in which the rods are transformed is a 22-foot long by 8-foot wide by 3-foot deep molten eutectic mixture of 46 per cent lithium carbonate (Li_2CO_3) and 54 per cent potassium carbonate (K_2CO_3) heated by alternating current through immersed electrodes. The entire cycle of the rods during transformation and subsequent quenching to room temperature is conducted automatically in the Ajax furnace and adjacent 22-foot long by 3-foot wide by 3-foot deep quench tank. The quench solution is circulating water containing a low concentration of heat-treating salt which is dissolved from the salt carried on the rod surfaces. The water circulation is not rapid enough to assure the absence of salt; consequently, 2 per cent salt concentrations are not uncommon. The heat treating furnace and quench tank are shown in Figure VII - 18.

The heat treating and quenching cycle currently in use is as follows:

1. Immersion time of rod in $720\text{ C} \pm 10\text{ C}$ salt bath - 12 minutes.
2. Transfer time of rods from salt bath to complete immersion in quench solution 20 seconds.
3. Rods remain submerged in quench solution 45 seconds before removal.

During heat treating and quenching, the rods (in pairs) are supported in a horizontal position on hooks spaced on 18-inch centers. The support hooks are suspended from an overhead continuous conveyor system which automatically moves the rods through the salt bath and quench tanks. The rods vary from 15 to 20 feet in length depending on the accuracy of the flying shear which measures and cuts the moving rod after it leaves the Number 6 finishing stand of the rolling mill. The last rod cut from each ingot may be shorter than the other because of variations of ingot

DECLASSIFIED

DECLASSIFIED

-719-

HW #10010-7

lengths prior to rolling.

After completing the heat treating and quenching cycle, each rod, after being stamped with an identification number on the cylindrical surface near its trailing end, is conveyed to the Medart straightener (Figure VII-19). The Medart is a roller-type straightener in which the rod rotates and advances while being maintained in a flexed or slightly bent position by two pairs of concave rolls. After straightening, the rod ends are squared with a power hack saw. Each rod is then accurately weighed for accountability purposes. Special samples (called red tag samples) are removed periodically from specific rods for laboratory study and process control.

11. Machining

The weighed rods are transferred to the machine shop where they are loaded in groups of five into spindle fed Acme Gridley lathes (Figures VII-20 and VII-21). These machines in a single operation cut slugs off the rods to the approximate finish lengths and dress the cylindrical surface to the finish diameter. Prior to mid-1955 the machining operation at FMPC was done by making only rough cut lengths and diameters on the Acme Gridleys and finishing by a centerless grinding operation. The current method was adopted after a careful study of the economics and determining that the differences in surface appeared to have but little effect on the irradiation behavior of the finished core. Each slug as it comes from the Acme Gridley is positioned by hand in a pallet and marked so its exact location in the original rod is known. * Finish length machining is done on a Bore-Matic machine which finishes both ends of each slug at the same time. The specified length is established as the ends are finished, after which the slugs are restamped. The finished slugs are degreased in trichloroethylene, pickled in 50 per cent HNO_3 (unheated), and sent to inspection. In inspection, each slug is examined for metal quality defects and a statistically determined number are examined for dimensions. In addition to these inspections, every third slug is ultrasonically tested for verification that complete beta transformation occurred

* It is known that errors are made in slug identities, but they occur only rarely.

DECLASSIFIED

DECLASSIFIED

-720-

HW-40000

during heat treatment.

Failure of the statistically determined samples to conform to the specified limits is cause for inspection of the entire lot represented. All slugs not meeting the minimum requirements are rejected.

The finished pieces that have survived all inspections are loaded into specially constructed wooden boxes which are marked with an identifying number. The slugs are then shipped to HAPO via rail. The boxes of slugs when received at HAPO are assigned to specific HAPO lots according to the prior history of the metal. The number on each box assigned to a lot is recorded, and throughout the rest of the processing, to acceptable finished pile fuel element, the entire HAPO lot stays intact. The prefix letter in the HAPO lot number is dictated by the name of the producer site and the fabrication history. The two most commonly used prefix letters and their meanings are shown below. HAPO lot identification is discussed in more detail in Chapter XV of this manual.

1. M - virgin slugs from ingot metal rolled to rod and beta heat treated in a Li-K carbonate salt bath prior to machining into slug form. Reduction and recasting to ingot made at MCW. The rolling, heat treating, and machining done at FMPC.
2. K - virgin slugs from ingot metal rolled to rod and beta heat treated in a Li-K carbonate salt bath prior to machining into slug form. Reduction, recasting to ingot, rolling, heat treating, and machining done at FMPC.

A statistical sample is chosen at HAPO (i. e., six randomly selected slugs from each box of 250,) for length, diameter, and warp measurements. If the dimensions of these statistical samples do not conform to acceptance specifications, then the rest of that entire lot is inspected and all non-conforming slugs are rejected from further processing. Every slug in each lot is then tested by ultrasonic methods⁽⁹⁾ for verification that complete beta transformation occurred during heat treatment. Virgin slugs

DECLASSIFIED

DECLASSIFIED

-721-

HWA 40800

rejected at this station are set aside and eventually re-heat treated in a molten salt bath at HAPO.

The salt-bath heat-treatment at HAPO is accomplished in a molten eutectic mixture of barium, sodium, and potassium chlorides at 730 ± 10 C for 4 1/2 minutes followed by a tap water quench within 10 seconds of removal from the salt bath. The re-heat treated and quenched slugs are fed back into the production stream at the ultrasonic station after a special pickling operation to remove the adhering salt. Slugs are re-heat treated at HAPO only once.

The acceptable slugs from the ultrasonic test are placed in stainless steel baskets, 24 slugs per basket, and charged into an automatic conveyor system which passes through a trichloroethylene degreaser, a hot (55 C) 50 per cent HNO_3 cleaning solution, a water wash and a warm air blast dryer. The dried slugs are visually inspected for metal quality defects (seams, folds, laps, and striations), and those failing to meet minimum established standards (Chapter XV) are rejected from the production stream, and returned to FMPC for reprocessing. The acceptable slugs from the pickle inspection are ready for assembling in the canning operation.

12. Development Programs

Development programs are continually being pursued at HAPO and other sites to modify current production processes or devise new ones to produce a less expensive fuel element, or to improve the irradiation performance of the element in current use, or both. Several of these programs, such as the "dingot" process and fabrication by extrusion, have been referred to above. In addition to the previously mentioned developmental studies, one other program, uranium heat treatment, has recently received attention. It is known that the current production beta heat-treating will and does produce core elements capable of economic production of plutonium at HAPO. However, future planning for HAPO production includes greater exposure

DECLASSIFIED

DECLASSIFIED

-722-

HW-40000

concentrations at much higher tube powers than are current; these conditions will increase the demands on the fuel element core.

It has been shown that different heat treatments will produce differences in macro- and micro-structures, degree of structure uniformity, and preferred grain orientations. For this reason, many basic data are being obtained on the effect of various thermal treatments. Results obtained from the heat-treating program should lead to a thermal treatment of uranium in either rod or slug form which will produce the structure, residual stress pattern, and preferred grain orientation required for the optimum pile performance of the cores for specific reactor conditions.

C. ENRICHED URANIUM-ALUMINUM SLUG FABRICATION^(10, 14, 16)

There are two different compositions of enriched uranium-aluminum alloys used at HAPO; namely, "J" and "C" slugs. The "J" alloy cores, which are about eight inches long and contain approximately 7.5 per cent enriched uranium by weight, are used for fuel material in large scale isotope production such as tritium and U-233 production. The "C" alloy cores, which are about six inches long and contain approximately 4.5 per cent enriched uranium by weight, are used for overall pile enrichment, to obtain pile flattening, to increase production through better heat distribution, and to augment reactivity. The enriched uranium in these two alloys contains a minimum of 92.5% U-235 by weight.

At HAPO, the first enriched uranium-aluminum alloys, canned in 1949 and 1950, included approximately 8500 "J" slugs for the tritium program. These were cast cores fabricated at Oak Ridge National Laboratory (ORNL) and canned at HAPO by the Al-Si dip process. The next group of "J" alloy cores, for tritium production and U-233 production, included about 48,000 pieces which were canned in 1953 and 1954. These "J" slugs were fabricated at ORNL from cast cores (except for about 1000 of the last pieces which were made from extruded rods) and canned at HAPO by the controlled-sized unbonded "C" process and the hot-press "HPA" process (Chapter VIII).

DECLASSIFIED

DECLASSIFIED

-723-

HW 40000

The first "C" slugs were canned in 1952; about 24,000 pieces had been canned by the last of 1955. All of the pieces canned were fabricated from cast cores, except the last 7000 pieces which were from extruded rods. The first slugs were canned by the sized unbonded "B" process, which was replaced in 1953 by the controlled-sized unbonded "C" process and in 1955 by the hot-press "HPA" process.

A flowsheet of the fabrication process for production of cast and extruded "C" and "J" alloy is shown in Figure VII-22. The first step in the fabrication of "C" and "J" alloy cores in the melting, alloying, and casting operation. Aluminum of 99.9 per cent purity is melted in a graphite crucible in a high frequency induction furnace. When the aluminum has completely melted, the enriched metallic uranium wrapped in aluminum foil is added to the molten bath. The metal is heated to 850 C and stirred vigorously for 10 minutes with a graphite rod and furnace induction currents to promote rapid dissolution of the uranium metal. When the temperature has dropped to 725 C, the metal is sampled for control analysis and cast in graphite molds into either slug ingots or extrusion billets. The high purity graphite molds have a high thermal conductivity which allows the rapid cooling necessary for a small grain size and a uniform distribution of the UAl_4 compound in the cast structure.

When slugs are produced from slug ingots, the ingots are cropped and the slugs machined directly to size (1.343 or 1.352 inches) and shipped to HAPO for canning. When slugs are produced from extruded rods, the cast extrusion billets are first cropped and scalped and preheated to the required extrusion temperature (about 325 C for "C" alloy and about 480 C for "J" alloy) in a resistance furnace. The billets are extruded into rods on a 700-ton Lake Erie extrusion press at a billet container temperature of about 225 C for "C" alloy and 400 C for "J" alloy, a die temperature of 200 C, a total force from 300 to 390 tons, and a ram speed of 25 to 38 feet per minute. The most satisfactory die design is one having a flat face with a very small radius (1/64 to 1/32 inch). The extruded rods (about 1.40 inch diameter) are then rough machined into slugs, centerless ground to size

S

DECLASSIFIED

DECLASSIFIED

(1.343 or 1.352 inches) and shipped to HAPO.

Most of the "C" and "J" alloy slugs were canned at HAPO by the "C" process which was replaced in 1955 by the "HPA" process. Only slug cores produced from extruded rods were suitable for canning by the "HPA" process since the cast slugs were porous and caused improper bonding during hot press canning.

Reject slugs not suitable for recanning from the "C" process, and all reject slugs from the "HPA" process (plus the aluminum jackets) are returned to ORNL. The scrap from slug machining and reject slugs from HAPO are thoroughly cleaned to remove any contamination that might lower the reactivity of the alloy. They are then remelted, realloyed (if necessary), recast, and sent back through the process stream.

Following irradiation, the slugs are shipped to Arco where the uranium is recovered from the alloy. The uranium, as uranyl nitrate, is shipped to ORNL where the nitrate is converted to gaseous UF_6 , sent through the gaseous diffusion process to attain the proper U-235 concentration, and reduced to metallic uranium which is again ready for alloying purposes.

The chemical impurities in the alloy are controlled and the fabrication process is controlled to prevent contamination of the alloy, since impurities lower the reactivity of the alloy by parasitic absorption of neutrons.

Throughout the entire process, care must be taken not to obtain a nuclear chain reaction by concentrating enough of the enriched uranium, the alloy scrap, the slugs, or the uranium solutions to obtain a critical mass. The number of slugs necessary for a chain reaction varies with such conditions as slug arrangement, the presence of a moderator such as water or wood, and the presence of other fissionable material and reflectors such as natural and enriched uranium. All of these factors must be considered to safeguard the operation. Therefore, handling, storage and transfer of

DECLASSIFIED

DECLASSIFIED

-725-

HW 40000

enriched uranium-aluminum alloy is closely controlled in all phases of the operation.

D. LITHIUM-ALUMINUM SLUG FABRICATION^(2, 3, 4, 5, 10)

Tritium is produced from neutron bombardment of the Li^6 isotope by the reaction: ${}_3\text{Li}^6 + {}_0\text{n}^1 \rightarrow {}_2\text{He}^4 + {}_1\text{H}^3$. The lithium-aluminum alloy slug was developed to produce tritium in large quantities for a period from 1949 to 1954. The slug was four inches long and contained 3.5% natural lithium (natural lithium contains about 3.5% Li^6). The major facilities for carrying out the tritium program were located at the 100-B Area.

Fabrication of the first 20,000 slugs consisted of (1) molten vacuum alloying, casting into billets, cropping and scalping the billets at HAPO - 100-B, (2) extrusion into rod at Detroit Gasket and Manufacturing Company, and (3) machining into slugs and canning at HAPO - 100-B.

The remaining slugs (about 50,000) were fabricated according to the flowsheet shown in Figure VII-23. This flowsheet shows that all fabrication prior to machining into slugs was performed by the E. I. duPont de Nemours and Company at the Savannah River Plant. Slug machining and canning was performed at HAPO in the 300 Area. The following is a description of the various steps shown on the flowsheet.

The vacuum furnace for melting, alloying and casting the Li-Al alloy was composed of three chambers; the charging, melting, and casting chambers. These chambers were separated by valves which allowed a continuous vacuum to be held in the central melt chamber. Clean, dry 99.95% aluminum ingots were placed in the charging chamber, and the charging chamber was evacuated. The ingots were added to the crucible, melted at 760 C, and outgassed at 725 C to approximately 3μ pressure. The 99.8% lithium in clean, dry aluminum cans, which had been previously punctured, was placed in the charging chamber and, after evacuating the charging chamber, the lithium was added to the molten aluminum. The alloy was stirred by induction at 725 C and 100 mm Hg argon pressure. The melt was then outgassed at 0.080 mm Hg

DECLASSIFIED

DECLASSIFIED

-726-

HW-40006

pressure. Purified argon was bubbled through the melt to assist the outgassing and to float any dross to the melt surface. Just prior to casting, the melt temperature was raised to 760 C. The melt was cast under an argon atmosphere through a heated graphite launder into hot-topped, water cooled molds. After the molds had cooled below 100 C they were removed from the furnace assembly.

The crucibles in the above operation were Dixon C-7, clay-graphite-silicon carbide lined with glass cloth, rammed with Norton RM 1992 ramming mix, coated with sillimanite cement, coated with clay-graphite cement, sintered, and outgassed. The molds used in the casting operation were graphite with asbestos paper hot-tops, coated with a zirconium oxide-isopropyl alcohol wash, sintered, and outgassed.

Following the casting operation the billets were removed from the molds and radiographed to determine billet soundness and the limit of the shrinkage cavity. The billet was then cropped to remove the shrinkage cavity and scalped to remove surface defects and contaminants prior to extrusion.

The billets were extruded into rods on a Watson-Stillman extrusion press at a billet and billet container temperature of 400 to 440 C, a die temperature of 175 to 300 C, a total force up to 2750 tons, and a ram speed from 10 to 100 feet per minute. "Aquadag" was the extrusion lubricant. The extruded rod was severed from the billet in about 11 foot lengths and the rough ends cropped prior to heat treating.

The rods were solution heat-treated in a closed furnace at 550 to 600 C for 3 hours, removed from the furnace, and quenched immediately in cold flowing water for 30 seconds. The solution heat-treatment allows the Li-Al phase to enter solid solution and the quenching holds the Li-Al phase in solution. The alloy was left in a supersaturated unstable state to age-harden.

After heat-treatment, the rods were swaged at room temperature to

DECLASSIFIED

DECLASSIFIED

-727-

HW-10000

straighten and size the bar to a minimum diameter of 1.400 inches. The sized rods were shipped to HAPO and machined to slug size (1.364 in. diameter) just prior to canning. Since the Li-Al alloy corrodes rapidly in air and water and the rods had been in contact with "Aquadag" and water during the fabrication process, the machining operation minimized the amount of hydrogen in the slug by removing the surface corrosion products. The slugs were canned immediately after machining to prevent further hydrogen contamination. Slugs canned in 1949 to 1951 were canned by the unbonded "B" process; slugs canned in 1953 and 1954 were canned by the controlled-sized unbonded "C" process and the hot press technique.

Reject slugs not suitable for recanning and solid scrap from slug machining were returned to Savannah River where this scrap was combined with scrap from billet and rod cropping. When sufficient scrap had accumulated to make a billet, the scrap was returned to the vacuum furnace, remelted, recast into billets and sent back through the process stream.

The canned slug quality requirements were stringent since any process water leaks would lower the quality of the tritium produced and might cause damage to the pile during irradiation.

After irradiation the slugs were shipped to 100-B for tritium extraction. The slug jackets were mechanically removed in a dry atmosphere and the bare core was then charged in the furnace pots under a helium atmosphere to prevent hydrogen contamination. The tritium and other gases were removed from the alloy by melting and heating the alloy to 800 C in a vacuum system. The spent alloy and furnace pots were sent to the burial pit after extraction.

The tritium extraction facilities were not designed to handle slugs with gross radioactivity. This required that the alloy be free of any elements that cause intense induced gamma activity upon irradiation. Therefore, the aluminum and lithium purities were maintained as high as possible and all precautions were taken to prevent contamination of the alloy with heavy

DECLASSIFIED

DECLASSIFIED

metals during fabrication. Also, to prevent gross contamination of the tritium produced, all measures were taken to remove and prevent as much hydrogen contamination of the alloys as possible throughout its fabrication, canning, irradiation, and extraction life.

Spectrochemical and chemical analyses were made of the aluminum ingots, the lithium metal, the alloy at billet cropping and scalping, the alloy at rod cropping and the alloy after slug machining. The Li content of the alloy was maintained at 3.3 to 3.7 weight per cent and Cl, B, and Cd contents were maintained at less than 50, 1, and 1 ppm respectively. An analysis for hydrogen content was made at rod cropping and after slug machining. The maximum hydrogen content acceptable was 0.0185 cubic centimeters (STP) per gram of alloy. Other tests included reactivity and induced radioactivity tests to prevent undue loss of neutrons and to prevent slugs from having a gamma radioactivity of such strength as to prevent the extraction of the slug after irradiation.

E. REFERENCES

- (1) J. J. Katz and E. Rabinowitch, Chemistry of Uranium, Part I, McGraw-Hill (1951).
- (2) DPSOP-4, Operating Procedure for Alloy Fabrication
- (3) DPSTS-320, 320 Building Technical Standards, Savannah River Plant
- (4) HW-23151, History of the Project as of February 1, 1951
- (5) HW-23772, P-10 Project Technical Manual
- (6) HW-24458, Mercury and Slug Jacket Corrosion, R. S. Dalrymple, 5-14-52
- (7) HW-26762, A Rapid Method for Determining Preferred Orientation in Rolled Uranium Rods, M. J. Sanderson and W. V. Cummings, 1-7-53.
- (8) HW-29552, A Rapid Ultrasonic Test for Transformation, D. C. Worlton 9-15-53
- (9) HW-29741, An Interim Report on PT 313-105-19M, A Comparison of Some Properties of Uranium Rolled at the FMPC and at Simonds Saw and Steel Company, R. L. Knecht, 10-9-53.

DECLASSIFIED

DECLASSIFIED

-729-

HW-30263

- (10) HW-30263, Acceptance Specifications for HAPO Slug Cores.
- (11) HW-33024, A Sonic Test for Preferred Orientation in Hanford Fuel Element Cores, A. A. Ferguson and E. C. Wood, 1-11-55.
- (12) HW-34868 C-6, Nuclear Metallurgy Lectures, W. T. Kattner, 5-26-55.
- (13) HW-35714, Banding in As-Rolled Uranium, H. R. Gardner, 3-10-55.
- (14) HW-37952, Nuclear Safety Specifications for Fuel Element Manufacturing Processes.
- (15) NNES IV 6A, Coatings and Corrosion, J. P. Howe and T. O. Jones.
- (16) ORNL-911, Fabrication of Uranium-Aluminum Alloys.
- (17) RH-3, The Reactor Handbook, Volume 3 (First Edition) April 1953.
- (18) TID-5295, Current Commission Methods for Producing UO_3 , UF_4 , and UF_6 , January 1956.

F. LIST OF TABLES AND FIGURES

Table VII-1	HAPO Slug Types
Table VII-2	Chemical Composition of Aluminum Cans and Caps
Figure VII-1	"F" Process Can Components and Assembly
Figure VII-2	Steps in Producing Impact Extruded Parts
Figure VII-3	As Extruded Aluminum Can Structure
Figure VII-4	As Canned Aluminum Can Structure
Figure VII-5	General Flow Sheet of Uranium for HAPO Production
Figure VII-6	Simplified Flowsheet for Salt Roast Acid Leach Concentration Process for Extraction of Uranium Low in Calcium Content
Figure VII-7	Ion Exchange Column for Extraction of Uranium from Sulphuric Acid Solutions
Figure VII-8	MCW Process for Purifying Uranium
Figure VII-9	Schematic Drawing of Hydrofluorination of UO_3 to UF_4
Figure VII-10	Sketch of a Bomb Assembly
Figure VII-11	Photograph of a Twelve Inch Derby
Figure VII-12	3300 Pound Dingot Produced at MCW
Figure VII-13	1000 Ton Press Forge for Primary Forming of Dingots at MCW

DECLASSIFIED

DECLASSIFIED

-730-

HW-40000

Figure VII-14 Bank of Vacuum Remelt Furnaces at FMPC
Figure VII-15 Ingot Preheat Furnace at FMPC
Figure VII-16 Two High Reversing Blooming Mill at FMPC
Figure VII-17 Six Stand Continuous Finishing Mill at FMPC
Figure VII-18 Beta Heat Treating Unit at FMPC
Figure VII-19 Medart Rod Straightener at FMPC
Figure VII-20 Bank of Acme-Gridley Lathes at FMPC
Figure VII-21 Acme-Gridley Lathe in Machining Operation at FMPC
Figure VII-22 Enriched Uranium Flow Sheet
Figure VII-23 Lithium-Aluminum Alloy Flow Sheet

05/18/84

DECLASSIFIED

DECLASSIFIED

TABLE VII-1
HAPO SLUG TYPES

Type Slug	Core Diameter	Core Length	O. D. of slug	Slug Length	Can Wall
"J" C process thin cans	1.364 ± 0.000 0.003	8.00 ± 0.01	1.430 ± 0.012	8.79 ± 0.11 0.14	0.030 ± 0.004 0.005
"J" C process thick cans	1.344 ± 0.000 0.003	8.29 ± 0.01	1.430 ± 0.012	9.08 ± 0.12 0.14	0.040 ± 0.004 0.005
"J" Hot Press thick cans	1.352 ± 0.002	8.19 ± 0.01	1.435 ± 0.010	8.89 ± 0.06 0.04	0.040 ± 0.005
"J" Hot Press thick cans	1.344 ± 0.000 0.003	8.29 ± 0.01	1.435 ± 0.010	8.89 ± 0.06 0.04	0.040 ± 0.005
"C" C process thick cans	1.343 ± 0.002	6.00 ± 0.01	1.430 ± 0.012	6.95 ± 0.30 0.31	0.040 ± 0.004 0.005
"C" Hot Press thick cans	1.352 ± 0.002	5.92 ± 0.01	1.435 ± 0.010	6.71 ± 0.12 0.14	0.040 ± 0.005
"N" C process	1.364 ± 0.000 0.003	3.80 ± 0.01	1.430 ± 0.012	4.20 ± 0.10	0.040 ± 0.004 0.005
"N" Hot Press thick can	1.364 ± 0.000 0.003	3.80 ± 0.01	1.435 ± 0.010	4.15 ± 0.05	0.040 ± 0.005
"Q" C process thick cans	1.338 ± 0.002 0.003	6.00 ± 0.01	1.430 ± 0.012	6.70 ± 0.005 0.006	0.040 ± 0.004 0.005
8" F process	1.336 ± 0.001 0.002	8.315 to 8.410	1.438 ± 0.010	8.860 ± 0.070 0.050	0.040 ± 0.005 0.010
8" F process High reactivity slug	1.360 ± 0.002	8.490 to 8.510	1.438 ± 0.010	$8.885 \pm .085$ $.055$	$0.030 \pm .005$ $.010$
4" F process	1.356 ± 0.002	4.000 to 4.055	1.438 ± 0.010	$4.432 \pm .083$ $.092$	$0.030 \pm .005$ $.010$
8" A process	1.330 ± 0.002	8.400 $\pm$.010	1.438 ± 0.010	$8.950 \pm .065$ $.075$	$0.040 \pm .005$ $.010$
4" A process	1.350 ± 0.002	4.045 $\pm$.010	1.438 ± 0.010	$4.450 \pm .105$ $.075$	$0.030 \pm .005$ $.010$

HW-40000

DECLASSIFIED

DECLASSIFIED

HW-40000

TABLE VII-2
CHEMICAL COMPOSITION OF ALUMINUM CANS AND CAPS
(HW MATERIAL NUMBER 302 AND 303 RESPECTIVELY)

Aluminum	99.30 - 99.80%
Iron plus silicon	0.70% maximum
Copper	0.04% maximum
Manganese	0.03% maximum
Titanium	0.05% maximum
Chromium	0.03% maximum
Zinc	0.03% maximum
Magnesium	0.01% maximum
Tin	0.01% maximum
Lead	0.01% maximum
Bismuth	0.01% maximum
Nickel	0.01% maximum
Lithium	0.008% maximum
Cadmium	0.003% maximum
Cobalt	0.001% maximum
Boron	0.001% maximum

DECLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE VII-1

"F" PROCESS CAN COMPONENTS AND ASSEMBLY

UNCLASSIFIED

FIGURE VII-2

STEPS IN PRODUCING IMPACT EXTRUDED PARTS

Movement of metal takes place in a fraction of a second. On the return upward stroke the punch carries with it the extruded shell, which adheres to the punch because of shrinkage. The shell is stripped from the punch when its top edge strikes a stationary stripped bridge through which the punch is drawn.

FIGURE VII-3

AS EXTRUDED ALUMINUM CAN STRUCTURE

FIGURE VII-4

AS CANNED ALUMINUM CAN STRUCTURE

DECLASSIFIED

HW-40000

FIGURE VII-5

GENERAL FLOW SHEET OF URANIUM FOR HAPO PRODUCTION

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE VII-6

SIMPLIFIED FLOW SHEET FOR SALT ROAST-ACID LEACH
CONCENTRATION PROCESS FOR EXTRACTION OF URANIUM FROM ORES
LOW IN CALCIUM CONTENT

DECLASSIFIED

DECLASSIFIED

ION EXCHANGE COLUMN FOR EXTRACTION OF URANIUM FROM SULFURIC ACID SOLUTIONS

FIGURE VII-7

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE VII-8

MCW PROCESS FOR PURIFYING URANIUM

DECLASSIFIED

DECLASSIFIED

FIGURE VII-9

SCHEMATIC DRAWING OF HYDROFLUORINATION OF
UO₃ TO UF₄

DECLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE VII-10

SKETCH OF BOMB ASSEMBLY

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE VII-11
PHOTOGRAPH OF A TWELVE INCH DERBY

UNCLASSIFIED

FIGURE VII-12

3300 POUND DINGOT PRODUCED AT MCW

UNCLASSIFIED

FIGURE VII-13

1000 TON PRESS FORGE FOR PRIMARY FORMING OF DINGOTS AT MCW. (NOTE SALT BATH
IN RIGHT REAR.)

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE VII-14

BANK OF VACUUM REMELT FURNACES AT FMPC

UNCLASSIFIED

HW-40000

UNCLASSIFIED

HW-40000

FIGURE VII-15
INGOT PREHEAT FURNACE AT FMPC

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE VII-16

TWO HIGH 22" REVERSING BLOOMING MILL AT FMPC

UNCLASSIFIED

FIGURE VII-17

SIX STAND CONTINUOUS FINISHING MILL AT FMPC. (NO. 1
STAND AT BOTTOM CENTER.)

UNCLASSIFIED

HW-40000

FIGURE VII-18

BETA HEAT TREATING UNIT AT FMPC

1. Rods from finishing mill	5. Chain drive
2. SRO untransformed rods	6. Salt bath
3. HAPO rods to heat treating	7. Baffle to keep quench water from salt bath
4. Hook support ready to drop down and receive incoming rods	8. Water quench bath
9. Ejection conveyor	

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE VII-19
MEDART ROD STRAIGHTENER AT FMPC

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE VII-20

BANK OF ACME-GRIDLEY LATHES AT FMPC

UNCLASSIFIED

UNCLASSIFIED

FIGURE VII-21

ACME-GRIDLEY LATHE IN MACHINING OPERATION AT FMPC

UNCLASSIFIED

HW-40000

DECLASSIFIED

HW-40000

FIGURE VII-22

ENRICHED URANIUM-ALUMINUM FLOW SHEET

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE VII-23

LITHIUM-ALUMINUM ALLOY FLOW SHEET

DECLASSIFIED

DECLASSIFIED

-801-

HW-40000

PART III: PROCESS (Cont.)
CHAPTER VIII: ASSEMBLY PROCESSES

<u>CONTENTS</u>	<u>Page No.</u>
A. DIP BRAZE CANNING	802
1. Lead Dip Process	802
1.1 Preparation of slug cores	803
1.2 Preparation of aluminum jacketing components.	804
1.3 Preparation of canning sleeves	805
1.4 Canning procedure	806
1.5 Canning bath	807
1.6 Impurities associated with lead dip canning	810
1.7 Slug quench	811
1.8 Slug facing	811
1.9 Welding	811
1.10 Non-destructive tests of canned assembly	812
1.11 Penetration test	813
1.12 Canned slug etch	813
1.13 Autoclaving	813
1.14 Final inspection	814
1.15 Slug storage and shipping	814
2. Triple Dip Process	815
B. HOT PRESS CANNING PROCESS	818
1. Preparation of Slug Core and Jacketing Components	819
2. Assembly of the Components	820
3. Sizing of the Slug Assembly	820
4. Preparation of the Sized Assembly	820
5. Pressing	821
6. Finishing of the Pressed Assembly	822
7. Bond Testing	822
8. Final Inspection	823
9. Nuclear Safety	823
C. UNBONDED CANNING PROCESSES	823
1. Preparation and Inspection of the Slug Core	825
2. Preparation and Inspection of the Jacketing Components	825
3. Component Assembly	826
4. Sizing of the Slug Assembly	826
5. Finishing of the Slug Assembly	827
6. Inspection of the Canned Assembly	827
D. REFERENCES	829
E. LIST OF FIGURES	830

DECLASSIFIED

DECLASSIFIED

-802-

A. DIP BRAZE CANNING

Uranium fuel element cores have been canned in aluminum jacketing components by two dip brazing techniques, both of which employ an aluminum-silicon alloy as the brazing medium. The triple dip process, a four-stage canning scheme using a bronze bath, a tin bath and two Al-Si baths, was in use until March, 1954. It was replaced by the lead dip process, a two-stage scheme using a duplex bath (lead and Al-Si) and an Al-Si canning bath. The fuel element components are assembled beneath the surface of the final Al-Si bath in both processes. In contrast to most industrial brazing operations, flux is not used in effecting a bonded assembly except during the first core preparation step in the triple dip process.*

Other Al-Si braze canning techniques which have been and are being studied include single dip schemes in which only the AlSi canning bath is used. An extension of the single dip scheme is the "Sevac" process, also under study. In this process the preheated components are brazed with Al-Si in an evacuated chamber.

1. Lead Dip Process⁽²⁾

The lead dip canning process, a two stage scheme for fabricating Al-Si bonded, aluminum-jacketed fuel elements, was introduced at HAPO as the standard canning process in March, 1954. This process has two principal advantages over the triple dip process; (1) canning costs are lower, and (2) the structure and properties of the uranium (which remains in the alpha phase throughout the canning cycle) is essentially unchanged, permitting the retention of the desirable slug core properties effected during fabrication and heat treatment of the uranium.

Flow sheets of the operations required to produce lead dip canned fuel elements are shown in Figures VIII - 1 through VIII - 3. Figure VIII - 1

* A three-stage lead dip process at ORNL used flux on the surface of the slug preheat (or duplex) bath. The second bath consisted of an Al-Si dip bath to wash off as much of the corrosive flux as possible prior to slug assembly in the final Al-Si bath.

DECLASSIFIED

DECLASSIFIED

-803-

REF ID: A60000

shows the steps for preparing the slug components and the canning sleeve for the canning operation; Figure VIII - 2, the canning (assembly) steps; and Figure VIII - 3, the finishing and testing steps. Figure VIII - 4 shows the slug after the canning, facing, and welding operations.

1.1 Preparation of slug cores

The uranium slug cores received from FMPC have been either cores machined from heat-treated rod, which may be canned directly, or cores machined from as-rolled rod which must be salt bath heat-treated at HAPO prior to canning. Only the uranium heat-treated in rod form has been used since April, 1955. The cores are inspected for dimensional conformance, weight, completeness of transformation as effected by the heat-treatment, and (after pickling) for visible fabrication defects. (1), (5) The slug core dimensions are selected to provide the largest slug core that can be routinely canned in components of the size specified for the HAPO production reactors. (Due to over-moderation of the older reactors, the available reactivity may be increased by increasing the mass of the slug core). The maximum practical length of the slug core is not necessarily fixed at the present value of about eight inches but is limited by (1) the erosion of the can during slug insertion which increases (near the top) as the slug length is increased, (2) the dimensional stability of the slug in the pile (the warp or increase in projected diameter of the slug is approximately proportional to the square of the slug length) and (3) the weight of the individual slug core that can be routinely canned in the manual canning process.

The slugs are inspected for completeness of transformation by an ultrasonic technique that measures the average grain size, which is increased by the beta heat-treatment. Although untreated cores are unacceptable, experience with early triple dip canned slugs indicates that partially transformed slug cores are more unstable in-pile than those which are completely untransformed.

DECLASSIFIED

DECLASSIFIED

-804-

HW41060

After the transformation test, the uranium cores are vapor degreased in trichloroethylene and pickled in hot nitric acid. The vapor degreasing step removes machining oils and other foreign materials that inhibit uniform etching or which may be carried through pickling and inhibit wetting of the slug in the canning baths. The pickling operation removes the accumulated uranium oxide from the slug surface to facilitate wetting of the uranium in the first molten bath. Pickling also prepares the surface for visual inspection. The cores are rinsed and dried to delay reoxidation as much as possible and to assure that the duplex bath does not erupt due to introduction of moisture. Slugs with cracks, seams, laminations, or gross stringers of non-metallic impurities are rejected at the pickle inspection.

1.2 Preparation of aluminum jacketing components

Finished aluminum jacketing components are procured from commercial sources and are tested for conformance to dimensional and chemical composition. Tests are performed usually on representative samples. (See Chapter XIV). The dimensions of the aluminum can and cap are chosen to facilitate assembly of slug and to provide adequate jacketing of the finished slug. The composition of the alloy, which contains a minimum of 99.35 per cent aluminum (more pure than the "commercially pure" aluminum) is controlled to avoid reactivity losses due to high cross-section elements and to withstand the corrosive environment encountered in service. The adjustment of the iron-silicon ratio in the cap alloy to prevent surface cracking during welding is the only composition limit resulting from canning process requirements.

The aluminum can and cap surfaces are cleaned and etched to promote wetting by the Al-Si braze metal. Standard cleaning practice involves vapor degreasing followed by an alkaline detergent wash. This removes surface contaminants, particularly residual die lubricants and oils deposited from handling. The cleaned surfaces are then readily etched to remove the aluminum oxide film. A number of proprietary solutions

DECLASSIFIED

DECLASSIFIED

-805-

100000

and common acids may be used for etching with the qualification that the reaction does not form significant amounts of film following dissolution of the aluminum oxide. For deoxidation Diversey 514 is used, replacing phosphoric acid which was used extensively in the past. The differences in the quality of bonding or the weldability of the assemblies resulting from the use of different reagents is not as marked as in unbonded canning where the weldability of the assemblies is significantly affected.

The etched components are then dehydrated by rinsing in methanol and hot air dried. The lowest practical air temperatures and drying times are desirable to limit reoxidation.

1.3 Preparation of canning sleeves

A sleeve is required to protect the exterior of the slug can from erosion by Al-Si during its period of immersion in the canning bath. During this period, when the can is extremely soft, the sleeve also prevents the can from deforming. The sleeves are fabricated from ferrous materials because these materials are not readily attacked by the bath metal, have a sufficiently high thermal conductivity, are cheap, and are adaptable to most fabrication practices. Low carbon steels have been used extensively and limited tests have been made using the heat-resistant grades of Mehannite (alloy cast iron). The higher density ferrous materials are more satisfactory in that a smaller volume of material is required to sink the sleeve in the bath. Also, the less dense porous materials are more prone to carry moisture into the bath. Moisture entrained in sleeves will deform the slug can during the preheat cycle and also constitutes a potential safety hazard. Dimensional instability of the canning sleeve due to repeated thermal cycling is the major factor affecting the service life of the sleeves. The dimensions of the sleeves are critical in that tight sleeves may cause the can to buckle during preheat. Loose-fitting sleeves may permit Al-Si to seep into the annulus between can and sleeve and contaminate the finished slug exterior. The contour of the inside of the sleeve affects the size and shape of the finished slug assembly. Any surface treatment of the sleeves that leads to the

DECLASSIFIED

DECLASSIFIED

-806-

REF ID: A66000

deposit of materials that cannot be removed from the canned assembly during subsequent processing must be avoided.

Steel sleeves, which are first blued* upon receipt from the vendor, are normally processed by cleaning in a hot caustic solution to remove any aluminum or Al-Si picked up on the previous canning cycle. The cleaning is followed by rinsing in hot water, coating by immersion in a hot soap solution, and air drying. The slug can is inserted in the sleeve prior to being sent to the canning line.

1.4 Canning procedure

Two molten metal baths are required for the lead dip process: 1) the duplex bath, consisting of an Al-Si layer floated on a lead layer, and 2) the canning bath of Al-Si alone. The duplex bath serves to preheat the slug core and to wet the core surface with the brazing alloy. The slug core is immersed in the duplex bath and agitated within the lead layer until the uranium reaches the canning temperature. The agitation is continued as the slug is raised into and then out of the Al-Si layer.

The slug core is immersed in the lead primarily to heat the uranium to the brazing temperature. Vigorous agitation during this heating cycle maximizes the heating rate and also helps to wet the uranium surface. The lead interacts with the uranium and/or uranium oxide on the slug surface but the relative importance of this interaction is not yet known. Higher agitation rates increase the uniformity of the intermetallic layers, reduce impurity carryover, principally lead, to the canning bath, and tend to reduce hydrogen-induced porosity. In general, then, increased slug agitation has a beneficial effect.

As in the triple dip process, the compound layer is formed during core preparation in the first molten Al-Si and is not significantly altered during

* Bluing is a treatment for improving the corrosion resistance of ferrous alloys by subjecting the surface (initially free from scale) to the action of hot air, thus forming a thin blue film of oxide.

DECLASSIFIED

DECLASSIFIED

-807-

REF ID: A40000

the assembly operation. The compound layer is thinner and more ductile when lower temperatures and silicon concentrations prevail. Fewer fracture-susceptible bonds (as observed in subsequent process steps) are produced during normal canning by the lead dip process than by the triple dip method.

1.5 Canning bath

The canning bath consists of a hypoeutectic* alloy of aluminum and silicon (See Figure VIII - 5) in which the jacketing components are preheated and the slug parts assembled. The bath provides the majority of the brazing material in the assembly. As in triple dip canning, the silicon content and the bath temperature are held within a narrow range to facilitate assembly without incurring unnecessary erosion of the can wall.

The can-sleeve assembly is immersed in the canning bath with the open end about 1/4 in. above the bath surface for the preheat period. At the end of the preheat period, the unit is submerged in the bath to fill the can. The submerge period refers to the time the unit is under the bath surface prior to insertion of the slug core. Two generalized canning cycles have been used at HAPO for lead dip canning and are applicable to any canning scheme in which a preheated and prebrazed core is provided from another source. The difference between the two cycles is the length of the can-sleeve preheat and submerge periods. The original cycle had a can-sleeve preheat of about 45 seconds and a can-sleeve submerge of about 35 seconds. The "long preheat-short submerge" cycle which replaced the original cycle in mid-1955, has a nominal 60 second preheat period, followed by a 5-10 second submerge. The two cycles are somewhat peculiar in that not all combinations of preheat and submerge times within the broad limits for the two cycles are satisfactory.

*A hypoeutectic alloy of aluminum and silicon contains less silicon than the eutectic which occurs at 12.5 weight per cent silicon (HAPO data).

DECLASSIFIED

DECLASSIFIED

-808-

11/12/80

The following steps comprise the canning bath cycle:

1. Can-Sleeve Preheat
2. Can-Sleeve Submerge
3. Cap Preheat
4. Slug Wash and Insertion
5. Cap Insertion

The can-sleeve preheat raises the temperature of the can to about 510-540 C. During the submerge period the temperature is raised to approximately the ambient bath temperature. Erosion and wetting of the can then occurs. The temperature of the metal within the sleeve must be above the eutectic temperature of the Al-Si at the end of the submerge cycle to preclude the existence of solid aluminum crystals within the melt that may inhibit insertion of the core. The slug cap is preheated by direct immersion in the bath. When the cap has been heated, it is removed from the bath and the base of the cap is abraded on a transite block to break up any remaining surface film. The cap is then re-immersed in the bath and agitated to wet the surfaces before assembly of the fuel element.

To replace the Al-Si coating with the more pure Al-Si in the canning bath, the slug core (coming directly from the duplex bath) is immersed and lightly agitated in the canning bath prior to insertion in the submerged can. The cap is also inserted while the can is submerged. The assembled slug is then removed from the bath and water quenched.

The output of the canning line is limited by the canning bath cycle, specifically the time required to preheat components by immersion in the bath. Canning output would be limited by the duplex cycle (slug core preparation) if preheated jacketing components were supplied to the canning bath. The most important variable in normal canning is the temperature of the bath because it has the greatest effect on the thickness of the residual can wall; i. e., the thickness of the aluminum can wall that has not been penetrated

DECLASSIFIED

DECLASSIFIED

-809-

HW-40009

by the action of the Al-Si brazing medium. The canning temperature is a compromise between the lower temperatures, resulting in greater residual wall thickness, and the higher temperatures which allow the greater ease of assembly. Also, incomplete seating of the slug becomes more prevalent as the temperature of the bath is lowered. In practice, the bath temperature is raised a few degrees as the bath becomes more aluminum-rich through use (the silicon concentration is normally adjusted by alloy additions only once per shift - a through-put of about 1050 slugs). Temperature adjustments conveniently compensate for most factors affecting the ease of assembly, such as bath composition, bath fluidity, minor changes in slug core diameter and variation in temperature of component preheat. It should be noted that the slight temperature adjustments possible do not significantly affect the temperature reached by the aluminum components during the short preheat cycles, nor do they significantly affect wettability of these components.

The silicon concentration is normally held within narrow limits and at slightly higher concentrations than in the duplex bath. Hypereutectic compositions are not used because excess silicon promotes increased attack of the can. The lower limit of silicon concentration is regulated by the bath temperature in that the existence of solid primary aluminum crystals must be avoided, as stated previously. Since the temperatures of the canning bath are lower than for the duplex bath, the minimum silicon concentration must be higher (See Figure VIII - 5).

Other variables affecting wetting and erosion of the can are the size of the annulus between slug and can, the rate of slug insertion, the coaxiality of the components during insertion, and the efficiency of the can preheat. Prototype mechanical canning devices have shown some potential for increasing the residual wall of well-brazed assemblies. These devices permit preserving of the alignment during assembly and provide for can-sleeve assemblies preheated outside the bath to or slightly above the Al-Si eutectic temperature. The relative importance of these two

DECLASSIFIED

DECLASSIFIED

-810-

DECLASSIFIED

factors, however, has not been firmly established.

1.6 Impurities associated with lead dip canning

As in triple dip canning, dissolution of the canning equipment (usually made from type 304 stainless steel) in the molten metal baths results in minor iron, chromium, and nickel contamination. The maximum concentration of the contaminants is generally less than that accounted for by bath "drag out" and replacement or the solubility of the contaminating element. This indicates that the elements are reacting in the melt to form solids that may settle in the bath or accumulate in the surface dross.

The major impurities in the duplex bath consist of lead in the Al-Si layer and a heterogeneous dross of metal oxides and other compounds that accumulate in the lead Al-Si interface. Dross carryover, which results in particulate contamination of the braze and may prevent successful welding of the closure, is reduced by skimming the interface with a porous ladle every few hours. Lead in the Al-Si layer of the duplex bath is important only because it is the source of lead contamination in the canning bath.

Lead is the most important contaminant in the canning bath. Concentrations of lead greater than about 0.2% (the limit of solubility in aluminum) result in a peculiar defect in the weld bead of the finished slug assembly. This defect consists of silicon-rich spikes or pipes originating at the base of the fusion zone and extending toward or through the homogenized portion of the fusion zone to the surface. Although no direct evidence is available to show that these "Al-Si spikes" are deleterious during irradiation, they are limiting in that they may be confused with more serious weld defects at weld inspection. Lead buildup does not appear to be a significant factor in operating expense, since control of the slug core surface, agitation rate in the duplex, etc., mitigate lead carryover and permit reasonable bath life.

Use of alloy compounds to jacket the dip-canned slugs could limit the

DECLASSIFIED

DECLASSIFIED

-811-

HW-40000

flexibility of the process insofar as bath life is concerned. Most of the aluminum alloys under investigation, however, have low alloy contents (about 1% or less) and should be satisfactory with small adjustments of bath temperature and silicon concentrations. Re-cycling of scrap from the slug facing operation (the usual practice when canning high purity alloy components) may not, however, be desirable.

1.7 Slug quench

The slug assembly and sleeve are water quenched. This cools the assembly so the sleeve may be removed and the slug may be handled in the finishing line. An immediate, rapid quench has some marginal advantages in that any continuing erosion of the can by the braze material is terminated. The components are resealed prior to quenching and held in place throughout cooling by axially applied pressure. This reduces non-seating of the slug and cap to a minimum.

1.8 Slug facing

The canned slug is faced to remove the excess aluminum cap and can and the Al-Si on the exterior of the assembly. The slug must be faced square (except where interlocking end contours are used) to mitigate slug cocking in-pile. In addition, the slug must be smoothly and cleanly cut to facilitate welding. The slug is faced without lubricant so the faced assemblies may be welded without intermediate cleaning steps.

1.9 Welding

The slug is welded to improve the integrity of the brazed closure and to reduce the silicon concentration at the slug exterior by mixing the braze layer with the cap and can alloy. The welding operation is recognized through years of experience to constitute an effective test for closure quality. Sub-surface defects and impurities in the top of the closure zone (braze layer between cap and can) usually result in visible surface imperfections in the finished weld bead.

DECLASSIFIED

DECLASSIFIED

-812-

HP 1000

Inert-arc welding is used without the addition of filler metal. Argon appears to be superior to helium for the slug welding application.

1.10 Non-destructive tests of canned assembly

Slugs have been tested for completeness of bonding using the frost test* or an ultrasonic bond test unit. The ultrasonic test is more sensitive and makes a more accurate delineation of the bond defects. It replaced the frost test method in March of 1956. Although the degree of unbonding that can be tolerated in-pile has not been defined, the maximum size of unbond considered acceptable is one centimeter in circumferential length. In practice the degree of unbonding (size of the unbonded area) has been controlled to original limits that were based on the possibility of increased corrosion due to the non-uniform surface temperature produced by the unbonded area. The specific slug powers now prevalent exceed those used in the original calculations by a factor of two to three. However, the original limit has been retained, somewhat arbitrarily, since slugs produced at this level have been irradiated without incurring a high rupture rate. Also, a rejection rate based on this limit is economically practical for production.

Generally, the braze layer has been more porous in lead dip canned slugs than in triple dip canned slugs. Most of this porosity has been attributed to the gas emanating from the uranium core (outgassing) during the canning cycle. The gas was determined to be essentially hydrogen which is in the uranium originally and/or is built up in the uranium during beta heat treating (see Chapter IX). Every effort has been expended to determine the sources of hydrogen contamination so adequate control might be exercised.

*In frost testing the slugs are coated with acenaphthene, a waxy hydrocarbon with a melting point of about 92 C. The slugs are passed through a high frequency induction coil. About 90% of the heat is generated in the can and braze layer. Local melting of the wax is indicative that a bond defect has prevented this heat from flowing into uranium core which in this case acts as a heat sink.

DECLASSIFIED

DECLASSIFIED

-813-

HW-100001

1.11 Penetration test

An eddy current device is used to ensure that all acceptable slugs have sufficient residual can wall to withstand the corrosion conditions in-pile. Pile corrosion limits (on service life or allowable exposure) are based on a minimum of 20 mils residual can wall at any point. This limit is revised upward as canning process improvements permit.

1.12 Canned slug etch

The finished slug assemblies are etched to remove from the slug surfaces any foreign materials which may initiate localized corrosion in service. Etching also facilitates the formation of a continuous protective film during the autoclave test. The slugs are vapor degreased prior to etching to assure a uniform etch. Hot nitric acid is used for etching as any Al-Si on the slug surface is darkened by the reaction and most of the heavy metal contaminants characteristic of the canning process are dissolved. About 1/2 mil of aluminum is normally removed from the surface of the assembly by the etch.

1.13 Autoclaving

Slugs are autoclaved for 40 hours at about 165 C in either steam or water. Defective closures or jackets cause the slugs to rupture in the autoclave, if the defects are continuous from exterior surface to slug core. Failure is due to the rapid attack of the core and the increased volume of the reaction products. Defective slugs are subsequently discarded during the final visual inspection. Slugs with closure defects tend to rupture early in the autoclave cycle, while the majority of side wall failures require longer exposure. The use of non-destructive test apparatus and improved quality control have markedly decreased the autoclave failures in recent years.

Although absence of corrosive attack during autoclaving cannot be presumed to ensure freedom from localized corrosion in-pile, many surface conditions are made visible through corrosive attack. Slugs so affected are rejected and the related process difficulties are remedied.

DECLASSIFIED

DECLASSIFIED

-814-

1.14 Final inspection

After autoclaving, the slugs are inspected to detect and reject those slugs that (1) failed the autoclave test (2) are dimensionally unsuitable and/or (3) have excessive surface damage or closure or sidewall abnormalities. A tube gauge is used for the dimensional inspection. The tube gauge inspection eliminates any oversize slugs that may restrict water flow through the process tubes. The test provides a measure of the combined effects of weld overhand, canned slug warp, and slug diameter. No test for minimum size is made since this is satisfactorily controlled by the processing conditions.

The slugs are visually inspected to detect surface abnormalities consisting of weld defects, defective cans or caps, embedded foreign materials, areas of localized corrosion initiated during autoclaving, and mechanical damage. Defective jacketing, the presence of foreign materials, or active corrosion areas increase the possibility of slug failure in the pile.

Mechanical damage limits are based on service life of the slug as limited by general corrosion and are set to preclude acceptance of slugs with more extensive surface mars than those caused by normal charging procedures.

The reactivity of production metal is estimated from test pile measurements of slugs sampled from each production lot (see Chapter XVI). In addition to maintaining minimum acceptable reactivity, lot shipments to the areas are arranged to avoid accumulation of sub-average lots in any one pile.

1.15 Slug storage and shipping

Slugs are handled and stored under conditions that minimize the possibility of reducing slug quality. The three most frequent problems are corrosion initiated by storage in wet containers, pick-up of foreign materials due to lack of cleanliness, and mechanical damage from rough handling.

DECLASSIFIED

DECLASSIFIED

-815-

REF ID: A60000

2. Triple Dip Process

The triple dip process was the standard procedure for canning uranium at HAPO until 1954, when it was replaced by the lead dip process*.

Early in project history, the uranium cores were machined from rods extruded in the gamma phase and the canning process had negligible effect on the metallurgical structure of these extruded slug cores. In 1948, to reduce localized surface distortion (bumping) which occurred during irradiation, alpha rolling replaced gamma extrusion as the method of uranium fabrication. The bronze-tin portion of the triple dip cycle was then further developed to provide controlled beta-phase heat-treatment.

The following discussion of the triple dip process will be confined to the canning steps. Component preparation steps and the canned assembly finishing and testing operations are identical to those described for the lead dip process except for the additional core inspection steps required for the heat treated core used for lead dip canning.

Triple dip canning is carried out in four metal baths. The pickled slug core is introduced into the bronze bath and subsequently into the tin bath, the Al-Si dip bath, and the Al-Si canning bath. The can-sleeve assembly and the slug cap are introduced directly into the canning bath (Figure VIII-6).

The bronze bath consists of a melt of 47 parts copper, 53 parts tin covered with a layer of chloride flux (a eutectic of BaCl_2 , KCl , and NaCl). The bath is maintained at a temperature range which corresponds to the upper portion of the beta phase region for uranium to effect the desired heat-treatment. The maximum temperature is set to preclude heating the slug cores into the gamma phase, which would result in excessive grain growth. The minimum temperature is set to prevent freezing out the copper constituent. The slugs are agitated in the bronze until all of the uranium is in the beta phase. The slugs are then agitated between the bronze and flux layers to promote

*The triple dip process is still in use at the DuPont-operated Savannah River Plant.

DECLASSIFIED

DECLASSIFIED

-816-

HY 10000

complete and uniform wetting of the uranium surface by the bronze.

The tin bath is made up of tin with a small amount of aluminum added to mitigate surface oxidation. The bronze-treated slug is immersed in the tin bath, which is maintained at 600 C, the approximate temperature of the subsequent assembly operation. This completes the heat treatment by quenching the uranium into the stable alpha phase. The slug core is agitated in the tin bath to reduce the amount of adhering bronze by dilution and to reduce the carryover of bronze bath flux to the Al-Si baths.

The slug cores are then centrifuged to remove as much metal as possible that has not alloyed with the uranium surface.

The Al-Si dip bath completes the removal of excess tinning constituents and removes most of the metal oxides or other surface contaminants, some of which are picked up in the centrifuge. The formation of the intermetallic bonding (compound) layers on the uranium surface is essentially completed at this time. The temperature of the bath, the silicon concentration, and the degree of slug agitation at this point control the final characteristics of compound layers. Higher temperatures and silicon concentrations and more vigorous agitation tend to increase the thickness and reduce the ductility of the compound layers.

The slug components are assembled in a canning bath of hypoeutectic alloy of aluminum and silicon (slightly less silicon than eutectic). The canning bath preheats the jacketing components and supplies the balance of the brazing material for the canned assembly. The silicon concentration is critical because free silicon in a hypereutectic (slightly more silicon than eutectic) alloy may promote excessive and non-uniform dissolution of the slug can. Too little silicon will permit solid aluminum crystals to form in the melt which may prevent full seating of the components during assembly.

The completed slug assembly is water-quenched and removed from the canning sleeve. The preparation of the jacketing components, the assembly

DECLASSIFIED

DECLASSIFIED

-817-

HW-40000

of slug in the canning bath, and all subsequent finishing operations are identical for both the triple dip and lead dip process.

Bath impurities associated with triple dip processing consist of metals, their oxides, or flux constituents. The impurities originate from dissolution of the processing equipment in the metal baths, dissolution of the slug components, and carryover of the constituents of any preceding bath.

Uranium is the primary impurity in the bronze bath where it either settles to the bottom of the crucible or combines with the spent portion of the flux layer. The flux is normally bailed and solidified at frequent intervals. The uranium-rich portion of solidified flux which contains up to 10 per cent uranium by weight is separated for recovery offsite, and the balance of the flux is reused.

Copper is the primary impurity picked up in the tin bath. The copper concentration of the tin bath is periodically reduced by a recovery procedure in which solid copper-rich constituents are formed by lowering the temperature of the melt. They are removed by straining the bath metal with a perforated ladle.

Tin is the primary contaminant of the two Al-Si baths. No economic method of removing tin from Al-Si was available during the period of triple dip operation. Replacement of tin-contaminated Al-Si was reduced as much as possible by charging virgin Al-Si in the canning bath and using the slightly contaminated canning bath metal for the Al-Si dip bath additions. Irradiation of test quantities of slugs canned in Al-Si with up to two per cent tin (process limit 0.3 per cent) was completed and satisfactory slug performance observed after the lead dip process was instituted.

Spent flux is sometimes carried over on the slug core surface in the form of large firmly adhering patches, but no irradiation difficulties appear to have been directly associated with these areas. The presence of minute quantities of flux in that portion of the braze layer that is fused during welding, however, generally results in an imperfect weldment.

DECLASSIFIED

DECLASSIFIED

B. HOT PRESS CANNING PROCESS

The hot press canning process⁽⁶⁾, originally developed for uranium slug cores, was adapted for the canning of U-Al alloy slug cores in aluminum jacketing components in 1954. A slug with a diffusion-bonded jacket is produced that has better heat transfer characteristics than the assembly canned by the unbonded "B" or "C" canning process (see Part C of this chapter).

The following types of slug cores have been canned in production quantities by the hot press canning process:

- a. "C" alloy slug cores: About 10,500 six-inch "C" slug cores, U-Al alloy containing 4.5% enriched uranium were canned from Jan. 1955 to May 1956.* "C" slugs are used for overall pile enrichment, to obtain pile flattening, to increase production through better heat distribution, and to augment reactivity.
- b. "J" alloy slug cores: About 2500 eight-inch "J" slug cores, U-Al alloy containing 7.5% enriched uranium, were canned from Jan. 1954 to Sept. 1954. "J" slugs are used for fuel in large isotope production such as for tritium or U-233.
- c. Li-Al alloy slug cores: Production test quantities of four-inch Li-Al alloy cores containing about 3.5% natural lithium for tritium production were also canned by this process.

The flowsheet of the hot press canning process ("HPA" canning process) used for "C" and "J" slug core canning shown in Figure VIII - 7. The basic canning steps are: (1) inspection and surface preparation of the slug core and the jacketing components; (2) assembly of the components; (3) sizing of slug assembly; (4) preparation of the sized assembly; (5) pressing; (6) finishing of the pressed assembly; (7) bond testing; and, (8) final inspection. Diagrams of the slug in the intermediate and finished states are shown in Figure VIII - 8.

*All of the "C" alloy slugs canned since Feb. 1955 have been canned with "Tru-line" interlocking end contours to reduce slug cocking in the pile.

DECLASSIFIED

DECLASSIFIED

-819-

HW-40000

1. Preparation of Slug Core and Jacketing Components

The finished slug cores are procured from Oak Ridge National Laboratory. They are inspected for conformance to dimensional tolerances and for fabrication defects. (1), (5) Cores with uniform diameter, i. e., with no taper, are required to insure that the aluminum can is pressed firmly to the core and the air is completely removed during the sizing operation. The slug cores are also inspected for inclusions, seams, and voids that may prevent bonding of the slug core to the aluminum jacket. Both cast and extruded alloy cores have been hot press canned. Higher canning yields can be achieved using extruded cores. The cast cores frequently contain large numbers of small internal gas voids that outgas during hot-press canning and cause unbonded areas in the finished assemblies.

The aluminum cans and 0.4-inch wafer caps used to jacket the slug core are inspected before use. The inspection is made to insure that the dimensions are satisfactory and that the aluminum components do not contain defects that may either allow pile water to penetrate the slug jacket or initiate localized corrosion*. The aluminum cans are expanded to an internal diameter of about 1.360 in. to allow insertion of the slug core without galling the slug components. The aluminum cans and wafer caps are fully annealed to facilitate sizing the slug assembly.

The surfaces of the aluminum jacketing components and the slug cores are prepared by:

- (1) Vapor Degreasing - to remove lubricants used in the manufacture of the components and any oily contaminants from subsequent handling.
- (2) Etching in 5 per cent NaOH for two minutes - a step that produces controlled roughening of the surface**. Roughening of the surface promotes formation of the diffusion bond and increases the strength of the bond formed.

* The M329 and M261 alloys that contain a minimum of 99.3% aluminum are used. These are the same alloys used for jacketing dip canned uranium cores.

** During development of the process, the component surfaces were roughened using an abrasive cleansing powder.

DECLASSIFIED

DECLASSIFIED

-820-

HW-40000

- (3) Water rinsing.
- (4) Deoxidizing in Diversey 514, a commercial deoxidizing solution, to remove the aluminum oxide film.
- (5) Water rinsing.
- (6) Dehydration with methanol.
- (7) Forced hot air drying.

The drying time and temperature (40 C, maximum) are closely controlled to limit reoxidation; also, the prepared components are pressed within 45 minutes after the drying operation.

2. Assembly of the Components

The slug core is firmly seated in the can and the wafer cap is firmly seated against the top of the core. The exterior of the can is lubricated with a water soluble wax lubricant prior to the sizing operation to prevent galling and scratching of the can wall.

3. Sizing of the Slug Assembly

The slug assembly is die-sized to assure good contact between the can wall and core. The die size is chosen, based on the measurements of each assembly to effect a reduction of 5-10 mils in the assembly diameter. The gap produced between the core and can wall by this method is less than 0.0001 inches. An axial pressure of 4000 to 4500 pounds is exerted on the slug assembly during passage through the die to produce and maintain complete seating of the core and wafer cap in the can.

4. Preparation of the Sized Assembly

After the sizing operation, the excess can wall is trimmed flush with the top of the wafer cap. The surface of the can wall is treated with a dry, powdered mica to prevent the can from adhering to the die during the hot pressing operation. The mica adheres to the can surface because of a thin residual layer of lubricating wax remaining on the can surface after sizing.

DECLASSIFIED

DECLASSIFIED

-821-

HW-40009

5. Pressing

The hot-pressing operation bonds the can, wafer cap, and core into one integral assembly. The sized slug assembly is pressed in a heated die assembly consisting of a die housing, a solid insert which forms a cylinder for holding the slug during pressing, and the cylindrical end punches (See Figure VIII - 9). The exterior surface of the insert is coated with Aqua-Dag to prevent the insert from sticking in the die housing. The insert, punch, and plug are pre-heated to 600-625 C in an auxiliary die housing prior to the hot pressing operation. The heated insert is seated in the die housing with about 12 tons total force. After a delay of about 45 seconds, the end punches and slug assembly are inserted and eleven tons total force is applied for 10 to 13 minutes. (When a cold-sized slug assembly is inserted into the hot die, the can wall expands away from the core and wafer cap due to thermal expansion, allowing air to be drawn into the assembly. If there is a delay before inserting and applying pressure to the top punch, the core and wafer cap will heat sufficiently to expand and close the annular opening, thus forcing the air from the assembly.) During development of the pressing technique, the size of annulus initially existing between the sized assembly and the die appeared critical in that bonding appeared to improve if this clearance was minimized. Tests during C-slug production indicate a much wider permissible annulus range. This has permitted the hot-press canning of cores 10 mils less in diameter than standard (originally procured for unbonded canning) and the extended use of the dies. (The internal diameter of the dies increased with use because of oxidation.) Differences of up to 20 mils between the diameter of the sized assembly and the internal diameter of the die insert have not affected the quality of the slugs produced. The temperature of the die assembly during hot pressing is maintained at 600 to 625 C. After pressing, the insert, punch, plug, and slug assembly are removed from the die housing and quenched in hot water.

DECLASSIFIED

DECLASSIFIED

-822-

HW-40000

6. Finishing of the Pressed Assembly

The slugs are cleaned in Alcoa R-3 (a mixture of sulphuric and chromic acid) at 80 C for 45 minutes to remove the parting material and carbon that has adhered to the can surface. The extruded portion of the can-cap closure is then removed by machining.

The closure between the wafer cap and can wall is inert-arc fusion welded to test the cap-to-can bond. An unbonded closure will become apparent as a void, a pinhole, or an area having the can wall melted down and pulled away from the cap. Two weld passes over the closure zone (140 amperes) are used for this test.

7. Bond Testing

The slugs are tested for unbonded areas using ultrasonic bond test equipment. The ultrasonic test indicates an unbonded condition only if there is a gap between the can and core. Weak attachments will not be detected. The test will indicate, however, large defects in the can wall and core defects near the slug core surface.

Destructive examination of hot pressed "C" and "J" alloy slugs has shown that ultrasonically-detectable unbonded areas are usually accompanied by larger, adjacent areas of weak can-core attachment - usually an oxide film attachment. Slugs that do not have ultrasonically detectable unbonded areas have either a true metallurgical can-core bond or a moderately strong can-core attachment (these are believed to be partially oxide-bonded, partially metallurgically bonded). The present inspection is conservative, being based on the assumption that the weakly-bonded areas have poor heat transfer coefficients and, in addition, may become completely unbonded during irradiation. The equipment sensitivity and rejection limit is set to preclude the possibility of accepting slugs with large weakly-bonded areas by the expedient of rejecting all slugs with completely unbonded areas of any size. Slugs that have core defects that can be distinguished by using an oscilloscope in conjunction with the ultrasonic bond tester are not rejected if no unbonded areas are found.

DECLASSIFIED

DECLASSIFIED

-823-

HW 40000

8. Final Inspection

The slugs are inspected for marred surfaces, slug warp, and imbedded material in the can or cap prior to final acceptance and storage for pile use. All reject slugs, both bare and canned are returned to ORNL for recovery.

9. Nuclear Safety⁽⁷⁾

The handling and storage of "C" and "J" slugs are closely controlled throughout processing to prevent a chain reaction. The number of slugs required to initiate a chain reaction varies with such conditions as slug arrangement, the presence of a moderator such as wood or water, and the presence of other fissionable material and reflectors such as natural or enriched uranium. For example: if the slugs are not surrounded by a moderator, the maximum number of slugs must be limited to 400 in any cubical volume less than six feet on an edge; if the slugs are submerged in water, surrounded by wood, or surrounded by other hydrogenous moderators, the maximum number of slugs must be limited to 81 in any cubical volume less than 4 feet on an edge, unless the slug spacing is controlled. In practice, the slug spacing is controlled to permit less restrictive handling procedures by storing and handling the slugs in 100-hole wood shipping containers, 66-hole wood cart pallets, and 54-hole "Bird Cages" that are stacked in specified arrays.

C. UNBONDED CANNING PROCESSES

Two canning processes have been used at HAPO for jacketing slug cores with aluminum without effecting a bond between the jacketing component and the core. The two processes, the "B" process and the "C" process, are similar except for the sizing of the slug assembly and the manner of welding and inspecting the slug closure. In general, the inexpensive unbonded jacketing techniques are used when (1) the unbonded assembly is capable of dissipating the heat generated in core material, (2) the core is relatively resistant to corrosion by pile-temperature water, and (3) the heat-generating core

DECLASSIFIED

DECLASSIFIED

-824-

HW-40000

materials are relatively dimensionally stable. Unbonded canning costs are lower than dip braze canning costs even though production of unbonded slugs has been on a small scale and has been intermittent.

The types of slug cores that have been canned as unbonded assemblies in production quantities are:

- a. Bismuth cores: Six-inch bismuth cores used primarily for the production of polonium were canned by the "B" Process until production was discontinued in 1952.
- b. Lead-Cadmium alloy cores: Six-inch Pb-Cd alloy cores, containing 3 to 4% Cd, used mainly for pile control during startup, are still being canned by the "B" process.
- c. Lithium-aluminum cores: Four-inch Li-Al alloy cores, containing 3.5% natural lithium, used for the production of tritium were canned from 1949 to 1951 and in 1953 and 1954. The "C" process was used for the latter program.
- d. Thorium cores: Six-inch thorium cores used primarily for the production of U-233 were canned from 1951 to October, 1955. "C" process canning was used starting in 1954.
- e. "C" slug cores: Six-inch "C" slug cores, U-Al alloy containing 4.5% enriched uranium, were canned from 1952 to 1955. "C" slugs are currently canned by the "HPA" Process (See Section B). "C" slugs are used for pile enrichment, to obtain pile flattening, to increase production through better heat distribution, and to augment reactivity.
- f. "J" slug cores: Eight-inch "J" slug cores, U-Al alloy containing 7.5% enriched uranium, were canned in 1953 and 1954. "J" slugs were used for fuel material in large scale isotope production such as tritium and U-233 production. Small quantities of bonded "J" slugs were subsequently canned by the "HPA" process.

The flowsheet of the "B" process⁽³⁾ as used for the production of Pb-Cd dummies is shown in Figure VIII - 10. The "C" process flowsheet is

DECLASSIFIED

DECLASSIFIED

-825-

HW-40000

shown in Figure VIII - 11. The discussion of unbonded canning will follow the "C" process steps; (1) preparation and inspection of the slug core, (2) preparation and inspection of the jacketing components, (3) component assembly, (4) sizing of the slug assembly, (5) finishing of the slug assembly; and, (6) inspection of the canned assembly.

1. Preparation and Inspection of the Slug Core

All slug cores except the Li-Al alloy core are received in the finished condition from the vendor. The Li-Al alloy cores are machined without lubricant from rod sections immediately prior to canning, a procedure required for minimizing the hydrogen content of the finished canned slug*.

The machining operation removes hydrogen-bearing corrosion products from the alloy, leaving a clean surface, which obviates exposure to hydrogenous cleaning agents. Other types of slug cores are prepared by vapor degreasing, washing in a detergent solution, rinsing, and dehydration in methanol followed by air drying. All cores are inspected for conformance to dimensional standards.^{(1) (5)} Slugs of uniform diameter, i. e., no taper, are needed to ensure that sizing will minimize the air gap between the can and the core. Slugs with visible fabrication defects or foreign contaminants are rejected.

2. Preparation and Inspection of the Jacketing Components

The aluminum can and wafer caps are inspected for conformance to dimensional standards and for fabrication defects. The aluminum cans and the 1/4 in. inner wafer**caps are fully annealed prior to surface preparation to promote a more intimate contact between the core and the jacket during sizing. Annealing of the 1/10 in. outer cap, however, is not necessary and

*Hydrogen contents less than 10 ppm are specified for obtaining the desired tritium (product) purities. Process cleanliness is also highly important. Contamination with foreign materials, particularly heavy metals, may seriously hamper extraction of the product because the extraction facilities were not designed to handle slugs with large amounts of gamma activity.

**Alloys containing a minimum of 99.3% aluminum are used.

DECLASSIFIED

DECLASSIFIED

-826-

FW-40080

a more satisfactory machined surface is produced on the unannealed wafer when the sized slug assembly is faced.

The surfaces of the components are prepared by (1) vapor degreasing, (2) washing in detergent, (3) deoxidation in a solution of Diversey 514, a commercial etching compound, (4) rinsing, (5) dehydration in methanol, and (6) hot air drying.

The temperature of the air blast and the drying time are minimized and the components are assembled within two hours to limit reoxidation. Inadequate component preparation affects the weldability of the unbonded assembly much more than it affects that of the dip canned slugs (see Section A).

3. Component Assembly

The slug core is firmly seated in the can, and the wafer caps are firmly seated against the top of the core. When thorium, "C", and "J" slug cores are canned, a 1/4 in. wafer cap is seated next to the core and a 1/10 in. wafer cap is used for the exterior cap (See Figure VIII - 12). Other slug cores are canned using two or three 1/10 in. wafer caps*. (The thicker wafer caps are used on cores having moderate heat generation to prevent local end-cap boiling during pile irradiation). At least two wafer caps are required for producing a weldable assembly. The extra cap inhibits transfer of heat from the weld into the core and decreases the amount of heat required to maintain a molten puddle under the arc. This decreases overheating of the assembly, which may distort the assembly or lead to weld porosity due to outgassing of the assembly.

4. Sizing of the Slug Assembly

The sizing operation ensures adequate heat transfer between the jacket and the slug core by minimizing the air gap. This also tends to localize any corrosion of the slug core and disruption of the slug jacket if the jacket is penetrated in-pile.

*When three wafers are used, the top cap may be removed by facing if a bad weld is obtained, and the slug re-welded at the second cap.

DECLASSIFIED

DECLASSIFIED

-827-

HW-40000

The slug assembly is prepared for sizing by applying a thin coat of water-soluble drawing wax. The lubricated assembly is then sized to reduce the can-core gap to less than 0.0001 inches. In practice the gap is controlled by using a die with an internal diameter 3-5 mils less than the sum of the diametral measurements of the can and core. About 2000 pounds of axial pressure is applied before and throughout the sizing operation to ensure seating of the components and to reduce the tendency of the assembly to warp.

After sizing, the lubricant is removed by hot water or steam. Organic degreasers are not used since unsatisfactory welds may result from entrapped degreasing vapors being volatilized during the welding operation.

5. Finishing of the Slug Assembly

The sized assembly is faced to remove the excess can wall and to square the end of the assembly. The closure between the wafer cap and can wall is made by an inert-arc fusion weld. Since the latter part of 1954, all slugs canned by the "C" process have been inert-arc fusion welded with high purity 2S aluminum filler wire added to the weld bead (GE "Fillerweld"). This produces a thicker weld than the ordinary inert-arc fusion welding process, giving the slug as much jacketing protection in the closure zone as in the side wall. The inert arc technique used previously without filler metal produced only about 20-25 mils of sound weld deposit which made the closure the weakest portion of the slug assembly; i. e., the thinnest portion of the jacket.

6. Inspection of the Canned Assembly

The welds are inspected for visually-detectable defects such as porosity, cracks, impurities, and non-uniformity indicative of underlying abnormalities. The weld width is checked to ensure adequate fusion of the wafer cap to the can wall. The weld overhang is checked to prevent unnecessary restriction of water flow in the pile process tubes.

DECLASSIFIED

DECLASSIFIED

-828-

AW-40000

All slugs canned by the "B" and "C" canning processes are bubble tested for weld defects. The bubble test consists of submerging the slug assembly in odorless kerosene under vacuum and detecting weld defects by the air bubbles that are emitted from cracks, voids, and porosities in the weld bead. After bubble testing the slug assemblies are vapor degreased to remove the kerosene from the slug surface.

All slugs canned by the "C" process have the weld inspected by radiographic examination as well as by the bubble test. Radiography will detect sub-surface weld defects such as porosity, voids, and insufficient weld fusion that cannot be detected by any other method.

Canned thorium slugs are the only slugs canned by the "B" and "C" processes which are tested for unsound jackets by autoclaving in steam or water at 165 to 180 C for 40 hours, because thorium is the only core material that will react sufficiently with water or steam. If there is a defect in the jacket that allows steam or water to come in contact with the thorium core, the reaction products formed deform or break the jacket and the assembly can be rejected at the final inspection station.

The dimensions of the canned assemblies are checked, and a visual examination of the surfaces for surface damage, foreign material, and corrosive pitting is made prior to final acceptance.

Cores recovered from canning rejects are re-canned, if they meet the original requirements for surface condition, warp, and diameter variation, and if the sized assembly after recanning will be not less than 1.418 inches in diameter.

Throughout the unbonded canning of "C" and "J" slugs the handling, storage, and transfer of "C" and "J" slugs is closely controlled to prevent a chain reaction from occurring. (See Part B-9, "HPA" Canning).

DECLASSIFIED

DECLASSIFIED

HW-40000

D. REFERENCES

- (1) HW-19156, Specifications, Acceptance and Sampling Procedures for Essential Materials.
- (2) HW-22556, Manufacturing Department Process Standards, Metal Preparation Section.
- (3) HW-23403, Process Specifications, "B" Canning Process.
- (4) HW-30146, Process Specifications, "C" Canning Process.
- (5) HW-30263, Acceptance Specifications for HAPO Slug Cores.
- (6) HW-32005, Process Specifications "HPA" Canning Process.
- (7) HW-37052, Nuclear Safety Specifications for Fuel Element Manufacturing Processes.

DECLASSIFIED

E. LIST OF FIGURES

- Figure VIII-1 Flowsheet of Lead Dip Canning Process - Preparation of Slug Components and Canning Sleeve.
- Figure VIII-2 Flowsheet of Lead Dip Canning Process - Dip Braze Canning.
- Figure VIII-3 Flowsheet of Lead Dip Canning Process - Canned Assembly Finishing and Testing.
- Figure VIII-4 Slug End After Canning, Facing, and Welding.
- Figure VIII-5 Aluminum-Silicon Equilibrium Diagram.
- Figure VIII-6 Flowsheet of Triple Dip Canning Process.
- Figure VIII-7 Flowsheet of Hot Press Canning Process.
- Figure VIII-8 Diagram of Slug After the Intermediate and Final Steps of the Hot Pressing Operation.
- Figure VIII-9 The Hot Press Unit with Assembled Slug in Place
- Figure VIII-10 Flowsheet of "B" Process for Unbonded Canning.
- Figure VIII-11 Flowsheet of "C" Process for Unbonded Canning.
- Figure VIII-12 Cross Section of Unbonded Canned Slug.

DECLASSIFIED

HW 40000

FIGURE VIII-1

FLOW SHEET OF LEAD-DIP CANNING PROCESS-PREPARATION OF SLUG COMPONENTS AND CANNING SLEEVE

DECLASSIFIED

DECLASSIFIED

HW 40000

FIGURE VIII-2

FLOW SHEET OF LEAD DIP CANNING PROCESS-- DIP BRAZE CANNING

DECLASSIFIED

DECLASSIFIED

FIGURE VIII-3

FLOW SHEET OF LEAD DIP CANNING PROCESS - CANNED ASSEMBLY
FINISHING AND TESTING

DECLASSIFIED

UNCLASSIFIED

AFTER QUENCHING

AFTER FACING

AFTER WELDING

FIGURE VIII-4

SLUG END AFTER CANNING, FACING, AND WELDING

UNCLASSIFIED

HW-40000

DECLASSIFIED

AL-SI EQUILIBRIUM DIAGRAM (HAPO data)

FIGURE VIII-5

DECLASSIFIED

AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910

301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

4 of 6

DECLASSIFIED

HW-40000

FIGURE VIII-6 FLOW SHEET OF TRIPLE DIP CANNING PROCEDURE

DECLASSIFIED

FIGURE VIII-7

FLOW SHEET OF HOT PRESS CANNING PROCESS

DECLASSIFIED

DECLASSIFIED

FIGURE VIII-8

DIAGRAM OF SLUG AFTER THE INTERMEDIATE AND FINAL STEPS OF THE HOT PRESS CANNING OPERATION

HW-40000

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE VIII-9 HOT PRESS UNIT WITH ASSEMBLED SLUG IN PLACE

DECLASSIFIED

DECLASSIFIED

FIGURE VIII-10

FLOW SHEET OF "B" PROCESS FOR UNBONDED CANNING

DECLASSIFIED

DECLASSIFIED

HW-40000

FIGURE VIII-11

FLOW SHEET OF "C" PROCESS FOR UNBONDED CANNING

DECLASSIFIED

DECLASSIFIED

FIGURE VIII-12

CROSS SECTION OF UNBONDED CANNED SLUG

DECLASSIFIED

HW-40000

DECLASSIFIED

PART III: PROCESS (Cont.)
CHAPTER IX; AUXILIARY PROCESSES

<u>CONTENTS</u>	<u>Page No.</u>
A. THE RECOVERY PROCESSES	902
1. Slug Recovery	902
2. Uranium Recovery	903
3. Aluminum and Al-Si Scrap Recovery	903
B. SALT BATH OUTGASSING	904

DECLASSIFIED

DECLASSIFIED

A. THE RECOVERY PROCESSES

1. Slug Recovery

Uranium slug cores are recovered from rejected Al-Si bonded slug assemblies by chemical dissolution of the aluminum jacketing, Al-Si braze layer, and the intermetallic compounds formed at the uranium surface. After recovery, those cores which meet the minimum weight and dimensional requirements are accumulated and sent to canning as recovered lots. (Slug cores, fabricated from standard material, which have been through the recovery process are marked and categorized as "Z" lot material.) Recovery and re-canning of the slug cores is limited to about three cycles because an appreciable amount of uranium is lost during each canning and each recovery cycle; hence, the pieces eventually fail to meet minimum weight and dimensional requirements. When these requirements are not met the cores are returned to the suppliers as scrap for reprocessing.

A flow sheet for the recovery cycle is shown in Figure IX-1. The jacketing and bonding layers are removed from the slug cores by immersion in hot sodium hydroxide solutions*. Most of the slug can, slug cap, and Al-Si is removed in about 1-1/2 hours in the first stripping tank solution, which contains 17% sodium hydroxide and 13% sodium nitrate by weight. Sodium hydroxide is the active agent; sodium nitrate is added to eliminate the free hydrogen which is evolved from the aluminum-sodium hydroxide reaction (the hydrogen is combined to form ammonia). The remaining jacketing material and the intermetallic compounds on the uranium surface are removed in a second stripping bath (the treating tank) which contains a 50% sodium hydroxide solution. Approximately 1-1/2 hours immersion

*The original process used at HAPO consisted of immersion in nitrated sodium hydroxide to remove the aluminum and the aluminum-silicon alloy and immersion in a hydrofluoric acid bath to remove the uranium bearing compound layers. The hydrofluoric acid bath was replaced by a concentrated sodium hydroxide solution to avoid the operating hazards and the excessive equipment maintenance associated with the use of hydrofluoric acid.

DECLASSIFIED

DECLASSIFIED

at 140 to 170° C is required in the second stripping bath.

The slug cores are then thoroughly rinsed and air dried. The recovered slug cores are inspected to ensure that all jacketing and bonding constituents have been removed from the core and that each core meets the minimum weight requirements.

2. Uranium Recovery

A second phase of the slug recovery operation is the recovery of uranium from the 50% caustic treating solution (see Figure IX-1). Spent nitric acid from the slug pickling tanks (canning process) is used to neutralize the treating solution. In this way the uranium is recovered from the slug pickling acids as well as the treating tank solutions. The caustic solution from the treating tank is pumped to the Caustic Receiving and Feed Tank. At infrequent intervals the sediment from the Rinse Tank is also transferred. Water is added to reduce the caustic concentration in the Caustic Receiving and Feed Tank to about 25 per cent*. The diluted solution is then stored in the Caustic Storage Tank. Spent acid from slug pickling operation is accumulated in the Spent Pickle Acid storage Tank.

The acid and the caustic solution from the two storage tanks are proportioned to the Neutralizing Tank to produce a pH of 11, thereby precipitating uranium in the form of sodium diuranate ($\text{Na}_2\text{U}_2\text{O}_7$). The sodium diuranate is recovered by means of a filter press and shipped to the National Lead Co. of Ohio at Fernald, Ohio for recovery and reuse as metallic uranium.

3. Aluminum and Al-Si Scrap Recovery

Aluminum and aluminum-silicon alloy Scrap (from the canning process) which has a low impurity content is reclaimed for use in the canning and duplex baths. The two primary sources of usable scrap are the slug facing operation, and cap and can inspection. The turnings from the facing operation and the jacketing components which were rejected for fabrication defects

*It is necessary to reduce the concentration to avoid precipitation in the Feed Tank.

DECLASSIFIED

~~SECRET~~
-904-

HW 40600

are melted down in either an induction or a resistance furnace. The melt is maintained at 700 C. The silicon concentration is raised to the desired level for canning use (about 11 per cent) by additions of elemental silicon or master aluminum-silicon alloy which contains a maximum of 25% silicon. When a resistance furnace is used, the melt is stirred during the additions to provide adequate mixing. The adjusted melt is normally fluxed to promote separation of the impurities and the entrained aluminum oxide. The usual fluxing practice is to add three one-pound quantities of Soffelite No. 2, a proprietary fluxing compound, and to skim the bath surface periodically for a minimum of three hours prior to use in the canning line. Flux is not used when the melt is made up in an induction furnace, since the inherent bath agitation is considered sufficient to force the impurities to the bath surface; also, the flux might deteriorate the furnace lining. Induction furnaces are used when they are available for melting down scrap and for master alloy makeup. Induction furnaces are used because of the greater heating rate, higher temperature and better temperature control. Furthermore, when the elemental silicon is added, the inherent agitation of the induction furnaces increases the amount of silicon that can be put into solution.

Melts of recovered aluminum are analyzed for silicon concentration by thermal analysis and for impurities by spectographic analysis before the aluminum is accepted for process use. Impurity content is limited by the concentrations of lead and iron, both of which are present in the scrap from the silicon additions.

B. SALT BATH OUTGASSING

Salt bath outgassing of uranium slug cores was introduced as an auxiliary process operation in the fall of 1954 to reduce gas porosity in the braze layers of the dip canned slugs. Gross braze porosity had become increasingly prevalent after the first six-month period of lead dip canning. Most of the porosity appeared to result from increased hydrogen absorption

~~SECRET~~
DECLASSIFIED

DECLASSIFIED

during the (carbonate) salt bath heat treatment of the uranium rod (at FMPC). As a remedial measure, virgin slug cores containing greater than ~ 2.5 ppm hydrogen were outgassed in a chloride salt bath. (Recovered canning rejects were sufficiently outgassed during the initial canning cycle to obviate the need for a re-treatment). The outgassing procedure was used for about six months after which time the hydrogen content of the production metal received from the vendor ranged from 2.0 to 2.5 ppm. At these lower hydrogen concentrations, the salt bath outgassing treatment offers no substantial improvement; hence it was discontinued as a treatment for regular production metal. Dingot uranium (See Chapter VII), which is under development and is being canned in production test quantities, inherently contains from 4 to 6 ppm hydrogen; therefore, it is routinely outgassed.

The solubility of hydrogen in uranium varies widely at different temperatures. Hydrogen, if it is available, can be picked up in the heat-treating bath because the hydrogen solubility at heat-treating temperatures is 8 to 9 ppm. Hydrogen solubility in the high alpha range is one ppm, which explains why the efficiency of the outgassing procedure decreases as the initial hydrogen concentrations in the metal approach the lower levels. A hydrogen concentration of a ~ 2.5 ppm is considered the lower limit at which salt-bath outgassing is effective.

Salt-bath outgassing is conducted in a eutectic chloride salt (consisting of the chlorides of barium, sodium, and potassium) maintained at 610 C and vigorously agitated to assure uniform temperatures throughout the working portion of the bath. Five to six minutes immersion is required; longer immersion times do no effect significant reductions in canned slug porosity. The heated slug core is quenched in water immediately upon removal from the bath.

This salt bath outgassing procedure does not significantly alter the metallurgical characteristics of the uranium; however, a similar treatment at

DECLASSIFIED

DECLASSIFIED

-906-

HW-40000

temperatures of $\sim 640^{\circ}$ C (still in the alpha range) will cause a recrystallization of the grain structure (See Chapter V). The surface of the uranium is affected by the reaction with the salt; therefore, longer pickling times are required when the slugs are prepared for canning.

DECLASSIFIED

DECLASSIFIED

FIGURE IX-1

FLOW SHEET FOR RECOVERY PROCESSES

DECLASSIFIED

DECLASSIFIED

-1001-

HW-40000

PART IV: PLANT AND EQUIPMENT

CHAPTER X: DESCRIPTION OF THE MANUFACTURING PLANT

<u>CONTENTS</u>	<u>Page</u>
A. INTRODUCTION	1002
B. CONSTRUCTION	1002
C. LAYOUT	1003
D. SERVICES AND FACILITIES	1004
1. Steam	1004
2. Water	1005
3. Air	1005
4. Electrical	1005
4.1 Normal Power	1005
4.2 Emergency Power	1006
E. FLOW OF MATERIALS	1006
1. Uranium Slugs	1006
2. Aluminum Components	1007
2.1 Caps	1007
2.2 Cans	1007
2.3 Aluminum-Silicon Ingots	1007
3. Chemical Solutions	1007
3.1 Sodium Hydroxide (Caustic)	1007
3.2 Trichloroethylene	1008
3.3 Methanol	1008
3.4 Nitric Acid	1008
4. Miscellaneous Receipts	1008
4.1 Argon Gas	1008
4.2 Steel Sleeves	1008
4.3 Sodium Nitrate	1009
4.4 Lead	1009

DECLASSIFIED

DECLASSIFIED

-1002-

HW-40000

A. INTRODUCTION

The facilities for the preparation of the fuel elements and special products are installed in Building 313, 300 Area. This building is located within the 303 exclusion area and is surrounded by auxiliary buildings which do not contribute directly to the actual production operations. (See Figure X-1.)

The 303 area is entered by passing through the 3707-D building where security standards must be met before entry. This building also serves as the change house and lunch room for personnel working within the area. There are approximately 450 individual lockers in the change house and the lunch room will seat 100 employees at a time. This building is located near the southeast corner of the 313 Building.

B. CONSTRUCTION

The 313 Building has a structural steel frame with concrete block exterior walls in the original section and insulated metal panels in the new addition. (See Figure X-2.)

The outer shell of the building addition was erected in the summer and fall of 1953. The floor slab, autoclave and furnace pits, and building mechanical equipment were installed by Minor Construction in 1954. Process equipment was installed as received, starting in mid 1954. The first uranium slugs were canned in the new canning area in November, 1954.

The basic layout utilizes the old building for bare storage, slug preparation and component preparation. Canning, finishing, inspection, and final storage areas are located in the building addition.

Steel trusses support a metal roof deck on the new addition. These trusses completely span the canning and finishing areas and provide unobstructed work areas. The roof deck in the old building is predominately pre-cast concrete slabs. Insulation and a four-ply built-up roof weatherproof the entire building.

DECLASSIFIED

DECLASSIFIED

-1003-

REF ID: A6690

Flexibility for future process changes was incorporated in the building addition design as follows:

- A. The furnace pit has continuous footings which allow for alternate spacing of steel framework. The size is adequate for any known type of automatic canning furnace.
- B. Drain trenches in the finishing area are designed to handle present equipment with added capacity for installation of new equipment as required.
- C. The trusses are designed to take a five ton monorail load at any point in the canning area. A two ton monorail load is possible at any point in the finishing area with a four ton limit above the autoclave area.
- D. Twenty-five foot head room has been provided in the canning area to allow for removal of a furnace without disturbing the other furnaces in operation. The rest of the building addition has a sixteen foot ceiling while the old portion averages fifteen feet of overhead clearance.
- E. Electrical power is available from either 440 or 110 volt plug-in bus ducts over the finishing area or from motor control centers located in various parts of the building.

The elevation of the concrete floor slab in the building addition is the same as that in the old building.

C. LAYOUT

The 313 building was designed to facilitate installation and operation of equipment and to provide space for the storage of raw and finished materials. It has an irregular shape, although basically it is rectangular (182 ft. 6 in. wide and 486 ft. 0 in. long). The building has a total of 76,540 square feet of floor space which is utilized in the following manner:

1. Office Space	4,722
2. Work Area	49,353
3. Laboratory	1,241
4. Shops	1,923
5. Storage	11,339
6. Common facilities	7,962
(corridors, rest rooms, etc.)	

76,540

CONFIDENTIAL

DECLASSIFIED

DECLASSIFIED

-1004-

HW-40000

Process and auxiliary equipment is arranged in the building as shown in Figure X-3. The manufacturing process lends itself to an in-line type layout in which raw materials enter the south end of the building, progress through a sequence of operations, and the finished product is placed in the north shipping storage areas. Wide aisles extend the full length of the building on each side. These aisles permit access to the equipment with hi-lift trucks and also provide for the safety of pedestrian traffic. This type layout permits the use of overhead, chain, and skate-wheel conveyors to move the uranium slugs through the sequence of operations. Hi-lift trucks transfer pallets of finished fuel elements from the autoclave area to shipping storage area in the north end of the building. Reject material is also placed in pallets along the production line; hi-lift trucks transfer them to the slug recovery operation for recycling through the process.

D. SERVICES AND FACILITIES

1. Steam

Steam supply lines enter the 313 Building at two points. A three-inch main enters the southeast corner of the building and an eight-inch main enters the southwest corner of the building. They are connected by a loop extending around the inside of the building. Steam serves the ventilation and heating, process equipment, hot water heater, and steam cleaning systems.

Ventilation equipment consists of seven 20,000 cfm air conditioning units located on the roof of new additions, one 6,000 cfm unit, one 4,500 cfm unit inside the building addition, five 12,000 cfm units on the roof of the original building, and two 4,200 cfm units and one 8,000 cfm unit inside the original building. Space heaters, serviced by steam, consist of 12 unit heaters located throughout the building.

In general, process equipment is equipped with steam coils for the initial heating of solutions and with electric immersion units for continuous operation. Cap and can preparation, sleeve cleaning, slug pickle, penetration etch, and the autoclaves all use steam.

DECLASSIFIED

DECLASSIFIED

-1005-

HW 2-1000

The water heating equipment consists of two instantaneous water heaters with pre-heaters to provide hot water required for the process, and two storage tank water heaters to meet sanitary demands.

2. Water

The plant water system supplies 50 psi water to all facilities in the 313 Building. Secondary and cut-off valves are provided in each area. Water is delivered by a three-inch and a four-inch main entering the south side of the building and a four-inch main entering the north side of the building. It is possible to connect the north and south mains in an emergency by an extension joint.

The water mains are separated into three categories, sanitary, process and emergency water. Estimated consumption of process water is 126,951,300 gallons per year, and of sanitary water, 1,307,000 gallons per year. The consumption of emergency water (which is used principally to extinguish fires) is not estimated because the demands are unpredictable.

3. Air

Air at approximately 90 psi is supplied by a two-inch main in the southwest corner and a one and one-half inch main in the southeast corner of the 313 Building. Piping mains and branches have been checked for both design load (280.1 cfm) and maximum demand (176.7 cfm) and were found adequate for required loads. The estimated annual consumption of air is 31,337,000 cubic feet.

4. Electrical

4.1 Normal electrical power is supplied to the 313 Building through two 1500 KVA 2400/480/277 volt three-phase transformers located on the west side of the new addition. Switch gear busses contain primary switch gear for the building distribution system. Three main power circuit breakers control the power supply from the transformers.

Switch gear busses A and B each contain twelve circuit breakers giving a potential of twenty-four separate circuits within the building. From the

CONFIDENTIAL

DECLASSIFIED

switch gear bus circuit breakers the power is routed to secondary distribution centers throughout the building. For reference regarding location of these centers see "Single Line Diagram Electrical", DWG No. H-3-10233.

4.2 Emergency Power - In the event of a normal power failure in the production area, a standby source is provided to protect operating personnel and equipment. The source of emergency power is a standby steam turbine generator located in the area power plant, Building 384. The overhead crane and the blower motor on the induction furnaces in the canning area are on the emergency circuit, as well as the fire alarm, intercom systems, and safety shower lights. Caustic and nitric acid tank exhaust fans, and emergency lighting throughout the building are also provided with emergency power. At various equipment locations the emergency power may be switched off or on as the situation demands.

E. FLOW OF MATERIALS

1. Uranium Slugs

All uranium slugs are received by freight car and unloaded on the freight dock which extends along the entire east side of the 313 Building. Hi-lift trucks remove the boxes of slugs from each car and place them on the dock where statistical samples and a piece count are taken before moving them into the 313 Building. The samples are sent to building 305 for testing.

Locked storage areas located in the southwest corner of the 313 Building, 24-B, 24-C, 24-D and 24-E are used to store the uranium slugs until they are transferred in lots to the slug preparation area.

After a "lot"* of uranium slugs has been started through the process, it follows a line sequence of operations through the preparation, canning, finishing, and final inspection areas (Figure X-4). Most of the material handling is accomplished by hi-lift trucks and different types of conveyors in the building with the exception of manual transfers between the furnace and quenching units in the canning area.

* A variable number of slugs (normally between 3500 and 4000) which are treated as a unit.

DECLASSIFIED

DECLASSIFIED

When the canned uranium slugs have passed final inspection, the entire "lot" is placed into 300-hole pallets and stored in one of the storage areas (77, 78, and 80) in the northeast corner of the building until it is shipped for irradiation.

2. Aluminum Components

All aluminum components are received by freight car and are stored in one of the various storage areas in or near the 313 Building.

2.1 Aluminum Caps - Aluminum caps are received in cartons that are loaded onto pallets in freight car. A hi-lift truck then transfers each pallet of approximately 27 cartons to building 303-B where a statistical sample is taken and the weight of each carton is checked before storing. Upon receipt of an order from the component parts preparation group, the caps are delivered to the cap and can cleaning machine where they are processed, inspected and routed by conveyor to the canning area.

2.2 Aluminum Cans - Aluminum cans are received in cartons and are manually loaded onto pallets in the freight car. A hi-lift then transfers each pallet of 18 cartons into the 313 Building where the cans are statistically sampled, inspected, and placed in either storage bin No. 24-F or the storage area immediately north of that bin. They are stacked two pallets high for subsequent transfer to the cap and can preparation machine. An overhead conveyor delivers the caps and cans to the canning area after they have been degreased, etched, thoroughly dried and inspected.

2.3 Aluminum-Silicon ingots - Aluminum-silicon ingots are received in bundles, which are placed on pallets and moved by the hi-lift to the 303-C storage building. As space becomes available, the ingots are delivered to the heating cabinet at the northwest corner of the canning area to dry out any residual moisture before usage in the canning furnaces.

3. Chemical Solutions

3.1 Sodium Hydroxide - Sodium-Hydroxide (Caustic) solution is received by heated railroad tank car at the unloading station located 100 yards east of the 313 Building on a special railroad siding. The caustic is pumped through

DECLASSIFIED

DECLASSIFIED

HW-40000

-1008-

[REDACTED]

a steam heated pipeline from the unloading station to two 10,000 gallon insulated storage tanks located in the east part of the tank farm (Figure XII-7). From the tank farm the caustic is metered and pumped through special lines to slug recovery and the sleeve cleaning machines.

3.2 Trichloroethylene - Trichloroethylene is received in 52 gallon drums by rail shipment and is transported on pallets by lift-truck to a concrete pad west of the 303-J Building. When the drums are needed, they are transferred to a rack near the center of the freight dock on the east side of the 313 Building. The solvent is then pumped to a head tank in the canning area trusses to provide gravity flow to the degreasing equipment throughout the building.

3.3 Methanol - Methanol is received by tank car at the unloading station and is loaded into an underground storage tank with a capacity of 4,000 gallons. Pumps at the tank farm distribute the methanol to the cap and can preparation machines and to the special products preparation room through direct pipe lines to the equipment where it will be used.

3.4 Nitric Acid - Tank trucks deliver nitric acid, which is stored in two stainless steel tanks at the east side of the tank farm (Figure XII-7). These tanks each have a capacity of 4,000 gallons. Pumping facilities at the tank farm distribute the acid to slug recovery, slug pickle, and to the final etch machines in Building 313 through stainless steel piping.

4. Miscellaneous Receipts

4.1 Argon gas - Argon gas cylinders are received by truck and placed in gas areas on the loading dock on the east side of the 313 Building. When they are ready for use, the cylinders are connected to a manifold in two banks of 10 each, and the argon flows through a regulated supply line to the semiautomatic welders in the finishing area. Automatic switch-over to the second bank is provided when the first bank of cylinders is exhausted.

4.2 Steel Sleeves - Steel sleeves are received in cartons by truck from Central Stores. These components are subjected to a statistical inspection

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1009-

[REDACTED]

and 100 per cent mandrel inspection, after which they are placed in Building 303-C for storage. They are transferred by hi-lift from storage to the sleeve cleaning area.

4.3 Sodium nitrate - Sodium nitrate is received by truck in 100 lb. burlap bags. These bags are stored in 303-F Building where they are opened and mixed with caustic for the slug recovery operation.

4.4 Lead

a. "Poison Dummies" are received in the 300 Area by Stores truck in 180 pound boxes containing 50 lead-cadmium pieces each. The lead slugs are individually packaged in each box. The boxes are delivered to Building 313 where the slugs are inspected and stored. When the slugs are needed for canning they are delivered to the special products room by high-lift truck.

b. Lead for use in the duplex canning furnaces is received in 100 pound bars. They are delivered to open storage on a concrete pad west of the 303-J building by the vendor's truck. The bars are taken as they are needed to the dryer cabinet near the canning area, where residual moisture is removed before use in the duplex furnace.

[REDACTED]

DECLASSIFIED

[REDACTED]

303-F	Tank Farm	314	Experimental Facility
305	Pile Building	3707-D	Badge & Change House
306	Fuel Element Pilot Plant	3717-B	Instrument Building
313	Manufacturing Facility	3722	Maintenance Shop

FIGURE X-1

303 EXCLUSION AREA

UNCLASSIFIED

FIGURE X-2 313 BUILDING

UNCLASSIFIED

HW-4000

UNCLASSIFIED

HW-40000

1. SLUG RECOVERY	10. WELDING	19. SPECIAL CANNING
2. BARE SLUG PICKLE	11. WELD QUENCH	20. URANIUM RECEIVING
3. CAP & CAN CLEAN	12. ULTRASONIC TEST	21. TOOL ROOM
4. SLEEVE CLEAN	13. ETCH	22. MAINTENANCE AREA
5. DISTRIBUTION CENTER	14. RADIOGRAPH	23. PROCESS OFFICE AREA
6. CANNING AREA	15. AUTOCLAVES	24. ADMINISTRATIVE OFFICE AREA
7. METAL RECOVERY AREA	16. FINAL INSPECTION	25. CAP & CAN INSPECTION
8. CUTOFF LATHES	17. SHIPPING STORAGE	
9. FLUOROSCOPE INSPECTION	18. RECEIVING STORAGE	

FIGURE X-3 METAL PREPARATIONS (313 Building- 300 Area)

UNCLASSIFIED

AS-GE RICHMOND, WASH.

DECLASSIFIED

FIGURE X-4 FUEL ELEMENT FABRICATION FLOW SHEET

HW-40000

DECLASSIFIED

DECLASSIFIED

-1101-

HW-40000

PART IV: PLANT AND EQUIPMENT (Contd.)

CHAPTER XI: PROCESS EQUIPMENT

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION.	1103
B. LEAD-DIP PROCESS EQUIPMENT	1103
1. Cap and Can Preparation Machine	1103
1.1 Degreasing unit	1104
1.2 Cold water rinse tank	1105
1.3 Duponal tank	1105
1.4 Hot water rinse tank	1105
1.5 Cold water rinse and spray tank	1105
1.6 Diversey tank	1106
1.7 Two cold water rinse and spray tanks	1106
1.8 Methanol tank	1106
1.9 Dryer tank	1107
2. The Ultrasonic Transformation Test	1107
3. The Slug Pickle Machine	1108
3.1 Degreasing unit	1108
3.2 Nitric acid spray unit.	1109
3.3 Rinse unit	1109
3.4 Dryer unit	1109
4. Overhead Power Conveyors	1110
5. AJAX Induxtion Furnaces	1111
6. Centralized Air Switch Control	1113
7. Automatic Quench Unit	1114
8. Acme Gridley Automatic Bar Machine	1116
9. Semi-Automatic Welding Units	1116
10. Penetration Test	1117
11. Ultrasonic Bond Tes	1118
12. Penetration Etch Machine	1120

DECLASSIFIED

DECLASSIFIED

-1102-

HW-40000

TABLE OF CONTENTS (Contd.)

	<u>Page No.</u>
12.1 Degreaser	1120
12.2 Nitric acid tank	1121
12.3 Cold water rinse tanks	1121
12.4 Hot water rinse tank	1122
12.5 Dryer tank	1122
13. Radiograph Machine	1122
14. Paco Developing Machine	1123
15. Autoclaves	1124
16. Gamma Ray Core Test	1125
C. SPECIAL PRODUCTS EQUIPMENT	1126
1. Hot Presses	1126
2. Manual Welders	1127
3. Etch Line	1128
4. Sizing Presses	1130
5. Manual Lathes	1130
6. Annealing Furnace	1131
7. Component Preparation Line	1132
7.1 Hot caustic tank	1132
7.2 Hot rinse tank	1132
7.3 Duponal tank	1132
7.4 Diversey tank	1133
7.5 Cold water rinse tank	1133
7.6 Methanol twin tanks	1133
8. Slug Stripper	1134
D. LIST OF FIGURES	1135

DECLASSIFIED

A. INTRODUCTION

This chapter contains a physical description of the process equipment installed in the 313 Manufacturing Building, 300 Area. Most of this equipment is specifically designed for operations peculiar to the preparation of fuel elements and special products for irradiation. With the exception of special test equipment, tools and fixtures, all equipment has been obtained from various industrial equipment vendors.

Great skill has been required to devise equipment rugged enough to withstand heavy production loads, including the features necessary to prevent marring or otherwise damaging materials during processing. The aluminum parts used in fuel element jackets must be handled with extreme care to meet stringent surface standards. All component parts used in the lead-dip process must be cleaned and etched in chemical solutions to insure an acceptable bond between the uranium cores and jackets of finished fuel elements. In addition, cleanliness is essential throughout all operations to avoid introducing impurities that may adversely affect product quality.

Equipment used to prepare fuel elements by the lead-dip process is described in the normal operating sequence, beginning with the preparation of component parts. Special products equipment is covered in the latter part of the chapter.

B. LEAD-DIP PROCESS EQUIPMENT

1. Can and Cap Preparation Machine

The cap and can machine is a large hydraulically operated unit (Figure XI-1) built by the Udyllite Corporation, which carries baskets of aluminum caps and cans from one cleaning solution to another preparatory to canning. Thirty-two baskets, each having a capacity of 24 cans and caps, are suspended from an overhead track. Beneath the tracks are ten large tanks, in which the following sequence of operations are performed:

(1) Degreaser, (2) Cold rinse, (3) Duponal wash, (4) Hot rinse,

[REDACTED] [REDACTED]
DECLASSIFIED

DECLASSIFIED

-1104-

(5) Cold rinse and spray, (6) Diversey etch, (7) Cold rinse and spray, (8) Cold rinse and spray, (9) Methanol rinse, (10) Hot air dry (See Flow Diagram Figure XI-2).

1.1 The degreasing unit

The degreasing unit is designed to remove grease or impurities from caps and cans prior to chemical cleaning and etching. This unit has two compartments in the bottom of the degreasing chamber. One serves as a storage compartment for the cold trichloroethylene solvent. The other compartment is a boiling sump, and it is equipped with steam coils to maintain the temperature of the solvent in the boiling range. The boiling solvent forms a vapor in the upper chamber, which has a water cooled jacket and condensing coils to control the vapor level. As "cold" caps and cans are lowered into the degreaser the vapor condenses on the surfaces to give a washing and cleaning action. The condensate is returned to the storage compartment which overflows into the boiling sump as the solvent level rises.

The degreasing unit is equipped with a lip-vent exhaust along the top edge of the chamber to prevent vapor and fumes from entering the work areas. The temperature of the boiling sump is controlled by a thermoswitch and solenoid steam valve located at the front condensing coil opening in the degreaser. A thermocouple located on the lower left hand side of the sump relays the temperature of the solvent to a Foxboro recording instrument in the control panel. Two sight glasses are provided to indicate the solvent level in the storage and boiling compartments.

A transfer pump is provided near the boiling sump to transfer solvent from the boiling sump to the solvent reclaiming still where water and other impurities are removed. A spray bank on each side of the vapor chamber is provided to spray-wash the caps and cans. Each spray bank consists of three legs containing four nozzles each. A pump connected to the boiling sump supplies solvent to the spray nozzles.

DECLASSIFIED

DECLASSIFIED

1.2 Cold water rinse tank

A cold water rinse is required to cool the aluminum components before they are cleaned in duponal. The tank is equipped with two spray banks for rinsing the material and has an open drain to the sewer. The water supply to the spray banks is controlled by a solenoid valve, which is actuated by the basket transfer mechanism on the overhead track.

1.3 Duponal tank

Duponal is used to further clean caps and cans by removing any soluble surface impurities. There are eight calrod heaters in the tank to maintain the detergent solution at the desired process temperature. Steam coils are also provided as boosters to heat the duponal during startup periods and to serve as an auxiliary heat supply in event of calrod element failure.

A recirculating pump connected to the bottom of the tank keeps the duponal solution mixed and maintains the proper solution level. An overflow sump is provided to supply this pump with solution.

1.4 Hot water rinse tank

The hot water rinse tank for flushing the remaining duponal from the aluminum components is equipped with two calrod heating elements controlled by a Fenwal thermostat. A steam plate coil is also provided as a booster unit during initial startup. A hot water supply line is connected to the tank for filling and has a manual control valve. An overflow sump is provided with an open drain to the sewer.

1.5 Cold water rinse and spray tank

This tank is used both as a cold water submersion-type rinse, and to spray the componenets with cold water as they are removed from the tank. The water supply to two banks of spray nozzles is controlled by a solenoid valve actuated by movement of the machine carriage. An overflow reservoir is provided in the tank to maintain water level and drains directly to the sewer.

DECLASSIFIED

DECLASSIFIED

1.6 Diversey tank

The diversey solution tank is provided to etch the surfaces of aluminum components and remove any oxides that may interfere with component "wetting" during the canning operation.

This tank is provided with an overflow sump and a recirculating pump to keep the solution mixed and maintained at the proper level. Since the diversey solution is used at room temperature no special controls are required.

1.7 Two cold water rinse and spray tanks

The two cold water rinse and spray tanks are designed to thoroughly rinse the aluminum components after the diversey etch. Each of the tanks is provided with a bank of spray nozzles above the water level so that as the machine lifts the baskets of components from the tanks a spray rinse is applied. The water level in both tanks is equalized by baffles between the tanks.

The sprays for both tanks are controlled by solenoid valves located in the water supply lines.

1.8 Methanol tank

The methanol rinse is provided to displace the water from the surfaces of the caps and cans to facilitate drying and to avoid water stains.

A circulatory pump is provided to agitate the methanol solution around the baskets of aluminum components. An overflow sump supplies the pump with solution. A transfer pump is also provided to remove the methanol from the tank and overflow sump to a reclaiming still. A push button on the control panel will start the pump after the manual drain valves are opened.

A 600 gallon underground tank has been provided for disposal of the inflammable methanol solution in case of fire or evacuation. This emergency tank is located beneath the floor surface between the No. 1 and No. 2 cap and can

DECLASSIFIED

DECLASSIFIED

-1107-

preparation machines.

1.9 Dryer tank

All components are thoroughly dried to ensure that no moisture comes in contact with the molten canning bath metals. The dryer unit is supplied with a stream of hot air from a BC 35 Universal Blower driven by a 2 HP motor. A steam heating unit is located in each of two openings where the blower duct enters the dryer tank. One opening is at the end and the other through the side of the tank. Steam is supplied to the heating units through two explosion-proof steam solenoids controlled by a switch labeled "Steam Control" on the control panel.

A Roots Connersville rotary blower located at the east end of the machine supplies a large stream of hot air to remove the remaining methanol from the caps and cans as they enter the dryer tank.

2. The Ultrasonic Transformation Test

The ultrasonic transformation test is used to determine whether the uranium in bare slugs has been completely "transformed" (i. e., heated to above 662 C) during "beta" heat-treating following alpha rolling.

The testing equipment actually measures the average grain size in the metal. This serves as a measure of transformation since the average grain size of alpha rolled (or alpha extruded) uranium of high purity is increased three to ten fold during beta heat-treatment. In general, the more impurities present in the uranium, the smaller the change in average grain size after complete alpha-beta transformation. Sound waves passing through the metal are broken up and scattered to a sharply increasing degree as the sound wave-length (the distance in the metal between pressure crests) approaches the diameter of the grains.

The test is conducted in a long rectangular tank about four feet long and fifteen inches wide. A drive motor under the tank is coupled to a series of rubber rollers that contact two rows of teflon balls upon which the bare

DECLASSIFIED

DECLASSIFIED

-1108-

slugs are rotated and moved longitudinally past the testing head. The tank is filled with water and the slugs are completely submerged during the test.

The test instrument emits short bursts of electrical waves that are converted to sound waves by a quartz crystal. These waves are directed from the crystal transversely through each slug, where their intensity is reduced by scattering (large grain size = more scattering). The waves are then picked up by a receiver crystal and reconverted to electrical waves. After simplification the wave signal is passed through an electronic "gate" which (1) stops the strong signal at the time of the initial emission; (2) stops waves travelling more slowly through a roundabout or an all water path; and (3) stops any wave signal smaller than a preset intensity. Thus only the stronger wavetrains passing through small grain untransformed metal will trip the reject alarm circuit. The wave cycle is repeated about 2000 times per second in order to completely examine the whole cross-section of each slug as it rotates past the testing head mounted on the conveyor.

3. The Slug Pickle Machine

The slug pickle machine is designed to prepare a maximum of 500 bare uranium slugs per hour for the canning operation. The pickling operation removes any oxide or other impurities (Figure XI-3) from the slug surfaces. The machine manufactured by the Metalwash Machinery Corporation, consists of four in-line units interconnected by an angle iron framework. A large endless chain conveyor carries baskets containing 24 bare slugs through the machine on a predetermined cycle and deposits them on a roller conveyor for inspection. The chain conveyor is also used to return the empty baskets for reloading. The four units in the slug pickle machine are: (1) Degreasing unit, (2) Nitric spray unit, (3) Rinse unit, (4) Dryer unit.

3.1 Degreasing unit

The degreasing unit has two compartments in the lower portion of the unit. One is a boiling solvent sump and the other is a solvent storage chamber. Each of these compartments is equipped with a visual solvent gauge glass.

DECLASSIFIED

DECLASSIFIED

-1109-

[REDACTED]

A dial thermometer on the front side of the unit indicates the boiling sump temperature in conjunction with a recording instrument on the control panel. The boiling sump is heated by a steam jacket and the solvent. A temperature controller and automatic valve assembly are located at the bottom of the degreaser. The temperature controller is actuated by the vapor level control thermostat, which is designed for safety and to prevent loss of solvent. This control prevents vapor from rising above the condensate coils (around the upper lip of the degreaser) if the water supply fails or is inadequate. A lip vent exhaust is also provided to remove any vapors that may reach the area above the degreaser.

3.2 Nitric acid spray unit

The nitric acid spray unit is equipped with an upper and lower bank of spray nozzles to spray acid on all surfaces of uranium slugs contained in each basket as they are conveyed into position for pickling. A recirculating pump is connected to a tank in the bottom of the unit to pump acid solution to the nozzles. The acid is heated by immersion-type electric elements and the temperature is controlled by a Fenwal adjustable thermostat. A thermocouple relays the acid temperature to a Foxboro recorder in the instrument panel.

3.3 Rinse unit

The rinse unit contains two banks of water spray nozzles which spray-rinse the excess nitric acid from the pickled slugs. Instead of being recirculated, the water is passed directly to the sewer drain. Blow-off slots are installed at the end of the water rinse unit to strip off as much of the water as possible. A Spencer Turbo air compressor supplies a blast of air to the water stripper slots through a duct outside of the water rinse chamber. The air blower is located on an overhead platform between the two pickle machines installed in 313 Building.

3.4 Dryer unit

The dryer unit is equipped with a fin-type element heater located in a

[REDACTED]

DECLASSIFIED

DECLASSIFIED

cabinet below the dryer chamber. The blower and motor, located under the rear end of the chamber, furnish the hot air blast by drawing air through the heater fins and forcing it through a large bank of nozzles in the dryer. An air vent is used to recirculate the hot air in the dryer chamber back through the blower. A fresh air inlet at the discharge end of the unit controls the fresh air intake to the blower.

The heat control for the dryer consists of a Fenwal thermostat control located on the side of the dryer cabinet. A "Dryer Motor" switch on the control panel actuates the blower and heater. A thermocouple relays the dryer temperature to a Foxboro recorder in the control panel.

4. Overhead Power Conveyors

All component parts for fuel element preparation are assembled at a distribution center (Figure XI-4) located between the component parts preparation machines and the canning lines.

Baskets of uranium slugs are transferred on a powered roller conveyor to the distribution table. Caps, cans and sleeves from the cleaning machines are conveyed to this table on a Richards-Wilson Zig-Zag continuous power conveyor. This conveyor also transfers the assembled components from the distribution center to each of the canning lines.

The Zig-Zag overhead conveyor consists of a steel tubular track through which a specially constructed chain, fitted with guide and load bearing wheels in both horizontal and vertical planes, is propelled by a caterpillar type drive unit. The loads to be carried are suspended by pendants attached to the vertical wheel units.

Flexibility is a major feature of this conveyor. Both the straight and curved sections are easily assembled, and the chain is designed to negotiate curves with a small radius. The variable speed drive units on the conveyor provide the necessary flexibility in the delivery of parts to the canning lines. Materials flow can be readily scheduled by coordinating the slug pickle,

[REDACTED] [REDACTED]

DECLASSIFIED

DECLASSIFIED

-1111-

sleeve cleaning, and can cleaning machine cycles, with the conveyor system so that prepared components will leave these machines as fast as they are used in canning. In this manner the in-process quantities of components may be reduced to a minimum.

5. Ajax Induction Furnaces

There are two induction furnaces being used on each of the six canning lines. The first is an AlSi-lead dip (duplex) furnace into which the uranium slugs are placed, two at a time, for pre-heating and coating with a layer of molten AlSi (Figure XI-5). The lower portion of the furnace is charged with approximately 3800 pounds of lead into which the slugs are submerged and agitated for preheating. The upper portion of the "duplex" furnace where the slugs are coated before being canned, is filled with approximately 560 pounds of molten AlSi. In the second furnace, called the "canning furnace", the slugs are inserted, two at a time, into aluminum cans and are capped while all parts are below the surface of the molten bath. This furnace is charged with approximately 1500 pounds of AlSi.

The Ajax furnace is an induction-type furnace which derives its heat from the flow of electrical energy in the metal bath. Electrically, the molten metal is analogous to the short circuited secondary of the transformer. In order to operate, an electrical path must be established in the furnace. When an empty furnace is charged, this path is provided by filling the inductor channels with molten metal. The furnace operates on 480 V single-phase, 60 cycle power.

The outer metal shell is nearly square with inner-connecting channels in the rear bottom section where the induction coil is mounted. The supporting framework is designed so the furnace may be tilted. Thus the charge in the molds can be emptied in the event of furnace operating failure or if the charge must be replaced for process reasons. An overhead crane in the canning area is used to tilt the furnace. Bailing the furnace by hand is time consuming and it is difficult to remove metal from the induction

DECLASSIFIED

DECLASSIFIED

[REDACTED] -1112- [REDACTED]

channel throat before it solidifies unless the charge is emptied rapidly.

A layer of suprex insulation is installed inside the metal shell to provide a heat transfer barrier to the outer surface of the furnace. The hearth is lined with a thick layer of fire brick, and specially shaped throat blocks above the induction coil provide channels through which the metal may circulate as it is being heated.

The power transformer of the induction furnace is cooled by a direct coupled fan located below the inductor channels. This fan is driven by a 3400 RPM, 440 V, 3 Phase, 1-1/2 HP motor. The exhaust air from this fan is piped into a header and passes through a Buffalo vane axial fan to the roof of the building. Cooling fan controls are located in the Ajax control panel. The vane axial fan is located on the wall at the west side of the canning area. The control for this fan is in control station "C" and is marked, "C6B - Furnace Inductor Exhaust Fan".

The power input is controlled through the Ajax power panel, which is serviced by a 480 V single phase circuit. The main disconnect switch controls all power to the panel. From the line side of the main fuses the instrument power for the control circuits is tapped off through a small instrument transformer located in the control panel. The power for heating the furnace is tied through variable tapped transformers and across fixed capacitors to the transformer coil in the furnace.

A float level is used in the lead-dip furnace to indicate the level of the lead beneath the AlSi. This furnace is also equipped with an agitator designed to lower the uranium slugs into the duplex bath for the preheating operation. The agitator frame, as shown in Figure XI-5, is tubular and resembles an inverted "L" from which a basket assembly is suspended. The raising and lowering of the basket is actuated by an 18 in. air cylinder mounted on the main agitator housing. An elevating cable connects the cylinder piston with the basket lift mechanism. The basket agitating action, a horizontal back and forth motion, is driven by a 1/2 HP Ratiomotor mounted on the side of

[REDACTED] [REDACTED]
DECLASSIFIED

DECLASSIFIED

-1113-

the housing. The agitator speed change gear is located between the motor and the agitator drive shaft.

6. Centralized Air Switch Control

The centralized air switch control furnishes power to the duplex furnace agitators, canning jacks and quenching units, and controls their sequence of operation to conform with process specifications.

The centralized air control consists of three control cabinets located in the furnace pit under the canning area. Each control cabinet is capable of controlling two lines with one line in stand-by capacity. The control unit for one line consists of two poppet-type air switches driven through a gear train by a Boston Ratiomotor. The switch drive motors are supplied with 115 V power through thermal switches at the front of each panel. The air switches are supplied with 90 pounds of pressure through a combination globe trap, pressure reducing valve and oiler. A cut-off valve is supplied for each air switch.

In addition to the switches, two additional auxiliary functions have been added to the centralized air control. They are:

1. Impulse reset timer - to provide a clock signal at the working area indicating the portion of the cycle sequence being completed.
2. Motor synchronizing device - to provide a set relationship between pairs of motors to facilitate dual line operation.

The air signals which control the operation of a canning line are controlled through 43 control valves in each switch panel. The panels are designated as A, B, and C in each control cabinet. The A and C panels contain the switches and control valves for direct operation of each line. The B panel is for standby operation.

7. Automatic Quench Unit

The automatic quench unit is designed to insure proper and controlled quenching of each slug, good cap seating, and a uniform cap surface for

DECLASSIFIED

DECLASSIFIED

-1114-

indexing in the facing operation. One unit is located at the end of each of the six canning lines.

The quench unit is operated by the central air control system in the furnace pit below the canning area. Air supply lines from the agitator and canning jack switches maintain the quench mechanism on a fixed time cycle. Lines originating at the agitator switch control the vertical motions of the unit, while those originating in the jack switch control the horizontal movements and the water flow.

The quench unit has an elevating cylinder on each side to raise and lower two sets of dual slug baskets during the quenching cycle. Each basket is equipped with a water jacket to spray quench the canned assemblies before submersion. When one basket is submerged in the tank, the other basket is moved to the load position by one of two horizontal transversing cylinders located on a channel iron support above the tank. Also mounted vertically on this support are two cap-clamping cylinders. These cylinders apply pressure on the slug caps before an air operated valve opens to permit water flow through the basket water jacket for an initial spray quench. Quenching is accomplished by the water spray within 12 seconds after the canning cycle has been completed. Each basket in sequence is then submerged for final quenching before it is raised and the canned slug assemblies discharged in a catch tray, where the steel sleeves are removed.

The air supply to each automatic quench unit may be shut off by turning the toggle switch located on the upper channel support. This switch operates a solenoid valve in the central air control for the unit.

8. Acme Gridley Automatic Bar Machines

Three automatic bar machines, or lathes, are located near the south end of the finishing area. These lathes automatically face off the cap end of canned slugs to a specified thickness.

The Acme-Gridley machines are built on a solid frame consisting of four high grade alloy castings: (1) Pan, (2) Headstock Section, (3) Gear Box Section,

DECLASSIFIED

DECLASSIFIED

[REDACTED]
-1115-

HW-40000
[REDACTED]

and (4) Top Section. The pan is a single heavy ribbed casting and forms the base of the machine. The one-piece top section ties and firmly holds the headstock and gear box in alignment.

The main drumshaft controls all tool movements, including indexing and the timing of operations. This shaft is located in the lower part of the headstock and gearbox castings.

The spindle carrier consists of two connected discs and the carrier stem or shaft which forms a unit. The end toolslide (Figure XI-6) is mounted on the carrier stem, and moves forward and backward in perfect alignment with the work spindle holes in the spindle carrier. The spindles are mounted in antifriction bearings. A Geneva mechanism indexes the spindle carrier to move the spindles between consecutive working positions. The machine indexes in a clockwise direction immediately after the cutting tools are withdrawn from the work (Figure XI-7).

The machine is fed by placing each canned slug on a short roller loading tray which is aligned with the No. 1 spindle position. An air-operated ram pushes the slug into the spindle collet and holds it firmly at the cut-off position until the collet clamps the slug firmly in place. When the facing operation is complete, a ram at the rear end of the collet forces the slug back onto the roller loading tray, for removal by the operator.

The motor drive for the Acme Gridley lathes is mounted on the left-hand end of the top casting. "V" belts connect the motor with the pulley drive shaft. This shaft, through a series of gears, drives the work spindles and the main drum shaft.

Bearings and moving parts in the gear box are lubricated by a splash system with oil pumped from a reservoir in the gear box. Several mechanisms (such as chucking and feeding slides, drum shaft mounting in rear support and stock reel indexing gears) are lubricated by grease fittings.

The control panel for the lathe is located at the rear of the drive motor on the upper right hand corner of the machine.

[REDACTED]
DECLASSIFIED

DECLASSIFIED

[REDACTED]
-1116-

HW-40000

A sound booth has been constructed around each Acme Gridley machine to reduce noise in the work area. Cut-outs are provided at the front operating position to facilitate operation of the machine. Doors at the side and rear of the booth allow for necessary maintenance and cleanup functions. Each booth is equipped with an exhaust fan to remove heat generated by the machine.

9. Semi-Automatic Welding Units

The welding units located in the finishing area are used to fusion weld the cap closures of canned slugs. These units are as shown in Figure XI-8. The welding table for each unit is supported by four 2-1/2 in. tubular legs with a 1/2 in. aluminum top. A welding collet is mounted at the front center of the table and the welding head is located directly above the torch support. A 3 in. tubular column mounted vertically on the front left-hand corner supports the safety shield, with controlling micro-switches, and the torch support arm. The welding collet is rotated by a Boston Ratiomotor located on the back side of the lower collet housing. A number of cams and micro-switches are located on the rotating mechanism to control the welding cycle for automatic operation.

The electrical controls and terminal boards are mounted in a rectangular box below the table top on the front side of each welder. To the right of this box is a panel with two toggle switches and a push button. The toggle switch on the left hand side is the emergency power cut-off switch. The center switch allows the welding cycle to be started by the push button if the toggle is up and by a foot pedal on the floor if the toggle is in the down position. The master switch for the automatic welder is located on the left wall of the welding booth. The power for welding passes through a portable transformer beside the welding machine.

An Oxweld regulator and gauge control the pressure of argon gas piped to each welder. From the regulator, the gas flows through an Oxweld Flowmeter and two Skinner two-way valves before entering the welding head assembly.

DECLASSIFIED [REDACTED]

DECLASSIFIED

-1117-

REF ID: A66004

The air line to the transformer runs parallel to the incoming argon supply. The air is filtered and regulated by a series of filter and glass settling bowls and a pressure regulator and gauge located directly behind the welding collet on the booth wall.

The power supply unit is designed for inert arc welding and is capable of making good quality aluminum welds. A large air-core transformer (AC) is located in the center of the power unit. It has a movable secondary coil which varies the welding amperage. The control panel is located in the rear side of the unit and has a bank of series electrolytic capacitors to maintain a constant frequency amplitude for welding.

10. Penetration Test

The purpose of the Penetration Tester is to non-destructively test fuel elements (canned slugs) for penetration of the AlSi braze layer into the aluminum can wall.

The bond and penetration test heads are mounted along the side of a 50 in. x 18 in. x 6 in. water tank (Figure XI-9) equipped with two rotating rubber rollers to convey the canned slugs for scanning by the test heads. The power units are mounted on portable tables behind the tank and are connected electrically by moisture proof cable connections.

Small eddy currents are induced in the fuel element by electromagnetic inductions. Differences in the electrical characteristics of aluminum and AlSi affect the manner in which the eddy currents flow. Therefore, excessive AlSi penetration into the aluminum can wall causes measurable changes in the flow of eddy currents. These changes are sensed by a small detector coil. The voltages induced in the coil due to AlSi penetration are amplified and measured with respect to amplitude and phase by a phase sensitive detector circuit, which is connected to the indicating meters and a reject alarm circuit.

The voltage which is induced in the detector coil by small surface scratches

DECLASSIFIED

DECLASSIFIED

[REDACTED]
-1118-

HW-540000-1

or by changes in the position of the coil with respect to the slug has a greater amplitude than the voltage induced as a result of AlSi penetration. It is therefore necessary to discriminate against the former, unwanted signals. This is accomplished in two ways. First, since the phase of the penetration signal differs from the phase of the unwanted signals, only those signal components which are 90 electrical degrees out of phase with the unwanted signals are detected by the phase sensitive detectors. Second, to minimize probe motion signals, the probe coil is held against the surface of each slug under spring tension. To protect the probe from excessive wear as the slugs travel beneath it, thin teflon tape passes between the probe and the slugs. After each slug is tested the tape automatically advances a short distance.

The eddy current tester is blinded to the large signals induced at each end of the slug by switches (also protected by the teflon tape) which prevent the reject alarm circuit from operating except when a slug is fully under the probe.

The speed of the mechanical conveyor is regulated so that the probe describes a helix with about 1/16 in. pitch on the slug surface.

11. Ultrasonic Bond Test

The ultrasonic bond test detects incompletely bonded areas between the cans and slugs and rejects fuel elements with unbonded areas larger than a specified size.

In this test, a short electrical wavetrain is converted to ultrasonic waves by a quartz crystal, and transmitted through water to the surface of the canned slug. Most of the wave energy is reflected from the slug surface so that it bounces back to the crystal transducer. Some energy, however, enters the can wall (if the can is well bonded) and is dissipated as heat in uranium. In the absence of a complete bond the can wall is induced to "ring", setting up standing waves in much the same manner as a bell or pipe organ. This ringing is transmitted by the can wall into the water and back to the

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1119-

HW 4800

crystal where, along with the reflected waves, it is converted into an electrical signal and returned to the instrument. Because the ringing persists for several microseconds after the reflected waves have died away, it is possible to establish the existence of an unbonded area by examining the returned signal a few microseconds after the surface echo has collapsed.

The received signal after amplification is passed through an electronic gate which (1) shuts out all signals except those received about 1 to 5 microseconds after the surface echo arrives, and (2) shuts out all signals received during this time that are lower than a preset amplitude. Thus, the signals which pass through the gate indicate the existence of an unbonded area under the crystal; these signals are transmitted to the read-out circuit. To adequately cover the surface, this cycle is repeated about 3500 times per second along a helical path which is traced on the slug by the sensing crystal. Since the slug is under the crystal for approximately nine seconds, the surface is investigated for unbonded areas more than 30,000 times along a helix with a 1/16 in. pitch.

To prevent the rejection of slugs for unbonded areas smaller than the minimum acceptable, it is necessary to count the number of interrogations which disclose unbonded areas. Two read-out devices are provided, either of which can be selected by a switch on the discriminator chassis, to operate a rejection circuit. The first read-out simply counts the number of echos received from unbonded areas while the slug is under crystal, trips the reject circuit after 100 unbond signals are received. The second read-out circuit stores unbond signals on a resistance capacitance network with a short time constant, and operates the rejection circuit when the voltage developed across this network exceeds a fixed amount. This read-out can be adjusted to trip the rejection circuit after 17 to 19 consecutive unbond signals are received. Thus, a slug having an unbonded area with a circumferential dimension exceeding one centimeter will be rejected.

DECLASSIFIED

12. Penetration Etch Machine

The Udyllite penetration etch machine (Figure XI-10) progressively carries canned uranium slugs through various solution tanks. The purpose of this machine is to clean and etch the surfaces of finished fuel slugs. There are six tanks through which 28 baskets, carrying 12 slugs each, pass on a controlled timed cycle: (1) Degreaser, (2) Nitric acid tank, (3) Cold rinse tank, (4) Cold rinse tank, (5) Hot rinse tank, (6) Dryer tank. The baskets are conveyed on an overhead track and hydraulically raised or lowered into the tanks as the machine carriage indexes. The cycle time in each tank is controlled in conformance with process specifications.

12.1 Degreaser

The degreaser unit contains two solution reservoirs, the boiling sump and solvent storage compartment. There are two sight glasses located outside of the degreaser for visual checking of the solvent level in each reservoir. The temperature of the boiling sump is controlled by a thermostatic and solenoid steam valve located at the front condensing coil opening in the degreaser. A thermocouple in the sump relays the temperature to a Foxboro recording instrument in the control panel. A water jacket and condensing coils control the vapor level of the degreaser solvent. These are located inside of the upper portion of the unit.

A spray bank on each side of the vapor chamber is provided to spraywash the finished fuel slugs after entry into the chamber. Pressure to the spray nozzles is supplied by a solvent pump located outside of the degreaser and connected to the boiling sump. The "off" and "on" sequence of the pump is controlled by the machine cycle.

A supply line is provided for addition of solvent to the storage compartment. This line is equipped with a manually operated valve and forms the right hand leg of the "Y" fitting at the upper front side of the degreaser. The line and valve in the left hand leg of the "Y" is the return line from a solvent reclaiming still.

[REDACTED]

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1121-

HW-40000

12.2 Nitric acid tank

The nitric acid tank is the largest compartment on the machine and holds approximately 1400 gallons of solution. Eleven baskets of material are submerged in this tank at one time. Eight Chromalox immersion-type heating elements heat the solution to process temperature. A Fenwal thermostat controls the heat input to the element heaters. The nitric acid tank is also equipped with two steam coils that function as boosters to heat the acid during start-up periods and to serve as an auxiliary heat supply when needed. Operation of the steam coils is controlled by a solenoid valve actuated by pressing the "Steam Heater" button on the control panel.

Exhaust vents, located along the upper section of the tank, remove vapors and fumes. Two fume separators are installed along the side of the nitric tank to remove as much of the nitric vapor as possible before discharging the exhaust to the atmosphere.

The level and concentration of the nitric acid in the tank is controlled by an automatic level box, utilizing the difference in specific gravities of water and nitric acid. A drain valve is located on the east side of the tank and an acid supply line is located at the upper southwest corner of the tank.

12.3 Cold water rinse tanks

The two cold water rinse tanks are almost identical in construction. Each tank holds only one basket of material at a time. There are two spray banks above the water level of each tank for spray-rinsing the slugs after they have been submerged. The spray time is controlled by a solenoid valve actuated by the machine cycle. This valve is located on the top right hand side of the tanks. Overflow drains located between the tanks maintain a constant water level for rinsing. A manual valve is also provided to drain and clean each of the tanks.

DECLASSIFIED

DECLASSIFIED

-1122-

12.4 Hot water rinse tank

The hot water rinse tank receives one basket of material during each cycle of operation. There are two Chromalox heating elements and one steam coil, each controlled as described above. An overflow sump, located on the back side of the tank, is provided to maintain the water level. Hot water is supplied to the tank and flow is controlled by a manually operated valve. An exhaust vent is also installed along the front side of the tank and the fan is operated from the control panel.

12.5 Dryer tank

The dryer tank is enclosed as much as possible to retain heat inside the unit. It is rectangular and holds seven baskets of material. Heat is supplied by two air duct fin-type heaters controlled by a Fenwal thermostat located on the upper right hand side of the tank. The air blast for the dryer is supplied by a Universal blower mounted on the side of the tank. A push button marked "Dry Tank Motor Starter" on the control panel is used to operate the blower. An external hot air duct runs the full length of the dryer to circulate the warm air through the tank and return it to the blower. A dial thermometer is installed at the right end of the air duct to indicate air temperature ($^{\circ}\text{F}$).

13. Radiograph Machine

The radiograph is an X-Ray unit designed to reveal voids, porosity masses, or unbonded areas in finished fuel elements between the uranium core and the top of the cap (including the weld closure). It is also possible to locate inclusions or foreign matter that may appear as clear or light spots on the X-ray film. Three X-ray pictures of each weld are made by rotating the slug 120° after each exposure.

The unit consists of a lead lined enclosure approximately 10 feet high which houses the X-ray source. A Eureka TG-2C water-cooled X-ray tube is mounted on an adjustable platform that may be varied from 30 to 54 inches from the work location. The control is a Keleket type 160 K unit which is

DECLASSIFIED

described in BPF-7078.

Canned slugs are loaded, 18 at a time, onto a tray (Figure XI-11) provided with a motor drive to rotate the slugs 120° after each exposure. The loaded tray is rolled into the unit until two positioning clamps hold it secure. Pneumatic entrance and exit door opening and closing devices are provided to assure a sealed enclosure and to facilitate operation on a controlled cycle. An interlock located on the upper flange of each door prevents the X-ray tube from being energized before the doors are closed. A ball conveyor table is provided on three sides of the machine to transfer slug trays through the unit and return for reloading.

Electric and pneumatic equipment is used to control the time cycles for slug rotation on the trays, X-ray exposure conditions and door closure mechanism. A Cycl-flex timer controls the time exposure of the X-ray film. This timer is mounted in a control cabinet on the right hand side of the machine. A one second time delay is provided to allow the slug rotation motor to stop coasting before the X-ray tube is energized.

14. Paco Developing Machine

This machine was designed to develop large quantities of X-ray film on a production basis. Its overall dimensions are approximately 14 feet long and 3 feet wide, with varying height. The machine was manufactured by the Paco Corporation and has three major parts of units: (1) The feeding magazine, (2) The transfer mechanism, and (3) The tunnel dryer.

(1) The feeding magazine is located in the 313 Building dark room. Initially the strips of film are placed onto hangetts to hold them flat while passing through the developing process. A hangett is a rod bent into a rectangular shape with pin-type inserts for attaching the film. The hangetts are placed manually in the feeding mechanism one at a time through a "feed-up" handle located on the right hand side of the unit. Double saw-tooth tracks on each side of the magazine serve to space the film hangetts evenly and to move them from the receiver toward the developing tank by

DECLASSIFIED

[REDACTED]
-1124-
[REDACTED]

an agitation movement of one set of tracks.

(2) The transfer mechanism consists of six solution tanks with equipment to move the film from one tank to another. The developing tank and short-stop tank are located inside of the darkroom wall. The hypo solution tank, two water rinse tanks and the wetting bath are located in the film drying room.

Three overhead revolving lifter arms, driven by a 1/16 HP motor, move the film hangetts from one tank to the other. The tanks vary in size from 16 in. x 20 in. x 20 in. for the hypo solution, to 7 in. x 20 in. x 20 in. for the short-stop solution. All tanks are equipped with Paco dual valves for emptying solutions. The developer tank is also equipped with a valve for refilling and adding solution as required.

(3) The tunnel dryer is equipped with eight Infra-ray heating elements 21 inches long with copper reflecting plates. The blower located in the bottom of the dryer unit circulates the air through louvers in the floor plate of the cabinet. A conveyor chain, mounted on wood rollers, moves the film hangetts through the dryer at a constant speed. The conveyor chain is driven by a fractional HP motor and gear box below the floor plate. There are two large hinged doors on the top of the dryer for inspection and removal of film if it is not desired to utilize the unloading rack at the end of the unit.

15. Autoclaves

Thirty-six autoclaves are used in the final test of finished fuel elements to detect any pinholes or channels in the jackets that may allow water entry during irradiation (Figure XI-12). These units are installed in a pit with only the lids and the top two feet of each unit above the steel floor plate. The insulated pressure vessels (Figure XI-13), 20 inches in diameter and 8 feet long are mounted in a vertical position. The various valve controls are located on the steel platform at the right hand side of each unit. These controls are the (1) condensate control valve, (2) relief control valve, (3) blow-off control valve, (4) steam supply control valve, (5) water supply control

[REDACTED] [REDACTED]

DECLASSIFIED

DECLASSIFIED

-1125-

HW-40000

valve, and (6) pneumatic lid control valve.

Each autoclave is equipped with an air cylinder to raise and lower the lid. A quick opening and closing mechanism is also provided to insure positive and safe sealing of the lid.

Each autoclave is equipped with a pressure locking pin to prevent the lid from being opened while operating under pressure. When steam pressure starts to build up in an autoclave, a piston is activated which pushes the locking pin into an opening in the lid handle and locks the lid in a closed position. Each line of five autoclaves has a temperature recorder which records on a chart the operating temperature of each autoclave. These recording instruments are located in a control panel on the west side of the autoclave area. A pressure gauge on the lid of each autoclave provides a means for visual checking of the pressure inside the autoclave vessel.

The autoclaves may easily be converted to either water or steam depending upon test requirements. A one-inch water supply line and a 1-1/2 in. steam supply line are provided at the bottom of each vessel. All plumbing connections are made in the pit below the autoclave loading area.

16. Gamma Ray Core Test

The gamma ray core test is used to detect canning bath metal (either lead or AlSi) in the center hole of cored slugs. Occasionally, bath metal enters a core during canning operation because of an imperfect seal around one or both of the end plugs.

The gamma ray source for the test is a small unit of cobalt-60 with about 13 millicuries activity. The source is mounted in a lead-shielded cask designed to reduce the gamma intensity at the cask surface appreciably below tolerance limits. A beam is formed by a 1/4 in. collimating hole in the end of the cask. The slug to be tested is placed on a V-block and slid into position with its axis lined up with the collimating hole;

DECLASSIFIED

DECLASSIFIED

-1126-

mechanical stops are provided to insure correct positioning. The beam passing through the center hole of the slug is detected with a scintillation detector, and the gamma protons received over a period of 10 seconds are counted with commercial counting equipment.

The test is made by comparison with a standard slug having a minimum acceptable quantity of bath metal in the core. Counts received from accepted slugs must exceed the minimum count limit based on the standard.

The electronic components of the test instrument are standard commercial units and consist of a stable high voltage power supply, a linear amplifier, and a Berkeley counter.

C. SPECIAL PRODUCTS EQUIPMENT

1. Hot Presses

Twelve hydraulic presses (Figure XI-14), manufactured by the Rucker Company, are installed in the special products room. These presses are used for the diffusion bonding of assembled "C" (enriched uranium-aluminum alloy) slugs under specified temperature and pressure. Each press is equipped with two resistance-type furnaces which are pivoted on each side of the press supports. The furnaces are cylindrical in shape and have a hole through the center in which the punches, tapered dies, and canned assemblies are placed prior to the hot pressing operation. There are two thermocouples in each furnace. One thermocouple relays the temperature to the high-temperature alarm and limit control, and the other is connected to the temperature control meter located in the control panel. The control panels are located parallel with the presses near the east wall of the room.

The upper head of the press is stationary and has two temperature indicating light panels mounted on the front side. A pressure gauge is mounted at approximately eye level between the two indicating light panels. A manual valve behind the right indicating light panel is used to turn off the pressure to the gauge.

DECLASSIFIED

A microswitch located at the rear of each press support closes as a furnace assembly is positioned for the pressing operation. This safety device is provided to assure that each furnace is swung completely into position before the press will operate.

The press is operated by setting the cycle selector and pressing both "Close" push buttons. The cycle selector is a twenty inch arm which pivots on a one inch iron rod at the rear of the press. This arm is located above the stationary head and may be set in one of three positions to obtain the different pressure ranges for hot-pressing. The "Set" position allows a maximum of 25 tons pressure to be applied to the ram of the press. The "cure" position is for 14 tons pressure, and the "Break" position is for a maximum of 50 tons pressure. The maximum pressure for each position greatly exceeds the pressure required in the canning process. The cycle selector completes three individual circuits in sequence as the arm is moved from one position to another. As the push buttons are depressed the hydraulic pumps are energized to supply the pressure demanded.

There are two small foot-operated air ejector cylinders on the furnaces to break the tapered dies loose after the pressing operation has been completed. One foot pedal is located at the left and one to the right of the press assembly.

Two hydraulic pump units located in the pump room supply the pressure needed to actuate the presses. The piping is such that either pump unit may be used on both banks of presses.

2. Manual Welders

Two manual inert-arc welders are used to fusion weld the cap closures on special products. Each unit is housed in a separate booth.

The welding head is mounted on a two-level table about three feet wide and four feet long constructed of three-quarter inch masonite on top and a

DECLASSIFIED [REDACTED]

DECLASSIFIED

-1128-

steel plate on the lower level. A welding collet is located in the front left hand corner of the table. The collet is connected to a Boston Reductor gear box located directly below on the second-level plate. Between the collet and the gear box a steel ball clutch assembly is provided for flexibility in stopping and starting the rotation of the collet. The gear box is connected to a fractional HP motor in the center of the second table level by a "V" belt.

A shaded glass welding shield is independently mounted on the welding table and is hung on hinges so that it may be manually swung into position before the welding operation is started. At the front right hand side of the table, channel iron supports extend above the table on which an adjustable welding head and a filler-weld attachment are mounted.

Power for the welders is turned on at the "Welder Disconnect Switch", located on the left side of the welding booths. Argon gas is piped into each booth in a copper line, equipped with a manual valve, a pressure regulator and gage. From the pressure gauge the argon passes through an Oxweld Flowmeter and two Skinner electric two-way valves to the welding head.

The air line to the power supply unit is equipped with a manually operated valve. A filter settling bowl removes moisture and impurities from the air supply. A lubricator is also installed in the air line to keep valves and moving parts oiled.

The portable power supply unit for each welder consists primarily of a large aircore transformer. This transformer has a movable primary coil which varies the amperage as the adjusting knob on top of the unit is turned. A control panel and series electrolytic-capacitor bank make up the balance of the unit.

3. Etch Line

An etch line is installed in the special products room to etch canned slugs prior to the welding operation. This line includes four insulated sulfuric

DECLASSIFIED

DECLASSIFIED

-1129-

HW 40000

acid tanks and a rinse tank mounted on an angle iron framework along the west wall of the room. A separate dryer unit is also provided on the discharge end of the line.

(1) The sulfuric acid tanks are identical in construction. The acid enters each tank through a 1/2 in. line from a supply tank. Each tank is equipped with a manual valve to control the amount of acid solution received. The solution is heated by a 6000 W Chromalox immersion-type heater extending in an "L" shape along the back and bottom of each tank. Solution temperatures are controlled by Chromalox adjustable thermostats located above the rear flanges of the tanks.

The tanks are lined with 1/4 in. lead plate. A water supply line is located behind the tanks. Manually operated valves with extension handles are used to regulate water additions to the tanks.

The slug baskets are suspended from agitator arms above the tanks; one set of agitator arms services two tanks. The arms are pivoted on a shaft equidistant between the tanks and are agitated by a linkage driven by a Boston Gearmotor located on a platform below the tanks.

The sulfuric acid tanks are not drained in a conventional manner. A water aspirator (siphon) system is used so the solution will be diluted with large amounts of water as it is passed to the sewer. The siphon pipe from the sump in each tank is connected to a central valve assembly.

The tank valve may be opened after the process water valve is turned on blending the water and acid solution in a specially constructed "T" joint to produce the siphoning effect on the acid drain line.

Three double-lip-vent exhausts are provided between the five tanks to remove the fumes or vapors from the work area.

(2) The rinse tank is lead-lined and has an overflow drain located at the water level in the rear of the tank. The water is added at the front of the tank by two valves joined by a "T" fitting to give either hot or cold rinse water.

DECLASSIFIED

DECLASSIFIED

-1130-

(3) The dryer unit merely consists of a rectangular tank mounted on an angle iron framework. It is equipped with a squirrel cage Utility Set blower at the bottom to furnish the air blast. There are no heaters in this unit. The dryer motor control push buttons and indicating light are located at the front of the unit.

4. Sizing Presses

Two sizing presses, located near the east wall of the special products room are used to size the jackets on assembled slugs before the slugs are faced and either hot pressed or welded.

The smaller press has a ten ton capacity, while the larger press is designed to supply a maximum pressure of forty tons. Both presses are equipped with top and bottom rams.

There are two levers connected to hydraulic piston valves on the left hand side of each press. The lower valve is used to raise or lower the bottom press ram and the upper one is a "dead man" valve which must be closed before the main valve will operate. On the right hand side of the press another manual piston valve actuates the upper cylinder pressure to control the top ram.

Hydraulic pressure for the lower ram is supplied by a high-pressure hydraulic pump mounted on a bracket at the lower left-hand side of the press. The hydraulic pump for the upper ram is located in the pump room near the southeast corner of the 313 building. The "Start" and "Stop" push buttons are located between the presses with an indicating light to show when the pumps are on. Two hydraulic accumulators, manufactured by Gear Hydraulics, Inc., are provided in the pressure lines to each press to prevent any surges in pressure originating from the pumps. These accumulators are located behind the large press.

5. Manual Lathes

Three manually operated lathes are used to face the canned assemblies prior to hot press canning and welding. These machines were manufactured by

DECLASSIFIED

DECLASSIFIED

[REDACTED]
-1131-

HW-40000

the Monarch Machine Tool Company and are ten inch precision lathes. Each lathe consists of a bed mounted on a cabinet base, built-in oil pan of reservoir type, headstock, 3 HP 100 to 1 variable speed electric drive with magnetic switch and start and stop push button station, six feed gear boxes and a feed rod.

The drive to the headstock spindle is through multiple "V" belts. A dynamic brake brings the spindle to a complete stop from the highest speed in only two or three seconds. A large tachometer located on the left front of the housing indicates the lathe speed. The gear box is totally enclosed and automatically lubricated. All gears have anti-friction bearings, and six speeds are obtained from the gear train. In the base of the lathe is a Reliance V-S Drive, consisting of an AC motor, a DC generator, an exciter and a DC motor with a control panel. The AC motor and DC generator are combined into one unit. Power is supplied to the DC motor from the motor generator and exciter. The control unit consists of a speed regulating rheostat and a control panel. The motor generator and exciter unit is operated by push buttons on the housing below the headstock spindle. The lathe will not start until the "Start, Stop and Reverse" lever is in the proper position. This lever is also located on the spindle housing. Cover doors on each end of the lathe provide for easy accessibility to the drive motor and the Reliance V-S drive assembly.

6. Annealing Furnace

A resistance-type electric annealing furnace, manufactured by the Hevi-Duty Company, is used to anneal aluminum cans prior to the sizing operation. This furnace has a rectangular hearth supported by four angle iron legs. An insulated door on the hearth is easily raised or lowered by a crank and chain mechanism. The interior of the furnace is fire brick insulation and the heating elements are mounted in the walls. The hearth is 31 in. long, 14-3/4 in. wide and 12 in. high, with five

[REDACTED]
DECLASSIFIED

DECLASSIFIED

-1132-

HW-100607

heating elements on each side, two in the rear and one in the door. Two thermocouples located in the rear of the hearth relay the temperature to instruments in the control panel. One thermocouple is connected with a Leeds and Northrop temperature controller, and the other is connected to the limit control. An air vent directly above the furnace removes excess heat and gases from the special products room.

7. Component Preparation Line

There are six stainless steel tanks (Figure XI-15) in the special products component preparation line. These chemical solution and rinse tanks are used to clean component parts shortly before they are used in the canning process. The six tanks are arranged from right to left as follows: (1) Hot caustic tank, (2) Hot rinse tank, (3) Duponal tank, (4) Diversey tank, (5) Cold water rinse tank, (6) Methanol twin tanks.

7.1 Hot caustic tank

The caustic tank is equipped with an immersion type electrical heating unit which is turned off and on by a toggle switch mounted on the right hand side of the tank and is thermostatically controlled. A lip-vent exhaust is provided in the rear panel above the tank to remove caustic fumes and vapor.

7.2 Hot rinse tank

The hot rinse tank is equipped with a hot water tap and a short piece of garden hose to direct a continuous flow of water into the bottom of the tank. This gives a circulating hot water rinse to the material being washed. An open overflow drain maintains the water level in the tank.

7.3 Duponal tank

The duponal tank has a hot water tap and is heated by an immersion-type electric heater. This heater is thermostatically controlled. A Weston thermometer indicates the temperature of the solution. A Thermo-element in the lower section of the tank relays the temperature to a Mercoid Thermostwitch mounted on a bracket between the duponal and diversey tanks.

DECLASSIFIED

DECLASSIFIED

HW-40000

A "Hand-Off-Auto" control switch and indicating light are provided at the front left end of the tank to control the temperature either manually or automatically.

7.4 Diversey Tank

The diversey tank is about twice as long as the other tanks in the preparation line. It is 40 in. long, 24 in. wide and 18 in. high. This tank is equipped with a hot and cold tap and an overflow drain to the sewer. A recirculating pump is provided beneath the tank to agitate the diversey solution and keep it circulating while components are being processed. A "Start" and "Stop" push button and indicating light panel are mounted on the front of the tank.

7.5 Cold water rinse tank

The cold rinse tank is provided with a line to supply either cold water or steam to the tank. Two manual valves are located above the back plate. An overflow drain is located at the water level in the rear right hand side of the tank to allow for a constant water flow and rinsing action.

7.6 Methanol twin tanks

The methanol tank is divided into two sections for two separate methanol rinses. The methanol solution is cold and can be drained by two valves at the bottom of the tank. A lip vent exhaust is provided to remove any fumes from above the solution.

An electric dryer is located at the end of the line to dry the components. Calrod heating coils are located directly below the top grill upon which the components are placed. A blower manufactured by the Western Blower Company is located at the rear of the dryer to supply an air blast through the heating coils. Push button controls and indicating lights are mounted on the rear side of the dryer unit.

All tanks are serviced by a Budget 1/2 ton monorail crane located directly above the tanks. Components are placed in stainless steel baskets and are

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1134-

HW-40000-3

carried from one tank to the other by pulling the crane along the monorail track.

8. Slug Stripper

The slug stripper is a small mechanism mounted on a table to strip the jackets from rejected canned slugs. The stripper consists of three two-inch diameter rolls, 9-1/2 in. long, mounted in a triangular pattern. One stationary roll is knurled and is driven by a chain drive system connected to a Master Gearhead 3/4 HP motor. The other stationary roll is located at the top of the triangle. The third roll is movable and may be moved by a vise-press equipped with a corresponding roll to allow rotation even though pressure is being applied inwardly to the triangle. Each canning reject is inserted through a hole in the side of the unit between the three rolls. A four star crank handle on the front of the vise is then tightened. The rolling action supplied by the knurled roll combined with the pressure supplied by the vise expands the can and allows the slug to drop out freely.

DECLASSIFIED

DECLASSIFIED

-1135-

HW-40000

D. LIST OF FIGURES

- Figure XI - 1 Cap and Can Preparation Machine and Feed Conveyors
- Figure XI - 2 Flow Diagrams
- Figure XI - 3 Slug Pickle Machine
- Figure XI - 4 Distribution Table and Overhead Power Conveyors
- Figure XI - 5 Ajax Induction Furnace and Agitator Mechanism
- Figure XI - 6 Acme-Gridley Automatic Bar Machine
- Figure XI - 7 Acme Gridley Lath Spindle Holder
- Figure XI - 8 Semi Automatic Welding Unit
- Figure XI - 9 Bond and Penetration Testers
- Figure XI - 10 Penetration Etch Machine
- Figure XI - 11 Radiograph Machine
- Figure XI - 12 Autoclave Area
- Figure XI - 13 Autoclave Vessel
- Figure XI - 14 Hot Presses (Special Products Room)
- Figure XI - 15 Component Preparation Line

DECLASSIFIED

FIGURE XI-1

CAP AND CAN PREPARATION MACHINE AND FEED CONVEYORS

DECLASSIFIED

FIGURE XI -2 FLOW DIAGRAMS (component preparation)

DECLASSIFIED

HW-40000

UNCLASSIFIED

HW-40000

FIGURE XI-3

SLUG PICKLE MACHINE

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XI-4

DISTRIBUTION TABLE AND OVERHEAD POWER CONVEYORS

UNCLASSIFIED

FIGURE XI-5

AJAX INDUCTION FURNACE AND AGITATOR MECHANISM

UNCLASSIFIED

FIGURE XI-6
ACME-GRIDLEY AUTOMATIC BAR MACHINE

- 1. Facing tool
- 2. Tool holder
- 3. Air supply valve
- 4. Spindles (6)

- 5. Spindle carrier
- 6. Tool holder (finishing)
- 7. Load & unload cradle
- 8. Cradle holder

FIGURE XI-7

ACME-GRIDLEY LATHE SPINDLE HOLDER

FIGURE XI-8

SEMI-AUTOMATIC WELDING UNIT

UNCLASSIFIED

HW-40000

FIGURE XI-9

BOND AND PENETRATION TESTERS

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XI-10
PENETRATION ETCH MACHINE

UNCLASSIFIED

FIGURE XI-11

RADIOGRAPH MACHINE

UNCLASSIFIED

HW - 40000

FIGURE XI-12
AUTOCLAVE AREA

UNCLASSIFIED

FIGURE XI-13

AUTOClave VESSEL

UNCLASSIFIED

UNCLASSIFIED

FIGURE XI-14

HOT PRESSES (SPECIAL PRODUCTS ROOM)

HW-40000

UNCLASSIFIED

HW-40000

FIGURE XI-15
COMPONENT PREPARATION LINE

UNCLASSIFIED

DECLASSIFIED

-1201-

HW-40000

PART IV: PLANT AND EQUIPMENT (Contd.)
CHAPTER XII: AUXILIARY EQUIPMENT

<u>CONTENTS</u>	<u>Page</u>
A. INTRODUCTION	1202
B. STEEL SLEEVE CLEANING MACHINE	1202
1. Caustic Tank	1202
2. Cold Water Spray Rinse Tank	1203
3. Cold Water Submerge Rinse Tanks	1203
4. Soap Tank	1203
5. Dryer Tank	1203
C. STEEL SLEEVE HONING MACHINE	1203
D. SLUG RECOVERY EQUIPMENT	1203
1. Caustic Receiving and Feed Tank	1204
2. Used Caustic Storage Tank	1205
3. Neutralizing Tank	1205
4. Spent Pickle Acid Tank	1206
5. Stripping and Treating Tanks	1207
6. Pressure Tank	1208
7. Filter Press	1208
E. TANK FARM (303-F Building)	1209
F. DEGREASER SOLVENT STILLs	1210
G. HEVI-DUTY RESISTANCE FURNACES	1211
H. MUFFLE FURNACE	1212

DECLASSIFIED

DECLASSIFIED

-1202-

A. INTRODUCTION

Auxiliary manufacturing equipment is defined as that equipment being used in support of the fuel element preparation process, but not directly in the process. Numerous operations are performed adjacent to the regular production lines. Steel sleeves, after each canning cycle, must have the AlSi adhering to the surface chemically removed before reuse. Rejected canned clugs are sent to Slug Recovery where the aluminum jackets and compound layer are removed and the slugs are prepared for recycling through the process. Solutions are mixed for use throughout the 313 Building at the 303-F Tank Farm. Solvent stills are provided to reclaim dirty degreasing solvents. Metal recovery and the thermal analysis of aluminum silicon conserves metal for reuse that would otherwise be sold for salvage value.

B. STEEL SLEEVE CLEANING MACHINE

The sleeve cleaning machine progressively carries steel sleeves through various solution tanks to remove AlSi and other surface impurities after each canning cycle in preparation for reuse. This machine (See Figure XII-1) is manufactured by the UdyLite Corporation and is hydraulically operated. There are six tanks through which 21 "baskets" of steel sleeves pass on a predetermined cycle: Caustic Tank, Cold Spray Rinse Tank, Two Cold Submerge Rinse Tanks, Soap Rinse Tank, and a Dryer Tank. (See Flow Diagram, Figure XI-2).

1. The caustic tank is filled with approximately 850 gallons of caustic solution which dissolves the AlSi from the sleeves after each cycle in the canning operation. This tank is equipped with 18 Chromalox immersion-type heaters controlled by a Fenwal adjustable thermostat. It also has two plate-type steam coils that serve as boosters to heat the caustic solution during startup periods. The steam input to the coils is controlled by a solenoid valve. A recirculating pump is provided to keep the hot caustic solution mixed and at the proper level. A transfer pump is located near the tank to pump the spent caustic to slug recovery.

DECLASSIFIED

2. Cold Water Spray Rinse Tank

The cold spray rinse tank is equipped with six banks of water nozzles to flush caustic and surface impurities from the sleeves to the sewer. Spray rinsing is actuated by a solenoid valve and Cycle-flex timer located in the machine control panel.

3. Cold Water Submerge Rinse Tanks

Two submerge rinse tanks are equipped with a bank of water spray nozzles on each side and circulating water to further rinse the sleeves.

4. Soap Tank

The soap tank is provided with two Calrod heating elements located at the front of the tank. A steam coil is also used to bring the solution up to required temperature during start-up periods. An overflow sump in the tank maintains the soap solution at a constant level. A recirculating pump transfers the solution from the overflow sump back into the tank, keeping the solution thoroughly mixed.

5. Dryer Tank

This tank is equipped with two Chromalox air duct fin-type heaters, which are controlled by a Fenwal thermostat. The heaters are protected by thermal cutouts in case the automatic control fails. An air blast for the dryer is supplied by a Universal blower. The air duct built around the outside of the tank circulates warm air through the dryer. Drying temperatures may be varied from 25 to 100 C as required to remove surface moisture from steel sleeves.

C. STEEL SLEEVE HONING MACHINES

Two sleeve honing machines are located between the slug pickle and sleeve cleaning machines in the south end of 313 Building. They are used to remove burrs from the inner surface of steel sleeves and to correct minor dimensional distortion that may occur during the canning operation. All steel sleeves are gaged after being processed in the cleaning machine.

[REDACTED]

DECLASSIFIED

[REDACTED]

If a sleeve will not pass full length over a 1.447 in. gage mandrel it is routed to the honing operation.

The honing machines were manufactured by the Sunnen Company and are electrically driven. The drive motor is energized by a switch located at the upper left hand side of the motor. Rotation of the machine spindle is controlled by a foot-pedal combination clutch and brake.

The honing mandrel is attached to the spindle and has two cutting stones mounted end-to-end that hone the inner face of a steel sleeve when placed over the revolving mandrel. A 3/4 in. iron rod work support is mounted parallel with the mandrel to absorb torque surges and reduce operator fatigue. The feed dial, located on the upper right hand side of the machine, and a foot pedal control expansion and contraction of mandrel.

A 12 gallon honing oil sump tank is located under the operating tray of the machine. The oil is pumped through a flexible oil nozzle onto the mandrel and material being honed by a pump suspended in the sump. The volume of oil being pumped to the nozzle may be varied by a control knob located at the operator position.

D. SLUG RECOVERY EQUIPMENT

1. Caustic Receiving and Feed Tank

Two caustic supply lines are connected to the caustic receiving and feed tank, which is identified as tank No. 1 in the Slug Recovery Room (Figures XII-2 and XII-3). One line delivers used caustic solution from the sleeve cleaning machines and the other delivers used solution from the slug recovery treating tank.

An agitator is installed in the tank to keep the solution mixed. This agitator is activated by a pushbutton on the control panel. A steam coil is also installed in the tank to keep the caustic hot and in solution.

A transfer pump is used to pump the caustic solution to the pressure tank of the filter press or to the No. 2 storage tank. Solution can be pumped to

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1205-

HW 4908

either tank by adjusting a double take-off valve in the line. The pump is located at the east side of the receiving and feed tank and has a steam jacket to maintain the temperature of the caustic solution.

Solution level in the tank is indicated by a Manometer gage in the control panel. A zero to 30 psi pressure gage is also installed in the discharge line to indicate any back pressure created between the transfer pump and the storage tank.

A process water line is provided to reduce the caustic solution to the desired concentration. This line and valve are located at the top northwest side of the tank. Vapor and fumes are removed from the tank through an atmospheric vent line located at the top northeast side of the tank.

2. Used Caustic Storage Tank

An agitator is installed in the storage tank to keep the solution mixed while in operation. The agitator is activated by pressing the "Caustic Storage Tank No. 2" button on the control panel. A steam coil is also installed in the tank.

The transfer pump for moving the solution to the neutralizing tank is located at the east side of the tank. This stage of pumping is controlled automatically by the neutralizing tank level control. A double take-off valve from the pump is used to manually control any transfer of solution from the storage tank to the filter press pressure tank.

A process water line enters the top northwest side of the tank and an atmospheric vent is also provided to remove fumes. The solution level in the tank is indicated by a Manometer gage in the control panel.

3. Neutralizing Tank

This tank (Figure XII-4) has an agitator to keep the precipitate mixed and the concentration of the solution uniform during neutralization. The agitator is activated by pressing the "Acid Neutralizing Tank Agitator No. 3" button on the control panel.

DECLASSIFIED

DECLASSIFIED

The liquid level control is set to turn off the storage tank transfer pump when the neutralizing tank level reaches the half-full mark. This control is located on the top southeast side of the tank.

A pH cell on the east side of the neutralizing tank measures the conductivity of the solution depending on the hydrogen or hydroxyl ion concentration. This measurement is relayed to a pH meter in the control panel and is in turn relayed to a Wheelco Controller. This controller regulates the operating sequence of the transfer pump during the four-step cycle of the neutralizing process.

A cold water jacket surrounds the neutralizing tank to control the heat generated by the neutralizing reaction of the caustic and nitric acid. The water supply line and valve are located on the west side of the tank. A tube thermometer is installed in the discharge line from the cooling jacket to measure the temperature of the effluent water. This tank is also equipped with an atmospheric vent to remove fumes.

Ten Flowraters located in the control panel are adjusted to create static air between the tanks and level gages. A Manometer gage located below the Flowraters indicates the liquid level of the neutralizing tank.

4. Spent Pickle Acid Tank

The spent pickle acid tank is used to store spent nitric acid until it is transferred to the neutralizing tank. There are two incoming lines which enter at the upper north side of the tank. One line delivers acid from the slug pickle machines and the other from the tank farm.

A liquid level control is provided at the upper right hand side to prevent the tank from overflowing. This control automatically shuts off the transfer pump at the slug pickle machine when a predetermined level has been reached. An overflow line to the sewer trench is provided in case the automatic level control does not function properly.

A metering pump, east of the spent pickle acid tank, meters the spent acid to the neutralizing tank. This pump may be operated either automatically

[REDACTED]
DECLASSIFIED

DECLASSIFIED

-1207-

HW-40000

or manually. A Manometer gage is installed on the control panel to indicate the acid level in the tank.

5. Stripping and Treating Tanks

The stripping and treating tanks are mounted end-to-end along the south wall of the Slug Recovery room. They were originally designed to perform the stripping and treating operations interchangeably, and are nearly identical in construction. A caustic solution is used in the stripping tank (No. 6) to chemically remove the aluminum jackets from rejected canned slugs for recycling through the fuel element preparation process. The treating tank (No. 5) is filled with a more concentrated caustic solution to remove the compound AlSi layer from the slugs following the stripping operation.

There are three steam heating coils in each of the tanks. A large steam coil in the bottom is supplemented by coils mounted vertically on the front and back side of each tank. These coils are made of stainless steel pipe.

There are two banks of hot water spray nozzles in the upper portion of each tank. These nozzles are actuated by a long-handled manual valve to facilitate operation from the front side of the tank.

Nitrated caustic solution and 50% caustic solution are piped from the tank farm to the tanks through 3 in. insulated lines in a covered trench.

The used caustic from the treating tank is piped to a Labour pump located behind the floor sump. This pump transfers the solution to the No. 2 caustic receiving tank. A steam line enters the tank drain line just ahead of a manual valve to supply an agitating action in the tank. The stripping tank drains through a manual valve into the sewer trench. The piping is arranged so the solution from this tank may also be pumped to the caustic receiving tank for neutralization if required.

Both tanks are equipped with top doors, elevated on the back side and have counterweights to facilitate easy opening. Each tank is equipped

DECLASSIFIED

DECLASSIFIED

-1208-

HW-40009

with a large exhaust vent and duct. A Robbins and Meyers two ton mono-rail crane is provided to transfer slugs through the tanks.

6. Pressure Feed Tank

The pressure feed tank (Figure XII-5) is located between the neutralizing tank and the filter press and was manufactured by the Birchfield Boiler Company. This tank is designed to supply the pressure necessary to force the neutralized solution through the filter press.

The solution from the neutralizing tank enters the pressure tank on the upper right side and is discharged at the bottom. Air pressure is supplied through a regulated line. A relief valve is provided to prevent the pressure to the tank from becoming excessive.

7. Filter Press

The filter press (Figure XII-6) is mounted on an angle-iron framework with a platform on three sides. It was manufactured by the D. R. Sperry Company. Two large cast iron end plates are separated by approximately 60 cast iron filter plates that have filter cloth interlaced between them.

Pressure to seal the outer edges of the plates is supplied by a manually operated hydraulic jack located at the east end of the press. When the "cakes" of uranium compound are unloaded from the press the jack must be swung aside to move the end plates back. A counter weight is provided to facilitate handling the jack during the unloading operation.

A line from the pressure tank enters the filter press at the upper corner of the stationary end plate. The filtered solution leaves the press through individual drains at the bottom corner of the plates. Solids are pressed into large "cakes" between the layers of filter cloth and a drip pan is provided beneath the press to catch any solution leakage and pass it to the floor drain.

DECLASSIFIED

DECLASSIFIED

-1209-

E. TANK FARM

The 303-F solution make-up building is divided into three rooms with insulated fire doors as shown in Figure XII-7. The rooms are utilized as follows: (a) Diversey mixing and pumping, and sulfuric acid pumping station, (b) Caustic mixing and pumping, and nitric acid pumping station, and (c) Sodium nitrate storage.

(a) The diversey mixing tanks (Figure XII-7) are large cylindrical stainless steel vessels equipped with Lightnin Mixer agitators. The agitators are set at an angle of about 20° from the vertical position. Each tank is covered with a hinged lid, which may be opened by a lever arm on the right hand side of the lid. Counter weights on the opposite end of the lever arms facilitate opening the lids.

The diversey solution is drawn from the tank by a Worthington pump in the northeast corner of the room. Mounted parallel with the main pump is a small metering pump designed to supply a small amount of diversey to the cap and can machines at a constant flow.

The sulfuric acid pump, located at the left of the diversey pumps, receives the acid from a barrel mounted on a rack. The diversey and sulfuric barrels are handled by a 1/2 ton monorail crane which moves on an overhead track above the tanks and pumps.

(b) The two caustic mixing tanks, located in the center room, are steel tanks equipped with Eastern mixer agitators and hinged covers. Each tank is provided with a gage glass to indicate solution level.

Fifty per cent caustic flows by gravity to the mixing tanks from the large storage tanks east of the building. After the solution has been diluted and mixed with sodium nitrate it is pumped to the treating tank in the Slug Recovery. The caustic pumps are located in the northeast corner of the room and were manufactured by the Ingersoll-Rand Company.

Nitric acid pumps, located in the southeast corner of this room, pump nitric acid from the main storage tanks to various operations in 313 Building.

DECLASSIFIED

DECLASSIFIED

-1210-

HW 40000

(c) The third room is reserved for storage of sodium nitrate. This material is received and stored in 100 lb. burlap bags and is kept in a fire-proof storage room separate from the other chemicals until it is loaded into a hopper and dumped into the caustic mixing tank.

F. DEGREASER SOLVENT STILLS

There are four degreaser solvent stills at strategic locations in the 313 Building. The purpose of these stills is to separate impurities and water from the solvent. Stills are provided at each of the final etch machines, one for the cap and can machine and one at the slug pickle machines. A typical still is shown in Figure XII-8.

Each solvent still has a boiling compartment, equipped with steam coils, that vaporizes the solvent. The boiling compartment is in the bottom chamber of the still and has two sight ports for a view of the solvent reaction. A liquid level gage is also installed on the outside wall of the boiling compartment to indicate solvent level. An automatic float in the compartment shuts off the transfer pump located on the degreaser when a predetermined level has been reached in the boiling compartment.

The solvent vapor from the boiling compartment rises around a circulating water coil in the top chamber of the still and is condensed into a liquid. Water separation is accomplished by allowing the water to drain from the top of the solution into a water box. A storage tank outside of the still receives the solvent from the water separator.

Each still is provided with a selective switch for manual or automatic action. Manual operation is selected by turning the two switches on the control panel to the left hand position. The automatic position is selected by turning the same two switches to the right hand position. The control float switch described above is energized only when the still selector switches are on the automatic position. Each still is equipped with a pump to transfer reclaimed solvent from the still storage tank to the degreaser storage tank. This pump is activated by a level float control in the still storage tank.

DECLASSIFIED

DECLASSIFIED

-1211-

HW-10000

G. HEVI-DUTY RESISTANCE FURNACES

The Hevi-Duty resistance furnaces in the canning area are used for metal recovery, salt bath heat treating and outgassing. These furnaces are supplied with 480 V 3-phase power through circuit breakers in "F" type control centers. Transformers reduce the initial voltage to 192 volts across the resistance elements.

The construction details of the Hevi-Duty resistance furnace are shown in Figure XII-9. A heavy metal shell provides a rigid housing in which the components of the furnace are contained. Inside of the metal shell a thick layer of magnesia insulating blocks are installed as a barrier to heat transfer from the hot refractory lining. Moving inward, toward the center of the furnace, the next component is a poured liner of refractory cement for the purpose of further curbing the heat transfer to the outer shell. A sand layer in the bottom helps contain metal spills and prevents spilled metal from adhering to the floor lining. The sand layer also provides a base on which the brick, used to support the crucible pedestal, may be leveled.

The electrical elements enter the furnace through the sides and extend through the various heat barrier layers to the element refractories, where insulation is provided for mounting the elements, and heat is reflected inward toward the crucible. Air vents are provided above the refractories through the furnace cover to allow an escape route for gases generated in the furnace.

A pedestal provides support and height adjustment for a flanged graphite crucible. The flange of the crucible extends over the edge of the refractory cement in the furnace cover and rests on a magnesia seal and ring to provide a thermal barrier between the crucible and cover. An element thermocouple extends through the side of the furnace and relays heat to the sensing instruments in the control panel. An air-and-metal vent hole penetrates the bottom sand layer through which gases may be expelled.

DECLASSIFIED

DECLASSIFIED

-1212-

HW-40000

H. MUFFLE FURNACE

The muffle furnace located in the thermal analysis room is a 27 KW, 48OV resistance type furnace. It is used to burn out new crucibles, heat metal samples, and to pre-heat used crucibles. The furnace is mounted on an angle iron framework and is equipped with a multi-tap transformer. A manually operated chain winch is used to open an insulated door on the front of the furnace. The heating elements are connected to the low side of the multi-tap transformer, which operates on the same principal as an electrical rheostat.

Temperature is controlled by a Leeds and Northrup controller located in the control panel. A red pointer on the instrument is set at the desired temperature and a black pointer indicates the actual furnace temperature. When the temperature reaches the red-pointer setting, power to the furnace elements is automatically shut off until the temperature drops below this setting. A recording instrument in the control panel provides both a visual and chart recording of the temperature variance.

DECLASSIFIED

FIGURE XII-1 STEEL SLEEVE CLEANING MACHINE

UNCLASSIFIED

HW-40000

FIGURE XII-2 SLUG RECOVERY ROOM

UNCLASSIFIED

UNCLASSIFIED

1. RECEIVING & FEED	6. STRIPPING TANK
2. CAUSTIC STORAGE	7. QUENCH TANK
3. NEUTRALIZING TANK	8. FILTER PRESS
4. PICKLE ACID	9. CONTROL PANEL
5. TREATER TANK	10. WATER TANK

UNCLASSIFIED

FIGURE XII-3 SLUG RECOVERY ROOM

HW-40000

UNCLASSIFIED

HW-40000

1-Water to Jacket
2-Agitator
3-Vent
4-From Acid Tank
5-Level Control

6-From Caustic Storage
7-Flush Tank
8-pH Cell
9-Water In
10-Neut. Soln. to Press.
Tank

11-Pressure Gage
12-Cell Circ. Pump
13-Soln. Transfer Pump
14-Neutralizing Tank

FIGURE XII-4 NEUTRALIZING TANK

UNCLASSIFIED

1-Access Cover
2-Air Inlet
3-Solution Inlet

4-Pressure Tank
5-Isolation Valve
6-Pressure Regulator
(air)

7-Pressure Release
Valve
8-Isolation Valve
9-Air Supply Line

FIGURE XII-5 PRESSURE TANK

UNCLASSIFIED

UNCLASSIFIED

UNCLASSIFIED

- 1-Shut-off Valve
- 2-Isolation Valve
- 3-End Plate (stationary)

- 4-Cake Plate
- 5-Waffle Plate
- 6-Adjustable End Plate

- 7-Hydraulic Mech. Counter-balance
- 8-Hydraulic Pressure Mechanism
- 9-Screw-twin
- 10-Drip and Cake Unload Tray

FIGURE XII-6 FILTER PRESS

HW-40000

AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910

301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

5 of 6

UNCLASSIFIED

FIGURE XII-7 LAYOUT OF TANK FARM AND STORAGE TANKS

UNCLASSIFIED

HW-40000

FIGURE XII-8 DEGREASER SOLVENT STILL

UNCLASSIFIED

FIGURE XII-9

RESISTANCE-RECOVERY FURNACE DETAILS

DECLASSIFIED

-1301-

HW-40000

PART V: PROCESS CONTROL AND IMPROVEMENT
CHAPTER XIII: INSTRUMENTATION

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION	1302
B. TEMPERATURE CONTROL	1302
1. Induction Furnaces	1302
2. Resistance Furnaces	1305
3. Cleaning and Recovery Solutions	1307
4. Building Heating	1310
C. FLOW AND PRESSURE CONTROL	1311
1. Welding Machines	1311
2. Hydraulic Presses	1311
D. OTHER CONTROLS	1312
1. Timers	1312
2. Chemical Control	1313

DECLASSIFIED

DECLASSIFIED

A. INTRODUCTION

The manufacture of fuel elements and special products requires several types of control instruments. These instruments are used to control process temperatures, flows, pressures, time cycles and solutions within specific limits. Such controls are necessary to insure uniformity and high quality of finished products.

B. TEMPERATURE CONTROL

1. Induction Furnaces

The furnaces used in the canning operation are low-frequency induction furnaces built by the Ajax Engineering Corporation. Heat is induced in the molten metal by a coil, which surrounds one leg of a "U" shaped channel containing a small part of the melt. The coil is essentially one winding of a transformer and the channel acts as a shorted secondary. Two induction furnaces are used in each canning line; a duplex slug pre-heating furnace and a canning assembly furnace. The two are identical in construction and operation, but differ in function and control.

The temperature of each molten metal is sensed by a thermocouple, which is the junction of two dissimilar strands of metal wire. The positive wire is made of iron as free of impurities as possible. The negative wire is made of an alloy called "Constantan" which contains 60 per cent copper and 40 per cent nickel. This is known as an iron-Constantan thermocouple. The junction of the two wires is placed in a stainless steel tube or well to protect it from the corrosive effects of the molten metal baths.

An electromotive force (emf) is generated at the thermocouple junction and, as the bath temperature increases, the emf is increased. The relationship of emf to temperature is not truly linear, but in the narrow span used to control bath temperature, the error caused by assuming a straight line relationship is negligible. An emf of approximately 0.055 millivolts per degree centigrade is generated by the iron-Constantan thermocouple. The

DECLASSIFIED

DECLASSIFIED

-1303-

HW-40000

[REDACTED]

emf generated by a thermocouple placed in a canning bath is compared to the emf generated at the "cold junction", which is the completion of the loop formed by the two dissimilar wires. The difference in emf is amplified electronically, and used to control the furnace.

The furnace control has three power positions; high power, intermediate power and low power. To control the power being applied, there are two set points on the control instrument. They are moved as a unit by a knob on the outside of the instrument panel to obtain the desired mean operating temperature. Moving the points closer together or farther apart changes the range of temperature variation around the mean temperature. At temperatures below the lowest set point the furnace operates on high power. When this set point is passed the controller is automatically changed, through a micro switch and set of relays, to intermediate power. If the temperature continues to rise and passes the second set point, the controller automatically switches to low power. As the temperature falls the controller is switched from low to intermediate and then to high power as each set point is passed.

At each of the three control positions several power taps are available. A power tap is selected for low power which will produce less heat than the minimum heat loss from the furnace. A value for high power is selected to be greater than the greatest heat loss under normal operation. The intermediate tap is set to give approximately the heat needed under normal operation. Thus a furnace continuously switches between the three power settings, depending on heat losses resulting from operation.

The instrument used for controlling the induction furnace is a type G Model R Speedomax, manufactured by the Leeds and Northrup Company. The Speedomax controller, in conjunction with the Ajax induction furnace, is capable of maintaining a bath temperature within a maximum range of 1.5 C. This applies to each canning bath under normal operating conditions.

The slug preheating furnace contains two molten metals; a 10 to 12 in. layer of AlSi floating on top of lead. Separate thermocouples are used to measure

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1304-

HW-40000

the temperatures of the two metals. Each thermocouple tip is carefully positioned in the duplex bath on the inductor channel side of the hearth, one to four inches from the furnace wall. The thermocouple in the AlSi is submerged five to eight inches below the surface of the bath; the thermocouple in the lead extends five to eight inches below the interface of the bath. Both temperatures are recorded but only the lead temperature is used for control. The lead bath temperature is adequate to maintain the AlSi temperature within the limits outlined in the process specifications and standards.

When induction furnaces were initially used to preheat slugs in the canning operation, the AlSi temperature was used for control. The comparative simultaneous temperatures of the two metals are shown in Figure XIII-1. The large variation in lead temperature indicated that the slugs were not being uniformly heated; variances in slug temperatures were as much as 7°C. When the control thermocouple was moved to the lead layer the temperature variation of the lead was markedly reduced and the AlSi temperature variation was slightly reduced. This case is shown in Figure XIII-2.

Each canning assembly furnace contains two thermocouples; one is used to measure and control the bath temperature and the other functions as part of an over-temperature protection device. The controlling thermocouple is centered on the inductor channel side of the hearth, three to five inches from the furnace wall, and is submerged six to eight inches below the bath surface. To obtain consistent temperature measurements, this thermocouple well is held in a clamp that does not permit movement from the set position. The furnace controller is the same type of unit used for the duplex furnace and the Iron-Constantan thermocouple is protected by a silicon-carbide well rather than the stainless steel well.

A yellow warning light and a red process limit light are located on top of the control cabinet for each canning furnace. These lights are operated by micro-switches on the Speedomax indicator. The red light is set to

DECLASSIFIED

DECLASSIFIED

HW 40060

go on when the maximum specified bath temperature is reached. Any material canned while the red light is on is rejected as "off-process". The yellow light is set to go on about 1 C before the process limit is reached and serves as a warning that the bath temperature is approaching the upper limit.

The over-temperature device is connected to the furnace controls to prevent damage that may occur if the furnace remains on high power for a long period of time. This protection device is set to operate at a temperature about 50 C to 75 C higher than normal operating temperature. When the bath temperature reaches the set point, the protector changes the furnace control to low power. The thermocouple for this device is an eight gage iron-Constantan couple in a silicon-carbide well. The thermocouple is positioned in the furnace beside the thermocouple used to control the bath temperature within process limits.

Two induction furnaces are installed in the recovery area. Their primary purpose is to melt AlSi and aluminum collected from the facing operation and other points in the process. The alloy is adjusted to specifications by adding elemental silicon and returned to the canning process for reuse. These furnaces also serve as a spare canning line, and are therefore, equipped with the same controls as the other induction furnaces.

2. Resistance Furnaces

Two Hevi-duty resistance furnaces are installed in the recovery area for the salt bath heat treating of bare uranium slugs. Each of the furnaces contain three nichrome resistance elements. They have two thermocouples; one in the molten metal or salt and the other in the shell of the furnace near the bottom of the heating elements. The element thermocouple is used to control the furnace and the bath thermocouple acts as an over-temperature shut-off device.

The thermocouples are made from chromel and alumel wires. Chromel is an alloy of approximately 90 per cent nickel and 10 per cent chromium. Alumel is an alloy containing 94.5 per cent nickel, 2.5 per cent manganese,

[REDACTED]

DECLASSIFIED

2 per cent aluminum and 1 per cent silicon. Fourteen gage wire is used for the bath thermocouple and eight gage wire is used for the element thermocouple. The element thermocouple is protected by a ceramic thermal well and the bath thermocouple is protected by a stainless steel well.

The emf generated by each thermocouple is transmitted to a Leeds and Northrup "Micromax" controller. The element temperature is indicated, but not recorded, while the bath temperature is both indicated and recorded.

Only one set point is used, and when the element temperature is below this point the furnace power is turned on. When the temperature is above this point the element power is off. There is no proportioning device incorporated in this unit. Due to the lag in heating and cooling the elements, bath temperatures are not as accurately controlled as in the induction furnaces. A spread of 6 C or 7 C is not uncommon under operating conditions.

The temperature controllers and recorders are checked with a standard millivolt box, which is a Leeds and Northrup No. 8662 box connected to fourteen-gage chromel-alumel thermocouples. The cold junction is maintained in an icewater bath for absolute reference. The older standard boxes are calibrated in millivolts and the temperature is obtained by comparing millivolt reading to a chart supplied. The newer standard boxes are calibrated once each week to make certain they are within the allowable tolerance of error, and newly calibrated thermocouples are also supplied once a week. The production furnace instruments are checked with the boxes at least once every four hours. The reproducibility of the standard box, even with different instrument personnel operating it, has been found by experience to be within a half a degree centigrade. When the standard box is used to check the furnace recorder, no change is made in the recorder if there is one-half of one degree or less temperature difference between the two. A total test

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1307-

HW-40000

consists of three temperature checks, and the average of the three is used to judge the accuracy of the recorder.

Small bucket furnaces with resistance heating elements are used to transport samples of molten AlSi from the canning furnaces to the thermal analysis room where the sample is analyzed for silicon content. The analysis consists of graphically plotting temperature versus time to determine the difference between the liquidus and solidus temperatures of the melt. This difference, in degrees, is a measure of the quantity of silicon contained in the sample. The bucket furnaces are controlled by a twenty gage Chromel-Alumel thermocouple and a Brown indicator controller. The temperature of the AlSi is recorded by a Brown strip chart recorder and sensed by a 14 gage Chromel-Alumel thermocouple.

The furnaces used in the hot press canning process are made up of simple resistance heater elements which surround cylindrical solid dies. A fourteen gage iron-Constantan thermocouple is placed at approximately the center of each die heater. The emf of the thermocouple is used to control the furnace temperature with a Leeds and Northrup Derivation Action Type (DAT) Controller. This controller contains a proportioning device which partially corrects for the time lag in heating the resistance elements and prevents overshooting. As the temperature approaches the set point, the current is gradually changed to provide power to the heating elements approximately as needed to maintain the canning dies at process temperature.

3. Cleaning and Recovery Solutions

Only two temperatures are controlled in the Slug Recovery operation and both are controlled manually. They are the temperature of the caustic stripper solution, which dissolves the aluminum caps and cans from reject canned fuel slugs, and the temperature of the treater solution, which removes the compound layer from the slugs following treatment in the stripper solution. The temperature of each solution is sensed by a pressure bulb, transmitted to a recorder by a capillary tube and indicated by a pointer

DECLASSIFIED

DECLASSIFIED

attached to a spiral pressure spring. The pressure from the capillary tube acts on the hollow spiral spring to move the pointer. The pointer is attached to a pen which traces a record of the temperature on a twenty-four hour circular chart.

The temperature controls on the sleeve cleaning machine, the cap and can cleaning machine and the canned slug etch machine are essentially the same and can be described in common terms. Each machine has a manual control panel which contains a Foxboro Dynalog multi-point temperature recorder. The temperatures detected by the thermocouples of the Foxboro are not used for control purposes although the recorder does have a temperature warning feature for each solution or dryer temperature being recorded. If any temperature exceeds a set limit, a light is turned on above the recorder. There is a separate, labeled light for each temperature being recorded. The temperature of each solution or dryer is transmitted to the Foxboro instrument by a fourteen gage iron-Constantan thermocouple.

Temperatures at several points in these machines are controlled by Fenwal thermostats (thermoswitches). The thermostats are an adaption of a bimetallic strip which controls an electrical device through changes in ambient temperature. The electrical device may be a relay which energizes an electric resistance heater or it may be a solenoid which opens or closes a valve in a steam line. A cylindrical brass case acts as one part of the bimetallic element and two nickel-iron alloy (invar) struts act as the non-expanding part of the element. The relative motion between the two causes a set of electrical contacts to open and close.

A Fenwal thermostats is used to control the temperature of the caustic in the sleeve machine, controlling both steam heat and electric heat. When the machine is started after being on standby for any length of time, a solenoid valve opens to admit steam to two panel heaters submerged in the caustic. At the same time, a bank of 18 Chromalox immersion heaters are energized. As soon as the set temperature has

[REDACTED]

DECLASSIFIED

DECLASSIFIED

-1309-

HW-40000

been reached, the Fenwal thermostats close the steam valve and shut off the electric heaters. Subsequent heating of the solution by the immersion heaters is controlled by the thermostats. The steam remains off until the solenoid valve is reactivated by a pushbutton on the control panel.

The soap rinse in the sleeve machine, the duPont in the cap and can machine, and the acid in the etch machine are heated in essentially the same way as the caustic, except that these solution tanks are each equipped with two Calrod immersion heaters.

Sleeves, caps and cans, and canned slugs are dried by hot air which is blown over them by a large squirrel-cage type blower. The air is heated by two 30 kw Chromalox resistance heaters. The heaters are controlled by a Fenwal thermostat, and in the event of a failure of the Fenwal, there is a pressure operated over-temperature control. A bulb is placed in the air stream above the heaters and if the air temperature gets too high the pressure of the expanding liquid in the bulb, acting through a capillary tube, will shut off the heaters.

The temperature of the boiling solvent in the trichloroethylene degreaser, both in the sleeve machine and in the cap and can machine, is controlled by a mechanically operated valve in the steam heating line. Pressure created by expansion of a liquid is used to control the steam valve. A liquid filled bulb is immersed in the solvent and the liquid expands with increasing temperature. A capillary line conducts the expanding fluid to a bellows. The pressure of the liquid acting against the large area of the bellows is capable of closing the steam valve. When the temperature falls, a spring returns the valve to its manual position. A similar device installed in the degreaser condensing jacket line maintains a steady effluent water temperature. The temperature sensing bulb is located at the discharge side of the cooling jacket and the pressure operated valves are on the inlet side.

The degreaser solvent in the slug pickle degreaser is also steam heated and the temperature is controlled by a Minneapolis-Honeywell Modutrol controller.

DECLASSIFIED

DECLASSIFIED

-1310-

HYC 4800

This controller has a small reversible motor which drives the steam valve. As the temperature of the solvent falls the Modutrol causes the motor to open the steam valve. The temperature is sensed by a pressure bulb and transmitted by a capillary tube.

4. Building Heating

The 313 Building is heated and ventilated primarily through seven air conditioning units. Each unit has a capacity of 20,000 cfm and is controlled by a Bristol duplex recorder-controller. A schematic diagram of the control equipment is shown in Figure XIII-3. For winter heating, air is drawn through the filter and into the pre-heater which heats the air to 55 F by steam heated coils. Temperature is sensed by a liquid filled pressure bulb located in the air stream on the exit side of the preheater. Pressure from this bulb is changed to an electrical impulse by the Bristol controller; the electrical impulse operates a solenoid valve in the steam line to the preheater.

The preheated air goes through the air washer, which further cleans the air and saturates it with water vapor. The air leaving the air washer is usually between 40 F and 50 F with relative humidity of 90 to 100 per cent. The air is then heated in the re-heater to the desired room temperature (usually 68 to 72 F). Heating the air without any change in total water vapor content results in relative humidity of the room air of 40 to 55 per cent, which is generally considered most desirable.

Temperature of the air supplied to the building is controlled by the amount of steam which passes through the reheater coils. Steam flow is controlled by a solenoid valve operated by the Bristol controller. A liquid filled pressure bulb located in the air stream actuates the controller.

For summer cooling, all steam is shut off and the air washer serves as an evaporative cooler. Temperature and humidity are not controlled.

DECLASSIFIED

DECLASSIFIED

-1311-

HW-40000

C. FLOW AND PRESSURE CONTROL

1. Welding Machines

Argon flow to the heads of the production welding machines is controlled by a manually operated valve. This valve is adjusted to produce the proper gas flow as measured by a flow meter or "rotameter". The rotameter is a tapered glass tube with a steel ball which is forced upward by gas flow. The tube is graduated for reading flow directly in cubic feet of gas per hour.

Cooling water flow through the welding torch is also regulated by a manually operated valve. However, a pressure operated switch is installed in the water line to avoid damage to the torch in the event of a water failure. If the water pressure in the cooling line drops below a predetermined amount the pressure switch opens the welder circuit to extinguish the arc.

2. Hydraulic Presses

The hydraulic presses used in the hot-press canning operation require different pressures for each of three separate process functions. In addition, a positive pressure must be maintained on the hydraulic lines at all times. Pressures produced by the pumps are reduced to required values by two types of special valves.

The highest operating pressure (1500 psi) is used to "break"* the dies loose from the press sleeves. Pressure is controlled by an "unloading" valve; that is, the pressure is built up by the hydraulic pump until the required pressure is reached, at which time the valve opens allowing the fluid to recirculate through the pump. The same type of unloading valve is used to maintain a positive head on the hydraulic lines and to supply pressure required to "set" the dies.

The "cure" pressure required during hot pressing is supplied through a pressure reducing valve. This valve maintains a constant pressure on its outlet side by bypassing the excess pressure from its inlet side.

* Accepted terminology for the three pressing operations are "set", "cure", and "break". These would correspond to (1) seating the dies, (2) pressing at temperature and (3) ejecting the pressed assembly from the dies.

DECLASSIFIED

DECLASSIFIED

D. OTHER CONTROLS

1. Timers

Electrically operated timers are used in several locations to control process equipment. The one most commonly used is the "Cycle-flex" timer made by the Eagle Signal Corp. It consists of a synchronous motor, equipped with a dial and reset handle and contacts which close when the timed cycle is completed. After the desired time interval is set, the timer is started manually or automatically and closes a circuit at the end of the time cycle.

"Cycle-flex" timers are used to control the immersion time (and thus the entire cycle) of the Udylite cap and can cleaning machines, sleeve machines, and etch machines. At the end of each cycle, relays operated by the timer close and cause the transfer mechanism to raise. Each part of the transfer cycle is started by relays operated by limit switches. As the last part of this cycle is completed, a limit switch is closed and through a relay causes the cycle-flex timer to start a new cycle.

A similar timer on the radiograph machine controls the X-ray exposure (time) of the film. When a loaded tray of canned slugs is placed in the machine and the doors closed, current to the X-ray tube is turned on and the timer is simultaneously started by limit switches on the doors. At the end of a preset time (about 7 seconds) the timer stops the current flow to the X-ray tube and starts the slug rotating mechanism. After the canned slugs are rotated 120° and the film is indexed to its next position, the X-ray tube and timer are again energized. This cycle is repeated until three exposures have been made, at which time the cycle is completed and the doors are opened.

The X-ray film is developed in a Pako automatic film processing machine. Cycle times of this machine may be changed in small increments by changing the gear train of the transfer mechanism.

[REDACTED] [REDACTED]

DECLASSIFIED

DECLASSIFIED

-1313-

HW-40000-3

2. Chemical Control

A diagram of the Slug Recovery Panel (Figure XIII-4) indicates the types of instruments used in the caustic stripping (decanning) of rejected canned slugs and the recovery of certain process solutions. The temperature recorder, described briefly elsewhere in this chapter, is not used for process control. Manometers indicate the liquid level in several tanks, and one is used to measure the specific gravity of caustic in the feed tank. The pH meter and Wheelco controller are a part of the automatic neutralization equipment described in the following paragraphs.

The nitric acid from the slug pickling operation is neutralized to recover the uranium dissolved in the acid. Sodium hydroxide from the slug recovery operation is used to neutralize the acid since it also contains uranium.

When the neutralization cycle is started (by a pushbutton on the control panel) nitric acid is pumped into the neutralizing tank and a motor driven agitator is operated throughout the cycle. When the acid reaches a level of eight inches, the acid pump is shut off and the caustic pump is started. Caustic is then pumped into the tank until the pH is raised to three, at which time the pump is stopped and a timer is started. A five minute time interval is included at this point to allow time for digestion of the solutions. After the five minute digestion period, the timer starts the caustic pump and sodium hydroxide is added until a pH of 11 to 13 is reached. This completes the cycle and the caustic pump and agitator is stopped. The solution is later pumped through a filter press to remove the uranium bearing salts.

The pH meter and the Wheelco controller are driven by the same signal. The meter is an indicator of pH and the controller indicates arbitrary units which are directly proportional to pH. There are two set points on the controller; one at a pH of 3 and the other at a pH of 11 to 13. At each of these points there is a split oscillator. When the pointer reaches the set point, a small coil attached to the pointer passes between the halves of the oscillator. This interrupts the oscillation causing the control relays to operate.

DECLASSIFIED

DECLASSIFIED

-1314-

HW-40000

The pH of the solution is determined by a Beckman pH instrument which consists of two electrodes, immersed in the solution. One of the two electrodes, which are immersed in the solution, is a glass bulb containing a solution of known and constant pH. The emf generated between this solution and the test solution is directly proportional to the pH of the test solution. A resistance thermometer is immersed in the solution with the electrodes for the purpose of correcting the pH readings for changes in solution temperature.

DECLASSIFIED

DECLASSIFIED

FIGURE XIII-2 LEAD vs AL-SI TEMPERATURE (lead controlled)

FIGURE XIII-1 LEAD vs AL-SI TEMPERATURE (Al-Si controlled)

HW-40000

DECLASSIFIED

FIGURE XIII-3

CONTROLS-313 BUILDING AIR CONDITIONING UNITS

- 1-Tank #3 High Pressure
- 2-Tank #3 Reference
- 3-Tank #1 Low Pressure
- 4-Tank #1 High Pressure
- 5-Tank #1 Reference
- 6-Tank #2 Low Pressure
- 7-Tank #2 High Pressure
- 8-Tank #2 Reference
- 9-Tank #4 High Pressure
- 10-Tank #4 Reference

- 11-Rotometer Flowrator
- 12-Temperature Recorder
- 13-Wheelco Recorder
- 14-Neut. Cycle Stop Switch
- 15-pH Meter
- 16-Pushbutton Controls
- 17-Nitric Pump Stop Switch
- 18-Spent Pickle Manometer
- 19-Used Caustic Manometer
- 20-Rec. & Feed Manometer

21-Neut. Tank Manometer

FIGURE XIII-4 SLUG RECOVERY CONTROL PANEL

UNCLASSIFIED

DECLASSIFIED

-1401-

HW-40000

PART V: PROCESS CONTROL AND IMPROVEMENT (Contd.)

CHAPTER XIV: QUALITY AND STANDARDS

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION	1402
B. ACCEPTANCE TESTS	1402
1. Bare Slugs	1402
2. Recovered Slugs	1404
3. Caps and Cans	1405
4. Other Essential Materials	1406
5. Screening	1407
C. FUNCTIONAL TESTS OF COMPONENTS	1407
1. Reactivity Tests	1408
2. Chemical Tests	1408
3. Wetting and Blister Tests	1409
4. Controlled Canning Test	1410
D. IN-PROCESS TESTING AND INSPECTION	1411
1. Quench Inspection	1411
2. Length Inspection	1411
3. Braze Inspection	1412
4. Weld Inspection	1412
5. Penetration and Bond Testing	1413
6. Radiograph Inspection	1413
7. Autoclave Testing	1414

DECLASSIFIED

A. INTRODUCTION

Stringent standards of quality must be applied in the manufacture of fuel elements to insure the ability of the finished product to withstand severe reactor operating conditions. All components and essential materials are subjected to acceptance tests to assure conformance with specifications. Statistical sampling methods are utilized as much as possible without sacrificing the quality of the final product. Assembled fuel elements are subjected to varied tests and inspections to maintain the highest possible degree of uniformity and quality.

B. ACCEPTANCE TESTS

1. Bare Slugs

Bare uranium slugs are received from the Feed Materials Production Center (FMPC) at Fernald, Ohio, in railroad freight cars. The slugs are divided into lots of convenient size for processing, and an attempt is made to maintain homogeneity of metal type in each lot. Uranium completely processed at FMPC is assigned a "K" lot number, and uranium cast by the Mallinckrodt Chemical Works at St. Louis, and rolled and machined at FMPC is assigned an "M" lot number. These two categories constitute the bulk of present production. Other types of material are identified by a different series of letters.

As soon as the boxes of slugs are removed from the freight car, the cover of each box is removed, and a statistical sample is taken and transferred to Inspection. The sample size is specified in the Process Standards (HW-22556) and varies from 16 pieces for a lot of 250 slugs to 78 pieces for a lot of 6,500 - 10,000 slugs. To assure a representative sample, an equal number of slugs is taken from each box, and the sample should not contain more than two slugs from any one rod. This can be readily accomplished since each bare slug is stamped with the ingot number, rod number and slug number within the rod.

Inspection measures each slug in the sample for diameter, length, and

[REDACTED]

DECLASSIFIED

weight. The diameter is measured with an electrical comparator which is accurate to within a few hundred-thousandths of an inch, although the diameter is recorded to the nearest ten-thousandth. The length is measured with a dial indicator held in a jig, and recorded to the nearest thousandth of an inch. Both the electric comparator (sometimes called a "shadow graph") and the dial indicator are set with field grade gage blocks. The weight of each slug is measured in grams. In addition, the samples are also examined to insure that the end edge radius meets Process Standards and that the surface roughness is less than 250 microinches, rms.

The information obtained on the samples from each lot of slugs by the Inspection Unit is analyzed by a Quality Control Statistician, who computes the average and standard deviation for each of the measurements submitted; i. e., diameter, length and weight. From the average length and diameter measurements and the standard deviation for each slug, the statistician computes acceptance data and either accepts or rejects the lot on the basis of this information.

The weight data sent to the statistician are not used for control purposes, but rather for accountability. An average weight, with a tolerance, is computed for the slug samples from each shipment at a 99 % confidence level. Based on these figures, total weight of slugs received is calculated and used to confirm or deny the shipper's weight.

When all measurements on a lot sample are completed by Inspection, eleven slugs are transferred to the 305 Test Reactor for reactivity testing. An additional slug is transferred to Quality Control for destructive testing. This slug is first tested on the ultrasonic transformer tester and then cut transversely into five wafers for density, chemical composition, grain size and grain orientation tests. One wafer is polished and macroetched to determine the average grain diameter at the center and at the edge. A macrophotograph is taken for a permanent record. The depth of intergranular network on the surface of this wafer is also measured. Another wafer is cut longitudinally

DECLASSIFIED

DECLASSIFIED

-1404-

HW-40000

and etched to show the inclusions present in the metal. Pieces punched from a thin wafer are used to determine the density of the metal. Chemical analyses are described elsewhere in this chapter.

The information obtained from the destructive tests outlined above is not used for strict quality control purposes in the sense that a lot of slugs can be accepted or rejected on the basis of the results. The data are closely monitored to insure that the uranium conforms with specifications. In addition, they serve as a check on similar information supplied to HAPO by the Mallinckrodt Chemical Works and the National Lead Company.

Warp measurements are also taken on all slugs in a statistical lot sample, but the data are not used in the same manner as length and diameter measurements. A lot is accepted or rejected on the basis of an attributes sampling plan. According to this plan each slug is classified as a reject or accepted, as indicated by the warp gauge. Length and diameter variations are controlled by a variables sampling plan in which an average outgoing quality limit (AOQL)* of 5 per cent is used. Under this plan the actual measurements are taken and recorded to compute acceptance data. Since length and diameter have both upper and lower limits, the sampling plan has been modified from a one-sided to a two-sided plan.

2. Recovered Slugs

Canned reject slugs, which are removed from the production stream at various operations, are sent to Slug Recovery where they are chemically stripped for recanning. A statistical sampling plan is used to accept or reject each lot of recovered slugs. After a lot of slugs has been accumulated, it is transferred to the Materials Unit for sampling and storage. A random sample which varies in size from 20 to 85 pieces is taken from lots containing 300 to 10,000 pieces. The sample is turned over to the Inspection Unit and visually inspected for unremoved compound layer

* The term, average outgoing quality limit or AOQL, is a statistical term defined as "the maximum average percentage of defective items in the product that is finally accepted if all rejected lots are screened and resubmitted" Sampling Inspection by Variables, A. H. Bowker and H. P. Goode. New York: McGraw-Hill (1952) p. 31.

DECLASSIFIED

DECLASSIFIED

-1405-

HW-40000

and measurements of both weight and warp. An attributes sampling plan is used to reject the lot for unremoved compound layer. If the sample is acceptable, from the standpoint of compound layer removal, each slug is weighed to the nearest gram and warp is measured to the nearest mil. Warp data is also used on an attributes sampling plan to accept or reject the lot. The weight data are used on a variable sampling plan to accept or reject the lot. An AOQL of between 0.90% and 1.50% is used. This is a one-sided test since only the minimum weight is specified. In case any lot of bare slugs either from receiving storage or slug recovery storage is rejected, the entire lot is returned for screening. The defective pieces are removed and replaced by good pieces and the lot is resubmitted for statistical sampling.

3. Caps and Cans

The statistical inspection of cans is planned to insure an AOQL of 1.5% for can wall thickness and mandrel size and an AOQL of 2.5% for base thickness, outside diameter, and inside diameter. Variables inspection plans are used for the can wall thickness, outside diameter, inside diameter, and base thickness. Attributes inspection plans are used for visual inspection, mandrel, and can wall thickness. Each incoming shipment is considered a lot, and a sample of about 3000 pieces is taken from each lot of 100,000 cans. Seven hundred fifty cans are taken randomly for visual inspection. Three hundred are used for mandrel inspection, 750 for the attributes can wall inspection, 125 for the variables can wall inspection and 60 for inside diameter, outside diameter, and base thickness. Following these inspections, 1500 cans are selected for functional tests in canning and 16 for a blister test as described under Part C, "Functional Test of Components". An additional sample of 16 cans is sent to the 305 Test Reactor for reactivity testing.

Statistical acceptance sampling of the caps is similar to the sampling of cans. An AOQL of 1.5% is given for the diameter and height of the caps, while an AOQL of .90% is used for metal quality. A random sample of 1500 caps is taken from each shipment, which amounts to approximately 14 caps per box.

DECLASSIFIED

DECLASSIFIED

-1406-

HW-200000

Eighty-five caps are used for diameter and height measurements, sixty for 305 Test Pile reactivity tests, three for spectographic analysis, forty for blister test and five for a can wetting test.

Measurements of diameter and maximum height are recorded in half-mil increments. The visual inspection includes a comparison of the sample caps to standards supplied by the Process Control Unit. A complete record is made of the number of sample caps classified as marginal or defective. From this information, the Process Control Unit determines the acceptability of the lot.

If the initial inspection shows that a lot is not acceptable, sample of 150 caps is inspected from each shipping box. The caps in each box are accepted if not more than one visual reject or two dimensional rejects are found in the 150 piece sample. If more than this number of rejects are found, then the entire box is screened to remove the reject caps.

4. Other Essential Materials

It is not economically feasible to sample for analysis each barrel of chemicals received from an off-plant vendor. Experience has shown that sampling 10 per cent of the barrels in each shipment gives a valid estimate of the entire lot. The same is true for other materials used in the preparation of fuel elements. A sample of three ingots is taken from each incoming shipment of lead or AlSi. Each sample is submitted to chemical and other tests to satisfy specifications for the acceptance of essential materials. Materials accepted on the basis of statistical sampling are acenaphthene, aluminum, aluminum-silicon, high silicon aluminum-silicon, carbon tetrachloride, diversey, duponal, lead, methanol, tetrasodium pyrophosphate and trichloroethylene. In each case, the lot or shipment of material is held in storage pending the results of laboratory and functional tests. Materials failing to meet specifications are rejected or accepted through an approved waiver if material can be used without affecting the quality of the finished product.

DECLASSIFIED

DECLASSIFIED

-1407-

HW-40000

5. Screening

In addition to the statistical sampling described above, 100 per cent tests and inspections are made on some materials. The first is the metal quality screening of bare slugs, which includes an ultrasonic transformation test and a visual surface inspection. The transformation test, although designed to segregate those slugs not completely transformed during the beta heat treatment of the rods from which they were machined, is in reality a grain size measurement test. Equipment used for this test is located in the production line just ahead of the slug pickle equipment. Operation is essentially automatic and the test is readily applied to all slugs in the production stream. Slugs rejected for incomplete transformation are reheat-treated in a salt bath under carefully controlled conditions to insure complete transformation before they are canned. Partial or incomplete transformation of uranium causes excessive warping during irradiation that may contribute to fuel element ruptures or may cause operational difficulties. Bare slugs are 100 per cent visually inspected for seams, striations and other defects recognized as being detrimental to fuel element performance. Because as-received slugs have a highly oxidized surface, this inspection is made following the pickle operation when the slug surface is clean and amenable to minute visual inspection. Bare slug rejects are returned to FMPC for reprocessing.

All caps and cans are given a 100% inspection for metal quality, which includes inclusions and other surface defects that may adversely affect fuel element quality. This inspection like the statistical inspections for visual characteristics, is a comparison of as-received components with visual standards supplied by the Process Control Unit. Components failing to meet acceptance standards are rejected.

C. FUNCTIONAL TESTS OF COMPONENTS

Fuel element components are subjected to four major functional tests. These are: (1) reactivity tests in the 305 Test Pile, (2) chemical tests including

DECLASSIFIED

DECLASSIFIED

-1408-

HW-40000

both chemical and spectrochemical analyses, (3) wetting and blister tests, and (4) controlled canning tests.

1. Reactivity Tests

The reactivity tests in the 305 Test Pile require sufficient quantities of each component to fill available space in the test stringer. On this basis, 11 samples of 8-inch bare slugs and canned slugs are tested from each lot. Billet eggs (See Chapter VII-B-8) are tested in multiples of sixteen. Normally 16 cans and 60 caps are tested from each shipment. In each test the material is compared with a standard and the results recorded either in in-hours of reactivity or in TDS (total danger sum) values. The TDS value is used primarily for uranium billet eggs and is an arbitrary unit designed to compare values between different test piles. Bare uranium slugs are tested to determine the degree of reactivity each lot would produce when irradiated. Canned slugs are tested to determine the amount of shielding provided by jacketing material and to detect any possible additions of high cross-section elements during processing. Other materials such as caps and cans are tested primarily to determine the amount of "blackening" they will add in a production reactor. Excessive "blackening" may result from high cross-section elements such as boron or cadmium.

One other use of the 305 Test Pile is to determine the amount of isotopic enrichment in uranium or aluminum alloy slugs. Standard slugs containing known amounts of U-235 are used to calibrate the pile and their value is compared with the reactivity value of the slugs being tested to measure isotopic content. A more complete description of the 305 test pile and its functions appears in Chapter XVI-part C.

2. Chemical Tests

Chemical tests are used to determine amounts of constituents where specified, as well as amounts of contaminants, in process materials. Limits for contaminants are based on the effect they may have on the

DECLASSIFIED

DECLASSIFIED

-1409-

HW 40000

quality and irradiation performance of finished fuel elements. Certain elements must be excluded from process materials because of their high neutron capture potential.

A quick hydrogen test is used to determine the hydrogen content of bare uranium slugs. Excess hydrogen in the uranium causes gross porosity in the braze layer of canned slugs. If the bare slug sample from a lot has a high hydrogen content, the entire lot is outgassed in a salt bath at 600 C for a maximum of 7 1/2 minutes to reduce the hydrogen in the metal to a level acceptable for canning.

As-received aluminum caps and cans are analyzed spectrochemically for about 32 elements. The aluminum specifications limit the inclusion of only sixteen of these elements, but if any others appear abnormal during the analysis they are included in the laboratory report. Certain impurities or elements which are determined by the spectrochemical analysis will be further noted in reactivity tests. Such elements as boron, cadmium, lithium and gadolinium are only determined in gross amounts by the spectrochemical analysis. The 305 Reactivity Test is much more sensitive to these high cross-section elements.

The iron and silicon values obtained by the spectrochemical analysis of caps and cans are used to determine the iron-silicon ratio. In addition to specifying the maximum content for each of these two elements, the iron content must be at least twice the silicon content. A lower ratio leads to hot short cracking during welding. Because of the relatively small quantities of elements other than aluminum in the standard caps and cans, no general chemical analysis is made of this material. Other essential materials such as AlSi and lead are analyzed by both spectrochemical and general chemical methods.

3. Wetting and Blister Tests

A small number of caps and cans taken at random from each incoming shipment are used for both wetting and blistering tests. The wetting test

DECLASSIFIED

DECLASSIFIED

[REDACTED]
-1410- [REDACTED] HW 10000

consists of immersing each cap in AlSi for the same cycle time required under normal canning conditions. At the end of this cycle, each cap is shaken to remove molten AlSi, quenched in water, and examined to determine if any non-wet areas exist. Evidence of non-wet areas on sample caps is not necessarily cause for rejection, but is sufficient cause to investigate the factor contributing to non-wetting and the extent of the problem.

Caps and cans for the blister test sample are placed in a muffle furnace, heated to 575 to 600 C, and held at temperature for 15 minutes. During this time any gases entrained in the aluminum will tend to form small blisters on the surface of the samples. The results of each test are used to insure that the metal is free of gas voids that may adversely affect the quality of the components.

4. Controlled Canning Test

The principal functional test for aluminum components is the controlled canning test applied to samples from each shipment, which usually amounts to about 1500 caps and/or cans. In this test, the sample pieces are given a normal process cleaning and closely scrutinized to note the wetting characteristics in water after cleaning. During canning, both the caps and cans are again observed to see if there is any abnormality in the sample being tested. After the samples have been used for normal canning and have passed through the usual finishing operations, many of the rejects and some of the acceptable pieces are stripped to note the quality of the bond between the can and the slug and to determine if any non-wet areas exist. The reject rates for each sample are compared with current process reject rates to note any differences other than random variation. Reject categories particularly observed are the bond test and final inspection rejects. The minimum residual can wall is also compared to residual can wall of other can shipments.

[REDACTED] [REDACTED]
DECLASSIFIED

DECLASSIFIED

[REDACTED]
-1411-

HW-40000

D. IN-PROCESS TESTING AND INSPECTION

1. Quench Inspection

Canned slug assemblies are inspected immediately after removal from the steel sleeves at the quench station for wrinkled cans, penetration of the AlSi through the can wall, non-seating, cocked caps, AlSi slopover, marred surfaces and off-process (described below). As this operation becomes more mechanized, the number of inspections will be reduced. The use of the existing quench machines essentially eliminates cocked cap rejects because the pressure exerted upon the caps before quenching tends to seat them squarely. Although AlSi penetration through the can wall is cause for rejection, rejects of this type are rare. Wrinkled can rejects, in which the slug tends to pull part of the can away from the wall of the sleeve, are usually also evident as a non-seat reject. Slug non-seating is one of two major causes for rejection at quench inspection. Prototype quenching equipment is being developed, which will include an automatic non-seat detector. At present, non-seated slugs are rejected by comparing the length of assembled slugs with a standard. The second major cause for rejects is a category called off-process. This includes any slug assembly which has not been processed through the canning operation in accordance with Process Standards.

2. Length Inspection

After canned slugs are faced, a statistical sample is checked for length. The limits for overall length measurements are determined by the sum of the nominal bare slug length, can base thickness, nominal cap thickness, and an amount added to allow for a certain degree of non-seating. A maximum length is specified to limit the amount of aluminum on the ends of finished fuel elements, and minimum length is specified to insure sufficient cap thickness. Since the overall bare slug length and the can base vary only slightly from the nominal dimensions, the principal variations are the amount of a slug non-seating in the can and the thickness of the cap.

[REDACTED]
DECLASSIFIED

DECLASSIFIED

-1412-

HW-40000

Cap thickness is controlled by setting the automatic Acme-Gridley screw machines used in the facing operation to index against the top of the caps and cut off a fixed amount. Under these conditions the thickness of the caps after facing is dependent on two variables, the as-received thickness of the caps and the ability of the machines to face caps to a given thickness. Usually any large number of rejects observed at the length inspection station are caused by the slugs not being completely seated in the cans.

3. Braze Inspection

At the braze inspection station the cap end of each faced slug is observed with the aid of a contour projector which magnifies the surface about ten times. The braze width (the distance between the inside of the can and the edge of the cap, which is filled with AlSi) is measured and all slugs with a braze width greater than 40 mils are rejected. Braze width is an important indication of canned slug quality for two reasons. First, a wide braze width indicates an abnormal aluminum erosion rate in the canning operation. This may result from a high canning bath temperature or a higher-than-normal silicon content of the AlSi bath. The second cause for braze width rejects involves poor capping techniques when an excessive amount of the cap surface is washed away in the canning bath.

4. Weld Inspection

The weld inspection is a very close visual examination of the canned, welded slugs and is intended primarily to remove defective welded pieces from the process stream. Those pieces on which the weld bead widths do not fall within the maximum and minimum widths specified in the Process Standards are rejected. Weld bead width is controlled by the rotational speed of the weldment past the torch and the welding current. Weld beads outside established width limits indicate that the welding operation is out of control and may be producing welds with insufficient penetration. A ring gage is used to determine whether there is excessive

DECLASSIFIED

DECLASSIFIED

-1413-

HW-40000

weld overhang. Each weld is visually examined to assure that the bond between the cap and can is complete, and that the weld bead does not contain excessive amounts of oxide or other impurities and is free of pinholes or voids. The entire cap, particularly the weld preheat path, is inspected for hot short surface cracking or any evidence of laminations. In general, the weld bead is expected to exhibit a smooth and sound appearance.

5. Penetration and Bond Testing

After the welding inspection, all finished fuel slugs are tested with an eddy current penetration tester and an ultrasonic bond tester. The slugs are placed on a conveyor submerged in water, which advances and rotates the slugs past a sensing head or crystals for each tester. The penetration tester measures the thickness of the residual can wall; ie. that part of the can which has not been dissolved in the AlSi. The machine is set to reject automatically the canned slugs with a residual can wall thickness less than that of the standard slug used to calibrate the machine. The bond tester is set to reject those slugs which have voids or other discontinuities in the braze layer greater than one centimeter as measured in the circumferential direction.

6. Radiograph Inspection

The welded closures of all finished fuel slugs are radiographed to determine the degree of porosity under the cap and to determine the soundness of the weld. The slugs are placed cap end down in a rack at 30° to the vertical and a vertical X-ray beam is passed through the caps to a film holder underneath. Three exposures are taken, rotating the slugs about 120° after each exposure. In this manner, the entire closure of each slug is photographed. The X-ray film is developed and dried in an automatic processing machine and visually examined. The inspector examines each image and accepts or rejects on the basis of length and width of each void, the amount of metal cover over each void and the number, type and location of inclusions. The principal cause of rejection is the presence of voids under the caps. A secondary cause of rejection is inclusion of foreign particles or gas voids

DECLASSIFIED

DECLASSIFIED

-1414-

HW-40000

in the welds. Voids under the caps may be caused by the uranium cores outgassing during canning, whereas voids or impurities in the weld beads may result from impurities in the canning baths or faulty welding techniques.

7. Autoclave Testing

The autoclave test consists of subjecting the finished fuel slugs to a steam or water pressure of 90 - 125 psi at 165-180°C for forty hours. Upright pressure vessels are used in this test, each having a capacity of 432 finished 8-inch fuel elements. The test is designed to detect any defects in fuel element jackets that may allow entry of water or steam under the conditions specified and to provide a hydrated aluminum oxide film on the surface of fuel elements to retard corrosion during irradiation. If a small pinhole or opening exists in a fuel element jacket, water or steam will react with the uranium core causing the jacket to swell or rupture. Rejects of this type are classified as autoclave failures.

DECLASSIFIED

DECLASSIFIED

-1501-

HW-40000

PART V: PROCESS CONTROL AND IMPROVEMENT (Contd.)

<u>CONTENTS</u>	<u>Page</u>
A. INTRODUCTION	1502
B. LOT DESIGNATION	1502
1. Uranium Slug Lots	1502
2. Can and Cap Lots	1506
C. PIECE MARKING	1507
1. Basis for Marking	1507
2. Production Marking Systems	1507
3. Marking of Special Production Slugs	1509
D. DATA COLLECTION	1510
1. Acceptance Sampling Reports	1510
2. Station Reports	1511
3. Conformance Reports	1512
4. Destructive Sampling Reports	1512
5. Quality Reports	1513
6. Routine Sampling Reports	1515
E. USE AND STORAGE OF DATA	1515
1. Process Control	1515
2. Process Improvement	1516
3. Engineering Studies	1516
4. Storage of Data	1517

DECLASSIFIED

DECLASSIFIED

-1502-

HW 40000

A. INTRODUCTION

A lot identification system is used during the preparation and irradiation of fuel elements and other materials exposed in the HAPO reactors. This system is followed not only in the collection of quality control data and the accountability of SS (Source and Special Nuclear) materials, but also is valuable in helping to pin-point factors contributing to sub-standard quality. In addition, the quality data collected on lots of material or individual slugs through use of an identification marking system, provide an effective means of locating deficiencies in the process for revision or improvement. Further, analysis of process and performance data may lead to new or improved processes for a superior product. The storage of accumulated data is normally governed by its usefulness for future reference.

B. LOT DESIGNATIONS

1. Uranium Slug Lots

Identification of uranium slugs during the preparation and irradiation of fuel elements is required principally for quality control purposes, and it is an aid in the accountability of SS material. It is important to differentiate between quality control and accountability because they require different types of information. The responsibility for accountability includes accurate and periodic physical inventories to describe the physical location of all SS material. Quality control is primarily concerned with the identification of rejects to trace and correct off-standard conditions. For this purpose a high degree of accuracy is not needed. A third use of lot and/or piece identification is to collect information for cost control. An integrated system of production records is necessary to obtain accurate standard cost comparisons.

In order to establish a suitable identification system it is necessary to consider the information required, the physical methods available, and the cost and inherent production problems associated with various systems. The present system is necessarily a compromise of these factors. It is designed to separate the major variables that effect canned slug quality,

DECLASSIFIED

DECLASSIFIED

-1503-

beginning with the reduction and casting of metallic uranium. This is achieved by assigning a different letter to each lot type.

The present lot identification system originated through an evolutionary process. When all slugs were machined at HAPO there were only two kinds of slugs: "M" slugs which were first-run machined slugs and "Z" slugs which were the recovered canned reject pieces. When the Feed Materials Production Center, operated by the National Lead Company of Ohio, began supplying the machined slugs to Hanford, it became necessary to assign a new lot letter to differentiate between the production of the two sites. The letter "F" was assigned to the first lots of material produced at FMPC. These were alpha rolled slugs for triple dip canning. When the beta heat-treating of uranium rods was started at FMPC, the letter "B" was assigned to the machined slugs, and these lots were canned by the lead-dip process. This system continued until about July of 1954.

Changes in technology and an added metal supplier necessitated assigning a total of six letters to identify types of slugs. The letter "M" was used for metal reduced by the Mallinckrodt Chemical Works. With both MCW and FMPC supplying metal, a program for evaluating different methods of beta heat-treating uranium added four more fabrication variables. The six lot types, including a brief description of the fabrication history of each, were as follows:

1. "K" type - This material was cast, rolled, and machined at the FMPC. It was beta heat-treated at FMPC in rod form in the eutectic mixture of lithium and potassium carbonate salts.
2. "L" type - This metal was also cast, rolled, and machined at FMPC, but was beta heat-treated in slug form in a barium-potassium-sodium chloride eutectic salt at HAPO. These slugs were machined to a slightly smaller diameter than the "K" type to allow for minor changes in dimensions resulting from heat treating in slug form.
3. "M" type - This metal was cast by Mallinckrodt Chemical Works and

DECLASSIFIED

DECLASSIFIED

-1504-

rolled and machined at FMPC. This metal was beta heat-treated at FMPC in rod form in the carbonate salt referred to above.

4. "N" type - This metal was the same as the "M" type above except that it was heat-treated in a chloride salt at HAPO. Slug dimensions were the same as the "L" type slug.

5. "P" type - This metal had a processing history similar to "K" type material except that it was heat-treated at FMPC in a chloride salt.

6. "Q" type - This metal was the same as the "M" type above except for being heat-treated in a chloride salt at FMPC.

Currently only eight-inch solid slugs of the "K" and "M" types are being processed at Hanford.

Two more lot types were introduced by the cored slug program, and the evaluation of dingot uranium added another. The letter "D" is used to identify alpha rolled cored slugs from which the core is removed by drilling. The letter "X" was assigned to identify extruded cored slugs. Although the preparation of extruded cored slugs has been discontinued, the lot designation was previously used to identify slugs machined from alpha extruded tubing. Slugs fabricated from dingot material are identified by the letter "V".

All canning rejects are chemically stripped (recovered) and recanned. The recovery operation removes a small but measurable amount of uranium from the surface of each slug. This weight loss causes a reduction in reactivity. Consequently, recovered slugs must be separately identified for quality reasons as well as for accountability.

The letter "Z" has been used to identify regular recovered solid slug lots since the beginning of recovery operations at Hanford. To separate cored slug lots by type the letters DZ and XZ were given to recovered pieces from D and X lots, respectively. The letters VZ were assigned to recovered lots of dingot material. In December 1955, a change in the accountability system was instituted and the prefixes of lots were changed

DECLASSIFIED

DECLASSIFIED

-1505-

HW

so that only one letter was used to define each lot type. To identify recovered slugs from D, X, or V lots the original letter and a number in the 801 to 999 series is assigned.

At the same time (December 1955) two new balance areas were established in the 313 Building. Lots are assembled in each area from miscellaneous slugs separated during processing from the original lots. The first of these is Miscellaneous Receiving Storage, and lots of accumulated slugs are assigned a "Y" lot number except for pieces from D, X, or V lots, which are assigned numbers in normal sequence using the original lot letter. These lots include the miscellaneous bare slugs returned from special tests, statistical inspection, and reactivity tests.

The other new balance area is Reprocess Storage. Only canned slugs are collected and most of these slugs are returned from final inspection for reprocessing through the etch machine to remove stains. Lots of normal solid material made up in reprocess storage are given an "S" lot number, while D, V, or X slugs are assigned a number in the 600 to 799 series.

To identify lots of slugs for special tests or evaluations that are specifically limited, the letter "C" is used. The history of each "C" lot is maintained by Quality Control and is documented periodically. Information concerning the various types of uranium slug lots is summarized in the following table.

DECLASSIFIED

DECLASSIFIED

-1506-

HW-40000

DESCRIPTION OF LOT TYPES

Lot Type	Casting Site		Heat Treatment				Geometry			Canning History	
	FMPC (NLO)	SLPC (MCW)	Rod Form@ FMPC	Slug Form@ HAPO	Chloride Salt	Carbonate Salt	Solid	Cored	I and E	Virgin	Recovered
K	X		X			X	X			X	
L	X			X	X		X			X	
M		X	X			X	X			X	
N		X		X	X		X			X	
P	X		X		X		X			X	
Q		X	X		X		X			X	
D	X	X	X			X		X		X	
X	X	X	X			X		X		X	
V (Dingot)		X	X			X	X			X	
E	X		X			X			X	X	
C	X	X	X	X	X	X	X			X	
D 600-799*	X	X	X			X		X		X	
D 800-999	X	X	X			X		X			X
V 600-799*		X	X			X	X			X	
V 800-999		X	X			X	X				X
E 600-799*	X		X			X			X	X	
E 800-999	X		X			X			X		X
Y	X	X	X			X	X			X	
S*	X	X	X			X	X			X	X

* Assigned to lots of canned slugs only

2. Cap and Can Lots

Caps and cans are received from vendors in freight car shipments and each carload is considered a lot. A three part code is used to identify each lot of caps or cans. The first part is a number which indicates the nominal finished slug length such as 4 for 4 in. slugs or 8 for 8 in. slugs. The second part is the letter C for cans or CP for caps, and the third part is a number which is serially issued to the incoming lots. A typical cap lot might be 8CP3, which would indicate the third lot of caps received for canning eight inch slugs.

DECLASSIFIED

DECLASSIFIED

-1507-

C. PIECE MARKING

1. Basis for Marking

Each canned slug is marked with a code which is intended to convey information about the type of material, the time it was canned, and process history. Reasons for marking canned slugs are the same as outlined for uranium slug lots. Primarily, slug numbering is used as an aid to quality control. The secondary function of marking is the accountability of SS material.

The quality control function concerns itself with the history of the components and the fabrication history of canned slugs. It is desired to know the type of material canned, the cap and can lots, the crew and canning facilities used, and the time of canning. These facts are useful in evaluating process variables and in tracing the cause of rejects. The time is quite important when the quality of a group of slugs is questionable because of process errors attributed to such items as temperature control or metal analyses. If different canning equipment or techniques are used, it is desirable to follow the material through the finishing and inspection operations, and in some cases the pile performance. Under these conditions, a slug identification system is necessary to collect quality data and to compare the effects of process variables. The descriptions of three identification systems follow. Two are currently in use and the third has been proposed for future application.

2. Production Marking System

Prior to the use of the conveyor line in the 313 Building slugs were transported from one station to the next on trucks which held sixty 8-in. slugs or one hundred 4-in. slugs. Each truck was given a number and all slugs on each truck were stamped the same. The slug identification marking consisted of six characters: a number indicating the year, a letter indicating the month, and a four digit number which indicated the sequential truck number within a block of numbers assigned to each canning crew.

DECLASSIFIED

DECLASSIFIED

-1508-

HW-40000

For example, a slug stamped 5G1206 was canned in 1955 during the month of July, on truck number 1206 by the B-2 canning crew, which had been assigned truck numbers 1,001 to 1,500. With this information it was possible to refer to quality records and determine what day the slug was canned, what canning line was used by the crew, and what lots of slugs, caps and cans were used.

When conveyors were installed in the 313 Building sequential stamping machines were installed. With this equipment the slugs processed from each lot on a canning line are stamped sequentially, beginning with number 1. This number constitutes the last four of nine characters on the stamp.

The first character stamped on each canned slug is a letter which indicates both lot number and year the piece was canned. The series A, B, C, D, E is used for lots canned in 1955, the series F, G, H, J, and K for 1956 and M, N, P, Q, and R for 1957. The first lot canned is identified by the first letter of the series and the second lot by the second letter, etc. The second and third characters of this nine digit stamp are numbers to designate the day of the month. The fourth character indicates the month. Numbers 1 through 9 are used for the months January through September, and letters O, N, and D are used for the last three months of the year. The fifth character is a letter which designates the canning line. The letter F designates line No. 1 which consists of furnaces 1-C and 1-D. Letter G is used for No. 2 line, H for No. 3, M for No. 4, N for No. 5, and O for No. 6 line. An example of this system is a slug stamped G 23NH1623. The letter G indicates the second lot and the year 1956. The "23N" indicates the slug was canned on the 23rd day of November. H indicates number three canning line (furnaces 3-C and 3-D). The last four numbers show that this is the 1623rd slug of the lot canned on the line.

The proposed time stamping system includes the use of a stamping machine which is indexed periodically by a timing device. The suggested time interval is a tenth of an hour and this would require a maximum of three numbers to define the time using the same system which applies to non-exempt

DECLASSIFIED

DECLASSIFIED

-1509-

HW-4084

employee time cards. For example, the time six minutes past 1:00 p.m. would be stamped as 13.1. In addition to the three numbers for time, there would be one letter or number indicating the canning line and up to 4 additional characters to identify the lot number. Since it is only necessary to index the three time stamps it would not be necessary for the automatic stamping head to be as complex as the head on the present sequential stamping machine. Stamping truline and I and E canned slugs is not possible with existing stamping equipment, but would be feasible with this proposed system. An example of the proposed system for marking the base of canned slugs is as follows:

K 124
9.30C

This would indicate that the slug was a part of lot K-124 and canned on C line at about 9:18 a.m. Reference to production records would be necessary to determine the day canned and the crew.

3. Marking of Special Production Slugs

The slug marking systems described above refer only to regular uranium slugs canned by conventional methods. Other types of slugs such as "poison" or thorium slugs canned by other processes are identified by different systems. The system usually includes a letter that is indicative of the type of core.

Canned lead-cadmium "poison" slugs are identified by stamping the letter "P" on the base and a red paint mark on the cap. No lot or individual piece markings are used. Thorium slugs are grouped into lots and the lot number is stamped on the base of the canned slugs. Prior to May 1955, a series of piece numbers preceded by the letter "M" was used for thorium slugs. Starting with a shipment of thorium slugs received in May 1955, each lot has been assigned a "T" lot number.

Slugs for the tritium program had the lot number stamped on the base of each slug. The lithium-aluminum alloy slugs were assigned "N" lot

HW-4084

HW-4084

DECLASSIFIED

DECLASSIFIED

-1510-

HW-40060

numbers, and an additional letter was used to signify different parts of the overall program. The aluminum-U²³⁵ alloy slugs were stamped with the program or type number as well as the lot number, such as J-2-13 for the 13th lot of J-2 slugs. In addition to the stamped number each had a number inscribed with a Vibro-tool. This number corresponded to the rack position in the radiograph and served to identify the slug with the radiograph film

D. DATA COLLECTION

1. Acceptance Sampling Reports

Uranium slugs, aluminum components and other essential materials are accepted on the basis of statistical sampling plans. Dimensions of the slugs and components are recorded, although these raw data are not used as often as derivations from the data. More important is the average of any dimension and some measure of central tendency such as the standard deviation. A record of average slug dimensions serves as a measure of long range dimensional fluctuations and provides a continuous check on the accuracy of the machining operation at FMPC. Records of can wall measurements are used in conjunction with residual can wall measurements to detect the effect of process and component variables on fuel element quality. Acceptance sampling records show length, diameter, and weight of bare uranium slugs. For aluminum cans the following dimensions are recorded: Can wall, base thickness, inside diameter, outside diameter, groove depth, groove height, dimple depth, length, and bevel. A record is also kept of the results of the blister and reactivity tests. The results of the spectrographic analysis are recorded in the laboratory. The following dimensions of aluminum caps are recorded: Cap diameter, cap height, the face flatness, parallelism of the sides, the face radii, outside diameter of the boss and the cap thickness. In addition, the results of reactivity, blister, and wetting tests and the spectrographic analyses are recorded. The only dimensions recorded for steel sleeves are length and inside diameter. A record is kept of the statistical sampling and measurement of recovered uranium slugs for warp and weight.

DECLASSIFIED

DECLASSIFIED

-1511-

HW-40000

A small sample of each type of bare and canned slugs is measured to compile a historical record of slug dimensions. The length is measured both at the axis of the slug and at the edge. The diameter is measured at each end, at the middle and one inch from each end. The weight and warp of each slug is also recorded. This information is compiled and documented quarterly.

In addition to the records of statistical sampling outlined above, the results of the screening tests, or 100 per cent inspections, are also recorded. The record of screening tests does not give the physical dimensions, but indicates the number of pieces rejected out of the total number inspected. For bare uranium slugs, screening tests include a thorough visual inspection and the beta transformation test. Inspection rejects are classified by type, which include seams, striations, cracks and other surface imperfections. All aluminum cans are inspected for marred surfaces, dents, voids, and inclusions. Caps are not subject to 100 per cent inspection unless they fail to meet statistical acceptance tests.

2. Station Reports

One source of information that is periodically used to measure performance and assess changes in canning techniques is the station reports. The canning reports compiled for each operating line show the number of slugs rejected for non-seating, AlSi slopover, wrinkled cans, and for being canned "off cycle". The braze inspection report shows the number of slugs which have braze widths in excess of the specified standard. The weld inspection report gives information both on cap braze and weld quality. Rejects noted are poor bonds between the cap and the can, excessive amounts of aluminum oxide or other impurities imbedded in the weld bead, pinholes and voids in the weld bead, laminated or cracked caps, and patched welds. The bond and penetration test station report indicates the number of pieces rejected for poor bonding between the can wall and the slug and sub-standard residual can and wall thickness. The etch inspection station report includes marred surface and AlSi penetration rejects. The final inspection station report shows the number of pieces rejected for inclusions in the can wall and the number of pieces which

DECLASSIFIED

DECLASSIFIED

-1512-

fail to pass a full length tube gage, including autoclave test failures.

3. Conformance Reports

A source of information on actual process conditions are the conformance reports prepared by Standards Technicians. These reports represent a record of routine observations made of the various fuel element manufacturing operations. These operations are observed to audit conformance to process standards and the records provide a long range check on variations in fuel slug quality.

Canning reports show the degree of conformance for those parts of the process which are limited by process standards such as cap preheat time, can sleeve assembly preheat and canning bath temperature. The report also includes other items not specifically limited by process standards, but which may affect the quality of canned slugs. Similar reports cover the preparation of aluminum components.

Conformance reports for the finishing operations include checks of the welding, facing, and inspection functions. The destructive testing described below constitutes a major part of the finishing conformance audit.

Special canning such as hot press and unbonded canning, which are non-routine operations, are audited on the basis of scheduled production. Each audit covers the entire operation from preparation of components to inspection of the final product. This includes the pressing, facing, welding, and the various inspections and tests for components and assembled pieces.

4. Destructive Testing Reports

Destructive testing constitutes an important phase of quality control performed by Technicians. Caps are removed from random samples of canned slugs rejected for marred surfaces, but otherwise acceptable. These caps are sectioned to measure the weld width, weld penetration, cap thickness, cap seating (distance from top of slug to bottom of cap) and distance from outside surface of each weld to the undiluted AlSi within the

DECLASSIFIED

DECLASSIFIED

-1513-

REV. 1-1-60

fusion zone (termed "AlSi stringer"). The bases of the slugs are removed to determine the degree of non-seating.

The cans are stripped from part of the slugs rejected by the bond test to check the accuracy of testing equipment. Cans are also stripped from slugs that pass the test as an additional audit. In addition to checking the bond test, this gives an indication of the degree of braze porosity in the finished canned slugs accepted for irradiation. The strength of the bond is also noted, but there is no qualitative test for bond strength at present.

Residual can wall thickness is determined by removing the aluminum can with sodium hydroxide. The diameter of each canned slug is carefully measured before the test and again after the first evidence of AlSi penetration is observed. Half of the difference between the two measurements is the "residual can wall" thickness. One canned slug is taken from each canning line twice each shift for this test and the results are plotted on a control chart. If any sample falls below the control limit for minimum residual wall thickness a second sample is taken from the canning line in question. If this sample is out of control, operation of the line is stopped to determine and correct factors contributing to the problem. The summary of the can wall data for each month is used to obtain the average can wall thickness and to compute new control limits.

5. Quality Reports

It is necessary to routinely summarize the quality data collected for presentation and distribution to those interested in fuel element quality. These summaries normally indicate what the quality level is, what improvements have been made, and what areas present targets for further improvement. This includes a bar chart which shows the percentage of the total months's production rejected for each of eight reject categories. The current month and the seven preceding months are shown for comparison.

The destructive testing summary presents in graphical form the information obtained from the destructive tests described above.

DECLASSIFIED

DECLASSIFIED

-1514-

HW-40000

One of the continuing problems in maintaining high yields is the number of canned slugs rejected for marred surfaces. The soft aluminum jacket and weight of uranium core, combined with the necessity of handling the slugs numerous times during processing, creates a high potential for rejects. To assist in controlling the number of marred surfaces, a monthly marred surface summary is published. This summary shows the reject rate for each of several stations and serves as a reminder of the production losses attributed to handling. Daily reports are closely scrutinized and corrective action is taken when marred surface rejects are excessive.

Special reports are issued to record information about certain non-routine matters. One of these is the autoclave failure report. It is issued each time a finished slug fails in the autoclave test and contains as much history of the slug as can be assembled. This includes the type of metal, lot number, time canned, canning conditions (temperature and silicon content of the AlSi bath), cap and can lots, and the reject rate of the companion material. In addition, pictures of the failure, macro and micro photographs where applicable, results of special tests and the cause of the failure if known are included as part of the report.

Vendor evaluation reports are issued primarily to record the quality level of the product of new suppliers and to aid prospective vendors in improving their products. These reports also provide information that is useful in designing future tests. In the future it is planned that vendor evaluation reports will form a basis for a vendor rating system.

There is a constant search to find vendors who can produce a better product at a lower cost. The greatest effort has been directed toward finding new suppliers for certain high cost items such as aluminum components, which have an important effect on canned slug quality. The product of prospective cap and can vendors is fully described in evaluation reports. Each report gives the results of the dimensional checks, detailed metal quality tests, corrosion tests, and the results of several functional tests. If the product is tested in the production reactors, the final report includes post-irradiation examination results.

DECLASSIFIED

DECLASSIFIED

-1515-

HW-40000

6. Routine Sample Storage

Questions often arise concerning fuel element quality levels of the past as compared with the present. An example might be a peculiar type of inclusion in the can wall or an unusual defect in the weld bead that is discovered and the investigator desires to know whether such a defect had been previously observed. The best and easiest way to answer the question is to examine representative samples of past production. For this purpose, Quality Control maintains a growing collection of caps and cans from past and present production. Samples are taken of each cap and can shipment, identified and stored. Jackets are removed from canned slugs and similarly stored. Typical examples of rejects are also cataloged and kept. In some cases photographs are used for this record and some actual samples of rejects are preserved for future reference.

E. USE AND STORAGE OF DATA

1. Process Control

The primary function served by quality control data is to provide a basis for acceptance or rejection of some discrete unit of production. This may amount to an audit of the canning temperature during the preceding two hours or it may involve computing acceptance limits from a series of slug measurements. The record of these data later furnishes justification for any decision to accept or reject as-received and in-process materials or the finished fuel elements.

Periodic review of quality data by production supervisors, standards technicians, and the quality control supervisor, assures conformance to standards and specifications. Added review by members of Process Engineering gives further assurance of conformance to specifications. Conformance to process standards and specifications is essential to insure a uniform and high quality product. A review of the data also discloses any particular need for process improvement.

DECLASSIFIED

DECLASSIFIED

-1516-

HW-40000

2. Process Improvement

Short term investigations are usually sufficient to find the cause of a sudden increase in any reject category. Reject rates are often influenced by more stringent inspection standards resulting from a continuous revaluation of quality requirements. These investigations may lead to a revision of standards and specifications.

Some problems are of a long range nature and require a more thorough investigation. This type of problem is not usually associated with a sudden increase in any reject category, but involves a constant reject rate which is considered too high. Occasionally an investigation is undertaken because of fuel element failures during irradiation that may be influenced by fuel element quality. Most of the long term investigations are instituted to improve fuel element quality, while others are made for economic reasons. Long term investigations may lead to changes in the process. In one investigation, residual can wall data showed that a shorter submerge time for the can-sleeve assembly in the canning operation produced a superior canned slug.

3. Engineering Studies

Engineering studies of past performance levels of fuel slugs in the production reactors may indicate a need for major changes in existing process. Studies of this type may also suggest a new and improved process. A comparison of the average and minimum residual can wall thickness with theoretical and actual pile corrosion rates was partly responsible for the development of an eddy current penetration tester to reject finished fuel elements having a can wall thickness of less than 20 mils. Simultaneous with the development of the tester was an effort to find ways of modifying the existing process to produce fuel elements with a thicker average can wall. The monthly destructive testing report furnished a ready measure of this effort and conclusive proof of the value of these efforts.

DECLASSIFIED

DECLASSIFIED

-1517-

DECLASSIFIED

4. Storage of Data

Information and reports relating to fuel element quality are stored at least for one year in the Quality Control office. Those with long range use are then permanently stored in the Record Center and the others are destroyed. Added information can be found in the Quality Control Central File. Monthly reports contain the reject summary chart and the destructive testing summary. Dimensions of bare and canned slugs are documented quarterly.

DECLASSIFIED

DECLASSIFIED

-1601-

HW-40000

PART V: PROCESS CONTROL AND IMPROVEMENT (Contd.)

CHAPTER XVI: AUXILIARY FACILITIES

<u>CONTENTS</u>	<u>Page No.</u>
A. INTRODUCTION.	1603
B. DEVELOPMENT FACILITIES	1603
1. Function	1603
2. Description of the 306 Pilot Plant Building	1604
3. Description of the 314 Building	1609
C. HANFORD TEST PILE	1610
1. Purpose	1610
2. Pile Description	1611
3. Quality Control	1614
4. Test Pile Calibration	1614
D. EXPERIMENTAL LOOPS	1617
1. Purpose	1617
2. Description	1618
2.1 H-Loop	1618
2.2 1706-KER Facility	1619
2.3 Single Pass Boiling Facility	1619
2.4 ELMO-2	1620
2.5 ELMO-4	1621
2.6 ELMO-5	1621
2.7 ELMO-6	1622
2.8 ELMO-7	1622
2.9 ELMO-9	1623
E. IRRADIATED METAL EXAMINATION FACILITIES	1624
1. Purpose	1624
2. Description	1624
2.1 Visual Examination	1626

DECLASSIFIED

DECLASSIFIED

-1602-

HW-40000

TABLE OF CONTENTS (Contd.)

	<u>Page No.</u>
2.2 Cleaner	1626
2.3 Radiation Intensity Measurements	1627
2.4 Photography	1628
2.5 Weighing	1628
2.6 Dimensioner	1629
2.7 End Cap Removal	1629
2.8 Dejacketer	1630
2.9 Grain Size Measurements	1630
2.10 Breaker	1630
2.11 Bond Tester	1630
2.12 Profilometer	1631
2.13 Packaging	1631
F. RADIOMETALLURGY BUILDING (327)	1631
1. Function of the Laboratory	1631
2. Description	1632
2.1 Location	1632
2.2 Building Data	1632
2.3 Equipment Data	1640
G. REFERENCES	1640
H. LIST OF TABLES AND FIGURES	1640

DECLASSIFIED

DECLASSIFIED

-1603-

HW-40000

A. INTRODUCTION

This chapter deals with the several facilities for conducting work related to the research and development phases of fuel element technology. Some of the functions of these facilities are directly related to production; e.g., the 305 Test Pile is used routinely to check the reactivity effects of production materials. Others are related indirectly through the development work and process support.

Part B of this chapter describes two buildings, the 314 Building and the 306 Pilot Plant, which house the development facilities. Part C is a description of the Test Pile, 305 Building, in which reactivity studies are performed on reactor materials. Part D concerns the experimental loops located both in-pile and out-of-pile. Experimental fuel element studies as well as process tube and water studies are carried out in these loops. Parts E and F are interrelated in that they describe the C-Basin and the Radiometallurgy Building (327 Building) both of which are concerned with the examination of irradiated material. The C-Basin handles material of slug size at a comparatively large rate of through-put whereas in the Radiometallurgy Building the more detailed and time consuming metallurgical studies on material from sample size up to large structural sizes are performed.

B. DEVELOPMENT FACILITIES

1. Function

The facilities for doing mechanical, chemical, and metallurgical work in support of the fuel element development program are installed in two buildings; the 314 and 306 Buildings. These buildings, which have a total floor area of 45,000 square feet, house a wide variety of both standard and special equipment for performing operations on both core material and jacketing material. Office space and control laboratories are included to provide for 75 - 100 people of all categories. External views of each building are shown in Figures XVI-1, XVI-2, and XVI-3.

DECLASSIFIED

DECLASSIFIED

-1604-

HW-40000

2. Description of the 306 Pilot Plant Building

The Fuel Element Pilot Plant, Building 306, has a floor area of about 32,000 square feet with offices and laboratory space for about fifty people. The building is a one story, steel frame structure with insulated metal wall panels, and an insulated flat roof over metal decking. In general the layout is based on four bays each having a span of forty feet and each 180 feet in length, with columns and roof trusses on 20 foot centers.

The concrete floor is six inches thick with special pads and isolated foundations where required. The normal permissible floor loading is greater than 8000 pounds per square foot. A firewall separates the first floor and mezzanine floor offices, control laboratory and special metal-finishing area from the remainder of the building. A cutaway view taken from a three dimensional model of the building is shown in Figure XVI-4.

The services provided include conventional steam, air, power and water systems, de-ionized water, a gas distribution system, normal heating and ventilating, and two exhaust systems, one for use with ordinary operations and a second for use with equipment which generates a contaminated exhaust. The contaminated exhaust system includes chip traps at various machine tools and an outside bag filter exhaust, which has a normal capacity of 30,000 cfm. The building is serviced by a 1500 KVA substation with a 2000 amp bus duct system, feeding individual bus ducts running the length of the building at the east-west column lines. The column lines also carry the other services of the building. A system of floor trenches and sumps is provided for ordinary drainage with a stainless steel process sewer connection provided for the control laboratory area.

The four bays of the building are partitioned to isolate some operations, as required, to minimize the spread of corrosive fumes, contamination or other hazards. The principal areas so sub-divided are the special metal fabricating area, the welding area, the chemical processing and plating area, the SS material storage area and general storage areas.

DECLASSIFIED

DECLASSIFIED

-1605-

HW-40000

Outside facilities in addition to the sub-station, include chemical storage tanks, fume separator exhaust system, bottled gas storage, bag filter, and exhaust fans. The building heating and cooling units are roof mounted, with a total of 19 individual units.

The completed building cost approximately twenty dollars per square foot not including any development equipment. The installed equipment in the building is estimated to represent a cost of over one million dollars.

The east wall and north wall are especially designed to permit ready expansion of the building in these two directions.

The control laboratories occupy space of about 1300 square feet and include a darkroom, a metallography control laboratory, a polishing room, a physical testing laboratory, a utility chemical laboratory, a non-destructive testing control laboratory, and a mechanical utility laboratory. Figures XVI-5, XVI-6, XVI-7 and XVI-8 show some of the equipment in the laboratories.

Details of the services available are as follows:

1. Heating and ventilating air is provided by sixteen (16) roof mounted units having a total capacity of 90,000 cfm. The office and laboratory area is serviced with three units having a total capacity of 22,500 cfm. The exhaust systems consists of nine (9) 5000 cfm power driven roof mounted exhaust fans, two (2) 10,000 cfm and one (1) 15,000 cfm equipment exhaust fan, and one (1) 30,000 cfm bag filtered, contaminated exhaust system. There is also one (1) 2500 cfm fan servicing the laboratories and one (1) 2100 cfm fan servicing the laboratories. Total exhaust capacity is 114,600 cfm.
2. Ceiling mounted mercury vapor lights provide a lighting level of approximately sixty (60) foot candles in the main building areas. Fluorescent fixtures provide 70-80 foot candles in the office and laboratories. An emergency lighting system is provided throughout the building, and includes battery operated wall mounted lamps.

DECLASSIFIED

DECLASSIFIED

-1606-

HW 111000

3. Power to the building is distributed at 480/277, three phase and 240/120 single phase. Direct-current power is provided at required points by individual rectifier systems, both selenium and germanium cell.
4. Water service includes five water systems; process water, building water, hot process and building water, and de-ionized water.
5. Compressed air is provided by connection to the 303 area 90 lb. service with pressure reducing valves at required locations.
6. The deionized water system includes a 16 gpm unit with a 1000 gallon aluminum storage tank. The water at 40 pounds pressure is distributed to the chemical processing room.
7. Outside chemical storage includes one 1000-gallon stainless steel tank for nitric acid storage. This tank is connected to the chemical processing room with a stainless piping system. A second 1000-gallon stainless tank is installed for storage of acid wastes. This tank is also connected to the chemical processing room.
8. Crane service in the building consists of one 1-ton power operated unit over the salt baths, one 2-ton power operated unit in the chemical processing room, and five power lift, hand traversed one-ton cranes in the main development areas and the metal fabricating area. All cranes except the two-ton unit can be moved to new locations in the building as required.
9. A bottled gas distribution system provides argon and helium to the special welding area. A second system provides propane, argon, hydrogen, acetylene, and oxygen to various use points in the building. The oxygen and propane are piped to the chemical processing area, argon and propane to the laboratory, hydrogen to the fixed development area, and acetylene to a point near the electric salt bath furnaces. Argon is piped to the metal fabricating area. The system is designed so that additional distribution lines may be connected as required.

The metal fabricating area includes engine lathes up to sixteen inch swing, turret lathes, milling machines, drill presses, surface grinder, universal

DECLASSIFIED

DECLASSIFIED

-1607-

HW-40000

grinder, centerless grinder, bar cut off, power specimen cut-off, hacksaw, shaper, do-all saw, tool grinders, and miscellaneous bench mounted equipment. Figure XVI-9 shows the equipment in the metal fabricating area.

The metal forming equipment includes two salt baths, 75 in. and 36 in., a 40 HP swaging machine, a 6 in. 40 HP rolling mill and a 25 HP forging hammer. The salt baths are immersed electrode type and are designed for carbonate salts at high temperatures. The swaging machine is equipped with a hydraulic feed mechanism and will handle bar up to 3 inches in diameter and tubing up to about 6 inches in diameter. It is equipped with a circulating coolant system and heat treated dies to permit swaging of materials at elevated temperatures. Figure XVI-10 shows the metal forming equipment.

The fuel element development equipment includes hydraulic presses, molten metal baths for dip canning, heat treating salt bath furnaces, a portable salt bath furnace, both standard and atmosphere controlled box furnaces, induction heating equipment, machine tools, degreasing and cleaning equipment, and miscellaneous supporting equipment such as hoods, sinks, etc. Figures XVI-11, XVI-12, XVI-13 show some of the development equipment.

The hydraulic press equipment covers a wide range of performance requirements with a complement of two 400 ton, one 50-ton deep drawing, one 50-ton ram, four 50-ton special purpose press units, and two 5-ton Logan presses. A combination oil-water quench tank is installed for use with one of the 400-ton presses.

The molten metal baths consist of a 60 kw induction heated Ajax, a 60 kw resistance heated pot type furnace, and three smaller units, one 6-in. and two 10-in. pot type resistance heated pot furnaces, which are also used for heat treating. The six box furnaces range in size from 2 kw up to 40 kw with one 11 kw unit equipped with an argon atmosphere.

The machine tools include three lathes, one milling machine, two pedestal grinders, and three drill presses.

DECLASSIFIED

DECLASSIFIED

-1608-

HW-40000

The cleaning equipment consists of various etching and pickling tanks and a vapor blasting unit.

The chemical processing equipment includes facilities for electro-plating, anodizing, can cleaning, slug pickling and autoclaving. Most of this equipment is located in one room to isolate, as much as possible, the corrosive fumes generated by the various processes. The equipment is serviced by a two ton bridge crane, a ventilation exhaust system, an open trench drainage system, and electrical services. A d-c distribution system has been provided to permit use of the output of any rectifier at any part of the room.

The exhaust system from the fume generating tanks includes an outside, 12,000 cfm, 20 HP fume separator.

The electroplating facility is primarily for plating nickle but other materials can be plated on an experimental basis. Equipment included is:

- (1) A 2,000 ampere 6 volt rectifier.
- (2) A 3,000 ampere 6 volt rectifier.
- (3) Two multiple range rectifiers each having 1200 kw output rating on 6, 12, 24, and 48 volt ranges.
- (4) Chemical cleaning, etching, rinsing and plating tanks.
- (5) Bench and hood space for plating research and development materials.

The capacity of the plating facility is approximately 120 pieces per day.

The anodizing equipment provides for the anodizing of aluminum using either sulfuric or oxalic acid electrolyte, and includes (1) dual range (400 ampere at 100 volts or 800 ampere at 50 volts) direct current selenium rectifier power source, (2) 25 ton refrigeration unit for cooling the anodizing bath, (3) tanks for pre-cleaning aluminum, (4) a 600 gallon anodizing tank, and (5) a 300 gallon rinsing and soaking tank. Capacity of this equipment is estimated to be 700 pieces per 8 hour day.

The cap and can cleaning and pickling facility contains tanks for chemical cleaning both aluminum and uranium. This unit is designed to permit developing and testing new methods of cleaning as well as routine pilot

DECLASSIFIED

DECLASSIFIED

-1609-

HW-40000

production. The facility is serviced by a 500 lb. capacity monorail and the capacity is estimated at 320 caps and cans, and 250 slugs per 8 hour day.

The autoclave is a standard production type autoclave having a batch capacity of 432 pieces. This unit is used as a pilot plant unit in developing improved seals for anodized films, studying autoclaving procedures and related work.

The welding equipment occupies an area of approximately 800 square feet. It includes four special welding tables, eight welding machines, weld testing equipment (such as a bubble tester and a tensile tester) equipment for welding specimen preparation, and a converted glass blowing lathe for making closure welds. The equipment is used to maintain and improve production welding techniques, and to develop welding techniques on special shapes and configurations as well as welding of new jacketing alloys and material.

The fuel element measurement equipment occupies an area of approximately 600 square feet and consists of balances, measuring fixtures, and density measuring equipment. The weight, length, diameter, warp, and occasionally the density of production test pieces are checked and used for comparison with similar data obtained after irradiation of the fuel element in a reactor.

The semi-works area of some 7000 square feet is for production of pilot quantities of Hanford type fuel elements. It is planned to install equipment in this area which will be capable of producing 10,000 pieces per month. The area is serviced by standard building utilities.

3. Description of the 314 Building

The 314 Building has a floor area of approximately 13,000 square feet with office and laboratory space for about ten people. The building is a one story, concrete block construction with roof clearance of about 20 feet. It was originally built for manufacturing use in metal preparation. As a result, the layout and facilities are not ideal for development use. Available services, however, are air, water and steam power, with fairly

DECLASSIFIED

DECLASSIFIED

-1610-

HW 400000

adequate heating and ventilating. The one main bay of the building is serviced by a 30-ton traveling crane with several cantilever jib cranes also located within the area. The building houses development equipment for corrosion study work and for uranium turning and broaching. There are also a high powered induction unit, a melt plant facility and some temporary test equipment.

The corrosion study equipment is made up largely of special high temperature autoclaves for investigation of water-aluminum-uranium corrosion problems. These units can handle small quantities of Hanford type fuel elements with temperatures up to 350 C and pressures up to 3000 psi. For other high temperature work a high pressure flow loop can be installed in this building.

The high power (200 KW) Tocco unit for induction heating is a 3000 cycle machine for thermal cycling of test elements. It is used for investigation of core material phenomena and characteristics. A power and distribution system is employed with up to seven work stations at which test samples may be induction heated. Some vertical heat treating of rod has also been done with this equipment. Figures XVI-14 and XVI-15 show the induction heating equipment.

The uranium turning equipment consists of two of the original Gisholt lathes used by the Manufacturing department, and is being replaced by modern and more efficient machinery. It is now used for turning and drilling operations on test pieces of uranium.

The broaching machine is a 20 HP, hydraulic broach and is capable of broaching internal holes, keyways, splines, etc., as may be required by the development program. It is a tool room machine and not intended for production use.

C. HANFORD TEST PILE

1. Purpose

The Hanford Test Pile was designed to measure the purity of the graphite used

DECLASSIFIED

DECLASSIFIED

-1611-

HW-40000

in the construction of the production piles and also to measure the reactivity effect of the uranium and other materials to be charged into the production piles.

2. Pile Description

The Hanford Test Pile is a heterogeneous, low power, graphite moderated, natural uranium pile. The pile, as shown in Figure XVI-16, consists of an eighteen foot cube of graphite containing 292 charged channels and surrounded by a five foot concrete biological shield.

The biological shield consists of poured concrete on three sides with the remaining side and the top made up of removable, interlocking concrete blocks. There are 33 holes through the shield for test holes, removable stringers, ion chambers, control rods and safety rods.

The graphite used in the construction of the pile was Gulf-Toledo grade with a diffusion length of 51 cm (estimated from reactivity measurements made on this type graphite). The pile was stacked with the axis of extrusion of the bars laid parallel, with the exception of the bars immediately above the test stringers.

Arranged in a square lattice, there are 292 metal bearing channels with an 8-1/2 in. lattice spacing. Each channel originally contained 20 bare uranium slugs with a 1-1/6 in. graphite spacer between each slug. The uranium slugs consist of 8-1/4 in. sections from extruded rods with a nominal diameter of 1.448 in. and an average weight of 9.20 pounds. There are ten removable metal bearing stringers of which three have been reloaded with 42 four inch canned slugs. The total weight of uranium charged into the pile is 53,700 pounds.

The Test Pile is provided with two safety rods, either of which will maintain the pile subcritical. The vertical safety rod controls 0.63% k (for definition of k, see Chapter II) and the horizontal safety rod controls 0.43% k compared to the excess reactivity of the pile of 0.19% k. In addition to the safety rods, a ball-shot safety is provided to be used in

DECLASSIFIED

DECLASSIFIED

-1612-

HW-40000

case the vertical and horizontal rods should fail. The ball-shot safety controls 0.65% k.

The vertical safety rod is a gravity operated boron steel cylinder 8 feet long and 1-1/2 inches in diameter located 12-3/4 in. north and 12-3/4 in. west of the pile center line. The rod is removed from the pile by an electric hoist and held out by an electric brake. Removal of the power from the brake due to a power failure, a power level trip of either safety circuit, or an intentional trip of the safety circuit results in the vertical safety rod dropping into the pile. The vertical safety rod will fall from the all out to the all in position in three seconds.

The horizontal safety rod consists of a boron steel bar 1-3/4 in. x 1 in. x 200 in. located 24 in. east and 21-3/4 in. below the pile center line. The rod is removed from the pile by an electric hoist and held in place by an electric brake. The rod is driven into the pile by a weight and pulley system whenever it is tripped by the same mechanisms as the vertical safety rod. The horizontal safety rod will go from the all out to the all in position in five seconds.

The ball-shot safety is a manually operated device located 12-3/4 in. east and 12-3/4 in. south of the vertical center line of the pile. The 1/4 in. diameter boron steel shot are located in a hopper in the top shield. The shot well is a 1-7/8 in. I.D. aluminum tube extending 14 ft. -2-1/2 in. into the graphite. The shot are held in the hopper by a steel stopper which is manually released by a cable extending into the control room.

The Test Pile is controlled by the shim rod and the control rod. The shim rod is a manually operated, 1-3/4 in. x 7/8 in. x 200 in. mild steel bar, located 24 in. west and 21-3/4 in. below the north-south center line of the pile. The shim rod controls 0.24 % k and is thus capable of maintaining the pile subcritical. The shim rod is not intended as a safety device, but is used solely to adjust the excess reactivity of the pile so the control rod may be operated in the calibrated region.

DECLASSIFIED

DECLASSIFIED

-1613-

HW 740010

The control rod is a 1-3/4 in. x 200 in. cadmium strip sandwiched between two pieces of mild steel. The rod is driven by a rack and pinion gear connected by gears and magnetic clutches to three electric motors. The use of three motors permits driving the control rod at three speeds: (1) 1.8 in. per second, (2) 0.48 in. per second, and (3) 0.021 in. per second. Tripping the safety circuit, with the exception of a power failure, automatically drives the control rod into the pile at the highest speed. While a three speed drive was provided for the control rod, in actual practice only the high and low speed drives are used. The control rod is set approximately to the desired position with the high speed drive and then the final positioning is accomplished with the low speed drive. The position of the rod is determined by selsyn generators and receivers connected to the control rod by a rack and pinion gear.

There are two independent safety circuits in the pile, each consisting of a B_4C neutron chamber, a Beckman micro-micro ammeter and a Beckman controller. The Beckmans may be set to release the safety rods and to drive the control rod into the pile at any desired power level.

In addition to the two Beckman safety circuits, there is one B_4C neutron chamber connected to a Beckman-Micromax circuit to continuously record the pile power level. The Test Pile is controlled and all data are taken at the console as shown in Figure XVI-17. All measurements are made in the Test Pile by means of a galvanometer-neutron chamber system. As is shown in Figure XVI-18, five boron coated, argon filled neutron chambers (Type GL-571) located in the pile reflector are connected in parallel to an L and N type R galvanometer (sensitivity 0.004 $\mu a/mm$ at one meter) through a 100,000 ohm resistor to ground. An L and N* type HS galvanometer (sensitivity 0.0008 $\mu a/mm$ at one meter) is connected to the 100,000 ohm resistor through an L and N type K potentiometer. Drift measurements are made by bringing the pile to a constant power level, then bucking out the EMF developed across the 100,000 ohm resistor by the type K potentiometer. The bucking voltage is left constant and changes in pile k are

* Leeds and Northrop

DECLASSIFIED

DECLASSIFIED

-1614-

HW-40000

measured by the high sensitivity galvanometer.

There are ten uranium bearing stringers and 20 graphite stringers in the Test Pile, of which one metal test stringer, as shown in Figure XVI-19, and one graphite test stringer are used routinely. The distribution of the test stringers is shown in Figure XVI-20. Two side test holes are also provided which permit access to the graphite immediately adjacent to and above the metal test stringer.

The pile temperature is monitored by a temperature sensitive resistor located 21-3/4 in. below the geometrical center of the pile. The changes in resistance of the thermohm are measured by a standard bridge circuit, and the pile temperature is calculated from the following relationship:

$$T(^{\circ}\text{C}) = 20^{\circ} + (2.729)(R - 99.980)$$

3. Quality Control

The Hanford Test Pile is used to measure the quality of the uranium being received by billet "egg" tests and bare slug tests. In addition, the slugs are tested after canning to detect the accidental inclusion of high cross section elements in the canning process. The Test Pile is also used to measure the purity of the aluminum cans and caps before they are used in the canning process, the reactivity of "J" and "E" slugs, and the lithium content of Li-Al alloy.

4. Test Pile Calibration

To make precise reactivity measurements in the Test Pile, it is necessary to know (1) the change in pile reactivity with changes in the control rod position, (2) the changes in pile reactivity with changes in atmospheric pressure, and (3) the changes in reactivity associated with small changes in pile power level. The methods for calibration and the results obtained are outlined in HW-37363.

The methods for performing tests, and the necessary calibrations for interpreting the results obtained in testing, are as follows:

DECLASSIFIED

DECLASSIFIED

-1615-

HW-400007

4.1 Billet Egg Tests

Uranium metal samples termed "billet eggs" or "eggs" are cast on the end of every fifth or sixth ingot and are submitted to Hanford for Test Pile measurements to determine the impurity content of the metal prior to slug fabrication. These reactivity measurements supplement chemical analysis and are believed necessary since certain impurities; e.g. rare earths, can adversely affect the neutron economy of the Hanford piles when present in sufficiently low concentrations to escape chemical identification.

At the present time, reactivity tests are made on 8 eggs spaced 8-1/2 inches on centers. Before September, 1954, the tests were made on 16 eggs spaced 4-1/4 inches on centers. The purity of billet eggs is reported in TDS units where TDS or Total Danger Sum is the percentage change in the Hanford production pile multiplication constant; i.e., the change in multiplication which would result if the pile were loaded with uranium of test quality rather than uranium containing no impurities, as expressed in per cent k. The TDS is determined at Hanford by measuring the difference in reactivity between the test eggs and the standard eggs. The currently accepted TDS value of the standards is related to the Argonne standards.

The increased spacing between the eggs results in making the test sensitive to variations in weight; hence, the relationship for calculating TDS from Test Pile reactivity data must include a correction item for minor variations in volume or density. The test requires that the billet eggs be machined to close tolerance.

DECLASSIFIED

DECLASSIFIED

-1616-

HW-40000

The relationships between reactivity measurements and TDS values are as follows: (HW-32412)

$$\Delta k\% (105) = 0.768 \left[\text{dih (Test Pile)} - a \sum \alpha_i (W_{t_i} - W_{s_i}) \right]$$

where a = change in reactivity with change in egg density or volume

$$= 3.31 \times 10^{-4} \text{ ih/gram}$$

α_i = reactivity weighting factor for i 'th test position

W_{t_i} = weight of the i 'th egg in the test

W_{s_i} = weight of the i 'th standard egg

and by definition

$$\text{TDS} = 0.11 - \Delta k\%$$

It has been the practice at Hanford to multiply the TDS values by 100 and report them as whole numbers; e.g., a TDS value of 0.11 is reported as a TDS of 11.

4.2 Slug Tests

Slug testing in the Hanford Test Pile consists of comparison in the central section of the metal test stringer of eleven test slugs with the eleven standard slugs. The slugs are tested bare to determine the quality of the uranium going into the canning process and are also tested after canning to insure that accidental inclusion of large cross section elements will be detected. The effect of small impurity content in uranium on pile reactivity is shown in Chapter II.

The effect of the variation in reactivity of the slugs as tested in the Test Pile can be converted into changes in reactivity of a production pile as follows:

$$\Delta k\% (105) = (0.35) (\text{dih Test Pile})$$

DECLASSIFIED

DECLASSIFIED

-1617-

HW-40600✓

where $\Delta k\%$ is the change in reactivity of a production pile due to full pile loading of uranium of the test quality. For the derivation of the constant 0.35 ih^{-1} , see HW-37363.

The difference in reactivity between the standard slugs and the test slugs can be related to the difference in purity between the standard slugs and the test slugs:

$$\text{cm}^2 \text{ (of absorber)} = (\Delta \text{ih})(2.88)$$

where $2.88 = \text{cm}^2$ of absorber/inhour for a standard metal test

cm^2 = sum of the microscopic cross section of the foreign atoms.

4.3 Enriched Uranium Testing

"J", "C", and "E" slugs (see Chapter II) are tested in the Test Pile to insure that the reactivity of the slugs is within the desired limits. The reactivity measurements serve as an index to the amount of uranium present in U^{235} -Al alloys and also to the degree of enrichment of "E" slugs. The limitations of the Test Pile for determining the amount of U^{235} present for accountability purposes are discussed in HW-38841.

Enriched slugs are tested singly in the center of the metal test stringer with the reactivity of the slug being the difference in reactivity between the test slug and a natural uranium slug.

4.4 Lithium-Aluminum Alloy Slugs

Lithium-aluminum alloy slugs are tested singly in the center of the metal test stringer. The reactivity values obtained can be converted to per cent lithium in the alloy by means of an appropriate calibration. The calibration is performed by making slugs containing known amounts of lithium and plotting the curve of reactivity versus per cent lithium.

D. EXPERIMENTAL LOOPS⁽⁶⁾

1. Purpose

The experimental loops described in this section are used for experimental

DECLASSIFIED

DECLASSIFIED

-1618-

HW-40000

and development work in the areas of fuel element testing, water chemistry studies, and pile materials evaluation. Also, the experience obtained in the operation of these facilities will be of considerable aid in establishing operating techniques and limits for existing reactors with coolant modifications and future water cooled reactors. The operating conditions of the various loops are shown in Table XVI-1.

2. Description

2.1 H-Loop

The H-loop facility provides for testing normal size fuel elements in a zirconium process tube at intermediate temperatures and pressures. Figure XVI-21 shows a flow diagram of the loop.

The facility consists of an in-pile zirconium process tube with associated stainless steel piping. Main instrumentation and loop equipment are located in 105-H Building. Two 1000-gallon retention tanks provide for activity reduction on the front face. These tanks also serve as a backup supply of water in the event of large leaks in the system. The water is sent through a mixed bed deionizer and is pumped into the tanks. A clean-up deionizer maintains loop purity at 1.5-2.0 megohm-cm. If low pH tests are desired the cleanup bypass flow is sent through a cation resin exchange unit which can maintain a loop pH in the range 5.0-5.3. The loop water is pumped from the -12 level via three centrifugal pumps. The flow is reduced by a flow control station and water is sent to the tube. Effluent water from the tube is returned to the -12 level and is cooled below the flash point of water at atmospheric pressure by a high pressure heat exchanger because the loop retention tanks are not pressurizable. From the high pressure heat exchanger the water is reduced to ~30 psig, sent through a supplementary heat exchanger (ordinarily not used), and then sent into the tanks. In addition a heat exchanger is provided for the influent water for either cooling or heating. Emergency process water automatically comes in if the pumps fail.

Safety devices include a high temperature scram, low back pressure scram,

DECLASSIFIED

DECLASSIFIED

-1619-

HM 340008

high panellit pressure scram, and/or low flow scram; loss of any pump will result in a scram and trip to process water. Also, a high activity alarm from the two HM chambers located at the entrance to the retention tanks will trip the system to process water and as a result scram the pile. Full instrumentation is provided for recording and controlling all pressures.

2.2 The 1706-KER Facility

The purpose of the 1706-KER recirculation facility (see Figure XVI-22) is to provide a means for determining the effect of recirculating high temperature-high pressure water in a closed reactor coolant system. The facility consists of four individual loops, three of stainless steel and one of carbon steel. Each loop is housed in an individual subterranean cell; a common tunnel adjacent to the 105-KE Building contains the loop piping leading to and from the pile itself. The instrument control center, water purification and make-up room, switchgear and ventilation system are common facilities located above or adjacent to the underground cells. There are four separate recirculation systems each consisting of (1) one zircaloy reactor process tube and necessary piping to provide a means for testing fuel elements and jacket materials, (2) a heat exchanger unit to dispose of the heat generated in the tube, (3) one pressurizer surge tank to maintain the system base pressure and to provide space for volume changes upon temperature changes, and (4) one clean-up system to maintain a given loop water quality.

2.3 Single Pass Boiling Facility

The purpose of this facility will be two-fold; first, to expose the normal aluminum jacketed fuel elements to demineralized water at outlet temperatures up to 260°C., and secondly, to expose both regular and special fuel elements to steam-water mixtures.

This facility (see Figure XVI-23) will consist of a B, D, F, size zirconium or zircaloy-2 process tube located in process channel 3043-KE. Although the physical location of the tube in the reactor is such that a

DECLASSIFIED

DECLASSIFIED

-1620-

HW-40000

tube power of 78 per cent of central zone tube power is available for normal charges of fuel elements, the maximum allowable tube power is between 350 and 500 KW, depending on flow inlet temperature and exit steam quality. The range of operating conditions is as follows:

Inlet temperature - 120 to 175 C.

Outlet temperature - 260 C.

Flow - 10 to 12 gpm.

Maximum steam quality - approximately 25 per cent based on a heat and flow balance. Burnout considerations may lower this value.

Maximum outlet pressure - 600 psi.

The controls for the facility will be located in the 1706-KE Building where 24 hour coverage will be available. Normally demineralized water will be furnished the process tube; however, almost any type of water might be used.

2.4 ELMO-2

ELMO-2 is an intermediate temperature (up to 185 C) recirculation loop. The loop can be used for studies of crud and corrosion and water treatment methods. The test section consists of a seven foot length of zirconium tube of old pile process tube dimensions. Thus it will be possible to test fabricated fuel elements as well as other materials.

A simplified flow diagram of ELMO-2 is shown in Figure XVI-24. The loop consists of a circulating pump, a steam jacketed process tube, pressurizer, and by-pass demineralizer, storage tank, make-up pump and rapid fill pump. Except for the zirconium process tube, the main loop is made of stainless steel.

In operation, the water level in the pressurizer is automatically maintained by the make-up pump. System pressure is maintained by helium introduced at the top of the pressurizer. Water purity is measured by conductivity cells before and after the demineralizer.

DECLASSIFIED

DECLASSIFIED

-1621-

HW-40000

2.5 ELMO-4

The ELMO-4 recirculating loop (see Figure XVI-25) is designed primarily for conducting slug rupturing experiments. The loop itself is constructed of both stainless steel and carbon steel for maximum operating conditions of 1280 psi, 280 C and 18 gpm flow rate. The pump is the canned motor type and the flow rate is measured by an orifice plate, d/P cell and pressure receiver. The main loop water is heated by an immersion heating element. Water level in the loop is maintained manually by starting and stopping the make-up pump to add water. The test section in the loop is designed specifically for conducting slug rupturing experiments where the fuel element is likely to swell excessively. The design includes a large outer pipe, three inches in diameter, to withstand the pressure in the loop and to allow sufficient room for slug expansion. Centered in the three inch pipe is a short section of process tubing with a connection at one end to insure that the total water flow in the loop goes through the process tubing. The usual procedure for conducting a test is to drill a hole in the fuel element jacket, place the slug in the test section, start the pump, then raise the temperature of the water by turning on the heaters. Actual slug rupturing is noted by a decrease in water flow through the loop as the rupturing slug reduces the flow annulus. Mainly the loop has been and will be used for testing various types of fuel elements to determine slug rupturing characteristics at elevated temperatures.

2.6 ELMO-5

The ELMO-5 loop is an intermediate pressure recirculating system with carbon steel piping (see Figure XVI-26). Maximum operating conditions are 250 C, 1350 psi, and 75 gpm flow rate. The loop consists of a mechanical seal pump, pressurizer-degassifier, heater section, test section, clean-up system, make-up system and appropriate instrumentation for automatic control. Because the loop is primarily carbon steel, a deoxygenator is included in the demineralized feed water supply. The

DECLASSIFIED

DECLASSIFIED

-1622-

HW

test section consists of 2-in. carbon steel pipe 10 feet long flanged at both ends. The loop is in the form of a package unit 6 feet wide by 10 feet long with all components attached to a common base.

Samples to be tested can be either slugs of the present size or small 1 in. by 2 in. coupons which fit in special holders. The present fuel element flow characteristics can be maintained by placing process tubing inside the 2 inch pipe test section. Flow velocities as high as 40 fps. can be maintained past the test pieces.

2.7 ELMO-6

The forced circulation water loop was designed and built by the Babcock and Wilcox Co., Atomic Energy Division. Maximum design conditions are 2000 psi, 600 F and 50 gpm flow rate. The loop is made of stainless steel pipe; the main loop piping is one inch in diameter. As in most of the recirculating loops, the various components are a process pump, pressurizer tank, external heater, test section, clean-up system, make-up pump, and appropriate instrumentation.

The test section in the loop consists of 2-1/2 in. diameter pipe, 27 in. long. A special sample holder will be made to hold coupons of various materials which are to be corrosion tested. This holder will be designed to allow several different water velocities in the same test section.

Water conditions in the loop can be varied in pH, purity, additive concentration, and temperatures. Tests using full size fuel elements can also be made, although the short length of the test section will limit the number of slugs which can be tested at one time.

2.8 ELMO-7

ELMO-7 is an out-of-pile recirculating water loop designed to provide a controlled environment within a test section for the purpose of testing fuel elements and metal samples under the action of high temperature water. The operating conditions of the loop are 100 to 150 gpm flow, 400 to 600 F

DECLASSIFIED

DECLASSIFIED

-1623-

HW-4000

temperature, and 235 to 2000 psi pressure.

The loop is constructed of Type 347 stainless steel, and contains its own by-pass purification system and make-up purification system. The test section is arbitrary and may be of any shape as long as the total test section volume is less than 18 gallons. Complete recording instrumentation is provided for the loop variables. Heat is supplied to the system by electric resistance heaters and operation is essentially isothermal.

2.9 ELMO-9

ELMO-9 is a high pressure, high temperature stainless steel natural convection loop now in advanced stages of construction. The loop is designed to recirculate water at a temperature of 300-315 C at a flow rate of one gallon per minute or less. The test section, a half-inch stainless steel pipe about one foot long, is designed to yield water velocities past the test samples up to 10 ft./sec.

The primary purpose of the loop is to provide means for making corrosion studies of various coupon-sized materials. Thus studies could be made of candidate materials for fuel element cladding, process tubing or out-of-pile piping.

A simplified flow diagram of the loop is shown in Figure XVI-27. Physically the loop consists of two vertically mounted 40 ft. long legs of quarter inch, schedule 40 stainless steel pipe connected at top and bottom. One leg is heated (5 KW total heat input) and the other leg is unheated. A cooling jacket is fitted around the pipe at the top of the loop and a pressurizer column connects to the loop near the bottom of the heated leg. In operation, the loop will be pressurized by maintaining a volume of helium gas at the top of the pressurizer. After startup, the loop operation will be semiautomatic. If the loop pressure falls below a set amount due to either leaks or intentional bleeding of the system, the make-up pump is automatically activated injecting additional water until a higher set pressure is attained at which time the pump automatically shuts off.

DECLASSIFIED

DECLASSIFIED

-1624-

HW

The loop is protected by a rupture disk plus controls which will automatically shut off the heaters on high or low pressure and high temperatures.

E. IRRADIATED METAL EXAMINATION FACILITIES

1. Purpose

The final criteria for evaluating any fuel element or any new and improved method of fuel element preparation are established by service testing the elements in reactors. The extensive and expensive development programs directed towards solving fuel element problems depend directly upon the information concerning irradiation behavior for guidance and direction. This type information can be obtained from two principal sources. One source is the detailed metallurgical examination on a few selected specimens which is carried out in the Radiometallurgical facility (described in Section F of this Chapter). The other source of information is the examination of a large number of pieces, which is carried out in the 100 Area Metal Examination Facilities. A portion of this type information is used as a guiding factor in setting the maximum outlet water temperature and hence operating power levels of the reactor.

The purpose of the Metal Examination Facilities, located principally at 105-C and 105-B reactors, is to provide a radiation safe means of collecting engineering data from irradiated fuel elements. Such facilities and the equipment installed therein require adequate shielding to protect operating personnel. Water shielding requires depths of 8 feet for a single fuel element, 10 feet for a bucket containing about 200 fuel elements, and 15 feet for an array of 24 closely spaced buckets to reduce the dosage rate at the water surface to tolerable limits.⁽¹⁾

2. Description

There are periscopes, manipulators, and ion chambers installed in the storage basins of each pile area. This equipment permits visual examination, photography and relative radiation intensity measurements of

DECLASSIFIED

DECLASSIFIED

-1625-

HW 40000

irradiated fuel elements. These facilities are used primarily for examination of failed fuel elements.

At 105-B, equipment has been installed in one complete storage row which will permit the following operations: visual examination, removal of film, weighing, measurements of diameter, warp, relative radiation intensity, average grain size and force required to fracture the fuel elements. This equipment serves to gather data and as prototypes or design bases for all new equipment.

The 105-C Metal Examination Facility represents the most advanced type of facility that has been developed to secure engineering type information on irradiated fuel elements. This facility is constructed adjacent to the storage area at C Pile and consists primarily of four basins varying from 17 ft. to 11 ft. in depth, an equipment decontamination area, and an office. (Figure XVI-28) The small basin adjacent to Basin IV is used for removal of equipment and for preparation of irradiated elements for shipment. Underwater doors isolate certain of these basins to permit selective draining for new equipment installation and repairs of existing equipment.

Equipment installed in the 105-C Metal Examination Facility permits visual examination, measurements of relative radiation intensity, length, diameter, warp, weight, grain size, breaking and/or shear strength and deflection prior to fracture. Equipment is also provided which will chemically remove the film formed in the pile, photograph the entire surface of both canned and dejacketed pieces, locate unbonded areas, remove both ends of the aluminum can and chemically dissolve the remaining jacket from slugs.

Examinations and operations performed in each of the Basins are:

Basin I - Visual examination, loading and unloading of cartridges and storage of slugs awaiting examination or disposal.

DECLASSIFIED

DECLASSIFIED

-1626-

HW-40000

Basin II - Removal of products formed in the pile, radiation intensity measurements, automatic photography, weighing and dimensioning.

Basin III - Stereo-microscopy, profile plotting and unbond testing.

Basin IV - End cap removal, dejacketing, automatic photography, grain size measurements, dimensioning, breaking and shear testing, cross section photography and packaging.

2.1 Visual Examination

Visual examination is accomplished with the aid of a manipulator (Figure XVI-29) and an under water viewer (Figure XVI-30). The manipulator is capable of holding 16 fuel elements in a tray where they can be placed individually on rollers so that the element may be identified, photographed, and the degree and extent of film, distortion, corrosion and pitting attack determined. If no further examination is required the pieces can be rejected from the rollers down a reject chute into a bucket. In addition, this piece of equipment will automatically load the elements into circular cartridges (Figure XVI-31) for transportation to other examination stations. The viewer consists essentially of a periscope extending from platform level underwater to the level of the element on the manipulator. The viewer in Basin No. I provides examination under varying powers of magnification up to 45 X. The base of these periscopes can be moved transversely over the slug surface and to and from the surface to permit accurate focusing.

Sixteen slugs are loaded in a cartridge, which is then removed from the manipulator with a cartridge crane (Figure XVI-33), placed in a bucket and raised by elevator to Basin II. The crane piston is moved by a hydraulic cylinder. On the base of the shaft there is an automatic pick-up head shown in the inset (Figure XVI-33).

2.2 Cleaner

Film, corrosion product, and scale are removed from the jackets of the slugs in the cleaner. (Figure XVI-34) This operation is necessary to

DECLASSIFIED

DECLASSIFIED

-1627-

HW-40000

permit the precise measurements to be carried out in Basin II. A mixture of 5% phosphoric - 2% chromic acid, when heated to 95° - 110°C , will dissolve these products without significantly altering the surface appearance or removing identifiable amounts of the aluminum can.⁽³⁾ The cleaning operation can be carried out manually or automatically and consists of the following sequence of events: lid is closed, basin water in cleaner tank is removed, hot acid solution is forced into cleaner tank from storage, solution is held at temperature 10 minutes, cleaner solution is drained to storage, filtered water is admitted twice, and lid is opened. The cartridge of slugs is then removed from the cleaner and placed on the slug dolly, (Figure XVI-31) which hangs from a monorail and transports the cartridge and slugs to various examination equipment in Basin II. The dolly base contains locating pins for accurate positioning at an examination station, a lifter to raise slugs individually at the desired stations, and an indexing ratchet to rotate the cartridge.

2.3 Radiation Intensity Measurements

The relative radiation intensity is determined by holding a slug near an ion chamber which is an integral part of the slug weasel shown in Figure XVI-35. The slug chamber and ionization chamber are encased in a lead shield to reduce background radiation from nearby slugs. The ionization chamber is pressurized with nitrogen to prevent water leakage into the chamber. The relative radiation intensity is read upon a Beckman micro-microammeter. A plot of these values yields the following information:

1. Confirmation of the element's position in the process tube.
2. An indication of the element's position in the process tube when correlated with visual film data, if the charge order is unknown.
3. An explanation of dimensional anomalies caused by control rod or poison column location.
4. The specific power of the individual fuel element.

DECLASSIFIED

DECLASSIFIED

-1628-

HW-40000

2.4 Photography

Single view photographs can be obtained with a Zeiss-Winkle eye-piece camera and the Basin I viewer or the Basin III stereomicroscope. Stereoscopic photographs which record both a series of conventional views and an optically flattened image of the jacket or bare slug cylindrical surface will be obtained with the slug surface camera (Figure XVI-36). The optically flattened image is produced by accurate synchronization of the rotation of the slug and the movement of a slit in front of a 5-1/2 in. wide roll of aerial film.

In addition to the above photographs, there is located in Basin IV a cross section camera (Figure XVI-37). This piece of equipment will provide stereopair images of the broken surfaces of slugs from the breaker. Light is reflected from the broken slug surface and enters a pair of objective lenses set at an angle of convergence of 15° . It is then deflected by mirrors twice and passes up a center tube onto a semi-cylindrical light shield. This shield contains a slit which upon rotation forms the stereo-pair images on film.

2.5 Weighing

The value of water treatment, jacket material, and jacket surface treatment studies is determined by the weight loss of slugs during pile exposure. In addition, the actual degree of corrosion is determined primarily from these weight losses. These data play a significant role in setting the outlet water temperature limit for pile operation. The weight losses are obtained using the slug weigher (Figure XVI-38). This equipment is keyboard operated and permits rapid weighing of irradiated elements in an air chamber under water with an accuracy to within ± 0.030 gram. A cartridge of 16 slugs is brought up into the under water weighing tank, the door closed, the basin water pumped from the tank and the slugs dried by a blast of warm air. Lowering of the cartridge to a midposition removes a slug from the cartridge and places it upon the weigh pan. Raising the cartridge returns the weighed

DECLASSIFIED

DECLASSIFIED

-1629-

HW-40000

slug to the cartridge and places the next slug on the pan. This operation is repeated until the weights of all 16 slugs are obtained. In addition to measuring the actual weight of irradiated slugs, this piece of equipment can be used to determine the density of irradiated uranium.

2.6 Dimensioner

Primary indications of core stability are determined by accurate measurements of length, diameter, and warp. The equipment located in Basin II is capable of holding an element in the vertical position so that probes (two touching the ends and six touching the sides) connected to magnetic gages will determine the dimensions mentioned. The impulses from these gages are transmitted to an indicating dial providing an accuracy to within ± 0.002 in.

Another dimensioner (Figure XVI-39) in Basin IV differs from the one in Basin II in that there are only two probes which touch the sides of the slug. These probes can be raised and lowered vertically, and the two end probes can be moved horizontally. When the slug is rotated, therefore, measurements of any diameter and length can be taken. This piece of equipment can also be used to determine the depth of pits or heights of bumps.

2.7 End-Cap Removal

The time required to chemically dissolve the aluminum jacket from fuel elements is materially shortened by first mechanically removing the end-caps. This is accomplished with the decapper (Figure XVI-40). The slugs are held vertically on a die so that a ram operated by a hydraulic cylinder can shear off the end-cap. Removal of the end-caps also permits identification of numbers stamped upon the bare uranium, these numbers relate the material to its particular rolling site. Anomalies caused by a particular heat-treatment or rolling history can thus be explained.

DECLASSIFIED

DECLASSIFIED

-1630-

HW

2.8 Dejacker

After end-cap removal the aluminum jackets are chemically dissolved using hot commercial sodium-hydroxide in the dejacker (Figure XVI-41). To assure the complete removal of the Al-Si layer a short acid rinse is incorporated into the dejacker cycle. Underground storage tanks are provided to house the basic and acid solutions. The off-gas from the reaction is diluted and vented through the 105-C reactor stack. The cycle is automatically controlled.

2.9 Grain Size Measurements

The average grain size of irradiated uranium can be determined by measuring the loss of energy of an ultrasonic beam as it passes through the material, since the energy absorbed depends upon the relationship between the wavelength of the transmitted pulse and the average grain size.⁽⁴⁾ Grain size determinations can be made on a large number of pieces to provide data for statistical analysis. This equipment is shown in Figure XVI-42.

2.10 Breaker

An indication of the changes in breaking strength and ductility is obtained with the slug fracturer (Figure XVI-43). The broken surface provides valuable data for interpreting the properties and behavior of uranium during irradiation, particularly when these data can be correlated with average grain size measurements. The fractured surface also gives an indication of the temperature to which a fuel element was subjected during irradiation.

The slug fracturer can also be used to determine the shear strength of irradiated uranium, if the anvil is replaced by a shear testing ram.

2.11 Bond Tester

This piece of equipment is used to determine the presence of bonded and unbonded areas between the can wall and the slug core after pile exposure. Information of this type, when correlated with pre-exposure bonding information, will be useful in determining whether or not the bond has

DECLASSIFIED

DECLASSIFIED

-1631-

HW-40000

deteriorated as a result of pile exposure.

2.12 Profilometer

This piece of equipment projects the magnified shadow of a portion of the slug surface onto a translucent screen. By movement of the slug in the horizontal plane and rotation of the slug, a complete profile of the entire slug surface can be plotted. These data can then be used to confirm warp measurements from the dimensioner and give accurate measurements of the extent and degree of bumping, or large pitted areas.

2.13 Packaging

After examinations have been completed, any broken or dejacketed fuel elements are packaged in aluminum tubing for storage and eventual disposal to the Separations Plant. The packaging equipment (Figure XVI-44) will also be used to hold broken slugs in such a manner that stereopair images of the broken surface can be obtained with the cross section photographic equipment.

F. RADIOMETALLURGY BUILDING (327)

1. Function of the Laboratory

The Radiometallurgy Unit functions both as a service organization and as a research group. The primary purpose of the laboratory is to provide examination and testing services on irradiated samples. The service function includes performing investigations of failures which may have occurred in pile structural members or fuel elements. Examinations and testing services are provided for both on-site and off-site organizations.

Research studies are conducted by members of the group to determine the effects of irradiation on structural materials and fissionable materials. These activities center around a determination of the mechanical and physical properties of existing irradiated fuel elements and pile structural members.

DECLASSIFIED

DECLASSIFIED

-1632-

HW-10000

2. Description

2.1 Location

The Radiometallurgy Building (Bldg. No 327) is located in the northeastern part of the laboratory area which comprises the library building, bio-physics laboratory, radiochemistry building, technical shops building, pile development and research building and radiometallurgy building. The construction of this new type metallurgical facility was completed in 1953 at a cost of \$1.6 million; the structure cost \$.85 million.

2.2 Building Data

The one story building with a full basement is constructed of reinforced concrete and steel and has a floor space of more than 14,000 square feet (Figure XVI-45). The space is divided into "cold" areas consisting of the entry hall, lunchroom and part of the locker room, and the "regulated" areas comprising the rest of the building. The main work area is a 173 ft. x 30 ft. canyon (Figure XVI-46) which lies at right angles to two wings - the north wing with the storage and decontamination rooms, and the south wing, with offices, dark room, chemical preparation room, and machine shop. See Figure XVI-47 for photograph of floor plan. Building service machinery and equipment, such as exhaust and intake fans, vacuum pumps and air compressors, are located in the basement beneath the south wing.

The building is designed to accommodate 14 personnel but by working two shifts, a staff of 21, plus supporting Radiological Sciences personnel, shop and maintenance personnel, and service personnel can be accommodated.

The regulated portion of the building is monitored by recording health monitoring instruments which indicate the general level of radiation within the work area. Personnel not directly assigned to the building are required to be accompanied by assigned personnel during their stay in these regulated areas. This philosophy of operation insures radiation safety, mechanical safety, and in the event of fire or other evacuation procedures, proper

DECLASSIFIED

DECLASSIFIED

-1633-

HW-40000

accountability of all personnel in the building. All air flow within the building is regulated to provide air-borne contamination control.

The accountability of all samples is accurately maintained during their long testing program to provide a sound foundation to the technical data and to satisfy the requirements of the A. E. C.

2.3 Equipment Data

2.3.1 Multicurie Cells

Most of the examination and testing work on irradiated materials is done within shielded enclosures called multicurie cells. Within the Radio-metallurgy Building there are four such cells designed for general purpose use. Three other cells having restricted use have been constructed around individual tensile testing machines and the cut-off apparatus.

The four general purpose cells are rectangular enclosures, each having an inside area of about 4 ft. x 6 ft. and an inside height of 4 ft. The walls, top and bottom of the cells are constructed of Meehanite cast iron and are 10-1/2 in. thick in three of the cells, 15 in. thick in the high level cell. The basic cost of each cell is about \$100,000; however, with installed testing equipment and servicing accessories the cost of the individual cells in some cases exceeds \$200,000.

In the high level cell (15 in. thick walls) samples with an activity of 2000 curies can be remotely handled with no significant radiation field occurring outside the cell. In general, the work on whole slugs is done in the high level cell and the testing and other work on smaller, less radioactive samples is done in the three intermediate level (10-1/2 in. wall) cells.

The cells are located in the work area or "canyon" of the Radio-metallurgy Building where an overhead, travelling 15 ton crane and lift truck are available for handling the sample casks and cell components.

DECLASSIFIED

DECLASSIFIED

HW 40000

-1634-

2.3.2 Cut-Off Cell

The Radiometallurgy cut-off cell contains equipment for the sectioning of radioactive samples for metallurgical, chemical, and physical investigations without undue personnel exposure to radiation. In addition to the abrasive cut-off unit, the cell contains sample canning and de-canning equipment, weighing equipment to facilitate the maintenance of accountability records, and waste collecting equipment.

Following a cursory examination, which may include electrocleaning, visual examination and macrophotography, material which must be sectioned is transferred to the cut-off cell. The rotary cut-off machine to section radioactive materials is shielded by lead brick to conserve cell space. Minimum shielding surrounding the unit is 8 inches of lead. An additional 2 inches of lead has been attached to the sides and top of the box to reduce the normal radiation level for maintenance. The abrasive cutting unit is shown in Figure XVI-48, prior to the installation of the lead shielding.

Major assemblies are:

1. 2 hp, 1800 rpm, motorized grinding spindle.
2. Double vise.
3. Stainless steel box.
4. Micrometer thickness gauge.
5. Feeding crank.
6. Vise adjusting rods.
7. Arbor and abrasive wheel.
8. Arbor wrench.

Material to be sectioned is placed in the vise with manipulator⁽²⁾ and positioned for desired specimen thickness with the micrometer thickness gauge. The vise jaws are then tightened and the vise adjusting rods disengaged. Next, the box is partially filled with water so that the material is completely submerged during sectioning. The box lid is lowered into position by means of a hydraulic cylinder. Feeding material into the

DECLASSIFIED

DECLASSIFIED

-1635-

HW-1635

wheel is accomplished by rotating the feeding shaft that operates a worm gear attached to the vise shaft and moves the vise downward through a circular arc into the wheel.

After completion of cutting, the vise is rotated to the loading position for subsequent sectioning operations. A number of cuts may be made before the cooling water is removed from the box. Provisions are made for solid contamination control by flushing the box and separating the water and waste by gravity separation and filtration. The solid waste is collected in a shielded container for subsequent removal.

Wheel changing is done by placing a socket on the end of the arbor wrench shaft and removing the arbor nut. Wheels are removed and replaced with the manipulator. The double-vise arrangement provides for the transverse sectioning of material 2-1/2 in. diameter and up to 12 in. in length. Excellent results are obtained with a rubber-bonded, 1/16 in. thick, 10-in. diameter, 90 grit silicon-carbide wheel.

2.3.3 Metallographic Cell

Metallographic examination of radioactive materials is performed by processing selected samples through the standard operations of mounting, grinding, polishing, etching, and microscopic viewing within one of the 10-1/2 in. thick shielded enclosures (Figure XVI-49).

As much equipment as practical has been designed to pass through the 7-1/4 in. diameter port holes. Considerable savings in maintenance result, because an individual piece of equipment can be handled independently without necessitating shut down and decontamination of the whole cell.

Samples are surfaced on plug-mounted polishers of the kind illustrated in Figure XVI-50. Abrasive cloths are cemented to sheet metal disks for easy changing with a manipulator. Eighty grit sandpaper is used where significant amounts of metal must be removed. The normal

DECLASSIFIED

DECLASSIFIED

-1636-

HW-40000

starting grit is 320 gritcloth followed by 600 gritcloth. For the final cloth polishing step, the abrasive varies with the material. Linde-A in oxalic acid solution is used for uranium. Aluminum is finished with magnesia. Diamond paste is used for samples whose constituents differ widely in hardness.

Etching is normally performed in a remotized vacuum cathodic etcher shown in Figure XVI-51. Vacuum cathodic etched surfaces are preferable to chemically etched surfaces for better quality microstructure with bright field examination. Remote electrochemical etching of the material is used for polarized light examination and for routine investigations.

Viewing and microphotography are done on a specially remotized Zeiss Metallograph. The control console of the metallograph may be seen at the right of Figure XVI-49. The instrument produces photomicrographs at magnifications up to the limit of dry objectives -- about 1000X. Darkening of optical members is a troublesome and expensive problem peculiar to examination of radioactive samples. Objectives darken more severely than other parts of the system because they approach the source of radiation more closely. High power objectives may darken sufficiently to absorb more than 95% of the light in a few hours use on highly radioactive samples.

For more detailed examination of radioactive samples, the cathodically etched samples can be replicated by the Faxfilm technique. After this film is processed, the replicated microstructure is viewed on the electron microscope.⁽⁵⁾

2.3.4 Physical Testing Cells

Hardness Testing

Macro-hardness tests of radioactive metal specimens may be performed with a remotely operated Wilson "Rockwell" Hardness Tester which is located in one of the low level cells. Tests may be carried out using both the standard "Rockwell" B and C scales, and the special A, D, E, F, G, and H Scales (See Figures XVI-52).

DECLASSIFIED

DECLASSIFIED

-1637-

HW-40000

Electrical Resistivity

The electrical resistivity of radioactive specimens is determined by the voltage drop method. The specimen is contained in a constant temperature oil bath which may be operated at any temperature from room temperature to 100 C. Voltages are measured with a Leeds and Northrup low resistance potentiometer. (See Figures XVI-53 and XVI-54).

Gamma Scintillation Scanning

Variations in fission product concentration in an irradiated fuel element may be determined by means of a Gamma Scintillation Scanner. These determinations are made in the following manner: a 1/8-inch thick wafer is placed in a remotely operated positioning device which is located in one of the cells. The wafer may then be positioned in such a manner that any point along any diameter may be lined up with a 1/8-in. diameter hole which extends through a 10-in. thick lead plug. The gamma ray photons emitted by the fission products in a very small volume of the wafer pass through the hole and are counted by a scintillation counter. Graphs of the measured gamma activity versus distance from the center of the wafer indicate the relative concentration of fission products across any diameter of the wafer. (See Figure XVI-55.)

Vacuum Annealing

Radioactive samples may be annealed in an in-cell vacuum furnace which is capable of annealing at temperatures up to 700 C and under a vacuum of 1×10^{-5} mm of Hg. The inside diameter of the furnace is two inches and the "flat" temperature zone is 3 inches long.

Impact Testing

A Sonntag Universal Impact Machine with a capacity of 240 ft. -lbs. is available for the impact testing of mildly radioactive specimens. This unit has not as yet been installed in a cell; consequently high radioactive samples cannot be tested.

DECLASSIFIED

DECLASSIFIED

-1638-

HW 10000

X-Ray Diffraction

X-ray diffraction studies of radioactive materials are accomplished by means of a Double Crystal X-Ray Diffraction Unit. Briefly, this unit consists of an X-ray tube, goniometer, monochromatic aluminum crystal, lead shielding and a Geiger-Muller tube, all of which are located inside a portable lead brick shield. The power supply, controls and recorder are located outside the cell. Different X-rays are allowed to reach the G-M tube without interference from the radiation emitted by the sample itself in the following manner. The X-rays which are diffracted by the specimen are passed through a slit in a lead block shield, diffracted by the monochromatic crystal, passed through a second slit and finally detected by the G-M tube. (See Figure XVI-56.)

2.3.5 Tensile Testing of Irradiated Materials

The tensile testing of irradiated materials is done on two shielded 60,000 lb. tensile machines. One machine is used to perform room temperature tensile tests. This machine cost approximately \$20,000 and is surrounded by radiation shielding walls of Meehanite cast iron 10-1/2 in. thick. The sample elongation is measured by a microformer type S-3 extensometer and recorded with load readings on an X-y recorder.

The second machine is radiation shielded with walls of lead brick. The machine performs elevated temperature tensile tests (max. temp. 700 C) while maintaining the sample at a high vacuum (10^{-5} mm). The elongation of the sample during test is determined optically by measuring the movement of two finely scribed lines on platinum strips which are welded to the sample before testing. The specially designed furnace has quartz windows in the side which permit viewing of the platinum strips on the sample during testing.

At both tensile machines samples are manipulated remotely from outside the cell.

DECLASSIFIED

DECLASSIFIED

-1639-

HW-40000

2.3.6 Dry Storage Cell

Recessed in the west end of the canyon floor is a unique repository for dry storage of radioactive samples. Usually samples are held here after and during the testing program to provide easy procurement and safe storage (Figure XVI-57).

The cell is designed on a principle similar to a rotating soft drink dispensing machine, with 5 perforated discs which can be rotated so that each of the 160 holes in each disc can be individually lined up to permit insertion or removal of individual samples. A 10-in. thick meehenite cast iron top shields the samples from floor level.

The cell is 7-1/2 ft. in diameter and 6-1/2 ft. deep and can hold 786 2-3/4 in. diameter x 9 in. long canned samples.

Air flow is maintained within the unit by drawing sufficient air through a CWS filter at its base to permit safe entry and exit to the unit.

2.3.7 Decontamination Cell

In the center part of the north wing of the building is the decontamination room. It contains a cell and a hood to disassemble and decontaminate the equipment that has been used in the multi-curie cells.

The decontamination cell is a 1-in. thick steel shell enclosing a 8 ft. diameter x 5 ft. high and two 4 ft. diameter x 5 ft. high spaces. Each space has a rotating steel disc on which pieces of contaminated equipment are given their final decontamination before removal to shop or storage. Decontamination is usually accomplished by swabbing with solvents, acids or bases.

The decontamination hood is the usual type of radiation hood which permits the complete soaking of small pieces with low level contamination to remove all traces of contamination.

DECLASSIFIED

DECLASSIFIED

-1640-

HW-10803

2.3.8 Junior Caves

This equipment has 3 ft. steel shielding surrounding an area of 2-1/2 x 4 ft. and is used primarily for testing of structural materials used on reactors or separation plants. It was originally designed for chemical use but is now used for a multiplicity of work on low level radioactive samples.

G. REFERENCES

- (1) HW-23874 Shielding Requirements - Materials Inspection Basin, R. L. Dickeman, 3/20/52.
- (2) HW-26175 Development of the Hanford Slave Manipulator for use in the Multicurie Cells, R. E. Field and J. F. Gifford, 10/31/52.
- (3) HW-29149 Comparison of Descaling Solutions for Aluminum Alloys, R. S. Dalrymple, 9/2/53.
- (4) HW-29473 Equipment for Measuring Grain Size of Irradiated Uranium, W. K. Kratzer, 9/28/53.
- (5) HW-34390 Investigations on the Microstructure of Uranium, T. K. Bierlein, 1/18/55.
- (6) HW-40463 A Tentative Program for the 1706-KER Recirculation Test Facility, J. M. Atwood, 12/15/55.

H. LIST OF TABLES AND FIGURES

Table XVI - 1 Operating Conditions for the Experimental Loops.

- Figure XVI -
- 1 External View of 306 Bldg. from S. W.
 - 2 External View of 306 Bldg. from S. E.
 - 3 External View of 314 Bldg. from S. E.
 - 4 Cutaway View of 306 Bldg.
 - 5 Metallographic Laboratory - 306 Bldg.
 - 6 Hardness Testing Equipment - Mechanical Laboratory - 306 Bldg.
 - 7 Specimen Polishing Laboratory - 306 Bldg.
 - 8 Sonic Testing Laboratory - 306 Bldg.
 - 9 Metal Fabricating Area - 306 Bldg.

DECLASSIFIED

DECLASSIFIED

-1641-

HW-40000

- Figure XVI -
- 10 Salt Bath, Forge, Rolling Mill, and Swaging Machine - 306 Bldg.
 - 11 400 Ton Multiple Cavity Hot Press - 306 Bldg.
 - 12 Processing Area - 306 Bldg.
 - 13 Dip Canning and Vacuum Furnace - 306 Bldg.
 - 14 Thermal Cycling - 200 KW Tocco - 314 Bldg.
 - 15 Thermal Cycling Test - 314 Bldg.
 - 16 The 305 Test Pile
 - 17 Test Pile Control Room
 - 18 Galvanometer System and Calibrating Potentiometer
 - 19 A Metal Test Stringer
 - 20 Test Pile Charging Face
 - 21 H-Loop Flow Diagram
 - 22 The 1706 KER Loop
 - 23 Single Pass Boiling Facility
 - 24 Simplified Flow Diagram of ELMO-2 Loop
 - 25 Photo of Elmo-4 Loop
 - 26 ELMO-5 Loop
 - 27 Simplified Flow Diagram of ELMO-9 Loop
 - 28 105-C Metal Examination Facility
 - 29 Cartridge Loader
 - 30 Basin I Viewer
 - 31 Slug Dolly
 - 32 Stereomicroscope
 - 33 Cartridge Crane
 - 34 Slug Cleaner
 - 35 Slug Weasel
 - 36 Slug Surface Camera
 - 37 Slug Section Camera
 - 38 Slug Weigher
 - 39 Slug Diemensioner
 - 40 Slug Decapper

DECLASSIFIED

DECLASSIFIED

-1642-

HW 940000

Figure XVI - 41 Slug Dejacketer
42 Ultrasonic Test Equipment
43 Slug Fracturer
44 Slug Packager
45 Exterior View of the Radiometallurgy Building (327)
46 The Canyon (327)
47 Ground Floor Plan (327)
48 Abrasive Cutting Unit
49 A General View of the Metallographic Cell
50 Hanford Remote Polisher
51 Remotized Vacuum Cathodic Etcher
52 Hardness Testing
53 Schematic Diagram for Electrical Resistivity
54 Electrical Resistivity Unit
55 Gamma Scintillation Scanning
56 X-Ray Diffraction
57 Dry Storage Unit

TABLE XVI - 1

OPERATING CONDITIONS FOR THE EXPERIMENTAL LOOPS

<u>Facility</u>	<u>Max. Temp. (°C)</u>	<u>Max. Pressure (psi)</u>	<u>FLOW (GPM)</u>	<u>Tube Power (KW)</u>	<u>Test Section</u>	<u>Remarks on Loop Construction</u>
H-Loop (in Pile)	210	450		500	Zr Tube	
1706 KER (in Pile)	300	2200	10-60	1600	Zircaloy (2.4 in. o. d.)	3 of SS 1 of Carbon Steel
Single Pass Boiling (in Pile)	260	600	10-12	350-500	Zr or Zr-2	
ELMO-2	175	340	25		7 ft. Zr Process Tube (H-Dimensions)	SS Low pH
ELMO-3						
ELMO-4	280	1280	18		20 in. 3 in. pipe 10 in. 1-1/2 in. pipe	SS
ELMO-5	250	1350	75		10 in. 2 in. pipe	C. S.
ELMO-6	315	1500	30		4 ft. 2-1/2 in. pipe	SS
ELMO-7	315	2000	150		15 ft. Zr-2 KER Tube	SS
ELMO-8	365	3100	100		Dual Sections 5 ft. 2 in. pipe	C. S.
ELMO-9	300	2500	< 1		1 ft. 1/2 in. pipe	SS (Natural Convection)

DECLASSIFIED

HW-40000

UNCLASSIFIED

HW-40000

FIGURE XVI-1

EXTERNAL VIEW OF 306 BUILDING FROM S.W.

UNCLASSIFIED

AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

6 of 6

UNCLASSIFIED

HW-40000

FIGURE XVI-2

EXTERNAL VIEW OF 306 BUILDING FROM S. E.

UNCLASSIFIED

UNCLASSIFIED

UNCLASSIFIED

FIGURE XVI-3

EXTERNAL VIEW OF 314 BUILDING FROM S. E.

HW-40000

UNCLASSIFIED

HW-40000

FIGURE XVI-4

CUTAWAY VIEW OF 306 BUILDING

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI-5
METALLOGRAPHIC LABORATORY - 306 BUILDING

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI-6

HARDNESS TESTING EQUIPMENT - MECHANICAL LABORATORY - 306 BUILDING

UNCLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE XVI-7

SPECIMEN POLISHING LABORATORY - 306 BUILDING

UNCLASSIFIED

HW-40000

FIGURE XVI-8

SONIC ORIENTATION LABORATORY - 306 BUILDING

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI-9
METAL FABRICATION AREA - 306 BUILDING

UNCLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE XVI-10

SALT BATH, FORGE, ROLLING MILL, AND SWAGING MACHINE - 306 BUILDING

UNCLASSIFIED

HW-40000

FIGURE XVI-11

400 TON MULTIPLE CAVITY HOT PRESS - 306 BUILDING

UNCLASSIFIED

UNCLASSIFIED

FIGURE XVI-12

PRESSING AREA - 306 BUILDING

UNCLASSIFIED

HW-40000

FIGURE XVI-13

DIP CANNING AND VACUUM FURNACE - 306 BUILDING

UNCLASSIFIED

FIGURE XVI-14

THERMAL CYCLING - 200 KW TOCCO - 314 BUILDING

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE XVI-15

THERMAL CYCLING TEST - 314 BUILDING

UNCLASSIFIED

HW-40000

FIGURE XVI-16

305 TEST FILE

UNCLASSIFIED

HW-40000

FIGURE XVI-17
TEST PILE CONTROL ROOM

UNCLASSIFIED

FIGURE XVI-18

GALVANOMETER SYSTEM AND CALIBRATING POTENTIOMETER

DECLASSIFIED

HW-40000

FIGURE XVI-19

A METAL TEST STRINGER

DECLASSIFIED

12

DECLASSIFIED

HW-40000

Metal Test Stringer

Graphite Test Stringer

FIGURE XVI-20

TEST PILE CHARGING FACE

UNCLASSIFIED

HW-40000

FIGURE XVI-21

H LOOP FLOW DIAGRAM

UNCLASSIFIED

FIGURE XVI-22
1706 KER LOOP

UNCLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

HW-40000

FIGURE XVI-23

SINGLE PASS BOILING FACILITY

UNCLASSIFIED

FIGURE XVI-24

SIMPLIFIED FLOW DIAGRAM OF ELMO-2 LOOP

UNCLASSIFIED

HW-40000

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI-25

ELMO-4 LOOP

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI-26
ELMO-5 LOOP

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI-27

SIMPLIFIED FLOW DIAGRAM OF
ELMO-9 LOOP

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI-28

105-C METAL EXAMINATION FACILITY

UNCLASSIFIED

ASG-GE MICHLAND, WASH.

FIGURE XVI - 29

CARTRIDGE LOADER

UNCLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

HW-40000

FIGURE XVI - 30

BASIN I VIEWER

UNCLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE XVI - 33

CARTRIDGE CRANE

UNCLASSIFIED

HW-40000

FIGURE XVI-34

SLUG CLEANER

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI - 35

SLUG WEASEL

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI - 36
SLUG SURFACE CAMERA

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI - 37
SLUG SECTION CAMERA

UNCLASSIFIED

UNCLASSIFIED

FIGURE XVI - 38

SLUG WEIGHER

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI - 39

SLUG DIMENSIONER

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVI - 40

SLUG DECAPPER

UNCLASSIFIED

UNCLASSIFIED

HW-40000

OFF-GAS OUTLET

FIGURE XVI-41

SLUG DEJACKETER

UNCLASSIFIED

UNCLASSIFIED

HW-40000

UNCLASSIFIED

FIGURE XVI- 43
SLUG FRACTURER

FIGURE XVI - 44

SLUG PACKAGER

UNCLASSIFIED

HW-40000

FIGURE XVI-45

EXTERIOR VIEW OF THE RADIOMETALLURGY BUILDING (327)

UNCLASSIFIED

FIGURE XVI-46
THE CANYON (327)

FIGURE XVI-47

GROUND FLOOR PLAN OF RADIOMETALLURGY BLDG.

FIGURE XVI-48

ABRASIVE CUTTING UNIT

FIGURE XVI-49

A GENERAL VIEW OF THE METALLOGRAPHIC CELL

UNCLASSIFIED

UNCLASSIFIED

Control Mechanism located on outside of cell

Plug Mounted Polisher viewed through port-hole

FIGURE XVI-50

HANFORD REMOTE POLISHER

UNCLASSIFIED

HW-40000

UNCLASSIFIED

Vacuum System and Controls

Etching Chamber inside Cell

FIGURE XVI-51

REMOTIZED VACUUM CATHODIC ETCHER

UNCLASSIFIED

HW-40000

UNCLASSIFIED

HW-40000

FIGURE XVI-52
HARDNESS TESTER

UNCLASSIFIED

1. Metal Specimen	5. Ammeter 0-1 Amp.
2. Variable Resistor for Current
Adjustments 0-20 Ohm	6. Battery 6 Volt DC
3. Standard Resistance 0.001 Ohm	7. DPDT Switch
4. Switch for Reversing Current
to Specimen	8. K-2 Potentiometer with
Standard Cell
E_1 Potential Drop over Fixed Length of Specimen	9. Rubicon Galvanometer
E_2 Potential Drop over Standard Resistance	

FIGURE XVI-53 SCHEMATIC DIAGRAM FOR ELECTRICAL RESISTIVITY

UNCLASSIFIED

UNCLASSIFIED

UNCLASSIFIED

FIGURE XVI-54

ELECTRICAL RESISTIVITY UNIT

HW-40000

UNCLASSIFIED

FIGURE XVI-55
SCINTILLATION SAMPLE POSITIONER

UNCLASSIFIED

HW-40000

FIGURE XVI-56

DOUBLE DIFFRACTION ARRANGEMENT

FIGURE XVI - 57

DRY STORAGE UNIT

PART VI: SAFETYCHAPTER XVII: RADIATION PROTECTION
AND CRITICAL MASS CONTROL

<u>CONTENTS</u>	<u>Page No.</u>
A. PHILOSOPHY AND OBJECTIVES OF RADIATION PROTECTION	1702
B. BIOLOGICAL EFFECTS OF RADIATION	1703
1. External Radiation	1703
2. Ingestion of Radioactive Material	1703
C. DETECTION INSTRUMENTS AND METHODS	1704
1. Personnel Meters and Bioassay Samples	1704
2. Dosage Rate and Count Rate Meters - Hand and Shoe Counters	1704
D. PROTECTIVE EQUIPMENT	1705
E. RADIATION AND CONTAMINATION SOURCES, AND MEANS OF CONTROL	1706
1. Normal Uranium	1706
2. Thorium	1707
3. "C" and "J" Material	1708
4. X-Ray Generating Machines	1708
5. Test Pile	1708
F. CRITICAL MASS CONSIDERATIONS	1709
G. LIST OF FIGURES	1710

A. PHILOSOPHY AND OBJECTIVES OF RADIATION PROTECTION

Hanford observes the radiation dose limits established by the National Committee on Radiation Protection. These limits are based on maximum permissible doses of 300 mrem per week to the body (normally not to exceed 50 mrem per day) and 1500 mrem per week to the hands. (The term "mrem" is an abbreviation for "milliroentgen equivalent mammal"). According to the present state of the science, these limits are such that a person could receive this amount of exposure every week in his life without experiencing any harmful effects. However, it should be noted that a single accidental exposure many times as high as the weekly limit is not necessarily harmful. The permissible limit (without respiratory protection) for uranium dust in air is 3.0×10^{-11} microcuries/cc. The maximum permissible amount of uranium deposited in the body is 0.009 microcuries (about 14 milligrams).

The program of radiation protection is designed not only to keep personnel exposures within the permissible limits but to reduce or eliminate radiation exposure wherever it is practical to do so. All of the controls and procedures used in radiation protection are developed with these objectives in mind. However, as in any other program of this type, its effectiveness is determined to a large extent by the cooperation of the people concerned. Ultimately, radiation protection is the responsibility of each individual.

The Radiological Sciences Department issues and maintains a manual entitled "Radiation Protection Standards". As stated in the preface of this manual, it "contains the latest policies for control of radioactive materials and radiation hazards at HAPO. These standards have been formulated from national policies of radiation protection, AEC requirements for control of radioactive materials, and working limits which have been adopted over a period of time at this location." The manual serves as a guide for all work with radioactive materials at HAPO.

B. BIOLOGICAL EFFECTS OF RADIATION

1. External Radiation

The biological effects of radiation exposure are extremely complex and depend upon the total dose, total duration of exposure period, organs receiving the exposure, the energy and type of radiation, etc. In general, the extent of biological damage produced by radiation exposure is determined by the amount of exposure and the ability of the human body to replace damaged body cells. In addition to the immediate damage produced by high, uncontrolled radiation doses, there is evidence which indicates that permanent body damage may result.

2. Ingestion of Radioactive Material

Exposure to radiation can occur in two different ways - exposure of the body to external radiation, and internal radiation resulting from deposition of radioactive material in the body. External exposure can be controlled by determining dosage rates and then regulating personnel exposure times accordingly. However, control of the ingestion of radioactive material is even more complex, since many of the radioactive elements are selectively deposited in different organs and are eliminated from the body at different rates. For example, soluble uranium is selectively deposited in the kidneys. When a soluble uranium compound is ingested, some is eliminated from the body in the urine and most of the remainder is deposited in the kidneys, where it has a two-fold effect. It acts not only as a heavy metal poison (similar to lead) but also continuously emits radiation which damages surrounding tissues. Since there is no known way of effectively removing such deposited material, it is imperative to control rigidly the ingestion of radioactive material. This is accomplished by the control of radioactive fines (small particles such as dust), careful evaluation of the hazard, and use of the proper protective equipment and work techniques.

C. DETECTION INSTRUMENTS AND METHODS

1. Personnel Meters and Bioassay Samples

The two properties of radiation which make it detectable are its ability to darken photographic film and to ionize gases.

All personnel at Hanford who work in areas where radioactive materials are processed are required to wear a combination security and film badge and, in most cases, a pair of "pencil" meters also. The film on the film badge darkens proportionally to radiation exposure and at regular intervals (weekly in 300 Area) the film packets are removed, developed, and the radiation exposure determined. These film badge recordings provide the primary record of personnel exposure. The "pencil" meters are essentially a pair of identical, fully charged electric condensers. Radiation entering the condenser chamber causes ionization and consequent reduction of the electric charge. The reduction in charge is approximately proportional to the amount of radiation striking the pencil. The residual charge on the pencils is determined daily, and the results may be interpreted directly in terms of radiation dose. Thus, these pencils provide a day-to-day estimate of personnel exposures to penetrating radiation.

In areas where ingestion of radioactive materials (e.g., uranium) may occur, bioassay (urine) samples are required. The frequency of the sampling is commensurate with the severity of the hazard, but the sampling frequency does not normally exceed once a week. For uranium a two-part sample is required - one at the end of the work week and the other at the start of the succeeding week. Analysis of these samples provides data from which uranium ingestion can be estimated.

2. Dosage Rate and Count Rate Meters - Hand and Shoe Counters

Radioactivity is detected by two basically different classes of portable instruments. Dose rate meters are used to evaluate radiation levels where radiation exposure from the source is the hazard. The response

of these instruments is proportional to the ionizing effect of the radiations, and the dial readings are readily converted to dose rates. Since total dose is the limiting factor, dose rates are used in determining safe working times for the conditions present. Examples of dose rate instruments are the "CP" and the "Juno". (See Figures XVII-1 and XVII-2)

Count rate instruments are more sensitive than dose rate instruments by a factor of about 100. The response of the count rate instruments is proportional to the number of emissions striking the counter per unit time. They are primarily for detecting and evaluating the presence of radioactive contamination on clothing, tools, equipment, floors, etc. Most of these instruments have the familiar Geiger-Mueller tube as the detector and are known by the group name of "GM's" (See Figure XVII-3). Some alpha counters, such as the "poppy" (See Figure XVII-4), are an exception. Hand and shoe counters (see Figure XVII-5) are essentially a fixed type of count rate instrument which is specifically designed for detecting significant amounts of contamination on hands or shoes.

D. PROTECTIVE EQUIPMENT

Protective equipment is used primarily to prevent ingestion of radioactive material, prevent contamination of personal clothing or the skin, or, in certain cases, to provide some degree of radiation shielding.

A variety of face masks and respirators are available and their use is required where significant air contamination conditions exist. The materials present in the air and their concentrations are the factors that determine the specific respiratory protection required.

White coveralls or laboratory coats are worn wherever there is possibility of contacting radioactive contamination. The white color is standard throughout the plant for protective clothing in jobs where contamination may occur, and no other color is substituted. Shoe protection or process shoes are used where floor contamination may be a problem. Many other types of protective clothing are available when conditions warrant it.

Many different types of gloves are used for handling radioactive material or contaminated equipment. The prime function is to prevent contamination of the hands, although in some cases they may provide significant radiation shielding as well. For example, leather gloves are estimated to provide about forty per cent shielding from the radiation emitted by natural uranium.

E. RADIATION AND CONTAMINATION SOURCES, AND MEANS OF CONTROL

1. Normal Uranium

Fuel elements are normally fabricated from natural uranium and consequently the radiological characteristics of this material are a primary consideration in radiation and contamination control in this part of the Hanford process.

Radiation levels from bare uranium can produce significant radiation exposure to both hands and body of personnel working in the immediate vicinity. Hand exposure can be minimized by wearing leather or plastic coated gloves. If prolonged handling is necessary (greater than one hour per day), the specific situation is studied to determine the appropriate handling time limits. Body exposure from bare uranium is highly dependent on both the source distance and size of the source. Radiation exposure can be minimized by maintaining a good working distance from the material whenever possible, staying at least several feet from the source when not actually working with it, and shielding the exposed uranium surfaces if large quantities of material are being processed. Experience has shown that radiation exposures encountered in a routine uranium processing operation can be effectively controlled by determining dose rates with time study methods and then establishing definite working procedures.

In addition to radiation exposure, contamination of the air, equipment, or work area is a potential hazard in bare uranium processing. Any hot

or cold metal working processes such as melting, burning, rolling, extrusion, machining, sawing, grinding, etc. may produce hazardous air contamination as well as contamination of the equipment and work area. Close control of these operations is necessary. Uranium oxidizes rapidly on contact with the air, and this easily removed oxide film is a major source of contamination. For this reason personnel who handle large quantities of uranium are normally required to wear protective clothing as well as gloves. A hand and shoe count is taken after working with uncanned uranium in any form. In the event of a high count the appropriate radiation monitoring group is contacted and decontamination efforts begun.

The canning of uranium reduces the radiation dose rate from the slug by about ninety per cent and essentially eliminates the contamination hazard. Fewer controls are necessary to regulate radiation exposure from this source. The main considerations with canned slugs are to maintain a reasonable working distance from the material and to avoid direct body contact for prolonged periods.

Solutions and compounds containing uranium are encountered in parts of the canning, slug preparation, and slug recovery operations and in the analytical laboratory. With the possible exception of Slug Recovery these are sufficiently dilute that with nominal contamination control measures they do not constitute a significant health hazard. The C-6 (sodium uranate) recovered from the filter press in Slug Recovery is quite concentrated and requires careful handling techniques.

2. Thorium

Small quantities of thorium slugs are occasionally processed, and special handling techniques are required because the gamma radiation intensity is greater from thorium than from uranium. Shielding requirements are greater than for uranium and significant dosage rates are encountered at greater distances than from uranium.

3. "C" and "J" Material

"C" and "J" slugs, which are an alloy of aluminum and U^{235} , are processed periodically. The radiation dose rate from this material is very low and may be neglected in considering external hand and body exposure. However, smearable contamination of relatively high alpha activity can be easily removed from the surface of these slugs, and for this reason gloves of some sort are always worn when handling the bare material. Regular five fold hand and shoe counters will not detect this type of contamination, and if hand or clothing contamination is suspected a survey is made with an alpha sensitive detection device such as a "poppy". If significant activity is detected, decontamination is accomplished by soap and water washing in a regulated sink.

4. X-Ray Generating Machines

X-Ray generating devices are used in several parts of the process for fluoroscoping the canned slug assembly and radiographing the weld bead. These machines generate high voltage X-rays which, if not properly shielded, are capable of producing extremely high radiation doses. For this reason, it is imperative that they be operated in strict conformance to the operating procedure. In addition, any alterations or repairs made on these machines may produce radiation "leaks", and therefore, it is always necessary to have competent personnel survey these machines after such work is done.

5. Test Pile

The 305 Test Pile normally operates at very low power levels, and radiation "leakage" from the pile is negligible under these conditions. Material which is tested in the pile, however, often has a very high initial activity when removed, and this must be considered in subsequent handling. After Test Pile irradiation normal uranium is handled with three foot tongs and placed in a locked storage area for at least twenty-four hours. At the end of this time the induced activity has essentially

returned to normal. Other materials exhibit even greater increases in activity immediately after irradiation. "C" and "J" slugs are examples. In general, if dose rates and handling techniques for a given material are not established from previous experience, individual monitoring and Special Work Procedure methods are necessary.

F. CRITICAL MASS CONSIDERATIONS

A critical mass may be defined as the amount of fissionable material of specific shape, size, and composition necessary to cause a chain reaction. This means that neutrons are being generated more rapidly than they are dissipated, and the reaction will continue to build up. Extreme gamma, beta, and neutron radiation plus extreme heat are emitted whenever criticality is exceeded. If such a reaction is uncontrolled all personnel in the immediate vicinity would be exposed to these radiations and possible fatal injuries could be incurred.

Natural uranium such as that used in the normal Hanford fuel element does not contain a sufficient concentration of the U^{235} isotope to produce a critical mass even when large quantities of it are being processed or stored in close proximity, except in the special environment of a reactor. However, "C", "J", and "E" slugs are processed periodically, and these slugs are artificially enriched with U^{235} to the extent that improper storage or handling techniques could produce a critical mass. Specific limitations are placed on quantities and configurations to assure complete safety in the storage and processing of these slugs. This information is given in detail in the back part of the Process Standards Manual, Metal Preparation Section, Document No. HW-22556, Standard No. H-1001 and C-901.

G. LIST OF FIGURES

Figure XVII-1	The "Cutie Pie" (CP)
Figure XVII-2	The "Juno"
Figure XVII-3	The Geiger-Mueller (GM)
Figure XVII-4	The "Poppy"
Figure XVII-5	A Hand and Shoe Counter

UNCLASSIFIED

HW-40000

FIGURE XVII-1
THE "CUTIE PIE" (CP)

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVII-2

THE "JUNO"

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVII-3

THE GEIGER-MUELLER (GM)

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVII-4
THE "POPPY"

UNCLASSIFIED

UNCLASSIFIED

HW-40000

FIGURE XVII-5

A HAND AND SHOE COUNTER

UNCLASSIFIED

DECLASSIFIED

-1801-

HW-40000

PART VI: SAFETY, (Contd.)

CHAPTER XVIII: SAFETY AND FIRE PREVENTION

CONTENTS

Page No.

A.	PHILOSOPHY AND OBJECTIVES OF SAFETY AND FIRE PREVENTION	1802
B.	THE SAFETY INFORMATION PROGRAM	1802
C.	INDUSTRIAL HAZARDS OF A GENERAL NATURE	1803
D.	SPECIFIC PROCESS HAZARDS AND CONTROL	1804
1.	Flammable Nature of Uranium	1804
2.	Hot Materials or Equipment	1804
3.	Al-Si Handling	1805
4.	Toxic Solvents, Acids, and Bases	1805
5.	Flammable Solvents and Combustion-Supporting Chemicals	1807
6.	Special Handling Problems	1808
7.	Welding Arc Shielding	1808
8.	Noise Problem	1808
9.	Bottled Gas Handling	1809

DECLASSIFIED

DECLASSIFIED

-1802-

HW-40000

A. PHILOSOPHY AND OBJECTIVES OF SAFETY AND FIRE PREVENTION

The ultimate objectives of the Safety and Fire Prevention Program at Hanford are the prevention of human suffering and property damage which result from industrial accidents and fires. The method of achieving this goal is basically two-fold. The first consists of providing the safest possible working conditions - adequate lighting, safely designed and arranged equipment, adequate ventilation, protective clothing and equipment, etc. The second, and even more important is a continuous safety information program which, as stated in Organization and Policy Guide 14.9 is designed "to educate employees in the necessity of forming safe working habits, in maintaining good housekeeping habits and of thinking and acting safely at all times."

B. THE SAFETY INFORMATION PROGRAM

All new employees receive a general plant safety orientation shortly after they are hired and an area safety orientation immediately after they are assigned to an area.

A book of specific Safety Bulletins has been issued and maintained. These bulletins suggest safe practices in dealing with a wide variety of industrial hazards. The books are widely distributed throughout the plant and provide an invaluable source of safety information. In addition, each group carries on a program of regular, scheduled safety meetings for its personnel and originates and maintains suitable Job Hazard Breakdowns and Safety Rules for its own operations.

Job Hazard Breakdowns have been written for almost all the jobs in Metal Preparation. The importance of these Job Hazard Breakdowns to job safety cannot be overemphasized. They provide a step by step analysis of each operation, note the hazard or hazards which may be encountered, and give the safe method of performing the operation. These Job Hazard Breakdowns are for routine or production type jobs. They

DECLASSIFIED

DECLASSIFIED

-1803-

HW-40004

are affixed to the machine or posted in the work location. In the case of experimental work, Job Hazard Breakdowns are filled out for representative jobs and filed in the building Supervisor's file. To provide a safe method for operation at the machine, a comprehensive set of Safe Operating Rules is posted at each work location. The Area Safety Engineer periodically holds a four hour "Supervisor Safety Training Program" in which all phases of the accident prevention program are discussed. The purpose of this program is to help train all supervisors so they are better equipped to carry out their part in the safety program.

Monthly safety topic and health topic pamphlets are issued to all supervisory personnel. In addition the Area Safety Engineer has available films and printed literature on a wide variety of safety topics which are suitable for safety meetings. Accident Prevention posters are prominently displayed in almost all work locations.

C. INDUSTRIAL HAZARDS OF A GENERAL NATURE

Many of the hazards present in fuel element production are common to most routine manufacturing operations. Heavy hi-lift traffic occurs through much of the production area, and special safety emphasis is placed on the operation of these machines. Machinery with moving parts, common throughout the production area, is well equipped with guards and maintained in safe operating condition. Storage methods are controlled to prevent the possibility of falling objects. Of prime importance to the safe performance of equipment maintenance is the "Lock and Tag"* procedure, which provides a uniform method of assuring positive equipment shutdown, when maintenance work is performed. Proper fire protection as well as high housekeeping standards are actively emphasized and maintained in all operations. Suitable fire fighting equipment is located at strategic points throughout the production area.

* The "Lock and Tag" procedure; padlocks and "do not operate" tags are placed on the equipment by building operating personnel or the craftsman concerned.

DECLASSIFIED

-1804-

HW-40000

D. SPECIFIC PROCESS HAZARDS AND CONTROL

1. Flammable Nature of Uranium

Uranium metal in finely divided form (e.g., turnings or chips) being pyrophoric by nature, is highly flammable and burns with an intense heat. Extinguishing uranium fires is very difficult because the burning metal reacts rapidly (and sometimes violently) with most extinguishing agents. Special "Met-L-X" fire extinguishers are provided for uranium fire fighting. Flooding with an excess of water (a solid stream - not spray) is fairly effective. "Blanketing" with argon gas is also a satisfactory method if the fire is in a closed container. Uranium turnings and chips are normally stored under water or oil to prevent spontaneous ignition. Any cutting operation with uranium requires adequate coolant flow to prevent ignition of the chips.

2. Hot Materials or Equipment

Hot equipment is one of the major hazards associated with fuel element preparation. Normal lead dip canning requires immersion of the slug twice in molten metal baths maintained at about 600 C. and strict adherence to operating procedures as well as use of appropriate safety equipment is necessary to prevent burns. Flame-proof coveralls, side shield safety glasses, face shields, leather spats, and long gauntlet leather gloves are used for protection against burns from spatters or drips of hot metal. The slugs are cold water quenched immediately after canning to permit safe handling.

Extreme care is exercised to prevent moisture-containing materials from being introduced in molten metal or salt baths, since such an event can cause eruption of molten material from the furnace. Whenever significant moisture content is a possibility, the material is pre-dried in a heated cabinet. Precautions are taken to ensure that the central cavity in cored slugs is moisture-free before canning. One particular hazard involves immersing tubular parts into hot baths of salt or metal.

DECLASSIFIED

They have a tendency to "percolate" and have been known to eject the bath material as far as 12 to 15 feet. Special precautions are necessary when handling material of this configuration.

Hot material is also an operating hazard in the hot press canning, slug welding, and autoclave processes and appropriate measures are taken for control.

3. Al-Si Handling

The aluminum-silicon alloy used in the canning furnace often forms sharp, brittle "spikes" on the cap end of slugs, sleeves, and other equipment with which it comes in contact. These spikes are capable of penetrating leather or plastic gloves, and inflicting puncture wounds. For this reason considerable caution is required in handling material which has been in contact with molten AlSi. This is particularly true in the slug quench, stamping and facing operations.

4. Toxic Solvents, Acids and Bases

Several liquid process chemicals are used which can be toxic to personnel if appreciable external exposure, inhalation, or ingestion should occur. Suitable protection is provided in operations where exposure to the liquid may occur, and safety showers are located in the immediate vicinity of all potentially hazardous chemicals.

Nitric acid, sulfuric acid, solidum hydroxide, trichloroethylene, carbon tetrachloride, and diversey are all hazardous from the standpoint of skin contact because of the burns or irritation which they may produce. In addition, nitric acid, trichloroethylene, and carbon tetrachloride are considered hazardous when inhaled as fumes because of the severe lung irritation which they may produce. Threshold limits are shown in the table below.

DECLASSIFIED

-1806-

HW 40000

THRESHOLD LIMIT VALUES FOR ATMOSPHERIC CONTAMINATION⁽¹⁾

<u>Material</u>	<u>Physical State</u>	<u>Vapor pressure mm Hg at 20°C</u>	<u>MAC⁽²⁾</u>
Nitric acid	Mist or vapor	47.9	10 ppm ⁽³⁾ (Fairhall) ⁽⁴⁾
Sulfuric acid	Mist	----- ⁽⁵⁾	1 mg/M ³
Sodium hydroxide	Mist	----- ⁽⁵⁾	2 mg/M ³ (tentative)
Trichloro- ethylene	Vapor	60.0	200 ppm
Carbon tetrachloride (Diversey 514)	Vapor	91.3	25 ppm
Chromic acid	Mist	----- ⁽⁵⁾	0.1 mg/M ³
Methanol	Vapor	94	200 ppm

- (1) Threshold limit values for 1955 - American Conference of Governmental Industrial Hygienist (except nitric acid)
- (2) Maximum Acceptable Concentration (8 hours exposure)
- (3) parts per million, by volume
- (4) Fairhall, Industrial Toxicology, P. 81, Williams and Wilkins 1949.
- (5) Vapor pressures for sulfuric acid, sodium hydroxide and chromic acid are negligible at room temperature. The hazard arises from the solution producing a mist, which is not related to vapor pressure.

Hot nitric acid is used in the bare slug pickling operation and in canned slug etching. Adequate ventilation is provided for fume removal, and the liquid is confined in such a way as to minimize the possibility of external contact.

Trichloroethylene is used in vapor degreasers, the bare slug pickle, component parts preparation, canned slug etch and special canning processes. Normal degreaser operation prevents the escape of a significant

DECLASSIFIED

-1807-

[REDACTED]

amount of vapor, and proper protective equipment (face shield, gauntlet rubber gloves, etc.) is worn whenever a possibility of external contact exists. Extended use of trichloroethylene, particularly for aluminum degreasing, may cause a breakdown of the stabilizer and produce a violent decomposition of the solvent. For this reason, degreaser liquid is sampled weekly to determine stabilizer content.

Sodium hydroxide in fifteen to fifty per cent concentrations is used in the Slug Recovery process, and here the primary problem concerns avoiding skin contact. This is accomplished primarily through use of a face shield, coveralls, side shield safety glasses, and long gauntlet rubber gloves. Carbon Tetrachloride was used in the slug spraying operation just prior to frost testing, and adequate ventilation was provided to prevent inhalation of the fumes.

A small "tank farm" is maintained for the storage, makeup, and pumping of chemicals used in the slug fabrication process. Nitric acid, sulfuric acid, sodium hydroxide, diversey, methanol, sodium nitrate, and trichloroethylene are handled and the hazards characteristic of these chemicals are encountered. All tank farm operations are strictly controlled by operating procedures based on accepted methods of handling industrial chemicals, and protective equipment such as acid suits, goggles, etc., are worn where appropriate.

5. Flammable Solvents and Combustion-Supporting Chemicals

Nitric acid, in addition to its toxicity (as described above), is a strong oxidizing agent and it is necessary to prevent it from coming in contact with any combustible substance, since fire or explosion could result. This is accomplished primarily by careful housekeeping in areas where nitric acid is used.

Methanol is highly flammable and extensive precautions are necessary in the vicinity of the cap and can machines, where it is used. Control is maintained partly through fume removal and partly through elimination of

[REDACTED]

DECLASSIFIED

-1808-

REF ID: A640000

all sources of flames or sparks in the immediate vicinity of the machines. Contact with any oxidizing chemical such as nitric acid or diversey must be avoided as spontaneous combustion may occur.

Hydrogen gas is generated in the reaction between aluminum and sodium hydroxide; and because of the severe fire and explosion hazard this would create in the Slug Recovery operation, sodium nitrate is mixed with the caustic. This converts the hydrogen to ammonia as rapidly as it is released, thus eliminating the hazard.

6. Special Handling Program

The very high density of uranium metal creates special handling problems. An eight inch slug weighs about eight pounds, and this very high weight-to-size ratio makes a secure grip more difficult and increases the pinch point hazard as well as the danger to the feet from dropped slugs.

Safety shoes or equivalent toe protection is required in all production operations. In addition to personnel handling hazards, all mechanical handling or processing equipment must be designed and built correspondingly stronger to prevent breakdown. Special consideration is also given to this characteristic in all storage and shipping operations.

7. Welding Arc Shielding

Canned slugs are cap-welded by arc-welding in an inert atmosphere, and the intense white light given off during welding is shielded by heavily tinted glass. Without these shields the eyes of the operator would be damaged by the exposure to such intense light; hence, these shields are automatically brought into position before the arc is struck, and no welding is done without shielding.

8. Noise Problem

Noise levels in two spots in the production area are of such intensity and frequency as to require ear protection. These areas are the Acme-Gridley slug facing lathes (protection required for lathe operator only),

DECLASSIFIED

[REDACTED]
-1809-

HW-40000

and the furnace pit below the canning furnaces.

9. Bottled Gas Handling

A large quantity of argon gas is consumed by the slug welding operation, and this requires the routine handling of a large number of gas cylinders. Hazards such as pinch points, cylinder or manifold ruptures, or dangerous reactions resulting from improper cylinder identification are inherent in compressed gas usage. Safe handling procedures, as recommended in Accident Prevention Bulletin No. C-10 are followed to minimize the hazard.

[REDACTED]

DECLASSIFIED

-1901-

HW-40000

INDEX

A

Acceptance tests, 1402
Acme Gridley lathes, 1114
Alloys of uranium, 505
Al-Si composition, 809
Al-Si recovery, 903
Aluminum
 Alloys, lithium, 508
 uranium, 509
 Components, 702, 804, 1007
 Composition, 703
 Corrosion, 314, 622, 705
 Properties, 506, 618-622
 Recovery, 903
Annealing furnace, 1131
"A" Process (See Triple Dip
 Canning)
Area (313, 300), 1002
Arrangement of manual, 102
Assembly process, 801
Autoclave, 313, 1124, 1414
Auxiliary equipment, 1202
Auxiliary processes, 902
Average Outgoing Quality Limit, 1404

B

Billet egg test, 1615
Biological effect of irradi., 1703
Bismuth slugs, 824
Blister Test, 1409
Bond Test, 1413, 1630
"B" Process, 823
Braze inspection, 1412
Braze porosity, 904
Breaker (irradi. slugs), 1630
Brookhaven National Laboratory
 Reactor, 106
Buckling, 206
Bumping, 409

C

Can and cap preparation
 machine, 1103, 1132
Canned slug etch, 813
Canning bath, 807
Canning sleeve, 805
Canning test, 1410
Cap failures, 408
C-Basin, 1624
Charge-discharge, 402
Chemical control (process), 1313
Chemical solutions, 1007
Chemical tests, 1408
Coaxial fuel elements, 313
Coefficient of heat transfer, 305, 307
Component fabrication, 703
Conductivity, aluminum, 307
 Uranium, 308
Conformance reports, 1512
Contamination sources, 1706
Control instruments (process), 1302
Control (test pile), 1611
Conversion ratio, 208, 210
Cored slug, 311
Core failure, 406
Core test (gamma ray), 1125
Corrosion, aluminum, 314, 622,
 705
 Intergranular, 315
 Uranium, 313, 702
"C" Process, 823
Crack propagation, 312
Critical mass, 1709
Crystal structure (uranium), 502
"C" slugs, 818, 824
Cut-off cell, 1634

D

Data collecting (process), 1510
Deformation (uranium), 503, 610

DECLASSIFIED

-1902-

HW-40000

INDEX (Contd.)

Degreaser solvent still, 1210
Degreasing unit, 1104, 1108, 1120
Dejacketer (irrad. slugs), 1630
Density (uranium), 502, 606
Description of fuel element, 103
Destructive testing, 1512
Developing machine, 1123
Development facilities, 1603
Diffusion, 313, 609
Dimensional instability, 409, 616
Dimensioner (irrad. slugs), 1629
Dimensions of standard elements
 Table VII-1, 703
Dingot uranium, 711
Dip braze canning, 802
Diversey, 1106
Duponal, 1105

E

Effective tubes, 213
Effect of irradiation on uranium, 602
Electrical resistivity (uranium), 605
Electron microscopy, 608
ELMO-2, 1620
ELMO-4, 1621
ELMO-5, 1621
ELMO-6, 1622
ELMO-7, 1622
ELMO-9, 1623
End cap removal (irrad. slugs), 1629
Energy of fission, 202
Enriched uranium, 211
Enriched uranium-aluminum slug
 fabrication, 722
Equipment (development), 1606, 1610
eta (η), 204
Etching and replica techniques, 608
Experimental Loops, 1617
Exponential pile, 207
Exposure, 403
Extrusion, uranium, 503

F

Fabrication of uranium, 503
Failures, 402-409
Fast effect, 204-210
Final inspection, 814
Fission process, 202
Fission products, 204, 614
Flat plate elements, 410, 411
Flattening, 213, 403
Flow and pressure control (process)
 1311
Flow of materials, 1006
Fluid flow, 302
"F" Process (see Lead-dip canning)
Functional tests of components, 1407
Funtion of fuel element, 104

G

Gas receipts (process), 1008
Grain size measurements (irrad.
 slug), 1630
Growth mechanisms, 617

H

Hardness (uranium), 603
Heat transfer, 304
Heat treatment (uranium), 504, 717
High purity aluminum, 318
H-loop, 1618
Hot press canning, 818
Hot presses, 1126
Hot spots, 315
"HPA" Process, 818
Hydraulic presses (controls), 1311
Hydrogen in braze, 806
 in lithium slugs, 825
 in uranium, 904

I

Identification System, 1502

DECLASSIFIED

-1903-

HW-40000

INDEX (Contd.)

Impact strength (uranium), 604
Induction furnaces, 1111, 1302
Industrial hazards, 1803
Ingestion (radioactive mat'l.), 1703
Inhour, definition, 205
Inspection, 1411
Insulated slug, 312
Interdiffusion, (U and Al), 313
Intergranular corrosion, 406
Internally and Externally cooled slug, 311
Irradiated metal examination, 1624
Irradiation damage, 612
Isotope production, 104

J-K

Jacket failures, 405
Job Hazard Breakdown, 1802
"J" Slug, 818-824
KER Facility, 1619

L

Lathes(manual), 1130
Lead-cadmium slugs, 824
Lead-dip canning, 802-814
Lead (dummy) slugs, 1009
Length inspection, 1411
Lithium-Aluminum slugs, 725, 818-824
Lot designations, 1502

M

Marking System, 1507
Materials Testing Reactor, 106, 411
Metallographic Cell, 1635
Metallography, 606, 621, 1635
Methanol, 1106
Microbuck (definition), 207
Migration area, 206
Modulus of elasticity (uranium), 606
Muffle furnace, 1212
Multicurie cells, 1633

Multiplication (k), 204, 210

N

Neutron source materials, 509
Neutron source reactors, 106
Nitric acid tank, 1109, 1124
Non-destructive testing, 812
Nozzle bore diameter, 303
NRX Reactor, 106

O

Operating conditions, 109
Operating experience, 401
Optical microscopy, 606
Outgassing, 904
Overhead power conveyors (process), 1110

P-Q

Packaging (irrad. slugs), 1631
Penetration test, 813, 1117, 1120, 1413
Photography (irrad. slugs), 1628
Physical Constants Test Reactor, 207
Physical properties (uranium), 604
Physical testing (irrad. mat'l.), 1636
Physics, lattice, 202
reactor, 212
Pickling, 804
Piece marking, 1507
Pitting, 315
Poison columns, 213
Power density, 410
Power levels, 403
Power production, 105
Preheat and submerge cycle, 807
Pressure drop, 303
Process control, 1402, 1515
Process equipment, 1103

DECLASSIFIED

-1904-

HW-40000

INDEX (Contd.)

Process hazards, 1804
Process synopsis, 112
Process tube, annulus size, 303
Profilometer (irrad. slugs), 1631
Properties of Aluminum, 506
 Fuel elements, 106
 Thorium, 508
 Uranium, 503
 Zirconium, 507
Pumping power, 304
Quality control, 1403, 1507, 1510, 1513
Quench inspection, 1411
Quench unit, 1113

R

Radiation detection, 1704
Radiation intensity measurement, 1627
Radiation limits, 1702
Radiation protection, 1702, 1705
Radiograph inspection, 1413
Radiograph machine, 1122
Radiometallurgy building, 1631
Reactions in the solid state, 609, 621
Reactivity, 203
 effect of impurities, 209
 effect of dimensions, 209
 effect of density, 210
Reactivity tests, 1408
Recovered slugs, 1404
Recrystallization(uranium), 610
Replica techniques, 608
Resistance furnaces, 1211
 control, 1305
Resonance escape probability, 204
Rolling (uranium), 504

S

Safety, 1802
"Sevac" canning process, 802
Silicon concentration (Al-Si), 809
Singlepass boiling facility, 1619

Sizing presses, 1130
Sleeve cleaning machine, 1202
Sleeve honing machine, 1203
Slug burnout, 310
Slug cleaner (irrad.), 1626
Slug core inspection, 803
Slug facing, 811
Slug identification, 1502
Slug pickle machine, 1108
Slug quench, 811
Slug recovery, 902
Slug recovery equipment, 1204
Slug storage and shipping, 814
Slug stripper, 1134
Slug tests (test pile), 1616
Slug welding, 813
Special products equipment, 1126
Spent pickle acid table, 1206
Stainless steel, 619, 621
Statistical inspection, 1405
Storage of data, 1517
Stress analysis, 311
Stresses, 407
Stripping tank, 902
Structural properties (uranium), 611
Stuck slugs, 402, 405, 410
Submarine Intermediate Reactor (SIR), 105
Submarine Thermal Reactor (STR), 105, 410

T

Tank farm, 1209
Temperature controls (process), 1302
Temperature drops, 305, 307
Tensile properties (uranium), 603
Test pile, 207, 1408, 1610, 1614, 1708
Thermal conductivity (uranium), 604
Thermal cycling, 616
Thermal expansion (uranium), 606

DECLASSIFIED

-1905-

HW-40000

INDEX (Contd.)

Thermal Stresses, 310
Thermal utilization (f), 204-210
Thorium, 211, 508, 824
Time control (process), 1312
Transformation mechanisms
 (uranium), 502, 503
Triple dip canning process, 815
Tritium, 211, 725

U

Ultrasonic bond test, 1118
Ultrasonic transformation test, 803,
 1107
Unbonded canning process, 823
Uranium
 alloys, 505
 corrosion, 313
 crystal structure, 502
 deformation, 503
 denitration, 709
 density, 606, 502
 electrical resistivity, 605
 extraction and purification, 707
 fabrication, 503, 707
 hardness, 603
 heat treatment, 504, 717
 hydride, 505
 hydrofluorination, 709
 impact strength, 604
 machining, 719
 melting and recasting, 713
 modulus of elasticity, 606
 ore concentration, 707
 physical properties, 503, 604
 processing, 705
 recovery, 903
 reduction, 710
 slugs (flow of material), 1006
 sources, 706
 structural properties, 611
 tensile properties, 503, 603
 thermal conductivity, 604
 thermal expansion, 606
 transformation, 502

V-W

Vapor degreasing, 804
Visual examination (irrad. slugs),
 1626
Warp, 410, 803, 1404
Weighing (irrad. slugs), 1628
Welding
 controls, 1311
 inspection, 1412
 machine, 1116, 1127, 1311
Wetting tests, 1409

X-Y-Z

X-ray, 1708
X-10 reactor, 104
Zirconium, 318, 507, 619, 621
"Z" - lot material, 902

DATE

FILMED

10 / 7 / 94

END