QUARTERLY REPORT NO. 4

"Fundamental Research on Surface Science of Coal
in Support of Physical Beneficiation of Coal."

Quarterly Technical Progress Report for July 1 - September 30, 1988

DOE Contract No. DE-AC22-87PC79905

Department of Chemical Engineering
State University of New York at Buffalo
Buffalo, New York 14260

Robert J. Good, Principal Investigator

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

Quarterly Report No. 4

"Fundamental Research on Surface Science of Coal in
Support of Physical Beneficiation of Coal"

Summary:

The experimental systems required for our research have been acquired. Contact angle measurements on unoxidized Upper Freeport coal and fresh Illinois #6 coal show small differences in the contact angles of water under decane. Adsorption measurements on Upper Freeport coal with cyclohexanol in decane reveal adsorption behavior similar to that of octanol. This indicates that the adsorption is taking place on the pore surface of the coal and that the pores are probably greater than 2 nm diameter.

WORK PERFORMED IN THIS QUARTER

Equipment:

A Ramé-Hart goniometer in our laboratory has been modified for measuring contact angles more accurately and rapidly than can be done with commercially available goniometer systems. This equipment will be used for measuring contact angles in air.

Personnel:

A post-doctoral research associate and 4 full-time graduate students (2 Ph.D. and 2 M.S.) have joined the present team of two people during this quarter.

Experimental Studies:

Cyclohexanol adsorption measurements were carried out on Upper Freeport (mvb) coal, to further determine the type of pore surface on which the adsorption of octanol was taking place. The adsorption measurements revealed that these surface active additives are adsorbed principally on macropores and mesopores. The adsorption surface area is estimated to be about $5 \text{ m}^2/\text{g}$, assuming the molecules were being adsorbed end on. The coal used in the cyclohexanol study, and in the earlier octanol adsorption study, was in the size range of 125 to 710 microns. It was oxidized for 7 days in the atmosphere. B.E.T. measurements by nitrogen adsorption are being undertaken on all our coal samples, to determine the macropore and mesopore surface area, i.e., pores larger than $10\text{\AA}$ diameter.

Contact angle measurements, made microscopically, have been consistent with earlier results. In this quarter, we have measured contact angles on Illinois #6 coal, which had been stored under water, since grinding at Otisca Industries. It was dried and baked for 4 hours at 150°C , and stored under nitrogen in the glove box. The contact angle measurements revealed an angle of 48° for the decane-water interface as measured through decane. The contact angle on iron pyrite that was in this coal was 80° , vs. 85° on pyrite in Upper Freeport coal.

The angle of 48° is somewhat higher than the 40° measured on oxidized Upper Freeport. A direct comparison cannot be made as yet, because the Illinois #6 coal was not oxidized, whereas the Upper Freeport was oxidized. Fresh samples of Upper Freeport are being acquired.

A preliminary theoretical model (qualitative in nature) has been developed, to investigate the liquid-bridged structures, with the assumption

that the bridged structures have flat, parallel solid surfaces. This theory was presented at the annual AR & TD Contractors' Meeting in Pittsburgh, in September. The theory clearly shows that, for these bridged structures to be stable, the contact angles made by the liquid drop on coal, as measured through the oil (the continuous phase) has to be appreciably less than 90° .

The significance of the research so far is, that we now have a qualitative explanation for the formation of coal/oil/water aggregates, with the exclusion of hydrophilic mineral matter such as iron pyrite.

Overview:

In this quarter, the experimental study was extended to include Illinois #6 coal, in addition to the Kentucky #9 and Upper Freeport samples that have been used.

Contact angle measurements on fresh Illinois #6 revealed a contact angle of about 80° on the iron pyrite component of the coal, and about 48° on the coal itself.

Adsorption measurements on Upper Freeport coal with cyclohexanol in decane show similar surface adsorption as n-octanol, that had been obtained in the previous quarter.

The major items of research equipment required for the project have been acquired. Additional personnel have been recruited. Coal samples with various maceral content, from the DOE sample bank at Pennsylvania State University, have been acquired.

FUTURE PLANS

In the next quarter, oil/water contact angle measurements will be carried out on fresh Kentucky #9 and Upper Freeport coals, and oxidized

Illinois #6 coal, and on coal samples that have had n-octanol adsorbed on them. Contact angle measurements in air will begin during the next quarter. Adsorption measurements will be carried out with higher alcohols in water, on fresh and oxidized coals of all three origins. These adsorption measurements will be correlated with the results of contact angle measurements. BET measurements by nitrogen adsorption will also be made to determine the macropore and mesopore surface area.

Contact angles on the coal samples from the DOE sample bank will be carried out, to determine the effect of maceral composition.

The qualitative theoretical model that has been proposed will be extended.

It will be possible, now, to start determining the surface properties of coal in an oxygen-free atmosphere. It will also be possible to investigate contact angles on coal under conditions of advancing three-phase line (θ_a), and also retreating (θ_r). We will determine the possibility of establishing whether θ_a or θ_r , or something between, is the relevant angle for the oil agglomeration process.

We will also investigate the theory of hydrogen bonding at coal/fluid interfaces. It will be possible to interpret the variation of contact angles with coal rank, in terms of the electron donor/electron acceptor properties of the chemical groups on coal surfaces.

**DATE
FILMED
9/01/92**