SURFACE ELECTROCHEMICAL CONTROL FOR FINE COAL AND PYRITE SEPARATION

DOE Project No. DE-AC22-89PC89758

**Technical Progress Report
April 1, 1990 - June 30, 1990**

Prepared by

**Weibai Hu
Ximeng Zhu
David M. Bodily
Milton E. Wadsworth**

University of Utah

Prepared for

**U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

SURFACE ELECTROCHEMICAL CONTROL FOR FINE COAL AND PYRITE SEPARATION

DOE PROJECT NO. DE-AC22-89PC-89758

Technical Progress Report
4/1/90 - 6/30/90

This is the fourth technical progress report prepared in accordance with the reporting requirements of DOE Project No. DE-AC22-89PC89758. It covers the work performed during the period, April 1, 1990 to June 30, 1990 and includes the results obtained on surface electrochemical properties of mineral pyrite and coal pyrite using cyclic voltammetry. The electrochemical study comprises three parts: steady state polarization, cyclic voltammetry and AC impedance studies. The steady state polarization has been reported in the first technical progress report and the AC impedance study will start immediately after completion of the cyclic voltammetry study.

CYCLIC VOLTAMMETRIC STUDY OF MINERAL PYRITE AND COAL PYRITE IN SODIUM BORATE/SULFATE SOLUTIONS

In this study, cyclic voltammetry was used to determine oxidation/reductions reactions occurring at coal and coal pyrite surfaces. The objective is to develop methods to control the oxidation/reduction potential in electro-flotation processes and ultimately to modify surface properties for the optimum separation of pyrite from fine coal.

EXPERIMENTAL

Electrodes

For each experiment, a selected pyrite sample was used as the working electrode. One mineral pyrite and two coal pyrite electrodes were prepared from pieces of natural crystals. The mineral pyrite was obtained from Ward's National Science Establishment and the coal pyrites were from sulfur refuses obtained from the Pittsburgh No. 8 seam of the Cumberland Mine, Greene County, PA and the Upper Freeport seam, Coshocton County, OH. The samples were cut to size, avoiding inclusions, cracks and voids and encapsulated in epoxy cement. The electrode surfaces were ground on 600 grit silicon carbide paper and polished sequentially using 1.0, 0.3 and 0.05 micron alumina before each measurement. The exposed surface area of the Upper Freeport coal pyrite sample was 0.3 cm² and the mineral pyrite and Pittsburgh No. 8 coal pyrite surfaces were 1 cm². A 12 cm² platinum sheet was used as the counter electrode and a saturated calomel electrode was used as the reference electrode.

Solution

An electrolyte solution of 0.01M sodium borate in 0.49M sodium sulfate was prepared

from reagent grade chemicals and deionized distilled water. The pH of the solution was 9.2. Higher and lower pH values were obtained by addition of concentrated NaOH or HCl solutions.

Experimental Procedure

Cyclic voltammetry measurements were conducted at room temperature in a three-compartment Pyrex cell. Both the saturated calomel reference electrode and the platinum counter electrode were kept in separate compartments. For comparison, experiments were performed with the solution in the working electrode compartment both quiescent and magnetically stirred. The solution was purged with bubbling argon for about two hours prior to insertion of the sample electrode. The flow of argon at the surface of the solution was continued during measurements to prevent diffusion of atmospheric oxygen to the solution surface. Data were recorded and plotted by an EG&G Model 273 Potentiostat/Galvanostat programmed with an IBM PC-XT computer. The scanning potential covered the range from hydrogen to oxygen evolution (-1.3 to +0.8V, vs SCE). Scan rates were varied between 5 and 400 mV/s. Because the electrode surface was oxidized very easily during polishing, the first few cycles were not reproducible, but reproducible results were obtained after several cycles. The results reported in this study were for the fifth cycle, unless otherwise indicated. The solution pH was 7.9, 9.2 and 10.5.

RESULTS AND DISCUSSION

Mineral Pyrite

Cathodic/anodic pairs of peaks were observed at potentials of about -1.0/-0.8V and -0.5/-0.15V for a pH of 9.2, a scan rate of 100mV/s and stirred electrolyte (Figure 1). An additional peak was observed at about 0.50V (SCE) for the quiescent solution at pH 9.2 and a scan rate of 100mV/s (Figure 2). Based on Pourbaix diagrams for the Fe-H₂O and Fe-S-H₂O systems (1,2) and the standard electrode potentials (3), the following reactions are proposed to explain the observed peaks:

Peaks 1 and 6 (Figure 2):

Surface oxide layers exposed to cathodic potentials more negative than $\approx -0.83V$ (SCE) (at pH = 9.2) would be expected to form metallic iron. The reaction is

$$E_a = -.0475 - 0.059pH \quad (2)$$

At pH = 9.2, $E_a = -0.59V$ and $E_{SCE} = -0.832$. This reaction would account for peak 6 and the anodic reaction, Eq. 1, would account for peak 1 corresponding to the formation of Fe(OH)₂.

Peaks 2 and 5

Ferrous hydroxide present on the surface would be expected to oxidize to ferric hydroxide at higher potentials according to the reaction

$$E_h = 0.271 - 0.059\text{pH} \quad (4)$$

At pH 9.2, $E_h = -0.272\text{V}$ and $E_{\text{SCE}} = -0.514\text{V}$. Also in this potential range, pyrite would be expected to oxidize to ferric hydroxide with the formation of sulfate ion,

$$E_h = 0.402 - 0.0747\text{pH} + 0.0075\log[\text{SO}_4^{2-}] \quad (6)$$

At pH = 9.2 for the above electrolyte, $E_h = -0.288$ and $E_{\text{SCE}} = -0.530$

In basic solutions, intermediate potential-determining, metastable sulfoxy anions are also expected to form. For example pyrite oxidation may result in the formation of dithionate ion according to the reaction

$$E_h = 0.50 - 0.0681\text{pH} + 0.0045\log[\text{S}_2\text{O}_6^{2-}] \quad (8)$$

Calculated values of voltage for $[\text{S}_2\text{O}_6^{2-}]$ activities in the range of 10^{-6}m to 10^{-2}m give E_h values of -0.154 to -0.136V and E_{SCE} values of -0.396 to -0.378V . If elemental sulfur is formed the reaction is

$$E_h = 0.58 - 0.059\text{pH} \quad (10)$$

At pH = 9.2, $E_h = 0.04$ and $E_{\text{SCE}} = -0.21$. Eqs. (6), (8) and (10) all predict a decrease in voltage with increasing pH.

Peaks 3 and 4

The high voltage associated with Peak 3 may result from the formation of soluble ferrate FeO_4^{2-} . The formation of ferrate ion from ferric hydroxide proceeds according to the reaction

$$E_a = 1.62 - 0.0983\text{pH} + 0.0197\log[\text{FeO}_4^{2-}] \quad (12)$$

For ferrate ion concentrations between 10^{-2} and 10^{-6} and at pH 9.2, E_a would fall in the range +0.676 to +0.621V and E_{SCE} +0.434 to +0.379V. The magnitude of Peak 3 compared to the ferric hydroxide peak (Peak 2) and the relatively high voltage suggests pyrite itself may react to form the ferrate ion and elemental sulfur,

$$E_a = 1.09 - 0.0787\text{pH} + 0.0098\log[\text{FeO}_4^{2-}] \quad (14)$$

For ferrate ion concentrations between 10^{-2} and 10^{-6} and at pH 9.2, E_a would fall in the range +0.346 to +0.307V and E_{SCE} +0.104 to +0.065V. These latter values fall on the zero potential region prior to Peak 3 (Figure 2).

Peaks 2 and 5 have been detected in pyrite oxidation in many studies (1,4-6). Peaks 1 and 6 and peaks 3 and 4 have not been reported in previous studies.

Rangel et al. (7,8) and Beck (9) detected an anodic peak preceding oxygen evolution together with the corresponding reduction peak in cyclic voltammetric studies of mild steel in unstirred carbonate/bicarbonate solutions and iron in concentrated hydroxide solutions. They proposed that this peak was due to the transpassive anodic dissolution of Fe(III)-oxide layer and hydrolysis to yield ferrate(VI) ion, FeO_4^{2-} .

Peak 4, if viewed as the conjugated cathodic peak corresponding to Peak 3, was not significant compared to the anodic peak. It is thought to be due to the chemical decomposition of superficial or solution ferrate, based on the observation that a larger reduction peak could be obtained at higher scan rates (Figure 2) or for the first cycle where time for chemical decomposition is minimized (Figures 3-5). Also Peak 4 may result from products formed at even higher potentials.

A double peak appeared at peak 1 when the sweep voltage was reversed at 0.8 V (SCE). This double peak first appeared at the second cycle and increased in intensity with cycling as shown in Figure 6. The effect of scan rate on this peak is shown in Figures 7 and 8. Peak 1 increased in intensity with increasing scan rate while peak 1a decreased in intensity with increasing scan rate.

The reaction associated with peak 1a is not clear. It appears to be related to the oxide formed at high oxidation potential, which is reduced during the cathodic cycle. The peak current was dependent on solution stirring and inversely dependent on scan rate. This indicates that the reaction rate might be slow and is related to the dissolution of some species formed at peak 1. Higher pH favored the reaction as shown in Figure 9.

The effect of scan rate on peak current and potential in quiescent solutions at pH 9.2 is shown in Figure 2. Increasing scan rate increases the intensity of each peak.

The potential was reversed at different anodic limits. The results are shown in Figure 10. Based on the results of measurements shown in Figures 2 and 10, it is suggested that peak 1 is related to peak 6, peak 2 is related to peak 5 and peak 3 is related to peak 4. The currents of peaks 1 and 6 increase significantly with increasing anodic reversal potential.

The effect of stirring is shown in Figure 11. All peak currents increased with stirring, indicating that the reactions on mineral pyrite surfaces may be diffusion controlled. Peaks 3 and 4 disappeared during stirring, suggesting that soluble species were formed. This is consistent with the preceding suggestion that this is related to the formation of FeO_4^{2-} . The double peak at peak 1 disappeared in quiescent solutions.

The effect of pH is shown in Figure 9. The intensity of all peak currents increased with increasing solution pH. The potential of peak 1 was not affected by the solution pH. This suggests reaction (Eq. 1) occurs in two steps

The potential of peak 2 shifted to more negative values with increasing pH as required by Eq. 4. Peak 3 was similar to Peak 1, showing little change with pH. At the highest pH (Figure 9) a slight shoulder is apparent, indicative of additional anodic processes at even higher potentials. The lack of response to pH suggests reaction (Eq. 13) may occur in two steps, the first producing Fe^{3+} followed by hydrolysis to the ferrate ion.

$$E_h = 0.484 + 0.020\log[\text{Fe}^{3+}] \quad (18)$$

Reaction (Eq. 17) is independent of pH. Also, Eq. 18 predicts a rest potential consistent with the observed anodic response. For example, for $[\text{Fe}^{3+}]$ in the range 10^{-2} to 10^{-6}M E_h would be in the range of 0.444 to 0.364V and E_{SCE} in the range 0.202 to 0.122V. Much additional work is required to explain the observed effect of pH, scan rates, degree of agitation and additional reactions in the high potential region.

The voltammograms do provide evidence of elemental sulfur formation. For mineral pyrite voltammograms, two new peaks appear after anodic treatment at higher potentials. These are evident in Figure 2 at -0.8V (cathodic) and -0.3V (anodic) for the 100 mV/s scan. These voltages correspond well with the reaction

$$E_h = -0.0653 - 0.0295\text{pH} - 0.0295\log[HS^{-}] \quad (21)$$

For $[HS^{-}]$ concentrations between 10^{-2} to 10^{-6}M E_h would fall in the range of -0.278 to -0.160V and E_{SCE} in the range -0.520 and -0.402V .

The effects of the initial potential, at the beginning of the scan, and the direction of scan are shown in Figures 3,4,5 and 12. Regardless of the initial potential and direction of scan, after three cycles the cyclic voltammograms all coincided with one another.

Pittsburgh No. 8 Coal Pyrite

The effect of scan rate on peak current and potential is shown in Figure 14. Reversing the potential at different anodic limits is shown in Figure 15.

Peaks 3,4 and 6, which appeared in cyclic voltammograms of mineral pyrite, were not observed, but a cathodic peak at 0.35 V was observed. The intensity of this peak increased with increasing anodic reversal potential.

If the electrode is held at 1.0V for 1.5 minutes ($I = 20\text{mA}$) and then swept cathodically, a large cathodic peak was observed at -1.0V , similar to that observed in the case of mineral pyrite. The intensity decreased with cycling and remained constant after the fifth cycle (see Figure 16).

The potential difference between peaks 2 and 5 was larger than that observed for the same peaks in mineral pyrite, indicating that the degree of irreversibility is greater in the coal pyrite. This effect was more pronounced at higher scan rates. Peak 6 appeared and, contrary to the results observed for mineral pyrite, peak currents decreased with the exception of peak 1 when the solution was stirred (see Figure 17). The effect of pH is shown in Figure 18.

Upper Freeport Coal Pyrite

Figure 19 shows the effect of scan rate on peak current and potential. Reversing the potential at different anodic limits is shown in figure 20. Similar to the case of Pittsburgh No. 8 coal pyrite, a cathodic peak was observed at about 0.35V . However, peak 1 was not detected at higher anodic reversing potentials. The effect of stirring is shown in Figure 21. Peak 1 appeared when the solution was stirred.

The pH effect (Figure 22) is similar to that for Pittsburgh No. 8 coal pyrite and is not as clear as that for mineral pyrite.

Comparison

Significant differences in the electrochemical response of the pyrites were observed and may be summarized as follows:

Three anodic peaks were observed at the mineral pyrite surfaces at about -1.0V, -0.3V and 0.4V, together with their corresponding reduction peaks. These peaks are proposed to be related to the formation of Fe(II), Fe(III) and Fe(VI) respectively. Only the first two pairs of peaks were observed at the surfaces of coal pyrites.

The current density for mineral pyrite was much less than those for coal pyrites, indicating that the reactivity of coal pyrites is much higher than that of the mineral pyrite. This is shown in figures 24 and 25. Chander (10) reached a similar conclusion. The reactivity sequence is Upper Freeport coal pyrite > Pittsburgh No. 8 coal pyrite > mineral pyrite.

Mineral pyrite is more sensitive to pH and the effect of stirring than were the coal samples examined in this study.

FUTURE WORK

To understand further the oxidation/reduction reactions occurring on the pyrite surface and to achieve the final goal of the project, electrochemical controlled flotation, The following areas of research are planned for future study:

1. Identification of the reactions species formed during the anodic and cathodic reactions of pyrite. This is to be accomplished by carrying out fixed potential vs. current scans, AC impedance measurements at selected pH values and mass balance measurements where possible.
2. Effect of temperature on the cyclic voltammetry.
3. Identification of surface reaction products using the scanning electron microscope and the electron microprobe.
3. Repetition of cyclic voltammetry measurements in the presence of flotation media.

REFERENCES

1. Hamilton, I.C.; Woods, R. J. Electroanal. Chem., **118**, 327 (1981).
2. Garrels, R.M.; Christ, C.L. Solutions, Minerals and Equilibria; Freeman Cooper: San Francisco, CA, pp 183, 221 (1965).
3. Milazzo, G.; Caroli, S. Tables of Standard Electrode Potentials; Wiley: NY, pp 320-323 (1978).
4. Janetski, N.D.; Woodburn, S.I.; Woods, R. Int. J. Min. Proc., **4**, 227 (1977).
5. Chander, S.; Briceno, A. Minerals Metal. Proc., 171 (1987).
6. Lai, R.W.; Diehl, J.R.; Hammack, R.W.; Khan, S.U.M. Preprints, SME Annual Meeting, Las Vegas, NV, preprint number 89-6 (1989).
7. Rangel, C.M.; Leitao, R.A. Electrochim. Acta., **34**, 225 (1989).
8. Rangel, C.M.; Fonseca, I.R.; Leitao, R.A. Electrochim. Acta., **31**, 1659 (1986).
9. Beck, R.; Kaus, R.; Oberst, M. Electrochim. Acta., **30**, 173 (1985).
10. Briceno, A.; Chander, S. Int. J. Min. Proc., **24**, 73 (1988).

Figure 1. Mineral Pyrite in Stirred Borate Solution
of pH 9.2. Scan Rate: 100 mV/s.

Figure 2. Mineral Pyrite in Quiescent Borate Solution of pH 9.2. at Different Scan Rate

Figure 3. Mineral Pyrite in Quiescent Borate Solution
of pH 9.2. Scan Rate: 50 mV/s.
Scan from 0.0V towards anodic.

Figure 4. Mineral Pyrite in Quiescent Borate Solution
of pH 9.2. Scan Rate: 50 mV/s.
Scan from 0.0V towards cathodic

Figure 5. Mineral Pyrite in Quiescent Borate Solution
of pH 9.2. Scan Rate: 50 mV/s.
Scan from -0.5V towards anodic

Figure 6. Mineral Pyrite in Stirred Borate Solution
 of pH 9.2. Anodic Reverse Potential: 0.8 V.
 Scan Rate: 100 mV/s.

Figure 7. Mineral Pyrite in Stirred Borate Solution
of pH 9.2 at Different Scan Rate

Figure 8. Mineral Pyrite in Stirred Borate Solution
of pH 9.2 at Different Scan Rate
Expanded Peak₁

Figure 9. Effect of Solution pH
 Mineral Pyrite in Quiescent Borate Solution
 Scan Rate : 50 mV/s

Figure 10. Mineral Pyrite in Quiescent Borate Solution of pH 9.2. Potential Reversed at Different Anodic Limit. Scan Rate : 100 mV/s.

Figure 11. Effect of Solution Stirring
Mineral Pyrite in Borate Solution of pH 9.2
Scan Rate : 100 mV/s

Figure 12. Mineral Pyrite in Quiescent Borate Solution
of pH 9.2. Scan Rate: 50 mV/s.
Scan from -0.5V towards cathodic

Figure 13. Mineral Pyrite in Quiescent Borate Solution of pH 9.2. Scan Initiate at Different Potential and Direction. Scan Rate : 50 mV/s, 3rd. Cycle.

Figure 14. Pittsburgh Coal Pyrite in Quiescent Borate Solution of pH 9.2. at Different Scan Rate

Figure 15. Pittsburgh Coal Pyrite in Quiescent Borate Solution of pH 9.2, Potential Reversed at Different Anodic Limit. Scan Rate : 100 mV/s.

Figure 16. Pittsburgh Coal Pyrite in Quiescent Borate
Solution of pH 9.2. Scan Rate : 100 mV/s.
Electrode Conditioned at 1.0V for 1.5 min.

Figure 17. Effect of Solution Stirring
Pittsburgh Coal Pyrite in Borate Solution
of pH 9.2. Scan Rate : 50 mV/s.

Figure 18. Effect of Solution pH
Pittsburgh Coal Pyrite in Quiescent Borate
Solution. Scan Rate : 50 mV/s.

Figure 19. Upper Freeport Coal Pyrite in Quiescent Borate Solution of pH 9.2. at Different Scan Rate

Figure 20. Upper Freeport Coal Pyrite in Quiescent Borate Solution of pH 9.2, Potential Reversed at Different Anodic Limit. Scan Rate : 100 mV/s.

Figure 21. Effect of Solution Stirring
Upper Freeport Coal Pyrite in Borate Solution
of pH 9.2. Scan Rate : 50 mV/s.

Figure 22. Effect of Solution pH
Upper Freeport Coal Pyrite in Quiescent
Borate Solution. Scan Rate : 50 mV/s.

Figure 23. Mineral Pyrite and Pittsburgh Coal Pyrite
in Quiescent Borate Solution of pH 9.2.
Scan Rate 100 mV/s.

Figure 24. Upper Freeport and Pittsburgh Coal Pyrites
in Quiescent Borate Solution of pH 9.2.
Scan Rate 100 mV/s.

**DATE
FILMED
8/25/92**