013524

1 OF 1

RECEIVED
USDOE/PETC
DOE/PC/90044-7
62 JUL 27 PM 1:27
FEDERAL ASSISTANCE

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Quarterly Technical Progress Report for the Period
April-June 1992

Kamil Klier and Richard G. Herman
with
Owen C. Feeley and Marie A. Johansson

Zettlemoyer Center for Surface Studies
and Department of Chemistry
LEHIGH UNIVERSITY
Bethlehem, PA 18015

July 1992

PREPARED FOR THE

U. S. DEPARTMENT OF ENERGY
PITTSBURGH ENERGY TECHNOLOGY CENTER

Contract No. DE-AC22-90PC90044

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States DOE, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

OBJECTIVES OF THE RESEARCH

The objective of the proposed research is to synthesize high octane ethers, primarily methyl isobutyl ether (MIBE) and methyl tertiary butyl ether (MTBE), directly from $H_2/CO/CO_2$ coal-derived synthesis gas *via* alcohol mixtures that are rich in methanol and 2-methyl-1-propanol (isobutanol). The overall scheme involves gasification of coal, purification and shifting of the synthesis gas, higher alcohol synthesis, and direct synthesis of ethers.

The last stage of the synthesis involves direct coupling of synthesis gas-derived methanol and isobutanol that has been demonstrated by us to occur over superacid catalysts to yield methyl isobutyl ether (MIBE) at moderate pressures and a mixture of methanol and isobutene at low pressures. MIBE is an isomer of MTBE and a process is proposed whereby MTBE from the two alcohols is maximized and MIBE is minimized. This will be achieved by the proper choice of reaction conditions, i.e. intermediate pressures, and of inorganic acid catalysts that are stable at temperatures higher than 200°C, at which the carbonium ion reaction coupling of the two alcohols to MTBE is more effective than the oxonium ion or ester reaction coupling to MIBE.

Both organic and inorganic catalysts will be investigated, and the better catalysts of these classes will be subjected to long term performance studies. The long term performance studies of the combined process will extend to 1000 hr and detailed analytical data for all products will be provided. The project is divided into the following three tasks:

Task 1. Synthesis of High Octane Ethers from Alcohol Mixtures Containing Predominantly Methanol and 2-Methyl-1-Propanol over Superacid Resins

Task 2. Inorganic Catalysts for the Synthesis of High Octane Ethers from Alcohols

Task 3. Long Term Performance and Reaction Engineering for Scale-Up of the Alcohols-to-Ethers Process

The expected result of the proposed research is a novel process for producing ethers, in particular MTBE, in which all five carbons of the unsymmetric C_1 -O- C_4 ethers originate from coal-derived synthesis gas.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

SUMMARY OF TECHNICAL PROGRESS

Catalytic testing of inorganic catalysts was continued with the sulfate-modified zirconia catalyst prepared here. It was observed that the biggest effect of reactor pressure (and thus the alcohol partial pressure over the catalyst) on the products formed from a methanol/isobutanol = 2/1 reactant was the large decrease in isobutene yield as the alcohol partial pressure was progressively increased. This was observed at both 116°C and 157°C.

In an experiment carried out at 1 atm and 157°C, the methanol feed rate (and thus methanol partial pressure) was held constant and the isobutanol feed rate was increased stepwise so that the methanol/isobutanol ratio = 7.8 to 0.2. It was observed that the yield of isobutene exhibited a broad maximum as the isobutanol partial pressure was progressively increased, resulting in a steadily decreasing methanol/isobutanol ratio. This indicates competitive adsorption of the reactants at high methanol/isobutanol ratios and ultimately a trend toward saturation of the surface of the catalyst with isobutanol and low methanol/isobutanol reactant ratios. A similar trend of decreasing isobutene yields with higher partial pressures of isobutanol was also observed in the absence of methanol. The linear butenes formed over these inorganic catalysts have been clarified to be trans-2-butene and cis-2-butene.

Calculations of the amount of sulfur on the surface of the sulfate-modified zirconia, based on elemental analyses and X-ray photoelectron spectroscopy analyses, indicated that the surface coverage of the sulfur is not sensitive to the particular crystallographic form of the zirconia.

TECHNICAL PROGRESS

Research carried out this quarter focused exclusively on further catalytic testing and characterization of the sulfate-modified zirconia catalyst ($\text{ZrO}_2/\text{SO}_4^{2-}$), which had been previously reported to be highly selective for isobutanol dehydration to isobutene in methanol/isobutanol mixtures (1).

A. Alcohol Pressure Dependence on Product Selectivity

The effect of reactant pressure on the activity and selectivity of the dehydration of a 2:1 molar methanol and isobutanol mixture to butenes and ethers was studied. Nunan et al. had previously studied this reaction over the strongly acidic ion-exchange resin Nafion-H (2). The reaction conditions chosen in the present study using $\text{ZrO}_2/\text{SO}_4^{2-}$ as catalyst are similar to those of Nunan et al (2). To allow for eventual kinetic analysis, the conversions were kept below 10%. The $\text{ZrO}_2/\text{SO}_4^{2-}$ catalyst has very low activity at 116°C, and a very low space velocity was needed to induce appreciable conversion. The catalyst has high activity at 157°C and the space velocity was adjusted accordingly.

The following experimental conditions were used for the two reaction temperatures:

Temperature	116°C
Pressure (total)	1-70 atm (0.1-7.1 MPa)
Methanol feed	1.18 mol/kg catalyst/hr
Isobutanol feed	0.59 mol/kg catalyst/hr
He (+ N ₂ trace) flow	20.94 mol/kg catalyst/hr
Catalyst weight	5.0 g

Temperature	157°C
Pressure (total)	1-62 atm (0.1-6.3 MPa)
Methanol feed	42.2 mol/kg catalyst/hr
Isobutanol feed	21.1 mol/kg catalyst/hr
He (+ N ₂ trace) flow	756 mol/kg catalyst/hr
Catalyst weight	2.0 g

Figures 1 and 2 show the space time yields of the major products under the conditions given above as a function of total alcohol partial pressure, which was increased stepwise by sequentially increasing the reactor pressure. The results at 116°C exhibit more scatter than those for 157°C, but the trends seen are the same. It is evident that isobutene production is strongly pressure dependent, decreasing with increasing alcohol pressure eventually. Ether production is only moderately pressure dependent, increasing somewhat with increasing alcohol pressure. Both the isobutene decrease and ether increase appear to level off to steady values. These results are similar to those observed with the Nafion-H resin catalyst (2). This suggests that the same catalytic functions and properties exist for the reaction over $\text{ZrO}_2/\text{SO}_4^{2-}$ as was observed over Nafion-H. This pressure effect was found to be reversible in a separate experiment using fresh catalyst, i.e. when the alcohol pressure was decreased to its original value, isobutene production increased and ether production decreased to their original rates. This work also shows that the selectivity toward isobutene, which was seen previously with a 1:1 methanol/isobutanol mixture (1), also holds for the 2:1 methanol/isobutanol mixture used in this study at low pressures.

It is apparent from Figures 1 and 2 that low pressures are needed to maximize the selective dehydration of isobutanol to isobutene while leaving the methanol relatively unconverted. It is also evident from Figure 3 that low temperatures are needed when pathways exist (*via* carbenium ion chemistry with Brønsted acids) for the formation of linear butenes in order to minimize the linear butenes and maximize the proportion of isobutene in the product stream. Figure 3 shows that below ≈ 425 K, i.e. the temperature range of interest, the equilibrium yield of 1-butene would be small compared to the 2-butenes. Indeed, it was found upon rechecking the experimental gas chromatographic analyses that

Figure 1. Effect of Alcohol Partial Pressure on Product Yields at 116°C

Figure 2. Effect of Alcohol Partial Pressure on Product Yields at 157°C

Figure 3. Plot of equilibrium constant, i.e. mole ratio of linear butene to isobutene, as a function of temperature for the conversion of isobutene to ■ 1-butene, ▲ cis-2-butene, and □ trans-2-butene.

the previously reported (1) 1-butene product was trans-2-butene and the 2-butene product was cis-2-butene.

B. Effect of Isobutanol Pressure on Mixed Alcohol Dehydration

The effect of increasing isobutanol pressure while maintaining the methanol partial pressure constant was investigated. Each alcohol flow was controlled with separate pumps.

The following experimental conditions were used:

Temperature	157°C
Pressure (total)	1 atm
Methanol feed	42.5 mol/kg catalyst/hr
Isobutanol feed	5.41-216.4 mol/kg catalyst/hr
He (+ N ₂ trace) flow	778.3 mol/kg catalyst/hr
Catalyst weight	0.40 g

Figure 4 presents the space time yields of the major products of the mixed alcohol dehydration. As the pressure of isobutanol was increased, the production of isobutene and MIBE initially increased, but at higher isobutanol pressures they tend to decrease. DME tended to decrease consistently as the isobutanol pressure increased.

C. Pressure Dependence of Isobutanol Dehydration

The effect of pressure on the dehydration of isobutanol over $\text{ZrO}_2/\text{SO}_4^{2-}$ in the absence of methanol was investigated. The following experimental conditions were used:

Temperature	157°C
Pressure (total)	1-30 atm (0.1-3.04 MPa)
Isobutanol feed	21.1 mol/kg catalyst/hr
He (+ N ₂ trace) flow	800.7 mol/kg catalyst/hr
Catalyst weight	0.40 g

Figure 5 presents the space time yields of the major products of isobutanol dehydration, mostly isobutene and some cis- and trans-2-butene, as a function of isobutanol pressure. It is apparent that the isobutene production is strongly dependent on isobutanol

Figure 4. Yields of Products as the Iso-
Butanol Pressure was Increased at 157 C

Figure 5. Isobutanol Dehydration over $\text{ZrO}_2/\text{SO}_4^{2-}$ at 157°C

pressure. As in the case of the dehydration reaction in the presence of methanol above, the formation of isobutene decreased with increasing alcohol pressure. The yields of all butenes were higher in the absence of methanol.

D. Calculation of Amount of Sulfur on Sulfated Zirconia

The amount of sulfur on the surface of sulfate modified zirconia has been calculated from data obtained from elemental analysis and from X-ray photoelectron spectroscopy (XPS) data. Elemental analysis was performed by Galbraith Laboratories, Inc.

Results from elemental analysis

Samples from two different preparations of sulfate modified zirconia were analyzed for sulfur and zirconium. The amount of oxygen could not be determined, according to Galbraith laboratory.

Table 1. Result of elemental analysis

Sample number	Zirconium (weight %)	Sulfur (weight %)
1	71.33	0.84
2	69.97	0.96

The results from samples 1 and 2 are in good agreement. The analytical data from sample number 1 were used to calculate the surface coverage of sulfur on zirconia. Assuming that the zirconia has a tetragonal structure, there will be $5.2 \times 10^{18} \text{ ZrO}_2/\text{m}^2$ and the amount of sulfur corresponds to 0.55 monolayer.

Results from XPS

Zirconia exists in three different phases (tetragonal, monoclinic or cubic) and has a fluorite-type structure. The monoclinic phase is the most stable at low temperature, the tetragonal phase is stable over 1170°C, and phase transfer to cubic occurs at 2700°C (3). However, the addition of sulfate to the zirconia stabilizes the tetragonal structure so that the tetragonal phase is prevalent at room temperature and at the reaction conditions used during catalytic testing (4). The 110 plane in a fluorite structure is electrically neutral, and therefore this plane was assumed to be the surface plane. In the tetragonal phase, the Zr-Zr distance is 3.64Å (5), while several values for the Zr-Zr distance are given for the monoclinic phase, ranging from 3.660 to 3.70Å (6,7). The cubic phase has a Zr-Zr distance of 3.73Å (8). To quantify the amount of sulfur, it was assumed that the sulfur was homogeneously distributed over the surface and the escape depth parameter was used only for the zirconia.

Table 2. Surface coverage of sulfur on sulfated zirconia

Crystal phase	Zr-Zr (Å)	Surface coverage (monolayer)
Tetragonal	3.64	0.24
Monoclinic I	3.660	0.24
Monoclinic II	3.677	0.23
Monoclinic III	3.70	0.23
Cubic	3.73	0.23

As can be seen in Table 2 the difference in surface coverage calculated using the different crystal phases is minor. The surface coverage obtained by XPS can be compared to the value obtained from elemental analysis data. Elemental analysis resulted in a surface

coverage of 0.55 (see above), whereas XPS analysis yielded a value of 0.24. These numbers are in fair agreement with one another, especially considering the major difference in techniques used and the assumptions applied.

References

1. K. Klier, R. G. Herman, M. A. Johansson, and O. C. Feeley, "High Octane Ethers From Synthesis Gas-Derived Alcohols", Quarterly Technical Progress Report DOE/PC/90044-6, 23 pp (April 1992).
2. J. G. Nunan, K. Klier, and R. G. Herman, J. Chem. Soc., Chem. Commun., 676 (1985) and J. Catal., submitted.
3. M. Yoshimura, Ceramic Bulletin, 67 (1988) 1950.
4. K. Tanabe, M. Misono, Y. Ono, and H. Hattori, New Solid Acids And Bases, Elsevier Science Publishing Company, Inc., New York, 1989, p 201.
5. G. Teufer, Acta Cryst. 15 (1962) 1187.
6. W. B. Pearson, ed., Structure Reports, N. V. A. Oosthoek's Uitgevers Mij, Utrecht, 1959, vol. 23.
7. K. H. Hellwege, ed., Atom und Molekularphysik, 4. Teil Kristalle, Springer-Verlag, Berlin, 1955, p 122.
8. W. B. Pearson, ed., Structure Reports, N. V. A. Oosthoek's Uitgevers Mij, Utrecht, 1962, vol. 27.

END

DATE
FILMED

6 / 29 / 93