**SUPPORTED ORGANOMETALLIC COMPLEXES:
SURFACE CHEMISTRY, SPECTROSCOPY, AND CATALYSIS**

**Progress Report
for Period July 15, 1989 - July 14, 1990**

Tobin J. Marks

**Department of Chemistry
Northwestern University
Evanston, IL 60208-3113**

February 1991

N O T I C E

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

Prepared for

**THE U.S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG02-86ER13511**

MASTER

ep
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Adsorbing organometallic molecules onto the surfaces of inorganic supports such as Al_2O_3 , MgCl_2 , SiO_2 , etc. can result in dramatic enhancements in catalytic activity. The reasons for this and the structures of the resulting surface organometallic centers are not well understood. We have addressed this problem using thorium, uranium, and early transition metal complexes as model adsorbates. Characterization tools include catalytic and stoichiometric reaction chemistry, reaction kinetics and isotopic labeling, quantitative poisoning studies, model solution chemistry, and a wide array of surface-sensitive physicochemical techniques such as CPMAS NMR, EPR, and optical spectroscopy as well as titration calorimetry. The chemical and physical experiments are closely coupled to provide maximum information yield.

A detailed kinetic and mechanistic study of heterogeneous olefin hydrogenation by $\text{Cp}'_2\text{Th}(\text{CH}_3)_2$ ($\text{Cp}' = \eta^5\text{-(CH}_3)_5\text{C}_5$) adsorbed on dehydroxylated alumina (DA) has been completed.¹ For both propylene and isobutylene, the kinetics can be accommodated by a two-step sequence: 1) olefin insertion into Th-H (rate constant ν_1), 2) hydrogenolysis of the resulting Th-alkyl bond (rate constant ν_2). Kinetic data can be fit to the rate law N_t (turnover frequency) = $\nu_1\nu_2 P_{\text{H}_2} / (\nu_1 + \nu_2 P_{\text{H}_2})$, where the

reaction is zero-order in olefin and where $\nu_1/\nu_2 = 0.55 \text{ bar}^{-1}$ (-63°C) and 0.47

bar⁻¹ (0°C) for propylene and isobutylene, respectively. Kinetic isotope measurements indicate $N_t(H_2)/N_t(D_2) = 1.5(1)$ for propylene hydrogenation at -63°C and 2.0(2) for isobutylene hydrogenation at 0°C. In reaction with D₂, propylene yields exclusively 1,2-propane-d₂. Arrhenius activation energies for catalytic hydrogenation are: 3.6(2) kcal mol⁻¹ (propylene, -63°C - -23°C) and 5.3(2) kcal mol⁻¹ (isobutylene, -23°C - +64°C); for isobutylene, it could be determined that the activation enthalpies for olefin insertion and alkyl hydrogenolysis are comparable (6.2(10) and 4.2(10) kcal mol⁻¹, respectively). Protonolytic poisoning experiments indicate that $\leq 4 \pm 1\%$ and $\leq 2 \pm 1\%$ of the thorium surface sites are responsible for the bulk of the propylene and isobutylene hydrogenation, respectively. As a function of olefin, the relative rates of Cp₂'Th(CH₃)₂/DA-catalyzed hydrogenation are: *cis*-2-butene > *trans*-2-butene > propylene > isobutylene; 1,3-butadiene yields only 1-butene and *cis*-2-butene as initial hydrogenation products. For several organoactinides supported on DA, the relative ordering of propylene hydrogenation activity is Cp₂'Th(CH₃)₂ ≥ Me₂SiCp₂"Th(*n*-Bu)₂ ≥ [Me₂SiCp₂"Th(μ-H)₂]₂ ≥ Cp₂'Th(CH₃)(O₃SCF₃) ≥ [Me₂SiCp₂"U(μ-H)₂]₂ >> U(η⁸-η-BuC₈H₇)₂. As a function of support, the relative rates of Cp₂'Th(CH₃)₂-catalyzed propylene hydrogenation are DA > dehydroxylated SiO₂-Al₂O₃ > dehydroxylated MgCl₂ >> dehydroxylated SiO₂-MgO. In contrast to results with DA, protonolytic poisoning experiments indicate that 35±10% of the Cp₂'Th(CH₃)₂/MgCl₂ sites are catalytically significant. Importantly, informative parallels can be drawn between these observations and homogeneous solution phenomenology for similar types of compounds.

In closely parallel work,² a 75.4 MHz ¹³C CPMAS NMR spectroscopic study of the surface structures and reaction chemistry of a series of organoactinides adsorbed on various inorganic supports has been carried out. On Lewis acid surfaces such as dehydroxylated Al₂O₃, MgCl₂, and SiO₂-Al₂O₃, it is found that organothorium complexes of the type Cp₂'ThR₂ (R = ¹³CH₃, ¹³CH₂¹³CH₃), Cp'ThR₃ (R = ¹³CH₂C₆H₅), and Cp₃ThR (Cp

$-\eta^5\text{-C}_5\text{H}_5$; $\text{R} = {}^{13}\text{CH}_3$), undergo heterolytic Th-C scission to transfer an alkyl anion to the surface forming $\text{Cp}_2'\text{ThR}$, $\text{Cp}'\text{ThR}_{3-n}$, or Cp_3Th adsorbate species with "cation-like" character (e.g., A-C). Probe studies with paramagnetic $\text{Cp}_2'\text{U}({}^{13}\text{CH}_3)_2$ indicate

that the transferred methyl groups of $\text{Cp}_2'\text{U}({}^{13}\text{CH}_3)_2/\text{DA}$ and $\text{Cp}_2'\text{U}({}^{13}\text{CH}_3)_2/\text{MgCl}_2$ are located $\geq 5\text{\AA}$ from the U(IV) ion (D). On less dehydroxylated or more basic supports such as $\text{SiO}_2\text{-MgO}$, SiO_2 , and MgO , μ -oxo species of the type $\text{Cp}_2'\text{Th}(\text{CH}_3)\text{O}$ -are formed, by Th-C protonolysis or by transfer of an alkyl group to the surface (E, F). For $\text{Cp}_2'\text{U}({}^{13}\text{CH}_3)_2/\text{SiO}_2$, the resulting ${}^{13}\text{CH}_3\text{-Si}(\text{surface})$ functionality is $\geq 5\text{\AA}$ from the

actinide center. In agreement with the aforementioned catalytic studies, the NMR data reveal that only a small percentage of $\text{Cp}_2'\text{Th}({}^{13}\text{CH}_3)_2/\text{DA}$ or $\text{Cp}'\text{Th}({}^{13}\text{CH}_2\text{C}_6\text{H}_5)_3/\text{DA}$ surface sites undergo reaction with ethylene or H_2 at 25°C . In contrast, $50 \pm 10\%$ of $\text{Cp}_2'\text{Th}({}^{13}\text{CH}_3)_2/\text{MgCl}_2$ sites undergo reaction with ethylene; $> 90 \pm 10\%$ of ethylene insertion/polymerization occurs at Th-CH_3 with $k(\text{propagation})/k(\text{initiation}) \approx 12$ in the initial stages. There is no evidence for methane evolution via C-H functionalization nor for significant rates of $\text{Th}(\text{CH}_2\text{CH}_2)_n {}^{13}\text{CH}_3 - {}^{13}\text{CH}_3\text{Mg}(\text{surface})$ alkyl group interchange. At 25°C , a large percentage of $\text{Cp}_2'\text{Th}({}^{13}\text{CH}_3)_2/\text{MgCl}_2$ Th-CH_3 and Mg-CH_3 functionalities undergo hydrogenolysis, with Th-CH_3 being slightly more reactive. In competition experiments, we also find that Th-CH_3 is far more reactive than Mg-CH_3 in migratory CO insertion, and products are inferred to be, inter alia,

η^2 -acyl complexes. $\text{Cp}_2\text{Th}(\text{}^{13}\text{CH}_3)_2/\text{MgCl}_2$ undergoes reaction with propylene to yield methane (derived from Th-CH_3), a $\text{Th}(\eta^3\text{-allyl})$ complex, and what appear to be propylene oligomers. There are very strong correlations between this surface chemistry and emerging solution model chemistry (vide infra).

In related solution chemistry, we are developing models and new homogeneous catalysts based upon what we have learned from the supported catalysts.³⁻⁵ The protonolytic, ammonium salt route (eq.(3)) offers a versatile entree into highly reactive, base-free cationic actinide alkyls and hydrides. The key is to devise

$\text{R} = \text{H, alkyl}$
 $\text{R}' = \text{bulky alkyl}$
 $\text{X}^- = \text{noncoordinating anion}$

a truly non-coordinating anion, and we have recently had great success with $\text{X}^- = \text{B}(\text{C}_6\text{F}_5)_4^-$. With respect to ethylene polymerization ($\text{An} = \text{Th}$, $\text{R} = \text{CH}_3$), we find that the $\text{X}^- = \text{B}(\text{C}_6\text{F}_5)_4^-$ catalyst is ca. 2000 x more reactive than the $\text{B}(\text{C}_6\text{H}_5)_4^-$ analogue, and even more reactive (>5000x) than the $\text{X}^- = \text{Fe}(\text{B}_9\text{C}_2\text{H}_{11})_2^-$ catalyst!

References

1. Gillespie, R. D.; Burwell, R. L., Jr.; Marks, T. J., Langmuir, in press.
2. Finch, W. C.; Gillespie, R. D.; Hedden, D.; Marks, T. J., J. Am. Chem. Soc., in press.
3. Yang, X.-M.; Rheingold, A. L.; Marks, T. J., manuscript in preparation.
4. Hathorne, R. A.; Marks, T. J., manuscript in preparation.
5. Lin, Z.; Le Marechal, J.-F.; Yang, X.-M.; Sabat, M.; Marks, T. J., manuscript in preparation.

**DATE
FILMED**
8/3/192