AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 1

INTRODUCTION AND PAST ACHIEVEMENTS

We propose to continue our fundamental research on passivity and passivity breakdown, starting on or about September 1, 1993, as the third year of Grant No. DE-FG02-91ER45461, "Fundamental Studies of Passivity and Passivity Breakdown." This current grant follows one that was held by the Principal Investigator (Dr. D. D. Macdonald) while at SRI International in Menlo Park, California. However, on July 1, 1991, Dr. Macdonald joined The Pennsylvania State University as Professor of Materials Science and Engineering and as Director of the Center for Advanced Materials. While the current grant seeks to continue the original work under the prior Grant No. DE-FG03-84ER45164, certain aspects of the work have been greatly expanded in light of our findings over the past year.

During the past eight years of this program (including the two three-year incrementally-funded grants prior to the present grant), we developed and experimentally tested various physical models for the growth and breakdown of passive films on metal surfaces. These models belong to a general class termed "point defect models" (PDMs), in which the growth and breakdown of passive films are described in terms of the movement of anion and cation vacancies. Specifically, our work during the past five years of this program has resulted in:

I. Theory of the Growth and Breakdown of Passive Films

- (I.1) Derivation of a theory for the steady-state properties of passive films on metal surfaces. This theory was found to give an accurate description of the dependence of the steady-state film thickness and current on potential and pH for passive nickel and tungsten in phosphate buffer solutions, as measured in this work, and for a variety of metals and alloys in various aqueous media, as determined from data taken from the literature.
- (I.2) Demonstration that the passive film on nickel is a cation conductor, whereas that on tungsten is an oxygen ion conductor. Ionic conduction in the passive film on nickel involves the irreversible ejection of cations from the film into the solution at the film/solution interface.
- (I.3) Development of deterministic models for the distributions in the critical voltage and induction time for passivity breakdown. The distributions in these parameters are attributed to distributions in the breakdown sites in terms of the cation vacancy diffusivity.
- (I.4) Derivation of distribution functions for the critical voltage (V_c) and induction time (t_{ind}) for passivity breakdown using different distributions for the breakdown sites with respect to the cation vacancy diffusivity. The continuous distributions used include the log and normal distributions. Other distributions (student "t" and χ -square) are now being developed. Numerical analysis of the derived distributions in V_c and t_{ind} is being performed for comparison with experimental data.
- (I.5) Extension of the Chao, Lin, and Macdonald theory for the impedance characteristics of passive films by incorporating kinetic effects caused by reactions involving vacancies at the metal/film and film/solution interfaces.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

We show that the impedance of passive nickel in phosphate buffer solutions (pH = 9-11) at high frequencies ($f > 100$ Hz) is dominated by the kinetics of reactions occurring at the metal/film interface, whereas the impedance at low frequencies ($f < 1$ Hz) is dominated by the movement of vacancies through the film. The mathematical techniques employed in this type of analysis are now being greatly improved, and the method is being used to analyze impedance data for passive tungsten. The passive film on tungsten is an oxygen ion conductor.

- (I.6) Exploration of passivity breakdown on liquid and solid gallium substrates in chloride-containing aqueous and non-aqueous environments. We have shown that passivity breakdown is inhibited on liquid gallium compared with solid gallium, which we attribute to the inability of liquid substrates to support vacancy condensates. While this is not an unambiguous demonstration of the role(s) of cation vacancy condensates in the breakdown process, it is strong circumstantial evidence that the nucleation of pits on a passive metal occurs through events that occur at the metal/film interface.
- (I.7) Extension of the PDM to account for the formation of the outer, precipitated hydroxide/oxyhydroxide/oxide layer on passive metals in contact with aqueous environments. This treatment has resulted in the derivation of four non-linear, simultaneous equations which may be solved for the thickness of the barrier layer, the thickness of the outer layer, the voltage at the barrier layer/outer layer interface, and the pH at the same location. This model has been developed to describe a bilayer passive film in the steady-state but, in principle, it may be extended to describe the kinetics of growth of the layers in response to a change in the applied voltage.

II. Theory of Corrosion-Resistant Alloys

- (II.1) Development of the solute-vacancy interaction model to account for the effects of alloying elements on the critical voltage and induction time for pit nucleation on an alloy surface.
- (II.2) Unification of the point defect and solute/vacancy interaction models to explore the effects of alloying elements on the distributions in the critical voltage (V_c) and induction time (t_{ind}) for passivity breakdown. The model was then used to account for critical pitting potential data for Fe-Cr-Ni-Mo alloys taken from the literature.
- (II.3) Measurement of distributions in the critical breakdown voltage and induction time for pit nucleation on Ni-xAl, Ni-xTi, and Ni-xMo alloys in buffered chloride-containing boric acid solutions. These data agree qualitatively with the predictions of the solute-vacancy interaction model for the effects of alloying elements on passivity breakdown.
- (II.4) Development of an equilibrium "point defect" model for the segregation of alloying elements into passive films. The predictions of the model are in accord with experimental segregation data obtained using a new technique, SALI (surface analysis by laser ionization), on dilute Ni-xAl, Ni-xTi, and Ni-xMo ($x < 8$ wt%) alloys.
- (II.5) Continued development of a kinetic model for describing the segregation of alloying elements at a passive interface. The model should account for the

segregation of alloying elements into the barrier layer and into the outer layer, and should describe the enrichment of some alloying elements on the metal side of the metal/film interface. We are also preparing a series of nickel-based, binary alloys containing minor amounts (0-5%) of Al, Ti, Ta, W, Mo, and Pd, to test the predictions of the model. The segregation of the alloying elements into the barrier and outer layers will be determined using a combination of XPS, AES, SIMS, and SALI, after the passive films have been grown under carefully controlled conditions.

III. Electronic Structure of Passive Films

- (III.1) Detection and explanation of photoinhibition of passivity breakdown, as observed on nickel in buffered KCl solution. Photogeneration of electron/hole pairs apparently quenches the electric field in the passive film, thereby reducing the driving force for the movement of cation vacancies from the film/solution interface to the metal/film interface. The lowered vacancy flux results in a positive shift in the breakdown voltage and in the induction time, and hence in enhanced resistance to pitting.
- (III.2) Development of methods for measuring photoelectrochemical impedance functions for metal- and semiconductor-solution interfaces by modulating the intensity of an incident, monochromatic light beam, and by transforming photocurrent transients from the time domain to the frequency domain. By using an He/Ne laser with a photon energy of 1.96 eV (632 nm), we measured the photoelectrochemical impedance spectra for n-Si and p-Si in contact with sodium hydroxide solution over wide ranges of modulation frequency and applied bias potential. We are currently developing theoretical models to explain the impedance data in terms of the photogeneration of electron/hole pairs and their recombination via surface states, and in terms of the reactions of electrons and holes with redox species in the solution. More recently, we have greatly extended the photon-energy range by using a square wave excitation function. This technique has now been used in this program to explore coupling between the electronic and crystallographic defect structures of passive tungsten and zirconium. This work has shown that these defect structures are strongly coupled, presumably because the vacancies ($V_O^{\bullet\bullet}$), $V_M^{\bullet}$ act as donors and acceptors in the normal, semiconductor sense.
- (III.3) The use of Kramers-Kronig (K-K) transforms of electrochemical impedance spectroscopy (EIS) data to ascertain whether electrochemical systems satisfy the linearity, causality, and stability constraints imposed by linear system analysis.¹²⁻¹⁴ We continue to examine how well experimental EIS data satisfy the K-K transforms by exploring one particular class of impedance functions known as constant phase impedances. We show, unequivocally, that constant phase impedances, which include those for passive films at low frequencies, transform provided that the loci are restricted to the right side of the complex plane. In a significant extension of this method, we have recently used the K-K transforms to explore the nature of the photoelectrochemical impedance and admittance functions. We found that the functions obey the transforms, so that they may be regarded as a true impedance or admittance. Accordingly, the system response may be analyzed in terms of linear systems theory.
- (III.4) Development of a model for the electronic structure of a barrier passive film, in which the cation vacancies and oxygen vacancies act as acceptors and donors,

respectively. The non-linear vacancy profiles are given by the solutions to the appropriate Nernst-Planck transport equations with voltage-dependent boundary conditions. Because of the high vacancy concentrations at the boundaries, the model incorporates degenerate structures, and is similar, in many respects, to models that have been developed in semi-conductor physics for tunnel diodes.

IV. Estimation of Damage Functions for Energy Systems

- (IV.1) Development of coupled environment models for pit growth and crack growth. During the current reporting period, this model has been combined with the distribution functions for V_c and t_{ind} to derive a deterministic treatment for predicting damage functions for pitting corrosion (distribution in pit depth versus exposure time). The algorithm has been used on a separate, GRI-funded program to compute damage functions and service lives for gas-fired condensing heat exchangers.

A central hypothesis of our theoretical work on the effect of alloying elements on passivity breakdown is that highly charged solutes, such as Mo^{6+} substituted into NiO passive films, form ion pairs with mobile cation vacancies of the type $Mo_{Ni}^{4\bullet} \cdots V_{Ni}^{2'}$. This interaction is described as a chemical equilibrium using the Debye-Huckel and Onsager-Fuoss ion-pairing theories, originally developed for aqueous electrolyte solutions but later used to describe vacancy-impurity interactions in semiconductors. This approach accounts very well for the effect of molybdenum on the pitting resistance of stainless steel and for the effects of Al, Ti, and Mo on the breakdown characteristics of nickel in buffered chloride solutions. The most effective alloying elements are those that

- (1) Segregate to the greatest extent into the passive film ($Mo > Ti > Al$).
- (2) Possess the greatest charge relative to the host cation (i.e., $Mo_{Ni}^{4\bullet} > Ti_{Ni}^{2\bullet} > Al_{Ni}^{\bullet}$).

The extent of segregation was attributed principally to the high dielectric constant of the thin, electronically conducting passive film, and hence to the ability of the film to "solvate" the substituted alloy solute. The magnitude of the charge is important because it determines the electrostatic energy of interaction with the negatively charged cation vacancies and hence the extent of ion-pair formation. However, these charges are also screened by oppositely charged entities (e.g., cation vacancies and electrons), and allowance for this effect is made using the Debye-Hückel screening radius.

As noted above, photoinhibition of passivity breakdown on nickel in buffered chloride solutions, as observed in this program, is a direct manifestation of coupling between the electronic and lattice defect structures of the film. Because the films are highly doped with vacancies, which act either as acceptors ($V_M^{\chi'}$) or donors ($V_O^{\bullet}$), where χ is the oxide stoichiometry, $(MO_{\chi/2})$, the model that emerges for the electronic structure of the film is that of a metal- n^+ -i- p^+ -solution junction, with the relative p^+ and n^+ characters depending on the relative concentrations of metal and oxygen vacancies, respectively.

As with classically degenerate n^+ -i- p^+ junctions, the potential drop occurs entirely across the depletion region, with the electric field strength being determined by the compensating processes of charge separation, owing to isoenergetic tunneling from filled levels in the valence band to unfilled levels in the conduction band, and electron/hole

recombination, possibly via surface states. The photogeneration of electron/hole pairs quenches the electric field (by the photodiode effect), thereby reducing the driving force for the transport of cation vacancies from the film/solution interface to the metal/film interface. Thus, incident light is expected to inhibit passivity breakdown, as observed experimentally. We are now exploring photoinhibition as a practical means of protecting equipment in the power generation industry from pitting corrosion. This concept is being explored under an EPRI Exploratory Research grant.

PROPOSED RESEARCH

During the third and final year of the current grant, we will emphasize five on-going tasks in our quest to develop a better understanding of the growth and breakdown of passive films on metal surfaces, of the electronic properties of passive films, and to develop more efficient deterministic methods for estimating the development of damage due to localized corrosion.

Task 1. Development of Growth Models for Bilayer Structures

Initial work carried out during the past year has resulted in the development of equations that describe the formation of bilayer passive films on metals in aqueous systems (Figure 1). The barrier layer is considered to form by growth of the metal/film interface into the metal phase via the generation of oxygen vacancies whereas the outer layer grows from cations that are ejected from the barrier layer at the film/solution interface. We have also developed a mathematical description of the growth of the barrier layer on stepping the voltage to a higher value within the passive region (Task 1 of Year 2), which leads to logarithmic and parabolic growth laws depending on the conditions. Our goal in this task will be to extend the treatment to consider the kinetics of growth of bilayer structures that are typical of passive films that form on transition metals in aqueous systems.

Researchers: Prof. Digby D. Macdonald (Faculty)
Prof. Mirna Urquidi-Macdonald (Faculty)

Task 2. Exploration of the Electronic Structures of Passive Films

Continuing our current work, we propose to explore the electronic structures of passive films formed on valve metals (W, Zr, Ti) in phosphate and borate buffer solutions. In particular, we are interested in assessing the type and extent of coupling between the electronic and crystallographic defect structures, as well as ascertaining the profiles of the potential and oxygen vacancies within the film. These problems are being addressed by using:

- (i) Photoelectrochemical Impedance Spectroscopy (PEIS), in which the electronic structure of the passive film is excited by using a modulated monochromatic light beam. The resulting (modulated) photocurrent is then divided into the excitation to yield an impedance function. We showed previously in this program that the function is indeed an impedance because, when measured over a wide modulation frequency range, it obeys the Kramers-Kronig transforms (see Task 6 of Year 2). We have now obtained extensive PEIS and photoelectrochemical admittance spectra (PAS) for tungsten and zirconium over wide ranges of voltage and as functions of other experimental variables (see, for example, Figure 2).

JA-M-7759-150A

Figure 1. Schematic of processes that lead to the formation of bilayer passive films on metal surfaces.

Figure 2. PEIS spectrum for W

- (ii) Theoretical modeling studies, in which the electrical properties of the film are modeled as a non-linearly doped semi-conductor. By solving the Nernst-Planck equations for the vacancies and assuming that the metal and oxygen vacancies act as acceptors and donors, respectively, we are able to identify the most likely electronic structure as being comparable to the class of junctions n^+-i-p^+ , with the relative n or p character being determined by the relative concentrations of the vacancies. In the case of the passive films formed on W and Zr, the principal crystallographic defect is the oxygen vacancy, and Mott-Schottky analysis yields an average vacancy concentration in the film of 10^{19} - 10^{20}cm^{-3} . Thus, in these cases, the electronic structure of the passive films may be viewed as a metal/ n^+-i /solution junction. We are currently attempting to fit the electronic model of the film to the extensive PEIS and PAS data that we have amassed over the past year. Our goal is to extract important parameters and properties that describe the electronic/crystallographic structures of passive films, including the potential profile, carrier lifetimes, electron/hole photogeneration rates, etc.

Researchers: Prof. Digby D. Macdonald (Faculty)
Dr. Elzbieta Sikora (Post Doctoral Fellow)
Dr. Janusz Sikora (Post Doctoral Fellow)

Task 3. Exploration of the role of Cation Vacancy Condensates in Passivity Breakdown

A key assumption in the point defect model (PDM) is that passivity breakdown occurs because of the formation of chloride-or potential-induced cation vacancy condensates at the metal/film interface, thereby leading to local separation of the barrier layer from the metal. These "blisters" eventually rupture due to growth stresses in the film and due to local dissolution at the film/solution interface, which is not balanced by growth at the metal/film interface due to loss of contact between the film and the metal. Considerable evidence exists for these blisters in the case of aluminum, and they have been shown to be the nucleation sites for pits on this metal in aqueous environments (see Appendix). Because a vacancy condensate cannot exist at the interface between a liquid metal and a passive film, a prediction of the PDM is that passivity breakdown on a liquid substrate should be much more difficult than on a solid substrate. We are testing this prediction by exploring passivity breakdown on gallium, which has a convenient melting temperature of 29.78°C (Figure 3). Our initial data for gallium in buffered chloride-containing solutions confirm the prediction, but attribution of this behavior to the lack of formation of vacancy condensates on the liquid substrate is not unambiguous because a difference in stress state is also expected to exist. We are currently measuring breakdown potentials for liquid and solid gallium in chloride containing solutions as a function of temperature and chloride concentration so as to ascertain the difference in behavior of the liquid and solid substrates, but future work in this task (not necessarily in this year) will include:

- (i) Spectroscopic microellipsometry to detect the formation of vacancy condensates ("blisters") as the precursors of passivity breakdown. This work will be carried out in cooperation with Prof. Richard Collins of PSU's Physics Department.
- (ii) An analysis of the electrochemical noise on liquid and solid gallium to ascertain what aspects of the noise can be attributed to passivity breakdown. It should be noted that the noise spectrum on liquid gallium is little different from that on solid gallium, even though the former does not suffer pitting attack whereas the latter does.

Fig. 3 Anodic polarization response of Ga in borate buffer, 0.1m KCl as a function of temperature.

The work being carried out in this task forms the basis of a M.S. thesis in Materials Science and Engineering, with submission of the thesis being scheduled for the fall of 1993. However, we propose to extend the work to a Ph.D. dissertation based on the ellipsometry and electrochemical noise studies outlined above.

Researchers: Prof. Digby D. Macdonald (Faculty)
Mr. David Ellerbrock (Graduate Student)

Task 4. Segregation of Alloying Elements at Passive Interfaces

In an earlier part of this program, we developed the solute-vacancy interaction model (SVIM) to account for the effects of "active" alloying elements, such as Mo, W, Cr, Ti, and Al, on the pitting susceptibilities of binary alloys of the type Ni-X ($X \equiv \text{Al, Cr, Ti, Mo, W}$). The basis of the SVIM is that, if the alloying elements segregate into the barrier layer in a substitutional form in a higher oxidation state than the host cation, they appear as positively charged centers in the oxide phase (in Kroger-Vink notation as $X_{\text{Ni}}^{(\delta-2)\bullet}$, where δ is the oxidation state of the solute). These positive centers may interact electrostatically with the mobile cation vacancies to form "ion pairs," thereby decreasing the concentration and mobility of the cation vacancies in the film and hence inhibiting passivity breakdown. The predictions of the SVIM are in good qualitative agreement with the known effects of molybdenum on the pitting resistances of stainless steels (Figure 4) and with preliminary pitting data obtained at SRI (on the preceding grant) for dilute alloys of the type Ni-X ($X \equiv \text{Al, Ti, and Mo}$), assuming that the alloying elements segregate into the barrier layer in their highest oxidation states. We also demonstrated in that previous grant that the extent of segregation of X into the barrier layer lies in the order $\text{Mo} > \text{Ti} > \text{Al}$ (Figure 5), and a quasi-equilibrium model was developed to account for these observations. The findings summarized above have led to the formulation of three rules for devising pitting-resistant alloys (see Appendix); to our knowledge, they are the only such rules that have been inspired on purely theoretical grounds and which are in general agreement with experiment.

In order to apply the SVIM for estimating, quantitatively, the pitting resistance of alloys, and recognizing that some solutes may segregate on the metal side of the metal/film interface (e.g. in the case of inert solutes, such as Pt), we require a much more comprehensive and accurate model for the segregation of the alloying element into the metal/barrier layer interphase. Such a model is currently being developed in this task. The model involves the solution of coupled transport equations for the movement of the host metal (e.g. Ni) and the alloying element (X) in the metal phase, Ni_{Ni} , $X_{\text{Ni}}^{(\delta-2)\bullet}$, O_O , and $(V_\text{O}^{\bullet\bullet})$ in the film, and ejection of cations (Ni^{2+} , $X^{\delta+}$) from the film into the solution. The problem is mathematically complicated by the fact that the equations are all coupled and that it is a moving boundary problem (the metal/film boundary moves into the metal and the film/solution interface dissolves and hence moves away from a fixed reference frame in the solution).

In order to test the predictions of the segregation model, we have prepared a number of single phase binary alloys, including Ni-Pt, Ni-Al, Ni-Cr, Ni-Ti, Ni-Mo, and Ni-W. These alloys will be anodized under well-controlled electrochemical conditions, and the compositions of the interphases (metal and barrier layer) will be determined using a combination of surface analytical techniques, including AES, XPS, and SALI (Surface Analysis by Laser Ionization, which is available at SRI International).

RA-m-320522-135

Figure 4. Effect of molybdenum concentration on $\bar{V}_c(x) - \bar{V}_c(x=0)$ for 6+-3- (O) and 4+-3- (Δ) complexes in the passive film of Fe-Cr-Ni-xMo alloys.

$n_v = 5 \times 10^{20} \text{ cm}^{-3}$, $K_1 = 1.13 \times 10^{-16} \text{ cm}^3$ (O)
 $K_1 = 1.13 \times 10^{-16} \text{ cm}^3$ (Δ).

● Lizbys and Bond: Fe-18 Cr in 1 M NaCl at 25°C
 ▲ Shibata: Fe-17 Cr in 3.5% NaCl at 30°C
 ▼ Shibata: Fe-18 Cr in 3.5% NaCl at 30°C
 (See Ref. 4.)

RA 350532-21B

Figure 5 Concentration profiles of H, O, Al, Ti and Mo in passive films formed on Ni-6% Al, Ni-6% Ti, and Ni-6% Mo in 0.1 N H₃PO₄/NaOH, pH = 12, at 25°C as determined by surface analysis by laser ionization. V = 0.30 V vs SCE. Ordinates are expressed as ratios of masses.

The work being carried out in this task forms the basis of a Ph.D. dissertation in Materials Science and Engineering with submission of the dissertation expected in mid-1995.

Researchers: Prof. Digby D. Macdonald (Faculty)
Mr. Lei Zhang (Graduate Student)

Task 5. Development of Deterministic Methods for Estimating Damage

One outcome of the development of the point defect model is that we now possess an analytic (deterministic) framework for estimating the distribution functions of the critical (breakdown) voltage (Figure 6) and induction time (Figure 7) for the nucleation of pits on alloy surfaces (see Appendix). Most importantly, the model yields analytical relationships between the nucleation rate and the activity of chloride, pH, temperature, and time. We have recently combined this treatment with a coupled environment model for pit growth, which is also deterministic because it satisfies the conservation of charge, to estimate pitting damage functions and service lines for gas-fired condensing heat exchangers (Figure 8, supported by GRI) and to estimate failure times for low pressure steam turbine disks (Figure 9, also see publications). A key component of the algorithm for estimating damage functions is the coupled environment model for pit (or crack) growth. The model invokes the conservation of charge as the condition that must be satisfied by a freely-propagating crevice, and it is this condition that determines the potential distribution in the system. The initial version of this model was originally developed by us with funding from the Swedish Nuclear Power Inspectorate, in order to describe cracking in water-cooled nuclear reactor heat transport circuits (Figure 10). Since then the model has been refined to describe pitting (with GRI support) and stress corrosion cracking of alloys under thin liquid films (this work).

In this task, we propose to continue the work outlined above with emphasis on improving the efficiencies of the numerical algorithms and by incorporating additional processes (e.g. cathodic reactions in the crevice) to render the model more physically realistic. Additionally, we propose to:

- (i) Continue developing artificial neural networks (ANNs) to improve the experimental data base against which the damage function algorithm will be tested. An ANN has been developed in the current grant to assess pitting damage function data for AL29-4C in synthetic chloride-containing condensate and a second network is being established to assess stress corrosion cracking data for sensitized Type 304SS in reactor heat transport circuits.
- (ii) Apply the algorithm for calculating damage functions for stress corrosion cracking in boiling water (nuclear) reactor (BWR) recirculation piping.

We have chosen to apply our technology for estimating damage functions and hence for calculating service life to nuclear power systems for three reasons:

- (i) It is an important (multi-billion dollar) problem in the US energy industry.
- (ii) A great need exists for deterministic methods for estimating damage, so that maintenance can be scheduled more effectively.
- (iii) A strong possibility exists for attracting matching funds from industrial and other sources. For example, the Swedish Nuclear Power Inspectorate has expressed a willingness to cost-share to the extent of \$50K/year to further develop the

JA-7759-19

Figure 6. Cumulative probabilities for the breakdown voltage as a function of $\bar{D}$ for normal distributions in the diffusivity D .
 $\beta = 0.01$, $\sigma_D = 0.75$, $\bar{D}$, $T = 298.25$ K, $a_x = 0.402$, $\chi = 3$.
 • Data for Fe-17Cr in 3.5% NaCl solution at 30°C from Shibata (see Refs. 2 and 3).
 $\bar{V}_c = -0.046$ V (SCE).

JA-7759-25

Figure 7. Differential cumulative probabilities for the induction time as a function of $\bar{D}$ for normal distributions in D.
 $\sigma_D = 0.75 \bar{D}$. (---) Data for Fe-17Cr in 3.5% NaCl solution at 30°C from Shibata (see Refs. 2 and 3), $\bar{V}_c = -0.046 \text{ V (SCE)}$, $V = 0.020 \text{ V (SCE)}$, $\bar{t} = 7.5 \text{ s}$, $\tau = 0$.

FIGURE 8. The measured and calculated service life for for Type 304L SS heat exchanger tubes as a function of the chloride concentration

FIGURE 9. Calculated crack initiation ($K_I \rightarrow K_{ISCC}$) and failure ($K_I \rightarrow K_{IC}$) times for a low pressure steam turbine disk as a function of temperature and oxygen concentration. ($[NaCl] = 10^{-3}$ mol/cm³, $[HCl] = 10^{-5}$ mol/cm³, $\sigma = 300$ MPa, $h = 1.0 \times 10^{-3}$ cm, $a_0 = 5.0 \times 10^{-5}$ cm, $L_0 = 1.0 \times 10^{-3}$ cm, $K_{ISCC} = 10 \text{ MPa}\sqrt{\text{m}}$, $K_{IC} = 190 \text{ MPa}\sqrt{\text{m}}$).

Figure 10 Observed and predicted crack growth rates vs. corrosion potential (ECP) for sensitized Type 304SS in pure water at 288°C at constant load (After Ford et al.¹)

- Ford et al. empirical model for different conductivities
 $K_I = 25 \text{ ksi}\sqrt{\text{in}} \text{ (} 27.5 \text{ MPa}\sqrt{\text{m}} \text{)}$.
- CEFM by Macdonald and Urquidi-Macdonald for pure water ($\approx 0.1 \mu\text{S cm}^{-1}$), $K_I = 20 \text{ MPa}\sqrt{\text{m}}$

**DATE
FILMED**

8 / 18 / 93

END