Quarterly Progress Report:
High Temperature Electrochemical Separation
of H₂S from Coal Gasification
Process Streams

^{FG}
Grant DE-~~PS~~22-91PC91288

January 1, 1992 - March 31, 1992

by

Professor Jack Winnick
Georgia Institute of Technology
School of Chemical Engineering
Atlanta, Georgia 30332-0100

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED
P

Purpose and Goals of Research

An advanced process for the separation of hydrogen sulfide from coal gasification product streams through an electrochemical membrane is being developed using the funds from this grant. H_2S is removed from the syn-gas stream, split into hydrogen, which enriches the syn-gas, and sulfur, which can be condensed from an inert gas sweep stream. The process allows removal of H_2S without cooling the gas stream and with negligible pressure loss through the separator. The process is economically attractive by the lack of adsorbents and the lack of a Claus process for sulfur recovery.

Research conducted during the present quarter is here highlighted, with an emphasis on progress towards the goal of an economically viable H_2S removal technology for use in coal gasification facilities providing polished fuel for co-generation coal fired electrical power facilities and Molten Carbonate Fuel Cell electrical power facilities.

Introduction

The process under development is presented schematically in Figure 1. The process gas, cleaned of particulates, is passed by the cathode. Here, the most easily reduced species will be electronated; under these conditions, it is H_2S :

The sulfide ions are maintained, with alkali-metal cations, as a fused electrolyte in a ceramic membrane. The sulfide is transported across to the anode, where it is oxidized to elemental sulfur. An inert gas such as N_2 is used at the anode to carry away the vaporous sulfur, S_2 , to be condensed for recovery downstream.

Figure 1.
Schematic of H_2S Removal Cell.

Theoretical Analysis

A theoretical analysis of cell electronic performance was performed in an attempt to model cross-cell potential as a function of cell H_2S removal (or applied current). This analysis proceeded in the following manner:

The minimum electrical work required to operate a separation cell at constant temperature and pressure is given by the change in Gibbs free energy (ΔG) of the electrochemical reaction:

$$W_e = \Delta G = -nFE \quad (3)$$

where n is the number of electrons transferred in the reaction, F is Faraday's constant (96500 coulombs/equivalent), and E is the reversible potential of the cell. If all the reactants and products are in the standard state, then

$$\Delta G^\circ = -nFE^\circ \quad (4)$$

If half-cell reactions (1) and (2) are summed, the overall cell reaction becomes:

So, for this overall cell reaction, the free energy change can be expressed by the equation:

$$\Delta G = \Delta G^\circ + RT \ln \left(\frac{P_{H_2, \text{Anode}} P_{S_2, \text{Anode}}^{\frac{1}{2}} a_{S^{2-}, \text{Analyte}}}{P_{H_2, \text{Cathode}} a_{S^{2-}, \text{Catholyte}}} \right) \quad (6)$$

When equations (6) and (7) are combined we have:

$$E = E^\circ + \frac{RT}{nF} \ln \left(\frac{P_{H_2, \text{Anode}} P_{S_2, \text{Anode}}^{\frac{1}{2}} a_{S^{2-}, \text{Analyte}}}{P_{H_2, \text{Cathode}} a_{S^{2-}, \text{Catholyte}}} \right) \quad (7)$$

which is the form of the Nernst equation specific to this system.

Additional electrical work is required to run the separation cell because of irreversible losses. These losses originate primarily from three sources: (i) ohmic polarization (η_{ohm}), (ii) concentration polarization (η_{conc}), and (iii) activation polarization (η_{act}). These losses result in a cell voltage (V) which is greater than the reversible potential.^[1]

Ohmic Polarization: The ohmic losses occur because of resistance to the flow of ions in the electrolyte and resistance to the flow of electrons through the electrode materials. Because both the electrolyte and the electrodes obey Ohm's law, the ohmic losses can be expressed by the equation:

$$\eta_{\text{ohm}} = IR \quad (8)$$

where I is the current flowing through the cell, and R is the total cell resistance, which includes electronic, ionic and contact resistances.

Concentration Polarization: As a reactant is rapidly consumed at the electrode by electrochemical reaction, concentration gradients are established. Several processes contribute to concentration polarization: slow diffusion in the gas phase in the electrode pores, solution/dissolution of reactants/products into/out of the electrolyte, of diffusion of reactants/products through the electrolyte to/from the electrochemical reaction site. At practical current densities, slow transport of reactants/products to/from the electrochemical reaction sites is a major contributor to concentration polarization.

The rate of mass transport to an electrode surface can be described by Fick's first law of diffusion

$$i = \frac{nFD(C_{H_2S_B} - C_{H_2S_s})}{\delta} \quad (9)$$

where D is the diffusion coefficient of the reacting species, $C_{H_2S_B}$ is the concentration of H_2S in the bulk, $C_{H_2S_s}$ is the concentration of H_2S at the electrode surface, and δ is the thickness of the diffusion layer. The limiting current (i_L) is the maximum rate at which reactant can be supplied to an electrode, and occurs when $C_{H_2S_s} = 0$:

$$i_L = \frac{nFDC_{H_2S_B}}{\delta} \quad (10)$$

By combining equations (9) and (10) we have:

$$\frac{C_{H_2S_s}}{C_{H_2S_B}} = 1 - \frac{i}{i_L} \quad (11)$$

The Nernst equation for the reactant species at equilibrium conditions, or when no

current is flowing, is:

$$E_{t=0} = E^{\circ} + \frac{RT}{nF} \ln C_{H_2S_s} \quad (12)$$

When current is applied, the surface concentration becomes less than the bulk concentration and the Nernst Equation becomes:

$$E = E^{\circ} + \frac{RT}{nF} \ln C_{H_2S_s} \quad (13)$$

the potential difference (ΔE) produced by a concentration change at the electrode is called the concentration polarization:

$$\Delta E = \eta_{conc} = \frac{RT}{nF} \ln \left(\frac{C_{H_2S_s}}{C_{H_2S_b}} \right) \quad (14)$$

By combining equations (11) and (14) we obtain the expression for concentration polarization in terms of applied current:

$$\eta_{conc} = \frac{RT}{nF} \ln \left(1 - \frac{i}{i_L} \right) \quad (15)$$

Activation Polarization: The activation polarization at the cathode and the anode of the cell is directly related to the rates of electrochemical reactions occurring at these electrodes. There is a close similarity between electrochemical and chemical reactions in that both involve an activation barrier that must be overcome by the reacting species. The standard model to describe the current-overpotential relationship behind

these electrochemical kinetics is the Butler-Volmer equation^[2]:

$$i = i_0 \left[\exp\left(\frac{\alpha_a F}{RT} \eta_{act, electrode}\right) - \exp\left(\frac{-\alpha_c F}{RT} \eta_{act, electrode}\right) \right] \quad (16)$$

This equations holds at a specified temperature, pressure, and concentration of reacting species. Since the electrochemical kinetics can be different at the cathode and anode of the cell, the electrochemical parameters α_a , α_c , and i_0 must be determined for each electrode. Also, the transfer coefficients, α_a and α_c , sum to the number of electrodes transferred in the reaction:

$$\alpha_a + \alpha_c = n \quad (17)$$

Electrode Polarization: The total polarization at each electrode is the sum of the activation polarization ($\eta_{act, electrode}$) and the concentration polarization ($\eta_{conc, electrode}$):

$$\eta_{electrode} = \eta_{act, electrode} + \eta_{conc, electrode}$$

The effect of polarization is to shift the potential of the electrode ($E_{electrode}$) to a new value ($V_{electrode}$):

$$V_{electrode} = E_{electrode} \pm |\eta_{electrode}| \quad (19)$$

For the cathode:

$$V_{cathode} = E_{cathode} - |\eta_{cathode}| \quad (20)$$

and for the anode:

$$V_{anode} = E_{anode} + |\eta_{anode}| \quad (21)$$

Cell Voltage: The cell voltage includes the contribution of the polarization and the anode and cathode potentials:

$$V_{cell} = V_{cathode} - V_{anode} - IR \quad (22)$$

When equations (20) and (21) are substituted into equation (22) we have:

$$V_{cell} = \Delta E_e - |\eta_{cathode}| - |\eta_{anode}| - IR \quad (23)$$

with ΔE_e equal to $E_{cathode} - E_{anode}$.

The following data was generated using this model. The run conditions models consisted of equal cathodic and anodic flowrates (200 cc/min), a system pressure of 1 atmosphere, a run temperature of 625°C, and the polishing of H₂S from 100 ppm down to 10 ppm. The cathodic and anodic exchange current densities were estimated at 40 mA/cm² after the results of the free electrolyte study performed by Banks^[3]. The exchange coefficients, α_a and α_c , were assumed to each be unity. Ohmic resistance across the cell was estimated to be only 1 Ω . The results of this model are presented in Table 1 and graphically in Figure 2.

Table 1.
Theoretical Cross-Cell Potentials

<u>Removal</u>	<u>Nernst (V)</u>	<u>Ohmic (V)</u>	<u>Cat.Act.(V)</u>	<u>An. Act.(V)</u>	<u>Conc.(V)</u>	<u>Total(V)</u>
10%	-0.081	-2.60E-4	-3.42E-5	3.42E-5	-0.004	-0.089
20%	-0.099	-5.20E-4	-6.85E-5	6.85E-5	-0.009	-0.117
30%	-0.112	-7.80E-4	-1.03E-4	1.03E-4	-0.014	-0.141
40%	-0.123	-1.04E-3	-1.37E-4	1.37E-4	-0.020	-0.165
50%	-0.135	-1.30E-3	-1.71E-4	1.71E-4	-0.027	-0.191
60%	-0.147	-1.56E-3	-2.05E-4	2.05E-4	-0.036	-0.221
70%	-0.162	-1.82E-3	-2.40E-4	2.40E-4	-0.047	-0.258
80%	-0.180	-2.08E-3	-2.74E-4	2.74E-4	-0.062	-0.308
90%	-0.209	-2.34E-3	-3.08E-4	3.08E-4	-0.089	-0.391

Figure 2.
Theoretical Cross Cell Potential vs % Removal.

Examination of this data shows that the activation polarization at both the cathode and the anode is negligible. This shows extremely rapid electrochemical kinetics when compared to diffusion effects in the gas phase and in the electrolyte. Actual exchange current densities in full removal cells will likely be smaller due to electrolyte wetting the pores of the electrodes, porosity, and tortuosity of the electrodes. However, activation polarizations at the electrodes are expected to remain negligible and the values used in this study represent an 'order-of-magnitude' estimate. All cross-cell potentials are shown to be primarily Nernstian and concentration polarization effects. Comparison of these results to the experimental cell results from Run 49C shows that as a rough estimate, they are correct.

Experimental Results

Seven experimental runs with simulated coal gasification product streams were attempted this quarter (Runs 49 through 55). Run 49 showed successful removal of H_2S as a function of applied current. Runs 50 through 55 were not successful. A summary of these experiments follows:

Successful Runs

Run 49

This experimental run used one mat of ZYW-30A zirconia cloth layered two tapes of MgO as the matrix material and Li/K eutectic carbonate electrolyte. The electrolyte was allowed to go to its equilibrium sulfide concentration in-situ. MACOR

machinable ceramic housings were used the gases were run through a stainless steel shift reactor to allow them to go to their equilibrium composition before entering the cell. The electrodes were both lithiated NiO.

The run was divided into three sections: the first confirmed ionic transport through the membrane by removal of CO₂ (and H₂O) from the syn-gas at 625°C (Run 49A), the second was an attempt at removal of H₂S from the syn-gas at 625°C (Run 49B), and the third was an attempt at removal of H₂S from the syn-gas at 700°C (Run 49C). The results of these studies follow:

Run 49A

CO₂ removal from the process gas as a function of applied current was recorded. Successful removal of CO₂ (and H₂O) with current showed that the cell was functioning properly with respect to ionic transport. At the cathode, CO₂ and H₂O combine to form CO₃²⁻ and H₂:

At the anode, CO₃²⁻ goes to CO₂ and O₂:

The recorded data is presented in Table 2.

Table 2.
Run 49A Recorded Data.

<u>Applied Current (mA)</u>	<u>Actual Cathode CO₂ Out</u>	<u>Calc. Cathode CO₂ Out</u>	<u>Actual Anode CO₂ Out</u>	<u>Calc. Anode CO₂ Out</u>
0	17.8%	17.8%	0.0%	0.0%
100	16.8%	16.8%	1.8%	1.2%
200	15.8%	15.7%	2.8%	2.4%
300	15.2%	14.7%	3.8%	3.7%

This data shows that the cell was functioning properly with respect to ionic transport of carbonate through the electrolyte. The fuel gas flow was set at 75 cc/min and the N₂ sweep was set at 63 cc/min.

Run 49B

No current effect on H₂S was observed after 27.7 hours with an applied current density of 0.63 mA/cm². Examination of the limiting current densities at this run temperature shows that at 625°C the gas phase limiting current density was only 1.1 mA/cm² while the membrane limiting current density was only 1.4 mA/cm². This membrane limiting current density assumes that the electrolyte diffusivity was 10⁻⁵ cm²/sec. Once membrane porosity and tortuosity are taken into account, this estimate is in all probability too large. As an 'order-of-magnitude' estimate, however, it does show that the transport through the membrane is on the same order as the transport through the gas phase. It is probable that at these temperatures, the membrane cannot support the necessary flux of sulfide ion to significantly affect the exit H₂S concentration.

Run 49 C

At 700°C, analysis of the limiting current densities within the system showed that the gas phase limiting current density was 1.2 mA/cm² while the membrane limiting current density was 3.3 mA/cm². This shows that even if the electrolyte diffusivity estimate is in error, the membrane flux is three times greater than at 625°C. H₂S removal at a variety of flow rates was observed and is presented in Figure 3. Overpotentials as a function of applied current and flowrate are presented in Figure 4. The lowest level to which H₂S was driven was 9.7 ppm (89.1% removal, zero current basis). This data shows good response of the system to applied current. The overpotentials required to accomplish this removal are negligible.

Figure 3.
H₂S Removal versus Applied Current and Flow Rate, Run 49C.

Figure 4.
Overpotential versus Applied Current and Flow Rate, Run 49C.

Unsuccessful Runs

Runs 50 through 55

After run 49, the cell housings were changed to type 316 stainless steel in an attempt to simulate an actual membrane separator configuration in an industrial environment. Runs 50 through 55 are outlined as follows:

Run 50

A 20 micron thick coating of Al was sputtered onto the wet contact surfaces. This Al coating would be converted in-situ to LiAlO_2 by reactions with the Li_2CO_3 in the electrolyte^[4]. The electrodes were lithiated NiO and the membrane was two tapes of MgO layered with two mats of ZYW-30A. The membrane was damaged at start-up

by adding molten electrolyte through the reference electrode hole on the cathode side of the cell. It appears that the density change caused by absorbing the electrolyte had damaged the membrane. The cell was shut down due to uncontrollable cross-flow.

Run 51

The stainless steel housings of this run were painted with 29 wt% Al paint. The electrodes were both lithiated Ni and were allowed to go to NiO in-situ. The membrane was two tapes of MgO layered with one mat of ZYW-30A and the electrolyte was added by pressing the amount required to saturate the matrix material into a disk and layering it within the membrane at start-up. Once the electrolyte melted cell seals were good and the system responded well to CO₂ removal. Cross cell electronic resistance was high ($R=1.4\ \Omega$), however, and two more grams of electrolyte were added. This excess electrolyte ran into the exit anode tube and froze, clogging the tube and rupturing the membrane with the subsequent pressure build-up. The cell was shut down because the membrane was destroyed.

Run 52

This experimental run was identical to run 51. It also was shut down due to excess electrolyte flooding the anode side of the cell and clogging the anode exit tube. In this case, however, the anode seal blew out before the membrane ruptured. The cell was cooled of and the anode exit line was replaced. On heating back up to run

temperature, the anode exit tube became clogged once again. The cell membrane did not survive this second temperature cycle as the best current efficiency that could be observed for CO₂ removal was only 30%. Hydrogen cross-over and CO₂ back diffusion were present at sufficient levels to offer no hope for successful H₂S removal. The cell was shut down for this reason.

Run 53

The set-up for this run was identical to the set-up for the previous two runs. The run was heated all the way to run temperature under O₂. This caused the electrolyte to decompose by the following reaction:

By analysis of this reaction at the run temperature of 700°C, at least 300 ppm CO₂ would have to be present in the cathode and anode streams to prevent this decomposition of the electrolyte. The cell was shut down because decomposition of the electrolyte led to membrane failure.

Run 54

This experimental run was used as a training run for the new graduate student. The set-up was identical to the previous run. Leaks in the tubes connecting the manometer across the cathode and the anode sides of the cell lead the student to believe that the membrane had blown and that there was bulk mixing of the process and sweep gas streams since no pressure difference across the membrane could be

detected when flow on either side of the cell was throttled. The cell was therefore shut down.

Run 55

The housings used in this experimental run were identical to the housings used in the previous experimental runs. Set up was also identical, except that O₂ was only applied during the binder burn-out period. Once the cell had reached 350°C and had stayed at this temperature for 1 hour, fuel gas was started to the cathode side of the cell and N₂ to the sweep side of the cell. Temperature was then allowed to go to the run temperature of 700°C. This prevented the electrolyte decomposition seen in run 53. Once the cell had reached temperature, the cathodic CO₂ removal rate was observed to be close to 100%. However, the anodic production rate of CO₂ was less than 100%. This means that there was an alternative oxidation reaction taking place at the anode. Since the housings were acting as the current collectors, if the AL coating on the anode did not go to a homogeneous layer of LiAlO₂ and thus insulate the housing wet seal area, it is possible that electrolyte which had seeped out into the wet seal area was being oxidized:

CO₂ from electrolyte oxidized in the wet seal area could escape to the furnace and would not be detected in the anode exit stream.

Once cathodic removal efficiency had been determined, H₂S was started to the

cell at a level of 122 ppm. Some current effect on H_2S was observed (cathode exit H_2S level of 35 ppm with no current applied dropped to a level of 28 ppm with 200% stoichiometric current applied). However, the shift reactor, which allows the simulated fuel gas to reach its equilibrium composition through the water/gas shift reaction:

began to clog with carbon. The reverse of the coal gasification reaction could occur at these conditions if the water level in the gas is too low:

It seems that this reaction was happening before the water/gas shift reaction could build up enough water vapor to prevent the carbon monoxide decomposition reaction from depositing carbon in the shift reactor. This problem was corrected by burning the carbon out of the shift reactor with an air stream. Unfortunately, seal integrity was lost on the cathode side of the cell during this process. Seals became so bad that all gas entering the cathode side of the cell was blown into the furnace and ignited. No gas analysis could be performed on the cathode exit gases. The ignited gases raised the cell housing temperature locally which lead to aggressive electrolyte corrosion of the wet seal area. The cell was shut down to progressive corrosion of the cathode cell housing and loss of seal integrity. Carbon deposition can be prevented in future runs by hydrating the gas stream before it enters the shift reactor.

Summary

Polishing application of this technology to coal gasification synthesis gas has been demonstrated with H_2S removals as high as 89.1% recorded (Run 49C). No successful runs with stainless steel housings have yet been achieved. However, since stoichiometric CO_2 removal with stainless steel housings has been achieved, H_2S removal is achievable.

Planned Work for Next Quarter

Work with the stainless steel housings will continue. Since the key to successful use of stainless steel seems to be insulating the wet seal area, this will be accomplished by forming an intimately bound layer of Al metal on the wet seal surfaces and then allowing the Al to go to the non-conductive and protective LiAlO_2 in-situ.

References

- 1) U.S. Dept. of Energy, Fuel Cells: A Handbook, DOE/METC-88/6090, Morgantown, West Virginia, 1988.
- 2) Prentice, G., Electrochemical Engineering Principles, Prentice Hall, Englewood Cliffs, New Jersey, 1991.
- 3) Banks, E., and Winnick, J., *J. Appl. Electrochem.*, **16**, 1986.
- 4) Swaroop, R., et. al., *J. Electrochem. Soc.*, **11**, 1978.

END

**DATE
FILMED**

9 / 8 / 92