MTR

Proj. 22130.6.3
DOE/mc/22130-T12

DOE/MC/22130--T12

DE92 017784

LOW COST HYDROGEN/NOVEL MEMBRANE TECHNOLOGY
FOR HYDROGEN SEPARATION FROM SYNTHESIS GAS,
PHASE I

Contract Number: DE-AC21-85MC22130

A Quarterly Technical Progress Report
for the Period ending December 31, 1986

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Contributors to this Report

R. W. Baker
I. Pinnau
J. G. Wijmans

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

APPROVED FOR PUBLICATION BY THE U.S. GOVERNMENT
FOR THE U.S. PATENT GROUP
BY *WGB* DATE *7/28/22*

MASTER

Membrane Technology and Research, Inc.
1030 Hamilton Court • Menlo Park, California 94025 • (415) 328-2228

Table of Contents

I. Introduction And Summary

II. Progress This Quarter

Task 3.1.(1) Poly(etherimide) Membranes

Task 3.1.(2) Poly(ether-ester-amide) Membranes

Task 3.2 Construct Modules

III. Plans For The Next Quarter

I. Introduction And Summary

This is the fifth quarterly technical progress report from Membrane Technology and Research, Inc. to the U.S. Department of Energy under contract number DE-AC21-85MC22130. The report covers the period 1 October - 31 December 1986.

During the last quarter, we developed several high performance membranes for the separation of hydrogen from nitrogen, carbon monoxide, hydrogen sulfide and carbon dioxide. The heat-resistant resin poly(etherimide) has been selected as the polymer with the most outstanding properties for the separation of hydrogen from nitrogen and carbon monoxide. Flat sheet and hollow fiber poly(etherimide) membranes have been prepared and evaluated with pure gases and gas mixtures at elevated pressures and temperatures.

Multilayer composite poly(ether-ester-amide) membranes were also developed. Poly(ether-ester-amide) is a block copolymer, having recurrent units of the general formula,

where A is a polyamide sequence and B is a polyether. These membranes are useful for the separation of carbon dioxide and hydrogen sulfide from hydrogen. They have very high selectivities and extremely high normalized carbon dioxide and hydrogen sulfide fluxes.

Separation of carbon dioxide/hydrogen streams is a key problem in hydrogen production from coal. The development of the two membranes described above gives us two approaches to separate these gas streams, depending on the stream's composition. If the stream contains small quantities of hydrogen, the hydrogen-permeable poly(etherimide) membrane would be used to produce a hydrogen-enriched permeate. If the stream contains small quantities of carbon dioxide or hydrogen sulfide, the poly(ether-ester-amide) membrane would be used to produce a carbon dioxide/hydrogen sulfide-free, hydrogen-enriched residue stream.

II. Progress This Quarter

Task 3.1.(1) Poly(etherimide) Membranes

Poly(etherimide) was selected as one of the most promising materials to separate hydrogen from nitrogen and carbon monoxide. Asymmetric poly(etherimide) membranes were obtained from GKSS, Geesthacht, West Germany. We have tested these membranes at 50 psig and 200C with pure gases. Table I shows that the membranes, as supplied, have a rather low hydrogen/nitrogen selectivity of 20. We overcoated the asymmetric membranes with a thin poly-

dimethylsiloxane layer in our laboratory. This results in a considerable increase in hydrogen/nitrogen selectivity. The polydimethylsiloxane coating affects the hydrogen flux only slightly, but dramatically reduces the nitrogen flux, presumably by plugging defects in the ultrathin skin layer of the asymmetric poly(etherimide) membrane.

Table I. Performance of GKSS Poly(etherimide) Membranes for Hydrogen/Nitrogen Separation

Membrane	Normalized flux (P/L) (cm ³ /cm ² sec.cmHg)		Selectivity (α) H ₂ /N ₂
	nitrogen	hydrogen	
GKSS integral- asymmetric poly(etherimide) uncoated	5x10 ⁻⁶	1x10 ⁻⁴	20
Integral- asymmetric poly(etherimide) + polydimethylsiloxane coating	3.5x10 ⁻⁷	7x10 ⁻⁵	200

The influence of feed pressure on the performance of poly(etherimide)/polydimethylsiloxane membranes was determined using the high pressure permeability system shown in Figure 1.

The experiments were carried out with pure gases at 200C and feed pressures between 100 and 500 psig. The effective membrane area was 34 cm². As shown in Figure 2, the normalized flux of all gases tested (N₂, CH₄, CO, CO₂ and H₂) was independent of feed pressure.

Figures 3a and 3b show the selectivities calculated from the ratios of the normalized gas fluxes. These graphs show that the poly(etherimide)/polydimethylsiloxane membrane is extremely selective for the separation of hydrogen from nitrogen, methane and carbon dioxide. However, the performance of this membrane is rather poor for hydrogen/carbon dioxide separation.

Additional experiments were carried out to determine the influence of feed gas temperature on the performance of poly(etherimide)/polydimethylsiloxane membranes. As shown in Figures 4a to 4c, the normalized fluxes of hydrogen, carbon dioxide and nitrogen strongly depend on the feed gas temperature. All gases tested strictly obey the Arrhenius equation.

Figure 1. High pressure permeability test system for pure gases and gas mixtures.

Figure 2. Normalized flux of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed pressure ($T=298\text{K}$).

Figure 3a. Selectivity of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed pressure (T=298K).

Figure 3b. Selectivity of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed pressure (T=298K).

Figure 4a. Normalized hydrogen flux of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed temperature.

Figure 4b. Normalized carbon dioxide flux of poly-(etherimide)/polydimethylsiloxane composite membranes as a function of feed temperature.

Figure 4c. Normalized nitrogen flux of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed temperature.

Figure 4a shows that the hydrogen flux of the poly-(etherimide)/polydimethylsiloxane membrane is increased four-fold between 200°C and 800°C. The nitrogen flux, however, is increased almost ten-fold (see Figure 4c). Therefore, as shown in Figure 5a, hydrogen/nitrogen selectivity of 250 at 200°C drops to about 100 at 850°C. Figures 5b and 5c show the calculated selectivities as a function of temperature for hydrogen/carbon dioxide and carbon dioxide/nitrogen, respectively. The carbon dioxide/nitrogen selectivity decreases from 40 to 16 from 200°C to 850°C, whereas the hydrogen/carbon dioxide selectivity increases slightly from 6 to 7, in the same temperature range.

Poly(etherimide)/polydimethylsiloxane membranes were also tested with gas mixtures. We investigated the influence of feed gas composition and feed gas pressure on the membranes' performances. The experiments were carried out with hydrogen/nitrogen mixtures at 200°C and feed pressures between 100 and 500 psig. The effective membrane area was 34 cm². To simplify interpretation of the results, the stage cut was maintained at close to zero, i.e. feed and residue concentration were essentially the same.

As shown in Table II, the performance of the poly-(etherimide)/polydimethylsiloxane membrane is independent of feed pressure. However, normalized hydrogen flux and hydrogen/nitrogen selectivity do depend on the feed gas composition. A high hydrogen concentration in the feed gas increases the normalized hydrogen flux and hydrogen/nitrogen selectivity. This result is unexpected and no reason could be found to explain this behavior, since hydrogen does not plasticize the membrane.

Table II. Performance of Poly(etherimide)/Polydimethylsiloxane Membranes for Hydrogen/Nitrogen Separation as a Function of Gas Composition and Feed Pressure

Feed gas composition (vol%)	Feed pressure (psig)	Normalized flux P/L (cm ³ (STP)/cm ² sec.cmHg)		Selectivity (α) H ₂ /N ₂
		N ₂	H ₂	
Hydrogen 50%	100	3.6x10 ⁻⁷	8.1x10 ⁻⁵	230
Nitrogen 50%	200	3.8x10 ⁻⁷	8.5x10 ⁻⁵	220
	300	3.9x10 ⁻⁷	8.5x10 ⁻⁵	220
Hydrogen 10%	300	4.5x10 ⁻⁷	7.7x10 ⁻⁵	170
Nitrogen 90%	400	4.4x10 ⁻⁷	7.5x10 ⁻⁵	170
	500	4.3x10 ⁻⁷	7.5x10 ⁻⁵	170

Figure 5a. Hydrogen/nitrogen selectivity of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed temperature.

Figure 5b. Hydrogen/carbon dioxide selectivity of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed temperature.

Figure 5c. Carbon dioxide/nitrogen selectivity of poly(etherimide)/polydimethylsiloxane composite membranes as a function of feed temperature.

Task 3.1.(2) Poly(ether-ester-amide) Membranes

During the last quarter, we developed polysulfone/poly(ether-ester-amide) multilayer composite membranes. Permeability studies showed these membranes to be extraordinarily selective for carbon dioxide over hydrogen. The experiments were carried out with pure gases at elevated pressures at 220C. As shown in Figure 6, the normalized carbon dioxide flux strongly depends on feed pressure, due to extremely high sorption of carbon dioxide in the selective poly(ether-ester-amide) layer. Since the normalized hydrogen flux increases only slightly with pressure, carbon dioxide/hydrogen selectivity increases from 9.5 to 17 between 50 and 500 psig.

Table III shows the performance of the MTR multilayer composite membrane compared to methyl cellulose acetate, the most selective membrane for carbon dioxide/hydrogen separation reported in the literature. These initial results are very encouraging. The membranes have almost ten times the flux and comparable selectivities to methyl cellulose acetate membranes. We expect an even better performance of the MTR multilayer composite membrane for the separation of hydrogen sulfide from hydrogen. During the next months, we will prepare continuous multilayer membranes and produce the first spiral-wound modules.

Table III. Performance of MTR Poly(sulfone)/polydimethylsiloxane/poly(ether-ester-amide) Composite Membranes for Carbon Dioxide/Hydrogen Separation

Membrane Type	Normalized Flux (P/L) [cm ³ (STP)/cm ² sec.cmHg]		Pressure [psig]	Selectivity (α) CO ₂ /H ₂
	H ₂	CO ₂		
MTR polysulfone/ polydimethylsiloxane/ poly(ether-ester-amide) composite membrane	3.2x10 ⁻⁵	3.0x10 ⁻⁴	50	9.5
	3.5x10 ⁻⁵	6.0x10 ⁻⁴	500	17
Methyl cellulose acetate	5.9x10 ⁻⁶	6.5x10 ⁻⁵	200	11

Task 3.2. Construct Modules

Poly(etherimide)/polydimethylsiloxane spiral-wound modules were prepared in our laboratory. The modules showed hydrogen/nitrogen selectivities between 6 and 10 and normalized hydrogen fluxes of 7-8x10⁻⁵cm³(STP)/cm²sec.cmHg. The low selectivity is

Figure 6. Normalized hydrogen and carbon dioxide flux of polysulfone/polydimethylsiloxane/poly(ether-ester-imide) multilayer composite membranes as a function of feed pressure.

due either to membrane damage during the rolling process or leaks along the glue lines of the membrane envelope.

Internal research funds were used to develop poly(etherimide) hollow fiber membranes. The fibers are coated with polydimethylsiloxane to prevent gas flow through the few defects of the selective layer. Several hollow fiber modules were prepared with an effective area of 70 cm². The properties of these modules are listed in Table IV.

Table IV. Performance of Poly(etherimide)/polydimethylsiloxane Hollow-fiber Modules for Hydrogen/Nitrogen Separation

Composition of spinning dope	Normalized flux P/L (cm ³ (STP)/cm ² sec.cmHg)		Selectivity (α) H ₂ /N ₂
	N ₂	H ₂	
18.8 wt% poly(etherimide), 1.5 wt% polyvinylpyrrolidone, 79.7 wt% N-methylpyrrolidone	8.2x10 ⁻⁸	1.2x10 ⁻⁵	150
20.5 wt% poly(etherimide), 1.5 wt% polyvinylpyrrolidone, 78.0 wt% N,N-dimethylacetamide	2.0x10 ⁻⁷	3.3x10 ⁻⁵	170
25 wt% poly(etherimide), 75 wt% N,N-dimethylacetamide	1.7x10 ⁻⁷	3.3x10 ⁻⁵	190

The performance of these modules is encouraging. The selectivity of the modules is comparable to that of our best flat-sheet composite membranes, although the normalized hydrogen flux is somewhat lower. We will carry out additional investigation in the preparation of the hollow fibers to improve the hydrogen flux.

III. Plans For The Next Quarter

Poly(etherimide)/polydimethylsiloxane membranes were tested with pure gases and gas mixtures at elevated pressures and temperatures. During the next months, we will test this membrane with hydrogen sulfide and with three-and four-component gas mixtures. We will improve the poly(etherimide)/polydimethylsiloxane spiral wound modules and prepare hollow fiber modules.

Poly(sulfone)/polydimethylsiloxane/poly(ether-ester-amide) multilayer composite membranes seem to be extremely attractive for the separation of carbon dioxide and hydrogen sulfide from nitrogen. During the next quarter, we will prepare continuous membranes and produce the first spiral-wound modules.

**DATE
FILMED**
8/27/92