AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 1

**STRUCTURAL STABILITY OF 1100 DEGREE C HEATED Pd/k
DURING ABSORPTION CYCLING IN PROTIUM (U)**

by

I. A. Fisher

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

RECEIVED
JUL 02 1993
OSTI

MASTER

DOE Contract No. **DE-AC09-89SR18035**

This paper was prepared in connection with work done under the above contract number with the U. S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U. S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

gf
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P. O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**WESTINGHOUSE SAVANNAH RIVER COMPANY
SAVANNAH RIVER LABORATORY**

March 12, 1993

TO: T. Motyka, 773-A

FROM: I.A. Fisher, 773-A *IAF***STRUCTURAL STABILITY OF 1100°C HEATED Pd/k DURING
ABSORPTION/DESORPTION CYCLING IN PROTIUM(U)****INTRODUCTION**

Palladium supported on kieselguhr (Pd/k) is a hydride forming packing material which is used in several unit operations in the Replacement Tritium Facility (RTF). Pd/k is used in the Thermal Cycling Absorption Process (TCAP), the Pd/k flow-through beds, and the diffuser vacuum beds. Palladium is supported on kieselguhr to create a packing material which will provide adequate void space in these unit operations to prevent excessive pressure drops and flow restrictions in the aforementioned RTF operations. The use of unsupported palladium would result in blockage of columns and clogging of filters due to the small particle size of unsupported palladium hydride powder.

The Advanced Hydride Laboratory (AHL) within the Savannah River Technology Center (SRTC) has operated several TCAP units to demonstrate the technology on a pilot scale. At one point during these investigations, it was noted that the Pd/k packing material had degraded causing severe flow restrictions within the TCAP column. It was determined that much of this degradation of the Pd/k packing material was caused by mechanical breakdown induced by fluidization of the packing material at the high TCAP flow rates. This problem was initially corrected by reducing the TCAP flow rates to minimize particle fluidization. However, reduced flow rates cause reduced process throughput. A more permanent solution to the problem involved the heating of Pd/k at 1100°C to strengthen the packing material, and render it more resistant to breakdown. The 1100°C heated Pd/k has been shown to be more resistant to mechanical breakdown than the Pd/k prior to heat treatment. The heating process and effects are described elsewhere [1,3].

Two primary modes of Pd/k particle degradation have been identified [1-3]. Mechanical breakdown caused by particle fluidization and degradation caused by absorption/desorption cycling. Absorption/desorption cycling causes the palladium particles within the packing to expand and contract upon formation and decomposition of the hydride, respectively. This expansion and contraction causes large localized stresses within the packing material, which if these stresses can not be accommodated within the packing will cause the material to crack and degrade. Mechanical breakdown can cause the Pd/k to degrade over a relatively short period of time, while cycling induced degradation occurs over a longer time.

W C Mosley

Technical Reviewer

3/16/93

Date

T. Motyka

Authorized Derivative Classifier

3/16/93

Date

The purpose of this report is to document the results of the absorption/desorption cycling of 1100°C heated Pd/k and compare these results to the results obtained from the absorption/desorption cycling of Pd/k which had not been heated at 1100°C [2].

SUMMARY

The results show that the 1100°C heated Pd/k is significantly more resistant to degradation caused by absorption/desorption cycling than the Pd/k which has not been 1100°C heated. The average particle size is reduced by only 20% for the 1100°C heated Pd/k after 4,500 cycles as compared to 40% for the non heated Pd/k after 4,000 cycles. A current specification for Pd/k for the RTF is that >80 wt% of the particles be greater than 50 mesh (300µm). The results of these investigations show that after 4,500 cycles the 1100°C heated Pd/k contains 92 wt% of particles >50 mesh as compared to 99 wt% before cycling. While after 4,000 cycles the non heated Pd/k contained only 71 wt% of particles >50 mesh as compared to 94 wt% prior to cycling. After ~4,000 cycles additional degradation of particles is negligible. Based on these results, the 1100°C heated Pd/k will remain within the specification that >80 wt% of the particles be greater than 50 mesh (300µm) for the lifetime of the material, if the material is not subjected to conditions which would induce mechanical breakdown. Conditions causing the mechanical break down of 1100°C heated Pd/k are described elsewhere [1,3].

EXPERIMENTAL DETAILS

Materials

The non heated Pd/k was prepared by Ionex Research Corporation. The kieselguhr used was 30-40 mesh particles of CHROMOSORB P (AW) procured from Manville Sales Corporation. The palladium chloride used in the process was procured from D.F. Goldsmith Chemical and Metal Corporation. The Ionex process for the preparation of Pd/k has been described previously [4,5]. The 1100°C heated Pd/k was prepared in the same manner as the non heated Pd/k. The only difference is the heating at 1100°C under an air atmosphere for 2 hours. The heating process is described elsewhere [1,3].

Absorption/Desorption Cycling

The procedure for quantifying the Pd/k decrepitation consisted of determining the particle size distribution of an uncycled Pd/k sample, thermally cycling the sample for a number of cycles, remeasuring the particle size distribution, followed by more cycling. To measure the particle size distribution an Addison-Bradley sonic sifter was used, with which samples were separated into 5 fractions; +40,+50,+100,+200, and -200 mesh fines.

The experimental equipment used to thermally cycle the Pd/k sample is shown in Figure 1. The Pd/k sample was placed into a stainless steel bed, which is connected to a 1 liter volume. A Keithley Series 500 data acquisition and control system records the temperature and pressure and controls the heating and cooling to the bed.

Prior to cycling the Pd/k sample was heated to 150°C for 10 min. under vacuum and evacuated overnight. The volume was filled with H₂ @ 1000 torr and the bed was exposed to the protium at room temperature. The sample was cycled for a number of cycles after which time the sample was fully desorbed @ 150°C under vacuum. The sample was sonically sieved and replaced into the bed for the next set of cycles.

A cycle is 10 minutes long and consists of 5 minutes of cooling and 5 minutes of heating. When the system is cooling, the control system activates a relay opening a solenoid valve allowing nitrogen to pass over the bed until the bed temperature falls to -40°C . The control system maintains the bed temperature between -40 and -30°C until the cooling half cycle is over. During the heating half cycle, the control system activates a relay allowing the heat gun to heat the bed until it reaches 150°C . The control system maintains the bed temperature between 140 and 150°C until the heating half cycle is over.

Figure 1.
Pd/k Absorption/Desorption
Cycling System

RESULTS

Absorption/Desorption Cycles

A typical absorption/desorption cycle is shown in Figure 3. Palladium hydride is formed during the cooling cycle according to eq. (1), and the system pressure drops. Protium gas is desorbed during the heating cycle and the pressure returns to its original value. The system pressure and bed temperature were collected every 30s.

Sieve Analysis Results

Figure 4 represents the particle size distributions for both the uncycled and cycled 1100°C heated and non heated Pd/k samples. From Figure 4 it can be seen that the cycling of non heated Pd/k causes a more significant reduction in the fraction of particles larger than 40 mesh or 420µm than does the cycling of 1100°C heated Pd/k. Also, the cycling of the non heated Pd/k results in the creation of significant quantities of fine particles, or particles less than 50 mesh or 300 µm in size. The majority of smaller particles created by the cycling of the 1100°C heated Pd/k are larger than 50 mesh or 300µm, and only a very small portion are smaller than 50 mesh or 300µm. The main difference between the cycling of 1100°C heated and non heated Pd/k is that the cycling of 1100°C heated Pd/k does not produce significant quantities of fine particles while the cycling of non heated Pd/k does.

Figure 3.
Absorption/Desorption Cycle

A way to represent the data more compactly is to calculate the weight averaged particle size ($\bar{\Pi}$) using the expression:

$$\bar{\Pi} = \frac{\sum_{i=0}^n x_i}{\sum_{i=0}^n \frac{x_i}{w_i}} \quad (2)$$

where x_i = weight fraction of fraction i
 w_i = size of fraction i
 n = number of fractions.

Figure 4
Particle size distributions

Π for each 1,000 cycles of the non heated Pd/k and for 0, 1,000, and 4,500 cycles of the 1100°C heated Pd/k is shown in Figure 5. Π for the non heated Pd/k dropped from 325μm to about 200μm after about 4,000 cycles and remained constant thereafter. The last data point represents a non heated Pd/k sample from TCAP III, a pilot scale unit operated at SRL in 1987-88 at TCAP operating conditions, which had accumulated 10,000 cycles. The data points for the 1100°C heated Pd/k follow the same shape as for the non heated Pd/k. Π starts at 395 μm and drops only to 315μm. No additional particle degradation due to absorption/desorption cycling is expected to occur.

Mechanism for Particle Decrepitation

Backscatter SEM micrographs were taken of the uncycled and cycled 1100°C heated Pd/k particles and representative micrographs are shown in Figures 6 and 7. The heat treatment changes the structure of the palladium rich layer in the uncycled Pd/k. The submicron Pd particles have sintered together and grown to form a network interlaced with the porous silica of the kieselguhr. The formation of this network is suspected to strengthen the Pd/k particles and reduce breakdown [3]. The SEM micrographs of the cycled Pd/k reveal that the palladium rich layer has become partially detached or loosened from the kieselguhr core. This is probably caused by the repeated swelling and contraction of the Pd particles upon the absorption and desorption of hydrogen. This repeated volume expansion and contraction causes large localized stresses between the palladium rich outer layer and the kieselguhr core. These stresses can not be completely accommodated, and therefore, the interface between the two regions breaks down in some cases.

Figure 5.
Weight averaged particles sizes

It should be pointed out that the palladium rich outer layer that does become detached from the kieselguhr core appears stable and does not continue to break down into smaller particles. This was also evidenced in the particle size distribution for the cycled 1100°C heated Pd/k, which showed that smaller particles which are formed are for the most part still greater than 300 μm or 50 mesh. This is not the case for the Pd/k which has not received the heating. The non heated Pd/k when cycled also had the palladium rich outer layer become detached from the kieselguhr core. But unlike the 1100°C heated Pd/k, the detached outer layer continued to breakdown and form fine particles.

CONCLUSIONS

1100°C heated Pd/k is significantly more resistant to particle decrepitation than non heated Pd/k. Particle decrepitation that does occur results in the formation of relatively large particles (>300 μm or 50 mesh). The majority of these particles are regions of the palladium rich outer layer which has become detached from the kieselguhr core. These detached regions appear stable and do not further degrade to form fine particles. No significant quantities of fine particles are formed as a result of cycling 1100°C heated Pd/k. Based on the results of these investigations, 1100°C heated Pd/k will remain within the specification that greater than 80% of the particles be greater than 50 mesh or 300 μm in size for the lifetime of the material, if the material is not subjected to conditions which would induce mechanical breakdown of the material. Conditions causing the mechanical break down of 1100°C heated Pd/k are described elsewhere [1,3].

Figure 6
Uncycled 1100°C heated Pd/k

Figure 7
1100°C heated Pd/k after 4,500 cycles

REFERENCES

1. K.J. Stoner, "The Effects of Heat Treatment on Pd/k (U)", SRL-HTS-90-0007, 1/10/90
2. I.A. Fisher, "Absorption/Desorption Cycling of Palladium/Kieselguhr (U)", SRL-HTS-89-0171, 1/22/90
3. W.C. Mosley, "Pd/k for RTF and 232-H TCAP Units (U)", WSRC-TR-90-554, 1/29/91
4. W.C. Mosley, "Palladium Deposited on Kieselguhr (Pd/k) for the Replacement Tritium Facility (RTF)", WSRC-TR-90-24, 1/11/90
5. A.R. Mochel, Trip Report: Ionex Research Corporation, 4/6/87

**DATE
FILMED**

9 / 9 / 93

END