NRTSC

NUCLEAR REACTOR TECHNOLOGY
AND SCIENTIFIC COMPUTATIONS

Keywords:

Reactor Materials Program
Moderator
Shield Water
Reactor
Corrosion
IGSCC
Stainless Steel
Aluminum
PTERM
CAMEL

Retention - Permanent

RESULTS AND RECOMMENDATIONS FROM THE REACTOR CHEMISTRY AND CORROSION TASKS OF THE REACTOR MATERIALS PROGRAM (U) Task #89-023-G-1

(By)

E. W. Baumann *E. W. Baumann*
R. S. Ondrejcin *R. S. Ondrejcin*

ISSUED: November, 1990

D. Thomas Perkins
Derivative Classifier

SRL SAVANNAH RIVER LABORATORY, AIKEN, SC 29808
Westinghouse Savannah River Company
Prepared for the U. S. Department of Energy under Contract DE-AC09-76SR00001

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

PROJECT: Reactor Materials Program

DOCUMENT: WSRC-TR-90-477

TITLE: Results and Recommendations from the Reactor Chemistry and Corrosion Tasks of the Reactor Materials Program (U)

TASK: Task #89-023-G-1, Measure Effect of Moderator Chemistry on Stress Corrosion of Sensitized and of Irradiated Stainless Steel

APPROVALS

G. R. Caskey, TECHNICAL REVIEWER
MATERIALS TECHNOLOGY

DATE: 11-6-90

D. T. Rankin, MANAGER
MATERIALS TECHNOLOGY

DATE: 11-7-90

J. M. Stone, MANAGER
MATERIALS TECHNOLOGY

DATE: 11-7-90

RQAP APPROVAL

DATE: 11-27-90

TABLE OF CONTENTS

	Page #
1.0 INTRODUCTION	1
2.0 SUMMARY & RECOMMENDATIONS	2
3.0 DISCUSSION	3
3.1 System Description	3
3.1.1 Primary System	3
3.1.2 Shield Systems	4
3.1.3 History	5
3.2 Reactor Moderator Chemistry	5
3.2.1 Implementation of pD Control	5
3.2.2 Chemical Aspects of pD Control	5
3.2.3 Chemistry Role in Stainless Steel Corrosion	6
3.2.4 Chemistry Role in Aluminum Corrosion	6
3.3 Results from the Reactor Materials Program	6
3.3.1 Background	6
3.3.2 Task 6: Aqueous Environment	7
3.3.3 Task 7: Corrosion	7
3.3.3.1 CERT Tests	8
3.3.3.2 Crack Growth Tests	9
3.3.4 Task 10: Electrochemical Potential	9
3.4 Application of Results	9
3.4.1 General Comments	10
3.4.2 Moderator	10
3.4.2.1 pD Control	10
3.4.2.2 pD Limits	10
3.4.2.3 Oxygen Control	10
3.4.2.4 Radiolysis	11
3.4.2.5 Impurity Control	12
3.4.2.6 Mode of Reactor Operation	12
3.4.3 Shield Water	12
REFERENCES	13
TABLE 1 Principal Dissolved Constituents in Moderator	15
TABLE 2 Dissolved Constituents in Thermal Shield Water	16
TABLE 3 Tasks of the Reactor Materials Program	17
TABLE 4 Concentration Ranges of Independent Variables	18
TABLE 5 Evaluation of Moderator & Shield Water Conditions from CERT Tests	19
TABLE 6 Synthetic Moderator Environments for Crack Growth Tests	20
TABLE 7 Technical Standards and Operating Limits	21
TABLE 8 Sampling Frequencies	22
FIGURE 1 105-K Reactor Complex	23

WESTINGHOUSE SAVANNAH RIVER COMPANY
INTER-OFFICE MEMORANDUM

WSRC-TR-90-477

November 1, 1990

TO: J. D. SPENCER, 773-A

FROM: E. W. BAUMANN, 773-41A/R. S. ONDREJCIN, 773-41A

**RESULTS AND RECOMMENDATIONS FROM THE REACTOR CHEMISTRY AND
CORROSION TASKS OF THE REACTOR MATERIALS PROGRAM (U)**

1.0 INTRODUCTION

Production reactors at the Savannah River Site (SRS) have operated successfully for over 30 years. Throughout the operating history, corrosion of both the aluminum clad assemblies and the stainless steel pressure boundary has occurred. The moderator chemistry must therefore be optimized to mitigate corrosion of both systems. The corrosion of the stainless steel materials of the pressure boundary by stress corrosion cracking have been confined to localized regions. The only known limitation to reactor service life is stress corrosion cracking of Type 304 stainless steel in portions of the primary components that cannot readily be repaired or replaced, such as the reactor tank or the thermal shields.

Within the general context of extended service life, the Reactor Materials Program was initiated in 1984. This comprehensive program addressed material performance in SRS reactor tanks and the primary coolant or Process Water System (PWS) piping. Three of the eleven tasks concerned moderator quality and corrosion mitigation.¹

Definition and control of the stainless steel aqueous environment is a key factor in corrosion mitigation. The unique chemistry of the SRS PWS, which was designed to minimize corrosion of both stainless steel and aluminum, differs from the primary coolant chemistry of power reactors, which has been extensively evaluated for corrosive properties. The Reactor Materials Program systematically investigated the SRS environment and its effect on crack initiation and propagation in stainless steel, with the objective of improving this environment.

The purpose of this report is to summarize the contributions of Tasks 6, 7 and 10 of the Reactor Materials Program to the understanding and control of moderator quality and its relationship to mitigation of stress corrosion cracking.

2.0 SUMMARY AND RECOMMENDATIONS

This report extracts the findings of the three tasks of the Reactor Materials Program that provide the basis for moderator quality improvement. The three tasks are:

- Task 6: to analyze impurities in reactor aqueous streams to provide data for subsequent corrosion testing.
- Task 7: to determine the effect of SRS environment and operating conditions on crack initiation and crack growth rates through Constant Extension Rate Tensile (CERT) tests and crack growth experiments.
- Task 10: to measure electrochemical potentials of stainless steel and platinum in the uncooled moderator of an SRS reactor during all phases of reactor operation.

The three tasks produced the following:

- a comprehensive view of moderator and shield water chemistry, based on offline analysis
- initiation of the concept of the value of online analysis, providing the groundwork for future online instrumentation for the reactor (although the purchased, custom design online analyzer was never installed)
- identification of temperature, chloride, sulfate, and the presence of peroxide as contributors to crack initiation and growth by IGSCC*
- a mathematical relationship that permits prediction of the effect of varying these contributions for optimization
- a range of crack growth rates that agrees with rates measured by ultrasonic testing and laboratory data. The rates show wide variability and incremental increases with perturbations such as temperature changes.
- confirmation of the expected high electrochemical potentials of stainless steel in the reactor system because of the nitric acid-hydrogen peroxide chemistry of reactor moderator.

Recommendations for maintaining/improving moderator and shield water quality in SRS systems are derived and discussed. The following recommendations are made:

For Moderator:

- that no changes in the fundamental operation with nitric acid and excess oxygen be made
- that updated pH limits in Table 7 remain unchanged
- that reliable online monitors for oxygen be maintained, and that the minimum oxygen concentration necessary to ensure nitrate stability be determined experimentally during reactor operation
- that extraneous dissolved impurities, beyond the nitric acid and oxygen needed for pD control be eliminated
- that chloride and sulfate concentrations be reduced to 2 and 7 ppb** respectively

*Intergranular Stress Corrosion Cracking

**parts per billion; micrograms per liter.

- that ion exchange resins and practices be reevaluated
- that potential sources of chloride and sulfate, such as filter and gasket materials, be replaced with lower source materials where possible
- that sampling frequency be increased as practical; in particular, during periods of charge and discharge when the system can receive impurities from outside sources, sampling should be increased to once a day
- that additional online sensors, such as for chloride and sulfate, be installed; and that ultimately a second generation multipurpose online analyzer be evaluated and installed
- that the beneficial effect of reduced operating temperature in mitigating IGSCC be recognized
- that during reactor operation, efforts be made to reduce reactor scrams or other rapid thermal or load changes.

For Shield Water:

- that shield water be deionized to lower the chloride ion concentration to 5 ppb, and sulfate to 7 ppb.

3.0 DISCUSSION

3.1 System Description

3.1.1 Primary System

The primary system of the SRS reactors consists of a stainless steel tank with six heat exchanger loops symmetrically placed around the tank. The sketch in Figure 1 shows one of these loops. The primary system is made from Type 304 Stainless Steel. Within the tank are aluminum-clad fuel and target assemblies plus ancillary aluminum fittings.

The system is filled with heavy water, which functions as coolant and neutron moderator as it is recirculated through the loops during reactor operation.² The primary system is a closed system because of the need to maintain isotopic purity and to conserve the heavy water. One of the six loops contains filters and mixed-bed ion exchangers to maintain moderator quality. This deionization loop is included in Figure 1. The temperature of the moderator in the primary system has historically been from ~35 to ~105°C.

Moderator quality for control of corrosion in the primary system must address the effect of the aqueous environment not only on stainless steel but also on the aluminum in the system. Table 1 gives the principal dissolved constituents in the moderator, their sources and their removal mechanisms.

3.1.2 Shield Systems

In addition to the primary system, the shield water systems in the reactors comprise another area where prevention of IGSCC is important to reactor service life. The thermal shields are located inside the concrete biological shield and would be very difficult to repair or replace. Figure 1 shows the location of the top, bottom, and thermal shields that surround the reactor tank. The primary concern about the

chemistry of the shield water systems is prevention of corrosion of the shielding structure.

The shield systems are made from Type 304 Stainless Steel. The top and bottom shields contain stainless steel Raschig rings; the thermal shields contain "Duriron" grids which, like the Raschig rings, give efficient shielding and can be readily cooled.^{3,4}

Each shield system is filled with light water, which is circulated from the shields through heat exchangers. The allowable temperature range is 55-65°C at full power.⁵ This temperature is maintained at full reactor power to prevent overstressing the T-weld on the bottom of the tank due to thermal stresses caused by the difference in moderator and shield water temperature. The stress limit on the welds is set at 28,000 psi.⁶ The water is purged and replaced with deionized water periodically to maintain the conductivity and pH within specified limits. The ionic content of the thermal shields is not routinely determined. Special analyses, summarized in Table 2, showed that the shield water is much more impure than the moderator and that the composition varies.⁷

3.1.3 History

The importance of moderator quality in controlling corrosion of the stainless steel tank and piping of the reactors has always been recognized.⁸ From the initial startup of the reactors in the mid-1950's until the late 1950's moderator was fully deionized and bulk moderator conductivity was $<0.2 \mu\text{S}/\text{cm}^*$. The two major known nonradioactive impurities were deuterium gas (primarily from aluminum corrosion) and deuterium peroxide.

The importance of moderator quality in controlling corrosion of aluminum as well as stainless steel became apparent in the late 1950's. Shortly after larger pumps were installed and the fuel assemblies were operated at substantially higher surface temperatures, the moderator in all reactors became turbid. The turbidity was caused by very fine particles of hydrated aluminum oxide that sloughed off the fuel assemblies. The turbidity caused reduced visibility, pluggage of instrument lines, and carryover of radioactivity into the disassembly basins. The turbidity problem was solved by the institution of "pD** control", in which the moderator was slightly acidified by addition of nitric acid.⁸ Turbidity is also reduced by use of distillation columns.

* $\mu\text{S}/\text{cm}$ = microSiemens per centimeter, the unit of conductivity measurement; $\mu\text{S}/\text{cm}$ is equivalent to micromhos/cm, the unit used in SRS reactor operation and procedures.

**pD = $-\log[D^+]$.

3.2 Reactor Moderator Chemistry

3.2.1 Implementation of pD Control⁸

Operation with pD control consists of maintaining the moderator approximately 10 μ molar in nitric acid, corresponding to the pD limits of 5.0 to 5.2.⁹ Because the acid is continually removed by the deionizers, nitric acid is added intermittently. pH(pD)*** and conductivity are measured online. The nitrate concentration, as well as pH(pD) and conductivity, are determined offline on grab samples.

Since the institution of moderator pD control, there have been only two occurrences of high turbidity, plus occasional periods of turbidities in the range 5 to 20 ppm during the first few weeks of a reactor cycle.¹⁰ High turbidity occurred in the L-2 cycle in 1964 when ability to control pD by nitric acid was temporarily lost. It occurred again, though less severely, throughout most of the Cf I cycles in K-Reactor in 1970; these cycles were of a few days duration, so short that pD control of corrosion could not be established.

3.2.2 Chemical Aspects of pD Control⁸

pD control was successful in minimizing aluminum corrosion and moderator turbidity problems, but it resulted in a system harder to monitor for tramp impurities. Moderator conductivity was increased from <0.2 to about 3 μ S/cm. The two online measurements, conductivity and pH, are nonspecific and cannot identify what ions are present in the moderator. Offline analyses for nitrate and other anions such as chloride are necessary to confirm the chemical system and detect the presence of deleterious impurities such as chloride.

Also, a slight excess of oxygen had to be maintained in the moderator system because without it the reducing environment from corroding aluminum destroyed the nitric acid. In at least one instance nitrate was reduced to ammonia. Ammonia formation would ultimately result in an increase in pD and lead to increased aluminum corrosion. Dissolved oxygen at about 500 ppb† is sufficient to ensure nitrate stability. It was recognized that the oxygen added should be minimized to avoid enhanced corrosion of stainless steel.

3.2.3 Chemistry Role in Stainless Steel Corrosion

The principal type of corrosion that has been found in the stainless steel of the primary system of the SRS reactors has been intergranular stress corrosion cracking (IGSCC). For IGSCC to occur, three factors must be simultaneously present: susceptible (sensitized) material, applied and/or residual tensile stress, and an environment that can provide the chemical driving force for corrosive reaction.¹¹ Because the environment is the only one of the three conditions readily accessible for change, improvements in moderator and shield water chemistry were among the goals of the Reactor Materials Program.

***The measured pH is empirically converted to pD by adding 0.4.
†ppb = parts per billion (micrograms per liter)

Coolant quality and its effect on corrosion in nuclear power reactors has been extensively considered.¹¹ However, boiling water reactors operate at 288°C, whereas the SRS reactors operate at only ~100°C. A literature survey performed for the Reactor Materials Program revealed only limited SSC data in near-SRS environments.¹² The survey concluded that, although the presence of impurities in the low temperature environment of the SRS reactors was not considered particularly damaging, the effects of the oxidizing SRS environment with oxygen and peroxide present, should be investigated.

3.2.4 Chemistry Role in Aluminum Corrosion

Acidification of the moderator to control alumina turbidity was based on knowledge that aluminum corrosion is reduced at pH ~5.^{13,14} Exact conditions for SRS reactor moderator chemistry were established by extensive in-reactor testing during which the corrosion rate (D_2 evolution) was minimized.⁸

Nitric acid was chosen as the final acidifier because it was most suitable in terms of thermodynamic and radiolytic stability as well as minimal radioactivity problems arising from neutron activation. Carbon dioxide was also tried, but was abandoned because attendant high peroxide levels were considered undesirable for stainless steel corrosion. Phosphoric and sulfuric acids were rejected because of the formation of ^{32}P and ^{35}S , bioactive isotopes that might eventually enter the environment.

3.3 Results from the Reactor Materials Program

3.3.1 Background

The purpose of the Reactor Materials Program was to evaluate material performance in SRS reactor tanks and moderator piping, with the objectives of assessing reactor safety and predicting and extending reactor service life.¹ The eleven tasks in the program are listed in Table 3. Three of these tasks were concerned with corrosion and with chemistry of the moderator and shield water systems. The results from each of these three tasks is summarized in this section. The results of these tasks form the foundation for improvements in moderator and shield water chemistry discussed in the next section.

3.3.2 Task 6: Aqueous Environment

Analyze Impurities in All K-Reactor Aqueous Streams with OnLine Analyzer

Objective: Quantitatively measure impurities in all K-Reactor moderator and thermal shield water to identify variables for intergranular stress corrosion cracking of stainless steel (Task 7).

Routine sample analyses and special analysis programs provided the historical basis for defining moderator and shield water compositions.^{8,9} To supplement these data for the Reactor Materials Program, special sampling and analysis programs were

carried out.^{15,16} These provided supplementary information on impurity levels and demonstrated ion chromatography as a viable technique for moderator analysis. For the baseline data needed for corrosion tests (Task 7) and for real-time characterization of moderator impurity sources and sinks, online analyses were planned.

A customized online analyzer was built and demonstrated.¹⁷ The analyzer was similar in design to those used to control and analyze the aqueous environment for the corrosion tests of Task 7. The online analyzer consisted of three ion chromatography systems to determine cations, anions and organic acids; an electrochemical system for peroxide; and a gas-stripping, infrared analyzer system for carbon dioxide. Chloride, nitrate, nitrite, sulfate, oxalate, lithium, sodium, potassium and ammonium ions could be determined at the 1 ppb level; organic acids could be determined to 5-10 ppb; hydrogen peroxide and carbon dioxide at 100 ppb.

The online analyzer was placed in a special facility in the -20 level of K-Reactor. From the sampling points shown in Figure 1, the heavy water moderator upstream and downstream of the deionizers, the light water shield water, and the deionized light water used for makeup in the thermal shields could all be circulated to the analyzer for analysis.

The analyzer was never connected to the reactor system because of anticipated problems with tritiated D₂O leakage and lack of priority for the analyzer in the production schedule. The online data needed for the corrosion tests was therefore not generated, and the test environments for Task 7 were chosen based on the knowledge at hand. With current enhanced recognition of the importance of coolant chemistry in IGSCC mitigation, the necessary priority for installation of a second-generation analyzer may be found in the future.

3.3.3 Task 7: Corrosion

Measure Effect of Moderator Chemistry on Stress Corrosion of Sensitized and of Irradiated Stainless Steel

Objective: Define moderator chemistry to minimize IGSCC and measure crack growth rates.

The majority of information on initiation and propagation of IGSCC in Type 304 Stainless Steel has been developed in conjunction with studies of boiling water reactors. These reactors are different from SRS reactors both in operating conditions, particularly temperature, and aqueous constituents. The addition of nitric acid and oxygen is unique to SRS reactors, as is the presence of peroxide at part-per-million levels. Other impurities, such as chloride, sulfate, and dissolved carbon dioxide, are common to both production and power reactors.

3.3.3.1 CERT Tests¹⁸

Constant Extension Rate Tensile (CERT) tests were performed to evaluate the relative influence of water impurities and temperature on IGSCC of Type 304 stainless steel and to provide guidance for moderator chemistry improvements.

Samples for testing were made from pipe taken from the SRS R-Reactor, to ensure that the stainless steel tested would be representative of that in operating SRS reactors (vintage 1950's). The coupons were heat treated to simulate the heat affected zones of welds. Both unirradiated coupons and coupons irradiated in the ORNL High Flux Isotope Reactor to neutron fluence levels comparable to reactor tank walls were tested. The temperature and aqueous environment were maintained in ranges representative of SRS primary coolant and shield water systems, as shown in Table 4.

The tests consisted of a central composite statistical design with temperature, and hydrogen peroxide, oxygen, carbon dioxide, sulfate, and chloride concentrations as independent variables.¹⁹ The logarithm of the adjusted time to maximum stress (LATMS) was chosen as the dependent variable signifying IGSCC. The variable included the time to maximum stress and ductility as measured by both elongation and reduction in area. As the LATMS increases, the possibility of IGSCC decreases, i.e. large values of LATMS are desirable. The tests revealed that the significant independent variables that contributed to IGSCC were, in the order of their decreasing importance: temperature, chloride, temperature-and-sulfate, chloride-and-chloride, chloride-and-sulfate. The presence of peroxide was significant, except at chloride concentrations at or below 8 ppb.

The product from the tests was an equation that sums the effect of each impurity on IGSCC. This equation has been used to predict effects of impurity levels and to specify remedial conditions. Table 5 presents the equation and examples of its application.

3.3.3.2 Crack Growth Tests²⁰

Crack growth experiments were performed with coupons made from the unirradiated R-reactor stainless steel and present-day Type 304 Stainless Steel. The coupons were heat treated to simulate the heat affected zones of welds, fatigue precracked, then environmentally precracked to produce an IGSCC crack.

The precracked coupons were tested at various stress intensities, under constant and transient loads, at 80 to 120°C in synthetic moderator environments. Environments were designated low, nominal, high, and improved, as shown in Table 6. Control and analysis of the environment was supplied by the loop and analyzer system used for the CERT tests. Crack growth measurements were made by the reversing DC potential method.

A wide range of crack velocities (10^{-7} to 10^{-4} inch/hour) was observed. These results compare favorably with a high-confidence crack growth rate of 4×10^{-5} inch/hour, that was developed reflecting laboratory, literature, and SRS reactor ultrasonic inspection.²¹ This crack growth rate is used as the conservative choice for pipe cracking calculations.

In the crack growth tests, systematic changes in temperature and environments did not always produce systematic changes in crack growth rates. Incremental growth occurred during test perturbations and caused 62% of the crack growth in 4% of the test time under constant load.

3.3.4 Task 10: Electrochemical Potential²²

Measure Moderator Electrochemical Potential

Objective: Provide data to interpret the corrosion results and correlate laboratory tests to SRS reactor moderator environment.

Electrochemical potential (ECP) measurements provide information about the chemical or electrochemical driving force for IGSCC. ECP is used in the nuclear power industry as an indicator for detecting conditions above the threshold potential of -230 millivolts(SHE)*, where IGSCC may occur. The lower temperatures of the SRS reactors (~100° versus 288°C) provide a higher ECP threshold for IGSCC cracking. However, both the added oxygen and the peroxide present in the SRS system are expected to increase the ECP.

Inline measurements of electrochemical potentials of both platinum and Type 304 stainless steel were made in K-Reactor moderator for about a year during 1986-7. Electrodes were placed in the hot leg of the "corrosion loop", shown in Figure 1. Here measurements could be made upstream of the heat exchangers and in moderator only a few seconds out of the reactor tank. Continuous data were collected during all phases of reactor operation.

As expected, the potentials indicated an oxidizing system. The potentials ranged from 400 to 600 mV(SHE) for stainless steel and from 200 to 400 mV(SHE) for platinum. The observed potentials were in agreement with values observed during the CERT tests in Task 7. Observed potentials were several hundred millivolts higher than the ECP threshold recommended for power reactors. However, data from the literature indicate that these higher potentials would be marginal in promoting IGSCC at the relatively low operating temperatures of the SRP reactors. The literature data implies that if it were possible to lower the potential of the stainless steel a few hundred millivolts, the steel would stop cracking.

3.4 Application of Results

3.4.1 General Comments

Results from the Reactor Materials Program have confirmed that current SRS moderator and shield water limits provide an environment that is relatively benign with respect to IGSCC. Certain improvements can be made, and some improvements recommended have already been implemented. Current moderator and shield water limits are given in Table 7. Sampling frequency for routine samples is given in Table 8.

The Systems Chemistry Group of the Reactor Engineering Department has recently addressed in depth the technical bases and adequacy of methods, systems, procedures, requirements, and administrative controls currently used at SRS to maintain, control, monitor, analyze, and record moderator quality during all phases of plant operation and layup.²³ This section supplements the Reactor Engineering documentation and defines areas for improvement that the Reactor Materials Program has identified.

*SHE designates potential versus the Standard Hydrogen Electrode.

3.4.2 Moderator

Operating limits (Table 7) for moderator quality address the following: pD control, oxygen control, radiolysis, stainless steel and aluminum corrosion, impurity control, and mode of reactor operation. Limits during wet layup and shutdowns have been addressed and specified to be similar to those during reactor operation in order to avoid chemical shock to the system.^{24,25}

3.4.2.1 pD Control

Low turbidity and low aluminum corrosion in the SRS reactors have been successfully maintained for about 30 years with pD control by nitric acid addition. Little or no IGSCC of the stainless steel system has developed for many years.²⁶ The reactor system is "seasoned" to this chemistry. Current operating limits for conductivity, pD, and nitrate content are adequate.

Recommendation: that no changes in the fundamental operation with nitric acid and excess oxygen be made.

3.4.2.2 pD Limits

Current limits and standards recognize that a change of pH(pD) in either direction will increase corrosion of aluminum. Recently another factor in the standards was addressed, namely that the pH must never be high enough to cause precipitation of gadolinium hydroxide after injection of gadolinium nitrate from the Supplementary Safety System. This recommendation is included in Table 7.

Recommendation: that updated pH limits in Table 7 remain unchanged.

3.4.2.3 Oxygen Control

Extrapolation of ECP values measured in K-moderator indicated that at 100°C conditions are marginal for IGSCC in an oxygenated system. Hence operation with the minimum dissolved oxygen concentration in the moderator, consistent with nitrate stability, is prudent. Continuing surveillance of oxygen concentration, plus an experimentally established minimum oxygen concentration would provide defensible oxygen concentration limits for reactor operation.

Recommendation: that reliable online monitors for oxygen be maintained, and that the minimum oxygen concentration necessary to ensure nitrate stability be determined experimentally online during reactor operation.

3.4.2.4 Radiolysis

Some radiolytic decomposition of the moderator is inevitable because of the high radiation field during operation and of the high residual gamma dose from activation products in the tank wall during shutdown. Maintaining low concentrations of dissolved material in the moderator minimizes radiolytic decomposition.

Principal radiolytic products in the SRS reactors are deuterium and deuterium peroxide. Deuterium from radiolysis is indistinguishable from the larger amounts released from the corrosion of aluminum in the heavy water during reactor

operation. Table 1 shows that peroxide is a major constituent indigenous to the moderator. Historically, peroxide has tracked the oxygen concentration in the system.⁸ The CERT tests showed that the presence of peroxide increased the ECP of the stainless steel. Also, peroxide generally enhanced IGSCC.

Recommendation: that extraneous dissolved impurities, beyond the nitric acid and oxygen needed for pD control be eliminated.

3.4.2.5 Impurity Control

The CERT tests have provided specific recommendations for impurity level limits. The tests revealed a dependence of IGSCC on temperature, chloride, temperature-sulfate, chloride-sulfate, and chloride-chloride. The tests revealed the need for knowledge and control of chloride and sulfate at concentrations <10 ppb. For example, at chloride concentrations below 8 ppb the effect of peroxide on IGSCC was eliminated.

A step toward improvement of control has been recently made by Analytical Laboratories²⁷ in lowering respective analytical sensitivities of chloride and sulfate to 1 and 7 ppb $\pm 25\%$. This will enable realistic trending of these impurities in the levels of interest.

Recommendation: that chloride and sulfate ion concentrations be reduced to 2 and 7 ppb respectively.

More fundamental is identification and elimination of sources of chloride and sulfate. Ion exchangers are major potential sources of both chloride and sulfate. The anion exchange resins are manufactured in the chloride form and are then exhaustively treated to remove the chloride; the cation exchange resins contain sulfonic acid ion exchange sites. While in theory the use of a mixed bed should result in removal of all ionic material, some leakage of impurities may occur. Other sources of impurities are materials in contact with the moderator that contain leachable chlorides and sulfates.

Recommendation: that ion exchange resins and practices be reevaluated.

Recommendation: that potential sources of chloride and sulfate, such as filter and gasket materials be replaced with lower source materials where possible.

Improved control of moderator quality is contingent upon timely information about impurity trends. As shown in Table 7, current routine sampling for identification of impurity parameters occurs only once a week. Only conductivity, pH(pD), and oxygen are measured online. Additional online capabilities would not only ensure better control of moderator quality but also eliminate radiation doses and hazards inherent in sampling, transport, and offline analysis.

Recommendation: that sampling frequency be increased as practical; in particular, during periods of charge and discharge when the system can receive impurities from outside sources, sampling should be increased to once a day.

Recommendation: that additional online sensors, such as for chloride and sulfate, be installed; and that ultimately a second generation multipurpose online analyzer be evaluated and installed.

3.4.2.6 Mode of Reactor Operation

In addition to the chemical environment, physical conditions during reactor operation can contribute to crack propagation and/or growth in stainless steel. Obviously changes in physical operation are not always possible, but recommendations about reactor operation stemming from the Reactor Materials Program are included for completeness.

The CERT tests have shown, not surprisingly, that temperature is by far the most important independent variable in promoting IGSCC. The obvious solution, then, is to reduce the temperature. In Table 5, where the CERT equation is evaluated for various conditions, it is seen that operation at lower temperature with nominal SRS impurities would be as effective in mitigating IGSCC as a 3- to 5-fold reduction in the already low nominal chloride and sulfate concentrations.

Recommendation: that the beneficial effect of reduced operating temperatures in mitigating IGSCC be recognized.

In the crack growth tests, most of the crack growth occurred during transients, such as a temperature change in the system. The physical shock accompanying such transients was postulated as contributing to crack growth through slip step emergence due to strain, with protective film rupture. Minimizing transient conditions would hence minimize propagation of existing cracks.

Recommendation: that during reactor operation, efforts be made to reduce reactor scrams or other rapid thermal or load changes.

3.4.3 Shield Water

Shield water limits allow higher concentrations of impurities than do those for moderator, as seen in Table 7. The pH is not as critical because no aluminum is present, and the higher concentrations are of less concern because the temperature is lower. The CERT test equation was applied to shield water conditions in Table 5. It is evident that satisfactory protection from IGSCC can be attained from either reducing the temperature or reducing the level of impurities.^{7,18} Cooling would put too large a stress on the vessel T-Weld.

Recommendation: that the shield water be deionized to lower chloride ion concentration to 5 ppb, and sulfate to 7 ppb.

REFERENCES

1. N. G. Awadalla, G. R. Caskey and R. S. Ondrejcin, Eds., Reactor Materials Program, DPST-84-820 (December 1984).
2. SRS Production Reactor SAR WSRC-SAR-RX-PLK, Table 4.1-1.
3. SRS Production Reactor SAR WSRC-SAR-RX-PLK, 5.1.1.1.
4. Drawings:
 - W133620: Top Tube Sheet Chimes, Plan Sections and Chimes
 - W133629: Top Tube Sheet, Plan and Cross Section, Arrangement
 - W133942: Annular Cooling Tanks, Plan and Sections, Arrangement
 - W134318: Main Tank Assembly; Cross Section, Arrangement
 - W133998: Annular Cooling Tank, Iron Ring, Plans and Sections
 - W133389: Tank Bottom Tube Sheet, Plan and Cross Section, Arrangement
 - W132762: Tank Bottom Tube Sheet, Sections and Details Sheet 1, Arrangement
5. DPSOL 105-1106 Graphic Panel Data Sheet (5/22/90).
6. DPE-913, Maximum Permissible Stresses and Deformation In Reactors and Thermal Shields (Secret) (5/8/56).
7. R. S. Ondrejcin and M. H. Anderson, Moderator and Shield Water Chemistry (U) SRL-MTS-900146, (June 18, 1990).
8. F. B. Longtin, Reactor Chemistry and Radioactivity Manual, RTR-1806 (August 9, 1978).
9. Sample Analysis Schedule and Control-Routine DPSOL 105-6101A-PLK, Revision 11, (5/11/89).
10. E. W. Baumann, Turbidity Levels in SRP Reactors 1958-1987, DPST-87-887, (December 30, 1987).
11. Metals Handbook, 9th Ed, Volume 13, Corrosion; p. 927, J. C. Danko, "Corrosion in the Nuclear Power Industry", ASM International, Metals Park, OH (1987).
12. B. M. Gordon and H. S. Mehta, Stress Corrosion Cracking Literature Review and Analysis for the Savannah River Plant, NEDC-30837, General Electric Co., San Jose, CA (December 1984).
13. J. E. Draley and W. E. Ruther, Aqueous Corrosion of Aluminum, Corrosion 12, 441t (1956).
14. E. Delmonde and M. Pourbaix, The Electrochemical Behavior of Aluminum, Corrosion, 14, 496t-500t (1958).

15. E. W. Baumann, Analysis of Moderator and Thermal Shield Water for Reactor Materials Program, DPST-84-963 (December 20, 1984).
16. E. W. Baumann, Analysis of Aqueous Systems of SRP Reactors by Ion Chromatography for the Reactor Materials Program, DPST-86-282 (February 24, 1986).
17. R. S. Ondrejcin and E. W. Baumann, "An On-line Analyzer for K Reactor (U)", WSRC-TR-90-565 (December 1990), to be issued.
18. R. S. Ondrejcin and G. R. Caskey, Assessment of Susceptibility of Type 304 Stainless Steel to Intergranular Stress Corrosion Cracking in Simulated Savannah River Reactor Environment (U), WSRC-RP-89-1230 (December 1, 1989).
19. R. S. Ondrejcin, G. R. Caskey, P. Aldred and S. A. Wilson, Aqueous Impurity Effects on Stainless Steel IGSCC: A Central Composite Matrix Analysis, Corrosion 89, Paper #505, New Orleans, LA, April 17-21, 1989.
20. G. R. Caskey, R. S. Ondrejcin and K. J. Stoner, Growth of Stress Corrosion Cracks in Type 304 Stainless Steel Under Savannah River Environmental Condition, in preparation.
21. K. J. Stoner, G. R. Caskey, and W. L. Daugherty, Reactor Materials Program - A Derivation of Nominal IGSCC Growth Rate for SRS Reactors (U) WSRC-RP-90-95 (March 1, 1990).
22. E. W. Baumann and R. S. Ondrejcin, Electrochemical Potentials of Stainless Steel and Platinum in K Reactor Moderator, DPST-88-621 (July 6, 1988).
23. L. V. DeWitt, A. Gibbs, D. P. Lambert, S. R. Bohrer, R. L. Fanning, M. W. Houston, S. L. Stinson, R. W. Deible, and S. I. Abdel-Khalik, Moderator Chemistry Program (U), WSRC-TR-90-42-125, in preparation.
24. E. W. Baumann for Reactor Corrosion Mitigation Committee, Guidelines for Corrosion Mitigation During Protracted Reactor Shutdowns (U), WSRC-RP-89-1023 (October 9, 1989).
25. D. P. Lambert to R. P. Taylor, K Reactor Moderator Chemistry Limits, OPS-RTD-0283 (October 18, 1989).
26. G. R. Caskey, K. E. Kehr, M. H. Hilker, D. E. Rahl and R. F. Mittelberg, Leak History, Reactor Primary Coolant Systems (U), WSRC-RP-89-126 (April 21, 1989).
27. G. D. Levi, Jr., Trace Anion Improvements, ESH-AL-901071 (July 2, 1990).
28. E. W. Baumann, Reactions of Hydrogen Peroxide and Ion Exchange Resins, DP-477 (April 1960).
29. 105-Building Technical Standards DPSTS-105-2.7 (April 1, 1975).

TABLE 1
PRINCIPAL DISSOLVED CONSTITUENTS IN MODERATOR

<u>Solute</u>	<u>Source</u>	<u>Sink</u>	Concentration, _____ppb ^a _____
Oxygen (O ₂)	Added Reaction of D ₂ O ₂ and deionizer resin	Reaction with D ₂ Reaction with organics	500-2000
Peroxide (D ₂ O ₂)	Radiolysis of D ₂ O	Reaction with deionizer resin ²⁸	500-2000
Deuterium (D ₂)	Corrosion of Al Radiolysis of D ₂ O	Reduction of nitrate Reaction with oxygen Escape into blanket gas	900 (estimate)
Nitric Acid (DNO ₃)	Added for pD control	Reduction by D ₂ Reduction by organics Removal by deionizers	600
Carbon Dioxide (CO ₂)	Oxidation of organics by O ₂ , D ₂ O ₂ or NO ₃ ⁻	Removal by deionizers Escape into blanket gas	200-400
Sulfate (SO ₄ ²⁻)	Cation exchange resin degradation	Removal by deionizers	50
Chloride (Cl ⁻)	Ubiquitous Anion exchange resin	Removal by deionizers	10
Organics (C)	Degradation of deionizer resins	Oxidation by O ₂ or D ₂ O ₂	not determined

^a ppb = parts per billion (micrograms per liter)

TABLE 2

DISSOLVED CONSTITUENTS IN THERMAL SHIELD WATER^{15,16}
[OBSERVED RANGE IN PLKC REACTORS]

<u>Ion</u>	<u>Concentration Range, ppb^a</u>
Chloride (Cl^-)	20-250
Nitrate (NO_3^-)	<50-3100
Nitrite (NO_2^-)	<10-40
Sulfate (SO_4^{2-})	230-1850
Sodium (Na^+)	<10-1600
Potassium (K^+)	<10-230
Ammonium (NH_4^+)	<10
Peroxide (D_2O_2)	<500-3000

^appb = parts per billion (micrograms per liter)

TABLE 3

TASKS OF THE REACTOR MATERIALS PROGRAM

<u>Task #</u>	<u>Task Title</u>
1	Measure Mechanical Properties of Moderator Piping
2	Irradiate Specimens for Corrosion and Mechanical Property Tests - UBR and HFIR
3	Measure Mechanical Properties of Irradiated Stainless Steel
4	Calculate Stresses in Reactor Tanks Including Seismic Loadings
5	Assess Structural Safety Margin for Reactor Tanks and Moderator Piping
6*	Analyze Impurities in All K-Reactor Aqueous Streams with On-line Analyzer
7*	Measure Effect of Moderator Chemistry on Stress Corrosion of Sensitized and of Irradiated Stainless Steel
8	Qualify Weld Repair Methods for Reactor Tanks and Moderator Piping
9	Establish Surveillance Program to Monitor Irradiation Effects on Wall of K-Reactor
10*	Measure Moderator Electrochemical Potential
11	Inspect Reactor Moderator Piping and Tanks

* Related to corrosion and coolant chemistry.

TABLE 4
CONCENTRATION RANGES OF INDEPENDENT VARIABLES*

<u>Variable</u>	<u>Range</u>
Temperature, °C	40-120
Chloride, ppb	2-100
Sulfate, ppb	7-500
Carbon Dioxide, ppb	20-1000
Hydrogen Peroxide, ppb	400-5000
Oxygen, ppb (either added or from peroxide decomposition)	100-8000

*Nitric acid added to maintain pH at 5.1 ± 0.2 ; light water was used as a stand-in for heavy water.

TABLE 5
EVALUATION OF MODERATOR AND SHIELD WATER CONDITIONS FROM
CERT TESTS

	<u>Moderator</u>			<u>Shield Water</u>		
	Nomi- nal	Lower Temp.	Recom- mended	Nomi- nal	Lower Temp.	<u>Recommended</u> Impurity Level
Chloride, ppb	10	10	2	100	100	5
Sulfate, ppb	25	25	7	300	300	7
Temp., °C	100	60	100	70	45	70
ATMS*, hours	70	250	280	100	360	300

$$\begin{aligned}
 * \text{Log ATMS} = & 4.993 - 0.03646(T) - 0.1553(\text{Cl}^-)^{0.43815} - 1.799(\text{SO}_4^{-2})^{-0.18508} \\
 & + 0.04071(T)[(\text{SO}_4^{-2})^{-0.18508}] - 0.3285[(\text{Cl}^-)^{0.43815}][(\text{SO}_4^{-2})^{-0.18508}] \\
 & + 0.02149 [(\text{Cl}^-)^{0.43815}]^2
 \end{aligned}$$

where Cl^- and SO_4^{-2} are in ppb and T is temperature in °C.

TABLE 6
SYNTHETIC MODERATOR ENVIRONMENTS FOR CRACK GROWTH TESTS

Designation	Concentration, ppb	
	Chloride	Sulfate
Low	2	10
Nominal	30	50
High	100	500
Improved	5	10

Note: Nitric acid was maintained to control pH at 5.1 ± 0.2 ; Carbon dioxide was held at 300 ppb. The oxygen from peroxide decomposition varied from 600-1600 ppb depending on the degree of decomposition. Light water was used as a stand-in for heavy water.

TABLE 7
TECHNICAL STANDARDS AND OPERATING LIMITS

Analysis	Moderator (D ₂ O) Tech. Standard ²⁹	Moderator (D ₂ O) Operating Limit ⁹	Shield Water (H ₂ O) Operating Limit ⁹
pD	4.5-8.0	5.0-5.2	
pH _{measured} ^a	4.1-7.6(7.2) ^b	4.6-4.8 (4.6-5.6) ^c	5-8
Conductivity, μS/cm at 25°C	<3.5; 3.5-5.1 for one day maximum ^d	1.9-3.0 (0.3-3.0) ^c	<20
Turbidity, ppm	---	<0.5	<10
Nitrate, ppb	---	500-630 ^c	---
Nitrite, ppb	---	<30	---
Chloride, ppb	---	<30	<500
Sulfate, ppb	---	<50	---
Oxalate, ppb	---	<50	---
Peroxide, ppb	---	<1000	---
Make-up D ₂ O	10 ppb Hg; <50 ppb Ag, Au, Cu <100 ppb Cl ⁻		

a $pD = pH_{\text{measured}} + 0.4$

b Recommended reduction to 7.2 to reduce precipitation of gadolinium hydroxide onto reactor surfaces after SSS injection.²³

c during layup²⁵; nitrate limits would also be changed.

d during reactor operation

TABLE 8
SAMPLING FREQUENCIES⁹

	MODERATOR		
	From RX to Purification	From Purifi- cation to RX	Shield Water
ANALYSIS			
Turbidity	3/week	2/week	1/week
Alpha	3/week	2/week	---
2-hr Beta-Gamma	3/week	2/week	1/month
Conductivity	1/week	1/week	1/week
pH	1/week	1/week	1/week
Nitrate	1/week	1/week	---
Nitrite	1/week	1/week	---
Chloride	1/week	1/week	---
Sulfate (new)	1/week	1/week	---
Oxalate (new)	1/week	---	1/week
Peroxide	1/week	4/week	---
Radionuclides	1/week	---	---
Tritium	2/month	---	---
Radionuclides	1/week	---	---
Metal Content	4/year	---	---
S-35, P-32	as required	---	---
Na-24, Cr-51, Co-60		---	4/year

M90oct021.01

Figure 1. 105-K Reactor Complex

**DATE
FILMED
9/01/92**