DOE/PC/91310--T2

DE92 015628

USE OF SOLID-STATE NMR TECHNIQUES FOR THE ANALYSIS OF
WATER IN COAL AND THE EFFECT OF DIFFERENT COAL DRYING
TECHNIQUES ON THE STRUCTURE AND REACTIVITY OF COAL

by
Daniel A. Netzel

Quarterly Report: December 1, 1991 - February 29, 1992

Work Performed Under Grant Agreement
DE-FG22-91PC91310

For
U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236-0940

By
University of Wyoming Research Corporation
a.k.a. Western Research Institute
Laramie, Wyoming

U.S. DOE Patent Clearance is Not Required Prior to the Publication of
This Document

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

JUN 17 1992

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION.....	1
OBJECTIVES.....	4
EXPERIMENTAL.....	5
RESULTS AND DISCUSSION.....	7
CONCLUSIONS AND FUTURE WORK.....	9
REFERENCES.....	10

INTRODUCTION

One area for improvement in the economics of coal liquefaction is coal drying, particularly for the lower rank coals. However, there is considerable evidence to show that drying has a detrimental effect on the liquefaction behavior of coals. Regarding the liquefaction of coal, there does not appear to have been any systematic study of the methods of coal drying on coal structure and the role water plays in enhancing or lessening coal reactivity toward liquefaction. In part, this may have been the result of not having the techniques that are now available, such as solid-state NMR.

There are many economical advantages to drying coal prior to liquefaction. Direct liquefaction conversion and kinetics are heavily dependent upon the partial pressure of hydrogen in the liquefaction reactor; thus, the removal of moisture in the coal allows the partial pressure of hydrogen to be increased without increasing the operating pressure. In addition, removal of most of the water from the coal prior to liquefaction reduces the cost of shipping coal to the liquefaction reactor. Finally, moisture in the coal reduces the throughput of coal on a dry basis if the liquefaction reactor has a fixed capacity.

The problem associated with drying coal is that removing the moisture prior to liquefaction reduces the reactivity of coal to liquefaction, and hence, the amount of coal converted to liquid during the liquefaction process is reduced. Therefore, to derive economic benefits from coal drying, the causes of the lower reactivity of dried

coals must be understood, or other methods of drying must be developed that circumvent this problem.

With the solid-state nuclear magnetic resonance (NMR) techniques of combined rotation and multiple pulse spectroscopy (CRAMPS) and cross polarization with magic-angle spinning (CP/MAS), studies of chemical structural changes that may occur in coals as a result of drying are feasible. These solid-state NMR techniques can be extremely useful for determining structural changes induced by drying by different methods and for determining the extent of condensation/retrograde reactions that may occur during drying. In particular, we need to know the chemical environment in which water exists in the coal structure. However, before any changes in coal structure can be evaluated, an appropriate method for determining the amount of water in coal at room temperature must be developed.

Several methods have been developed recently to determine the moisture content of coals (Wroblewski et al. 1991; Robertson et al. 1979; Cutmore et al. 1986; Graebert and Michel 1990). Finseth (1987) discussed the need for accurate moisture determinations in coal. In that study, Finseth employed isotopic dilution to study the exchange of oxygen in moisture equilibration experiments. His results showed higher moisture levels obtained by isotopic dilution than by the standard ASTM method for the Argonne Premium coal samples as well as for two coals that were not as well prepared as the Premium coals. The results suggest that the classic thermal drying method may not yield true moisture values for coals.

Also, thermal methods of drying alter the physical structure of coal as well as promote undesirable chemical reactions. Low-temperature drying of coal, on the other hand, should preserve the structural integrity, reduce retrograde reactions, reduce thermal degradation, and provide information on nonbonded, chemisorbed, and physisorbed water. Therefore, there is a need for developing a more accurate method not only to determine the moisture content of coal, but to understand the role of water in retrograde reactions and liquefaction

The use of the dehydration agent 2,2-dimethoxypropane to dry coal is a novel and innovative approach to understand the role of water in coal chemistry and to determine the moisture content in coal. This method of dehydrating coal should provide a baseline for studying initial stages of retrograde/condensation reactions. That is, decarboxylation and low-temperature oxidation reactions can then be studied in the presence and absence of water and gases and as a function of temperature. 2,2-Dimethoxypropane has been used in inorganic chemistry to remove water of hydration in inorganic compounds (Donoghue and Drago 1962) and in biological sciences for drying tissues for microscopic examination (Adams 1974; Muller and Jacks 1975). The reaction of 2,2-dimethoxypropane with water is shown in scheme I.

Scheme I

This reaction is rapid and endothermic. The excess reagent and reaction products, methanol and acetone, are easily removed by vacuum at ambient temperature. Removing water by chemical means rather than by physically forcing exchange by mass action preserves the ultrastructural integrity of the coal components. It should also be possible to measure the water content remaining in coals that have been partially dried (thermally or microwave methods) by reacting the water remaining in the coal with 2,2-dimethoxypropane and measuring the methanol or acetone content.

The ^1H NMR of the reaction products, methanol and acetone, give single resonances for the methyl hydrogens, which are easily identified. These resonances do not overlap the hydrogen NMR resonances of 2,2-dimethoxypropane. Integration of the methyl hydrogens resonances from methanol and/or acetone is a direct measure of the moles of water reacted.

OBJECTIVES

The overall objectives of this study are to develop an NMR method for measuring the water in coal, to measure the changes in coal structure that occur during coal drying, to determine what effect water has on retrograde/condensation reactions, and to determine the mechanism by which water may enhance coal reactivity toward liquefaction. Different methods of drying will be investigated to determine if drying can be accomplished without destroying coal reactivity toward

liquefaction, thereby making coal drying an attractive and economical method for coal pretreatment. Coal drying methods will include thermal drying under different atmospheres and temperatures, drying with microwave radiation, and low-temperature chemical dehydration.

The objectives for this quarterly report period were (1) to determine the limit of detection of water by NMR, (2) to determine the reproducibility of the NMR integration method using the Lab CalTM PC software, (3) to determine the amount of water in standard solutions, and (4) to determine the amount of water in a coal sample.

EXPERIMENTAL

Instrument

Hydrogen-1 NMR spectra were obtained on a JEOL GSX-270 NMR spectrometer. The experimental conditions for recording a ¹H spectrum were eight scans, a pulse width of 5.4 μ s (45°), an acquisition time of 1.5 s, a pulse delay of 20 s, and 16K time-domain data points. Spectral integrations were performed on a Gateway 2000 PC using Lab CalTM software developed by Galactic Industries Corporation.

The impurities in the reagents were determined using an HP 5890 gas chromatograph with a flame ionization detector and a 30-meter DB-5 (0.53 mm) column.

Reagents

Analytical reagent grade anhydrous magnesium sulfate from Mallinckrodt was used to dry the various reagents. 2,2-Dimethoxypropane (98%) from Aldrich Chemicals was used as received except for drying with anhydrous magnesium sulfate. Gas chromatographic analysis indicated the purity to be 99% with three impurities components of 0.16, 0.45, and 0.38 relative percent. The NMR spectrum of the reagent showed a small acetone peak. 1,4-Dioxane, HPLC grade, from Aldrich Chemicals was dried with anhydrous magnesium sulfate and used to prepare a standard solution of water in dioxane. A 0.08 N solution of methanesulfonic acid in nitromethane was prepared using methanesulfonic acid (99%) from Aldrich Chemicals and spectra grade nitromethane from Eastman Organic Chemicals. Cycloheptane (>97%), used as the analytical hydrogen standard, was obtained from Fluka AG, Chemische Fabrik. Gas chromatographic analysis indicated the purity to be 97.36% with three impurities components of 1.27, 0.67, and 0.69 relative percent. All calculations of the hydrogen content were corrected for the percent purity. Type I distilled water was used to make the standard solutions of water in dioxane.

Procedure

All reagents were accurately weighed into a centrifuge tube (to be used later for moisture determination in coal). To 1.0 g of dioxane, various amounts of water (0.0, 0.01, 0.1, 0.3, and 0.5 g) were added along with 3.5 g of 2,2-dimethoxypropane and 0.8 g of cycloheptane. To each solution, 3.4 g of 0.08 N methanesulfonic acid in nitromethane was

added and the reaction allowed to proceed for 10 minutes. An aliquot (0.75 mL) was taken and diluted with deuterated chloroform. This solution was then transferred to an NMR tube and the ^1H spectrum recorded.

The integrated values of cycloheptane and acetone resonances at 1.5 and 2.2 ppm, respectively, relative to TMS were used to determine the grams of water in the standard water samples.

RESULTS AND DISCUSSION

In the presence of a strong acid, the reaction of 2,2-dimethoxypropane with water to form the theoretical amount of acetone is practically instantaneous. Table 1 shows the weighed amount of water added to dioxane, the amount of water in the standard solutions as determined by NMR, and percent recovery. It appears that, as the water content increases, the percent recovery decreases. This trend was also noted by Critchfield and Bishop (1961). It may be that the reaction time may not be instantaneous as presupposed. Additional experiments are planned to determine the reason for the decrease in recovery for high concentrations of water.

Table 1. Determination of Water in Standard Solution of Water in Dioxane by ^1H NMR

<u>Water, grams</u>		<u>Recovery Percent</u>
<u>Added</u>	<u>Found</u>	
0.0000	0.0126	
0.0098	0.0099*	101
0.0993	0.0926*	93
0.3395	0.3070*	90
0.5626	0.5001*	89

*Samples corrected for blank.

Also noted in Table 1 is the fact that the blank experiment resulted in an appreciable amount of water. Quantification of the acetone in 2,2-dimethoxypropane by NMR integration gives an acetone content of 0.352% which is in agreement with one of the minor impurities peaks by gas chromatography (0.38%). This amount of acetone is equivalent to 0.109% water. Based on the total weight of the blank solution, the grams of water in the blank is equivalent to 0.149%. Thus, the small amount of acetone in 2,2-dimethoxypropane accounts for most of the water in the blank (73%). Other sources of moisture may be due to the atmospheric transfer of reagents or residual moisture in the various reagents. The limit of detection for water in any given sample is estimated to be less than 0.1% based on the detection of the small amount of acetone in 2,2-dimethoxypropane.

Reproducibility of the NMR integration was found to be 0.3% based on three separate Fourier transforms, rephasings, and integrations of a given NMR FID spectrum.

Preliminary experiments were conducted to determine the amount of water in Eagle Butte subbituminous coal using the ^1H NMR method. For two separate experiments, the amount of water was found to be 17.92 and 19.79% uncorrected, resulting in an average of 18.85%. Thermal drying of the coal at 110°C for one hour yielded a moisture content of 18.1%. The spread in the moisture content as determined by NMR precludes any discussion of the total water content relative to the water content of the thermally dried coal.

CONCLUSIONS AND FUTURE WORK

The studies performed this last quarter have shown that the ^1H NMR method for determining water in a coal sample via the reaction with 2,2-dimethoxypropane will be suitable for determining the water content in coals. The method should be most suitable for coals having low moisture content; that is, those coals which have been subjected to other drying techniques.

Future development on the methodology will be to determine the cause of the decrease in percent recovery of water with increasing water concentrations and to improve the accuracy of the water determination. In addition, the suite of Argonne Premium coals for which the moisture content is known will be subjected to chemical dehydration and the moisture content determined by ^1H NMR.

REFERENCES

- Adams, R.F., 1974, Determination of Amino Acid Profiles in Biological Samples by Gas Chromatography. J. of Chrom., 95: 189-212.
- Critchfield, F.E., and E.T. Bishop, 1961, Water Determination by Reaction with 2,2-Dimethoxypropane. Anal. Chem., 33: 1034-1033.
- Cutmore, N.G., B.D. Sowerby, L.J. Lynch, and D.S. Webster, 1986, Determination of Moisture in Black Coal Using Pulsed Nuclear Magnetic Resonance Spectrometry. Fuel, 58: 770-774.
- Donoghue, J.T., and R.S. Drago, 1962, Non-Aqueous Coordination Phenomena--Complexes of Hexamethylphosphoramide. I. Preparation and Properties of Tetrahedral $[\text{Zn}(\text{PO}[\text{N}(\text{CH}_3)_2]_3)_4]^{+2}$, $[\text{Co}(\text{PO}[\text{N}(\text{CH}_3)_2]_3)_4]^{+2}$, and $[\text{Ni}(\text{PO}[\text{N}(\text{CH}_3)_2]_3)_4]^{+2}$ Compounds. Inorg. Chem., 1: 866-872.
- Finseth, D., 1987, An Isotope Dilution Study of Exchangeable Oxygen in Premium Coal Samples. ACS Div. of Fuel Chem. Preprints, 32(4): 260-265.
- Graebert, R., and D. Michel, 1990, Determination of Water in Coals by Means of Proton Spin Relaxation Measurements. Fuel, 69: 826-829.
- Muller, L.L., and T.J. Jacks, 1975, Rapid Chemical Dehydration of Samples for Electron Microscopic Examinations. J. of Histochemistry and Cytochemistry, 23: 107-110.
- Robertson, S.D., F. Cunliffe, C.S. Fowler, and I.J. Richmond, 1979, Rapid Measure of Moisture in Coal and Total Solids in Coal Slurries by Low-Resolution Proton Nuclear Magnetic Resonance. Fuel, 58: 770-774.
- Wroblewski, A.E., K. Reinartz, and J.G. Verkade, 1991, Moisture Determination of Argonne Premium Coal Extracts by ^{31}P NMR Spectroscopy. Energy and Fuels, 5: 786-791.

**DATE
FILMED**

9/04/92