Coal Liquefaction Process Streams Characterization and Evaluation

FT-IR Methods for Characterization of Coal Liquefaction Products

Topical Report

Prepared by:

Advanced Fuel Research, Inc.
87 Church Street
East Hartford, CT 06108

Michael A. Serio
Hsisheng Teng
Rosemary Bassilakis
Peter R. Solomon

Prepared for:

CONSOL Inc.
Research & Development
4000 Brownsville Road
Liberty, PA 15129

F. P. Burke
R. A. Winschel
S. D. Brandes

April 1992

Under Contract to:

United States Department of Energy
Contract No. DE-AC22-89PC89883

U.S. DOE Patent Clearance was provided by
Chicago Operations Office on 3/26/92.

PROJECT ASSESSMENT

Introduction

Under subcontract to Consolidation Coal Co. (U.S. DOE Contract No. DE-AC22-89PC89883), Advanced Fuel Research studied the use of quantitative Fourier-transform infrared (FTIR) spectroscopy and thermogravimetric (TG)-FTIR for the analysis of coal-derived materials in support of direct coal liquefaction process development. Additionally, AFR assessed the feasibility of applying FTIR on-line in a liquefaction plant. In the application of quantitative FTIR, functional group concentrations are determined through the use of curve-resolving techniques. The TG-FTIR method continuously monitors the pyrolysis of the samples by analyzing the time-dependent evolution of the volatile portion of the sample and the combustion products of the non-volatile portion. The full report authored by the AFR researchers is presented here. The following assessment briefly highlights the major findings of the project, and provides CONSOL's evaluation of the potential of the methods for application to direct coal liquefaction process development. These results will be incorporated by CONSOL into a general overview of the application of novel analytical techniques to coal-derived materials.

Summary

This study was designed to demonstrate the use of two FTIR techniques for the analysis of direct coal liquefaction process-derived materials. The two methods were quantitative FTIR analysis and thermogravimetric (TG) analysis with FTIR analysis of evolved products (TG-FTIR).

The quantitative FTIR analyses of both whole resids and THF-soluble resids provided quantitation of total hydrogen, aliphatic and aromatic hydrogen, total carbon, total oxygen, hydroxyl and etheric oxygen, and ash contents. The FTIR results were usually in agreement with values derived by other, more conventional methods. However, the accuracies of specific measurements, in comparisons with results from conventional methods, ranged from good to poor.

The TG-FTIR method provided proximate analyses of coals and resids. The data provided included the time dependent evolution profiles of the

volatile species and the elemental composition of the char. Reproducible data of gaseous species and pyrolysis tar yields for whole resid samples larger than 10 mg were obtainable. The yields and evolution profiles of certain volatiles (tar, CO, and methane) provided structural information on the samples.

There were some experimental and interpretational difficulties associated with both techniques. Optimization of the curve-resolving routine for coal-liquefaction samples would improve the quantitative FTIR accuracy. Aerosol formation limited the full application of the TG-FTIR technique with the THF-soluble resid samples. At this time, further development of these analytical methods as process development tools will be required before their use for that purpose can be recommended. The use of FTIR as an on-line analytical technique for coal liquefaction process streams requires demonstration before it can be recommended; however, such a demonstration may be warranted.

Program Description

This report describes the work performed by Advanced Fuel Research (AFR) under a subcontract to CONSOL Inc., Research and Development. CONSOL's prime contract to the U.S. Department of Energy (Contract No. DE-AC22-89PC89883, "Coal Liquefaction Process Streams Characterization and Evaluation") established a program for the analysis of direct coal liquefaction derived materials. The program involves a number of participating organizations whose analytical expertise is being applied to these materials. This Participants Program has two main objectives. The broad objective is to improve our understanding of fundamental coal liquefaction chemistry to facilitate process improvement and new process development. The specific approach to achieving this objective is to provide a bridge between direct coal liquefaction process development and analytical chemistry by demonstrating the application of various advanced analytical methods to coal liquefaction materials. The methodologies (or techniques) of interest are those which are novel in their application for the support of coal liquefaction and those which have not been fully demonstrated in this application. CONSOL is providing well-documented samples from different direct coal liquefaction development facilities to the program participants. The participants are required to interpret

their analytical data in the context of the processing conditions under which the samples were generated. The methodology employed is then evaluated for its usefulness in analyzing direct coal liquefaction derived materials.

Participant's Methodology

AFR applied quantitative FTIR analysis using KBr pellets to nine whole coal liquefaction distillation resids (850°F+) and the corresponding tetrahydrofuran (THF)-soluble portions of those distillation resids. They also analyzed a whole process oil and four (solids-free) pressure-filter liquids. TG-FTIR analysis was performed on the same nine whole resids and THF-soluble resids that were analyzed by quantitative FTIR and also on three feed coals. A task summary is given in the work plan presented below.

The samples were produced at two different continuous liquefaction facilities: the Wilsonville pilot plant and the Hydrocarbon Research Inc. (HRI) bench unit. The major processing parameters which varied among the Wilsonville runs included feed coal and catalyst, though there were numerous other differences as well. Samples from Wilsonville were taken from three different locations in the plant. These samples are expected to represent different extents of coal liquefaction. The Wilsonville samples, with the exception of the single whole oil sample, were composites of samples taken over long periods of single runs. The whole oil sample was obtained from a single run day. The HRI samples were chosen to represent production of material as the catalyst was batch-aged during one liquefaction run. The experimental procedures used in AFR's work are described on pages 12-15 of the attached report.

Participant's Major Findings

The following principal observations for the application of quantitative FTIR and TG-FTIR to coal liquefaction materials were reported by AFR. An expanded discussion can be found in the attached report, pages 16-26.

Generally, it was shown that numerous sample properties could be determined by the quantitative FTIR method. The properties determined included total hydrogen content, aromatic and aliphatic hydrogen

distribution, total carbon content, total oxygen content, hydroxyl group concentration, and ash content. Comparisons of the values obtained by quantitative FTIR to those obtained by conventional methods (such as NMR and elemental analysis) show that the FTIR method provides values which are consistent with the trends observed by other methods. However, the accuracy of the FTIR method, determined by comparison with results from other methods, is good in some cases and poor in others. For specific properties, the values obtained from FTIR averaged 77% to 130% of the values obtained by conventional methods. The inaccuracies are in some cases attributable to sample preparation; in other cases, the limitations are apparently inherent in the FTIR method. This is especially notable in the case of the mineral matter analyses. FTIR is unable to discern iron sulfides, a major component of the mineral matter.

Processing trends observable by the FTIR analysis included the increase in total hydrogen content and the decrease in hydroxyl and aromatic hydrogen contents across the second reactor of the Wilsonville plant, consistent with the upgrading of the coal liquid across that reactor. The expected decrease in product quality (higher aromaticity, oxygen functional group content, and carbon content) with catalyst age was observed with samples obtained during a catalyst aging study at the HRI bench unit.

The TG-FTIR method is divided into two steps; the pyrolysis of the sample under inert atmosphere and the combustion of the residual char in oxygen. In both steps, the evolved volatile species are monitored and analyzed by FTIR. Data obtained by TG-FTIR were compared to conventional analyses to ascertain the quality of the TG-FTIR method. Application of the method to coal proximate analyses yielded good agreement with conventional methods. The temperature range of the tar evolution peak is indicative of the boiling range of the material. This range for the resid samples was the same regardless of feed coal or sampling point in the liquefaction process; however, in all cases, the range was lower for resids than for the respective feed coals. The pyrolysis char yield correlated well with the fraction of condensed aromatic protons, as determined by other methods. The evolution of oxygen-containing gases (CO , CO_2 , and H_2O) is used to determine the relative amount of total

oxygen in the sample. However, CO and CO₂ can be evolved from both organic oxygen groups and mineral carbonates. The evolution profile of the oxygen-containing gases can be used to partially resolve the contributions from organic functional groups and minerals. The total amounts of CO and methane evolved followed the same trend with sample type as char yield and hydroxyl concentration; i.e., coal >> interstage > second stage > recycle. The resids not only evolved less CO than the feed coals, they also evolved it at much higher temperatures. This reflects the removal of loosely-bound CO during liquefaction. The methane evolution temperature varied little with sample type. This suggests that liquefaction changes the total amount but not the distribution of methyl groups. Char and tar yields, and to a lesser extent gas evolution profiles, from the resids were found to depend upon the feed coal (or specific Wilsonville run) from which the sample was derived.

The use of FTIR as an on-line method is discussed in the attached report (pages 32-37). Two recent technological developments are described: 1. new infrared-transmitting optical fibers and 2. rugged low-cost FTIR spectrometers. These two factors make on-line analysis by FTIR in direct coal liquefaction process streams feasible. There are, however, trade-offs in usable frequency range with fibers that are able to withstand high temperatures. Alternative near-line systems are currently commercially available and could be used for this application.

Consol Evaluation

The quantitative FTIR technique can provide a number of sample properties from a single analysis normally obtained by multiple analytical techniques. This could make the method very useful as a process development tool. However, data quality, when compared to the values obtained by the other methods, is not consistently good. For example, up to 4% ash was determined by FTIR in ash-free THF-soluble samples. It is expected that optimization of the curve-resolving data analysis method would improve the data quality. Some of the data obtained from the gas evolution profiles from the TG-FTIR analysis of the resids are not quantitative because 1) the instrument has not yet been calibrated for NH₃, COS, and CS₂; 2) CS₂ evolution mimics H₂O and can be confused with it; and 3) SO₂

evolution is found in two peaks, one the result of small traces of oxygen in the helium carrier gas. Apparently, only the CH_4 , CO_2 , CO , and H_2O evolution peaks were reported with quantitative reliability. However, it should be noted that the CO_2 measurement is sensitive to the state of oxidation of the sample. Interpretation of the CO_2 data is, therefore, more difficult. In addition to these experimental difficulties for the whole resid samples, reliable tar evolution peaks could not be obtained for the THF-soluble resid samples because of aerosol formation. The TG-FTIR technique, if fully optimized, could be able to provide structural information of the samples by first monitoring the evolution of the volatile species from pyrolysis and then the combustion gases from the char.

Commercially available FTIR equipment ranges in price from approximately \$20,000 to \$250,000. The TG-FTIR equipment, also commercially available, increases the cost of the FTIR instrument by about \$25,000. Consumables for the analyses, as performed under this subcontract, are on the order of \$10/sample. It requires less than one hour per sample to prepare and run a single sample by the quantitative FTIR method. The TG-FTIR analysis performed in these experiments requires approximately three hours per sample to complete.

The utility of the FTIR as an on-line analytical technique requires demonstration with process samples at approximate operating conditions before it can be recommended for process application.

Further Development

There are a number of avenues for further development of the techniques described here. Optimization of the curve fitting technique for direct coal liquefaction process samples would improve the accuracy and, therefore, the utility of the quantitative FTIR method for process development. More extensive statistical evaluations of the FTIR data would contribute to this utility. A study with the TG-FTIR technique of the CO and CO_2 evolution profiles of coal resid samples to establish the origin of the gases (organic or inorganic) should be done. A demonstration of FTIR in an on-line application should be made to test

the recent advances in the technology discussed in the attached report (pages 32-37).

Contractor's Statement of Work

Fourier Transform Infrared (FTIR) spectroscopy can be used to provide organic structural information for coals, lignins, and products of thermal decomposition, and to yield quantitative information on the concentrations of hydroxyl, aliphatic and aromatic hydrogen and aromatic carbon present in a sample. Thermogravimetric FTIR (TG-FTIR) can be applied to the analysis of solid (but volatile) material. On-line FT-IR Monitoring (utilizing both an ATR cell and a fixed path-length transmission cell) has been used to couple the information as described above with real-time events. The application of these techniques to coal liquefaction process streams and solid or solid-containing heavy materials from coal liquefaction process streams has not been demonstrated and, as such, these techniques are novel and fit within the scope of the participants program.

Consol will supply AFR with twenty-six separate samples. The twenty-six samples (three coals, nine distillation resids, thirteen solids-free distillation resids, and one whole process oil) will be supplied to AFR with the following information, as appropriate: elemental analyses, ash content, ash elemental analysis, phenolic -OH concentration, calorific value, hydrogen classes by $^1\text{H-NMR}$, and the full history of the sample (plant, process conditions, age, and storage conditions). Resid sample size will be at least 30 mg. Most resid samples will be brittle pitch-like materials that will be supplied as approximately minus 8 mesh (2.4 mm) pieces.

In order to fully evaluate the usefulness of the FTIR methods for coal liquefaction process development the following tests (totaling 45 in number) will be made using the twenty-six samples described above.

1. Quantitative IR analysis of nine whole resid materials produced by distillation of the process oils generated from three different feed coals and obtained from three different sampling points during coal liquefaction runs at the Wilsonville facility.

2. Quantitative IR analysis of the tetrahydrofuran (THF) soluble portion of the same nine resid materials.
3. Quantitative IR analysis of four solids-free resids obtained during a catalyst aging study at the HRI facility.
4. Quantitative IR analysis of a whole process oil sample obtained from the Wilsonville facility.
5. TG-FTIR analysis of three feed coals.
6. TG-FTIR analysis of the same nine whole resid materials as described above.
7. TG-FTIR analysis of the THF soluble portion of the same nine resid materials.
8. On-line test: Evaluation of the data obtained by analysis of a whole process oil will determine if an on-line test is feasible.

The functional groups (e.g., aliphatic, aromatic, and hydroxyl hydrogen, and O-C bonds) in each sample, which will be analyzed by quantitative FTIR, will be measured by curve-fitting techniques. The TG-FTIR technique will provide information on the time-dependent evolution of individual volatile species, weight of the non-volatile portion, and an analysis of C, H, and S in the non-volatile portion (by burning the residue and analyzing the combustion products).

Replicate analyses will be performed as appropriate to define precision.

**ADVANCED
FUEL
RESEARCH**

P.O. Box 380379
East Hartford, Connecticut 06138-0379
Telephone (203) 528-9806

COAL LIQUEFACTION PROCESS STREAMS CHARACTERIZATION AND EVALUATION:

FT-IR Methods for Characterization of Coal Liquefaction Products

Topical Report

Prepared by:

ADVANCED FUEL RESEARCH, INC.
87 Church Street
East Hartford, CT 06108

Michael A. Serio
Hsisheng Teng
Rosemary Bassilakis
and
Peter R. Solomon

Prepared for:

CONSOLIDATION COAL COMPANY
Research and Development
4000 Brownsville Road
Library, PA 15129

January 1992

TABLE OF CONTENTS

LIST OF FIGURES	iii
LIST OF TABLES	vii
1. EXECUTIVE SUMMARY	1
2. BACKGROUND	9
2.1 Introduction	9
2.2 FT-IR Analysis	10
2.3 TG-FTIR Analysis	11
3. OBJECTIVES	11
4. RESULTS	12
4.1 Description of Experimental Methods	12
4.2 Summary of FT-IR Results	16
4.3 Summary of TG-FTIR Results	20
4.4 Interpretation of Data in the Context of the Liquefaction Processes	26
4.5 Feasibility of On-Line Analysis	32
5. CONCLUSIONS AND RECOMMENDATIONS	37
6. ACKNOWLEDGEMENTS	38
7. REFERENCES	38
8. FIGURES	42
9. APPENDICES	
A. Summary of Samples Analyzed	61
B. Table of Analytical Data	63
C. FT-IR Spectra	87
D. TG-FTIR Plots	100

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
4.1-1. FT-IR Spectrum of THF Soluble Portion of Recycle Oil Resid from Wyodak Coal, Wilsonville, Run 251-III (sample #2) Showing Regions Used for Quantitative FT-IR Analysis.	43
4.1-2. Correction of Resid Spectrum for Scattering and Minerals.	44
4.1-3. TG-FTIR Results for Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #5).	45
4.1-4. TG-FTIR Post Combustion Results for Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #5).	46
4.1-5. Spectrum from TG-FTIR During Pyrolysis of Recycle Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #8).	47
4.2-1. Comparison of Aromatic Hydrogen Distributions.	48
4.2-2. Comparison of Aliphatic Hydrogen Distributions.	48
4.2-3. Comparison of Hydroxyl Content.	49
4.2-4. Comparison of Oxygen Contents.	49
4.2-5. Comparison of Hydrogen Contents.	50
4.2-6. Comparison of Carbon Contents.	50
4.2-7. Comparison of Ash Contents.	51
4.2-8. Comparison of CaO Contents.	51
4.3-1. Comparison of Char Yield with Fixed Carbon.	52
4.3-2. Comparison of Coal Ash Contents.	52
4.3-3. Comparison of Volatile Contents in Coal.	53
4.3-4. Comparison of Moisture Contents in Coal.	53
4.3-5. Comparison of Ash Contents for Resids.	54
4.3-6. Comparison of Char Yield with Condensed Aromatic Proton Fraction.	54
4.4-1. Phenolic-OH Content at Different Stages for Wilsonville Resids.	55

4.4-2. OH Content at Different Stages for Wilsonville Resids.	55
4.4-3. CO Evolution from Pyrolysis of Wilsonville Resids.	56
4.4-4. CH ₄ Evolution from Pyrolysis of Wilsonville Resids.	56
4.4-5. Hydrogen Content at Different Stages for Wilsonville Resids.	57
4.4-6. Aromatic Hydrogen Fraction at Different Stages for Wilsonville Resids.	57
4.4-7. Aromatic Hydrogen Content at Different Stages for Wilsonville Resids.	58
4.4-8. Efficiency of Deash Process for Wilsonville Resids.	58
4.4-9. Hydrogen Analysis for HRI Liquids.	59
4.4-10. Aromatic Hydrogen Content with Time for HRI Liquids	59
4.4-11. Oxygen Functional Group Analysis for HRI Liquids.	60
4.4-12. Carbon Content with Time for HRI Liquids.	60
C-1. FT-IR Spectrum of Interstage Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #1).	88
C-2. FT-IR Spectrum of Recycle Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #2).	88
C-3. FT-IR Spectrum of Second Stage PO Resid from Wyodak Coal, Wilsonville Run 251-III (sample #3).	89
C-4. FT-IR Spectrum of Interstage Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #4).	89
C-5. FT-IR Spectrum of Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #6).	90
C-6. FT-IR Spectrum of Second Stage PO Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #6).	90
C-7. FT-IR Spectrum of Interstage Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #7).	91
C-8. FT-IR Spectrum of Recycle Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #8).	91
C-9. FT-IR Spectrum of Second Stage PO Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #9).	92

C-10.	FT-IR Spectrum of THF Soluble Portion of Sample #1 (sample #10).	92
C-11.	FT-IR Spectrum of THF Soluble Portion of Sample #2 (sample #11).	93
C-12.	FT-IR Spectrum of THF Soluble Portion of Sample #3 (sample #12).	93
C-13.	FT-IR Spectrum of THF Soluble Portion of Sample #4 (sample #13).	94
C-14.	FT-IR Spectrum of THF Soluble Portion of Sample #5 (sample #14).	94
C-15.	FT-IR Spectrum of THF Soluble Portion of Sample #6 (sample #15).	95
C-16.	FT-IR Spectrum of THF Soluble Portion of Sample #7 (sample #16).	95
C-17.	FT-IR Spectrum of THF Soluble Portion of Sample #8 (sample #17).	96
C-18.	FT-IR Spectrum of THF Soluble Portion of Sample #9 (sample #18).	96
C-19.	FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-2 (sample #19).	97
C-20.	FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-9 (sample #20).	97
C-21.	FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-18 (sample #21).	98
C-22.	FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-25 (sample #22).	98
C-23.	FT-IR Spectrum of Whole Process Oil from Pittsburgh Seam Coal, Wilsonville Run 259E (sample #23).	99
D-1.	TG-FTIR Results for Interstage Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #1).	101
D-2.	TG-FTIR Results for Recycle Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #2).	102
D-3.	TG-FTIR Results for Second Stage PO Resid from Wyodak Coal, Wilsonville Run 251-III (sample #3).	103
D-4.	TG-FTIR Results for Interstage Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #4).	104
D-5.	TG-FTIR Results for Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #5).	105

D-6.	TG-FTIR Results for Second Stage PO Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #6).	106
D-7.	TG-FTIR Results for Interstage Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #7).	107
D-8.	TG-FTIR Results for Recycle Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #8).	108
D-9.	TG-FTIR Results for Second Stage PO Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #9).	109
D-10.	TG-FTIR Results for THF Soluble Portion of Sample #1 (sample #10).	110
D-11.	TG-FTIR Results for THF Soluble Portion of Sample #2 (sample #11).	111
D-12.	TG-FTIR Results for THF Soluble Portion of Sample #3 (sample #12).	112
D-13.	TG-FTIR Results for THF Soluble Portion of Sample #4 (sample #13).	113
D-14.	TG-FTIR Results for THF Soluble Portion of Sample #5 (sample #14).	114
D-15.	TG-FTIR Results for THF Soluble Portion of Sample #6 (sample #15).	115
D-16.	TG-FTIR Results for THF Soluble Portion of Sample #7 (sample #16).	116
D-17.	TG-FTIR Results for THF Soluble Portion of Sample #8 (sample #17).	117
D-18.	TG-FTIR Results for THF Soluble Portion of Sample #9 (sample #18).	118
D-19.	TG-FTIR Results for Illinois No. 6 Coal, -100 Mesh, (sample #24).	119
D-20.	TG-FTIR Results for Illinois No. 6 Coal, -100 Mesh, (sample #24).	120
D-21.	TG-FTIR Results for Pittsburgh Seam Coal, -100 Mesh, (sample #25).	121
D-22.	TG-FTIR Results for Wyodak Coal, -100 Mesh, (sample #26).	122

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1-1 Summary of FT-IR Measurements.	7
1-2 Summary of TG-FTIR Measurements.	8
4.3-1 The Pyrolysis Char Yields (wt%, MAF) of the Whole Resid Samples.	24
4.3-2 The Pyrolysis Tar Yields (wt%, MAF) of the Whole Resid Samples.	24
4.3-3 The Tar Evolution Peak Temperatures of the Whole Resid Samples.	25
4.4-1 Comparison of Properties of Whole Resids and THF Soluble Fractions as Revealed by FT-IR and TG-FTIR Analysis.	30
4.5-1 Characteristics of IR Fiber Materials.	33
4.5-2 Comparison of FT-IR Analysis of a Whole Process Oil and Resid Fraction from Liquefaction of Pittsburgh Seam Coal.	36

1. EXECUTIVE SUMMARY

Introduction

The objective of this work was to evaluate the use of two Fourier Transform Infrared (FT-IR) methods for characterization of products from coal liquefaction process streams. The first method is quantitative FT-IR analysis of samples pressed into KBr pellets. The functional group concentrations (e.g., aliphatic, aromatic, and hydroxyl hydrogens) in each sample are determined using curve-resolving techniques. The second method was Thermogravimetric Analysis (TG) with FT-IR analysis of evolved products (TG-FTIR). In addition, an assessment was made of the application of on-line FT-IR analysis to coal liquefaction processes.

Work Accomplished

Quantitative FT-IR analysis was done of 23 samples.

- Nine whole resid samples produced by distillation of process oils generated from three different feed coals (Wyodak, Illinois, and Pittsburgh) and obtained from three different sampling points (interstage, recycle, second stage) during liquefaction runs at the Wilsonville facility.
- Nine THF soluble portions of the above whole resids.
- Four additional solids free resids obtained during a catalyst aging study at the HRI facility.
- A single whole process oil obtained from the Wilsonville facility.

In addition, quantitative TG-FTIR analysis was done of the following samples.

- The three feed coals.

- The nine THF soluble portions of the nine resid samples described above.

The FT-IR analysis provides a measure of aliphatic hydrogen, hydroxyl hydrogen, aromatic hydrogen, the distribution of aromatic hydrogen (1-adjacent, 2-adjacent, 3 or more), aliphatic carbon, carbonyl, hydroxyl oxygen, and ether oxygen in the organic portion. It provides a measure of mixed clay, quartz, calcite, and kaolin for the mineral portion. The samples were made into KBr pellets (in duplicate) and then scanned. The results from the FT-IR analysis studies were used to determine the feasibility of an on-line test.

The TG-FTIR analysis provides information on the time-dependent evolution of individual volatile species (tar, CH_4 , H_2O , CO_2 , CO , SO_2 , C_2H_4 , CS_2 , NH_3 , COS, olefins), weight of the non-volatile residue, and analysis of the C, H, and S in the non-volatile residue (by burning the residue and analyzing the combustion products such as CO , CO_2 , SO_2 and H_2O). A standard temperature program is used for these samples.

Summary of FT-IR Results

- The FT-IR method provided reproducible, quantitative data for the organic functional groups. Some care was required in the baseline corrections used in the determination of oxygen functional groups which were present in relatively low concentrations.
- The FT-IR determinations of the aliphatic hydrogen contents for the THF soluble portions of the Wilsonville Resids were in good agreement with the proton NMR data supplied by CONSOL. The FT-IR data for aromatic hydrogen content were consistent with the proton NMR data, although the latter numbers were higher by about 20% (relative basis).
- The FT-IR determinations of hydroxyl OH for the THF soluble fractions were in good agreement with the data supplied by CONSOL.

- The FT-IR determinations of the oxygen content of the whole resid samples (based on measurements of the ether and hydroxyl oxygen) were in general agreement with the data on total oxygen content provided by CONSOL, although the data are widely scattered.
- The FT-IR determinations of the total hydrogen concentration for all of the samples (based on measurements of aliphatic, aromatic, and hydroxyl hydrogen) were generally in good agreement with the data on total hydrogen content supplied by CONSOL.
- The FT-IR determinations of the total carbon content for all of the samples (based on subtraction of hydrogen and oxygen contents from 100%) were generally in good agreement with the data on total carbon content supplied by CONSOL.
- The FT-IR values of the total ash content for the whole resid samples agreed well with the trends in the values supplied by CONSOL, although the latter numbers were lower by about 30%. This is an expected result since the FT-IR measurement is closer to a low temperature ash measurement. However, problems with absolute mineral quantitation were identified in the FT-IR method which was developed and optimized for coal samples.
- The FT-IR data show clear trends in the Wilsonville whole resids through the various stages of the process. Between the interstage and 2nd stage there is an increase in total hydrogen and a decrease in the -OH and aromatic hydrogen contents. The same general trend is observed when comparing the 2nd stage and recycle stream, although the differences are less dramatic.
- The FT-IR measurements of the fraction of aromatic hydrogen followed the same trends for the three sample points regardless of whether the whole resids or THF soluble portions were examined. For other functional group concentrations, the measurements were not as well correlated.

- Some surprising trends were observed in the rank variation of the FT-IR results for the whole resids. Neither the phenolic OH content or the aromatic hydrogen content followed the rank variation that would be expected based on analysis of the raw coals.
- The FT-IR data show clear trends in the catalyst aging study done at HRI. As the catalyst age increases, the product quality decreases steadily (higher aromaticity, oxygen functional group content, and carbon content).

Summary of TG-FTIR Results

- The TG-FTIR method provided good quantitative data on the coal liquefaction process samples with the following exceptions. Except for small sample sizes (< 10 mg), the ash values from TG-FTIR were in good agreement with the values supplied by CONSOL. The problem occurs when the drift in the balance (<0.5 mg) is comparable to the amount of ash in the sample. It was also not possible to get quantitative measurements of the tar evolution from the THF soluble portion of the resid samples. This is believed to be due to the formation of relatively large diameter aerosols which scatter the IR light in a manner that cannot be corrected for in the current version of the analysis software.
- For the sample sizes used (10-20 mg), the TG-FTIR method provides reproducible pyrolysis data on whole resids, THF soluble fractions and coals for char yields and for gas species which are present in amounts larger than ~ 0.5 wt.%. The data for pyrolysis tar yields are also quantitative, except for the THF soluble fractions.
- The analysis of the principal combustion products (CO_2 , CO, H_2O , SO_2) for the residue from the pyrolysis cycle indicated that the remaining material was > 90 wt.% (MAF) carbon in most cases. The results for the combustion cycle are not as reproducible as observed for the pyrolysis cycle, since this feature of the instrument has not yet been optimized.
- The pyrolysis char yields from TG-FTIR analysis of the whole resids and THF soluble portions are correlated with the fraction of condensed aromatics from proton-NMR

analysis (or the H_{ar} fraction from FT-IR analysis). The pyrolysis tar yield from TG-FTIR analysis is inversely correlated with these quantities.

- The proximate analysis results (fixed carbon, volatiles, moisture, ash) from TG-FTIR analysis of the raw coals are in excellent agreement with the data supplied by CONSOL, except for the moisture content, which is likely due to differences in handling the samples.
- The TG-FTIR method can determine the relative amount of oxygen in resid samples based on the analysis of CO, CO₂ and H₂O from pyrolysis. On this basis, it appears that samples 1, 2 and 3 from run 251-III have either been significantly oxidized since the elemental analysis was completed or contain large amounts of minerals such as calcite which can decompose to produce CO and CO₂. One advantage of the method is that it can partially resolve the contributions of organic functional groups and minerals to the pyrolysis gas evolutions by examination of the shapes of the evolution profiles.
- The width of the tar peak of the whole resid samples is indicative of the boiling range of the materials. The boiling range for all three resid samples (interstage, second stage, recycle) does not vary much for the three coals. However, the temperature range for tar evolution is significantly lower than for the raw coal. This makes sense since the resids are derived from materials which have been pyrolyzed in the presence of a donor solvent which allows stabilization of reactive fragments.
- The amount of CO evolution from the whole resid samples is significantly lower than from the raw coals (except for the 251-III samples from the Wyodak coal) and generally decreases in the order coal > > interstage > second stage > recycle, thus following the same trends as the phenolic OH content (from FT-IR) and the char yield (from TG-FTIR). The temperature for the maximum rate of CO evolution is significantly higher for the resids when compared to the raw coal, suggesting that the liquefaction process preferentially removes the loosely bound CO.

- The amount of CH₄ evolution from the whole resid samples is at least 50% lower than from the raw coal (except in the case of the Wyodak) and generally follows the order coal > interstage > second-stage > recycle. The temperature of the maximum rate of CH₄ evolution is not much different for the resids when compared to the raw coal, suggesting that the liquefaction process changes the total amount but not the distribution of methyl groups.
- The ash analysis results from TG-FTIR indicate that the efficiency of the deash process varies significantly with coal type, which results in the ash content of the resids not following the same order as for the raw coals.

Conclusions and Recommendations

Both FT-IR and TG-FTIR have been clearly shown to provide a wide variety of useful information for process stream characterization. Both techniques can be applied to whole process oils, resids, or distillates, including ash components, and require relatively small samples (<50 mg). Significant differences are observed between process stages, coal types, and with catalyst aging. Both methods indicate that trends observed for the raw coals do not always hold when comparing the resid samples derived from these coals. A summary of the composition parameters that can be obtained by FT-IR and TG-FTIR is shown in Tables 1-1 and 1-2, respectively. In many respects, FT-IR is probably the single most useful technique for this purpose, since it can provide measurements on both organic and mineral components. The current FT-IR method can be made more quantitative for the mineral components and the organic functional groups by a re-optimization of the curve resolving program for coal liquefaction samples. FT-IR is also one of the few current techniques which is amenable to on-line analysis. FT-IR can provide information on total hydrogen content, hydroxyl content and aromatic hydrogen content, all of which are useful for monitoring product quality and catalyst activity. It is reasonable to assume that the chemical information provided by FT-IR could be correlated with other chemical and physical properties using chemometric techniques such as factor analysis. It is likely that on-line FT-IR measurements could be made in-situ using a sapphire fiber optic element in the Attenuated Total Reflectance (ATR) mode.

TABLE 1-1
SUMMARY OF FT-IR MEASUREMENTS

FT-IR MEASUREMENT	ALTERNATIVE TECHNIQUE
Hydroxyl Hydrogen	Chemical Titration
Aliphatic Hydrogen	^1H -NMR
Aliphatic Carbon*	^{13}C -NMR
Aromatic Hydrogen	^1H -NMR
Aromatic Hydrogen Distribution	---
Hydrogen Content	Elemental Analysis
Carbon Content*	Elemental Analysis
Hydroxyl Oxygen	Chemical Titration
Ether Oxygen	---
Carbonyl Oxygen**	---
Total Ash	TGA
Mineral Components	ICP

- * Estimated
 ** Relative values

TABLE 1-2
SUMMARY OF TG-FTIR MEASUREMENTS

TG-FTIR MEASUREMENT	ALTERNATIVE TECHNIQUE
Direct	
Volatiles content	Proximate analysis
Fixed Carbon	Proximate analysis
Moisture	Proximate analysis
Total Ash	Proximate analysis
Mineral Components	ICP
C,H,N,S	Elemental analysis
Indirect	
Char Yield - condensed aromatics	¹ H-NMR
CO Yield - phenolic content	FT-IR
CH ₄ Yield - methyl group content	¹³ C-NMR
Tar Evolution Profile - boiling range	Distillation

The TG-FTIR method can provide proximate analysis information (volatiles, fixed carbon, moisture, and ash) for feed coals and residues. In principle, it can also provide elemental analysis information, if a post-oxidizer accessory is used and two runs are made for each sample. Similar to the case of FT-IR, a very broad characterization of a sample can be achieved with a single instrument in a relatively short amount of time (30-60 minutes). The technique would be very useful in a quality control application for feed coals and heavy process streams like resids. It also has the potential to provide indirect measurement of the average structural components based on the pyrolysis measurements, as was demonstrated for methyl groups, phenolic groups and condensed aromatic rings. The utility of the TG-FTIR instrument for the second purpose will require additional study and correlation with other analytical measurements. However, the potential appears to be significant.

2. BACKGROUND

2.1 Introduction

Advanced Fuel Research, Inc., (AFR) has previously applied FT-IR methods to problems in hydrocarbon fuel chemistry, including the application of quantitative FT-IR as a tool for functional group determinations in coals, coal liquids, and other hydrocarbons (1,2). In particular, FT-IR and TG-FTIR analyses of coal liquefaction residues were used to follow changes in the solid phase due to catalytic pretreatment of coal (3). The FT-IR transmission method allows changes in the functional group composition to be measured, while TG-FTIR allows measurement of the evolved products during programmed thermal decomposition. These two techniques were recently used to study the mechanisms of crosslinking during coal pyrolysis (4). In a recent study done for the Air Force, quantitative FT-IR analysis was used to characterize a set of 25 jet fuels and the spectral information was used to make predictions of the results from pyrolysis and combustion experiments with these fuels (5). In general, excellent agreement was obtained between the predictions and the data. In a second study, recently completed for the Air Force, the use of on-line FT-IR diagnostics was demonstrated to be a useful technique for monitoring the thermal stability of jet fuel (6).

2.2 FT-IR Analysis

Fourier transform infrared spectroscopy (FT-IR) is one of the most versatile analytical techniques available for the study of fossil fuel structure and reaction chemistry. Among its advantages are: 1) its ability to study feedstocks and reaction products as solids, liquids and gases, since almost all have characteristic absorptions in the infrared; 2) its high sensitivity, allowing the study of strongly absorbing materials such as coal and char, and the use of techniques such as photoacoustic or diffuse reflectance spectroscopy; 3) its speed (instruments commercially available can obtain a complete spectrum every 20 ms) allowing the possibility of following chemical reactions on-line. Because of these advantages, FT-IR spectroscopy has achieved increasing use in fuel science.

Among the applications of FT-IR, the quantitative analysis of solids using the halide pellet method has received attention by several investigators. Painter and co-workers have developed FT-IR techniques for quantitative analysis of mineral constituents in coal (7,8) and for studying coal oxidation (9) and liquefaction (10,11). Solomon and co-workers established procedures for determining the concentrations of organic constituents of fossil fuels, especially the aliphatic, aromatic and hydroxyl hydrogen concentrations from the integrated areas or amplitudes of appropriate absorption peaks (1,2,12-17).

Recent work has been performed to improve and validate methods for quantitative analysis of the organic components (17-22). To obtain quantitative concentrations, it is necessary to establish the absorptivities (or extinction coefficients) which relate peak intensity to concentration. The absorptivity for the hydroxyl hydrogen concentration, H_{OH} , was determined by Solomon and Carangelo (1) using a procedure similar to that employed by Osawa and Shih (23). The infrared absorption intensity at 3200 cm^{-1} was calibrated with one set of samples for which H_{OH} concentrations were determined chemically (24). Using this calibration, H_{OH} concentrations determined in a second set of samples by FT-IR were found to match the correlation with rank established by Yarzab et al. (24) (by chemical methods) to within $\pm 10\%$.

A recent paper considered the use of FT-IR for quantitative determination of aliphatic hydrogen (H_a) and aromatic hydrogen (H_{ar}) in coals (2). Graphical and mathematical regression analysis techniques were used to determine absorptivities, which relate concentrations to peak areas in the FT-IR spectra. This

work demonstrated that the absorptivities were rank dependent and a regression analysis based on the coal oxygen concentration was used to describe this dependence. Using rank dependent absorptivities, the results of FT-IR and NMR methods appear to converge on reasonable values for H_{ar} for coals of all rank and for H_{ar} above 85% carbon. Below 85% carbon, the values of H_{ar} determined by FT-IR are more scattered.

2.3 TG-FTIR Analysis

Thermogravimetric analysis (TGA) has been employed in coal science to perform a number of characterizations including proximate analysis, (25) kinetics of weight loss, (26,27) char reactivity, (28-33) and gas adsorption measurements (34). A complementary technique, evolved-product analysis, has been employed to study pyrolysis product distributions and kinetics, (35-42) functional group compositions, (38,43-45) and temperature-programmed desorption (46-48). A TG-FTIR instrument was developed at AFR which combines TGA with evolved-product analysis by Fourier transform infrared (FT-IR) spectroscopy. FT-IR analysis of evolved products has advantages over mass spectroscopy in allowing analysis of very heavy products and over gas chromatography in speed.

The application of TG-FTIR to coal and petroleum source rocks has recently been described (49,50). To analyze coal, a sequence of drying, pyrolysis, and combustion is employed to obtain proximate analysis, volatile composition, volatile kinetics, and relative char reactivity. By employing several different heating rates, kinetic rate constants have been obtained (51-53). The apparatus has been very useful in studying the effects of pretreatments such as catalytic preliquefaction (3), demineralization (54), ion exchange (54), methylation (54), or oxidation (4) on the volatile product distribution.

3. OBJECTIVES

The overall objective was to investigate the application of two FT-IR methods to the characterization of coal liquefaction process streams, including the possible application of on-line methods. This was accomplished through the following specific tasks:

- Characterization of 23 samples by quantitative FT-IR transmission spectroscopy using the KBr pellet method (nine whole resids from Wilsonville, nine THF soluble portions of the same resids, four PFL liquids from HRI, one whole process oil from Wilsonville).
- Characterization of the same samples using a TG-FTIR (except PFL liquids from HRI and whole process oil, with the addition of the three feed coals).
- Correlation and comparison of the results from the two methods.
- Assessment of how FT-IR techniques could be used for on-line and off-line characterization of coal liquefaction process streams.

4. RESULTS

4.1 Description of Experimental Methods

A brief description of the various FT-IR techniques and their application to hydrocarbon fuel analysis problems is given below.

Quantitative FT-IR - To provide quantitative organic structural information for coals, lignins, products of thermal decomposition (tar, char and gases), jet fuels, and other natural and synthetic hydrocarbons, techniques have been developed at AFR using a Nicolet 7199 Fourier Transform Infrared Spectrometer (FT-IR). The techniques, which are described in previous publications (1,2), have been used to determine quantitative concentrations of the hydroxyl, aliphatic and aromatic hydrogen, and aliphatic and aromatic carbon, ether oxygen and mineral content for a wide number of coals, lignins, chars, tars, coal liquefaction products, oil shales, coal extracts and jet fuels. Qualitative information is also obtained concerning the types of ether linkages (oxygen linked to an aliphatic or aromatic carbon), carbonyl contents and the forms of aliphatic hydrogen (methyl or methylene).

The samples are analyzed as KBr pellets in a Nicolet 7199 FT-IR. The procedure for the FT-IR analysis is to grind ~50 mg of sample in a Wig-L-Bug under N₂ for 10 minutes. From the homogenized sample,

a 1 mg portion is removed and mixed in a second Wig-L-Bug with 300 mg of KBr (also under N_2). Next the sample is pressed into a pellet under vacuum and weighed. It is scanned wet and then rescanned after drying. Each sample is made up in duplicate. If the scans of the wet samples do not produce similar spectra, a new set of samples is made. Only the dry scans are used for quantitative analysis.

For quantitative analysis of such spectra, a curve analysis program is employed to synthesize the IR spectra. The program uses a basic set of adsorption peaks identified with various functional groups. Most of the hydrocarbon samples studied in our laboratory could be synthesized by varying only the magnitudes of a set of peaks whose widths and positions were held constant. The synthesis routine can produce a spectrum which matches the actual spectrum well. An FT-IR spectrum of the THF soluble portion of a recycle oil resid is shown in Fig. 4.1-1. The regions used for quantitative FT-IR analysis are identified. The correction of a whole resid spectrum for scattering and minerals is demonstrated in Fig. 4.1-2. The details of the quantitative analysis routine are described below.

The curve analysis program can provide the quantitative data for aliphatic hydrogen from the aliphatic C-H stretching vibrations between 2930 and 2850 cm^{-1} and aromatic hydrogen from the C-H out of plane bending at 700-900 cm^{-1} . The ratios among 1, 2 and 3 or more adjacent aromatic hydrogens are also determined by the peak heights (absorbances) of C-H out of plane bending at 700-900 cm^{-1} . With these ratios and the total quantity of aromatic hydrogen obtained from the curve analysis, the quantitative values of different adjacent aromatic hydrogens can be determined. The quantity of aliphatic carbon can be evaluated from that of aliphatic hydrogen assuming an elemental composition $CH_{1.8}$. The C=O stretching vibrations around 1700 cm^{-1} indicate the presence of carbonyl functional groups. Although absolute quantitative data for carbonyl groups cannot be determined from the IR spectra, the area under the carbonyl peak can provide a quantitative comparisons among different samples. The quantitative amounts of hydroxyl functional groups and ethers are determined from the combination of the absorbances of O-H stretching vibrations at 3200 cm^{-1} and the C-O stretching at 1200 cm^{-1} , respectively, and the calibration tables constructed at AFR for coal analysis. The total quantity of hydrogens is determined as the sum of aliphatic, aromatic and hydroxyl hydrogens. The mineral contents are also provided from the curve analysis. The quantitative amounts of kaolin, calcite, quartz, and illite are determined from 3600-3700 cm^{-1} , 900 cm^{-1} , 750-800 cm^{-1} , and 850-1050 cm^{-1} bands, respectively.

For the organic functional groups the data are usually accurate to within $\pm 10\%$ of the measured value for each functional group; i.e., the relative error is within $\pm 10\%$. The measurements are less accurate for low concentrations of organic functional groups and for mineral species (relative errors within $\pm 20\%$).

TG-FTIR - The apparatus consists of a sample suspended from a balance in a gas stream within a furnace. As the sample is heated, the evolving volatile products are carried out of the furnace directly into a 5 cm diameter gas cell (heated to 150 °C) for analysis by FT-IR. The FT-IR can obtain spectra every 0.2 s to determine quantitatively the evolution rate and composition of several hydrocarbon compounds. The system allows the sample to be heated on a pre-programmed temperature profile at rates between 3 °C/min and 100 °C/min up to a temperature between 20 and 1000 °C and held for a specified time. The system continuously monitors: 1) the time-dependent evolution of the gases (including specific identification of the individual species such as, CH₄, C₂H₆, C₂H₄, C₂H₂, C₃H₈, benzene, etc.; 2) the heavy liquid evolution rate and its infrared spectrum with identifiable bands from the functional groups, and 3) weight of the non-volatile material (residue). An analysis of C,H,N and S in the residue at the end of the pyrolysis experiment can be obtained by introducing oxygen to burn the residue and analyzing the combustion products.

As an example of the analysis procedure, the programmed pyrolysis of a resid is described. A 10-20 mg sample of resid is taken on a 30 °C/min. temperature excursion in helium, first to 150 °C to dry, then to 900 °C for pyrolysis. After cooling, a small flow of O₂ is added to the furnace at the 57 minute mark and the temperature is ramped to 700 °C (or higher) for oxidation. Figure 4.1-3a includes three plots: 1) the weight loss from this sample (labeled "balance"); 2) the sum of evolved products from FT-IR analysis; and 3) the temperature history. This figure shows the drying, pyrolysis and initial cooling stages. The oxidation part of the cycle, is shown in Fig. 4.1-4, which reveals that CO₂ is the dominant product of the residue combustion.

During this excursion, infrared spectra are obtained once every thirty seconds. The spectra show absorption bands for CO, CO₂, CH₄, H₂O, SO₂, COS, CS₂, C₂H₄, Olefins, HCl, NH₃, and HCN. The spectra above 300 °C also show aliphatic, aromatic, hydroxyl, carbonyl and ether bands from tar. The evolution of gases derived from the IR absorbance spectra are obtained by a quantitative analysis program (49-51). Examples of the evolution curves are plotted in Figs. 4.1-3b to 4.1-3l. The aliphatic

region is used for the tar evolution curve. Quantitative analysis of tar is performed with the aid of the weight loss data (Fig. 4.1-3b). The sum of the integral of the evolution curves in Figs. 4.1-3b to 4.1-3l is plotted in Fig. 4.1-3a as the cumulative evolved product amount for comparison to the weight loss (balance) curve. Because the data are quantitative, the sum of these curves usually agrees with the weight loss as determined by the TG balance (also shown in Fig. 4.1-3a). It should be noted that in the TG-FTIR plots of Appendix D, that the balance curve is labeled twice in cases where the sum and balance curves cross each other and become indistinguishable. Small discrepancies will occur in this match because of components such as H_2 which cannot be seen by IR. Figure 4.1-5 shows a typical spectrum obtained during TG-FTIR analysis of a resid which identifies the key absorption bands.

The TG-FTIR method provided good quantitative data on the coal liquefaction process samples with the following exceptions. Except for small sample sizes (< 10 mg), the ash values from TG-FTIR were in good agreement with the values supplied by CONSOL. The data for ash content shown in Appendix B (column 73) were all obtained from experiments in which large sample sizes (> 10 mg) were used. The problem occurs when the drift in the balance (< 0.5 mg) is comparable to the amount of ash in the sample.

It was not possible to get quantitative measurements of the tar evolution from the THF soluble portion of the resid samples. This is believed to be due to formation of large aerosol particles which scatter the IR light. The system is designed to make quantitative measurements of tar in the presence of scattering from aerosol particles in the Rayleigh regime. If the aerosol is large enough in average diameter so that Mie scattering occurs, the correction algorithm does not work. This is apparently what happens for the THF soluble fractions of the resids. This phenomenon was not observed for tars from whole resids or from coal pyrolysis. These materials produce a tar which is less uniform in composition and therefore more likely to form smaller aerosols.

The relative error of the TG-FTIR measurements is usually within $\pm 10\%$ for major species (char, tar, CO_2 , CO , CH_4) and within $\pm 20\%$ for minor species (SO_2 , COS , CS_2 , C_2H_4 , Olefins, HCl , NH_3 , HCN), which are generally present in amounts of less than 0.5 wt.% (MAF), and H_2O . Examples of repeat measurements for the same sample are given in Appendix D (Figs. D-19 and D-20). The tabulated data for the major volatile species for these repeat runs are listed in Appendix B (see rows 24 and 25, columns 72 through 88).

4.2 Summary of FT-IR Results

The quantitative data from FT-IR analysis of the samples are tabulated in Appendix B (columns 50 to 71). The results indicate that characterization of liquefaction products using the FT-IR technique was successful and useful as far as providing information about sample properties and process conditions. As shown in Appendix B, the quantitative data derived from the FT-IR method include a determination for aliphatic, aromatic (1, 2 and 3 or more adjacent), and hydroxyl hydrogens, carbonyl, hydroxyl and ether oxygens, aliphatic carbon, and various mineral species. This information provides a good understanding of the average functional group compositions of products from the various stages of a coal liquefaction process. In order to demonstrate the reliability of FT-IR results, correlation and comparison of the FT-IR results with those supplied by CONSOL using different methods are described below.

Aromatic and Aliphatic Hydrogen (Proton) Distribution - CONSOL provided proton distribution information of the products obtained by using ^1H -Nuclear Magnetic Resonance Spectroscopy (^1H -NMR) analysis. These data are listed in columns 25 to 33 of Appendix B. A curve fitting program was used to determine the hydrogen distribution from the FT-IR spectra, as discussed in Section 4.1. Since the whole and THF-soluble resid samples analyzed by CONSOL were dissolved in pyridine d_5 and then filtered, a direct comparison can only be made with the FT-IR data on the THF soluble fractions. The comparison of the aromatic to total hydrogen ratio (H_{ar}/H_{total}) using FT-IR analysis with the aromatic proton fraction from the ^1H -NMR method analysis for the THF soluble samples is shown in Fig. 4.2-1. Fig. 4.2-2 shows the comparison of the aliphatic hydrogens for the same set of samples. The results show that the FT-IR H_{ar}/H_{total} agrees reasonably well with the fraction of aromatic protons derived from the ^1H -NMR method. The same was true of the aliphatic hydrogen. Both Figures 4.2-1 and 4.2-2 (as well as Figures 4.2-3 through 4.3-6) contain two lines. The solid line is the mean value of the ratios between the two sets of measurements. The dashed line is a parity line. Figures 4.2-1 and 4.2-2 provide a relation between the results obtained by these two methods:

H_{ar}/H_{total} (% , THF sol.), FT-IR | AFR = 0.77 (Aromatic Proton Fraction (% THF sol.), CONSOL)

H_{al}/H_{total} (% , THF sol.), FT-IR | AFR = 1.1 (Aliphatic Proton Fraction (% THF sol.), CONSOL)

The absolute variations are similar between the two methods for the H_{ar} and H_{al} determinations while the relative variations are higher for the latter because of the smaller concentration. The absorption coefficients for H_{ar} are more variable with sample type, particularly for samples which have a lot of oxygen (which is not the case here) (2). The agreement between the values from proton NMR and FT-IR are also better in the case of H_{al} , which has also been found previously (2).

Some of the discrepancy between the FT-IR and NMR results could also be due to the fact that the FT-IR methods have been optimized for powdered coal samples. The resid samples are more homogeneous materials, particularly the THF soluble fractions. This gives rise to sharper peaks which may require a modification of the curve resolving algorithm to maintain absolute quantitation.

Hydroxyl Groups - The major problems in making this determination are the overlap of a band due to water in the sample (or water absorbed in preparing the KBr pellet) and scattering which affects this region of the spectrum. The latter problem makes the measurement sensitive to the construction of a baseline. These measurements do not distinguish between phenolic OH and alcoholic OH, which is why the AFR results are reported as hydroxyl content rather than phenolic OH content. However, in the coal liquefaction samples studied in this project, the amount of non-phenolic OH is likely to be small. Both AFR and CONSOL used an FT-IR method to determine the concentration of hydroxyl groups in the samples. CONSOL used the -OH stretch band found between 3200 and 3400 cm^{-1} to determine the phenolic -OH concentration from measurements on THF-soluble portions of the samples. Based on analysis of a wide range of coal and coal products, AFR has chosen to determine the concentration of hydroxyl groups in coal using the 3200 cm^{-1} O-H stretch to avoid the interference from the KBr- H_2O band which peaks at 3400 cm^{-1} (1). A comparison of the quantitative data for the hydroxyl groups from the analysis by AFR and CONSOL for the THF soluble fractions is shown in Fig. 4.2-3. The hydroxyl results obtained by AFR and CONSOL are in very good agreement, considering the differences in sample preparation and quantitative analysis routines. The relation between them is:

$$\text{-OH (wt\% THF sol.), FT-IR/AFR} = 0.90 \text{ (Phenolic-OH (wt\%, THF sol.), CONSOL)}$$

Oxygen Analysis - In general, most of the oxygen atoms in coal and coal products are contained in hydroxyl, ether, and carbonyl functional groups. As indicated in Section 4.1, only relative values of the

carbonyl content are determined with the current method. Assuming that the amount of oxygen in carbonyl functions is negligible, the oxygen contents of the samples can be obtained through quantitative analysis of hydroxyl and ether by the FT-IR method. The oxygen contents of the samples provided by CONSOL were determined by difference. The comparison of the oxygen data from AFR and CONSOL for the whole resids and whole process oil is shown in Fig. 4.2-4, and the results show that they agree reasonably well with each other, although the data are somewhat scattered. The relation between these two different methods is:

$$\text{Oxygen Content (wt\%, MAF), FT-IR} / \text{AFR} = 1.1 (\text{Oxygen Content (wt\%, MAF, diff), CONSOL})$$

It is difficult to say whether the scatter is due to the inherent inaccuracy of determining oxygen by difference, the assumption that most of the oxygen is in hydroxyl or ether groups and/or limitations of the FT-IR technique in determining low levels of oxygen.

In general, the results of the FT-IR method suggest somewhat higher values of oxygen content for the Wyodak and Pittsburgh resids and lower values for the Illinois resids. However, because of the assumptions involved in both calculations, it is difficult to draw any firm conclusions. The results from TG-FTIR analysis are more reliable in this respect and these do indicate that the Wyodak resid samples may have been oxidized since the elemental analysis was determined (either that or the oxygen by difference calculations are very inaccurate for these samples). This point is discussed further in Section 4.4.

Hydrogen Analysis - The total hydrogen content for each of the samples was determined by summing up the aliphatic, aromatic, and hydroxyl hydrogen determined by FT-IR. The hydrogen analysis provided by CONSOL was determined with a Leco CHN-600 instrument. The comparison of the results of these two methods is shown in Fig. 4.2-5, and it is found that they are in good agreement. The relation between them is:

$$\text{Hydrogen Content (wt\%, MAF), FT-IR} / \text{AFR} = 1.1 (\text{Hydrogen Content (wt\%, MAF), CONSOL})$$

Carbon Analysis - Using the FT-IR method, the quantity of aliphatic carbon can be determined from that of aliphatic hydrogen assuming an elemental composition of $\text{CH}_{1.8}$. However, it is impossible to

determine the amount of aromatic carbon from that of aromatic hydrogen, since the H/C varies tremendously with the degree of condensation in the aromatic structure. Because carbon, hydrogen, and oxygen are the dominant major elemental components in coal (MAF) and the fraction of others, such as nitrogen and sulfur, is negligible compared with carbon, the carbon content of each sample was determined by mass balance difference with oxygen and hydrogen contents obtained with the FT-IR method. The values supplied by CONSOL were obtained from carbon analysis with a Leco CHN-600 instrument. The comparison of the results from AFR and CONSOL is shown in Fig. 4.2-6. It reveals that these two sets of data from different methods are in good agreement with each other, and the relation between them is:

$$\text{Carbon content (wt\%, MAF), FT-IR | AFR} = 1.0 (\text{Carbon Content (wt\%, MAF), CONSOL})$$

Ash - FT-IR analysis can determine the contents of major minerals, i.e. mixed clays (mostly illite, potassium-rich clays $(\text{Al}_2\text{K}(\text{OH})_2 \text{Si}_4\text{O}_{10})$, Kaolinite (pure Si-Al clay $(\text{Al}_2(\text{OH})_4\text{Si}_2\text{O}_5)$, Quartz (SiO_2), and Calcite (CaCO_3). The results are shown in Appendix B (columns 66-71). The total ash content determined by FT-IR is the sum of these four minerals. Since the FT-IR measurement of minerals includes the associated water and is done at ambient temperature, it is expected to be higher than the high temperature ash determinations supplied by CONSOL. However, it is also true that the FT-IR method does not determine pyrite, so it may underestimate the ash content for coals which contain large amounts of this mineral. The comparison of the ash contents determined by AFR using FT-IR and by CONSOL is shown in Fig. 4.2-7. The results show that the trends in the FT-IR values of the total ash content agreed well with the values supplied by CONSOL, although the latter numbers were lower as expected. The relation between the two measurements is:

$$\text{Ash (wt\%, dry), FT-IR | AFR} = 1.3 (\text{Ash (wt\%, dry), CONSOL})$$

Comparison of the individual values of CaO is shown in Fig. 4.2-8. The two sets of results agree with each other in quantitative trend, but the values supplied by CONSOL were significantly lower. This discrepancy is probably a result of the fact that the mineral species occur in regions of the FT-IR spectrum which include organic species (see Fig. 4.1-2). The fact that the curve resolving algorithm has been optimized for coal samples which have broader peaks will lead to errors which can affect the determination of mineral (and organic) species. The best evidence for this is the fact that the THF

soluble fractions, which have been filtered, were determined by FT-IR to have finite amounts of mixed calcite (and mixed clay) (see Appendix B). The values for quartz and kaolin were essentially zero, as expected. Consequently, it is not surprising that the values for CaO do not agree.

Summary - FT-IR is one of the most versatile analytical techniques for the study of fuel structure and reaction chemistry. It is able to study fuel feedstocks and reaction products as solids, liquids and gases, since they have characteristic absorptions in the infrared. Its speed allows the possibility of following chemical reactions on-line. The above results have demonstrated the versatility and reliability of this technique, by the generally good comparisons with the data supplied by CONSOL obtained from several different analytical techniques. The comparison of FT-IR values with those supplied by CONSOL is summarized as follows:

H_{ar}/H_{total} (% , THF sol.), FT-IR | AFR = 0.77 (Aromatic Proton Fraction (% , THF sol.), CONSOL)

H_{al}/H_{total} (% , THF sol.), FT-IR | AFR = 1.1 (Aliphatic Proton Fraction (% , THF sol.), CONSOL)

-OH (wt%, THF sol.), FT-IR | AFR = 0.90 (Phenolic-OH (wt%, THF sol.), CONSOL)

Oxygen Content (wt%, MAF), FT-IR | AFR = 1.1 (Oxygen Content (wt%, MAF, dif), CONSOL)

Hydrogen Content (wt%, MAF), FT-IR | AFR = 1.1 (Hydrogen Content (wt%, MAF), CONSOL)

Carbon content (wt%, MAF), FT-IR | AFR = 1.0 (Carbon Content (wt%, MAF), CONSOL)

Ash (wt%, dry), FT-IR | AFR = 1.3 (Ash (wt%, dry), CONSOL)

4.3 Summary of TG-FTIR Results

The TG-FTIR system continuously monitors the pyrolysis process to give the time-dependent evolution of gases, the heavy liquid evolution rate and its infrared spectrum with identifiable bands from the functional groups, and weight of the non-volatile material (residue). The analysis of C, H, N, and ash contained in the residue is carried out after pyrolysis by introducing oxygen to burn the residue and analyzing the combustion products.

The post combustion products contain mainly CO₂, with H₂O, CO and SO₂ as the minor components as revealed in Appendix B (columns 85 to 88). It should be noted that the post combustion data, which are in units of wt%, MAF, do not include the weight of oxygen in each product, since oxygen

comes from the gas phase; not from the sample. If the amount of carbon evolved as CO and CO₂ is compared to the weight of the char residue (column 74 in Appendix B), it can be determined that most of the residues are >90% carbon on a MAF basis. These data are more scattered than from the pyrolysis part of the cycle because of baseline drift and the fact that the much higher concentrations of CO₂ require a different set of calibration curves. The combustion cycle portion of the TG-FTIR instrument has not yet been fully optimized.

The TG-FTIR could not provide elemental analysis of the complete resid samples since most of the sample is lost as tar during the pyrolysis stage. However, a new version of the instrument is being developed which has a post-oxidizer attachment that can be used to measure C, H, N, S, in the tar through analysis of its combustion products. The full implementation of this modification requires two TG-FTIR runs for each sample, one with and one without the post-oxidizer in use.

The results of TG-FTIR analysis are shown in tabular form in Appendix B (columns 72 to 88) and are plotted in Appendix D (Figs. D-1 to D-22). The comparison of results obtained by AFR and with those supplied by CONSOL is described below.

Feed Coal Analysis - Pyrolysis up to 900 °C followed by combustion of the residue, when carried out in the TG-FTIR apparatus gives a good proximate analysis for feed coals. The proximate analysis with TG-FTIR reveals the contents of ash, volatile matter, fixed carbon, and moisture in coal.

Pyrolysis of coal at temperatures as high as 900 °C will produce a char with a high carbon content (>90%, MAF). The carbon in the char is initially fixed in the macromolecular domain of the raw coal. Therefore, the char yield in pyrolysis represents the fixed carbon content in the coal. The comparison of the pyrolysis char yield obtained by TG-FTIR and the fixed carbon content in the feed coal supplied by CONSOL is shown in Fig. 4.3-1. It shows that the two sets of values are in good agreement and the relation between them is:

$$\text{Char Yield (wt\%, dry), TG-FTIR} / \text{AFR} = 1.0 \text{ (Fixed Carbon (wt\%, dry), CONSOL)}$$

The ash content is determined by burning the char in the presence of oxygen. A comparison of ash analyses supplied by AFR and CONSOL is shown in Fig. 4.3-2, and the results show a very good agreement. The relation between the two sets of data is:

$$\text{Ash (wt\%, dry), TG-FTIR|AFR} = 1.1 (\text{Ash (wt\%, dry), CONSOL})$$

The volatile matter of coal includes all the species evolved during pyrolysis. These species are gases and tars, which are measured by TG-FTIR during the process of pyrolysis. The comparison of the volatile matter contents determined by TG-FTIR with those provided by CONSOL is shown in Fig. 4.3-3. The results show that they are in good agreement with each other and the relation is:

$$\text{Volatile (wt\%, dry), TG-FTIR|AFR} = 1.0 (\text{Volatile (wt\%, dry), CONSOL})$$

The moisture content of coal is determined by TG-FTIR prior to pyrolysis. A comparison of coal moisture contents determined by AFR and CONSOL is shown in Fig. 4.3-4. The results obtained by TG-FTIR are not in good agreement with those supplied by CONSOL, although the trend is correct, the relation between them is:

$$\text{Moisture (wt\%, as rec.), TG-FTIR|AFR} = 0.45 (\text{Moisture (wt\%, as det.), CONSOL})$$

This difference is not surprising since the moisture content depends on how the sample is stored and handled.

Ash Analysis for Resids - The ash content of the distillation resids was determined using TG-FTIR by burning the char residue from the resids in the presence of oxygen. The comparison of the resid ash content obtained by AFR using TG-FTIR and that supplied by CONSOL is shown in Fig. 4.3-5. The results show that the ash contents determined by TG-FTIR are in very good agreement with those provided by CONSOL. The relation between the ash contents determined by AFR and by CONSOL is:

$$\text{Ash (wt\% dry), TG-FTIR|AFR} = 1.0 (\text{Ash (wt\%, dry), CONSOL})$$

Fig. 4.3-5 also reveals that the ash content of the distillation resids depends on the type of feed coal. The values decrease with coal rank, following the order Wyodak > Illinois > Pittsburgh, which agrees with the results determined by FT-IR (see Figure 4.2-7), whereas the feed coals decrease in ash content in the order Illinois > Wyodak > Pittsburgh. This result demonstrates that it is not necessarily true that the properties of the liquefaction product are proportional to those of the raw coal.

Char Analysis for Resids - Coal chars produced at temperatures above 900 °C consist mainly of large condensed aromatic rings. The char yield from pyrolysis of resids in the TG-FTIR was determined after pyrolysis up to 900 °C. It was expected that the char yield from resid pyrolysis would have a proportional relation with the content of condensed aromatics. The comparison of the char yield for pyrolysis performed in the TG-FTIR and the condensed aromatic proton fraction from NMR is shown in Fig. 4.3-6 for the THF soluble fractions. The results show that the char yield in resid pyrolysis increases with increasing condensed aromatic proton fraction. The relation between the two sets of values is:

$$\text{Char Yield (wt\%, THF sol.), TG-FTIR} / \text{AFR} = 0.65 (\text{Condensed Aromatic Proton (\%, THF sol.)})$$

CONSOL)

The data in Appendix B show that the pyrolysis char yield and proton distribution of the resids depends on the type of feed coal. The pyrolysis char yields of the resids and feed coal are summarized in Table 4.3-1. It is found that both the char yield and condensed aromatic proton fraction of the resids follow the order Pittsburgh > Wyodak > Illinois in coal type. Again, the results from coal analysis show that the fixed carbon content or pyrolysis char yield of the feed coals decreases with decreasing coal rank, i.e. Pittsburgh > Illinois > Wyodak, which is not consistent with that of liquefaction products. This inconsistency may be attributed to retrogressive reactions in the liquefaction process in the case of the Wyodak coal, which produce a resid with more char forming chemical structures or, possibly, due to the differences in operating conditions.

TABLE 4.3-1 The Pyrolysis Char Yields (wt%, MAF) of the Whole Resid Samples

	Feed Coal	Interstage	2nd Stage	Recycle
Pittsburgh	55	28	28	23
Illinois	54	18	16	14
Wyodak	51	23	21	20

The effects of bond cleavage from the liquefaction process are also revealed in Table 4.3-1, by the lower char yields from resids than from raw coals. The presence of a donor solvent during the liquefaction process allows additional depolymerization of the coal to occur when compared to pyrolysis in an inert atmosphere and increases the amount of donatable hydrogen in the structure. Consequently, when the resid material is subsequently re-pyrolyzed in the TG-FTIR, many of the coal fragments can simply vaporize directly or the fragments produced can be stabilized by hydrogen, resulting in a relatively low char yield.

Tar Yield from Resids - The tar yield from resid pyrolysis was also determined in the TG-FTIR system. It is found that the tar yield from resid pyrolysis also depends on the type of feed coal. Data for the pyrolysis tar yield for the resids and raw coals are summarized in Table 4.3-2, which shows that the tar yield follows the order Illinois > Pittsburgh > Wyodak. It should be noted that tar yield from coal pyrolysis follows the order Pittsburgh > Illinois > Wyodak, which is again not relatively consistent with that for the resids. Similarly, this can be explained by the structure changes due to the competition between bond cleavage and retrogressive reactions in liquefaction or, possibly, due to differences in operating conditions. The results consistently show that the tar yield is much higher for resids than for raw coals, which is due to depolymerization during the liquefaction process, as discussed above.

TABLE 4.3-2 The Pyrolysis Tar Yields (wt%, MAF) of the Whole Resid Samples

	Feed Coal	Interstage	2nd Stage	Recycle
Pittsburgh	33	65	66	67
Illinois	26	70	70	74
Wyodak	20	52	57	58

The width of the tar peak of the whole resid samples is indicative of the boiling range of the materials. The boiling range for all three resid samples (interstage, second stage, recycle) does not vary much for the three coals. However, the temperature range for tar evolution is significantly lower than for the raw coal. This makes sense since the evolution of tar from the coals requires a higher degree of depolymerization than the resid samples which have already been pyrolyzed under conditions where the fragments can be easily stabilized. The tar evolution peak temperatures for the interstage resids and raw coals are shown in Table 4.3-3. Again, the liquefaction process has changed the order of T_{max} for the resid samples relative to the raw coals, although the differences are not large in either case.

TABLE 4.3-3 The Tar Evolution Peak Temperatures of the Whole Resid Samples

	Feed Coal	Interstage
Pittsburgh	492	330
Illinois	493	341
Wyodak	477	338

Gas Yield - The gas evolution data from TG-FTIR analysis of resids are plotted in Appendix D, and the yields are tabulated in Appendix B. It is found that the yields of both CO and CO₂ depend on the type of feed coal and decrease with coal rank, i.e., Wyodak > Illinois > Pittsburgh, which is relatively consistent with the order for the pyrolysis of the feed coals. It is of interest to note that the yields of CO and CH₄ from resid pyrolysis are lower than those from coal pyrolysis, whereas the converse is true for the CO₂ yield (except for the Wyodak resids which appear to have been oxidized).

During pyrolysis, the SO₂ evolves in two separate peaks. It is thought that the second peak might be a result of oxidation of sulfur retained in the residue by traces of oxygen contained in the carrier gas (helium) at high pyrolysis temperatures. The TG-FTIR has not been well calibrated for NH₃, COS, CS₂, and olefins. In the cases of NH₃ and COS, the data can be off by as much as a factor of two. This is caused by the interference from the absorbances of other species. Because COS is a broad band absorber, its values are probably applicable over a wider range of concentrations than for NH₃.

The CS₂ and olefins data are not quantitative. In addition, the CS₂ evolution often "mimics" the H₂O evolution even if no CS₂ is evolving. This is because H₂O overlaps the region of absorbance for CS₂.

Additional discussion of the gas evolution data from TG-FTIR analysis is included in Section 4.4.

Summary

TG-FTIR is able to provide a proximate analysis for coal and resids. The analysis not only provides the product yields, but also the time dependent evolution of each species during pyrolysis, which can be used to provide structural information on a coal or resid. The comparisons are summarized for feed coals as follows:

Char Yield (wt%, dry), TG-FTIR|AFR = 1.0 (Fixed Carbon (wt%,dry), CONSOL)

Ash (wt%, dry), TG-FTIR|AFR = 1.1 (Ash (wt%, dry), CONSOL)

Volatile (wt%, dry), TG-FTIR|AFR = 1.0 (Volatile (wt%, dry), CONSOL)

Moisture (wt%, as rec.), TG-FTIR|AFR = 0.45 (Moisture (wt%, as det.), CONSOL)

The comparisons for the resids are summarized as follows:

Ash (wt%, dry), TG-FTIR|AFR = 1.0 (Ash (wt%, dry.), CONSOL)

Char Yield (wt%, THF sol.), TG-FTIR|AFR = 0.65 (Condensed Aromatic Proton (%), THF sol.),
CONSOL)

4.4 Interpretation of Data in the Context of the Liquefaction Process

Wilsonville Runs - Coal liquefaction was performed in a catalytic/catalytic Close-Coupled Integrated Two-Stage Liquefaction (CC-ITSL) System with ash recycle for the Wilsonville runs. The two-stage liquefaction process consists of coal dissolution followed by upgrading of the solubilized products, using dispersed and supported catalysts. Samples from the Wilsonville facility were taken from three locations to represent different degrees of coal processing. The Interstage Product samples were distillation resids obtained from a high pressure flash separation system located between the first stage and second stage reactors. The 2nd Stage Product samples were resids collected from the bottom

product hold tank of a separation system following the second stage reactor. The Recycle samples were obtained from the solvent surge tank. According to the flow sheet provided by CONSOL, the Recycle samples are actually the partially deashed products of the 2nd Stage Product. The structural differences of the samples, revealed in the analytical data provided by AFR and CONSOL, are due to differences in the feed coals and to different degrees of coal processing in liquefaction, as discussed below.

The comparison of Phenolic -OH contents from THF soluble resid fractions (determined by CONSOL) of samples from different degrees of processing is shown in Fig. 4.4-1. The results show that the Interstage Product has a higher phenolic -OH content than the 2nd Stage Product due to upgrading by the second reactor. Roughly 33% of the phenolic -OH was reduced by the second stage reactor for Wyodak samples, ~24% for Pittsburgh, and ~16% for Illinois. The TG-FTIR results show a corresponding reduction of CO evolution in pyrolysis for the 2nd Stage Product, as discussed below. Fig. 4.4-1 shows a slight phenolic -OH reduction due to the deash process. The FT-IR analyses provided by AFR also show the reduction of OH groups by the second stage reactor, but show little effect from the deash process. The results from FT-IR analysis on the whole resids at AFR are shown in Fig. 4.4-2. In general, the -OH content of the resids decreases in the order Interstage > 2nd Stage > Recycle. The trends for char yield from TG-FTIR analysis follow the same general order, which is consistent with the role of oxygen functions in retrogressive reactions under pyrolysis (4) and liquefaction conditions (54).

It has been indicated previously that the CO evolution from coal pyrolysis is much higher than that from resid pyrolysis, and this makes sense since the oxygen content of the feedstock would be reduced in the liquefaction process. Thus, the amount of CO evolution in pyrolysis is expected to decrease in the order coal > Interstage > 2nd Stage > Recycle, and the results shown in Figure 4.4-3 for the whole resids indicate that this is the case. If the results in Figs. 4.4-2 and 4.4-3 are compared, it can be seen that the -OH content and the CO evolution from pyrolysis are related.

Similar to the result of CO evolution in pyrolysis, more CH_4 is evolved in coal pyrolysis than in resid pyrolysis. Because most of the CH_4 forming components in coal are consumed in the liquefaction process in which gaseous product CH_4 is separated from the process stream to become fuel gas, it is reasonable to see less CH_4 evolution in resid pyrolysis. A comparison of CH_4 yields from pyrolysis

of the feed coals and various whole resid samples is shown in Figure 4.4-4. Since CH_4 forming components would be further reduced by the Second stage reactor, it is also not surprising to see less CH_4 evolution in the pyrolysis of the 2nd Stage Product than the Interstage Product. The amounts of CH_4 evolution from the 2nd Stage Product and from the Recycle are similar, which reveals that the deash process has little effect on the CH_4 forming structures in resids. In general, the amount of CH_4 evolution in the pyrolysis of liquefaction products follows the order coal > Interstage > 2nd Stage ~ Recycle.

The hydrogen content analyses provided by AFR using FT-IR and CONSOL with a Leco CHN-600 both indicate a slight increase of hydrogen concentration in the whole resids from the second stage reactor by comparing the 2nd Stage Product with the Interstage Product (except for Pittsburgh resid). These results are shown in Fig. 4.4-5. This figure also shows the expected increase in hydrogen concentration for the resid products when compared to the feed coal. The proton distribution determined by a ^1H -NMR technique on the THF soluble fractions shows a decrease in the fraction of condensed aromatic protons for the 2nd Stage Product due to the second stage reactor, whereas little effect on the uncondensed aromatic protons is observed. The total aromatic hydrogen fraction ($\text{H}_{\text{ar}}/\text{H}_{\text{total}}$) determined by the FT-IR method on the whole resid shows a corresponding reduction in the 2nd Stage Product, as shown in Figure 4.4-6. Similar trends were observed for the THF soluble fractions (see Appendix B). The deash process shows little effect on hydrogen quantity and distribution, as shown in Figures 4.4-5 and 4.4-6. As the material is upgraded, the absolute amount of aromatic hydrogen decreases, as shown in Figure 4.4-7.

The ash contents of the 2nd Stage Product and the Recycle from TG-FTIR analysis are shown in Fig. 4.4-8 for the whole resids. The results show that ~12% of ash was reduced by the deash process for the Wyodak samples, ~7% for the Pittsburgh, and ~34% for the Illinois. The ash contents determined by CONSOL also show ~6% of ash reduction for the Wyodak samples, ~20% for the Pittsburgh, and ~45% for the Illinois.

A comparison was made of the properties of the whole resids and the THF soluble fractions of the resids. The data are summarized in Table 4.4-1. The measurements include three from FT-IR Analysis ($\text{H}_{\text{ar}}/\text{H}_{\text{total}}$, H_{OH} , H_{total}) and three from TG-FTIR analysis (char, CO, CO_2). In general, it appears that the

results for H_{ar}/H_{total} and TG-char show similar trends between the whole resid and the THF soluble portions. The rest of the measurements are not as well correlated.

One of the most interesting comparisons in this table is the data on CO and CO₂ evolution from the Wyodak samples. The whole resids evolve large quantities of CO and CO₂ upon pyrolysis in the TG-FTIR, while the THF soluble fractions evolve very small amounts by comparison. The observations made on the whole resids had led us to believe the Wyodak resids had been oxidized since the elemental analysis was completed. The oxidized organic material must be concentrated in the insoluble organic fraction (IOM) according to this reasoning.

A second possibility is that the excess CO and CO₂ arises from the ash material which is removed from the THF soluble fraction. Pure calcite (CaCO₃) decomposes at about 750°C to produce mainly CaO and CO₂. However, in the presence of coal the decomposition temperature is lower and additional amounts of CO are produced which are believed to result from catalytic decomposition of phenols by CaO (55). The temperature of the main CO₂ evolution peak for the whole resid samples is somewhat lower (~ 680°C) but is within the range of values observed for calcite in coal or mixed with coal.

The main CO₂ peak for these whole resids is also fairly sharp, indicative of a mineral peak rather than the broad peak usually observed for organic CO₂ evolution in the TG-FTIR. This sharp peak is absent in the THF soluble fractions, as expected. In addition, the FT-IR results (column 69, Appendix B) also indicate large amounts of calcite for the whole resids. The only problem with this explanation is that the CO₂ produced from the calcite would be expected to show up as oxygen in the difference calculations. The oxygen (by difference) numbers supplied by CONSOL for the whole resid samples were not unusually large.

HRI Runs - The pressure-filter liquid (PFL) samples from HRI were chosen to represent production of material from a Continuous Two-Stage Liquefaction (CTSL) facility for different periods of time in a single run. These samples are the heaviest portion of the liquid product, and they are recycled to mix with feedstocks. It has been reported by CONSOL that the properties of the PFL product from CTSL changed with the run period. These changes corresponded to declines in the qualities of the product

**TABLE 4.4-1 Comparison of Properties of Whole Resids and THF Soluble Fractions
as Revealed by FT-IR and TG-FTIR Analysis**

Sample No.	Coal		$H_{ar}/H_{total}, \%$		$H_{OH}, wt. \% MAF \times 1000$		$H_{total}, wt. \% MAF$		TG-char wt. % MAF		TG-CO wt. % MAF		TG-CO ₂ wt. % MAF	
	a	b	a	b	a	b	a	b	a	b	a	b	a	b
1	10 (Int)			23	73	75	6.7	10.0	23	13	10.9	1.2	8.6	0.8
2	11 (Rec)			18	55	61	6.7	10.9	20	9	8.5	1.0	6.5	0.0
3	12 (2nd)			17	55	44	7.7	9.7	21	12	10.2	0.6	9.3	0.6
4	13 (Int)			29	73	59	6.8	6.7	28	23	1.2	0.6	1.7	0.4
5	14 (Rec)			23	53	64	6.8	9.7	23	20	0.8	0.5	1.0	0.5
6	15 (2nd)			25	66	59	6.3	9.0	28	22	1.1	0.3	1.0	0.0
7	16 (Int)			18	70	59	8.8	9.7	18	14	1.8	0.4	1.4	0.3
8	17 (Rec)			14	53	45	9.8	11.5	14	8	0.5	1.0	1.4	0.0
9	18 (2nd)			13	50	48	9.6	10.9	16	10	1.4	1.1	0.7	2.3

Notes: a = Whole Resid
b = THF Soluble Portion

analyzed, for example, the increase in resid and phenolic content as the run progressed. These changes in product properties are due to catalyst aging as well as to the reduction in the solvent/coal ratio with run time.

The PFL samples were analyzed by the FT-IR method at AFR. Interpretation of the data provided by AFR and CONSOL reveals a consistent variation of the properties of the samples with the length of run period of the HRI CTSL facility. The interpretation of these variations is discussed below.

Hydrogen Analysis: The variation of the hydrogen content of the sample with the length of the run period is shown in Fig. 4.4-9. The results show that the total hydrogen and aliphatic hydrogen content decreases with increasing run time, whereas the aromatic hydrogen shows an opposite trend. Fig. 4.4-10 gives both AFR and CONSOL results showing the variation of the aromatic hydrogen fraction (H_{ar}/H_{total}) with the length of the run period.

The decrease of the hydrogen content of the liquefaction product with run time may be attributable to catalyst aging as well as to the reduction in the solvent/coal ratio and to the increase in solvent cut point, as stated by CONSOL. It is reasonable to observe a reduction in aliphatic hydrogen content since the hydrogenation rate slows down with time due to catalyst aging. The increase in H_{ar}/H_{total} with run time may also result from the increasing reaction temperature which would tend to increase the amount of aromatic hydrogen.

Oxygen Analysis: The variation of the hydroxyl and ether contents of the samples with the length of the run period is shown in Fig. 4.4-11. Both AFR (-OH) and CONSOL (phenolic -OH) results show an increase of the hydroxyl content with run time. The change in -OH concentration is due to catalyst aging as well as to the reduction in the solvent/coal ratio and to the increase in solvent cut point. It is of interest to note that the FT-IR results obtained by AFR also show an increase in the ether content with time. The increase of the ether content in the liquefaction products can be attributed mostly to the catalyst aging which would result in slowing down bond cleavage on ether linkages. A second possibility is an increase in the amount of ethers formed from retrogressive reactions involving hydroxy and dihydroxy functionalities structures.

Carbon Analysis: The carbon analyses obtained by AFR and provided by CONSOL both show an increase in the carbon content of liquefaction product with the length of the run period. The results are shown in Fig. 4.4-12. This increase can also be explained by the catalyst aging which reduces the hydrogenation rate and results in a corresponding increase in the carbon content of the product.

4.5 Feasibility of On-Line Analysis

Background - The feasibility of on-line FT-IR analysis rests on two questions: 1) is the information useful? 2) are there any technical barriers that must be overcome? The results in sections 4.2 and 4.4 demonstrate the utility of FT-IR analysis in monitoring the quality of the process streams and, indirectly, the catalyst aging. Given that it would be a good idea to have this information in real time, how might this be accomplished?

Two recent technological developments have made in-situ FT-IR measurements possible:

- The development of new infrared transmitting optical fibers with low optical loss and sufficient mechanical strength and temperature range to meet the demanding conditions of many process environments.
- The availability of an improved, ruggedized low-cost FT-IR spectroscopy utilizing PC computers and software.

Recent improvements in IR fiber technology, particularly in the mid-IR wavelengths have dramatically opened the so called "fingerprint region" to remote fiber measurements (56-61). The properties of these and other fibers used in fiber optic FT-IR spectroscopy are shown in Table 4.5-1.

TABLE 4.5-1. CHARACTERISTICS OF IR FIBER MATERIALS

Property	Chalcogenide	Fluoride	EFG ¹ Sapphire	LAPG ² Sapphire	AgBr/Cl
Core Diameter	250 μ	250 μ	250 μ	250 μ	250 μ
Coating Thickness	45 μ	45 μ	none	none	none
Cladding Thickness	30 μ	40 μ	core only	core only	core only
Wavelength Range	3 to 10 μ 3300-100 cm ⁻¹	0.5 to 4.3 μ 20,000-2325 cm ⁻¹	0.2 to 4 μ 50,000-2500 cm ⁻¹	0.2 to 4 μ 50,000-2500 cm ⁻¹	3 to 20 μ 3300-500 cm ⁻¹
Attenuation	0.5 dB/m at 6 μ m	0.02 dB/m at 2.6 μ	20 dB/m at 3 μ	2 dB at 3 μ	0.7dBm at 10.6 μ
Refractive Index	2.9	1.51	1.7	1.7	2.0
Use Temperature	400°C	250°C	>900°C	>1400°C	400°C

- ¹ EFG - Edge Fed Growth Method
² LAPG - Laser Assisted Pedestal Growth Method

In order to accommodate the temperature (~400 °C) and pressure (~3000 psig) requirements of a coal liquefaction process, a sapphire fiber optic element used in the Attenuated Total Reflectance (ATR) mode (see below) would probably be required for in-situ measurements. This will cut out the information below about 2000 cm⁻¹ (see Table 4.5-1 and Fig. 4.1-1) but will allow significant amounts of chemical structural information to be obtained, particularly if a spectrometer system is used which can make measurements in the near-infrared region, which meets the visible region at about 12,500 cm⁻¹ (0.8 μ m) and extends to about 4000 cm⁻¹ (2.5 μ m). In this region one can find several absorption bands resulting from harmonic overtones of fundamental bands and combination bands often associated with hydrogen atoms. Some examples are the first overtones of the O-H and N-H stretching vibrations near 7140 cm⁻¹ (1.4 μ m) and 6667 cm⁻¹ (1.5 μ m), respectively, and combination bands resulting from C-H stretching and deformation vibrations of alkyl groups at 4548 cm⁻¹ (2.2 μ m) and 3850 cm⁻¹ (2.6 μ m), respectively. There are some parts of a liquefaction process where the much better transmitting properties of chalcogenide fibers could be used (see Table 4.5-1). However, these materials also are much more brittle than the sapphire fibers and do not transmit IR light well at temperatures above 300 °C. Because the sapphire fibers have relatively high losses, in an actual

process situation they would be coupled with zirconium fluoride fiber cables to bring the signal to the spectrometer.

An in-situ high temperature probe could be based on the approach of Compton et al. (62) who used a mid-IR transmitting optical fiber to monitor a composite curing reaction. The fiber was run from the spectrometer to the measurement point and back to the spectrometer, with its usual cladding for high transmission. The cladding was removed at the measurement point. The region with the cladding removed acts as an Attenuated Total Reflectance (ATR) detector. The basis for ATR spectroscopy is the phenomenon whereby a light beam reflecting at a surface with a high refractive index actually penetrates a short distance into the adjoining medium with a low refractive index. The use of suitable high refractive index crystals (Internal Reflection Elements or IRE) will allow an IR beam inside the IRE to be used to analyze the composition of the adjacent surface. The details of ATR spectroscopy are described by Harrick (63) and by Sperline et al (64). In principle, if the fiber can be brought into proximity with the liquid, it will be sensitive to the composition. The appropriate length of the F-O/ATR element depends on the fiber, the application and the process conditions.

A related issue is the fact that the pathlength is a function of wavelength. However, this can be dealt with as discussed by Sperline et al. (64) to obtain quantitative spectra.

Many of these issues will be addressed by AFR in a DOE sponsored Phase I SBIR program titled "In-Situ FT-IR Diagnostics for Coal Liquefaction Processes", which is scheduled to be completed in March, 1992.

Application to Coal Liquefaction Processes - Table 4.5-2 compares the results from FT-IR analysis of a whole process oil from a recycle stream and the 850°F⁺ resid from the same sample. Even though the distillate amount was only ~ 6 wt.% (as det.), the analyses are quite different. The changes were all in the direction of what would be expected by the addition of a small amount of hydrogen rich material (distillate) to the resid. In a previous section, Table 4.4-1 compares FT-IR analyses on the whole resids from the three different sampling points. These results consistently show the recycle and 2nd stage samples as being closer in composition than the interstage sample, which is expected

based on the process design. From these two examples, one can conclude that FT-IR is a reliable and sensitive monitor of the changes in liquefaction process streams. This is the first requirement for an on-line diagnostic tool.

The second requirement is that the method is able to measure parameters which are of direct interest in process control. There are three quantities which would be desirable to measure on-line in a coal liquefaction process stream which reflect product quality and catalyst activity: 1) Hydroxyl concentrations; 2) Total hydrogen concentration; 3) Aromatics concentration. All of these can be measured by FT-IR, as discussed above and in Sections 4.2 and 4.4, even in cases where a fiber optic is used which cuts off below 2000 cm^{-1} (e.g., sapphire). In addition, it is reasonable to assume that the use of chemometric techniques such as factor analysis would allow correlations to be developed between the chemical information provided by FT-IR analysis and other chemical and physical properties.

If a more transparent fiber is used, such as chalcogenide, the FT-IR analysis can provide additional information about the distribution of aromatic hydrogens, the ether and carbonyl concentrations, and the ash content. Except for the ash content, these are probably of second order importance in a process control strategy. There are additional quantities such as the molecular weight distribution and nitrogen and sulfur content which cannot be measured by on-line FT-IR spectroscopy. These quantities could be inferred (boiling range) or measured (N and S) by TG-FTIR analysis in about one hour, although there are competing techniques which are also suitable.

In principal the on-line FT-IR measurements can be made by using a relatively short length of fiber-optic as the sensing element and bringing the material to be analyzed in contact with that surface. In order to provide a reliable measurement the material has to be in solution and must be within ~ 10 micron of the surface of the fiber. This requirement would eliminate possibility of making measurements on ash components unless they are well dispersed in the liquid. The presence of particles in slurry form (either ash, coal, or catalyst) should not interfere with the measurements on the liquid phase unless they irreversibly stick to the surface of the fiber or cause problems with erosion. These are questions which can only be answered through actual testing.

TABLE 4.5-2 Comparison of FT-IR Analysis of a Whole Process Oil and Resid Fraction
from Liquefaction of Pittsburgh Seam Coal

(All values wt. % MAF unless noted)

Sample No.	H _{al}	H _{OH}	H _{ar}	H _{total} *	H _{ar} /H _{total} (%)	Carbonyl (abs x cm ⁻¹)	O _{ether}	Carbon	Ash (dry wt. %)
5	4.9	0.05	1.9	6.8	28	1.6	0.4	91.9	10.7
23	8.7	0.08	2.4	11.1	21	5.1	1.4	86.3	8.7

* H_{total} = H_{al} + H_{OH} + H_{ar} from FT-IR Analysis

An alternative approach would be to make the measurements on-line but not in-situ by using a spectrometer set-up next to the process which is equipped with a large flat ATR crystal. A sample of the process stream is withdrawn and "painted" onto the surface of the crystal. An FT-IR spectrum can be obtained in a manner of minutes (as opposed to seconds for the in-situ fiber optic approach) and an ATR crystal can be selected which includes the entire mid-IR region. Such an instrument is already commercially available from Nicolet to allow rapid analysis of used motor oil in order to diagnose engine problems.

5. CONCLUSIONS AND RECOMMENDATIONS

Both FT-IR and TG-FTIR have been clearly shown to provide a wide variety of useful information for process stream characterization. Both techniques can be applied to whole process oils, resids, or distillates, including ash components, and require relatively small samples (<50 mg). Significant differences are observed between process stages, coal types, and with catalyst aging. Both methods indicate that trends observed for the raw coals do not always hold when comparing the resid samples derived from these coals. A summary of the composition parameters that can be obtained by FT-IR and TG-FTIR is shown in Tables 1-1 and 1-2, respectively. In many respects, FT-IR is probably the single most useful technique for this purpose, since it can provide measurements on both organic and mineral components. The current FT-IR method can be made more quantitative for the mineral components and the organic functional groups by a re-optimization of the curve resolving program for coal liquefaction samples. FT-IR is also one of the few current techniques which is amenable to on-line analysis. FT-IR can provide information on total hydrogen content, hydroxyl content and aromatic hydrogen content, all of which are useful for monitoring product quality and catalyst activity. It is reasonable to assume that the chemical information provided by FT-IR could be correlated with other chemical and physical properties using chemometric techniques such as factor analysis. It is likely that on-line FT-IR measurements could be made in-situ using a sapphire fiber optic element in the Attenuated Total Reflectance (ATR) mode.

The TG-FTIR method can provide proximate analysis information (volatiles, fixed carbon, moisture, and ash) for feed coals and residues. In principle, it can also provide elemental analysis information, if a post-oxidizer accessory is used and two runs are made for each sample. Similar to the case of FT-IR, a very broad characterization of a sample can be achieved with a single instrument in a relatively short

amount of time (30-60 minutes). The technique would be very useful in a quality control application for feed coals and heavy process streams like resids. It also has the potential to provide indirect measurement of the average structural components based on the pyrolysis measurements, as was demonstrated for methyl groups, phenolic groups and condensed aromatic rings.

6. ACKNOWLEDGEMENTS

This work was supported by a subcontract from the Consolidation Coal Company under U.S., Department of Energy Contract No. DE-AC22-89PC89883. The authors also wish to acknowledge Dr. Susan Brandes and Mr. Richard Winschel of CONSOL Research and Development for many helpful discussions. Marie DiTaranto of Advanced Fuel Research did the FT-IR analyses. Robert Carangelo consulted on the interpretation of the FT-IR and TG-FTIR results. The preparation of the manuscript and illustrations was ably performed by Laura Jamieson and Lori Bellone.

7. REFERENCES

1. Solomon, P.R., and Carangelo, R.M., *Fuel*, **61**, 663 (1982).
2. Solomon, P.R., and Carangelo, R.M., *Fuel*, **67**, 949 (1988).
3. Solomon, P.R., Serio, M.A., Deshpande, G.V., Kroo, E., Schobert, H., & Burgess, C., An Investigation of the Chemistry of Catalytic Preliquefaction, in "Recent Advances in Coal Science", ACS Symp. Series, (H. Schobert, K. Bartle, & L. Lynch, Eds.), pp. 193-212, (1991).
4. Solomon, P.R., Serio, M.A., Deshpande, G.V., and Kroo, E., Crosslinking Reactions During Coal Conversion, *Energy & Fuels*, **4**, (1), 42, (1990).
5. Hamblen, D.G., Solomon, P.R., Tarantul, K.S., and Carangelo, R.M., Correlations Between Fuel Structure and Sooting Potential, *ACS Div. of Petroleum Chemistry*, **32**, (2), 530, (1987).
6. Serio, M.A., Malhotra, R., Kroo, E., Deshpande, G.V., and Solomon, P.R., A Study of Thermal Stability of JP-5 Using FT-IR and FIMS, *ACS Div. of Petroleum Chemistry*, **34**, (4), 816, (1989).
7. Painter, P.C., Coleman, M.M., Jenkins, R.G., Whang, P.W., and Walker, P.L., Jr., *Fuel*, **57**, 337 (1978).
8. Painter, P.C., Coleman, M.M., Jenkins, R.G. and Walker, P.L., Jr., *Fuel*, **57**, 125 (1978).
9. Painter, P.C., Snyder, R.W., Pearson, D.E. and Kwong, J., *Fuel*, **59**, 282 (1980).
10. Painter, P.C. and Coleman, M.M., *Fuel*, **58**, 301 (1979).

11. Painter, P.C., Yamada, Y., Jenkins, R.G., Coleman, M.M., and Walker, P.L., Jr., *Fuel*, **58**, 293 (1979).
12. Solomon, P.C., *Adv. Chem. Ser.*, **192**, 95 (1981).
13. Solomon, P.R., Hamblen, D.G., and Carangelo, R.M., 'Applications of Fourier Transform IR Spectroscopy in Fuel Science', *Am. Chem. Soc. Symp. Ser.*, **205**, 77 (1982).
14. Solomon, P.R., *Fuel*, **60**, 3 (1981).
15. Solomon, P.R., and Miknis, F.P., *Fuel*, **59**, 893 (1980).
16. Solomon, P.R., Hobbs, R.H., Hamblen, D.G., Chen, W., LaCava, A., and Graff, R.A., *Fuel*, **60**, 342 (1980).
17. Solomon, P.R., Hamblen, D.G., Carangelo, R.M., Markham, J.R., and Chaffe, M.R., *Am. Chem. Soc. Div. Fuel Chem. Prepr.*, **30** (1), 1 (1985).
18. Kuehn, D.W., Snyder, R.W., Davis, A., and Painter, P.C., *Fuel*, **62**, 682 (1982).
19. Painter, P.C., Starsinic, M., Squires, E. and Davis, A.A., *Fuel*, **63**, 742 (1983).
20. Sobkowiak, M., Riesser, E., Given, R., and Painter, P., *Fuel*, **63**, 1245 (1984).
21. Riesser, B., Starsinic, M., Squires, E., Davis, A., and Painter, P.C., *Fuel*, **63**, 1253 (1984).
22. Painter, P.C., Snyder, R.W., Starsinic, M., Coleman, M.M., Kuehn, D.W., and Davis, A., *Appl. Spect.*, **35**, 475 (1981).
23. Osawa, Y. and Shih, J.W., *Fuel*, **50**, 53 (1971).
24. Yarzab, R.F., Abdel-Baset, Z. and Given, P.H., *Geochim. Cosmochim. Acta.*, **43**, 281 (1979).
25. Ottaway, W., *Fuel*, **61**, 713 (1982).
26. Ciuryla, V.T., Welmer, R.F., Bivans, A., Motika, S.A., *Fuel*, **58**, 748 (1979).
27. van Krevelen, D.W., van Heerden, C., Huntjens, F.J., *Fuel*, **30**, 253 (1951).
28. Solomon, P.R., Serio, M.A., Heringer, S.G., *Prepr. pap. - Am. Chem. Soc., Div. Fuel Chem.*, **31** (3), 200 (1986).
29. Best, P.E., Solomon, P.R., Serio, M.A., Suuberg, E.M., Mott, W.R., Jr., Bassilakis, R., *Prepr. Pap - Am. Chem. Soc., Div. Fuel Chem.*, **33** (4), 138 (1987).
30. Serio, M.A., Solomon, P.R., Bassilakis, R., Suuberg, E.M., *Prepr. Pap - Am. Chem. Soc., Div. Fuel Chem.*, **34** (1), 9 (1989).
31. Serio, M.A., Solomon, P.R., Suuberg, E.M., The Variation in Char Reactivity with Pyrolysis Conditions and Coal Type, submitted for Presentation at the Twenty-Fourth International Symposium on Combustion.
32. Jenkins, R.G., Nandi, S.P., Walker, P.L., Jr., *Fuel*, **52**, 228 (1973).

33. Sahu, R., Levendis, Y.A., Flagan, R.C., Gavalas, G.R., *Fuel*, **67**, 275 (1988).
34. Suuberg, E.M., Calo, J.M., Wojtowicz, W., *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.*, **31** (3), 186 (1986).
35. Juntgen, H., van Heek, K.H., *Fuel Process. Technol.*, **2**, 261 (1979).
36. Winans, R.E., McBeth, R.L., Neill, P.H., *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.*, **33** (3), 85 (1988).
37. Chakravarty, T., Windig, W., Hill, G.R., Meuzelaar, H.L.C., *Energy Fuels*, **2**, 400 (1988).
38. Solomon, P.R., Hamblen, D.G., *Finding Order in Coal Pyrolysis Kinetics; Topical Report submitted to U.S. Department of Energy under Contract No. DE-AC21-81-FE05122; also Prog. Energy Combust. Sci.*, **9**, 323 (1983).
39. Fitzgerald, D., van Krevelen, D.W., *Fuel*, **38**, 17 (1959).
40. Campbell, J.H. *Fuel*, **57**, 217 (1978).
41. Burnham, A.K., Oh, M.S., Crawford, R. W., Samoun., A.M., *Energy Fuels*, **3**, 42 (1989).
42. Weimer, R.F., Ngan, D.Y. *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.*, **24** (3), 129 (1979).
43. Attar, A., Dupuis, F., *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.*, **23** (2), 44 (1978).
44. Attar, A., Hendrickson, G.G., *Coal Structure; Meyers, R.A., Ed.; Academic Press: New York, Chapter 5 p. 131* (1982).
45. LaCount, R.B., Anderson, R.R., Friedman, S., Blaustein, B.D., *Fuel*, **66**, 873 (1987).
46. Hall, P.J., Calo, J.M., *Energy Fuels*, **3**, 370 (1989).
47. Zhang, Z.G., Kyotani, T., Tomita, A., *Energy Fuels*, **3**, 566 (1989).
48. Kyotani, T., Zhang, Z.G., Hayashi, S., Tomita, A., *Energy Fuels*, **2**, 1136 (1988).
49. Carangelo, R.M., Solomon, P.R., and Gerson, D.J., Application of TGA/FT-IR to Study Hydrocarbon Structure and Kinetics, *ACS Div. of Fuel Chem. Preprints*, **31**, (1), 152, (1986).
50. Whelan, J.K., Solomon, P.R., Deshpande, G. V., and Carangelo, R.M., Thermogravimetric Fourier Transform Infrared Spectroscopy (TG-FTIR) of Petroleum Source Rock - Initial Results, *Energy and Fuel*, **2**, 65, (1988).
51. Serio, M.A., Solomon, P.R., Yu, Z.Z., Deshpande, G., V., *An Improved Model of Coal Devolatilization. In International Conference on Coal Science Proceedings; IEA: Tokyo, Japan, p. 209* (1989).
52. Solomon, P.R., Serio, M.A., Carangelo, R.M., Bassilakis, R., Gravel, D., Baillargeon, M., Baudas, F., and Vail, G., Analysis of the Argonne Premium Coal Samples by TG-FTIR*, *Energy & Fuels*, **4**(3), 319 (1990).

53. Serio, M.A., Solomon, P.R., Yu, Z.Z., Bassilakis, R., Markham, J.R., Klapheke, J.G., Prepr. pap. - Am. Chem. Soc., Div. Fuel Chem., **34**, (4), 1324 (1989).
54. Serio, M.A., Solomon, P.R., Kroo, E., Bassilakis, R., Malhotra, R., McMillen, D., Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem., **35**, (1), 61 (1990).
55. Franklin, H.D., "Mineral Matter Effects in Coal Pyrolysis and Hydropyrolysis," Ph.D Thesis, Dept. of Chemical Engineering, Mass. Inst. of Tech. (1980).
56. Druy, M., P.R. Young, W.A. Stevenson, and D. Compton, "In Situ Composite Cure Monitoring using Infrared Transmitting Optical Fibers," SAMPE Journal, Vo. 25, No. 2, 1988.
57. Stevenson, W.A., Monitoring Technology, U.S. Patent No. 4,789,954, January 17, 1989.
58. Compton, D.A.C., Hill, S.L., Wright, N.A., Stevenson, W.A. and Piche, J., "In Situ FTIR Analysis of a Composite Curing Reaction using a Mid-Infrared Transmitting Optical Fiber", Applied Spectroscopy (in press) 1989.
59. Compton, D.A.C., Hill, S.L., Wright, N.A., Stevenson, W.A. and Piche, J., "In Situ FTIR Analysis of Samples Using a Mid-Infrared Transmitting Fiber Optic Probe," presented at 1988 Pittsburgh Conference, New Orleans, LA, 1988.
60. Druy, M.A., "Composite Cure Monitoring with Infrared Transmitting Optical Fibers," Proc. SPIE, 986 (Fiber Optic Smart Structures and Skins), 1988.
61. Druy, M.A., "In Situ Composite Cure Monitoring Using Infrared Transmitting Optical Fibers," SAMPE J., 25 (2), 1989, 20th International SAMPE Technical Conference, Minneapolis, MN, September, 1988.
62. Compton, D.C., Hill, S.L., Wright, N.A., Druy, M.A., Piche, J., Stevenson, W.A., Vidrine, D.W., "In Situ FT-IR Analysis of a Composite Curing Reaction Using a Mid-Infrared Transmitting Optical Fiber", Appl. Spectr., **42**(6), 972, (1988).
63. Harrick, N.J., Internal Reflection Spectroscopy, Harrick Scientific Corp., Ossining, New York, 1979, 2nd printing.
64. Sperline, R.P., Muralidharan, S., and Freiser, H., Applied Spectroscopy, **40**(7), 1019, (1986).

8. FIGURES

Figure 4.1-1. FT-IR Spectrum of THF Soluble Portion of Recycle Oil Resid from Wyodak Coal, Wilsonville, Run 251-III (sample #2) Showing Regions Used for Quantitative FT-IR Analysis.

Figure 4.1-2. Correction of Resid Spectrum for Scattering and Minerals. a) Correction of Resid Spectrum; b) Determination of Mineral Spectrum by Addition of Reference Spectra. Data for Whole Resid Sample (2nd stage) from Illinois No. 6 Coal, Run 257 (sample #9).

AFR1501 (AFR#5) w: run 259

AFR1501 (AFR#5) w: run 259

Figure 4.1-3. TG-FTIR Results for Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #5).

AFR 1501 AFR#5

Figure 4.1-4. TG-FTIR Post Combustion Results for Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #5).

Figure 4.1-5. Spectrum from TG-FTIR During Pyrolysis of Recycle Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #8). The Spectrum was Taken at a Temperature of 730°C.

Figure 4.2-1. Comparison of Aromatic Hydrogen Distributions.

Figure 4.2-2. Comparison of Aliphatic Hydrogen Distributions.

Figure 4.2-3. Comparison of Hydroxyl Content.

Figure 4.2-4. Comparison of Oxygen Contents.

Figure 4.2-5. Comparison of Hydrogen Contents.

Figure 4.2-6. Comparison of Carbon Contents.

Figure 4.2-7. Comparison of Ash Contents.

Figure 4.2-8. Comparison of CaO Contents.

Figure 4.3-1. Comparison of Char Yield with Fixed Carbon.

Figure 4.3-2. Comparison of Coal Ash Contents.

Figure 4.3-3. Comparison of Volatile Contents in Coal.

Figure 4.3-4. Comparison of Moisture Contents in Coal.

Figure 4.3-5. Comparison of Ash Contents for Resids.

Figure 4.3-6. Comparison of Char Yield with Condensed Aromatic Proton Fraction.

Figure 4.4-1. Phenolic-OH Content at Different Stages for Wilsonville Resids.

Figure 4.4-2. OH Content at Different Stages for Wilsonville Resids.

Figure 4.4-3. CO Evolution from Pyrolysis of Wilsonville Resids.

Figure 4.4-4. CH₄ Evolution from Pyrolysis of Wilsonville Resids.

Figure 4.4-5. Hydrogen Content at Different Stages for Wilsonville Resids.

Figure 4.4-6. Aromatic Hydrogen Fraction at Different Stages for Wilsonville Resids.

Figure 4.4-7. Aromatic Hydrogen Content at Different Stages for Wilsonville Resids.

Figure 4.4-8. Efficiency of Deash Process for Wilsonville Resids.

Figure 4.4-9. Hydrogen Analysis for HRI Liquids.

Figure 4.4-10. Aromatic Hydrogen Content with Time for HRI Liquids.

Figure 4.4-11. Oxygen Functional Group Analysis for HRI Liquids.

Figure 4.4-12. Carbon Content with Time for HRI Liquids.

APPENDIX A

Summary of Samples Analyzed

SAMPLES

Ref. No.	Coal Feed	Source/Conditions	Comments
<u>Quantitative FTIR</u>			
1.	Wyodak	W; Run 251-III; C/C	Interstage oil resid
2.	Wyodak	W; Run 251-III; C/C	Recycle oil resid
3.	Wyodak	W; Run 251-III; C/C	2nd stage PO resid
4.	Pittsburgh seam	W; Run 259; C/C	Interstage oil resid
5.	Pittsburgh seam	W; Run 259; C/C	Recycle oil resid
6.	Pittsburgh Seam	W; Run 259; C/C	2nd stage PO resid
7.	Illinois No.6	W; Run 257; C/C	Interstage oil resid
8.	Illinois No.6	W; Run 257; C/C	Recycle oil resid
9.	Illinois No.6	W; Run 257; C/C	2nd stage PO resid
10.	THF-sol. portion of Sample 1		
11.	THF-sol. portion of Sample 2		
12.	THF-sol. portion of Sample 3		
13.	THF-sol. portion of Sample 4		
14.	THF-sol. portion of Sample 5		
15.	THF-sol. portion of Sample 6		
16.	THF-sol. portion of Sample 7		
17.	THF-sol. portion of Sample 8		
18.	THF-sol. portion of Sample 9		
19.	Illinois No.6	HRI; Run I-27	PFL P 2
20.	Illinois No.6	HRI; Run I-27	PFL P 9
21.	Illinois No.6	HRI; Run I-27	PFL P 18
22.	Illinois No.6	HRI; Run I-27	PFL P 25
23.	Pittsburgh seam	W; Run 259 E	Whole Process Oil
<u>TG-FTIR</u>			
24.	Illinois 6	COAL	Ground to pass 100 mesh
25.	Pittsburgh seam	COAL	" " " " "
26.	Wyodak	COAL	" " " " "
1.	Wyodak	W; Run 251-III; C/C	Interstage oil resid
2.	Wyodak	W; Run 251-III; C/C	Recycle oil resid
3.	Wyodak	W; Run 251-III; C/C	2nd stage PO resid
4.	Pittsburgh seam	W; Run 259; C/C	Interstage oil resid
5.	Pittsburgh seam	W; Run 259; C/C	Recycle oil resid
6.	Pittsburgh Seam	W; Run 259; C/C	2nd stage PO resid
7.	Illinois No.6	W; Run 257; C/C	Interstage oil resid
8.	Illinois No.6	W; Run 257; C/C	Recycle oil resid
9.	Illinois No.6	W; Run 257; C/C	2nd stage PO resid
10.	THF-sol. portion of Sample 1.		
11.	THF-sol. portion of Sample 2.		
12.	THF-sol. portion of Sample 3.		
13.	THF-sol. portion of Sample 4.		
14.	THF-sol. portion of Sample 5.		
15.	THF-sol. portion of Sample 6.		
16.	THF-sol. portion of Sample 7.		
17.	THF-sol. portion of Sample 8.		
18.	THF-sol. portion of Sample 9.		
<u>On-line</u>			
23.	Pittsburgh seam	W; Run 259 E	Whole Process Oil

Note: PO = Process Oil (may contain IOM and ash); W = Wilsonville;
C/C = Catalytic/Catalytic; PFL = Pressure Filter Liquid; P = Period

APPENDIX B

Table of Analytical Data

INDEX TO TABLE OF ANALYTICAL DATA

Row Directory

1-3	Wilsonville Resids (whole), Wyodak
4-6	Wilsonville Resids, (whole), Pittsburgh
7-9	Wilsonville Resids, (whole), Illinois
10-12	Wilsonville Resids (THF soluble), Wyodak
13-15	Wilsonville Resids (THF soluble), Pittsburgh
16-18	Wilsonville Resids (THF soluble), Illinois
19-22	HRI Pressure Filter Liquids
23	Wilsonville, Whole Process Oil, Pittsburgh
24	Illinois No. 6 Coal Sample
25	Illinois No. 6 Coal Sample (repeat)
26	Pittsburgh Seam Coal Sample
27	Wyodak Coal Sample

Column Directory

Data Supplied by Consol

1.	Ref. No.	34.	Oils (sol. fraction %)
2.	Plant	35.	Asphaltenes (sol. fraction %)
3.	Run No.	36.	Preasphaltenes (sol. fraction %)
4.	Sample Design	37.	Phenolic-OH (meq/g, THF sol.)
5.	Sampling Point	38.	Phenolic-OH (wt.%, THF sol.)
6.	Feed Coal	39.	Phenol Peak (1/cm)
7.	Ash Wt.% as det.	40.	Heat. Value (Btu/lb, ash free)
8.	C Wt.% MAF	41.	Insol. Organic (wt.%, dry)
9.	H Wt.% MAF	42.	THF soluble (wt. %, dry)
10.	N Wt.% MAF	43.	850-F Distillate (wt.%, dry)
11.	S Wt.% MAF	44.	Coal Ash (wt. %, dry)
12.	O (dif) Wt.% MAF	45.	Coal Oxygen (wt.%, dry)
13.	Na ₂ O (ash%)	46.	Coal Moisture (wt. %, as
14.	K ₂ O (ash%)	47.	Coal Volatile (wt. %, dry)
15.	CaO (ash%)	48.	Coal Fixed Carbon (wt. %, dry)
16.	CaO (wt.%, dry)	49.	HRI Period (day)
17.	MgO (ash%)		
18.	Fe ₂ O ₃ (ash%)		
19.	TiO ₂ (ash%)		
20.	P ₂ O ₅ (ash%)		
21.	SiO ₂ (ash%)		
22.	Al ₂ O ₃ (ash%)		
23.	SO ₃ (ash%)		
24.	Unaccounted (ash%)		
25.	Cond. Aromatics (proton %)		
26.	Uncond. Aromatics (proton %)		
27.	Con+Uncon. Ar (proton%)		
28.	Cyclic Alpha (proton %)		
29.	Alkyl Alpha (proton %)		
30.	Cyclic Beta (proton %)		
31.	Alkyl Beta (proton %)		
32.	Gamma (proton %)		
33.	Aliphatic (proton %)		

<u>AFR FT-IR Data</u>	
50.	Hal (wt. %) maf/FTIR
51.	Hoh (wt. %) maf/FTIR
52.	Har (wt. %) maf/FTIR
53.	Htotal (wt. %) mat/FTIR
54.	Har/Htotal (%) maf/FTIR
55.	Hal/Htotal (%) maf/FTIR
56.	1 Adj (wt.%) maf/FTIR
57.	2 Adj (wt. %) maf/FTIR
58.	3 or more (wt. %) maf/FTIR
59.	Aliph. Carbon (wt. %) maf/FTIR
60.	Carbonyl (absxcm-1)/FTIR
61.	Ooh (wt. %) maf/FTIR
62.	OH (wt. %) maf/FTIR
63.	Oether (wt. %) maf/FTIR

AFR FT-IR Data

- 64. Ooh+Oether (wt.%) maf/FTIR
- 65. Carbon (wt.%) maf/FTIR (100-O-H)
- 66. Total ash (wt. %, dry)/FTIR Mixed
- 67. Clay (wt. %, dry)/FTIR
- 68. Quartz (wt. %, dry)/FTIR
- 69. Calcite (wt. %, dry)/FTIR
- 70. CaO in Calcite (wt. %, dry)/FTIR
- 71. Kaolin (wt. %, dry)/FTIR

AFR TG-FTIR Data

- 72. TG-wt.%, as rec. Ash
- 73. TG-wt. %, dry, Ash
- 74. TG-wt.% Char daf
- 75. TG-wt.% Tar daf
- 76. TG-wt.% CH 4 daf
- 77. TG-wt.% H2O, as rec.
- 78. TG-wt.% H2O pyr. daf
- 79. TG-wt.% CO2 daf
- 80. TG-wt.% CO daf
- 81. TG-wt.% SO2 daf
- 82. TG-wt.%, dry, Coal Char
- 83. TG-wt.%, dry, Coal Ash
- 84. TG-wt.%, dry Coal Volatile
- 85. TG-wt.%, MAF, H2O, Combustion
- 86. TG-wt.%, MAF, CO, Combustion
- 87. TG-wt.%, MAF, CO2, Combustion
- 88. TG-wt.%, MAF, SO2, Combustion

Analytical Data					
1	2	3	4	5	
Ref. No.	Plant	Run. No	Sample Design	Sampling Point	
1	1.000	Wilsonville	251-III	V1258	Interstage
2	2.000	Wilsonville	251-III	V131B	Recycle
3	3.000	Wilsonville	251-III	V1067	2ng Stage Prod.
4	4.000	Wilsonville	259	R1235	Interstage
5	5.000	Wilsonville	259	V131B	Recycle
6	6.000	Wilsonville	259	V1067	2ng Stage Prod.
7	7.000	Wilsonville	257	R1235	Interstage
8	8.000	Wilsonville	257	V131B	Recycle
9	9.000	Wilsonville	257	V1067	2ng Stage Prod.
10	10.000	Wilsonville	251-III	R1258	Interstage
11	11.000	Wilsonville	251-III	V131B	Recycle Stream
12	12.000	Wilsonville	251-III	V1067	2ng Stage Prod.
13	13.000	Wilsonville	259	R1235	Interstage
14	14.000	Wilsonville	259	V131B	Recycle Stream
15	15.000	Wilsonville	259	V1067	2nd Stage Prod.
16	16.000	Wilsonville	257	R1235	Interstage
17	17.000	Wilsonville	257	V131B	Recycle Stream
18	18.000	Wilsonville	257	V1067	2nd Stage Prod.
19	19.000	HRI	1-27	PFL	Day 2 Generated
20	20.000	HRI	1-27	PFL	Day 8 Generated
21	21.000	HRI	1-27	PFL	Day 18 Generated
22	22.000	HRI	1-27	PFL	Day 25 Generated
23	23.000	Wilsonville	259G	V131B	5/2/90
24	24.000	III#6 Coal Analysis			
25	24.100	III#6 Coal Analysis			
26	25.000	Pitts Coal Analysis			
27	26.000	Wyod Coal Analysis			

Analytical Data

Mon, Feb 3, 1992 12:57 PM

⁶ Feed Coal		⁷ Ash Wt.% as det.	⁸ C Wt.% MAF	⁹ H Wt.% MAF	¹⁰ N Wt.% MAF
1	Wyodak Seam Clovis Pt. Mine	27.900	87.960	6.660	1.000
2	Wyodak Clovis Pt. Mine	28.640	87.430	6.780	0.910
3	Wyodak Seam Clovis Pt. Mine	30.330	87.400	6.890	0.820
4	Pittsburgh Seam Ireland Mine	8.740	90.120	6.190	1.150
5	Pittsburgh Seam Ireland Mine	8.510	91.010	6.500	1.040
6	Pittsburgh Seam Ireland Mine	10.210	90.240	6.390	1.050
7	Ill.#6 Seam Burning Star #2	12.520	88.050	7.700	0.860
8	Ill.#6 Seam Burning Star #2	9.280	88.640	8.080	0.780
9	Ill.#6 Seam Burning Star #2	13.490	87.990	7.870	0.770
10	Wyodak Seam Clovis Pt. Mine		89.380	7.260	0.880
11	Wyodak Seam Clovis Pt. Mine		89.430	7.920	0.740
12	Wyodak Clovis Pt. Mine		88.750	8.020	0.700
13	Pittsburgh Seam Ireland Mine		89.790	6.490	1.060
14	Pittsburgh Seam Ireland Mine		90.540	6.740	0.910
15	Pittsburgh Seam Ireland Mine		89.800	6.800	1.000
16	Ill.#6 Seam Burning Star #2		88.410	8.040	0.860
17	Ill.#6 Seam Burning Star #2		88.750	8.150	0.660
18	Ill.#6 Seam Burning Star #2		88.320	8.160	0.650
19	Ill.#6 Seam Burning Star #2		88.060	9.140	0.480
20	Ill.#6 Seam Burning Star #2		88.250	8.180	0.590
21	Ill.#6 Seam Burning Star #2		89.580	7.120	0.900
22	Ill.#6 Seam Burning Star #2		90.310	6.500	1.090
23	Pittsburgh Seam Ireland Mine	6.410	83.740	6.920	0.490
24	Ill#6 Coal Analysis				
25	Ill#6 Coal Analysis				
26	Pitts Coal Analysis				
27	Wyod Coal Analysis				

Analytical Data

Mon, Feb 3, 1992 12:57 PM

	11	12	13	14	15	16	17
	S Wt.% MAF	O(dif) Wt.% MAF	Na2O(ash%)	K2O(ash%)	CaO(ash%)	CaO(wt.%,dry)	MgO(ash%)
1	2.580	1.800					
2	2.560	2.330					
3	2.780	2.110	1.370	0.310	22.380	6.788	4.100
4	1.500	1.040	0.520	1.630	2.620	0.229	0.840
5	1.250	0.200	0.520	1.650	2.970	0.253	0.870
6	1.490	0.830	0.510	1.600	2.720	0.278	0.840
7	1.340	2.050					
8	0.790	1.710					
9	1.200	2.160	0.410	1.880	6.550	0.884	0.910
10	0.060						
11	0.030						
12	0.320						
13	0.630						
14	0.390						
15	0.410						
16	0.260						
17	0.140						
18	0.150						
19	0.030						
20	0.060						
21	0.150						
22	0.160						
23	0.760	1.680					
24							
25							
26							
27							

Analytical Data

Mon, Feb 3, 1992 12:57 PM

	18	19	20	21	22	23
	Fe2O3(ash%)	TiO2(ash%)	P2O5(ash%)	SiO2(ash%)	Al2O3(ash%)	SO3ash%)
1						
2						
3	14.940	0.650	0.570	26.770	12.310	14.550
4	20.670	0.910	0.150	44.300	24.770	1.460
5	20.760	0.930	0.150	44.010	25.290	1.090
6	21.830	0.910	0.150	43.890	24.300	1.370
7						
8						
9	17.120	0.760	0.150	46.770	17.740	6.150
10						
11						
12						
13						
14						
15						
16						
17						
18						
19						
20						
21						
22						
23						
24						
25						
26						
27						

Analytical Data

Mon, Feb 3, 1992 12:57 PM

	24 Unaccounted(ash%)	25 Cond. Aromatics(proton%)	26 Uncond. Aromatics(proton%)	27 Con+Uncon. Ar(proton%)
1		30.000	3.500	33.500
2		23.200	3.500	26.700
3	2.050	17.100	3.800	20.900
4	2.130	30.700	2.600	33.300
5	1.760	26.100	5.400	31.500
6	1.880	27.800	3.800	31.600
7		18.100	3.700	21.800
8		16.800	3.100	19.900
9	1.560	16.900	3.400	20.300
10		24.400	4.100	28.500
11		19.100	3.300	22.400
12		18.600	3.200	21.800
13		30.700	2.600	33.300
14		26.100	5.400	31.500
15		28.600	3.600	32.200
16		17.800	4.900	22.700
17		16.700	4.400	21.100
18		17.700	3.000	20.700
19		12.000	2.500	14.500
20		17.800	2.900	20.700
21		25.300	3.900	29.200
22		33.500	4.800	38.300
23		21.700	4.100	25.800
24				
25				
26				
27				

Analytical Data

Mon, Feb 3, 1992 12:57 PM

28		29		30		31	
Cyclic	Alpha(proton%)	Alkyl	Alpha(proton%)	Cyclic	Beta(proton%)	Alkyl	Beta(proton%)
1	21.000		8.800		13.800		16.400
2	21.600		9.000		16.400		17.000
3	20.100		8.700		18.300		22.300
4	20.900		10.200		13.800		13.400
5	18.900		9.400		14.800		14.600
6	21.200		9.600		15.500		13.400
7	19.600		9.200		19.200		19.900
8	19.100		8.900		20.700		20.700
9	19.400		9.200		19.800		20.700
10	17.600		8.900		14.200		20.500
11	18.600		9.200		17.100		22.000
12	19.300		9.200		16.200		22.700
13	20.900		10.200		13.800		13.400
14	18.900		9.400		14.800		14.600
15	21.700		9.100		14.800		13.500
16	18.600		9.200		18.100		19.700
17	17.900		9.400		18.600		20.400
18	18.900		9.300		19.500		19.600
19							
20	19.600		8.700		20.000		19.800
21	20.800		9.400		16.500		15.200
22	19.700		9.100		13.900		11.800
23	17.800		8.400		16.600		20.300
24							
25							
26							
27							

32 33 34 35
Gamma(proton%) Aliphatic (proton%) Oils(sol. fraction%) Asphaltenes(sol. fraction%)

1	6.500	66.500		
2	9.400	73.300		
3	9.700	79.100		
4	8.400	66.700		
5	10.800	68.500		
6	8.700	68.400		
7	10.400	78.200		
8	10.600	80.100		
9	10.700	79.700		
10	10.300	71.500		
11	10.600	77.600		
12	10.700	78.200		
13	8.400	66.700		
14	10.800	68.500		
15	8.700	67.800		
16	11.700	77.300		
17	12.500	78.900		
18	11.900	79.300		
19		85.500	90.600	9.200
20	11.200	79.300	83.000	12.900
21	8.800	70.800	78.200	18.500
22	7.100	61.700	79.000	18.100
23	11.100	74.200		
24				
25				
26				
27				

Analytical Data

Mon, Feb 3, 1992 12:57 PM

36

37

38

Preasphaltenes(sol. fraction%) Phenolic-OH(meq/g, THF sol.) Phenolic-OH(wt%, THF sol.)

1		0.850	1.445
2		0.520	0.884
3		0.570	0.969
4		0.920	1.564
5		0.690	1.173
6		0.700	1.190
7		0.680	1.156
8		0.500	0.850
9		0.570	0.969
10		0.850	1.445
11		0.520	0.884
12		0.420	0.714
13		0.920	1.564
14		0.690	1.173
15		0.700	1.190
16		0.680	1.156
17		0.500	0.850
18		0.570	0.969
19	0.200	0.250	0.425
20	4.100	0.410	0.697
21	3.700	0.660	1.122
22	3.000	0.710	1.207
23			
24			
25			
26			
27			

Analytical Data

Mon, Feb 3, 1992 1:15 PM

39

40

41

42

Phenol Peak (1/cm) Heat. Value(Btu/lb, ash free) Insol. Organic(wt%, dry) THF Soluble(wt%,dry)

1		15843.000	20.400
2		15989.000	16.100
3	3303.000	15922.000	19.300
4		14896.000	
5		15177.000	
6		14845.000	
7		16708.000	21.300
8		17056.000	14.800
9		16915.000	21.300
10			
11			
12			
13			
14			
15			
16			
17			
18			
19	3305.000		
20	3301.000		
21	3297.000		
22	3297.000		
23			53.200
24			
25			
26			
27			

Analytical Data

Mon, Feb 3, 1992 12:57 PM

43 44 45 46
850-F Distillate(wt%,dry) Coal Ash(wt%, dry) Coal Oxygen(wt%,dry) Coal Moisture(wt%, as)

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27

6.410

10.920
10.920
4.680
8.343

8.010
8.010
7.690
19.380

7.610
7.610
0.850
19.890

Analytical Data

Mon, Feb 3, 1992 12:57 PM

47

48

49

50

Coal Volatile(wt%,dry) Coal Fixed Carbon(wt%,dry) HRI Period(day) Hal(wt%)maf/FTIR

1				4.040
2				4.670
3				5.450
4				4.270
5				4.870
6				4.080
7				6.920
8				7.980
9				8.020
10				7.635
11				8.950
12				7.920
13				4.630
14				7.330
15				6.710
16				7.970
17				9.640
18				9.320
19			2.000	8.810
20			9.000	7.830
21			18.000	6.560
22			25.000	5.270
23				8.710
24	38.740		50.340	
25	38.740		50.340	
26	43.820		51.500	
27	48.250		43.410	

Analytical Data

Tue, Feb 4, 1992 4:50 PM

	51	52	53	54
	Hoh(wt%)maf/FTIR	Har(wt%)maf/FTIR	Htotal(wt%)maf/FTIR	Har/Htotal(%)maf/FTIR
1	0.073	2.600	6.710	39.000
2	0.055	2.030	6.730	30.000
3	0.055	2.190	7.690	28.000
4	0.073	2.450	6.770	36.000
5	0.053	1.910	6.850	28.000
6	0.066	2.180	6.290	34.000
7	0.070	1.830	8.840	20.000
8	0.053	1.720	9.770	17.500
9	0.050	1.590	9.630	16.500
10	0.075	2.295	9.960	23.000
11	0.061	1.940	10.910	18.000
12	0.044	1.710	9.700	17.000
13	0.059	1.950	6.660	29.000
14	0.064	2.220	9.660	23.000
15	0.059	2.290	9.000	25.500
16	0.059	1.740	9.720	18.000
17	0.045	1.690	11.520	14.500
18	0.048	1.410	10.930	13.000
19	0.025	1.040	9.900	10.000
20	0.043	1.830	9.660	19.000
21	0.059	2.200	8.820	25.000
22	0.061	2.620	7.450	33.000
23	0.080	2.350	11.090	21.000
24				
25				
26				
27				

55

56

57

58

	Hal/Htotal(%)maf/FTIR	1Adj(wt%)maf/FTIR	2 Adj(wt%)maf/FTIR	3 or more(wt%)maf/FTIR
1	60.209	0.760	.89	0.960
2	69.391	0.590	.69	0.740
3	70.871	0.610	.78	0.795
4	63.072	0.750	.88	0.815
5	71.095	0.580	.71	0.615
6	64.865	0.650	.78	0.750
7	78.281	0.570	.65	0.610
8	81.679	0.500	.605	0.615
9	83.281	0.570	.555	0.470
10	76.657	0.740	.08	0.760
11	82.035	0.660	.66	0.620
12	168.511	0.460	.62	0.600
13	69.520	0.580	.72	0.640
14	75.880	0.650	.85	0.360
15	74.556	0.900	.75	0.635
16	81.996	0.630	.67	0.485
17	83.681	0.450	.69	0.550
18	85.270	0.400	.56	0.440
19	88.990	0.270	.41	0.350
20	81.056	0.640	.65	0.490
21	74.376	0.690	.78	0.720
22	70.738	0.730	.98	0.910
23	78.539	0.640	1.01	0.650
24				
25				
26				
27				

Analytical Data

Mon, Feb 3, 1992 12:57 PM

59 60 61 62
Aliph. Carbon (wt%)maf/FTIR Carbonyl (absxcm-1)/FTIR Ooh(wt%)maf/FTIR OH(wt%)maf/FTIR

1	26.940	5.510	1.200	1.275
2	31.130	5.320	0.870	0.924
3	36.300	6.405	0.880	0.935
4	28.460	0.110	1.200	1.275
5	32.460	1.560	0.850	0.903
6	27.230	1.810	1.100	1.169
7	46.130	7.180	1.100	1.169
8	53.200	6.750	0.850	0.903
9	53.440	8.240	0.810	0.861
10	50.900	8.110	1.230	1.307
11	59.670	9.010	0.980	1.041
12	52.830	3.750	0.700	0.744
13	30.860	0.470	0.940	0.999
14	48.900	2.250	1.020	1.084
15	44.700	4.250	0.940	0.999
16	53.170	10.040	0.940	0.999
17	64.270	6.820	0.720	0.765
18	62.160	5.910	0.770	0.818
19	58.730	5.330	0.390	0.414
20	52.200	6.820	0.680	0.723
21	43.730	2.480	0.930	0.988
22	35.160	3.440	0.980	1.041
23	58.070	5.130	1.250	1.330
24				
25				
26				
27				

Analytical Data

Mon, Feb 3, 1992 12:57 PM

	⁶³ Oether(wt%)maf/FTIR	⁶⁴ Ooh+Oether(wt%)maf/FTIR	⁶⁵ Carbon(wt%)maf/FTIR(100-O-H)
1	1.650	2.850	90.440
2	1.250	2.120	91.150
3	1.550	2.430	89.880
4	0.310	1.510	91.720
5	0.430	1.280	91.870
6	0.430	1.530	92.180
7	0.300	1.400	89.760
8	0.380	1.230	89.000
9	0.750	1.560	88.810
10	0.820	2.050	87.990
11	0.730	1.710	87.380
12	0.000	0.700	94.600
13	0.290	1.230	92.110
14	0.910	1.930	88.410
15	0.950	1.890	89.110
16	0.380	1.320	88.960
17	0.410	1.130	87.350
18	0.310	1.080	87.990
19	0.000	0.390	89.710
20	0.310	0.990	89.350
21	0.480	1.410	89.770
22	0.690	1.670	90.880
23	1.360	2.610	86.300
24			
25			
26			
27			

Analytical Data

Mon, Feb 3, 1992 12:57 PM

66 67 68 69
Total Ash(wt%,dry)/FTIR Mixed Clay(wt%,dry)/FTIR Quartz(wt%,dry)/FTIR Calcite(wt%,dry)/FTIR

1	36.070	4.050	2.100	27.530
2	31.710	3.750	2.820	23.430
3	37.160	3.780	2.450	28.180
4	12.280	5.700	0.290	2.390
5	10.720	5.620	0.000	2.080
6	13.880	6.960	0.580	2.250
7	15.050	8.700	1.780	2.050
8	18.920	7.050	7.780	2.050
9	16.330	8.690	2.270	2.320
10	3.775	0.730	0.000	2.900
11	3.700	1.090	0.000	2.580
12	3.490	1.530	0.000	1.960
13	3.900	1.720	0.000	2.180
14	3.920	1.080	0.000	2.840
15	4.320	1.100	0.000	3.120
16	3.510	1.090	0.110	2.180
17	3.540	2.050	0.000	1.490
18	4.030	2.360	0.000	1.670
19	5.180	1.300	0.000	1.290
20	3.705	0.915	0.005	2.710
21	7.500	0.640	0.000	3.110
22	9.300	0.950	0.000	3.700
23	8.730	6.190	0.000	1.840
24				
25				
26				
27				

Analytical Data

Mon, Feb 3, 1992 12:57 PM

	70	71	72	73
	CaO in Calcite (wt%,dry)/FTIR	Kaolin(wt%,dry)/FTIR	TG-wt%, as rec. Ash	TG-wt%,dry, Ash
1	15.417	2.390	28.300	28.434
2	13.121	1.710	27.200	27.419
3	15.781	2.750	30.800	30.903
4	1.338	3.900	9.110	9.110
5	1.165	3.020	9.500	9.500
6	1.260	4.090	10.200	10.200
7	1.148	2.520	13.400	13.509
8	1.148	2.040	8.730	8.752
9	1.299	3.050	13.300	13.386
10	1.624	0.145	0.206	0.206
11	1.445	0.030	0.251	0.251
12	1.098	0.000	0.200	0.200
13	1.221	0.000	0.980	0.980
14	1.590	0.000	0.000	0.000
15	1.747	0.100	0.980	0.980
16	1.221	0.130	0.000	0.000
17	0.834	0.000	0.000	0.000
18	0.935	0.000	0.000	0.000
19	0.722	2.590		
20	1.518	0.075		
21	1.742	3.750		
22	2.072	4.650		
23	1.030	0.700		
24				
25				
26				
27				

Analytical Data

Wed, Apr 1, 1992 8:05 PM

74 75 76 77 78
 TG-wt% Char daf TG-wt% Tar daf TG-wt% CH₄ daf TG-wt% H₂O, as rec., Moisture TG-wt% H₂O pyr. daf

1	23.128	52.079	1.704	0.471	3.748
2	20.422	58.176	1.383	0.797	3.856
3	20.779	57.091	1.606	0.332	3.190
4	27.798	65.008	1.750	0.000	4.027
5	22.880	67.070	1.460	0.000	4.280
6	28.391	65.558	1.370	0.000	6.571
7	17.500	70.480	1.210	0.700	7.140
8	14.153	73.486	1.190	0.250	2.631
9	15.881	69.901	1.147	0.644	0.000
10	12.676	0.000	1.122	0.000	2.846
11	8.663	0.000	0.831	0.000	0.000
12	12.380	0.000	0.880	0.000	1.620
13	22.880	0.000	1.220	0.000	0.790
14	20.460	0.000	1.050	0.000	1.870
15	21.620	0.000	1.010	0.000	0.000
16	14.200	0.000	0.810	0.000	1.450
17	8.200	0.000	0.860	0.000	0.000
18	10.420	0.000	1.090	0.000	1.850
19					
20					
21					
22					
23					
24	54.170	26.630	2.980	3.330	12.050
25	53.950	25.710	2.880	3.200	11.810
26	54.600	33.080	3.660	1.330	3.550
27	51.460	19.950	2.230	8.740	4.600

79 80 81 82 83
 TG-wt%CO2 daf TG-wt%CO daf TG-wt%SO2 daf TG-wt%,dry, Coal Char TG-wt%,dry,Coal Ash

1	8.568	10.883	0.471		
2	6.501	8.500	0.242		
3	9.335	10.234	0.385		
4	1.677	1.242	0.921		
5	0.980	0.760	0.410		
6	0.974	1.124	0.428		
7	1.420	1.790	0.430		
8	1.390	0.510	0.620		
9	0.694	1.428	1.046		
10	0.802	1.243	0.431		
11	0.000	0.951	0.861		
12	0.580	0.600	0.150		
13	0.430	0.610	0.450		
14	0.510	0.540	0.340		
15	0.000	0.290	0.120		
16	0.280	0.430	0.490		
17	0.000	1.010	1.030		
18	2.270	1.150	0.570		
19					
20					
21					
22					
23					
24	1.450	4.280	0.210	47.670	12.000
25	1.480	4.240	0.180	48.090	10.860
26	0.540	3.240	0.350	51.450	5.780
27	5.050	14.140	0.430	47.340	8.010

Analytical Data

Mon, Feb 3, 1992 12:57 PM

84

85

86

TG-wt%,dry Coal Volatile TG-wt%,MAF, H2O,Combustion TG-wt%,MAF, CO,Combustion

1		3.100	1.070
2		2.000	0.980
3		5.250	0.470
4		0.370	1.710
5		0.290	2.000
6		4.140	2.040
7		4.450	1.390
8		4.680	0.550
9		0.000	2.800
10		6.540	3.700
11		3.420	1.460
12		1.090	0.190
13		0.910	0.390
14		1.500	0.230
15		0.360	0.170
16		1.090	0.290
17		0.350	1.990
18		0.060	1.880
19			
20			
21			
22			
23			
24	40.330	0.940	4.770
25	41.050	1.240	2.950
26	42.770	1.160	6.840
27	44.650	0.020	1.480

Analytical Data

Mon, Feb 3, 1992 12:57 PM

87

88

TG-wt%,MAF, CO2,Combustion TG-wt%,MAF, SO2,Combustion

1	12.160	0.030
2	19.790	0.030
3	24.300	0.040
4	23.300	0.770
5	20.800	0.700
6	20.850	0.860
7	16.660	0.840
8	12.830	0.560
9	13.520	1.710
10	11.970	0.000
11	7.400	0.360
12	7.860	0.010
13	15.880	0.130
14	12.530	0.180
15	10.400	0.180
16	7.910	0.140
17	7.220	0.340
18	8.820	0.000
19		
20		
21		
22		
23		
24	Not Available	1.550
25	Not Available	0.370
26	Not Available	1.610
27	Not Available	0.140

APPENDIX C

FT-IR Spectra

Figure C-1. FT-IR Spectrum of Interstage Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #1).

Figure C-2. FT-IR Spectrum of Recycle Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #2).

Figure C-3. FT-IR Spectrum of Second Stage PO Resid from Wyodak Coal, Wilsonville Run 251-III (sample #3).

Figure C-4. FT-IR Spectrum of Interstage Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #4).

Figure C-5. FT-IR Spectrum of Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #5).

Figure C-6. FT-IR Spectrum of Second Stage PO Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #6).

Figure C-7. FT-IR Spectrum of Interstage Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #7).

Figure C-8. FT-IR Spectrum of Recycle Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #8).

Figure C-9. FT-IR Spectrum of Second-Stage PO Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #9).

Figure C-10. FT-IR Spectrum of THF Soluble Portion of Sample #1 (Sample #10).

Figure C-11. FT-IR Spectrum of THF Soluble Portion of Sample #2 (Sample #11).

Figure C-12. FT-IR Spectrum of THF Soluble Portion of Sample #3 (Sample #12).

Figure C-13. FT-IR Spectrum of THF Soluble Portion of Sample #4 (Sample #13).

Figure C-14. FT-IR Spectrum of THF Soluble Portion of Sample #5 (Sample #14).

Figure C-15. FT-IR Spectrum of THF Soluble Portion of Sample #6 (Sample #15).

Figure C-16. FT-IR Spectrum of THF Soluble Portion of Sample #7 (Sample #16).

Figure C-17. FT-IR Spectrum of THF Soluble Portion of Sample #8 (Sample #17).

Figure C-18. FT-IR Spectrum of THF Soluble Portion of Sample #9 (Sample #18).

Figure C-19. FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-2 (Sample #19).

Figure C-20. FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-9 (Sample #20).

Figure C-21. FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-18 (Sample #21).

Figure C-22. FT-IR Spectrum of Pressure Filter Liquid Resid from Illinois No. 6 Coal, HRI Run I-27, P-25 (Sample #22).

Figure C-23. FT-IR Spectrum of Whole Process Oil from Pittsburgh Seam Coal, Wilsonville Run 259E (Sample #23).

APPENDIX D

TG-FTIR Plots

AFR1486 (AFR#1) w; run 251-III

AFR1486 (AFR#1) w; run 251-III

Figure D-1. TG-FTIR Results for Interstage Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #1).

AFR1582 (AFR#2) w; run 251-III

AFR1582 (AFR#2) w; run 251-III

Figure D-2. TG-FTIR Results for Recycle Oil Resid from Wyodak Coal, Wilsonville Run 251-III (sample #2).

AFR1494 (AFR#3) w; run 251-III

AFR1494 (AFR#3) w; run 251-III

Figure D-3. TG-FTIR Results for Second Stage PO Resid from Wyodak Coal, Wilsonville Run 251-III (sample #3).

AFR1496 (AFR#4) w; run 259

AFR1496 (AFR#4) w; run 259

Figure D-4. TG-FTIR Results for Interstage Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #4).

AFR1501 (AFR#5) w: run 259

AFR1501 (AFR#5) w: run 259

Figure D-5. TG-FTIR Results for Recycle Oil Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #5).

AFR1504 (AFR#6) w; run 259

AFR1504 (AFR#6) w; run 259

Figure D-6. TG-FTIR Results for Second Stage PO Resid from Pittsburgh Seam Coal, Wilsonville Run 259 (sample #6).

AFR1508 (AFR47) W: run 257

AFR1506 (AFR#7) W. run 257

Figure D-7. TG-FTIR Results for Interstage Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #7).

AFR1556 (AFR#8) w: run 257

AFR1556 (AFR#8) w: run 257

Figure D-8. TG-FTIR Results for Recycle Oil Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #8).

AFR1569 (AFR#9) w; run 257

AFR1569 (AFR#9) w; run 257

Figure D-9. TG-FTIR Results for Second Stage PO Resid from Illinois No. 6 Coal, Wilsonville Run 257 (sample #9).

APR1572 (APR#10) w; run 251-III; R-1258

APR1572 (APR#10) w; run 251-III

Figure D-10. TG-FTIR Results for THF Soluble Portion of Sample #1 (Sample #10).

AFR1609 (AFR#11) w; 251-III

AFR1609 (AFR#11) w; run 251-III; V-131B

Figure D-11. TG-FIR Results for THF Soluble Portion of Sample #2 (Sample #11).

AFR1466 (AFR#12) w; run 251-III; V-1067A

AFR1466 (AFR#12) w; run 251-III

Figure D-12. TG-FTIR Results for THF Soluble Portion of Sample #3 (Sample #12).

AFR1468 (AFR#13) w; run 259

AFR1468 (AFR#13) w; run 259; R-1235

Figure D-13. TG-FTIR Results for THF Soluble Portion of Sample #4 (Sample #13).

AFR1472 (AFR#15) w; run 259

AFR1472 (AFR#15) w; run 259; V-1067

Figure D-15. TG-FTIR Results for THF Soluble Portion of Sample #6 (Sample #15).

AFR1473 (AFR#16) w; run 257 T-1235

AFR1473 (AFR#16) w; run 257

Figure D-16. TG-FTIR Results for THF Soluble Portion of Sample #7 (Sample #16).

AFR1632 (AFR#17) w; run 257

AFR1632 (AFR#17) w; run 257; VIS1B

Figure D-17. TG-FTIR Results for THF Soluble Portion of Sample #8 (Sample #17).

AFR1633 (AFR#18) w; run 257

AFR1633 (AFR#18) w; run 257

Figure D-18. TG-FTIR Results for THF Soluble Portion of Sample #9 (Sample #18).

AFR1381 (AFR 24)

Burning star #2

AFR1381 (AFR 24)

Burning star #2

Figure D-19. TG-FTIR Results for Illinois No. 6 Coal, -100 Mesh, (Sample #24).

AFR1367 (AFR 24)

AFR1367 (AFR 24)

Figure D-20. TG-FTIR Results for Illinois No. 6 Coal, -100 Mesh, (Sample #24).

AFR1407 (APR 25)

AFR1407 (APR 25)

Figure D-21. TG-FTIR Results for Pittsburgh Seam Coal, -100 Mesh, (Sample #25).

AFR1412 (AFR 26)

AFR1412 (AFR 26)

Figure D-22. TG-FTIR Results for Wyodak Coal, -100 Mesh, (Sample #26).

END

**DATE
FILMED**

12 / 9 / 92