DOE/PC/89805--T6

DE92 016120

Arthur D Little

**CROSS-FLOW,
FILTER-SORBENT
CATALYST FOR
PARTICULATE,
SO₂ AND
NO_x CONTROL**

**Technical Progress
Report:**

Fourth Quarterly

4 Qtr 1990

For

U.S. Department of Energy
Office of Fossil Energy
Pittsburgh Energy
Technology Center
Pittsburgh, PA

November 1990

Work Performed Under
Contract No.
22-89PC89805-00

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Arthur D. Little, Inc.
Cambridge, MA 02140

ADL Reference 64303

MASTER

Table of Contents

	<u>Page</u>
List of Figures	iii
List of Tables	iv
Summary of Test Results - Fourth Quarter Progress	1
1.0 Introduction	2
1.1 Background	2
1.2 Description of Single-Unit, Three Pollutant Control Device	2
1.3 Research and Development Activity	5
2.0 Task Description Summary	6
3.0 Objectives for Fourth Quarter Activity	7
4.0 Approach	7
4.1 NO _x Reduction Test Approach	7
4.2 Sorbent-Catalysts Used for NO _x Reduction Tests	10
5.0 Results	11
5.1 NO _x Reduction on Fresh Sorbents	11
5.2 NO _x Reduction on Partially Sulfated Sorbents	11
5.3 NO _x Reduction.. Summary	16
5.4 Effect of Sulfation at Lower Temperature on Sorbent-Catalyst Sulfation Performance	16
6.0 Plans for Next Quarter	18
6.1 System Evaluation and Design	18
6.2 Sorbent Studies	18
7.0 References	18

List of Figures

<u>Figure No.</u>		<u>Page</u>
1	Schematic of a Ceramic Cross-Flow Filter-Sorbent Catalyst	3
2	Close-Up of Filter-Sorbent-Catalyst Wall and Gas Flow Scheme	4
3	Schematic of Packed-Bed Microreactor System	9
4	NO _x Reduction on Fresh Sorbents	12
5	NO _x Reduction on Cu-7Al-O	13
6	NO _x Reduction on CeO ₂	14
7	NO _x Reduction on Cu-Ce-O	15

List of Tables

<u>Table No.</u>		<u>Page</u>
1	Summary of Tasks	7
2	Program Schedule and Milestone Plan	8
3	Physical Properties of Sorbent-Catalysts Tested	10
4	DeNO _x Summary	17

Summary of Test Results: Fourth Quarter Progress

NO_x Reduction on Sorbent-Catalysts

The NO_x reduction activity of three sorbent-catalyst materials was tested over a temperature range from 200 to 500°C. We were primarily interested in the sorbent-catalyst NO_x reduction performance at 400°C because this appears to be a minimum temperature for acceptable sulfur capture with these sorbents. The tradeoff between sulfur capture and NO_x reduction performance for these sorbent-catalysts is clear: sulfation improves with higher temperatures (e.g., 400-600°C) while NO_x reduction improves at lower temperatures (e.g., 200-300°C).

NO_x reduction tests were performed on three sorbent-catalyst materials:

1. Cu-7Al-O;
2. Cu-Ce-O; and
3. CeO₂.

The first two materials showed good to excellent performance in sulfur capture tests. Ceria was tested to establish baseline data and to determine whether the addition of small amounts of ceria to the Cu-Al-O sorbent (for improved NO_x reduction efficiency at 400°C) was warranted.

Both Cu-7Al-O and Cu-Ce-O showed high NO_x reduction efficiency (>90%) at 200°C. However, both sorbents showed a decrease in NO_x reduction efficiency with increasing temperature. At 400°C, the conversion of NO over the Cu-7Al-O catalyst decreased to 60%. Over Cu-Ce-O, the conversion of NO at 400°C was only 20%. The decrease in NO conversion with increasing temperature was due to ammonia oxidation on the sorbent-catalysts at higher temperature.

NO_x reduction on ceria (Ce-5) was 90% at 400°C. With ceria, NO_x reduction goes through a maximum of 95% at 380°C. Unfortunately, ceria alone is not an effective sulfur capture sorbent at these temperatures; at 400°C the sulfation conversion of CeO₂ was only 7% prior to SO₂ breakthrough. Good sulfur capture with this sorbent was achieved at 600°C. At this temperature, however, NO conversion is less than 60% due to ammonia oxidation.

Partial sulfation of the sorbent-catalysts resulted in significantly improved NO_x reduction activity at 400°C.

1.0 Introduction

1.1 Background

Emission control systems for small-scale combustors must be designed to provide highly effective removal of three criteria pollutants (particulate matter, SO_2 and NO_x) under a set of operational constraints that are unique to the small-scale application. In residential homes, commercial buildings, and light industrial facilities, the availability of space is limited and there may be no trained, on-site technicians. In this environment, any piece of installed equipment must be safe, reliable, quiet, small, easy to access and maintain, and should produce no waste by-products that cannot be handled by local waste handling systems.

In addition to satisfying these operational requirements, the emission control systems must clean the flue gas down to emission levels that are comparable to those produced by existing (fuel-oil) combustors. Reduction or elimination of respirable particulates, odors, and acid mists will be critical because the stacks of these combustors will be low and located in densely populated areas. The deposition of acid-coated particulates will be particularly noticeable in residential areas because these acid smuts eat away the paint on cars and houses.

For high reliability, safety, compactness and cost effectiveness, the emission control system should have few moving parts, involve a minimum of extra flows or treatment process, have high area to volume ratios and produce no additional waste products. It would be desirable to have particulate matter, SO_2 and NO_x controlled by one device that could be easily serviced on a monthly, quarterly or seasonal basis.

These requirements make dry, regenerative clean-up processes particularly attractive. This report describes a new concept for integrated pollutant control: a cross-flow filter comprised of layered, gas permeable membranes that act as a particulate filter, an SO_2 sorbent, and a NO_x reduction catalyst.

1.2 Description of Single-Unit, Three Pollutant Control Device

The device described in this section will simultaneously remove particulates, SO_2 and NO_x from the combustion gases of coal combustors. The device is configured as a cross-flow filter, as shown in Figure 1.¹ The gas flows from the inlet passages to orthogonally oriented discharge channels via thin, multilayered porous walls. As shown in Figure 1, flue gas enters from both the front and back of the device. With the left wall of the filter sealed, gas discharges from the right side of the device. The key to combined physical (fly ash) and chemical (SO_2/NO_x) cleaning is to utilize chemically active sorbent-catalysts (e.g., metal oxides) in the layered walls of the filter. A cross-flow filter wall with layered construction is shown in Figure 2. (This concept is currently under evaluation at MIT; a patent application has been filed.)² This arrangement avoids use of pellet beds that plug in the presence of soot and fly ash and require larger reactor volumes because of low surface/volume ratios.

Figure 1. Schematic of a Ceramic Cross-Flow Filter-Sorbent Catalyst

Figure 2. Close-Up of Filter-Sorbent-Catalyst Wall and Gas Flow Scheme

The top (tight-pore) layer serves as a barrier filter blocking passage of fly ash particles. As the gas flows through the porous walls, particulate impurities are trapped on the walls of the inlet passage. The second layer of the porous walls carry at least one active sorbent-catalyst material to absorb SO_2 into the porous wall. Once the metal oxide is bound with sulfur-oxides (e.g., CuSO_4), it becomes a catalyst for NO_x reduction. Thus, with the addition of NH_3 into the flue gas stream, the sorbent layer could also serve as a NO_x reduction catalyst. However, in order to effect NO_x reduction throughout the absorption time, a second metal oxide serving as a selective NO_x reduction catalyst, e.g., $\text{CeO}_2^{(5,4)}$, will be added in the (second) sorbent layer. If it becomes necessary, a third layer, containing (and protecting) the deNO_x catalyst phase can be provided.

This configuration offers a compact filter (10 times higher surface-to-volume ratio than a typical baghouse), a low-attribution sorbent-catalyst (no moving or fluidized solid bed), low pressure drop (through a few mm-thick macroporous membrane), and a very simple flow scheme.

We estimate that better than 90% removal efficiency of SO_2 and NO_x is achievable with the use of mixed metal oxides (CuO , CeO_2 , or Fe_2O_3) in the device. Also, high sulfur capacity is possible by increasing the metal oxide content of the active SO_2 sorbent phase. Aluminum oxide, Al_2O_3 , is planned to be used as a dispersant and/or catalyst support in the active sorbent-catalyst layer(s). The composite is expected to keep its bifunctional characteristics throughout its operation and not deactivate or lose its structural integrity in the presence of fly ash and trace metals.

Fly ash particles trapped by the cross flow structure can be periodically removed by a back-flushing procedure. Pulse-jet backflushing is a well established technique for high pressure applications of the cross-flow filter.¹ This technique may have to be modified for small-scale applications. Modifications may include frequency of backflush, duration and pressure of each pulse, and pressure source for the pulsation. The modifications may be necessary to make the system as simple as possible for small-scale use. The active composition for SO_2 absorption can be renewed by a regeneration procedure that produces either elemental sulfur or concentrated gaseous sulfur species which can be converted to elemental sulfur by well established processes.

The single unit, particle filter, SO_2 sorbent, NO_x reduction catalyst is an ideal device for small-scale applications. It is modular in configuration, compact, without any moving parts, quiet, producing no toxic materials or new solid wastes to be disposed of and requiring little auxiliary power.

1.3 Research and Development Activity

In October 1989, the team of Arthur D. Little, Massachusetts Institute of Technology, and GTE began a three-year, USDOE/PETC (Pittsburgh Energy Technology Center) funded program to research and develop the filter-sorbent-catalyst. The research priorities of this effort are listed below:

- Sorbent-catalyst material development

- Which metal oxide materials provide best combined performance for SO₂ removal, NO_x reduction, and sorbent regeneration?
- Under what regeneration conditions is the production of elemental sulfur maximized?
- Active Filter selection
 - What ceramic filter design (thickness, porosity, size, active-phase layering) leads to acceptable pressure drop, particulate matter capture, and structural integrity at expected operating conditions?
 - What backflushing scheme is required?
- System design
 - How will these systems be incorporated into furnaces?
 - What will be the device size, seals, cost, and operating constraints?

2.0 Task Description Summary

The objective of this program is to successfully carry out the experiment and design tasks described herein that will lead to the development a single-unit, cross flow filter-sorbent-catalyst. We plan to carryout this research and design work in two stages.

The first stage of the work will be fundamental in nature: we will investigate the SO₂ removal and NO_x reduction characteristics of different sorbent-catalyst compositions (in bulk, granular form), and we will conduct exploratory tests of cross-flow filters under conditions similar to those found in the combustion gases of small-scale combustors. After a year of these fundamental studies, we will conduct a preliminary evaluation of the component performance and will design two or three prototype configurations.

In the subsequent stage of the program, we will investigate the pollutant control characteristics of prototype filter-sorbent-catalyst devices. The SO₂ removal and NO_x reduction efficiency of a 'unit-element' prototype will be investigated. This 'unit element' will be a slot reactor comprised of two flat porous walls, or 'slabs' of filter-sorbent-catalyst material separated by a 0.5 centimeter gap. The particulate collection efficiency and back-flushing requirements of a multi-element version of this device will be tested.

Concurrent with these efforts will be the investigation of a sorbent regeneration scheme that has the potential to produce elemental sulfur in a one step process. Final evaluation of component performance and the design of these emissions control devices for residential, commercial, and small industrial applications will be conducted at the conclusion of the project.

Table 1 summarizes the tasks to be performed in this program. A milestone chart is shown in Table 2. A complete description of each task can be found in March Technical Progress report (First Quarterly Report).³

Table 1. Summary of Tasks

Task #	Description	Lead Contractor	Schedules
1	Test Plan	ADL	Oct. 1989 - Dec. 1989
2	Component Development		
	2.1 Preparation for SO ₂ /NO _x Studies	MIT	Oct. 1989 - Oct. 1990
	2.2 SO ₂ /NO _x Screening Tests	MIT	Oct. 1989 - Sept. 1990
	2.3 Particulate Tests	ADL	Jan. 1990 - June 1990
	2.4 Regeneration Studies	MIT	Aug. 1990 - Aug. 1991
3	Prototype Tests		
	3.1 Filter Fabrication	GTE	Jan. 1991 - Mar. 1991
	3.2 SO ₂ /NO _x Tests	MIT	Sept. 1990 - April 1991
	3.3 Particulate Tests	ADL	Sept. 1991 - April 1992
4	Evaluation and Design	ADL	Aug. 1990 - Nov. 1990 and Nov. 1991 - Mar. 1992
5	Management and Reports	ADL	Oct. 1989 - Oct. 1992

3.0 Objectives for Fourth Quarter Activity

The objectives for the July-September 1990 period were to:

1. Screen mixed metal-oxide sorbent-catalysts for their NO_x reduction efficiency.
2. Investigate the effect of sulfation reaction temperature on SO₂ capture efficiency for promising sorbent-catalysts.

4.0 Approach

4.1 NO_x Reduction Test Approach

The microreactor test facility used for NO_x screening is the same as that used for SO₂ removal screening.

The reactor consists of a quartz tube of 1.5 cm I.D. vertically mounted inside an electric furnace equipped with a temperature controller. The sorbent-catalyst granules are supported on a fritted quartz disc in the middle in the reactor tube. A K-type thermocouple moving inside a quartz thermowell (0.3 cm I.D.) concentric to the reactor is used to monitor the axial bed temperature. The reactor pressure is slightly above atmospheric. Premixed gas streams of typical flue gas compositions flow through the reactor in the upward (sulfation-NO_x reduction) or downward (regeneration) direction. The reactor system is shown schematically in Figure 3.

A chemiluminescent NO_x analyzer is used to monitor the composition change of the flue-gas flow passing through the reactor tube packed with sorbent powders. The feed gas contains 600 ppm NO, 600 ppm NH₃, 3% O₂ and N₂ balance. The gas flow rate corresponds to a space velocity of 2,000 hr⁻¹. With the present chemiluminescent NO_x

Table 2
Program Schedule and Milestone Plan

- △ Test Plan Complete
- △ Topical Report Particulate/SO₂/NO_x Control
- △ Revised Test Plan for Prototype Development
- △ Topical Report: Regeneration Studies
- △ Program Review/Tech. Feasibility/Preliminary Design Guidelines
- △ Technical Feasibility Evaluation Complete
- △ Design Complete
- ① Draft Report
- △ Final Report

Figure 3. Schematic of Packed-Bed Microreactor System

analyzer, the concentration of NO component and ($\text{NO}_x + \text{NH}_3$) mixture can be determined precisely. However, no direct information about concentrations of other single nitrogen oxides (except NO) is available. The conversion of NO can be obtained by monitoring the NO concentration change in the flue gas flow passing through the reactor tube. In addition, selectivities and conversions of NO reduction by ammonia can be reconfirmed by monitoring the concentration change of the ($\text{NO}_x + \text{NH}_3$) mixture.

4.2 Sorbent-Catalysts Used for NO_x Reduction Tests

NO_x reduction tests were performed on three sorbent-catalyst materials:

1. Cu-7Al-O;
2. Cu-Ce-O; and
3. CeO_2 .

The first two materials showed good to excellent performance in sulfur capture tests. Ceria was tested to establish baseline data and to determine whether the addition of small amounts of ceria to the Cu-Al-O sorbent (for improved NO_x reduction efficiency at 400°C) was warranted.

The mixed metal oxide sorbents tested in this program are prepared according to the well established amorphous-citrate technique.^{6,7} This involves rapid dehydration (under vacuum, at 70°C) of an aqueous solution containing the metal salts and citric acid in desired proportions, followed by pyrolysis and further calcination of the resulting amorphous solid foam at relatively low temperatures (500 - 650°C). Citric acid is added in a 1 to 1 mole ratio to the metal salts included in the solution. For most sorbents, the nitrate form of metal salts has been used. Homogeneous, highly dispersed mixed oxides or oxide solid solutions are formed. These materials can be made with larger average pore size than is generally the case in coprecipitated mixed oxides. This is an important feature in gas-solid reactions where a higher molecular volume product (e.g., sulfate) can cause pore mouth blocking. Also, for the application intended here, large pores are needed to allow free gas flow (low pressure drop).

The surface areas of the sorbent catalysts used for these DeNO_x tests are shown in Table 3.

Table 3. Physical Properties of Sorbent-Catalysts Tested

Sorbent-Catalyst	Surface Area (m^2/g)	Pore Volume (cc/g)
Cu-7Al-O (B2)	373	1.6
Cu-Ce-O (B2)	24	4.1
CeO_2 (B5)	23	-

5.0 Results

5.1 NO_x Reduction on Fresh Sorbents

The NO_x reduction efficiency of the three fresh, bulk, mixed metal-oxide sorbents (Cu-7Al-O, Cu-Ce-O, and CeO₂) is shown in Figure 4.

Both Cu-7Al-O and Cu-Ce-O showed high NO_x reduction efficiency (>90%) at 200°C. However, both sorbents showed a decrease in NO_x reduction efficiency with increasing temperature. At 400°C, the conversion of NO over the Cu-7Al-O catalyst decreased to 60%. Over Cu-Ce-O, the conversion of NO at 400°C was only 20%. The decrease in NO conversion with increasing temperature was due to ammonia oxidation on the sorbent-catalysts at higher temperature.

To test the effect of ammonia oxidation on overall NO conversion, we passed 600 ppm NH₃ - 3% O₂ - N₂ balance flue gas through the reactor tube packed with Cu-Ce-O. At 300°C, about 14% of the ammonia was converted to NO. Oxidation of ammonia increases with increasing reaction temperature. The conversion of ammonia to NO was 37% at 400°C and 55% at 473°C, respectively.

NO_x reduction on ceria (Ce-5) was 90% at 400°C. With ceria, NO_x reduction goes through a maximum of 95% at 380°C. Unfortunately, ceria alone is not an effective sulfur capture sorbent at these temperatures; at 400°C the sulfation conversion of CeO₂ was only 7% prior to SO₂ breakthrough. Good sulfur capture with this sorbent was achieved at 600°C. At this temperature, however, NO conversion is less than 60% due to ammonia oxidation.

5.2 NO_x Reduction on Partially Sulfated Sorbents

Over the course of emission control system use, the sorbent-catalysts will become sulfated. We were interested in investigating the change in NO_x reduction performance that occurs as these sorbent catalysts become partially sulfated.

The effect of partial sorbent sulfation on the NO_x reduction efficiency of the three sorbents tested is shown in Figures 5, 6, and 7. For all three sorbent-catalysts, some degree of sulfation improved NO_x reduction efficiency at temperatures above 300°C.

The effect of partial sulfation on the deNO_x activity of Cu-7Al-O is shown in Figure 5. For this material, sulfation of the sorbent-catalyst significantly improved NO_x reduction activity at higher temperatures (e.g., 400°C). Three degrees of sulfation are shown: fresh (0% sulfation) sulfated at 300°C (20% sulfation), and sulfated at 375°C (30% sulfation). At 20% sulfation of Cu-7Al-O, NO_x conversion was between 85 and 95% in this temperature regime. The NO_x conversion over the fresh sorbent catalyst, by comparison, decreased from 80% to 60% as temperatures increased from 300 to 400°C.

Similarly, sulfation of the Cu-Ce sorbent has a significant effect on its own catalytic properties for NO_x reduction. The results are shown in Figure 6. For this test, the Cu-Ce (B2) sorbent had been previously sulfated at 400°C for 32 minutes in 1500 ppm SO₂-3% O₂-N₂ balance flow (about 20 percent sulfation conversion of the sorbent). The

NO_x REDUCTION ON FRESH SORBENTS

FIGURE 4

NO_x REDUCTION ON Cu-7Al-O

FIGURE 5

FIGURE 6

NO_x REDUCTION ON Cu-Ce-O

FIGURE 7

NO_x REDUCTION ON CeO₂

active temperatures for selective NO_x reduction by ammonia shifted to higher temperatures as compared to the activity of fresh (unsulfated) sorbent. The obtained NO conversion was 84% at 300°C and 62% at 400°C, respectively. A comparison of the NO_x reduction effectiveness of partially sulfated versus fresh sorbent shows that the sulfated sorbent has superior performance.

The same trend of improved NO_x reduction performance on sulfated sorbent-catalysts held true for CeO_2 , as shown on Figure 7. For partially sulfated CeO_2 (7% conversion), the overall NO_x reduction performance improved as compared to the fresh sorbent, but the temperature at which maximum NO_x reduction occurred did not shift upward as much as with the other two sorbent-catalysts.

5.3 NO_x Reduction Summary

The NO_x reduction activity of three sorbent-catalyst materials was tested over a temperature range from 200 to 500°C. We were primarily interested in the sorbent-catalyst deNO_x performance at 400°C because this appears to be a minimum temperature for acceptable sulfur capture with these sorbents: The tradeoff between sulfur capture and NO_x reduction performance for these sorbent-catalysts is clear: sulfation improves with higher temperatures (e.g., 400-600°C) while NO_x reduction improves at lower temperatures (e.g., 200-300°C).

Table 4 summarizes the deNO_x performance of the three sorbent-catalysts tested, both in their fresh and partially-sulfated states. The data showed that at low temperature (i.e., 200°C), both Cu-7Al-O and Cu-Ce-O could catalyze the reduction of 90% of the NO_x introduced to the system. At 400°C, CeO_2 and partially sulfated Cu-7Al-O and partially sulfated Cu-Ce-O could provide 90% NO_x reduction, while the fresh materials could provide only 60% NO_x reduction. We found no sorbent catalysts that could achieve 60%-90% NO_x reduction at 600°C.

5.4 Effect of Sulfation at Lower Temperature on Sorbent-Catalyst Sulfation Performance

One objective of this quarter's activity was to investigate the effect of sulfation reaction temperature on the SO_2 capture efficiency of our most promising candidate sorbent-catalyst: Cu-7Al-O. We are interested in investigating SO_2 absorption at lower temperatures (300-350°C) because we found that catalytic activities for NO_x reduction improved at lower temperatures (200-350°C).

We found, however, that a reaction temperature of 400°C may be the lowest acceptable temperature to obtain complete sulfation of Cu-Al sorbents. At 300 and 350°C, this sorbent showed a sulfation conversion of 0.2 and 0.3, respectively. (Sulfation conversion was measured as t/t^* at 150 ppm breakthrough, where t^* is the calculated time it would take for all the sorbent material in the test reactor to sulfate completely and t is the actual time for SO_2 emissions from the reactor to equal 10% of the incoming SO_2 concentration.) Nearly complete sulfation conversion was obtained at 400°C, as previously reported. At 400°C, NO_x conversion over the Cu-7Al-O sorbent was 60%. The conclusion, therefore, is that there is no opportunity to operate this sorbent-catalyst at a temperature more conducive to high levels of NO_x reduction.

TABLE 4

DENOX SUMMARY

TEMPERATURE	> 90% REMOVAL	60% REMOVAL
200°C	Cu-7Al Cu-Ce	Cu-7Al Cu-Ce
400°C	Ce Cu-7Al (20% SULFATED) Ce (7% SULFATED)	Cu-7Al Cu-Ce (23% SULFATED) Ce
600°C	NONE	NONE

Last month we also reported that ceria sorbent-catalysts were very effective NO_x reduction catalysts at 400°C . We had found previously, however, that ceria was not an effective sulfur sorbent at this temperature. This month, we examined ceria sorbents prepared in two different ways to determine whether improved sulfur conversion (at 400°C) could be obtained with this sorbent. It appears that the ceria sorbents are effective sulfur sorbents at higher temperatures (600°C) only.

6.0 Plans for Next Quarter

6.1 System Evaluation and Design

We will conduct a preliminary system evaluation and design for residential, commercial, and light industrial applications.

6.2 Sorbent Studies

We will summarize experiments with binary and ternary sorbents to investigate the effect of sorbent and NO_x reduction.

7.0 References

1. Ciliberti, D.F., et al., "Hot Gas Clean-up Using Ceramic Cross Flow Membrane Filters," Final Report under DOE Contr. No. DE-AC21-79ET15491, December 1983.
2. Flytzani-Stephanopoulos, M., "Methods and Devices for Gas Cleaning," U.S. Patent Application - Serial No. 113, 572, filed October 23, 1987.
3. March Technical Progress Report. Contract No. 22-89PC-89805-00.
4. Ginger, A., "Process for the Simultaneous Separation of Sulfur and Nitrogen Oxides from a Gaseous Mixture," U.S. Patent #4258020, 1981.
5. Ginger, A., "Process for the Simultaneous Separation of Sulfur and Nitrogen Oxides from a Gaseous Mixture," U.S. Patent #4192855, 1980.
6. Marcily, C., Courty, P., and Delmon, B., *J. Am. Cer. Soc.* 53 (1), 56 (1970).
7. Courty, P., and Marcilly, C., "A Scientific Approach to the Preparation of Bulk Mixed Oxide Catalysts," in *Preparation of Catalysts III*, ed. by G. Poncelet, P., Grange and P.A. Jacobs, Elsevier, Amsterdam, pp. 485-519, 1983.

**DATE
FILMED**

8 / 17 / 92