AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 1

PRETREATMENT OF PLUTONIUM FINISHING PLANT (PFP) SLUDGE:
REPORT FOR THE PERIOD OCTOBER 1990 - MARCH 1992

Gregg J. Lumetta
John L. Swanson

April 1993

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

MASTER

SUMMARY

The current mission of the U.S. Department of Energy's Hanford Site is one of environmental restoration. A major task within this mission is the disposal of large volumes of high-level wastes (HLW) that are stored in underground tanks on the site. Under the current planning assumptions, all high-level tank waste will be vitrified as borosilicate glass and then disposed of in a geologic repository. The costs associated with this disposal scheme are very high. Thus, methods to reduce the volume of glass required to vitrify these wastes are currently being investigated.

Plutonium Finishing Plant (PFP) sludge is a unique transuranic waste that is stored in tank 241-SY-102 on the Hanford site. As the name implies, the bulk of this material consists of waste from operations at the Plutonium Finishing Plant; but, other wastes have also been added (e.g., wastes from decontamination activities). Because the quantities of plutonium and americium in the PFP sludge are greater than 100 nCi/g, this sludge must be handled as a HLW. Approximately 6000 glass canisters would result from vitrifying this waste directly. Sludge washing would reduce the required number of canisters to ~2500, with the volume of glass being driven by the low allowable concentration limit for Cr in the vitrification plant feed. The cost of production and subsequent geologic disposal of each canister of glass is expected to be \$0.5 M to \$1 M. Thus, an economic incentive exists to develop methods of pretreating the sludge to reduce the number of glass canisters needed to contain the final vitrified product.

Two approaches to pretreating PFP sludge are being investigated: 1) selective leaching of chromium from the sludge and 2) dissolution of the sludge followed by separating the TRU elements by solvent extraction. Removing the TRUs by solvent extraction would result in a greater reduction in the number of glass canisters required to vitrify the TRU component of PFP sludge, but would require a greater capital investment in facilities and equipment. The Cr leach approach offers the advantage of greater simplicity. Although a detailed analysis of the impact of each pretreatment option has not yet been performed, it is estimated that ~1250 canisters would be produced if Cr is

removed. This can be reduced to ~700 if P and S are also removed. If the sludge is dissolved and TRUs separated by solvent extraction, then ~150 canisters of glass would be produced in the disposal of PFP sludge.

In the PFP sludge samples studied, 20 to 34% of the Cr present exists as Cr(VI), which can be removed from the sludge by washing with water or dilute sodium hydroxide. Most of the remaining insoluble chromium can be converted to Cr(VI) by treatment with an alkaline permanganate solution. If the leach with KMnO_4 is done at room temperature, approximately 85% of the chromium can be removed from PFP sludge; up to 96% of the Cr can be removed if the leach is done at 100°C. Furthermore, if the sludge wash (with 0.1 M NaOH) and Cr leach are done at 100°C, 99% of the Al and 100% of the P present in the sludge can be removed. The latter two elements become significant with regards to the number of glass canisters required to vitrify PFP sludge if the Cr is removed. This approach may compete economically with the acid dissolution/TRU extraction approach in reducing the number of glass canisters required to vitrify the PFP sludge.

Although excellent results have been achieved in the Cr leach studies, additional development is required before this process can be implemented. In particular, the TRU content of some of the sludge wash solutions^(a) exceeded the current limits for disposal of aqueous waste in grout. Further work will be required to ensure that these solutions are non-TRU.

If the Cr leach approach is pursued, the leach solution itself would constitute a low-level waste which must be disposed of in grout. From an environmental standpoint, it would be desirable to have the Cr being grouted in the Cr(III) state. The CrO_4^{2-} present in the PFP wash and leach solutions can easily be reduced to Cr(III) with hydroxylamine.

Dissolution of the sludge in nitric acid followed by extraction of Am and Pu with octyl(phenyl)-N,N-diisobutylcarbamoylmethylphosphine oxide (CMPO) has also been shown to be a promising approach to pretreating PFP sludge. Good dissolution of the PFP sludge in dilute (2 to 3 M) nitric acid has been

(a) Sludge washing would be done prior to or in concurrence with the Cr leach procedure.

demonstrated; for most sludge components, greater than 90% dissolution was achieved. Solvent extraction experiments indicated that the TRUs can be extracted from the dissolved PFP sludge solution to very low levels, with adequate decontamination factors easily achievable.

In some initial tests, long phase disengaging times were observed, which could cause problems in the solvent extraction equipment. However, adding complexants (e.g., oxalic acid or acetohydroxamic acid) seems to overcome this problem without seriously affecting the efficiency of the TRU extraction. Also, heating the dissolved PFP sludge solution (then allowing it to cool to ambient temperature prior to the solvent extraction contact) leads to improved phase disengagement behavior.

The two pretreatment options for PFP sludge investigated here, Cr leaching and TRU solvent extraction, both show great promise for reducing the volume of borosilicate glass required to vitrify this waste. Further investigations of these two approaches are planned.

ACKNOWLEDGMENTS

This work was funded by Westinghouse Hanford Company through the Waste Pretreatment Technology Group managed by J. N. Appel. The responsible engineers on this project were S. S. Lowe and S. A. Barker, whose assistance and advice are much appreciated.

Much of the experimental work was conducted by M. J. Wagner. The assistance of M. C. Burt, C. O. Harvey, P. K. Melethil, D. E. Rinehart, S. W. Thompson, and M. W. Urie of PNL's Analytical Chemistry Laboratory is gratefully acknowledged. The authors would like to thank J. E. Coleman for performing scanning electron microscopy studies and R. D. Scheele and W. C. Cosby for reviewing this document.

CONTENTS

Summary	iii
Acknowledgements	vi
1.0 Introduction	1.1
2.0 METHODS AND MATERIALS	2.1
2.1 MATERIALS	2.1
2.2 GENERAL METHODS	2.1
2.2.1 Sludge Settling	2.1
2.2.2 Sludge Washing	2.2
2.2.3 Solvent Extraction	2.2
2.2.4 Analytical Methods	2.2
2.3 EXPERIMENT PFP-1	2.4
2.3.1 Treatment of Washed Sludge with Hydrogen Peroxide	2.4
2.3.2 Dissolution in Nitric Acid	2.4
2.3.3 Treatment of Undissolved Residue	2.5
2.4 EXPERIMENT PFP-2	2.5
2.4.1 Treatment of Washed Sludge with Hydroxylamine	2.5
2.4.2 Treatment of Washed Sludge with Hydrazine	2.6
2.5 EXPERIMENT PFP-3	2.6
2.5.1 Digestion of Washed Sludge in Dilute Sodium Hydroxide	2.6
2.5.2 Treatment of Washed Sludge with Potassium Permanganate	2.7
2.5.3 Dissolution in Nitric Acid	2.7

2.6	EXPERIMENT PFP-6	2.8
2.6.1	Dissolution of PFP-6A	2.8
2.6.2	Dissolution of PFP-6B	2.9
2.7	EXPERIMENT PFP-7	2.9
2.8	EXPERIMENT PFP-8	2.10
2.8.1	Sludge Dissolution	2.10
2.8.2	Solvent Extraction	2.11
3.0	RESULTS AND DISCUSSION	3.1
3.1	SLUDGE WASHING	3.1
3.1.1	Sludge Settling Behavior	3.1
3.1.2	Behavior of Sludge Components During Sludge Washing	3.4
3.2	SELECTIVE LEACH OF CHROMIUM FROM PFP SLUDGE	3.10
3.2.1	Attempted Leaching of Cr With Hydrogen Peroxide	3.12
3.2.2	Attempted Leaching of Cr With Hydroxylamine and Hydrazine	3.12
3.2.3	Leaching of Cr by Alkaline Digestion and Oxidation with Permanganate	3.13
3.2.4	Mechanism of the Reaction of Cr(III) with Permanganate	3.15
3.2.5	Reduction of Leached Cr With Hydroxylamine	3.17
3.3	SOLVENT EXTRACTION of TRANSURANIC ELEMENTS	3.17
3.3.1	Acid Dissolution of Washed PFP Sludge	3.18
3.3.2	SEM and Particle Size Analyses	3.20
3.3.3	TRU Removal by Solvent Extraction	3.23
3.4	CONCLUSION	3.32
4.0	REFERENCES	4.1

FIGURES

3.1	PFP Sludge Settling Data	3.2
3.2	UV-Vis Spectra of the Reaction of Cr_2O_3 with KMnO_4 in 0.1 M NaOH Indicating the Transition from MnO_4^- a) to MnO_4^{2-} b) CrO_4^{2-} c)	3.16
3.3	Particle Size Analysis of Washed PFP Sludge and Residual Solids Remaining After Dissolution in HNO_3 : Cumulative Distribution Graphs	3.21
3.4	Particle Size Analysis of Washed PFP Sludge and Residue Remaining After Dissolution in HNO_3 : Probability Density Graphs	3.22
3.5a	Scanning Electron Micrograph of Washed PFP Sludge	3.24
3.5b	Scanning Electron Micrograph of the Residue Remaining After Dissolution of PFP Sludge in Nitric Acid	3.25
3.6	Energy Dispersive Spectra Obtained During Scanning Electron Microscopy Studies: a) Washed PFP Sludge, X-ray Beam Directed Over a Wide Area; b) Washed PFP Sludge, X-ray Beam Directed Upon Al-Rich Cubic Particle; and c) Undissolved Residue, X-ray Beam Directed Over a Wide Area	3.26
3.7	Conceptual Flowsheet for the Pretreating PFP Sludge by Extracting the TRU Components of the Sludge With CMPO	3.33

TABLES

2.1	Summary of PFP Sludge Washing Experiments	2.3
2.2	Solvent Extraction Experiment PFP-8	2.11
3.1	The Effects of Water Washing on Sludge Settling Behavior in Experiment PFP-8	3.3
3.2	Summary of PFP Sludge Washing, Cr Leaching, and Acid Dissolution	3.5
3.3	Summary of Radionuclide Behavior for PFP-1	3.8
3.4	Alpha Activity in PFP Sludge Wash Solutions	3.9
3.5	Molar Concentrations of Selected Anions in the Wash Solutions from PFP-1	3.10
3.6	Effect of AHA on CMPO Solvent Extraction Process, Experiment PFP-3	3.28
3.7	Effect of Complexants and Heating on Phase Separation	3.29
3.8	Behavior of Major PFP Sludge Constituents in the CMPO Solvent Extraction Process	3.31

1.0 INTRODUCTION

Plutonium Finishing Plant (PFP) sludge is a high-level waste that is stored in tank 241-SY-102 on the Hanford site. As the name implies, the bulk of this material consists of waste from operations at the Plutonium Finishing Plant; but other wastes have also been added (e.g., wastes from decontamination activities). The primary metallic components of this sludge are Al, Ca, Cr, Mn, Fe, and Th. Because the quantities of plutonium and americium in the PFP sludge are greater than 100 nCi/g, this sludge must be handled as a high-level waste. Approximately 6000 glass canisters would result from vitrifying this waste directly. Sludge washing would reduce the required number of canisters to ~2500, with the volume of glass being driven by the low allowable concentration limit for Cr in the vitrification plant feed. The cost of production and subsequent geologic disposal of each canister of glass is expected to be \$0.5 M to \$1 M. Thus, an economic incentive exists to reduce the volume of glass produced in the disposal of PFP sludge waste.

At the request of Westinghouse Hanford Company (WHC), a project has been undertaken at Pacific Northwest Laboratory^(a) to evaluate pretreatment options for PFP sludge. The minimal pretreatment option is assumed to be washing of the sludge with water or dilute sodium hydroxide. The effects of such washing on the removal of various sludge components are discussed in this report. Two other pretreatment options have been considered: 1) leaching Cr (which is a glass volume controlling element) from PFP sludge, and 2) dissolving PFP sludge in nitric acid followed by separating the TRU material by solvent extraction so that only the undissolved sludge portion (if any) and the separated TRUs would require vitrification. The results of initial experiments to assess these options are presented here.

(a) Pacific Northwest Laboratory is operated by Battelle Memorial Institute for the U.S. Department of Energy under Contract DE-AC06-76RLO 1830.

2.0 METHODS AND MATERIALS

This section describes the materials and procedures used to study pre-treatment options for PFP sludge.

2.1 MATERIALS

Two different PFP sludge samples were used in this study. PFP sludge sample 102SY-3T4S consisted of centrifuged solids from the composite of segment 3 and the top portion of segment 4 from the October 1988 core sample of tank SY-102. PFP sludge sample 34COMP was a homogenized composite of segments 3 and 4 from the February 1990 sampling of tank SY-102. Sample 102SY-3T4S had dried out upon storage in the shielded facility, whereas 34COMP was a fluid slurry.

The solvent (supplied by WHC) used to extract the TRUs from the dissolved PFP sludge solutions consisted of 0.2 M octyl(phenyl)-N,N-diisobutylcarbamoylmethylphosphine oxide (CMPO) plus 1.4 M tributyl phosphate (TBP) in normal paraffin hydrocarbon (NPH). This solvent mixture will be referred to as 0.2 M CMPO in this report.

2.2 GENERAL METHODS

All experiments described in this report had several procedural elements in common. These are described in this section. Subsequent sections will detail procedures that were unique to the individual experiments.

2.2.1 Sludge Settling

Typically, sludge settling studies were conducted by mixing a measured amount of PFP sludge with a measured amount of water (or dilute sodium hydroxide) in a glass vial with a cross-sectional area of 380 mm². After mixing, the sludge was allowed to settle and the sludge height was periodically measured with a ruler. These settling studies were done in conjunction with the sludge washing studies.

2.2.2 Sludge Washing

Sludge samples were washed with either water or 0.1 M NaOH. In general, the wash solution was added to the sludge, and the mixture was homogenized by stirring with either a magnetic stir bar or on a vortex mixer. The sludge was then allowed to settle by gravity or was centrifuged. The solution was decanted and replaced with fresh wash solution, or the washed sludge was treated as described in Sections 2.2 through 2.7. Table 2.1 provides the details of each sludge washing experiment, including the volumes and types of wash solutions used and the amount of wash solution decanted.

2.2.3 Solvent Extraction

Solvent extraction experiments were carried out by contacting an aqueous feed solution, prepared by acid dissolution of PFP sludge, with 0.2 M CMPO in a small glass vial. In certain cases, the dispersion number (N_{Di}) was determined. The dispersion number defines how well the two phases will separate, which is an important factor in the success of any solvent extraction process. The higher the dispersion number, the more rapidly the phases will separate. N_{Di} was determined by measuring 1) the total height of the two phases (ΔZ) and 2) the time required for the two phases to separate (t_b). The dispersion number is given by the following equation:

$$N_{Di} = \frac{1}{t_b} \sqrt{\frac{\Delta Z}{g}} \quad (1)$$

where g = acceleration due to gravity = 9.81 m/s^2 .

2.2.4 Analytical Methods

The analytical methods used were similar to those described by Swanson (1991). Metal ion concentrations were determined by inductively coupled plasma/atomic emission spectroscopy (ICP). Alpha-emitting radionuclides were

TABLE 2.1. Summary of PFP Sludge Washing Experiments

Experiment	PFP-1	PFP-2	PFP-3	PFP-6	PFP-7A	PFP-7B(a)	PFP-8	PFP-9
Sludge Sample	102SY-3T4S	102SY-3T4S	102SY-3T4S	34COMP	34COMP	34COMP	102SY-3T4S	102SY-3T4S
Core Date	1988	1988	1988	1990	1990	1990	1988	1988
Mass of sludge, g	2.08	2.01	2.07	1.00	0.63	0.65	2.08	2.01
Wash 1								
Volume added, mL	water	water	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	water	0.04 M NaOH
Volume decanted, mL	11.0	9.0	10.0	5.0	4.9	5.0	5.2	6.0
Volume decanted, mL	6.1(c)	6.5(c)	8.6	5.0	4.6	5.0	4.3	5.0
time (b)	6 days	48 days	30	30	60	60	24 h	24 h
Wash 2								
Volume added, mL	water	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.05 M NaOH	0.05 M NaOH
Volume decanted, mL	10.0	8.0	10.0	5.0	5.0	5.0	5.0	5.0
Volume decanted, mL	13.6	9.2	9.8	4.9	5.0	4.7	note (e)	note (e)
time (b)	10	120	30	5	60	60	24 h	150
Wash 3								
Volume added, mL	water	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	water	0.05 M NaOH
Volume decanted, mL	10.0	8.0	10.0	5.0	5.0	5.0	5.0	5.0
Volume decanted, mL	9.4	8.0	9.7	5.0	4.9	5.0	note (e)	note (e)
time (b)	1 day	18 hr	30	5	60	60	72 h	24 h
Wash 4								
Volume added, mL	water	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	0.1 M NaOH	water	0.05 M NaOH
Volume decanted, mL	10.0	8.0	10.0	5.0	5.0	5.0	5.0	5.0
Volume decanted, mL	11.6	7.3	9.8	4.7	4.8	4.9	5.1	15.0(e)
time (b)	6 days	5 hr	30	5	60	60	24 h	24 h
Wash 5								
Volume added, mL	--	--	--	--	--	--	0.07 M NaOH	
Volume decanted, mL	--	--	--	--	--	--	5.0	
Volume decanted, mL	--	--	--	--	--	--	4.8	
time (b)	--	--	--	--	--	--	7 d	

- (a) PFP-7B was washed at 100°C, while all others were washed at room temperature.
 (b) Total time wash solution was in contact with the solids; in minutes (unless otherwise specified).
 (c) Sludge was allowed to settle by gravity prior to decanting the solution, in all other cases the wash/sludge mixture was centrifuged prior to decanting the wash solution.
 (d) Solids did not settle after 6 days. 1 mL of 10 M NaOH was added. The solution then cleared upon centrifugation.
 (e) The second, third, and fourth wash solutions in Experiment PFP-9 were combined to give a total volume of 15.0 mL.

analyzed on dried mounts of diluted solutions of interest. Alpha activity was usually determined as total alpha activity, but in selected cases, alpha energy analyses (AEA) were performed to determine the concentrations of specific isotopes. Acid concentrations were determined by titration with standard NaOH. The nitric acid concentration was determined by subtracting the contribution of the major hydrolyzable ions from the total acid concentration: $[HNO_3] = [H^+]_{total} - 3([Al] + [Cr] + [Fe])$.

2.3 EXPERIMENT PFP-1

The primary purpose of this experiment was to assess whether hydrogen peroxide would be a suitable oxidant for leaching Cr from washed PFP sludge. Of secondary interest was the ability of HNO_3 to dissolve the treated sludge.

2.3.1 Treatment of Washed Sludge with Hydrogen Peroxide

This treatment was performed to test a report that insoluble Cr(III) can be oxidized to soluble Cr(VI) by reaction with H_2O_2 . Ten mL of 0.1 M NaOH was added to the washed sludge (see Table 2.1), and the mixture was stirred for 18 h. After centrifuging, the supernatant solution was sampled for titration with standard HCl; the equivalent concentration of base was found to be 0.16 M. The sludge/NaOH mixture was stirred and 0.1 mL of 30% H_2O_2 was added. Foaming occurred immediately upon adding the H_2O_2 , suggesting rapid consumption of the H_2O_2 . After stirring overnight, an additional 1.9 mL of 30% H_2O_2 was added in 0.1 mL increments over a period of one hour. Foaming occurred after each addition. After the final addition of 30% H_2O_2 , the sludge was allowed to settle, and the supernatant solution was then sampled for ICP analysis. The remainder of the sludge/NaOH mixture was treated with HNO_3 as described below.

2.3.2 Dissolution in Nitric Acid

In this experiment, 2.6 mL of concentrated HNO_3 (15.7 M) was added with stirring to the 14 mL of sludge/NaOH mixture. No foaming was observed during the acidification process. The mixture was stirred at ambient temperature for 2 h, then centrifuged. The supernatant solution was a dark amber color. Two distinct types of solids had settled: A grayish white solid had settled on

the bottom of the vial, and a rust colored layer was on top of the gray-white solid. The supernatant solution was sampled for ICP analysis and titration with standard NaOH. The concentration of HNO_3 was found to be 1.7 M. In an attempt to achieve additional dissolution, another 0.475 mL of concentrated HNO_3 was added, and the mixture was stirred at ambient temperature for 2 h, then centrifuged. This additional treatment with HNO_3 did not appear to result in a significant increase in dissolution. The supernatant solution was again sampled for ICP analysis and titration with standard NaOH. The final concentration of HNO_3 was found to be 2.1 M. The supernatant solution (solution P-1-8) was decanted from the undissolved residue.

2.3.3 Treatment of Undissolved Residue

The undissolved solids were quantitatively transferred to a filter funnel and washed successively with three 5 mL portions of water. The wash solutions were combined and sampled for ICP analysis. The washed solids were treated with 2 mL of concentrated HCl (12 M) at 100°C for 2.25 h. All of the rust colored solid dissolved, giving a pale green solution. The gray-white solid still remained. The solution was decanted, and the gray-white solid was treated with strong NaOH (approx. 13 M) at 100°C for 1.5 h. After standing at ambient temperature for 2 h, the solution was filtered. The filtered solids were washed with three 5 mL portions of water, and the wash solutions were combined with the initial filtrate. A small amount of residual solid remained, but there was too little to work with so it was discarded.

2.4 EXPERIMENT PFP-2

In this experiment, the use of hydroxylamine or hydrazine to leach Cr from PFP sludge by oxidation of Cr(III) to Cr(VI) was tested. Based on published reduction potentials (Huheey 1978), these reagents were expected to oxidize Cr(III) under alkaline conditions.

2.4.1 Treatment of Washed Sludge with Hydroxylamine

This portion of the experiment was aimed at determining whether hydroxylamine could be used to solubilize chromium. The washed sludge (see Table 2.1) was stirred with 10 mL of 1.0 M NaOH, then was allowed to settle

overnight. The supernatant solution had a faint yellow color suggesting that some Cr(VI) was already present in solution. Then 1.00 mL of 1.5 M hydroxylamine nitrate (in 0.5 M HNO₃) was added with stirring. After 2 h, the supernatant solution had turned colorless, suggesting that the small amount of chromate ion that had been in solution (as evidenced by the initial faint yellow color) had been reduced to insoluble Cr(III). This was the opposite of what was expected based on the published reduction potentials. The mixture was next heated for 2 h at 100°C; the solution remained colorless. The mixture was then centrifuged and the solution was decanted and analyzed by ICP.

2.4.2 Treatment of Washed Sludge with Hydrazine

The sludge remaining after the treatment with hydroxylamine was slurried in 0.1 M NaOH and 0.06 mL of 15 M hydrazine solution was added. After stirring for 1 h, the mixture was centrifuged. No color change was observed, suggesting that no chromium was dissolved by this method.

2.5 EXPERIMENT PFP-3

The primary focus of this experiment was to determine whether Cr(III) could be oxidized to Cr(VI) with potassium permanganate, thus solubilizing the Cr. Prior to the test with permanganate, the ability to leach Cr simply by heating the sludge in dilute NaOH was also tested.

2.5.1 Digestion of Washed Sludge in Dilute Sodium Hydroxide

The primary purpose of this digestion was to determine if Cr could be solubilized by reaction with MnO₂ that is also present in the sludge. Ten mL of 0.1 M NaOH was added to the washed sludge sample PFP-3 and the mixture was stirred at room temperature for 30 min. After standing overnight, a small portion of the supernatant solution was removed for analysis. The remaining sludge/NaOH mixture was stirred and heated at 100°C for 3 h, then was allowed to stand overnight at ambient temperature. The supernatant solution was yellow, indicating that some chromium had dissolved as chromate ion. The mixture was centrifuged, and the solution was decanted.

2.5.2 Treatment of Washed Sludge with Potassium Permanganate

Ten mL of 0.1 M NaOH was added to the sludge remaining after the digestion in dilute NaOH, and the mixture was stirred at room temperature for 1 h. After sampling the supernatant liquid, 0.048 g of KMnO_4 (which was estimated to be about one-half of the KMnO_4 required to react with the Cr present in the sludge) was added and the mixture was stirred at ambient temperature for 2.5 h, then centrifuged. The solution was deep yellow, indicating that all of the permanganate (deep purple color) had been consumed, and that chromate ion (yellow color) was in solution. The presence of chromate ion was confirmed spectrophotometrically, after dilution with 0.3 M HNO_3 ($\lambda_{\text{max}} = 355 \text{ nm}$ with a shoulder at 440 nm).

Another 0.042 g of KMnO_4 was added, and the mixture was stirred at room temperature. After 1 h, the solution had turned the emerald green color of the MnO_4^{2-} ion (see Section 3.2), and after standing overnight, the solution had become deep yellow (CrO_4^{2-}). The mixture was centrifuged and the solution was decanted. The solution was tested qualitatively for alpha activity by placing a drop of the solution on a cotton swab and scanning the swab with an alpha detector. No alpha activity was indicated.^(a)

The remaining sludge was washed successively with three 5 mL portions of 0.1 M NaOH. The sludge was slurried in 10 mL 0.1 M NaOH and another 0.042 g KMnO_4 was added. The mixture was stirred overnight, then centrifuged. The purple permanganate color was still present. The solution was decanted and the remaining solids were washed successively with three 5 mL portions of 0.1 M NaOH. The remaining sludge was dissolved in nitric acid as described below.

2.5.3 Dissolution in Nitric Acid

Eight mL of water and 2 mL of concentrated HNO_3 were added to the sludge remaining after the KMnO_4 treatment. The mixture was stirred at room

(a) For comparison the dissolved sludge solution from Expt PFP-1 (solution P-1-8) was qualitatively tested for alpha activity in the same manner. The alpha activity in this solution was easily detected by this method.

temperature for 1 h, then at 100°C for 1 h. After centrifugation, the solution (solution P-3-13) was decanted. Eight mL of water, 2.076 g of acetohydroxamic acid,^(a) and 2 mL of concentrated HNO₃ were added to the undissolved solids. After stirring at ambient temperature for 1 h, all the rust colored solids had dissolved, giving a purple solution (solution P-3-14), which was decanted from the undissolved gray-white solid. The solid was washed successively with three 5 mL portions of water. Although some undissolved residue still remained, the amount was so small that it was imbedded in the filter membrane. This material was discarded.

The concentration of HNO₃ in solutions P-3-13 and P-3-14 was determined to be 1.7 M and 2.3 M, respectively, by titration with standard NaOH.

2.6 EXPERIMENT PFP-6

The primary purpose of this experiment was to study the effect of oxalic acid on PFP sludge dissolution; i.e., to determine if increased dissolution would be achieved as compared to HNO₃ alone. After being washed repeatedly with 0.1 M NaOH (Table 2.1), the sludge was slurried in 5 mL of water and this slurry was divided equally into two portions (PFP-6A and -6B). These two portions of washed PFP sludge were treated as follows.

2.6.1 Dissolution of PFP-6A

Water (2.5 mL) was added to PFP-6A followed by 0.05 mL of concentrated HNO₃. The pH of the resulting mixture was 0.98, and the volume of the mixture was 5.1 mL. Concentrated HNO₃ (1.2 mL) was added to give an approximate [HNO₃] of 3 M. The mixture was stirred for two hours, then centrifuged. The dissolved sludge solution (P-6A-5) was decanted. The residual solid was

(a) Acetohydroxamic acid (CH₃CONHOH) was used in this experiment because of the high affinity of hydroxamic acids for Fe³⁺. The presence of acetohydroxamic acid (or other complexant) in the dissolved sludge solution may have benefits with regards to the performance of the solvent extraction process for separation of TRUs (see Section 3.6). This compound does not appear to have any severe toxicological properties (Windholz et al. 1983).

washed with water, then dissolved in 0.64 M HCl/0.13 HF at 100°C for analysis. Titration of the dissolved sludge solution (P-6A-5) indicated that the concentration of HNO₃ was 3.26 M.

2.6.2 Dissolution of PFP-6B

Water (2.5 mL) was added to PFP-6B followed by 0.126 g H₂C₂O₄·2H₂O. The pH of the resulting mixture was 1.09, and the volume of the mixture was 5.3 mL. Concentrated HNO₃ (1.2 mL) was added to give an approximate [HNO₃] of 3 M. The mixture was stirred for two hours, then centrifuged. The dissolved sludge solution (P-6B-5) was decanted. Titration of the dissolved sludge solution (P-6B-5) indicated that the concentration of HNO₃ was 3.21 M. The residual solid was washed with water, then was dissolved in 1.3 M HCl/0.22 HF at 100°C for analysis.

2.7 EXPERIMENT PFP-7

The primary purpose of experiment PFP-7 was to assess the effects of temperature on sludge washing and Cr leaching with KMnO₄. A 1.29 g portion of PFP sludge sample 34COMP was mixed with 10 mL 0.1 M NaOH, and the resulting slurry was divided into two portions (PFP-7A and PFP-7B). PFP-7A was washed with 0.1 M NaOH at room temperature and PFP-7B was washed with 0.1 M NaOH at 100°C; the volumes of the wash solution used are listed in Table 2.1.

Washed PFP sludge PFP-7A was divided into two portions (PFP-7A1 and PFP-7A2). Each of these was slurried in 5 mL 0.1 M NaOH and treated with 2.55 mL 0.02 M KMnO₄ (the KMnO₄ was added in 0.25 mL increments over a period of several days; the mixture was stirred overnight after the last addition of KMnO₄); this was done at room temperature for PFP-7A1 and at 100°C for PFP-7A2. The leach solutions were decanted from the sludges, then the leached sludges were washed with 0.1 M NaOH and dissolved in HNO₃ (6.1 mL 2.32 M for PFP-7A1 and 6.1 mL 2.54 M for PFP-7A2). The residual solids were dissolved in HCl/HF (1.6 M HCl + 0.3 M HF for PFP-7A1 and 1.4 M HCl + 0.2 M HF for PFP-7A2).

Washed PFP sludge PFP-7B was mixed with 10 mL 0.014 M KMnO₄ in 0.1 M NaOH. After stirring overnight, the mixture was heated at 100°C for

1 h, then cooled. The mixture was centrifuged and the supernatant solution was decanted. After washing with 0.1 M NaOH, the leached sludge was dissolved for analysis by heating at 100°C with 13.5 mL 1.8 M HCl/1.1 M HF.

2.8 EXPERIMENT PFP-8

The purpose of experiment PFP-8 was to assess the overall process for extracting TRUs from PFP sludge, including sludge washing, sludge dissolution, and solvent extraction. Variations of the TRU removal flowsheet that has been demonstrated for Hanford neutralized cladding removal waste (Swanson 1991) were tested. These variations included: 1) using an aqueous oxalic acid solution as the only scrub solution and 2) using sodium citrate as the stripping agent.

The importance of effectively scrubbing nitric acid from the extract prior to the stripping steps has been demonstrated (Lumetta and Swanson 1993). By using an oxalic acid scrub, it was hoped that both the non-TRU metal ions and the nitric acid could be removed from the extract in one step. Earlier TRU removal flowsheets called for the use of 0.2 M 1-hydroxyethane-1, 1-diphosphonic acid (HEDPA) as stripping agent (Lumetta and Swanson 1993). Because of concern about excessive amounts of phosphorus in the vitrification feed (due to the use of HEDPA), alternative stripping agents, such as sodium citrate, are being sought.

Also, particle size and scanning electron microscopy (SEM) analyses were performed on the washed sludge and the residue remaining after acid dissolution to obtain data on the composition and physical characteristics of these solids.

2.8.1 Sludge Dissolution

Concentrated (15.7 M) HNO_3 (1.0 mL) was added directly to the washed sludge. After stirring for 30 min, the mixture was heated for 1 h. After the mixture had cooled to room temperature, 4 mL water was added, then the mixture was stirred for an additional 1 h. Upon centrifuging, two types of solids were observed: a white solid was on the bottom of the vial, and a dark brown solid was on top of this. The mixture was again stirred and an additional

5 mL of water and 1 mL of concentrated HNO_3 were added. After stirring for 1 h, the mixture was allowed to stand overnight. The dissolved sludge solution was decanted and filtered through a $0.2\ \mu\text{m}$ filter.

The undissolved solids were washed with water, then samples of these solids were taken for particle size and SEM analyses. The solids were then dissolved for analysis in a mixture of $1.2\ \text{M}\ \text{HCl} + 0.5\ \text{M}\ \text{HF} + 0.7\ \text{M}$ aceto-hydroxamic acid.

2.8.2 Solvent Extraction

The extraction, scrub, and strip contacts that were performed are listed in Table 2.2. The feed solution was prepared by diluting the dissolved sludge solution with an equal volume of water. After each contact, the phases were separated by centrifugation.

TABLE 2.2. Solvent Extraction Experiment PFP-8

<u>Contact Number</u>	<u>Aqueous Phase</u>	<u>Organic Phase</u>
Extr 1	16.4 mL feed solution	8.2 mL $0.2\ \text{M}\ \text{CMPO}$
Extr 2	4.50 mL aqueous from Extr 1	1.5 mL $0.2\ \text{M}\ \text{CMPO}$
Extr 3	3.00 mL aqueous from Extr 2	1.0 mL $0.2\ \text{M}\ \text{CMPO}$
Scrub 1	3.00 mL $0.1\ \text{M}\ \text{H}_2\text{C}_2\text{O}_4$	6.0 mL organic from Extr 1
Scrub 2	2.00 mL $0.1\ \text{M}\ \text{H}_2\text{C}_2\text{O}_4$	4.0 mL organic from Scrub 1
Strip 1	1.00 mL $0.2\ \text{M}$ sodium citrate	3.0 mL organic from Scrub 2
Strip 2	0.80 mL $0.2\ \text{M}$ sodium citrate	2.4 mL organic from Strip 1
Strip 3	0.50 mL $0.2\ \text{M}$ sodium citrate	1.5 mL organic from Strip 2

3.0 RESULTS AND DISCUSSION

3.1 SLUDGE WASHING

The initial step in pretreating PFP sludge will probably be sludge washing, regardless of whether the Cr leach approach or the TRU solvent extraction approach is pursued, because this removes the bulk sodium from the sludge (and thus reduces the volume of the sludge to be processed). Thus, a variety of PFP sludge washing experiments were performed, both at room temperature and at 100°C. Information was obtained concerning sludge settling behavior and the behavior of the various sludge components during the sludge wash procedures.

3.1.1 Sludge Settling Behavior

Sludge settling behavior is an important parameter with regards to the rate at which PFP sludge can be processed. If sludge settling is slow enough that a settle/decant step becomes process rate limiting, then more sophisticated solid/liquid separation methods (e.g., centrifugation or filtration) may be required.

Sludge settling data were collected in several experiments. The data from experiments PFP-1 and PFP-2 are presented in Figure 3.1; these data were collected during the first wash step for each of these experiments (see Table 2.1). Although the sludge used in both of these experiments came from the same sample (102SY-3T4S), the rate of settling in PFP-2 was found to be much greater than in PFP-1. The initial settling rate for PFP-1 was 0.15 mm/min whereas that for PFP-2 was 1.29 mm/min. The reason for this difference is not entirely clear. A magnetic stir bar was present in the PFP-1 experiment, but not in the PFP-2 experiment. All other aspects of the sludge settling experiments in PFP-1 and -2 were identical.

One possible explanation for the observed differences in the settling behavior is that the magnetic field from the stir bar in PFP-1 may have perturbed the settling behavior of the sludge. There is considerable ferromagnetic and paramagnetic material present in the PFP sludge, e.g., Fe(III), Mn(II), and Cr(III). Subsequent sludge settling studies were done without magnetic stir bars present.

FIGURE 3.1. PFP Sludge Settling Data

In experiment PFP-8, the effects of extensive water-washing on sludge settling behavior were explored. In this experiment, 2.076 g of PFP sludge sample 102SY-3T4S was slurried with 5.2 mL water--this volume of water was approximately three times the volume of the sludge, which would likely be the amount that would be used at a process scale. After mixing for one hour, the sludge settling rate was measured. The initial settling rate was 0.04 mm/min which was much lower than expected (based on experiments PFP-1 and -2). This slow settling rate is most probably due to the concentrated nature of the slurry, resulting from the relatively small amount of wash water used in this experiment. Settling studies with synthetic neutralized cladding removal waste (NCRW) indicated that slow settling behavior occurs when there is a high concentration of particles in the slurry.^(a) Because adequate volumes of

(a) Lumetta, G. J., and J. L. Swanson. 1992. "Use of the TRUEX Process for the Pretreatment of Neutralized Cladding Removal Waste (NCRW) Sludge - Results of FY 1991 Studies. (Manuscript in preparation.)

wash water were not used to achieve "unrestricted" settling, quantitative conclusions from the settling data collected in experiment PFP-8 could not be made; however, the qualitative observations were significant.

Eight settling runs, summarized in Table 3.1, were performed in experiment PFP-8. In general, the settling behavior worsened with successive water washes. Adequate settling behavior was only observed when the total alkali concentration was at least 0.07 M. Thus, NaOH solutions of concentration 0.1 M or greater should be used to wash PFP sludge if the method of solid/liquid separation is settle-decant.

TABLE 3.1. The Effects of Water Washing on Sludge Settling Behavior in Experiment PFP-8

Wash Number	Wash Solution	mL Wash Solution Decanted ^(a)	Total Alkali in Wash Solution M ^(b)	Observations
P-8-1	5.2 mL water	4.3	0.00	Solids settled in one layer at an initial rate of 0.01 mm/min.
P-8-2	5.0 mL water	4.7	0.21	Floating solids present, even after standing overnight. These solids settled upon centrifugation.
P-8-3	5.0 mL water	5.0	0.074	Same as P-8-2
P-8-4	5.0 mL water	5.1	0.034	Same as P-8-2
P-8-5	5.0 mL water	--	--	Bulk of sludge had settled after 4 h, but supernatant solution remained cloudy, even after standing overnight. ^(c)
P-8-5b	+50 μ L 0.1 M NaOH to P-8-5 ^(d)	--	--	Two distinct layers settled: dark brown on the bottom, light brown on top. The supernatant solution was cloudy.
P-8-5c	+45 μ L 1.0 M NaOH to P-8-5b ^(d)	--	--	Two distinct layers settled: dark brown on the bottom, light brown on top. Settling was faster than in P-8-5b. The supernatant solution was cloudy.
P-8-5d	+45 μ L 10 M NaOH to P-8-5c ^(d)	4.8	0.072	Solids settled in one layer at an initial rate of 0.03 mm/min; supernatant solution was clear.

(a) After each settling measurement was complete, the mixture was centrifuged and the supernatant solution decanted.

(b) Total alkali in the wash solution was determined by titration with standard HCl.

(c) After P-8-5, samples of the slurry were withdrawn for scanning electron microscopy (SEM) and particle size analyses (see Section 3.5).

(d) In P-8-5b through P-8-5d, the solids were slurried in the wash solution using a vortex mixer after each addition of NaOH. The solids were allowed to settle after 1 h of mixing.

3.1.2 Behavior of Sludge Components During Sludge Washing

The effectiveness of different sludge washing conditions in removing sludge components were investigated in experiments PFP-1, PFP-3, PFP-6, PFP-7, and PFP-8. The wash solutions used are listed in Table 2.1, along with the volume of solution added and decanted in each wash step. The compositions of the wash solutions were determined by ICP analysis, and the percentages of each sludge component found in the decanted wash solutions are summarized in Table 3.2.

Because sodium hydroxide was added at various points in the experimental procedures, the behavior of Na during the wash steps could not be determined accurately. However, useful information regarding the behavior of Na can be obtained from experiments PFP-6 and PFP-8. In the case of PFP-6, a total of 0.170 g Na was found; this total includes the Na present in the sludge as well as the Na added in the wash steps. The amount of Na found in the decanted wash solutions was 0.166 g, which corresponds to 98% of the total Na. Similar results were obtained in experiment PFP-8. In this case, a total of 0.307 g Na was found; 92% (0.283 g) of this Na was found in the wash solutions.

Of the major sludge components other than sodium, only chromium was removed to a significant extent by washing with water or dilute NaOH at room temperature. When PFP sludge sample 102SY-3T4S was washed with water or dilute NaOH, 32 to 34% of the chromium in the sludge sample was removed as CrO_4^{2-} as determined spectrophotometrically (experiments PFP-1, -3, and -8). However, a smaller percentage (18-20%) of the Cr present was removed from PFP sludge sample 34COMP when this was washed (experiments PFP-6 and -7). These results suggest that the amount of chromium present in PFP sludge can be significantly reduced by simple sludge washing; this in turn would decrease the number of glass canisters needed to vitrify this waste. However, it is expected that sludge washing would result in only a modest reduction in the number of canisters needed.

Once the Cr has been removed, it would be advantageous to remove Al and P because the number of glass canisters saved by their removal would also be significant.

TABLE 3.2. Summary of PFP Sludge Washing, Cr Leaching, and Acid Dissolution

Experiment	Sludge Sample	Sludge Component									
		Al	Ca	Cr	Fe	K	Mn	P	Pb	Th	U
PFP-1	102SY-3T4S % in wash	0.1	0.0	33.9	0.0	100	0.0	18.7	0.0	0.0	0.0
	% in H ₂ O ₂ leach	5.3	0.0	1.3	0.1	0.0	0.0	20.7	0.0	0.0	0.0
	% in HNO ₃ diss.	18.7	98.8	59.6	94.7	0.0	95.1	60.3	96.5	100	100
	% in Residue	75.9	1.2	5.2	5.2	0.0	4.9	0.3	3.5	0.0	0.0
	g/g dry sludge	0.0336	0.0071	0.0235	0.0427	0.0018	0.0171	0.0049	0.0032	0.0086	0.0020
PFP-3	102SY-3T4S % in wash (room temp.)	1.7	0.3	32.8	0.0	(b)	(b)	22.1	0.0	0.0	0.0
	% in wash (100°C)	10.5	0.2	2.3	0.0	(b)	(b)	0.0	0.0	0.0	0.0
	% in KMnO ₄ leach	11.9	1.1	50.9	0.0	(b)	(b)	0.0	0.0	0.0	0.0
	% in HNO ₃ diss.	61.2	84.9	6.6	76.4	(b)	(b)	46.0	81.7	81.5	100
	% in HNO ₃ /AHA (a) diss. g/g dry sludge	10.4	13.5	6.7	23.6	(b)	(b)	31.9	18.3	18.5	0.0
		0.0286	0.0078	0.0242	0.0431	(b)	(b)	0.0050	0.0033	0.0084	0.0026
PFP-6	34COMP % in wash	10.1	0.6	18.4	0.4	100	0.2	100	0.0	0.0	(c)
PFP-6A	% in HNO ₃ diss.	18.2	99.4	68.5	90.9	0.0	93.4	0.0	100	100	(c)
	% in residue	71.8	0.0	13.1	8.7	0.0	6.4	0.0	0.0	0.0	(c)
PFP-6B	% in HNO ₃ /H ₂ C ₂ O ₄ diss.	6.9	99.4	25.5	87.5	0.0	92.5	0.0	100	(c)	(c)
	% in residue	83.1	0.0	56.1	12.0	0.0	7.3	0.0	0.0	(c)	(c)
	g/g wet sludge	0.0190	0.0016	0.0102	0.0100	0.0017	0.0027	0.0095	0.0007	0.0004	(c)
PFP-7A	34COMP % in wash	9.5	10.5	19.2	0.0	(b)	(b)	100	0.0	0.0	(c)
PFP-7A1	% in KMnO ₄ leach (r.t.)	8.6	19.0	65.0	0.0	(b)	(b)	0.0	0.0	0.0	(c)
	% in HNO ₃ diss.	59.2	67.7	14.2	93.1	(b)	(b)	0.0	100	100	(c)
PFP-7A2	% in KMnO ₄ leach (100°C)	48.5	18.1	71.6	0.0	(b)	(b)	0.0	0.0	0.0	(c)
	% in HNO ₃ diss.	26.7	68.3	7.4	88.4	(b)	(b)	0.0	100	100	(c)
	% in residue	15.2	3.0	1.8	11.6	(b)	(b)	0.0	0.0	0.0	(c)
	g/g wet sludge	0.0224	0.0027	0.0116	0.0104	(b)	(b)	0.0078	0.0007	0.0010	(c)

TABLE 3.2. (contd)

Experiment	Sludge Sample	Sludge Component									
		Al	Ca	Cr	Fe	K	Mn	P	Pb	Th	U
PFP-7B	% in wash	69.1	100	27.1	0.2	(b)	(b)	100	0.0	(c)	(c)
	% in KMnO_4 leach	29.8	0.0	69.3	0.0	(b)	(b)	0.0	0.0	(c)	(c)
	% in leached sludge	1.1	0.0	3.6	99.8	(b)	(b)	0.0	100	(c)	(c)
PFP-8	102SY-3T4S	0.6	1.6	33.9	0.0	100	0.0	100	0.0	10.5	32.4
	% in wash	46.1	98.4	62.0	93.3	0.0	95.9	0.0	100	89.5	67.6
	% in HNO_3 diss.	53.3	0.0	4.2	6.7	0.0	4.1	0.0	0.0	0.0	0.0
	% in residue	0.0431	0.0064	0.0277	0.0517	0.0014	0.0211	0.0012	0.0038	0.0091	0.0025
	g/g dry sludge										

(a) AHA = acetohydroxamic acid.

(b) Not determined because of uncertainties associated with the amount of KMnO_4 added.

(c) Not detected.

Mixed results concerning Al were obtained. Very little Al washed out of PFP sludge sample 102SY-3T4S, yet about 10% of the Al present in sample 34COMP dissolved in 0.1 M NaOH at room temperature (experiment PFP-7A). When 34COMP was washed with 0.1 M NaOH at 100°C (experiment PFP-7B), a much greater amount of Al was dissolved (69.1%). This suggests that a large portion of the Al present in PFP sludge can be removed by washing the sludge with a caustic solution at an elevated temperature. This would greatly reduce the volume of TRU waste requiring subsequent processing.

Mixed results were also obtained with the behavior of phosphorus in sludge washing. Results from initial experiments with PFP sludge sample 102SY-3T4S (experiments PFP-1 and -3) indicated that only 20% of the P present was removed by sludge washing. However, subsequent experiments with both 102SY-3T4S (experiment PFP-8) and 34COMP (experiments PFP-6 and -7) showed that 100% of the P present in the sludge is removed by sludge washing.

Fe and Mn remained in the sludge during sludge washing. In general, this was also true for Ca, Pb, Th, and U. Experiment PFP-8 was an exception; in this case 10.5% of the Th and 32.4% of the U dissolved during sludge washing. This observation may be related to the observed high TRU content in the wash solutions from PFP-8 (see below).

Because of their potential impact on grout feed, the behavior of the various radionuclides during the washing of PFP sludge was investigated in experiment PFP-1; the results are summarized in Table 3.3. The primary gamma emitting nuclide in the sludge is ^{137}Cs , which is present in a concentration of 747 $\mu\text{Ci/g}$ of sludge. The washing procedure removed 97% of the ^{137}Cs from the sludge. The total β activity in the sludge was 625 $\mu\text{Ci/g}$ of sludge; the primary β emitter is presumed to be ^{90}Sr , but analyses for ^{90}Sr were not done due to their high cost. Only 15% of the β activity was removed from the sludge by sludge washing with water. The transuranic content of the wash solutions was found to be well below the 0.100 $\mu\text{Ci/g}$ limit for transuranic waste; the total alpha activity was 0.0068, 0.0007, 0.0021, and 0.0003 $\mu\text{Ci/mL}$ for washes 1, 2, 3, and 4, respectively.

In contrast to the total alpha content in the wash solutions from experiment PFP-1, the first wash solution from experiment PFP-8 was found to

TABLE 3.3. Summary of Radionuclide Behavior for PFP-1

Isotope	$\mu\text{Ci/g}$ Sludge	% Found In		
		Wash	H ₂ O ₂ Leach + Acid Dissolution	Undissolved Residue
Co-60	0.1	91.0	0.0	9.0
Sb-125	0.4	0.0	0.0	100
Cs-137	747	96.7	3.3	0.1
Am-241, gamma	2.6	0.0	99.4	0.6
Eu-154	2.6	0.0	99.4	0.6
Eu-155	2.8	0.0	99.3	0.7
Pu-239,240	22	0.1	97.4	2.5
Pu-238/Am-241	84	0.0	99.1	0.9
Cm-243/244	0.2	0.0	99.6	0.4
total alpha	105	0.0	98.8	1.2
total beta	625	15.2	83.8	1.1

contain 0.380 $\mu\text{Ci/mL}$ of TRU, which exceeds the LLW limit.^(a) Because of this discovery, a number of the wash solutions from other experiments were tested both qualitatively and quantitatively for alpha activity (Table 3.4). All of the wash solutions were found to be non-TRU except those in experiments PFP-8 and -9.

The reason these two wash solutions have significant TRU concentrations is not known at this time, but this fact has serious implications regarding 1) the Cr-leach approach to pretreating PFP sludge, and 2) dissolution of the sludge. If the wash solutions are high in TRU, then it is likely that the Cr-leach solutions will also be high in TRU. Thus, the Cr-leach approach to pretreating PFP sludge would not be viable. Likewise, if the wash solutions are high in TRU, then sludge washing cannot be done prior to sludge dissolution. Not washing the sludge would leave large quantities of nitrite ion in the sludge, which would be released as NO_x during the acid dissolution of the sludge, thus potentially causing the need for NO_x abatement processes.

(a) The second wash solution contained only 0.07 $\mu\text{Ci/mL}$ TRU.

TABLE 3.4. Alpha Activity in PFP Sludge Wash Solutions^(a)

<u>Experiment</u>	<u>PFP Sludge Sample</u>	<u>Qualitative^(b)</u>	<u>Quantitative,^(c) $\mu\text{Ci/mL}$</u>
PFP-2	102SY-3T4S	no	not analyzed
PFP-6	34COMP	no	not analyzed
PFP-7A	34COMP	no	0.0025
PFP-7B	34COMP	no	0.0025
PFP-8	102SY-3T4S	yes	0.350
PFP-9	102SY-3T4S	yes	0.313

- (a) Only the first wash solution from each experiment was tested.
- (b) Qualitative test for alpha activity: 20 μL of solution to be tested was placed on the tip of a cotton swab. The tip of the swab was scanned with an alpha detector to check for alpha activity.
- (c) Quantitative test for alpha activity: 100 μL of the solution to be tested was added to 900 μL of water. The resulting solution was contacted for 60 s with 1000 μL of 0.2 M AliquatTM 336 in 1-octanol. This was done to separate CrO_4^{2-} and TcO_4^- from the TRU (which remains in the aqueous phase). 100 μL of the aqueous phase was added to 1000 μL 1.8 M HNO_3 and was contacted for 60 s with 1100 μL 0.2 M CMPD . 100 μL of the organic phase from this last contact was added to 5 mL of Opti-FluorTM liquid scintillation cocktail and the alpha activity was counted. The wash solution from experiment PFP-8 was analyzed by both this method and by direct-mount total alpha analysis. The 0.350 $\mu\text{Ci/mL}$ was detected by this liquid scintillation method is comparable to the 0.380 $\mu\text{Ci/mL}$ found by the direct mount method.

Ion chromatographic data for the sludge wash solutions from PFP-1 are summarized in Table 3.5. These anions are of interest because, in the current strategy, the wash solutions would be cast into grout for disposal. Of the anions listed here, nitrate and nitrite ions are dominant as would be expected. However, except for bromide ion, there are also considerable concentrations of the other ions listed. For the first and fourth wash solutions, the concentration of phosphate ion determined by ion chromatography agreed well with the concentration of phosphorus determined by ICP, which was

TABLE 3.5. Molar Concentrations of Selected Anions in the Wash Solutions from PFP-1

	<u>Wash 1</u>	<u>Wash 2</u>	<u>Wash 3</u>	<u>Wash 4</u>
[F ⁻]	4.2 x 10 ^{-3(a)}	2.1 x 10 ⁻³	<7.1 x 10 ⁻⁴	2.1 x 10 ^{-3(a)}
[Cl ⁻]	1.2 x 10 ⁻²	5.7 x 10 ⁻³	1.3 x 10 ⁻³	2.5 x 10 ⁻³
[Br ⁻]	<6.7 x 10 ⁻⁴	<6.7 x 10 ⁻⁴	<3.4 x 10 ⁻⁴	<3.4 x 10 ⁻⁴
[NO ₂ ⁻]	1.2 x 10 ⁻¹	4.2 x 10 ⁻²	5.3 x 10 ⁻³	1.9 x 10 ⁻³
[NO ₃ ⁻]	3.2 x 10 ⁻¹	1.1 x 10 ⁻¹	1.6 x 10 ⁻²	3.3 x 10 ⁻³
[PO ₄ ³⁻]	5.5 x 10 ⁻³	3.2 x 10 ⁻³	2.1 x 10 ⁻³	3.1 x 10 ⁻³
[SO ₄ ²⁻]	1.6 x 10 ⁻²	6.3 x 10 ⁻³	1.3 x 10 ⁻³	6.3 x 10 ⁻⁴

(a) Matrix interference observed during analysis.

5.6 x 10⁻³ M for the first wash solution and 2.4 x 10⁻³ M for the last wash solution. On the other hand, the ICP data indicated that there was no phosphorus in washes 2 and 3. This discrepancy has not been resolved.

3.2 SELECTIVE LEACH OF CHROMIUM FROM PFP SLUDGE

If the plutonium finishing plant sludge is washed to remove the bulk sodium, then the chromium content becomes the controlling factor in the volume of glass required to vitrify this waste (if it is not processed to separate the TRU elements). A simple method to selectively remove Cr from PFP sludge is highly desirable because this would significantly reduce the number of canisters required to vitrify this waste without using a more elaborate process, such as TRU extraction with CMPO. It has been estimated that removal of Cr from (washed) PFP sludge would reduce the number of glass canisters required by a factor of two; removal of phosphorus and Al would further reduce the number of canisters required. ^(a)

(a) A letter report to Westinghouse Hanford Company by D. E. Kurath, et al. (1991) entitled Intermediate processing Approaches to the Pretreatment of Selected Double and Single Shell Tank Wastes.

The approach investigated to selectively remove chromium from this waste is to oxidize the insoluble Cr(III) to soluble Cr(VI) in alkaline solution. A number of oxidants have been investigated for this purpose. The reduction potential for the Cr(VI)/Cr(III) couple in alkaline solution along with those for some possible oxidants are listed below (Huheey 1978):

		ϵ° (V)
$\text{CrO}_4^{2-} + 4\text{H}_2\text{O} + 3\text{e}^-$	$\rightarrow$	$\text{Cr(OH)}_3 + 5\text{OH}^-$ -0.13
$\text{MnO}_2 + 2\text{H}_2\text{O} + 2\text{e}^-$	$\rightarrow$	$\text{Mn(OH)}_2 + 2\text{OH}^-$ -0.05
$\text{N}_2\text{H}_4 + 4\text{H}_2\text{O} + 2\text{e}^-$	$\rightarrow$	$2\text{NH}_4\text{OH} + 2\text{OH}^-$ +0.11
$\text{IO}_3^- + 3\text{H}_2\text{O} + 6\text{e}^-$	$\rightarrow$	$\text{I}^- + 6\text{OH}^-$ +0.26
$\text{MnO}_4^- + 2\text{H}_2\text{O} + 3\text{e}^-$	$\rightarrow$	$\text{MnO}_2 + 4\text{OH}^-$ +0.59
$\text{BrO}_3^- + 3\text{H}_2\text{O} + 6\text{e}^-$	$\rightarrow$	$\text{Br}^- + 6\text{OH}^-$ +0.61
$2\text{NH}_2\text{OH} + 2\text{e}^-$	$\rightarrow$	$\text{N}_2\text{H}_4 + 2\text{OH}^-$ +0.73
$\text{HO}_2^- + \text{H}_2\text{O} + 2\text{e}^-$	$\rightarrow$	3OH^- +0.88
$\text{O}_3(\text{g}) + \text{H}_2\text{O} + 2\text{e}^-$	$\rightarrow$	$\text{O}_2 + 2\text{OH}^-$ +1.24

Iodate and bromate were not further considered because it was deemed undesirable to introduce halide ions into the waste stream. Oxidation of chromium from PFP waste with ozone in an aqueous system has not been tried yet. Experiments using other oxidants in this list are described below. Using hydrogen peroxide as a possible oxidant was tried upon suggestion by W. W. Schulz (consultant).

3.2.1 Attempted Leaching of Cr With Hydrogen Peroxide

In experiment PFP-1, a portion of the PFP sample 102-SY-3T4S that had been washed with water (Table 2.1) was mixed with 10 mL of 0.1 M NaOH,^(a) and 2.1 mL of 30% H₂O₂ was added in 0.1 mL increments at room temperature in an attempt to oxidize chromium(III) to chromium(VI). This amount of H₂O₂ represented at least a 10 fold excess of that needed to oxidize the Cr(III) present in the sludge. Adding peroxide caused severe foaming, suggesting rapid decomposition of the hydrogen peroxide. Little change was observed in the color of the supernatant liquid. ICP analysis of the solution indicated that little chromium was dissolved (Table 3.2). Thus, use of peroxide to leach chromium from PFP sludge showed little promise. The peroxide was apparently destroyed rapidly (probably catalytically) under such conditions, and thus could not react with chromium(III).

3.2.2 Attempted Leaching of Cr With Hydroxylamine and Hydrazine

In experiment PFP-2, a portion of the PFP sample 102-SY-3T4S was washed with water and 0.1 M NaOH (see Table 2.1). The washed sludge was suspended in 10 mL of 1 M NaOH and 1.00 mL of 1.5 M hydroxylamine nitrate (in 0.5 M HNO₃) was added. After stirring 1.3 h, the supernatant solution changed from a pale yellow color to colorless, suggesting that the small amount of chromate present was *reduced* rather than oxidized, forming the insoluble Cr(III). No Cr was detected in the supernatant solution by ICP analysis. This is consistent with what was observed with non-radioactive alkaline chromate solutions and actual PFP wash solutions (see below). Thus, although the published reduction potential (Huheey 1978) predicts that hydroxylamine should oxidize Cr(III) in alkaline solution, the opposite is true. Hydroxylamine is not suitable for the leaching of insoluble chromium(III) from PFP sludge waste, but it is suitable for reducing chromate to Cr(III) for safer storage and disposal (as grout).

(a) A sample of the supernatant solution was titrated with standard HCl, which indicated the equivalent concentration of base in the solution was 0.16 M.

Treatment of the washed PFP-2 sludge with hydrazine at room temperature also did not result in any dissolution of chromium. No Cr was detected in the supernatant solution after treating the washed PFP sludge with hydrazine. In this case, an excess of hydrazine was not used--the amount added was approximately the stoichiometric amount needed to oxidize the Cr(III) present in the sludge.

3.2.3 Leaching of Cr by Alkaline Digestion and Oxidation with Permanganate

In experiment PFP-3, potassium permanganate was found to oxidize Cr(III) to Cr(VI) under mild conditions; thus it is considered to be the most promising reagent for selective leaching Cr from PFP sludge.

In experiment PFP-3, a portion of PFP sludge that had been washed with 0.1 M NaOH (Table 2.1) was first treated with 10 mL of 0.1 M NaOH at 100°C for 2 h. The supernatant solution turned yellow, and spectrophotometry revealed that chromium was present in solution as chromate ion. This is presumably due to oxidation of Cr(III) by manganese dioxide:

If all the Mn present in the sludge were present as MnO_2 , and 70% of the Cr were present as Cr(III), a nearly stoichiometric amount of MnO_2 would be present to react with the Cr(III). However, ICP data show that only 2.3% of the chromium was dissolved in this treatment (Table 3.2). The majority of the Mn present in the sludge is probably in the form of $\text{Mn}(\text{OH})_2$ and would thus not react with Cr(III).

The supernatant solution was decanted and replaced with an equal volume of 0.1 M NaOH. Then 0.048 g of KMnO_4 (~ are equivalent MnO_4^- /equivalent of Cr in the sludge) was added, and after stirring for 2.5 h at room temperature, the solution had turned yellow; spectrophotometry showed that the yellow color was due to chromate ion. The reaction of Cr(III) with KMnO_4 is described by the following equation:

Treatment with an additional 0.042 g of KMnO_4 resulted in a deeper yellow solution, indicating that more chromium had dissolved and that all the permanganate had been reduced. To ensure maximum leaching of chromium, the remaining sludge was treated with another 0.042 g KMnO_4 in 10 ml of 0.1 M NaOH. The total amount of KMnO_4 added represented a slight stoichiometric excess (approximately 1.3 fold) of that required to oxidize the Cr(III) present in the sludge. After stirring overnight, the purple permanganate color still remained, indicating that the limit had been reached on the amount of chromium that could be removed under these mild conditions. At this point, 14% of the Cr initially present remained in the sludge (Table 3.2).

The solution obtained by leaching PFP sludge with permanganate was tested qualitatively^(a) for alpha activity and none was found; thus, the leach solution appears to be non-TRU. However, more rigorous testing remains to be done.

In experiment PFP-7B, the effect of temperature on the leaching of Cr with KMnO_4 was investigated. In this experiment, 0.648 g of PFP sludge sample 34COMP was washed four times with 5 mL 0.1 M NaOH at 100°C. The washed sludge was then treated with 10 mL 0.014 M KMnO_4 in 0.1 M NaOH. After stirring overnight, the sludge/ KMnO_4 mixture was heated for 1 h at 100°C. After this, the purple color of permanganate remained, indicating that an excess of KMnO_4 had been used. Analysis of the wash solutions, leach solution, and the residual solids revealed that 27.1% of the Cr was dissolved in the wash step and 69.3% was dissolved in the leach step, leaving only 3.6% of the Cr remaining in the leached solids (Table 3.2).

Two other significant results were obtained in experiment PFP-7B. The behavior of P is of interest because, if the Cr is removed from PFP sludge,

(a) The qualitative method for detecting alpha activity is described in footnote (b) of Table 3.4.

this component defines the volume of glass required to vitrify the waste. Likewise, if Cr and P are removed, Al becomes the limiting component of the sludge.

As can be seen from Table 3.2, 100% of the P was removed in the wash step of experiment PFP-7B. Sludge washing with 0.1 M NaOH at 100°C removed 69.1% of the Al, and another 29.8% was removed in the Cr leach step, leaving only 1.1% of the Al in the leached solids. Thus, it would appear that the three major glass limiting components, Cr, P, and Al, can be removed from PFP sludge by washing with 0.1 M NaOH at 100°C followed by leaching with alkaline KMnO_4 at 100°C. If it can be ensured that the wash and leach solutions are non-TRU, this pretreatment approach may compete economically with the acid dissolution/TRU extraction process in reducing the volume of glass required to vitrify PFP sludge.

3.2.4 Mechanism of the Reaction of Cr(III) With Permanganate

The oxidation of Cr(III) to Cr(VI) with MnO_4^- proceeds through at least two steps. When a solution of KMnO_4 in 0.1 M NaOH is mixed with an excess of Cr_2O_3 , the purple permanganate color disappears within 5 min, and the solution becomes emerald green.^(a) Upon standing overnight, a beige precipitate forms (presumably MnO_2), and the solution turns yellow. The green intermediate has been identified as manganate ion (MnO_4^{2-}) by spectrophotometry.

Figure 3.2 shows the uv-vis spectrum of the solution at various time intervals during the reaction of Cr_2O_3 with KMnO_4 . It can be seen that after 5 min, the bands due to permanganate ($\lambda_{\text{max}} = 305, 349, 436, 526, 546, 568,$ and 598 nm) have disappeared and are replaced by bands with λ_{max} at 360, 434, and 604 nm. The latter bands are characteristic of MnO_4^{2-} (Carrington and Symons 1956). These bands slowly decrease with concomitant formation of the beige precipitate. After standing overnight, the spectrum reveals only CrO_4^{2-} ($\lambda_{\text{max}} = 374$ nm). Thus, when Cr(III) reacts with MnO_4^- , the MnO_4^{2-} ion is formed along with an unidentified Cr intermediate. The MnO_4^{2-} is ultimately reduced to MnO_2 , while the Cr intermediate is oxidized further to CrO_4^{2-} .

(a) This green color was also observed in chromium leaching experiments with actual PFP sludge waste.

FIGURE 3.2. UV-Vis Spectra of the Reaction of Cr_2O_3 with KMnO_4 in 0.1 M NaOH Indicating the Transition From MnO_4^- (a) to MnO_4^{2-} (b) to CrO_4^{2-} (c). (The conversion from MnO_4^- to MnO_4^{2-} occurs in less than 5 min, while the complete oxidation of Cr^{3+} to CrO_4^{2-} requires up to several hours.

The fact that the permanganate oxidation of Cr(III) proceeds through an intermediate step might afford an opportunity to remove the chromium from the sludge without adding additional manganese (as MnO_2) to the sludge. Equation 2 dictates that for every molar equivalent of chromium that is leached from the sludge, a molar equivalent of Mn must be added. However, as discussed in the preceding paragraph, the precipitation of MnO_2 is not immediate, yet the reaction of permanganate with Cr(III) to form MnO_4^{2-} is rapid. Thus, the leach solution containing MnO_4^{2-} , and the intermediate chromium species (if it is soluble) could be separated from the sludge prior to precipitation of MnO_2 . Regardless of whether the MnO_2 is allowed to precipitate, removing Cr from PFP sludge by treatment with permanganate will greatly reduce the glass canisters required to dispose of this waste, because there is a tenfold greater tolerance for Mn in the vitrification feed compared to Cr.

3.2.5 Reduction of Leached Cr With Hydroxylamine

As indicated earlier, the leaching of chromium from PFP sludge with alkaline permanganate solution results in a solution of Cr(VI), which will most probably have to be reduced to Cr(III) before permanent disposal as grout. Preliminary tests suggest that this can be achieved by treating the alkaline chromate solution with hydroxylamine. A chromate solution prepared by treating Cr_2O_3 with KMnO_4 in alkaline solution was treated with hydroxylamine nitrate. Within 75 min, the solution had become colorless, suggesting the reduction of Cr(VI) to Cr(III); the latter presumably precipitated as chromium(III) hydroxide.

The reduction of Cr(VI) to Cr(III) with hydroxylamine was also demonstrated using an actual PFP sludge wash solution. The first wash solution in experiment PFP-6 contained 0.0065 M Cr. The 1.0 mL of this solution was treated with 0.13 mL 1.5 M hydroxylamine nitrate at 100°C. After 1 h, the solution had changed from yellow to colorless and a pale green precipitate had formed. Analysis of the resulting solution revealed that the Cr content of the solution had decreased only to 0.0016 M. A much larger decrease is expected from the solubility product of $\text{Cr}(\text{OH})_3$; this suggests that Cr(VI) reduction was not complete under these conditions and/or that complexing agents were present in the sludge.

3.3 SOLVENT EXTRACTION of TRANSURANIC ELEMENTS

The second approach for pretreating PFP sludge being investigated is to dissolve the washed sludge in HNO_3 and then extract the TRU elements from the dissolved sludge solution. In this way, the TRU material requiring vitrification would be concentrated into a very small fraction, while the bulk sludge material could be disposed of in grout.

The extractant that is currently being investigated to extract the TRUs from acid dissolved sludges is octyl(phenyl)-N,N-diisobutylcarbamoylmethylphosphine oxide (CMPO). The overall pretreatment process will involve the following steps: 1) sludge washing, 2) sludge dissolution, and 3) extraction of TRUs with CMPO. In this section, we discuss the acid dissolution of PFP sludge and the results of preliminary extraction tests with CMPO.

3.3.1 Acid Dissolution of Washed PFP Sludge

Most of the major components of PFP sludge can be dissolved in dilute (1-3 M) nitric acid. The results of acid dissolution studies done in experiments PFP-1, -3, -6, -7, and -8 are summarized in Table 3.2; the details of the acid dissolution process are given in Sections 2.3 to 2.8. In experiment PFP-1, the washed PFP sludge was treated at ambient temperature with 2.1 M HNO_3 (total volume of 17.5 mL). Of the major components in the sludge, only aluminum did not show good dissolution under these conditions. As can be seen in Table 3.2, greater than 90% dissolution of Cr,^(a) Fe, and Mn was achieved in 2.1 M HNO_3 , whereas only 18.7% of the aluminum dissolved. Thorium and uranium both dissolved readily under these conditions.

The vast bulk of the radionuclides present in the sludge after sludge washing dissolves in nitric acid. Table 3.3 lists the percentages of each radioisotope that dissolved in the acid dissolution step of experiment PFP-1. Except for ^{125}Sb , greater than 90% of the radionuclides dissolved in nitric acid. A significant fraction (9%) of ^{60}Co remained in the undissolved

(a) In the case of chromium, 59.6% of the total chromium in the sludge sample was found in the acid dissolution step. This represents 92% of the chromium that remained in the sludge after the sludge washing and H_2O_2 leaching procedures.

residue, along with 100% of the reported ^{125}Sb . Significantly, 98.8% of the alpha emitting transuranic elements were dissolved. Between the sludge washing and acid dissolution steps, 98.9% of the total β activity (presumed to be mostly ^{90}Sr) and 99.9% of the ^{137}Cs were dissolved.

Results of Experiment PFP-3 also indicate that the bulk of the solids in PFP sludge remaining after the MnO_4^- leach treatment can be dissolved in nitric acid. In this experiment, 86% of the chromium had been removed by permanganate leach prior to the acid dissolution step. After the washing and leaching procedures had been carried out, the sludge was mixed with 10 mL of 1.7 M HNO_3 at ambient temperature for 1 h, then at 100°C for 1 h.

The amount of various sludge components dissolved by this treatment is summarized in Table 3.2. These results indicate that the amount of aluminum dissolved in this experiment was much greater than was observed in experiment PFP-1. In experiment PFP-3, 61.2% of the total Al was found in the dissolved sludge solution; this represents 85% of the aluminum that remained in the sludge after the washing and permanganate leaching procedures. Only 76.4% of the iron in the sludge dissolved under these conditions, but the remaining iron could be dissolved by adding acetohydroxamic acid (AHA).

After separating the undissolved residue from the dissolved sludge solution, 10 mL of 2.3 M HNO_3 was added to the remaining solids, and the solution was made 2.8 M in acetohydroxamic acid. After stirring for 1 h, at room temperature, virtually all of the remaining solids had dissolved.^(a) The percentage of each element found in this 2.3 M HNO_3 /2.8 M AHA solution are listed in Table 3.2.

To determine if better dissolution was achieved in the presence of oxalic acid, a sample of washed PFP sludge was dissolved (at room temperature) in 3 M HNO_3 in the presence (PFP-6B) and absence (PFP-6A) of 0.2 M oxalic acid. The percentages of the major sludge components dissolved are summarized in Table 3.2. Surprisingly, these data indicate that the dissolution of Al,

(a) There was a small amount of undissolved residue, but the quantity of this material was too small to work with. This residue was removed from the solution by filtration.

Cr, and Fe (which are the three most abundant components of the washed sludge) are decreased by the addition of oxalic acid. This is especially true for Cr; 84% of the Cr in the washed sludge dissolved in the absence of oxalic acid whereas only 31% dissolved when oxalic acid was present.

The reason for the decrease in sludge dissolution by the addition of oxalic acid is not understood. To determine if oxalate was present, we tested both solutions (after standing at room temperature for 80 days) for oxalate ion by treating an aliquot of the solution with a small amount of potassium permanganate in 0.9 M H_2SO_4 at 60°C. For both solutions, the MnO_4^- color persisted which indicated that *neither* solution contained oxalate ion.

Thus it appears that oxalate ion was destroyed under the conditions that dissolution PFP-6B was done (or on standing). The destruction of oxalate may have been catalyzed by some component of the sludge. Because of the lack of understanding of the chemical phenomenon occurring during the dissolution in $\text{HNO}_3/\text{H}_2\text{C}_2\text{O}_4$, we can make no conclusions regarding the efficacy of oxalate as an aid in PFP sludge dissolution.

As was the case in experiments PFP-1 and -3, the results from experiment PFP-6A indicate that good dissolution of PFP sludge was achieved in dilute (3 M) HNO_3 at ambient temperature. Greater than 80% dissolution was obtained for most components. Again, the exception to this was Al; only 20% of the Al in the washed sludge dissolved. However, the low Al dissolution may not be a major problem for the following reasons:

- improved removal of Al can likely be achieved by doing the sludge wash step at elevated temperature (vide supra)
- there is a fairly high tolerance for Al in the feed to HWVP.

The solutions prepared by dissolution of PFP sludge appear to be stable towards precipitation for long periods of time (months).

3.3.2 SEM and Particle Size Analyses

Particle size analyses were performed on samples of washed PFP sludge and on the residue remaining after dissolution of PFP sludge in HNO_3 (from experiment PFP-8). The results were obtained in terms of the percentage of the total *number* of particles present in a given particle size range, and in

terms of the percentage of the total particulate *volume* comprised by particles within a given particle size range.^(a) Data from these analyses are presented in Figures 3.3 and 3.4.

On average, the particles found in the washed sludge were smaller than those found in the undissolved residue. This is seen most readily by referring to Figure 3.3; 75% of the total number of particles in the washed sludge are smaller than 1 μm , whereas in the undissolved residue only 30% of the particles are smaller than 1 μm . The volume distributions show a similar trend in that 100% of the volume of the washed sludge particles consists of particles smaller than 21 μm whereas a significant portion of the volume of the undissolved residue is occupied by particles greater than 21 μm (but less than 74 μm).

SEM analyses were conducted on the washed sludge and undissolved residue from experiment PFP-8; energy dispersive spectra were also obtained during these SEM studies. The electron micrographs are shown in Figure 3.5, and selected energy dispersive spectra are shown in Figure 3.6.

The washed sludge consisted mostly of agglomerated particles (Figure 3.5a). The energy dispersive spectrum taken over a wide range of this material indicates that the predominant elements present are Al, Ca, Cr, Mn, and Fe (Figure 3.6a). The presence of Th is also evident. The energy dispersive spectrum indicates that little Na is present in the washed sludge.

In addition to the agglomerated particles, distinct rectangular particles are evident in the washed PFP sludge. The energy dispersive spectrum of such particles shows them to be an Al species (Figure 3.6b). SEM examination of the undissolved residue indicates that the residue consists primarily of the same type of Al species (Figure 3.5b and 3.6c). Presumably, this is some insoluble form of aluminum oxide.

(a) The volumes were calculated assuming the particles to be spheres.

FIG33.SPG

FIGURE 3.3. Particle Size Analysis of Washed PFP Sludge and Residual Solids Remaining After Dissolution in HNO_3 : Cumulative Distribution Graphs

FIGURE 3.4. Particle Size Analysis of Washed PFP Sludge and Residue Remaining After Dissolution in HNO_3 : Probability Density Graphs

FIGURE 3.5a. Scanning Electron Micrograph of Washed PFP Sludge. (Agglomerated chunks such as **A** are high in Al, Cr, Fe, and Mn. The primary metallic component of the cubic particles (e.g., **B**) is Al.)

3.3.3 TRU Removal by Solvent Extraction

Experiments addressing the utility of solvent extraction for the pre-treatment of PFP sludge have shown that CMPO is capable of extracting sufficient quantities of TRUs from dissolved PFP sludge solutions so that the bulk of the material originally in the sludge can be disposed of as low-level waste. However, slow disengaging times have sometimes been observed upon contacting dissolved PFP sludge solutions with 0.2 M CMPO. Adding complexants to or heating the feed solution improves phase disengagement behavior.

The dissolved sludge solution from PFP-1 was diluted with an equal volume of water to give a feed solution that was 0.8 M HNO_3 . When this solution

FIGURE 3.5b. Scanning Electron Micrograph of the Residue Remaining After Dissolution of PFP Sludge in Nitric Acid. (The residue consists primarily of cubic particles that are high in Al [compare to particle B in Figure 3.5a]).

was contacted with 0.2 M CMPO at an organic-to-aqueous phase ratio of 0.33, the transuranic content of the aqueous phase decreased 89% (this corresponds to a distribution coefficient of 24), which indicates that extraction with CMPO should be effective in removing TRUs from dissolved PFP sludge solutions. However, the time required for the organic phase to separate from the aqueous phase was quite long. After the phases were mixed by shaking for 60 sec, the mixture was allowed to stand. The phases had not separated after 5 min. Even after centrifuging for one minute, the organic phase was still cloudy. Centrifugation for 10 min was required to clear both phases.

FIGURE 3.6. Energy Dispersive Spectra Obtained During Scanning Electron Microscopy Studies (see Figure 3.5): a) Washed PFP Sludge, X-ray Beam Directed Over a Wide Area; b) Washed PFP Sludge, X-ray Beam Directed Upon Al-Rich Cubic Particle (Particle B in Figure 3.5a); and c) Undissolved Residue, X-ray Beam Directed Over a Wide Area.

In experiment PFP-3, two parallel solvent extraction experiments were carried out. In one case (P-3-14A), the feed solution was 1.2 M HNO_3 plus 1.4 M acetohydroxamic acid (AHA); in the other case (P-3-13A), the feed solution was 0.8 M in HNO_3 . The presence of the complexant had two effects on the extraction contact: (1) the extraction of key inert components (i.e., Cr, Fe, Al, and Si) was suppressed, and (2) the phases separated much more quickly when AHA was present.

The latter effect has been quantified by the measuring the dispersion number. The dispersion number for the contact with P-3-14A was 1.5×10^{-3} , whereas that for P-3-13A was less than 4.3×10^{-4} . A viable process utilizing centrifugal contactors can be designed for systems where the dispersion number is as low as 3×10^{-4} , but if the dispersion number is below this, considerable phase carry-over will occur (according to R. Leonard of Argonne National Laboratory in a personal communication). Thus, for feed solutions similar to that of P-3-13A, the long disengaging time may preclude using CMPO. However, CMPO solvent extraction flowsheets have generally assumed the presence of complexants (oxalate or fluoride) in the feed solutions (as in P-3-14A), so this may not be a problem.

The feed solutions (P-3-13A and P-3-14A) were each contacted with 0.2 M CMPO at an organic-to-aqueous phase ratio of 0.32. Two subsequent contacts ($o/a = 0.33$) of the aqueous phases with fresh 0.2 M CMPO were also carried out. The concentration of some of the important components in the feed solutions P-3-13A and P-3-14A are given in Table 3.6, along with the concentrations after the first extraction contact; also presented in this table are the alpha activities of the aqueous phases after each contact. As can be seen, AHA suppresses the extraction of Al, Cr, Fe, and Si. AHA also suppresses the extraction of the TRUs, but the distribution coefficients for the TRUs are sufficiently high even in the presence of AHA to yield a viable process. In the case where no complexant was present, 99.9% of the alpha activity had been removed after the third contact; whereas when AHA was present, 99.7% of the total alpha activity had been removed. In both cases, the raffinate from the third extraction contained less than 10 nCi/mL.

Phase disengagement behavior was also studied as part of experiment PFP-6. This experiment utilized PFP sludge sample 34COMP. A number of different contacts were carried out using feeds prepared by dissolving washed 34COMP in HNO_3 or $\text{HNO}_3/\text{H}_2\text{C}_2\text{O}_4$. The results are summarized in Table 3.7.

In general, the phase disengagement behavior observed with these solutions prepared from PFP sludge sample 34COMP was better than that observed with solutions prepared from 102SY-3T4S (experiments PFP-1 and -3). In all

TABLE 3.6. Effect of AHA on CMPO Solvent Extraction Process, Experiment PFP-3

P-3-13 (without AHA)				P-3-14 (with AHA)		
After first contact				After first contact		
	Feed,M	Extr., M	D	Feed, M	Extr., M	D
Al	0.0687	0.0666	0.09	0.0086	0.0090	~0
Cr	0.0033	0.0028	0.55	0.0025	0.0026	~0
Fe	0.0623	0.0595	0.14	0.0144	0.0149	~0
Si	0.0098	0.0070	1.16	0.0015	0.0017	~0

P-3-13 (without AHA)				P-3-14 (with AHA)		
Total alpha, dpm/mL						
Contact	Feed,M	Extr., M	D	Feed, M	Extr., M	D
1	4.86×10^7	2.27×10^7	30	2.83×10^6	4.61×10^5	16
2		1.71×10^5	37		6.10×10^4	20
3		1.30×10^4	37		7.35×10^3	22

cases, the gross phases separated rapidly (in less than 120 sec); however, in certain cases, a few bubbles persisted in the organic phase for greater than 5 min. In experiment PFP-1, it took much longer than 2 min for the gross phases to separate.

The results presented in Table 3.7 also indicate that heating the dissolved sludge solution prior to contacting with the 0.2 M CMPO improved phase disengagement behavior as did addition of complexants. The phase disengagement behavior seen in contacts P-6B-SX1, P-6B-SX1', P-6A-SX2, and P-6A-SX3 was similar to that observed with dissolved NCRW solutions.

Processing dissolved PFP sludge by CMPO solvent extraction was also investigated as part of experiment PFP-8. Of interest in this experiment were 1) the effective removal of TRU from the dissolved PFP solution, 2) the possibility of using just one scrub solution (oxalic acid), and 3) the use of

TABLE 3.7. Effect of Complexants and Heating on Phase Separation^(a)

Contact Number	[Fe]	[Cr]	[Al]	[Mn]	[Ca]	[H ⁺]	[H ₂ C ₂ O ₄]	[AHA] ^(b)	Heated ^(c)	t, sec ^(d)	Dispersion Number
P-6A-SX1	0.0062	0.0043	0.0028	0.0018	0.0014	1.7	0	0	N	>300 ^(e)	<0.00011
P-6B-SX1	0.0064	0.0022	0.0024	0.0019	0.0014	1.6	0 ^(f)	0	N	80	0.00042
P-6B-SX1'	0.0064	0.0022	0.0028	0.0019	0.0014	1.6	0.1 ^(g)	0	N	70	0.00048
P-6A-SX5	0.0062	0.0043	0.0028	0.0018	0.0014	1.7	0	0	N	>300	
P-6A-SX2	0.0062	0.0043	0.0028	0.0018	0.0014	1.7	0	0	Y	135	
P-6A-SX6	0.0062	0.0043	0.0028	0.0018	0.0014	1.7	0.1	0	N	>300	
P-6A-SX3	0.0062	0.0043	0.0028	0.0018	0.0014	1.7	0.01	0	Y	90	
P-6A-SX7	0.0062	0.0043	0.0028	0.0018	0.0014	1.7	0	0.1	N	>300	
P-6A-SX4	0.0062	0.0043	0.0028	0.0018	0.0014	1.7	0	0.1	Y	>300 ^(e)	

(a) Concentrations of the various sludge components in the feed solutions are given in moles/L.

(b) AHA = acetoxyhydroxamic acid = CH₃CONHOH.

(c) If yes, the aqueous phase was heated at 100°C for one hour, then was allowed to cool prior to contact.

(d) t = time for phases to break.

(e) The gross phases broke rapidly, but bubbles persisted in the organic phase.

(f) Based on the amount of oxalic acid added during the dissolution process, the concentration of oxalic acid should have been 0.1 M; however subsequent analysis of the dissolved sludge solution indicated there was no oxalic acid present (see Section 3.4).

(g) Oxalic acid added to P-6B-SX1.

sodium citrate as the stripping agent.^(a) In this experiment, the dissolved sludge solution was diluted with an equal volume of water and was then contacted three successive times with 0.2 M CMPO; the organic phase from the first extraction contact was scrubbed with 0.1 M $\text{H}_2\text{C}_2\text{O}_4$ and then was stripped with 0.2 M sodium citrate (see Table 2.2).

Extraction with CMPO was shown to effectively remove TRU from dissolved PFP sludge solutions. The feed solution contained 10200 nCi TRU/mL (as determined by total alpha analysis); the raffinates from the first, second, and third extraction steps contained 1120, 45, and 4 nCi TRU/mL, respectively. Thus, a decontamination factor of 2250 was achieved. It should be noted that no oxalic acid was present in the feed solution. Under counter-current process conditions, the aqueous phase in the extraction contactors would be expected to contain oxalic acid (from the scrub stages); this would presumably lower the extraction efficiency somewhat. However, it can be concluded that the CMPO is capable of separating TRUs from bulk components of PFP sludge waste.

The distribution coefficient for the TRUs would be expected to decrease for each subsequent extraction contact due to the decrease in the HNO_3 concentration that results from the extraction of HNO_3 by the CMPO solvent. The distribution coefficients for the TRUs in the first, second, and third extraction steps were 16, 72, and 31, respectively. For the second and third extraction contacts, the expected decrease in the distribution coefficient for the TRUs was observed. However, the distribution coefficient for the first contact was lower than expected. This is likely due to loading of the solvent with Th. The feed solution contained 0.0315 M Th, which was extracted quantitatively into the CMPO solvent. Am and Pu must compete with the Th for coordination to CMPO. Because the Th was removed in the first extraction, better extraction of the TRUs was achieved in subsequent extraction contacts.

(a) Earlier studies of the CMPO solvent extraction process utilized 1-hydroxyethane-1,1-diphosphonic acid as stripping agent (Lumetta 1992a, Swanson 1991). However, use of this reagent could result in excessive amounts of phosphorus being introduced into the feed to the vitrification plant. Thus, a search for alternative stripping agents was undertaken; sodium citrate is one such alternative.

The behavior of other important non-TRU sludge components is summarized in Table 3.8. The distribution coefficients for the major non-radioactive sludge components (Al, Ca, Cr, and Fe) are small, whereas La, Th, and U are extracted by CMPO, as would be expected.

During the scrub with 0.1 M oxalic acid solution, a considerable amount of precipitate formed. This solid was found to consist primarily of Th. Thus, the amount of Th present in PFP waste precludes the use of one scrub solution of straight oxalic acid. We would recommend that a $\text{HNO}_3/\text{H}_2\text{C}_2\text{O}_4$ solution should be used in the first scrub step to remove extracted inert components (e.g. Fe), followed by water in the second scrub step to reduce the acid concentration in the extract prior to the strip step.

Because of the precipitate that formed in the scrub steps, a detailed analysis of the stripping data from this experiment, in terms of mass balance, could not be done. However, it did appear that nearly all of the alpha activity in the scrubbed extract was removed in the first strip contact. The aqueous phase from this contact contained 12600 nCi TRU/mL. The second and third strip steps contained only 79 and 10 nCi TRU/mL, respectively. Based on these results, we conclude that sodium citrate effectively strips the TRUs from 0.2 M CMPO.

TABLE 3.8. Behavior of Major PFP Sludge Constituents in the CMPO Solvent Extraction Process

Component	Feed, M	Raffinate from Extr 1, M	D
Al	0.0690	0.0686	0.010
Ca	0.0134	0.0118	0.275
Cr	0.0298	0.0302	~0
Fe	0.0781	0.0780	0.004
La	0.00014	$<2 \times 10^{-5}$	>18
Mn	0.0332	0.0338	~0
Na	0.0458	0.0466	~0
Th	0.0315	$<1 \times 10^{-4}$	>940
U	0.0011	$<1 \times 10^{-3}$	?

Thus, it has been demonstrated that CMPO is capable of extracting TRUs from dissolved PFP sludge solutions. The raffinate solutions typically contain less than 10 nCi/mL. Figure 3.7 shows a conceptual flowsheet for this process; details such as flow rates and the strip solution to be used are not given because additional work is required to determine these details. The sludge will be washed with dilute NaOH at 100°C. The wash solution containing most of the Na, Al, and P, and a portion of the Cr will be disposed of in grout. The washed sludge will be dissolved in HNO₃. The residue that remains after dissolution will contain sufficient TRU material that it must be disposed of in glass. After a solid liquid separation step, the dissolved sludge solution will be fed into the CMPO extraction process. The raffinate from the extraction will contain the bulk sludge components (Fe, Cr, Mn, etc.) while the solution from the stripping stages will contain the Am and Pu. Depending on the strip solution used, the Th and U will end up either in the strip solution (along with the Am and Pu) or in the solvent wash (sodium carbonate) solution.

3.4 CONCLUSION

The two pretreatment options for PFP sludge investigated here, Cr leaching and TRU solvent extraction, both show great promise for reducing the volume of borosilicate glass required to vitrify this waste. Further investigations of these two approaches are planned.

FIGURE 3.7. Conceptual Flowsheet for the Pretreating PFP Sludge by Extracting the TRU Components of the Sludge with CMPO. (Flow rates and the strip solution to be used are not given, because these are yet to be determined.)

4.0 REFERENCES

Carrington, A., and M. C. R. Symons. 1956. "Structure and Reactivity of the Oxy-anions of Transition Metals. Part I. The Manganese Oxy-anions." *J. Chemical Society* 1956:3373-3380.

Huheey, J. E. 1978. *Inorganic Chemistry: Principles of Structure and Reactivity*. 2nd ed., Harper & Row, New York, pp. 318-322.

Lumetta, G. J., and J. L. Swanson. 1993. "Evaluation of 1-Hydroxyethane-1,1-diphosphonic Acid and Sodium Carbonate as Stripping Agents for the Removal of Am(III) and Pu(IV) from TRUEX Process Solvent." *Sep. Sci. Technol.*, 28:43-58.

Swanson, J. L. 1991. *Use of the TRUEX Process for the Pretreatment of Neutralized Cladding Removal Waste (NCRW) Sludge - Results of a Design Basis Experiment*. PNL-7734, Pacific Northwest Laboratory, Richland, Washington.

Windholz, M., S. Budavari, R. F. Blumetti, and E. S. Otterbein, eds. 1983. *The Merck Index*. 10th Edition. Merck & Co., Rahway, New Jersey. P. 56.

DISTRIBUTION

No. of Copies

OFFSITE

12 DOE/Office of Scientific and
Technical Information

C. Frank
U.S. Department of Energy
1000 Independence Avenue, SW
Mail Stop 5B014
Washington, DC 20855

T. Fryberger
EM-542, Trevion II
U.S. Department of Energy
19901 Germantown Road
Germantown, MD 20874

J. C. Tseng
7A-075/FORS
U.S. Department of Energy
1000 Independence Avenue
Washington, DC 20585

E. P. Horwitz and
G. F. Vandegrift
Argonne National Laboratory
9700 South Cass Ave.
Argonne, IL 60439

S. L. Yarbrow
Los Alamos National Laboratory
Los Alamos, NM 87545

No. of Copies

ONSITE

3 DOE Richland Field Office

P. E. Lamont, A5-16
C. K. Liu, A5-16
J. C. Peschong, A5-16

7 Westinghouse Hanford Company

J. N. Appel, S4-58
S. A. Barker, S4-58
W. B. Barton, L4-75
R. A. Kirkbride, S4-58
B. C. Landeene, S4-58
S. S. Lowe, H5-49
R. M. Orme, S4-58

35 Pacific Northwest Laboratory

G. H. Bryan, P7-25
W. C. Cosby, P8-08
L. K. Holton, P7-43
E. O. Jones, P8-38
W. W. Laity, K2-50
G. J. Lumetta, P7-25 (20)
B. M. Rapko, P7-25
R. D. Scheele, P7-25
L. J. Sealock, K2-10
M. J. Wagner, G2-02
Publishing Coordination
Technical Report Files (5)

**DATE
FILMED**

7 / 22 / 93

END