DOE/ER/45132--7

DE92 040210

DYNAMICS AND PATTERN SELECTION AT THE CRYSTAL-MELT INTERFACE

PROGRESS REPORT

For the Period March 1, 1992 to February 29, 1993

Prepared for

THE U. S. DEPARTMENT OF ENERGY
DE-FG02-84ER45132

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Prepared by:
Professor Herman Z. Cummins
Principal Investigator
Department of Physics
The City College of CUNY
Convent Avenue @ 138th Street
New York, NY 10031

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

II. SUMMARY OF RESULTS OF PRIOR D.O.E. GRANTS

A. MORPHOLOGICAL INSTABILITY AND PATTERN SELECTION

At the end of the preceding grant period, we completed a quantitative study of the time evolution of the Mullins-Sekerka instability at the crystal-melt interface^(a,T1) and the dynamics of the associated pattern initiation process by noise^(b). We then turned to the problem of pattern selection in steady-state dendritic growth.

Microscopic solvability theory (MST), which is currently thought to be the correct approach to this problem, provides specific numerical predictions for the tip radius ρ and growth velocity V of steady state dendrites, uniquely determined by the undercooling of the melt and the material parameters of the solidifying substance. Attempts to test these predictions have been hampered by the absence of precise values of the surface tension anisotropy ϵ which is a crucial parameter in the theory. We therefore undertook the construction of an apparatus designed to measure ϵ accurately, and measured it for succinonitrile, pivalic acid, and pivalic acid with 1% ethanol. The results of these measurements were used to compare the MST predictions with previous experimental results^(c,T3). A reprint of the resulting publication is attached as Appendix I.

B. SIDEBRANCHING

The continuous generation of sidebranches on a growing dendrite is not addressed by the steady-state MST, and is generally thought to reflect a secondary instability of the steady-state dendrite to thermal noise. To investigate this phenomenon quantitatively we built a new

apparatus in which a pulse of laser light can be focussed on the tip of a single dendrite growing in directional solidification. The experiment demonstrated that the thermal perturbation of a laser pulse can generate a sidebranch, and that the development of the induced sidebranch is in good qualitative agreement with theoretical predictions^(d). A reprint of this publication is attached as Appendix II. Subsequently, we extended this experiment to study the effects of a periodic perturbation, in the form of a sequence of laser pulses with period τ , applied to a growing dendrite. This experiment is currently in progress and will be continued in the next grant period. A discussion of the experiment, and some preliminary results, are presented in Section IV. An article based on our first completed experiment is currently in preparation.

C. PLANAR-TO-CELLULAR TRANSITION

In directional solidification of binary alloys, the initial instability (with increasing growth velocity) is a planar-to-cellular Mullins-Sekerka instability. There has been considerable theoretical and experimental work concerning the subcritical or supercritical nature of this bifurcation.

We have constructed a new apparatus to study this bifurcation. Initially we have looked for hysteresis in cell amplitude vs growth speed as was done in previous experiments. However, the new aspect of our experimental approach is the application of a localized heat pulse which creates a bump on the otherwise flat interface. Monitoring the time evolution of the bump provides a sensitive probe of the bifurcation. The apparatus for this experiment was completed in April, and preliminary results have recently been obtained. The preliminary experimental res-

ults are described in detail in Section V.

D. DYNAMIC LIGHT SCATTERING AT THE CRYSTAL-MELT INTERFACE

During the current grant period we completed our final experiments on this phenomenon. We have demonstrated that the strong interfacial light scattering observed on the liquid side of the interface is caused by gaseous microbubbles produced by the build-up of dissolved gases in the boundary layer due to solute rejection during solidification, as we had previously proposed. We showed that after prolonged directional solidification, the bubbles grow to sizes large enough to be observed visually and photographed^(f). Finally, in a collaborative experiment with Ladeira and Mesquita in Brazil, we showed that the properties of this dynamic light scattering in succinonitrile and in naphthalene can be very well described by the microbubble model^(g,T2).

These experiments completed the verification of the explanations for the two light scattering mechanisms responsible for the observed spectra in crystal growth experiments. Light scattered from the crystal side of the interface reveals the dynamics of growing screw dislocations or layers, while light scattered from the fluid side of the boundary is due to microbubbles. Both mechanisms were proposed and verified in this laboratory.

PUBLICATIONS - (References for Section II)

a. Evolution of the Dendritic Instability in Solidifying Succinonitrile, Henry Chou and H.Z. Cummins, Phys. Rev. Lett. 61, 173 (1988).

b. Role of Noise in the Initial Stage of Solidification Instability,

X.W. Qian, Henry Chou, M. Muschol and H.Z. Cummins, Phys. Rev. B 39, 2529 (1989).

c. Surface Tension Anisotropy of Succinonitrile and Pivalic Acid: New Measurements and Comparison with Microscopic Solvability Theory, M. Muschol, D. Liu and H.Z. Cummins, Phys. Rev. A 46, 1038 (1992).

d. Dendritic Sidebranching Initiation by a Localized Heat Pulse , X.W. Qian and H.Z. Cummins, Phys. Rev. Lett. 64, 3038 (1990).

e. Pattern Forming Instabilities at the Crystal-Melt Interface, H.Z. Cummins in: *Fundamental Problems in Statistical Mechanics VII* (Altenberg, F.R.G. 18-30 June, 1989), edited by H. van Beijeren (Elsevier Science Publishers, 1990) p. 11.

f. Direct Observation of Microbubbles in Directional Solidification of Salol, L.M. Williams, M.R. Srinivasan and H.Z. Cummins, Phys. Rev. Lett. 64, 1526 (1990).

g. Angular Intensity of Nonequilibrium Interfacial Dynamic Light Scattering: Succinonitrile and Naphthalene, L.M. Williams, H.Z. Cummins, L.O. Ladierra and O.N. Mesquita, Phys. Rev. A 45, 3880 (1992).

h. Dynamic Light Scattering at the Nonequilibrium Crystal-Melt Interface, H.Z. Cummins and L.M. Williams, in: *Light Scattering by Liquid Surfaces and Complementary Techniques* edited by D. Langevin (New York: Marcel Dekker, 1992).

Ph.D. Dissertations Completed During the Current Grant Period

T1. Henry Chou, July 29, 1988 "Morphological Instability and Pattern Selection in Solidifying Succinonitrile"

T2. Lloyd Williams, July 31, 1991 "Light Scattering at the Nonequilibrium Crystal Melt Interface: Salol and Succinonitrile"

T3. Martin Muschol, April 2, 1992 "Surface Tension Anisotropy of Succinonitrile and Pivalic Acid: New Measurements and Comparison with Microscopic Solvability Theory"

END

DATE
FILMED

10 / 22 / 92