NOVEL CONCEPT DEVELOPMENT OF AN INTERNAL RECIRCULATION CATALYST FOR MILD GASIFICATION

Progress Report for the Period March 1, 1988-May 31, 1988

By
**R. A. Knight
S. P. Babu**

September 1988

Work Performed Under Contract No.: DE-AC21-86MC23057

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia 26505

By
Institute of Gas Technology
Chicago, Illinois

**TECHNICAL INFORMATION CENTER
OFFICE OF SCIENTIFIC AND TECHNICAL INFORMATION
UNITED STATES DEPARTMENT OF ENERGY**

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

YOB

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Printed in the United States of America

Available from
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road
Springfield, VA 22161

NTIS price codes
Printed copy: A01
Microfiche copy: A01

NOVEL CONCEPT DEVELOPMENT OF AN INTERNAL RECIRCULATION CATALYST FOR MILD GASIFICATION

Progress Report for the Period March 1, 1988-May 31, 1988

By
R. A. Knight
S. P. Babu

September 1988

Work Performed Under Contract No.: DE-AC21-86MC23057

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26505

By
Institute of Gas Technology
IIT Center, 3424 S. State Street
Chicago, Illinois 60616

MASTER

GROUP
2/28/93
FBI
BY 1010

EXECUTIVE SUMMARY

This report presents the results of work performed between March 1 and May 31, 1988 under DOE Contract No. DE-AC21-86MC23057. The objective of this program is to provide an overall evaluation of a novel process concept for mild gasification by completing work in three major tasks: 1) Laboratory-Scale Experiments, 2) Bench-Scale Tests, and 3) Proof-of-Concept Tests and Evaluation (optional).

During this quarter, experimental work involving zinc chloride as a potential recirculating catalyst for coal, initiated in the previous quarter, was continued. The design of an all-quartz laboratory-scale isothermal free-fall reactor was completed, and construction was begun. One free-fall experiment was performed in an existing stainless-steel free-fall reactor with methanol-treated Illinois No. 6 high-volatile bituminous coal.

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
Task 1. Laboratory-Scale Tests	1
Task 2. Bench-Scale Tests	1
Task 3. Proof-of-Concept Tests and Evaluation	1
TECHNICAL PROGRESS	2
Task 1. Laboratory-Scale Tests	2
Objective and Approach	2
Discussion	2
Isothermal Free-Fall Experiments	3
Problems and Solutions	7
REFERENCES CITED	8

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

LIST OF FIGURES

<u>Figure No.</u>		<u>Page</u>
1	Sketch of Main Components of Quartz Isothermal Free-Fall Reactor System	4
2	Schematic Diagram of Quartz Isothermal Free-Fall Reactor System	5

LIST OF TABLES

<u>Table No.</u>		<u>Page</u>
1	Analysis of Methanol-Treated Feed Coal Samples	6
2	Free-Fall Devolatilization Experiment RC-051388	6

INTRODUCTION

The goal of this program is to evaluate a novel process concept for mild gasification of coal using an internal recirculating catalyst. This report describes progress during the seventh quarter of the program. The work is divided into three major tasks:

1. Laboratory-Scale Tests
2. Bench-Scale Tests
3. Proof-of-Concept Tests and Evaluation (optional).

The objectives of the individual tasks are described below.

Task 1. Laboratory-Scale Tests

The objective of this task is to obtain detailed information on the effects of the selected internal recirculation catalyst on the products of mild coal gasification using a pyrolysis-gas chromatograph (PY-GC) system. Three different types of coals (Illinois No. 6, Wyodak subbituminous, and North Dakota lignite) are to be tested. The effects of operating conditions on product quality will be investigated.

Task 2. Bench-Scale Tests

The objective of this task is to conduct larger-scale tests than those of Task 1 to determine the effects of the catalyst on the products of mild coal gasification. These tests are to be conducted with a selected test coal in existing experimental equipment.

Task 3. Proof-of-Concept Tests and Evaluation

The objective of this task, which is subject to the approval of DOE/METC to proceed, is to conduct large-scale testing of the effect of the internal recirculation catalyst on mild coal gasification and process design and economic studies. These large-scale tests are to be conducted in an existing 8-inch-diameter gasifier.

TECHNICAL PROGRESS

Task 1. Laboratory-Scale Tests

Objective and Approach

The objective of this task is to obtain detailed information on the effects of the selected internal recirculation catalyst of the products of mild coal gasification under various reaction conditions. These experiments are to be conducted using a laboratory-scale pyrolysis-gas chromatographic system. Three different types of coals (Illinois No. 6, Wyodak subbituminous, and North Dakota lignite) are to be tested.

All work performed during this reporting period was under Subtask 1.2, Laboratory-Scale Catalytic Coal Devolatilization Tests.

Discussion

In the previous technical progress report for the period of December 1, 1987 to February 29, 1988, the results of the experiments using the PY-GC device were reported, along with data from experiments conducted in a thermogravimetric analyzer, a Fischer Assay apparatus, and a combustion-tube reactor. Comparisons were made on the effects of zinc chloride catalyst on the yields and properties of products from these four types of devolatilization apparatus.

There is evidence in the literature on ZnCl_2 -catalyzed coal devolatilization work, particularly in the study by Kandiyoti *et al.*,¹ that this catalyst will enhance tar yields at high particle heating rates, but will have the opposite effect under slow-heating conditions. To explore this possibility, a series of rapid-heating free-fall devolatilization experiments have been scheduled, and a quartz-tube reactor system will be constructed for that purpose. A decision was made not to use an existing stainless-steel free-fall reactor for experiments with catalyzed coal because of potential corrosion from HCl generated by ZnCl_2 in the presence of moisture.

The reactor system will consist of an (existing) screw/star feeder which can feed -100+200 mesh coal at up to 3 grams/minute (0.4 lb/h), two interchangeable 1-inch-ID quartz reactor tubes of 24-inch and 36-inch lengths, a heated Pyrex char receiver vessel with a high-capacity ceramic fiber filter, and a series of coolers and tar traps to recover condensable products. The

vertically oriented reactor tube will be heated by an external electric furnace, and will allow for the coal to be rapidly heated in free-fall with concurrent gas flow. The particle residence time at mild gasification temperatures will be 0.5 to 2.0 seconds, and the vapor residence time will be approximately 1 to 3 seconds. The operating pressure will not exceed 20 psig.

A sketch of the main system components as they will be assembled is shown in Figure 1, and a schematic diagram is shown in Figure 2. The product recovery subsystem is a unique design in which a solvent (methylene chloride) will be introduced at the char filter inlet and the char filter bottom to serve two purposes: as a quench for the hot, volatiles-laden gas stream entering the char filter, and as a purging solvent to wash tars and oils from the char and help carry these materials over to the downstream condensing section. The use of solvent in this way also reduces the need for posttest washing of the system components to remove condensibles, and also will tend to dilute the condensibles, helping to avoid secondary polymerization and degradation reactions. The char filter will be maintained at about 220° to 230°F in order to vaporize the incoming solvent.

A fabricator has been selected for the quartz isothermal free-fall reactor system glassware, and the system components have all been ordered. A coal feeding system has also been assembled, including fabrication of a stainless steel star feeder module.

A freshly mined sample of Illinois No. 6 coal has been obtained from the Peabody Coal Company, Randolph Preparation Plant. This sample has been wet-crushed and wet-screened to the required -100+200-mesh size range and stored under inert gas in preparation for free-fall devolatilization experiments.

Isothermal Free-Fall Experiments

To establish baseline operating data with uncatalyzed samples of the Illinois No. 6 coal received from the Peabody Coal Company, Randolph Preparation Plant, a series of experiments were scheduled for the existing 1-1/2-inch-ID stainless-steel isothermal free-fall reactor. One experiment was performed during the report period using methanol-treated coal under CO₂ atmosphere. The analysis of the treated feed coal is shown in Table 1, and the experimental conditions and resulting data are shown in Table 2.

Figure 1. SKETCH OF MAIN COMPONENTS OF QUARTZ ISOTHERMAL FREE-FALL REACTOR SYSTEM

Figure 2. SCHEMATIC DIAGRAM OF QUARTZ ISOTHERMAL FREE-FALL REACTOR SYSTEM

Table 1. ANALYSIS OF METHANOL-TREATED FEED COAL SAMPLES

Coal type: Illinois No. 6 high-volatile bituminous
Source: Peabody Coal Company, Randolph Prep Plant

	<u>Analysis</u>
Proximate, wt %	
Moisture	6.35
Volatile Matter	37.42
Ash	6.99
Fixed Carbon	49.24
Total	100.00
Ultimate, dry ash-free %	
Carbon	80.49
Hydrogen	5.67
Sulfur	3.60
Nitrogen	1.80
Oxygen (by difference)	8.43
Total	100.00
HHV (Btu/lb, measured, dry)	13,405.0

Table 2. FREE-FALL DEVOLATILIZATION EXPERIMENT RC-051388

Coal size range, mesh	-100+200
Feed sample type	MeOH-treated
Coal feed rate, g/min	1.75
Duration of coal feed, min	25.3
Reactor temperature, °F	1490
Reactor pressure, psig	66.3
Inlet gas composition	100% CO ₂
Inlet gas flow rate, SCF/h	1.1
Particle residence time, s	1.5
Gas/vapor residence time, s	83.2

The Illinois No. 6 coal was pretreated with methanol according to the following procedure: Coal was mixed with an equal weight of methanol and stirred for 3 hours at room temperature; the methanol was then boiled off until all free liquid was gone; the coal was then dried overnight under vacuum at 104°F and stored under CO₂ at partial vacuum until used. During the experiment, difficulty was encountered in maintaining a steady gas composition, as indicated by the on-line CO monitor. A plug of agglomerated

coal/char had accumulated in the inlet probe, thus restricting the passage of coal into the reactor. For this reason, only 44.3 grams of coal were actually fed to the reactor. Corrective modifications were made to the operating procedure to avoid the recurrence of this problem.

More detailed data from this experiment, including yield and material balance data, will be reported when the remaining two experiments in the existing free-fall reactor are completed during the next quarter.

Problems and Solutions

The previously generated data indicate that the zinc chloride catalyst does not have any significant effect on devolatilization yields at slow heating rates. Rapid-rate devolatilization experiments can be conducted in a free-fall reactor, but the existing stainless-steel system is unsuitable for the following reason. Zinc chloride, heated in the presence of moisture, which is generated during coal devolatilization, may produce a significant amount of corrosive hydrogen chloride; the sintered stainless-steel filter used in the existing system to separate the hot (600°F) gas stream from the char, as well as other metallic system components, would be expected to undergo significant corrosion under these conditions, leading to sample contamination, flow disruption, damage to valves, etc. This problem is being addressed by constructing a simple, low-pressure corrosion-resistant free-fall reactor to conduct these experiments. All heated components in this system are to be made from quartz, glass, or Teflon.

REFERENCES CITED

1. Kandiyoti, R., Lazaridis, J. I., Dyrvold, B. and Weerasinghe, C. R., "Pyrolysis of a ZnCl_2 -Impregnated Coal in an Inert Atmosphere", Fuel, 63, 11, 1583-1587 (1984).

19WP/61086Ma/RPP

**DATE
FILMED
8/3/92**