CATALYTIC FABRIC FILTRATION FOR SIMULTANEOUS NO.
AND PARTICULATE CONTROL

DOE/PC/90361--T6

DE92 017974

Quarterly Technical Progress Report
for the period January 1 - March 31, 1992

by

Greg F. Weber, Project Manager
Sumitra R. Ness, Research Engineer
Dennis L. Laudal, Research Engineer
Grant Dunham, Research Engineer

Energy and Environmental Research Center
University of North Dakota
Box 8213, University Station
Grand Forks, ND 58202-8213

Contracting Officer's Representative: Ms. Felixa Eskey

for

U.S. Department of Energy
Pittsburgh Energy Technology Center
626 Cochran Mill Road
Pittsburgh, PA 15236-0940

May 1992

MASTER

Work Performed under Contract No. DE-AC22-90PC90361

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

TABLE OF CONTENTS

	<u>Page</u>
1.0 INTRODUCTION	1
2.0 SCOPE OF WORK	2
3.0 GOALS AND OBJECTIVES	3
4.0 ACCOMPLISHMENTS	4
4.1 Task 2--Design and Construct Test Unit	4
4.2 Subtask 3.1--Fundamental Testing	4
4.3 Subtask 3.2--Process Testing/Reverse-Gas System	12
4.3.1 Nitric Oxide Removal Efficiency	12
4.3.1.1 PTC-IL6-414	12
4.3.1.2 PTC-IL6-115	16
4.3.1.3 PTC-IL6-416	20
4.3.1.4 PTC-IL6-417	21
4.3.1.5 PTC-IL6-418	27
4.3.1.6 PTC-IL6-419	27
4.3.1.7 PTC-NG-420	31
4.3.1.8 PTC-NG-421	34
4.3.2 Particulate Collection	36
4.3.2.1 Run No. PTC-IL6-414	36
4.3.2.2 Run No. PTC-IL6-415	38
4.3.2.3 Run No. PTC-IL6-416	38
4.3.2.4 Run No. PTC-IL6-417	49
4.3.2.5 Run No. PTC-IL6-419	49
4.4 Subtask 3.3--Process Testing/Pulse-Jet System	61
4.5 Subtask 3.4--Fabric Durability Testing/Pulse-Jet System	61
5.0 KEY PERSONNEL STAFFING REPORT	62
6.0 REFERENCES	62

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1 Schematic of the on-line ammonia analysis system	5
2 Percent NO _x removal versus heat treatment temperature for bench-scale tests with Fabric DE484	8
3 Percent NO _x removal versus heat treatment temperature for bench-scale tests with Fabric DE992	8
4 Percent NO _x removal versus heat treatment temperature normalized to an NH ₃ /NO _x molar ratio of 0.9 for Fabric DE992	9
5 Percent NO _x removal versus heat treatment temperature normalized to an NH ₃ /NO _x molar ratio of 0.9 for Fabric DE484	9
6 Percent NO _x removal versus heat treatment temperature for Fabric DE484 with aqueous-based coating	10
7 NO _x removal efficiency as a function of time for Run PTC-IL6-414 .	14
8 NO _x removal efficiency as a function of time for Run PTC-IL6-415 .	17
9 NO _x removal efficiency as a function of air-to-cloth ratio and NH ₃ /NO _x molar ratio for Run PTC-IL6-415	20
10 NO _x removal efficiency as a function of time for Run PTC-IL6-416 .	22
11 NO _x removal efficiency as a function of time for Run PTC-IL6-417 .	24
12 NO _x removal efficiency as a function of air-to-cloth ratio and NH ₃ /NO _x molar ratio for Run PTC-IL6-417	26
13 NO _x removal efficiency as a function of time for Run PTC-IL6-419 .	28
14 NO _x removal efficiency as a function of air-to-cloth ratio and NH ₃ /NO _x molar ratio for Run PTC-IL6-419	30
15 NO _x removal efficiency as a function of time for Run PTC-IL6-420 .	32
16 NO _x removal efficiency as a function of air-to-cloth ratio and NH ₃ /NO _x molar ratio for Runs PTC-IL6-417 and PTC-NG-420	33
17 NO _x removal efficiency as a function of time for Run PTC-NG-421 .	35
18 Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.0 ft/min for Run PTC-IL6-414	37
19 Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.4 ft/min for Run PTC-IL6-414	37

LIST OF FIGURES (Continued)

<u>Figure</u>	<u>Page</u>
20 Baghouse differential pressure as a function of time for Run PTC-IL6-414	42
21 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-415	42
22 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-415	43
23 Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.5 ft/min for Run PTC-IL6-415	43
24 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.3 ft/min for Run PTC-IL6-415	44
25 Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min for Run PTC-IL6-415	44
26 Baghouse differential pressure as a function of time for Run PTC-IL6-415	45
27 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416	46
28 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416	46
29 Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.3 ft/min for Run PTC-IL6-416	47
30 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416	47
31 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.2 ft/min for Run PTC-IL6-416	48
32 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416	48
33 Baghouse differential pressure as a function of time for Run PTC-IL6-416	50
34 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-417	50
35 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-417	51

LIST OF FIGURES (Continued)

<u>Figure</u>	<u>Page</u>
36 Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.5 ft/min for Run PTC-IL6-417	51
37 Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.5 ft/min for Run PTC-IL6-417	52
38 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.3 ft/min for Run PTC-IL6-417	52
39 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.3 ft/min for Run PTC-IL6-417	53
40 Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.5 ft/min for Run PTC-IL6-417	53
41 Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.5 ft/min for Run PTC-IL6-417	54
42 Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min for Run PTC-IL6-417	54
43 Baghouse differential pressure as a function of time for Run PTC-IL6-417	55
44 Baghouse differential pressure as a function of time for Run PTC-IL6-419	57
45 Coulter Counter data for Runs PTC-IL6-408 through PTC-IL6-419 . .	58
46 Multicyclone data for Runs PTC-IL6-408 through PTC-IL6-419	58

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1 Bench-Scale Catalyst-Coated Fabric Heat Treatment Test Results . .	5
2 Initial Catalyst-Coated Fabric Deactivation Experiments	11
3 Coal and Ash Analyses of Illinois #6 Bituminous Coal Used for Runs PTC-IL6-408 Through PTC-IL6-419	13
4 Summary of Run No. PTC-IL6-414	15
5 Summary of Run No. PTC-IL6-415	18
6 Summary of Run No. PTC-IL6-416	23
7 Summary of Run No. PTC-IL6-417	25
8 Summary of Run No. PTC-IL6-419	29
9 Summary of Run No. PTC-NG-420	33
10 Summary of Run No. PTC-NG-421	36
11 Particulate Sampling Data for Pilot-Scale Catalytic Fabric Filter Tests	39
12 Multicyclone Data from Run PTC-IL6-408	41
13 Multicyclone Data from Run PTC-IL6-414	41
14 Multicyclone Data from Run PTC-IL6-415	45
15 Multicyclone Data from Run PTC-IL6-416	49
16 Multicyclone Data from Run PTC-IL6-417	55
17 Multicyclone Data from Run PTC-IL6-419	56
18 Reverse-Gas Baghouse Ash Analysis Results	59
19 Vanadium Concentration Analysis Results	60
20 Planned Versus Actual Workhours for Key Personnel Through March 1992	62

CATALYTIC FABRIC FILTRATION FOR SIMULTANEOUS NO_x AND PARTICULATE CONTROL

1.0 INTRODUCTION

The University of North Dakota Energy and Environmental Research Center (EERC); Owens-Corning Fiberglas Inc. (OCF); and Stearns-Roger, a division of United Engineers & Constructors (UE&C) are conducting research to develop a catalytic fabric filter for simultaneous NO_x and particulate control. Funding for the project is being provided by the U.S. Department of Energy/Pittsburgh Energy Technology Center (DOE/PETC), Consolidated Edison Company of New York Inc. (Con Edison), and the Empire State Electric Energy Research Corp. (ESEERCO).

The DOE/PETC funding was secured as a result of a competitive award from the DOE/PETC Advanced NO_x Control program. The objective of this program is to develop advanced concepts for removal of NO_x from flue gas emitted by coal-fired utility boilers, or for the control of NO_x formation by advanced combustion modification techniques. Funded projects are required to focus on the development of technology that significantly advances the state of the art using a process or a combination of processes capable of reducing NO_x emissions to 60 ppm or less. The concept must have successfully undergone sufficient laboratory-scale development to justify scaleup for further evaluation at the pilot scale (not to exceed 5 MWe in size). Other requirements include production of a nonhazardous waste or a salable by-product. The concept should have application to both new and retrofit coal-fired systems. The concept should also show the potential for a 50% cost savings when compared to a commercial selective catalytic reduction (SCR) process capable of meeting the 60-ppm NO_x emission limit.

The EERC approach to meeting the program objective involves the development of a catalytic fabric filter for simultaneous NO_x and particulate control. The idea of applying either permanent or throwaway catalysts to a high-temperature fabric filter for NO_x control is not new (1-4). However, advances at OCF have shown that a high-activity catalyst can be applied to a high-temperature woven glass cloth resulting in a fabric filter material that can operate at temperatures higher than the maximum operating temperatures of commercially available, coated glass fabric. The NO_x is removed by catalytic reduction with ammonia to form nitrogen and water. The catalyst employed at this time is vanadium/titanium, but the exact catalyst composition and the unique method of applying the catalyst to high-temperature glass fabric are the property of OCF (5). Other catalyst options are being evaluated by OCF in order to improve catalyst performance and minimize catalyst cost.

Bench-scale experimental results to date have shown that over 90% NO_x removal can be achieved, the catalyst/fabric has promising self-abrasion characteristics, and the potential exists for substantially reduced cost when compared with conventional SCR/fabric filtration technology (6, 7). However, development of the technology requires further evaluation of air-to-cloth ratio, ammonia slip, SO₂ oxidation to SO₃, temperature cycling, catalyst-coated fabric preparation, fuel impacts, fabric cleaning (reverse-gas versus pulse-jet), catalyst life (poisoning and resistance to erosion), and filter performance/life (particulate control, differential pressure, and durability).

2.0 SCOPE OF WORK

The specific approach being used to address these issues is represented by the following:

- Task 1--Program Definition
- Task 2--Design and Construct Test Unit
- Task 3--Experimental Program and Data Reduction
- Task 4--Conceptual Design and Economic Evaluation
- Task 5--Test Unit Removal

Task 1, Program Definition, required preparation of a Project Management Plan. This document contains a detailed scope of work, project schedule, and project budget; identifies key project personnel; and presents an appropriate QA/QC plan for the project. Task 2, Design and Construct Test Unit, is divided into three subtasks. Subtasks 2.1 and 2.2 involved the detailed design of the test facility on which the experimental program is being performed, the construction of the test facility, and an operational shakedown of the system prior to initiating the experimental effort. Subtask 2.3 involves OCF preparation of the catalyst-coated fabric filters that are being evaluated in the experimental effort.

Task 3, Experimental Program and Data Reduction, has four subtasks. Subtask 3.1, Fundamental Testing, is intended as a support effort to the primary experimental test plan. This effort should supply information needed to thoroughly understand the process mechanism, allow screening of additional fabric samples, address the issue of catalyst poisoning, and generally support the pilot-scale effort. Subtask 3.2, Process Testing/Reverse-Gas System, is intended to evaluate process performance in a pilot-scale reverse-gas fabric filter, identify and optimize important process variables, and provide data for a conceptual design. Subtask 3.3, Process Testing/Pulse-Jet System, will evaluate process performance in a pilot-scale pulse-jet fabric filter. Subtask 3.4, Fabric Durability Testing/Pulse-Jet System, will evaluate catalyst-coated fabric durability/performance for up to 12,000 hours in a slipstream pulse-jet baghouse.

Based on the results of Task 3, a technical and economic assessment of the catalytic fabric filter concept will be completed in Task 4, Conceptual Design and Economic Evaluation. Task 5, Test Unit Removal, requires the identification of all major test facilities, equipment, and instruments and hardware, and their condition, ownership, and proposed disposition.

EERC is the primary contractor for the project and is responsible for the management/direction of all technical and administrative project activities. EERC has specifically performed all work associated with Task 1 and Subtasks 2.1 and 2.2 and will perform Tasks 3 and 5.

OCF will perform and/or supervise all work associated with Subtask 2.3, including manufacturing the "S" glass fabric, coating the fabric, and manufacturing the filter bags for the reverse-gas and pulse-jet systems. This effort, as well as technical support, is being provided by OCF as a cost share to the project.

UE&C, as a subcontractor to EERC, provided technical support for Task 1 and will perform Task 4. EERC personnel involved in the Task 3 effort and OCF personnel will provide input to UE&C Task 4 activities.

The project schedule is based on a project start date of October 1, 1990, and assumes a project duration of 36 months. Therefore, the planned project completion date is September 30, 1993.

Federal funding accounts for roughly 56% of the total project budget. Commercial funding for the project makes up the remaining 44%. Con Edison and ESEERCO are each funding 12% of the project cost, and OCF is contributing 10% in the form of catalyst-coated filter bags and technical support for the project. The remaining 10% is uncommitted at this time, but EERC is pursuing funding options in an effort to obtain a formal commitment for the remaining commercial cost share as soon as possible.

3.0 GOALS AND OBJECTIVES

The overall objective of this project is the development of a catalyst-coated fabric filter for simultaneous NO_x and particulate control. The catalyst-coated fabric filter must provide high removal efficiency of NO_x and particulate matter. An acceptable bag and catalyst life must be demonstrated, and process economics must show a significant cost savings when compared to a commercial SCR process and conventional particulate control. Specific goals include the following:

- Reduce NO_x emissions to 60 ppm or less.
- Demonstrate particulate removal efficiency of >99.5%.
- Demonstrate a bag/catalyst life of >1 year.
- Control ammonia slip to <25 ppm.
- Show that catalytic fabric filtration can achieve a 50% cost savings over conventional fabric filtration and SCR control technology.
- Determine compatibility with SO_2 removal systems.
- Show that the concept results in a nonhazardous waste product.

Specific project activities during the past quarter (January through March 1992) were to include the following:

- Complete Task 2, Design and Construct Test Unit.
- Continue Subtask 3.1, Fundamental Testing.
- Continue Subtask 3.2, Process Testing/Reverse-Gas System.
- Initiate Subtask 3.3, Process Testing/Pulse-Jet System.
- Initiate Subtask 3.4, Fabric Durability Testing/Pulse-Jet System.

4.0 ACCOMPLISHMENTS

4.1 Task 2--Design and Construct Test Unit

Setup of the Siemens on-line ammonia analyzer was completed. The ammonia analyzer has three parts: the SO_2 absorption system, the NH_3 converter, and the IR analyzer. Each of these components is shown in Figure 1. To prevent water condensation in the system, all components and sample lines are maintained at a temperature of $\geq 100^\circ\text{C}$.

Ammonia will react quickly with SO_2 at temperatures below 250°C ; therefore, the SO_2 must be removed from the gas stream. This is accomplished by passing the flue gas through a container of sodium carbonate that is maintained at a temperature of 340°C . Each charge of sodium carbonate will absorb essentially 100% of the flue gas SO_2 for approximately 18 hours, depending on the SO_2 concentration in the flue gas.

The next primary component of the ammonia analysis system is the ammonia converter. The analyzer is designed with a flowthrough reference cell. To measure the concentration of ammonia in the flue gas, it is then necessary to remove the ammonia from the gas stream entering the reference cell. This is accomplished by using a small selective catalytic reduction reactor (ammonia converter). As in most SCR processes, the catalyst is composed of vanadium and titanium and is operated at 300°C . There is a large excess of catalyst in comparison to the amount of ammonia entering the unit; therefore, near 100% conversion is accomplished.

The Siemens analyzer is an infrared spectrophotometer with flowthrough reference and detector cells. As shown in Figure 1, the gas stream is split prior to the analyzer, with part of the stream entering the detector cell and the other stream entering the reference cell after the ammonia has been removed by the converter. Since the gases, with the exception of the ammonia, are the same in each cell, the interferences are minimized.

An important part of the instrument operation is the calibration procedure. With the ammonia turned off, the instrument is zeroed on the actual flue gas to be tested. This is done three times per day. After the instrument has been zeroed, it is spanned with a known calibration gas. The calibration gas must be reasonably close to the expected ammonia concentration in the flue gas (0-50 ppm, 50-100 ppm, >100 ppm). This must be done daily.

To evaluate the accuracy of the analyzer, several tests were completed using the particulate test combustor (PTC) while firing natural gas. A known quantity of ammonia was injected into the system, and the ammonia concentration in the flue gas was then monitored using both the ammonia analyzer and wet chemistry techniques. Due to a leak in the ammonia injection system, the test results are invalid.

4.2 Subtask 3.1--Fundamental Testing

Data collected from bench-scale runs in support of the pilot-scale testing to date are shown in Table 1 and Figures 2-6. The figures show the data in two forms: as collected and normalized to an ammonia/ NO_x molar ratio

Figure 1. Schematic of the on-line ammonia analysis system.

TABLE 1
Bench-Scale Catalyst-Coated Fabric Heat Treatment Test Results

Fabric Type	Heat Treatment Temp. (°F)	Heat Treatment Time (hrs)	Run Temp. (°F)	NO Removal (%)	NH ₃ Slip (ppm)	NH ₃ /NO Molar Ratio ^a	Heat Treatment Medium
DE484	504	1	650	48.0	400	0.88	Air
DE484	504	1	504	18.0	670	0.85	Air
DE484	563	1	650	64.0	170	0.81	Air
DE484	589	1	650	67.0	280	0.95	Air
DE484	589	1	589	58.0	380	0.96	Air
DE484	613	1	650	68.0	180	0.86	Air
DE484	636	1	650	70.0	170	0.87	Air
DE484	669	1	650	70.0	180	0.88	Air
DE484	688	2	650	84.0	90	0.93	Air
DE484	689	2	650	81.3	110	0.92	Air
DE484	692	2	650	76.0	190	0.95	Air
DE484	693	1	650	77.0	130	0.90	Air

Continued...

TABLE 1 (continued)

Fabric Type	Heat Treatment Temp. (°F)	Heat Treatment Time (hrs)	Run Temp. (°F)	NO Removal (%)	NH ₃ Slip (ppm)	NH ₃ /NO Molar Ratio ^a	Heat Treatment Medium
DE484	504	1	550	48.0	400	0.88	Air
DE484	504	1	504	18.0	670	0.85	Air
DE484	693	4	650	89.8	10	0.91	Air
DE484	718	1	650	82.6	44	0.87	Air
DE484	745	2	650	37.7	5	0.88	4% O ₂ /N ₂
DE484	747	1	650	90.0	7	0.91	Air
DE484	747	25	650	92.6	46	0.97	Air
DE484	749	5	650	95.6	45	1.00	Air
DE484	773	24	650	81.0	76	0.89	Air
DE484	775	2	650	95.2	30	0.92	4% O ₂ /N ₂
DE484	777	1.33	650	95.5	20	0.98	Air
DE484	800	1	650	94.4	30	0.97	Air
DE484	800	2	650	95.0	34	0.98	4% O ₂ /N ₂
DE484	825	2	650	88	60	0.94	4% O ₂ /N ₂
DE484	850	2	650	91.4	70	0.98	4% O ₂ /N ₂
DE484	875	2	650	62	200	0.82	4% O ₂ /N ₂
DE484	900	2	650	56.0	360	0.92	4% O ₂ /N ₂
DE992	504	1	650	81.0	105	0.92	Air
DE992	504	1	504	50.0	440	0.94	Air
DE992	523	1	650	75.5	85	0.84	Air
DE992	523	1	523	60.0	315	0.92	Air
DE992	563	1	650	82.0	40	0.86	Air
DE992	589	1	650	84.8	56	0.90	4% O ₂ /N ₂
DE992	589	1	650	86.2	28	0.89	Air
DE992	589	1	589	83.0	40	0.87	Air
DE992	613	1	650	86.5	25	0.89	Air
DE992	636	1	650	87.0	25	0.90	Air
DE992	669	1	650	87.0	25	0.90	Air
DE992	693	1	650	90.0	15	0.92	Air
DE992	693	4	650	92.6	6	0.93	Air
DE992	707	1	650	86.5	8	0.87	Air
DE992	707	2	650	91.2	4	0.92	Air
DE992	718	1	650	93.4	14	0.95	Air

Continued...

TABLE 1 (continued)

Fabric Type	Heat Treatment Temp. (°F)	Heat Treatment Time (hrs)	Run Temp. (°F)	NO Removal (%)	NH ₃ Slip (ppm)	NH ₃ /NO Molar Ratio ^a	Heat Treatment Medium
DE484	504	1	650	48.0	400	0.88	Air
DE484	504	1	504	18.0	670	0.85	Air
DE992	730	1	650	88.4	6	0.89	Air
DE992	730	2	650	98.6	36	1.02	4% O ₂ /N ₂
DE992	730	2	650	92	70	0.99	Air
DE992	730	2	650	97.4	40	1.01	Air
DE992	730	2	650	91.5	6	0.92	Air
DE992	730	2	650	88.0	120	1.00	N ₂
DE992	730	4	650	96.2	30	0.99	Air
DE992	745	2	650	89.0	26	0.92	Air
DE992	747	1	650	91.6	13	0.93	Air
DE992	747	25	650	93.1	16	0.95	Air
DE992	749	5	650	97.0	8	0.98	Air
DE992	750	1	650	89.5	0	0.90	Air
DE992	750	2	650	92.0	3	0.92	Air
DE992	773	24	650	88.0	44	0.92	Air
DE992	775	2	650	84	---	---	4% O ₂ /N ₂
DE992	775	2.5	650	90.6	50	0.96	4% O ₂ /N ₂
DE992	777	1.33	650	98.4	8	0.99	Air
DE992	800	1	650	98.0	10	0.99	Air
DE992	800	2	650	81.5	10	0.83	4% O ₂ /N ₂
DE992	825	2	650	75	125	0.88	4% O ₂ /N ₂
DE992	850	2	650	74	40	0.78	4% O ₂ /N ₂
DE992	875	2	650	62	200	0.82	4% O ₂ /N ₂
DE484-A	550	2	550	15.0	---	---	4% O ₂ /N ₂
DE484-A	550	2	650	33.0	---	---	4% O ₂ /N ₂
DE484-A	650	2	650	52.0	410	0.93	4% O ₂ /N ₂
DE484-A	700	2	650	55.0	360	0.91	4% O ₂ /N ₂
DE484-A	750	2	650	74.0	200	0.94	4% O ₂ /N ₂
DE484-A	800	2	650	78.0	100	0.88	4% O ₂ /N ₂
DE484-A	825	2	650	84	100	0.94	4% O ₂ /N ₂
DE484-A	875	2	650	73.5	200	0.94	4% O ₂ /N ₂
DE484-A	900	2	650	60	425	1.03	4% O ₂ /N ₂

^a Determined from ammonia slip and % NO_x removal.

Figure 2. Percent NO_x removal versus heat treatment temperature for bench-scale tests with Fabric DE484.

Figure 3. Percent NO_x removal versus heat treatment temperature for bench-scale tests with Fabric DE992.

Figure 4. Percent NO_x removal versus heat treatment temperature normalized to an NH_3/NO_x molar ratio of 0.9 for Fabric DE992.

Figure 5. Percent NO_x removal versus heat treatment temperature normalized to an NH_3/NO_x molar ratio of 0.9 for Fabric DE484.

Figure 6. Percent NO_x removal versus heat treatment temperature for Fabric DE484 with aqueous-based coating.

of 0.9. As reported in the Quarterly Technical Progress Report for October 1 through December 31, 1991, the nonnormalized data in Figures 2 and 3 indicate that at a constant air-to-cloth ratio, operating temperature, heating time, and ammonia/NO_x molar ratio, the percent NO_x removal appeared to increase linearly with increasing heat treatment temperature (500°-800°F) for both the DE992 and the DE484 fabrics. However, the normalized DE992 data in Figure 4 indicate a constant 85%-90% NO_x removal over a heat treatment temperature range from about 575°-800°F. For the DE484 fabric, the normalized data in Figure 5 show 85%-90% NO_x removal from about 725°-850°F and roughly 80% NO_x removal at 700°F. The DE484 fabric treated with an aqueous binder showed a definite increase in percent NO_x removal from 650°-825°F and a definite decrease from 825°-900°F.

As part of the fundamental studies task, a series of tests will be performed on the bench-scale reactor to determine the effect of several suspected deactivation agents on the performance of catalyst-coated fabric. The first catalyst-coated fabric selected is DE484, which was coated with an organic-based catalyst. A second fabric may be chosen based on pilot-scale data at a later date. Table 2 lists the deactivation agents chosen for the initial experiments. The experimental approach represents a worst-case scenario where the catalyst-coated fabric filters are wetted as a result of an upset condition in a full-scale baghouse. In such an upset condition, the water may leach various components from the ash layer on the fabric, creating an alkali-, acid-, or sulfur-rich solution. This solution would quickly evaporate at catalytic fabric filter operating temperatures. The bench-scale tests are designed to determine the effect of an upset condition on the NO_x removal efficiency of the catalyst-coated fabric.

TABLE 2

Initial Catalyst-Coated Fabric Deactivation Experiments

Fabric Type	A - Fabric DE484 (organic-based, V/Ti coating, equivalent to Fabrics #17 and #106A) B - Unselected
Deactivation Agents	Distilled Water Baseline Tap Water Baseline Sodium Hydroxide (0.001, 0.01, 0.1 Molar) Sulfuric Acid (0.001, 0.01, 0.1 Molar) Hydrochloric Acid (0.001, 0.01, 0.1 Molar) Calcium Sulfate and Calcium Sulfite Sodium Sulfate and Sodium Sulfite Calcium Oxide Fine Silica Lignite Ash (High Sodium, High Calcium) Lignite Ash (Low Sodium, High Calcium) Bituminous Ash (Low Sodium, High Calcium) Subbituminous Ash (High Sodium, Low Calcium)

Bench-Scale Screening Experiments:

<u>Temperature</u>	<u>Air-to-Cloth Ratio</u>	<u>Inlet NO_x Concentration</u>	<u>NH₃/NO_x Molar Ratio</u>
650°F	2 ft/min	1000 ppm	0.9

For the bench-scale simulation, three weak molar solutions (0.001, 0.01, 0.1) of sodium hydroxide, sulfuric acid, and hydrochloric acid will be used to represent basic and acidic conditions. To simulate an upset condition, fabric samples, previously heat-treated at 720°F, will be immersed in the given solution and dried at 93°C overnight. NO_x removal rates from these samples will be compared against those from a baseline nonwetted sample and samples wetted with distilled and tap water. In addition, four ash samples: a bituminous, a subbituminous, and two lignites will be tested to determine if catalyst deactivation occurs when ash-coated fabric has been wetted and dried. Samples will be prepared by wetting the fabric with tap water, coating with 2 mm of ash, immersing in tap water, and drying overnight at 93°C. Excess ash remaining on the fabric will be brushed off. As a check, additional tests using fine silica will be performed to determine if the preparation technique causes blinding of the catalyst-coated fabric. These samples will be compared with used fabrics from the pilot-scale tests to determine if the wetting step significantly changes the NO_x removal rates. If a significant difference is noted, subsequent tests will try to determine which ash component or components are responsible for deactivation. Since sodium and calcium sulfates are already strongly indicated as catalyst deactivation agents, they will be tested first.

The fabrics contaminated with acidic and basic solutions have been prepared. They are noticeably stiffer, and the 0.1 M sulfuric acid changed the fabric color from a light tan to chartreuse. The NO_x and NO₂ mass flow

controllers on the bench-scale system were sent in for repair in March. It appears that the o-rings have been decomposing, even after a short operating time. The manufacturer suspects improper installation of o-rings made of material readily attacked by NO_x and NH_3 . The mass flow controllers should be repaired in two weeks and available for experimental use by late April. While the mass flow controllers are being repaired, the bench-scale system will be reconfigured with a simpler valving arrangement. Once the controllers have been returned, the bench-scale system will be recalibrated prior to initiating experimental activities.

4.3 Subtask 3.2--Process Testing/Reverse-Gas System

Subtask 3.2, Process Testing/Reverse-Gas System, was continued this past quarter with the completion of five 100-hour tests (PTC-IL6-414, PTC-IL6-415, PTC-IL6-416, PTC-IL6-417, and PTC-IL6-419) and two 48-hour tests (PTC-NG-420 and PTC-NG-421). The purpose of the 100-hour tests was to evaluate several catalyst-coated fabric filters in a pilot-scale reverse-gas baghouse to simultaneously control particulate and nitric oxide (NO) emissions. In the original test plan, twelve individual experimental periods were planned for each 100-hour test, in order to address the effects of air-to-cloth ratio (1.5, 2, 3, 4 ft/min) and ammonia/ NO_x molar ratio (0.8, 0.9, 1.0). Baghouse temperature was to be held constant at 650°F, and flue gas was generated by firing a washed Illinois #6 bituminous coal in a pilot-scale pc-fired combustor. The average ultimate, proximate, and sieve analyses for the washed Illinois #6 coal used for the tests are presented in Table 3.

Owens-Corning Fiberglas Inc. provided catalyst-coated reverse-gas filter bags, woven from high-temperature glass fibers, for each 100-hour test. All bags tested were 12 inches in diameter by roughly 26 feet long.

4.3.1 Nitric Oxide Removal Efficiency

4.3.1.1 PTC-IL6-414

The catalyst-coated fabric filters used for this test were made from a 22-oz/yd² double-beam weave (DE992) fabric, coated with seven coats of an organic-based vanadium/titanium catalyst. For the pilot-scale tests, this fabric has been designated DE992. The bags were heat-treated for 4 hours at 730°F in a convective oven. This catalyst-coated fabric corresponds to Fabrics #17 and #106B from previous bench-scale tests.

Results from the 100-hour test were poor, with deteriorating NO_x removal efficiency throughout the test. After approximately 36 hours of operation, it was determined the bags were not performing as expected, and the test was terminated. Bench-scale results indicated that NO_x reduction with this fabric should have ranged as high as 85% to 93%, at a baghouse temperature of 650°F and an ammonia/ NO_x molar ratio of 0.9. Figure 7 shows the NO_x removal efficiency as a function of time, and Table 4 summarizes each test period. At an air-to-cloth ratio of 2.0 ft/min (two bags on line), the NO_x removal efficiency averaged 69%. When the air-to-cloth ratio was increased to 4.0 ft/min (one bag on line), the average removal efficiency dropped to 46%. After operating at air-to-cloth ratios of 1.5 and 3.0 ft/min, the air-to-cloth ratio was returned to 2.0 ft/min, and the NO_x removal efficiency averaged 53%. At this time, it was decided that there was a problem with the bags, and the

TABLE 3
Coal and Ash Analyses of Illinois #6 Bituminous Coal
Used for Runs PTC-IL6-408 Through PTC-IL6-419

	Average	Maximum	Minimum					
Proximate Analysis (wt%)								
Moisture	5.62	8.00	4.1					
Volatile Matter	34.26	35.85	32.8					
Fixed Carbon	48.74	51.45	45.81					
Ash	11.36	11.89	10.59					
Ultimate Analysis (wt%)								
Hydrogen	4.93	5.04	4.76					
Carbon	64.67	67.05	62.19					
Nitrogen	1.25	1.63	1.08					
Sulfur	3.28	3.37	3.22					
Oxygen	14.48	16.51	11.87					
Ash	11.36	11.89	10.59					
Heating Value								
(Btu/lb)	11,539	11,791	11,143					
Percent as Oxides (wt%)								
SiO ₂	48.14	50.9	42					
Al ₂ O ₃	19.00	20.1	17					
Fe ₂ O ₃	19.34	21.8	16.7					
TiO ₂	0.84	0.94	0.71					
P ₂ O ₅	0.32	0.37	0.3					
CaO	4.15	4.92	3.68					
MgO	1.20	1.41	1.06					
Na ₂ O	0.79	0.93	0.63					
K ₂ O	2.09	2.22	1.94					
SO ₃	3.78	5.7	2.61					
Ash Fusion								
Temp. (°F)								
Initial	2112	2222	2025					
Softening	2179	2263	2110					
Hemisphere	2259	2317	2204					
Fluid	2339	2370	2302					
Sieve Analysis								
Screen Mesh Size	wt% Retained							
	PTC-IL-408	PTC-IL-415	PTC-IL-416	PTC-IL-417	PTC-IL-419	Average	Max.	Min.
100	14.40	21.72	22.35	18.51	19.58	19.31	22.35	14.4
140	12.02	13.17	13.36	13.34	13.57	13.09	13.57	12.02
170	5.34	14.43	---	---	---	9.89	14.43	5.34
200	8.55	6.13	15.06	5.08	4.35	7.83	15.06	4.35
230	---	---	5.88	14.44	15.74	12.02	15.74	5.88
270	12.14	5.44	5.60	21.08	7.37	10.33	21.08	5.44
325	1.00	2.60	3.86	0.06	0.58	1.62	3.86	0.06
Pan	45.54	35.81	33.85	26.30	37.79	35.86	45.54	26.3
Total %	98.99	99.30	99.96	98.81	98.98	99.21	99.96	98.81

Figure 7. NO_x removal efficiency as a function of time for Run PTC-IL6-414.

TABLE 4

Summary of Run No. PTC-IL6-414

Reverse-Gas Baghouse					Measured					NO _x ^a Removal %	NH ₃ Slip ppm	SO ₂ ^b Conc. ppm	
Average		Bulk Gas Temp.		Average	East Bag wt. lb	West Bag wt. lb	SO ₂ Flue Gas Concentration ppm	O ₂ Inlet %	O ₂ Outlet %				NO _x Inlet ppm
Test Period #1, A/C=2.1, Molar Ratio=0.81													
Average	637	621	1	49	51		2772	5	5	918	294	66.49	350
Max.	649	635	2	52	52		2954	5	6	960	321	71.97	720
Min.	623	547	0	48	49		2656	3	4	863	240	62.18	
Test Period #2, A/C=1.9, Molar Ratio=0.89													
Average	622	609	3	50	48		2785	4	5	941	275	69.35	0.84
Max.	623	610	4	51	49		2867	4	5	992	304	71.88	
Min.	621	607	3	50	48		2715	3	4	902	254	66.68	
Test Period #3, A/C=1.8, Molar Ratio=0.85													
Average	631	601	2	51	52		2744	4	5	979	393	58.19	
Max.	633	604	4	53	55		2894	5	5	1006	426	61.85	
Min.	629	598	1	50	49		2656	4	4	938	363	54.37	
Test Period #4, A/C=1.7, Molar Ratio=1.13													
Average	623	597	4	51	50		2644	4	5	972	347	62.69	
Max.	627	602	4	51	51		2750	5	6	1004	378	66.91	
Min.	620	593	3	51	49		2564	4	4	936	308	59.39	
Test Period #5, A/C=3.4, Molar Ratio=1.21													
Average	627	---	4	51	53		2763	3	4	897	453	46.46	860
Max.	631	---	4	53	53		2894	4	5	944	491	49.51	
Min.	617	---	3	50	53		2680	3	4	829	417	43.88	
Test Period #6, A/C=3.3, Molar Ratio=0.87													
Average	624	---	4	46	53		2678	4	6	916	447	46.97	
Max.	626	---	4	46	53		2694	5	6	921	468	49.30	
Min.	621	---	4	46	53		2629	4	5	906	438	44.70	
Test Period #7, A/C=1.3, Molar Ratio=0.66													
Average	594	579	1	49	53		2659	5	5	927	448	50.60	
Max.	595	582	1	49	53		2673	5	5	934	457	53.10	
Min.	594	576	1	49	53		2639	4	5	919	431	48.25	
Test Period #8, A/C=1.6, Molar Ratio=0.9													
Average	605	590	2	48	52		2707	4	5	901	397	52.96	
Max.	606	592	3	48	52		2788	4	7	916	409	57.51	
Min.	604	589	2	48	52		2673	4	4	846	378	47.79	

* Corrected to 4% O₂.b NH₃ injection turned off.

test was terminated. When the bags were inspected, after the test, several holes were found in the bags. At first it was thought the bags were damaged by thermocouple probes during bag installation. However, it is believed the bags were damaged when they came in contact with a hot metal grate in the convective oven during the heat-treating process. In subsequent tests, the bags were heat-treated in the baghouse chambers using flue gas generated by firing natural gas. Results of multiple point surface area analysis on a damaged and undamaged sample of the fabric showed an increase in surface area on the damaged fabric. This may be due to "shattering of the catalyst coating, with accompanying fractures adding surface area." This fabric will be retested at a later date.

Results from ammonia slip and SO_3 measurements using wet chemistry techniques are also presented in Table 4. The ammonia slip measurements tend to confirm the low NO_x removal efficiencies, but appear to be very poor quantitative data. The SO_3 measurement was less than what might have been expected for a 3% sulfur coal, indicating no conversion of SO_2 to SO_3 across the filter bags. Ammonia injection was turned off during SO_3 sampling periods to avoid the potential for ammonia to interfere with the SO_3 measurement.

4.3.1.2 PTC-IL6-415

The catalyst-coated fabric filters used for this 100-hour test were the same bags used for test PTC-IL6-408, which were determined to be inadequately heat-treated. The bags were made from a 14-oz/yd² fabric with single-beam weave (DE484), coated with seven coats of an organic-based vanadium/titanium catalyst. The bags correspond to Fabrics #17 and #106A in previous bench-scale tests. For the pilot-scale tests, this fabric has been designated DE484.

The bags were heat-treated by exposing them to flue gas containing roughly 4.5% oxygen as a result of firing natural gas for approximately 9 hours. For the first 4.5 hours, the average bulk gas temperature in each chamber increased from 600° to 700°F. During the last 4 hours, the average bulk gas temperature ranged from 700° to 715°F. This seemed to have provided adequate heat treatment.

Results from the 100-hour test were good. Figure 8 shows the NO_x removal efficiency as a function of time, and Table 5 summarizes each test period. Nitric oxide removal ranged from 68% to 90%, depending on system operating conditions. At an air-to-cloth ratio of 2.0 ft/min, an ammonia/ NO_x molar ratio of 1.0, and an average baghouse bulk gas temperature of 680°F, NO_x removal averaged 89%. At an air-to-cloth ratio of 3.5 ft/min, an ammonia/ NO_x molar ratio of 0.9, and an average baghouse bulk gas temperature of 655°F, NO_x removal averaged 68%. Previous bench-scale results indicated NO_x removal of 76% to 90% for this fabric at an air-to-cloth ratio of 4.0 to 2.0 ft/min, an ammonia/ NO_x molar ratio of 0.9, an average bulk gas temperature of 650°F, and similar heat treatment. Figure 9 plots the NO_x removal efficiency as a function of air-to-cloth ratio and ammonia/ NO_x molar ratio. It can be seen that NO_x removal decreases with increasing air-to-cloth ratio and decreasing ammonia/ NO_x molar ratio.

Results from ammonia slip and SO_3 measurements using wet chemistry techniques are also presented in Table 5. During operation, the ammonia

Figure 8. NO_x removal efficiency as a function of time for Run PTC-IL6-415.

TABLE 5
Summary of Run No. PTC-IL6-415

	Reverse-Gas Baghouse					Measured					NO _x ^a Removal %	NH ₃ Slip ppm	SO ₂ ^b Conc. ppm
	Average Bulk Gas Temp.		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	SO ₂ Flue Gas Concentration ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm			
	East	West											
	°F	°F											
Test Period #1, A/C=2.0, Molar Ratio=1.02													
Average	683	680	1	89	68	2781	4.3	6.0	942	100	89.38	109.1 307.3	525.93
Max.	686	681	2	89	69	2858	4.9	6.6	976	121	91.59		
Min.	673	680	1	89	68	2702	3.8	5.4	867	75	87.41		
Test Period #2, A/C=1.7, Molar Ratio=1.20													
Average	681	669	3	71	61	2742	4.4	5.4	983	114	88.41	109.1 307.3	525.93
Max.	690	682	4	78	73	2918	4.9	6.1	1063	144	90.86		
Min.	678	665	1	62	56	2628	3.4	4.5	853	85	84.97		
Test Period #3, A/C=1.8, Molar Ratio=1.04													
Average	675	669	3	69	63	2696	4.4	6.1	1014	113	88.81	109.1 307.3	525.93
Max.	679	680	4	71	64	2793	4.8	6.9	1055	132	89.76		
Min.	667	664	2	67	63	2634	3.9	5.1	954	102	86.83		
Test Period #4, A/C=1.7, Molar Ratio=0.69													
Average	675	664	3	69	63	2713	4.2	6.1	1018	298	70.76	109.1 307.3	525.93
Max.	679	666	4	73	69	2829	4.9	6.9	1044	339	76.40		
Min.	671	661	1	67	62	2645	3.6	5.2	957	236	66.00		
Test Period #5, A/C=1.7, Molar Ratio=1.18													
Average	678	665	3	71	63	2776	4.1	4.9	892	89	90.03	109.1 307.3	525.93
Max.	679	667	3	73	64	2856	4.7	5.9	993	120	91.72		
Min.	674	663	2	68	63	2663	3.4	4.4	842	70	86.43		
Test Period #6, A/C=1.7, Molar Ratio=1.03													
Average	678	668	2	66	61	2717	4.4	5.0	846	115	86.48	109.1 307.3	525.93
Max.	679	670	3	68	64	2805	4.8	5.5	869	129	88.65		
Min.	677	665	1	65	58	2656	3.7	4.7	816	94	84.84		
Test Period #7, A/C=3.4, Molar Ratio=1.06													
Average	666	—	4	66	55	2743	4.2	4.9	793	180	77.29	109.1 307.3	525.93
Max.	677	—	5	67	58	2824	4.7	5.7	857	214	79.60		
Min.	655	—	3	65	54	2605	3.6	4.1	698	156	72.49		
Test Period #8, A/C=3.6, Molar Ratio=0.99													
Average	657	—	4	62	54	2691	4.3	4.7	752	205	72.76	109.1 307.3	525.93
Max.	657	—	6	63	54	2758	4.9	5.3	775	229	75.36		
Min.	656	—	3	61	54	2616	4.0	4.3	727	186	69.52		
Test Period #9, A/C=3.6, Molar Ratio=0.92													
Average	657	—	5	61	54	2656	4.2	4.7	717	242	67.61	109.1 307.3	525.93
Max.	657	—	6	72	54	2716	5.0	5.3	795	297	71.73		
Min.	655	—	3	61	54	2573	3.7	4.2	697	199	60.57		
Test Period #10, A/C=3.5, Molar Ratio=1.14													
Average	655	—	4	60	54	2691	4.1	4.9	720	191	73.45	109.1 307.3	525.93
Max.	657	—	6	61	54	2774	4.5	5.4	847	215	76.40		
Min.	653	—	3	59	54	2629	3.7	4.4	678	160	70.28		
Test Period #11, A/C=3.5, Molar Ratio=1.07													
Average	653	—	5	59	54	2711	4.2	4.9	686	204	70.30	109.1 307.3	525.93
Max.	654	—	6	60	54	2759	5.0	5.6	707	234	72.70		
Min.	652	—	3	57	54	2604	3.9	4.6	652	193	66.33		
Test Period #12, A/C=1.3, Molar Ratio=1.05													
Average	654	646	2	56	57	2643	4.6	5.2	685	83	87.94	109.1 307.3	525.93
Max.	661	651	3	57	58	2736	5.0	5.7	728	105	90.11		
Min.	641	635	2	56	56	2587	4.0	4.3	617	61	84.83		

TABLE 5 (continued)

Reverse-Gas Baghouse						Measured					NO _x ^a Removal %	NH ₃ Slip ppm	SO ₂ ^b Conc. ppm
Average Bulk Gas Temp.		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	SO ₂ Flue Gas Concentration ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm				
East	West												
°F	°F												
Test Period #13, A/C=1.3, Molar Ratio=0.9													
Average	651	645	1	56	58	2720	4.5	5.7	684	111	83.86		888.71
Max.	652	645	2	57	59	2783	4.9	6.1	716	140	85.14		
Min.	649	644	1	56	58	2668	4.0	4.6	666	99	79.68		
Test Period #14, A/C=1.3, Molar Ratio=1.11													
Average	652	647	2	56	58	2771	4.2	4.9	696	85	87.78		
Max.	652	647	2	57	58	2837	4.9	5.7	729	97	89.22		
Min.	651	647	2	56	58	2689	2.5	3.0	671	76	85.86		
Test Period #15, A/C=2.4, Molar Ratio=0.98													
Average	640	—	3	57	55	2824	4.1	5.3	718	207	71.32		
Max.	643	—	4	57	57	2981	4.7	6.1	782	238	75.57		
Min.	638	—	2	57	54	2744	3.0	4.8	618	151	67.79		
Test Period #16, A/C=2.4, Molar Ratio=0.85													
Average	638	—	3	57	54	2728	4.6	5.5	756	236	68.70		
Max.	638	—	4	57	54	2788	5.1	6.2	789	257	71.96		
Min.	638	—	2	57	54	2648	4.1	5.1	708	211	66.49		
Test Period #17, A/C=2.4, Molar Ratio=1.17													
Average	637	—	3	57	54	2657	4.7	5.7	767	228	70		
Max.	637	—	4	57	54	2737	5.0	6.3	800	261	74		
Min.	636	—	2	57	54	2608	4.3	5.2	722	194	65		
Test Period #18, A/C=2.0, Molar Ratio=0.84													
Average	661	661	2	57	57	2598	5.0	6.0	816	213	73.89	3.7	
Max.	661	661	3	57	58	2644	5.4	6.3	828	226	75.49		
Min.	661	661	2	56	56	2545	4.7	5.7	803	199	71.98		
Test Period #19, A/C=2.0, Molar Ratio=0.87													
Average	662	663	3	57	59	2622	5.0	6.0	807	181	77.75		
Max.	663	665	4	57	59	2747	5.6	6.4	900	256	81.20		
Min.	661	661	1	56	57	2537	4.3	5.6	734	138	71.56		
Test Period #20, A/C=2.0-2.3, Molar Ratio=0.94													
Average	669	670	2	57	58	2541	5.5	6.0	842	262	72.18		
Max.	669	670	2	57	58	2564	5.7	6.3	989	291	74.81		
Min.	669	670	1	57	57	2519	5.3	5.7	397	233	67.74		
Test Period #21, A/C=2.0-2.3, Molar Ratio=1.04													
Average	646	627	3	57	58	2630	4.9	5.2	1021	186	81.75		
Max.	647	627	3	57	58	2693	5.1	5.4	1052	222	83.04		
Min.	645	627	2	57	57	2591	4.5	5.0	979	166	78.32		

^a Corrected to 4% O₂.^b NH₃ injection turned off.

Figure 9. NO_x removal efficiency as a function of air-to-cloth ratio and NH_3/NO_x molar ratio for Run PTC-IL6-415.

injection rate was calculated using flue gas flow rates from an annubar flowmeter. Flue gas flow rates calculated using an orifice plate were much lower than those calculated using the annubar (i.e., 123 scfm compared to 147 scfm). It was later found (Test PTC-IL6-417) that the pipe in which the annubar and the orifice plate were located had a buildup of an unknown substance on the pipe wall, effectively decreasing the diameter of the pipe. This, in turn, affected the flow calculations of the annubar, which resulted in higher-than-expected ammonia injection rates. Using the flow rate from the orifice to calculate ammonia slip yields values as high as 311 ppm. Thus the second ammonia slip value of 307 ppm could be valid. A great deal of uncertainty in the wet chemistry values for ammonia slip is evident. This uncertainty may be due to error in flue gas flow rate calculations and ammonia injection rates. The SO_2 concentration values are also high, indicating an SO_2 to SO_3 conversion of 19% to 32%, which is very unlikely.

4.3.1.3 PTC-IL6-416

The catalyst-coated fabric filters used for this test were woven from D-fibers (6.5 microns) having a fabric weight of 14 oz/yd² in a single-beam weave (DE484). The bags were coated with seven coats of an aqueous-based vanadium/titanium catalyst and correspond to Fabric #143 in previous bench-scale tests.

The bags were heat-treated by exposing them to flue gas containing roughly 4.5% oxygen as a result of firing natural gas for approximately 7 hours. For the first 4 hours, the average bulk gas temperature in each chamber increased from 600° to 675°F. During the last 3 hours, the average bulk gas temperature was 690°F.

Results from the 100-hour test were quite good initially, but degraded with time. Figure 10 shows the NO_x removal efficiency as a function of time, and Table 6 summarizes each test period. Nitric oxide removal averaged 90% for the first two test periods (approximately 10 hours). After the first bag cleaning, at the 25-hour mark, NO_x removal decreased from approximately 90% to less than 80%. As a dust cake developed on the bags, the NO_x removal again increased to approximately 90%. The bags were cleaned for a second time, at the 31-hour mark, and the NO_x removal again dropped below 80%. When the air-to-cloth ratio was changed to 3.3 ft/min, the pattern continued, as can be seen in Figure 10. Each time the bags were cleaned, the NO_x removal decreased sharply and increased slowly with the buildup of a dust cake. It can also be seen that the maximum NO_x removal from cleaning cycle to cleaning cycle was also decreasing so that, when the air-to-cloth ratio was changed to 1.2 ft/min, the NO_x removal had decreased from approximately 70% to roughly 40%. To check for loss of catalyst from the bags, used and unused fabric samples were submitted for vanadium analysis. The results show a decrease from 11,300 $\mu\text{g/g}$ to 7700 $\mu\text{g/g}$ vanadium concentration on the bags. This is a 32% decrease in vanadium concentration and could account for the decreased performance.

Results from ammonia slip and SO_2 measurements using wet chemistry techniques are also presented in Table 6. The ammonia slip values again reflect the inaccurate flue gas flow readings from the annubar and the decreasing NO_x removal efficiency of the bags. The SO_2 measurements were well within the range expected for a 3% sulfur coal, indicating little if any conversion of SO_2 to SO_3 across the filter bags.

4.3.1.4 PTC-IL6-417

The catalyst-coated fabric filters used for this test were woven from G-fibers (9 microns) having a 14-oz/yd² fabric weight and single-beam weave (G143). The bags were coated with seven coats of a organic-based vanadium/titanium catalyst, which corresponds to Fabric #2 from previous bench-scale tests. The bags were heat-treated by exposing them to flue gas containing roughly 4.5% oxygen as a result of firing natural gas for approximately 8 hours. For the first 4 hours, the average bulk gas temperature in each chamber increased from 500° to 690°F. During the last 4 hours, the average bulk gas temperature ranged from 690° to 715°F.

Results from the 100-hour test were reasonably good, but did not match the results from previous bench-scale testing of a similar fabric. Nitric oxide removal ranged from 66% to 87%, depending on test conditions. At an air-to-cloth ratio of 1.3 ft/min, an ammonia/ NO_x molar ratio of 1.0, and an average baghouse bulk gas temperature of 650°F, NO_x removal averaged 87%. At an air-to-cloth ratio of 3.5 ft/min, an ammonia/ NO_x molar ratio of 0.9, and an average baghouse bulk gas temperature of 665°F, NO_x removal averaged 66%. Figure 11 shows NO_x removal as a function of time, and Table 7 summarizes each test period. Figure 12 plots the NO_x removal efficiency as a function of air-to-cloth ratio and ammonia/ NO_x molar ratio. Again it can be seen that NO_x removal decreases with increasing air-to-cloth ratio and decreasing ammonia/ NO_x molar ratio. Note there is little difference in NO_x removal at ammonia/ NO_x molar ratios of 1.0 and 1.1.

Figure 10. NO_x removal efficiency as a function of time for Run PTC-IL6-416.

TABLE 6

Summary of Run No. PTC-IL6-416

Reverse-Gas Baghouse						Measured					NO _x ^a Removal %	NH ₃ Slip ppm	SO ₂ ^b Conc. ppm
Average		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	SO ₂ Flue Gas Concentration ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm				
Bulk Gas Temp.													
East °F	West °F												
Test Period #1, A/C=1.7, Molar Ratio=1.15													
Average	669	668	1.4	88.6	89.5	2692	4.2	4.7	878	80	90.60	18.5	
Max.	675	670	1.7	88.7	89.6	2741	4.9	5.7	893	87	91.79	101.1	
Min.	665	666	1.2	88.5	89.3	2642	3.9	4.3	860	70	89.91		13.8
Test Period #2, A/C=1.7, Molar Ratio=1.07													
Average	660	664	3	88	90	2641	4.3	4.8	880	81	90.51		
Max.	661	666	4	89	90	2729	4.7	5.1	899	92	91.28		
Min.	658	662	2	88	90	2592	3.6	4.2	838	74	89.10		
Test Period #3, A/C=1.7, Molar Ratio=0.94													
Average	656	664	4	89	90	2615	4.5	4.8	898	102	88.44		
Max.	656	664	4	89	90	2707	5.0	5.3	901	108	89.20		
Min.	656	664	4	89	90	2546	3.8	4.2	895	95	87.66		
Test Period #4, A/C=1.7, Molar Ratio=0.94													
Average	660	658	2	88	91	2675	4.2	4.6	891	167	80.84		
Max.	661	660	3	89	91	2701	4.8	5.3	903	193	83.86		
Min.	658	657	1	88	91	2582	4.0	4.3	876	140	78.06		
Test Period #5, A/C=1.6, Molar Ratio=1.21													
Average	659	660	3	88	90	2701	4.1	4.4	870	104	87.87		
Max.	660	660	4	89	91	2767	4.6	4.8	883	117	89.85		
Min.	659	660	3	88	90	2641	3.6	4.0	830	86	86.35		
Test Period #6, A/C=1.6, Molar Ratio=1.17													
Average	642	666	1	88	91	2716	4.1	4.4	860	171	79.78		
Max.	642	666	3	89	91	2788	4.5	5.4	875	191	82.54		
Min.	642	666	1	88	91	2650	3.8	4.0	837	145	77.73		
Test Period #7, A/C=3.4, Molar Ratio=1.04													
Average	659	—	3	89	94	2715	4.2	4.5	838	262	68.35	181.9	
Max.	662	—	4	95	95	2938	5.0	5.1	891	321	72.38		
Min.	656	—	2	88	93	2591	3.0	3.3	759	221	63.19		43.8
Test Period #8, A/C=3.3, Molar Ratio=1.04													
Average	652	—	3	90	95	2675	4.1	4.5	824	341	57.72		
Max.	655	—	4	91	95	2734	4.7	5.3	901	411	65.84		
Min.	651	—	2	90	95	2592	3.7	4.1	774	264	52.00		
Test Period #9, A/C=3.3, Molar Ratio=1.00													
Average	649	—	3	90	95	2684	4.1	4.9	899	432	49.60		
Max.	649	—	4	91	95	2862	4.6	5.7	916	464	53.32		
Min.	649	—	2	90	95	2592	2.7	3.4	855	398	46.25		
Test Period #10, A/C=3.3, Molar Ratio=0.9													
Average	648	—	3	91	95	2816	4.4	5.0	896	470	45.43		
Max.	649	—	3	91	95	2899	5.1	6.2	922	510	48.32		
Min.	647	—	2	90	95	2526	3.8	4.3	865	436	41.69		
Test Period #11, A/C=3.3, Molar Ratio=1.11													
Average	648	—	3	91	95	2579	4.5	5.1	900	506	41.71		
Max.	646	—	4	91	95	2726	5.0	5.9	922	528	45.76		
Min.	651	—	2	90	95	2492	3.5	4.2	850	454	36.06		
Test Period #12, A/C=3.3, Molar Ratio=1.04													
Average	649	—	2	91	95	2564	4.5	5.2	912	502	42.32		
Max.	649	—	3	91	95	2639	4.8	5.9	933	518	44.27		
Min.	649	—	1	90	95	2520	3.9	4.7	883	461	40.12		
Test Period #13, A/C=1.2, Molar Ratio=1.04													
Average	644	650	1	91	91	2538	4.7	5.1	927	297	67.04		
Max.	644	650	2	92	92	2580	5.0	5.5	947	335	68.71		
Min.	644	650	1	91	91	2497	4.5	4.8	914	282	64.15		
Test Period #14, A/C=1.7, Molar Ratio=1.06													
Average	654	662	2	91	90	2565	4.4	4.6	925	290	68.24	278.2	
Max.	658	664	2	91	91	2613	4.8	5.0	946	327	71.94		
Min.	651	660	2	91	90	2509	4.0	4.2	911	262	64.31		

^a Corrected to 4% O₂.^b NH₃ injection turned off.

Figure 11. NO_x removal efficiency as a function of time for Run PTC-IL6-417.

TABLE 7
Summary of Run No. PTC-IL6-417

	Reverse-Gas Baghouse					Measured					NO _x ^a Removal %	NH ₃ Slip ppm	SO ₂ ^b Slip ppm
	Average Bulk Gas Temp.		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	SO ₂ Flue Gas Concentration ppm	O ₂		NO _x Inlet ppm	NO _x Outlet ppm			
	East °F	West °F					Inlet %	Outlet %					
Test Period #1, A/C=1.8, Molar Ratio=1.05													
Average	664	653	0.6	71.5	86.1	2542	5	5	852	141	83.09	174.5	229.9
Max.	665	654	1	72	87	2620	5	6	872	154	87.40		
Min.	664	652	0	71	86	2480	4	4	825	107	81.88		
Test Period #2, A/C=1.8, Molar Ratio=1.03													
Average	667	654	1.6	72.9	84.7	2591	4.6	5.1	821	127	83.99		4.5
Max.	671	655	2.1	73.1	85.5	2724	8.3	6.7	897	152	85.75		
Min.	665	651	1.1	71.6	79.7	2130	3.8	4.3	727	103	82.64		
Test Period #3, A/C=1.7, Molar Ratio=1.09													
Average	666	646	1.4	67.4	86	2622	4.4	4.9	853	143	82.78		
Max.	669	647	2	68	86	2690	5	5	882	160	84.71		
Min.	664	643	1	67	85	2579	4	4	753	126	80.91		
Test Period #4, A/C=1.7, Molar Ratio=0.95													
Average	665	647	2.3	68.1	86.2	2548	4.5	5.1	857	166	79.84		
Max.	666	650	3	69	89	2636	5	6	886	175	81.03		
Min.	664	641	2	68	85	2465	4	5	770	139	78.42		
Test Period #5, A/C=3.4, Molar Ratio=1.04													
Average	669	—	2.6	59.7	90.1	2548	4.5	4.8	943	254	72.68	75.6	
Max.	669	—	3.8	61.0	90.7	2600	5.0	6.4	989	298	76.66		
Min.	668	—	1.6	58.2	89.5	2481	4.0	3.9	913	222	68.93		
Test Period #6, A/C=3.7, Molar Ratio=1.08													
Average	671	—	3.9	72.6	89.4	2579	4.4	4.8	875	225	73.72		18.6
Max.	672	—	6	82	91	2795	5	7	945	274	76.96		
Min.	665	—	2	69	89	2423	3	4	754	183	70.49		
Test Period #7, A/C=3.4, Molar Ratio=1.09													
Average	666	—	4.7	66.9	88.7	2738	4.4	5.3	766	200	72.32		
Max.	662	—	6	69	89	2839	5	6	794	220	76.09		
Min.	670	—	3	66	88	2649	4	4	726	181	68.22		
Test Period #8, A/C=3.5, Molar Ratio=0.93													
Average	667	—	5.0	65.1	88.8	2719	4.5	5.2	776	251	66.29		
Max.	671	—	7	68	89	2932	5	6	837	289	71.64		
Min.	663	—	3	65	89	2609	3	4	710	225	62.11		
Test Period #9, A/C=1.3, Molar Ratio=1.08													
Average	659	645	1.9	64.3	85.5	2654	4.6	5.1	867	122	85.62	185.1	
Max.	661	655	2	65	86	2719	5.0	5.7	972	148	88.80	144.1	
Min.	656	641	1	64	85	2571	4	5	784	86	83.21		
Test Period #10, A/C=1.3, Molar Ratio=1.03													
Average	658	647	2.5	65.8	85.8	2617	4.9	5.5	870	107	87.07		12.5
Max.	660	651	3	73	87	2694	5.9	6	950	126	93.83		
Min.	654	642	1	65	86	2501	4.1	4.8	817	56	85.21		
Test Period #11, A/C=1.3, Molar Ratio=1.15													
Average	655	643	2.4	66.2	85.9	2739	4.5	5.0	831	124	84.70		
Max.	656	645	3	67	86	2912	5	6	871	157	86.69		
Min.	654	642	1	66	86	2652	4	4	790	102	81.65		
Test Period #12, A/C=1.3, Molar Ratio=0.98													
Average	654	643	2.7	66.3	86.2	2891	4.5	5.1	801	139	81.90		
Max.	655	646	3.7	66.8	86.4	3029	5.1	5.6	937	174	85.57		
Min.	652	642	1.5	66.0	85.9	2786	3.5	4.0	715	110	78.52		

Continued ...

TABLE 7 (continued)

	Reverse-Gas Baghouse					Measured					NO _x ^a Removal %	NH ₃ Slip ppm	SO ₂ ^b Slip ppm
	Average Bulk Gas Temp.		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	SO ₂ Flue Gas Concentration ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm			
	East °F	West °F											
Test Period #13, A/C=2.6, Molar Ratio=1.06													
Average	665	—	3.1	64.2	89.2	2744	4.4	4.9	902	228	73.95	231.9	5.6
Max.	668	—	5	67	90	2920	5.3	5.7	969	281	79.31		
Min.	662	—	2	62	88	2573	2.9	3.4	829	171	67.84		
Test Period #14, A/C=2.5, Molar Ratio=1.05													
Average	661	—	4.3	60.0	89.8	2650	4.8	5.6	798	192	74.66	231.9	5.6
Max.	664	—	6	62	91	2805	6	7	965	274	80.77		
Min.	658	—	3	58	90	2531	4	5	688	140	69.52		
Test Period #15, A/C=2.4, Molar Ratio=1.33													
Average	660	—	4.1	59.0	89.6	2609	4.4	5.0	713	175	74.42	231.9	5.6
Max.	661	—	4.8	60.0	89.8	2812	5.3	5.7	793	192	78.04		
Min.	659	—	3.2	58.1	89.5	1983	3.9	4.2	609	159	67.72		
Test Period #16, A/C=2.5, Molar Ratio=0.89													
Average	659	—	4.8	57.7	89.6	2273	4.4	5.1	795	224	70.50	231.9	5.6
Max.	661	—	5.7	59.3	89.8	2666	5.0	5.8	962	273	75.27		
Min.	656	—	3.3	56.4	89.4	1992	3.4	4.3	624	174	66.89		
Test Period #17, A/C=2.0, Molar Ratio=0.92													
Average	665	670	3.9	59.5	84.5	2694	4.4	5.0	710	133	80.91	166.5	75.5
Max.	687	683	5	61	85	2794	5	6	866	210	85.86	75.5	
Min.	632	659	3	59	84	2585	4	4	560	84	72.04	75.5	

^a Corrected to 4% O₂.

^b NH₃ injection turned off.

Figure 12. NO_x removal efficiency as a function of air-to-cloth ratio and NH₃/NO_x molar ratio for Run PTC-IL6-417.

Results from ammonia slip and SO_3 measurements using wet chemistry techniques are also presented in Table 7. The ammonia slip values again reflect the incorrect flue gas flow readings from the annubar. It was during this test that the unknown substance was found on the walls of the flue gas pipe housing the orifice plate and annubar. Some of the material was submitted for analysis by x-ray diffraction and was found to be ammonium aluminum sulfate ($\text{NH}_4\text{Al}[\text{SO}_4]_2$ and $[\text{NH}_4]_3\text{Al}[\text{SO}_4]_3$) and ammonium hydrogen sulfate (NH_4HSO_4), which are water soluble and were easily removed from the pipe. The material condensed on the inside surface of cool spots in uninsulated pipe and formed due to the high ammonia slip and SO_2 concentration in the flue gas stream. The SO_3 measurements were well within the range expected for a 3% sulfur coal, indicating little if any conversion of SO_2 to SO_3 across the filter bags.

4.3.1.5 PTC-IL6-418

A one-day test was completed as a demonstration for the project review meeting. No significant data were collected.

4.3.1.6 PTC-IL6-419

The catalyst-coated fabric filters used for this test were woven from D-fibers resulting in a 22-oz/yd² fabric with double-beam weave (DE992). Three coats of an undercoat were applied, to increase fabric surface area and possibly improve fiber abrasion resistance, before seven coats of an organic-based vanadium/titanium catalyst were applied. The catalyst coating corresponds to Fabrics #17 and #106B in previous bench-scale tests, with the exception of the undercoat. The bags were heat-treated by exposing them to flue gas containing roughly 4.5% oxygen as a result of firing natural gas for approximately 8 hours. For the first 4 hours, the average bulk gas temperature in each chamber increased from 500° to 690°F. During the last 4 hours, the average bulk gas temperature ranged from 690° to 700°F.

Results from the 100-hour test were reasonably good, with NO_x removal ranging from 62% to 90%, depending on operating conditions. Figure 13 shows the NO_x removal efficiency as a function of time, and Table 8 summarizes each test period. At an air-to-cloth ratio of 2.0 ft/min, an ammonia/ NO_x molar ratio of 0.9, and an average baghouse bulk gas temperature of 665°F, NO_x removal averaged nearly 90%. At an air-to-cloth ratio of 2.8 ft/min, an ammonia/ NO_x molar ratio of 0.8, and an average baghouse bulk gas temperature of 648°F, NO_x removal averaged 62%. Results from previous bench-scale testing of a similar fabric (Fabric #17) showed NO_x removal efficiency ranging from 75% at an air-to-cloth ratio of 4.0 ft/min to 90% at an air-to-cloth ratio of 2.0 ft/min, both at an ammonia/ NO_x molar ratio of 0.9. On the final day of the test, the air-to-cloth ratio was returned to 1.8 ft/min and the ammonia/ NO_x molar ratio to 0.9. The NO_x removal efficiency averaged 76% during this test period, which is significantly lower than the NO_x removal at similar conditions, on the first day of the test. Figure 14 shows the NO_x removal efficiency as a function of air-to-cloth ratio and ammonia/ NO_x molar ratio. It can be seen that the average NO_x removal efficiencies at air-to-cloth ratios of 1.4 and 2.7 ft/min are lower than the NO_x removal efficiencies at air-to-cloth ratios of 1.9 and 3.8 ft/min. The test periods at air-to-cloth ratios of 1.4 and 2.7 ft/min occurred after the test periods at air-to-cloth ratios of 1.9 and 3.8 ft/min. This decrease in performance may indicate

Figure 13. NO_x removal efficiency as a function of time for Run PTC-IL6-419.

TABLE 8
Summary of Run No. PTC-IL6-419

Reverse-Gas Baghouse						Measured								
Average Bulk Gas Temp.			Average	East	West	NH ₃ ^a	SO ₂ Flue Gas	O ₂	O ₂	NO _x	NO _x	NO _x ^b	NH ₃	SO ₂ ^c
East °F	West °F	ΔP In H ₂ O	Bag wt. lb	Bag wt. lb	Slip ppm	Concentration ppm	Inlet %	Outlet %	Inlet ppm	Outlet ppm	Removal %	Slip ppm	Conc. ppm	
Test Period #1, A/C=2.2, Molar Ratio=0.89														
Average	662	652	1.9	73.4	76.8	8	2670	4.1	4.7	834	114	86.37	1.0	
Max.	671	655	3.3	78.9	78.9	10	2799	5.1	8.2	1056	174	88.94	11.1	
Min.	655	649	0.8	65.6	70.0	7	2523	2.7	2.7	607	78	81.77		
Test Period #2, A/C=1.8, Molar Ratio=1.00														
Average	652	630	2.9	66.8	71.6	7	2712	4.0	5.4	936	87	89.97		14.0
Max.	654	645	4.2	73.0	77.4	7	2894	5.5	8.3	1010	139	92.72		
Min.	649	626	0.9	64.4	70.0	6	2490	2.9	4.1	813	59	84.61		
Test Period #3, A/C=1.9, Molar Ratio=0.8														
Average	652	609	1.7	61.1	68.8	6	2641	4.4	5.3	879	126	84.86		
Max.	653	617	2.7	62.5	69.9	8	2752	5.3	7.8	905	157	88.25		
Min.	647	603	0.7	59.3	67.9	6	2522	3.6	4.4	807	94	82.08		
Test Period #4, A/C=1.8, Molar Ratio=1.0														
Average	651	612	1.5	59.5	68.3	9	2666	4.4	5.3	877	118	85.77		
Max.	653	619	2.4	69.9	77.4	11	2769	5.4	8.5	907	167	88.96		
Min.	647	607	0.6	57.3	67.0	8	2449	3.7	4.4	824	86	80.01		
Test Period #5, A/C=3.8, Molar Ratio=0.92														
Average	658		3.2	67.2	73.9	15	2655	4.5	5.6	903	207	75.34	54.6	
Max.	661		4.2	78.6	78.9	39	2742	5.8	7.9	933	235	79.08		
Min.	653		2.0	56.3	63.2	11	2472	3.9	4.7	867	169	71.67		
Test Period #6, A/C=3.7, Molar Ratio=0.95														
Average	651		3.7	65.0	74.0	129	2632	4.5	5.6	841	226	70.97		5.6
Max.	654		4.7	78.2	74.7	174	2740	5.5	9.3	979	272	76.43		
Min.	646		2.5	60.8	73.6	96	2489	3.8	4.6	721	177	65.94		
Test Period #7, A/C=3.7, Molar Ratio=0.83														
Average	651		3.8	68.5	73.7	97	2639	4.5	5.1	876	227	73.09		
Max.	655		5.1	71.0	73.9	118	2832	5.5	8.7	929	265	79.46		
Min.	646		2.8	67.3	73.5	66	2536	3.9	2.2	805	166	69.10		
Test Period #8, A/C=3.8, Molar Ratio=1.03														
Average	653		3.7	66.9	73.6	157	2631	4.5	5.4	838	204	74.39		
Max.	656		4.9	68.7	73.9	178	2703	5.5	8.2	885	236	78.28		
Min.	648		2.8	66.0	73.4	92	2503	4.3	4.5	759	144	70.03		
Test Period #9, A/C=1.4, Molar Ratio=0.88														
Average	640	593	1.7	64.1	74.5	157	2591	4.7	5.6	811	181	76.39	32.3	
Max.	674	643	2.7	66.5	79.0	192	3001	6.0	7.5	853	207	82.50	54.8	
Min.	630	566	1.2	61.4	71.3	114	2404	3.7	4.4	733	138	71.79		
Test Period #10, A/C=1.4, Molar Ratio=0.95														
Average	649	618	2.5	74.8	80.0	157	2628	4.5	5.6	682	104	83.71		4.0
Max.	650	625	3.8	80.4	82.1	187	2871	5.6	8.7	813	172	89.38		
Min.	648	605	0.6	66.2	79.3	132	2461	2.8	3.4	566	63	76.60		
Test Period #11, A/C=1.4, Molar Ratio=0.75														
Average	647	625	1.4	76.1	77.4	138	2671	4.4	5.8	730	135	79.88		
Max.	648	626	1.9	76.4	77.5	169	2787	5.6	8.2	804	155	82.57		
Min.	646	620	0.5	75.8	77.1	127	2531	3.6	4.9	657	106	77.33		
Test Period #12, A/C=1.4, Molar Ratio=0.95														
Average	646	623	1.4	75.3	77.7	174	2638	4.4	5.4	728	132	80.80		
Max.	648	624	2.0	76.5	78.3	204	2809	5.6	7.5	806	160	85.89		
Min.	612	590	0.6	72.0	73.3	121	2415	2.6	3.7	651	95	77.09		

Continued ...

TABLE 8 (continued)

	Reverse-Gas Baghouse					Measured						NO _x ^b Removal %	NH ₃ Slip ppm	SO ₂ ^c Conc. ppm	
	Average Bulk Gas Temp.		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	NH ₃ ^a Slip ppm	SO ₂ Flue Gas Concentration ppm	O ₂		NO _x Inlet ppm	NO _x				
	East °F	West °F						Inlet %	Outlet %		Inlet ppm				Outlet ppm
Test Period #13, A/C=2.7, Molar Ratio=0.95															
Average	650		2.5	73.2	74.1	84	2623	4.5	5.6	634	184	68.87	337.4	5.4	
Max.	652		3.9	77.0	77.6	103	2781	5.8	7.1	729	205	75.45			
Min.	648		1.6	71.2	72.9	52	2424	3.4	4.4	541	140	64.59			
Test Period #14, A/C=2.7, Molar Ratio=0.97															
Average	647		2.3	70.7	72.2	33	2596	4.5	5.4	805	197	74.47			
Max.	649		3.0	72.6	72.5	36	2921	5.7	6.4	966	245	80.93			
Min.	646		3.0	72.6	72.5	29									
Test Period #15, A/C=2.7, Molar Ratio=0.83															
Average	631		2.2	67.0	71.4	39	2619	4.3	5.9	885	297	62.91			
Max.	640		3.3	95.5	72.2	50	2890	5.4	7.9	936	373	72.79			
Min.	613		1.6	65.1	71.2	26	2445	3.0	4.4	797	211	52.91			
Test Period #16, A/C=2.8, Molar Ratio=0.8															
Average	648		2.4	69.0	71.2	33	2551	4.6	5.6	883	317	61.87			
Max.	652		3.3	71.1	71.4	42	2741	5.5	7.0	939	380	68.40			
Min.	636		1.7	67.6	71.0	20	2408	3.1	4.3	757	239	56.90			
Test Period #17, A/C=2.8, Molar Ratio=0.99															
Average	650		2.5	68.4	70.9	56	2588	4.5	5.6	901	314	62.60			
Max.	652		3.3	82.8	71.1	68	2673	6.1	8.5	932	346	67.85			
Min.	645		1.7	67.0	70.7	30	2369	3.9	4.6	846	239	58.34			
Test Period #18, A/C=1.8, Molar Ratio=0.86															
Average	650	628	1.9	69.4	73.2	41	2561	4.8	6.5	862	187	75.62	204.8	159.6	
Max.	654	642	2.6	70.9	76.5	52	2691	6.6	8.6	918	273	81.30			
Min.	646	588	0.9	66.7	69.1	20	2270	3.9	5.5	791	131	65.65			
Test Period #19, A/C=1.9, Natural Gas; Molar Ratio = 1.6															
Average	652	645	2.9	71.7	76.5	33	32	4.5	6.5	333	42	85.86			
Max.	660	653	3.1	73.6	76.7	78	61	6.7	9.0	376	50	94.38			
Min.	647	640	2.7	70.7	76.4	21	12	4.2	5.9	241	12	80.66			

^a Corrected to 4% O₂.

^b NH₃ injection turned off.

^c Siemens ammonia analyzer.

Figure 14. NO_x removal efficiency as a function of air-to-cloth ratio and NH₃/NO_x molar ratio for Run PTC-IL6-419.

a loss of catalyst from the fabric. Fabric samples from the bags have been submitted for vanadium analysis. Another possible explanation for the poor performance is pin-holing, which would cause gas channeling and lower NO_x removal. The bags were cut up and samples submitted for bench-scale testing and vanadium analysis. The results of these tests are not yet available, but should provide an answer to the question of decreasing NO_x removal.

Results from ammonia slip and SO₂ measurements using wet chemistry techniques are also presented in Table 8. The ammonia slip values from the wet chemistry measurements, the on-line ammonia analyzer, and the theoretical values at an ammonia/NO_x molar ratio of 0.9 do not agree. Some difference between the flue gas flow rates calculated using the annubar and the orifice plate is still evident. A new annubar was ordered and will be installed for future tests. The new annubar should minimize differences in the planned and actual flue gas flow rates and the ammonia injection rates. Values from the on-line ammonia analyzer are still erratic, and further testing will be needed. The SO₂ measurements were well within the range expected for a 3% sulfur coal, indicating little if any conversion of SO₂ to SO₃ across the filter bags.

4.3.1.7 PTC-NG-420

A 2-day test was completed to determine if additional fabric heat treatment would result in improved NO_x removal. The bag used in the west chamber during Run PTC-IL6-417, a 14-oz/yd² single-beam weave bag, was used for this test. The bag was previously heat-treated by exposing it to flue gas containing roughly 4% oxygen as a result of firing natural gas.

After system heatup, the air-to-cloth ratio was set at 4.0 ft/min, and tests were run with the ammonia/NO_x molar ratio set at 0.9, 1.0, and 1.1. The average NO_x removal for each test period was 59%, 64%, and 65%, respectively. Following the first three test periods, the bag was heat-treated at 715°F for 2 hours. The final two test periods were conducted at an air-to-cloth ratio of 4.0 ft/min, an ammonia/NO_x molar ratio of 1.0, and average baghouse bulk gas temperatures of 715° and 670°F, respectively. The average NO_x removal efficiencies for these test periods were 57% and 54%. Figure 15 plots NO_x removal efficiency as a function of time, and Table 9 summarizes each test period. The results of these tests are poor, compared to results from Run PTC-IL6-417 at similar conditions. Based on previous bench-scale testing of other fabrics, degradation of fabric performance should not begin until the bags have been exposed to bulk gas temperatures exceeding 800°F. Fabric swatches were removed from the bag so additional bench-scale testing and vanadium concentration analysis could be performed. The average NO_x reduction for the swatches in the bench-scale testing was 74% at an air-to-cloth ratio of 2.0 ft/min, ammonia/NO_x molar ratio of 0.9, and an average bulk gas temperature of 650°F. This is consistent with the NO_x removal efficiency seen at the end of the 100-hour test (PTC-IL6-417) and indicates a decrease in the catalyst performance from the beginning of that test. This tends to discount the theory of pin-holing and gas channeling. Results from the vanadium analysis, which were not available, will show if there has been a net decrease in vanadium concentration on the fabric. Figure 16 plots the NO_x removal efficiency as a function of air-to-cloth ratio and NH₃/NO_x molar ratio for Runs PTC-IL6-417 and PTC-NG-420. The data for this 100-hour test continue the trend of decreasing NO_x removal efficiency with increasing air-to-cloth ratio.

Figure 15. NO_x removal efficiency as a function of time for Run PTC-IL6-420.

TABLE 9
Summary of Run No. PTC-NG-420

Reverse-Gas Baghouse						Measured						
Average		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	NH ₃ ^a Slip ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm	NO _x ^b Removal %	NH ₃ Slip ppm	
Bulk Gas Temp.												
East °F	West °F											
Test Period #1, A/C=3.9, Molar Ratio=1.02												
Average	669	—	3.4	85.3	0.5	57	4.3	4.4	239	8*4	64.63	112.4
Max.	670	—	3.4	85.5	0.5	61	4.5	4.9	253	91	71.60	
Min.	668	—	3.3	85.2	0.4	37	3.8	4.1	229	68	60.49	
Test Period #2, A/C=3.9, Molar Ratio=0.89												
Average	670	—	3.3	85.2	0.4	54	4.2	4.2	247	101	59.00	101.6
Max.	670	—	3.4	85.3	0.4	59	4.3	4.3	249	103	60.42	
Min.	670	—	3.3	85.2	0.4	52	4.0	4.1	244	96	58.05	
Test Period #3, A/C=3.9, Molar Ratio=1.13												
Average	671	—	3.3	85.2	0.4	72	4.0	4.1	251	89	64.24	
Max.	671	—	3.4	85.2	0.4	77	4.3	4.3	257	91	65.03	
Min.	670	—	3.3	85.1	0.4	57	3.8	4.1	242	88	61.27	
Test Period #4, A/C=4.0, Molar Ratio=1.04												
Average	716	—	3.0	82.6	0.4	64	3.1	3.1	286	124	56.69	229.5
Max.	716	—	3.1	82.7	0.4	71	3.9	3.5	320	130	60.94	236.1
Min.	715	—	3.0	82.5	0.4	45	2.7	2.9	263	118	53.70	
Test Period #5, A/C=3.9, Molar Ratio=1.07												
Average	673	—	2.9	82.1	0.4	60	4.4	4.5	243	110	54.43	
Max.	673	—	2.9	82.1	0.4	66	4.4	5.2	249	116	55.20	
Min.	672	—	2.9	82.1	0.4	49	4.3	4.4	231	103	53.13	

^a Corrected to 4% O₂.

^b Siemens ammonia analyzer.

Figure 16. NO_x removal efficiency as a function of air-to-cloth ratio and NH₃/NO_x molar ratio for Runs PTC-IL6-417 and PTC-NG-420.

Results from ammonia slip measurements using wet chemistry techniques are also presented in Table 9. Again, the ammonia slip values do not agree, but the wet chemistry values follow the trend of the theoretical values. Values from the on-line ammonia analyzer are low compared to the wet chemistry values. Additional tests will be completed to further evaluate the ammonia analyzer.

4.3.1.8 PTC-NG-421

A 2-day test was completed to determine if decreasing NO_x removal efficiency was due to pinholes or decreasing catalyst reactivity. Also, further evaluation of the Siemens ammonia analyzer and evaluation of a new annubar flow measurement device were completed. The bags used in the test were previously used during Run No. PTC-IL6-415, using a 14-oz/yd² single-beam weave bag, coated with seven coats of an organic-based vanadium/titanium catalyst. The bags correspond to Fabrics #17 and #106A in previous bench-scale tests. The bags were previously heat-treated by exposing them to flue gas containing roughly 4% oxygen as a result of firing natural gas.

The reverse-gas bags were exposed to flue gas containing roughly 4% oxygen as a result of firing natural gas. After system heatup, the first test involved operation at an air-to-cloth ratio of 2 ft/min, an ammonia/ NO_x molar ratio of 0.9, and an average baghouse temperature of 665°F. Nitric oxide (NO_x) reduction was 79%. Decreasing the ammonia/ NO_x molar ratio to 0.8 resulted in a 75% NO_x reduction. Reducing the air-to-cloth ratio to 1.5 and increasing the ammonia/ NO_x molar ratio to 0.9 resulted in an 81% NO_x reduction. Increasing the air-to-cloth ratio to 4 ft/min resulted in the NO_x reduction falling to 72%. The fifth and last test period involved returning to an air-to-cloth ratio of 2 ft/min and an ammonia/ NO_x molar ratio of 0.9. Nitric oxide reduction returned to 79%, as observed in the first test period. Figure 17 plots NO_x removal efficiency as a function of time, and Table 10 summarizes each test period.

Although 90% NO_x reduction was not observed, these results are consistent with results from the previous 100-hour test (PTC-IL6-415) with this fabric. Specifically, at an air-to-cloth ratio of 4 ft/min and an ammonia/ NO_x molar ratio of 0.9, 70% to 75% NO_x reduction was observed. In addition, since NO_x reduction was 79% during the first and last test periods, this fabric type did not exhibit the tendencies exhibited by other fabric types with respect to decreasing NO_x reduction as a result of exposure to flue gas or pinhole development. Fabric swatches have been cut from one bag in order to perform bench-scale screening tests and to determine vanadium concentration on the fabric. This data will be valuable for comparison with similar data for other fabric types.

Ammonia slip measurements were made using wet chemistry techniques, and results show ammonia slip was roughly 50 ppm at an 80% NO_x reduction, to 100 ppm at a 72% NO_x reduction. The on-line ammonia analyzer was used during this 2-day test period and indicated changes in ammonia slip consistent with changes to experimental conditions. The values are also within 10 ppm of the theoretical values. The Siemens ammonia analyzer appears to be working reasonably well if carefully calibrated for the ammonia concentration range expected (0-50 ppm, 50-100 ppm, or >100 ppm). If the analyzer can consistently provide on-line data within 10% to 20% of the wet chemistry values, this may be satisfactory when considering the inherent inaccuracies of the wet chemistry method.

Figure 17. NO_x removal efficiency as a function of time for Run PTC-NG-421.

TABLE 10
Summary of Run No. PTC-NG-421

	Reverse-Gas Baghouse					Measured						NH ₃ Slip ppm
	Average		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	NH ₃ ^a Slip ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm	NO _x ^b Removal %	
	Bulk Gas Temp.											
	East °F	West °F										
Test Period #1, A/C=2.0, Molar Ratio=0.90												
Average	665	663	3	75	77	33	3	3	281	57	79	57
Max.	667	665	3	76	78	38	4	4	293	63	82	57
Min.	663	659	2	75	77	24	2	2	265	48	77	
Test Period #2, A/C=2.0, Molar Ratio=0.78												
Average	667	663	3	75	77	34	3	3	288	70	75	
Max.	668	665	3	75	77	40	4	4	314	80	77	
Min.	666	660	3	74	76	29	3	3	251	61	72	
Test Period #3, A/C=1.5, Molar Ratio=0.89												
Average	658	650	3	75	74	30	3	3	299	54	81	59
Max.	659	652	3	76	75	33	4	4	311	61	83	
Min.	658	648	3	75	74	26	3	3	282	47	79	
Test Period #4, A/C=4.1, Molar Ratio=0.89												
Average	676	—	9	74	69	46	3	3	307	84	72	102
Max.	677	—	10	74	72	52	3	4	321	88	74	113
Min.	674	—	9	74	67	37	3	3	291	79	70	
Test Period #5, A/C=1.9, Molar Ratio=0.89												
Average	667	650	4	75	75	42	3	3	304	64	79	
Max.	667	660	5	75	78	49	4	5	311	73	82	
Min.	666	639	3	74	68	36	2	3	284	50	76	

^a Corrected to 4% O₂.

^b Siemens ammonia analyzer.

Flue gas flow rate values measured with the new annubar flow measurement device correlated well (within 1%) with the orifice plate measurements. The old annubar measurement device generally indicated flue gas flow rates were 5% higher than the orifice plate indicated. Therefore, the new annubar and the orifice plate will be used in combination to measure flue gas flow rates during future pilot-scale experiments.

4.3.2 Particulate Collection

Pressure drop and particulate emissions data were also collected during the 100-hour tests during which Illinois #6 bituminous coal was fired. Using an aerodynamic particle sizer (APS), respirable mass data were collected for each 100-hour test. EPA Method 5 and multicyclone particulate sampling data were also collected for each 100-hour test.

4.3.2.1 Run No. PTC-IL6-414

For Test PTC-IL6-414, respirable mass was plotted as a function of time for air-to-cloth ratios of 2.0 and 3.4 ft/min in Figures 18 and 19. The outlet respirable mass emissions averaged roughly 0.10 mg/m³ and 5.0 mg/m³ at air-to-cloth ratios of 2.0 and 3.4 ft/min, respectively. These correspond to collection efficiencies of 99.9% and 95.0%, based on an inlet respirable mass

Figure 18. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.0 ft/min for Run PTC-IL6-414.

Figure 19. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.4 ft/min for Run PTC-IL6-414.

loading of 100 mg/m^3 . Tables 11 through 13 summarize EPA Method 5 and multicyclone particulate-sampling data for Runs PTC-IL6-408 and PTC-IL6-414. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 2.80 to 3.51 grains/scf. An inlet dust loading of 0.76 gr/scf, which is believed to be incorrect, was observed during a multicyclone sampling period. The overall collection efficiency for the reverse-gas baghouse ranged from 96.07% to 99.78%, depending upon operating conditions. When the bags were inspected, it was evident the poor particulate collection efficiency was due to holes in the bags caused by heat treatment.

The operational pressure drop across the bags was the second parameter for performance evaluation. The bags were cleaned such that the maximum differential baghouse pressure was approximately 4 inches W.C. Figure 20 shows the pressure drop as a function of time. As expected, the time between bag-cleaning cycles was dependent on air-to-cloth ratio, every 5 hours at 2 ft/min and every 30 minutes at 3.4 ft/min.

4.3.2.2 Run No. PTC-IL6-415

For Test PTC-IL6-415, respirable mass was plotted as a function of time for air-to-cloth ratios of 1.3, 1.7, and 3.5 ft/min (see Figures 21-25). The outlet respirable mass emissions averaged roughly 0.04 mg/m^3 for an air-to-cloth ratio of 1.3 ft/min, $0.10\text{--}0.01 \text{ mg/m}^3$ at an air-to-cloth ratio of 1.7-2.0 ft/min and 0.1 mg/m^3 at an air-to-cloth ratio 3.5 ft/min. These correspond to collection efficiencies of 99.96%, 99.9%, 99.99%, and 99.9% based on an inlet respirable mass loading of 100 mg/m^3 . Tables 11 and 14 summarize EPA Method 5 and multicyclone particulate-sampling data, respectively. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 2.74 to 3.23 grains/scf. The overall collection efficiency for the reverse-gas baghouse ranged from 99.08% to 99.90%, depending on operating conditions.

Figure 26 plots the pressure drop across the bags as a function of time. The bags were cleaned such that the maximum pressure drop was approximately 4 inches W.C. for an air-to-cloth ratio of 2.0 ft/min. In order to maintain a maximum baghouse differential pressure of 4 inches W.C. at an air-to-cloth ratio of 3.5 ft/min, the bags needed to be cleaned every twenty minutes. Since this was difficult to maintain, a 30-minute cleaning cycle was used instead. At this interval, it was easy to maintain a maximum differential pressure of roughly 6 inches W.C. At air-to-cloth ratios of 1.3 and 2.4 ft/min, a maximum differential pressure of roughly 4 inches W.C. was maintained.

4.3.2.3 Run No. PTC-IL6-416

For Test PTC-IL6-416, respirable mass was plotted as a function of time for air-to-cloth ratios of 1.2, 1.7, and 3.3 ft/min (Figures 27-32). The outlet respirable mass emissions averaged roughly 0.01 mg/m^3 for an air-to-cloth ratio of 1.2 ft/min, 0.045 mg/m^3 at an air-to-cloth ratio of 1.7 ft/min, and 0.01 mg/m^3 at an air-to-cloth ratio 3.3 ft/min. These correspond to collection efficiencies of 99.99%, 99.96%, and 99.99% based on an inlet respirable mass loading of 100 mg/m^3 . Tables 11 and 15 summarize EPA Method 5 and multicyclone particulate-sampling data. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 2.68 to 3.38 grains/scf. The overall collection efficiency for the reverse-gas baghouse ranged from 99.40% to 99.74%, depending on operating conditions.

TABLE 11

Particulate Sampling Data for Pilot-Scale Catalytic Fabric Filter Tests

<u>Test Date</u>	<u>Inlet gr/scf</u>	<u>Outlet gr/scf</u>	<u>% H₂O</u>	<u>% Efficiency</u>
Shakedown				
08-28-91	3.4774	---	10.5	---
08-28-91	---	0.0015	9.1	99.96
08-28-91	2.6611	---	10.2	---
PTC-IL6-408				
11-18-91	3.1843	---	10.7	---
11-18-91	---	0.0028	8.1	99.91
11-18-91	---	0.0036	7.8	99.89
11-19-91	2.7771*	---	5.2	---
11-19-91	---	0.0008	7.5	99.97
11-19-91	2.8891	---	7.6	---
11-20-91	3.109	---	9.6	---
11-20-91	---	0.0065	7.9	99.79
11-21-91	3.3357	---	9.1	---
11-21-91	2.4938*	---	3.9	---
11-21-91	---	0.0014	7.6	99.58
11-22-91	3.191	---	8.1	---
11-22-91	---	0.0008	7.6	99.97
PTC-IL6-414				
01-13-92	3.5102	---	9.1	---
01-13-92	---	0.0127	6.6	99.64
01-13-92	---	0.0076	5.6	99.78
01-14-92	0.7608*	---	3.4	---
01-14-92	2.7997	---	9.5	---
01-14-92	---	0.1099	6.9	96.07
PTC-IL6-415				
02-03-92	3.2273	---	7.5	---
02-03-92	---	0.0033	6.8	99.90
02-04-92	2.7413	---	8.5	---
02-04-92	---	0.007	6.5	99.74
02-04-92	3.1062	---	8.5	---
02-04-92	---	0.0134	8.3	99.57
02-05-92	2.5742	---	7.7	---
02-05-92	---	0.0182	7.9	99.29
02-05-92	2.3597*	---	6.7	---
02-06-92	3.025	---	7.6	---
02-06-92	---	0.0122	6.2	99.60
02-07-92	2.7319	---	7.6	---
02-07-92	---	0.025	6.3	99.08
02-07-92	2.7653*	---	7.8	---

TABLE 11 (continued)

<u>Test Date</u>	<u>Inlet gr/scf</u>	<u>Outlet gr/scf</u>	<u>% H₂O</u>	<u>% Efficiency</u>
PTC-IL6-416				
02-10-92	2.6814	---	8.5	---
02-10-92	---	0.0114	7.5	99.57
02-10-92	---	0.0069	8.2	99.74
02-11-92	2.8368	---	7.6	---
02-11-92	---	0.0170	5.5	99.40
02-11-92	3.3836*	---	6.3	---
02-12-92	2.8452	---	7.8	---
02-12-92	---	0.0138	5.7	99.52
PTC-IL6-417				
02-24-92	3.0147	---	9.3	---
02-24-92	---	0.0154	7.9	99.49
02-24-92	---	0.0186	7.3	99.38
02-25-92	2.8668	---	7.3	---
02-25-92	---	0.0178	7.7	99.38
02-25-92	2.8518*	---	4.6	---
02-26-92	2.9464	---	8.0	---
02-26-92	---	0.0182	8.1	99.37
02-26-92	---	0.0338	8.1	99.85
02-27-92	3.0054	---	13.6	---
02-27-92	---	0.0322	7.6	99.13
02-27-92	3.6961*	---	7.4	---
02-28-92	2.8621	---	7.2	---
02-28-92	---	0.0164	6.6	99.43
02-27-92	---	0.0186	7.5	99.35
PTC-IL6-419				
03-09-92	3.2729	---	8.3	---
03-09-92	---	0.0279	8.3	99.15
03-09-92	---	0.0126	8.5	99.61
03-10-92	2.9588	---	7.5	---
03-10-92	---	0.0212	7.2	99.28
03-10-92	2.8594*	---	7.0	---
03-11-92	2.4762	---	9.1	---
03-11-92	---	0.0006	0.0	99.98
03-11-92	---	0.0088	7.2	99.64
03-12-92	2.7558*	---	7.4	---
03-12-92	2.2041	---	6.5	---
03-12-92	---	0.3520**	7.7	84.03**
03-13-92	2.9318	---	8.0	---
03-13-92	---	0.0190	7.3	99.35
03-13-92	---	0.0157	7.0	99.47

* Multicyclone sampling.

** Sampling error.

TABLE 12
Multicyclone Data from Run PTC-IL6-408

	<u>CY1</u>	<u>CY2</u>	<u>CY3</u>	<u>CY4</u>	<u>CY5</u>	<u>Backup Filter</u>
<u>11-19-91</u>						
D ₅₀ (μm)	8.66	4.28	2.91	1.47	0.91	---
Mass Collected (g)	1.8436	0.2010	0.1243	0.0507	0.0250	0.0216
% Total Mass	81.35	8.87	5.49	2.24	1.10	0.95
Cumulative % Mass less than D ₅₀	18.65	9.787	4.29	2.05	0.950	---
Total Mass Collected = 2.2662 g, Dust Loading = 2.7771 gr/scf, % Isokinetic = 97.51						
<u>11-21-91</u>						
D ₅₀ (μm)	10.16	5.37	3.83	1.93	1.15	---
Mass Collected (g)	0.76802	0.08811	0.09376	0.04958	0.04391	0.02444
% Total Mass	71.92	8.25	8.78	4.64	4.11	2.29
Cumulative % Mass less than D ₅₀	28.08	19.82	11.09	6.40	2.29	---
Total Mass Collected = 1.0678 g, Dust Loading = 2.4938 gr/scf, % Isokinetic = 92.59						

TABLE 13
Multicyclone Data from Run PTC-IL6-414

	<u>CY1</u>	<u>CYaw</u>	<u>CY3</u>	<u>CY4</u>	<u>CY5</u>	<u>Backup Filter</u>
<u>01-14-92</u>						
D ₅₀ (μm)	9.08	4.58	3.28	1.56	0.90	---
Mass Collected (g)	0.48939	0.05053	0.04631	0.01317	0.00613	0.00984
% Total Mass	79.53	8.21	7.53	2.14	1.00	1.60
Cumulative % Mass less than D ₅₀	20.47	12.26	4.74	2.60	1.60	---
Total Mass Collected = 0.6154 g, Dust Loading = 0.7608 gr/scf, % Isokinetic = 97.51

Figure 20. Baghouse differential pressure as a function of time for Run PTC-IL6-414.

Figure 21. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-415.

Figure 22. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-415.

Figure 23. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.5 ft/min for Run PTC-IL6-415.

Figure 24. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.3 ft/min for Run PTC-IL6-415.

Figure 25. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min for Run PTC-IL6-415.

TABLE 14
Multicyclone Data from Run PTC-IL6-415

	CY1	CY2	CY3	CY4	CY5	Backup Filter
<u>02-05-92</u>						
D ₅₀ (μm)	9.46	6.09	3.27	2.25	0.95	---
Mass Collected (g)	1.6110	0.1475	0.1095	0.0392	0.0255	0.0429
% Total Mass	81.55	7.46	5.54	1.98	1.29	2.17
Cumulative % Mass less than D ₅₀	18.45	10.99	5.44	3.46	2.17	---
Total Mass Collected = 1.9755 g, Dust Loading = 2.3597 gr/scf, % Isokinetic = 99.00						
<u>02-07-92</u>						
D ₅₀ (μm)	9.12	5.73	3.06	2.12	0.89	---
Mass Collected (g)	2.0202	0.1558	0.1335	0.0423	0.0342	0.0621
% Total Mass	82.52	6.37	5.45	1.73	1.39	2.54
Cumulative % Mass less than D ₅₀	17.48	11.12	5.66	3.93	2.54	---
Total Mass Collected = 2.4482 g, Dust Loading = 2.7653 gr/scf, % Isokinetic = 97.60

Figure 26. Baghouse differential pressure as a function of time for Run PTC-IL6-415.

Figure 27. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416.

Figure 28. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416.

Figure 29. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.3 ft/min for Run PTC-IL6-416.

Figure 30. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416.

Figure 31. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.2 ft/min for Run PTC-IL6-416.

Figure 32. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-416.

TABLE 15
Multicyclone Data from Run PTC-IL6-416

	<u>CY1</u>	<u>CY2</u>	<u>CY3</u>	<u>CY4</u>	<u>CY5</u>	<u>Backup Filter</u>
<u>02-05-92</u>						
D ₅₀ (μm)	10.31	6.99	3.81	2.58	1.08	---
Mass						
Collected (g)	2.1735	0.1320	0.1232	0.0464	0.0350	0.0614
% Total Mass	84.53	5.13	4.79	1.80	1.36	2.39
Cumulative %						
Mass less						
than D ₅₀	15.47	10.34	5.55	3.75	2.39	---
Total Mass Collected = 2.5714 g, Dust Loading = 3.3836 gr/scf,						
% Isokinetic = 97.60						

The bags were cleaned such that the maximum pressure drop was approximately 4 inches W.C. Figure 33 shows the pressure drop as a function of time. As expected, the time between bag cleanings was dependent on air-to-cloth ratio.

4.3.2.4 Run No. PTC-IL6-417

For Test PTC-IL6-417, respirable mass was plotted as a function of time for air-to-cloth ratios of 1.3, 1.7, 2.5, and 3.5 ft/min (see Figures 34-42). The outlet respirable mass emissions ranged from 0.015 mg/m³ to 0.04 mg/m³ which correspond to collection efficiencies of 99.96% to 99.985% based on an inlet respirable mass loading of 100 mg/m³. Tables 11 and 16 summarize EPA Method 5 and multicyclone particulate-sampling data. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 2.85 to 3.70 grains/scf. The overall collection efficiency for the reverse-gas baghouse ranged from 99.13% to 99.85%, depending on operating conditions.

The baghouse differential pressure is plotted as a function of time in Figure 43. At an air-to-cloth ratio of 1.3 ft/min, the bags were cleaned such that the maximum baghouse differential pressure did not exceed 3 inches W.C. A 4-hour cleaning cycle was maintained at an air-to-cloth ratio of 1.7 ft/min. In order to maintain a maximum baghouse differential pressure of roughly 5 inches W.C., a 1-hour cleaning cycle was required at an air-to-cloth ratio of 2.5 ft/min. The maximum baghouse differential pressure at an air-to-cloth ratio of 3.5 ft/min was kept below 8 inches W.C. with a 2-hour cleaning cycle.

4.3.2.5 Run No. PTC-IL6-419

For Test PTC-IL6-419, the APS unit had been sent in for repairs and was not available for collection of respirable mass data. Tables 11 and 17 summarize EPA Method 5 and multicyclone particulate-sampling data. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 2.20 to 3.27 grains/scf. The overall collection efficiency for the reverse-gas baghouse ranged from 99.15% to 99.98%, depending on operating conditions.

Figure 33. Baghouse differential pressure as a function of time for Run PTC-IL6-416.

Figure 34. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-417.

Figure 35. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.7 ft/min for Run PTC-IL6-417.

Figure 36. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.5 ft/min for Run PTC-IL6-417.

Figure 37. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.5 ft/min for Run PTC-IL6-417.

Figure 38. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.3 ft/min for Run PTC-IL6-417.

Figure 39. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.3 ft/min for Run PTC-IL6-417.

Figure 40. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.5 ft/min for Run PTC-IL6-417.

Figure 41. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.5 ft/min for Run PTC-IL6-417.

Figure 42. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.0 ft/min for Run PTC-IL6-417.

TABLE 16
Multicyclone Data from Run PTC-IL6-417

	CY1	CY2	CY3	CY4	CY5	Backup Filter
<u>02-05-92</u>						
D_{50} (μm)	10.21	6.77	3.67	2.51	1.09	---
Mass						
Collected (g)	1.8582	0.1217	0.1039	0.0310	0.0238	0.0446
% Total Mass	85.11	5.57	4.76	1.42	1.09	2.04
Cumulative %						
Mass less than D_{50}	14.89	9.31	4.55	3.13	2.04	---
Total Mass Collected = 0.6154 g, Dust Loading = 2.8518 gr/scf, % Isokinetic = 93.70						
<u>02-27-92</u>						
D_{50} (μm)	12.97	10.20	5.88	3.79	1.53	---
Mass						
Collected (g)	1.5784	0.1175	0.1253	0.0537	0.0532	0.0444
% Total Mass	80.02	5.96	6.35	2.72	2.70	2.25
Cumulative %						
Mass less than D_{50}	19.98	14.02	7.67	4.95	2.25	---
Total Mass Collected = 1.0678 g, Dust Loading = 3.6961 gr/scf, % Isokinetic = 94.70

Figure 43. Baghouse differential pressure as a function of time for Run PTC-IL6-417.

TABLE 17
Multicyclone Data from Run PTC-IL6-419

	<u>CY1</u>	<u>CY2</u>	<u>CY3</u>	<u>CY4</u>	<u>CY5</u>	<u>Backup Filter</u>
<u>11-19-91</u>						
D ₅₀ (μm)	9.72	6.33	3.41	2.34	0.99	---
Mass						
Collected (g)	1.9956	0.1193	0.0988	0.0261	0.0156	0.0576
% Total Mass	86.28	5.16	4.27	1.13	0.68	2.49
Cumulative %						
Mass less						
than D ₅₀	13.72	8.56	3.17	2.49	2.49	---
Total Mass Collected = 2.3130 g, Dust Loading = 2.8594 gr/scf, % Isokinetic = 95.70						
<u>02-11-92</u>						
D ₅₀ (μm)	11.96	8.67	4.84	3.22	1.34	---
Mass						
Collected (g)	1.2635	0.1601	0.1061	0.0455	0.0400	0.0499
% Total Mass	75.88	9.61	6.37	2.73	2.40	3.00
Cumulative %						
Mass less						
than D ₅₀	24.12	14.51	8.13	5.40	3.00	---
Total Mass Collected = 1.6651 g, Dust Loading = 2.7558 gr/scf, % Isokinetic = 97.70						

The operational pressure drop across the bags is plotted as a function of time in Figure 44. After 11 hours at an air-to-cloth ratio of 1.4 ft/min, the baghouse differential pressure was 4 inches W.C., and the bags were cleaned. After this, the maximum baghouse differential pressure was maintained at 2 inches W.C. with a 2-hour cleaning cycle. A 4-hour cleaning cycle was used at an air-to-cloth ratio of 1.9 ft/min to maintain a maximum differential baghouse pressure of 4 inches W.C. A 2-hour cleaning cycle was used at an air-to-cloth ratio of 2.7 ft/min to maintain a maximum differential baghouse pressure of roughly 3 inches W.C. In order to maintain a maximum baghouse differential pressure of roughly 5 inches W.C., a 1-hour cleaning cycle was required at an air-to-cloth ratio of 3.8 ft/min.

To this point, the particulate collection efficiency for the reverse-gas bags made from fabric DE484 has ranged from 99.08%, based on a measured outlet loading of 0.025 gr/scf, during PTC-IL6-415, to 99.97%, based on a measured outlet loading of 0.0008 gr/scf during PTC-IL6-408. The particulate collection efficiency for the DE484 fabric averaged 99.66% over three tests, which meets the project objective of 99.5% particulate collection efficiency. However, at an air-to-cloth ratio of 2.0 ft/min, 99.9% particulate control should be possible with the DE484 fabric.

Collection efficiency for bags made with fabric DE992 has ranged from 99.15% during PTC-IL6-419, based on a measured outlet loading of 0.0279 gr/scf to 99.98%, based on a measured outlet loading of 0.0006. The two lowest

Figure 44. Baghouse differential pressure as a function of time for Run PTC-IL6-419.

particulate collection efficiencies for this fabric are questionable. The lowest, 84.03%, occurred during PTC-IL6-419 and is based on a measured outlet loading of 0.352. The sampling filter became wet during this outlet and invalidated the results. The bags had several holes in them by the time sampling was performed for the period that yielded the second lowest particulate collection efficiency. The efficiency was 96.07%, based on a measured outlet loading of 0.1099 gr/scf, during PTC-IL6-414. The particulate collection efficiency for the DE992 fabric averaged 99.55% over three tests. Again, this does not quite meet the 99.9% particulate collection efficiency expected, but does meet the original project objective of 99.5%.

Multicyclone sampling at the inlet of the baghouse was completed in order to determine the aerodynamic particle size of the fly ash in the flue gas stream entering the baghouse for each test. Results show that roughly 81% of the mass had a particle size greater than 10 μm .

From the multicyclone and Coulter Counter data, shown in Figures 45 and 46, the mass median diameter (volumetric median diameter) of the fly ash was determined to be about 17 micrometers.

Bulk ash samples collected from the hopper of the reverse-gas baghouse for each test were analyzed for carbon and major elements. The carbon content of the ash as determined by loss on ignition averaged 4.76%. Table 18 presents the major elements as determined by x-ray fluorescence (XRF) analysis.

Figure 45. Coulter Counter data for Runs PTC-IL6-408 through PTC-IL6-419.

Figure 46. Multicyclone data for Runs PTC-IL6-408 through PTC-IL6-419.

TABLE 18
Reverse-Gas Baghouse Ash Analysis Results

	<u>Average</u>	<u>Maximum</u>	<u>Minimum</u>
Loss on Ignition (wt%)	4.76	7.97	3.04
Oxides (wt% of ash)			
SiO ₂	51.56	52.60	49.80
Al ₂ O ₃	19.59	20.90	17.60
Fe ₂ O ₃	18.29	21.90	16.10
TiO ₂	0.92	1.16	0.68
P ₂ O ₅	0.26	0.40	0.18
CaO	3.80	4.63	3.21
MgO	1.06	1.16	0.95
Na ₂ O	0.82	1.08	0.54
K ₂ O	2.05	2.20	1.87
SO ₃	1.59	3.77	1.13

A concern with the use of catalyst-coated bags is the possibility of catalyst erosion resulting in an increase in the vanadium content of the fly ash. Because vanadium is listed as a RCRA element, and some vanadium compounds are considered to be hazardous materials, it is important to monitor vanadium concentration in the fly ash. Table 19 presents the vanadium content of the coal, the fly ash from the inlet to the reverse-gas baghouse, and the ash from the baghouse hopper as determined by atomic absorption (AA) analysis. From the results, it appears the vanadium catalyst did not erode from the bags for any of the 100-hour tests, except possibly Run No. PTC-IL6-416. The vanadium in the baghouse ash after running at an air-to-cloth ratio of 2 ft/min was 290 ppm. This sample was taken after the first two bag cleanings. This corresponds to the decreased NO_x removal observed after the first cleaning of the bags and may indicate a loss of catalyst from the fabric. For the remainder of the samples, when comparing the vanadium concentration in the inlet fly ash to the theoretical concentration based on the concentration of the vanadium and ash in the coal, there is a distinct increase in the vanadium in the fly ash. An explanation is that vanadium is known to be enriched in the fine particulate matter as a result of initial vaporization in the flame zone and subsequent condensation on fine ash particles. Although the concentration of the vanadium in the combustor bottom ash was not measured, it is expected to be less than the concentration in the fly ash.

TABLE 19
Vanadium Concentration Analysis Results

	<u>Coal Composite (ppm)</u>	<u>Coal Ash (ppm)</u>	<u>Inlet (ppm)</u>	<u>RGBH Ash (ppm)</u>	<u>Sample Conditions</u>
PTC-IL-408	19		220 250	240 250	
		160			Calculated Theoretical (11.89% ash)
PTC-IL-414				260	A/C Ratio = 2.0 ft/min
PTC-IL-415				270 260 260 260	A/C Ratio = 1.5 ft/min A/C Ratio = 2.0 ft/min A/C Ratio = 3.0 ft/min A/C Ratio = 4.0 ft/min
PTC-IL-416				260 250 290	A/C Ratio = 4.0 ft/min A/C Ratio = 2.0 ft/min
PTC-IL-419				260 230 250 240 240	A/C Ratio = 1.5 ft/min A/C Ratio = 2.0 ft/min A/C Ratio = 2.0 ft/min A/C Ratio = 3.0 ft/min A/C Ratio = 4.0 ft/min

Based on pilot-scale results observed through March, the 14-ounce/yd² (DE484) fabric prepared using an organic-based catalyst coating will be used during the last five 100-hour reverse-gas tests. This fabric was evaluated during a 100-hour test in February (Run No. PTC-IL6-415) and a 2-day test in March (Run No. PTC-NG-421).

Future tests will include retesting DE992 bags, which will complete the catalyst-coated fabric testing phase. The next three 100-hour tests will determine the effect of coal type on the performance of catalyst-coated fabric. The coals will include a Blacksville eastern bituminous, a Black Thunder western subbituminous, and Beulah western lignite. A new set of bags will be used for each 100-hour test, made from the DE484 fabric with the 7-coat vanadium/titanium catalyst. Following the coal tests, two 100-hour tests will be completed to determine the effect of temperature on catalytic fabric performance. The first of the temperature tests will determine the effect of cycling through normal operating temperatures ranging from 500° to 750°F. The second 100-hour test will determine the effect of cycling to lower temperatures (250°-700°F) and passing through several dew points on catalytic fabric performance. Again a new set of bags made from the DE484 fabric with the 7-coat vanadium/titanium catalyst coating will be used for each of these tests.

The Illinois #6 bituminous coal will be fired to generate flue gas for these two 100-hour test periods.

4.4 Subtask 3.3--Process Testing/Pulse-Jet System

Work was initiated in March with respect to evaluating equipment needs and options for the oil-fired test to be completed as part of Subtask 3.3. At this point in time, it appears that all equipment needs can be met with existing components or minor modifications to existing components already available at the EERC. Performance of the three 100-hour tests planned for this subtask should begin in mid-June with completion in July. The 500-hour test will most likely take place in September or October.

4.5 Subtask 3.4--Fabric Durability Testing/Pulse-Jet System

Subtask 3.4 activities were initiated in September 1991 in order to prepare the baghouse slipstream system at the UND Steam Plant for operation. A shielded cable was ordered for installation between the slipstream baghouse data logger and the UND Steam Plant computer. Directly connecting the data logger to the computer will permit high-limit alarms programmed on the data logger to appear on the UND Steam Plant computer terminal. This will make it easier for Steam Plant personnel to monitor the slipstream baghouse during the normal performance of their duties and result in a faster response to any operational problems the slipstream baghouse may experience. Also data acquisition, storage, retrieval, and evaluation should be simplified.

EERC personnel completed a few days of operation with the slipstream pulse-jet baghouse at the UND Steam Plant in March to verify that baghouse operating temperature can be adequately controlled. Temperature control appears to be adequate for the range of operational loads (30,000 to 80,000 lbs of steam/hour) anticipated for the Steam Plant Boiler. A combination of heat exchanger capacity, flue gas flow rate adjustments, and the use of tempering air are available to maintain baghouse temperature in the range of 550° to 750°F. Preparation of the baghouse slipstream system has been completed; therefore, the long-term catalyst-coated filter bag performance/durability test can begin as soon as a set of pulse-jet filter bags are available.

Selection of a catalyst-coated fabric for Subtask 3.4 was discussed during the project review meeting on March 3, 1992. Participants agreed that the 22-ounce/yd² fabric would be the best for pulse-jet applications; therefore, the DE992 fabric will be used. This fabric will be prepared using an organic-based vanadium/titanium catalyst coating corresponding to Fabric #17 and #106B in previous bench- and pilot-scale tests. Pulse-jet bags should be available for installation by late April.

Whether or not 12,000 hours of baghouse operation at the UND Steam Plant can be achieved will depend on when the durability test actually begins and on UND Steam Plant operating plans in 1992 and 1993. At this point, it appears that the boiler, from which the flue gas slipstream will be removed, will be operating over the summer. Therefore, some of the time lost during this past heating season can be recovered.

5.0 KEY PERSONNEL STAFFING REPORT

Table 20 presents planned versus actual workhours for key EERC and UE&C personnel involved in the Catalytic Fabric Filtration project through March 1992.

TABLE 20
Planned Versus Actual Workhours
for Key Personnel Through March 1992

<u>Key Personnel</u>	<u>Planned Hours</u>	<u>Actual Hours</u>	<u>% of Total Available Workhours Used</u>
Greg Weber	1256	1060	84
Dennis L. Laudal	1868	761	41
Chris Robie	29	16	55

6.0 REFERENCES

1. Pirsh, E.A. U.S. Patent 4 220 633, September 2, 1980, assigned to Babcock and Wilcox Co.
2. Pirsh, E.A. U.S. Patent 4 309 386, January 5, 1982, assigned to Babcock and Wilcox Co.
3. Doyle, J.B. et al. U.S. Patent 4 793 981, December 27, 1988, assigned to Babcock and Wilcox Co.
4. Weber, G.F. "SO_x/NO_x Control, Low-Rank Coal Research under the UND/DOE Cooperative Agreement," Quarterly Technical Progress Report, University of North Dakota Energy and Environmental Research Center, Grand Forks, ND, DOE\FE\60181-1531, January 1984, Section 6.
5. Kalinowski, M.R.; Nishioka, G.M. "Method for Applying Porous Metal Oxide Coatings to Relatively Nonporous Fibrous Substrates," United States Patent No. 4 732 879, March 22, 1988.
6. Weber, G.F.; Laudal, D.L. "SO_x/NO_x Control - Catalytic Fabric Filtration for Simultaneous NO_x and Particulate Control," Final technical report for the period April 1, 1988, through June 30, 1989; Grand Forks, ND, DE-FC21-86MC10637, August 1989.
7. Weber, G.F.; Miller, S.J.; Laudal, D.L. "Flue Gas Cleanup," Final technical report for the period July 1, 1989, through June 30, 1990; Grand Forks, ND, DE-FC21-86MC10637, October 1990.

END

**DATE
FILMED**

9 / 11 / 92