ANL-92/25

ANL--92/25

DE93 000561

ARGONNE NATIONAL LABORATORY
9700 South Cass Avenue
Argonne, IL 60439

NUCLEAR TECHNOLOGY PROGRAMS
SEMIANNUAL PROGRESS REPORT

April - September 1990

Chemical Technology Division

M. J. Steindler, Director
J. E. Battles, Associate Director
J. E. Harmon, Editor

June 1992

Previous Reports in this Series

October 1989-March 1990	ANL-91/42
April 1989-September 1989	ANL-91/26
October 1988-March 1989	ANL-90/16
April 1988-September 1988	ANL-90/15

MASTER

ED
REPRODUCTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	1
SUMMARY	1
I. APPLIED PHYSICAL CHEMISTRY	9
A. Behavior of Core-Concrete Mixtures under Accident Conditions	9
1. Introduction	9
2. Experimental	12
3. Results and Discussion	14
B. Thermophysical Property Studies	20
1. Plutonium-Uranium System	20
2. Iron-Uranium System	23
3. Minor Actinide Systems	23
C. Support Studies for New Production Reactor	24
1. Fission Product Release from HWR-NPR Fuel and Targets	24
2. Containment Habitability	29
D. Fusion-Related Research	31
1. Desorption Characteristics of $\text{LiAlO}_2\text{-H}_2\text{-H}_2\text{O(g)}$ System	32
2. Tritium Release from Lithium Ceramics	37
3. Processing System for the Li_2O Blanket in ITER	41
REFERENCES	48
II. SEPARATION SCIENCE AND TECHNOLOGY	51
A. Revisions to Generic TRUEX Model	51
B. Development of Spreadsheet Algorithm for Stagewise Solvent Extraction	53
1. Introduction	53
2. Extraction Efficiency	53
3. Fixed Effluent Flow Rate	55
C. Modeling of Oxalic Acid Extraction	56
1. Extraction by TBP	56
2. Extraction by CMPO	57
3. Extraction by TRUEX Solvent	59
D. Extraction Studies	60
1. Plutonium(IV) Extraction	60
2. Neptunium Extraction	62
3. Thorium Extraction	65

TABLE OF CONTENTS (contd)

	<u>Page</u>
4. Americium Extraction	66
5. Curium Extraction	69
6. Aqueous Solution Behavior of Neodymium	72
7. Use of ²⁴¹ Am Extraction as a Purity Check for CMPO	77
E. Data Base Development	77
F. Monitoring and Controlling TRUEX Processes	78
1. Introduction	78
2. Selection of Process Flowsheet	79
3. Operating Limits for TRUEX Process	82
4. Sensor Requirements	82
5. Dynamic Response of GTM	85
6. Sensitivity Analysis	90
G. Processing of New Brunswick Laboratory Waste Solution	95
1. Introduction	95
2. Process	96
3. Plutonium-Containing Waste Solutions	97
4. TRUEX Flowsheet Development	99
5. Four-Stage Neodymium Precipitation Test	100
6. Filtration, Evaporation, and Calcining Procedures	103
H. Model Verification Studies	105
1. Introduction	105
2. Verification Run 12	105
I. Centrifugal Contactor Development	115
1. Vibrations	115
2. Contactor Concentrator	117
3. 10-cm Contactor	122
4. 2-cm Contactor	123
J. Aqueous Biphasic Separation of Plutonium from Solid Residues	123
1. Introduction	123
2. Particle Characterization	124
3. Particle Separation by Biphasic Partitioning	131
4. Use of Plutonium Polymer as Model System	131
K. Measurement of Plutonium in Particulate Matter	135
1. Liquid Scintillation Counting	136
2. X-Ray Counting	140
3. Gamma-Ray Counting	140
4. Optical Spectroscopy	140
5. Biphasic Separations	141

TABLE OF CONTENTS (contd)

	<u>Page</u>
L. Decontamination of Groundwaters Containing Volatile Organic Compounds	142
1. Introduction	142
2. Literature Survey	142
3. Conceptual Design of the MASX/MADS Process	144
4. Demonstration of MASX Technical Feasibility	144
5. Technical Feasibility of MASX/MADS Process	145
REFERENCES	150
 III. NUCLEAR WASTE PROGRAMS	 155
A. Unsaturated Glass Testing Program for Office of Environmental Restoration and Waste Management	155
1. Critical Review of Parameters Affecting Glass Reaction in an Unsaturated Environment	155
2. Long-Term Testing of Fully Radioactive Glass	156
3. Effect of Radiation	162
4. Relationship between High SA/V Experiments and MCC-1	164
5. Analytical Electron Microscopy	171
6. Natural Analogs	176
B. Glass Studies for Yucca Mountain Project	179
1. Tests with Unsaturated Test Method	179
2. Parametric Experiments	179
3. Leach Experiments	179
C. Radiation Effects Studies for Yucca Mountain Project	191
1. Background	191
2. Experimental	191
3. Results and Discussion	192
4. Conclusions	196
D. Spent Fuel Studies for Yucca Mountain Project	197
E. Spectroscopic Investigation of Radionuclide Speciation	198
1. Background	198
2. Hydrolysis of Pu(VI) in Noncomplexing Media	200
F. Radiation-Effects Studies for Waste Isolation Pilot Plant (WIPP)	206
1. Background	206
2. Gamma Radiolysis of N ₂ -CO ₂ Mixture	207

TABLE OF CONTENTS (contd)

	<u>Page</u>
3. Gamma Radiolysis of O ₂ /CO ₂ /H ₂ /N ₂ Mixture	208
4. Plutonium Stability in WIPP Brine	209
REFERENCES	215

NUCLEAR TECHNOLOGY PROGRAMS
SEMIANNUAL PROGRESS REPORT
April - September 1990

ABSTRACT

This document reports on the work done by the Nuclear Technology Programs of the Chemical Technology Division, Argonne National Laboratory, in the period April-September 1990. These programs involve R&D in three areas: applied physical chemistry, separation science and technology, and nuclear waste management. The work in applied physical chemistry includes investigations into the processes that control the release and transport of fission products under accident-like conditions in a light water reactor, the thermophysical properties of the metal fuel in the Integral Fast Reactor, and the properties of selected materials in environments simulating those of fusion energy systems. In the area of separation science and technology, the bulk of the effort is concerned with developing and implementing processes for the removal and concentration of actinides from waste streams contaminated by transuranic elements. In the area of waste management, investigations are underway on the performance of materials in projected nuclear repository conditions to provide input to the licensing of the nation's high-level waste repositories.

SUMMARY

Applied Physical Chemistry

The program in applied physical chemistry involves studies of the thermochemical, thermophysical, and transport behavior of selected materials in environments simulating those of fission and fusion energy systems.

During this report period, solidus-liquidus temperatures were determined by differential thermal analysis (DTA) measurements on three calcined concretes (limestone, limestone-sand, and siliceous) and mixtures of each of these concretes with $\text{UO}_2\text{-ZrO}_2$. Such mixtures are expected to occur during the molten core-concrete interaction phase of severe reactor accidents in light water reactors. The results are to be incorporated into a thermal-hydraulic code (CORCON) that treats core-concrete interactions in hypothetical severe reactor accidents and is an integral part of the Nuclear Regulatory Commission's Source-Term Code Package. The differences between the solidus and liquidus temperatures for the three core-concrete mixtures (27 wt % concrete plus 73 wt % $\text{UO}_2\text{-ZrO}_2$) were found to be more than 1200°C, while the differences currently employed in CORCON (for same core-concrete composition) range from 500 to 700°C. Our results are in reasonable agreement with hypothetical liquidus-solidus curves obtained by assuming limited solubilities between the urania-zirconia-calcia phase and the concrete. Additional DTA experiments at 10, 60, and 85 wt % concrete will be required to establish liquidus-solidus curves over the range of core-concrete mixtures that may be encountered in severe reactor accidents.

Measurements and calculational analyses are being performed to provide needed thermophysical property data for Integral Fast Reactor (IFR) fuels. Our efforts are focused on gaining a more thorough understanding of the phase relations involved in the U-Pu-Zr fuel and in fuel-cladding compatibility. Results are presented for an analysis of the Pu-U and the Fe-U systems. Calculations of the Pu-U phase

diagram indicated that some of the assignments in the generally accepted diagram are probably incorrect. A revised Pu-U phase diagram is presented. Also, DTA measurements were completed for the Fe-U system, and a revised phase diagram was calculated for that system. Good agreement was obtained between our DTA measurements and the calculated diagram.

In several IFR fuel cycle concepts under consideration, the recycled fuel could contain concentrations of the so-called minor actinides. We conducted a preliminary analysis of metallic fuel systems containing these actinides. It was found that properties of actinide-containing metallic fuel can change markedly depending on the actinides present. Thus, if IFR fuel is to contain significant amounts of minor actinides, particularly Am or Cm, careful study will be needed to determine their effect on the fuel properties.

The DOE initiated the New Production Reactor (NPR) Program to plan, design, and construct safe and environmentally acceptable new reactor capacity for an assured supply of tritium. The CMT Division has supported this program by conducting several studies on an NPR that is a heavy water reactor (HWR). One such study concerns the release of fission products and tritium from U-Al fuel and Li-Al targets in a hypothetical severe accident with the HWR-NPR. Two approaches are being pursued in this study: experimental measurements using transpiration and high-temperature mass spectrometry and thermodynamic analyses using the SOLGASMIX computer code. Preparatory work needed before initiating the experimental measurements is underway. Preliminary results are reported for SOLGASMIX calculations for U-Al, Li-Al, and selected fission products at 1000 and 1700 K. Conclusions reached from these calculations are that LiI is important as a gaseous species and in the condensed phases, tellurium is bound by uranium as UTe and is retained in the condensed phases, iodine is essentially not bound as UI_3 or AlI_3 in the gas or condensed phases, and AlTe is significant in the gas phase.

In another HWR-NPR study, a computer model was developed to simulate detritiation processes in the event of either chronic or burst releases of tritiated species into the containment structure. The model incorporates the interaction between the vapor phase species and species on the surfaces and the bulk interior of the structural components, such as concrete walls and coatings. Calculated results indicate that, under a wide range of circumstances, the time necessary to reduce the activity level to an acceptable limit after a tritium spill is dominated by the retention capability of the tritiated species in the structural components. This implies that development of optimal barriers against tritium penetration into these components is important.

A critical element in the development of a fusion reactor is the blanket for breeding tritium fuel. Several studies are underway with the objective of determining the feasibility of using lithium-containing ceramics as breeder material. In one such study, temperature programmed desorption (TPD) measurements are in progress to provide data that describe the kinetics of desorption of $H_2(g)$ and $H_2O(g)$ from one of the candidate ceramic breeders, $LiAlO_2(s)$, under a helium pure gas (with and without 990 ppm H_2). The TPD spectra for H_2O evolution from $LiAlO_2$, pretreated with helium containing 900 ppm $H_2(g)$ at high temperature (673 K), indicated first-order desorption processes involving three different types of sites on the $LiAlO_2$ surface. The activation energies for desorption from $LiAlO_2$ in pure helium and He- H_2 mixtures were calculated for each type of site. An explanation is given for the previously reported enhancement of tritium release attending the use of H_2 in the helium purge gas.

In another blanket study, data from experiments carried out at the Centre d'Etudes Nucleaires (CEN) de Grenoble were analyzed to determine the effects of key parameters (tritium residence time, temperature, ceramic microstructure, and purge gas composition) on tritium release. This analysis revealed that a model with multiple desorption activation energies (as opposed to one) is necessary to

account for variations in tritium inventory observed with different purge gas compositions. Some data also suggest that a second mechanism, probably diffusion, contributes to the tritium inventory.

Blanket design studies are in progress for the International Thermonuclear Experimental Reactor (ITER)--an international project whose purpose is to produce a conceptual design of a tokamak reactor that can be used to test components for a prototype fusion reactor and plasma operations. The blanket for this facility will use Li_2O as the breeder, beryllium as the neutron multiplier, and water as the coolant. We have defined the components needed for the processing system to recover and purify tritium from the blanket. The components were selected to minimize the tritium inventory of the recovery system and to minimize waste products.

Separation Science and Technology

The Division's work in separation science and technology is mainly concerned with removing and concentrating actinides from waste streams contaminated with transuranic (TRU) elements by use of the TRUEX solvent extraction process. The extractant found most satisfactory for the TRUEX process is octyl (phenyl)-N,N-diisobutylcarbamoylmethylphosphine oxide, which is abbreviated CMPO. This extractant is combined with tributyl phosphate (TBP) and a diluent to formulate the TRUEX process solvent. The diluent is typically a normal paraffinic hydrocarbon (NPH) or a nonflammable chlorocarbon such as tetrachloroethylene (TCE). Other projects in separation science and technology include developing processes for plutonium recovery from pyrochemical wastes and incinerator ash and for cleanup of contaminated groundwater.

The major TRUEX effort involves development of a generic data base and modeling capability for this solvent extraction process. The Generic TRUEX Model (GTM) was developed for site-specific flowsheet development directed to (1) establishing a TRUEX process for specific waste streams, (2) assessing the economic and facility requirements for installing the process, and (3) improving, monitoring, and controlling on-line TRUEX processes. In September 1990, version 2.1 of the model for the Macintosh computer was issued. New options available in this version include the ability to calculate distribution ratios for a user-specified aqueous phase, where the organic phase is assumed to have been pre-equilibrated; calculate distribution ratios for equilibration of user-specified aqueous and organic phases; estimate solvent degradation for a specific TRUEX process; and generate reports from existing TRUEX flowsheets or space and cost calculations.

One of the sections in the GTM, the Spreadsheet Algorithm for Stagewise Solvent Extraction (SASSE), was modified so that a user can specify (1) an extraction efficiency for each stage in the process and (2) a fixed effluent flow rate for either the organic or aqueous phase at any stage. In previous SASSE calculations, extraction efficiency was assumed to be 100%, and effluent flow was specified as a fraction of the total flow of the organic or aqueous phase from a stage.

Mathematical models of extraction data for the GTM continue to be improved as more extraction data are collected. Current efforts are directed toward providing a realistic model of oxalic acid extraction by TRUEX-NPH solvent.

Laboratory studies were conducted to obtain data on the extraction behavior of feed components (including Pu, Np, Am, and Cm) under a variety of process conditions. Distribution ratios were measured for Pu(IV) extraction from nitric acid solution by TRUEX-NPH at 25°C. This polymer was found to be poorly extracted. Distribution ratios were in the range of 1 to 10, compared to ratios of 10^4 - 10^5 for monomeric plutonium in the same solution. Hydrofluoric acid (0.05M) was ineffective in stripping the extracted plutonium from the organic phase. Only 15-20% was stripped, although monomeric plutonium

is almost completely removed under the same conditions. Distribution ratios were also measured for Np(IV) between TRUEX-NPH and either nitric acid/sodium nitrate solution or nitric acid/sodium nitrate/sulfuric acid solution at 25°C. For both nitric acid-containing solutions, the nitrate ion concentration was kept constant at 3.2M. With the former solution, the neptunium distribution ratios ranged from about 400 at 0.01M HNO₃ to 3×10^5 at 1.0M HNO₃. This behavior contrasts with that of americium and curium, whose distribution ratios decrease with increasing nitric acid concentration. The high nitrate ion concentration increases the neptunium distribution ratios over those in nitric acid solution alone. With the solution containing sulfuric acid, the neptunium distribution ratios decreased with increasing acid concentration due to the complexing action of the sulfate ion. Distribution ratios were also measured for the extraction of ²⁴¹Am and ²⁴⁴Cm by TRUEX-NPH at 50°C with each of the following complexants: oxalic acid, sulfuric acid, phosphoric acid, and hydrofluoric acid. These solutions also contained sodium nitrate with nitric acid. Preparations are in progress to measure distribution ratios for Th and Nd.

Much of the extraction data generated through September 1990 have been entered into the GTM data base. Emphasis has also been placed on collecting relevant data from the literature. To that end, literature searches have been conducted using the DOE Energy Data Base and the data base of the American Chemical Society. The search was for all abstracts mentioning CMPO and yielded 109 references.

A literature review was carried out to determine the instrumentation and control requirements for the TRUEX process. An examination of the conceptual design flowsheet for the generic TRUEX process indicated that one can characterize the instrumentation requirements as follows: (1) conventional instruments to detect, monitor, and control basic process variables and (2) more sophisticated analytical techniques for measurement and control of transuranics. Analytical techniques for on-line monitoring of transuranics are not well developed and would require development of instruments and monitoring techniques. In a modeling effort, equations were derived to determine the effect of deviations from steady state due to perturbations in feed composition at constant flow rates.

The GTM was used in performing a sensitivity analysis to determine the effect of perturbations in feed composition and flow rates for a base-case flowsheet with regard to meeting goals set for processing nuclear waste generated by the Plutonium Finishing Plant (PFP) of Westinghouse Hanford. Also calculated was whether losing a stage in the extraction section, scrub section, first strip, or second strip would result in one of the process goals being exceeded.

The GTM was also used to develop a TRUEX flowsheet for treating plutonium-containing waste (approximately 200 L) generated at ANL and the New Brunswick Laboratory (NBL). This flowsheet will be used in converting the bulk of this waste into a nonTRU product by removing the TRU elements to activity levels <10 nCi/g. This waste can then be disposed of under existing regulations. The recovered plutonium will be converted into solid PuO₂ for storage and subsequent shipment to the DOE defense complex. A safety review, which covers the evaporation, filtration, and calcination of the plutonium oxalate that will be recovered from the processing of plutonium waste solutions, has been completed and awaits approval.

Laboratory verification tests of the TRUEX process are being completed to gain a better understanding of the process chemistry, to test and verify process modifications, and to verify the results of GTM calculations. One verification test was completed in this period with a 2-cm centrifugal contactor with 16 stages. The titration results from the organic phase collected from the contactor stages agreed favorably with the GTM calculations. However, the agreement between the titration results for the

aqueous phase and GTM calculations was not as good. Reasons for this discrepancy are likely due to the shutdown procedures for the contactor and are under further investigation.

Centrifugal contactor development continues to be an important part of the TRUEX process development. To support the design of new contactors, a worksheet (called "Beam") using Microsoft Excel software was developed to calculate the first natural frequency of rotating systems. It provides the vibrational analysis needed to complete the mechanical design of motor/rotor systems for centrifugal contactors. The Beam worksheet was tested against calculated results from other vibrational models and experimental data and found to work well. Techniques for measuring vibrations and the application of Beam to the design of high-throughput contactors are discussed.

We are exploring the use of the centrifugal contactor as a concentrating device. This work builds on an impressive feature of centrifugal contactors--their ability to operate at very high and very low organic-to-aqueous (O/A) ratios. The ability of the centrifugal contactor to act as a concentrating device was experimentally demonstrated over a wide range of O/A flow ratios, from 0.01 to 33. In addition, a set of equations was derived to facilitate the design of contactors for this application. Other contactor efforts included (1) modifying the design of a 10-cm contactor for the proposed TRUEX facility at the Westinghouse Hanford PFP and (2) fabricating and testing a 24-stage 2-cm contactor to be used by Chalk River Laboratories.

Work is also underway on separation science and technology not using TRUEX. One such project involves plutonium recovery from pyrochemical wastes and incinerator ash. An aqueous biphasic separation process is being examined as a means of recovering and concentrating actinides in particulate form. The biphasic extraction of polymeric plutonium was studied with the use of 7.5% sodium sulfate solution (Na_2SO_4), 15% polyethylene glycol (PEG) solution, and a variety of transfer agents (0.1 and 0.01 wt %) at 25°C. Of the transfer agents examined, humic acid had the most pronounced influence on the partitioning behavior of the plutonium polymer. The distribution ratios of the plutonium polymer increased from 0.001 to 2.2 for the PEG/ Na_2SO_4 system with and without 0.01 wt % humic acid, respectively. In almost every case, poor plutonium recoveries occurred when a transfer agent was added to the biphasic system. Much of the plutonium was found on the walls of the glass tubes employed in these tests and in the interfaces between the phases. With the addition of Aerosol OT, most of the unaccounted plutonium was found at the liquid/liquid interface. This finding implies that the transfer agent completely prevented the plutonium polymer from adsorbing onto the test tube walls. Aged plutonium polymer is known to adsorb onto all kinds of surfaces (e.g., glass, metal). This tendency makes it difficult to process aqueous solutions containing polymerized plutonium.

Studies on the biphasic separation of plutonium from solid waste require the measurement of plutonium in particles ranging in size from 1 to 0.001 μm . Four methods for this measurement were evaluated: liquid scintillation alpha counting, L X-ray counting, gamma-ray counting, and optical absorption spectrometry. Advantages and disadvantages of each are discussed.

A process is being developed for cleanup of volatile organic compounds in contaminated groundwater. The contaminants will be extracted by membrane-assisted solvent extraction and then recovered in a membrane-assisted distillation stripping section. This process is being evaluated as an alternative to groundwater remediation procedures using activated carbon or air stripping/activated carbon. Work at the University of Minnesota has demonstrated, on a laboratory scale, the membrane-assisted solvent extraction of dilute volatile components from water using sunflower oil. The regeneration of the solvent and recovery of the volatile contaminants by membrane-assisted distillation stripping have not yet been demonstrated. Work in this area of solvent regeneration is now in progress.

Nuclear Waste Programs

The volcanic tuff beds of Yucca Mountain, Nevada, are being studied as a potential repository site for isolating spent reactor fuel and high-level defense and commercial waste. The behavior of this spent fuel and waste in the host environment must be sufficiently well understood to project its stability over very long time periods.

A nuclear waste program has been established for DOE Environmental Restoration and Waste Management to evaluate factors that are likely to affect waste glass reaction in an unsaturated environment. Such an environment may exist at the potential Yucca Mountain site. Six tasks in this program are underway in CMT.

The first task involves a critical review of the literature relevant to those parameters that affect the reactivity of glass in an unsaturated environment. Temperature is the first parameter examined in detail. A general conclusion reached from this review is that temperature can be used as an accelerating parameter for chemical reactions that affect waste glass/water interactions when they are identified and understood. However, key aspects of these reactions must be investigated further to develop an understanding of the complex overall reaction that will occur under repository conditions.

The objective of the second task is to evaluate the reactivity of fully radioactive glasses in a high-level waste repository environment and compare it to the reactivity of nonradioactive glasses of similar composition. Static leach tests at 90°C were initiated using SRL 165/42 and SRL 131/11 glasses and simulated nonradioactive glasses. Tests with monolith and powder samples have been in progress for 180 days, but the data are too preliminary to draw any conclusions as yet. Tests with 200R glass will begin as soon as the complete shipment of glass is received.

The third task entails determining the effect of radiation upon the durability of waste glasses at high ratios of glass surface area to liquid volume (SA/V). These tests examine (1) the effect of radiation on the environment of a moist air system, (2) glass reaction in a radiolytic field, and (3) the influence of radiation and radiolytic products on the formation and stability of glass alteration phases. Results from blank tests (no glass, moist air under alpha or gamma radiation field at 25°C) indicate that NO_3^- , organic carbon, and inorganic carbon are readily produced in gamma and alpha fields, and that NO_3^- varies linearly with respect to time and dose. The results also suggest that the radiolytic products are concentrated in thin films of water that condense on the test vessel walls and/or radioactive source materials. Preliminary qualitative results (56 days) from glass reaction tests indicated that the reaction rates in an irradiated water vapor environment (0.005 rad/h with 200°C steam) may be significantly increased compared to those in a nonirradiated water vapor environment.

A fourth task is underway to compare the extent of reaction of waste glasses (SRL 131 and SRL 202) at SA/V ratios from 10 to 20,000 m^{-1} . Short-term test results (30 days at 90°C) indicate that the SRL 131 glass is more reactive than the SRL 202 glass, and that the extent of reaction is greater for tests at the higher SA/V ratios.

In a fifth task, analytical electron microscopy (AEM) is being used to assess the glass/water reaction pathway by identifying intermediate phases that appear on the reacting glass. Significant experience was gained in sample preparation and microscopy by applying AEM to a wide variety of existing glass samples, which ranged from glass with no reacted layer, to a reacted layer forming as the glass etches, to a reacted layer forming *in situ* as the glass restructures.

The objective of the sixth task is to assess the reaction of naturally occurring glasses (obsidian, tektite, basalt) with water under conditions where the SA/V ratio is large. A number of different obsidians were hydrated in vapor between 100 and 230°C for up to 256 days at relative humidities of 60-100%. The rate of growth in the hydration layer was found to be proportional to the square root of time, a dependence consistent with a diffusion process. Further investigations are being pursued to characterize the strong dependence of the isothermal hydration rate for obsidian on its intrinsic water content.

Several different experiments involving the reaction of glass and spent fuel under simulated repository conditions are being performed in support of DOE's Yucca Mountain Site Characterization Project (YMP).

In an ongoing YMP study, simulated waste glasses (SRL 165 and ATM-10) have been intermittently contacted with dripping well water (J-13) using an unsaturated test method at 90°C. These tests have been in progress for 234 weeks with SRL 165 glass and 219 weeks with ATM-10 glass. In another YMP glass study, results were analyzed from previously performed leach tests (SRL 165 glass reacted with well water at 90°C in stainless steel vessels for 14 to 280 days at an SA/V ratio of about 30 m⁻¹). This analysis led to the proposal of a model for glass reaction under unsaturated conditions. In addition, the model from the EQ3/6 computer code, which is currently used in the YMP to simulate the long-term reaction of glass under various possible repository environments, was compared with the reaction path suggested by the leach tests. The test results were consistent with the EQ3/6 model but did not sufficiently validate it. Longer term data are needed to verify the EQ3/6 predictions.

In corrosion studies for the YMP, oxygen-free copper, 70/30 copper-nickel, and aluminum bronze are being evaluated as candidate materials for the construction of the high-level nuclear waste container in the mined geologic disposal system. Experiments were performed at a dose rate of 1-2 x 10⁴ rad/h, temperatures of 90 and 150°C, durations of 30 and 75 days, and dry and moist air (40% relative humidity at 90°C). Under these experimental conditions, only oxides of copper (cuprite and tenorite) were identified as corrosion products. No evidence of localized corrosion (e.g., pit formation) was found. General corrosion rates observed were between 0.1 and 3 mg/(cm²-yr) and increased with temperature. At 150°C, the corrosion rate increased by 50% due to the presence of the ionizing radiation. Comparisons between analytical results from the dry and moist air experiments indicated that radiolytic products of water are more effective oxidants than those of molecular oxygen.

In spent fuel studies for YMP, two sets of experiments are underway to investigate the reaction behavior of Zircaloy clad-UO₂ pellets (unirradiated) exposed to dripping groundwater in an oxidizing environment at 90°C. Tests have been in progress for 5.5 years with a Teflon support stand. A pulse of uranium release from the UO₂ solid, in conjunction with the formation of several uranyl oxide hydrate mineral phases across the sample surface, was observed after one or two years of testing. Thereafter, the uranium release decreased, and a second set of secondary phases was observed.

In groundwater-speciation work, photoacoustic spectroscopy is being employed to study the solubility and speciation of radionuclides in groundwater. This work has yielded information concerning complexant and temperature effects on the solubilities of important radionuclide species. Recent emphasis has been on the Pu(VI) hydrolysis in near-neutral aqueous systems. Absorption spectra of the initial hydrolysis products of Pu(VI) were obtained over a range of Pu(VI) concentrations (10⁻²-10⁻⁴ M) in 0.1M sodium perchlorate at room temperature. The data indicate that the extent of hydrolysis is greater and the contribution of polynuclear hydrolysis products is much more important than previously thought. The formation constant for the initial hydrolysis product of Pu(VI) was estimated. The influence of temperature (10-45°C) on the formation of the initial hydrolysis product of Pu(VI) was also determined. The results indicate that the temperature effect is much lower than estimates published in the literature.

Experimental effort is also underway to investigate the effect of ionizing radiation on the potential for gas generation in the Waste Isolation Pilot Plant (WIPP) site. In this report period, experiments were performed to determine the effect of gamma and alpha radiation (dose up to 367 Mrad) on two gas compositions: (1) 90% nitrogen and 10% carbon dioxide and (2) 90% nitrogen, 6.25% carbon dioxide, 2.5% hydrogen, and 1.25% oxygen. The two-component gas mixture was stable to radiolytic decomposition, with only minor amounts of oxygen and carbon dioxide generated from the carbon dioxide at absorbed dose greater than 40 Mrad. In the four-component gas mixture, nitrous oxide, carbon monoxide, ammonia, and NO_x were generated. Stability studies of Pu(VI) in WIPP brine were also completed. Plutonium concentrations [as Pu(VI) and Pu(V)] above 0.001M were stabilized for over two months as dissolved species in actual WIPP groundwater. This indicates that the plutonium was sufficiently stable as a dissolved species to proceed with planned work on gas generation due to dissolved actinides in WIPP brine.

I. APPLIED PHYSICAL CHEMISTRY

(C. E. Johnson)

The program in applied physical chemistry involves studies of the thermodynamic, thermophysical, and transport behavior of selected materials in environments simulating those of fission and fusion energy systems.

A. Behavior of Core-Concrete Mixtures under Accident Conditions (M. F. Roche)

1. Introduction

The objective of this research program is to provide experimental data on the onset of melting (solidus temperature) and the onset of solidification (liquidus temperature) for mixtures of urania and zirconia with four types of concrete: limestone, limestone-sand, basalt, and siliceous. Such mixtures are expected to occur during the molten core-concrete interaction (MCCI) phase of hypothetical severe reactor accidents at light-water reactors (LWRs) and pressurized-water reactors (PWRs). The MCCI phase is preceded by a series of other phases: loss of coolant, heatup and degradation of the reactor core (urania and its fission products, Zircaloy cladding, control rods, and structural materials), melting of the stainless-steel vessel, and collapse of the hot core debris and melted vessel onto the concrete basemat. A knowledge of the thermophysical properties of the solids, liquids, and gases that exist during each of these phases is crucial for understanding and modeling the consequences of an accident.

In the previous report in this series (ANL-91/42, Sec.I.A) we reviewed the state of knowledge of certain thermophysical properties of concretes and core-concrete mixtures at elevated temperatures. We concluded that experiments are needed to measure liquidus-solidus temperatures, viscosity, thermal conductivity, and foaming-emulsification characteristics of core-concrete mixtures. A three-year program plan and test matrix to investigate these properties were submitted to the Nuclear Regulatory Commission (NRC) in November 1989.

In this report period, we measured the liquidus and solidus temperatures of core-concrete mixtures using a differential thermal analysis (DTA) technique. The results are to be incorporated in the CORCON¹ thermal-hydraulic code, which is an integral part of the NRC's Source-Term Code Package.² At the present time, CORCON employs an ideal-solution model to compute liquidus and solidus temperatures for mixtures of concrete with UO_2 and ZrO_2 . Liquidus- and solidus-temperature curves are shown in Figs. I-1 and -2 for the three concrete types (limestone, limestone-sand, and basalt) that are currently treated as defaults in the CORCON code. These concretes are typical of those employed in reactors in the United States. We generated the curves in Figs. I-1 and -2, which differ only in the units for their abscissas (mol % concrete in Fig. I-1 and wt % concrete in Fig. I-2), from the appropriate subroutines in the CORCON code. At the time that the CORCON code was written, there were few data to support a realistic modeling of core-concrete mixtures; the properties of the concretes were either estimated (heats of melting) or approximated (initial melting-temperature ranges³ of the highly inhomogeneous concretes were assumed to be equivalent to their equilibrium solidus-liquidus temperature ranges). Thus, the curves shown in Figs. I-1 and -2 involved a number of untested assumptions.

Solidus temperatures of ~ 1140 and $\sim 2100^\circ\text{C}$ were reported by Skokan et al.⁴ for two concretes of unspecified composition, but labeled as "basaltic concrete" and "limestone concrete." For increasing concentrations of $\text{UO}_2\text{-ZrO}_2$ in mixtures with "basaltic concrete," the reported⁴ solidus temperature increased continuously up to $\sim 2550^\circ\text{C}$, which corresponds to the $\text{UO}_2\text{-ZrO}_2$ solid solution.

Fig. I-1. Liquidus-Solidus Curves from CORCON for Urania-Zirconia (mole ratio = 1.625:1) Mixtures with Three Concretes (compositions in mol %)

Fig. I-2. Liquidus-Solidus Curves from CORCON for Urania-Zirconia (mole ratio = 1.625:1) Mixtures with Three Concretes (compositions in wt %)

Solidus temperatures were also reported⁴ for mixtures of "limestone concrete" with either UO_2 or $\text{UO}_2\text{-ZrO}_2\text{-FeO-Cr}_2\text{O}_3$ (but not with $\text{UO}_2\text{-ZrO}_2$); these curves exhibited minima (~ 1550 to $\sim 1700^\circ\text{C}$) at about 50 wt % concrete. The data from Ref. 4 (and an assumption of ideal solid and liquid solutions) were later employed in the WECHSL code⁵ to approximate solidus and liquidus temperatures for mixtures of $\text{UO}_2\text{-ZrO}_2$ and siliceous concrete (siliceous concrete is the type employed in European reactors). Liquidus-solidus curves for mixtures of limestone, limestone-sand, and siliceous concretes with $\text{UO}_2\text{-ZrO}_2$ have been estimated by Cenerino⁶ using the limited data contained in Ref. 4; however, additional data are needed to test these estimates.

The ideal-solution assumption was shown to be a poor approximation during our earlier study⁷ of the vaporization of refractory fission products from core-concrete mixtures. The compositions of the four concretes (limestone, limestone-sand, siliceous, and basalt) that were employed in our vaporization study are presented in Table I-1. The limestone, limestone-sand, and basalt compositions

Table I-1. Results from Analyses of Concretes (in weight percent)

Constituent	Limestone Concrete	Limestone-Sand Concrete	Siliceous Concrete	Basalt Concrete
Na_2O	0.034	1.09	0.69	3.06
K_2O	0.40	0.57	1.41	1.41
MgO	7.44	9.62	0.70	3.03
CaO	42.96	26.02	13.47	12.51
SrO	0.030	0.031	0.023	0.046
BaO	0.007	0.032	0.021	0.07
Al_2O_3	1.91	3.48	4.04	11.26
SiO_2	7.13	28.27	68.99	52.80
TiO_2	0.097	0.143	0.81	1.35
V_2O_5	0.011	0.012	0.0	0.045
Cr_2O_3	0.006	0.009	0.007	0.016
MnO	0.014	0.054	0.028	0.137
Fe_2O_3	0.80	1.64	1.00	8.58
CoO	0.003	0.003	0.0	0.006
NiO	0.004	0.005	0.0	0.006
CuO	0.011	0.005	0.0	0.008
ZnO	0.005	0.007	0.0	0.024
ZrO_2	0.004	0.019	0.0	0.026
$\text{CO}_2\text{+H}_2\text{O}$	40.64	27.54	7.91	4.36
(CO_2)	(33.63)	(21.41)	(4.23)	----
Sum:	101.5	98.6	99.1	98.7

are similar to those employed in the CORCON code.¹ The major components (ignoring the CO_2 and H_2O , which are lost by decomposition of the concretes at temperatures below 1000°C) are CaO , SiO_2 , and MgO . Significant concentrations of Na_2O , K_2O , Al_2O_3 , TiO_2 , and Fe_2O_3 are also present, particularly in the basaltic concrete. If the ideal-solution assumption were valid, only one phase (the ideal solid solution) would form on cooling molten mixtures of these concretes with urania and zirconia. However, two distinct solid phases crystallized from the melt on cooling mixtures of $\text{UO}_2\text{-ZrO}_2$ with limestone-sand or siliceous concrete from a temperature of 2125°C .⁷ One phase was rich in urania and zirconia, and the other was rich in silica, calcia, and magnesia. (The basaltic-concrete phases were not determined, but are expected to be similar to the siliceous-concrete phases.) A mixture of the limestone concrete with

$\text{UO}_2\text{-ZrO}_2$, when cooled from a temperature of 1875°C , yielded not only these two solid phases (with the $\text{UO}_2\text{-ZrO}_2$ phase also containing a significant concentration of CaO) but also two others: MgO and CaZrO_3 .⁷ We concluded that there were only two oxide phases in this mixture at 1875°C : a solid oxide phase containing mainly urania, zirconia, and calcia, and a liquid oxide phase containing mainly calcia, zirconia, silica, and magnesia. The very small concentrations of magnesia and silica in the solid and urania in the liquid indicated non-ideal behavior.

We completed DTA measurements for each of the concretes shown in Table I-1 (limestone, limestone-sand, and siliceous) and mixtures of each (27.5 wt % concrete) with $\text{UO}_2\text{-ZrO}_2$. The mole ratio of UO_2 -to- ZrO_2 was 1.625:1. The experiments were designed to aid researchers in the ACE program⁸ at ANL in analyzing their large-scale MCCI experiments (now in progress). The DTA measurements, in addition to providing the desired liquidus-solidus temperatures, are also useful in determining the type of crystallization pattern. The presence of a single, broad peak in the DTA curve extending from the liquidus to the solidus temperature would suggest solid-solution formation (supporting phase studies would be needed to confirm this). A sharp peak in the DTA curve at the solidus temperature would suggest a eutectic. Multiple peaks in the liquidus-solidus temperature range would indicate that the course of crystallization included a number of phases crystallizing at different temperatures. Glass formation also has a unique DTA signature. An excellent discussion of crystallization paths in complex systems is given in the first volume of *Phase Diagrams for Ceramists*.⁹

2. Experimental

a. Development of DTA Apparatus

Our studies began in November 1989 with assembly of a high-temperature DTA apparatus needed for the experiments. A new diffusion pump, a Eurotherm programmable temperature controller, and a DTA head (which we designed and fabricated after receiving two defective DTA heads from a commercial source) were added to the Brew Model 1064-C High Temperature Vacuum Furnace (Richard D. Brew, Inc.) that had been used in our earlier transpiration studies⁷ of $\text{UO}_2\text{-ZrO}_2$ -concrete mixtures. The DTA head was designed to use the same tungsten cups as were used in the commercial DTA head. It consisted of two adjacent tungsten tubes (6-mm OD, 5-mm ID, 20-cm long) to which were physically attached tungsten-rhenium wires to form W-25 wt % Re vs. W-3 wt % Re thermocouples. The tubes extended half way into the cylindrical (7-cm dia x 20-cm height) furnace cavity and were supported in an alumina base that electronically isolated them. The small tungsten cups rested in the tops of the tubes; one cup held the sample, while the other contained an inert material, yttria (mp, 2410°C).

During the period November 1989-April 1990, we developed computer programs to be used in the thermodynamic analysis of data from the DTA experiments. The thermodynamic data base was an extension of one we had employed in earlier transpiration experiments.⁷ The necessary programming was completed to permit generation of a thermodynamic data file for each temperature of interest. We have continued to add data for important gaseous, liquid, and solid species during this research program (the data base now contains about 500 species). At this time, however, we have not tested the thermodynamic data base against our DTA experiments because the data base is incomplete. When it is complete, we will compare its output with the results from the DTA experiments and will report the results to the NRC. Researchers in France and England are also calculating solidus-liquidus temperatures for core-concrete mixtures from their thermodynamic data bases. We plan to compare our results with theirs.

By April 1990, assembly and testing of the DTA apparatus were completed, and a DTA experiment was conducted on a calcined limestone-concrete sample weighing 70 mg and held in the

small tungsten cup. (All concretes employed in our experiments were finely divided with the aid of a shatterbox to approximately -100 mesh and were then calcined in air at 1000°C in alumina crucibles.) A DTA peak was detected at about 1650°C on heating and cooling as the sample was cycled between 1200 and 2200°C, but the data were not reliable because the sample had completely vaporized from the tungsten cup during the DTA measurements (the furnace was being operated under vacuum, which accentuated vaporization). This experiment was repeated, but short circuiting between the sample and reference thermocouples prevented accurate temperature measurements, and the sample again vaporized completely. Examination of the thermocouples after the experiment revealed that they had become contaminated by the samples and had also become disconnected from the cup holders. At this point we decided to redesign the apparatus.

The redesigned apparatus was assembled for use with much larger samples (5 to 6 g of calcined concrete and about 20 g of the mixtures of concrete, UO_2 , and ZrO_2). These samples were held in covered molybdenum crucibles (9 cm³) that rested on a molybdenum-sheathed, beryllia-insulated W-26 wt % Re vs. W-5 wt % Re thermocouple obtained from Omega Engineering, Inc. The Brew furnace was controlled by an identical thermocouple placed above the crucible and connected to the Eurotherm programmable temperature controller. The voltage difference between the sample thermocouple and control thermocouple (sample TC - control TC) was amplified electronically and plotted to detect transitions occurring in the sample. In a preliminary test of this apparatus with a 5-g limestone-concrete sample, two peaks (one at ~1560°C and the other at ~1230°C) were detected on cooling from 2000 to 1200°C. However, after several cycles to temperatures as high as 2200°C, the 5-g sample had lost 1.2 g. Thus, the sample vaporization was still unacceptable. In addition, shunting of the thermocouples through their sheaths and the resulting coupling of their voltages caused severe temperature oscillations above 2000°C.

To reduce vaporization losses, Ar-3% H_2 gas (at a pressure of about 0.3 atm) was added to the furnace; vaporization losses were then reduced to less than 2% of the mass of concrete in subsequent experiments. To solve the problems of thermocouple shunting and coupling, a new electronic device was designed and constructed with independent, isolation amplifiers, which multiplied the millivolt-range thermocouple voltages (by a factor of about 100) prior to taking their difference. This effectively solved the problem of coupling between the sample- and control-thermocouple voltages and permitted DTA measurements to temperatures as high as 2400°C. The upper limit was dictated by the tendency of the beryllia insulation in the thermocouples to degrade at temperatures above 2400°C.

The thermocouple voltages, their amplified difference, and the voltage from an ambient-temperature thermocouple were stored by an MRL data logger (Esterline-Angus Instrument Corp.) and a VAX 6220 mainframe computer (Digital Equipment Corp.). These data were later used to produce the DTA curves. Thermocouple voltages were converted to temperatures using an equation recommended in Ref. 10. Baseline corrections were required because of the large difference in thermal mass indicated by the sample and control thermocouples. A slightly nonlinear baseline correction was applied, as needed, by fitting a cubic polynomial to the raw data (amplified difference signal vs. sample temperature). The relative positions and heights of the peaks were unaffected by these baseline corrections.

b. Experimental Procedures

With the redesigned apparatus, DTA experiments were first performed with the calcined concretes alone (limestone, limestone-sand, and siliceous). The programmed temperature cycling sequence consisted of cooling at 20°C/min, heating at 20°C/min, cooling at 10°C/min, and, finally, heating at 10°C/min over the chosen temperature range. Next, 72.5 wt % UO_2 - ZrO_2 (1.625:1

mole ratio of UO_2 to ZrO_2) was added to each concrete. For instance, a mixture of 12.7 g UO_2 and 3.6 g ZrO_2 was added to the 6.2-g sample of siliceous concrete. The weight fractions of urania, zirconia, and concrete in these mixtures were chosen to be identical to those in an ACE large-scale MCCI experiment employing siliceous concrete as a basemat.⁸ The DTA experiments were then successfully completed on each of the three UO_2 - ZrO_2 -concrete mixtures with the same programmed sequence as described above.

The UO_2 - ZrO_2 mixtures added to the three concretes were individually prepared for each experiment from $\text{UO}_{2.25}$ (< 150 ppm total impurities) and ZrO_2 (Spectrographic Grade, 99.95% minimum assay, Atomergic Chemetals Corp.). The appropriate weights of $\text{UO}_{2.25}$ and ZrO_2 powders were mixed together in a molybdenum crucible and treated for 8 h or more in flowing He-6% H_2 at 1550°C, while the water concentration in the outlet gas stream was monitored with a thin-film alumina hygrometer (Model 550, Panametrics, Inc.) to ensure that the reduction process was essentially complete (<100 ppm H_2O). Weight-loss measurements indicated that the $\text{UO}_{2.25}$ in each mixture was reduced to $\text{UO}_{2.00}$. The above process sintered the gray mixture of finely divided powders into a reddish-brown cylindrical pellet of UO_2 - ZrO_2 , which could be conveniently added to each concrete sample.

3. Results and Discussion

a. Limestone Concrete and its Mixture with Urania-Zirconia

The DTA curves for a calcined limestone-concrete sample (5.0 g) are presented in Fig. I-3. The two lower curves are for heating, and the two upper curves are for cooling. Three very broad peaks are seen in the 10°C/min heating curve. These are centered at approximately 1500, 1900, and 2250°C. The onset of melting (or solidus temperature), which is taken from the first break detected in the

Fig. I-3. Differential Thermal Analysis of Limestone Concrete (TC = thermocouple readings)

10°C/min heating curve, is 1222°C. At least three broad peaks and two narrow peaks (at approximately 1565 and 1220°C) are also seen in the 10°C/min cooling curve. These narrow peaks were the only ones that were detected in our preliminary experiments with the limestone concrete (Sec.I.A.2.a). The onset of crystallization (liquidus temperature) is taken from the first break detected in the 10°C/min cooling curve at 2304°C.

The limestone-concrete composition (see Table I-1), after calcining to remove CO₂ and H₂O, may be approximated as 71 wt % CaO, 12 wt % SiO₂, 12 wt % MgO, and 5 wt % other ingredients (mainly Al₂O₃). Ternary sections of the quaternary system CaO-SiO₂-MgO-Al₂O₃ are available for 10 wt % MgO⁹ and for 5 wt % Al₂O₃.¹¹ These sections indicate a solidus-liquidus temperature range of 1235°C to ~2250°C for a mixture containing 71 wt % CaO, 12 wt % SiO₂, 12 wt % MgO, and 5 wt % Al₂O₃. This range is in reasonable agreement with our solidus-liquidus temperature range of 1222 to 2304°C for the more complex limestone concrete.

To the limestone-concrete sample (5.0 g) was then added 10.4 g UO₂ and 2.9 g ZrO₂. The DTA curves for this sample are shown in Fig. I-4. The solidus temperature is taken from the first break detected in the heating curves and is approximately 1247°C. There is a large peak beginning at 2130°C and extending well beyond 2350°C at the 10°C/min heating rate; this peak is associated with melting of a UO₂-ZrO₂-CaO solid solution. Phase diagrams have been published for the UO₂-CaO⁹ and ZrO₂-CaO¹² systems. From these phase diagrams and the DTA curves in Fig. I-4, we estimate a liquidus temperature of greater than 2450°C for the UO₂-ZrO₂ mixture with limestone concrete. The DTA curves could not be extended to that temperature; the thermocouples (beryllia-insulated, molybdenum-sheathed W-Re alloys) failed when we attempted to do so.

Fig. I-4. Differential Thermal Analysis of Urania, Zirconia, and Limestone Concrete

The crystallization path involves a number of phases. In our earlier study,⁷ a CaO- UO_2 - ZrO_2 solid solution, CaZrO_3 , MgO, and a CaO-MgO- SiO_2 phase were identified in a sample containing limestone concrete, UO_2 , and ZrO_2 . As noted in the introduction, the ideal-solution model currently employed in CORCON is a poor approximation for this system. Our measured solidus-liquidus temperature range exceeds 1200°C , while the range in CORCON is about 500°C at 27.5 wt % concrete (see Fig. I-2).

b. Limestone-Sand Concrete and its Mixture with Urania-Zirconia

The DTA curves for a limestone-sand concrete sample (4.9 g) over a temperature range of 1000 to 1600°C are shown in Fig. I-5. Solidus and liquidus temperatures are obtained from the $10^\circ\text{C}/\text{min}$ heating and cooling curves and are 1120°C and 1295°C , respectively. Another sample of this concrete was tested to temperatures as high as 2000°C ; no higher temperature peaks were detected. The composition of the calcined limestone-sand concrete (see Table I-1) may be approximated as 37 wt % CaO, 40 wt % SiO_2 , 13 wt % MgO, 7 wt % Al_2O_3 (combining Al_2O_3 and Fe_2O_3), and 3 wt % other ingredients (mainly Na_2O). The Na_2O -CaO-MgO- Al_2O_3 - SiO_2 system has been studied in some detail;¹¹ it contains compositions similar to that of the limestone-sand concrete. The reported phase diagrams for this system show that a solidus-liquidus temperature range of 1120 to 1295°C is reasonable for the limestone-sand concrete.

Fig. I-5. Differential Thermal Analysis of Limestone-Sand Concrete

The DTA curves for the mixture of limestone-sand concrete (4.9 g), urania (10.2 g), and zirconia (2.9 g) are shown in Fig. I-6. The solidus temperature is 1087°C , as determined from the

Fig. I-6. Differential Thermal Analysis of Urania, Zirconia, and Limestone-Sand Concrete

first break detected in the 10°C/min heating curve. The onset of a very large peak occurs at this temperature on cooling and suggests the possibility of a eutectic. The liquidus temperature is given in Fig. I-6 as greater than 2365°C because the onset of the broad peak, which is centered at about 2150°C and extends down to about 2000°C on cooling, is above 2365°C. This peak is associated with crystallization of a $\text{UO}_2\text{-ZrO}_2\text{-CaO}$ solid solution.

c. Siliceous Concrete and its Mixture with Urania-Zirconia

The DTA curves for the siliceous concrete sample (6.2 g) over a temperature range of 900 to 1550°C are shown in Fig. I-7. No crystallization peaks were detected; instead, the sample exhibited a glass transition extending from 1130 to 1250°C. These temperatures are not equilibrium solidus and liquidus temperatures. Skokan et al.⁴ reported the "softening temperature" of this concrete to be ~1140°C and also noted that this softening temperature is more relevant than the thermodynamic crystallization temperature because the silicate-type melt solidifies to a glass. Our 1130°C value for the onset of the glass transition is in good agreement with the previously reported value of 1140°C. Another sample of this concrete was tested to temperatures as high as 2000°C; no higher temperature peaks were detected.

The composition of the siliceous concrete, after calcining, may be approximated as 15 wt % CaO, 77 wt % SiO_2 , and 8 wt % other ingredients (mainly Al_2O_3). A ternary diagram for the

Fig. I-7. Differential Thermal Analysis of Siliceous Concrete

$\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ system has been published.⁹ The equilibrium crystallization temperatures for 15 wt % CaO , 77 wt % SiO_2 , and 8 wt % Al_2O_3 are 1170°C (solidus) and -1520°C (liquidus). Thus, the glass transition of the siliceous concrete occurs over a smaller temperature range (1130 to 1250°C) than the equilibrium temperature range (1170 to -1520°C).

To the siliceous-concrete sample (6.2 g) was then added 12.7 g UO_2 and 3.6 g ZrO_2 . The DTA curves for this mixture over the range 900 to 2300°C are shown in Fig. I-8. The onset of melting is tentatively assigned a value of 1134°C (very close to the value for the siliceous concrete); the 10°C/min heating curve is labeled to indicate a glass transition extending from this temperature to 1322°C . Note that the DTA curves in the 1100 to 1500°C temperature range are similar in this figure and Fig. I-7. However, a minor peak (beginning at $\sim 1005^\circ\text{C}$) precedes the region labeled as a glass transition, and we cannot exclude the possibility that it represents melting of some crystalline material in the sample.

In Fig. I-8, the liquidus temperature is assigned a value of 2276°C from the onset of the first peak detected on cooling at 10°C/min . The large, complex peak centered at $\sim 2100^\circ\text{C}$ and extending to $\sim 2300^\circ\text{C}$ on heating is believed to be caused by fusing of the $\text{UO}_2\text{-ZrO}_2$ solid-solution phase with the liquid silicate phase. There are very sharp "reverse" peaks embedded within the higher temperature peaks in Fig. I-8. The average temperature of these "reverse" peaks is $\sim 2035^\circ\text{C}$ at a rate of 10°C/min . From an analysis of the sample- and control-thermocouple voltages, these "reverse" peaks were found to be associated with the control thermocouple. A possible mechanism is contamination of the molybdenum sheath of the control thermocouple by reaction of silicon monoxide gas from the sample to form Mo_3Si (the $\text{Mo-Mo}_3\text{Si}$ eutectic occurs at 2025°C).¹³

Fig. I-8. Differential Thermal Analysis of Urania, Zirconia, and Siliceous Concrete

Our earlier studies⁷ indicated that a $\text{UO}_2\text{-ZrO}_2$ phase and a silicate phase were present on cooling mixtures of UO_2 , ZrO_2 , and siliceous concrete. A ternary diagram for the $\text{UO}_2\text{-ZrO}_2\text{-SiO}_2$ system is not available, but our measured liquidus temperature of 2276°C for the mixture of $\text{UO}_2\text{-ZrO}_2$ with siliceous concrete appears to be reasonable when compared with the liquidus temperatures in the two binary systems: $\text{SiO}_2\text{-UO}_2$ ¹¹ and $\text{SiO}_2\text{-ZrO}_2$.¹¹

d. Liquidus-Solidus Curves

The liquidus-solidus temperatures from our measurements are plotted in Fig. I-9; the values for $\text{UO}_2\text{-ZrO}_2$ (at 0 wt % concrete) were taken from the published phase diagram.¹² Also shown in Fig. I-9 are hypothetical liquidus-solidus curves that assume limited solubilities between the urania-zirconia-calcia phase and the concretes; these curves are not calculated from any theoretical model. The limited-solubility assumption, which is supported by our earlier phase studies,⁷ is more reasonable than the solid-solution assumption currently employed in the CORCON code. The solidus-liquidus temperature intervals shown in Fig. I-9 are hundreds of degrees greater than the ideal-solution values shown in Fig. I-2. At 27.5 wt % concrete, our measured values differ by over 1200°C , while the differences in CORCON range from 500 to 750°C .

Additional data (at approximately 10, 60, and 85 wt % concrete) are needed to refine the hypothetical liquidus-solidus curves shown in Fig. I-9. It is possible, for instance, that eutectic-type liquidus curves will be found for mixtures of either limestone concrete or limestone-sand concrete with $\text{UO}_2\text{-ZrO}_2$ since CaO forms eutectics with both UO_2 ⁹ and ZrO_2 .¹²

Fig. I-9. Liquidus-Solidus Data and Hypothetical Curves for Urania-Zirconia (1.625:1 Mole Ratio) and Concrete Mixtures. Arrow on top of symbols indicates "greater than." Data on 0 wt % concrete are for $\text{UO}_2\text{-ZrO}_2$ alone.

B. Thermophysical Property Studies (L. Leibowitz and R. A. Blomquist)

Measurements and analyses are being performed to provide needed information on the thermodynamic and transport properties of Integral Fast Reactor (IFR) fuels. Current increased interest in metallic fuel for nuclear reactors has prompted a re-examination of the thermodynamic and transport properties of alloys containing U, Pu, and Zr. We previously reported on an assessment of the U-Zr phase diagram.¹⁴ We have performed a similar evaluation of the Pu-U and Fe-U systems. Also studied was the behavior of minor actinides in IFR fuel. The results are summarized below.

1. Plutonium-Uranium System

A phase diagram for the Pu-U system has been published by Peterson and Foltyn.¹⁵ Aside from the phase diagram itself, relatively little thermodynamic data exist for the Pu-U system. What is available has been summarized by Chiotti et al.¹⁶ and has been previously discussed by us.¹⁷ The data appear to be so imprecise and their interpretation involves so many assumptions that they should be viewed cautiously and, therefore, were not included in our calculation. The general methods used in our analysis are discussed in our work on the U-Zr system¹⁴ and have been well documented in the literature.^{18,19} In general, these involve the critical evaluation and analysis of all relevant thermodynamic data for the system to obtain mathematical expressions for the thermodynamic properties of all phases as functions of composition and temperature.

The Gibbs energies of transition for pure Pu and U are required in our analysis. Data for the solid-state transitions were taken from a review by Oetting et al.²⁰ The melting transition for uranium presented a problem, which was discussed previously.^{14,17} In brief, the generally accepted value for the enthalpy of fusion (ΔH_f) of uranium of 2185 cal/mol at the melting point²⁰ appears to be inconsistent with

the solidus-liquidus in the Pu-U system.²¹ Another value for ΔH_f was obtained by Savage and Seibel,²² 2900 cal/mol, which agrees much better with the U-Pu phase diagram. This problem was resolved by us earlier^{14,17} in favor of the ΔH_f of uranium recommended by the International Atomic Energy Agency.²⁰ The result is that, while this ΔH_f agrees reasonably well with the Pu-U liquidus, our calculated solidus is somewhat higher. Ellinger et al.²¹ also reported difficulties in measuring the solidus.

The Pu-U phase diagram given by Peterson and Foltyn¹⁵ is shown in Fig. I-10, which we have assessed and modified. As can be seen from the diagram, solubility of U in the Pu phases is very low, and we have treated these as Henrian solid solutions. Although the solubility of Pu in U(α) and U(β) ranges up to about 20 at. %, we have found that these phases could also be treated satisfactorily as Henrian solid solutions. The two body-centered cubic phases, Pu(ϵ) and U(γ), form a solid solution, which we will refer to as the ϵ -phase. Two intermediate phases, ξ and η , also exist over fairly wide composition and temperature ranges. Despite the complexity of the system, we were able to describe it using sub-regular models.

Fig. I-10. Published Plutonium-Uranium Phase Diagram from Peterson and Foltyn.¹⁵ (Reproduced with permission.)

Henry's law coefficients were calculated for the Pu and U phases for the appropriate measured solubilities. The solubility of uranium in Pu(ϵ) was considered to be negligible. For each of the other phases, the solvent was considered ideal (as in the case in Henrian solutions).

The intermediate η and ξ phases presented the greatest difficulties in performing our assessment. Gibbs energies of hypothetical pure Pu(η), U(η), Pu(ξ), and U(ξ) were required.

Extrapolation of the appropriate phase boundaries to pure Pu and pure U provided us with some guidance for estimation of hypothetical transition temperatures. As can be seen from Fig. I-10, however, there is no reasonable way to extrapolate the η - ξ two-phase field to the plutonium edge. We took this to indicate some inconsistency in that portion of the diagram. Other regions of the diagram were also used to help determine parameters for the η and ξ phases. For example, the wide two-phase $\xi + U(\infty)$ field seems to be well supported experimentally. Because the boundaries are essentially parallel, the entropy of the $\xi \rightarrow U(\infty)$ transition for both pure Pu and pure U was taken to be zero. The region of the diagram containing the two invariants at 560 and 590°C was crucial in determining the choices made for the thermodynamic properties of the η and ξ phases.

Our calculated Pu-U phase diagram is shown in Fig. I-11 and, in general, is similar to the diagram of Peterson and Foltyn¹⁵ shown in Fig. I-10. As discussed above, our solidus is higher than that in the literature because of the value chosen for the ΔH_f of uranium. The η and ξ fields are consequently shifted as well. The minimum in the calculated solidus-liquidus appears at 626°C and about 10 at. % U, compared with the Ellinger et al. values of 610°C and 12 at. % U.²¹ The absolute positions of the $\eta + \xi$ two-phase field could have been preserved. However, this would have produced a very broad ϵ solid-solution field, for which there is no evidence. It seemed more reasonable, particularly in view of the reported difficulties in measuring the liquidus, to preserve the relative positions of the $\eta + \epsilon$ and liquid + ϵ boundaries, rather than their absolute positions.

Fig. I-11. Calculated Plutonium-Uranium Phase Diagram

The region shown in Fig. I-10 between 560 and 705°C contains three invariants. Our calculated eutectoid at 702°C agrees well with Fig. I-10. The calculated two-phase $\eta + U(\beta)$ field differs from that shown in Fig. I-10, but there are essentially no data for that area. At 590°C we could not maintain the broad two-phase $\xi + U(\infty)$ field and also produce a peritectoid. We chose to maintain the $\xi + U(\infty)$ region because it appeared to be well supported experimentally and to modify the transition at 590°C to produce a eutectoid. However, the calculated ξ - η - $U(\beta)$ eutectoid, which appears at 590°C, is not in serious disagreement with the experimental data. Also, the calculated ξ - $U(\beta)$ - $U(\infty)$ eutectoid at

560°C is in good agreement with Fig. I-10. In general, only a relatively small number of experimental points need be rejected in the calculated diagram.

Overall, our calculated diagram is a reasonable representation of the available data. One of the key points of disagreement involves the calculated solidus and the ΔH_f of uranium. Our calculated phase diagram will be used to help guide further measurements on the Pu-U system, which could clarify areas of concern.

2. Iron-Uranium System

Experimental and analytical work is continuing on the Fe-U system to gain better understanding of the phase relations involved in fuel-cladding systems. Differential thermal analysis studies of the Fe-U system have essentially been completed, and scanning electron microscope examination of a selected set of residues has been performed. In Fig. I-12 is shown our measurements (solid points) along with our calculated results (dotted line) incorporated in the Fe-U phase diagram provided by Massalski.²³ As can be seen, our calculated results are in better agreement with our measurements than is the published diagram. Based on our new data, a refined calculation is being performed, and the results of this work will be published.

Fig. I-12. Uranium-Iron Phase Diagram of Massalski²³ along with Data from this Work

3. Minor Actinide Systems

In several IFR fuel cycle concepts under consideration, the recycled fuel could contain concentrations of the so-called minor actinides, which would have an effect on the fuel properties and behavior. We conducted a preliminary analysis of metallic fuel system containing the minor actinides.

It is important to recognize that the actinides are not simple analogs of the lanthanides. In the lanthanides, the 4f electrons are highly localized and interact little with electrons in the 5d shell. In

contrast, in the "light" actinides, elements from Th through Pu, the 5f electrons interact strongly with 6d and 7s states, thus forming a series more akin to the 3d transition metals than to the lanthanides. For the "heavy" actinides beginning with americium, the 5f electrons are more localized, and this group behaves somewhat more as a lanthanide-like series. As a result, a great many properties of the actinide elements change markedly between Pu and Am.^{20,24,25}

Crystal structure and phase relations also change notably as one traverses the actinide series. The crystal structure that exists at the melting point is body-centered cubic (bcc) in the lighter actinides but changes after plutonium to face-centered cubic. A bcc phase expected to exist for americium has evidently not been found.²⁵ The heavier actinides, beginning with americium, also show a double hexagonal close-packed structure, which is not seen in the lighter elements of the series. These differences are also shown in phase diagrams. There is a broad solid-solution field below melting, which is bcc for Np-Pu and fcc for Am-Pu. These effects could be elaborated upon but the main point is clear: properties of actinide-containing alloys can change markedly in going from Pu to Am. If IFR fuel alloys are to contain significant amounts of minor actinides, particularly Am or Cm, careful study will be needed on the behavior and properties of this fuel.

C. Support Studies for New Production Reactor

The DOE initiated the New Production Reactor (NPR) Program to plan, design, and construct safe and environmentally acceptable new reactor capacity for an assured supply of tritium. We are supporting this program by performing experimental and calculational studies on an NPR that is a heavy water reactor (HWR-NPR).

1. Fission Product Release from HWR-NPR Fuel and Targets (P. E. Blackburn, A. K. Fischer, and S. W. Tam)

This effort consists of two parts: (1) development of thermodynamic models to predict the release of fission products and tritium from Al-U fuel and Al-Li targets in a severe accident with the HWR-NPR and (2) experimental measurements using transpiration and mass spectrometry, along with results of experiments planned in several other programs, to verify the thermodynamic predictions. The modeling will include (1) initial release from fuel during melting, (2) release from targets during melting, (3) longer-term release from melts as a function of temperature, and (4) release from molten aluminum during high-temperature oxidation or burning. The work will encompass thermodynamic analyses using the SOLGASMIX computer code to establish vapor species and their pressures for fuel only, target only, and fuel/target mixtures. The calculations should cover D₂O steam reaction with fuel and/or target. In the experiments, mixtures of Al-U and Al-Li with selected fission products will be tested in flowing steam-hydrogen-helium mixtures at temperatures up to 1700 K.

a. Preliminary Analysis for Experimental Work

Preliminary analysis has shown that, because fission product iodine and cesium have such high partial pressures, difficulty may be experienced in dissolving them in aluminum. Table I-2 gives the melting and boiling points of the three major elements (Al, U, Li) and the simulated fission products. As indicated by Table I-2, elemental cesium and iodine will vaporize before aluminum melts as the temperature is raised from room temperature. The pressure of cesium is almost an atmosphere at the melting point of aluminum (932 K). Iodine pressure is much higher, boiling at 458 K. Since the vapor pressures of iodine and cesium are too high, these two elements must be added to the fuel, target, and fission product mixture/melt as compounds with lower vapor pressures. Table I-3 lists melting points, boiling points, and enthalpy of formation at 298 K ($\Delta H_{f,298}$) per iodine atom of the fuel, target, and

simulated fission product iodides. The enthalpy of formation is a measure of the iodide stability. It is apparent that iodine may be introduced as LiI, CsI, SrI₂, BaI₂, or LaI₃ without vaporizing before the aluminum melts. With the exception of CsI, we have not found any stable compounds of cesium with the other elements in the system. To maintain the cesium-to-iodine ratio of about 18 produced by fission of ²³⁵U, cesium may be introduced as CsOH.

Table I-2. Melting and Boiling Points for Selected Elements

Element	Ref No.	Temp., K	
		Melting	Boiling
Iodine	26	387	458
Cesium	27	302	952
Tellurium	27	723	1282
Lithium	26	454	1620
Strontium	27	1041	1650
Barium	27	1002	2171
Aluminum	27	933	2767
Lanthanum	27	1193	3730
Uranium	27	1405	4407
Ruthenium	27	2523	4423
Molybdenum	27	2892	4919

Table I-3. Melting and Boiling Points and Enthalpy of Formation ($\Delta H_{f,298}$) for Fission Product Iodides and Cesium Halides

	Ref No.	Temp., K		$\Delta H_{f,298}$, kcal per I atom
		Melting	Boiling	
Iodine	26	387	458	
AlI ₃	26	464	658	-24.6
UI ₄	27	779	1030	-25.6
LiI	26	742	1449	-64.6
CsI	26	894	1553	-80.5
SrI ₂	28	811	2181	-67.0
BaI ₂	28	985	2340	-72.4
LaI ₃	27	1051	1745	-52.3

b. Determination of Compatible Container Materials

We conducted a search for container materials compatible with Al-U fuel, Al-Li target, and simulated fission products at temperatures as high as 1700 K. These materials will be used in experiments to determine the extent of fission product release expected in a severe accident. We have considered oxides, carbides, borides, and nitrides. The enthalpies of formation for the fuel, target, and fission product oxides are given in Table I-4. Aluminum oxide appears to be compatible with the fuel elements (Al and U), target elements (Al and Li), and all fission products included in this study. Graphite is unsatisfactory for container material. Aluminum and uranium form stable carbides: Al₄C₃, UC, U₂C₃, UC_{1.9}, and UC_{1.93}. Strontium, barium, and molybdenum react with graphite to form SrC₂, BaC₂, MoC, and Mo₂C. Some of the other elements may also form carbides. The enthalpies of formation for the

carbides are listed in Table I-5. Boron nitride is the most stable boride found, as shown by the data in Table I-6. However, as shown by Table I-7, AlN, LaN, and UN are more stable than BN. Since most of the experiments will be carried out in a steam, neither the borides nor the nitrides will be stable enough to resist steam oxidation.

Since aluminum oxide is compatible with the steam environment and aluminum oxide crucibles and tubes are readily available, it was chosen as the container material. One disadvantage of aluminum oxide is the problem of distinguishing between condensed aluminum and the aluminum in the oxide tube. In cases where this is necessary, we will use another container material.

Table I-4. Enthalpies of Formation for Fuel, Target, and Fission Product Oxides

Oxides	Ref No.	$\Delta H_{f,298}$, kcal per O atom
Cs ₂ O	27	-75.9
TeO ₂	27	-38.6
Li ₂ O	27	-143.1
SrO	27	-141.5
BaO	26	-132.3
Al ₂ O ₃	27	-133.3
La ₂ O ₃	26	-142.9
UO ₂	26	-129.7
RuO ₂	27	-36.4
MoO ₂	26	-70.3
B ₂ O ₃	27	-101.2

Table I-5. Enthalpies of Formation for Fuel, Target, and Fission Product Carbides

Carbides	Ref No.	$\Delta H_{f,298}$, kcal per C atom
SrC ₂	27	-10.1
BaC ₂	27	-8.9
Al ₄ C ₃	26	-16.5
UC	26	-23.2
Mo ₂ C	26	-11.0

Table I-6. Enthalpies of Formation for Fuel, Target, and Fission Product Borides

Borides	Ref No.	$\Delta H_{f,298}$, kcal per B atom
BI ₃ (g)	26	-17.0
BN	26	-60.3
AlB ₂	27	-8.0
UB ₂	27	-19.7

Table I-7. Enthalpies of Formation for Fuel, Target, and Fission Product Nitrides

Nitrides	Ref No.	$\Delta H_{f,298}$, kcal per N atom
Li_3N	26	-47.2
Sr_3N_2	27	-46.8
Ba_3N_2	27	-40.8
AlN	27	-76.0
LaN	27	-71.5
UN	26	-70.4
Mo_2N	26	-16.6
BN	26	-60.3

c. Experimental Design for Transpiration Studies of Fission Product Release

Prediction of release of fission products from core-melt accidents in the HWR-NPR requires information on the kinetic, transport, and thermodynamic factors. The transpiration technique is uniquely suited for this work because all aspects of the release and transport process can be investigated. The transpiration technique involves passing a gas at a known flow rate over the material to be studied, and measuring the amount of material volatilized. Experimental studies are performed as functions of flow rate, temperature, and condensed phase composition and provide data on material behavior.

Our transpiration system consists of a closed-end tube in which resides a crucible to hold the sample material. Gas is passed down the tube, and an inner collector tube is positioned so that the gas flows over the sample and up through the collector tube. As the gas flows up the inner tube, a thermal gradient causes volatilized material to condense. At the end of the experiment, the collector tube is removed and the condensed material is analyzed. In some experiments, the sample will be held in a crucible which will be suspended from a vacuum balance to measure the rate of vaporization during the experiment. This will allow us to measure the pressures of the most-volatile species. Partial pressures of less-volatile species can be determined from analysis of the condensed material.

The first phase of the program involves construction of the transpiration system, initial testing, and benchmarking. Initial testing will involve measurement of the vapor pressure of pure aluminum to verify that our apparatus is providing reliable data. Following this, measurements will be performed on mixtures of aluminum and Al-U with selected fission product elements. These mixtures will be studied from about the melting point of aluminum, 932 K, to 1700 K. Relevant fission product concentrations will be used in these mixtures. The flow rate needed to achieve saturation of the flowing gas with the vapor will be determined. From the measured vapor pressure of the fission product, its activity coefficient in the solution can be calculated. By raising the flow rate, information on the liquid-phase diffusion control for release of a given fission product from the melt can be obtained. Following calibration and initial testing, transpiration measurements will be performed in flowing steam-hydrogen-helium gas mixtures. In a steam-containing environment, formation of a surface layer of aluminum oxide will be expected on the molten aluminum and aluminum alloys. Transport of vapor species through this surface layer will be important in determining the vaporization rate.

d. SOLGASMIX Calculations on Fuel-Target-Fission Product System

The initial system for which we assembled data and performed SOLGASMIX calculations consists of U-Al fuel, the Li-Al target, and selected fission products (Cs, I, Te, and Ba) at

1000 and 1700 K. This is a metallic system without oxygen. The thermodynamic properties were taken from the JANAF tables,²⁸ where possible, and from Barin and Knacke otherwise.²⁶ The temperature of 1000 K was selected because it is slightly above the melting point of the intermetallic compound, LiAl, and the temperature of 1700 K is a little higher than the 1673 K (1400°C) considered to be the upper temperature of interest.

The amounts of the elements in the initial system were determined from information provided by J. E. Matos (ANL Reactor Analysis Division) to be 19.7 g-atoms uranium, 30.0 g-atoms lithium, and 1841 g-atoms aluminum. The system is extremely aluminum-rich, and the SOLGASMIX code had difficulty reaching equilibrium at 1000 K, but was able to do so when the amount of aluminum was reduced by a factor of ten. This was still a very aluminum-rich system. However, the impact on the calculated fates of the fission products is not expected to be significant because the important species are not aluminum compounds. The SOLGASMIX code had no difficulty in handling the 1700 K calculations with the full amount of aluminum.

The condensed phases were taken to be two in number, an U-Al phase and Li-Al phase. For the U-Al phase, the parent element species were Al and UAl_4 at 1400 K and Al and UAl_2 at 1700 K. Although the phase diagrams might suggest that these aluminum-rich systems are far removed from the indicated intermetallic compounds, they were included in our calculations to make some allowance for attractive interactions between Al and U, rather than just to treat the U as a simple solute in Al. This is a point for future work to clarify. For the Li-Al phase, data for the intermetallic compound, LiAl, were found only up to the melting point (966 K) and were extrapolated slightly to 1000 K. For the 1700 K calculation, the aluminum-rich system was treated as a solution of Li in Al. More careful consideration of the best way to treat Li-Al at high temperature should also be a future effort.

In the calculations, UTe was included as a species in the condensed phases, although no data for it were in the consulted literature sources. Instead, data for USe were used. The importance of UTe that emerged (certainly at 1000 K, though less so at the higher temperature) suggests that more detailed search for information or experimental efforts to derive it would be useful future work.

To summarize the results from the SOLGASMIX calculations, the results are grouped by fission product element.

Cesium. At 1000 K, the elemental species, Cs(g), is the dominant cesium carrier in the gas phase. Its vapor pressure of 4×10^{-4} atm is about four orders of magnitude greater than that of CsI. However, in the system considered, the quantity of this cesium in the gas phase is only about 0.001% of the cesium in the system. At 1000 K, about 94% of the system cesium is distributed in the elemental form in the two condensed phases. Another 5% is dissolved as CsI.

At 1700 K, the gas-phase species that predominantly carries cesium is Cs(g) at a partial pressure of 8×10^{-4} atm, amounting to about 0.01% of the cesium in the system; the amount of CsI is four orders of magnitude smaller. Essentially 100% of the cesium is distributed as the elemental solute cesium between the two condensed phases. Only about 0.08% is distributed as CsI.

Iodine. At 1000 K, the strongest iodine-bearing species is CsI with a vapor pressure of about 2×10^{-8} atm; therefore, the iodine content of this phase is regarded as negligible. The condensed phases at 1000 K contain 91% of the system iodine as CsI and 8% as LiI.

At 1700 K, LiI(g) is the strongest contributor of iodine to the gas phase, with a partial pressure of 4×10^{-6} atm, about two orders of magnitude greater than that for CsI(g) or AlI(g). Its quantity

is still small, however, about 0.001% of the system's inventory. At 1700 K, LiI distributed in the condensed phases accounts for 99% of the iodine in the system; CsI accounts for 1.1%.

Tellurium. The gas phase at 1000 K contains Te(g) at 2×10^{-26} atm as the "strongest" tellurium species. Tellurium is absent from the gas phase. Also, 100% of the system tellurium is contained in the U-Al phase as UTe; 0.004% is in the Li-Al phase as Li_2Te .

At a Te(g) partial pressure of 2×10^{-11} atm and temperature of 1700 K, the tellurium in the gas phase is still negligible. Also, 5% of the tellurium is dissolved in the U-Al phase as UTe and 95% is dissolved in the Li-Al phase as Li_2Te .

Barium. At 1000 K, Ba(g) at 7×10^{-9} atm makes the barium level in the gas phase negligible. Also, barium is dissolved in elemental form, with 39% in the U-Al phase and 61% in the Li-Al phase.

At 1700 K, the Ba(g) partial pressure is about 10^{-6} atm, and still probably negligible. At 1700 K, barium is distributed in the elemental form between the U-Al phase (39%) and the Li-Al phase (61%), the same distribution calculated for the lower temperature.

Several conclusions emerged from the calculations for 1000 and 1700 K. One is that LiI is important both as a gaseous species and in the condensed phases. Tellurium is bound by uranium as UTe and is retained in the condensed phases, especially at the lower temperature. Iodine is essentially not bound as UL_3 or AlI_3 either in the gas or condensed phases. Also, AlTe is significant in the gas phase.

In the available time, no inquiry was made into the ternary system, U-Al-Li. This needs to be done. It will also be important to determine the immiscibility of the U-Al and U-Li systems so that the most realistic calculations of distributions of fission products may be made. Experimental exploration of the overall features of the phase diagram could be pursued by thermal analysis or quench-and-analyze techniques. A further question to be examined is whether it is more realistic to group the salt-like species (e.g., LiI, CsI, BaI_2 , Li_2Te) as a separate phase rather than as solutes in the metallic phases.

2. Containment Habitability

(S. W. Tam, A. K. Fischer, and B. Karr)

The principal objective of this effort in the HWR-NPR Program is to provide an analytic tool for meeting the detritiation requirements in the event of accidental releases of tritiated species into the HWR-NPR containment environments, given a particular release and subsequent removal scenario. A critical parameter is the time required to reduce the activity within the containment structure to a level that is acceptable for human entry (for the purpose of repair, maintenance, etc.) without elaborate protective measures. The reactor containment is composed of different compartments. We are developing a detailed model for detritiation in an individual compartment. This single-compartment model will be integrated into a multi-compartment effort for the total containment environment, which is being carried out by Westinghouse Savannah River Laboratory.

Because of the oxidizing containment environment, the tritiated species in the event of leakage is expected to be dominated by DTO. This is in contrast to the fusion reactor environment, where both HT and HTO species are expected.^{29,30} Furthermore, in the present detritiation model for fusion reactors, detailed consideration is given to the temporal and spatial evolution of the penetration profile of leaked species (e.g., DTO and D_2O) into the structural components, which are assumed to consist of

concrete walls with a barrier/coating on its inner surface (i.e., the surface that is facing the containment chamber). For the results that follow, the barrier/coating is considered to be epoxy paint. However, the model could easily be used for barrier of other materials, e.g., steel, provided the appropriate materials characteristics such as diffusion coefficient and adsorption rate constant are employed.

We developed a Dynamic Tritium Release and Analysis Model (DTRAM), which simulates the detritiation processes in the event of either chronic or burst releases of tritiated species into the containment structure of the HWR-NPR. The model incorporates the interaction between vapor-phase species and species on the surfaces and the bulk interior of structural components. The interactions include exchange, desorption, adsorption, dissolution, and bulk diffusion. The boundary conditions were chosen to be consistent with the physics and chemistry of the system. For example, a condition that is consistent with the dynamics of the adsorption/desorption processes on the surface of the barrier has been adopted. At the same time, the outer boundary condition for the concrete wall is chosen to be consistent with the expectation that the transport of tritiated species through the concrete is diffusion limited. The materials characteristics were obtained from an extensive literature search supplemented by available information from literature on fusion-technology-related activities.^{29,30}

A series of calculations using DTRAM was carried out for both chronic and burst release scenarios. Figure I-13 shows the case for a burst release with a duration of 3×10^5 s into a chamber with a volume of 1.6×10^5 m³. The concentrations of DTO in the vapor phase as well as in various components of the structural materials are shown as a function of time. The vapor-phase concentration is the highest up to approximately 10^3 s. Then, it reaches a steady state from which it abruptly declines after the leakage was stopped at $\sim 3 \times 10^5$ s. However, the concentrations in the paint and the concrete continue to rise long after the vapor concentration has reached a steady state. For the paint surface, the concentrations actually surpass that of the vapor phase by well over an order of magnitude before they decline. For the concrete surface, they reach a lower but still significant level at about 10^8 s. This behavior indicates the relative difficulty of removing tritiated species from structural materials compared with the vapor species. This difficulty is due primarily to the lower transport rate in a heterogeneous structure such as concrete. The time necessary to reduce activity level to an acceptable regime is dominated by the retention capability of tritiated species of the structural materials. Thus, the present analysis indicates that one of the primary objectives in detritiation is to select the right combination of barrier/concrete materials and configuration such that tritium permeation is minimized initially.

It is important to realize that despite the "open" nature of the barrier/concrete structural components (in the sense that tritiated species can, in principle, diffuse through these structural units to be released to the external environment), the present study indicates that virtually no such escape occurs. Even after 10^8 s, the concentration level 1 m into the concrete is only of the order of 10^{-10} $\mu\text{Ci}/\text{m}^3$, a truly infinitesimal amount. Most of the DTO that penetrates into the concrete remains close to the paint/concrete interface even after such a long period of time. The important operating parameters here are the low value of the effective diffusion coefficient of water in paint and concrete and the thickness of the concrete barrier used (~ 2 m). These factors give rise to the result of the virtual absence of tritiated-species escape from the concrete to the external environment.

The effective diffusion coefficient of tritiated water through concrete is represented by the molecular diffusion of tritiated water through the capillary pathways that extend throughout the porous concrete medium. This molecular diffusional process is modified significantly by the convoluted nature of the capillary network and the (reversible) trapping of tritium onto the surfaces of those capillaries by exchange and/or adsorption processes. These factors render the effective diffusion coefficient dependent on the composition and microstructure of the concrete, which, in turn, are affected by the method in which

Fig. I-13. Calculated Concentrations of DTO in Vapor Phase, Concrete, and Paint after Burst Release of Tritiated Species into Single Chamber

the concrete is made. For the purpose of the present study, we circumvented accounting for these factors, in part, by using experimentally determined effective diffusion coefficients available in the literature. These transport properties are valid for that class of concrete that has been used in those experiments. The same approach was used for the molecular diffusion of tritiated species such as DTO through paint. Correlating quantitatively the general dependence of transport properties of tritiated species in concrete and paint on their microstructure is an important issue that needs to be investigated in future work.

D. Fusion-Related Research

A critical element in development of a fusion reactor is the blanket for breeding tritium fuel. We are conducting experimental and calculational studies with the objective of determining the feasibility of using lithium-containing ceramics (e.g., Li_2O , LiAlO_2 , Li_4SiO_4 , Li_2ZrO_3) as breeder material. We also completed conceptual design of the tritium processing systems for the International Thermonuclear Experimental Reactor (ITER)--a tokamak fusion reactor that will be used to test plasma operations and reactor components for prototype fusion power reactors.

1. Desorption Characteristics of $\text{LiAlO}_2\text{-H}_2\text{-H}_2\text{O(g)}$ System (A. K. Fischer)

a. Introduction

Recent work has shown that multiple desorption processes, attributable to different types of surface sites, contribute to the evolution of $\text{H}_2\text{O(g)}$ from ceramic oxides that are candidates for tritium breeders in fusion reactors.³¹ One may regard the desorption sites as kinds of surface "traps" for tritium, with various activation energies of desorption. For the application of tritium release models, accurate measured values are necessary for the kinetic parameters of the constituent processes. Especially important are measurements for desorption of $\text{H}_2\text{O(g)}$, the major desorbed species, though the desorption of HT (or H_2) is also of interest because of the widespread use of H_2 (in the helium purge gas) as a promoter of tritium release. However, the appearance of HT must also be considered in relation to post-release interactions of HTO(g) with the metallic walls³² or to gas phase exchange with H_2 . An established experimental technique for measuring desorption activation energies, reaction order, and the pre-exponential terms in the rate equations is temperature programmed desorption (TPD).³³

For some limited conditions TPD measurements have been reported on the desorption of $\text{H}_2\text{O(g)}$ and $\text{H}_2\text{(g)}$ from LiAlO_2 , one of the tritium breeders considered for a fusion reactor. Corresponding to the desorption processes, the inverse process of $\text{H}_2\text{O(g)}$ adsorption was shown to involve differently activated adsorption processes.³⁴ However, the apparent ability of H_2 in the helium purge gas to enhance the rate of tritium release in various tests of breeder performance under irradiation conditions makes it important to understand, in addition to post-release effects, the interaction of H_2O and H_2 with the breeder substrate. This information can then be used to define the optimum purge gas composition for a balance between (1) the amount of H_2 added as a tritium release promoter to the helium purge gas and (2) the amount of protium that must be separated from tritium in processing the recovery stream. This study, emphasizing the kinetics of desorption for $\text{H}_2\text{O(g)}$, a non-equilibrium process, complements the earlier study³⁴ on adsorption isotherms, which relates to surface inventory at equilibrium.

b. Experimental

A quadrupole mass spectrometer was used for the continuous detection of gaseous species: H_2O , H_2 , O_2 , and N_2 . In addition, the H_2O level in the gas stream was monitored with an electrolytic moisture analyzer. The mass spectrometric data were recorded and processed digitally. The gas-carrying lines of the all-stainless-steel apparatus were heated to minimize holdup of $\text{H}_2\text{O(g)}$. High-temperature chromatographic valves enabled gas streams to be changed very quickly with a sharp concentration profile. A programmable temperature controller provided linear heating rates.

The thermocouple measuring the temperature was immersed directly in the ceramic sample, which weighed 0.52 g. The $\gamma\text{-LiAlO}_2$ sample was from a batch prepared at Centre d'Etudes Nucleaires (Saclay, France), for the EXOTIC V experiment.³⁵ The specific surface area was $6.6 \text{ m}^2/\text{g}$, and the mean grain diameter was 0.28 or $0.35 \mu\text{m}$, depending on whether it is calculated from the porosity and pore radius or from the surface area and density.

After a preliminary drying, six TPD runs were performed with temperature ramps from 473 to 1023 K (200 to 750°C); for 5 of the 6 runs, the ramp rate was 5.6 K/min; for one (number 5), it was 2.0 K/min. Between runs, the sample was kept at 673 K (400°C), while a stream of helium with

990 ppm H_2 passed through it. This soaking period ranged from 20 to 264 h. Just before a run, the temperature was reduced quickly to 473 K (200°C) while the He-900 ppm H_2 stream was maintained. Then, the gas was switched to pure helium if a desorption into pure helium was planned (runs 1 and 2), or the flow of helium-990 ppm H_2 was maintained for desorptions into H_2 -containing sweep gas (runs 3-6). The temperature ramp was started at 473 K (200°C) 5 min later.

c. Results and Discussion

Figures I-14 to I-19 plot the experimental results for the six runs. For desorption into pure helium (Figs. I-14 and I-15), the H_2 trace remained at essentially the baseline level until a temperature of approximately 873 K (600°C) was reached. This result suggests that the amount of H_2 absorbed at 673 K (400°C) in the period before the run is small, or negligible, or is not being desorbed. The rise in evolved H_2 at higher temperature is most likely the result of interaction of the evolved H_2O with the stainless steel tube wall, as reported in the previous semiannual report (ANL-91/42, Sec.I.C.1), and/or the evolution of H_2 dissolved in the steel during the pretreatment with H_2 .

The spectra were obviously not single peaks and were, therefore, deconvoluted. We found that the spectra are the sums of two (in four cases) or three (in two cases) sub-peaks. The sub-peaks are identified as the A, B, and C peaks in the figures and are taken to correspond to desorption processes involving three different types of sites on the surface of the $LiAlO_2$. The overall rate of desorption (r) of $H_2O(g)$ expressed by the measured curves is given by

$$r = \sum v_i \theta_i \exp(-E_{di}/RT) \quad (I-1)$$

Fig. I-14.

Desorption of H_2O into Pure Helium after 264 Hours Pretreatment with 990 ppm H_2 in Helium at 673 K. Ramp rate is 5.6 K/min.

Fig. I-15.

Desorption as in Fig. I-14 but after 120 Hours Pretreatment

Fig. I-16.

Desorption of H_2O into Helium Containing 990 ppm H_2 after 20 Hours Pretreatment with 990 ppm H_2 in Helium at 673 K. Ramp rate is 5.6 K/min.

Fig. I-17.

Desorption as in Fig. I-16, but after 41 Hours Pretreatment

Fig. I-18.

Desorption as in Fig. I-16, but after 66 Hours Pretreatment. Ramp rate is 2.0 K/min.

Fig. I-19.

Desorption as in Fig. I-16, but after 210 Hours Pretreatment. Ramp rate is 5.6 K/min.

This is the functional form used in the deconvolution. Here, θ_i is the individual fractional surface coverage for each of the types of sites ($i=A, B$, or C) at a given moment.³⁶ Total fractional coverage is $\theta_T = \sum \theta_i$. The pre-exponential term, ν_i , is in units of mol/min-m², where m² refers to total BET surface area. The activation energy for desorption, E_{di} , is in units of kcal/mol. The sub-peaks are for first-order desorption. The numerical values for the pre-exponential terms and the activation energies from the deconvolution of the spectra in Figs. I-14 to I-19 are given in Table I-8. Attempts to reproduce the curves as a mixture of first- and second-order processes, or as completely second-order processes, did not yield as good fits to the data. The θ values for the A, B, and C peaks were in the range of 0.01 to 0.02.

Table I-8. Kinetic Parameters Determined for First-Order Desorption of H₂O from A, B, and C Sites on LiAlO₂^a

Run No.	Sweep Gas	ν_A	E_{dA}	ν_B	E_{dB}	ν_C	E_{dC}
1	He	0.090	17.8	0.28	23.0	--	--
2	He	0.072	17.5	0.28	23.0	--	--
3	He-H ₂	0.078	17.0	0.39	22.9	1.74	28.5
4	He-H ₂	0.017	15.7	0.13	23.0	--	--
5	He-H ₂	0.025	16.3	0.20	22.7	0.62	27.5
6	He-H ₂	0.022	16.0	0.15	22.6	--	--

^aSymbols and units defined in text for Eq. I-1.

In comparing the A and B peaks, one sees that the B peak is substantially smaller than the A peak in the absence of H₂ (Figs. I-14 and I-15) but comparable to or larger than the A peak in the presence of H₂ (Figs. I-16 to I-19). In the absence of H₂, the B peak contributes to the overall curve as a shoulder, whereas in the presence of H₂ it is a distinct second or dominant peak. The frequently reported increase in tritium release attending the use of H₂ in the sweep gas might be related, therefore, to enhanced population of B sites and to the emerging participation of C sites, which apparently were not involved in the runs without H₂.

It is apparent from Table I-8 that the activation energies for a given type of site are reproducible. The pre-exponential terms are more variable but not dramatically so. The numerical values for these kinetic parameters for the A and B sites suggest that the effect of 990 ppm H₂ in the sweep gas is small. There appears to be a small decrease in the activation energy for the A sites in the presence of 990 ppm H₂, but this is compensated by a small decrease in the pre-exponential term. Considering that the conditioning of the LiAlO₂ with H₂ was at a relatively low temperature in the context of operation of solid breeders, 673 K (400°C), the small effect of the H₂ addition observed here is consistent with the results from tritium residence time measurements in at least two release experiments. In the TEQUILA experiment,³⁷ the tritium residence times in 0.15- μ m grain size LiAlO₂ were equal at approximately 750 K (477°C) for helium purge gases containing either 1% or 0.1% H₂, or a mixture of 100 vppm H₂O and 50 vppm H₂. That is, the H₂ additions had no effect at this temperature. However, the additions to the purge gas became increasingly influential at higher temperatures. A similar conclusion was reported in the study by Tanaka et al.³⁸ on the residence times for tritium release from LiAlO₂. They found that the residence time was shortened by a factor of 6.8 at 973 K (700°C) and by a factor of only 3.8 at 803 K (530°C) when the H₂ concentration in the sweep gas was changed from 10 to 1000 ppm. These results suggest that even smaller effects would be expected at lower temperatures, e.g., 673 K (400°C).

The spectra in Figs. I-16, I-17, and I-19 indicate that the amplitude of the A and B peaks increased as duration of pretreatment increased. This suggests that the buildup of surface OH⁻ was time dependent and aided by the H₂, but that the process was slow because the pretreatment periods were of the order of days. It appears reasonable that at higher temperature the buildup processes would be faster. Future work should inquire whether the peaks increase in amplitude for higher pretreatment temperatures.

In interpreting the C peaks, we are still uncertain whether the H₂O(g) released at these higher temperatures reflects only desorption from the surface, whether diffusion from the bulk is increasingly augmenting the surface OH⁻ concentration, or if interactions are occurring between H₂ and the steel surface. These questions require further study. When the C peaks appeared, evolution from the C sites was comparable in magnitude to the evolution from the A and B sites. Possibly, the soaking temperature of 673 K (400°C) was only marginally adequate to activate chemisorption of H₂ to populate the C sites.

The 28 kcal/mol value for the activation energy for the C peaks is close to the 29.5 kcal/mol reported by Kudo for the activation energy of decomposition of LiOH, a process of H₂O(g) evolution.³⁹ In Kudo's case, the decomposing LiOH produced a Li₂O surface with scattered OH⁻ groups. The apparent similarity between the two cases suggests that the C sites on LiAlO₂ resemble sites on Li₂O in their H₂O-evolving behavior, but there also remains the question of possible steel surface effects in the work with the LiOH.

The observation of first-order kinetics requires consideration because of the generally accepted view that the desorption of H₂O derived from chemisorbed OH⁻ on oxide surfaces is a bimolecular process involving recombination of OH⁻, even in the presence of H₂.³⁸ In general, the observation of first-order kinetics for a bimolecular process can be understood in terms of a theory originated by Lindemann.⁴⁰ If the surface is represented by s, the surface-bonded OH⁻ groups are s-OH, and the transition state is s-H₂O*, then the stepwise process can be represented as the bimolecular step:

with rate constants k_2 to the right and k_{-2} to the left, followed by the unimolecular step:

with rate constant k_1 . The Lindeman theory leads to the expression

$$\frac{d[\text{H}_2\text{O(g)}]}{dt} = \frac{k_1 k_2 [s\text{-OH}]^2}{k_{-2} [s\text{-OH}] + k_1} \quad (\text{I-4})$$

which is a first-order expression relating to a bimolecular process and provides the conceptual rationale for the observations of first-order kinetics. The condition $k_{-2} \gg k_1$ implies that the reversal of the bimolecular step is faster than the evolution of H₂O, and that increasing the concentration of s-OH will increase the evolution of H₂O(g) according to the rate equation. Higher temperatures could alter the

relationship between the rate constants so that, if $k_1 \gg k_2$, the observed kinetics would become second order, though the total mechanism would still involve a bimolecular step followed by a unimolecular one.

2. Tritium Release from Lithium Ceramics

(J. P. Kopasz, M. Bricc,^{*} S. Casadio,^{**} and H. Werle^{***})

a. Introduction

Numerous data are available from in-pile tritium recovery experiments (using lithium ceramic breeders) investigating the effects of the tritium generation rate, sample microstructure, purge gas composition, and temperature on tritium inventory and release. The results have led to a qualitative understanding of the dependence of tritium inventory and release on these factors; however, a detailed interpretation of the results leading to an understanding of the rate-controlling mechanisms is not straightforward. The diffusion-desorption model⁴¹ has been widely used to interpret the results. This model treats the desorption as pseudo first order in tritium and generally considers the desorption occurring with one activation energy. Other work has suggested that the desorption step is second order in tritium, or that the desorption may be occurring with different activation energies.³⁴ Using data from experiments carried out at the Centre d'Etudes Nucléaires (CEN) de Grenoble, we have examined the effects of the key parameters mentioned above on tritium release and inventory and have compared the magnitude of these effects with those predicted from various tritium release models.

b. Key Parameters Affecting Tritium Release

The tritium release kinetics depends on the tritium generation rate, temperature, microstructure of the ceramic, and composition of the purge gas. The tritium residence time (defined here as the ratio of the tritium inventory to the tritium generation rate) is a convenient indicator of the release kinetics. The tritium residence time should be independent of the generation rate if a diffusion or first-order desorption mechanism is the rate-controlling step, while it should depend on the generation rate if a second-order desorption mechanism is rate controlling.

The sample microstructure is a crucial factor affecting tritium release kinetics. For a diffusion mechanism, the tritium residence time (t) is given by

$$t = a^2/15D \quad (I-5)$$

where a is the grain radius, and D is the diffusion coefficient. For a desorption mechanism, the residence time is given by the sample volume divided by the product of the surface area times the desorption rate constant. For a sphere, this leads to

$$t = a/3K_d \quad (I-6)$$

^{*}Commissariat à l'Energie Atomique, Centre d' Etudes Nucléaires de Grenoble, France.

^{**}ENEA/CRE, Cassaccia, Italy.

^{***}Kernforschungszentrum Karlsruhe, Germany.

where K_d is the effective desorption rate constant. For other geometries, an effective radius a^* , defined as three times the ratio of the sample volume to the specific surface area, can be used to calculate the residence time. The residence time will be proportional to this effective radius if desorption is the rate-controlling mechanism.

The composition of the purge gas has been demonstrated to have a substantial effect on the tritium residence time. It is obvious that the surface processes are influenced by the purge gas chemistry. However, the bulk properties may also be affected by the purge gas. For example, water addition to the purge gas is expected to increase the tritium desorption from the surface. Water addition in the purge gas may also lead to a hydrogen concentration in the bulk which exceeds the solubility limit, causing the precipitation of a second phase of LiOH/LiOT. This effect would change the bulk properties, including diffusivity. This is likely to occur for Li_2O at temperatures below 723 K (450°C), where the hydrogen solubility is low.

c. Results and Discussion

(1) Effect of Generation Rate

In an effort to clarify the order of the desorption reaction, the LILA-LISA experiment was performed with different thermal neutron fluxes and, consequently, different tritium generation rates.³⁸ For a desorption mechanism which is first order in tritium, the tritium residence time will be independent of the generation rate, while for a desorption mechanism which is second order in tritium, the tritium residence time will be inversely proportional to the square root of the generation rate. Transient temperature changes were performed on Li_4SiO_4 samples with He + 0.1% H_2 as the purge gas for two thermal neutron fluxes, 0.4 and $0.93 \times 10^{17} \text{ n}/(\text{m}^2 \cdot \text{s})$. The calculated tritium residence times are shown in Table I-9. The residence times at a given temperature are identical, within the error of the calculations, for the two fluxes, indicating that the rate-determining step is not second order in tritium. Other factors indicate desorption is rate controlling for these samples. We thus conclude that desorption is first order in tritium under these conditions.

Table I-9. Tritium Residence Time versus Thermal Neutron Flux for Li_4SiO_4 sample (He + 0.1% H_2 as purge gas)

Neutron Flux, $10^{17} \text{ n}/\text{m}^2 \cdot \text{s}$	Temp., °C	Tritium Residence Time, h
0.93	450	$17.5 < t < 27$
	500	$4 < t < 4.2$
0.40	450	26.5
	500	4.1

(2) Effect of Microstructure

The effect of sample microstructure on tritium inventory was investigated in the TEQUILA experiment.³⁷ Temperature-transient runs were performed on samples of LiAlO_2 with different microstructures. Results for experiments with He + 0.1% H_2 purge gas and two different grain sizes are given in Table I-10. The results indicate that tritium residence time decreases with decreasing grain size. This was also observed in the LILA III experiment.⁴²

Table I-10. Effect of Microstructure on Tritium Residence Time

Grain Size (a), μm	a* (calc. from spec. surf. area), μm	Temp., $^{\circ}\text{C}$	Tritium Residence Time, h	t_2/t_1
0.15	0.45	670	0.95	--
6	6	"	>10.3	>10.8
0.15	0.45	620	1.3	--
6	6	"	>21.2	>16.3
0.15	0.45	560	3.9	--
6	6	"	>103.8	>26.6
0.15	0.45	510	9.7	--
6	6	"	>140.2	>14.4

It follows from Eq. I-5 that, for diffusion-controlled release, the tritium residence time will increase in proportion to the square of the grain size. Thus, a ratio of 1600 is expected for the tritium residence times of the two samples with 6 and 0.15 μm grain sizes. The observed ratios (>10.8 at 670 $^{\circ}\text{C}$, >16.3 at 620 $^{\circ}\text{C}$, >26.6 at 560 $^{\circ}\text{C}$, and >14.4 at 510 $^{\circ}\text{C}$) are much lower, indicating that diffusion is not rate limiting for these temperatures and grain sizes. Likewise, if desorption is rate limiting, the tritium residence time will increase in proportion to the effective grain radius calculated from the specific surface area. Thus, a ratio of 13.3 is expected for the tritium residence times of the two samples with 6 and 0.45 μm effective grain radii (a*). The observed ratios (see Table I-10) are of the same order of magnitude as expected for the desorption-controlled release, suggesting that desorption determines the tritium residence time for these materials. The variations from the expected ratios suggest that other processes may be playing a minor role in determining the tritium residence time.

(3) Effect of Purge Gas Composition

It is obvious that the surface processes (desorption of tritium or tritiated water) are influenced by the purge gas chemistry. Researchers have repeatedly demonstrated that hydrogen addition to the purge gas improves the tritium release rate.^{43,44} Thus, water addition should also improve the tritium release rate.

In the TEQUILA experiment, three purge gas compositions were investigated: He + 0.1% H₂, He + 1.0% H₂, and He + 50 vppm H₂ + 100 vppm H₂O. The results for samples with grain radius of 0.15 μm are illustrated in Fig. I-20 as plots of the natural logarithm of tritium residence time versus the inverse temperature.

The tritium residence times obtained in TEQUILA indicate that, for small grain radius samples, tritium release is better for a purge gas containing 1.0% H₂ than for one containing 0.1% H₂. This conclusion is supported by the tritium release observed for a change in purge gas from He + 0.1% H₂ to He + 1.0% H₂, which shows a decrease in tritium inventory. The TEQUILA results also indicate that tritium release was better for a purge gas of He + 0.1% H₂ than for He + 50 vppm H₂ + 100 vppm H₂O at high temperatures (> 510 $^{\circ}\text{C}$), while at low temperatures (460 $^{\circ}\text{C}$) release was better for the purge gas containing water.

In TEQUILA, for small grain samples, the desorption activation energies were the same (within the experimental errors) for purge gases of He + 0.1% H₂ (23 kcal) and He + 1.0% H₂ (25 kcal), while the desorption activation energy for He + 50 vppm H₂ + 100 vppm H₂O was substantially lower (16 kcal). This observation suggests that the activation energy may depend on the hydrogen (OH

Fig. I-20. Residence Time vs. Temperature for Three Purge Gas Compositions in TEQUILIA Experiment

groups) surface coverage. The degree of hydrogen gas adsorption on LiAlO_2 is certainly less than that for water; therefore, it is not surprising that the desorption activation energy is smaller when water is added to the purge gas. In addition, since H_2 adsorption is expected to be dissociative, the hydrogen surface coverage is expected to vary as the square root of the hydrogen pressure. This suggests that the hydrogen surface coverage for $\text{He} + 1\% \text{H}_2$ is of the same order of magnitude as for $\text{He} + 0.1\% \text{H}_2$ and, therefore, the desorption activation energies should be similar.

(4) Effect of Temperature

The effect of temperature was investigated in temperature transient tests. Generally, the tritium inventory and tritium time constant (defined as the time for a temperature transient peak to decay to 35% of its maximum value) decrease with increasing temperature. The tritium time constants, however, exhibit an interesting trend. In some cases, the time constant determined for a temperature increase from temperature T_1 to temperature T is not the same as the time constant determined for a temperature decrease from temperature T_2 to T (e.g., see Table I-11).

For a pure first-order desorption process or a pure diffusion process, the time constant is independent of the previous temperatures, while for a second-order desorption process the time constant will depend on the previous temperature. In the case of mixed diffusion-desorption, the mathematics is less straightforward, and it is not obvious whether the time constant is dependent on, or independent of, the previous conditions. To solve this problem, calculations were performed using the DISPL Code⁴⁴ for diffusion with a first-order desorption boundary condition in spherical geometry. The results indicate that, in the mixed diffusion-desorption regime, the time constant depends on the previous conditions, but as the ah/D ratio (where $h=K_d/D$) increases toward diffusion-controlled release or decreases toward desorption-controlled release, this dependence disappears. This suggests that either tritium release is in the mixed diffusion-desorption regime at the temperature when the time constants for temperature increases and temperature decreases are unequal, or desorption is second order in tritium in these cases. However, separate tests on Li_4SiO_4 indicate that desorption is first order.

Table I-11. Time Constants of Tritium Release for Temperature Increase and Decrease^a

Grain Size, μm	Temp., $^{\circ}\text{C}$	Previous Temp., $^{\circ}\text{C}$	Time Constant, h
12	620	670	10.75
	"	570	5.5
0.2-5 (bimodal)	"	670	11
	"	570	3.7

^aHe + 0.1% H₂ purge gas.

d. Conclusion

The results from our studies have provided some insight into the rate-limiting mechanism for tritium release from in-pile experiments with lithium ceramics. The relationship between the tritium residence time and the sample grain size indicates that desorption is the dominant mechanism in tritium release for the conditions investigated. The importance of surface processes is further illustrated by the effect of the purge gas composition on tritium release. The different activation energies for the rate-limiting process for the different purge gases indicate that use of a simple desorption model with a single activation energy is inadequate. A model with multiple desorption activation energies is necessary to account for the variations in inventory with different purge gas compositions.

Some data also suggest that a second mechanism contributes to the tritium inventory. Diffusion is the most likely candidate, and a diffusion-desorption model is able to account for the observed differences in time constants for temperature increases and temperature decreases to the same final temperature. An alternative explanation is a second-order desorption mechanism, which would account for the differences in time constants, but separate tests on Li₄SiO₄ have indicated the tritium release is independent of the generation rate and, therefore, not second order.

3. Processing System for the Li₂O Blanket in ITER
(P. A. Finn and D. K. Sze)

The International Thermonuclear Experimental Reactor (ITER) is a tokamak fusion reactor which will be used to test components for prototype power reactors and to test plasma operations. It will be fueled by tritium which is bred in the blanket system around the plasma chamber. This blanket contains Li₂O as the breeder, beryllium as the neutron multiplier, and water as the coolant. The Li₂O blanket consists of a series of semi-rectangular zones which contain, in order, water, beryllium, and Li₂O. Each of these zones is isolated from the next by thin welded sections of stainless steel.

The tritium recovery system for this Li₂O/Be water-cooled blanket possesses two separate helium purge streams to recover tritium from the Li₂O and the beryllium zones of the blanket, to process the waste products, and to recirculate the helium back to the blanket. We have defined the needed components for the processing system to recover and purify tritium from the blanket. The components were selected to minimize the tritium inventory of the recovery system and to minimize waste products. The system is able to adequately handle either an increase in the tritium release rate or water leakage in the purge system. A detailed conceptual design of the system is given in Ref. 45.

a. Process Description and Design Considerations

Three major components are used to process the helium streams: 5A molecular sieves at -196°C separate hydrogen from the helium, a solid oxide electrolysis unit reduces all molecular water, and a palladium/silver diffuser ensures that only hydrogen species reach the cryogenic distillation unit. Other units are present to recover tritium from waste products, but these three major components are the basis of the blanket tritium recovery system.

The concentration of the major species in the helium purge streams as they leave the blanket are listed in Table I-12. Several filters are used between the blanket and the subsystems of the blanket tritium recovery unit to remove particulates, vapor species, and other impurities. Regenerative heat exchangers prior to the cold trap reduce the helium purge gas temperature from 400°C to -100°C . The effect of these removal units is shown in Table I-13 for the Li_2O zone and in Table I-14 for the beryllium zone.

Table I-12. Characteristics of Li_2O and Beryllium Zone Purge Streams

Parameter	Be	Li_2O
Flow, L(STP)/s		
He	0.84	650
H_2	0.00022 ^a	0.65
H_2O	0.144	0.0065
H/T Ratio	10^3 ^b	10^2
Impurity (CO_2), g/day	4	4.7
Radionuclides, $\mu\text{g/day}$		
S-35(SO_2)	46	36
C-14(CO_2)	1500	3000
Ar-39	2	61
Kr-85	<0.01	0.74
Xe-135	0.01	0.05
Xe-133	0.014	0.16
Residence Time, s	10^4	4

^aTotal hydrogen isotope, includes tritium.

^bRatio if 10 kg/day water leak is assumed.

Table I-13. Species in Helium Purge Stream from Li_2O Zones
(units are g/day for element listed)

Element	Species	Blanket Ex. (400°C)	Filter (25°C)	Cold Trap (-100°C)	Sieves (-196°C)	Trapped in Sieves
He	He	10^7	10^7	10^7	10^7	0.0
H	H_2	4964	4964	4964	0.0	4964
H	H_2O	50	50	0.0	0.0	0.0
T	HT	148.5	148.5	148.5	0.0	148.5
T	HTO	1.5	1.5	0.0	0.0	0.0
O	H_2O	400	400	0.0	0.0	0.0
C	CO_2	4.7	4.7	4.2	0.0	4.2
Na	Na	0.1	0.0	0.0	0.0	0.0
a,b	a,b	a,b	a	0.0	0.0	0.0

^aImpurities present but <1 g/day at 400°C . Impurities include K,Cl,N,P,As,Br,Rb,Mo,S,F.

^bImpurities which could be presented at <0.1 g/day, depending on blanket impurities, at 400°C include Ca,Fe,Al,Si,Mg,Ni,Cu,Zn,Ti,Ba,V,Cr,Be,B,Mn,Ga,Sr,Zr,Sn,Sb,Co,Sc,Cd,Pb,U.

Table I-14. Species in Helium Purge Gas from Beryllium Zones
(units of g/day of element listed)

Element	Species	Blanket Ex. (400°C)	Filter (25°C)	Trapped in Filter	Sieves (-196°C)	Trapped in Sieves
He	He	1.33E5	1.33E5	0.0	1.33E5	0.0
H	HT, H ₂	1	1	0.0	0.0	1.0
T	HT, T ₂	2.0	2	0.0	0.0	2.0(max)
Be	Be	1.4 E-4	0.0	0.0	0.0	0.0
O	BeO	9. E-28	0.0	0.0	0.0	0.0
C	CO ₂ ^a	4.0	4.0	0.0	0.0	3.6
Mg	Mg	1060	0.0	4.3	0.0	0.0
Na	Na	2760	0.0	59.3	0.0	0.0
Cl	BeCl ₂	2300	0.0	2300	0.0	0.0
F	BeF ₂	16	0.0	0.0	0.0	0.0
Pb	Pb	12.5	0.0	0.042	0.0	0.0
Zn	Zn	184	0.0	2.4	0.0	0.0
Li	Li	40	0.0	0.12	0.0	0.0
Br	BeBr ₂	4.5	0.0	0.4	0.0	0.0
Rb	Rb	4.5	0.0	4	0.0	0.0
K	K	4.5	0.0	0.2	0.0	0.0
Cd	Cd	4.5	0.0	4	0.0	0.0
I	BeI ₂	4.5	0.0	1	0.0	0.0
b	b	b	0.0	b	--	--

^aSome of the carbon dioxide is retained in the cold trap prior to the molecular sieves held at -196°C.

^bImpurities <5 g/day at 400°C include N,P,As,Mo,S,Ca,Fe,Al,Si,Ni,Cu,Zn,
Ti,Ba,V,Cr,B,Mn,Ga,Sr,Zr,Sn,Sb,Co,Sc,Cd,Pb,U.

Seven units (Fig. I-21) process the helium/hydrogen purge gas from the Li₂O zones. First, a set of cold traps separates water, 0.47 kg/day, and some of the carbon dioxide from the helium. Second, two compressors and a storage system circulate the helium gas. Third, a solid oxide electrolysis unit decomposes water. Fourth, a set of 5A molecular sieves, termed X1, at -196°C removes hydrogen isotopes, 1% of the helium, and all remaining impurities from the helium. Fifth, a set of 5A molecular sieves at 25°C, termed Y1, recovers water, carbon dioxide, and other impurities when the X1 sieves are regenerated and also removes water from the hydrogen stream coming from the electrolysis unit. Sixth, a palladium/silver diffuser separates inert elements from the hydrogen isotopes when they are passed to the cryogenic distillation unit. Seventh, an SAES getter held at 350°C prevents impurities from entering the cryogenic distillation unit.

Partial regeneration of the X1 sieves to -100°C will be frequent, occurring every two hours. Hydrogen gas passed through the sieves will assist in desorbing the hydrogen and helium. The helium will be removed first, followed by the hydrogen. Most of the hydrogen will be removed before the sieves are at -100°C, with the last portion of the hydrogen gas containing most of the tritium and none of the helium. It may be possible by judicious temperature control to return the major fraction of the hydrogen stream back to the Li₂O purge stream and send only the tritium-rich portion of the recovered hydrogen stream to the cryogenic distillation unit. Regeneration at 25°C to remove entrapped hydrogen species or inert elements and later heating to 250°C to remove water and carbon dioxide may be required once a month, or more frequently, if the impurity level is higher than expected.

Fig. I-21. Schematic of Processing System for Tritium Recovery (MS = molecular sieve)

Also shown in Fig. I-21 are units to process the helium purge from the beryllium zones: (1) a set of cold traps separates water, a maximum of 10 kg/day, from the helium, (2) a compressor and a storage system circulate the helium gas, (3) several linked solid oxide electrolysis units decompose water, (4) a set of 5A molecular sieves at -196°C , termed X2, remove impurities, including tritium from the helium (regeneration of the X2 sieve beds is done once a day using hydrogen as the carrier gas and warming to 250°C), and (5) a set of 5A molecular sieves at 25°C , termed Y2, separates hydrogen from other impurities and removes water in the hydrogen stream from the electrolysis unit. The exit hydrogen species from the X2 and the Y2 sieves are routed to the Y1 sieves. Waste products are sent to a common waste recovery unit.

After purification through the Y1 and Y2 beds, the protium/tritium stream permeates through the palladium/silver diffuser to ITER's common cryogenic distillation unit, in which the tritium is separated from the excess protium. The tritium product fuels the plasma, while the H_2 is recycled to the helium purge stream for the Li_2O blanket zones.

To recover tritium waste species, the Y1 and Y2 molecular sieve beds are regenerated every 12 h by flowing helium gas through them at 250°C . The helium stream is passed to the waste recovery unit, in which the tritium is recovered as tritiated water and non-tritiated waste is passed to the plant's stack system. The components of the waste recovery unit include a set of 5A molecular sieves (termed Z), a set of copper oxide beds held at 500°C , and a set of cold traps held at -100°C . If necessary, zeolite beds could be added to trap radioactive Ar, Kr, and Xe at -196°C , and a calcine solution may be required to trap carbon dioxide as calcium carbonate. Access also has to be provided to solid waste disposal facilities at the plant when the end-of-life of components is reached.

The blanket tritium recovery system is linked with the blanket, the other subsystems of the fuel processing system, the cryogenic isotopic separation system, the general roughing vacuum system, the waste disposal unit, and the stack system. Valves and control circuits have to be provided between these systems to ensure reliable operation.

Localized control for processing is maintained on each unit using feedback from temperature and flow sensors. Data collection is maintained at a centralized control unit. A separate system, which is linked to a centralized control unit, is responsible for safety.

b. Physical Configuration

The space requirements for the blanket tritium recovery system are listed in Table I-15. Access space needed for maintenance of the components is not included. A system layout of the components is shown in Fig. I-22. The three rooms (Li_2O , beryllium, and tritium) are, respectively, 13 x 12 x 4 m, 13 x 7 x 3 m, and 8 x 11 x 3 m.

Table I-15. Space Requirements and Dimensions for Blanket Tritium Recovery System

Component ^a	Vol., m ²	Dimensions, m		
		Length	Width	Height
Li ₂ O Components				
He Compressors (2)	16 ^b	2	2	2
He Storage	8 ^c	2	2	2
He/H ₂ Mix Tank	1	1	1	1
H ₂ Surge Tank	2	2	1	1
Heat Exchangers (2)	2	1	1	1
Cold Trap (2)	4	1	1	2
Electrolysis [*]	1	1	1	1
MS(-196°C) (2)	16	2	2	2
MS(25°C) (2) [*]	2	1	1	1
Be Components				
He Compressors (2)	1	1	1	1
He Storage	8	2	2	2
Cold Trap (2)	2	1	1	1
Electrolysis [*]	4	2	1	2
MS(-196°C) (2)	2	1	1	1
MS(25°C) (2) [*]	2	1	1	1
Common Components				
Diffuser [*]	6	3	1	2
Waste [*]	6	3	1	2
Filters (2) ^d	2	1	1	1
Total	85			

^aA two in parentheses signifies two units; MS = molecular sieves.

Components in tritium room indicated by asterisk.

^bThe compressor volume is given, not the room volume.

^cThe gas is assumed to be held at ≤ 0.6 MPa.

^dOne for Li_2O ; one for Be.

Fig. I-22. Layout of Tritium Recovery System

The large compressor units and regenerative heat exchangers for the helium purge stream for the Li₂O zones are in the Li₂O room, which has a crane that can be operated remotely to ensure that these units can be maintained in the event of gamma contamination. Other units in this room include low-temperature molecular sieve beds and cold traps. In an adjacent beryllium room are the units used to recycle the helium stream for the beryllium zones. In a third room, the units which purify the tritium and recover the waste tritium are located.

c. Reliability, Maintenance, and Safety

There is a general lack of qualification data for most components needed for tritium operation. Palladium/silver diffusers need extended testing at the tritium concentrations and pressures expected in ITER. Ceramic electrolysis units consisting of series of 10-20 cells are currently under commercial development for protiated water and still require tritium qualification.

The purpose of qualification tests will be to obtain data which indicate the reliability of individual components in tritium service, the time between failures, the type of maintenance schedules to be followed, and any synergistic effects between components during operation. The overall goal of qualification tests will be to ensure 99% availability of the blanket tritium recovery system, including planned maintenance.

Maintenance of the components of the blanket tritium recovery system may require gamma shielding, especially the filters located immediately after the outlet of the purge gases from the blanket. To provide ease in maintenance, components which have a high probability to be gamma activated, i.e., those used to recycle the helium stream, are located in a separate room. Cranes which can be remotely directed are used for large units, like the compressors for the helium purge for the Li₂O zones, to minimize worker exposure to gamma contamination. In addition, components are designed as modular units to minimize downtime if replacement of units is required.

The most crucial component of the blanket tritium recovery system is the compressor for the helium purge in the Li_2O zones. If this unit fails, then there will be a static gas atmosphere in the Li_2O zones, which may allow the tritium to concentrate in cold areas of the blanket. Therefore, a spare compressor is included in the design plans to handle failure of the primary unit.

Some failures can be tolerated due to the long regeneration times (12 h for beds Y1, Y2, and Z; 24 h for beds X2; and 48 h for the Be cold trap). If a failure occurs in the X1 beds, the helium purge gas could be recycled to the Li_2O zones for four days, the net result being a 4% increase in the hydrogen partial pressure of the stream.

For safety purposes, all units and process lines are assumed to have primary and secondary containment. The major components of the blanket tritium recovery system are installed in secondary containment gloveboxes. Lines between the blanket and the compressor units will be doubly contained. Tritium release from these systems cannot occur as a result of a single component failure. Because of the size and mass of the compressors used to circulate the helium for the Li_2O zones and the need to have access to a crane if one fails, the room in which they are located is assumed to provide secondary containment of these units. In addition, a distributed control system was selected for the operation of the process system.

For the processing system for the Li_2O and Be zones, the total dynamic tritium inventory is estimated as < 20 g. However, the total residual tritium inventory (i.e., that incorporated in the 5A molecular sieves after several years of operation) could reach 134 g. Releasing this tritium requires prolonged heating of the bed at 250°C while hydrogen is circulated. Since this method was chosen to regenerate these molecular sieve beds, we expect the long-term bed inventory to be appreciably less than 134 g.

d. Cost Estimate

Component costs were extrapolated from experience at the Tritium Systems Test Assembly of Los Alamos National Laboratory, the Japan Atomic Energy Research Institute, and elsewhere. The capital cost of the blanket tritium recovery system is estimated at \$14 M, which is approximately 5-10% of the capital cost of the blanket.

REFERENCES

1. R. K. Cole, Jr., D. P. Kelly, and M. A. Ellis, *CORCON-Mod2: A Computer Program for Analysis of Molten Core-Concrete Interactions*, U. S. Nuclear Regulatory Commission Report NUREG/CR-3920 (1984).
2. J. A. Gieseke, P. Cybulskis, H. Jordan, K. W. Lee, P. M. Schumacher, L. A. Curtis, R. O. Wooton, S. F. Quale, and V. Kogan, *Source Term Code Package*, U.S. Nuclear Regulatory Commission Report NUREG/CR-4587 (1986).
3. D. A. Powers and F. E. Arellano, *Large-Scale Transient Tests of Interaction of Molten Steel with Concrete*, U.S. Nuclear Regulatory Commission Report NUREG/CR-2282 (1982).
4. A. Skokan, H. Hollek, and M. Peehs, *Nucl. Technol.* 46, 255 (1979).
5. M. Reimann and S. Steifel, *The WECHSL-Mod2 Code: A Computer Program for the Interaction of a Core Melt with Concrete including the Long Term Behavior*, Kernforschungszentrum Karlsruhe Report KfK-4477 (1989).
6. G. Cenerino, "Application of the Core-Concrete Interaction Code WECHSL to Reactor Case," in *Proc. Committee on Safety of Nuclear Installations (CSNI) Specialist's Mtg. on Core-Debris Concrete Interactions*, Electric Power Research Institute Report EPRI NP-5054-SR p. 6-3 (1987).
7. M. F. Roche, J. L. Settle, L. Leibowitz, and C. E. Johnson, *Vaporization of Strontium, Barium, Lanthanum, and Uranium from Mixtures of Urania, Zirconia, Steel, and Concretes at 2150 K and 2400 K*, Electric Power Research Institute Report EPRI NP-6613 (1990).
8. D. H. Thompson and J. K. Fink, *ACE MCCI Test L2, Test Data Report, Volume I - Thermal Hydraulics*, ACE Consortium Report ACE-TR-C10, Volume I (1990).
9. E. M. Levin, C. R. Robbins, and H. F. McMurdie, *Phase Diagrams for Ceramists*, American Ceramic Society, Columbus, OH (1964).
10. *1990 Annual Book of ASTM Standards*, Volume 14.03, American Society for Testing and Materials, Philadelphia, PA (1990).
11. E. M. Levin, C. R. Robbins, and H. F. McMurdie, *Phase Diagrams for Ceramists, 1969 Supplement*, American Ceramic Society, Columbus, OH (1969).
12. E. M. Levin and H. F. McMurdie, *Phase Diagrams for Ceramists, 1975 Supplement*, American Ceramic Society, Columbus, OH (1975).
13. T. B. Massalski, Ed., *Binary Alloy Phase Diagrams*, American Society for Metals, Metals Park, OH (1986).
14. L. Leibowitz, R. A. Blomquist, and A. D. Pelton, *J. Nucl. Mater.* 167, 76 (1989).
15. D. E. Peterson and E. M. Foltyn, *Bull. Alloy Phase Diagrams* 10, 160 (1989).

16. P. Chiotti, V. V. Akhachinskij, I. Ansara, and M. H. Rand, *The Chemical Thermodynamics of Actinide Elements and Compounds, Part 5, The Actinide Binary Alloys*, Int. At. En. Agency, Vienna (1981).
17. L. Leibowitz, E. Veleckis, R. A. Blomquist, and A. D. Pelton, *J. Nucl. Mater.* 154, 145 (1988).
18. C. W. Bale, A. D. Pelton, and W. T. Thompson, *F*A*C*T Guide to Operations*, McGill University/Ecole Polytechnique, Montreal (1985).
19. A. D. Pelton, Ch. 7 in *Physical Metallurgy*, 3rd ed., R. W. Cahn and P. Haasen, Eds., North-Holland, New York (1984).
20. F. L. Oetting, M. H. Rand, and R. J. Ackermann, *The Chemical Thermodynamics of Actinide Elements and Compounds, Part I, The Actinide Elements*, Int. Atom. En. Agency, Vienna (1976).
21. F. H. Ellinger, R. O. Elliott, and E. M. Cramer, *J. Nucl. Mat.* 3, 233 (1959).
22. H. Savage and R. D. Seibel, *Heat Capacity Studies of Uranium and Uranium-Fission Alloys*, Argonne National Laboratory Report ANL-6702 (1963).
23. T. B. Massalski, Ed., *Binary Alloy Phase Diagrams*, American Society for Metals, Metals Park, OH (1986).
24. A. J. Freeman and J. B. Darby, Jr., Eds., *The Actinides, Electronic Structure and Related Properties*, Academic Press, New York (1974).
25. J. J. Katz, G. T. Seaborg, and L. R. Morss, Eds., *The Chemistry of the Actinide Elements*, 2nd ed., Chapman and Hall, New York (1986).
26. I. Barin and O. Knacke, *Thermodynamic Properties of Inorganic Substances*, Springer-Verlag, Berlin (1973).
27. I. Barin, O. Knacke, and O. Kubaschewski, *Thermodynamic Properties of Inorganic Substances*, Springer-Verlag, Berlin (1977).
28. M. W. Chase, J. L. Curnutt, H. Prophet, R. M. McDonald, and A. N. Syverud, *JANAF Thermochemical Tables, 1975 Supplement*, J. Phys. Chem. Reference Data, Vol. 4, No. 1 (1975).
29. S. Tanaka, F. Ono, T. Masegi, and Y. Takahashi, *Fusion Eng. Design* 7, 353 (1989).
30. R. G. Clemmer et al., *Simulation of Large Scale Air Detritiation Operations by Computer Modeling and Bench Scale Experimentation*, Argonne National Laboratory Report ANL/FPP/77-3 (1977).
31. J. P. Kopasz, A. K. Fischer, and C. E. Johnson, "Multiple Activation Energies for Tritium Release from Ceramic Breeders," to be published in *Advances in Ceramics*.
32. A. K. Fischer and C. E. Johnson, "Desorption of H₂O and H₂ from Steel and LiAlO₂ by Temperature Programmed Desorption," to be published in the *Journal of Nuclear Materials*.

33. J. L. Falconer and J. A. Schwartz, *Catal. Rev. - Sci. Eng.* 25, 141 (1983).
34. A. K. Fischer and C. E. Johnson, *Fusion Tech.* 15, 1212 (1989).
35. H. Kwast, R. Conrad, L. Debarberis, A. J. Flipot, P. Kennedy, and J. D. Elen, *J. Nucl. Mater.* 155-157, 558 (1988).
36. D. O. Hayward and B. M. W. Trapnell, *Chemisorption* 2nd ed., Chapter 4, Butterworths, London (1984).
37. M. Briec, J. Kopasz, S. Cassadio, and H. Werle, "In-Pile Tritium Release from Lithium Ceramics and Influence of Surface Processes," *Proc. of 16th Symp. on Fusion Technol.*, London, September 3-7, 1990, pp. 857-861 (1991).
38. S. Tanaka, A. Kawamoto, M. Yamawaki, T. Terai, Y. Takahashi, H. Kawamura, and M. Saito, *Fus. Eng. Des.* 8, 155 (1989).
39. H. Kudo, *J. Nucl. Mater.* 87, 185 (1979).
40. W. J. Moore, *Physical Chemistry*, 3rd ed., Prentice Hall, New York, p. 278 (1962).
41. J. Kopasz, S. W. Tam, and C. E. Johnson, *J. Nucl. Mater.* 155-157, 500 (1987).
42. S. Tanaka, T. Terai, H. Mohri, and Y. Takahashi, *J. Nucl. Mater.* 155-157, 533 (1988).
43. M. Briec, J. J. Abassin, C. E. Johnson, M. Masson, N. Roux and H. Watanabe, *Fusion Tech.* 15, 1105 (1988).
44. G. K. Leaf, and M. Minkoff, *DISPLI: A Software Package for One and Two Spatially Dimensional Kinetics-Diffusion Problems*, Argonne National Laboratory Report ANL-84-56 (1984).
45. P. A. Finn, D. K. Sze, and R. G. Clemmer, *Conceptual Design Description for the Tritium Recovery System for the U.S. ITER Li₂O/Be Water Coolant Blanket, Revision 1.0*, Argonne National Laboratory Report ANL/FPP/TM-249 (1990).

II. SEPARATION SCIENCE AND TECHNOLOGY

(G. F. Vandegrift)

The Division's work in separation science and technology is mainly concerned with developing a technology base for the TRUEX (TRansUranic EXtraction) solvent extraction process. The TRUEX process extracts, separates, and recovers TRU elements from solutions containing a wide range of nitric acid and nitrate salt concentrations. The extractant found most satisfactory for the TRUEX process is octyl(phenyl)-N,N-diisobutylcarbamoylmethylphosphine oxide, which is abbreviated CMPO. This extractant is combined with tributyl phosphate (TBP) and a diluent to formulate the TRUEX process solvent. The diluent is typically a normal paraffinic hydrocarbon (NPH) or a nonflammable chlorocarbon such as carbon tetrachloride (CCl_4) or tetrachloroethylene (TCE). The TRUEX flowsheet includes a multistage extraction/scrub section that recovers and purifies the TRU elements from the waste stream and multistage strip sections that separate TRU elements from each other and the solvent. Our current work is focused on facilitating the implementation of TRUEX processing of TRU-containing waste and high-level defense waste, where such processing can be of financial and operational advantage to the DOE community.

The major effort in TRUEX technology-base development involves developing a generic data base and modeling capability for the TRUEX process, referred to as the Generic TRUEX Model (GTM). The GTM will be directly useful for site-specific flowsheet development directed to (1) establishing a TRUEX process for specific waste streams, (2) assessing the economic and facility requirements for installing the process, and (3) improving, monitoring, and controlling on-line TRUEX processes. The GTM is composed of three sections. The heart of the model is the SASSE (Spreadsheet Algorithm for Stagewise Solvent Extraction) code, which calculates multistage, countercurrent flowsheets based on distribution ratios calculated in the SASPE (Spreadsheet Algorithms for Speciation and Partitioning Equilibria) section. The third section of the GTM, SPACE (Size of Plant and Cost Estimation), estimates the space and cost requirements for installing a specific TRUEX process in a glovebox, shielded-cell, or canyon facility. The development of centrifugal contactors for feed- and site-specific applications is also an important part of the effort.

Two other projects are in progress: the application of aqueous biphasic extraction for concentrating and removing plutonium in solid radioactive waste, and development of a solvent extraction process for cleaning up contaminated groundwater.

A. Revisions to Generic TRUEX Model (J. M. Copple, R. J. Jaskot, and J. Zitnik)

The Generic TRUEX Model is a computer program that has been developed to (1) act as a tool for designing TRUEX process flowsheets for specific waste stream compositions, process constraints, and process goals, (2) estimate the space and cost requirements for installing a TRUEX process, and (3) act as a guide to process monitoring and control. Last year the first version of the Generic TRUEX Model, GTM 1.1, was released for the Macintosh and IBM-compatible computers. Since that time new features have been added and improvements have been made to existing code.

In September 1990, the Generic TRUEX Model, version 2.1, for the Macintosh computer was given to the National Energy Software Center (NESC) for distribution. A document entitled "The Generic TRUEX Model Version 2.1 for the Macintosh Computer: Getting Started" was also given to the NESC. This document explains how to use the new version of the model to those users already familiar with GTM 1.1.

Options available in GTM 2.1 include the calculation of aqueous-phase speciation and thermodynamic activities, distribution ratios (D) of extractable species, and solvent radiolytic and hydrolytic degradation, based on user input of aqueous- and organic-phase compositions and other important variables. A list of all the available options in GTM 2.1 is displayed in Table II-1. Several of these options are new and were not available in GTM 1.1. The remaining options have been significantly upgraded from the earlier version of the program.

Table II-1. Available Options in GTM 2.1

Option No.	Description
1	Calculate the complete Generic TRUEX Model for a specific feed solution.
2	Calculate the charge balance, density, ionic strength, speciation, and activities (hydrogen, nitrate, and water) of an aqueous feed solution.
3	Calculate oxalic-acid additions to fission-product-containing waste.
4 ^a	Calculate D values for a user-specified aqueous phase, where the organic phase is assumed to have been pre-equilibrated.
5 ^a	Calculate D values for equilibration of user-specified aqueous and organic phases.
6	Complete flowsheet analysis with user-specified distribution ratios.
7	Generate a TRUEX flowsheet for a specific feed solution.
8	Estimate space and costs for user-specified flowsheet.
9 ^a	Estimate solvent degradation for a specific TRUEX process.
10 ^a	Generate reports from existing TRUEX flowsheets or space and cost calculations.

^aNot included in version 1.1.

New versions of SPACE were included in the model. There are now three versions of SPACE, one for each type of solvent extraction unit (centrifugal contactor, pulsed column, and mixer settler). The model has been changed to show the correct Excel worksheet based on the extraction unit chosen by the user. Since each worksheet requires different information, the SPACE_generate macro also had to be changed. In addition, three new SPACE summary report templates were created. In order that the most useful information could be presented to the user on the summary report, the template had to be specialized for each corresponding SPACE worksheet.

The Generic TRUEX Model, version 2.1, was converted from the Macintosh version to be useable with IBM-PC computers and compatibles. After the conversion, testing of the model located problems with inadequate computer memory. Two of the options required more conventional memory than is available under Microsoft Windows 2.0 or Run-time Windows. Further testing is required to see if Window 3.0 can be used to run all the options available in Table II-1.

B. Development of Spreadsheet Algorithm for Stagewise Solvent Extraction
(R. A. Leonard, D. B. Chamberlain, J. M. Copple, and M. C. Regalbuto)

1. Introduction

The SASSE electronic worksheet was developed for detailed evaluation of proposed TRUEX flowsheets in conjunction with D values calculated by the SASPE worksheet. In addition to establishing that each effluent reaches or exceeds its specified composition, sensitivity analysis using the SASSE worksheet allows one to develop a strategy for process monitoring and control. The SASSE worksheet is designed so that it works for any amount of other-phase carryover. The calculational algorithm gives the steady-state concentration profile for each feed component without requiring any iterations.

Two Excel macros have been written to improve SASSE. The one macro, SASSE_generate, generates SASSE worksheets for flowsheet calculations. When used independently, the appropriate distribution-ratio values or equations must be supplied by the user. Within the Generic TRUEX Model, these ratios are calculated by SASPE. The other macro, report_generator, prepares reports from the results in the SASSE worksheet in tabular and graphical form.

In the work reported here, the SASSE worksheet was revised so that a user can specify (1) an extraction efficiency for each stage and (2) a fixed effluent flow rate for either the organic or aqueous phase at any stage. In previous SASSE calculations, extraction efficiency was assumed to be 100%. By allowing the extraction efficiency to have any value between 1 and 100%, stagewise equipment that does not operate at 100% extraction efficiency can be easily integrated into the GTM, with the number of actual stages being used rather than some reduced number of theoretical stages to approximate the actual extraction efficiency. In the past, the effluent flow has been specified as a fraction of the total flow of that phase from a stage. By including the additional option of fixed effluent flow rates, we were able to incorporate effluents taken at a known rate into the SASSE worksheet without an iterative calculation involving the total flow rate for that phase at that stage. The SASSE_generate macro will be modified to incorporate these revisions in the SASSE worksheet.

2. Extraction Efficiency

In our work with the Argonne centrifugal contactor at organic-to-aqueous (O/A) flow ratios far from 1.0, the extraction efficiency was found to be significantly less than 1.0, that is, less than 100%. In addition, mixer settlers have extraction efficiencies much less than 1.0. To integrate solvent extraction units such as these into the GTM, a method was developed for making extraction efficiency an integral part of the SASSE worksheet.

For the simple flow case shown in Fig. II-1, the effective distribution ratio, $D_{\text{eff},i}$, is given by

$$D_{\text{eff},i} = \frac{y_i}{x_i} \quad (\text{II-1})$$

where x_i and y_i are the aqueous- and organic-phase concentrations of a species, respectively, in the phases that have been separated after passing through the mixing zone in stage i . If these phases are equilibrated, their concentrations are marked with an asterisk, and $D_{\text{eff},i}$ becomes the true distribution ratio, D_i , given by

$$D_i = \frac{y_i^*}{x_i^*} \quad (\text{II-2})$$

Within the GTM, SASPE calculates the D_i values. The extraction efficiency for stage i , E_i , is defined as the amount of a component extracted relative to the amount that would be extracted if stage i were an equilibrium stage. This is written as

$$E_i = \frac{x_{i+1} - x_i}{x_{i+1} - x_i^*} \quad (\text{II-3})$$

The O/A flow ratio for stage i , R_i , is given as

$$R_i = \frac{q_{o,i}}{q_{a,i}} \quad (\text{II-4})$$

where $q_{a,i}$ and $q_{o,i}$ are the total aqueous and organic flow rates, respectively, out of stage i , and the concentration ratio for stage i , S_i , is defined as

$$S_i = \frac{y_{i-1}}{x_i} \quad (\text{II-5})$$

Then, as given by Leonard,¹ $D_{\text{eff},i}$ can be written as

$$D_{\text{eff},i} = \frac{D_i E_i + R_i D_i S_i (1 - E_i) + S_i (1 - E_i)}{1 + R_i D_i (1 - E_i)} \quad (\text{II-6})$$

This is the basic general equation for the simple flow scheme shown in Fig. II-1. In the material balance equations in SASSE and elsewhere, if $D_{\text{eff},i}$ replaces D_i , then the equations still hold, but one can take extraction efficiency into account. Note that this results in an iterative solution since S_i depends on x_i and y_{i-1} , which are calculated by the material balance equations. Within the Excel worksheet, this iterative calculation can be handled without any problem.

In a typical solvent extraction stage, the flows can be more complex. For the general case shown in Fig. II-2, Eq. II-6 can still be used if the incoming organic and aqueous streams are each combined into one stream to calculate an average O/A flow ratio for R_i , and the incoming organic streams are each combined into one stream to calculate an average concentration for the organic phase entering stage i , that is, for y_{i-1} . This average y_{i-1} is used to calculate an average value for S_i . These average values for R_i and S_i are then used in Eq. II-6 to calculate an appropriate $D_{\text{eff},i}$ value.

Fig. II-1. Simple Flow Case for Stage i (see text for explanation of symbols)

Fig. II-2. General Flow Case for Stage i

3. Fixed Effluent Flow Rate

One of the main new features of the revised SASSE is the ability to include sample flow rates in any given stage throughout the process. This has been accomplished by specifying the fraction of

the organic or aqueous flow rate with respect to the total flow exiting from a stage to be used as a sample. These fractions are defined as:

$$FEOI = \frac{\text{organic flow rate for effluent at stage } i}{\text{organic flow rate coming out of stage } i}$$

$$FEAI = \frac{\text{aqueous flow rate for effluent at stage } i}{\text{aqueous flow rate coming out of stage } i}$$

The main reason why FEOI and FEAI were defined is to relate the unknown flow going on to the next stage with the effluent coming out of that stage. This creates only one unknown quantity, the flow going on to the next stage. Because sample flow rate is a known quantity in terms of the flow rate, we have updated our model to include this known term in the flow and material balances. By doing so, the user has the advantage of specifying a flow rate at a sampling point instead of a fraction. Any unknown effluents can still be specified in terms of a fraction. In summary, we have made a fundamental distinction between an effluent of known flow rate and one of unknown flow rate.

C. Modeling of Oxalic Acid Extraction

(D. J. Chaiko)

Extraction data for ^{14}C -labeled oxalic acid at tracer levels (ANL-91/26, pp. 78-82) have indicated that the distribution ratios of this acid are slightly greater than one. However, the present GTM model of oxalic acid extraction assumes that the distribution ratio of oxalic acid is zero. Current efforts are directed toward providing a realistic model for the extraction of this important species. The first step in developing such a model requires separate data for the extraction of oxalic acid by CMPO and TBP. Models of these systems are combined for the TRUEX-NPH solvent. Preliminary modeling efforts have been completed for TBP-dodecane, CMPO-dodecane, and the TRUEX-dodecane solvents and are reported here.

1. Extraction by TBP

Oxalic acid solutions at concentrations of 0.02-0.6M were prepared and contacted with TBP-dodecane solvent at 25°C. The equilibrium oxalic acid concentrations in both the organic and aqueous phases were measured by titration with tetrabutylammonium hydroxide (TBAOH) in isopropanol. Radiotracer experiments (ANL-91/26, pp. 78-82) have shown that the reaction of oxalic acid and TBP is second order with respect to TBP concentration and first order with respect to aqueous-phase oxalic acid concentration. Extraction data collected at these high oxalic acid concentrations by others^{2,3} have shown the same trends.

Taking into account the dissociation of the acid, the fully protonated acid concentration is given by:

$$[\text{H}_2\text{C}_2\text{O}_4] = \frac{[\text{C}_2\text{O}_4^{2-}]_{\text{total}}}{\left[1 + \frac{K_{a1}}{[\text{H}^+]} + \frac{K_{a2}}{[\text{H}^+]^2} \right]} \quad (\text{II-7})$$

The literature values of the acid dissociation constants, K_{a1} and K_{a2} , are 0.0559 and 5.42×10^{-5} , respectively.⁴ All concentrations [] are expressed in molar units. Activity data are not currently

available for aqueous oxalic acid solutions. The extraction model of $\text{H}_2\text{C}_2\text{O}_4$ by TBP is based on the following equilibrium:

where the overbar indicates an organic species. Consequently, the organic-phase oxalic acid concentration is given by

$$\overline{[\text{H}_2\text{C}_2\text{O}_4] [\text{TBP}]_2} = KT [\overline{\text{TBP}}]_{\text{free}}^2 [\text{H}_2\text{C}_2\text{O}_4] \quad (\text{II-9})$$

From the appropriate mass balance equations, the concentrations of free H^+ and TBP are given by Eq. II-7 and the following:

$$[\text{H}^+]_{\text{free}} - [\text{H}^+]_{\text{total}} + [\text{C}_2\text{O}_4]_{\text{total}} \left\{ \frac{2 [\text{H}^+]_{\text{free}}^2 + K_{a1} [\text{H}^+]_{\text{free}}}{[\text{H}^+]_{\text{free}}^2 + K_{a1} [\text{H}^+]_{\text{free}} + K_{a2}} \right\} = 0 \quad (\text{II-10})$$

$$[\overline{\text{TBP}}]_{\text{free}} = \frac{-1 + \sqrt{1 + 8 KT [\text{H}_2\text{C}_2\text{O}_4] [\overline{\text{TBP}}]_{\text{total}}}}{4 KT [\text{H}_2\text{C}_2\text{O}_4]} \quad (\text{II-11})$$

The free hydrogen ion concentration in Eq. II-10 is solved by the Newton-Raphson equation. From a least-squares fit of the extraction data at 0.7 and 1.4M TBP, the value of KT was found to be 0.67M^{-2} . The experimental and calculated extraction isotherms are shown in Fig. II-3.

The fact that this simple model fits the extraction data for 0.7 and 1.4M TBP suggests that organic phase nonidealities due to changes in activity coefficients are insignificant compared with the effects of complex formation. Using ^{14}C -labeled oxalic acid, the extraction data in Fig. II-3 will be extended to include oxalic acid concentrations in the range of 10^{-5} - 10^{-4}M . This will more closely approximate the free oxalic acid concentrations expected in a TRUEX feed.

2. Extraction by CMPO

Extraction data were obtained by contacting equal volumes (5 mL) of aqueous oxalic acid and 0.20M CMPO-dodecane solutions at 25°C . Oxalic acid concentrations were determined by titrating both the organic and the aqueous phases with TBAOH in isopropanol. Contacts at the four highest oxalic acid concentrations listed in Table II-2 produced extremely viscous liquid/liquid interphases. At the three

Fig. II-3. Measured and Calculated Extraction Isotherms for 0.7 and 1.4M TBP-Dodecane Solvents

highest acid concentrations, the initial aqueous-phase oxalic acid concentrations were 0.604, 0.406, and 0.204M. Mass balance calculations at these acid concentrations accounted for only ~80% of the acid, indicating that an undesirable third phase had formed. For modeling purposes, only the data at the two lowest oxalic acid concentrations were used. As mentioned earlier, tracer-level experiments with ^{14}C -labeled oxalic acid indicated that the extraction of $\text{H}_2\text{C}_2\text{O}_4$ is second order with respect to CMPO concentration. Accordingly, oxalic acid extraction was modeled using the following equilibrium:

Table II-2. Equilibrium Oxalic Acid Concentrations and Distribution Ratios with 0.2M CMPO-Dodecane Solvent

Aqueous Oxalic Acid, M	Organic Oxalic Acid, M	Distribution Ratio
0.0166	0.0041	0.247
0.0381	0.0122	0.320
0.0760	0.0177	0.233
0.1525	0.0150	0.098
0.3375	0.0126	0.037
0.5189	0.0116	0.022

By fitting the data at the two lowest oxalic acid concentrations in Table II-2, the extraction constant (KC) was found to be $(28.6\text{M})^{-2}$. In the future, extraction data for the CMPO-dodecane solvent will have to be collected at lower oxalic acid concentrations. By using a combination of ^{14}C -labeled and unlabeled oxalic acid, we could easily extend the extraction data to aqueous-phase oxalic acid

concentrations of about 10^{-4} - 10^{-5} M. This concentration range would then more closely resemble the free oxalic acid concentration in a TRUEX feed.

3. Extraction by TRUEX Solvent

The extraction of oxalic acid by the TRUEX-dodecane solvent was measured at 25°C. As a first approximation, the two separate models for oxalic acid extraction by CMPO and TBP were combined to produce a model for the TRUEX solvent. The values of the extraction constants were unchanged from the single-extractant systems. As the results in Fig. II-4 indicate, however, this model significantly underestimates the extraction data and becomes progressively worse as the oxalic acid concentration increases. This suggests that the stoichiometry of the extracted complex is reduced from second order, with respect to either CMPO or TBP or both, to first order.

Fig. II-4. Measured and Calculated Extraction Isotherm for TRUEX-NPH Solvent at 25°C

To compensate for this behavior, a third, organic-phase oxalic acid complex was postulated. Several possibilities were examined [e.g., $\text{H}_2\text{C}_2\text{O}_4 \cdot (\text{CMPO})(\text{TBP})$, $\text{H}_2\text{C}_2\text{O}_4 \cdot (\text{CMPO})$, and $\text{H}_2\text{C}_2\text{O}_4 \cdot (\text{TBP})$]. Based on a weighted least-squares analysis, the best fit to the data was obtained with the following equilibria:

The complete model of oxalic acid extraction by the TRUEX-NPH solvent contains three extraction equilibria:

$$\overline{[\text{H}_2\text{C}_2\text{O}_4]} = [\text{H}_2\text{C}_2\text{O}_4] \left[KC \cdot [\overline{\text{CMPO}}]_{\text{free}}^2 + KT [\overline{\text{TBP}}]_{\text{free}}^2 + KM [\overline{\text{CMPO}}]_{\text{free}} \right] \quad (\text{II-14a})$$

An expression for the distribution ratio of oxalic acid can be obtained by rearranging Eq. II-14a and taking into account the aqueous-phase dissociation of oxalic acid:

$$D_{\text{H}_2\text{C}_2\text{O}_4} = \frac{KC [\overline{\text{CMPO}}]_{\text{free}}^2 + KT [\overline{\text{TBP}}]_{\text{free}}^2 + KM [\overline{\text{CMPO}}]_{\text{free}}}{\left\{ 1 + \frac{K_{a1}}{[\text{H}^+]} + \frac{K_{a2}}{[\text{H}^+]^2} \right\}} \quad (\text{II-14b})$$

As shown in Fig. II-5, Eq. II-14a fits the extraction data quite well. The values of the extraction constants KC , KT , and KM are 28.6M^{-2} , 0.67M^{-2} , and 16M^{-1} , respectively. To obtain the free CMPO and TBP concentrations, the mass balance equations for the extractants are solved explicitly. Additional extraction data will be collected to more thoroughly validate the extraction model.

Fig. II-5. Measured and Calculated Extraction Isotherms for TRUEX-NPH Solvent at 25°C. The model is represented by Eq. II-14a.

D. Extraction Studies

In this report period, laboratory studies were carried out to determine the extraction behavior of Pu, Np, Th, Am, Cm, and Nd. These studies provide extraction data which will be used in modeling the TRUEX process.

1. Plutonium(IV) Extraction (J. Sedlet)

Plutonium(IV) tends to form polymers and colloidal particles in dilute acid solutions, which have Pu-O bonds that are difficult to break once formed. It is therefore of considerable interest to establish the behavior of polymeric plutonium in the TRUEX extraction process.

a. Procedure

The extraction behavior of a polymeric plutonium(IV) from two different aqueous phases (1.0M HNO₃ and 1.0M HNO₃/2.2M NaNO₃) by TRUEX/NPH solvent was studied. Forward and reverse extractions were performed, as was the removal of plutonium from the final organic phase by 0.05M HF. The extractions were performed without pre-equilibrating the TRUEX solvent with the aqueous phase. The characteristics of the polymer are described in Sec.II.J.2 of this report.

We added 2 mL of the aqueous phase to a culture tube, then 50 μ L of the polymer ($\sim 10^6$ dpm ²³⁹Pu), and the solution was mixed by a vortex stirrer for a few seconds. Next, 2 mL of TRUEX-NPH* solvent was added, and the solution was mixed in a vortex stirrer for 1 min at 25°C. The phases were then separated by centrifuging and transferred to small glass vials, as follows. The top (organic) phase was removed to within a few millimeters of the interface with a transfer pipet. The remaining organic phase and a few millimeters of the bottom (aqueous) phase were removed with a clean pipet. The volume of this "interface" was about 300 μ L. The aqueous phase was then transferred with a clean pipet, the tip of which was wiped with an absorbent tissue before the liquid was discharged. Each phase was sampled, and the alpha activity measured by liquid scintillation counting. To sample the interface, 5 μ L of a 2% Triton surfactant solution was added, the solution shaken to emulsify the mixture, and an aliquot taken for counting. Thus, the interface sample contained a small amount of the two liquid phases. No correction was made for this in calculating the results, but since the bulk phases contained very little alpha activity compared with the interface, a correction was not necessary. The interface was separated and counted because of the tendency of colloids to concentrate at liquid-liquid interfaces.

A reverse extraction was performed by contacting 1 mL organic phase from the forward extraction with 1 mL fresh aqueous solution. The extraction, separation, sampling, and counting were performed as described for the forward extraction.

The ability of hydrofluoric acid to strip plutonium(IV) was measured by contacting 0.5 mL organic phase from the reverse extraction with 0.5 mL of 0.05M HF. The procedure was the same as previously described, except that the interface was not separated and counted.

b. Results

The distribution ratios and mass balances for the forward and reverse extractions are given in Table II-3. The distribution ratios were very low compared to Pu(IV) monomer, ranging from 1.0 to 12.3. Monomeric Pu(IV) gives ratios of 10^4 - 10^5 with the aqueous phases used here. The mass balances were very poor, ranging from 17% to 79%. The recoveries were much better in the reverse extraction, indicating a more tractable plutonium species in the organic phase after the forward extraction. Possible explanations for the plutonium losses are adsorption on the glass walls of the culture tube, inaccurate sampling of the interface, and inaccurate counting of the alpha activity. If the latter is the problem, it may be due to phase separation in the scintillation cocktail (Insta-Gel XF). The alpha particle spectra of some of the samples exhibited a severely degraded spectrum.

The results of the HF stripping are given in Table II-4. The extracted plutonium species is poorly complexed and stripped by HF. In this case, the surface and interface problems have disappeared, since the mass balances were good.

*1.4M TBP and 0.2M CMPO dissolved in C₁₂-C₁₄ normal paraffinic hydrocarbon diluent.

Table II-3. Extraction of Plutonium Polymer by TRUEX-NPH Solvent

Aqueous Phase	Dist. Ratio		Mass Balance ^a	
	For.	Rev.	For.	Rev.
1.0M HNO ₃	1.0	7.9	30% ^b	64% ^c
1M HNO ₃ /2.2M NaNO ₃	8.0	12.3	17% ^d	79% ^e

^aPercent of plutonium recovered from organic, aqueous, and middle (interface) phases.

^bOf the amount recovered, 79% was in the interface and 21% was in the two liquid phases.

^cThe corresponding figures for this extraction are 15% in the interface, 85% in the liquid phases.

^dThe corresponding figures for this extraction are 74% in the interface, 26% in the liquid phases.

^eThe corresponding figures for this extraction are 9% in the interface, and 95% in the liquid phases.

Table II-4. Removal of Plutonium Polymer from TRUEX-NPH by HF

	Dist. Ratio	Mass Balance	Pu Removed
1.0M HNO ₃	4.0	106%	20%
1.0M HNO ₃ /2.2M NaNO ₃	5.8	94%	16%

The culture tubes used for the forward and reverse extractions were later rinsed with 1 mL of 1M HF. The HF solution was vortexed for 5 s, allowed to stand in the tubes for 1.5 h, then removed and counted. Thirty percent of the added plutonium was recovered from the culture tube used in the forward extraction from 1M HNO₃ and 59% from the 3.2M NO₃ forward extraction. The amount recovered from the culture tubes used for the reverse extraction was negligible, but these tubes contained only plutonium that had extracted into TRUEX solvent. These results show that polymeric plutonium has a strong affinity for glass, and probably other particulates that collect at interfaces, at least in strong acid solution. These results call for a study of methods to de-polymerize plutonium in waste solutions to be processed by the TRUEX procedure.

2. Neptunium Extraction (J. Sedlet)

Distribution ratios for Np(IV) between aqueous solutions containing a high nitrate ion concentration (3.2M) and standard TRUEX-NPH solvent were measured at 25°C as a function of nitric and sulfuric acid concentrations. The experimental procedure was the same as described for curium extraction in ANL-91/26, pp. 89-90, with one major exception. In the studies with curium, the ²⁴⁴Cm tracer in dilute nitric acid solution was added to the aqueous phase. For the neptunium measurements, a

^{239}Np - ^{237}Np tracer solution was prepared by extracting the neptunium from a reducing solution, 2M $\text{HNO}_3/0.1\text{M}$ $\text{Fe}(\text{NO}_3)_2/0.2\text{M}$ $\text{NH}_2\text{OH}\cdot\text{HNO}_3$ [to maintain the $\text{Np}(\text{IV})$ state], into TRUEX-NPH pre-equilibrated with nitric acid. For the measurements, 20 to 40 μL of this "solvent-loaded" tracer was added to 2 mL of the organic phase. The ^{237}Np , which constituted the bulk of the neptunium mass, was present at a concentration of 10^{-5}M . As was done in the curium experiments, the organic phase was not pre-equilibrated, so the acid concentrations given below are the initial concentrations only. In addition, only one extraction of each organic phase was performed. This extraction should be termed a reverse extraction since the neptunium was initially present in the organic phase. Aliquots of each phase were analyzed by counting the ^{239}Np gamma rays with a sodium iodide crystal in a Packard Instrument Co. spectrometer.

Two sets of experiments were performed. In one set, the nitric acid concentration was varied from 0.02 to 1.0M , while the nitrate ion concentration was kept constant at 3.2M by varying the sodium nitrate concentration. The aqueous solutions were also made 0.02M in $\text{Fe}(\text{NO}_3)_2$ and 0.04M in $\text{NH}_2\text{OH}\cdot\text{HNO}_3$ (to maintain a reducing environment), and 0.01M in sulfamic acid to destroy nitrite ion, which catalyzes the oxidation of $\text{Np}(\text{IV})$ to $\text{Np}(\text{VI})$ in strong nitric acid solutions. The results are given in Table II-5 and Fig. II-6.

In the absence of sodium nitrate, the distribution ratios for $\text{Np}(\text{IV})$ with pre-equilibrated solvent ranged from about 10 at 0.02M HNO_3 to about 10^4 at 1M HNO_3 (ANL-91/26, pp. 94-96). The distribution ratios increase sharply with increasing nitric acid concentration, in contrast with the behavior of $\text{Am}(\text{III})$ and $\text{Cm}(\text{III})$. The distribution ratios for the trivalent actinides decrease with increasing nitric acid concentration. This decrease is attributed to the competition between the actinide ion and nitric acid for the CMPO, since extraction of nitric acid is quite high in strong nitrate solutions, and the formation of the $\text{CMPO}\cdot\text{HNO}_3$ complex reduces the free CMPO concentration. In the case of neptunium, its complex with CMPO is evidently strong enough to displace nitric acid from the CMPO, and the distribution ratio becomes quite large above 0.1M HNO_3 . At 0.02M $\text{HNO}_3/3.18\text{M}$ NaNO_3 the ratio for $\text{Cm}(\text{III})$ is greater than for $\text{Np}(\text{IV})$, while at 0.1M $\text{HNO}_3/3.1\text{M}$ NaNO_3 , the $\text{Np}(\text{IV})$ ratio becomes larger than for $\text{Cm}(\text{III})$.

In the second set of experiments, sulfuric acid (0.01 to 0.05M) was used in addition to nitric acid and sodium nitrate. Sulfate ion forms a weak complex with neptunium. Ferrous ion was not used as a reducing agent since it is oxidized to ferric ion, which also complexes sulfate. Hydroxylamine nitrate (0.02M) was added to maintain a reducing environment.

Table II-5. Distribution Ratios for $\text{Np}(\text{IV})$ between Aqueous Nitrate Solutions and TRUEX-NPH Solvents at 25°C

Conc., <u>M</u>		Dist. Ratio
HNO_3	NaNO_3	
0.02	3.18	386
0.10	3.10	760
0.50	2.70	6.35×10^3
1.0	2.20	2.92×10^5

Fig. II-6. Distribution Ratios for Np(IV) between Aqueous Nitrate Solutions and TRUEX-NPH Solvent at 25°C as Function of Nitric Acid Molarity. The total nitrate ion concentration was kept constant at 3.2M by adjusting the sodium nitrate concentration.

The results from the second set of experiments are shown in Table II-6 and Fig. II-7. The data show that the distribution ratios decrease with increasing sulfuric acid concentration, as would be expected if a Np(IV)-sulfate complex is formed. The results fall into two separate groups: the two lower acid concentrations with ratios of about 650, and the two higher acid concentrations with ratios of about 500. However, if the result at 0.02M H_2SO_4 is neglected, the remaining three points fall approximately on a straight line with a slope of about 0.13. Data at higher sulfuric acid concentrations are needed to determine the composition of the complex. A major discrepancy in the results is the high ratios at all sulfuric acid concentrations, compared to the ratio of 386 at 0.02M in the absence of sulfuric acid (Table II-5).

Table II-6. Distribution Ratios for Np(IV) between Sulfuric Acid/Nitric Acid/Sodium Nitrate Solutions and TRUEX-NPH Solvent at 25°C*

[H ₂ SO ₄], M	Dist. Ratio
0.01	640
0.02	653
0.03	493
0.05	490

*The nitric acid and sodium nitrate concentrations were maintained at 0.02M and 3.18M, respectively, in all four solutions.

Fig. II-7. Distribution Ratios for Neptunium between Sulfuric Acid and TRUEX-NPH Solvent at 25°C and Constant Nitric Acid and Sodium Nitrate Concentrations of 0.02M and 3.18M, respectively, as Function of Sulfuric Acid Molarity

3. Thorium Extraction (J. Sedlet)

The behavior of thorium in the TRUEX separation process is being studied with the ^{230}Th isotope, an alpha emitter with a half-life of 7.54×10^4 years and a specific activity of 4.6×10^7 dpm/mg. Effort in this period focused on preparing ^{230}Th stock solutions for later distribution ratio measurements. To this end, 20 mg of ^{230}Th as thorium dioxide was obtained from the Isotope Distribution Office, Oak Ridge National Laboratory (ORNL). The oxide was dissolved in the vial (about 4 mL capacity) in which it was received by adding 2 mL 5M HNO_3 and 4 μL 1M HF and heating the vial under a heat lamp on a hot plate on low setting for about 3.5 h. The HF , present at a concentration of 0.002M, is needed as a catalyst to increase the dissolution rate of thorium and its compounds. The solution was evaporated to dryness and the thorium dissolved in 0.5 mL 1M HNO_3 . This solution was transferred to a 13 mm culture tube with several portions of 1M HNO_3 , totaling 1 mL, in preparation for a radiochemical purification of the thorium.

A portion of the same ^{230}Th stock from ORNL was obtained in May 1989. This tracer gave substantially greater distribution ratios in reverse extractions than in forward extractions, an indication that more than one thorium species was present, or that sufficient ^{226}Ra and ^{224}Ra decay products (of ^{230}Th and ^{232}Th , respectively) were present to warrant purification of the thorium. This was done by extracting the thorium into TRUEX-NPH to obtain a "solvent-loaded" stock tracer solution. The extraction was performed from 0.1M HNO_3 into pre-equilibrated solvent, and was satisfactory. However, the distribution ratio of thorium from 0.1M HNO_3 is only about 10.

We thus decided to extract the thorium from 1.0M HNO_3 , since its distribution ratio is about 5×10^3 . The extraction from the 1M HNO_3 solution of thorium was performed at an O/A phase ratio of one into acid pre-equilibrated TRUEX-NPH, and three phases were obtained. Evidently the combined thorium and nitric acid concentrations were too high, and loaded the solvent beyond its capacity. The thorium concentration (in 1.5 mL of solution) was 0.058M. At a CMPO concentration of 0.2M, if only two moles of CMPO are needed to complex the thorium, more than 50% of the CMPO in the solvent is

required to complex the thorium. If four moles are needed, obviously the CMPO concentration is inadequate.

The two top (organic) phases were removed to a second culture tube and scrubbed with 1 mL of 0.1M HNO_3 to reduce the nitric acid concentration. The third phase appeared again but was smaller in volume; however, the solution became cloudy. Perhaps some thorium had precipitated. Pre-equilibrated TRUEX-NPH (0.4 mL) and 1 mL of 0.1M HNO_3 were next added to the two organic phases, the mixture was vortexed and centrifuged. The third phase remained. Next, 0.5 mL TRUEX-NPH was added. The mixture was not pre-equilibrated to avoid adding more nitric acid, but it was vortexed and centrifuged. The third phase remained, but appeared to have diminished. The upper phase was initially cloudy, but cleared on standing. Since the third phase was judged to be too small in volume to contain much thorium mass, we decided to separate and analyze the top phase for alpha activity. This solution (estimated volume, 2.5 mL) contained about 8.4×10^8 dpm of alpha activity, or about 93% of the calculated ^{230}Th alpha activity originally present. Since 5-10 μL aliquots of this solution are sufficient to measure a distribution ratio of 10^4 with good counting statistics, we decided to use this solution as the stock tracer. All other solutions from this purification were saved for further study. The original solution of 1M HNO_3 from which the thorium was extracted contained about 3.8×10^7 dpm of alpha activity (which includes radium isotopes and their daughters), or about 4.2% of the ^{230}Th alpha activity. The 0.1M HNO_3 wash of the TRUEX-NPH contains 2.6×10^6 dpm, or 0.3% of the ^{230}Th alpha activity.

4. Americium Extraction (D. R. Fredrickson)

Experiments have been run at 50°C to study the effects of various complexants on the extraction of ^{241}Am by TRUEX-NPH. The complexants included (1) oxalic acid, (2) sulfuric acid, (3) phosphoric acid, (4) hydrofluoric acid, and (5) nitrate. In addition, extractions were done at 50°C with ten concentrations of nitric acid alone. The present study extends the work previously done at 25°C on extractions of ^{241}Am with TRUEX-NPH from a series of complexants.

Our standard technique for performing distribution ratio measurements with radioactive tracers has generally begun by pre-equilibrating the organic phase with all the aqueous phase constituents but the tracer. When distribution ratios of these constituents are low (≤ 0.3), pre-equilibration is simple. The solvent is contacted with fresh aqueous solution three times at an organic-to-aqueous (O/A) volume ratio of 1/3. However, pre-equilibration is impractical when (1) nitrate salts are in the aqueous phase, causing the distribution ratio of nitric acid to be >1 , or (2) HF ($D \sim 0.9$) or oxalic acid ($D \approx 2$) are present. Pre-equilibration at higher temperatures causes difficulty in obtaining reproducible results due to inabilities in maintaining the solutions at constant temperature.

The experimental procedure used here differs from that ordinarily used, the main difference being no pre-equilibration and only a forward extraction. This procedure also requires a titration of the aqueous phase (for acidity), which is done in separate experiments under identical conditions except without the ^{241}Am spike. All of the data reported will require an adjustment of the actual acid concentration when titration results become available. This is because acid pre-equilibration was not done.

The results were obtained with 2 mL of organic phase and 2 mL of aqueous phase. The aqueous phase was spiked with ^{241}Am (and mixed), and then the organic phase was added. At this point, a general procedure developed for the 50°C measurements was followed. This includes equilibration of the mixture in a 50°C water bath for 15 min followed by three 20-s contacts, with 5-min water bath equilibrations in between, and then 5 min in the bath before centrifuging. Centrifuging was for 2 min

followed by 5 min in the 50°C water bath. Samples were then separated, and aliquots taken and counted. Most of the samples counted were 50 µL for the organic phase and 200 µL for the aqueous phase.

In the past, we have had problems attaining consistent D values at 50°C. As a starting point, we tested ten concentrations of nitric acid (0.02, 0.05, 0.10, 0.20, 0.50, 1, 2, 3, 6, and 8M) at 50°C. In addition, selected concentrations (0.05, 0.20, 0.50, and 3M) were re-run on a different day. All of the results are presented in Table II-7. Since the results for the duplicate runs were consistent, work was started with complexants at 50°C.

Table II-7. Distribution Ratios for ^{241}Am Extraction^a by TRUEX-NPH at 50°C

$[\text{HNO}_3]$, ^b M	D_{Am}	$D_{\text{Am}}(\text{repeat})$
0.02	0.0139	
0.05	0.066	0.067
0.10	0.229	
0.20	0.626	0.636
0.50	2.73	2.70
1	5.62	
2	9.03	
3	10.1	10.1
6	8.39	
8	7.69	

^aModified extraction technique, i.e., no pre-equilibration of the organic solvent with nitric acid.

^bInitial concentration before contact at an O/A volume ratio of one.

Tables II-8 and II-9 summarize the data obtained for oxalic acid (0.01 to 0.05M) with 0.02M and 0.1M nitric acid (total nitrate 3.2M), respectively. (At 0.02M nitric acid, however, oxalate at 0.04M or 0.05M could not be prepared.) Tables II-10 and II-11 summarize data for sulfuric acid and phosphoric acid (0.01 to 0.5M), respectively, with 0.02M HNO_3 and 3.18M NaNO_3 . Table II-13 summarizes data for 0.02 to 1.0M HNO_3 and a total of 3.2M nitrate.

All these extraction data will be used in developing models for calculating D_{Am} at 50°C with the GTM.

Table II-8. Distribution Ratios for ^{241}Am Extraction^a by TRUEX-NPH at 50°C with Oxalic Acid, 0.02M HNO_3 , ^b and 3.18M NaNO_3

[Oxalic Acid], ^b M	D_{Am}
0.01	29.7
0.02	15.9
0.03	10.6

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-9. Distribution Ratios for ^{241}Am Extraction^a by TRUEX-NPH at 50°C with Oxalic Acid, 0.1M HNO_3 ,^b and 3.1M NaNO_3

[Oxalic Acid], ^b M	D_{Am}
0.01	112.0
0.02	71.9
0.03	49.3
0.05	29.7

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-10. Distribution Ratios for ^{241}Am Extraction^a by TRUEX-NPH at 50°C with Sulfate, 0.02M HNO_3 ,^b and 3.18M NaNO_3

$[\text{H}_2\text{SO}_4]$, ^b M	D_{Am}
0.01	304
0.02	253
0.03	230
0.05	187

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-11. Distribution Ratios for ^{241}Am Extraction^a by TRUEX-NPH at 50°C with Phosphate, 0.02M HNO_3 ,^b and 3.18M NaNO_3

$[\text{H}_3\text{PO}_4]$, ^b M	D_{Am}
0.01	317
0.02	293
0.03	251
0.05	220

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-12. Distribution Ratios for ^{241}Am Extraction^a by TRUEX-NPH at 50°C with Fluoride, 0.1M HNO_3 ,^b and 3.1M NaNO_3

[HF], ^b M	D_{Am}
0.01	273
0.02	262
0.05	229
0.10	152
0.20	118
0.50	51.4

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-13. Distribution Ratios for ^{241}Am Extraction^a by TRUEX-NPH at 50°C with HNO_3 and NaNO_3

[HNO_3], ^b M	[NaNO_3], M	D_{Am}
0.02	3.18	368
0.1	3.1	273
0.5	2.7	90.8
1.0	2.2	39.4

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

5. Curium Extraction (D. R. Fredrickson)

Experiments have been run at 50°C to determine the effect of various complexants on the extraction of ^{244}Cm by TRUEX-NPH. The complexants are (1) oxalic acid, (2) sulfuric acid, (3) phosphoric acid, (4) hydrofluoric acid, and (5) nitrate. In addition, extractions were done at 50°C with ten concentrations of nitric acid alone. All of the experiments reported used the procedure described in Sec.II.D.4.

Results for the extraction with nitric acid alone are presented in Table II-14. Tables II-15 and II-16 summarize the data for oxalic acid (0.01 to 0.05M) at 0.02M and 0.1M nitric acid (total nitrate 3.2M), respectively. Tables II-17 and II-18 summarize data for sulfuric acid and phosphoric acid (0.01 to 0.05M), respectively, with 0.02M HNO_3 and 3.18M NaNO_2 . Table II-19 summarizes data for HF (0.01 to 0.5M) with 0.1M HNO_3 and 3.2M nitrate. Table II-20 summarizes data for 0.02 to 1.0M HNO_3 and a total of 3.2M nitrate.

Table II-14. Distribution Ratios for ^{244}Cm Extraction^a
by TRUEX-NPH at 50°C with HNO_3 Alone

$[\text{HNO}_3],^b \text{ M}$	D_{Cm}
0.02	0.0102
0.05	0.048
0.10	0.160
0.20	0.484
0.50	1.74
1	3.86
2	6.12
3	7.45
6	6.63
8	6.69

^aModified extraction technique, no pre-equilibration.

^bInitial aqueous-phase concentration before equilibration
with TRUEX-NPH solvent at 50°C.

Table II-15 Distribution Ratios for ^{244}Cm Extraction^a
by TRUEX-NPH at 50°C with Oxalate, 0.02M
 HNO_3 ,^b and 3.18M NaNO_3

$[\text{H}_2\text{C}_2\text{O}_4],^b \text{ M}$	D_{Cm}
0.01	19.28
0.02	10.52
0.03	7.04
0.03	7.02

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-16. Distribution Ratios for ^{244}Cm Extraction^a by
TRUEX-NPH at 50°C with Oxalate, 0.1M
 HNO_3 ,^b and 3.1M NaNO_3

$[\text{H}_2\text{C}_2\text{O}_4],^b \text{ M}$	D_{Cm}
0.01	83.9
0.02	53.2
0.03	37.9
0.05	21.6

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-17. Distribution Ratios for ^{244}Cm Extraction^a by TRUEX-NPH at 50°C with Sulfate, 0.02M HNO_3 ,^b and 3.18M HNO_3

$[\text{H}_2\text{SO}_4]$, ^b M	D_{Cm}
0.01	239
0.02	210
0.03	190
0.05	156

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-18. Distribution Ratios for ^{244}Cm Extraction^a by TRUEX-NPH at 50°C with Phosphate, 0.02M HNO_3 ,^b and 3.18M NaNO_3

$[\text{H}_3\text{PO}_4]$, ^b M	D_{Cm}
0.01	254
0.02	241
0.03	220
0.05	201

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-19. Distribution Ratios for ^{244}Cm Extraction^a by TRUEX-NPH at 50°C with Fluoride, 0.10M HNO_3 ,^b and 3.1M NaNO_3

$[\text{HF}]$, ^b M	D_{Cm}
0.01	207
0.02	199
0.05	182
0.10	160
0.10	145
0.20	92.8
0.20	93.3
0.50	42.9

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

Table II-20. Distribution Ratios for ^{244}Cm Extraction^a by TRUEX-NPH at 50°C with HNO_3 and NaNO_3

$[\text{HNO}_3], ^b \text{ M}$	$[\text{NaNO}_3], \text{ M}$	D_{Cm}
0.02	3.18	302
0.1	3.1	218
0.5	2.7	67.6
1.0	2.2	29.3

^aModified extraction technique, no pre-equilibration.

^bInitial concentration before equilibration.

All the data will be used to develop models for calculating D_{Cm} at 50°C in an upcoming version of the GTM.

6. Aqueous Solution Behavior of Neodymium (I. R. Tasker and J. J. Takarewski)

Prior experimental work⁵ demonstrated some unusual extraction behavior of americium. For example, if the extraction of americium at low nitrate concentrations can be represented as

then one would expect a plot of $\log D$ vs. $\log \{\text{NO}_3\}$ to have a slope of about 3. The slope is, in fact, closer to 2. The values of the first and second overall stability constants inferred from in-house work (86.5 and 63.2, respectively) are nearly two orders of magnitude larger than the literature values (1.89 and 0.89, respectively).⁶ Another unexpected finding was that the organic titration data of organic solutions containing Nd^{3+} and nitric acid showed large deviations from expected results. The most obvious explanation for these results would be that hydrolysis of Am^{3+} is occurring:

In an attempt to clarify this situation and to give some assurance that hydrolysis products are not complicating our modeling efforts, a series of experiments involving the extraction of Nd^{3+} into TRUEX solutions has been planned; Nd^{3+} was chosen as both a representative of the range of rare earth ions and as a model for Am^{3+} . In experiments such as these, accurate analyses of Nd^{3+} and other rare earth ions, both in the aqueous and organic phases, are important. However, present analysis for all rare earth metal ions is done by inductively coupled plasma/atomic emission spectroscopy (ICP/AES), an analytical method that offers an accuracy only in the ~5-20% range for complex matrices. Moreover, in the case of the organic phase, it has been necessary to employ the time-consuming procedure of reverse extraction into an aqueous medium. In an effort to address these problems prior to undertaking the extraction experiments, another method for metal analysis was sought. Currently, a complexometric method is being tested for determining neodymium concentrations. It is hoped that a rapid and easy

spectrophotometric method will eventually become available. In the interim, the complexometric titration described below will serve as an absolute, gravimetric analysis of solutions to be used for the spectrophotometric calibration.

Problems can occur when using tracer levels of material to perform distribution ratio measurements; for example, under low acid conditions, where D values and nitric acid extraction are small, the presence of small amounts of strongly complexing acidic impurities in the CMPO can greatly affect experimental results. This problem can be mitigated by treating the extractant with diazomethane to methylate the acid impurities or by using a carrier to "soak up" the impurity. The availability of a method for easily analyzing concentrations of rare earth ions at greater than tracer levels opens up wider possibilities of experimentation, such as the more accurate investigation of loading effects of rare earths.

a. Analytical Methods

Earlier work on the organic-phase titration of TRUEX-TCE (that had been contacted with a solution of neodymium in nitric acid) with TBAOH in isopropanol showed significant deviations from the titration results predicted by the GTM. A detailed inspection of the previous experimental method allowed certain improvements to be made when the procedure was repeated. The results of the new and old experiments are shown in Table II-21, and the new results are in much better agreement with the GTM predictions.

Table II-21. Neodymium Concentrations from Titration of TRUEX-TCE Contacted with 1.0M HNO₃/Nd³⁺ Solution

Year	Conc., M			% Error ^d
	[Nd]aq ^a	[Nd] EP2 ^b	[Nd] GTM ^c	
1989	0.01	0.024	0.00919	+160
1990	0.01	0.010	0.00919	+8.8

^aBased on weighed amount of Nd(NO₃)₃·6H₂O.

^bBased on volume at second end point and Nd³⁺:3 TBAOH.

^cFrom Generic TRUEX Model.

^d([Nd] EP2 - [Nd] GTM)/[Nd] GTM x 100%.

Regarding the aqueous phase titrations of Nd³⁺ systems, it is well known that accurately titrating strong acid is sometimes difficult in the presence of hydrolyzable metal ions. To investigate the effect of Nd³⁺ concentration on the titration of nitric acid, two systems were studied. In both cases, the bare nitric acid was titrated, and the same acid was titrated with a weighed amount of Nd(NO₃)₃·6H₂O added. The results are given in Table II-22. It is clear that in systems with high [H⁺]/[Nd³⁺] ratios, the acid may be titrated with no effect from the neodymium. When [H⁺]/[Nd³⁺] = 7.6, however, the error in [H⁺] increases beyond the error associated with the method.

Though the results of these experiments eased concern about the anomalous behavior observed in these systems, the need for a more effective means of analysis remained. To start the search for a metal analysis technique, thermogravimetric analysis (TGA) was investigated. This method was found to be complicated and equipment intensive.⁷

Table II-22. Neodymium Concentrations from Titration of Nitric Acid in Presence of Neodymium

Conc., M		[H ⁺]/[Nd ³⁺]	No. of Samples	Rel. A.D. ^c	Error in [H ⁺] ^d
[Nd ³⁺] ^a	[H ⁺] ^b				
0	0.3044	-	3	0.49%	-
0.0390	0.2960	7.6	3	0.47%	-2.8%
0	0.2880	-	3	0.17%	-
0.0120	0.2881	24	1	-	+0.035%
0.0084	0.2892	24	1	-	+0.42%

^aBased on weighed amount of Nd(NO₃)₃·6H₂O.

^bBased on first end point.

^cRelative average deviation among sample population.

^dUsing the neat acid solution as the correct value.

The results of further literature search revealed that Misumi and Taketatsu⁸ have reported a complexometric titration method for the accurate determination of rare earth elements. The rare earth oxalate is precipitated from a weak acid aqueous solution of the 3+ ion. The oxalate is filtered and dissolved in excess standard EDTA and ammonia. The pH is adjusted to 10 with NH₄OH/NH₄Cl and ammonia. An Eriochrome black T solution is added, and the mixture is back titrated with standard MgSO₄. The limit of analysis ranges from 1 to 5 mg, and the error of the method varies from 0.62% for Nd³⁺ to 2.2% for La³⁺. Since the precipitate must stand overnight, the procedure requires two days but is not otherwise time-consuming.

The following is an abbreviated procedure which incorporates relevant comments from Skoog and West⁹ and Welcher.¹⁰

b. Preparation of Reagent Solutions

One-half gram of Eriochrome black T (EBT) and 4.5 g hydroxylamine hydrochloride are dissolved in absolute ethanol, and the total volume is filled up to 100 mL with ethanol. It may be very difficult to dissolve the solids in this volume of ethanol. However, it is not important that all of the solid be dissolved. The solution deteriorates quickly and may need to be replaced every two weeks. Refrigeration of the solution slows deterioration.

To prepare the buffer solution, dilute 570 mL of concentrated NH₃ and 70 g NH₄Cl to about one liter. A standard 0.001M magnesium sulfate solution is prepared by dissolving 0.25 g MgSO₄·7H₂O in distilled water and diluting to one liter. A standard 0.001M disodium-EDTA dihydrate solution is prepared by dissolving 0.37 g EDTA in distilled water and diluting to one liter.

A standard 0.001M calcium solution is prepared by dissolving 0.1 g of dried primary standard calcium carbonate in the least amount of dilute hydrochloric acid. The resulting calcium chloride solution is diluted to exactly one liter. Care must be taken in dissolving the calcium carbonate or solid material will be lost through entrainment.

c. Standardization of Solutions

Among the complexing agents EDTA is apparently unique in forming 1:1 complexes with cations regardless of their valence. Thus,

where M^{n+} is a metal ion with charge $n+$, and Y^{4-} is a metal-complexing ion. The EDTA solution is standardized against the primary standardized Ca^{2+} solution. A 10 mL aliquot of the Ca^{2+} solution is pipetted into an Erlenmeyer flask. Ten millimeters of distilled water, 2.5 mL of the buffer solution, one drop of 1% $MgCl_2$ solution, and five drops of the EBT solution are added. Titrate with the EDTA solution until no trace of purple color remains. A blank determination must be made using water, buffer, magnesium chloride, and indicator in the same amounts as in the titrations.

The $MgSO_4$ solution is standardized by direct titration with EDTA. Pipet 10 mL of the $MgSO_4$ solution into an Erlenmeyer flask and add 10 mL of water, 2.5 mL of buffer solution, and five drops of EBT solution. This mixture is titrated with EDTA until all traces of red color have been removed.

d. Precipitation, Dissolution, and Titration of $Nd_2(C_2O_4)_3$

The amount of solution to be analyzed, which contains about 2 mg of Nd^{3+} ion, is calculated. This volume is then diluted to 10 mL with distilled water and warmed at $60^\circ C$ for a few minutes; 20 mL of saturated oxalic acid solution is added. The solution is again warmed for several hours and left to stand overnight. The volume must be maintained or oxalic acid crystallization becomes a problem. Good neodymium oxalate crystal formation has been achieved by allowing the covered beakers to remain on the hot plate as they cool.

The precipitate is then filtered using a micro glass filter (30 fine porosity) by suction and washed with saturated oxalic acid solution. Two millimeters of $2M$ NH_3 is added. The filter is placed in a 150 mL beaker, and 25 mL of $0.001M$ EDTA is pipetted into the beaker. The neodymium oxalate dissolves as the complex anion, with the excess EDTA (HY^{3-}) remaining in solution. The reaction proceeds as

Misumi and Taketatsu⁸ used disodium EDTA (H_2Y^{2-}) for their work, and yet Eq. II-18 is for trisodium EDTA. Nonetheless, the rare earth-EDTA complex is known to be a 1:1 complex.

Two millimeters of $2M$ ammonia is added, and the mixture is warmed again carefully for about five minutes. When the precipitate is completely dissolved, the solution is cooled rapidly. The filter is removed from the beaker as it is rinsed with distilled water.

The pH of the solution is adjusted to 10 with 2 mL of the buffer solution and additional $2M$ ammonia. The total volume is filled up to about 60 mL with distilled water. Five drops of

the EBT indicator solution are added. The excess EDTA is back titrated with standard 0.001M MgSO_4 . At the end point, the blue color changes completely to red. The end point is not sharp, and practice is needed to obtain suitable precision.

e. Preparation of Standard $\text{Nd}(\text{NO}_3)_3$ Solution

Having obtained an analytical technique of suitable accuracy, we then needed a means of preparing a pure solution of neodymium. Spedding and Pikal¹¹ have reported a procedure for the preparation of rare earth nitrate and chloride solutions with accurately known concentrations. A modified procedure has been adopted to prepare a 0.8M $\text{Nd}(\text{NO}_3)_3$ solution from Nd_2O_3 and HNO_3 , where excess Nd_2O_3 is dissolved in a measured amount of standardized HNO_3 .

The Nd_2O_3 was 99.999% pure (rare earth oxide) obtained from Alfa Inorganics. To begin, 16.5217 g of the oxide (molecular weight = 336.54) was added to 49.00 mL of 5.984M HNO_3 . The beaker containing the solution was allowed to stand in a sonic water bath for an hour to ensure complete reaction. A small amount of solid remained in the beaker. This excess oxide was suction filtered through a fine sintered glass filter.

Spedding and Pikal suggest that the equivalence point of the hydrolysis reaction

can be determined by removing "a small portion of the solution." Since the scale of the procedure is never discussed, it is not possible to know what is meant by "small." Certainly, the titration aliquot must be small with respect to the total solution volume. Since the volume is not accurately known, the amount of Nd^{3+} removed by the aliquots must be estimated. When small aliquots are taken, errors in estimating the total volume will have a small effect on the final concentration.

The volume was estimated to be 175 mL. Two 50 μL and two 100 μL aliquots were removed and titrated with 0.0603M HNO_3 . Only 0.17% of the total Nd^{3+} was removed by this operation. The aliquots were treated separately. Each was diluted to about 10 mL with distilled water and titrated with the 0.0603M HNO_3 . The titration curves were not like the typical strong acid-weak base curves reported by Spedding and Pikal.¹¹ The pH of the diluted stock solution was about 3.5. It was impossible to determine the equivalence pH of the reaction from the titration curves. Following Spedding and Pikal's instructions, the solution was heated (90°C for 90 min) to react with HNO_3 .

The stock solution had a pH of 1.1. Since this pH is below the expected equivalence pH, we assumed that the hydrolysis of $\text{Nd}(\text{NO}_3)_3$ would be suppressed. No further titration of the stock solution was attempted.

The density of the stock solution and its total mass were measured. The concentration of the stock solution was calculated from the following data:

density: 1.2129 g/mL
 total mass of solution: 146.2044 g
 weight Nd_2O_3 : 16.5217 g (99.999%)
 volume HNO_3 : 49.00 mL (5.984 M)

Total Nd^{3+} removed as 100 and 50 μL aliquots: 0.171%

The concentration of Nd^{3+} in the stock solution was calculated according to the equivalent amount of standard HNO_3 . The concentration of the stock was found to be 0.8094M $\text{Nd}(\text{NO}_3)_3$.

From this point, R&D is now proceeding in two directions. In the first, from the 0.8094M $\text{Nd}(\text{NO}_3)_3$ stock solution will be prepared a series of solutions of varying Nd and NO_3^- concentration for use in extraction experiments with TRUEX-NPH. It is hoped that the results of these experiments will shed light on the source of the aforementioned anomalies and aid in our understanding of loading behavior. The second direction taken is the development of an acceptably accurate, rapid method of neodymium analysis using a spectrophotometer. A series of standard solutions of neodymium in aqueous and organic media has been prepared for ultraviolet/visible spectroscopic measurement. Upon obtaining standard absorbance concentration curves for these solutions, we will investigate the potential in using a spectrophotometer for direct measurement of neodymium concentration in aqueous and TRUEX-NPH solution.

7. Use of ^{241}Am Extraction as Purity Check for CMPO
(D. R. Fredrickson)

The quality of the CMPO purified by our standard procedure¹² was checked by measuring the americium distribution ratios between TRUEX-NPH and 0.01M and 2M HNO_3 at 25°C.

To start, three different batches of CMPO were used to prepare samples containing 100 mL of 0.2M CMPO with 1.4M TBP in NPH. Distribution ratio measurements were made in the conventional manner, where an acid pre-equilibration of the TRUEX-NPH was done first. The acid-equilibrated TRUEX-NPH was then contacted with an aqueous phase which had been spiked with ^{241}Am . The samples prepared in this manner were labeled MIKE #1, MIKE #2, and CLIFF #3. In addition, JEFF #4 and JEFF #5 were run. The last two were standard TRUEX-dodecane solutions already prepared.

We have a considerable base of previous data for comparative purposes (LUCINDA JULY 89, LUCINDA MAY 89, and NINUS 1988). The TRUEX-NPH presently being used was also run (triplicate samples) and labeled SEDLET/DRF (1990). Table II-23 summarizes current and previous americium extraction data with 0.01M and 2M HNO_3 . Based on this compilation, the only suspect sample is CLIFF #3 for 0.01M HNO_3 , which falls out of the spread of data.

Americium distribution ratios measured at low acid concentrations are more sensitive to acidic impurities present in the CMPO, i.e., the extraction of americium with these impurities increases as $[\text{H}^+]$ decreases. Distribution ratios measured at 2M HNO_3 give some indication that the TRUEX solvent was prepared correctly.

E. Data Base Development
(W. B. Seefeldt)

The success of the TRUEX process and the development of models useful to designing flowsheets strongly depend on the quality and the retrievability of underlying distribution ratio measurements for the many chemical species likely to be present. An effort was therefore initiated to collect all such information into a data base using the software package 4th Dimension on a Macintosh computer. The design of the data base places strong emphasis on various modes of retrievability and anticipated report formats useful to the project. The data base is intended to be useful to at least four customer types:

Table II-23. ^{241}Am Extraction as Purity Check for CMPO

Sample	Distribution Ratios	
	0.01M HNO_3	2M HNO_3
SEDLET/DRF (A)	0.0132	27.7
SEDLET/DRF (B)	0.0132	28.2
SEDLET/DRF (C)	0.0132	29.5
MIKE #1	0.0155	27.4
MIKE #2	0.0156	28.5
CLIFF #3	0.0388	29.4
JEFF #4	0.0192	30.5
JEFF #5	0.0170	28.9
LUCINDA JULY 89	0.0116	29.4
LUCINDA MAY 89	0.0127	28.6
NINUS 1988	0.0131	29.5

program managers, individual experimenters who measure distribution coefficients, modelers who develop the algorithms useful to the design of TRUEX flowsheets, and quality assurance auditors. The ability to rapidly identify categories of information in need of development is especially important to program managers and modelers.

The design of the structure of the data base has been completed, and the data base is functional. Debugging continues, and further improvements to facilitate use are in progress. Data are routinely incorporated as additional measurements are made in CMT.

Recent emphasis had been on the collection of data appearing in the literature and their incorporation into the data base. Two literature searches have been conducted using the DOE Energy Data Base and the data base of the American Chemical Society. In both cases the search was for all abstracts containing mention of CMPO. The total number of abstracts was 45 and 64, respectively. These searches will form the basis for further data base work.

F. Monitoring and Controlling the TRUEX Processes (B. Misra and M. C. Regalbuto)

1. Introduction

Development of an optimized TRUEX process will depend, to a large extent, not only on selection of monitoring instruments for the critical process variables, but also on implementation of control strategies based on the inherent characteristics of multistage centrifugal contactors. It is expected that selection and placement of sensors will play a dominant role in gaining an insight into both the static and dynamic behavior of the multicomponent separation process. Successful development of a control system will depend on on-line monitoring of key variables, such as concentration and activity levels, by the latest analytical techniques. Since the concentration of the TRU elements in the TRUEX feed solution is low, monitoring of the impurity concentrations in the product streams with the desired degree of accuracy may be, in many cases, beyond the capability of existing instruments.

In the current efforts, we are evaluating the TRUEX process in the light of monitoring and control instrument requirements, and we are mathematically modeling the interrelationship among the various components and process variables. One of the goals of these efforts is to develop a knowledge-based (expert) system which will be used to (1) analyze potential and hypothetical failure modes, (2) study propagation of failure modes and their consequences, (3) select instruments for detecting fault-initiating events, and (4) develop a control system for an optimized TRUEX process.

2. Selection of Process Flowsheet

Literature review and modeling efforts were carried out to determine the instrumentation and control requirements for the TRUEX solvent extraction process. To identify the important process variables, a typical process flowsheet, as shown in Fig. II-8, was examined. Design of a monitor-and-control system for the TRUEX process requires not only a general understanding of the process and its

Fig. II-8. Recommended TRUEX Flowsheet for Processing Waste from the Plutonium Finishing Plant (PFY). (Relative flow rates shown in parentheses).

goals but also the role of major process variables in governing the mass transfer and the interaction between the process variables. This necessitates distinguishing between

1. Primary process variables such as the aqueous and organic flow rates, compositions of the feeds, and other-phase carryover.
2. Secondary process variables such as liquid levels in the contactor, liquid levels in the process tanks, and temperature, pressure, and pH at strategic locations.
3. Tertiary process variables such as conductivity and density.

The flow streams, storage tanks, receiving and supply tanks, and the centrifugal contactor were all examined for placement of appropriate sensors and transducers. Table II-24 presents a summary of the major flow streams and storage vessels that need to be instrumented for monitoring and control purposes.

Table II-24. Potential Monitoring and Control Requirements for the TRUEX Process

Aqueous Feed Tank and Feed Stream (DF)*

Process Variables

Liquid Level

Fluid Flow Rate

Density

Color

Conductivity

pH

α Activity

γ Activity

Control Instruments

Liquid Level

Fluid Flow Rate, Fluid Transport

(Metering Pump, Pump Speed, Control Valve)

Organic Feed Tank and Fluid Transport (DX)

Process Variables

Liquid Level

Density

α and γ Activity

Color

Control Instruments

Fluid Flow Rate, Fluid Transport

(Metering Pump, Pump Speed, Control Valve)

Scrub, Strip, and Solvent Wash Tanks and Feed Systems

Process Variables

pH

Density

Conductivity

Liquid Level

Control Instruments

Liquid Level

Fluid Flow Rate, Fluid Transport

(Metering Pump, Pump Speed, Control Valve)

(contd)

Table II-24. Potential Monitoring and Control Requirements for the TRUEX Process (contd)

Raffinate and Storage Tank (DW)Process Variables

Liquid Level

 α Activity γ ActivityAm-Product Effluent and Storage Tank (EW)Process Variables

Liquid Level

 α Activity γ Activity

Conductivity

Color

Pu-Product Effluent and Storage Tank (FW)^aProcess Variables α Activity γ Activity

Color

Liquid Level

Conductivity

Solvent Wash Waste (GW)Process Variables

Liquid Level

pH

Conductivity

Color

 α Activity γ ActivityCentrifugal Contactor (Mechanical Operation)Process Variables

Temperature

Voltage

Current

Control Instruments

Shut Down of Cell Motors and Pumps

Liquid Level

(contd)

Table II-24. Potential Monitoring and Control Requirements for the TRUEX Process (contd)

Centrifugal Contactor (Interstage Lines)Process Variables

α Activity
 γ Activity
 Conductivity
 pH
 Color
 Density

Control Instruments

Data to Expert System for Control
 of Feed Rates or Shut Down Process
 Liquid Level

^aA feed adjustment tank will likely be in front of this tank to add oxalate if necessary and thereby suppress extraction of Zr^{4+} and other noble metal species and/or adjust nitric acid concentration.

3. Operating Limits for TRUEX Process

Since the TRUEX process involves solutions containing radioactive elements, the monitor-and-control system is expected to be more complex than that used in a conventional industrial chemical process. However, because of the operation of the processing equipment at essentially ambient conditions, the overall monitor-and-control system is expected to be less complex. Table II-25 lists the upper and lower operating limits envisioned for TRUEX processes.

Table II-25. Operating Limits for TRUEX Processes

Operating Parameter	Operating Limits
Temperature	Ambient (15-60°C)
Pressure	Ambient (13-16 psia)
Liquid Level, m	0.005-7
Flow Rate, L/min	0.001-20
Density, g/mL	0.8-1.2
Actinide Concentration, <u>M</u>	10^{-2} - 10^{-10}
pH	(-1)-2
α , β , γ activity	System Dependent

4. Sensor Requirements

The various sensors required for a typical TRUEX process (Table II-24) were analyzed to determine the control system requirements. Examination of commercial instrument catalogs showed that several manufacturers supply sensors for temperature, pressure, fluid flow rate, and liquid level. In addition, the same manufacturer often offers a wide choice of sensors of a given measurement with varying degrees of sophistication.

For remote monitoring and control, the signals must be sent a great distance in a noisy electronic environment. Also, for process control, the signals must be interfaced with a computer system. Hence, we decided that all sensors must provide a uniform 4-20 mA signal.

Our study of a typical TRUEX process flowsheet showed that the most important monitor-and-control variables are fluid flow rate, liquid level, and chemical composition. The characteristics of flow rate and liquid-level sensors and their cost data are presented below.

Although the physical size of the system plays only a minor role in selection of the types of sensors required, it is important for selection of flow rates, pumps, valves, level detectors, etc, in making cost estimates. The data presented in Table II-26 were used as a basis for making cost estimates, especially for flow meters.

Table II-26. Nominal Fluid Flow Rates for Typical TRUEX Process

Fluid Stream	Maximum Flow Rate, L/min
Aqueous Feed (DF)	5-10
Organic Solvent (DX)	5-10
Strip #1 (EF)	0.5-5
Strip #2 (FF)	0.3-0.6
Scrub (DS)	0.2-0.4
Solvent Wash #1 (GP)	0.1-0.2
Solvent Wash #2 (HP)	0.1-0.2
Solvent Rinse (IF)	0.1-0.2

a. Volumetric and Mass Flow

Measurement of flow is fundamental to all process industries, and it comprises one of the oldest technologies. Without measurement and control of this crucial variable, no automatic process can be developed for the TRUEX process. The physical, chemical, and hydrodynamic characteristics of the fluids are important to flowmeter selection. The fluid streams must be analyzed in terms of either mass flow or volumetric flow requirements, with maximum and minimum flow rates set. Different flowmeters may be chosen depending on whether the stream is a pure liquid, a slurry, an acid, a base, or a solvent. All types of flowmeters (e.g., those based on the conservation-of-mass principle such as the orifice plate, venturi tube, rotometer; those based on rate equations such as velocity, heat, and mass transfer; and those based on some dynamic aspect of flow such as vortex shedding and the Coriolis effect) are suitable for flow monitoring of one or more streams. However, our analysis of literature data indicated that flowmeters based on recent technologies, such as those based on the Coriolis effect, deserve first consideration for flow streams that require precise measurement and control.

By examining a typical flowsheet for the TRUEX process, we divided the flow requirements into two categories:

1. Process streams that operate at low flow rates and do not require precise monitoring and control, such as solvent-wash feeds.
2. Process streams that operate at high flow rates and require precise flow measurement and control, i.e., all other aqueous feed streams and the solvent feed stream.

Table II-27 summarizes the pertinent data for flowmeters based on the Coriolis effect and an accurate metering pump based on positive displacement. In the case of the metering pumps, use of a flowmeter backup may be desirable to give feedback to the pump and to avoid flow offsets if the pump calibration changes. One can also monitor flow offsets by measuring how the liquid level in the feed tank changes with time.

Table II-27. Flowmeter Data from Two Industrial Firms

	Micro Motion, Inc.	Fluid Meter, Inc.
Operating Principle	Coriolis Effect	Positive Displacement
Flow Range	0-25,000 lb/min	0-1200 mL/min
Operating Range	-240°C to 200°C	-200°C to 200°C
Accuracy	±0.1-0.2%	±1%
Response Time	0.1-1.1 s	<2 s
Cost	\$4000-5000	<\$1000
Availability	From Stock	From Stock
Control Function	4-20 mA Output	Indication Only, No Analog Signal Output
Adaptability	No Major Impact on Design	Minor Impact on Design
Environment	Acid, Base, Solvent, and Radioactive Fluids, Slurries	Corrosive and Radioactive Fluids, Slurries

b. Liquid Level

Liquid-level monitoring and control are required at a number of locations. While the liquid level is not controlled in the centrifugal contactors, problems in their operation are often revealed by changes in the liquid level in the annular zone of one or more stages. The volume held in a storage tank can also be monitored with a liquid-level probe.

There is a wide choice in sensors for monitoring liquid level (mechanical, electric, electronic, and pneumatic), varying from very simple and inexpensive devices to very sophisticated and expensive transducers which incorporate the latest electronic technology. Typical characteristics of liquid level sensors are presented in Table II-28. From the standpoint of remote monitoring and control of liquid level, consistent with accuracy and other design requirements, the radio frequency (RF) admittance type level detectors appear to satisfy the needs of the TRUOX process. Our choice is based on those sensors that provide continuous level measurement with an analog signal output, moderate cost, and versatility, along with ease of calibration, installation, and replacement.

A study of the catalog data on level sensors indicated that they are, in general, rather bulky. Monitoring and control of liquid levels in supply and receiving tanks with bulky sensors do not present serious design problems. However, using level sensors to measure the liquid level in a centrifugal contactor stage presents a formidable challenge.

Table II-28. Cost Data and Other Information on Typical Level Sensors

Specifications and Cost	
Type	Non-contact, both point and continuous measurement
Range	From sensor face, 0.25-180 in. (0.6-450 cm) level
Accuracy	±0.5%
Response Time	1 s
Temperature	0-500°C
Environment	Corrosive, Radioactive
Impact on System	
Design	Major
Weight	5-9 lb (2-4 kg)
Cost	
RF Admittance Type	\$1,500-2,000
Microwave Type	\$4,000-6,000
Resistance Tape Type	\$1,000-1,500

5. Dynamic Response of GTM

Version 2.1 of the GTM uses a new method for calculating the mass and flow balances in the SASSE worksheet, in that an analytical steady-state solution is calculated in a single step. This SASSE section can be used independently of the GTM when the appropriate distribution ratios or equations are specified by the user, or, if SASSE is used in conjunction with the GTM, the distribution ratios are calculated by SASPE. We employed the new SASSE worksheet to determine the dynamic response of the organic- and aqueous-phase compositions to changes in the inlet compositions or the flow rates of the TRUEX process.

Because of the complexity of the GTM, we first studied the concept of process dynamics for a much simpler system. The most elementary of the simple systems is the first-order transfer stage.¹³ An example of a first-order transfer stage is the continuous stirred-tank reactor (CSTR), in which mixing conditions occur, or a simple first-order chemical reaction takes place.

For the case of a perfect mixer, the volumetric inflow and outflow rates are equal to q , and the respective stream compositions are x and y , expressed in moles of solute per unit volume. This case can be represented as

A material balance for the solute yields:

$$\frac{Vdy}{dt} = qx - qy \quad (\text{II-20a})$$

or simply accumulation equals inflow minus outflow. In Eq. II-20a, V is the volume of liquid in the reactor. Perfect mixing is assumed, i.e., effluent concentration is taken to be the same as the average in the tank. We can divide Eq. II-20a by q and set T equal to V/q . Here, the time constant T is the average holdup time in the reactor, in other words, the time required for a volume equal to the liquid volume in the reactor to flow through the reactor. This yields

$$T \frac{dy}{dt} = x - y \quad (\text{II-20b})$$

For most problems in process dynamics, it is advantageous to write the dynamic equations in terms of a deviation variable rather than the absolute values of the variable. This can be accomplished as follows. For steady state-conditions, Eq. II-20a can be written as

$$q x_{ss} - q y_{ss} = 0 \quad (\text{II-21})$$

where the subscript ss denotes steady state. From Eqs. II-20b and II-21, we obtain

$$T \frac{d(y - y_{ss})}{dt} + (y - y_{ss}) = (x - x_{ss}) \quad (\text{II-22})$$

Defining the deviation variable $Y = y - y_{ss}$ and $X = x - x_{ss}$ yields

$$T \frac{dY}{dt} + Y = X \quad (\text{II-23})$$

The form of Eq. II-23 is known as a first-order transfer stage, in which Y is the response variable to the forcing function X . If we abruptly change the concentration in the feed tank to some new steady-state value A units different from the initial condition, the forcing function X will be a step function of magnitude A . Therefore, Eq. II-23 becomes

$$T \frac{dY}{dt} + Y = A \quad (\text{II-24})$$

whose solution

$$Y = A (1 - e^{-t/T}) \quad (\text{II-25})$$

can be verified by substitution of Eq. II-25 into II-24 and the fact that at $t = 0$, $Y = 0$. The response to the forcing function A , shown in Fig. II-9, indicates that, for each time interval equal to the time constant T , the recovery that occurs, expressed as a fraction of the forcing function at the start of the interval, is $1 - e^{-1} = 0.632$. In other words, the response in any time interval T , after the step, covers 63.2% of the amount left to be covered at the start of the time interval.

Fig. II-9. First-Order Step Response to the Forcing Function A (see Eq. II-25)

The quantity accompanying the time variable (in this case, $-1/T$), is known as the eigenvalue of the system, defined as λ . Thus,

$$Y = A (1 - e^{\lambda t}) \quad (\text{II-26})$$

Equation II-26 clearly shows how the eigenvalues are directly related to the stability of the system. Since λ is negative in this case, the system will reach a new steady state. If the time constant is small, the system will respond quickly, and if the time constant is large, the system will respond slowly.

In complex systems, multivariable interactions, as well as nonlinearity, often complicate the solution of the differential equations that describe the dynamic behavior of the process. In many cases, computational algorithms can be used to aid in the solution, especially to calculate the eigenvalues or time constants of the system. In the majority of cases, these values are not as obvious as in the CSTR mixers.

We conducted a similar dynamic analysis for a much more complex system, the TRUEX process. In this analysis, all the equations needed to calculate the eigenvalues, as well as the response of the system to a step-forcing function, were derived. Numerical calculations with these equations can easily be performed once a flowsheet has been specified.

As a result of this analysis, the process time delays can be identified, helping in the selection of monitor-and-control instruments. Also, several control systems or control settings can be compared by evaluating which one responds better to a perturbation.

a. Analysis of Changes in Feed Composition

The GTM (Version 2.1) has been analyzed for dynamic behavior with regard to changes in feed-stream compositions at constant flow rates. Flow rates are considered as totally observable and controllable environmental variables. Therefore, a perturbation in the flow can easily be

detected and corrected by on-line mechanisms. However, changes in composition of the aqueous feed to the extraction section are beyond immediate control and, therefore, represent a perturbation to the system.

In the new GTM, solvent extraction contact equipment (either continuous or differential) is analyzed as if it were a stagewise process,¹⁴ where the backmixing or other-phase carryover for either phase can be large.

An unsteady-state mass balance for component j in stage i with constant volumes and D values can be written as:

$$a_{j,i}x_{j,i-1} + b_{j,i}x_{j,i} + c_{j,i}x_{j,i+1} - d_{j,i} = [v_{a,i} + D_{j,i}v_{o,i}] \frac{dx_{j,i}}{dt} \quad (\text{II-27})$$

where the coefficients $a_{j,i}$, $b_{j,i}$, $c_{j,i}$, and $d_{j,i}$ for component j at stage i can be obtained in Ref. 14. These coefficients are based on backmixing for both phases, distribution ratios for component j , and organic and aqueous flow rates in and out of stage i . Equation II-27 also contains the organic and aqueous stage volumes $v_{o,i}$ and $v_{a,i}$ and the distribution ratio $D_{j,i}$ for component j at stage i .

At steady state, the right-hand side of Eq. II-27 equals 0, and that equation can be written as

$$a_i x_{i-1,ss} + b_i x_{i,ss} + c_i x_{i+1,ss} - d_{i,ss} = 0 \quad (\text{II-28})$$

where the index j has been dropped for convenience. Subtracting this steady-state equation from Eq. II-27 and introducing the deviation variables $X_i = x_i - x_{i,ss}$ and $U_i = d_i - d_{i,ss}$ yield

$$a_i X_{i-1} + b_i X_i + c_i X_{i+1} - U_i = \frac{[v_{a,i} + D_{j,i}v_{o,i}]dX_i}{dt} \quad (\text{II-29})$$

The introduction of a deviation variable results in a more general solution, which is free of initial conditions because the initial value of X is zero. In control theory the primary concern is the deviations of system variables (in this case concentration) from their steady-state values. Therefore, the use of deviation variables is natural as well as convenient.

Equation II-29 can be written for every component at every stage. Solution of Eq. II-29 will yield the transient response of the given component, at stage i , to any forcing function. These forcing functions are reflected in the variable U_i , since we are concerned with changes in the feed composition only.

The system of equations generated by writing Eq. II-29 for $i = 1 \dots m$, where m is the total number of stages, can be solved in several different ways, e.g., root-locus methods (Laplace transforms), frequency-response methods (Bode and Nyquist diagrams), and phase space analysis.¹⁵ Our analysis indicated that Eq. II-29 is suited for a phase-space solution. These types of solutions are preferred over the other two since they do not introduce many mathematical concepts.

b. Solution

Writing Eq. II-29 for a given component, for all m stages, results in a system of m linear differential equations with constant coefficients. A matrix representation of these equations is given as follows:

$$\begin{aligned}
 b_1' X_1 + c_1' X_2 - U_1' &= \frac{dX_1}{dt} \\
 a_2' X_1 + b_2' X_2 + c_2' X_3 - U_2' &= \frac{dX_2}{dt} \\
 a_3' X_2 + b_3' X_3 + c_3' X_4 - U_3' &= \frac{dX_3}{dt} \\
 a_4' X_3 + b_4' X_4 + c_4' X_5 - U_4' &= \frac{dX_4}{dt} \\
 &\dots\dots\dots \\
 a_i' X_{i-1} + b_i' X_i + c_i' X_{i+1} - U_i' &= \frac{dX_i}{dt} \\
 &\dots\dots\dots \\
 a_{m-1}' X_{m-2} + b_{m-1}' X_{m-1} + c_{m-1}' X_m - U_{m-1}' &= \frac{dX_{m-1}}{dt} \\
 a_m' X_{m-1} + b_m' X_m - U_m' &= \frac{dX_m}{dt}
 \end{aligned} \tag{II-30}$$

where

$$\begin{aligned}
 a_i' &= a_i / (v_{a,i} + D_i v_{o,i}) \\
 b_i' &= b_i / (v_{a,i} + D_i v_{o,i}) \\
 c_i' &= c_i / (v_{a,i} + D_i v_{o,i}) \\
 U_i' &= U_i / (v_{a,i} + D_i v_{o,i})
 \end{aligned}$$

Note that the subscript j, which represents the component number, has been omitted for clarity. Nevertheless, these m equations are for the single component j. The solution of this system of equations can be given in terms of the eigenvalues of the matrix of coefficients defined as $\underline{T}$. Equation II-27 can then be written in terms of $\underline{T}$ as

$$\underline{T} \underline{X} - \underline{U}' = \frac{d\underline{X}}{dt} \tag{II-31}$$

whose solution is

$$\underline{X} = \sum_{i=1}^m \frac{\underline{w}_i^T \underline{T}^{-1} \underline{U}'}{\underline{w}_i^T \underline{z}_i} \underline{z}_i e^{\lambda_i t} + \underline{T}^{-1} \underline{U}' \tag{II-32}$$

$\underline{w}$, $\underline{z}$, and λ are the eigenrows, eigenvectors, and eigenvalues of the system (or matrix $\underline{T}$), respectively. The eigenvalues are given by solving

$$|\underline{T} - \lambda \underline{I}| = 0 \quad (\text{II-33})$$

The eigenvectors by solving

$$(\underline{T} - \lambda_i \underline{I}) \underline{z} = 0 \quad (\text{II-34})$$

and the eigenrows by solving

$$(\underline{T}^T - \lambda_i \underline{I}) \underline{w} = 0 \quad (\text{II-35})$$

Using these equations, one can determine the effect of deviations from steady state due to perturbations in the feeds. In the next stage of this project, we will numerically solve this eigenvalue problem for specific TRUEX flowsheets. By focusing on the time response of a system to a perturbation, it is possible to observe which stages and which components respond faster to a perturbation and also to determine which variables change by orders of magnitude. Those variables that respond quickly to perturbations, with large changes (orders of magnitude), are good candidates for monitoring.

For dynamic control to have any quantitative meaning, some measure or criterion must be available to specify how good the control is, i.e., how far the process is from the desired conditions. Once the process is defined, the needed quantities in Eq. II-32 (eigenvalues, vectors, and rows) can be computed. Using Eq. II-32, a measurement of how the system responds to a given perturbation can be employed as a guide in selecting monitoring instruments and the control algorithm. The instruments and algorithms selected can be tested by adding a constraint in the dynamic system and solving the new controlled system. The best instruments and algorithms will be those in which the system response to a perturbation is dampened in the least amount of time within the production bounds.

Further work on the transient response of the system to perturbation on feed composition and/or flow rate will be done in the next stage of this study. Perturbation in the feed flow rate profile, which represents a much more complicated analysis than the one presented in this report, will also be done in the future. One of the key steps in developing a dynamic model is for the stage volumes ($v_{a,i}$ and $v_{o,i}$) to be expressed as functions of the flows. Only then can we solve for the flows at every stage. Once stage flows and volumes are determined, concentrations can be obtained.

6. Sensitivity Analysis

Using the GTM for a specific flowsheet with a given number of sections and stages, feed flow rates, compositions, and back-mixing coefficients, one can obtain the steady-state concentration for all components present in both phases in every stage. By altering the value of one or several of the feed variables (composition or flow rate) and re-evaluating the model, one can perform a numerical sensitivity analysis, from which an appropriate strategy can be identified for process monitoring and control.

We thus performed a sensitivity analysis, using GTM 2.1, on a TRUEX process flowsheet for PFP waste (Fig. II-10). This flowsheet gives flow rates in parentheses (all changes in flow rates can be considered as relative to that of the extraction feed). This base case meets all process goals for treatment of this waste; namely, the raffinate should be non-TRU ($[TRU] \leq 10 \text{ nCi-}\alpha/\text{g solid}$), 99.7% or more of the americium should be extracted by strip 1, 98.9% or more of the plutonium should be extracted by strip 2, and less than 0.01% of the TRU should be in the organic solvent as it leaves the second strip section. The calculated compositions of the feeds and the effluent streams, for this base case, are shown in Table II-29.

Fig. II-10. Flowsheet for Tests with Synthetic Plutonium Finishing Plant (PFP) Waste. (Parenthetical entries indicate relative stream flow rates).

In future work we will discuss how sensors for monitoring and control of variables such as flow rate and feed compositions can be selected based on the perturbation analysis. Tables II-30 and -31 give the bounds obtained for flow rate and feed composition. Given in these tables are four process goals used in the sensitivity analysis. For each goal, we give a range in which it is satisfied. For every perturbation study, we also give its base-case value. Note that these values are relative, and therefore, the bounds are given as fractions. Tables II-32 shows the calculated effect of losing a stage in a given section.

Table II-29. Calculated Component Concentrations (with GTM 2.1) for Base Case (Fig. II-10)

Stream ID ^a	Flow Rate ^b	Component Concentration, <u>M</u>					
		H	Fe	Ni	Al	Na	Ca
DX	150	1.00E-15	1.00E-15	1.00E-15	1.00E-15	1.00E-15	1.00E-15
DF	400	1.50E+00	3.00E-02	4.00E-04	4.30E-01	4.00E-02	6.00E-02
DS	40	4.00E-02	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
EF	150	4.00E-02	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
FF	75	1.00E-01	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
DW	440	1.26E+00	2.73E-02	3.64E-04	3.92E-01	3.64E-02	5.46E-02
EW	150	3.66E-01	9.74E-08	5.62E-13	5.11E-10	5.62E-11	8.43E-11
FW	75	5.37E-02	2.22E-14	3.29E-28	1.51E-25	3.29E-26	4.93E-26
FP	150	2.53E-02	1.33E-17	5.61E-37	3.54E-39	5.61E-35	8.42E-35

Stream ID ^a	Flow Rate ^b	Component Concentration, <u>M</u>						
		Cu	Mg	UO ₂	Am	Pu(IV)	F	HSO ₄
DX	150	1.00E-15	1.00E-15	1.00E-15	1.00E-15	1.00E-15	1.00E-15	1.00E-15
DF	400	3.00E-04	6.00E-02	3.00E-06	6.00E-06	3.00E-05	9.00E-02	1.00E-02
DS	40	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
EF	150	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
FF	75	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	5.00E-02	0.00E+00
DW	440	2.73E-04	5.46E-02	2.15E-14	4.65E-11 ^c	1.25E-13 ^c	8.19E-02	9.11E-03
EW	150	4.22E-13	8.43E-11	3.54E-08	1.60E-05	6.69E-07	1.55E-04	1.08E-11
FW	75	2.46E-28	4.93E-26	6.86E-06	7.43E-08	1.57E-04	2.51E-03	3.28E-27
FP	150	4.21E-37	8.42E-35	4.50E-06	4.91E-11 ^d	2.63E-08 ^d	2.37E-02	1.62E-36

^aSee Fig. II-10 for identity of each stream.^bFlow rates can be in any unit of volumetric flow rate. The important criterion is that flow rate is relative to the extraction feed (DF).^cThis is equal to 3.86×10^{-2} nCi/g of α activity from TRU.^dCorresponds to only 0.003% of TRU in this stream.

Table II-30. Control Bounds for Flow Rates

Variable (Base Case Value)	Allowable Fractional Change ^a	Range in which the Am mol% in Strip 2 effluent is less than 0.3%	Range in which the Pu mol% in Strip 1 effluent is less than 1.1%	Range in which the TRU concentration in the raffinate is less than 10 nCi/mL	Range in which the TRU lost in the organic flow exiting Strip 2 is less than 0.01%
Organic Extraction Feed (150)	0.935-1.01	<1.01	>0.935	Not Limiting	<1.08
Aqueous Extraction Feed (400)	0.1-4.03	Not Limiting	>0.1	<4.03	Not Limiting
Aqueous Scrub Feed (40)	0.959-1.17	>0.959	<1.17	Not Limiting	>0.477
Aqueous Strip 1 Feed (150)	0.986-1.13	>0.986	<1.13	Not Limiting	>0.842
Aqueous Strip 2 Feed (75)	>0.902 ^b	Not Limiting	Not Limiting	Not Limiting	>0.902

^aFractional change with respect to the base case for which the process goals still holds.^bLimit not determined by flowsheet; however, other conditions such as storage capacity may limit this variable.

Table II-31. Control Bounds for Feed Concentration

Perturbed Variable (Base Case Value)	Allowable Fractional Change ^a	Range in which the Am mol % in Strip 2 effluent is less than 0.3%	Range in which the Pu mol % in Strip 1 effluent is less than 1.1%	Range in which the TRU concentration in the raffinate is less than 10 nCi/mL	Range in which the TRU lost in the organic flow exiting Strip 2 is less than 0.01%
Am in Aqueous Extraction Feed (6×10^{-6} M)	<12.7	<12.7	<90.2	<203	Not Limiting
Pu in Aqueous Extraction Feed (3×10^{-5} M)	<4.14	Not Limiting	<103	<689	<4.14
UO ₂ in Aqueous Extraction Feed (3×10^{-6} M)	<620	Not Limiting	Not Limiting	Not Limiting	<620
Al(NO ₃) ₃ in Aqueous Extraction Feed (0.43M)	0.904-1.15	<1.15	>0.904	Not Limiting	Not Limiting
Al(NO ₃) ₃ and F in Aqueous Extraction Feed (0.43M and 0.09M)	<1.17	<1.17	Not Limiting	Not Limiting	Not Limiting
HNO ₃ in Aqueous Extraction Feed (1.5M)	0.435-1.11	<1.11	>0.435	Not Limiting	Not Limiting
HNO ₃ in Aqueous Scrub and Strip 1 Feed (0.04M)	0.43-1.02	<1.02	Not Limiting	Not Limiting	Not Limiting
F at Constant H ⁺ in Aqueous Strip 2 Feed (0.05M)	>0.886	Not Limiting	Not Limiting	Not Limiting	>0.886
HF at Constant HNO ₃ in Aqueous Strip 2 Feed (0.05M)	>0.745	Not Limiting	Not Limiting	Not Limiting	>0.745

^aFractional change with respect to the base case for which the process goals still holds.

Table II-32. Effect of Losing a Stage in a Given Section

No. Stages Lost in Given Sec.	Effect
1 Stage, Extraction Section	No negative effect in the process goals, i.e., the TRU concentration in the raffinate is less than 10 nCi/mL, the Am mol % in strip 2 effluent is less than 0.3%, the Pu mol % in strip 1 effluent is less than 1.1 %, and the TRU lost in the organic flow exiting strip 2 is less than 0.01%.
2 Stages, Extraction Section	The TRU concentration in the raffinate is greater than 10 nCi/mL; therefore, the process goal is not met.
1 Stage, Scrub Section	The Am mol % in strip 2 effluent is greater than 0.3 %; also the TRU lost in the organic flow exiting strip 2 is greater than 0.01%; therefore, the process goal is not met.
1 Stage, First Strip Section	The Am mol % in strip 2 effluent is greater than 0.3%; therefore, the process goal is not met.
1 Stage, Second Strip Section	No negative effect in the process goals, i.e., the TRU concentration in the raffinate is less than 10 nCi/mL, the Am mol % in strip 2 effluent is less than 0.3%, the Pu mol % in strip 1 effluent is less than 1.1 %, and the TRU lost in the organic flow exiting strip 2 is less than 0.01%.

G. Processing of New Brunswick Laboratory Waste Solution

(D. B. Chamberlain, C. J. Conner, J. A. Dow, D. R. Fredrickson, J. C. Hutter, F. C. Mrazek, M. A. Tranovich, E. Van Deventer, R. A. Leonard, and G. F. Vandegrift)

1. Introduction

Analytical residue solutions from plutonium analysis have been accumulating over the past several years at the New Brunswick Laboratory (NBL) and Argonne National Laboratory (ANL). These residues contain varying concentrations of nitric, sulfuric, phosphoric, and hydrochloric acids, as well as uranium, plutonium, neptunium, and americium. Originally destined for Idaho and eventual disposal at the Waste Isolation Pilot Plant (WIPP) in New Mexico, these wastes now appear to have no place that will accept them. In this project, the TRUEX process will be used to convert the bulk of this waste into a nonTRU (i.e., low-level) product by removing the TRU elements to activity levels of less than 100 nCi/g (our goal is <10 nCi/g). This waste can then be disposed of under existing regulations. The recovered plutonium will be converted into solid PuO₂ for return to NBL for storage and subsequent transport to the DOE defense complex.

In this project, we are planning to demonstrate the use of the TRUEX solvent extraction process to separate and recover TRU elements from acidic waste solutions. Approximately 200 L of mixed TRU waste generated by NBL and ANL will be converted into a nonTRU waste using the TRUEX process. This demonstration will show the applicability of TRUEX to the much larger volumes of similar wastes being generated at Rocky Flats Plant, Los Alamos National Laboratory, and Westinghouse Hanford and will act as a basis for considering this process as a future waste treatment process at

ANL/NBL. After processing, the nonTRU waste stream will be transported to ANL's Plant Facilities and Services, Waste Management Operations (PFS-WMO), for final disposal as low-level waste.

A second stream from the TRUEX process containing 150 g of plutonium will be converted into solid PuO_2 . Other wastes, including operational trash (gloves, plastics, and paper wipes) and a liquid stream containing uranium generated during this project, will be transported to PFS-WMO for disposal as low-level waste. Americium and neptunium product streams will be saved for use in our ongoing laboratory experiments. For this project, only a limited amount of equipment will need to be purchased and/or modified. Process operations will be completed in two existing gloveboxes. A multistage centrifugal contactor is installed in one of these gloveboxes and will be used for the TRUEX portion of the project.

2. Process

The bulk of this waste is currently stored by Waste Management Operations. These wastes will be transported to the Chemical Technology (CMT) Division, Building 205. Because of the fissile-material limits in Building 205, transfers and subsequent processing will be completed in four to six batches, with each batch containing 30-50 g of fissile material. After processing, the PuO_2 will be returned to NBL for storage. Approved ANL/NBL/DOE procedures and containers will be used for these transfers.

A simplified flowsheet for processing the plutonium-containing waste solutions is shown in Fig. II-11. The TRUEX solvent extraction process, used to generate the nonTRU waste stream and recover the plutonium, will be completed in a 16-20 stage centrifugal contactor installed in a glovebox.

Fig. II-11. General Flowsheet for Processing Plutonium Waste Solutions of New Brunswick Laboratory

The organic solvent (TRUEX-NPH) used in this process consists of a TBP, CMPO, and normal dodecane (nDD). Several waste and product streams are generated by the TRUEX process. The composition of the eight to ten waste feed stocks will require small modifications in the flowsheets (e.g., stages in each section, feed-stream flow rates), which will be based on calculations made with the GTM and data from test-tube experiments.

The plutonium product stream will be evaporated to dryness, then converted to an oxide by calcining in an oven at 600°C. A separate glovebox is available for the concentration, precipitation, and conversion steps. The product from the calcining operation, PuO_2 , will be returned to NBL prior to accepting the next batch of plutonium residue solution.

Other streams will also be generated by the TRUEX process--an americium product stream, a uranium product stream, and, in one case, a neptunium product stream. The americium stream will be concentrated in the glovebox by evaporation, and the concentrated solution will be saved for use in ongoing laboratory experiments. Plutonium waste solutions that contain neptunium will be collected separately from the other NBL waste solutions and processed to recover neptunium and plutonium in individual product streams. The neptunium stream will be concentrated and also saved for ongoing laboratory experiments. In some cases, the uranium and plutonium will be stripped together in a single product stream.

3. Plutonium-Containing Waste Solutions

Most of the 115 L of waste solution is stored in 250 mL Nalgene bottles; NBL uses this size bottle because it allows them to store their solutions overnight in pressure cookers. To dispose of these solutions, NBL collects 18 to 22 bottles and places them in a 5-gal (0.02 m³) secondary container, called a waste pail. The total TRU and acid content of each pail are reported to WMO on a waste disposal requisition form (PFS-199). The 115 L of solution that we will process is housed in 21 waste pails.

The average composition of the 115 L of waste solution being stored by WMO is reported in Table II-33. (Composition data are not available for the 50 g plutonium that is being prepared at NBL, though its composition should be similar to that reported in this table.) Only the average composition of the solution in each waste pail is known. We do not know the specific solution composition in each bottle. Generally, this does not cause any difficulty except for the case of chloride contamination, which will be discussed later.

Because we are limited to working with 55 g of Pu (plus ²³⁵U) in the glovebox, the 115 L of solution was divided into four to six batches, each of which contain less than 50 L of solution and less than 50 g of Pu (plus ²³⁵U).

Approximately 4.5 h is needed to process a typical batch (50 L) of waste solution by the TRUEX process. During the run, samples will be collected for analysis to verify that the test is proceeding as expected. Samples will be analyzed on both a gamma counter (for americium) and a scintillation counter (for plutonium). Some variation in the flowsheet may be needed for each batch to optimize the process for each particular solution composition. We expect that operations will be completed in the glovebox at room temperature, but operation at elevated temperatures (40°C) has not been ruled out. Although verification tests have been approved for operation at elevated temperatures, no extensive verification tests have been completed. Nonetheless, 4-h tests in the glovebox have shown that a temperature of 40°C can be achieved and maintained.

Table II-33. Average Composition of NBL Waste Solutions^a to be Processed (115 L, 421 bottles)

	Average Concentrations, g/L	Total Mass, g
Pu-239	0.97	111.7
Pu-240	0.071	8.18
Pu-241	0.0043	0.90
Total Pu	1.04	120 ^b
Am-241	0.00018	0.021
U-233	0.0045	0.052
U-235	0.15	17.24
U-238	0.61	70.74
Total U	0.76	87.89 ^c
Np-237	0.0015	0.17

^aAverage HNO₃ concentration is 4.7M.

^bApproximately 28.5 g of this Pu is contained in mixed NO₃⁻ and Cl⁻ solutions. The remainder is in NO₃⁻ only solutions.

^cApproximately 13.1 g of this U is contained in mixed NO₃⁻ and Cl⁻ solutions. The remainder is in NO₃⁻ only solutions.

Anticipated solution volumes generated during the processing of one 50 L batch of waste feed are reported in Table II-34. Additional processing of the nonTRU product stream from the extraction section will not be required. After analysis to verify its TRU composition, this solution will be transferred from the glovebox directly into 10 L waste containers for shipment to PFS-WMO. The Pu and Am product streams will be transported to a glovebox in 1-gal (0.004 m³) bottles for additional processing -- i.e., concentration and, in the case of plutonium, solidification and calcination. One of the batches will also contain neptunium -- the flowsheet may have to be modified for this batch to prevent contaminating the Pu with Np.

Table II-34. Solution Volumes Generated during the Processing of 50 L Plutonium Waste Solution

Stream	Solution Volume, ^a L
Extraction Raffinate	80.3
Am Product	0.6
Pu Product	8.8
Carbonate Wash	3.8
Organic Product	3.5 ^b

^aThese volumes are based upon processing 50 L plutonium waste solution.

^bThe organic product stream is recycled and not disposed of. This number represents the solvent inventory in the glovebox.

4. TRUEX Flowsheet Development

The criteria used to develop a flowsheet for processing these solutions include the following:

- Convert the TRU feed solution to a nonTRU waste (<10 nCi/g).
- Keep total number of stages to a minimum.
- Generate a pure plutonium product stream (i.e. the plutonium product stream should not have any other metals present).
- Recover as much plutonium as possible in the plutonium product stream.
- Generate as pure an americium product stream as possible (keep plutonium contamination to a minimum).
- Incorporate an adequate solvent cleanup section so that the TRUEX solvent can be recycled.
- Use the TRUEX-nDD solvent.
- Base flow rates upon 4-cm centrifugal contactors with the organic phase as the less-dense phase (i.e., less than 400 mL total throughput).
- Keep the Am and Pu product stream volumes to a minimum.

Several different flowsheets (and variations of this flowsheet) were evaluated before selecting the base flowsheet shown in Fig. II-12. In Fig. II-12, two different feed streams normally present in a TRUEX flowsheet were replaced with two alternative feed solutions. First, the acid rinse that typically follows the carbonate wash was eliminated, saving one stage. Since the acid concentration in the DF feed is fairly high, the small amount of carbonate carried over from the last stage with the organic phase should not affect the flowsheet. Two separate carbonate wash solutions were added to the flowsheet to help prevent uranium from being recycled to the extraction feed section. The sodium carbonate concentration in the first carbonate wash, stage 19, was increased from 0.25 to 0.5M to counteract the amount of acid being carried over from the plutonium strip section.

The second feed was dropped by combining the operation of the americium strip solution with the scrub solution. Normal TRUEX flowsheets remove 100% of the americium strip solution from that section of the flowsheet. In our flowsheet, we are only planning on removing a fraction of this stream (5%)--the rest of the solution will carry down through the "scrub" section. This solution will act the same as a normal scrub solution, removing nitric acid from the organic phase. As a result, this flowsheet will act to concentrate the americium in the aqueous phase. Americium loading with this flowsheet will not be a problem because of the low americium concentrations involved. Removing only 5% of the americium stream also keeps the product volumes low.

The plutonium strip section was modified by employing two different feed solutions. First, oxalic acid is metered into the first stage of the plutonium strip section at a rate that equals the amount needed to complex all of the plutonium in the organic phase. The second feed to the plutonium strip section consists of oxalic acid and nitric acid to complex any residual plutonium not removed in the first

Fig. II-12. TRUEX Flowsheet for Processing NBL Plutonium Waste Solutions

stage. Nitric acid was added to this feed to maintain a high D value for uranium so that it is not stripped from the organic phase with the plutonium.

As shown by Fig. II-12, our desire to keep the process to 16 stages was not successful; this flowsheet has 20 stages. By decreasing the product volumes (Am and Pu), the number of stages needed to obtain the desired separations increases. Several extra stages were added to the extraction section to ensure that, even with small variations in the actinide distribution ratios, a nonTRU waste is generated.

5. Four-Stage Neodymium Precipitation Test

In the flowsheet processing the NBL waste solutions, we are planning to use oxalic acid to strip the plutonium from the organic phase. At the plutonium concentration in this waste, however, the plutonium will precipitate from solution. One question that we needed to answer was how this precipitate will behave in the centrifugal contactor, i.e., will the precipitate be collected in the rotor or will it pass out with the raffinate solution? To answer this question, a four-stage test was set up using the 4-cm centrifugal contactor and substituting Nd for Pu. The flowsheet for this test (Fig. II-13) incorporates one extraction stage to load the organic phase with neodymium, then three strip stages to strip the neodymium back out of the organic phase. We expected that only one strip stage would be needed, but we wanted to see the effect if problems (e.g., plugging) developed in the first strip stage.

The contactor operated without any problems, with neodymium precipitate being discharged from the first stage with the strip raffinate. At 26 min into the run, we noticed that the organic solution going into stage 2 (from stage 1) was backing up in the interstage line. At the same time, the aqueous phase flowing into stage 2 (from Stage 3) was also starting to back up. This indicates that the stage 2 rotor was filling with precipitate and starting to plug. Because of limited solution volume (not because of the plugging problems), the test was terminated at 27 min, 45 s into the run.

Fig. II-13. Flowsheet for the Four-Stage Neodymium Precipitation Test

A summary of the flow rates measured during this test is given in Table II-35. Several observations were made from these data. First, the flow rate of the EW raffinate based upon the four samples differs from the average calculated by measuring the raffinate volume. Second, organic phase was detected in the third and fourth EW samples, indicating that plugging problems in rotor 2 began affecting the organic phase flow rates sometime between 11 and 22 min into the run. Based upon the two EW samples, the organic flow averaged 47.5 mL/min. Since we measured the volume of organic phase in the EW raffinate tank (365 mL), we calculated the time that the organic started flowing out with the EW raffinate, assuming the flow was constant at 47.5 mL/min. The time from this calculation is 19 min into the run, which is in the period between 11 and 22 min. Third, the organic effluent flow rate was measured late in the run (as reported in the table), but since a portion of the organic phase was exiting with the EW raffinate, the flow was reduced (to 58 mL/min). At the 22-min mark, the sum of the two exiting organic streams equaled 102 mL/min (44 + 58 mL/min), close to the expected flow rate of 100 mL/min.

At the end of the test, solution from the rotors was drained, and the volume measured. Results are reported in Table II-36. Table II-37 lists the measured weights of the precipitates in each rotor immediately following the test. These precipitates were wet--they were not allowed to dry. The data in these two tables are consistent in that the rotor with the most solids had the lowest volume (rotor 2). Most of the volume decrease between rotor 2 and the other rotors is in the aqueous phase. This is as expected, since the precipitate collected on the inner wall of the rotor, displacing the aqueous (more dense) phase. As shown in Table II-37, all three rotors contained some precipitate, though a majority of the solids were located in rotors 2 and 3.

Table II-35. Measured Flow Rates during Four-Stage Neodymium Precipitation Test

Sample	Time of Sample ^a	Measured Flow Rates, mL/min		Aqueous Flow Rate (from Flowsheet), mL/min
		Aqueous	Organic	
DW #1 ^b	7:30	142	0	150
DW #2	11:00	152	0	150
DW #3	22:00	156	0	150
DW #4	26:00	154	0	150
DW Raffinate		146.8	0	150
EW #1 ^c	7:30	138	0	150
EW #2	11:00	144	0	150
EW #3	22:00	142	44	150
EW #4	26:00	150	50	150
EW Raffinate		155.7	e	150
EP #1 ^d	22:00	0	58.0 ^f	100 ^g

^aTime given as minutes: seconds into run.

^bDW is the extraction section raffinate.

^cEW is the strip section raffinate.

^dEP is the organic product stream.

^eThis flow rate not measured directly. Based upon the last two EW samples, it was estimated to be 47.5 mL/min.

^fThis sample collected after organic was detected in the EW raffinate. Therefore, the flow is less than the expected 100 mL/min.

^gThis is an organic flow rate.

Table II-36. Rotor Solution Volumes after Completion of Test

Stage Number	Vol., mL		
	Aqueous	Organic	Total
1	61	17	78
2	~3	~12	~15
3	40	18	58
4	53	25	78

Table II-37. Weight of Precipitates Collected in Each Rotor

Stage Number	Weight of Precipitate (wet), g
1	2.32
2	82.24
3	21.12
4	1.28

The strip raffinate samples (EW) were filtered and the precipitate weighed. These results are listed in Table II-38. These solids were weighed twice, once immediately after filtration and then 12 days later after drying in the laboratory at ambient temperature. Based upon the weight loss, the wet precipitate contained approximately 62% water. Based upon the precipitate concentration in the EW samples and the solids collected in the rotors, approximately 37% of the precipitate was collected in the four rotors, and 63% passed through the rotors and ended up in the raffinate stream. Of the precipitate collected in the rotors, 77% was located in the first strip stage (rotor 2).

Table II-38. Precipitate Weights in Strip Section Raffinate

Sample Number	Weight, g		% of Original Weight Due to Water
	Wet ^a	Dry ^b	
EW# 1	5.50	2.11	61.6
EW# 2	6.05	2.32	61.7
EW# 3	6.24	2.65	57.5
EW# 4	6.66	2.56	61.6

^aWeight measured immediately after filtering sample.

^bWeight measured 12 days later.

In conclusion, precipitate formation inside the rotors is detrimental to the continued operation of the contactors. Eventually, the rotors will fill with precipitate and affect the solution throughput. Since the precipitate formed immediately and operation problems were not evident until approximately 19 min into the run, some precipitate can be tolerated. However, this precipitate is difficult to remove from the rotors.

6. Filtration, Evaporation, and Calcining Procedures

a. Safety Review

A safety review, which covers the evaporation, filtration, and calcination of plutonium oxalate that will be recovered from the processing of NBL waste solutions, has been completed and awaits approval. Details from this safety review follow.

b. Filtration Procedures

To complete the plutonium recovery process, further treatment of the plutonium product (FW) is required. This product will typically consist of approximately 9 L of slurry containing plutonium oxalate present in a solution of ~0.05M oxalic acid. Since the plutonium oxalate is not very soluble, most of it will be present as a precipitate. Accordingly, we plan to filter this product first, then evaporate the solution, and recover the dissolved fraction.

After numerous tests with various filtration equipment using neodymium oxalate as a stand-in for plutonium oxalate, we have decided that a Kontes filter assembly best meets our needs. This filter assembly was chosen because it is readily disassembled, and its contents are easily removed. Filtering efficiency will be enhanced with the use of a rotary-vane pump having a capacity of 30 in.

(76 cm) of mercury (vacuum). A 1 L polypropylene vacuum flask will be used, which eliminates implosion concerns.

Removal of the pasty filter cake is a very messy operation and would be very difficult to perform in a glovebox. However, we have found that if the upper portion of the filter apparatus is placed in a 200°C muffle furnace for several hours, the cake dries and shrinks and, after cooling, can be easily removed with the aid of a rubber policeman. This cake is directly transferred, along with the polycarbonate filter, to a quartz crucible in which the calcination will occur.

c. Volume Reduction of Plutonium Product Stream

The 9 L of plutonium product filtrate, which still contains a substantial amount of dissolved plutonium oxalate, must be reduced to dryness before the calcination process can be accomplished. Use of a rotary evaporator was considered and rejected since it seemed to create more problems than it solved. A better solution was to simply evaporate the filtrate to dryness and then calcine the residue.

Initial tests revealed that even this approach presented a few problems. Since the primary constituent of the residue will be oxalic acid, solutions of neodymium oxalate with large excesses of oxalic acid were evaporated in glass beakers. A fraction of the residue was always liquid (at elevated temperature); considerable quantities of oxalic acid sublimated on the beaker walls; and, upon cooling, the residue was very difficult to remove. This later problem is especially bothersome, since it could result in glass breakage, especially difficult to clean up in a plutonium glovebox. All of the problems were circumvented by carrying out the evaporation in a Teflon beaker. Recovery of the residue from the Teflon beaker is particularly easy since the oxalic acid does not adhere strongly to the Teflon.

Concerns have been raised that the oxalic acid vapor will carry some plutonium away. We believe that this is highly unlikely, but this is easily monitored by collecting oxalic acid sublimate on a watchglass placed atop the hot beaker. This can then be dissolved and counted.

During evaporation, it would be helpful to know when the water has essentially all evaporated. We can determine this by checking the pH of the watchglass condensate. During evaporation, the pH remains relatively constant at approximately 4. The pH of the condensate changes to 0 or 1 just before the oxalic acid solidifies.

d. Calcination of Filter Cake and Residue

Calcination of a dried plutonium oxalate filter cake is straightforward. The polycarbonate filter and as much of the cake as can be recovered from the Kontes filter assembly with the aid of a rubber policeman will be transferred in its entirety to a quartz crucible. The weighed crucible and contents will be transferred to a muffle furnace whose temperature will be elevated to 500°C. It will remain at this temperature until no further weight or color change is observable. The furnace temperature will then be elevated to 640°C, and the weight will be further monitored until no change is apparent. At this point, we should have a good plutonium oxide product.

Treatment of the residue left after evaporation has occurred will be slightly different since it will consist of a mixture of plutonium oxalate in a large excess of oxalic acid. The residue will again be transferred in its entirety to a quartz crucible. At this point, it is desirable to sublime the oxalic acid, which occurs at about 300 to 350°C. During this step, the crucible evolves a white "smoke." After

cessation of this "smoking," the temperature is elevated to 500°C. These two products can then be combined and sent for reduction to plutonium metal.

H. Model Verification Studies

(D. B. Chamberlain, C. J. Conner,* J. A. Dow,** D. R. Fredrickson, J. C. Hutter,
F. C. Mrazek, M. A. Tranovich,** E. Van Deventer, R. A. Leonard, and G. F. Vandegrift)

1. Introduction

Laboratory verification tests of the TRUEX process are being completed to (1) develop a better understanding of the process chemistry, (2) test and verify process modifications, and (3) verify the results of GTM calculations. This model is being developed for predicting species extraction behavior and calculating flowsheets for the TRUEX process.

As described above, the purpose of these tests is not to demonstrate flowsheets for specific waste streams, but to collect data to verify that the TRUEX model predicts actual extraction behavior. Therefore, flowsheets have not been optimized to produce a nonTRU waste stream, or to produce a "clean" rare earth (americium) or plutonium stream, but to evaluate the extraction behavior in all stages. One verification test (No. 12) was completed this period in the 2-cm contactor setup with TRUEX-nDD solvent.

2. Verification Run 12

Run 12 was completed in April 1990. The flowsheet for this test used a TRUEX solvent that substituted the diluent dodecane for the NPH normally recommended (C_{12} - C_{14}). Concentrations of TBP (1.4M) and CMPO (0.2M) were the same as in the conventional TRUEX-NPH solvent. Dodecane was substituted for the NPH diluent to prevent the formation of a second organic phase at room temperatures, since the equipment was installed in a glovebox without provision for operations at elevated temperatures (i.e., 50°C). The purpose of this run was to

- test our recently developed minicontactor (2-cm dia) for personnel from the Chalk River Laboratories, Chalk River, Canada,
- refine our sample collection and analysis procedures with the limited sample volumes generated from the 2-cm contactor,
- measure the concentration of HNO_3 and metals included in the feed solution in both the stage samples and the raffinate streams, and
- compare these data with concentrations calculated by the GTM.

a. Flowsheet

The flowsheet for this test is shown in Fig. II-14. Because of the simplified feed solution, only one strip section was used. The organic interstage samplers shown schematically in

*Co-op student, University of Cincinnati.

**Co-op student, Purdue University.

Fig. II-15 were installed on all of the organic interstage lines, but not on the aqueous side. For the aqueous stage samples, the bottom drain was cracked open and samples were collected there. Stage samples were also collected at the end of the run to compare with the interstage sample concentrations.

Fig. II-14. Flowsheet for Verification Run 12

Fig. II-15. Design for Interstage Sampler for 2-cm Centrifugal Contactor used in Run 12

Originally, the DF feed concentrations were prepared at twice the concentrations reported in Fig. II-14. Prior to starting the test, a batch contact was made with fresh TRUEX solvent and the DF feed to check whether a second organic phase would form (due to loading). Since a second organic phase did form, the feed solution was diluted in half with distilled water, and a second batch contact was completed. This time, a second organic phase did not form.

b. Run Summary

The test plan checklist used for this run is shown in Table II-39. This table includes both the planned schedule and the actual times when various operations were completed.

As shown in Table II-39, the run lasted about 1/2 hour longer than planned, with the delay occurring during startup of the system. During startup, the scrub feed took much longer to fill the first seven stages than planned. For future tests, the startup time could be reduced by (1) increasing the scrub flow rate during startup, or (2) adding solution to each stage before starting all of the pumps. One of these two techniques will probably be incorporated into future experiments.

Table II-39. Schedule for Verification Run 12

Planned Time ^a	Actual Time ^a	Action Required/Noted
		Verify purge air pumps ON.
		Measure feed solution temperatures and hood temperature and record pump settings.
		Verify sample valves are closed.
-2:00	-1:00	Contact motor ON.
0:00	0:00	DS, EF, FF, GF pumps ON.
6:50	--	FW raffinate detected (Carbonate Wash).
6:50	--	GW raffinate detected (Acid Rinse).
12:00	--	EW overflow detected (1st Strip).
47:35	60:36	DW raffinate detected.
48:00	62:00	DX pump on (TRUEX solvent).
	82:00	Organic overflow into stage 12.
	86:40	Organic overflow into stage 14.
	88:09	Organic overflow into stage 15.
	90:40	Organic overflow into stage 16.
68:50	--	HP raffinate detected (TRUEX solvent).
70:00	100:07	DF pump ON (Extraction Feed).
70:30		Color change, DW raffinate.
70:30	105:10	Begin sampling period.
90:30	125:00	Install 1 st set of bottom drip samples.
110:30	145:10	Install 2 nd set of bottom drip samples.
130:00	165:00	End of sampling.
131:00		Shut off all pumps and open drain valves.
+131:00		Close drain valves.
+131:00	169:02	Shut off rotors, sample stages.

^aTime given as minutes: seconds into run.

The only problem encountered during the run involved the interstage samples. These samplers (shown in Fig. II-15) plugged during startup of the system and could not be fixed. Although

much time was spent on trying to get them to work, only two stages, Nos. 4 and 14, yielded enough solution from the interstage samples to accurately titrate. More tests will need to be completed to increase the reliability of these samples. The aqueous drain samples taken from each stage were more successful, though setting the flow rates took a considerable amount of time during startup. Two sets of samples were collected from each stage during the run, the first set collected solution for 20 min starting at 125 min into the run. These samples were replaced by the second set at 145 min. The second set was also collected for 20 min. Raffinate samples were collected during the sample period at 8-min intervals.

The shutdown procedure was the same procedure used in previous experiments, i.e., the pumps were turned off and then all of the stage drain valves were immediately opened. In this test, all of the drain valves were opened within 13 s. The rotors were left on during this operation to prevent solutions inside them from draining. After removing the solution from the annular region, we closed the sample valves and shut off the contactor motors. Solution from the rotors was then drained into Teflon sample bottles. Results from the analysis of these samples will be compared with the interstage sample results and raffinate sample analysis.

c. Aqueous Titrations

All the samples taken in Run 12 were titrated; the titrant was NaOH, dispensed from a 1.0 mL burette. Sample aliquots used approximately one-half of the burette volume, or in cases where the sample size was inadequate, one-half of the collected sample volume.

Titration results for the feed solution are listed in Table II-40. In the case of multiple endpoints, the first endpoint was assumed to be the nitric acid peak. Other endpoints were detected and are likely due to the neodymium present in solution. Sample DF#1 was from the original, undiluted feed solution, and sample DF#2 was collected from the feed tank after dilution. Agreement between duplicate analysis and the expected (flowsheet) concentrations is good except for the extraction feed samples (DF#1 and DF#2).

Table II-40. Aqueous Titration Results for the Feed Solutions from Run 12

Feed Solution	Conc. from Flowsheet, <u>M</u>	Conc. from Analyses, <u>M</u>	
		First	Second
Extraction (DF #1) ^a	1.0	0.981	1.263
Extraction (DF#2) ^b	0.5	0.499	0.601
Scrub (DS)	0.040	0.039	0.039
Am Strip (EF)	0.040	0.042	0.039
Acid Rinse (GF)	0.10	0.099	0.099

^aUndiluted sample.

^bSample diluted 1:1 with distilled water.

Results from the titration of the aqueous raffinate samples (DW, EW, GW) are given in Table II-41. The GTM predictions listed in this table were calculated using Version 2.1. The measured and calculated data are plotted in Figs. II-16 through II-18.

In general, agreement between duplicate samples for the various process streams is good (Table II-41), and the trend is as expected: the nitric acid concentration in the DW and EW raffinate streams starts low and increases to a constant steady-state concentration. However, the steady-state concentration does not agree with the GTM predictions -- the GTM predictions are lower for the raffinate samples (Figs. II-16 to II-18). The opposite is true for the samples collected from the stage bottom drains (Table II-42 and Fig. II-19). In addition, the series B sample concentrations are greater than the series A concentrations (see Table II-42). This means that the system was not at steady state during sample collection, or that something upset the system between sample collection to change the steady-state concentrations. Unfortunately, the results from the raffinate sample titrations do not support either conclusion -- those results indicate that steady-state operation was achieved in the test.

Samples collected from the stage rotors show much better agreement between duplicate samples (Table II-43) and with the GTM predictions (Fig. II-20). At this time, it is not known why the results from the rotor samples are in better agreement with the GTM than those from the bottom drain samples.

Table II-41. Calculated and Measured Aqueous Titration Results for Raffinate Samples from Run 12

Sample	GTM Prediction, <u>M</u>	Sample Time, min	Measured Sample H ⁺ Conc., <u>M</u>	
			First	Second
DW#1	0.700	12	0.669	0.663
DW#2	0.700	24	0.757	0.750
DW#3	0.700	32	0.729	0.735
DW#4	0.700	44	0.764	0.758
DW#5	0.700	52	0.770	0.772
EW#1	0.146	16	0.118	0.117
EW#2	0.146	28	0.176	0.160
EW#3	0.146	36	0.195	0.194
EW#4	0.146	48	0.199	0.199
EW#5	0.146	56	0.193	0.193
GW#1	a	16	0.078	0.068
GW#2	a	28	0.070	0.073
GW#3	a	36	0.077	0.076
GW#4	a	48	0.074	0.075
GW#5	a	56	0.070	0.075

*Concentration of the acid rinse stream (GF) was started at 0.10M. This stream was not recycled for this test. No prediction of the raffinate concentration is available from the GTM.

Fig. II-16 Concentration of the Extraction Section Raffinate Samples (DW) during Sample Collection in Run 12

Fig. II-17. Concentration of the Strip Section Raffinate Samples (EW) during Sample Collection in Run 12

Fig. II-18. Concentration of the Acid Rinse Raffinate Samples (GW) during Sample Collection in Run 12

Table II-42. Titration Results for Aqueous Stage Samples
Collected from Bottom Drains during Run 12

Stage Number	GTM Prediction, $\underline{M}$	Series A Samples, ^{a,b} $\underline{M}$		Series B Samples, ^{a,c} $\underline{M}$		Average Raffinate Sample, $\underline{M}$
		1st	2nd	1st	2nd	
1(DW)	0.715	0.660	0.633	0.701	0.717	0.754
2	0.958	0.964	0.967	1.012	1.009	
3	1.026	0.877	0.899	0.971	0.932	
4	1.296	0.563	0.545	0.865	0.855	
5	1.198	0.574	0.536	0.835	0.711	
6	1.003	0.276	0.455	0.473	0.501	
7	0.666	0.289	0.321	0.472	0.502	
8(EW)	0.296	0.110	0.111	0.159	0.165	0.195
9	0.132	0.065	0.070	0.070	0.078	
10	0.068	0.047	0.041	0.048	0.045	
11	0.049	-----		-----		
12	0.044	0.042	0.042	0.042	0.042	
13	0.042	0.045	0.044	0.047	0.040	
14	0.041	0.041	0.042	0.043	0.042	

^aSampling period started 1 h, 45 min, 10 s into the run.

^bSamples labeled "A" were collected between 20 and 40 min into the sample period.

^cSamples labeled "B" were collected between 40 and 58:30 min into the sampling period.

Fig. II-19. Aqueous Phase Titration Results from Stage
Samples Collected from the Bottom Drain
Valves during Run 12

Table II-43. Aqueous Titration Results for Stage Samples Collected from Rotors at Completion of Run 12

Stage Number	GTM Prediction, $\underline{M}$	Sample Conc., $\underline{M}$		Average Raffinate Sample, $\underline{M}$
		1st	2nd	
1(DW)	0.715	0.711	0.732	0.754
2	0.958	0.933	0.939	
3	1.026	1.039	1.033	
4	1.296	1.293	1.284	
5	1.198	1.087	1.089	
6	1.003	0.855	0.847	
7	0.666	0.482	0.480	
8(EW)	0.296	0.245	0.228	0.195
9	0.132	0.084	0.082	
10	0.068	0.051	0.051	
11	0.049	0.043	0.021	
12	0.044	0.040	0.041	
13	0.042	0.041	0.042	
14	0.041	0.039	0.040	
15		-----	-----	0.075
16		0.071	0.070

Fig. II-20. Aqueous Phase Titrations Results from Rotor Samples Collected at Completion of Run 12

d. Organic Titrations

Acid concentrations of DX, GP, and interstage samples were calculated from the organic titration results.

Table II-44 shows experimentally obtained acid concentrations for each interstage sample and the GTM predictions. Interstage samples 2, 3, 6, 8, and 9 were not titrated due to an insufficient amount of sample available. The measured and calculated data are plotted in Fig. II-21. Overall, the agreement between the experimental data and the GTM predictions is good.

Table II-44. Organic Titration Results for the Interstage Samples from Run 12

Stage Number	GTM Prediction, <u>M</u>	Experimental Results, <u>M</u>		
		1st	2nd	3rd
1A	4.24E-01	5.14E-01	4.67E-01	4.87E-01
2A	5.44E-01	a		
3A	5.73E-01	a		
4A	5.48E-01	4.81E-01	4.84E-01	
4B	5.48E-01	5.09E-01	5.22E-01	
5A	5.00E-01	4.01E-01	3.23E-01	4.09E-01
5A (cont.)		4.30E-01	4.12E-01	
6A	4.15E-01	a		
7A	2.59E-01	1.82E-01	1.75E-01	
8A	9.49E-02	a		
9A	3.07E-02	a		
10A	1.13E-02	7.34E-03	1.25E-02	
11A	6.11E-03	2.93E-03	2.93E-03	
12A	4.18E-03	4.65E-03	6.36E-03	
13A	3.09E-03	3.26E-03	4.89E-03	
14A	2.57E-03	2.64E-03	2.97E-03	
14B	2.57E-03	2.84E-03	2.62E-03	

*Insufficient sample to titrate.

Fig. II-21. Measured and Calculated Acidic Titration Results for the Organic Interstage Samples from Run 12

The titration results for the organic feed and product samples are listed in Table II-45. The GP sample results are plotted in Fig. II-22. These data show that the organic acid concentration in the product stream was fairly constant during the run. The rotor drain samples from Run 12 were not titrated because of problems with the organic titration equipment. Once the titration equipment was repaired, the samples were too old to have confidence in the analytical results.

Table II-45. Organic Titration Results for Organic Feed and Product Samples from Run 12

Sample Name	Time of Collection, min	Experimental Results, <u>M</u>	
		1st	2nd
GP1	12	9.88E-03	9.88E-03
GP2	24	8.51E-03	9.05E-03
GP3	32	8.22E-03	7.82E-03
GP4	44	8.31E-03	7.87E-03
GP5	52	7.92E-03	7.87E-03
DX1	--	4.77E-03	4.43E-03
DX2	--	4.76E-03	4.93E-03

Fig. II-22. Measured Titration Results (duplicate, GP stream) for the Organic Product Samples from Run 12

e. Conclusions

Although the organic titration results agreed favorably with the GTM predictions, the agreement for the aqueous titrations was not as good. Rerunning a newer version of the GTM that incorporates stage sampling would probably improve the accuracy of the GTM predictions for this test. In addition, agreement between the raffinate samples and the corresponding interstage samples (see

Tables II-42 and II-43) was not good either. Some of the difference could be due to the instability in the sample flow(s); we had a very difficult time getting our samplers (Fig. II-15) to work. Before being used again, we need to reevaluate their design to improve operation. One other interesting observation is that the Series A and Series B samples (Table II-42) do not agree with each other, particularly in the scrub section. This indicates that the system was not at steady state at the beginning of the sampling period.

I. Centrifugal Contactor Development

(R. A. Leonard, D. B. Chamberlain, L. Chow, F. C. Mrazek, M. O. Wasserman,*
D. G. Wygmans,** and K. A. Barnhouse***)

The Argonne centrifugal contactor is modified as necessary to work with specific solvent extraction processes. To evaluate processes involving high levels of alpha/beta activity (in a glovebox) and/or high gamma radiation (in a shielded cell facility), contactors have been designed and built for remote handling. To minimize the feed needed for testing solvent extraction flowsheets, a 2-cm contactor (minicontactor) was designed and built. For each new process, solution densities and organic-to-aqueous (O/A) flow ratios are reviewed, and if necessary, the rotor weirs are modified.

In support of our contactor development efforts, vibrational measurements are being made using proximity probes and real-time analyzers. The results are related to the rotor design by the use of a vibrational model for rotating systems. We are also testing centrifugal contactors for use as concentrators and are continuing to improve our contactor designs for TRUEX applications.

1. Vibrations

To support the design of new contactors, methods for modeling and measuring vibrations have been developed. In general, vibrations will not be a problem if (1) the first natural frequency is at least 20% higher than the rotating speed of the system, and (2) the amplitude of the vibrations for the motor shaft are within the manufacturer's specifications. Vibrational amplitudes and natural frequencies are measured using proximity probes and real-time analyzers (such as the Zonic Real Time Spectrum Analyzer), respectively. The first natural frequency for a rotor can be calculated through the method of transfer matrices. A BASIC program called BEAM IV (developed by L. D. Mitchell et al., Mechanical Engineering Department, Virginia Polytechnic Institute and State University, Blacksburg, Virginia) was developed to do these calculations. To make the transfer matrix method relatively easy to use, we have developed a Beam worksheet using Microsoft Excel. Vibration data needed for these transfer matrix calculations were obtained by laboratory tests on motors and motor/rotor systems. The Beam worksheet and the other vibrational tools can now be applied as needed to various design problems, including (1) the effect of temperature on the first natural frequency, (2) the use of bearings below the motor, and (3) the construction of contactors made of plastic, e.g., Kynar.

a. Beam Worksheet

An Argonne report on the Beam worksheet is being prepared to (1) document the Beam worksheet and macro, (2) give the relevant vibration theory, (3) compare the first natural frequency calculated from this massless beam model with the equivalent uniform beam model from the BEAM IV program, and (4) compare natural frequencies calculated using the Beam worksheet with experimental

* Graduate co-op student from University of Illinois at Chicago.

** Co-op student from University of Illinois at Chicago.

*** Co-op student from University of Cincinnati.

results from 2-, 4-, and 10-cm contactors. The first natural frequencies (f_n) calculated with various vibration models for a 2-cm motor/rotor assembly are given in Table II-46. For the identical case of a massless beam with 11 sections, the Beam worksheet and BEAM IV give nearly identical results. This result validates these two implementations of the transfer matrix method. When the Beam worksheet model was improved by dividing it into 21 sections, the calculated value for f_n increased by 0.5%. When the BEAM IV model was improved by changing to a beam with continuous mass, a feature not available in the Beam worksheet, f_n increased by 0.5%. Compared with the experimental value for f_n of 37.5 ± 2.5 Hz, the various calculated values are essentially identical.

Table II-46. Comparison of Various Vibration Models for a 2-cm Motor/Rotor Assembly

Vibration Model	Type of Beam Section	Number of Sections	Calculated ^a Natural Frequency, Hz
Beam Worksheet	Massless	11	38.73
Beam Worksheet	Massless	21	38.94
BEAM IV	Massless	11	38.74
BEAM IV	Continuous	11	38.96

^aThe measured first natural frequency (f_n) was 37.5 ± 2.5 Hz. The solid stainless-steel rotor was 2.5 cm (1 in.) in diameter and 12.7 cm (5 in.) long and was attached to a Bodine 710 motor by a shaft that was 1.1 cm in diameter and 4.8 cm long. Measurements were made by increasing the rotor frequency to 60 Hz then decreasing it through f_n . A stroboscope was used to measure the rotor speed just above and below f_n .

In general, the experimental f_n values from the various tests with 2-, 4-, and 10-cm contactors were within $\pm 10\%$ of the model values. However, the motor had to be taken apart so that a good motor model could be developed. When the motor model was estimated from the overall length of the motor and the diameter of the motor shaft, the experimental f_n values were still fairly close to the model values, typically within $\pm 20\%$. Thus, transfer matrices can be used to model the rotating motor/rotor assembly of a centrifugal contactor.

b. Experimental Work

The Zonic 6088 Real Time Spectrum Analyzer (RTSA) has worked well. When we have had problems, they have usually been caused by the way in which the experimental test was carried out. For example, when the Zonic RTSA was used to measure the first natural frequency of a motor/rotor assembly from our remote-handled 4-cm contactor, it produced a very broad band for the first natural frequency with peaks at 31 and 104 Hz. For this static test, the motor/rotor assembly was vibrationally isolated from the environment by placing it on a foam pad. The two peaks were eliminated by changing our test procedure. In the new procedure, the motor of the motor/rotor assembly was clamped to a rigid surface (for example, a table top). When we did this, only one peak appeared, at 80 ± 5 Hz. This result agrees well with the first natural frequency of 80.9 Hz calculated from the Beam worksheet.

c. Applications

In some cases, it is desired to increase throughputs for a contactor yet keep the rotor diameter constant. For example, one may want to keep the contactor at a certain diameter so that built-in safety with respect to nuclear criticality will be maintained. Or, one may simply want a higher throughput from an existing contactor. To achieve higher throughputs, the contactor rotors have to be made longer or run at higher speeds. In either case, vibrational problems become more severe.

A problem of limited capacity in the 10-cm contactor being operated at Westinghouse Hanford (see Sec.II.I.3) was solved by doubling the rotor speed, from 30 Hz (1800 rpm) to 60 Hz (3600 rpm). To solve the vibrational problems, a stiffer shaft above the rotor with two external bearings has been proposed. The motor would be located above the shaft and connected to it by a flexible coupling. Our analysis showed that the first natural frequency for this arrangement will be 88.5 Hz (5310 rpm). Since this f_n is 48% higher than the new operating speed for the contactor, the proposed modifications to the 10-cm Hanford contactor should not introduce any vibrational problems.

We are now starting to investigate a second way of increasing contactor throughput. In this method, the use of a pin bearing below the rotor would eliminate the need for any external bearings above the rotor. Our ultimate goal is to identify the hydraulic and vibrational factors that limit contactor throughput for a given rotor diameter.

2. Contactor Concentrator

An impressive feature of centrifugal contactors, when compared with other solvent extraction equipment, is their ability to operate at very high and very low O/A flow ratios. In this work, we have demonstrated that, at these extreme O/A flow ratios, the extraction efficiency is still high. Since this is the case, contactors can be used to concentrate (by factors of 10 to 1000 or more) those metal ions that have a high distribution ratio during extraction and a low ratio during stripping. For such metal ions, one should be able to reduce, and in some cases eliminate, the need for downstream processing of one or more effluent streams.

This work was broken into two parts. The first part was to develop a theory so that one can estimate the amount of concentration that might be achieved in a contactor concentrator for a specific component in the feed. The second part was to measure the extraction efficiency of centrifugal contactors at very high and low O/A flow ratios.

a. Theory

(1) Simple Analysis

In solvent extraction processes, the distribution ratio (D) of each component is important for process analysis. The D value is defined as the concentration of that component in the organic phase divided by its concentration in the aqueous phase after the two phases have been equilibrated. A second quantity, the O/A flow ratio (R), is also important. These two quantities are combined to form the extraction factor (E), which is given by

$$E = RD$$

(II-36)

For a given process stage, the extraction factor gives the moles of a component in the organic phase divided by the moles of this same component in the aqueous phase. If E is greater than 1.0, the component is being concentrated in the organic phase; if less than 1.0, in the aqueous phase. Also, a stripping factor (S) is defined as $1/E$. When E is high, conditions are favorable for extraction. When S is high, conditions are favorable for stripping.

When a component is being extracted, its extraction factor should be greater than two, although ten or higher is preferable. Since, for a given system, the D value is fixed, the extraction factor is set by the choice of R value. On the one hand, a high R value gives a high E value, so that extraction is easy and only a few process stages are required for a given decontamination factor ($D.F.$). As a first approximation, the $D.F.$ for an extraction section with n stages is given by

$$D.F. = E^n \quad (II-37)$$

Thus, a process with an E of 10 will typically need considerably fewer stages than a process with an E of 2 for a given $D.F.$ On the other hand, a low R value gives good component concentration in the organic phase. However, the E value will also be lower, so that extraction is harder and many process stages may be required for a given $D.F.$ In designing the extraction section of a concentrator, the R value chosen is a compromise between (1) a high value for good component extraction with only a few contactor stages and (2) a low value for good component concentration in the organic phase but with more contactor stages.

Conversely, when a component is being stripped, its extraction factor should be less than 0.5 and preferably 0.1 or lower. Since, for given solvent and aqueous phase compositions, the D value is fixed, the extraction factor is set by the choice of R value. On the one hand, a low R value gives a low E value, so that stripping is easy and only a few process stages are required for a given stripping factor ($S.F.$). As a first approximation, the $S.F.$ for a stripping section with n stages is given by

$$S.F. = E^{-n} \quad (II-38)$$

Thus, a process with an E of 0.1 will typically need considerably fewer stages than a process with an E of 0.5 for a given $S.F.$ On the other hand, a high R value gives good component concentration in the aqueous phase. However, the E value will also be higher, so that stripping is harder and many process stages may be required for a given $S.F.$ In designing the stripping section of a concentrator, the R value chosen is a compromise between (1) a low value for good component stripping with only a few contactor stages and (2) a high value for good component concentration in the aqueous phase but with more contactor stages.

In estimating the amount that a component can be concentrated without requiring an excessive number of stages, one balances the number of stages required with the desired concentrating effect. To this end, the flow ratio for a section can be related to the D value for the key component to be concentrated in the section using

$$R = \frac{1}{\sqrt{D}} \quad (II-39)$$

Then, combining Eqs. II-36 and II-39 gives

$$E = \sqrt{D} \quad (\text{II-40})$$

With this choice for a balanced design, the overall concentrating factor (O.C.F.) is given by

$$\text{O.C.F.} = \sqrt{\frac{D_{\text{extr}}}{D_{\text{strip}}}} \quad (\text{II-41})$$

Equation II-41 gives a rule-of-thumb for estimating the nominal O.C.F. that might be achieved in a balanced concentrator design for a component which has D values of D_{extr} in the extraction section and D_{strip} in the strip section.

(2) Concentrator Design

A schematic of a typical concentrator design is shown in Fig. II-23. Each section will have one or more stages. In this schematic, four stages are shown for each of the two sections. With a high extraction factor in the extraction section (that is, 10 or higher), 90% of the concentrating effect in the organic phase will be realized with only one stage. The use of additional extraction stages lowers the component concentration in the aqueous raffinate and increases the concentrating effect even closer to 100%. With lower extraction factors, typically greater than or equal to two, several stages will be required to realize a concentrating effect of 90% or higher in the organic phase.

Fig. II-23. Schematic of Concentrator with Eight Contactor Stages

Conversely, with a low extraction factor in the strip section (that is, 0.1 or lower), 90% of the concentrating effect in the aqueous phase will be realized with only one stage. The use of additional stripping stages increases the component concentration in the concentrated aqueous effluent and pushes the concentrating effect even closer to 100%. With higher extraction factors, typically less than or equal to 0.5, several stages will be required to realize a concentrating effect of 90% or higher in the aqueous phase.

In addition to the extraction and strip sections shown in Fig. II-23, some processes may have one or more components entrained or partially extracted into the organic phase coming from the extraction section. If these components are harmful or unwanted in the concentrated effluent, a scrub section of one or more stages can be inserted between the extraction and strip sections. Typically, the aqueous effluent from the scrub section joins with the aqueous feed to form a combined feed for the extraction section and emerges as part of the aqueous raffinate.

A final feature of the concentrator design shown in Fig. II-23 is the complete recycle of the organic phase. This feature requires that the extraction and strip sections be balanced. To achieve this, enough of the concentrated component must be removed from the organic phase (EP), leaving the strip section so that one achieves the low component concentration desired in the aqueous raffinate (DW) from the extraction section. In some cases, it will be necessary to include a solvent cleanup section after the strip section.

(3) Complex Analysis of Performance

Concentrator performance was analyzed by using the GTM. The SASSE worksheet in the GTM is being modified so that extraction efficiencies less than 1.0 (100%) can be included. The extraction efficiency being somewhat less than 1.0 reduces the concentrating effect, but separations are still high enough to allow the contactor to be used as a concentrator. Calculations were performed using neodymium in a salt solution with the configuration shown in Fig. II-23. An extraction efficiency of 70% in every stage was found to reduce the neodymium concentration in the EW effluent by only 10%. However, the neodymium concentration in the DW effluent was increased by a factor of eight. For this case, about four more stages would have been required in both sections to overcome this reduction in extraction efficiency.

A second question, the effect of other-phase carryover, was explored with this analysis. Since the flow of the low-flow phase can be very low, the amount of other-phase carryover on a percentage basis might be large even if its absolute amount is low. Using the SASSE worksheet, we calculated that large amounts of other-phase carryover in the low-flow phase, e.g., 35%, had almost no effect on the operation of the concentrator. This limited effect of other-phase carryover in the low-flow phase agrees with a more qualitative analysis that predicts the same result.¹⁶

b. Extraction Efficiency

In the first phase of the experimental work, we conducted two series of tests for neodymium extraction efficiency at very low O/A flow ratios (0.0101 and 0.0096). These tests were made in stage 5 of a 4-cm remote-handled contactor. The aqueous feed contained $7 \times 10^{-5} \text{M}$ Nd with 2.0M NaNO_3 and 0.02M HNO_3 . The organic feed was TRUEX-nDD, essentially TRUEX-NPH. Total throughputs, which ranged from 200 to 400 mL/min, had little effect on the extraction efficiency. We found that contactor efficiency remains high for neodymium at the low O/A ratios. However, the average extraction efficiency was 84%, with individual values ranging from 74 to 92%, rather than the >95% extraction efficiency typically seen when the O/A flow ratio ranged from 0.5 to 2.5.

In the second and final phase of this experimental work, we showed that contactor efficiency remains high for neodymium in a series of tests at a very high O/A flow ratio (33). However, the average extraction efficiency was 85%, with individual values ranging from 46 to 100% because of experimental problems, rather than the >95% extraction efficiency typically seen when the O/A flow ratio ranged from 0.5 to 2.5. These tests used stages 5 and 6 of the 4-cm remote-handled contactor. In the first stage (stage 5) of this two-stage test, neodymium was loaded into the organic phase from a high-salt, low-acid aqueous feed containing $2.88 \times 10^{-6} \text{M}$ Nd with 1.925M NaNO_3 and 0.02M HNO_3 . The O/A flow ratio in the extraction stage was 2.7 so that the amount of aqueous feed needed was reduced. The loaded solvent was then stripped of its neodymium in the second stage (stage 6) at a very high O/A flow ratio (40, actually 33 when the aqueous phase carried over with the organic phase from the first stage is included) so that the aqueous effluent from the second (strip) stage has a much higher neodymium concentration than the aqueous feed solution. Higher O/A flow ratios were considered but rejected because the error in measuring the extraction efficiency would have been unacceptable. The aqueous feed to the second stage contained no Nd or NaNO_3 ; however, it had 0.02M HNO_3 and 0.05M 1-hydroxyethane-1,1-diphosphonic acid (HEDPA). The HEDPA is a water-soluble organic complexant that strips the neodymium from the organic phase. As with the earlier tests, the organic feed was TRUEX-nDD, essentially TRUEX-NPH, in complete recycle. Since the flow rate for the organic phase was 390 mL/min and the total volume of organic phase was about 600 mL, the organic phase was recycled many times during the 28-min run.

Thus, the Argonne centrifugal contactor has been tested as a concentrating device at both high (33) and low (0.01) O/A flow ratios and found to work reasonably well. The extraction efficiency results, summarized in Table II-47 and plotted in Fig. II-24, were correlated by the empirical equation

$$E = 0.986 (1 - 0.08 |\log R|) \quad (\text{II-42})$$

which is also plotted in Fig. II-24.

Table II-47. Summary of Extraction Efficiency Data at Various O/A Flow Ratios

Element	O/A ^a	E ^a	Notes
Nd	0.0096 ± 0.0004	0.796 ± 0.075	b
Nd	0.0101 ± 0.0013	0.877 ± 0.099	c
U	0.5 to 2.5	$0.986 \begin{matrix} + 0.01 \\ - 0.03 \end{matrix}$	d
Nd	2.68 ± 0.03	0.960 ± 0.025	e
Nd	32.8 ± 1.7	0.851 ± 0.130	f

^aExcept as noted, 1- σ error limits are shown.

^bComposite of three tests in the second test series at O/A = 0.01.

^cComposite of three tests in the first test series at O/A = 0.01.

^dExtraction efficiency and error range are estimated from earlier measurements where the O/A flow ratios ranged from 0.5 to 2.5.¹⁷⁻¹⁹ Most of these extraction efficiency measurements were made at an O/A of 1.0.

^eComposite of two test results obtained while the solvent was loaded with Nd for the high O/A flow ratio tests.

^fComposite of two tests at different residence times for the test series at O/A = 33.

Fig. II-24. Overall Correlation of O/A Flow Ratio with Extraction Efficiency

As seen in this figure, the greatest error occurred at an O/A flow ratio of 33. Three reasons were identified for the high error of this test series. First, the value for D_{Nd} in the stripping stage (stage 6) was 0.12, higher by a factor of 2 to 4 than the value we expected based on preliminary tests. As a result, the stripping factor was only 4.0. As the stripping factor drops nearer to 1.0, the error involved in measuring E is magnified. Second, the initial concentration of neodymium in the solvent was high. Since the stripping factor for neodymium in the stripping stage was only 4.0, the neodymium was removed more slowly than expected as the solvent was recycled. As a result, the process never reached a true steady state, and calculations for E are based on quasi-steady-state operation using neodymium concentrations for various effluents taken at the same residence time into the test. Finally, since the neodymium concentrations were higher than expected, the neodymium concentrations in the EW samples were above the $5.8 \times 10^{-5} M$ limit that we had set to prevent precipitation of the neodymium salt of HEDPA. As a result, the plasma and the nebulizer of the ICP/AES were erratic during analysis of the EW samples, indicating that solid particles were in these solutions and introducing additional error into the E value at an O/A flow ratio of 33.

3. 10-cm Contactor

Based on initial tests at ANL and Westinghouse Hanford and on revised process needs for the TRUEX process (the use of NPH as the diluent in place of TCE), the 10-cm contactor for the proposed TRUEX facility at the Westinghouse Hanford Plutonium Finishing Plant (PFP) required some modifications. Changes have been proposed by both Hanford and Argonne. Based on these proposals, one of the 10-cm motor/rotor assemblies will be modified and tested at Hanford. Then the assembly will be shipped to Argonne, where the upper weir of the rotor will be modified and tested to determine if it operates properly with the new solvent (TRUEX-NPH) at higher rotational speed (3600 rpm instead of 1800 rpm). The vibrational characteristics will be modeled and tested at the same time. Based on this work, the final design for the 10-cm contactor will be specified.

A stand for testing the modified 10-cm motor/rotor assembly was built and set up in a walk-in hood. However, because of a loss of funding for this project, the new motor/rotor assembly was never built. As a variety of TRUEX projects are continuing to be explored at Hanford, we expect that this effort could be refunded at a later date.

4. 2-cm Contactor

Based on our plans to send a sixteen-stage 2-cm contactor (minicontactor) to Chalk River Laboratories, we have built and tested a new twenty-four-stage 2-cm contactor. The volume tests, which also check for rotor leaks, showed that the average rotor volume is 6.2 mL, with a standard deviation of ± 0.2 mL. Single-phase flow tests gave an apparent radius for the upper weirs of 5.93 mm (diameter = 0.467 in.), with a standard deviation of ± 0.04 mm, somewhat less than the apparent radius of 6.06 ± 0.06 mm (diameter = 0.495 in.) found for the original minicontactor. The actual radius of the upper weirs for both units is 6.12 mm (diameter = 0.4815 in.). The new minicontactor was evaluated further by running the two-phase flow test on a typical rotor (rotor 7). The results of this test, listed in Table II-48, show that the rotors have acceptable performance, that is, less than 1% other-phase carryover in either phase over a reasonable range of O/A flow ratios. The design criterion of 40 mL/min at all O/A flow ratios with this contactor should be easily met.

Table II-48. Results of Two-Phase Flow Tests for Typical 2-cm Rotor

O/A ^a	Total Flow Rate, mL/min	A in O, %	O in A, %	Appearance	
				Organic	Aqueous
0.40	106	0.0	0.7	Sl. Cloudy	Clear
	140	38.8	0.0	Cloudy	Cloudy
1.13	113	0.0	0.0	Cloudy	Cloudy
	174	19.6	6.1	Very Cloudy	Cloudy
5.94	222	0.0	0.0	Very Cloudy	Cloudy
	280	0.0	5.0	Very Cloudy	Very Cloudy

^aOrganic phase (O) is TRUEX-nDD (essentially TRUEX-NPH), and the aqueous phase (A) is 0.01M HNO₃.

J. Aqueous Biphasic Separation of Plutonium from Solid Residues (D. J. Chaiko)

1. Introduction

Many of the plutonium residues generated during fuel reprocessing and plutonium recovery operations are heterogeneous materials in which the plutonium is distributed as discrete grains within a larger particle matrix. Ultrafine grinding of these residues to an average particle size of about 1 μm can be used to liberate the plutonium from the particle matrix and thereby provide an opportunity to produce a plutonium concentrate in a significantly reduced volume. Physical beneficiation of these materials to produce a plutonium-concentrate would significantly reduce the amount of reagents used during subsequent chemical processing, reduce the mass (volume) of chemical processing wastes, and produce a richer product stream from leaching or dissolution operations.

As particle size decreases below 20-50 μm , physical beneficiation techniques such as flotation, magnetic separation, electrostatic separation, and gravity concentration become increasingly ineffective. However, aqueous biphasic extraction is particularly suited to the treatment of ultrafine particle systems having an average particle size of 1 μm or less. In this size range, particle behavior is no

longer dominated by bulk phase properties like density and magnetic susceptibility but by surface chemical properties.

Aqueous biphasic systems were originally developed by Albertsson in the mid-1950s for the separation of microbial cells, cell organelles, and viruses.²⁰ In recent years, interest in aqueous biphasic systems for application in biotechnology,^{21,22} including separations of metal ions,²³ ultrafine particles,²⁴ and organics,²⁵ has increased dramatically.

In aqueous biphasic extraction, colloid-size particles selectively partition between two immiscible aqueous phases. These aqueous/aqueous systems form spontaneously from mixtures of polymer and inorganic salt solutions. For example, combining equal volumes of a 15 wt % solution of sodium sulfate and a 15 wt % solution of polyethylene glycol (PEG) produces a turbid mixture which will separate after a few minutes. As a result of this separation, the sodium sulfate concentrates in the bottom layer, and the polymer concentrates in the top layer. Particles suspended in such a system will migrate to one aqueous phase or the other, depending on a complex balancing of particle interactions with the surrounding solvent through hydrogen bonding, hydrophobic bonding, etc. Process selectivity can be improved by system modification with surfactants containing the appropriate functional groups. Aqueous biphasic extraction processes could be used in place of other techniques, such as oil flotation and conventional solvent extraction utilizing an oil/water system. This would eliminate the need for costly petroleum-based diluents, which may generate concern as a source of pollution or a potential fire hazard. The water-soluble polymers that can be used in biphasic formation are inexpensive, nontoxic, and biodegradable. An additional attractive feature of the aqueous/aqueous system is that extractions can be carried out using conventional contacting equipment, such as mixer/settlers, pulsed columns, and centrifugal contactors.

A number of DOE waste streams would be good candidates for aqueous biphasic extraction processes. Some examples of specific waste streams involving particulates are pyrochemical wastes such as sands, slag, and crucible residues from Savannah River Site, and incinerator ash and ceramic crucibles from Rocky Flats Plant. These materials contain significant amounts of plutonium and are being stockpiled. In cases where the plutonium content is high enough to exceed economic discard limits, the material must be processed. With currently available technology, this can generate large volumes of mixed wastes. Physical beneficiation by aqueous biphasic extraction could significantly reduce the volume of mixed wastes generated from chemical recovery processes.

The scope of work for this project includes (1) particle characterization of plutonium residues, (2) demonstration of aqueous biphasic separation of model particle systems on a test-tube scale, (3) evaluation of plutonium polymer as a model system for correlating the partitioning behavior of plutonium-containing particles, (4) preliminary tests of biphasic separation with Na_2SO_4 and PEG. Progress in each of these tasks is described below.

2. Particle Characterization

a. Analysis of Plutonium-Containing Residues

Since aqueous biphasic separation processes exploit subtle differences in the surface properties of particles, characteristics such as size distribution and surface composition play an important role in extraction performance. Samples from two different plutonium-containing residues were examined by scanning electron microscopy (SEM). The first was an ash heel sample obtained through Lawrence Livermore National Laboratory. The original feed material for producing the heel was an incinerator ash from Rocky Flats Plant that was calcined, ground to a particle size of 10-20 μm , and

leached by mixtures of nitric acid and hydrofluoric acid. In many of the particles, the plutonium appears as discrete grains of $\sim 1\text{-}\mu\text{m}$ dia embedded in a complex matrix of metal oxides and silica. In other particles from this sample, only aluminum was detected in the matrix surrounding the plutonium. At the same time, a number of particles in the ash heel appeared to be composed entirely of plutonium. The electron micrographs were published in the previous semiannual (ANL-91/42, Sec.II.L.1).

The other plutonium-containing residues examined were ceramic crucibles used in analytical procedures for the determination of carbon in plutonium. The waste crucibles typically contain about 0.2 g of plutonium in the form of PuO_2 embedded in the crucible. Because of the refractory nature of high-fired PuO_2 , the plutonium cannot be leached from the LECO crucibles with HNO_3/HF mixtures.

During the carbon analysis, the crucible, with its sample, is rapidly heated (~ 10 s) to temperatures between 1600 and 2400°C. A combustion accelerator, such as Fe, Cu, or Sn, is added to the sample. An oxygen stream is passed over the crucible to ensure conversion of the carbon (in the form of plutonium carbide) to CO and CO_2 . Before carrying out a quantitative analysis for CO_2 , the gas stream is directed over a catalyst bed to ensure complete conversion of CO to CO_2 .

A flux is added to the plutonium sample to completely dissolve the plutonium and thus allow oxygen access to any carbon in the sample. Three different fluxes (Cu, Sn, Fe) are used in analyzing plutonium samples.

A LECO crucible was crushed and ground to produce samples for particle characterization by SEM. During dry grinding in a coffee mill, the ceramic fraction of the crucible was easily reduced in size to -200 mesh ($<74\text{ }\mu\text{m}$), while a metal oxide fraction (primarily copper oxide) larger than 200 mesh remained despite repeated grinding. Figures II-25 and II-26 are electron micrographs of particles from the -200 mesh and +200 mesh portions, respectively. In a large majority ($\sim 90\%$) of the particles from the -200 mesh fraction, only silica was detected (see Fig. II-27), while in other particles of this size fraction, Si and Al were primarily detected (see Fig. II-28). Interestingly, plutonium was observed only in particles that also contained significant amounts of copper, as shown in Fig. II-29.

— = 100 microns

Fig. II-25. Backscattering Electron Micrograph of -200 Mesh Fraction from Crushed LECO Crucible

Fig. II-26. Backscattering Electron Micrograph of +200 Mesh Fraction from Crushed LECO Crucible

Fig. II-27. Energy Dispersive X-Ray Spectrum of Typical Gray Particle in Fig. II-25

Fig. II-28. Energy Dispersive X-Ray Spectrum of Light Gray Particle in Fig. II-25

— = 10 microns

Fig. II-29. Backscattering Electron Micrograph of Typical Plutonium-Containing Particle from Crushed LECO Crucible

The particle shown in Fig. II-29 is the bright particle in the upper left-hand corner of Fig. II-26. The substrate in this particle contained primarily copper, as evidenced by the energy dispersive X-ray spectrum (EDS) shown in Fig. II-30. The bright specks in the particle in Fig. II-29 were shown to contain plutonium (see Fig. II-31). The EDS spectrum in Fig. II-31 also shows the presence of copper. This may be evidence of a Pu/Cu alloy or simply an artifact produced from our inability to focus the electron beam into a spot small enough to completely exclude any contributions from the copper matrix surrounding the plutonium speck. The dark circles within the particle are a mixture of primarily Cu, Al, and Si, with small amounts of Pu and Ca (see Fig. II-32). Presumably the Al and Si originated from the crucible. At higher magnification, the matrix in the particle from Fig. II-29 shows a dendritic microstructure suggestive of eutectic formation.

Fig. II-30. Energy Dispersive X-Ray Spectrum of Particle Matrix from Fig. II-29

Fig. II-31. Energy Dispersive X-Ray Spectrum of Light Specks in Particle from Fig. II-29

Fig. II-32. Energy Dispersive X-Ray Spectrum of Dark Circles within Particle from Fig. II-29

The geometric arrangement of the plutonium in Fig. II-29 is quite interesting. Intersecting lines at 120° are clearly visible and show the positions of the grain boundaries within the particle. As in the ash heel, the plutonium grains in the crucible sample are about $1\ \mu\text{m}$ in diameter. The breakage pattern suggests that grinding to a top size of about $100\ \mu\text{m}$ would be sufficient to liberate the plutonium from the bulk of the ceramic. Continued size reduction into the ultrafine regime ($\sim 1\ \mu\text{m}$) should further liberate some of the plutonium from the bulk of the copper.

b. Particle Size Analysis

Aqueous biphasic extraction can be only used with feed materials where particle size is less than about $1\ \mu\text{m}$. To routinely measure particle sizes in this range, photon correlation spectroscopy, sometimes referred to as dynamic laser light scattering, will be used. A schematic diagram of the system used in the aqueous biphasic extraction studies is shown in Fig. II-33.

Fig. II-33. Schematic Diagram of Photon Correlation Spectroscopy System

In this system, samples can be suspended in aqueous or organic solvents and are contained in a cuvette of either optical quartz or a clear plastic, such as polycarbonate or polystyrene. Light from the laser source (in this case, a 35 mW He-Ne laser) is directed through an index matching chamber which contains the cuvette. The chamber contains a refractive index matching fluid such as water or toluene.

During a measurement, the fluctuation in scattering intensity from a sample is recorded over a time scale of a few nanoseconds to several seconds. The fluctuations arise from the diffusion of particles or macromolecules through the laser beam and depend on the diffusion rate, the wavelength of the laser, and the angle of observation. The intensity and fluctuations of the scattered light are measured by a photomultiplier as discrete photons. The output from the photomultiplier is fed into a correlator, which calculates the autocorrelation function. From this function, a diffusion coefficient can be obtained, and then a particle size can be estimated through the Stokes-Einstein equation.

Under optimal conditions, the spectroscopic instrument (purchased from Malvern) can measure particle sizes as small as 5-10 nm and as large as 1-5 μm . The practical limit on the upper size boundary is determined by the settling rates of the larger particles under the influence of the earth's gravitational field. Size distributions are calculated using Mie theory, which requires the refractive index of the particles and that of the supporting medium. If the refractive index of the particles is unknown, then Rayleigh-Gans-Debye (RGD) theory is used. A comprehensive review of the theory and application of dynamic light scattering has been presented by Stock and Ray,²⁶ as well as others.²⁷

Two types of cuvettes can be used for routine size analysis: square plastic cells (12 x 12 x 46 mm), which are disposable, and precision, round optical glass cells (10 mm dia x 70 mm long), which can be used for multiangle analysis. The square cells are unsuitable for use with radioactive samples because of the lack of tight-fitting caps. Safety caps can be obtained for the round glass cells through Fisher Scientific (Cat. No. 02-706-5). These would be adequate for containing aqueous suspensions. Unfortunately, the high cost of the optical glass cuvettes (\$15.00 each from Malvern Instruments or \$5.00 each from Wilmad-Glass Co., Cat. No. WG-99-G) is prohibitive for use with radioactive samples since they could be used only once and then must be disposed. Disposable, optically

clear polystyrene tubes (10 mm dia x 75 mm long) can be purchased from Evergreen Scientific (Cat. No. 214-2003-010, \$25.00 per 10000). These tubes are supplied with two different types of tight-fitting polyethylene caps, which are similar to the caps used on the plastic gamma counting tubes.

Particle size standards were purchased from Duke Scientific (P.O. Box 50005, Palo Alto, CA 94303). Calibrated standards ranging in size from 20 to 900 nm are available for \$110/15 mL. Three different sizes of latex spheres were purchased: 30, 63, and 300 nm (mean diameter). The diameters of the particles were calibrated by the manufacturer using transmission electron microscopy (TEM) and photon correlation spectroscopy (PCS). All three standards are supplied as aqueous suspensions at solids concentrations of 2 wt %. To dilute the standards for size measurement, the bottle should be sampled using a microliter pipettman. For statistically consistent samples, the bottle should be **GENTLY** inverted several times. If an ultrasonic water bath is to be used to help disperse the particles, **EXTREME** caution should be exercised since even short exposure to high-level ultrasonic energy can damage the latex spheres.

For PCS measurement of the particle size standards, the suspensions were diluted with distilled water to a known solids concentration. The 30 nm standard was diluted to 5.5×10^{-2} wt % solids, giving a clear suspension. This solids concentration will give an optimum balance between the signal-to-noise ratio of the scattered light and a minimum of multiple scattering and particle-particle interactions. As a guide, if the suspension looks milky or cloudy, then multiple scattering (that is, light scattered by one particle is scattered again by another) is occurring, and the solids concentration is too high for PCS analysis. The Z-average mean, measured as 29.4 nm, is within the certified mean diameter of 30 ± 2.3 nm.

A large dependence of measured size on particle concentration indicates that either multiple scattering is occurring, or the laser-detector system is not properly aligned. Based on light scattering theory, multiple scattering would result in a lower measured mean size than the actual value. Therefore, as the sample is diluted (assuming multiple scattering is occurring), the average particle size should increase until a plateau is reached. If low enough concentrations are not possible (because of limitation in laser power), the measurements at higher concentrations can be extrapolated to zero concentrations.

It is interesting to note that increasing the particle concentration of the 30 nm standard up to 1 wt % had very little effect on the measured particle size distribution.

Analysis of the 63 ± 2.8 nm particle standard, at solids concentrations of 4×10^{-3} and 8×10^{-3} wt %, gave measured Z-average means of 67 nm and 67.8 nm, respectively. A 1.6×10^{-3} wt % suspension was prepared for the largest particle size standard. The measured Z-average mean was 306.5 nm--within the calibrated size of 301-313 nm reported by Duke Scientific. At this concentration of solids, however, the suspension had a slight, milky color, suggesting that the solids concentration was high enough to cause significant levels of multiple scattering. Further dilution of the standard by approximately five fold, to 3×10^{-4} wt % solids, produced a measured Z-average mean of 318.8 nm. At 3×10^{-4} wt % (2.1×10^3 particles/mL), the suspension was colorless. This large increase to 318 nm suggests that the laser may not be properly aligned. The laser alignment will be checked by measuring the light scattering intensity from toluene at several angles between 20° and 150° . With proper alignment, the scattering intensity should be independent of the measuring angle.

3. Particle Separation by Biphasic Partitioning

Preliminary work has shown that metal oxides like hematite (Fe_2O_3) and rutile (TiO_2) can be quantitatively separated from quartz (SiO_2) in a single stage using aqueous biphasic extraction. The biphasic system contained 15% PEG/7.5% Na_2SO_4 . A feed size of about 1 μm was obtained by wet grinding in a planetary ball mill. During biphasic extraction, greater than 99.99% of the metal oxide particles reported to the bottom (Na_2SO_4) phase, while slightly greater than 99.99% of the quartz particles reported to the top (PEG) phase. This partitioning behavior was also achieved when mixtures of particles were added to the aqueous biphasic system, giving extremely large separation factors between the metal oxides and quartz.

Aqueous biphasic separations depend upon differences in the surface properties of particles and not on bulk phase properties like density. Consequently, those factors that influence surface properties can be used to selectively control the partitioning of particles in an aqueous/aqueous system. Many of the same chemical reagents used in froth flotation to promote or suppress particle attachment at the air/water interface can be used in aqueous biphasic systems for promoting separations between metal oxides, phosphates, carbonates, silicates, sulfides, etc.

4. Use of Plutonium Polymer as Model System

a. Partitioning of Polymers

Partitioning studies of aged plutonium polymer were carried out in an effort to evaluate its applicability as a model system for predicting the partitioning behavior of plutonium-containing residues. If feasible, this would greatly simplify and speed the systematic study of partitioning behavior and reduce the amount of waste generated. The plutonium-polymer studies might also lead to a better understanding of the behavior of hydrolyzed metal polymers in conventional oil/water solvent extraction systems. In addition, the potential application of aqueous biphasic extraction for separating plutonium polymer is of interest, since processing aqueous wastes containing this plutonium form is not currently possible by conventional solvent extraction or ion exchange.

In future studies, the partitioning behavior of the polymerized plutonium will be correlated to partitioning behavior of ultra-fine PuO_2 powder as a means of validating this model system. The polymerized plutonium was obtained from H. Diamond (ANL's Chemistry Division). Several plutonium polymers were prepared by M. Toth et al. of Oak Ridge National Laboratory and were characterized by Thiagarajan et al.²⁸ using small-angle neutron scattering (SANS).

The preparation of the present polymer solution (designated as sample #4) has been described in detail.²⁸ From the SANS studies, Thiagarajan et al. concluded that the plutonium polymer particle is ellipsoidal, with a diameter of 22 Å and a length of 120 Å. The plutonium atoms are linked through oxygen bridges. X-ray diffraction patterns of aqueous plutonium polymer solutions resembled those reported for crystalline PuO_2 .

The influence of surfactants on the distribution ratio of the plutonium polymer in the 7.5% Na_2SO_4 /15% PEG-3400 system was examined. Two surfactant concentrations were used -- 0.1 and 0.01 wt %. Numerous surfactants (nonionic, cationic, and anionic) were screened. The distribution ratios of plutonium and the mass balance results are shown in Tables II-49 and II-50.

Table II-49. Partitioning of Polymeric $^{239}\text{Pu}(\text{IV})$ in 7.5% Na_2SO_4 /15% PEG-3400 System with 0.1% Added Surfactant at 25°C

Surfactant	Counts per min ^a (0-2000 keV)		Dist. Ratio	% Pu Recovery
	Top Phase	Bottom Phase		
Tween 20	69	19668	0.0035	59
Brij 30	97	8898	0.01	27
Triton X-100	59	12372	0.0047	37
Humic Acid	3184	3802	0.84	21
Cetyl Trimethyl Ammonium Bromide	239	931	0.25	4
Poly(ethylenimine)	14	1969	0.0071	6
Naphthalene Disulfonic Acid	39	20280	0.0019	60
Naphthalene Trisulfonic Acid	60	19268	0.0031	58
Sodium Dodecylsulfate	72	13326	0.0054	40
HEDP ^b	185	31853	0.0058	96
Dodecylbenzene Sulfonate	71	15610	0.0045	47
Oxalic Acid	183	18433	0.0099	56

^aBackground counts have been subtracted.

^bChemical formula of HEDP is $\text{CH}_3\text{C}(\text{OH})[\text{P}(\text{O})(\text{OH})_2]_2$.

Table II-50. Partitioning of Polymeric $^{239}\text{Pu}(\text{IV})$ in 7.5% Na_2SO_4 /15% PEG-3400 System with 0.01% Added Surfactant at 25°C

Surfactant	Counts per min ^a (0-2000 keV)		Dist. Ratio	% Pu Recovery
	Top Phase	Bottom Phase		
Tween 20	48	256	0.18	0.9
Brij 30	130	162	0.80	0.8
Triton X-100	55	126	0.47	0.5
Humic Acid	616	278	2.2	27
Cetyl Trimethyl Ammonium Bromide	69	221	0.31	0.8
Poly(ethylenimine)	29	981	0.029	3
Naphthalene Disulfonic Acid	83	22269	0.0037	67
Naphthalene Trisulfonic Acid	43	24704	0.0017	74
Sodium Dodecylsulfate	54	33005	0.0016	98
HEDP ^b	42	9194	0.0045	28
Dodecylbenzene Sulfonate	39	17342	0.0022	52
Oxalic Acid	50	12651	0.0039	38

^aBackground counts have been subtracted.

^bChemical formula is $\text{CH}_3\text{C}(\text{OH})[\text{P}(\text{O})(\text{OH})_2]_2$.

The results in Tables II-49 and II-50 indicate that humic acid is a strong complexant for the plutonium polymer. This agrees with findings from studies of natural water systems in which Nelson et al.²⁹ found that plutonium is strongly associated with colloidal organic compounds. Humic acids are a heterogeneous and ill-defined collection of compounds derived from the decay of plant matter.

In fact, Lindquist³⁰ has shown that aqueous two-phase systems can be used to fractionate humic acids. If properly fractionated, the humic acid may be capable of producing plutonium distribution ratios greater than two.

As shown in the tables, plutonium recovery varied widely, from a low of 0.5% to a high of 98%. Obviously, some error is associated with these estimates due, in part, to uncertainties in the exact phase ratio and total volume of the biphasic system. Nevertheless, the high levels of unaccountable plutonium are troublesome.

In other experiments, the aqueous biphasic partitioning of freshly hydrolyzed Pu(IV) was measured in the 7.5% Na₂SO₄/15% PEG-3400 system. In this case, the distribution ratio of the plutonium monomer was considerably larger than that for the polymer (see Table II-51).

Table II-51. Distribution Ratios of ²³⁸Pu(IV) Monomer and ²³⁹Pu(IV) Polymer in 7.5% Na₂SO₄/15% PEG-3400 System at 25°C

	Dist. Ratio	% Pu Recovery
Pu Monomer	0.17	100
Pu Polymer	0.001	85

The partitioning of plutonium polymer in the presence of colloidal silica was also measured. The silica was ground to an average particle size of 0.5 μ m in a planetary ball mill. The particle size distribution was measured by dynamic light scattering. In the 7.5% Na₂SO₄/15% PEG-3400 system, the silica partitioned quantitatively into the top phase. After the phases separated, the bottom phase was clear, with no trace of cloudiness, indicating that the silica concentration in the bottom phase was less than 10⁻⁴ wt %. (In the 0.5- μ m size range, 10⁻⁴ wt % suspensions appear slightly cloudy to the naked eye.) The distribution ratio of the plutonium polymer in the presence of the colloidal silica was about 0.009. A mass balance of plutonium from the two phases showed a plutonium recovery of about 85%. Given the reported tendency of plutonium(IV) polymer to adsorb onto all surfaces,^{31,32} it is quite surprising to find that the distribution ratio of the polymer is little affected by the presence of colloidal silica with its large surface area. This behavior suggests that the PEG prevented the polymeric plutonium from adsorbing into the SiO₂ surface.

b. Salting Out of Plutonium Polymer

It is well known that the aqueous solubility of plutonium polymers is greatly decreased in the presence of electrolytes.³³ Since an aqueous biphasic system may contain fairly high salt concentrations, plutonium-polymer precipitation may be a problem. Precipitation tests were carried out to gauge the stability of plutonium polymer in an aqueous biphasic system. A 3 μ L spike of the plutonium polymer stock (2.04 x 10⁵ cpm/ μ L) was added to 2 mL of each of the following 7.5 wt % electrolyte solutions: sodium sulfate, sulfuric acid, nitric acid, and sodium nitrate. Parallel experiments were carried out in which the solutions were contained in either glass or plastic vials. The counts per 50 μ L samples as a function of time are shown in Tables II-52 and II-53. The counts per minute expected per 50 μ L from each of the eight solutions is 15,300. At t=0, most of the samples registered more than 15,300 cpm. This is probably due to pipetting errors associated with delivering the 3 μ L spike. The results indicate that

very little, if any, loss of plutonium occurred in the H_2SO_4 solutions. For the other three electrolytes, plutonium losses were consistently greater in the plastic than the glass vials.

Table II-52. Plutonium Polymer Adsorption in Glass Vials

Electrolyte (7.5 wt %)	Electrolyte Conc., <u>M</u>	Counts per min (0-2000 keV) ^a			
		0 h	1 h	18 h	24 h
Na_2SO_4	0.53	13776	11929	10129	10208
H_2SO_4	0.76	17413	17576	17547	17097
NaNO_3	0.88	12405	12570	10404	14334
HNO_3	1.2	15753	14921	13635	13345

^a100% plutonium recovery would give 15,300 cpm.

Table II-53. Plutonium Polymer Adsorption in Polyethylene Vials

Electrolyte (7.5 wt %)	Counts per min (0-2000 keV) ^a			
	0 h	1 h	18 h	24 h
Na_2SO_4	14617	10855	7523	7507
H_2SO_4	17799	17980	17852	17482
NaNO_3	17452	14608	6665	6314
HNO_3	16263	12655	5952	5372

^a100% plutonium recovery would give 15,300 cpm.

The plutonium concentration in the stock solution was approximately 4.6 μM . In each of the solutions in Tables II-52 and II-53, the initial plutonium concentration was about 7 μM . Equilibrium required up to 18 h to be reached, probably reflecting the low mass transfer rates in such dilute plutonium solutions. It is surprising that the H_2SO_4 solutions were stable, while the Na_2SO_4 and HNO_3 solutions were not. This suggests that the H_2SO_4 dissolved the plutonium polymer--though this is considered unlikely. If the precipitation was due to electrostatic interactions between the positively charged polymer and the negatively charged glass surfaces, then one would expect that precipitation from H_2SO_4 and HNO_3 should be minimal. In acid solutions, the surface potential of glass would become positive, and electrostatic repulsion should prevent polymer adsorption. Since HNO_3 solutions also suffered plutonium losses, this cannot be the only mechanism of plutonium adsorption.

The percent of plutonium polymer lost from the nitrate solution in Table II-52 at $t = 0$ agrees fairly well with data published by Bell et al.³³ The data were collected by sampling the electrolyte solutions immediately after mixing the plutonium polymer and the nitrate solutions. For the NaNO_3 solution ($[\text{NO}_3^-] = 0.9\text{M}$), about 18% of the plutonium appears to precipitate immediately. This result agrees fairly well with literature data.³³

In addition to adsorption at solid/liquid interfaces, plutonium polymer adsorption at the liquid/liquid interface may be responsible for the poor mass balance in plutonium that was observed

for some of the surfactant systems in Tables II-49 and II-50. Adsorption phenomena can be particularly troublesome when working at trace levels. Clear evidence for interfacial adsorption was found in the 7.5% Na_2SO_4 /15% PEG-3400 system in which 0.1% and 0.01% concentrations of Aerosol OT were used. The total system volume was 1 mL, and the total amount of plutonium polymer added equaled 1.12×10^6 cpm. After phase separation by centrifugation, samples from the top phases (representing ~90% of the top phase volume) and from the bottom phases (representing 90% of the bottom phase volume) were carefully collected, so as to minimize the disturbance of the interface. The top, bottom, and interface samples were transferred to glass shell vials, and 15 μL aliquots were removed from each for counting. These results are shown in Table II-54. To obtain representative aliquots from the interfacial samples, they were first emulsified by vortexing and then sampled immediately.

Table II-54. Plutonium Polymer Partitioning in Top, Bottom, and Interfacial Regions of 7.5% Na_2SO_4 /15% PEG-3400 System at 25°C

[Aerosol OT], wt %	Counts per min (0-2000 eV) ^a			Dist. Ratio ^b
	Top	Interface	Bottom	
0.1	65	54775	25556	0.0025
0.01	39	42039	20498	0.0019

^aBackground counts have been subtracted from 10-min counts.

^bDefined as cpm top phase/cpm bottom phase.

Clearly, the results in Table II-54 indicate that the highest concentration of plutonium was at the liquid/liquid interface. Based only on the top and bottom phase samples, plutonium recoveries of 76% and 61% are calculated for the systems containing 0.1% and 0.01% Aerosol OT, respectively. By recombining the top and bottom phases with their respective interface samples, we quantitatively demonstrated that the remaining plutonium was located at the liquid/liquid interface, and that only insignificant amounts of plutonium were adsorbed on the glass tube surfaces. The recombined solutions were thoroughly mixed on the vortex mixer immediately before 15 μL aliquots were taken for counting. Based on the total biphasic volume of 1 mL, the cpm plutonium recovered for the 0.1% and 0.01% Aerosol OT samples was 1.3×10^6 and 1.1×10^6 cpm, respectively. These values are very close to the 1.12×10^6 cpm of plutonium spiked into the samples originally.

The poor mass balance for plutonium reported in Tables II-49 and II-50 may, in part, be due to plutonium adsorption at the liquid/liquid interface. The anionic surfactant, Aerosol OT, may have formed a protective layer around the plutonium polymer through electrostatic interactions between the positively charged polymer and the negatively charged functional group of the surfactant.

K. Measurement of Plutonium in Particulate Matter (J. Sedlet)

Studies on the biphasic separation of plutonium from solid waste require the measurement of plutonium in particles ranging in size from about 1 to 0.01 μm . Four methods of measurement can be used for this work: (1) liquid scintillation alpha counting, (2) counting the L X-rays emitted by the uranium decay product, (3) counting the low-abundance gamma rays emitted in plutonium decay, and (4) optical absorption spectrometry. Advantages and problems of each method are discussed below.

1. Liquid Scintillation Counting

With liquid scintillation counting, samples are quick and easy to prepare, and an automatic sample changing counter is available. However, the counting efficiency may be unacceptably low or variable because the particulate matter may not emulsify or remain in intimate contact with the scintillating compounds, or the particles may be too large to allow the alpha particle to lose enough energy in the scintillation cocktail and give an adequate size pulse. Figures II-34 to II-37 show spectra of ionic ^{239}Pu samples in Insta-Gel-XF with 0.1 or 2% water over two energy regions (0-25 keV and 0-500 keV). Most of the signal has energies greater than 20 keV. However, some of the counts are in the energy region below 10 keV, with a peak at about 3 keV. This is typical of plutonium. The very low energy counts may be X-rays and/or ^{241}Pu beta particles.

Fig. II-34. Liquid Scintillation Spectrum of ^{239}Pu Monomer at 0-500 keV with 2% Water in Insta-Gel-XF Scintillation Cocktail (Packard Instrument Co.)

Fig. II-35. Liquid Scintillation Spectrum of ^{239}Pu Monomer at 0-25 keV with 2% Water in Insta-Gel-XF

Fig. II-36. Liquid Scintillation Spectrum of ^{239}Pu Monomer at 0-500 keV with 0.1% Water in Insta-Gel-XF

Fig. II-37. Liquid Scintillation Spectrum of ^{239}Pu Monomer at 0-25 keV with 0.1% Water in Insta-Gel-XF

There is an interesting difference in the two peaks in the alpha particle energy region. In the sample which contained 2% water (Fig. II-34), the peak is sharp, and the energy range is from about 140 to 240 keV, with the peak maximum at about 180 keV. In the 0.1% water sample (Fig. II-36), the range is about 200 to 400 keV, and two peaks appear, with a valley at about 300 keV. This difference is a function of the water content. Water acts as a pulse height quencher in this cocktail system and shifts the alpha pulses to lower energies. The single sharp peak indicates that the ^{239}Pu solution is well emulsified in the cocktail. The sample containing less water gives higher energy pulses, but the diffused spectrum is probably due to incomplete emulsification of the water and cocktail. This double peak formation will be studied with a scintillation cocktail that does not depend on detergent emulsification to incorporate aqueous samples into organic solvents. No counts are lost by this double peak formation. Measurement of the alpha activity in the ^{239}Pu stock solution by counting an evaporated aliquot in a 2- π counter showed agreement between the 2- π count and the liquid scintillation count in the 100-500 keV region, where alpha particles appear in the liquid scintillation spectrum. In these samples, the counts were distributed 81.5% in the 20-500 keV region, 18.0% in the 0-20 keV region, and 0.5% for greater than 500 keV.

Figures II-38 to II-41 show spectra of polymeric plutonium. The peak between 100 and 500 keV remains, as does the peak at about 3 keV. The alpha peak is degraded and shows some straggling from 200 keV until the 3 keV peak is reached. Figures II-40 and II-41 show spectra from a sample of the above plutonium polymer that has been through a biphasic separation. These spectra indicate increased degradation of the alpha particles. This is likely due to incomplete incorporation of the plutonium polymer into the scintillator. Loss of energy in the plutonium oxide polymer particle is unlikely since the range of the alpha particles in plutonium itself is calculated to be 6 μm , and the polymer particle is considerably smaller. Until this question is resolved, the safest counting technique is to use the entire 0-500 keV range for the plutonium measurement.

For comparison, spectra of ^{244}Cm are shown in Figs. II-42 and II-43. The bulk (99.3%) of the counts are in the alpha region (100-500 keV), and only 0.6% are less than 100 keV. Apparently, curium is free of low energy photons or electrons. Alpha scintillation counting is a satisfactory method for plutonium measurement up to a counting rate at which dead-time losses become significant. This is at least 10^6 cpm (7.2 μg), and above this rate, dead-time losses can be measured and correlations made.

Fig. II-38. Liquid Scintillation Spectrum of ^{239}Pu Polymer at 0-500 keV in Insta-Gel-XF

Fig. II-39. Liquid Scintillation Spectrum of ^{239}Pu Polymer at 0-25 keV in Insta-Gel-XF

Fig. II-40. Liquid Scintillation Spectrum of ^{239}Pu Polymer at 0-500 keV in Insta-Gel-XF after Biphaseic Separation

Fig. II-41. Liquid Scintillation Spectrum of ^{239}Pu Polymer at 0-25 keV in Insta-Gel-XF after Biphaseic Separation

Fig. II-42. Liquid Scintillation Spectrum of ^{244}Cm from 0 to 500 keV in Insta-Gel-XF

Fig. II-43. Liquid Scintillation Spectrum of ^{244}Cm from 0 to 25 keV in Insta-Gel-XF

2. X-Ray Counting

All plutonium isotopes and other heavy radioactive elements emit L X-rays when they decay (the X-rays are characteristic of the decay product). This decay can be measured at high resolution with a 3-5 mm thick germanium or silicon (lithium-drifted) detector operated at liquid nitrogen temperatures. The thickness need only be sufficient to absorb the X-ray, and thus the background is reduced. Thin beryllium detector windows (1 mil or less) are needed. Such a detection system is available at ANL, as is a very low background, Si(Li) X-ray system used for actinide lung measurements. Both systems are manually operated, one sample at a time. The energies and line intensities of the X-rays emitted by plutonium and americium have been published by Strauss and Sherman.³⁴ The 17.22 keV plutonium X-ray is the most suitable one in the presence of americium.

The first attempt to measure these X-rays in one of our stock ^{239}Pu solutions with the Si(Li) system was unsatisfactory. The X-rays were attributed to ^{238}Pu by the computer program that analyzes the X-ray spectrum, although an alpha particle spectrum showed that the plutonium had a mass number of 239. This problem can no doubt be corrected, since examination of the computer program showed that ^{239}Pu X-rays were not a part of the program. The sample was also counted by A. Keane (ANL Environmental, Health & Safety Division) with the Si(Li) X-ray system but the results have not been examined.

3. Gamma-Ray Counting

A sample containing 3.3 μg of plutonium as the polymer was counted in a Nuclear Data germanium gamma-ray spectrometer. Many peaks were identified, several of which were attributable to ^{239}Pu . These gamma-rays are in the 100-400 keV energy range and have abundances of the order of $10^{-3}\%$. Thus, for samples containing sufficient plutonium, gamma-ray counting is a good method for quantifying plutonium. The most abundant gamma-ray in this sample was due to the decay of ^{241}Am (59.5 keV). This will be the case for all weapons-grade plutonium.

4. Optical Spectroscopy

The plutonium polymer obtained from ORNL (see Sec.II.J.4.a) is green, and spectra of samples containing Pu(IV) polymer and monomer have been published.³⁵ The two spectra differ significantly. A spectrum of this polymeric plutonium between 400 and 1300 μm was taken with a Cary

spectrophotometer and was very similar to the published spectrum of the polymer. A plutonium concentration of 0.006M was needed to obtain sufficient absorbance, and at this concentration, X- and gamma-ray counting is preferable. However, there may have been some operational problems with the spectrophotometer that, when corrected, may increase the sensitivity greatly.

5. Biphasic Separations

Four biphasic extractions of polymeric plutonium were performed by D. R. Fredrickson (CMT Division) using 7.5% Na_2SO_4 as one phase and 15% PEG as the second. The phase transfer agents used were Aerosol OT, humic acid, naphthalene disulfonic acid, and oxalic acid. Distribution ratios* for plutonium were 0.015, 0.40, 0.003, and 0.006, respectively, all quite low. Mass balances were also poor, ranging from 8 to 78%. The missing plutonium was probably present at the interface or on the walls, which were not checked for plutonium. The plutonium concentration was measured by liquid scintillation counting.

Since humic acid is a mixture of organic compounds, fractionating humic acid by a biphasic separation might concentrate the substances that can complex plutonium. Accordingly, equal volumes of 15% Na_2SO_4 and 30% PEG solutions containing 0.02% humic acid were mixed by vortexing for one minute. Then, the mixture was centrifuged, and the main two phases separated. An aliquot of polymeric plutonium solution was added to each phase in a culture tube. Then, an equal volume of 15% Na_2SO_4 was added to pre-equilibrated 30% PEG phase and an equal volume of fresh 30% PEG was added to pre-equilibrated 15% Na_2SO_4 phase. The mixtures were vortexed for one minute, the major phases were again separated by centrifuging, and the plutonium in each phase was measured by liquid scintillation counting. The results are shown in Table II-55. The distribution ratios are significantly higher than reported above, but not high enough to be useful. Problems with poor material balances, and losses at the interface and on the walls are apparent from the mass balance results.

Table II-55. Results of Biphasic Separation of Plutonium

Phases	Dist. Ratio	Mass Balance, %			
		Phases	Wall	Interface	Total
PEG + Humic Acid with Fresh Na_2SO_4	1.0	16	16	39	71
Na_2SO_4 + Humic Acid with Fresh PEG	2.3	14	10	44	68

A second experiment was performed with the Na_2SO_4 -PEG system using xylenol orange as the transfer agent. This highly colored complexing agent has been used in similar experiments to extract Fe(III) in the $(\text{NH}_4)_2\text{SO}_4$ -PEG system.²³ A distribution ratio of about 6 was reported. Xylenol orange forms complexes with some metals and is used as an indicator in complexometric titrations for calcium at other metals. Its complex with thorium is particularly strong. In a system containing 1 mL of 15% Na_2SO_4 , 1 mL of 30% PEG, and 20 μL of 2% xylenol orange and polymeric plutonium, the distribution

*[Pu] in top phase (PEG)/[Pu] in bottom phase (Na_2SO_4).

ratio for the fraction of plutonium that appeared in the bulk phases was 0.2, but only 7% of the added plutonium was accounted for. In the other fractions measured, 35% was in the interface, and 22% was removed from the walls of the culture tube. Thus, a total of 64% of the added plutonium was accounted for. This is the pattern observed in all the biphasic extractions conducted thus far.

The problem of plutonium loss should be explored before additional experiments are conducted. Possible experiments to clarify the problem are as follows:

1. Perform the same experiments with monomeric plutonium and with americium to determine if the losses are due to a property of the polymer or the (IV) oxidation state.
2. Perform the same experiments with scrupulously cleaned culture tubes and with culture tubes that have been treated to form a non-wettable hydrophobic surface.

L. Decontamination of Groundwaters Containing Volatile Organic Compounds
(J. C. Hutter, G. F. Vandegrift, A. K. Zander, and M. Semmens)

1. Introduction

A process is being developed for cleanup of volatile organic compounds in contaminated groundwater. The contaminants will be extracted by membrane-assisted solvent extraction (MASX) and then recovered in a membrane-assisted distillation stripping (MADS) section. This process is being evaluated as an alternative to groundwater remediation procedures using activated carbon or air stripping/activated carbon.

2. Literature Survey

Groundwater accounts for up to 40% of the drinking water used in the United States.³⁶ It is becoming common to find contaminants of various organic chemicals, metals, and radionuclides at levels far above those considered safe for human consumption in drinking water.³⁷⁻⁴⁰ The drinking water standards of the Environmental Protection Agency (EPA) are established to reduce the cancer risk in the population to a lifetime occurrence risk of one in one million.⁴¹ Often this requires a remediation procedure to reduce contamination levels into the low part-per-billion (ppb) range. Close to the contamination source, levels approaching the solubility of the contaminant in water can be detected. In some situations, such as near fuel spills, even two-phase contaminations are possible. Away from the contamination source, levels 10 to 100 times the drinking water standards are typical. Currently in some areas, the problem is so bad that a continuous air stripping process is run to prevent the spreading of a contaminant plume to drinking water sources. The contamination is so disperse that remediation procedures can only be used to prevent further migration, and not eliminate the problem.

To define the problem at DOE sites, a groundwater contamination survey was completed by Oak Ridge National Laboratory.⁴² The ten most common contaminants found are listed in Table II-56. These contaminants were typically found at concentrations of greater than 1 ppm. The maximum concentrations found and the most recent drinking water standard concentrations are listed in Table II-56. This survey is the most exhaustive done to date and includes nine DOE sites.

The problem is to remove dilute organic contaminants from an aqueous system to the parts per billion level. The current technology most widely used is air stripping, which removes the volatile components from the liquid stream but transfers them to the air. Air stripping with gas-phase carbon

Table II-56. Common Groundwater Contaminants Found at Nine DOE Sites^a

Contaminant	Max. Concentration, ppb	EPA Drinking Water Standard, ppb
Chloroform	1000	100
Carbon Tetrachloride	10000	5
1,1,1-Trichloroethane	3100	200
cis-Dichloroethylene	349	70
trans-Dichloroethylene	349	100
Trichloroethylene	8500	^b
Tetrachloroethylene	2300	5
Methylene Chloride	6300	^b
Benzene	36000	5
Vinyl Chloride	510	2

^aKansas City Plant, Lawrence Livermore National Laboratory, Y12 Oak Ridge, Hanford, K25 Oak Ridge, Oak Ridge National Laboratory, Paducah, Rocky Flats, Savannah River Laboratory.

^bNot under federal regulation.

adsorption is more expensive, but most of the volatile components can be recovered by the carbon solid phase. Regeneration of the carbon is possible, and a substantial amount of the volatile contaminants on the carbon can be recovered or destroyed. It is also possible to remove the contaminants by contacting activated carbon directly with the water phase. Usually this process is the most expensive alternative, but it is in use in some cleanup applications. Solvent extraction to remove organic pollutants from water has also been investigated.⁴³⁻⁴⁶ Using current technology, solvent extraction is feasible only for waste streams with contamination levels exceeding those found in most groundwaters.⁴⁷

Solvent extraction and distillation research has generated a strategy for solvent selection to recover key components from waste streams.^{43,44,48-51} Solubility trends of various contaminants can be correlated by hydrogen bonding and Lewis acid-Lewis base concepts. Solvent selection can be directed by looking for materials that have strong complementary molecular interactions with the target contaminants, for example, extraction of a target Lewis base with a Lewis acid solvent. The distribution coefficient of the target Lewis base will be affected by the strength of the Lewis acid solvent: the stronger the Lewis acid, the higher the distribution coefficient. Similar types of phenomena can be ascribed to hydrogen bonding interactions. The trade-off with a good solvent is that, the more powerful the solvent, the more difficult the regeneration.

In the last ten years, researchers have demonstrated that microporous membranes can be used in solvent-extraction equipment.⁵²⁻⁵⁸ In a shell-and-tube module, with two counter-current liquid phases separated by a microporous membrane, components can be extracted from one phase to the other by transferring through the membrane. Thus, membranes can be used to independently control the flow rates of either liquid phase without the flooding, channeling, or emulsification problems of conventional extraction equipment, such as mixer settlers or packed columns. The membrane establishes a high interfacial mass transfer area for contact between the two phases. Usually one phase wets the pores preferentially, and by manipulation of the transmembrane pressure gradient, the second phase can be prevented from transporting through the membrane and contaminating the first phase. In addition, composite microporous membranes can be used to prevent phase intermixing. In this case, a hydrophobic membrane and a hydrophilic membrane form a composite. The organic liquid is in contact with the

hydrophobic membrane, and the aqueous liquid is in contact with the hydrophilic membrane. The wetting properties at the membrane-membrane interface prevent carryover of either liquid phase into each other, while good interfacial contact of the two liquids allows extraction to occur.⁵⁵ Composite membranes have also included dense-phase layers on top of microporous supports.⁵⁹ These membranes prevent the direct contact of the two phases by separating them by a solid film.

3. Conceptual Design of the MASX/MADS Process

A conceptual design of the MASX/MADS process is shown in Fig. II-44. Contaminated groundwater enters the extraction unit and is contacted on the other side of the microporous hollow fiber membranes with a nontoxic natural oil solvent. The contaminants are extracted from the groundwater into the oil phase. The groundwater exits the extraction module with the contaminants removed to levels at or below current drinking water standards. The oil phase is then heated and fed to a distillation stripping unit. This unit may be operated under vacuum. In the stripping unit, the VOC contaminants are removed from the oil phase. The contaminants are then recovered in a cold-trap condenser. The regenerated oil solvent is cooled and recycled to the extraction module. Some type of energy recovery system will be used to recover the heat of the regenerated oil phase.

Fig. II-44. Flow Diagram of Conceptual MASX/MADS Process

4. Demonstration of MASX Technical Feasibility

Work at the University of Minnesota has demonstrated on a laboratory scale the membrane-assisted solvent extraction of dilute volatile components from water using sunflower oil.⁵⁹ In this effort, a hollow-fiber module was used to contact an oil and water phase to selectively remove volatile contaminants from the water. The membrane in the Minnesota demonstration is a unique composite membrane, depicted in Fig. II-45. Water is inside the fibers in contact with a microporous polypropylene surface. The hydrophobic character of this surface keeps the water from wetting these pores, which are designed to be gas filled. The outside of the membrane has a plasma polymerized disiloxane coating, so that the oil phase cannot wet the polypropylene pores. Mass transfer of volatile components through the membrane is very rapid, and in general operation, the controlling mass transfer resistance is on the water

side. It has been found that the water-side mass transfer coefficients fit the correlations for laminar flow in tubes.^{60,61} The oil phase controls the mass transfer in certain operating regimes with high water rates and low oil rates. The oil phase resistance outside of the tubes also fits the general mass transfer correlations.^{62,63} The membrane resistance was found to be negligible in the flow regimes tested. In the microporous film, resistance can be predicted if transport through the pores is controlled by diffusion through tortuous capillaries that have pore sizes much larger than the dimensions of the molecules.⁵⁵⁻⁵⁷ The total membrane resistance can be determined by adding this microporous resistance to the resistance of the dense film.

Fig. II-45. Composite Membrane Used at Minnesota Demonstration
(Applied Membrane Technologies, Minneapolis, MN)

Zander⁵⁹ evaluated several candidate solvents for the extraction process. Sunflower oil was selected out of five possible solvents because of its low volatility, high affinity for the VOC contaminants, and nontoxic composition. Based on our own literature search, sunflower oil has a very favorable degree of unsaturation and complementary Lewis acid-base character and should be a good solvent for extraction of the target VOCs. Castor oil, corn oil, peanut oil, and soybean oil, and maybe some others should also be evaluated, since these materials have molecular structural characteristics which make them good potential solvents. The structures of these natural oils are given in several references.^{64,65} Further work on solvent selection would only be a refinement for the extraction process.

5. Technical Feasibility of MASX/MADS Process

Several areas are of special concern in determining the technical feasibility of the proposed process for membrane-assisted decontamination of groundwater. These areas are the properties of the membranes, the recovery of the volatile organics in the cold-trap condenser, and the regeneration of the oil phase. These areas will be discussed for a laboratory-scale demonstration unit, as proposed at the University of Minnesota. A full-scale design must account for these uncertainties.

a. Properties of Microporous Membranes

Zander's laboratory demonstration of the liquid-extraction hollow-fiber membrane module used a synthetic groundwater solution in contact with the microporous polypropylene pores. The synthetic groundwater was made from deionized water contaminated with analytical grade VOC

standards. The polypropylene pore sizes ranged from 0.02 to 0.05 μm . The manufacturer, Applied Membrane Technologies, measured the contact angle for this material as 92° . This contact angle can be used to calculate a wetting pressure of 29 psia (2×10^6 dyne/cm²) to wet the polypropylene pores⁶⁶⁻⁶⁸:

$$P = \frac{2\sigma \cos \theta}{r} \quad (\text{II-43})$$

where P = pressure to wet the pores, dyne/cm² (to convert to psia, multiply by 1.45×10^{-5})

σ = surface tension of liquid, dyne/cm

θ = contact angle, degrees

r = pore radius, cm

This calculation assumes that water has a surface tension of 72 dynes/cm. Actual groundwater has a surface tension lower than this due to the presence of dissolved impurities, and the calculated value of the wetting pressure is less than that for pure water. The hydrodynamic pressure drop in the fibers can be calculated by the Hagen-Poiseuille equation.⁶⁹ For the laboratory-scale demonstration module, the 7.62 cm fibers have a pressure drop of almost 1.0 psia (7×10^4 dyne/cm²). In any full-scale unit, the value of 29 psia (2×10^6 dyne/cm²) can be reached with a fairly short fiber length. Thus, these calculations indicate that water will fill the membrane pores, and the gas filled pores will no longer exist. The mass transfer rate will be drastically reduced.

The contact angle of 92° is disputed in the literature. Angles of 96.9° have been reported for similar Celgard membranes. This angle gives a pressure of 100 psia (7×10^6 dyne/cm²) for wetting. The contact angle for solid polypropylene is 108° .⁶⁷ The actual contact angle remains uncertain at this time and is under further investigation.

The structure of these microporous polypropylene membranes also leads to some limitations. The reported pore radius was determined from mercury porosimeter measurements. These reported numbers are determined at the surface of the membrane. In the interior of the membrane, the pore size is found to be much different. Electron microscopy of the internal pore structure shows that the inside of these membranes is a large cavity with dimensions much larger than the surface pore radius.⁷⁰ This structure makes the membrane vulnerable to wetting. If any of the pores are larger than indicated or are defective, the entire internal membrane structure cavity can be filled through the hole in the surface created by the largest surface pore.

Membrane processes have not been widely employed in full-scale industrial applications because of their tendency to foul and their unreliability. (This fouling problem must be evaluated for the proposed application.) Nevertheless, membranes have found a few industrial uses, such as reverse osmosis and some filtration applications. Hollow-fiber membranes have also been used for direct air stripping of VOCs from water.⁵⁹ In this application, water is inside the lumen and air is passed through the shell side of the module. The mass transfer rate per unit volume is considerably higher than that in a packed tower due to the high interfacial area. However, the thermodynamic constraints of Henry's Law require a high ratio of gas flow rate to liquid flow rate. Due to this effect, the pressure drop on the shell side of the lumen becomes so large that the packed column air stripper becomes a much more economical process. Passing a large gas volume through a small module is very difficult; the small module is a considerable hindrance to the process.

b. Condensation of VOCs in the Cold Trap Condenser

To remove the VOCs from the oil phase by air stripping, a still larger volume of air is required compared with that required to strip the same amount of VOCs from the water directly. This result is a direct consequence of Henry's Law, and can be evaluated directly using published experimental data collected at Minnesota.⁵⁹ The data were evaluated for room temperature and can be estimated for higher temperatures. To recover the organics from the gas phase, the partial pressure of the organic contaminant in the oil must be less than the vapor pressures of the organic contaminant in the condenser. The temperature of the condenser used can be estimated from a simple forced convection heat transfer calculation.^{69,71} Using liquid nitrogen at -196°C (77 K), condenser temperatures of about -73°C (200 K) or maybe lower can be expected for the exiting gas. The exact exiting temperature of the gas stream is a complex function of the condenser conditions.

The Henry's Law constants for five candidate VOCs in sunflower oil (H_{oil}) can be calculated from the Henry's Law constants for water (H_{water}) and the distribution coefficients (K_D) of the VOCs between water and sunflower oil. These results are summarized in Table II-57. Using these and other published data, the performance of the laboratory-scale MASX/MADS can be estimated. An estimated material balance for this unit is given in Fig. II-46. This flow scheme results in an oil which has 10 ppm VOC contaminants in it; the oil must be purified before it can be recycled back to the solvent extraction unit. Using Henry's Law, the minimum gas flow to strip the VOCs from the oil can be calculated. The partial pressure of chloroform above oil is 4.70×10^{-5} psia (3.2 dyne/cm^2). This is 1/10 of the partial pressure of chloroform at 1 ppm above water at the same temperature of 25°C . If the chloroform were at 100 ppm, its partial pressure above the oil would be the same as the partial pressure above 1 ppm in water. This result is due to the value of $K_D = 100$. From the partial pressure, the mole fraction (y_i) of chloroform in the gas phase can be calculated. These results at various total pressures are:

$$y_i = 3.2 \times 10^{-6} \text{ at } 14.7 \text{ psia } (1.01 \times 10^6 \text{ dyne/cm}^2)$$

$$y_i = 6.7 \times 10^{-6} \text{ at } 7.0 \text{ psia } (0.48 \times 10^6 \text{ dyne/cm}^2)$$

$$y_i = 47 \times 10^{-6} \text{ at } 1.0 \text{ psia } (0.07 \times 10^6 \text{ dyne/cm}^2)$$

Table II-57. Thermodynamic Values Calculated for Five Candidate Contaminant Compounds at 25°C

Compound	K_D	H_{WATER} , psia/ppm	H_{OIL} , psia/ppm
Chloroform	100	0.156	4.70×10^{-6}
1,1,2-Trichloroethylene	142	0.035	6.65×10^{-7}
Trichloroethylene	413	0.421	2.79×10^{-6}
Carbon Tetrachloride	867	1.235	3.33×10^{-6}
Tetrachloroethylene	2576	0.753	6.34×10^{-7}

Fig. II-46. Material Balance on the Laboratory-Scale Extraction Unit

The low partial pressures of these contaminants make them difficult to recover in the condenser. The required condenser temperature for chloroform and carbon tetrachloride can be estimated from the data in Table II-58. The challenge is to produce a high-contaminant-concentration gas stream from a very dilute oil stream. As shown in Table II-58, the process is not feasible at a stripping temperature of 25°C. Higher temperatures would favor VOC recovery since the contaminant partial pressure exceeds the vapor pressure in the condenser. The temperature at which this is feasible will be determined from future experiments.

Table II-58. Partial Pressures and Vapor Pressures of Typical Contaminants in the MADS

Temperature, °C	Partial Pressure above 10 ppm in Oil, psia (dynes/cm ²)	Vapor Pressure of Pure Component in Condenser, psia (dynes/cm ²)
<u>Chloroform</u>		
25	4.6×10^{-5} (3.2)	3.85 (2.64×10^5)
0	--	1.18 (8.11×10^4)
-20	--	0.38 (2.6×10^4)
-40	--	9.1×10^{-2} (6.3×10^3)
-60	--	1.6×10^{-2} (1.1×10^3)
<u>Carbon Tetrachloride</u>		
25	3.3×10^{-5} (2.3)	2.21 (1.52×10^5)
0	--	0.63 (4.3×10^4)
-20	--	0.19 (1.3×10^4)
-40	--	4.2×10^{-2} (2.8×10^3)
-60	--	7.2×10^{-3} (4.9×10^2)
-70	--	2.5×10^{-3} (1.7×10^2)
-100	--	6.0×10^{-5} (4.1) ^a
-196 (77 K)	--	1.0×10^{-18} (6.9×10^{-14}) ^a

^aExtrapolated Values.

c. Regeneration of Oil Phase

As discussed previously, the mole fractions in the exiting gas phase set the required minimum gas flow rate to strip the chloroform from the oil. The material balance for chloroform indicated that a 40 mL/min oil flow with 10 ppm chloroform results in 3.35×10^{-6} mol/min of chloroform transferred. At 1 atm ($\sim 10^6$ dyne/cm²), using the exit mole fraction calculated previously, the minimum gas rate is 390 cm³/s (std. cond.). At lower pressures this flow is reduced; for example, at 1.0 psia (7×10^4 dyne/cm²) the minimum flow is 26 cm³/s. At a stripping temperature of 25°C, these flows are too dilute to condense the contaminants in the liquid nitrogen cold trap. By comparison, to strip 3.35×10^{-6} mol/min from a 400 mL/min water stream with 1 ppm chloroform at 25°C and 1 atm ($\sim 10^6$ dyne/cm²) would only require 39 cm³/s. The stripping step must be done at higher temperature to be effective. At this time the solvent regeneration problem is being investigated further.

REFERENCES

1. R. A. Leonard, "Use of Electronic Worksheets for Calculation of Stagewise Solvent Extraction Processes," *Sep. Sci. Technol.* 22, 535-556 (1987).
2. Y. Jiang, "Extraction Ability of Organic Phosphate Esters for Some Organic Acids," *Huaxue Shijie* 25, 86 (1984).
3. V. N. Startsev, "Extraction of Oxalic Acid by Tributyl Phosphate," *Sb. Nauch. Tr. Vses. Nauch. Lssled. Gorno-Met. Inst. Tsvet. Metal.*, No. 12, 58 (1968).
4. R. C. Weast, Ed., *Handbook of Chemistry and Physics*, 56th ed., CRC Press, Cleveland, OH, p. D-150 (1976).
5. D. J. Chaiko, D. R. Fredrickson, L. Reichley-Yinger, and G. F. Vandegrift, "Thermodynamic Modeling of Chemical Equilibria in Metal Extraction," *Sep. Sci. Technol.* 23, 1435 (1988).
6. W. G. O'Brien and R. G. Bautista, "The Excess Gibbs Free Energy and the Activity Coefficients of the Neodymium(III) Nitrate-Nitric Acid-Water System at 25°C," *Adv. Chem. Ser.* 177, ACS, Washington, DC, p. 299 (1979).
7. M. Goheen and R. J. Robinson, "Thermogravimetric Investigation of Scandium, Yttrium and the Rare Earth Metal Diliturates," *Anal. Chim. Acta*, 31, 71-80 (1964).
8. S. Misumi and T. Taketatsu, "Anion-exchange Studies of Beryllium(II), Cerium(IV), Thorium(IV), and Uranium(VI) Carbonate Complex Ions," *Bull. Chem. Soc., Japan* 32, 873 (1959).
9. D. A. Skoog and D. M. West, *Fundamentals of Analytical Chemistry*, 4th ed., Saunders, New York, pp. 749-753 (1982).
10. F. J. Welcher, Ed., *Standard Methods of Chemical Analysis*, Part A, Van Nostrand, New York, pp. 267-269 (1963).
11. F. H. Spedding and M. J. Pikal, "Relative Viscosities of Some Aqueous Rare Earth Chloride Solutions at 25°C," *Phys. Chem.* 70 (8), 2440-2449 (1966).
12. P. K. Tse and G. F. Vandegrift, *Development of Supercritical Fluid Chromatography for Analysis of TRUEX Process Solvents*, Argonne National Laboratory Report ANL-89/21 (August 1989).
13. E. F. Johnson, *Automatic Process Control*, McGraw-Hill, New York (1964).
14. R. A. Leonard, M. C. Regalbuto, D. B. Chamberlain, and G. F. Vandegrift, "A New Model for Solvent Extraction in Columns," *Sep. Sci. Technol.* 25 (13-15), 1689-1707 (1990).
15. F. H. Raven, *Automatic Control Engineering*, McGraw-Hill, New York (1978).
16. R. A. Leonard, M. C. Regalbuto, D. B. Chamberlain, and G. F. Vandegrift, "A New Model for Solvent Extraction in Columns," accepted for publication in *Sep. Sci. and Technol.*

17. G. J. Bernstein, D. E. Grosvenor, J. F. Lenc, and N. M. Levitz, "A High Capacity Annular Centrifugal Contactor," *Nucl. Technol.* 20, 200 (1973).
18. A. T. Clark, *Performance of a 10-inch Centrifugal Contactor*, Savannah River Laboratory Report DP-752 (1962).
19. R. A. Leonard, G. J. Bernstein, A. A. Ziegler, and R. H. Pelto, "Annular Centrifugal Contactors for Solvent Extraction," *Sep. Sci. Technol.* 15, 925 (1980).
20. P. A. Albertsson, *Partition of Cell Particles and Macromolecules*, 3rd ed., Wiley-Interscience, New York (1986).
21. M. R. Kula, "Extraction and Purification of Enzymes Using Aqueous Two-Phase Systems," in *Enzyme Technology, Applied Biochemistry and Bioengineering*, Vol. 2, L. B. Wingard, Jr., E. Katchalski-Katzier, and L. Goldstein, Eds., Academic Press, New York, p. 74 (1979).
22. H. Walter, D. E. Brooks, and K. Fisher, Eds., *Partitioning in Aqueous Two-Phase Systems*, Academic Press, New York (1985).
23. T. I. Zvarova, V. M. Shkinev, G. A. Vorob'eva, B. Ya. Spivakov, and Yu. A. Zolotou, "Liquid-Liquid Extraction in the Absence of Usual Organic Solvents; Application of Two-Phase Aqueous Systems Based on a Water-Soluble Polymer," *Mikrochimica Acta [Wien]* 3, 449 (1984).
24. A. P. Ananthapadmanabhan and E. D. Goddard, "Process for the Separation of Solid Particulate Matter," U.S. Patent No. 47,225,358 (1987).
25. N. D. Gullickson, J. F. Scamehorn, and J. H. Harwell, in *Surfactant-Based Separation Processes*, J. F. Scamehorn and J. H. Harwell, Eds., Surfactant Science Series, Vol. 33, Marcel Dekker, New York, p. 305 (1989).
26. R. S. Stock and W. H. Ray, "Interpretation of Photon Correlation Spectroscopy Data: A Comparison of Analysis Methods," *J. Polymer Sci.* 23, 1393 (1985).
27. T. Provder, Ed., *Particle Size Distribution, Assessment and Characterization*, ACS Symposium Series 332, American Chemical Society, Washington DC (1987).
28. P. Thiagarajan, H. Diamond, L. Soderholm, E. P. Horwitz, L. M. Toth, and L. K. Felker, "Plutonium (IV) Polymers in Aqueous and Organic Media," *Inorg. Chem.* 29, 1902 (1990).
29. D. M. Nelson, R. P. Larsen, and W. R. Penrose, "Chemical Speciation of Plutonium in Natural Waters," in *Environmental Research on Actinide Elements*, Department of Energy Report DOE CONF-841142, p. 27 (1983).
30. I. Lindquist, "A New Fractionation Method for Humic Acids," *Swedish J. Agric. Res.* 14, 171 (1984).
31. D. W. Ockenden and G. A. Welch, "The Preparation and Properties of Some Plutonium Compounds. Part V. Colloidal Quadrivalent Plutonium," *J. Chem. Soc.*, p. 3358 (1956).

32. S. C. Carniglia, Paper 4.13 in *The Transuranium Elements*, National Nuclear Energy Series, Vol. 14B, McGraw-Hill, New York (1944).
33. J. T. Bell, C. F. Coleman, D. A. Costanzo, and R. E. Biggers, "Plutonium Polymerization-III: The Nitrate Precipitation of Pu(IV) Polymer," *J. Inorg. Nucl. Chem.* 35, 629 (1973).
34. M. G. Strauss and I. S. Sherman, "Considerations in Measuring Trace Radionuclides in Soil Samples by L X-ray Detection," *IEEE Trans., Nuclear Science*, Vol. NS-25, No. 1 (February 1978).
35. J. M. Cleveland, *The Chemistry of Plutonium*, American Nuclear Society, LaGrange Park, IL (1979).
36. P. L. McCarthy, M. Reinhold, and B. E. Rittmann, "Trace Organics in Groundwater," *Environ. Sci. Technol.* 15(1), 40-51 (1981).
37. J. L. Symons, "National Reconnaissance Survey for Halogenated Organics," *J. AWWA* 67, 634-647 (1975).
38. M. Reinhold and J. F. Baker, "Occurrence and Distribution of Organic Chemicals in Two Landfill Leachate Plumes," *Environ. Sci. Technol.* 18(12), 953-961 (1984).
39. F. B. Dewalle and E. S. K. Chian, "Detection of Trace Organics Near a Solid Waste Landfill," *J. AWWA* 73, 206-211 (1981).
40. D. H. Stuermer et al., "Organic Contaminants in Groundwater near an Underground Coal Gasification Site in Northeastern Wyoming," *Environ. Sci. Technol.* 16(9), 581-587 (1982).
41. *Drinking Water Regulations and Health Advisories*, U.S. Environmental Protection Agency, Washington, DC, Office of Drinking Water (1990).
42. S. B. Garland et al., Oak Ridge National Laboratory, unpublished information (1990).
43. C. J. King et al., "Equilibrium Distribution Coefficients for Removal of Polar Organic Pollutants from Water," *Ind. Eng. Chem., Pro. Des. Dev.* 23(4), 748-754 (1984).
44. C. J. King, T. A. Barbari, D. K. Joshi, N. E. Bell, and J. J. Senatar, *Equilibrium Distribution Coefficients for the Extraction of Organic Priority Pollutants from Water - I,II*, Robert S. Kerr Environmental Research Laboratory, Ada, OK, EPA-600/2-84-060 (1984).
45. R. J. Earhart et al., "Waste Recovery: Recovery of Organic Pollutants Via Solvent Extraction," *Chem. Eng. Prog.* 73, 67-73 (1977).
46. S. T. Hwang, "Treatability of Toxic Wastewater Pollutants by Solvent Extraction," *AIChE Symp. Ser.* 77(209), 304-315 (1981).
47. L. A. Robbins, "Liquid-Liquid Extraction: A Pretreatment Process for Wastewater," *Chem. Eng. Prog.* 76, 58-61 (1980).
48. R. H. Ewell et al., "Azeotropic Distillation," *Ind. Eng. Chem.* 36(10), 871-875 (1944).

49. C. T. Chiou et al., "Partition Coefficient and Bioaccumulation of Selected Organic Chemicals," *Environ. Sci. Technol.* 11(5), 475-478 (1977).
50. S. Banerjee et al., "Water Solubility and Octanol/Water Partition Coefficients of Organics, Limitations of the Solubility-Partition Coefficient Correlation," *Environ. Sci. Technol.* 14(10), 1227-1229 (1980).
51. T. A. Barbari and C. J. King, "Equilibrium Distribution Coefficients for Extraction of Chlorinated Hydrocarbons and Aromatics from Water into Undecane," *Environ. Sci. Technol.* 16(9), 624-627 (1982).
52. K. K. Sirkar and R. Prasad, "Solvent Extraction with Microporous Hydrophilic and Composite Membranes," *AIChE J.* 33(7), 1057-1066 (1987).
53. Z. Qi and E. L. Cussler, "Microporous Hollow Fibers for Gas Absorption, II- Mass Transfer Across the Membrane," *J. Membr. Sci.* 23, 333-345 (1985).
54. D. O. Cooney and C. L. Jin, "Solvent Extraction of Phenol from Aqueous Solution in a Hollow Fiber Device," *Chem. Eng. Comm.* 37, 173-191 (1985).
55. A. Kiani et al., "Solvent Extraction with Immobilized Interfaces in a Microporous Hydrophobic Membrane," *J. Membr. Sci.* 20, 125-145 (1984).
56. R. Prasad and K. K. Sirkar, "Hollow Fiber Solvent Extraction: Performances and Design," *J. Membr. Sci.* 50, 153-175 (1990).
57. R. Prasad and K. K. Sirkar, "Microporous Membrane Solvent Extraction," *Sep. Sci. Technol.* 22(2&3), 619-640 (1987).
58. H. Takeuchi et al., "Mass Transfer in Single Oil Containing Microporous Hollow Fiber Contactors," *Ind. Eng. Chem. Res.* 29(7), 1471-1476 (1990).
59. A. K. Zander et al., "Membrane Oil Stripping of VOCs from Water in Hollow Fiber Contactor," *J. Environ. Eng.* 115(4), 768-784 (1989).
60. R. H. Norris and D. D. Streid, "Laminar Flow Heat Transfer Coefficients for Ducts," *Trans. ASME* 62(6), 525-533 (1940).
61. M. A. Leveque, "Les Lois de la Transmission de Chaleur par Convection," *Annales des Mines* 13, 201-362 (1928).
62. E. L. Cussler, *Diffusion: Mass Transfer in Fluid Systems*, Cambridge University Press, Cambridge (1984).
63. J. G. Knudsen and D. L. Katz, *Fluid Dynamics and Heat Transfer*, McGraw Hill, New York (1958).
64. D. A. Shirley, *Organic Chemistry*, Holt, Rinehart and Winston, Inc., New York (1964).

65. E. W. Eckley, *Vegetable Fats and Oils*, Reinhold Publishing, New York (1954).
66. F. W. Sears, *Mechanics, Heat, and Sound*, Addison-Wesley, New York, pp. 326-333 (1950).
67. J. T. Davies and E. K. Rideal, *Interfacial Phenomena*, Academic Press, New York, pp. 435-436 (1963).
68. A. W. Adamson, *Physical Chemistry of Surfaces*, J. Wiley and Sons, New York, pp. 9-10, 333-371 (1976).
69. R. B. Bird, W. E. Stewart, and E. N. Lightfoot, *Transport Phenomena*, J. Wiley & Sons, New York (1960).
70. D. J. Chaiko and K. Osseo-Asare, "Characterization of Liquid Membrane Supports," *Sep. Sci. Technol.* 17(15), 1659-1679 (1982-83).
71. R. W. Fahien, *Fundamentals of Transport Phenomena*, McGraw-Hill, New York (1983).

III. NUCLEAR WASTE PROGRAMS

(J. K. Bates)

A. Unsaturated Glass Testing Program for Office of Environmental Restoration and Waste Management

The Unsaturated Glass Testing Program is part of the technology support activity performed for DOE's Office of Environmental Restoration and Waste Management (EM). This program was initiated in 1989 with the goal of evaluating factors that will likely affect glass reaction in an unsaturated environment before hot start-up of the Defense Waste Processing Facility (DWPF). The EM Office recognizes that (1) the long-term prediction of glass performance in a repository environment, and (2) the relationship between the release of radionuclides from a glass waste package and performance assessment of the repository are tasks that must be addressed. However, these tasks will not be completed until application is made for a repository license, several years after the DWPF begins production of waste for storage and disposal. The Unsaturated Glass Testing Program is being undertaken so that the modeling and performance assessment programs will have a firm basis that (1) accounts for important physical parameters which will affect glass reaction in an unsaturated environment and (2) relates the mechanistic basis of glass reaction to conditions which will exist in an unsaturated environment.

The goals of the Unsaturated Glass Testing Program are to (1) review parameters that will be important to evaluating glass performance, (2) perform testing to further quantify the effects of variables deemed important to the glass performance, and (3) initiate a long-term testing program that will characterize glass performance under a range of bounding conditions relevant to the potential repository as identified in the "Yucca Mountain Project Scientific Investigation Plan."¹ Results from the testing program will also be used to validate models generated to predict long-term performance. The information developed in the Unsaturated Glass Testing Program, when combined with data generated by the glass waste producers and by the Yucca Mountain Project (YMP), will form the basis of a well-founded program that will ultimately qualify vitrified high-level waste for repository disposal.

The physical parameters and processes that affect glass reaction in an unsaturated environment were identified and evaluated previously.² These include (1) glass composition, (2) radiation, (3) temperature, (4) surface area of glass/volume of liquid (SA/V), (5) the effect of unsaturated conditions, and (6) the effect of alteration layers. Prior to hot DWPF start-up, these factors will be critically evaluated such that their role in long-term glass performance in the repository will be established. In FY 1990, the effects of temperature and other parameters were reviewed, while testing was planned and initiated in the remaining areas.

1. Critical Review of Parameters Affecting Glass Reaction in an Unsaturated Environment (J. J. Mazer)

An interim draft of the critical review, in which all important parameters affecting glass reaction in an unsaturated environment were examined, has been previously issued.² This draft presents preliminary assessments of the relative importance of each parameter and is intended to form the basis for a more detailed and complete evaluation of each parameter.

The first factor subjected to additional in-depth review was the effect of temperature on waste glass/water interactions. Temperature is an important parameter to consider because it affects glass reaction mechanisms and rates in laboratory glass durability tests, as it will within the repository itself. A review of the chemical reactions that affect nuclear waste glass/water interactions indicated that the overall glass/water reaction is a cumulative result of the constituent reactions: molecular water diffusion,

ion exchange, silicate network dissolution, and secondary mineral precipitation. These reactions often operate simultaneously, and their interactions are poorly understood at present.

The temperature dependence of the individual reactions has been examined by various researchers; however, these studies are generally for other chemical systems (i.e., the reactions are usually unable to be isolated in glass/water systems). The constituent reaction mechanisms of glass reactions often have a temperature dependence that can be quantitatively expressed using the Arrhenius equation, a phenomenological relationship. The temperature dependence is often described by the activation energy, i.e., the threshold energy above which a chemical reaction is likely to occur. The basis for Arrhenius-type formulations can be related to basic physical chemistry principles, although the connection has not been rigorously defined. The Arrhenius equation has been used to describe the temperature dependence of glass dissolution based on several kinetic measurements, including the cation release rate to solution and the growth rate of alteration layers and secondary minerals. Volcanic glass, or obsidian, hydrated in water vapor provides an opportunity to study a single reaction mechanism, molecular water diffusion, as a function of temperature in a glass/water system. Such studies have concluded that use of the Arrhenius equation is acceptable for describing the effect of temperature in accelerating obsidian hydration. Furthermore, studies of secondary mineral precipitation have also found that the Arrhenius equation successfully describes the temperature dependence of these reactions, over the temperature ranges examined. In general, we found that temperature can be used as an accelerating parameter when the chemical reaction is identified and understood.

The effect of glass composition on glass durability is the next factor to undergo a detailed critical review. The emphasis of this effort is focused on expanding the interim report to include brief reviews of models of glass dissolution and glass structure. This information will form a basis for critically reviewing theoretical and empirical models relating glass composition to glass durability. The remaining parameters (radiation, SA/V ratio, surface layers, and unsaturated environments) will be critically reviewed after the experimental work has been completed.

2. Long-Term Testing of Fully Radioactive Glass (J. K. Bates, J. W. Emery, T. J. Gerding, J. C. Hoh)

a. Introduction

Before glass can be stored in a waste repository, it is necessary to develop a model that will predict how the glass will perform in the repository. Information that goes into the model includes data describing glass reaction mechanisms, rates of initial and final reaction, the affinity of the glass to react, and dependence of the glass reaction on interactions with other components in the waste package. The model must be mechanistically, not empirically based. To demonstrate its predictive capability, the model must be validated. Validation tests include long-term tests that closely simulate the expected conditions for storage, including parameters related to the glass and the repository. This task addresses tests to be performed that will provide information that can be used to validate glass reaction models, and can be used to demonstrate an understanding of glass reaction processes that will occur in an unsaturated environment. The results will also indicate whether differences exist in the reaction of fully radioactive glass compared to nonradioactive glass of the same nominal composition. This is important to demonstrate because model development has generally been done using results from nonradioactive glass tests. The results of the radioactive and nonradioactive tests can be used to demonstrate glass reaction in an unsaturated environment, but by themselves should not be used to predict glass reaction to repository time frames.

b. Objective and Rationale

The objective of this task is to evaluate the performance of fully radioactive glasses, similar to those that will be produced by the DWPF, in meeting the performance objectives for glass storage in a high-level waste repository located in an unsaturated horizon. Specifically, long-term data will be generated such that (1) reaction of fully radioactive glass can be compared with that of nonradioactive glass of the same nominal composition; (2) interactions between waste package components that must be accounted for in independent reaction path models are identified; and (3) the long-term behavior of glass is established under anticipated unsaturated disposal conditions, such that validation of glass performance models can be achieved.

In the DWPF process, glass will be produced by combining sludge and supernatant waste components with nonradioactive frit. Waste components will be combined in large "macro-batches," homogenized, and processed. Each macro-batch will establish the glass composition for an extended time period (campaign), and it is possible that the final glasses produced in each campaign will have different compositions. A range of possible compositions is provided by the Waste Compliance Plan,³ including an average or blend glass if all the waste were processed as one batch, and end-member compositions based on viscosity. The goal during frit development was to produce glass with a durability similar to that of sludge-only 165-based glass, and no worse than sludge-only 131-based glass.⁴ The identification of 131-based glass as the lowest-durability glass to be produced is also made in the environmental impact statement for the DWPF.³ These glasses were produced by Westinghouse Savannah River Co. (WSRC) over the past several years and represent glasses developed as the process engineering matured.

The glass produced in the DWPF will be radioactive, such that it must be processed and handled in remotely operated facilities. However, most testing to evaluate the performance of glass has been done using simulated nonradioactive analogs of the same composition as the radioactive glass. It must be demonstrated that the simulated experiments are adequate representations of reactions that will occur with the actual glass to be produced by the DWPF. The issues of concern are: (1) is there an effect due to radioactivity that is not adequately simulated using nonradioactive glass? and (2) is there an effect of using glasses that may not contain all the nonradioactive components that will be present in the sludge, supernate, and frit feeds to the DWPF? Nonradioactive glasses are generally produced from pure starting materials, and thus minor components that will be present in the DWPF glass may not be present in the simulated glass. The effect of minor components may be accentuated when glass is reacted under the high SA/V conditions expected in the unsaturated repository. Testing of radioactive glass has been performed by WSRC.⁵⁻¹⁰ The present tests will extend the duration of testing to longer time periods and will generate results that permit comparison between radioactive and nonradioactive glasses for three different compositions. A comparison between the leaching of radioactive and nonradioactive glasses was also done as part of the joint Japanese, Swiss, Swedish (JSS) Program. Results from that program¹¹ indicated that after one year there may be a factor of two difference in reaction. The present tests will extend the time period to assess glass performance under conditions which should approach the final rate-controlling processes.

c. Technical Approach

To determine the long-term performance of glass under repository conditions, tests must be conducted such that the "final" reaction conditions (steady state) are achieved. The unsaturated repository presents a challenge in performing long-term testing because, over the duration of storage, the repository conditions are expected to change, perhaps significantly, with respect to the amount of water available to react with the glass and to transport radionuclides.

Tests to evaluate the performance of glass in an unsaturated environment must address the unique features of such an environment and must be performed for time periods of long enough duration so that the stage is reached where secondary phase formation (as opposed to supersaturated solution concentrations) controls the glass reaction. Relevant tests include static tests performed at high SA/V ratios, and high SA/V flow tests done to simulate the waste package environment. The information obtained from these tests must include the solution composition as a function of time, combined with a description of the glass alteration. To meet these goals, three types of tests will be performed:

- (1) Long-term static tests (i.e., no water flow) at high SA/V with monoliths and powders. These tests provide temporal solution trends, plus easy identification of secondary phases combined with the distribution of radionuclides in the reacted glass layers.
- (2) Long-term intermittent flow tests at high SA/V following a modified version of the Unsaturated Test Procedure¹² as applied to "aged" and fresh glass monoliths.
- (3) Long-term repository environment tests following the laboratory analog procedure as applied to "aged" and fresh glass monoliths.¹³

The tests will be performed with the three different general groups of glass compositions: 165-, 200-, and 131-frit based glasses. A description of the tests to be performed in each test category is given below.

(1) Long-Term Static Tests at High SA/V

The long-term static tests will be performed following the test matrix shown in Table III-1. The matrix is divided into three sections, based on the glass type (165, 131, and 200). The tests to be performed with the 165 and 131 glass types are identical except for the number of replicates. The tests done with the 131 glass type are not replicated due to the limited amount of 131/11 glass available for testing. The tests done with 165 and 200 type glasses are done in duplicate. The schedule allows for all long-term tests (>364 days) to be started at the same time ($t = 0$). The short-term tests (<280 days) will be staggered such that at the end of 280 days, all the TBD (to be determined) tests will be started. Static tests are performed in the batch mode to allow for examination of solids at each test period so that the mass balance between the residual solids (reacted glass and secondary phases) and the solution composition can be documented. The tests are static, i.e., no exchange of leachant to promote conditions representative of the YMP site (little or no flow), and the reaction environment is disturbed as little as possible; thus, optimal conditions exist for secondary phase nucleation and growth.

Tests are done with monoliths at $SA/V=340 \text{ m}^{-1}$ and with powdered samples (100-200 mesh) at 2000 and $20,000 \text{ m}^{-1}$. Twelve tests are performed with a TBD termination period, and it is hoped that enough data will be available to allow temporal trends to be established.

Tests performed without glass but with EJ-13 water* are termed "blank tests." The results from such tests will indicate whether any cross-contamination of radioactivity occurred during

*EJ-13 is J-13 well water that is prereacted 14 days at 90°C with tuff rock.

Table III-1. Test Matrix^a for Long-Term Static Tests at High SA/V Ratios

SA/V (m ⁻¹)	131 Glass Type ^b				202 Glass Type ^c				165 Glass Type ^c				Blank ^b	
	131/11		Simulated		200R		Simulated		165/42		Simulated			
	340	2000	340	2000	340	2000	20,000	340	2000	20,000	340	2000		
Reaction Progress ^d														
1,620														3
2,380														14
4,760					14			14						28
6,000						3								30
9,520			28											56
14,000														70
19,040					56			56						91
28,000						14								98
30,940	91		91											140
60,000		30		30										182
61,880														280
123,760	364		364		182			182						364
140,000		70		70	364			364						546
247,520	728		728		728	70		728						728
280,000		140		140			14			14				980
495,000	1456		1456		1456									1456
560,000		280		280										1820
990,080	2912		2912		2912	280		2912						2912
1,120,000		560		560		560	56			56				TBD
1,960,000		980		980		980	98			98				TBD
3,649,000		1820		1820		1820	182			182				TBD
7,280,000							364			364				TBD
10,920,000							546			546				TBD
14,560,000							728			728				TBD
					TBD ^e	TBD	TBD	TBD	TBD	TBD	TBD	TBD	TBD	
					TBD	TBD	TBD	TBD	TBD	TBD	TBD	TBD	TBD	

^aThe entries in the table indicate the duration of a specific test in days. The tests done at 340 m⁻¹ use monoliths, the tests done at 2000 and 20,000 m⁻¹ use powder.

^bTests will be single tests.

^cTests will be duplicate.

^dReaction progress in terms of SA/Vt (units of m⁻¹day⁻¹). No significance is implied to the use of this reaction progress indicator.

^eTBD = to be determined.

test initiation or test termination. The tests are not true blanks that can be used to monitor EJ-13 reaction with the vessels because they are done without an internal radiation field. However, the solution composition measured in these tests may be used in evaluating the results of tests containing glass. The matrix for the blank tests mirrors that of the glass-containing tests and is shown in Table III-1.

(2) Long-Term Intermittent Flow Tests at High SA/V

The long-term intermittent flow tests will be conducted using the Unsaturated Test (UT) procedure developed by the YMP to assess glass performance in an unsaturated environment.^{12,14} The standard UT matrix was modified to include effects of aging both the glass and metal components to make the results more relevant to an actual storage environment. The tests will be performed with 200R glass, and the objectives of the tests are to (1) provide data that describe the release of radionuclides from a specifically designed waste package under strictly controlled test conditions and (2) provide information concerning synergistic effects that may occur between waste package components.

There are two sets of five replicate tests and one blank test. All the tests will be initiated concurrently. The first set of five tests will be performed with unaged or as-cast glass, and the results will be comparable with previous test series using the UT method.¹⁴ These tests represent the scenario whereby the container and pour canister are breached at a time after liquid water has penetrated the waste package environment and liquid water immediately passes through one breach, contacts and reacts with the glass, and passes out through a second breach. While the scenario is unlikely because it represents a bounding condition with fresh glass, the results will form a basis for comparison with tests done with aged components.

The second set of five tests will be done with aged components. Previous testing¹⁵ indicated that the reaction between glass and steam at temperatures above 100°C can accelerate glass reaction in a manner whereby the glass forms secondary alteration products but no radionuclide release occurs. The hydration of glass is accelerated compared to tests using low-SA/V leaching solution because the liquid in contact with the glass in the steam environment rapidly becomes saturated with components released from the glass and stable secondary phases form. The onset of secondary phase formation allows the hydration of glass to continue because components released from the glass are incorporated into the secondary phases. The higher the temperature of hydration, the more rapid the reaction and the greater the extent of acceleration. The hydration of glass in a vapor environment is not only a process that can be used to age the glass in the laboratory, but also a process that likely will occur in the repository. Repository aging could occur in a steam environment if containment breach occurs before the temperature of the waste package cools below 95°C. It could also occur in a vapor environment if a breach occurs at a temperature below ~95°C in the absence of liquid water inundating the bore hole. The latter case is the expected environment for the unsaturated repository; thus, the present tests are being done to induce a degree of vapor hydration aging that likely will occur in the repository. Aging will be imparted to both the glass and the metal components of the test system.

Several issues must be addressed before tests can be done with aged components, including the following: (1) is the laboratory acceleration method acceptable in that the reaction is accelerated without altering the reaction mechanism? (2) is there an analytical expression that relates the results generated in the laboratory with results expected in the repository? and (3) how much hydration aging is expected in the repository? These questions are being addressed by other tasks in this program, and the tests with fully radioactive glass will not be initiated until the above questions are resolved and more details of the aging process are circulated for comment.

(3) Long-Term Repository Environment Tests

The laboratory analog test has been developed¹³ to relate the performance of glass as observed in the Unsaturated Test with a more repository-relevant environment. In the laboratory analog test, the waste package assemblage (WPA) as used in the Unsaturated Test is placed within a bored-out cavity in a tuff core. The dimensions of the WPA and the cavity are similar to those used in the Unsaturated Test. The tuff core and WPA are assembled, and an unsaturated flow of water is forced through the core by using a vapor pressure slightly above ambient.

The objective of this test is to evaluate glass performance in an environment that closely matches that expected in the repository. Emphasis is placed on measuring glass reaction by examining the reacted glass and surrounding tuff rock at the test termination, and by monitoring the radionuclide content of the groundwater as it is released from the test vessel.

Two analog tests will be performed. One will be done with unaged glass and a sensitized 304L stainless steel retainer, and one will be done with aged glass and stainless steel. The aging process will be similar to that used in the long-term, intermittent flow experiments.

d. Status

The 165/42 and 131/11 glasses have been received from WSRC, their compositions determined and compared with compositions provided by WSRC, and simulated glasses and test samples manufactured. The tests with 165/42, 165/42S, and 131/11 glass (Table III-1) have been ongoing for ~180 days, and scheduled test periods through 140 days have been completed. Because several dissolutions of 131/11 glass were required before we felt confident enough to make a simulated glass, tests with 131/11 glass have just been initiated. Blank tests without glass present have also just been initiated.

One shipment of 200R glass has been received and the final shipment is expected shortly. Once we have received the entire batch of glass, the batches will be homogenized, the composition determined, and the remainder of the tests initiated.

e. Future Progress

It is anticipated that the complete shipment of 200R glass will be received early in FY 1991. Immediately on final receipt of the glass, the batches will be homogenized and compositionally analyzed. Powdered and monolithic samples of the 200R glass will be made to initiate the remainder of the long-term static test matrix. A batch of simulated 200R glass will also be made so that the matrix of nonradioactive tests can be started.

Upon initiation of the static tests with 200R glass, effort will begin on starting the long-term intermittent flow tests with this glass. This will require making the required monolithic blocks, aging half of the monoliths under vapor hydration conditions, and adapting the Unsaturated Test apparatus to operate with fully radioactive glass. It is anticipated that the intermittent flow tests will be started ~9 months after receipt of the glass.

The ongoing static tests will be continued and emphasis will be placed on analysis of the reacted samples. Each sample will be examined by optical microscopy to identify regions of interest for microscopic analysis and to obtain a visual description of the sample. Analyses will then be conducted using scanning electron microscopy (SEM), analytical electron microscopy (AEM), and/or

secondary ion mass spectroscopy (SIMS) based on the information required. Data will be generated to compare the reactivity of the radioactive and nonradioactive glasses and to provide a data base for validation of glass performance models.

3. Effect of Radiation

(D. J. Wronkiewicz and J. E. Young)

The environment of irradiated moist air systems may be influenced by the buildup of radiolytic products that accumulate in the limited amounts of solution present. This situation is similar to that expected at the potential Yucca Mountain repository, where high-SA/V conditions may create an environment that is particularly detrimental to glass stability. In this scenario, the limited buffering capacity of small amounts of bicarbonate present in water condensed on the glass may be quickly overwhelmed by nitric acid produced in radiolysis reactions. The present experiments are designed to examine the effects of radiolysis and the formation of radiolytic products on the performance of simulated nuclear waste glass in an unsaturated repository environment.

The objective for the first phase of the experiments is to identify which radiolytic products will form in an irradiated moist air environment, determine at what concentrations the species occur, and establish the principal location of radiolytic product condensation. Two sets of "blank" experiments were conducted in the presence of either gamma or alpha radiation fields to examine radiolytic product formation in the absence of glass.

Blank experiments at room temperature with α -radiation have been carried out in several experimental configurations, with each experiment conducted in duplicate. In the first series of experiments, the source of the α -radiation was a foil containing 1500 μCi ^{241}Am cemented onto a 1-1/8 in. (2.9 cm) diameter lucite rod. The rod was then attached to the underside of a wide-mouth Mason jar lid with a 3/32-in. (0.2 cm) thick silicone gasket to ensure a gas-tight seal at the attachment to the Mason lid. This assembly was then placed in a two-quart Mason jar along with 18 mL deionized water, and sealed in place with the standard Mason outer ring. This configuration was selected so that the entire alpha dose is imparted to the air. None of the α -radiation from the foil impinges on the glass vessel, lid, or the foil support. Duplicate blank experiments with an external γ -radiation source were carried out at room temperature in standard 22-mL Parr pressure vessels. The dose rate was 0.00036 MR/h.

Results suggest that the extent of nitrogen fixation, measured as a function of nitrate plus nitrite production, varies at a rate that is linear with respect to exposure time (Fig. III-1). For the alpha blank experiments, the rate of nitrogen fixation approached amounts similar to those obtained experimentally by Linacre and Marsh.¹⁶ Gamma radiation analyses display higher fixed nitrogen concentrations and a greater range of variability than the alpha tests. This variation may arise as a result of the proximity of the test vessels to the gamma source, with the radiation dose effect varying as a function of the inverse distance squared from the radiation source. Thus, small distance variations between source and sample may have a relatively large effect on the total absorbed dose of the experimental system. Because the alpha blank tests were conducted with internally housed Am-241 foils, they are not subjected to any source-sample distance variations that may influence the total dose rate.

The fixed nitrogen species that formed in both the alpha and gamma blank tests were concentrated in thin films of water that had condensed on the test vessel walls and/or Am-241 foils. Significant amounts of formic acid, oxalic acid, and carbon (both organic and inorganic) were also detected in solutions rinsed from the test vessel walls, while lesser concentrations of these species were present in the small quantities of fluid present at the bottoms of the test vessels.

Fig. III-1. Nitrogen Fixation in Blank Radiolysis Tests Measured as a Function of Nitrate + Nitrite Formation: (a) Alpha Blank Tests with Am-241 Foils Supported by Lucite Rods and (b) Gamma Blank Tests Conducted with External Radiation Source. "Pre-rinse" refers to solution aliquot collected from bottom of test vessel. "Rinse" fraction includes portion rinsed from the vessel walls with deionized water plus the pre-rinse fraction. Line was obtained from experimentally determined data of Linacre and Marsh¹⁶ and gives a nitrogen fixation rate of 1.9 molecules/100 eV absorbed dose.

Another series of experiments was done to determine the cumulative effect of radiolytic-product formation on the performance of a simulated borosilicate waste glass. For this purpose, SRL 202 composition glass was reacted in a 200°C steam environment, with and without radiation (0.005 rad/h). The thin films of water in contact with the glass in the irradiated tests turned out to be so corrosive that the samples had reacted completely through their 2-mm thicknesses between 35 and 56 days (Fig. III-2). By contrast, 35- and 56-day samples reacted in a nonirradiated environment displayed reaction layer thicknesses of 55 ± 11 and 132 ± 15 μm , respectively. This preliminary comparison of the two sets of results suggests that glass reaction rates in a radiation field exceed those in a nonradiation field by a factor of ~ 10 to 20.

Fig. III-2. Reflected Light Photomicrographs Showing Glasses Reacted under Nonirradiated and Irradiated Environments for 202U (U-238 Doped) and 202A (Actinide Doped) Compositions, Respectively. Both glasses were exposed to a vapor-saturated environment at 200°C for 35 days. The 202A glass was exposed to an external gamma source of 3.6×10^3 R/h and an internally produced alpha source of ~ 100 R/h.

The radiation field also appears to have influenced the development of secondary mineral precipitates on the glass surfaces. Samples reacted in a radiation field developed thick precipitate layers that contain analcime ($\text{NaAlSi}_2\text{O}_8 \cdot \text{H}_2\text{O}$), weeksite ($\text{K}_2(\text{UO}_2)_2(\text{Si}_2\text{O}_5)_3 \cdot 4\text{H}_2\text{O}$), and an acicular calcium silicate phase [possibly tobermorite, $\text{Ca}_5(\text{OH})_2\text{Si}_6\text{O}_{16} \cdot 4\text{H}_2\text{O}$]. By contrast, samples reacted without radiation have relatively thin and discontinuous precipitate layers that contain analcime, relatively minor weeksite, a bladed rosette-shaped calcium silicate phase [possibly gyrolite, $\text{Ca}_4(\text{Si}_6\text{O}_{16})(\text{OH})_2 \cdot 3\text{H}_2\text{O}$], unidentified K-Al silicate buttons, and unidentified sodium silicate radiating fibrous masses.

4. Relationship between High SA/V Experiments and MCC-1 (W. L. Ebert)

a. Objective and Rationale

The purpose of this task is to compare the reaction of waste glass in static leach tests at different SA/V ratios through analysis of the leachate and the reacted glass and to relate changes in the

leachate compositions with changes in the glass surface. Static leach tests are commonly used by glass producers as a measure of production consistency. Because of the simplicity of these tests and the large amount of data available under these test conditions, they have been used extensively to measure the durability of glasses being formulated to contain high-level nuclear waste for emplacement in a geologic repository. The very long service life of the repository requires the glass durability to be projected over a 10,000-year period. It is therefore necessary to accelerate the glass reaction in laboratory tests to approximate the durability over very long times. Two methods of accelerating durability tests have been commonly used: either increasing the temperature or the SA/V ratio.

Tests at elevated temperatures require that the reaction steps involved in the glass dissolution mechanism maintain Arrhenius behavior over the temperature range of interest, and that the rate-determining step of the mechanism remains the same. The effect of temperature is discussed elsewhere in this report.

Use of high SA/V ratios does not increase the reaction rates directly; rather, the rate of solution saturation is increased. In static leach tests at high SA/V ratios, the glass reaction rate is quenched as the solution approaches apparent saturation. It has been speculated that tests performed for short times at high SA/V may be equivalent to tests performed for long times at low SA/V. Such an equivalency is very attractive for durability tests of glasses produced for use in a repository, and many tests have been performed at various SA/V ratios with the goal of extrapolating the results to long reaction times. Efforts to use such tests to project long-term durabilities have met with success in many instances where the glass dissolution followed a simple rate expression.¹⁷ Other investigations have shown the reaction rate to deviate from a simple dissolution rate law at long reaction times and the equivalency to fail.¹⁸

Work is in progress to understand the source of deviation and to develop tests that better approximate the long-term behavior of the glasses. At present, laboratory tests are not expected to be used to demonstrate long-term reaction trends. Rather, computer models which incorporate mechanistic understanding derived from laboratory experiments and glass dissolution tests will be utilized to project glass performance under a variety of possible repository environments over very long time periods. Thus, durability tests are performed both to measure the extent of glass reaction over short time periods and to support computer simulations of glass reactions over long time periods.

The rate law derived by Aagaard and Helgeson¹⁹ for mineral dissolution has been successfully used to describe glass dissolution over time periods up to a year and incorporated into computer codes to describe the glass reaction over repository-relevant time periods.^{20,21} This rate law combines a rate coefficient with an affinity term to account for the influence of the solution chemistry:

$$\frac{dm_i}{dt} = SA \cdot k_- \left[1 - \frac{Q}{K} \right] \quad (\text{III-1})$$

Here, m_i is the number of moles of species i lost from the glass during reaction, SA is the glass surface area, k_- is the rate coefficient, which is a function of temperature and pH, Q is the ion product, and K is the equilibrium constant of the glass. Because the computer models are based on saturation indices, the number of moles of i is replaced by the solution concentration as $C_i = m_i/V$, where C_i is the molar concentration of i , and V the solution volume (see Eq. 1 in Ref. 21). Hence,

$$\frac{dC_i}{dt} = \frac{SA}{V} k_- \left(1 - \frac{Q}{K} \right) \quad (\text{III-2})$$

Note that for Eq. III-2 to hold, all i released from the glass must go into solution. This equation clearly shows that the rate of solution concentration increase (dC_i/dt) is directly proportional to SA/V , and integration of Eq. III-2 shows the proposed equivalency of tests run at different SA/V ratios for equivalent products of $SA/V \cdot t$. The formation of colloids or secondary products precludes the substitution of $C_i = m_i/V$ and invalidates Eq. III-2. Likewise, changes in the reacting glass are not accounted for in this model, nor are changes in glass reaction mechanism as a function of SA/V . Nonstoichiometric release changes the composition of the glass in the near-surface region and presumably affects the rate coefficient and perhaps the equilibrium constant.

The tests performed within this task are designed to study changes in both the solution chemistry and the reacting glass surface as the reaction progresses at different SA/V ratios. Comparing the solution and solids results at various SA/V ratios provides evidence on whether or not the reaction mechanism changes as colloids or precipitates form or as the reacting glass surface changes during the reaction. Because solution saturation effects occur simultaneously with changes in the glass structure, the role of each in affecting long-term glass durability must be more clearly understood before a method of accelerating the reaction can be deemed valid.

The MCC-1 static leach test is widely used as a measure of relative glass durability, wherein glass monoliths are reacted and the leachate solution is analyzed to measure the extent of reaction. However, with this test, highly durable glass may require long reaction times to reach sufficiently high solution concentrations for solution affinity effects to be observed. The MCC-3 and PCT tests, which use powdered glass, were developed to achieve a higher SA/V . These tests generate concentrated solutions at a greater rate than the MCC-1 test and thus show concentration effects after short reaction times. While the MCC-1 test (low SA/V) provides information on the initial glass reaction rate and high SA/V tests (MCC-3 and PCT) provide information on the longer-term glass reaction rate, the relationship between the MCC-1 and high SA/V tests has not been demonstrated conclusively. That is, a glass that is highly durable in an MCC-1 test may be significantly less durable in a high SA/V test due to a change in the rate-limiting step, eventual alteration of the glass surface, or the generation of a secondary phase that alters the solubility limits and thus the reaction rate of the glass.

As described above, in the absence of secondary solids formation, equivalent solution compositions may be achieved at equivalent values of $SA/V \cdot t$. Several waste glasses of interest have been shown to dissolve nonstoichiometrically and to produce reaction layers on the glass surface enriched in elements with low solubility limits. The formation of these layers and secondary solids may preclude use of the $SA/V \cdot t$ equivalence. Complex interactions such as the influence of the pH on the solubility of the reaction layers may also invalidate the use of $SA/V \cdot t$ equivalence. It is necessary to show how secondary products and the solution chemistry affect the relation between MCC-1 tests and high SA/V tests if static tests are to be used to project glass durabilities under repository-relevant conditions.

The tests performed under this task will address the following issues:

- (1) Can different SA/V ratios be used to predictably accelerate the approach to leachate saturation as $SA/V \cdot t$?
- (2) Is the reacted surface similar after equivalent $SA/V \cdot t$?

- (3) Do secondary phases form, and if so, what phases form?
- (4) What is the effect of secondary phase formation on the leachate and on the reacting glass?
- (5) Is the reaction accelerated at high SA/V relative to low SA/V through solution effects? That is, are the MCC-1 test and tests performed at higher SA/V mechanistically equivalent?

b. Technical Approach

Two glass compositions are reacted at three different SA/V ratios and 90°C. Test duration was varied so that reaction trends for the three SA/V ratios could be compared at equivalent SA/V•t. A glass composition that has been shown to be highly reactive in previous MCC-1 type leach tests (SRL 131) was selected to demonstrate a large SA/V effect within a short time period. A second, more durable glass (SRL 202) was selected to represent the actual glass waste form to be used in waste disposal. By using glasses of different known durabilities in MCC-1 type tests, the magnitude of any effects of different SA/V can be compared. The glasses were doped with actinide elements having a long half-life, which will remain active after long disposal times. The release mechanisms of these species and their behavior in the repository environment must be understood because they will account for the majority of the radioactivity present beyond the 300/1000-year isolation period. The dopant levels are such that leachate analysis may be performed without extensive separation procedures, as determined in previous experiments with similar glass compositions.²²

Monolith samples are reacted at 10 m⁻¹, and granular glass is reacted at 2000 m⁻¹ and 20,000 m⁻¹. These values of SA/V include that used in the MCC-1 test (10 m⁻¹), that used in the MCC-3 and PCT tests (2000 m⁻¹), and a high ratio (20,000 m⁻¹), which permits complete solution analyses and allows comparison of the reaction at several equivalent SA/V•t values. [At a later date, tests with glasses having an intermediate SA/V ratio (340 m⁻¹) are to be performed using monolith samples with these same glass compositions.]

The reactions are characterized by the solution chemistries (pH, anion and cation concentrations) and by the abundance and composition of the reacted layer remaining on the glass and the secondary phases formed. Special attention will be given to the distribution of released actinide species between dissolved and colloidal fractions in the leachate, that sorbed onto the vessel walls, and that left as insoluble residue on the glass surface or incorporated into secondary phases. The amount of actinides in each fraction will be quantified by appropriate sampling procedures. These and other analytical procedures are performed in accordance with the data needs of modelers and application of Eq. III-2.

The leachate solutions are filtered through 0.45 μm filters to remove any glass particulates from the analyzed solution. This filtration may also remove large colloids from the solution. The filtration is performed at the reaction temperature to prevent temperature-induced precipitation of secondary phases from solution prior to filtration. Analyses are then performed on the cooled filtrate.

The reacted glass is analyzed using optical microscopy, SEM with X-ray analysis, and AEM. The surfaces and cross sections of reacted particles will be examined to quantify the extent of reaction by the thickness of a reaction layer formed on the surface, secondary product formation, and compositional changes in the glass itself.

c. Matrix

The matrix of tests performed under this task is shown in Table III-2. All tests are performed in duplicate, and the entire matrix is performed using SRL 202 and SRL 131 glass (for a total of 116 tests).²³ Tests are performed in 304L stainless steel vessels with pre-equilibrated J-13 tuff groundwater (EJ-13) as the leachant. This leachant is a slightly basic silicate solution with a high sodium and bicarbonate content. The calcium is near its solubility limit. Both glasses are, in the short term, expected to be more stable in this solution than in deionized water (DIW). Blank tests using only EJ-13 solution are being performed in Part II of this task. The results of these tests will be utilized as background correction values.

Table III-2. Test Matrix to Determine Effect of SA/V^a

Targeted SA/V•t, days/m	Reaction Time, days		
	10/m	2000/m	20,000/m
70	7		
280	28		
910	91		
2,380	238		
6,000	600	3	
14,000	1400	7	
28,000	2800	14	
60,000		30	3
140,000		70 ^c	7
280,000		140 ^c	14
560,000		280	28
1,120,000		560	56 ^c
1,960,000		980	98 ^c
3,640,000		1820	182 ^c
7,280,000		3640	364
14,560,000			728
TBD ^b	TBD ^b	TBD ^b	TBD ^b

^aTwo tests are performed at each SA/V•t for each glass.

^bTBD = duration of tests to be determined.

^cAll tests not yet initiated.

d. Status

Initial efforts were focused on producing the monolith and powdered glass samples. A known amount of actinides was added to the two base glass compositions. The glasses were then mixed and melted at about 1150°C, then poured into platinum molds and annealed for about two hours at 500°C. A diamond core drill was used to remove cores about 1 cm in diameter. The core circumferences were polished, and the cores cut to produce disks about 1-2 mm thick. The faces of the disks were then polished to a 600-grit finish and washed before use in the 10 m⁻¹ tests. The remainder of the glass was mechanically crushed and sieved, and the fraction between 100 and 200 mesh was retained. This was washed thoroughly in ethanol to remove fines. A sample of the powdered glass was viewed by SEM to assure that fines had been removed and the correct size fraction was produced.

Tests were initiated by placing the appropriate mass of powdered glass or a glass monolith plus stainless steel support stand in a clean stainless steel reaction vessel and adding the appropriate mass of leachant. The SA/V ratio was computed using the geometric surface area of the monoliths and the surface area of the powdered glass. The latter was calculated by assuming the particles to be cubes with a cube edge of the average mesh size and the glass to have a density of 2.7 g/cm^3 . Visual inspection of the powder confirmed that, although the particles were not cubic, the average facial area of a scanned side was well approximated by the area of such a cube face. The density of the leachant was assumed to be one. The approximate SA/V ratio calculated for each test was typically within a few percent of the targeted ratio (10, 2000, or $20,000 \text{ m}^{-1}$).

At present, all but about 20 tests have been initiated. The remaining tests will be initiated as soon as vessels become available when short-term tests are terminated. The durations of these tests are given in Table III-2. Note that the matrix provides extra tests to replace those that failed or had anomalous results or to provide tests of intermediate duration not originally scheduled. These tests will be started as test vessels become available.

e. Preliminary Results

Tests of 30-day duration or less have been terminated, and the results are being analyzed. Figure III-3a shows the leachate pH values of these tests. The leachate was sampled at the reaction temperature and allowed to cool to room temperature in individual sample vials prior to analysis. The values shown in Fig. III-3a were obtained at room temperature (26°C). The leachant (EJ-13) pH value was measured to be 8.1. As shown in Fig. III-3a, the SRL 202A series at $20,000 \text{ m}^{-1}$ and 2000 m^{-1} reached pH values of about 11 and 10, respectively, after 14 days. Experiments with SRL 131A glass at $20,000$ and 2000 m^{-1} reached higher pH values than those with SRL 202A at similar SA/V for all reaction times. This result indicates that the SRL 131A glass is more reactive. The higher pH is due, in part, to ion exchange reactions which remove protons from solution as alkali metals are released into solution. Other solution analyses and analysis of the reacted glass should confirm that SRL 131A is more reactive. The reaction at 10 m^{-1} has not progressed enough that the solution pH is significantly different for the two glass types. After 7 days, the pH of the 10 m^{-1} experiments with either glass type is not significantly different from that of the EJ-13 leachant, but both glass types have pH values higher than the leachant after 28 days.

The uranium analyses of the leachate solutions of tests reacted for 30 days or less have been completed, and the results are plotted in Fig. III-3b. Two features of the plots are noteworthy: the uranium concentration in tests performed at 2000 or $20,000 \text{ m}^{-1}$ shows an initial increase and then decreases as the reaction progresses. This is most clearly seen in the reaction of SRL 202A at $20,000 \text{ m}^{-1}$, where the uranium concentration increases to about 15.5 ppm after 14 days and then decreases to about 10 ppm. This behavior is seen in the 2000 m^{-1} tests as well and for both glass types. The uranium release from the 10 m^{-1} tests is too low to show any trend. The observed decrease in the uranium concentration at high SA/V is believed to be the result of secondary phase formation (mineral phases or colloids). Observation of the reacted solids should indicate if secondary minerals form. Another interesting observation about Fig. III-3b is that the uranium concentration is greater at $20,000 \text{ m}^{-1}$ than at 2000 m^{-1} for SRL 202A but less for SRL 131A. The pH results in Fig. III-3a show that the extent of reaction is greater at $20,000 \text{ m}^{-1}$ than at 2000 m^{-1} for both glass types. This suggests that secondary phases containing uranium form earlier in the reaction of SRL 131A at $20,000 \text{ m}^{-1}$ to maintain very low uranium concentrations at all reaction times tested. Again, analysis of the reacted solids is required to support this interpretation.

Fig. III-3. Leachate pH and Uranium Concentration vs. Reaction Time for Experiments Performed with SRL 202A and SRL 131A Glasses at 20,000 m^{-1} , 2000 m^{-1} , and 10 m^{-1} at 90°C

Special attention is given to the fate of the released actinide elements. The actinide content of the leachant is analyzed as samples that are unfiltered, passed through a 0.45 μm filter, or passed through a filter with an estimated pore size of 50 Å. The amount of actinide sorbed onto the stainless steel vessel is also analyzed in an acid rinse which redissolves any sorbed species. Analysis of the actinide content is in progress, but too few tests have been completed to establish any reaction trends. The reacted glass samples have not yet been analyzed, and efforts will be made to identify actinide-containing phases on or in the reacted glass.

5. Analytical Electron Microscopy
(J. K. Bates, C. R. Bradley, and N. L. Dietz)

a. Introduction

Analytical electron microscopy (AEM) is a combination of transmission electron microscopy (TEM), energy dispersive X-ray spectroscopy (EDS), energy electron loss spectroscopy (EELS), and electron diffraction (ED) applied to prepared thin sections (~500 Å) of reacted glass. The AEM technique is used to examine the structure of reacted glass and thereby provide information as to the reaction processes and identification of secondary phases. For AEM to be successful, three areas of expertise must be developed: (1) sample identification and segregation, (2) sample preparation, and (3) AEM examination.

Sample identification and segregation involves examining the reacted glass using optical microscopy, identifying regions of the sample that warrant further examination, and dissecting the sample to yield a region for examination. Generally, regions studied must have specific spatial characteristics to produce successful thin sections. The regions must be small (~10-50 µm in diameter), both the reacted layer and bulk glass must be present (preferably mostly layer and minor bulk glass), and the orientation of the layer and bulk glass must be such that when cut with a knife, representative sections are obtained.

Sample preparation requires taking the segregated region of the sample and preparing a thin section that is electron transparent. The sample must retain its original orientation and must not be chemically or structurally altered during the preparation process. We have found ultramicrotomy to be the best preparation method for these samples. Ultramicrotomy involves mounting the region of interest of the sample at the tip of an epoxy block and cutting thin sections of the block with a diamond knife. The thin sections are then gathered onto a TEM grid for examination.

Examination of the samples with AEM is done by obtaining a low magnification overview of the sample, ascertaining whether the sample segregation and preparation steps were successful, correlating the appearance of the sample in the TEM with the appearance of a sister sample prepared for thick-section SEM examination (this allows the AEM operator to determine from where in the sample the sectioned regions were actually derived), and then applying the analytical techniques to the examination of the sample.

Reacted glasses are one of the more difficult types of samples to examine for several reasons: they are nonconductive and contain diversely opposite materials (the layers are generally soft while the glass is brittle), both the layers and glasses are readily damaged by the electron beam, and the complexity of the layer structure may require several months of detailed examination to unravel. Thus, we have spent considerable effort in refining general AEM techniques as applied to a wide variety of reacted, nonradioactive glasses. This experience will allow us to examine the radioactive glasses with more confidence and provides useful information regarding glass reaction processes. In this section of the report, we provide an overview of an examination of a sequence of samples.

b. Results and Discussion

Table III-3 provides a listing of samples examined, a reaction history, and an overview of observations. At this time, we have completed the initial examination of all of the samples to judge whether the sample preparation steps were successful. In general, we have been successful in

preparing adequate TEM sections for all glass types ranging from those with no layers to those with layers 100- μm thick.

One example is discussed below, where the samples were generated in a series of static leach tests supported by the YMP, and detailed solution and SEM results have been presented previously.²² The applicability of AEM to the interpretation of glass reaction is presented.

These experiments consisted of a series of static, batch tests terminated between 14 and 278 days. The tests were performed with as-cut monoliths of simulated SRL 165A frit-based glass (see Table II-1 of Ref. 23) with an SA/V of 30 m^{-1} . The tests were performed in 304L type stainless steel vessels at a temperature of 90°C with J-13 water that had been pre-equilibrated with tuff at 90°C . The experiments were conducted with and without a polished tuff wafer present in the bottom of the test vessel. The results described herein are from those tests with tuff present, and the complete experimental details are presented elsewhere.²²

The SEM examination indicated that more detailed characterization of the layer was required to determine the structure and composition of the bands. Thus, AEM was utilized to provide the required detail. Electron transparent thin sections of the reacted glass bands were prepared using an ultramicrotomy procedure specifically developed for preparation of sections of fine-grained geological materials.²⁴ Small fragments of the glass, together with the leached layer intact, were removed from a bulk specimen by using a diamond blade. Care was taken to select fragments that are smaller than $100\text{ }\mu\text{m}$ and contain as little unreacted glass as possible so that fragmentation of the brittle glass is minimized during sectioning. The selected fragment was mounted in epoxy or acrylic resin in an orientation which would yield cross-sectional slices of the leached layers and unreacted glass.

Brightfield transmission electron micrographs of glass reacted for 56, 91, and 278 days are shown in Fig. III-4. After 56 days, the leached layer is 0.2- and $0.25\text{-}\mu\text{m}$ thick and remains firmly attached to the unreacted glass (Fig. III-4a). Iron has begun to segregate toward the center of the layer, where it forms a dark stain, and no evidence of crystallinity can be detected throughout the layer. No evidence for a precipitated metal film on the outer surface is observed. The sample was taken from a reflective, nonreacted-appearing region of the glass surface.

After 91 days, the iron has segregated into a well-defined iron oxide "backbone" at the center of the reacted layer (Fig. III-4b). This iron region also shows the presence of calcium and zirconium. The lower half of the leached layer retains textural characteristics of the 56-day sample, but the upper half is dominated by a fibrous material identified as smectite clay by electron diffraction, lattice fringe imaging, and quantitative EDS. There is evidence that smectite is beginning to form on the lower half of the layer also. The unreacted glass is now separated from the layer by an open region that contains stringers of partially reacted glass. The glass is retreating from the leached layer by dissolution, and the thickness of the layer itself is about $0.8\text{ }\mu\text{m}$, while the distance between the outer surface of the layer and the unreacted glass is $1.2\text{ }\mu\text{m}$.

After 278 days the banded structure is now mature, with fibrous smectite bands dominating both the upper and lower regions on either side of the "backbone." The thickness of the layer reaches up to $1.0\text{ }\mu\text{m}$, while the total thickness is about $1.3\text{ }\mu\text{m}$.

The glass reaction process can be described by combining the solution and structural data. At 56 days, the amount of glass that must have reacted to give a normalized elemental release for lithium, $(\text{NL})_{\text{Li}}$, of 3.2 g/m^2 is $1.1\text{ }\mu\text{m}$. However, the layer thickness is only $0.2\text{ }\mu\text{m}$. Reaction of the glass is occurring at two fronts. At the interface between the layer and glass, preferential depletion of Li,

Table III-3. Conditions and Test Results for AEM Analysis of Glass from Leach Tests

Glass Type	Test Type	Temp., °C	SA/V, m ⁻¹	Duration, days	Leachate	AEM Results
ATM-1c	Long-term, MCC-1 type leach test, static	90	30	365	EJ-13	Complex layer structure with banding and precipitation at outer surface (Fig. 14, in Ref. 23).
ATM-1c	Long-term, MCC-1 type leach test, static	90	30	730	EJ-13	Complex layer structure, several precipitates identified, U-Ti phase present in layer.
ATM-1c	Long-term, MCC-1, static with tuff rock	90	30	365	EJ-13	Complex layer structure, comparison with tests done without tuff possible.
SRL 131	Long-term, MCC-1 type leach test, static	90	10	7-520	DIW	A series of samples showing the development of a complex layer as a function of time. The details of this study are presented in Ref. 25.
SRL 131	Long-term, MCC-1, samples provided by G. Wicks	90	10	1280	DIW	Complex layer structure to be compared with the samples reported in Ref. 21; this glass contains U and discrete U-Ti phases were observed.
SRL 131	Long-term, MCC-1, samples provided by G. Wicks	40	10	1460	DIW	Very thin layer showing no structure, some U-Ti segregation. Does not have the same appearance as the same glass composition reacted at 90°C.
SRL 131	Short-term, MCC-1, to examine SA/V effects	90	10	100	DIW	Complex layer structure similar to that reported by Ref. 25, layer attached to glass.
SRL 131	Short-term, MCC-1, to examine SA/V effects	90	50	20	DIW	Simplified layer structure with very limited precipitated phase formation, layer not connected to glass.
SRL 131	Short-term, MCC-1, to examine SA/V effects	90	50	50	DIW	Simplified layer structure with very limited precipitated phase formation, layer not connected to glass.
SRL 131	Short-term, MCC-1, to examine SA/V effects	90	100	10	DIW	Simplified layer structure with very limited precipitated phase formation, layer not connected to glass.
SRL 131	Short-term, MCC-1, to examine SA/V effects	90	100	25	DIW	The structure of the 50 and 100 m ⁻¹ SA/V layers and precipitates is different from the 10 m ⁻¹ samples.
SRL 131	Short-term vapor hydration, 100% RH	200		7	Vapor	Section with a calcium silicate phase intact on the surface showing a complex layer structure near the surface, including a near-pulse Si layer. The bulk of the layer is a clay with varying degrees of crystallinity (Fig. 11 in Ref. 23).

(contd)

Table III-3. (contd)

Glass Type	Test Type	Temp., °C	SA/V, m ⁻¹	Duration, days	Leachate	AEM Results
SRL 165	Long-term, MCC-1 type leach test, static	90	30	56	EJ-13	Simple layer structure with no precipitated phases and no crystallinity, Fig. III-4a.
SRL 165	Long-term, MCC-1 type leach test, static	90	30	91	EJ-13	Emerging complex layer structure with separation between layer and glass, Fig. III-4b.
SRL 165	Long-term, MCC-1 type leach test, static	90	30	280	EJ-13	Complex layer structure with precipitated phases either side of an Fe-rich backbone, Fig. III-4c.
SRL 165	Long-term, MCC-2 type leach test, static	187	10	364	DIW	Carefully prepared section over 100 μ m thick, complex layer structure at the layer/glass interface with discrete apatite phases, outer surface of layer is fairly nondiscrete, coarse clay grains make up the bulk of the layer, no glass.
SRL 165	Short-term, MCC-2, samples provided by B. Bourcier	150		7, 14		Complex outer layer structure with large crystalline grains making up the inner portion of the layer, there is a clear difference in texture and structure of the 7- and 14-day samples.
SRL 165	Long-term drip test with sensitized steel	90		364	EJ-13	An overlapping layer backbone structure reminiscent of layers formed on leach samples (above) (Fig. 16a in Ref. 23).
SRL 165	Long-term drip test with reduced glass SA	90		364	EJ-13	An overlapping layer backbone structure reminiscent of layers formed on leach samples (above) (Fig. 16b in Ref. 23).
SRL 202	Short-term vapor hydration, 100% RH	200			Vapor	No discrete secondary phases on surface but a layer structure indicating separation of layer and glass.
SRL 202	Long-term vapor hydration, 100% RH	200			Vapor	Discrete phase on surface of glass, difficult to retain the phases during sectioning, complex layer structure.
Basalt	Long-term vapor hydration, 100% RH	200		60	Vapor	Layer structure similar to that observed for waste glass.
Obsidian	Long-term vapor hydration, 100% RH					No layer structure or evidence of reaction observed in AEM, water has diffused into glass as determined optically.
Tektite	Long-term vapor hydration, natural conditions					A thin overlying clay structure interspersed with discrete mineral phases, also a water diffusion layer as determined optically.

(a)

(b)

(c)

Fig. III-4. Brightfield Electron Micrographs of Cross Sections of Glass Reacted for (a) 56 days, (b) 91 days, and (c) 278 days

B, and Na occurs as the glass becomes hydrated. The glass must also be reacting at the solution/layer interface where etching of the layer occurs. As the etching occurs, there is no apparent precipitation of insoluble metals or metal oxides directly onto the layer surface. Iron, while enriched, is nearly uniformly spread throughout the layer, while Ni and Mn are noticeably depleted in the layer.

By 91 days, however, evidence for precipitation exists, with smectite eventually covering the entire surface. The iron-rich "backbone" now marks the condensation of Fe, Ca, and Zr within the layer that was just beginning to occur at 56 days. Smectite, as it forms from the 56-day layer, excludes Fe, Ca, and Zr from its structure and incorporates Mn and Ni from solution. Surprisingly, by 91 days, the position of the surface at 56 days becomes marked by the "backbone," and the glass continues to react by two means: a partial hydrolysis which releases $\text{Li} > \text{B} > \text{Na}$ (cf. SIMS and solution results), and an etching process of the partially hydrolyzed glass.

After 278 days, the 56-day structure is completely transformed to two smectite layers formed on either side of the "backbone." The clay has nearly identical composition and structure on either side of the "backbone." This finding indicates that the solution composition and precipitation processes occurring within the main solution component and the near glass solution component are similar. This suggests that the clay-backbone structure is not impeding transport of material and does not act as a protective barrier. In fact, clear transport pathways can be observed in the "backbone" structure (Fig. III-4c).

While a reasonably consistent picture of the glass reaction process has been obtained through 278 days, questions remain as to how to extend these types of experimental data to provide input to model development for long-term glass performance. These include the following. What is the fate of the reacted layer? Will it remain weakly attached to the reacting glass surface and eventually provide a barrier to mass transport, or will it spall from the glass surface and be available for transport as colloidal material? If spallation does occur, how will the glass reaction continue? Will other secondary phases form as the solution becomes concentrated in leached glass components, thus changing the affinity for reaction? The answer to these questions is best addressed by performing experiments of longer duration or under conditions that accelerate the reaction process. Such data are necessary for the eventual validation of the modeling approach being taken by the YMP.

6. Natural Analogs (J. J. Mazer)

The reaction of naturally occurring rhyolitic glass (obsidian) with water under conditions where the SA/V ratio is large (i.e., reaction in water vapor) has been identified as a system with a relatively simple reaction mechanism, molecular water diffusion. A detailed study of this reaction process has been undertaken to assist in understanding more complicated reaction mechanisms for nuclear waste glasses. Although obsidians are enriched in silica and depleted in alkalis and boron, relative to nuclear waste glass compositions, their survival in nature for extensive periods of time (up to millions of years) can offer insights into the long-term corrosion of glass in a geologic setting.

A number of different obsidians and one tektite glass were hydrated in vapor between 100 and 230°C for up to 256 days at relative humidities (RH) of 60, 90, 95, and 100%. Reaction progress was monitored by noting the growth rate of the birefringent hydration layer, thought to be caused by the formation of a strained glass network as molecular water diffuses into the glass. In all cases the rate of growth was proportional to the square root of time, a dependence consistent with a diffusion process. We previously reported results demonstrating that the hydration rate for obsidian is significantly affected by relative humidity, an effect previously believed to be negligible.²⁶

Further investigations are being pursued to characterize the strong dependence of the isothermal hydration rate for obsidian on the obsidian composition, specifically, the intrinsic water content (Fig. III-5). Our correlation between intrinsic water content and hydration rate (correlation coefficient of 0.96) is superior to that obtained with previously proposed models.^{27,28} Moreover, the temperature dependence of obsidian hydration rates conforms to an Arrhenius relationship in which the activation energy strongly depends on the intrinsic water content (Fig. III-6).

Fig. III-5. Relationship between Intrinsic Water Content and Diffusion Coefficients at 160°C. The equation of the linear regression fit to the data is $y = 1.537 + 1.01x$, where the correlation coefficient is 0.96.

Fig. III-6. Measured Activation Energies of Hydration for Eleven Obsidians and One Tektite Glass as Function of Logarithm of Intrinsic Water Content. The equation of the linear regression fit to the data is $y = 82.70 - 8.428x$, where the correlation coefficient is 0.95.

As a test of our model, we also considered the experimental hydration of tektite. Tektite is a natural glass, somewhat similar in composition to obsidian, but containing a very small (~ 0.01 wt %) amount of water. The tektite data are consistent with intrinsic water content control of the diffusion process, whereas the other compositional models could not successfully incorporate these tektite values.

These results suggest that obsidian hydration dating,^{29,30} a chronometric tool utilized extensively by archaeologists, has the potential to be accurately calibrated. The technique currently relies on experimental determinations of the activation energy of hydration for each obsidian being studied. Our results will allow researchers, knowing only the intrinsic water content, to estimate the ages of obsidian artifacts or features. Furthermore, better age estimates will result when the effects of RH are taken into account.

Additional experiments with high-water-content obsidians have confirmed our preliminary findings that the isothermal hydration rate of obsidian depends on the obsidian composition, specifically, the intrinsic water content. Our experimental results at 400-1000°C and those from studies of molecular water diffusion in rhyolitic glasses and melts at 400-1000°C suggest that this effect is pervasive over a large temperature range (Fig. II-7). The discovery of a concentration dependence for molecular water diffusion in obsidian at low temperatures may be useful for researchers trying to understand this process at higher temperatures. We are trying to apply these results to improving our understanding of molecular water diffusion in nuclear waste glasses.

Fig. III-7. Temperature Dependence of Some Water Diffusion Coefficients (D_w) Measured for Rhyolitic Glasses

Open Circles:	Red Hill Obsidian, This Study
Open Squares:	Antelope Wells Obsidian, This Study
Open Diamonds:	Indochinite Tektite, This Study
Filled Squares:	Rhyolitic Glass, Ref. 31
Filled Circles:	Rhyolitic Glass, Ref. 32

B. Glass Studies for Yucca Mountain Project

The Yucca Mountain Project (YMP) is investigating the tuff beds of Yucca Mountain, Nevada, as a potential location for a high-level radioactive waste repository. As part of the waste package development portion of this project, which is directed by Lawrence Livermore National Laboratory (LLNL), work is being performed at CMT to study the behavior of the waste form under anticipated repository conditions. Work includes (1) development and performance of a test to measure waste form behavior in unsaturated conditions, (2) performance of experiments to study the behavior of waste package components in an irradiated environment, (3) development of test methods to study the reaction of glass in water vapor and, subsequently, in liquid water, (4) development of static leaching tests to provide long-term release data to the glass modeling effort, and (5) detailed characterization of reacted glass surfaces.

1. Tests with Unsaturated Test Method (J. K. Bates and T. J. Gerding)

The YMP Unsaturated Test Method (see ANL-91/26, pp. 188-189) is being used in the N2 and N3 test series, which are being conducted with actinide-doped glasses. Because of the alpha decay of the predominant radionuclides, these tests can be conducted in a contained area but without shielding. Since the N4 test series will be conducted with "fully" radioactive sludge-based glass, modifications to the test method will have to be made. These tests will be performed as part of the EM program (see Sec. III.A.2).

a. N2 Unsaturated Tests

The N2 continuing tests (SRL 165 glass) have been completed through the 234-week sampling period. All the batch tests have been completed, and three continuous tests and one blank test are ongoing with samplings at yearly intervals.

b. N3 Unsaturated Tests

The N3 Unsaturated Test uses ATM-10 glass (simulated West Valley glass containing actinides plus ^{99}Tc) that was received from the Materials Characterization Center (MCC) and remelted to obtain the required form of the glass. This ongoing test was started July 6, 1987, according to the Unsaturated Test Method, and has been completed through the 219-week sampling period.

2. Parametric Experiments (A. B. Woodland)

Because the Unsaturated Test Method rigidly sets many of the test parameters, the effect that each parameter may have on the final radionuclide release needs to be studied. This is being done in parametric experiments. A description, purpose, and status of the parametric experiments in progress were given in detail in the previous semiannual (ANL-91/42, Sec. III.A.2). The experiments are continuing as scheduled. A topical report describing the results of all of the parametric experiments is being written.

3. Leach Experiments (W. L. Ebert)

The goal of the YMP Glass Task is to develop a methodology that will predict the performance of glass waste forms over the 10,000-yr service life of the repository under likely

environmental conditions. The approach taken is to generate a computer code which can be used to simulate the behavior of various waste glass compositions over very long time periods under a wide range of environmental conditions. Experiments in support of the simulation effort are designed to characterize the glass reaction and derive a reaction algorithm for computer simulation. Experiments are also performed to determine the influence of various environmental parameters on the glass reaction. These experiments are not designed to simulate the repository, and the results are not intended to be extrapolated to long times.

This section presents an interpretation of the results from a set of static leach experiments. The experimental results are then compared to the model currently used in long-term simulations of the glass reaction. Both leachate and solids analyses are utilized in describing the experimental results in terms of an overall glass reaction scheme.

The experiments were performed at ANL as a part of a three-year study on the effects of penetrating gamma radiation on the reaction of SRL 165-type glass. Only the results of nonirradiated experiments are discussed here. The complete results and experimental details are given by Ebert.²² Briefly, SRL 165 glass was reacted with J-13 groundwater at 90°C in 304L stainless steel vessels for 14 to 280 days at an SA/V of about 30 m⁻¹. Both the leachates and the reacted glass were analyzed to assess the extent and nature of the reaction. Recent analysis using AEM has permitted a more detailed description of the reaction process to be proposed.

Our description of the glass reaction is compared with the model used in the EQ3/6 simulation³³ for glass reaction because (1) experiments such as the type reported here were used to establish the model, and (2) any results generated by these experiments will be used to "fine tune" (or disqualify) the model. The primary use of these experiments and the following interpretation is to better define parameters utilized in the simulation.

The discussion below is presented in two subsections. First, selected experimental results are presented, and the reaction path of the glass is inferred. Then, the model from the EQ3/6 simulation is compared with the reaction path suggested by the experiments.

a. Experimental Results

(1) Leachate Results

The leachates were analyzed to determine pH, as well as the content of selected anions and cations. The leachate solutions were not filtered prior to analysis (except specific aliquots taken for actinide analysis) and so include both dissolved and suspended material. The leachate was acidified while still in the vessels. Thus, any material sorbed to the steel vessel walls was included in the leachate analyses. The values presented, therefore, include all material removed from the glass and provide a good measure of the extent of glass reaction. The normalized elemental mass losses, NL(i), of several species are shown plotted against the reaction time in Fig. III-8. The values plotted have been corrected for background levels as determined by earlier blank tests.²²

The release of species follows one of two trends. The curves for release of highly soluble species like the alkali metals and boron are approximately parabolic throughout the test period. Other species, such as Si and U, are released at a rate similar to the alkali metals through 56 or 91 days, but then level off to nearly constant values at longer reaction times. Species with low solubilities, such as Al and Fe, are not released to solution in significant amounts throughout the test

period. The leachate pH was about 9 for the nonirradiated experiments at all times tested beyond 28 days. The solubility limits for most metals are low under such alkaline conditions.

Fig. III-8. Normalized Elemental Mass Loss of (a) Li, Na, and B, (b) Si, U, and Mg vs. Reaction Time for SRL 165 Glasses

(2) Glass Results

The reacted solids were analyzed using secondary ion mass spectrometry (SIMS) in a depth-profiling mode. Mass spectra between $m/e = 1$ and 75 were periodically collected as the sample was sputtered to generate signal vs. time profiles. The depths of the craters of several analyzed samples were measured with a profile meter to determine the sputter rate as depth/sputter time, and the profiles are presented as signal vs. depth. Representative profiles for a sample reacted 180 days are given in Fig. III-9 for Li, Na, B, and Mg. Other profiles are included in Ebert.²² The outer 1 μm of the glass is depleted in alkali metals and boron and enriched in Mg compared to the unreacted glass. This is consistent with the leachate results. The Li, Na, and B releases result in smooth, diffusion-like profiles. The observation that the outer $\sim 0.5 \mu\text{m}$ of the layer has a constant low concentration of Li, Na, and B indicates that the layer does not impede the release of these species. The diffusional appearance of the

inner $\sim 0.5 \mu\text{m}$ of the $1 \mu\text{m}$ layer may be due to atomic mixing or roughness rather than a true diffusional distribution of these species. The region of composition change is referred to as the "reaction" or "alteration layer." The outer $\sim 0.5 \mu\text{m}$ of the layer is seen to have a greater enrichment of magnesium than the inner part. Coupled with the solution results, this suggests that magnesium is partly released to solution and partly retained in the layer early in the reaction. Later in the reaction, magnesium is removed from solution and reenters the outer half of the layer.

Fig. III-9. Secondary Ion Mass Spectrometry of Sample Reacted 180 Days for (a) Li and Na and (b) B and Mg

Resonant nuclear reaction spectroscopy (RNRS) for hydrogen was performed on some samples. Figure III-10 shows a typical profile for a sample reacted 180 days. Hydrogen is seen to be enriched in the outer $1 \mu\text{m}$ of the sample, consistent with the depth of alkali depletion. The profile within the layer is somewhat complicated. The outermost surface has a large hydrogen peak. This is thought to be water condensed on the sample surface during analysis. (The sample is cooled to liquid

nitrogen temperature during analysis and so acts like a cold finger in the vacuum chamber.) The outer $\sim 0.5 \mu\text{m}$ of the layer has a lower hydrogen level than the inner $\sim 0.5 \mu\text{m}$ of the layer. This finding could be due to a greater extent of dehydration of the layer either after the sample was removed from the leachate or when it was placed in the vacuum chamber for RNRS. This finding could also be due to the layer having different structural water content on the inner and outer parts. The depth axis on the figure was calculated from the theoretical stopping power of the layer and is only approximate.

Fig. III-10. Resonant Nuclear Reaction Spectroscopy for Hydrogen in Sample Reacted for 180 Days

Scanning electron microscopy (SEM) showed the glass surface to progress from an initially smooth appearance (on the scale of a few micrometers) to a nodular appearance, with the nodes being a few tenths of a micrometer across. Samples reacted for 180 or 270 days sometimes had regions with a "house of cards" appearance typical of clay minerals.

Several very small features were detected on the outer surfaces of some samples that were rich in Al, Ca, Si, or U; however, they were too small to identify.

The reacted layers were readily distinguished from the underlying unreacted glass in SEM analysis of cross-sectioned samples. The altered layers were more electron dense than the glass and had a less homogeneous appearance. The layers on the free surfaces of the 180- and 278-day samples were separated from the glass by a thin band of mounting resin. This volume was probably filled with fluid during the reaction.

Several cracks in the original sample had reacted to produce altered layers within the cracks. These layers were likewise separated from the glass by mounting resin. A bright rib was seen in the center of the layer in the crack. A SIMS analysis showed an iron-rich band to form in the center of the layer on the free surface as well, although the band was not readily seen in the SEM analysis. The bright rib in the layer in the crack is probably iron-rich.

Figure III-4 shows high-resolution images of the layers from samples reacted 56, 91, and 278 days. These micrographs clearly show the progression of the layer development from an amorphous, homogeneous, gel-type structure to a crystallized, heterogeneous clay layer. After 56 days, the layer is distinct from the glass and has an amorphous appearance. A few lattice fringes exist in the outer half of the layer, but the layer is predominantly amorphous. The segregation of iron to the center of the layer to form an iron-rich rib appears to have occurred as the outer layer crystallized after about 91 days. The altered layers outside and inside this band are structurally distinct. The inside layer looks very much like the gel layer seen after 56 days of reaction, while the layer outside the iron band is highly structured and crystalline. Electron diffraction produces good crystalline diffraction patterns, and lattice fringes are abundant in the image of the outer layer. Notice that the entire layer is separating from the glass, and that most of the inner layer material is attached to the iron band but some is still attached to the glass.

After 280 days of reaction, the inner layer has crystallized, and the layer has completely separated from the glass. No inner layer material is found attached to the glass after 278 days. The layer outside the iron band has not changed in appearance from 91 days.

Energy dispersive X-ray spectroscopy (EDS) of the different layers showed that compositional changes occur with the observed structural changes. Table III-4 gives the layer compositions of the 56-day gel layer, the inner and outer layers at 91 and 278 days, and the unreacted glass (normalized to 100% cations). The iron-rich rib was excluded from the analyses. Note the similarities in cation weight percents between the unreacted glass, the gel layer at 56 days, and the inner layer at 91 days. Similarity is also seen in cation weight percent between the outer layer at 91 days and both layers at 278 days. Formation of the crystallized layer from the gel results in an enrichment of Mg, Al, Mn, Fe, and Ni and a depletion of Si and Ca relative to the original glass. Other elements, such as the alkali metals, B, and U, are not present in either the gel or the layer. Recall that SEM analysis of the surface was used to detect small precipitates rich in Al, Si, Ca, and U, although they were too small to further identify. This is consistent with the expulsion of the elements from the gel as the layer crystallized. The limited solubilities of these species resulted in additional secondary phases being formed.

Table III-4. Cation Weight Percent Measured with EDS for Unreacted Glass, the Layer Formed at 56 days, and the Inner and Outer Layers Formed after 91 and 278 Days of Reaction

Cation	Unreacted	56 days	91 days		278 days	
			Inner	Outer	Inner	Outer
Mg	1.0	-	0.4	2.1	3.4	3.7
Al	5.5	8.2	12.5	13.4	14.9	15.7
Si	63.1	45.5	51.4	41.8	40.4	40.2
Ca	2.9	2.8	2.8	0.2	0.2	0.1
Ti	0.2	0.3	0.1	-	-	-
Mn	4.5	1.1	5.2	8.6	8.8	8.9
Fe	20.9	41.9	25.9	29.5	28.8	28.2
Ni	1.7	0.1	1.4	4.3	3.2	3.2

(3) Model

The above analyses allow a model for glass reaction under unsaturated conditions to be proposed. Figure III-11 shows the layers formed after 56 and 280 days in schematic cross section with representative release of alkali metals and B, Si, and Fe. After 56 days, a mostly amorphous gel-like layer is observed on the surface. This layer is highly depleted in alkali metals and boron. The alkali metals and boron must, therefore, be released at the glass/gel interface. The alkali metals and boron had to be released from about a 1 μm depth to generate the measured solution concentrations. Since the measured gel depth is only about 0.2 μm , the observed surface must have retreated from the original surface by about 0.8 μm . The measured silicon content in the gel is about 25% less than that in unreacted glass (see Table III-4). This suggests that silicon is released primarily from the gel/solution interface and partially throughout the gel. The measured solution concentration of silicon is consistent with the total dissolution of the glass to a depth of about 0.8 μm . Transition metals such as iron have very low solubilities under the alkaline pH conditions attained during these tests. Iron, therefore, remains as insoluble residue within the gel layer as the silicon framework dissolves and the surface retreats. The gel layer becomes highly enriched in insoluble metals such as iron. These species are evenly distributed throughout the gel layer.

Doped actinide elements behave as follows. Uranium and neptunium have relatively high solubility limits and are released into solution. The gel layer is depleted in both U and Np. Plutonium is neither depleted nor enriched in the gel, has a low solubility limit under high pH conditions, and has a low measured solution concentration in these tests. Moreover, plutonium is found sorbed onto the stainless steel vessel walls. Americium is found in small quantities on the vessel walls but primarily remains in the gel layer as insoluble residue.

Between 56 and 278 days, the gel layer becomes transformed into clay laths. Small areas of crystallized clay occur in the outer half of the gel layer after 56 days of reaction. The outer portion of the layer crystallizes before the inner layer because the silica network is more completely disintegrated in the outer portions of the layer. As the gel crystallizes, some species are expelled from the layer, for example, Ca and Fe, while others are incorporated from solution, for example, Mg. The iron migrates away from the solution into the center of the layer, where the silicon network has not completely disintegrated. The iron does not redistribute in the inner layer, which has not yet crystallized.

As the reaction continues, the inner layer eventually crystallizes. Iron excluded from the inner layer migrates to the center of the layer to complete the formation of the iron rib.

After 278 days the entire layer crystallizes into a clay phase(s) which is in near-equilibrium with the leachate solution. The composition of the clay layer indicates those species which have their solubility limits determined by the clay phase(s). These species include Si, Al, Fe, Mg, and others given in Table III-4. At 91 days and beyond, when the layer begins to crystallize, the solution concentration of silicon is nearly constant. Other species, such as Fe and Al, maintain low solubilities throughout the reaction. Magnesium, which has a high solubility limit and releases into solution prior to clay formation, is removed from solution as the clay forms. This was seen in the analyses of the layer (Table III-4) and the leachate.

While the leachate is in near-equilibrium with the layer, it is not in equilibrium with the glass, which continues to react, albeit at a low rate. Alkali metals and boron continue to be released from the glass surface unimpeded by the layer, which is now completely separated from the glass. Leachate can now attack the exposed glass beneath the layer. The layer offers no deterrence to either incoming water or released species. Species such as Si, Al, and Fe, which are components of the

Fig. III-11. Schematic View of Cross Section Indicating Elemental Release Trends at (a) 56 Days and (b) 280 Days

layer, are released from the glass and nucleate as additional clay on the layer, and the layer grows as the glass dissolves. Other species released from the glass which are not a part of the layer, such as Ca and U, may form other secondary phases as their solubility limits in the solution are reached.

(4) Kinetics

The extent of the glass reaction may be measured by using the solution concentrations of various species or measuring the amount of selected secondary phases formed (i.e., the layer thickness). Obviously, the selected means of monitoring the reaction must be related to the true reaction progress. The solution concentrations of highly soluble species, such as the alkali metals or boron, are frequently used to monitor the reaction progress. These species often have the advantage of not being incorporated into secondary phases; thus, the amount released from the glass is the same as that measured in the solution. Other species, such as silicon, may be released partially into solution and partially into a secondary solid. Thus, the solution concentration of silicon will not accurately reflect the amount of glass reacted.

Once a secondary phase is formed, the solution concentrations of species in that phase become constant, and species released from the glass subsequent to phase formation are totally incorporated into the solid phase. The layer thickness can be used as a measure of the extent of reaction beyond about 91 days, because the amount of silicon released as the glass reacts is equal to the amount of silicon that goes into the layer while the solution concentration of silicon remains constant. Therefore, the increase in the layer thickness is proportional to the amount of glass dissolved.

b. Computer Modeling with EQ3/6 Code

(1) EQ3/6 Simulation

The EQ3/6 computer code is being used by the YMP Glass Task to simulate the long-term reaction of glass under various possible repository environments. A brief discussion of the simulation technique will simplify discussions relating the experimental results and above reaction model to the computer simulations. The computer code requires the glass and leachant solution compositions to be defined. A small amount of glass is then added stoichiometrically to the leachant by the EQ6 part of the simulation. In the EQ3 part of the simulation, this solution is then equilibrated by use of a large data base of minerals and other stable phases. If the solubility product of a phase in the data base is exceeded in the solution, then that phase is generated by the simulation, and the solution composition is adjusted until the equilibrium is reached. Other secondary phases may likewise be formed until the data base and the adjusted solution are in equilibrium. The equilibrated solution then influences the subsequent addition of glass to the leachate and the process is repeated. This is the kinetic part of the EQ6 portion of the code.

Experiments are needed to support the kinetics of glass dissolution in the EQ6 code and the thermodynamics (i.e., the solubility products) of secondary phases in the EQ3 code. Although precipitation kinetics are not formally included in the EQ3/6 code, phases with known slow kinetics such as quartz are removed from the data base. In lieu of including precipitation kinetics, experiments are needed to identify which phases preferentially form and must be included in the data base.

layer, are released from the glass and nucleate as additional clay on the layer, and the layer grows as the glass dissolves. Other species released from the glass which are not a part of the layer, such as Ca and U, may form other secondary phases as their solubility limits in the solution are reached.

(4) Kinetics

The extent of the glass reaction may be measured by using the solution concentrations of various species or measuring the amount of selected secondary phases formed (i.e., the layer thickness). Obviously, the selected means of monitoring the reaction must be related to the true reaction progress. The solution concentrations of highly soluble species, such as the alkali metals or boron, are frequently used to monitor the reaction progress. These species often have the advantage of not being incorporated into secondary phases; thus, the amount released from the glass is the same as that measured in the solution. Other species, such as silicon, may be released partially into solution and partially into a secondary solid. Thus, the solution concentration of silicon will not accurately reflect the amount of glass reacted.

Once a secondary phase is formed, the solution concentrations of species in that phase become constant, and species released from the glass subsequent to phase formation are totally incorporated into the solid phase. The layer thickness can be used as a measure of the extent of reaction beyond about 91 days, because the amount of silicon released as the glass reacts is equal to the amount of silicon that goes into the layer while the solution concentration of silicon remains constant. Therefore, the increase in the layer thickness is proportional to the amount of glass dissolved.

b. Computer Modeling with EQ3/6 Code

(1) EQ3/6 Simulation

The EQ3/6 computer code is being used by the YMP Glass Task to simulate the long-term reaction of glass under various possible repository environments. A brief discussion of the simulation technique will simplify discussions relating the experimental results and above reaction model to the computer simulations. The computer code requires the glass and leachant solution compositions to be defined. A small amount of glass is then added stoichiometrically to the leachant by the EQ6 part of the simulation. In the EQ3 part of the simulation, this solution is then equilibrated by use of a large data base of minerals and other stable phases. If the solubility product of a phase in the data base is exceeded in the solution, then that phase is generated by the simulation, and the solution composition is adjusted until the equilibrium is reached. Other secondary phases may likewise be formed until the data base and the adjusted solution are in equilibrium. The equilibrated solution then influences the subsequent addition of glass to the leachate and the process is repeated. This is the kinetic part of the EQ6 portion of the code.

Experiments are needed to support the kinetics of glass dissolution in the EQ6 code and the thermodynamics (i.e., the solubility products) of secondary phases in the EQ3 code. Although precipitation kinetics are not formally included in the EQ3/6 code, phases with known slow kinetics such as quartz are removed from the data base. In lieu of including precipitation kinetics, experiments are needed to identify which phases preferentially form and must be included in the data base.

(2) EQ6 Kinetics

The algorithm describing the glass dissolution in the EQ6 code is similar to that used for mineral dissolution. Equation III-3 gives the rate of release of glass into solution according to the equation currently used in EQ6:

$$\frac{dn}{dt} = SA (H^+)^h k_{\text{glass}} \left[1 - \frac{Q_{\text{soln}}}{K_{\text{glass}}} \right] \quad (\text{III-3})$$

where n is the amount of glass dissolved, t is time, SA is the surface area of the glass available for reaction, (H^+) is the hydrogen ion activity and h the order, and k_{glass} is the rate coefficient for glass dissolution. The term in parentheses on the far right-hand side is the affinity for reaction, which is a measure of how far the reaction is from equilibrium. It is expressed here in terms of the solution composition, where K_{glass} represents the solubility product of the glass, and Q_{soln} is the solution activity product of those species included in K_{glass} . Not all species in the glass contribute to K_{glass} . Experiments have shown K_{glass} to be dominated by the activity of silica, and several models represent K_{glass} by the solubility product of amorphous silica as a first-order approximation. The YMP Glass Task is refining the definition of K_{glass} to better model the reaction.

The form of Eq. III-3 shows two limits of the glass reaction rate. Under highly dilute conditions, $Q_{\text{soln}} \rightarrow 0$, and the term in parentheses thus goes to 1. The reaction then proceeds at a maximum rate of $SA(H^+)^h k_{\text{glass}}$, which is a (weak) function of the glass composition through the rate coefficient term. Experiments are in progress to directly measure K_{glass} under highly dilute conditions. Under high solution concentrations, $Q_{\text{soln}} \rightarrow K_{\text{glass}}$, and the term in parentheses goes to zero. The reaction then approaches apparent equilibrium and the rate goes to zero. In reality, the substitution of K_{glass} for the solubility product term in Eq. III-3 is only approximate, and a very low residual rate of reaction is maintained until all the glass has reacted. This rate is often too low to measure experimentally.

When precipitates form in the EQ3/6 simulation, solubility limits are set for species incorporated in those phases. If a precipitate forms which incorporates a species that is included in the K_{glass} term, then Eq. III-3 will be affected through the Q_{soln} term. If Q_{soln} is limited by precipitates to a maximum value that is (necessarily) less than K_{glass} , then a minimum reaction rate is attained, which is greater than the residual rate when $Q_{\text{soln}} = K_{\text{glass}}$. If the layer seen to form on the samples discussed previously represents the assemblage of phases which contain all species relevant to the K_{glass} term, then $Q_{\text{soln}} = K_{\text{layer}}$ after 278 days, where K_{layer} is the solubility product of the layer at equilibrium.

The model in the EQ3/6 simulation, therefore, predicts that the glass reacts at a constant rate after the layer forms, where

$$\frac{dn}{dt} = SA (H^+)^h k_{\text{glass}} \left[1 - \frac{K_{\text{layer}}}{K_{\text{glass}}} \right] \quad (\text{III-4})$$

The model also predicts those species included in K_{layer} to have constant solution concentrations after the layer has formed.

The glass behavior as described by the model is shown schematically in Fig. III-12. This figure shows a schematic plot of the amount of glass that has been reacted or is in solution vs. time up to and including layer formation. The thin solid curve represents the reaction without precipitate (layer) formation according to Eq. III-3. The solution composition approaches the value of K_{glass} in this case. When precipitates (layer) form, the reaction rate becomes constant (Eq. III-4), as shown by the dashed line, and the solution composition becomes constant, as shown by the dotted line.

Fig. III-12. Schematic Plot of Glass Dissolution Kinetics with Precipitate Formation

The test results can be compared to the predictions of the model. The test results discussed in Sec. III.B.3.a are consistent with the model but do not sufficiently validate it. As predicted by the model, the silicon concentration in solution becomes constant after about 91 days. The magnesium concentration also becomes constant. Other species in the layer, such as Al and Fe, have nearly constant solution concentrations throughout the reaction times tested.

The Li, B, and Na solution concentrations are plotted vs. the square root of time in Fig. III-13, and the measured layer thickness vs. reaction time is shown in Fig. III-14. This is done for convenience and is not meant to suggest a release mechanism. The effect of precipitate formation on the glass reaction rate is predicted to accelerate the rate relative to the rate in Eq. III-3. The NL(i) values of the alkali metals and boron are expected to deviate positively from the $t^{1/2}$ plots beyond about 91 days. The data in Fig. III-13 do not show such deviation beyond the experimental error.

Likewise, the model predicts that the layer will grow at a constant rate (assuming the density remains constant). The measured rate of layer growth between 56 and 280 days may be linear but is better represented by parabolic growth (see Fig. III-14). Clearly, longer term data are needed to verify the model predictions.

(3) Tests at High SA/V

Instead of performing long-term experiments at low SA/V ratios for model verification, short-term tests at high SA/V ratios may be used to attain concentrated solutions and subsequent precipitate formation. We have performed tests in vapor at high temperatures (up to 240°C) which attain SA/V ratios in excess of 4000 m⁻¹. These tests are useful in identifying secondary phases

Fig. III-13. Normalized Elemental Mass Loss of B, Li, and Na vs. Square Root of the Reaction Time

Fig. III-14. Measured Layer Thickness vs. Reaction Time

which form on different glass compositions and also in identifying reaction trends. The extent of glass reaction is significantly greater after secondary phases form. Whereas layers are typically a few tens of micrometers thick in low SA/V tests at elevated temperatures, they may be several hundred micrometers thick in high SA/V tests at equivalent reaction times. Prior to secondary phase formation, the layers at high SA/V are immeasurably thin ($<0.1 \mu\text{m}$). In most cases the layer growth at high SA/V is linear with time after precipitates form. While tests in vapor at high temperatures may not be directly comparable to the tests at 90°C and $\text{SA/V}=30 \text{ m}^{-1}$ discussed in this report, they provide valuable evidence that the reaction rate changes upon secondary phase formation, and that the rate of glass reaction increases, as predicted by the model.

C. Radiation Effects Studies for Yucca Mountain Project
(D. T. Reed)

The YMP is investigating the feasibility of locating a nuclear high-level waste repository in the tuff formations in southern Nevada. The placement of high-level waste containers in the underground facility will perturb the pre-emplacment environment by raising the ambient temperature and exposing the environment to gamma radiation levels that initially may be greater than 0.1 Mrad/h. Determining the effects of temperature and radiation level on the gaseous/aqueous environment of the waste package is important to characterizing the performance of the high-level waste package during the containment period of repository history. An important radiolytic concern is container metal performance in the expected irradiated system. This was preliminarily characterized for the three copper-based materials being considered by the YMP. Emphasis was on investigating corrosion uniformity, corrosion product formation, and the existence of localized corrosion.

1. Background

Oxygen-free copper (CDA-102), 70/30 copper-nickel (CDA-715), and aluminum bronze (CDA-613) are being evaluated by the YMP as candidate materials for the construction of the high-level nuclear waste container in the mined geologic disposal system. After emplacement, the container will be subjected to an irradiated air-steam environment at elevated temperatures. General atmospheric corrosion and, in particular, the relationship between the radiolytic environment and the type and extent of corrosion observed are important aspects in evaluating the long-term performance of these materials in the proposed repository.

The atmospheric corrosion of copper-based alloys has been relatively well established in nonirradiated systems.^{34,35} Exposure to atmospheric conditions results in the following: initially a brown film, presumably cuprite (Cu_2O), forms, followed by a dull black film, presumably tenorite (CuO), which in time will form a patina that can vary in color depending on the presence of other species in the gas phase. In low RH systems, corrosion rates are low, ranging from 0.04 to 0.18 mg/cm²/yr. The rates obtained strongly depend on the RH and the presence of anionic species, such as chloride and sulfide in the gas phase.

In irradiated systems, however, much less is known about the corrosion behavior of copper-based alloys. Existing information about the nature of the phases generated in irradiated moist-air systems is summarized in Ref. 36. Some work has already been done in connection with the high-level waste effort^{37,38} and nuclear-related research.³⁹ Our work³⁶ established that the irradiated moist-air environment can, under some conditions, be very corrosive toward copper-based materials. Nitrogen oxides and nitric acid are generated in the gas phase due to radiolysis and form copper nitrate phases, which are associated with the formation of pits in copper-nickel alloy and oxygen-free copper. To further characterize the behavior of copper-based materials in irradiated moist-air systems, we undertook a series of experiments designed to establish (1) the nature of the corrosion products generated and (2) the initial corrosion rates in an irradiated moist-air environment.

2. Experimental

The copper-based materials used in the experiments were purchased commercially by the YMP. These were originally obtained to perform stress corrosion experiments. For our experiments, they were cut into 0.2 x 1 x 2 cm specimens. These were subsequently polished to 600 grit, cleaned, thoroughly rinsed with high-purity water and air dried. After drying, they were weighed to an accuracy of ± 0.00002 g. Four coupons of a single material type (three types tested) were placed in 304L stainless

steel corrosion vessels. They were suspended by a Pyrex glass supporting rod and attached to this rod with stainless steel wire. The irradiation conditions of the experiments are given in Table III-5.

Following irradiation, the composition of the gas phase was reanalyzed for both the initial components and some of the expected radiolytic molecular products (carbon dioxide, carbon monoxide, nitrous oxide). Here CO and CO₂ are formed from reaction of oxygen with species on the vessel wall. Hydrogen and ammonia/NO_x analyses were also performed in some of the one-month experiments, but these species were not detected. After removal from the gamma facility, the vessels were disassembled and the coupons removed. The weights were redetermined to determine the change in weight due to exposure to the irradiated dry/moist air systems. All of the coupons were inspected using a 50X microscope for general appearance and evidence for localized corrosion. After visual inspection, three of the four coupons were then cleaned (rinsed in 10% HCl ultrasonically for 1 or 2 min) to remove the corrosion buildup on the surface of the metal. These were then air dried and reweighed to determine the weight change. Corrosion rates were calculated based on the weight difference between either (1) the initial and after-cleaning weight of the coupon or (2) the weight gain and after-cleaning weight of the coupon.

The fourth coupon was reserved for corrosion product analysis either directly with an X-ray diffractometer and/or by Debye-Scherrer analysis of the corrosion products alone. After surface analyses, these coupons were retained as a record of the general corrosion observed and for more extensive surface analyses should they be warranted.

Table III-5. Environmental and Irradiation Conditions for Radiation-Effect Experiments

Experiment Designation (AB-, CN-, or CU-) ^a	Environment	Duration, days	Dose Rate, Mrad/h	Absorbed Dose, Mrad
-1R-90M	94°C, 40% RH @ 90°C Air	35	0.021	17.4
-3R-90M	94°C, 40% RH @ 90°C Air	73	0.021	36.6
-3R-90D	94°C, Dry Air	75	0.021	37.6
-1R-150M	152°C, 40% RH @ 90°C Air	30	0.015	10.7
-3R-150M	152°C, 40% RH @ 90°C Air	76	0.011	20.0
-3R-150D	152°C, Dry Air	78	0.015	27.9

^aConditions same for all three copper-based materials, where AB=aluminum bronze, CN=copper nickel, CU=oxygen free copper.

3. Results and Discussion

The corrosion rates and corrosion products are given in Table III-6. These results are discussed below.

a. Effect of Ionizing Radiation on Gas Phase

The initial composition of the gas phase was air (21.1 mol% O₂, 78.9 mol% N₂, and <0.1 mol% CO₂) or air with approximately 30 mol% water vapor. Gamma irradiation resulted in the

formation of carbon dioxide, carbon monoxide, nitrous oxide, and nitrogen dioxide/nitric acid, as well as oxidizing products of water/oxygen (ozone, hydrogen peroxide, and the hydroxy and hydroperoxyl radicals).

In the 90°C experiments, significant amounts of carbon dioxide and carbon monoxide were generated due to reaction with carbonaceous species at the vessel wall. We typically observed an increase in the CO₂ content from <0.1 mol% to the range of 0.3 to 0.8 mol%. Carbon monoxide was also found, at levels of 0.03 to 0.1 mol%. The concentrations of both these species increased with absorbed dose and/or time.

Table III-6. Corrosion Rates and Corrosion Products for the Copper (CU), Copper-Nickel (CN), and Aluminum Bronze (AB) Experiments

Experiment Designation ^a	Corrosion Rate, mg/cm ² /yr	Corrosion Products ^b	
		Major	Minor
CU-1R-90M	1.5 ± 0.1	ND	
CU-3R-90M	0.56 ± 0.06	ND	
CU-3R-90D	0.14 ± 0.02	NA	
CU-1R-150M	2.6 ± 0.1	Cu ₂ O	CuO
CU-3R-150M	2.3 ± 0.1	Cu ₂ O	CuO
CU-3R-150D	1.6 ± 0.05	Cu ₂ O	CuO
CN-1R-90M	0.33 ± 0.05	Cu ₂ O (brown spots)	
CN-3R-90M	0.21 ± 0.03	NA	
CN-3R-90D	0.12 ± 0.04	NA	
CN-1R-150M	1.4 ± 0.1	Cu ₂ O	CuO
CN-3R-150M	1.1 ± 0.2	CuO	Cu ₂ O
CN-3R-150D	0.18 ± 0.04	CuO	Cu ₂ O
AB-1R-90M	0.71 ± 0.13	ND	
AB-3R-90M	0.23 ± 0.05	ND	
AB-3R-90D	0.16 ± 0.01	ND	
AB-1R-150M	3.0 ± 0.4	Cu ₂ O	CuO
AB-3R-150M	1.2 ± 0.2	CuO	Cu ₂ O
AB-3R-150D	0.89 ± 0.02	Cu ₂ O	CuO

^aSee Table III-5 for conditions.

^bND=none detected; NA=results not available yet.

Nitrous oxide was detected in all the final gas phase analyses performed. Concentrations ranged from trace amounts (0.002 mol%) in the one-month experiments to as high as 0.07 mol% in the 2.5-month experiments. This species is radiolytically generated from nitrogen dioxide; thus, its presence indicates that nitrogen dioxide, as well as nitric acid in the moist-air systems, was being generated. No nitric acid (as nitrate) was detected in the final gas phase. Greenish-white phases observed on the surface of some of the coupons were determined to be Cu₂(OH)₃NO₃,³⁹ indicating that NO_x, when formed, was reacting with the metal.

The nitrogen concentration in these experiments remained essentially constant over time, with nitrous oxide and NO_x/NH_3 as the most likely degradation products. Oxygen, by reaction with the metals present and conversion to carbon dioxide and carbon monoxide, was reduced in concentration by 3-4 mol%.

Similar trends were noted in the 150°C experiments. The extent of conversion of oxygen to carbon dioxide was, however, more extensive, with CO_2 buildup reaching as high as 3 mol%. Nitrous oxide yields were typically lower by a factor of two or more than those observed at 90°C, particularly in the case of the oxygen-free copper and copper-nickel alloy.

b. Corrosion of Oxygen-Free Copper

The extent of corrosion in the 90°C experiments with oxygen-free copper was relatively small, leading to significant scatter in the corrosion data obtained. The overall appearance of the test specimens was a dull and slightly darkened copper color. The extent of corrosion was too small to identify the corrosion products using X-ray diffraction (XRD) by the Debye-Scherrer method.

In the one-month experiment CU-1R-90M, several greenish white deposits were observed on the surface of the metal. This experiment had been held at room temperature for seven days before several types of analyses were performed on the gas phase. Similar phases, but to a lesser extent, were noted on the coupons from the longer-term experiments (CU-3R-90M and CU-3R-90D), although these were analyzed within 6 h of being removed from the gamma facility. These phases were taken to be evidence for the formation of copper nitrates on the metal surface since they were identical in appearance to phases we had analyzed in previous work. However, the corrosion product in these experiments were not formed in sufficient amounts to analyze directly.

The initial corrosion rate in the moist-air experiments at 90°C was $1.5 \pm 1 \text{ mg/cm}^2/\text{yr}$, decreasing to $0.56 \pm 0.06 \text{ mg/cm}^2/\text{yr}$ in the longer-term experiment. These data were, however, widely scattered due to the low extent of corrosion present. A rate of $0.14 \pm 0.02 \text{ mg/cm}^2/\text{yr}$ was noted in the dry-air experiment.

As expected, more extensive corrosion was observed at 150°C. In the 30-day moist-air experiment (CU-1R-150M), a green-brown tarnish covered the surface of the coupon. Cuprite was identified as the major corrosion product, with some tenorite also detected. In the two longer-term experiments (CU-3R-150M and CU-3R-150D), the cuprite remained as the major corrosion product, with tenorite present as a minor phase. The general appearance of the coupons in the moist-air experiments was brown with black patches. There was no evidence of the green-white surface deposits, noted in the 90°C experiments, for either of the moist-air experiments at 150°C. The coupons in the dry-air experiment had a black-colored scale that did not appear to be strongly adherent.

The corrosion rates obtained for the coupons in the 150°C experiments were more reproducible owing to the greater extent of mass loss that occurred. The corrosion rates were 2.6 ± 0.1 and $2.3 \pm 0.1 \text{ mg/cm}^2/\text{yr}$ in the 30 and 76 day moist-air experiments, corresponding to penetration rates of 2.9 and $2.6 \mu\text{m}/\text{yr}$, respectively. These rates are factors of two and four higher than those observed for the analogous moist-air experiments performed at 90°C. The extent of corrosion in the dry-air experiment was $1.6 \pm 0.05 \text{ mg/cm}^2/\text{yr}$ ($1.8 \mu\text{m}/\text{yr}$), which is comparable to, but lower than, those obtained in the moist-air experiments.

c. Corrosion of 70/30 Copper Nickel

At 90°C, the overall color of the copper-nickel coupons in the two moist-air experiments (CN-1R-90M and CN-3R-90M) was a dull bronze. Greenish-white phases surrounding a brown-colored center were noted on the surface of the coupons in both experiments. The brown center was identified as cuprite. The phases were on the coupon surface, with no significant pit formation evident. General corrosion rates were 0.33 ± 0.05 mg/cm²/yr in the 35-day experiment and 0.21 ± 0.03 mg/cm²/yr in the 73-day experiment.

In the dry-air experiment at 90°C (CN-3R-90D), the coupons were silver in color (original color of the metal), with only very light tarnishing evident. The corrosion rate was 0.12 ± 0.04 mg/cm²/yr and was a factor of two lower than that observed in the moist-air experiment. The extent of corrosion product formation in both the moist- and dry-air experiments was too small to analyze by XRD. The brownish phase present in the CN-1R-90M experiment was identified as cuprite.

Significantly more corrosion was evident at 150°C, resulting in gray-black coupons in the two moist-air experiments (CN-1R-150M and CN-3R-150M). A dark bronze color was also noted at 50X magnification in lighter areas on the surface, as were a few greenish-white specks. The coupons in the dry-air experiment (CN-1R-150D) were predominantly dark bronze in color, with some black patches also evident. The major corrosion product identified in the 35-day experiment was cuprite with some tenorite present. This was reversed in both the longer-term experiments performed.

In the moist-air experiment at 150°C for 35 days, the corrosion rate was 1.4 ± 0.07 mg/cm²/yr, which is a factor of four higher than that observed at 90°C. In the moist-air experiment at 150°C for 76 days, this rate decreased to 1.1 ± 0.2 mg/cm²/yr. These correspond to penetration rates of 1.6 and 1.3 μm/yr, respectively. In the dry-air experiment, the corrosion rate was 0.48 ± 0.4 mg/cm²/yr, which is a factor of 2.4 lower than that observed in the analogous moist-air experiment.

d. Corrosion of 7% Aluminum Bronze

At 90°C, the coupons from the two moist-air experiments (AB-1R-90M and AB-3R-90M) had a very light greenish tarnish but were mostly bronze in color. A few black patches were noted in the 73-day experiment. The extent of corrosion was not sufficient to analyze using XRD. The general appearance of the coupon in the dry-air experiment (AB-3R-90D) was similar but darker. At 50X magnification, a black phase with lighter patches that were more bronze in color (base metal) was noted. No evidence of localized corrosion was observed.

The corrosion rates were 0.71 ± 0.13 and 0.23 ± 0.05 mg/cm²/yr in the moist-air experiments for 35 and 73 days, respectively. Penetration rates were 0.9 and 0.3 μm/yr, respectively. The corrosion rate in the dry-air experiment was 0.16 ± 0.01 mg/cm²/yr, which is comparable to, but slightly lower than, that observed in the analogous moist-air experiment.

The extent of corrosion was again significantly higher in the 150°C experiments. The general appearance of the coupons in the two moist-air experiments was initially dark bronze to black and changed to a speckled dark black-green in the longer-term experiment. The predominant corrosion product was cuprite in the 30-day and tenorite in the 76-day experiment. The corrosion rates were 3.0 ± 0.4 mg/cm²/yr and 1.2 ± 0.15 mg/cm²/yr in the 30- and 76-day experiments, respectively. These were a factor of four higher than in the analogous experiments performed at 90°C.

In the dry-air experiment (AB-3R-150D), the coupon was black to dark gray. The major corrosion product was cuprite rather than tenorite, as was the case in the moist-air experiment. The corrosion rate was $0.89 \pm 0.02 \text{ mg/cm}^2/\text{yr}$, which is slightly lower than that observed in moist-air experiment and a factor of 5.5 higher than that observed at 90°C .

4. Conclusions

In nonirradiated systems, the atmospheric corrosion of metals is generally categorized into three distinct regimes with respect to relative humidity (low, intermediate, and vapor saturated). The low humidity regime is characterized by direct interaction of the gaseous species with the metal surface. Here, surface oxidation is the dominant process and the corrosion rates are usually quite low. In the intermediate humidity regime, a thin surface layer of water exists. The corrosion rate is substantially greater than in the low humidity regime, and trace constituents of the gas phase have a greater role in defining the nature of the corrosion observed since they can be concentrated in the thin film of water. In the high humidity regime, the general corrosion observed approaches that of aqueous systems.

In irradiated systems, the same corrosion regimes have also been observed. The relative humidity at which the transition between low and intermediate humidity regimes occurs is not as clear-cut, with values of 30% to 80% RH typically reported. This value is expected to depend on material and probably on the temperature and trace constituents present. In the irradiated moist-air system, the trace constituents of interest are the fixation products of nitrogen (NO_x and ammonia) and the oxidizing species that are generated as radiolytic products of water and oxygen (ozone, hydrogen peroxide, and the OH and HO_2 free radicals). Since the concentration of these species depends on both the dose rate and the absorbed dose, an added complexity in the irradiated system is the competition between the interaction of the radiolytic products generated and the general corrosion processes.

The moist-air experiments reported herein were performed in the low humidity regime (40% RH at 90°C and 0.06% RH at 150°C), although the water vapor content of the gas phase was 30 mol%. The general corrosion behavior was similar to that observed in nonirradiated systems in that cuprite and tenorite were the predominant corrosion products identified. In all cases, cuprite was the initial product observed, changing over to tenorite as increased oxidation occurred. This result is significantly different from what we previously observed at gamma dose rates that were effectively ten times higher. In the higher dose rate and total pressure experiments,³⁶ nitrate phases were the predominant corrosion products for both copper-nickel and aluminum bronze and appeared as a minor product on the oxygen-free copper.

The relative corrosion rates observed decreased in the order of copper > copper-nickel = aluminum bronze in the moist-air experiments at 90°C . This same order was noted in the moist-air experiments at 150°C . In the dry-air experiments, no consistent trend in corrosion was observed, with all three having nearly the same corrosion rate at 90°C and copper-nickel undergoing the least corrosion at 150°C .

The vast majority of data for copper-based materials relates their behavior in outdoor environments. Typical values for the atmospheric corrosion of copper-based materials subjected to long-term exposures of dry air (at ambient temperatures) are in the range of 0.04 to $0.18 \text{ mg/cm}^2/\text{yr}$.⁴⁰ Some data were, however, reported for oxygen-free copper in air-steam conditions in the same humidity regime as in our experiments. At 150°C ,³⁶ corrosion rates of 2.45, 1.39, and $0.88 \text{ } \mu\text{m/yr}$ were obtained for 1-, 4-, and 10-month exposure times, respectively. This compares to the 3.5 and $2.7 \text{ } \mu\text{m/yr}$ that we obtained in 1-month and 2.5-month experiments at the same temperature and a gamma dose rate of 0.02 Mrad/h .

Although some of the experimental methodology differed, there was a significant enhancement of corrosion (approximately a factor of 1.5) due to the gamma radiation present.

In our experiments, the total pressures of the dry- and moist-air experiments were approximately the same. The gas phases, however, differed in that water vapor replaced some of the air (particularly oxygen) as the source of oxidizing species. Radiolytically, only ozone, nitrogen fixation products, and associated transients were generated in the dry-air experiments. The presence of water vapor resulted in a partial replacement of these species with the OH and HO₂ free radicals, as well as molecular products such as hydrogen peroxide.

The effect of replacing air with water vapor can be evaluated, on a preliminary basis, by comparing the corrosion rates observed in the dry- and moist-air experiments. At 90°C and 150°C, corrosion rates were significantly lower in the dry-air experiments. Although further work is needed, this result is consistent with the more strongly oxidizing environment present when water vapor, rather than oxygen, is subjected to ionizing radiation.

D. Spent Fuel Studies for Yucca Mountain Project
(D. J. Wronkiewicz)

Experiments are continuing to investigate the reaction behavior of Zircaloy clad-UO₂ pellets exposed to dripping EJ-13 water in an oxidizing environment. These experiments employ Teflon support stands in a reaction vessel (see ANL-90/16, p. 194) and have been in operation for nearly 5.5 years. They are designed to develop procedures for tests to be conducted with spent fuel, identify secondary alteration phases, and describe parameters that control the release of uranium from the waste package assembly. All experiments are being conducted at 90°C and at variable SA/V ratios to simulate potential Yucca Mountain repository conditions.

Solution results from the Teflon-supported tests are characterized by a large pulse of uranium release from the samples between one and two years of reaction time. After this interval, the uranium release rates decrease (Fig. III-15), and the leachate solutions are characterized by depletions in alkali, alkaline earth, and silicon concentrations.

Optical microscopy, SEM/EDS, and XRD investigations of the altered UO_{2+x} surfaces indicate the early formation of several uranyl oxide hydrate phases (UOH) and uranyl silicates on the reacted surfaces. Included among these phases are dehydrated schoepite (UO₃•0.8H₂O), schoepite (UO₃•2H₂O), becquerelite (CaU₆O₁₉•10H₂O), compreignacite (K₂U₆O₁₉•11H₂O), and soddyite (U₅SiO₁₉•6H₂O). Several uranyl alkali silicates have also been detected on samples reacted for 3.5 years, including uranophane [Ca(UO₂)₂(SiO₃)₂(OH)₂•5H₂O], boltwoodite [K(H₃O)UO₂(SiO₄)•nH₂O], and sklodowskite [Mg(UO₂)₂(SiO₃)₂(OH)₂•5H₂O].

Mineral relationships observed during microscopic examinations suggest a paragenetic sequence where the UO₂ pellets are altered to UOH phases, followed closely by precipitation of soddyite, and finally the formation of alkali and alkaline earth uranyl silicates. This sequence is identical to that which is found in alteration rims on naturally occurring uraninite exposed to surficial weathering conditions.^{41,42} By contrast, this sequence is opposite to that predicted in initial attempts to model uraninite alteration using the EQ3/6 code.⁴³

Detailed surface examinations indicated that both the intergranular regions of the UO_{2+x} surface and tabular UOH crystals are dissolving after one year of reaction (Fig. III-16). Samples terminated after 1.5 years display surfaces that are so extensively corroded that the UO_{2+x} granules are nearly detached

from the sample surfaces. An abundance of fine-grained, uranium-rich particulate matter was also noted to occur across the pellet surfaces after 1.5 and 2.25 years of reaction (Fig. III-16F). The occurrence of these particulates, combined with the highly corroded sample surfaces, indicates that spallation of small particles from the UO_2 pellets is responsible for the rapid pulsed release of uranium that characterizes the reactions between one and two years. The rapid corrosion of the UO_{2+x} and/or UOH phases may, in turn, arise from one or more factors, including pH decreases, decreasing uranium solution concentrations, increasing temperatures (not tested for in the present experiments), and spontaneous dehydration of schoepite.

Fig. III-15. Selected Cumulative Release Patterns of Uranium from Experiments PMP8U-1 and -2. The rapid release period for uranium begins after approximately 40 weeks of reaction. Uranium release rates represent total uranium recovered after a 10-min acid strip of the accumulated leachate in the bottom of the test vessel.

E. Spectroscopic Investigation of Radionuclide Speciation (S. Okajima and D. T. Reed)

The hydrolysis of Pu(VI) at $\text{pH} = 1-7$ is being investigated with a combination of laser photoacoustic spectroscopy (LPAS) and UV-visible-IR absorption spectrometry. Emphasis is on the initial hydrolysis product obtained as a function of total plutonium concentration in noncomplexing media. This work is a continuation of past studies in which both laser-induced fluorescence and LPAS⁴⁴⁻⁴⁷ were used to investigate radionuclide speciation in groundwater-relevant systems. This work is performed as part of the Co-contaminants Chemistry Subprogram in support of the Subsurface Science Program within the Office of Health and Environmental Research.

1. Background

There has been recent interest in the environmental chemistry of plutonium because of its importance in waste management-related concerns. The role of Pu(VI) in the migration of plutonium in natural systems is, however, uncertain. Its high solubility in natural systems relative to Pu(IV) , combined

Fig. III-16. Scanning Electron Photomicrographs of UO_2 Pellet Stages. (A) unreacted UO_2 pellet surfaces showing unreacted pellet after 1.5 years of reaction exhibiting highly irregular intergrain boundary corrosion; (C) bottom surface of pellet exhibiting surface pitting, relatively minor intergrain corrosion; (D) granule surface where overlying grain has appeared; (E) becquerelite crystal showing evidence of extensive fine-grained particulate matter deposited on the surface; (F) schoepite crystals and underlying UO_{2+x} substrate. Acicular bundles of uranophane also are visible throughout the surface. Both uranophane and becquerelite have precipitated from the surface visible to the lower-left and lower-right corners of the image.

with the high mobility of U(VI) in natural systems, suggests that greater importance may need to be placed on its role. The chemistry of Pu(VI) is expected to be most important to modeling the release of plutonium at its source, and in environments such as near-surface groundwaters, where oxidizing conditions may exist.

The hydrolytic behavior of plutonyl is of importance to natural systems because many of these have a pH that is near-neutral or mildly alkaline. Polynuclear Pu(VI) species are readily formed and predominate at higher plutonium concentrations and pH. An unqualified determination, for this reason, of the 1:1 hydrolysis formation constant has not been made, and the initial hydrolytic product formed as a function of plutonium concentration is not clear.

2. Hydrolysis of Pu(VI) in Noncomplexing Media

The hydrolysis of Pu(VI) is being systematically investigated to (1) characterize the spectroscopic features associated with the various hydrolytic products formed and (2) more clearly establish the nature of the hydrolytic species generated and its dependence on temperature, the concentration of the plutonium present, and pH. This work is performed with noncomplexing media (0.1M sodium perchlorate) at constant ionic strength.

The systematic characterization of the spectroscopic features associated with the hydrolysis of Pu(VI) is the most important objective of this work. Such information will serve as the basis for undertaking experiments and interpreting results from spectroscopic studies of Pu(VI) speciation in more complex real groundwater systems and mixed organic-Pu(VI) systems. This will need to be done for each plutonium oxidation state considered.

The most important spectral features of the U-V-visible spectrum of the Pu(VI) aquo ion are the two sharp f-f electron transitions centered at 832 and 622 nm. Our work centered on the effect of hydrolysis on the absorption band located at 623 nm, even though its extinction coefficient is significantly lower, since the overall sensitivity with our LPAS system is greater in this wavelength region.

Before initiation of this effort, we had completed a preliminary characterization of the changes in absorption due to hydrolysis. It has been generally proposed in the literature, based on indirect potentiometric methods, that the initial hydrolysis product of Pu(VI) is the PuO_2OH^+ (1:1 complex) species. This, however, was not fully supported by the spectra that we observed. It was our hypothesis that the wide discrepancies reported (almost four orders of magnitude) for the formation constant of this species were, in part, due to an incorrect speciation assignment.

The general spectroscopic features associated with hydrolysis of Pu(VI) are shown in Fig. III-18 as a function of pH. We identified four spectroscopically distinct species in the 600-700 nm spectral region. These species, along with our current speciation assignments, are given in Table III-7.

a. Effect of Total Pu Concentration on Pu(VI) Spectra

The absorption spectrum of Pu(VI) was obtained as a function of pH at total plutonium concentrations of $1.2 \times 10^{-2}\text{M}$ (Fig. III-17). This extends past work, using indirect methods, to almost an order of magnitude lower concentration and covers the range of concentrations used by others to determine the formation constants reported for the PuO_2OH^+ hydrolytic species. The initial hydrolysis reactions, along with the equation defining each formation constant, are the following:

$$\beta_{11} = \frac{[\text{PuO}_2\text{OH}^+][\text{H}^+]}{[\text{PuO}_2^{2+}]} \quad (\text{III-5})$$

$$\beta_{22} = \frac{[(\text{PuO}_2\text{OH})_2^{2+}][\text{H}^+]^2}{[\text{PuO}_2^{2+}]^2} \quad (\text{III-6})$$

The formation constant for the 1:1 complex (Eq. III-5) does not have any second-order terms. Thus, when PuO_2^{2+} and PuO_2OH^+ are the only two plutonium species present, their relative concentration only depends on the pH. Spectra obtained at the same pH and different plutonium concentrations will, therefore, have a constant ratio for the optical density (OD) observed at 622 and 632 nm.

Table III-7. Assignments of Pu(VI) Absorption Bands and Probable Speciation

Species	Spectral Region, nm		
	600-750 nm	800-900 nm	>900 nm
PuO_2^{2+} (aquo ion)	622	833	952, 982
$(\text{PuO}_2\text{OH})_2^{2+}$ (2:2 complex)	632, 665	846	840-1000 ^a
$(\text{PuO}_2)_3(\text{OH})_5^+$ (3:5 character) ^b	638, 685	852	996
$\text{PuO}_2(\text{OH})_2$ (1:2 complex)	655, 715	870	1020

^aBroad multiple-band absorption.

^bThat is, co-existence of hydrolytic complexes and polymers ($\text{PuO}_2:\text{OH}$ ratio of 3:5) is suspected.

When a polynuclear species, such as the 2:2 complex, is formed, the ratio of the aquo ion and polynuclear complex present in solution will depend on the total concentration of plutonium present in solution. Spectra obtained at the same pH but different plutonium concentrations will, therefore, vary according to Eq. III-6. The distinction between polynuclear species and the 1:1 complex can be observed by simply comparing the absorption spectrum at different total plutonium concentrations.

The spectra of Pu(VI), at pH = 4.8, are shown in Fig. III-18 for 1.2×10^{-2} and Fig. III-19 for $6.9 \times 10^{-5}\text{M}$ plutonium. It is clear that the absorbance spectrum has changed significantly. The hydrolytic species corresponding to the 632 nm absorption band is, therefore, polynuclear rather than mononuclear.

Fig. III-17. Absorption Spectra of 0.0126M Pu(VI) in 0.1M Sodium Perchlorate Media at pH = 4.7, 5.2, and 6.9. These are offset to show spectra features.

Fig. III-18. Absorption Spectrum Observed at $1.2 \times 10^{-2} \text{ M}$ of Pu(VI) and pH = 4.8

Fig. III-19. Laser Photoacoustic Spectrum Observed at $6.9 \times 10^{-5} \text{M}$ of Pu(VI) and pH = 4.8

The relative concentrations of the aquo ion, 632 nm species, and 638 nm species (second hydrolysis product) are shown in Fig. III-20 at total plutonium concentrations of 1.2×10^{-2} , 1.6×10^{-4} , and $6.9 \times 10^{-5} \text{M}$. Two trends are evident in this figure. First, the onset of hydrolysis strongly depends on the total plutonium concentration. At $[\text{Pu}] = 0.012 \text{M}$, spectroscopic evidence of hydrolysis was observed at pH = 3.8. At the lowest plutonium concentration investigated ($6.9 \times 10^{-5} \text{M}$), no evidence of hydrolysis was observed until pH = 4.9.

The second trend, which relates to establishing Pu(VI) speciation in groundwater-relevant systems, is that the 638 nm species (second hydrolytic product that is spectroscopically evident) increases in predominance relative to the 632 nm species as the total plutonium concentration is lowered. Groundwater-relevant research should more appropriately be focused on the competition between this species and other complexants (e.g., anthropogenic and natural organics). This trend is significant since we have indications from past work that this species is polynuclear; in particular, the complex and slow dehydrolysis kinetics suggest that it has polymeric character. The long-term characterization of this second hydrolytic species is underway.

b. Effect of Temperature on Initial Hydrolysis of Pu(VI)

The range of solution temperatures being addressed by research supported by the Subsurface Science Program is relatively narrow since it is directed toward the remediation and restoration of contaminated sites on DOE lands. These near-surface sites are at temperatures between 10 and 35°C. To account for this small temperature range and determine the enthalpy and entropy of the hydrolytic species being formed, we determined both LPAS and UV-visible spectra at 10–45°C.

The absorption spectra for $0.5 \times 10^{-4} \text{M}$ Pu(VI) are shown in Fig. III-21 at temperatures of 10°, 25°, and 45°C. As is evident, temperature had no significant effect on the relative absorbance of the aquo and 632 nm species. Similar results were obtained at lower plutonium concentrations using the LPAS system. This finding is not in agreement with theoretical estimates of the temperature dependence of Pu(VI) hydrolysis made by Lemire and Tremaine.⁴⁸ They predict a tenfold

change in the formation constant in the temperature range that we investigated. Our data represent the first experimental determination concerning the effect of temperature on Pu(VI) hydrolysis.

Fig. III-20. Relative Concentration of the Aquo Ion, First Hydrolysis Complex (632 nm), and Second Hydrolysis Complex (638 nm) at Total Pu(VI) Concentration of (a) $1.2 \times 10^{-2} M$, (b) $1.6 \times 10^{-4} M$, and (c) $6.9 \times 10^{-5} M$

Fig. III-21. Absorption Spectra of Pu(IV) Aquo Ion and First Hydrolysis Complex Observed at 10°, 25°, and 45°C. These are offset to show spectral features.

c. Formation Constants of Initial Hydrolytic Product

The above spectra established that the initial hydrolytic product was polynuclear. This observation was further established by quantitative analyses that we performed. The formation constant was determined assuming both a 1:1 and 2:2 hydrolysis product (see Eqs. III-5 and III-6). These results are summarized in Table III-8. The formation constant obtained by assuming a 2:2 hydrolytic species, in contrast with that obtained assuming a 1:1 species, did not vary significantly with total plutonium concentration.

Table III-8. Estimated Formation Constants^a for Eqs. III-5 and III-6 at 25°C

$[\text{PuO}_2^{2+}]_0, \text{M}$	$-\log \beta_{11}$	$-\log \beta_{22}$
3.0×10^{-2}	5.2	8.0
1.2×10^{-2}	5.0	7.2
1.6×10^{-4}	6.2	7.5
6.9×10^{-5}	6.3	7.5

^aFor the reaction, $q \text{ PuO}_2^{2+} + p \text{ H}_2\text{O} \rightleftharpoons (\text{PuO}_2)_q(\text{OH})_p + p \text{ H}^+$, where $(p,q) = (1,1) \text{ or } (2,2)$.

Figure III-22 provides a plot of $[H^+]^2$ vs. $2[Pu(VI)]^2/([Pu(VI)]_0 - [Pu(VI)])$ for a total plutonium concentration of $6.9 \times 10^{-5} M$. The plot is linear with a correlation coefficient of 0.99. The formation constant for the $(PuO_2OH)_2^{2+}$ species corresponds to a $-\log \beta_{22}$ value of 7.5 ± 0.2 .

Fig. III-22. Plot of $[H^+]^2$ vs. $2[Pu(VI)]^2/([Pu(VI)]_0 - [Pu(VI)])$ for a Total Plutonium Concentration of $6.9 \times 10^{-5} M$

F. Radiation-Effects Studies for Waste Isolation Pilot Plant (WIPP)
(D. T. Reed)

A potential result of the presence of ionizing radiation in the WIPP site is the direct or indirect generation of gaseous species. This will contribute to the overall gas generation rate, which has been identified by the WIPP Project as a key concern with respect to the long-term performance of this pilot plant. To address the concerns associated with ionizing radiation, we have (1) irradiated WIPP-relevant plastic materials to help determine if the radiolytic alteration changes nonbiodegradable plastics to plastics that can be degraded (reported in ANL-91/42, Sec. III.E), (2) performed some supporting studies to assess the effect of ionizing radiation on the gas phase, and (3) determined the stability of Pu(VI) in WIPP brine in preparation for planned gas generation studies. Results from the latter two efforts are reported below.

1. Background

The two gas phases used in the plastic irradiation experiments (experimental details and results given in ANL-91/42, Sec. III.E) were a two-component (90% N_2 -10% CO_2) mixture and a four-component gas phase (1.25% O_2 , 2.5% H_2 , 6.75% CO_2 , and balance N_2). In the absence of oxygen, carbon dioxide and nitrogen are known to be stable to radiolytic degradation. Significant radiolytically induced change was, however, expected for the four-component gas phase, leading to the formation of nitrogen oxides (N_2O , HNO_3 , and NO_2), ammonia, hydrogen peroxide, ozone, and carbon monoxide.

Yields of the various species depend on the relative concentrations of the bulk components, dose rate, temperature, and solid surfaces present. The objective of the experiments was to establish the nature of the radiolytic products generated and to measure their yield. These data will provide initial input to the WIPP Project on radiolytic changes of the anticipated environments.

In addition to the gas-phase radiolysis experiments, we evaluated the stability of Pu(VI) in WIPP brine. This was done in preparation for *in situ* gas generation studies. The radiolytically induced formation of gas, owing to the radioactive decay of actinides present in WIPP waste, was identified by WIPP Project staff as an important data need for performance assessment. This may become an important consideration should brine move into the WIPP site and dissolve the actinides present.

The predominant actinide in WIPP waste, in terms of inventory and activity, is ^{239}Pu . From a radiolytic viewpoint, the source of ionizing radiation that best simulates its radiation chemistry is simply ^{239}Pu dissolved in WIPP brine. The VI oxidation state was selected because it was predicted to be highly soluble (albeit in a metastable form), and we had previously characterized the spectroscopy associated with its hydrolysis (this report, Sec. III.E).

2. Gamma Radiolysis of $\text{N}_2\text{-CO}_2$ Mixture

The anoxic environment utilized in the plastic irradiation experiments was the 90% N_2 -10% CO_2 mixture. This gas mixture was irradiated in a gamma facility (no plastic present) to establish the long-term trend with respect to radiolytic degradation. Since neither nitrogen nor carbon dioxide is readily degraded by ionizing radiation, little change was expected. The irradiation conditions and gas phase analyses for this experiment are shown in Table III-9. The gas mixture was placed in a 150 cm^3 stainless steel vessel fitted with a stainless steel Nupro H-series bellows valve. This vessel was periodically removed from the gamma facility to analyze the gas phase by gas chromatography. The dose rate, determined by nitrous oxide dosimetry, was 0.30 Mrad/h. The total duration of the experiment was 51.4 days, corresponding to a cumulative absorbed dose of 367 Mrad.

Table III-9. Irradiation Conditions and Gas Phase Composition of 90% N_2 -10% CO_2 Gas Mixture. Nominal pressure was 0.089 MPa.

Time, h (days)	Dose Rate, Mrad/h	Cum. Absorb. Dose, Mrad	Composition, mol %				
			O_2	N_2	CO	CO_2	N_2O
0	0.3	0	ND	89.8 ± 0.2	ND	10.2 ± 0.2	ND
0			ND	89.5 ± 0.2	ND	10.5 ± 0.2	ND
250.9 (10.5)	0.28	75	ND	89.8	ND	10.2	ND
411.1 (17.1)	0.3	120	ND	89.8	ND	10.2	ND
907.3 (37.8)	0.3	269	0.002 ± 0.001	89.8	0.004 ± 0.001	10.2	ND
1232.9 (51.4)	0.3	367	0.004 ± 0.001	89.8	0.008 ± 0.001	10.2	ND
			0.003 ± 0.001	89.8	0.008 ± 0.001	10.2	ND

The relative nitrogen and carbon dioxide concentration remained constant throughout the experiment. No degradation products of nitrogen were noted (nitrous oxide or NO_x). After 120 Mrad,

small amounts of oxygen and carbon monoxide were detected. Their buildup increased nonlinearly with absorbed dose and may be self-catalytic, i.e., the formation of oxygen and carbon monoxide may lead to a greater rate of CO₂ breakdown. Since these species were present in a 2:1 carbon monoxide-to-oxygen ratio, the following degradation reaction was most likely occurring:

For this reaction, based on the data for the highest absorbed dose, $G(-\text{CO}_2) = G(\text{CO}) = 2 G(\text{O}_2) \approx 7 \times 10^{-3}$ molecules/100 eV. The tangential CO₂ yield, once CO₂ breakdown was initiated, was 0.013 molecules/100 eV. This corresponds to an induction period of 170 Mrad prior to the onset of CO₂ breakdown.

3. Gamma Radiolysis of O₂/CO₂/H₂/N₂ Mixture

The four-component (1.25% oxygen, 2.5% hydrogen, 6.76% carbon dioxide, and balance nitrogen) gas mixture was also subjected to gamma radiation to determine the nature and yield of the radiolytic products generated. Gamma irradiation resulted in the formation of carbon monoxide, nitrous oxide, NO_x, ammonia, and probably ozone and hydrogen peroxide (which were not analyzed). Significant decreases in the hydrogen and oxygen concentrations were also noted.

Two replicate experiments were performed using the same stainless steel vessels as employed in the N₂-CO₂ experiments. The irradiation conditions and results of the gas-phase analyses are given in Table III-10. The dose rate for each vessel, measured using nitrous oxide dosimetry, was 0.28 and 0.30 Mrad/h for the two experiments, corresponding to absorbed doses of 152 and 163 Mrad, respectively.

Table III-10. Irradiation Conditions and Gas Phase Analysis for O₂/H₂/CO₂/N₂ Gas Experiments

Irradiation Time, h	Absorbed Dose, Mrad	Concentration, mol %					
		H ₂	O ₂	N ₂	CO	CO ₂	N ₂ O
0		2.4	1.24	90.0	ND	6.32	ND
29.0	8.7						
95.8	29	1.7	0.86	91.1	0.015	6.3	0.07
188.2	56	1.7	0.83	91.0	0.092	6.2	0.12
543.5	163	0.9	0.35	92.1			
		0.9	0.35	92.1	0.004		
		0.9	0.35	92.1	0.004	6.4	0.28
0		2.4	1.24	90.1	ND	6.2	ND
29.0	7.8	2.3	1.15	90.3	ND	6.2	0.02
95.8	27	2.0	1.07	90.6	0.05	6.2	0.05
188.2	53	1.8	0.93	90.9	0.05	6.3	0.10
543.5	152	1.0	0.45	91.8	0.01	6.4	0.26

The yield of carbon monoxide and nitrous oxide as a function of absorbed dose is shown in Fig. III-23. As indicated in this figure, the formation of nitrous oxide was linear with dose. Carbon monoxide, in both experiments, went through a maximum and was then removed from the system. The reason for this decrease cannot be understood from these experiments but was probably due to changes in the relative concentrations of the other components of the gaseous system.

Fig. III-23. Yield of CO and N₂O in Four-Component WIPP Gas Phase (exposed to 0.3 Mrad gamma dose)

The actual concentration of nitrogen and carbon dioxide was essentially unchanged due to irradiation. The relative concentration, however, increased because of significant decreases in the partial pressure of hydrogen and oxygen.

4. Plutonium (as PuO₂²⁺) Stability in WIPP Brine

The work described in this section was performed to evaluate the feasibility of retaining actinides as truly dissolved species in WIPP brine for the duration of planned experiments. The VI oxidation state of plutonium was selected for study based on our past experience with near-neutral pH systems, which had indicated that this oxidation state could most likely be kept in solution. The general approach used was to oxidize plutonium to the VI state in acid medium, add WIPP brine, adjust the pH to 6.2 (ambient pH of the brine), and sequentially dilute this solution into WIPP brine. Absorption spectra of the plutonium-spiked brine were then obtained to establish the gross speciation of the plutonium and to monitor changes in oxidation state as a function of time. Results obtained were then analyzed in the context of the established redox and radiation chemistry of the actinide to assess the stability of the truly dissolved species observed.

In this report period, 50 mg of plutonium-239 was oxidized to the VI state in perchlorate media by the same procedure as used in past Pu(VI) hydrolysis studies.^{49,50} The ²³⁹Pu, received as Pu(IV) in hydrochloric acid, was taken to dryness, redissolved in nitric acid, and passed through a gravity feed bio-rad column. This column separates the plutonium [predominantly as Pu(IV)] from the other ions in the solution. The exchanged Pu(IV) was eluted from the column by washing with hydrochloric acid.

This hydrochloric acid solution was then taken to dryness. The plutonium was redissolved in nitric acid mixed with 0.5 to 1 mL of perchloric acid, which was taken to near-dryness to oxidize the sample to Pu(VI). Approximately 7 mL of brine (WIPP GSEEP) was added to the Pu(VI) sample, causing a rapid lowering of the brine pH and some solid precipitation. The pH was adjusted to a pH of 6.2 with sodium hydroxide (using a Ross combination electrode). This resulted in the redissolution of most of the precipitates and a plutonium concentration of 0.023M (established by gamma counting) in an "altered" WIPP brine.

After 3 days, 3 mL of this solution was filtered through a 0.2- μ m Dynagaard filter and placed in a 1 x 1 cm cuvette. The UV-VIS spectrum of this solution and the unfiltered stock solution was taken to establish the speciation (primarily oxidation state) of the sample. The initial spectrum of the filtered solution is shown in Fig. III-24a. The appearance of this solution was pale yellow but clear, and the UV-VIS spectrum was identical to that obtained for the unfiltered solution. As evident in Fig. III-24a, a small amount of Pu(V) had already formed since some absorption due to the Pu(V) oxidation state is evident (at 572 nm). The other features of the spectrum appear to correspond to Pu(VI). The spectra of this solution obtained at 9, 19, and 79 days are also shown in Fig. III-24 and will be discussed below.

Fig. III-24. Absorption Spectra of 0.023M Pu(VI) in WIPP Brine as Function of Time

Two subsequent dilutions of this solution were prepared 11 days after the initial solution preparation. The first solution was made by adding 0.3 mL of the filtered stock solution into 3 mL of WIPP brine, resulting in a 0.0023M plutonium solution. The spectra of this solution as a function of time are shown in Fig. III-25. The second dilution was made by taking 0.3 mL of the 0.0023M solution and diluting it to 3 mL with WIPP brine, resulting in a plutonium concentration of $2.3 \times 10^{-4}\text{M}$. This solution could not be monitored in the 600-700 nm region because the absorbance was too low. It was not tracked as a function of time.

Fig. III-25. Absorption Spectra of 0.0023M Pu(VI) in WIPP Brine as Function of Time

The absorption spectrum of Pu(VI) in noncomplexing media was discussed in Sec. III.E. The absorption spectra as a function of pH are shown in Fig. III-18. The aquo species has an absorption maximum at 622 nm, with three spectroscopically distinguishable hydrolysis products apparent at higher pH: (1) a polynuclear species at 632 nm, (2) a polynuclear species at 638 nm, and (3) a lesser characterized species at 655 nm. The 638 nm species was directly associated with pH hysteresis, as noted by others in titration experiments.⁴⁶ This hysteresis, based on our work, has unusually slow hydrolysis kinetics in that re-equilibration after lowering of pH takes on the order of weeks. The species at 655 nm was apparent at the highest pH and was associated with the formation of precipitates.

As evident in the spectra of Pu(VI) in WIPP brine shown in Figs. III-24 and III-25, the initial dominant feature is a major peak at 638 nm with a shoulder at longer wavelength. The clear differences between the spectra obtained in brine and that obtained in noncomplexing media indicate that the speciation of the two is not equivalent. Exact speciation, however, cannot be precisely established without additional supporting experiments. The concentration data, based on a calculated effective extinction coefficient of $12.4 \text{ M}^{-1} \text{ cm}^{-1}$ at 638 nm and the published value of $19.3 \text{ M}^{-1} \text{ cm}^{-1}$ for Pu(V) at 572 nm, are given in Table III-11.

Table III-11. Estimated Concentration of Pu(VI) and Pu(V) in Pu-Spiked WIPP Brine Experiments

Time, days	OD _{638nm} ^a	OD _{572nm} ^a	Conc., <u>M</u>		
			Pu(VI)	Pu(V)	Total Pu
<u>0.023M Sol.</u>					
3	0.271	0.023	0.022	0.0012	0.023
5	0.265		0.021		
9	0.254	0.035	0.020	0.0018	0.022
11	0.245		0.020		
12	0.244		0.020		
16	0.232		0.019		
17	0.226		0.018		
19	0.222	0.062	0.018	0.0032	0.021
79	0.189	0.085	0.015	0.0044	0.020
<u>0.0023M Sol.</u>					
11	0.0335	0.004	0.0027	0.00019	0.0029
19	0.035	0.005	0.0028	0.00026	0.0031
79	0.0218	0.011	0.0018	0.00054	0.0023

^aOD = optical density.

In the 0.023M solution (Fig. III-25), there was a slow reduction of the Pu(VI) to Pu(V), as evidenced by the increase in the absorbance at the 572 nm band. This absorption band is characteristic of the aquo species and is much more straightforward to interpret than the Pu(VI) band since significant hydrolysis of Pu(V) should not occur until pH>9. The shape of the Pu(VI)-related features (at 638 nm band) up until day 19 after solution preparation shows little change. There, however, is a significant change in the 638 nm band between day 19 and day 79 that cannot be fully understood based on the data

we have obtained to date. Here, the predominance of the longer wavelength shoulder increased with time. In all the analyses of this solution, we observed no visual evidence of precipitation or a significant increase in background absorbance (indicating colloidal scattering of the light).

The estimated decrease in Pu(VI) concentration, based on absorbance at 638 nm, is given in Table III-11 and shown as a function of time in Fig. III-26. Also shown in this figure is the increase in the Pu(V) concentration and our estimate of the total plutonium concentration. This is a nonrigorous interpretation of the spectra shown since both total Pu(VI) concentration and its speciation clearly change as a function of time. The "effective" extinction coefficient at 638 nm is not, therefore, truly representative of the 79-day spectrum observed. Even with these qualifications, our results account for over 80% of the initial plutonium present in the solution. Since there was no increase in background absorbance and no visual evidence of precipitates, we inferred that a more precise spectroscopic analysis would indicate that all the plutonium initially present was being retained in solution.

The lower concentration (0.0023M) sample (Fig. III-25) showed little change in the 638 nm band and associated shoulder as a function of time. The normalized concentrations in this sample are also given in Table III-11. As with the higher concentration sample, no evidence of precipitation or change in background scatter was observed.

Fig. III-26. Estimated Concentrations of Pu(VI), Pu(V), and Total Pu in WIPP Brine as Function of Time

The spectra obtained provide some guidelines as to the species present in solution. Two effects and spectral features were noted. First, the formation of Pu(V) was evidenced by an increase in absorbance at 572 nm. The absorbance for this species initially increased linearly, in intensity, with time and then approached a steady state or plateau value. Second, absorbance related to Pu(VI) was noted in the 600-700 nm region. This effect was produced by a composite of two bands: (1) a 638 nm band that was associated with the second hydrolysis product in noncomplexing media, which is polynuclear and probably 3:5 in character (see Table III-7), and (2) a red-shifted shoulder that, based on our previous work,⁵⁰ is due to the presence of the brine. The spectral shape as well as intensity in this region of the

spectrum changed with time. The longer wavelength shoulder appears to be more stable toward reduction than is the shorter wavelength species but cannot be characterized based on our work to date.

The conversion from Pu(V) to Pu(VI) appears to decrease with time. This is consistent with the results reported by Kim et al.,⁴⁹ who showed that the Pu(V) initially generated in Pu(VI) spiked brines was, in time, reoxidized to Pu(VI). This resulted from the buildup of chlorine-based oxidizing species in solution due to radiolysis. The predominance of Pu(VI) has also been confirmed in other work performed at ANL⁵⁰ and predicted by Aston.⁵¹

Although significant questions remain about the speciation of Pu(VI) and Pu(V) in WIPP brine, our preliminary experiments suggest that essentially all the plutonium can be retained in solution at 0.023 and 0.0023M total concentrations for the 2-3 month durations in the planned gas generation experiments.

REFERENCES

1. R. D. Aines, *Plan for Glass Waste Form Testing for NNWSI*, Lawrence Livermore National Laboratory Report UCID-21190 (1987).
2. J. K. Bates, T. A. Abrajano, Jr., B. M. Biwer, C. R. Bradley, W. L. Ebert, J. J. Mazer, D. J. Wronkiewicz, and J. E. Young, "Critical Review of Parameters Affecting Glass Reaction in an Unsaturated Environment," draft submitted to DOE-HQ/EM (1990).
3. C. M. Jantzen, *Glass Compositions and Frit Formulations Developed for DWPF*, memo C. M. Jantzen to M. J. Plodinec, Savannah River Laboratory Report DPST-88-952 (1988).
4. *Waste Form Selection for SRP High-Level Waste*, U.S. Department of Energy Report DOE/EA-1079 (1982).
5. N. E. Bibler, "Leaching of Fully Radioactive SRP Nuclear Waste Glass in Tuff Ground Water in Stainless Steel Vessels," *Adv. Ceram.* 20, 619 (1986).
6. N. E. Bibler, G. G. Wicks, and V. M. Oversby, "Leaching Savannah River Plant Nuclear Waste Glass in a Saturated Tuff Environment," *Mater. Res. Soc. Symp. Proc.* 44, 247-256 (1985).
7. N. E. Bibler and J. K. Bates, "Product Consistency Leach Tests of Savannah River Site Radioactive Waste Glasses," presented at the Fall 1989 Meeting of the Mater. Res. Soc., Boston, MA, November 26-December 1, 1989.
8. N. E. Bibler and G. Wicks, *Leaching Savannah River Plant Nuclear Waste Glass in a Saturated Tuff Environment*, Savannah River Laboratory UCRL-91258 (November 1984).
9. N. E. Bibler and C. M. Jantzen, *The Product Consistency Test and Its Role in the Waste Acceptance Process*, Savannah River Laboratory Report DP-MS-88-188 (1989).
10. N. E. Bibler, "Characterization of Borosilicate Glass Containing Savannah River Plant Radioactive Waste," *Am. Chem. Soc. Symp. Ser.* 246, 359-372 (1983).
11. *JSS Project Phase II: Final Report of Work Performed at Studsvik Energiteknik AB and at Swiss Federal Institute for Reactor Research*, Japanese, Swiss, Swedish Project Report JSS-85-01 (1985).
12. J. K. Bates and T. J. Gerding, *One-Year Results of the NNWSI Unsaturated Test Procedure: SRL 165 Glass Application*, Argonne National Laboratory Report ANL-85-41 (1986).
13. J. K. Bates et al., *Annual Report to the Repository Technology Program*, Argonne National Laboratory Report ANL-90/21 (1990).
14. J. K. Bates and T. J. Gerding, *Application of the NNWSI Unsaturated Test Method to Actinide Doped SRL 165 Type Glass*, Argonne National Laboratory Report ANL-89/24 (1990).
15. J. K. Bates, W. L. Ebert, and T. J. Gerding, "Vapor Hydration and Subsequent Leaching of Transuranic-Containing SRL and WV Glasses," *Proc. of Int. High-Level Radioactive Waste Mgmt. Topical Meeting*, Am. Nucl. Soc., Las Vegas, NV, April 8-12, 1990, p. 1095 (1990).

16. J. K. Linacre and W. R. Marsh, *The Radiation Chemistry of Heterogeneous and Homogeneous Nitrogen and Waste Systems*, AERE Report R-10027 (1981).
17. L. R. Pederson, C. Q. Buckwalter, G. L. McVay, and B. L. Riddle, "The Effects of Surface Area to Solution Volume on Waste Glass Leaching," *Nucl. Technol.* 62, 151 (1983).
18. E. Vernaz, T. Advocat, and J. L. Dussossoy, "Effects of the SA/V Ratio on the Long-Term Corrosion Kinetics of R7-T7 Glass," *Ceramics Transactions; Nuclear Waste Management III*, Vol. 9, Ed., G. Mellinger (1990).
19. P. Aagaard and H. C. Helgeson, "Thermodynamic and Kinetic Constraints on Reaction Rates among Minerals and Aqueous Solutions. I. Theoretical Considerations," *Am. J. Sci.* 282, 237-285 (1982).
20. B. Grambow, "A General Rate Equation for Nuclear Waste Glass Corrosion," in *Scientific Basis for Nuclear Waste Management VIII*, Eds., C. M. Jantzen, J. A. Stone, and R. C. Ewing, Mater. Res. Soc., Pittsburgh, PA (1985).
21. W. L. Bourcier, K. G. Knauss, and C. I. Merzbacher, "A Kinetic Model for Dissolution of Borosilicate Glass," presented at Sixth Int. Symp. on Water-Rock Interactions, Malvern, England, U.K., August 3-12, 1989.
22. W. L. Ebert, J. K. Bates, and T. G. Gerding, *The Reaction of Glass during Gamma Irradiation in a Saturated Tuff Environment, Part 4: SRL 165, ATM-1c, and ATM-8 Glasses at 1E3 R/h and 0 R/hr*, Argonne National Laboratory Report ANL-90/13 (1990).
23. J. K. Bates, C. R. Bradley, J. P. Bradley, N. L. Dietz, W. L. Ebert, J. W. Emery, T. J. Gerding, J. C. Hoh, J. J. Mazer, and J. E. Young, *Unsaturated Glass Testing for DOE Program in Environmental Restoration and Waste Management, Annual Report, October 1989-September 1990*, Argonne National Laboratory Report ANL-90/40, p.7 (1991).
24. J. P. Bradley, "Analysis of Chondritic Interplanetary Dust Thin-Sections," *Geochim. Cosmochim. Acta* 52, 889 (1988).
25. T. A. Abrajano, Jr., J. K. Bates, A. B. Woodland, J. P. Bradley, and W. L. Bourcier, "Secondary Phase Formation during Nuclear Waste-Glass Dissolution," *Clays and Clay Miner.* 38, 537-548 (1990).
26. J. J. Mazer, C. M. Stevenson, W. L. Ebert, and J. K. Bates, "The Experimental Hydration of Obsidian as a Function of Relative Humidity and Temperature," *Am. Antiq.* 56(3), 504-513 (1991).
27. I. Friedman and W. Long, "Hydration Rate of Obsidian," *Science* 191, 347-352 (1976).
28. J. E. Ericson, A. Makishima, J. D. Mackenzie, and R. Berger, "Chemical and Physical Properties of Obsidian: A Naturally Occurring Glass," *J. Non-Cryst. Solids* 17, 129-142 (1975).
29. I. Friedman and R. L. Smith, "A New Dating Method Using Obsidians: Part I, The Development of the Method," *Am. Antiq.* 25(4), 476-522 (1960).

30. I. Friedman and F. W. Trembour, "Obsidian: The Dating Stone," *Am. Sci.* 66, 44-51 (1978).
31. Y. Zhang, E. M. Stolper, and G. J. Wasserburg, "Diffusion of Water in Rhyolitic Glasses," *Geochim. Cosmochim. Acta* 55, 441-456 (1991).
32. J. L. Karsten, J. R. Holloway, and J. R. Delaney, "Ion Microprobe Studies of Water in Silicate Melts: Temperature-Dependent Water Diffusion in Obsidian," *Earth Planet. Sci. Lett.* 59, 420-428 (1982).
33. W. L. Bourcier, P. W. Peiffer, K. G. Knauss, K. D. McKeegan, and D. K. Smith, "A Kinetic Model for Dissolution Based on the Dissolution Affinity of a Surface Alteration Layer," *Mat. Res. Soc. Symp. Proc.* 176, 209 (1990).
34. H. Leidheiser, *The Corrosion of Copper, Tin and Their Alloys*, John Wiley and Sons, New York (1971).
35. G. E. Gdowski and D. B. Bullen, *Survey of Degradation Modes of Candidate Materials for High-Level Radioactive-Waste Disposal Containers, Oxidation and Corrosion*, Lawrence Livermore National Laboratory Report UCID-21362, Vol. 2 (1988).
36. D. T. Reed, V. Swayambunathan, B. S. Tani, and R. A. Van Konynenburg, "Corrosion Production Identification and Relative Rates of Corrosion of Candidate Metals in an Irradiated Air-Steam Environment," *Mat. Res. Soc. Symp. Proc.* 176, 517 (1990).
37. *Feasibility Assessment of Copper-Based Waste Package Container Materials in a Repository in Basalt*, Rockwell Hanford Operations Report SO-BWI-TA-023 (1986).
38. W. H. Yunker and R. S. Glass, "Long-Term Corrosion Behavior of Copper-Base Materials in a Gamma Irradiated Environment," *Mat. Res. Soc. Symp. Proc.* 84, 579 (1987).
39. A. V. Byalobzhetskii, *Radiation Corrosion*, Izdatel' Stuo "Nauk," Moskua (1976).
40. A. W. Tracy, "Symposium on Atmospheric Corrosion of Non-Ferrous Metals," *ASTM-STP* No. 175, p. 67 (1955).
41. C. Frondel, "Mineral Composition of Gummite," *Am. Mineral. J.* 41, 539-568 (1956).
42. R. J. Finch and R. C. Ewing, "Alteration of Natural UO₂ Under Oxidizing Conditions from Shinkolobwe, Katanga, Zaire: A Natural Analogue for the Corrosion of Spent Fuel," Swedish Nuclear Fuel and Waste Management Co. SKB Technical Report 89-37 (1989).
43. C. J. Bruton and H. F. Shaw, "Geochemical Simulation of Reaction between Spent Fuel Waste Form and J-13 Water at 25°C and 90°C," *Mat. Res. Soc. Symp. Proc.* 112, 485-494 (1988).
44. J. V. Beitz, D. L. Bowers, M. M. Doxtader, V. A. Maroni, and D. T. Reed, "Detection and Speciation of Transuranium Elements in Synthetic Groundwater Via Pulsed-Laser Excitation," *Radiochim. Acta* 47/48, 87-93 (1988).

45. J. V. Beitz, M. M. Duxtader, V. A. Maroni, S. Okajima, and D. T. Reed, "High Sensitivity Photoacoustic Spectrometer for Variable Temperature Solution Studies," *Rev. Sci. Instr.* 61(5), 1395 (1990).
46. S. Okajima, D. T. Reed, J. J. Mazer, and C. A. Sabau, "Speciation of Pu(VI) in Near-Neutral to Basic Solutions via Spectroscopy," *Mat. Res. Soc. Symp. Proc.* 176, 583-590 (1990).
47. S. Okajima, D. T. Reed, J. V. Beitz, C. A. Sabau, and D. L. Bowers, "Speciation of Pu(VI) in Near-Neutral Solutions via Laser Photoacoustic Spectroscopy," *Radiochim. Acta* 52/53, 111-117 (1991).
48. R. Lemire and P. Tremaine, "Uranium and Plutonium Equilibria in Aqueous Solution to 200°C," *J. Chem. Phys. Data* 25, 361 (1980).
49. J. I. Kim, Ch. Lierse, K. Buppelmann, and S. Magirius, "Radiolytically Induced Oxidation Reactions of Actinide Ions in Concentrated Salt Solutions," *Mat. Res. Soc. Proc.* 84, 603 (1988).
50. K. Nash, Private Communication, Argonne National Laboratory (1990).
51. S. R. Aston, "Evaluation of the Chemical Forms of Plutonium in Seawater," *Marine Chem.* 8, 319 (1980).

Distribution for ANL-92/25Internal:

J. K. Basco
 J. K. Bates (5)
 J. E. Battles
 P. E. Blackburn
 R. A. Blomquist
 E. C. Buck
 D. J. Chaiko
 D. B. Chamberlain
 Y. I. Chang
 L. S. H. Chow
 J. M. Copple
 J. C. Cunnane
 N. L. Dietz
 W. L. Ebert
 P. A. Finn
 A. K. Fischer
 T. J. Gerding
 M. Gong

D. W. Green
 J. E. Harmon
 E. P. Horwitz
 R. J. Jaskot
 I. Johnson
 C. E. Johnson (5)
 T. R. Johnson
 J. P. Kopasz
 J. Laidler
 L. Leibowitz
 R. A. Leonard
 M. J. Lineberry
 J. J. Mazer
 B. Misra
 F. C. Mrazek
 L. Nunez
 S. Okajima

D. T. Reed
 M. C. Regalbuto
 R. T. Riel
 M. F. Roche
 J. Sedlet
 W. B. Seefeldt
 M. J. Steindler
 S.-W. Tam
 C. E. Till
 L. E. Trevorrow
 G. F. Vandegrift (10)
 E. H. Van Deventer
 L. C. Walters
 R. D. Wolson
 ANL Patent Dept.
 ANL Contract File
 TIS Files (3)

External:

DOE-OSTI, for distribution per UC-500 (102)
 ANL Library (2)
 Manager, Chicago Operations Office, DOE
 A. Bindokas, DOE-CH
 J. Haugen, DOE-CH
 A. L. Taboas, DOE-CH/AAO
 Chemical Technology Division Review Committee Members:
 S. Baron, Brookhaven National Laboratory, Upton, NY
 D. L. Douglas, Consultant, Bloomington, MN
 N. Jarrett, Noel Jarrett Associates, Lower Burrell, PA
 J. G. Kay, Drexel University, Philadelphia, PA
 J. Stringer, Electric Power Research Institute, Palo Alto, CA
 J. B. Wagner, Arizona State University, Tempe, AZ
 R. G. Wymer, Oak Ridge National Laboratory, Oak Ridge, TN
 M. G. Adamson, Lawrence Livermore National Laboratory, Livermore, CA
 J. Allison, USDOE, Office of Waste Operations, Germantown, MD
 J. T. Bell, Oak Ridge National Laboratory, Oak Ridge, TN
 S. E. Berk, USDOE, Office of Fusion Energy, Germantown, MD
 N. E. Bibler, Westinghouse Savannah River Co., Aiken, SC
 W. Bourcier, Lawrence Livermore National Laboratory, Livermore, CA
 D. F. Bowersox, Los Alamos National Laboratory, Los Alamos, NM
 L. Brewer, University of California, Berkeley, CA

M. H. Campbell, Westinghouse Hanford Co., Richland, WA
 K. A. Chacey, USDOE, Office of Waste Management, Germantown, MD
 M. O. Cloninger, Yucca Mountain Project Office, Las Vegas, NV
 M. S. Coops, Lawrence Livermore National Laboratory, Livermore, CA
 D. Cubicciotti, Electric Power Research Institute, Palo Alto, CA
 J. Dennison, Dennison Environmental, Woburn, MA
 M. Dinehart, Los Alamos National Laboratory, Los Alamos, NM
 M. C. Dionisio, USDOE, Office of Technology Development, Washington, DC
 M. Duff, USDOE, Office of Waste Operations, Germantown, MD
 R. C. Ewing, University of New Mexico, Albuquerque, NM
 R. Fish, B&W Fuel Co., Las Vegas, NV
 C. W. Frank, USDOE, Office of Technology Development, Washington, DC
 W. S. Groenier, Oak Ridge National Laboratory, Oak Ridge, TN
 K. Hain, USDOE, Office of Technology Development, Germantown, MD
 J. O. Honeyman, Westinghouse Hanford Operations, Richland, WA
 C. Interrante, U. S. Nuclear Regulatory Commission, Washington, DC
 C. Jantzen, Westinghouse Savannah River Co., Aiken, SC
 L. J. Jardine, Lawrence Livermore National Laboratory, Livermore, CA
 R. T. Jubin, Oak Ridge National Laboratory, Oak Ridge, TN
 W. S. Ketola, USDOE, West Valley Project Office, West Valley, NY
 D. A. Knecht, Westinghouse Idaho Nuclear Co., Idaho Falls, ID
 M. Levenson, Menlo Park, CA
 S. C. T. Lien, USDOE, Office of Technology Development, Washington, DC
 Los Alamos National Laboratory, Los Alamos, NM
 J. Matuszek, State of New York, Department of Health, Albany, NY
 W. H. McVey, USDOE, Division of LMFBR Fuel Cycle Projects, Germantown, MD
 R. Morissette, Science Applications International Corp., Las Vegas, NV
 A. C. Muscatello, Los Alamos National Laboratory, Los Alamos, NM
 P. K. Nair, Southwest Research Institute, San Antonio, TX
 L. Nelson, Sandia Corp., Albuquerque, NM
 J. Nelson, Westinghouse Hanford Co., Richland, WA
 M. O'Hara, Martin Marietta Energy Systems, Oak Ridge, TN
 D. R. Olander, University of California, Berkeley, CA
 A. L. Olson, Westinghouse Idaho Nuclear Co., Inc., Idaho Falls, ID
 M. Palmer, Los Alamos National Laboratory, Los Alamos, NM
 R. Palmer, West Valley Nuclear Services, West Valley, NY
 G. Pfennigworth, Martin Marietta Energy Systems, Oak Ridge, TN
 W. G. Ramsey, Westinghouse Savannah River Co., Aiken, SC
 L. Reichley-Yinger, Columbus, OH
 C. G. Russomanno, USDOE, Civilian Radioactive Waste Management, Washington, DC
 P. S. Schaus, Westinghouse Hanford Co., Richland, WA
 H. Shaw, Lawrence Livermore National Laboratory, Livermore, CA
 M. W. Shupe, USDOE, Office of Technology Development, Germantown, MD
 J. Sproull, Westinghouse Savannah River Co., Aiken, SC
 D. Stahl, B&W Fuel Co., Las Vegas, NV
 R. B. Stout, Lawrence Livermore National Laboratory, Livermore, CA
 I. R. Tasker, IIT Research Institute, Bartlesville, OK
 D. W. Tedder, Georgia Institute of Technology, Atlanta, GA
 T. A. Todd, Westinghouse Idaho Nuclear Co., Inc., Idaho Falls, ID
 USDOE, Office of Basic Energy Sciences, Washington, DC

S. Yarbrow, Los Alamos National Laboratory, Los Alamos, NM
W. Lutze, Hahn-Meitner-Institut, Berlin, GERMANY
P. Van Iseghem, BELGIUM
E. Vernaz, Centre d'Etudes Nucleaires de la Valle du Rhone, FRANCE
L. Werme, Svensk Kärnbränslehantering AB, Stockholm, SWEDEN

END

DATE
FILMED

11 / 4 / 92