DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

**A NOVEL APPROACH TO HIGHLY DISPERSING CATALYTIC
MATERIALS IN COAL FOR GASIFICATION**

DOE/PC/89760--T9

DE92 019728

First Quarterly Report

for the Period

October 1, 1989 - December 31, 1989

Godfried M.K. Abotsi and Kofi B. Bota

Principal Investigators

Research Center for Science and Technology

Clark Atlanta University

Atlanta, Georgia 30314

PREPARED FOR

UNITED STATES DEPARTMENT OF ENERGY

UNDER CONTRACT NO. DE-FG22-89PC89760

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

This project seeks to develop a technique, based on coal surface properties, for highly dispersing catalysts in coal for gasification and to investigate the potential of using potassium carbonate and calcium acetate mixtures as catalysts for coal gasification. The lower cost and high catalytic activity of the latter compound will produce economic benefits by reducing the amount of K_2CO_3 required for high coal char reactivities.

The work is focused on the elucidation of coal-catalyst precursor interactions in solution and the variables which control the adsorption and dispersion of coal gasification metal catalysts. In order to optimize coal-metal ion interactions and hence maximize catalyst activity, the study examines the surface electrochemistry of a lignite, a subbituminous, and a bituminous coals and their demineralized and oxidized derivatives prior to loading with the catalytic materials. The surface electrical properties of the coals are investigated with the aid of electrophoresis, while the effects of the surface charge on the adsorption of K^+ and Ca^{2+} are studied by agitating the coals with aqueous solutions of potassium and calcium.

A zeta meter, a tube furnace, and other equipment required for the investigation have been acquired and installed. Preliminary work shows that the lignite (PSOC 1482) is negatively charged between pH 1.8 and pH 11.0 and has an isoelectric point of pH 1.8.

TECHNICAL PROGRESS REPORT

The primary task for the first quarter was the acquisition of materials and equipment required for the research. A Pen Kem Model 501 Lazer Zee Meter has been purchased, calibrated, and is operational for the surface charge measurement of the selected coals. The determination of the surface charge properties of the coals involves measuring the electrophoretic mobilities of coal particles suspended in an aqueous medium. The Pen Kem zeta meter has the advantage of measuring the velocities of several particles simultaneously. This allows rapid data collection and minimizes time-dependent errors such as convection currents caused by sample heating, bubble formation due to evolution of gases from the solution and the concomitant changes in the location of the stationary layer, sample contamination by reaction products diffusing from the electrode, and particle sedimentation which hinders accurate velocity measurements.

Sufficient quantities of a lignite (PSOC 1482), a subbituminous (PSOC 1485), and a bituminous (PSOC 1493, Illinois No. 6) coals have been procured from the Pennsylvania State University/Department of Energy Coal Sample Bank.

Preliminary electrophoretic mobility studies on the lignite in a 10^{-3} kmol m^{-3} $AgNO_3$ solution, for ionic strength control, shows that the coal has an isoelectric point of pH 1.8, the coal surface being positively and negatively charged, respectively, below and above this pH value. The negative charge density increased with increase in pH up to about pH 11, the maximum zeta potential being -96 mV.

A "Wrist Action Shaker" model 75 has been acquired for equilibrating the coal samples prior to the zeta potential measurements and for the potassium and calcium adsorption studies.

A Lindberg tube furnace (model 55341) with a maximum operating temperature of 1473K and equipped with a temperature control console has been procured and is being installed for the preparation of large and uniform coal char samples for the gasification work.

About 300 g of each coal are currently being treated in hydrofluoric and hydrochloric acids to dissolve the inorganic constituents in the coals.

A graduate student has been appointed to work on the project. In this first quarter, his responsibilities included extensive reading of literature relevant to the project.

During the next quarter, zeta potential measurements will be continued on the parent coals and their demineralized derivatives. The kinetics of potassium and calcium adsorption on to the coals will be initiated to determine the optimum conditions for adsorption.

END

**DATE
FILMED**

10 / 22 / 92