**DEVELOPMENT OF AN ADVANCED, CONTINUOUS MILD-GASIFICATION
PROCESS FOR THE PRODUCTION OF COPRODUCTS**

**Report for Task 4.8, Decontamination and Disassembly of the Mild-
Gasification and Char-to-Carbon PRUs and Disposal of Products from
Testing**

DOE/MC/24268--T28

DE92 017793

By
Norman W. Merriam¹
Mahesh C. Jha²

November 1991

Work Performed Under Contract DE-AC21-87MC24268

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia

By
¹Western Research Institute
Laramie, WY
and
²AMAX Research and Development Center
Golden, Colorado

APPROVED FOR RELEASE OR
PUBLICATION - O.R. PATENT GROUP
BY *W.E.B.* DATE *7/28/92*

MASTER

EB

LEGAL NOTICE

THIS REPORT WAS PREPARED BY AMAX RESEARCH AND DEVELOPMENT CENTER AND WESTERN RESEARCH INSTITUTE AS AN ACCOUNT OF WORK SPONSORED BY THE U.S. DEPARTMENT OF ENERGY. NEITHER AMAX RESEARCH AND DEVELOPMENT CENTER NOR WESTERN RESEARCH INSTITUTE NOR ANY PERSON ACTING ON THEIR BEHALF:

- (A) MAKES ANY WARRANTY, EXPRESSED OR IMPLIED, WITH RESPECT TO THE USE OF ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT OR THAT SUCH USE MAY NOT INFRINGE PRIVATELY OWNED RIGHTS; OR**
- (B) ASSUMES ANY LIABILITIES WITH RESPECT TO THE USE OF, OR FOR THE DAMAGES RESULTING FROM THE USE OF, ANY INFORMATION, APPARATUS, METHOD, OR PROCESS DISCLOSED IN THIS REPORT.**

ABSTRACT

This report contains descriptions of mild-gasification and char-to-carbon process research units (PRUs) used by WRI and AMAX R&D Center to conduct tests under contract DE-AC21-87MC24268. Descriptions of materials produced during those tests are also contained herein.

Western Research Institute proposes to dispose of remaining fines and dried coal by combustion and remaining coal liquids by incineration during mid-1992. The mild-gasification PRU will be used for additional tests until 1993, at which time WRI proposes to decontaminate and disassemble the PRU.

AMAX R&D Center intends to return the spent char, any remaining feed char, and unusable product carbon to the Eagle Butte Mine near Gillette, Wyoming, from where the coal originally came. The solid products will be added to the mine's coal product stream. Coal liquids collected from condensers will be concentrated and sent to a local oil and solvent recycling company where the liquids will be burned as fuel. The char-to-carbon PRU will be operated periodically until 1993 when the plant will be decontaminated and disassembled.

ACKNOWLEDGEMENT

The authors wish to thank the Morgantown Energy Technology Center of the U.S. Department of Energy for funding this work. We also wish to thank AMAX Coal Company for their support and guidance.

EXECUTIVE SUMMARY

Western Research Institute (WRI) is working with AMAX Research and Development (AMAX R&D) Center on development of an advanced, continuous mild-gasification process for the production of coproducts under contract DE-AC21-87MC24268 from the Morgantown Energy Technology Center of the U.S. Department of Energy. WRI conducted mild-gasification tests using a process research unit (PRU) that is designed to test minus 8-mesh Wyodak coal at a feed rate of 100 lb/hr. AMAX R&D conducted char upgrading tests using a char-to-carbon (CTC) PRU designed to process char from the mild-gasification PRU at a feed rate of 50 lb/hr. This report describes the plans, estimated costs, and proposed schedules for decontamination and disassembly of the PRUs and disposal of the materials produced by testing in an environmentally acceptable manner.

WRI has disposed of the feed coal oversize, the gas produced, the water from drying, and the product char as part of the mild-gasification program. Fines, dried coal, and coal liquids are the products remaining to be disposed of. WRI proposes to burn the coal and fines and incinerate the liquids during mid-1992. WRI proposes to maintain the PRU in operating condition until mid-1993, at which time the PRU will be decontaminated and dismantled.

AMAX R&D Center operated the CTC PRU from August 1990 to July 1991. Feed char, spent char, carbon black, and Desulco seed are the main solid products from PRU campaigns. During that operation, liquid by-products were also collected. All of these feedstocks and products need to be disposed. AMAX R&D Center intends to modify and operate the PRU during the next two years, converting the char to carbon and activated carbon. This will reduce the amount to be disposed in half. The remaining spent char will be returned to the Eagle Butte Mine and combined with product coal. By-product liquids produced during the PRU operation will be burned for heating value. Upon completion of the testing, the PRU will be cleaned and dismantled. Equipment (all purchased by AMAX) will be removed and stored on site. The building in which the PRU was built will be repaired and restored to its previous condition.

TABLE OF CONTENTS

	<u>Page</u>
List of Tables and Figures.....	vii
1.0 Introduction.....	1
2.0 Background.....	2
3.0 Description of the PRUs and the Material Produced by Testing.....	6
3.1 Description of the Mild-Gasification PRU.....	6
3.2 Materials Produced by Mild-Gasification.....	9
3.3 Description of the Char-to-Carbon PRU.....	11
3.4 Materials Produced by Upgrading Char.....	14
4.0 Decontamination and Disassembly of the PRUs.....	14
4.1 Decontamination and Disassembly of the Mild-Gasification PRU.....	14
4.2 Decontamination and Disassembly of the Char-to-Carbon PRU.....	15
5.0 Disposal of Materials Produced by Testing.....	16
5.1 Disposal of Products from Mild-Gasification Tests.....	16
5.2 Disposal of Products from Char-Upgrading Tests.....	18
6.0 Cost of Decontamination, Disassembly, and Disposal.....	19
6.1 Mild Gasification.....	19
6.2 Char Upgrading.....	21
7.0 Proposed Schedule.....	24
8.0 References.....	25

LIST OF TABLES and FIGURES

<u>Table</u>	<u>Page</u>
1. Equipment Used in the Mild-Gasification PRU.....	9
2. Materials Produced by Mild-Gasification Tests in the PRU.....	11
3. Char-to-Carbon PRU Equipment.....	12
4. Materials from Char-to-Carbon PRU.....	14
5. Composition of Water Produced by Drying Coal.....	17
6. Materials Remaining from Mild-Gasification Tests.....	17
7. Proximate Analyses for Fines, Dust, and Dried Coal.....	18
8. Solid Products Composition.....	19
9. Liquid Products Composition.....	19
10. Cost of Disposal of Dust, Fines, Dried Coal and Liquids from Mild-Gasification.....	20
11. Cost for Decontamination and Disassembly of the Mild- Gasification PRU.....	21
12. Char-to-Carbon Materials Disposal Cost Estimate.....	22
13. Char-to-Carbon Equipment Disassembly Cost Estimate.....	23
14. Proposed Schedule.....	24

Figure

1. Process Flow Diagram for Mild Gasification PRU.....	7
2. Char-to-Carbon PDU Process Flowsheet.....	10

1.0 INTRODUCTION

The U.S. Department of Energy (DOE) is developing several gasification and liquefaction processes to convert coal to usable gaseous and liquid forms. Successful development of the processes will increase the use of coal, the largest domestic potential source of fossil energy. However, these processes, which require high temperatures and pressures in most cases, have been slow in receiving commercial acceptance because they require high capital and operating costs.

To overcome this problem, Morgantown Energy Technology Center (METC), the lead technical center in gasification technology, has developed a concept called mild gasification. In this concept, devolatilization of coal under nonoxidizing and relatively mild temperature and pressure conditions can yield three marketable products: (1) a high-heating-value gas, (2) a high-aromatic coal liquid, and (3) a high-carbon char.

METC awarded contract DE-AC21-87MC24268, Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products, to Western Research Institute (WRI) in Laramie, with AMAX Research and Development Center (AMAX R&D) in Golden, Colorado, and Wiley Stoker in Worcester, Mass, as subcontractors to further enhance the technology and the economics of mild gasification.

The objective of this program is to develop an advanced, continuous, mild gasification process to produce products that will make the concept economically and environmentally viable.

The program consists of four tasks:

Task 1--Literature Survey and Market Assessment

Task 2--Bench-Scale, Mild-Gasification Study

Task 3--Bench-Scale, Char-Upgrading Study

Task 4--System Integration Studies

Task 1 has been completed and reported by Cha et al. (1988). Tasks 2 and 3 have been completed and reported by Merriam and Cha (1989) and Jha and McCormick (1989), respectively.

The work in task 4 includes:

Task 4.4 Mild-Gasification Tests

This work has been completed using a process research unit (PRU) at WRI and was reported by Merriam et al. (1990).

Task 4.4 Char-Upgrading Tests

This work was completed in mid-1991 using a PRU at AMAX R&D Center built with equipment purchased by AMAX and was reported by Jha et al. (1991).

Task 4.6 Economic Assessment

This work was completed in mid-1991 and was reported by Hogsett and Jha (1991).

Task 4.7 Design of a 20 TPD Process Development Unit

This work was completed by Ralph M. Parsons Company on a subcontract from AMAX R&D Center. The final report has been completed (Parsons 1991).

Task 4.8 Decontamination and Disassembly of the Mild-Gasification and Char-to-Carbon (CTC) PRUs and Disposal of Products From Testing

This plan, schedule, and cost estimate are the topic of this report.

2.0 BACKGROUND

Much work has been done during the last several decades to produce fuels and feedstocks from coal. However, nearly all of the development has focused on severe conditions to produce maximum yields of liquid and gaseous products. Although some of the processes have been shown to be technically feasible, the high temperatures ($>1292^{\circ}\text{F}$ (700°C)) and high pressure (>50 psig) used in those processes have resulted in high-cost technologies that do not appear to be economically feasible for commercial implementation in the foreseeable future.

One approach to developing low-cost processes is to use mild conditions (i.e., lower temperatures and pressures) to reduce the cost of producing fuels and feedstocks from coal. The use of mild conditions may produce less than maximum yields of gas and liquid products; however, it is likely that low-cost processes can produce a slate of products with marketable properties and economically acceptable yields. The focus of mild gasification is, therefore, upon developing and demonstrating processes that can be built and operated with relatively low cost on the commercial scale and that will give a satisfactory return on the investment.

Cost estimates for plants using severe processing conditions show that investments of billions of dollars are needed to construct a single plant. Few organizations have the capital needed for such an undertaking and are willing to accept the enormous risk. One goal of the mild gasification work is to prove that processes can be built for a small fraction of the investment needed for severe processes, thus, significantly lowering the financial risk of constructing a mild-gasification plant. Mild-gasification processes must also have low operating costs to be economically feasible.

Versions of mild gasification of coal, commonly called devolatilization, are presently practiced in England, India, and South Africa and have been used commercially in many countries in the past. The development of new mild-

gasification processes will be based on experience with older technology combined with recent technological improvements and systems approach to optimize the overall value of the products.

Market assessment studies were performed by AMAX Coal Company and JDS Group, Inc. as part of task 1 (Cha et al. 1988). The studies showed that revenue from a commercial plant could be significantly improved if char is converted to carbon black, electrode-grade carbon, activated carbon, or metallurgical coke. The fact that Alumax, a division of AMAX, consumes over 250,000 tons of anode-grade carbon per year at delivered prices of about \$200 per ton resulted in a decision to develop a process to produce anode-grade carbon from char.

We decided to produce four liquid products: (1) dirty pitch, (2) clean pitch, (3) heavy oil, and (4) light oil. The dirty pitch will be used to coat dried coal before shipment. It will displace a petroleum product purchased for \$100 per ton. Clean pitch will be used as electrode-binder pitch by Alumax, displacing pitch imported for \$150 to \$250 per ton. Heavy oil will be blended with diesel fuel to operate equipment at the mine or sold to a refinery for about \$100 per ton. Low-boiling tar acids will be sold as feedstock to a cresylic acid plant for \$300 per ton.

It is presently not economically attractive to convert the gas produced to pipeline gas, although it is technically feasible. The best economic use for this process gas is to burn the gas to supply heat for the mild-gasification process.

Only one of the selected products, the light oil, will not be consumed within AMAX. All other products will be used at the mine or within divisions of AMAX. The internal use will help gain market acceptance for the products.

A preliminary economic evaluation of the process was performed by Stearns-Roger (1988). The evaluation showed that the process may be commercially attractive. This evaluation also reaffirmed our perception that we must develop a low-cost process if we are to achieve commercial success.

Results of the bench-scale mild-gasification tests (Merriam and Cha, 1989) and char-upgrading tests (Jha and McCormick, 1989) are briefly summarized below for the convenience of the reader (Tasks 2 and 3).

WRI conducted 23 successful coal drying tests and 14 successful mild-gasification tests using inclined, fluidized-bed reactors. The tests in the 10-lb/hr reactor ran for four to sixteen hours with most tests maintaining steady-state conditions for eight hours. The effects of bed temperature, particle size, and drying-gas water content on the drying rates and residual moisture content of the dried coal were determined. Coal was readily dried to zero moisture and about 1 wt % of the raw coal was driven off as carbon dioxide by partial decarboxylation at a maximum bed temperature of 575°F (302°C) using a solids residence time of five minutes. The drying rate was slightly slower using 0.050 lb of water per lb of dry carbon dioxide than when 0.030 and 0.015 lb per lb were used. Differences in particle size

from 0.004 to 0.020 inch did not measurably affect the drying rate or residual moisture content of the coal.

The effects of bed temperature, heating rate, coal particle size, solids residence time, and fluidizing-gas composition on the yield of liquid products and the composition of char and gas produced were determined from the mild-gasification tests. The char contained 11 to 19 wt % volatiles, had hydrogen-to-oxygen mass ratios of 0.18 to 0.30, and had heating values of 12,333 to 12,905 Btu/lb. The volatiles content and the hydrogen-to-oxygen ratios of the char were reduced by increasing the maximum bed temperature in the mild gasification reactor from 1100 to 1200°F (590 to 650°C). The hydrogen-to-oxygen mass ratios were greater than the 0.125 value needed to supply hydrogen for formation of water during conversion of carbon, avoiding any need for makeup hydrogen.

Liquid products collected varied from 8.3 to 18.1 wt % moisture- and ash-free (MAF) coal with most of the coal liquids boiling above 700°F (371°C), a characteristic needed for electrode-binder pitch. The median hydrogen-to-carbon atomic ratio of the condensates was 1.23. Maximum liquid yield occurred at a maximum bed temperature of about 1150°F (620°C). The yield of coal liquids increased with higher heating rates in the inlet portion of the mild-gasification bed. We were not able to determine any effect of particle size on yield from 0.004 to 0.020 inch average particle size.

Gas produced had typical heating values of about 675 Btu/scf and contained 30 to 50 vol % carbon monoxide and about 3600 ppm of hydrogen sulfide. A test using steam as the fluidizing gas resulted in production of gas containing about 40 vol % hydrogen.

Evaluation of the chars produced from bench-scale tests showed volatile matter content was correlated with average mild-gasification bed temperature, residence time, and starting coal particle size for most samples. Higher average bed temperatures lead to lower hydrogen content and lower H:O ratios in the chars. These data are consistent with the higher hydrogen content of the mild-gasification liquids relative to the starting coal. The amount of sulfur in the final char is not affected by mild gasification conditions. The amount of nitrogen is lower for chars with a lower volatile matter content (chars produced at higher temperatures). The use of steam in mild gasification produces a low-volatile, relatively low-oxygen char. Surface areas for the chars also correlated with average bed temperature and inversely with volatile matter content. All of the chars exhibited a very open pore structure with most of the surface area in relatively large macropores.

Bench-scale, char gasification (methanation) studies suggest that conversion up to 70 percent can be obtained in less than 2 hours at relatively moderate temperature and pressure. Temperatures in the range of 1290 to 1560°F (700 to 850°C) and pressures of about 200 to 400 psig are adequate.

The use of gasification catalysts appears to offer no advantage in runs conducted in the bench-scale system, in contrast to results obtained in the micro-

fixed bed. Catalysts did not increase the gasification rate; however, they did increase the final conversion obtainable with a given char.

The results of a char reactivity test indicated that there were some significant differences in the chars produced by mild gasification at different conditions. These differences in reactivity could not be conclusively correlated with char properties or with mild gasification conditions. It did appear, however, that chars with a low volatile matter content were less reactive.

The use of steam does not have a beneficial effect on the methane formation rate and can result in gasification of a large portion of the carbon to form carbon oxides.

The results from methane decomposition tests indicated that carbons similar to both thermal blacks and furnace blacks can be produced in an indirectly-heated system. The type of carbon produced depends upon the conditions selected for the reactor. The physical properties of the carbon product can be controlled by varying residence time, temperature, and methane partial pressure. Also, the carbon and hydrogen content can be controlled by varying conditions. If sulfur is present in the feed gas as H_2S , very little will become incorporated into the carbon. Although this will be important in premium fuel and anode carbon applications, the presence of low levels of sulfur does not significantly affect the performance of carbon black in elastomers. The overall test results are summarized as follows:

- The mild-gasification chars have a very open pore structure, relatively low volatile-matter content, and maintain their reactivity when stored in an inert atmosphere.
- Sulfur in the mild-gasification chars is present in a very refractory form, so it is not gasified. The sulfur remains with the spent char or ash.
- A fluidized-bed reactor is the most appropriate choice of reactor design for the char-methanation reactor.
- The production of carbon from methane in indirectly-heated, tubular-reactors was proven to be feasible.
- The carbon produced in this type of reactor has properties that depend on the temperature, gas composition, and residence time employed.
- Carbon samples exhibited particle size distributions, surface areas, and structure similar to those observed for commercial grade thermal and furnace blacks.
- The overall process of conversion of char to high-purity carbon is technically feasible.

3.0 DESCRIPTION OF THE PRUs AND THE MATERIAL PRODUCED BY TESTING

The 100-lb/hr, mild-gasification PRU and the 50-lb/hr, char-to-carbon PRU are described in this section. Materials produced by testing are also described.

3.1 Description of the Mild-Gasification PRU

The mild-gasification PRU (Figure 1) consists of a coal feed system and drying system (left half of Figure 1) and a mild-gasification system (right half). The PRU was designed and the equipment procured by Riley Stoker Corporation. After assembly of the drying and mild-gasification systems at Riley Research Center, the equipment was partially disassembled and shipped to WRI. WRI reassembled the system, added utilities systems, and conducted shakedown tests to locate and fix problems with the equipment (Table 1).

A series of 24-hr and 5-day tests were conducted using the process research unit (PRU) designed by Riley Stoker and assembled by WRI (Merriam et al. 1990). Minus 8 mesh Wyodak coal was fed at rates varying from 93 to 149 lb/hr. The effects of maximum bed temperatures of 950 to 1150°F (510 to 620°C) and coal (char) residence times of five to nine minutes upon the yield and properties of products were determined.

Results of the tests using the PRU indicate the yield of coal liquids increases from about 10 wt % of the MAF coal feed to the mild-gasification reactor when using a maximum bed temperature of 950°F (510°C) to about 15 wt % at 1150°F (620°C). We were not able to test bed temperatures above 1150°F because of the limited heater capacity in the PRU.

The coal liquids are heavy, tarry substances with 55 to 60 wt % boiling in the range of 700+°F (370°C) needed for anode-binder pitch. Typical H/C atomic ratios vary from 1.15 to 1.25. The liquids are sufficiently low in ash content to meet specifications for binder pitch. However, they contain too much hydrogen and oxygen, and the specific gravity is low. Heat treatment of the liquid has been shown to reduce the hydrogen and oxygen content, while increasing the specific gravity.

Figure 1. Process Flow Diagram for Mild-Gasification PRU

The yield of char produced varies from about 42 wt % of the raw coal at a bed temperature of 950°F (510°C) to about 38 wt % at 1150°F (620°C). The char contains 15 to 21 wt % volatiles and is highly reactive in both hydrogen (for gasification) and air (for combustion). Tests at Oak Ridge National Laboratories (Daw 1990) indicate that the char is sufficiently reactive for firing in a wide variety of combustors, possibly including those burning pulverized fuel.

The hydrogen and oxygen content of the char can be controlled by the degree of devolatilization used in the mild-gasification reactor. Increased devolatilization, using higher bed temperature and/or longer residence time, results in reduction of the hydrogen and oxygen contents of the char at different rates.

The rate of oxygen removal from the char is higher than the rate of hydrogen removal at temperatures up to about 1100°F (590°C). Above about 1150°F (620°C) the rate of hydrogen removal greatly exceeds the rate of oxygen removal. Thus, a maximum H:O ratio in the char is obtained when using bed temperatures of 1100 to 1150°F (590 to 620°C). The sulfur content of the char remains essentially constant at different volatiles contents, whereas the nitrogen content decreases with further removal of volatiles.

Gas produced by mild gasification of Wyodak coal using the WRI PRU varies from 4 to 10 wt % of the raw coal with the quantity of gas produced increasing at higher temperatures. Heating value of the gas varies from 550 to 600 Btu/scf with the highest heat content gas produced at higher temperatures. The concentrations of methane, carbon monoxide, and hydrogen in the gas produced increase from about 22 to 34 vol %, 16 to 20 vol %, and 4 to 13 vol %, respectively, as reactor bed temperature is increased from 950 to 1150°F (510 to 620°C).

Closures of mass balances for the ten 24-hour and 5-day tests using the PRU are excellent with only one closure falling outside the range of 98.0 to 103.7%. Elemental balances show that most of the carbon from the raw coal remains in the char, whereas hydrogen is concentrated in the gas, coal liquids, and pyrolysis water. Nitrogen remains mostly in the char, whereas sulfur is distributed roughly in proportion to the weight of the products. Over one-half of the oxygen in the MAF feed coal is converted to gas and water during pyrolysis.

Results of tests with the PRU using raw coal feed rates of 100 to 150 lb/hr agree well with results from tests using the bench-scale system at a feed rate of 10 lb/hr.

The most notable problems with the PRU were caused by occasional plugging in the coal feed line to the dryer and high pressure drop across the air-cooled and water-cooled condensers in the mild-gasification liquid recovery system, also caused by partial plugging. We recommend use of heated outer surfaces on the coal feed hopper and feed screw in addition to the dry-gas purge and vibrator we already use at the feed lockhopper. The warm outer surface will prevent condensation of moisture on the walls of the feed hopper and feed system.

We also recommend the use of two stages of wet-scrubbing as the coal liquid recovery system. The first stage will operate above the dew point of water in the recovery system and also above the pour point of the coal tar. Most of the liquid product (700+ °F/370+ °C boiling range) would be recovered from the first-stage. The second-stage scrubber will operate in the 40 to 100 °F (4 to 38 °C) range depending upon economic tradeoffs, and avoidance of formation of hydrates.

Table 1. Equipment Used in the Mild-Gasification PRU

Bucket Elevator
Coal Feed Hopper
Coal Feed Screw
Inclined Fluidized-Bed Dryer
Inclined Fluidized-Bed Mild Gas Reactor
Dryer Recycle-Gas Blower
Dryer Recycle-Gas Heater
Dryer Cyclone
Bag Filter
Mild-Gasification, Recycle-Gas Blower
Mild-Gasification, Recycle-Gas Heaters (2)
Mild-Gasification Cyclone
Air-Cooled Condensers (6)
Water-Cooled, Dryer Condensers (5)
Water-Cooled, Mild-Gas Condensers (3)
Electrostatic Precipitator
Chilled Condenser
Carbon Dioxide Storage Tank
Exhaust Fan
Coolant Circulating System
Constant Temperature Trailer For Chromatographs
Data-Collection System
Instrument-Air Compressor
Motor-Control Center
Propane-Fired Flare

3.2 Materials Produced by Mild Gasification

The oversized coal (Table 2) was produced as a result of screening the feed coal on 8 mesh screen to prepare -8 mesh coal used for testing. Dried coal was produced during tests in which the dryer only was operated. Detailed analyses of the products have been reported (Merriam et al. 1990). General analyses of dust, fines, and dried coal are shown in Table 7.

Figure 2. Char-to-Carbon PRU Process Flowsheet

Table 2. Materials Produced by Mild-Gasification Tests in the PRU, lb

Material	Weight
Oversized coal	6,900
Fines from drying	3,756
Dust from drying	146
Water from drying	20,639
Gas from drying	681
Dried coal	1,235
Fines from mild gas	3,720
Char	25,679
Gas from mild gas	4,020
Liquids from mild gas	7,614

3.3 Description of the Char-to-Carbon PRU

The CTC PRU (Figure 2) was built in 1990 to process char from the WRI's mild gasification PRU. The plant includes two reactors used for char conversion to methane (methanator) and methane conversion to hydrogen and carbon (carbon reactor). Each reactor system includes a compressor, heat exchanger, heater, and gas filtration system. Also included in the PRU are a membrane for gas separation, emergency generator, baghouse, and two solid metering systems.

The plant was erected in an existing building at AMAX R&D Center in Golden, Colorado, by TIC and AMAX. A portion of the pilot plant facility at AMAX R&D Center was modified for the CTC PRU. Equipment was purchased or fabricated according to specifications and designs prepared by BEI. The equipment was shipped to AMAX R&D Center and installed by TIC and AMAX. AMAX then finished the piping, electrical and control installation and connected all utilities. Shakedown tests were conducted to locate design adjustments. The reactors and auxiliary systems were modified numerous times to improve the process performance. A list of the equipment purchased by AMAX and located in the PRU is presented in Table 3.

Table 3. Char-to-Carbon PRU Equipment

<u>Equipment Name</u>	<u>Manufacture</u>
Heat Exchanger	
CH4 Reactor Feed Flowmeter	
CH4 Reactor Discharge Flowmeter	
Membrane in Flowmeter	
CP-102 Discharge Flowmeter	
Combustor Detectors	ICS Sales/MSA
Combustion Detectors	MSA
Char Feed Lock Hopper Valves	Everlasting Valve Company
Char Discharge Lock Hopper Valve	Everlasting Valve Company
H2 Make-Up Control Valve	
System Bleed Control Valve	
Carbon Lock Hopper Valves	Valvtron
Char Feed Surge Hopper	AMAX
Methane Reactor	Metalcraft Custom Fab.
Reactor Refractory	Braggs Inc.
Spent Char Lock Hopper	AMAX
Carbon Reactor	Metalcraft Custom Fab.
Carbon Lock Hopper	AMAX
Membrane Heater	Watlow
Carbon Heater	I Squared R Element Company
Incolloy Muffle Tubes	Huntingdon Alloy
Membrane Separator	DuPont
Condenser Separator and Trap	Anderson
Moisture Separator and Trap	Anderson
Membrane Heat Trace	Pyrotenax
Char Feed Lock Hopper	AMAX
Carbon Cyclone	Gallagher
Hydrogen Loop Exchanger	Kennedy Tank and Manufacturing
Membrane Condenser	Graham Manufacturing Company
Methane Loop Exchanger	Kennedy Tank and Manufacturing
Lock Hopper Vent Filters	
Condenser Filters	Nowata Filtration
Membrane Filters	Nowata Filtration
Hydrogen Trim Heater	Watlow
Ventilation Blower	AMAX
Air Handler	AMAX
Hydrogen Compressor	Corken
Methane Compressor	Corken
Char Feed Screw	AMAX
Char Discharge Screw	
Carbon Discharge Screw	
Methane Reactor Cyclone	Castel
Carbon Baghouse	Metalcraft
Carbon Reactor Preheater	Watlow
Carbon Reactor Glow Bars (60")	I & R
Emergency Generator	Generac
Lightening Umbrella	LEC Inc.
Methane Fired Flare	John Zinc

The plant was operated for one year from August 1990 to July 1991. The test program encompassed 35 runs (6 shakedown, 10 methanation, 8 carbon formation and 11 integrated runs). The test data have been analyzed and compiled in the form of a topical report. The draft copy was submitted to DOE in October. The following paragraphs present a general summary of plant operation and results.

The plant was heavily instrumented and computer monitored and controlled. These instruments, including the on-line mass spectrometer, worked well except for the turbine flowmeters. The plant start-up and shut down was controlled by computer to insure safe handling of toxic and explosive gases such as methane, hydrogen, and carbon monoxide. The system operated as designed.

The plant consists of two reactors, both of novel design. The methane reactor was designed as a moving-bed reactor on top of a slugging fluidized-bed reactor to take advantage of thermodynamics as well as kinetics. However, it could be operated well only as a fluidized-bed reactor, which required a reduction in bed inventory and, therefore, char residence time. This resulted in lower conversion of char to methane and lower methane concentrations in the exist gas than originally designed. The feed and discharge systems also had to be modified.

The mixed methane-hydrogen gas was passed through a membrane to recover excess hydrogen for recycle and passed on methane-rich gas to the carbon reactor. The unit worked on design specifications, needing no attention, and generating gas as rich as 70 percent methane. The two compressors that recirculated the hydrogen and methane-rich gases worked satisfactorily, although they had to be repaired a few times due to entrapment of fine carbon and/or condensable hydrocarbons.

The methane-rich gas exiting from the membrane was fed to an indirectly-heated fluidized-bed reactor for production of fine and coarse carbons for different target markets. The process operates at lower temperature and higher pressures than the commercial thermal black processes. Heat was supplied by glow bars enclosed in IncolloyTM muffle tubes. During early operation, difficulty was experienced in transferring enough heat. The system was modified to make the tubes vertical, and stainless steel fins (due to their low cost and ready availability) were welded to the tubes for additional heat transfer surface. A baghouse was also added to collect the fine carbon escaping the cyclones. Desulco, a high-purity petroleum coke, was used as a seed material.

The results indicated both the formation of fine carbon and growth of seed carbon particles. However, pyrolytic carbon formation on the heat transfer tube surface restricted heat transfer and resulted in lower conversions of methane to carbon. Corrosion and erosion of Incolloy tubes and particularly the stainless steel fins resulted in fine metal powders contaminating the product. Weakening of the tubes made their further use at high temperatures and pressures questionable.

In summary, the operation of the PRU provided the proof of concept for the CTC process. However, the carbon reactor design did not work due to a materials of

construction problem, and an alternative design will have to be employed when the process is scaled up.

3.4 Materials Produced by Upgrading Char

Char received from WRI was fed to the CTC PRU and processed to produce carbon, spent char, and by-product liquids. Approximately 4,000 pounds of char was processed, resulting in 2,700 pounds of spent char and 400 pounds of carbon. Seed carbon was purchased and used in the carbon reactor to initiate carbon nucleation. The seed carbon, desulco, and lampblack were purchased and tested for their impact on carbon conversion. Table 4 presents the solid and liquid materials, feedstocks, and products that resulted from the PRU operation.

Table 4. Materials from Char-to-Carbon PRU

Material	Weight, Pounds
Feed Char	22,000
Spent Char	2,700
Solvent	2,500
Water/By-product Liquids	1,200
Product Carbon	400
Lampblack	1,000
Desulco	2,000

4.0 DECONTAMINATION AND DISASSEMBLY OF THE PRUs

Our approach to removing the PRUs and freeing the respective work areas for other use is described in this section.

4.1 Decontamination and Disassembly of the Mild-Gasification PRU

The mild-gasification PRU has five different levels of contamination:

1. Equipment which was not contacted by coal or any of the products of mild gasification and, therefore, requires no decontamination. This includes the data acquisition system, the instrument air compressor, the gas analysis trailer, etc.
2. The coolant system that is contaminated by a solution of ethylene glycol and water.

3. The clean portion of the drying-gas, recycle loop from the bag filter to the drying reactor. This equipment has been contacted by recycle gas and condensing water only. No cleaning is necessary.
4. The coal flow path from the bucket elevator through the dryer. This includes the coal feed system, the dryer, the dryer cyclone, and the bag filter. This equipment is contaminated with coal dust.
5. The mild-gasification system including the condenser drain lines, the gas vent line to the flare, and the coal liquid containers. This equipment is contaminated with coal liquids that are known to contain carcinogens.

The equipment subjected to only level 1 contamination requires no special decontamination before or during disassembly. The coolant will be drained from the equipment having level 2 contamination and stored for reuse. Equipment from the area defined as having level 3 contamination will be inspected. Any equipment found in level 3 which is contaminated with coal dust or tars will be reclassified as level 4 or 5 and cleaned using the procedures specified for levels 4 and 5.

Equipment having level 4 contamination (coal dust) will be washed using high-pressure water. The coal dust will be removed from the water by settling followed by filtration. By reusing the water, we can perform all of the level 4 decontamination with less than 500 gallons of water.

WRI standards for employee health and hygiene must be rigorously adhered to while cleaning the equipment having level 5 contamination. The coal tars contain carcinogens. Care must be taken to avoid ingestion, inhalation, or prolonged skin contact.

We plan to clean the process side of the water-cooled condensers, the electrostatic precipitation, and the chilled condenser using a solvent. This cleaning will be done with the condensers in place. The condensers and associated piping will be disassembled and any remaining coal tars will be burned from the equipment using a relatively low-temperature flame to avoid damage to the equipment. The contaminated solvent will be incinerated using the procedure from section 5.0 of this report.

The high-temperature part of the mild-gasification system will be cleaned by chipping the brittle deposits from the heaters, the reactors, and the cyclone. The carbonaceous scale will be removed from the pipes by vibration or by burning, if necessary. The scale will be burned. Ash will be hauled to a nearby landfill.

4.2 Decontamination and Disassembly of the Char-to-Carbon PRU

AMAX R&D Center will continue testing with the CTC PRU and make necessary modifications to optimize the process. There are specific process modifications which should improve the process performance and economics. These

changes will be made, and the plant will be operated using char feedstocks from WRI. After the tests have been completed, the plant will be decontaminated and disassembled.

The CTC PRU will be decontaminated by burning off any residue remaining in portions of the process piping. This will be followed by a solvent wash if the piping sections are found to contain any remaining residue. The plant will then be disassembled. Equipment purchased by AMAX will be stored and extraneous materials will be discarded. After all equipment is removed from the building, repairs to the structure and interior will be completed.

Parts of the CTC PRU will contain residue left from operating the plant. The residue can be removed by providing a high temperature, oxidizing environment in the associated equipment and piping. This will be achieved by using compressed air and operating the PRU with an inert solids heat transfer medium such as silica. Temperatures in excess of 1,000 °F can be achieved in nearly all of the process piping. The combustion gases will be vented through the methane flare to ensure all reactants are fully combusted.

After the process piping and reactors have been burned out, the PRU will be shut down and inspected for contamination. Any suspect equipment or piping will be flushed with acetone. Workers will be properly protected to perform this solvent cleaning, and special care will be taken to collect all of the solvent. Any residual acetone will then be collected by a solvent collection and disposal firm for use as a fuel. Proper documentation of handling and disposal of the solvent will be followed.

The PRU will be disassembled after the piping and equipment have been cleaned. The piping will be removed and sent to an iron salvage company. The equipment will be removed and stored on site for future use.

The building which housed the PRU will be repaired after the equipment has been removed. Structural repairs to the roof, floors, and walls will be completed. The building will be returned to its original configuration.

5.0 DISPOSAL OF MATERIALS PRODUCED BY TESTING

The methods we plan to use to dispose of the materials remaining after testing is completed are described in this section.

5.1 Disposal of Products from Mild-Gasification Tests

Some of the products from mild-gasification tests have already been disposed of because it was not practical or cost-effective to keep some materials. Oversize coal (plus 8-mesh) was hauled to a nearby power plant and burned as fuel. Gas produced by drying was vented into the atmosphere. Water from drying was cleaned and put into the municipal water treatment plant. The product char, except for retained

samples, was shipped to AMAX and used as feed for char-upgrading tests. Gas produced by mild gasification was burned in the propane-fueled flare.

We disposed of the water produced by drying coal to avoid having to store the water in a heated place during the winter. Our attempt to dispose of the water by evaporation from an open tank was not successful because of unusually rainy weather. Also, temperature upsets in the dryer, particularly during tests using feed rates of 150 lb/hr, caused the water from later tests to become more contaminated than the water from earlier tests.

The Wyoming Department of Environmental Quality and the Laramie Water Department agreed that the 1500 gallons of water from drying be cleaned to less than 300 ppm of total organic carbon (TOC) and the clean water fed into the municipal water-treatment plant over a period of three days. The water was passed through two millipore filters and a drum containing straw to remove large solids. The liquid was then filtered through activated carbon. The TOC was reduced from a maximum of 1327 ppm to an average of 177 ppm. (Table 5). After cleaning, we fed all of the water produced by drying coal into the municipal treatment plant.

Table 5. Composition of Water Produced by Drying Coal

Compound	Dirty	Cleaned
Benzene, ppb	143	ND ^a
Toluene, ppb	28	1
Xylenes, ppb	3	ND
Phenols, ppb	740	170
TOC, ppm	1327	177

^a ND indicates compound was not detected.

The quantity of crude, coal liquids remaining for disposal was reduced by 1065 lb after liquid produced during test 122 was distilled. Thus, we have the materials listed in Table 6 remaining for disposal. Some of the materials listed may be consumed by testing, thereby further reducing the quantity of materials remaining for disposal.

Table 6. Materials Remaining from Mild-Gasification Tests, lbs

Fines from drying	3756
Dust from drying	146
Dried coal	1235
Fines from mild gasification	3720
Liquids from mild gasification	6549

The fines, dust, and dried coal all have about the same composition (Table 7). The moisture content of the solid products varies from about six wt% in the fines from the dryer to zero in the dried coal and the fines from mild gasification.

Table 7. Proximate Analyses for Fines, Dust, and Dried Coal, wt % (moisture free)

	Volatile Matter	Fixed Carbon	Ash
Dust from filter	41.8	51.4	6.8
Fines from dryer	44.9	46.8	8.3
Dried coal	39.4	51.0	9.6
Fines from mild gasification	40.3	51.4	6.8

We tested low-cost disposal of the fines from the dryer by dumping 2 drums of the fines in the city landfill. The fines caught fire and the fire spread into the landfill. The city landfill will not accept any more of the fines. We plan to dispose of the remaining fines, dust, and dried coal by burning them.

The liquids produced by mild gasification are about one-third water and two-thirds hydrocarbons. The hydrocarbons contain known carcinogens such as benzene, anthracene, and pyrene. Thus, great care must be taken to assure that good health and hygiene practices are followed during disposal and that the liquids are completely destroyed. We plan to use a two-stage incineration system to dispose of the coal liquids. We will construct the first-stage incinerator and attach it to an existing gas-fired incinerator. This 2-stage system will burn 50 lb/hr of the coal liquids. The liquid will be burned in the first stage, and the products of combustion will be exposed to 1800°F in an oxidizing environment in the second stage. This will assure complete destruction.

5.2 Disposal of Products from Char-Upgrading Tests

The products from the char-to-carbon PRU are primarily spent char and char feedstock from the WRI mild-gasification PRU. Both of these solid products will be returned to the Eagle Butte Mine from where the coal originally came. The other products of much lesser amounts are carbon and by-product liquids. The carbon will also be sent back to the Eagle Butte Mine, as it is a product from the process. The composition of the solids which will be disposed are presented in Table 8.

Table 8. Solid Products Composition

Material	Carbon	Hydrogen	Sulfur	Ash
Spent Char	86.0	1.0	0.5	10
Product Carbon	87.0	0.2	0.0	13
Lampblack	99.6			
Desulco	99.9			

The liquid collected from condensers (approximately 150 gallons) is primarily water contaminated by hydrocarbons, which will be reduced in volume by evaporation and sent to an oil recycling company. The liquids will be combined with oil for use as a fuel by the recycling company. The composition of the liquids are shown in Table 9.

Table 9. Liquid Products Composition

Material	ppm			Weight %
	Phenols	Sulfide	Oil	Acetone
Water By-Product	328	0.55	10	0
Solvent	0	0	0	100

Solvent analyses are of solvent before use.

6.0 COST OF DECONTAMINATION, DISASSEMBLY, AND DISPOSAL

The estimated costs for decontamination and disassembly of the mild-gasification and char-to-carbon PRUs and disposal of products are presented in 1991 dollars.

6.1 Mild Gasification

WRI plans to dispose of the materials produced by mild-gasification tests during the summer of 1992, provided that funding is available. However, we plan to use the PRU for additional tests and do not want to disassemble the PRU until the summer of 1993. Costs for disposal of the materials produced by mild gasification (Table 10) and disassembly of the PRU (Table 11) are shown separately because of the difference in proposed time of performance.

Table 10. Cost of Disposal of Dust, Fines, Dried Coal, and Liquids from Mild-Gasification

	Hrs	Rate	\$
Direct Labor			
Division Manager	80	28.00	2,240
Senior Research Engineer	280	30.00	8,400
Master Technician	80	17.00	1,360
Technician 3	920	12.00	<u>11,040</u>
			\$23,040
Fringe Benefits 23% DL			5,300
Labor Overhead 16% DL			<u>3,686</u>
			\$32,026
Materials			
Combustor			3,200
Feed pump			1,600
Solvent - 400 gallons			<u>800</u>
			\$37,626
General Overhead - 92%			34,616
Total Cost			<u>\$72,242</u>
Fee - 5%			3,612
Total Cost Plus Fee			<u>\$75,854</u>

Table 11. Cost for Decontamination and Disassembly of the Mild-Gasification PRU

	Hrs	Rate	\$
Direct Labor			
Division Manager	120	28.00	3,360
Senior Research Engineer	570	30.00	17,100
Master Technician	570	17.00	9,690
Technician 3	1,730	12.00	20,760
			<u>\$50,910</u>
Fringe Benefits, 23% DL			11,709
Labor Overhead, 16% DL			<u>8,146</u>
			\$70,765
Materials			
Solvent - 1,000 gallons			2,000
Propane - 1,000 gallons			750
Containers - 20 drums			900
Personnel Protective Equipment			1,500
Corrugated Roofing Sections			4,000
Services			
Crane Rental - 3 days			3,600
Tool Rental			<u>400</u>
			\$83,915
General Overhead - 92%			<u>77,202</u>
Total Cost			\$161,117
Fee - 5%			8,056
Total Cost Plus Fee			\$169,173

6.2 Char Upgrading

Amax R&D Center plans to dispose of the materials produced by the char-to-carbon PRU in 1992. Disassembly of the PRU is not planned until 1993. Estimated costs for disposal are presented in Table 12 and costs for disassembly are shown in Table 13. Costs in both of these tables are in 1991 dollars.

Table 12. Char-to-Carbon Materials Disposal Cost Estimate

Labor	
Project Engineer, 120 Hours at \$25/Hour	\$3,000
Chemist, 80 Hours at \$19/Hour	1,520
Lead Technician, 120 Hours at \$14.50/Hour	1,740
Technician, 200 Hours at \$10/Hour	<u>2,000</u>
Total Direct Labor	\$8,260
 Fringe Benefits at 45% of DL	3,681
Labor Overhead at 30% of DL + FB	3,558
Indirect at 60% of DL + FB + LO	<u>9,252</u>
Total Labor	24,751
 Materials	
10 Barrels at \$40/Barrel	\$400
30 Pallets at \$10/Pallet	300
Solvent, 6 Barrels at \$200/Barrel	1,200
1 Recycle Pump at \$2,000	<u>2,000</u>
 Total Materials	 \$3,900
 Services	
Transportation, 180 Barrels at \$10/Barrel	\$1,800
Solvent Disposal, 6 Barrels at \$150/Barrel	<u>900</u>
 Total Services	 \$2,700
 Total Cost	 \$31,351

Table 13. Char-to-Carbon Equipment Disassembly Cost Estimate

Labor	
Project Engineer, 600 Hours at \$25/Hour	\$14,520
Mechanic, 800 Hours at \$15/Hour	12,000
Lead Technician, 480 Hours at \$14.50/Hour	6,960
Technician, 480 Hours at \$10/Hour	<u>4,800</u>
Total Direct Labor	\$38,280
Fringe Benefits at 45% of DL	\$17,226
Labor Overhead a 30% of DL + FB	16,652
Indirect at 60% of DL + FB + LO	<u>43,295</u>
Total Labor	\$115,453
Materials	
Welding/Cutting, Miscellaneous Supplies	\$1,000
Roofing Sections	3,500
Solvent, 6 Barrels at \$200/Barrel	1,200
Decking, 10 Sections at \$50/Section	500
Protective Equipment	<u>1,500</u>
Total Materials	\$7,700
Services	
Haulage	\$500
Solvent Disposal, 6 Barrels at \$150/Barrel	900
Crane, 3 Days	3,600
Mechanical, 3 Men for 8 Weeks	<u>33,600</u>
Total Services	\$38,600
Total Cost	\$161,753

7.0 PROPOSED SCHEDULE

The times for the proposed disposal of materials and decontamination and disassembly of the PRUs are listed in Table 14.

Table 14. Proposed Schedule

<u>Mild Gasification</u>	
Disposal of Materials	August - September 1992
Disassembly of PRU	April - July 1993
<u>Char Upgrading</u>	
Disposal of Materials	1991-1992
Disassembly of PRU	1993

8.0 REFERENCES

- Cha, C.Y., N.W. Merriam, M.C. Jha, and R.W. Breault, 1988, Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products, Topical Report for Task 1, Literature Survey and Market Assessment. DOE Report, DOE/MC/24268-2700.
- Daw, C.S., R.L. Graves, R.P. Krishnan, B.H. West, A.L. Compere, W.L. Griffith, 1990, Mild-Gasification Product Characterization--1990 Results, Proceedings of Tenth Annual Gasification and Gas Stream Cleanup Systems Contractor Review Meeting, METC, Morgantown, WV, in press.
- Hogsett, R.F., and M.C. Jha, 1991, Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, Topical Report for Task 4.6, Technical and Economic Evaluation. AMAX R&D Center, Golden, CO, Morgantown Energy Technology Center, DOE, in press.
- Jha, M.C., and R.L. McCormick, 1989, Development of an Advanced, Continuous Mild Gasification Process for the Production of CoProducts, Topical Report for Task 3, Bench-Scale Char Upgrading and Utilization Study, AMAX R&D Center, Golden, CO.
- Jha, M.C., R.L. McCormick, R.F. Hogsett, R.M. Rowe, and K.R. Anast, 1991, Development of an Advanced, Continuous Mild-Gasification Process for the Production of Coproducts, Topical Report for Task 4, System Integration Studies--Char Upgrading. AMAX R&D Center, Golden, CO, Morgantown Energy Technology Center, DOE, in press.
- Merriam, N.W., and C.Y. Cha, 1989, Development of an Advanced, Continuous Mild Gasification Process for the Production of CoProducts, Task 2 Topical Report, Mild Gasification Tests, Western Research Institute, Laramie, WY, WRI-91-RO18.
- Merriam, N.W., C.Y. Cha, T.W. Kang, and M.B. Vaillancourt, 1990, Development of an Advanced, Continuous Mild-Gasification Process for the Production of CoProducts, Topical Report for Task 4 - Mild Gasification Tests. Western Research Institute, Laramie, WY, WRI-91-RO29.
- The Ralph M. Parsons Company, 1991, Preliminary Engineering Design and Cost Estimate for a 20-Tons/Day Coal Mild-Gasification and Product Upgrading Process Development Unit (PDU). AMAX R&D Center, Golden, CO, Morgantown Energy Technology Center, DOE.
- Stearns-Roger, Division of United Engineers and Constructors, 1988, Engineering Evaluation and Cost Estimate of an Advanced Continuous Mild-Gasification Process. AMAX R&D Center, Golden, CO, Morgantown Energy Technology Center, DOE.

END

**DATE
FILMED**
9/16/92