DOE/PC/89877-10
JUL 17 1992

CATALYST DISPERSION AND ACTIVITY UNDER CONDITIONS OF TEMPERATURE-STAGED LIQUEFACTION

DOE/PC/89877--10

DE92 017296

Technical Progress Report for the Period
January to March 1992

by

Alan Davis, H.H. Schobert, G.D. Mitchell
and L. Artok

RECEIVED
USDOE/PETC
92 JUL 13 PM 12:10

Energy and Fuels Research Center and Fuel Science Department
The Pennsylvania State University
University Park, PA 16802

Date Published, July 1992

PREPARED FOR THE UNITED STATES
DEPARTMENT OF ENERGY
under
Contract No. DE-AC22-89PC89877

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. References herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

Two coals, a Texas subbituminous C and a Utah high volatile A bituminous, were used to examine the effects of solvent swelling and catalyst impregnation on liquefaction conversion behavior in temperature-staged reactions for 30 minutes each at 275° and 425°C in H₂ and 95:5 H₂:H₂S atmospheres. Methanol, pyridine, tetrahydrofuran, and tetrabutylammonium hydroxide were used as swelling agents. Molybdenum-based catalyst precursors were ammonium tetrathiomolybdate, molybdenum trisulfide, molybdenum hexacarbonyl, and bis(tricarbonylcyclopentadienyl-molybdenum). Ferrous sulfate and bis(dicarbonylcyclopentadienyliron) served as iron-based catalyst precursors. In addition, ion exchange was used for loading iron onto the subbituminous coal. For most experiments, liquefaction in H₂:H₂S was superior to that in H₂, regardless of the catalyst precursor. The benefit of the H₂S was greater for the subbituminous, presumably because of its higher iron content relative to the hvAb coal. Tetrabutylammonium hydroxide was the only swelling agent to enhance conversion of the hvAb coal significantly; it also caused a remarkable increase in conversion of the subbituminous coal. The combined application of solvent swelling and catalyst impregnation also improves liquefaction, mainly through increased oil yields from the hvAb coal and increased asphaltenes from the subbituminous. A remarkable effect from use of ammonium tetrathiomolybdate as a catalyst precursor is substantial increase in pristane and phytane yields. Our findings suggest that these compounds are, at least in part, bound to the coal matrix.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	iii
PROGRAM OBJECTIVES	1
PROGRAM OUTLINE	1
Catalyst Transformation	1
Catalysts and Their Dispersion	2
Coal Pretreatment	3
Evaluation of Impregnated Coals and Residual Materials from Other DOE Programs	4
DESCRIPTION OF TECHNICAL PROGRESS	6
1. THE EFFECT OF CATALYST PRECURSOR AND ATMOSPHERE ON LIQUEFACTION OF COALS	6
OPTICAL MICROSCOPY OF LIQUEFACTION RESIDUES	7
APPENDIX	
SWELLING PRETREATMENT OF COALS FOR IMPROVED CATALYTIC TEMPERATURE-STAGED LIQUEFACTION	9
Introduction	10
Experimental Section	12
Catalyst preparation and testing	12
Coal sampling and characterization	13
Impregnation of coals with catalyst precursors	13
Analysis of liquefaction products	16
Results and Discussion	17
Catalyst precursor transformation	17
Comparison of catalyst precursors for the liquefaction of coals	20
Effect of preswelling on liquefaction	31
Characterization of selected products	36
Summary and Conclusions	48
Acknowledgement	50
References	50

PROGRAM OBJECTIVES

The general objectives of this research are 1) to investigate the use of highly dispersed catalysts for the pretreatment of coal by mild hydrogenation, 2) to identify the active forms of the catalysts under reaction conditions and 3) to clarify the mechanisms of catalysis. The ultimate objective is to ascertain if mild catalytic hydrogenation resulting in very limited or no coal solubilization is an advantageous pretreatment for the transformation of coal into transportable fuels. The experimental program will focus upon the development of effective methods of impregnating coal with catalysts, evaluating the conditions under which the catalysts are most active and establishing the relative impact of improved impregnation on conversion and product distributions obtained from coal hydrogenation.

PROGRAM OUTLINE

Catalyst Transformation

Four catalyst materials have been selected for this investigation: ammonium tetrathiomolybdate, ferrous sulfate, molybdenum hexacarbonyl, and iron pentacarbonyl. Insofar as it is possible, these catalysts will be evaluated by TGA in order to determine 1) the temperature at which a chemical change occurs in the catalyst precursor, 2) the holding time at that temperature needed to reach completion of the transformation, and 3) and effects of heating rate on catalyst precursor transformation. Experiments will be performed for each catalyst for a matrix of conditions,

as follows: 1) three heating rates: 5°, 50°, and about 125°C/min; 2) three final temperatures: 275°, 350°, and 425°C; 3) two atmospheres, namely nitrogen and hydrogen; and 4) one "soak time" at temperature (1 h). Also, in order to define the heating regimes over which both catalysts and coals decompose, each of the two test coals will be evaluated in the TGA under the same reaction conditions employed with the catalysts.

Each of the catalyst precursors will be tested in 25 Ml microautoclaves (tubing bombs) in order to prepare larger quantities of the transformed materials for subsequent characterization. The time-temperature regimes used in these experiments will be selected based on results from the TGA study. Three atmospheres will be used: 1) nitrogen, 2) hydrogen, and 3) 95:5 hydrogen:hydrogen sulfide. In each of these experiments the tubing bomb will be pressurized to 1000 psi (cold).

Catalysts and Their Dispersion

The purpose of this portion of the research effort is to investigate methods of impregnating coal with catalysts prior to liquefaction. A variety of techniques that are best suited for a particular catalyst will be explored. Those planned include:

- a) using the ammonium tetrathiomolybdate or ferrous sulfate in aqueous solution; the coals will be slurried with the solution of catalyst precursor and then freeze-dried;
- b) these same precursors will be applied to coal in solvents that are known to swell coal structures; THF, pyridine, methanol and tetrabutylammonium hydroxide. However, the catalyst materials must be either soluble or form a fairly stable suspension in the appropriate solvent in order to promote access of catalyst to interior surfaces of the coal;
- c) iron pentacarbonyl and molybdenum hexacarbonyl will be applied to

coal in hydrocarbon or other organic solvents that may promote coal swelling;

- d) ion exchange of iron, as ferrous sulfate, onto the lignite selected for this project will also be investigated.

With some basic information with respect to solvent and catalyst interactions, both individual large particles and fine particulate samples of each coal will be impregnated or ion-exchanged with the catalyst, and the dried sample prepared and observed under the SEM to determine the extent of impregnation and dispersion of the catalyst.

Coal Pretreatment

Two coals, a lignite and an hvCb, will be selected from the Penn State Sample Bank in consultation with DOE. Each coal will possess high vitrinite and low sulfur contents and ash yields, and will have been thoroughly characterized by proximate and ultimate analyses, maceral and reflectance analyses, as well as major and trace elements.

The principal objective of this work is to explore the influences of catalyst presence, dispersion and chemistry on coal pretreatment. All experiments will be carried out in 25 Ml microautoclave reactors, under 1000 psi (cold) pressure and using a nominal 5 g of coal and 5 g of vehicle. The time-temperature regimes will be defined on the basis of results obtained from the catalyst transformation investigations. Temperature-staged liquefaction consists of two distinct steps, the low-temperature pretreatment and the high-temperature liquefaction reaction. The main focus of this work is on pretreatment, and therefore most of the experiments will be carried out in the range of 275°-350°C. In order to

assure that the pretreatment stage has been effective in converting the starting coal into an "active coal" intermediate, a limited number of experiments will be performed incorporating the second, high-temperature stage (425°C) as well. The gas atmosphere will be hydrogen. If tests from the catalyst transformation work are encouraging, additional experiments will be performed in 95:5 H₂:H₂S atmospheres.

Experiments will be run without catalyst to obtain baseline data and with each of the four catalyst precursors. The level of catalyst loading will be chosen to ensure that the amount of metal left in the residue is detectable by the planned characterization techniques. Also, catalyst loading will be adjusted so that the same loading on a gram-atom basis is achieved for the iron and molybdenum. Furthermore, the experiments will be run with and without a hydrogen-donor vehicle. It is planned to use phenanthrene as a non-donor vehicle and dihydrophenanthrene as a donor vehicle.

Following liquefaction, a variety of conventional techniques will be used to characterize gaseous, liquid and solid products. Gases will be routinely analyzed by gas chromatography. Oils and asphaltenes will be routinely analyzed by GC, GC/MS, and ¹H NMR, and by FTIR and ¹³C (solution) NMR for selected samples. Selected samples of the solid residue will be characterized by DRIFT, ¹³C (solid) NMR and optical and electron optical microscopy.

Evaluation of Impregnated Coals and Residual Materials from Other DOE Programs

Impregnated coals and liquefaction residues will be solicited from DOE

and its contractors for microscopic study of materials generated in larger scale experiments than ours, and through other novel approaches to hydrogenation. Samples also will be sought from projects that are developing unique techniques for the impregnation of catalyst into coals for liquefaction. It is expected that many of these samples will come from PETC and the Advanced Research program to assess the degree of catalyst dispersal and to assess the relative extent of hydrogenation and condensation reactions.

DESCRIPTION OF TECHNICAL PROGRESS

1. THE EFFECT OF CATALYST PRECURSOR AND ATMOSPHERE ON LIQUEFACTION OF COALS

As noted in our last quarterly progress report, all of the experimental work concerning coal pretreatment and product work-up has been completed. Now, most of the data synthesis has also been undertaken. Three manuscripts have been prepared for publication as part of the technology transfer process, two of which have been included in prior technical progress reports. The first of these dealt with the results of experiments in which the improvement in liquefaction obtained by swelling pretreatment was investigated. The second reported results of studies into the effects of addition of catalyst precursor and of reaction atmosphere (H_2 ; H_2/H_2S) on temperature-staged liquefaction.

The report appended herewith is entitled "Swelling Pretreatment of Coals for Improved Catalytic Temperature-Staged Liquefaction"; it deals with the effects of swelling pretreatment upon reaction in the higher temperature stage of staged liquefaction. The third report has been submitted to Energy & Fuels for publication. The text of this report appears in the Appendix.

OPTICAL MICROSCOPY OF LIQUFACTION RESIDUES

A systematic qualitative characterization of twenty liquefaction residues has been completed using optical microscopy. The samples were about equally divided between runs made with Blind Canyon (DECS-6) and Texas subbituminous (DECS-1) coals. For each coal, residues from runs at pretreatment and temperature-staged conditions were selected based on process conditions and coal treatment, i.e., presence or absence of catalysts, swelling solvents and different gas atmospheres. Generally, this investigation has demonstrated that reaction conditions have separate influences on the different coals during pretreatment. For the hvAb Blind Canyon coal, reaction at 275°C under 7 mPa hydrogen pressure results in some minor agglomeration of coal particles which suggests that coal particles become sticky along their edges. Other than this no large-scale deformation of coal particles was observed. However, the influence of solvent pre-swelling and the addition of active catalyst not only enhanced particle plasticity, but in some cases, contributed to rather large-scale particle deformation and agglomeration. Reaction of Blind Canyon coal pre-swollen with 10% tetrabutylammonium hydroxide (TBAH) in the presence of ammonium tetrathiomolybdate (ATTM) had the most profound influence on particle plasticity and agglomeration. Total conversion for this run was slightly lower compared with experiments where TBAH and ATTM were employed separately, thus suggesting that particle agglomeration resulting from coal plasticity may be detrimental to mass transport of hydrogen to catalyst/coal interfaces. The experimental condition that resulted in the

greatest conversion at 275°C (i.e., pre-swelling with pyridine, an Mo(CO)_6 catalyst using 95:5 H_2 : H_2S atmosphere) also showed signs of particle agglomeration, but not particle plasticity. Agglomeration in this sample was caused by the presence of a presumably high molecular weight liquefaction product that was insoluble in the extraction solvent (THF).

In comparison, pretreatment using the Texas subbituminous coal generally showed particle size reduction resulting presumably from desiccation. No other signs of reaction were observed even when pyridine was used as a pre-swelling agent. However, swelling of this coal with TBAH caused enlargement of coal particles with separations of 1-5 μm along bedding planes. Reaction along these new surfaces must have occurred, as total conversion was the greatest with this swelling solvent in the absence of catalyst. The combined use of active catalysts (Fe(CO)_5 and Mo(CO)_6 in 95:5 H_2 : H_2S atmosphere) and TBAH resulted in coal particle swelling, plasticity and minor agglomeration, features which contributed to increased total conversion under these reaction conditions.

From this investigation, we begin to understand some of the relationships between the effects of swelling agents and catalysts on coal residue properties that may effect mass transport during second-stage reactions. The next phase of this research will employ SEM and microprobe techniques to determine the location and interrelationships of catalyst material with the residue materials under pretreatment conditions.

APPENDIX

SWELLING PRETREATMENT OF COALS FOR IMPROVED CATALYTIC TEMPERATURE-STAGED LIQUFACTION

Swelling Pretreatment of Coals for Improved Catalytic Temperature-Staged Liquefaction

Levent Artok¹, Alan Davis[†], Gareth D. Mitchell[†], and Harold H. Schobert[‡]

[‡]Fuel Science Program, Department of Materials Science and Engineering, and

[†]Energy and Fuels Research Center, The Pennsylvania State University,
University Park, Pennsylvania, 16802

Two coals, a Texas subbituminous C and a Utah high volatile A bituminous, were used to examine the effects of solvent swelling and catalyst impregnation on liquefaction conversion behavior in temperature-staged reactions for 30 minutes each at 275° and 425C° in H₂ and 95:5 H₂:H₂S atmospheres. Methanol, pyridine, tetrahydrofuran, and tetrabutylammonium hydroxide were used as swelling agents. Molybdenum-based catalyst precursors were ammonium tetrathiomolybdate, molybdenum trisulfide, molybdenum hexacarbonyl, and bis(tricarbonylcyclopentadienyl-molybdenum). Ferrous sulfate and bis(dicarbonylcyclopentadienyliron) served as iron-based catalyst precursors. In addition, ion exchange was used for loading iron onto the subbituminous coal. For most experiments, liquefaction in H₂:H₂S was superior to that in H₂, regardless of the catalyst precursor. The benefit of the H₂S was greater for the subbituminous, presumably because of its higher iron content relative to the hvAb coal. Tetrabutylammonium hydroxide was the only swelling agent to enhance conversion of the hvAb coal significantly; it also caused a remarkable increase in conversion of the subbituminous coal. The combined application of solvent swelling and catalyst impregnation also improves liquefaction, mainly through increased oil yields from the hvAb coal and increased asphaltenes from the subbituminous. A remarkable effect from use of ammonium tetrathiomolybdate as a catalyst precursor is substantial increase in pristane and phytane yields. Our findings suggest that these compounds are, at least in part, bound to the coal matrix.

Introduction

Reaction pathways during the initial stages of coal liquefaction are likely to be driven predominantly by thermal reactions. The thermally derived radicals must be stabilized promptly to prevent retrogressive reactions which could lead to the formation of refractory, high-molecular weight-species such as those found in preasphaltenes and asphaltenes. In particular, low-rank coals have a higher tendency to undergo condensation reactions.

The large number of oxygen functionalities in low-rank coals is one of the most important factors affecting their tendency to participate in retrogressive reactions. Phenolic and carboxylic functional groups are known to be involved in polymerization reactions. The radicals formed during heat-up

¹Present address: Department of Chemistry, Cukurova University, Adana 0110, Turkey

of the coal can participate in a number of competing reactions (e.g., hydrogenation and condensation). When a catalyst is not available, gas-phase, molecular hydrogen is not sufficiently reactive to quench promptly all the radicals formed. Therefore, a good hydrogen-donor solvent, an active catalyst, or both are necessary to achieve a fast transfer of hydrogen to the reactive sites. A good donor solvent capable of a high degree of contact with the coal surface can limit condensation reactions by donating its own hydrogen to the nascent radicals. However, a solvent itself is not sufficient to drive hydrocracking reactions of asphaltenes to lower molecular weight products in relatively short liquefaction reaction times (1-30 min). A catalyst with high activity (e.g., MoS_2) dissociates molecular hydrogen molecules into active hydrogen atoms that stabilize radicals promptly and facilitate the hydrogenolysis of carbon-carbon and carbon-oxygen bonds. Unfortunately, solid catalysts have the disadvantage of not being accessible to all the reactive sites of the coals. For that reason, coals generally can be solubilized in a good donor solvent (even in the absence of catalyst) to a greater extent than during dry catalytic liquefaction (i.e., liquefaction in the absence of solvent). Nevertheless, a catalyst is essential for the rehydrogenation of dehydrogenated solvent and for facilitating the further reactions which are necessary to obtain liquid yields of high quality, such as hydrocracking of heavy products and hydrodesulfurization or hydrodenitrogenation.

Viable alternatives to minimize retrogressive reactions include pretreating the coals before liquefaction experiments and utilizing the catalyst more efficiently by enhancing its dispersion. Pretreatment methods include low-temperature hydrogenation (often carried out as the first stage of a temperature-staged liquefaction), chemical treatment methods and solvent swelling techniques. The favorable effect of a low-temperature hydrogenation step on liquefaction has been demonstrated,¹⁻³ and was attributed to an inhibition of retrogressive reactions.⁴ A recent example of the beneficial effect of chemical treatments is the work of Baldwin *et al.*, who reported that the alkylation of coals improved liquefaction.⁵ Rincon and Cruz were the first to report the beneficial effect of tetrahydrofuran (THF) preswelling on liquefaction.⁶ Later, Joseph established a direct correlation between the extent of preswelling and the conversion of coal under liquefaction conditions.⁷ We have also found that preswelling was beneficial for conversion at a pretreatment temperature of 275° C (refs. 8,9).

A more efficient catalyst dispersion (smaller particle sizes and deeper pore penetration) on coal increases the coal-catalyst surface contact per unit catalyst, thus resulting in improved conversion. Weller and Pelipetz were the first to point out the importance of catalyst dispersion for promoting the conversion of coals under liquefaction conditions.¹⁰ Dispersed-phase catalysts for direct coal liquefaction have been thought to be more efficient than insoluble catalysts¹¹⁻¹³. Impregnation of coals using water- or oil-soluble catalyst precursors should enhance their dispersion. The decomposition of these catalyst precursors into a catalytically active form in the initial stage of liquefaction improves conversion.^{8, 9, 14-18} Cugini *et al.*¹⁹ found that it is possible to have a high yield of liquids when using a well-dispersed

iron catalyst, as high as obtained from a molybdenum catalyst. The extent to which catalyst can be dispersed on coal is highly dependent on the properties of the coal (e.g., surface functionalities and porosity), and on the type of catalyst precursor used. Impregnation techniques can be accompanied by an undesirable agglomeration of the catalyst particles during the removal of the impregnation solvent, and by inability of the catalyst precursor to penetrate the pores within coal structure.⁹ In this regard, oil-soluble organometallic compounds can produce dispersed catalysts of higher activity than water-soluble precursors.²⁰ For example, Yamada *et al.* determined that as low as 0.1% molybdenum loading on the coal, in the form of Mo(CO)_6 , is sufficient to obtain a high liquefaction yield.²¹ This was attributed to the attainment of smaller catalyst particle sizes with the organometallic precursors. One of the techniques to improve dispersion is the use of reagents known to swell coal as the solvents for impregnation of the coal with the catalyst precursor. An appropriate solvent might open and enlarge pores, thus enabling the precursor to penetrate the coal matrix. Joseph confirmed that higher yields could result from the proper combination of swelling solvent and catalyst for the liquefaction of coals.²² We also observed this positive effect, even at a pretreatment temperature of 275°C (refs. 8,9). In contrast, however, Warzinski and Holder reported that the impregnation of a coal with ammonium tetrathiomolybdate (ATTM) using pyridine (which is a well known swelling agent) as the solvent gives a performance comparable to that using water as the impregnation vehicle.²³

In the present paper, we report the results of an investigation on the effects of the catalyst precursors, impregnation techniques and solvent swelling on the conversion of two coals, a subbituminous C and a high volatile A bituminous coal, during temperature-staged liquefaction and the effects on the product slate and composition. This paper is an extension of previous work from this laboratory, in which we reported results of catalyst impregnation and solvent swelling on the same coals only for the first, low-temperature stage.⁹ In that work, we demonstrated that, at 275°C, catalyst impregnation without swelling pretreatment improved conversion of both coals, mainly by enhancing preasphaltene yields. In the absence of catalyst, swelling the subbituminous coal with any solvent enhanced conversion as a result of increased oil and gas yields. Only THF and tetrabutyl-ammonium hydroxide (TBAH) increased the conversion of the hvAb coal, by increasing preasphaltenes. Combining catalyst impregnation with solvent swelling enhanced conversion of the subbituminous coal by up to a factor of two, and increased the yields of all products. Little benefit was obtained for the hvAb coal. We now show how temperature-staging, with the addition of a second stage at 425°C, extends and modifies the previous findings.

Experimental Section

Catalyst preparation and testing.

Ammonium tetrathiomolybdate (ATTM), and molybdenum trisulfide were synthesized in our laboratory in a manner described elsewhere⁸. Molybdenum

hexacarbonyl, ferrous sulfate, bis(tricarbonylcyclopentadienylmolybdenum) (CPMC) and bis(dicarbonylcyclopentadienyliron) (CPIC) catalyst precursors were purchased from Johnson Matthey/Alfa products and were used without further treatment. One gram samples of ATTM, Mo(CO)_6 , and FeSO_4 were reacted in microautoclaves at 7 MPa (cold) N_2 , H_2 or $\text{H}_2\text{S}:\text{H}_2$ at temperatures of 275°C, 350°C and 425°C for one hour. When $\text{H}_2\text{S}:\text{H}_2$ was the reaction atmosphere, a 5:95 ratio of $\text{H}_2\text{S}:\text{H}_2$ was used for the ATTM and ferrous sulfate experiments, but the ratio was 13.6:86.4 for the Mo(CO)_6 in order to give a sulfide:metal ratio of 2.5. X-ray diffraction analyses (XRD) of the products were made using Cu-K α radiation with a Rigaku instrument operated at 40 kV and 20 mA. Sulfur analyses were performed using a Leco Model SC-132 Sulfur analyzer and were also obtained from the Penn State Materials Characterization Laboratory using a Leco iodometric titration sulfur analyzer. Carbon, hydrogen and nitrogen analyses were performed using a Leco model CHN-600 elemental analyzer. Molybdenum and water (by the Karl Fisher method) analyses were performed by Galbraith Laboratories, Inc.

Coal sampling and characterization.

Samples of Blind Canyon (Utah) high volatile A bituminous coal (DECS-6) and Big Brown (Texas) subbituminous coal (DECS-1) were used in this study. The principal characteristics of these coals are summarized in Table I. Further details of the origin and characterization of these coals were presented elsewhere.⁸

Swelling of coals prior to liquefaction. The coal samples were swollen using methanol, pyridine, THF and 10% TBAH solution (in a 1:1 w/w water:methanol mixture). Approximately 30 grams of the as-received coal sample were mixed with sufficient swelling reagent to give approximately a solvent-to-coal ratio of 3:1 and were stirred for 6 hours under nitrogen. This was followed by vacuum drying at room temperature for the methanol-, THF- and TBAH-treated coals (until less than 3% of water remained on each coal) and at 100°C for the pyridine-treated coals (to limit amount of pyridine retained on the coal samples). Residual TBAH was allowed to remain on the coals.

Impregnation of coals with catalyst precursors.

Each catalyst precursor was loaded onto batches of coal in an amount based on 1 wt% molybdenum or 0.59 wt% iron (as the metal, not metal compound) on a dry, ash-free (daf) basis regardless of the impregnation method, except for the ion-exchange method discussed below. The different percentages of loaded iron and molybdenum were used in order to provide the same metal loading on a gram-atom basis. Except for molybdenum trisulfide, experimental conditions were selected to favor the following factors during impregnation of the catalyst precursors onto coal: a) to keep each catalyst precursor in a soluble form during impregnation in order to maximize its dispersion on, and penetration of, the coals; b) to remove the swelling and impregnation reagents efficiently; and c) to keep the coal matrix at maximum level of swelling during impregnation with the catalyst precursor. Therefore, the selection of

Table I. Coal Characteristics

Sample	DECS-1	DECS-6
Seam	Bottom (Big Brown)	Blind Canyon
County	Freestone	Emery
State	Texas	Utah
ASTM rank	sub C	h _v Ab
Equilibrium Moisture %wt	31.47	4.85
Mineral Matter %wt (dry)	17.97	6.67
Pyrite Sulfur %wt (dry)	0.11	0.02
<u>Elemental Composition (%dmmf)</u>		
C	76.13	81.72
H	5.54	6.22
N	1.5	1.56
S (org)	1.05	0.40
O (diff)	15.78	10.10

both solvent and the method for the impregnation of the catalyst precursor was dependent upon the solubility and volatility of the catalyst precursor and the type of coal used.

When swelling of the coal was not induced, the coal samples were impregnated with a aqueous solution of ATTM or ferrous sulfate, an aqueous suspension of molybdenum trisulfide, a pentane solution of $\text{Mo}(\text{CO})_6$, and methanol solutions of CPIC and CPMC. Undried coal samples were used for impregnation except when $\text{Mo}(\text{CO})_6$ was used. In the latter case it was necessary to dry the coal prior to impregnation, because the prolonged drying of the catalyst-coal mixture after impregnation causes sublimation of $\text{Mo}(\text{CO})_6$ even at room temperature. Catalyst-solvent mixtures were added to the coal and stirred for 30 min; then the excess solvent was removed while stirring under vacuum, and the impregnated samples were dried at room temperature in vacuum until the solid contained less than 3% moisture.

ATTM, CPIC and CPMC catalyst precursors were used in the investigation of the effect of swelling on liquefaction. In the case of ATTM, the swelling solvent was added to the undried coal (solvent:coal ratio of 3:1) and stirred for 6 hours under nitrogen. Subsequently, the water-methanol solution of ATTM was added to the coal-solvent mixture (ATTM being soluble in this mixture regardless of the type of solvent used as swelling reagent) and stirred for an additional 30 minutes under nitrogen. When TBAH was used as the swelling agent, ATTM was dissolved in a 10% TBAH solution of a 1:1 (w/w) ratio water:methanol mixture (ATTM is insoluble in 10% TBAH solution in water only). This solution was added to coal and stirred for 6 hours under nitrogen. We have shown elsewhere that 6 hours are enough to reach the maximum level of swelling.⁹ Stirring was then followed by the removal of excess solvent at room temperature in vacuum and subsequent drying at room temperature for THF and TBAH, and at 100°C in vacuum for pyridine. TBAH was allowed to remain in the coal. In the case of CPIC and CPMC, the catalyst precursor was dissolved in a swelling agent, and then mixed with the coal and stirred for 6 hours. Removing the solvent and drying the coal were done as in the case of ATTM, until the solids contained less than 3% moisture.

For ion-exchange loading of iron, approximately 30 grams of as received Big Brown coal were slurried in 150 cc of 1M ammonium acetate and stirred for 20 hours in nitrogen at 65-70°C. Subsequently, the mixture was filtered and washed with 1 L of distilled water. The filtrate solution was monitored for calcium ion content using 0.3 M ammonium oxalate. The filtered, washed and ammonium ion-exchanged coal was slurried with 0.05 M of FeSO_4 . After 20 hours of stirring, the mixture was filtered and the filtrate was washed with 1 L of distilled water. The coal ion-exchanged with iron was dried at room temperature in vacuum until it contained less than 3% of moisture. The Fe, Ca, Na, K and Mg contents of untreated coal and ion-exchanged coal sample were analyzed by the Penn State Materials Characterization Laboratory

Liquefaction experiments and fractionation of products. A temperature-staged reaction scheme was applied for the liquefaction experiments, 30 min at

275°C followed by 30 min at 425°C. Five grams of coal and five grams of phenanthrene (as a hydrogen-shuttler vehicle) were used for each experiment. The details of sample loading, reactor preparation and reaction performance at 275°C were given elsewhere⁹. At the end of the 275°C the first stage of reaction, the microreactor was quenched in water. The gas volume was measured by displacement of water (saturated with NaCl in order to limit CO₂ dissolution) by the gas. When the reaction was performed a H₂S:H₂ mixture, the H₂S content of the gas was absorbed by bubbling the product gas through a cadmium acetate solution before measuring the volume of gas produced. Gas samples were collected for further analysis. The microautoclave was repressurized to 7 MPa (cold) with the desired gas mixture and heated for 30 min at 425°C in a preheated sandbath. During the reaction period at each stage, the reactor was oscillated through an amplitude of 2 cm at 350 cycles/min. At the end of the reaction, the reactor was quenched to room temperature and the volume of the gas product was measured as explained above, after which portions of gas were taken for analysis.

The fractionation procedure of the products was described in detail previously.⁹ Briefly, the preasphaltenes are THF-soluble and toluene-insoluble, the asphaltenes are toluene-soluble, hexane-insoluble, and the oils are the hexane-solubles. The conversion is determined from the weight of the THF-insoluble residue (corrected as appropriate for weight of added catalyst). The moisture content of coal sample corrected for in calculation of yields. Gas chromatographic analyses (GC) were performed for CO and CO₂ using a packed Carbosieve column and thermal conductivity detector, and C₁-C₅ analyses of the gas were performed using a Chemipack C18 column with flame ionization detector. Hydrogen consumption during the reaction was calculated from the difference between the amount of hydrogen initially charged to the reactor and that found by gas chromatographic analysis of the gas left after reaction. Analysis of the hexane-solubles revealed that less than 3% of the phenanthrene was transformed to hydrogenated products. Since the amount of hydrogen in the solvent is within the accuracy limits of the measured amount of hydrogen consumed, no attempt was made to correct the amount of calculated hydrogen consumption from the gas phase.

Analysis of liquefaction products.

Saturated fractions of selected samples were eluted as follows; 80 grams of neutral alumina (activity Super I, purchased from ICN) and 25 grams of silica were wet-packed using hexane on top of a 22 x 500 mm glass column. One gram of sample was impregnated on ten grams of silica using chloroform and the sample so prepared was packed on top of the alumina. The sample was eluted with 1100-1300 mL of hexane. The eluted fraction was analyzed by GC with 1-phenyldodecane as an internal standard on a Perkin Elmer model 5800 gas chromatograph equipped with a RT₁-50 (0.25 mm x 30 m) column. The column temperature was programmed from 40°C to 280°C at a rate of 4°C/min and with a hold for 10 min at 280°C. Gas-chromatography/mass spectrometry (GC/MS) of saturate fractions was performed on a Hewlett Packard GC/MS Model 5971A instrument operated using 70 eV impact voltage and equipped with a DB-17

(0.25 mm x 30 m) column. The column temperature was programmed in the same fashion that for GC analysis. Selected samples of THF-insoluble residues were analyzed by solid state ^{13}C NMR and FTIR, and both asphaltenes and preasphaltenes were analyzed by FT-IR. The NMR spectra were recorded on a Chemagnetics M-100 NMR spectrometer by using the cross polarization/magic angle spinning technique (CPMAS).

FTIR spectra were obtained on a Digilab FTS-60A system. Spectra were recorded by coadding 200 scans (interferograms) at a resolution of 2 cm^{-1} . The samples used for FTIR analysis were prepared as KBr pellets. This involved grinding $2 \pm 0.02\text{ mg}$ sample with $300 \pm 1\text{ mg}$ KBr for 60 s in a Perkin-Elmer Wig-L-Bug and holding under 10 tons of pressure for 5 min in an evacuated cylinder. The recorded spectra were normalized to 2 mg of sample.

Results and Discussion

Catalyst precursor transformation.

Elemental analysis of the products obtained in microautoclave tests of $\text{Mo}(\text{CO})_6$ in H_2 , N_2 and $\text{H}_2\text{S}:\text{H}_2$ are given in Table II. $\text{Mo}(\text{CO})_6$ is largely unreactive at 275°C in H_2 and N_2 , as indicated by XRD and elemental analyses. At the higher temperatures, $\text{Mo}(\text{CO})_6$ transforms to carbide and oxide forms. The elemental analyses do not concur with any stoichiometric empirical formula, but rather suggest the presence of excess carbon. Leclercq *et al.*²⁴ pointed out that during the carbiding process of molybdenum by CO, the molybdenum carbides contained free carbon. Optical microscopy of the 275°C products in both H_2 and N_2 revealed a low reflecting, submicron amorphous phase that could be soot.

$\text{Mo}(\text{CO})_6$ can be sulfided efficiently at temperatures as low as 275°C . It is likely that sulfidation at low temperatures is more efficient than at higher temperatures, because the rates of oxidation and carbiding increase at the higher temperatures (*i.e.*, 350° and 425°C). These competing reactions reduce the formation of sulfided molybdenum, which is the desired form of molybdenum for liquefaction catalysis. XRD of the $\text{H}_2\text{S}:\text{H}_2$ products (Figure 1) shows peak intensities increasing with increasing reaction temperatures, although no strongly crystalline phases were observed. As the reaction temperature increases, the (hkl) reflections corresponding to the (002), (101), (103) and (110) planes of hexagonal MoS_2 begin to develop.

Elemental analyses of the products obtained from microautoclave reactions of ATTM in H_2 , N_2 and $\text{H}_2\text{S}:\text{H}_2$ are given in Table III. The water analysis of the sample (by the Karl Fisher method) obtained from the reaction of ATTM in hydrogen at 275°C gave 6.4%. The samples contain various amounts of nitrogen that generally decreased with increasing reaction temperature. Since these reactions are carried out in a static reactor without exchange of gas atmosphere, ammonia formed during the thermal decomposition of ATTM in the reactor might have recombined with molybdenum sulfide. The S:Mo ratios of all the samples are less than 3, except for the sample obtained at a temperature

**Table II. Elemental Analysis of the Products Obtained from Microautoclave
Experiments with Mo(CO)_6**

Reaction Atm.	Reaction Temp. °C	%Mo (wt)	%C (wt)	%S (wt)	100-(%Mo +%C+%S)
H ₂	275	40.8	24.5	—	34.7
H ₂	350	81.8	3.3	—	14.9
H ₂	425	84.7	3.0	—	12.3
N ₂	275	40.8	23.3	—	35.9
N ₂	350	87.3	4.5	—	8.2
N ₂	425	90.3	5.2	—	4.5
H ₂ S:H ₂	275	57.4	0.9	32.9	8.8
H ₂ S:H ₂	350	69.7	1.3	25.8	3.2
H ₂ S:H ₂	425	69.5	1.4	26.5	2.6

**Table III. Elemental Analysis of Products Obtained from Microautoclave
Experiments with $(\text{NH}_4)_2\text{MoS}_4$ (ATTM).**

Reaction Gas	Reaction Temp. °C	%S (wt)	%Mo (wt)	%N (wt)	S:Mo Mol Ratio
H ₂	275	39.4	49.7	3.3	2.4
H ₂	350	42.7	51.2	1.2	2.5
H ₂	425	42.2	53.5	1.0	2.4
N ₂	275	48.5	42.1	3.2	3.5
N ₂	350	45.5	53.0	0.6	2.6
N ₂	425	44.3	52.7	0.6	2.5
H ₂ S:H ₂	275	39.7	49.4	3.4	2.4
H ₂ S:H ₂	350	42.6	52.3	1.3	2.4
H ₂ S:H ₂	425	41.9	53.8	1.0	2.4

Figure 1. Comparison of X-ray diffractograms of products obtained from Mo(CO)_6 at 275°C, 350°C and 425°C in $\text{H}_2:\text{H}_2\text{S}$.

of 275°C in N_2 , for which the S:Mo ratio is 3.4, suggesting the presence in this case of MoS_3 . Thermogravimetric analysis of ATTM also confirmed the stability of MoS_3 up to 350°C (ref. 9). However, as can be seen in Table III, H_2 readily reduces MoS_3 to MoS_2 even at 275°C. The S:Mo ratio of all the samples obtained by reaction in H_2 or $H_2:H_2S$ is greater than 2, suggesting a molybdenum deficiency in the product. As in the case of pyrrhotite, this deficiency might be responsible for the activity of MoS_2 . XRD (Figure 2) shows the same trends with increasing temperature for ATTM as those of $Mo(CO)_6$; however, the lines are more intense for the ATTM reaction products than for the $Mo(CO)_6$ products.

Comparison of catalyst precursors for the liquefaction of coals.

The activities of various iron and molybdenum catalyst precursors were compared for the liquefaction of Big Brown (DECS-1) and Blind Canyon (DECS-6) coals in H_2 and $H_2S:H_2$ (5:95). The results are given in Tables IV and V.

We consider first the reactions in H_2 . For both coals, the addition of any of the catalyst precursors improved hydrogen consumption and conversion of the coal. For Blind Canyon coal, the molybdenum-containing precursors were, as a group, superior to the iron-containing compounds, with regard to enhancing hydrogen consumption, coal conversion, and asphaltene and oil yields. Among the molybdenum compounds, those already sulfided (*i.e.*, ATTM and MoS_3) were superior to the $Mo(CO)_6$; furthermore, the results obtained with the sulfided molybdenum catalyst precursors were generally comparable to each other.

Regardless of which precursor were used, the conversion, asphaltene and oil yields correlate well with hydrogen consumption, as shown in Figure 3. The linear least squares coefficients of determination, r^2 , are 0.956 for conversion as a function of hydrogen consumption, and 0.944 and 0.792 for asphaltene and oil yields, respectively. Preasphaltene yields are not plotted in Figure 3 since, as can be seen from Table IV, the yields vary only between 10 and 18% with no evident trend. The relationships shown in Figure 3 indicate that the primary reactions at these conditions are the conversion of coal into soluble materials, and that this conversion is enhanced by increased hydrogen consumption.

For Big Brown subbituminous coal in H_2 , similar behavior is observed: any catalyst precursor provides improved hydrogen consumption, coal conversion, and oil and asphaltene yields relative to a non-catalytic reaction; the molybdenum-containing precursors are superior to the iron compounds; and, among the molybdenum compounds, those that are sulfided are superior to those that are not. Also, conversion, asphaltene yield, and oil yield all show linear relationships with hydrogen consumption, although in this case the correlations are not as good (*e.g.*, r^2 of 0.792 for the dependence of conversion on hydrogen consumption). Again similar to the results with Blind Canyon coal, the preasphaltene yields are low (5-11%) and show no evident trends.

Figure 2. Comparison of X-ray diffractograms obtained from ATTM at 275°C, 350°C and 425°C in H₂.

Table IV. Comparison of Catalyst Precursors for the Liquefaction of Blind Canyon bituminous coal (DECS-6)

Catalyst	Gas Atmosp.	H ₂ Cons. wt% (daf) ^b	Conversion% (daf)					
			Total	Preas.	Asph.	Oil	CO _x ^a	C ₁ -C ₅
None	H ₂	0.56	48.0	12.3	8.5	21.9	3.1	2.2
None	H ₂ S:H ₂	0.97	58.2	12.1	17.2	22.3	2.8	3.8
FeSO ₄	H ₂	0.83	52.4	10.2	15.4	21.0	3.3	2.5
FeSO ₄	H ₂ S:H ₂	1.58	78.5	15.5	29.2	27.3	2.9	3.6
CPIC	H ₂	1.33	69.2	17.7	18.3	26.7	3.3	3.2
CPIC	H ₂ S:H ₂	1.66	76.0	16.2	20.6	31.9	3.8	3.5
ATTM	H ₂	2.16	85.1	14.7	32.5	34.9	1.9	2.0
MoS ₃	H ₂	1.94	86.1	16.9	25.3	38.9	2.3	2.7
Mo(CO) ₆	H ₂	1.74	72.5	11.7	26.9	28.1	1.7	4.1
Mo(CO) ₆	H ₂ S:H ₂	1.90	86.0	14.2	28.9	36.8	2.9	3.2
CPMC	H ₂ S:H ₂	1.89	88.3	10.9	39.0	32.5	2.6	3.3

^a Corrected for CO content of CPIC, CPMC and Mo(CO)₆

^b daf basis.

Table V. Comparison of Catalyst Precursors for the Liquefaction of Big Brown Subbituminous Coal (DECS-1) .

Catalyst	Gas Atmosp.	H ₂ Cons. wt%, (daf)	Conversion% (daf)					
			Total	Preas.	Asph.	Oil	CO _x ^a	C ₁ -C ₅
None	H ₂	0.61	53.1	8.2	10.9	21.2	9.9	2.9
None	H ₂ S:H ₂	1.17	56.7	11.2	13.9	28.1	10.0	3.5
FeSO ₄	H ₂	1.26	61.2	6.7	13.0	27.2	12.0	2.3
FeSO ₄	H ₂ S:H ₂	1.43	71.5	5.1	24.4	27.7	10.2	4.1
CPIC	H ₂	1.53	63.7	11.2	15.6	22.0	11.6	3.3
CPIC	H ₂ S:H ₂	1.87	74.3	9.6	23.2	30.0	8.1	3.4
Fe ^b	H ₂ S:H ₂	2.21	79.3	7.6	23.0	37.0	8.0	3.7
ATTM	H ₂	2.42	78.9	10.6	19.3	36.4	10.3	2.3
MoS ₃	H ₂	2.16	82.4	8.5	21.5	39.3	8.6	4.5
Mo(CO) ₆	H ₂	1.92	86.2	9.3	26.5	36.0	11.0	3.4
Mo(CO) ₆	H ₂ S:H ₂	2.05	80.1	9.1	18.3	38.7	10.5	3.5
CPMC	H ₂	2.03	84.5	7.0	31.4	34.1	8.0	4.0
CPMC	H ₂ S:H ₂	1.82	79.2	20.5	18.6	27.5	7.0	5.6

^a Corrected from CO content of CPIC, CPMC and Mo(CO)₆.

^b Ion-exchanged

Table VI. Inorganic Elemental Analyses of Original and Iron Ion-Exchanged Big Brown Subbituminous Coal (DECS-1) (wt%, dry basis).

Sample	Fe	Ca	Mg	Na	K
Raw	0.32	1.47	0.19	0.05	0.04
Ion-Exch.	2.54	0.28	0.02	<0.01	0.04

Figure 3. The dependence of conversion, asphaltene yield, and oil yield on hydrogen consumption for liquefaction of Blind Canyon bituminous coal (DECS-6), in non-catalytic experiments and with FeSO_4 , CPIC, ATTM, MoS_3 , and $\text{MO}(\text{CO})_6$ catalyst precursors.

The apparent lack of dependence of preasphaltene yield on hydrogen consumption has at least two explanations: First, it may be that, since asphaltene formation appears to depend on hydrogen consumption while preasphaltene formation does not, most of the asphaltene yield was produced directly from the coal, rather than from preasphaltenes. This has been observed in a previous study of the liquefaction of Wandoan (Australian) subbituminous coal and up-grading of coal-derived liquids, in which it was suggested that asphaltenes can form directly from the coal.²⁵ Second, it may be that preasphaltenes are being hydrogenated to asphaltenes and oils simultaneously with breakdown of the coal structure. To test the second possibility, the following sequence of assumptions and calculations was made: It was assumed that the distribution of products among preasphaltenes, asphaltenes, and oils would have the same proportion in a catalytic experiment as in a non-catalytic experiment. That is, the ratios preasphaltenes/conversion, asphaltenes/conversion, and oils/conversion are assumed to be the same for any experiment with a given coal. Numerical values of these ratios were calculated from the reaction without added catalyst. Then, for any other experiment, the "expected values" of the product yields could be calculated from the experimentally observed conversion and the appropriate values of the ratios. For example, for Blind Canyon coal, the ratio preasphaltenes/conversion in the non-catalytic experiment is 0.256. For reaction with added ATTM, the observed conversion was 85.1%; thus the expected preasphaltene yield would be 21.8% (i.e., 0.256×85.1). Of course, the actual values of the product yields are measured as part of the experiment. Having both the experimentally measured yield and the "expected yield" allows calculation of an "excess yield," from

$$\text{Excess yield} = \text{Experimental yield} - \text{Expected yield.}$$

Continuing the example of Blind Canyon coal with ATTM, the experimentally observed preasphaltene yield was 14.7% (Table IV). Hence the "excess yield" is -7.1%, the negative value indicating that the experimentally observed preasphaltene yield is lower than would have been anticipated on the basis of the yield structure observed in the reaction without catalyst. (A positive value would represent an experimentally observed yield higher than anticipated by extrapolating results of the non-catalytic experiment.) These calculations can be performed for each combination of coal, catalyst precursor, and gas atmosphere, and for each of the products. In Figure 4 we show the relationship between the excess yields of (asphaltenes + oils) and excess yields of preasphaltenes, using data for both coals and all catalyst precursors tested in hydrogen atmosphere. The linear least squares coefficient of determination, r^2 , for this curve is 0.704. The negative slope, and the fact that (asphaltene + oil) yields are higher than would be extrapolated from a non-catalytic experiment while the corresponding preasphaltene yields are lower, indicate that preasphaltenes are being converted to the lighter products.

The $\text{H}_2\text{S}:\text{H}_2$ atmosphere is generally superior to H_2 . The beneficial effects of H_2S for liquefaction processing have been documented in the literature.²⁶⁻²⁸ The promoting effect of H_2S , in the absence of other catalyst

Figure 4. The relationship of "excess" asphaltenes + oils with "excess" preasphaltene yields, using data for liquefaction of both coals in H_2 with $FeSO_4$, CPIC, ATTM, MoS_3 , $Mo(CO)_6$, and CPMC catalyst precursors. The "excess" yields represent the difference between the experimentally observed yield and that calculated assuming that a catalytic experiment would have the same relative proportions of products as observed in a non-catalytic experiment.

precursors, is more pronounced for Big Brown than for Blind Canyon. This is attributed to the higher iron content of the Big Brown (*i. e.*, 0.42% vs. 0.18%, dry basis), because sulfided iron species already in coal can also act as liquefaction catalysts. Ferrous sulfate as a catalyst precursor is the least active in H_2 for both coals, even though it is a sulfur-containing compound. However, in the presence of H_2S , it shows a remarkable activity. It was found that ferrous sulfate is quite stable in H_2 , but in the presence of H_2S it completely transforms to an active pyrrhotite phase. The details of these reactions are given elsewhere.²⁹

When the behavior of a $H_2S:H_2$ atmosphere is combined with an added catalyst precursor, several effects are noted. In all but two cases ($Mo(CO)_6$ and CPMC added to Big Brown subbituminous) the conversions are higher than attained for the same precursor in a H_2 atmosphere. Usually the enhanced conversion is a result of substantially increased oil yields. Although molybdenum-containing precursors are still generally superior to iron compounds, the distinction between the two families of compounds is much less in a $H_2S:H_2$ atmosphere. For Big Brown, for example, in a H_2 atmosphere the best conversion obtained with an iron compound was 63.7%, while the poorest observed with a molybdenum compound was 78.9%. In a $H_2S:H_2$ atmosphere, though, the conversion obtained with ion-exchanged iron, 79.3%, is quite comparable with conversions observed for $Mo(CO)_6$ and CPMC.

The superiority of results in $H_2S:H_2$ relative to those in H_2 alone is attributed to those catalyst precursors not containing sulfur being transformed by H_2S into sulfided compounds which are desirable active phases for liquefaction catalysis. The effect of sulfiding the catalyst precursor by adding H_2S to the gas phase is illustrated by the results for the molybdenum compounds added to Blind Canyon coal, where similar total conversions are obtained by using sulfided precursors (ATTM or MoS_3) in H_2 and non-sulfided precursors (CPMC or $Mo(CO)_6$) in $H_2S:H_2$. For these four systems, the conversions were all in the range 85-88%, although the distribution of products among preasphaltenes, asphaltenes, and oils varied somewhat for different precursors. It is interesting to note that although MoS_3 is not soluble in water or in organic solvents, the conversion obtained using this catalyst precursor was comparable those obtained with the soluble ATTM, CPMC, and $Mo(CO)_6$. Utz *et al.* also reported similar results when comparing MoS_3 with ATTM.³⁰ The results obtained with Blind Canyon - but not Big Brown - show an apparent synergy between the added catalyst precursor and the H_2S . By comparing the non-catalytic experiments in H_2 and $H_2S:H_2$, one can determine the enhancement in conversion and product yields due to the added H_2S . Similarly, by comparing a non-catalytic experiment in H_2 with results from using a catalyst precursor in H_2 , one can determine conversion and yield enhancements caused by the added catalyst. For the Blind Canyon coal with added $FeSO_4$, CPIC, or $Mo(CO)_6$, the increase in oil yield for reaction in $H_2S:H_2$ atmosphere relative to using the same catalyst precursor in H_2 is in all cases greater than the sum of the increases in yield caused by H_2S and the precursors acting alone. This behavior represents another beneficial effect of sulfiding the catalyst. When non-sulfided precursors (*i.e.*, $FeSO_4$, CPIC, or

$\text{Mo}(\text{CO})_6$) and a H_2 atmosphere are used, the change in oil yields is quite small, in the range -1 to +6%. In comparison, sulfided precursors - ATTM or MoS_3 - in a H_2 atmosphere increase oil yields by 13 and 17%, respectively.

With Big Brown subbituminous coal, the organometallic molybdenum precursors showed more activity in H_2 alone than in a $\text{H}_2\text{S}:\text{H}_2$ or when using sulfur-containing molybdenum compounds. This was not observed for the Blind Canyon coal. Suzuki *et al.*³¹ reported that a $\text{Mo}(\text{CO})_6$ -S combination is comparable to $\text{Mo}(\text{CO})_6$ alone for hydrocracking C-C and C-O bonds and for hydrogenation of pyrene and phenanthrene. On the basis of Suzuki's results, one might expect that $\text{Mo}(\text{CO})_6$ would exhibit an activity in $\text{H}_2\text{S}:\text{H}_2$ comparable to that in H_2 . In a $\text{H}_2\text{S}:\text{H}_2$ atmosphere, the $\text{Mo}(\text{CO})_6$ and CPMC provide conversions similar to those observed for the sulfided precursors ATTM and MoS_3 in H_2 , which would be reasonably expected as a result of sulfidation of the $\text{Mo}(\text{CO})_6$ and CPMC by the H_2S . The remarkable feature of the organometallic molybdenum compounds is that, in H_2 , they provide the highest conversions of the subbituminous coal observed for any combination of catalyst precursor and gas atmosphere tested. When reacted in the absence of coal in H_2 at 275°C, $\text{Mo}(\text{CO})_6$ is largely stable to decomposition, but when the gaseous product was analyzed after reaction of Big Brown lignite impregnated with $\text{Mo}(\text{CO})_6$ at 275 C in H_2 , the CO in the gas was equal to the amount CO in the added $\text{Mo}(\text{CO})_6$. We hypothesize that small, activated arene moieties in the lignite may participate in CO displacement reactions with the added carbonyl (as are well known for analogous carbonyls, as in the reaction of anisole with $\text{Cr}(\text{CO})_6$)³², possibly leading to better dispersed and more active Mo species.

For the iron-containing precursors, the presence of H_2S in the gas atmosphere allows their transformation to a more active phase. With Big Brown subbituminous coal, ion exchange provided a highly active iron-based catalyst, probably due to its success in providing a better dispersion of iron throughout the lignite. The conversions and oil yields are very similar to those obtained with ATTM and MoS_3 precursors in a H_2 atmosphere. The change in inorganic composition of the subbituminous coal after ion exchange is shown in Table VI. Figure 5 illustrates the FTIR spectra of the coal with iron (ion exchanged) and in its original form. The shoulder near 1700 cm^{-1} becomes more distinguishable after ion exchange. This finding is in contrast with the FTIR results of Ohtsuka and Asami.³³ However, the Loy Yang brown coal used by Ohtsuka and Asami had a mineral matter content is only 0.5% (dry basis). Hence, most of the carboxylic groups of the Loy Yang coal were already in the acid (i.e., $-\text{COOH}$), rather than the salt form. A partial combination of H^+ ions from the mildly acidic (pH 4.2) iron solution used for ion exchange with the carboxylic groups causes an increase in the intensity of the absorbance band near 1700 cm^{-1} .

As in the H_2 atmosphere, a relationship between the "excess yield" of asphaltenes + oils and the "excess yield" of preasphaltenes is also observed in the $\text{H}_2\text{S}:\text{H}_2$ atmosphere, as illustrated in Figure 6. For the linear fit of these data r^2 is 0.916. The negative slope and the fact that asphaltene + oil yields are higher than would be expected from a non-catalytic reaction while

Figure 5. Comparison of FTIR spectra of untreated Big Brown subbituminous coal (DECS-1) and Big Brown ion-exchanged with iron. 1) Untreated coal, 2) Ion-Exchanged.

Figure 6. The relationship of "excess" asphaltenes + oils with "excess" preasphaltene yields, using data for liquefaction of both coals in $\text{H}_2\text{S}:\text{H}_2$ with FeSO_4 , CPIC, ion-exchanged Fe, ATTM, MoS_3 , $\text{Mo}(\text{CO})_6$, and CPMC catalyst precursors. "Excess" yields determined as in Figure 4.

preasphaltene yields are lower again implies that preasphaltenes are being hydrogenated to lighter products.

Effect of preswelling on liquefaction.

The degree of swelling of the two coals by various solvents has been given elsewhere^{8, 9}. THF and pyridine are effective swelling agents for the Blind Canyon coal, while pyridine and TBAH are effective swelling agents for the Big Brown subbituminous coal.

Table VII provides the results from non-catalytic liquefaction of Blind Canyon and Big Brown with and without preswelling. Treatment of Blind Canyon with methanol, THF, or pyridine provides essentially no improvement in hydrogen consumption or conversion. The principal effect of these solvents is to shift the product distribution slightly, enhancing the formation of lighter products at the expense of preasphaltenes. Both of these consequences of solvent pretreatment were also observed for reaction only at 275°, although of course conversions and yields were much lower.⁹ The shift to lighter products is illustrated in Figure 7, which shows the relationship between product yield and solvent swelling ratio. Generally, the better the swelling ability of the solvent used for pretreatment, the lower the preasphaltene yield and the higher the yields of the asphaltenes, oils, and gases. This suggests that a "loosening" of the structure as a result of swelling may provide better access of the liquefaction vehicle into the coal or easier egress of products. TBAH must be considered a separate case, because its effect on enhancing conversion of Blind Canyon is disproportionate to its rather modest swelling ratio (1.2) for this coal. We have shown previously that residual TBAH remaining after solvent treatment decomposes to amines (mainly tributylamine) during reaction, and have suggested that tributylamine generated *in situ* acts as a very effective solvent for dissolving coal and possibly facilitating transport of products out of the coal particles.⁹

The beneficial effects of preswelling are more pronounced for the Big Brown. For reaction at 275°, conversions of the subbituminous coal are lower than those of the bituminous coal.⁹ For example, without solvent pretreatment, the conversion of the lignite is 6.6% as compared to 17.7% for the bituminous coal; with pyridine swelling, the respective conversions are 10.0% and 16.0% (ref. 9). However, with temperature-staging and solvent pretreatment, conversion, asphaltene yields and oil yields are now higher from the subbituminous than from the bituminous coal treated with the same solvent. Again the best results are obtained with TBAH pretreatment, although in this case TBAH had by far the highest swelling ratio (2.6) of any of the solvents.⁹

The highly beneficial effect of treating the subbituminous coal with pyridine or TBAH may result from several factors. The nitrogen-containing basic compounds may interact with acidic oxygen functionalities, such as -COOH and -OH functional groups, to limit retrogressive cross-linking reactions. As we will explain below, additional evidence for this interaction is the reduced yields of CO_x gases and changes in the FTIR spectra of preasphaltenes and

Table VII. Effect of Preswelling on the Liquefaction of Blind Canyon Bituminous (DECS-6) and Big Brown (DECS-1) Coals

Coal	Solvent	H ₂ Cons.	Conversion (daf)					
		wt%(daf)	Total	Preas.	Asph.	Oil	CO _x	C ₁ -C ₅
DECS-6	None	0.54	48.0	12.3	8.5	21.9	3.1	2.2
DECS-6	CH ₃ OH	0.50	46.7	7.2	10.1	22.6	3.8	3.0
DECS-6	THF	0.50	49.7	9.8	12.0	20.5	3.6	3.8
DECS-6	Pyridine	0.54	51.6	7.3	11.3	26.5	3.7	2.8
DECS-6	TBAH ^a	0.60	58.7	9.9	17.3	21.8	5.7	4.0
DECS-1	None	0.61	53.1	8.2	10.9	21.2	9.9	2.9
DECS-1	Pyridine	0.73	60.1	9.2	9.7	29.5	9.3	2.4
DECS-1	TBAH ^a	0.97	72.1	10.9	24.3	25.8	6.9	4.2

^a Hydrocarbon content of the yield corrected using the gas analysis result of TBAH, which obtained by hydrogenating TBAH at liquefaction condition without coal.

Table VIII. Effect of Preswelling on the Liquefaction of Blind Canyon Bituminous (DECS-6) and Big Brown Subbituminous (DECS-1) Coals with ATTM.

Coal	Solvent	H ₂ Cons.	Conversion% (daf)					
		wt%(daf)	Total	Preas.	Asph.	Oil	CO _x	C ₁ -C ₅
DECS-6	Water	21.6	85.1	14.7	32.5	33.9	1.9	2.1
DECS-6	THF	22.2	88.0	13.4	28.1	41.9	1.7	2.9
DECS-6	Pyridine	24.4	90.3	9.4	33.7	43.0	0.8	3.3
DECS-6	TBAH ^a	22.4	81.7	9.5	45.9	26.3	2.6	4.0
DECS-1	Water	24.3	78.9	10.6	19.3	36.4	10.3	2.3
DECS-1	Pyridine	28.4	88.8	10.9	30.1	37.4	5.6	4.3
DECS-1	TBAH ^a	25.4	88.9	8.9	35.6	34.6	6.3	4.2

^a Hydrocarbon content of yield corrected using the gas analysis obtained by hydrogenating TBAH at the same liquefaction conditions but in the absence of coal.

Figure 7. The change in liquefaction product slate with pre-swelling of Blind Canyon (DECS-6) coal. Solvents used include none, methanol, THF, and pyridine.

asphaltenes from pyridine- or TBAH-treated coals. TBAH might also alkylate the coal, possibly in the course of the first-stage reaction.³⁴ Alkylation of coals may be beneficial for liquefaction.⁵ As noted previously, TBAH decomposes to amines during liquefaction; amines are known to be good promoters for coal liquefaction.³⁵⁻³⁷

Swelling agents were used to impregnate ATTM, CPIC and CPMC catalyst precursors to investigate the combined effect of solvent treatment and catalyst impregnation of these precursors. With ATTM, using THF and pyridine as impregnation solvents enhanced the total conversion of Blind Canyon coal from 85.1% to 88.0% and 90.3%, respectively (Table VII). The beneficial effect of swelling was seen mainly in the formation of oils. Oil production increased from 33.9% to 41.9% with THF and to 43% with pyridine. Improved conversions were consistent with a higher consumption of hydrogen. In contrast, TBAH addition was slightly detrimental for the liquefaction of Blind Canyon coal with ATTM, decreasing both the conversion and oil yield, though increasing the asphaltene yield. We have shown elsewhere that tetrahydroquinoline may convert to propylcyclohexylamine in the presence of a sulfided molybdenum catalyst and poison the catalyst;³ butylamines generated from TBAH may do the same in the present system. The use of swelling solvents for impregnation of ATTM on Big Brown increased conversions even more than was observed for Blind Canyon, about 10% for both pyridine and TBAH. This increase was mainly reflected in the production of asphaltenes. In addition, both TBAH and pyridine treatments reduced the formation of CO_x gases. The improvements in conversion and oil and asphaltene yields are attributed to an improved catalyst dispersion resulting from better impregnation of the catalyst precursor. The swelling of the coal by the organic impregnation solvent, may allow the catalyst to penetrate into the coal.

The effectiveness of solvent swelling on liquefaction with CPIC in H₂S:H₂ is not pronounced (Table IX). Using THF as impregnation solvent slightly increased the conversion of Blind Canyon coal from 76% to 80%, with a higher formation of asphaltenes. However, when pyridine was used, conversion and hydrogen consumption both decreased. The residual pyridine content, calculated from the increase in nitrogen content of the pyridine-treated coal compared to untreated coal, was 2-4% for the Blind Canyon. (The calculation of yields of pyridine-treated coals was corrected for residual pyridine content.) Pyridine may have interrupted the transformation of CPIC to pyrrhotite, the active catalyst for hydrogenation. Addition of TBAH increased the conversion of Big Brown to 80.2%, but this increase was a result of an increase of asphaltenes and preasphaltenes, and reduction of oil yield.

With CPMC, THF and pyridine treatments were beneficial for the liquefaction of both coals, mainly by shifting the product slate to favor enhanced oil yields (Table X). Swelling with pyridine provided a slight increase in total conversion of the Blind Canyon coal. Particularly, using pyridine gave a 10% increase in oil yield for both coals. In general a higher amount of hydrogen consumption occurred, concomitant with a higher formation of oil. Another effect of pyridine treatment was a decrease in the formation

Table IX. Effect of Solvent Swelling on Liquefaction of Blind Canyon (DECS-6) and Big Brown (DECS-1) Coals with CPIC in H₂S:H₂

Coal	Solvent	H ₂ Cons. wt%(daf)	Conversion% (daf)					
			Total	Preas.	Asph.	Oil	CO _x ^a	C ₁ -C ₅
DECS-6	CH ₃ OH	1.7	76.0	16.2	20.6	31.9	3.8	3.5
DECS-6	THF	1.8	80.0	17.0	25.2	28.9	4.8	4.1
DECS-6	Pyridine	1.5	69.1	8.8	25.5	27.4	3.3	4.1
DECS-1	CH ₃ OH	1.9	74.3	9.6	23.2	30.2	8.0	3.4
DECS-1	Pyridine	2.1	73.6	6.2	24.0	30.2	8.7	4.5
DECS-1	TBAH ^b	1.9	80.22	11.3	29.8	24.6	9.0	5.5

^a Corrected for the CO content of CPIC

^b Hydrocarbon content of yield corrected using the gas analysis from TBAH, obtained by hydrogenating TBAH at the liquefaction conditions in the absence of coal.

Table X. Effect of Solvent Swelling on Liquefaction of Blind Canyon Bituminous (DECS-6) and Big Brown Subbituminous (DECS-1) Coals with CPMC in H₂S:H₂

Coal	Solvent	H ₂ Cons. wt% (daf)	Conversion% (daf)					
			Total	Preas.	Asph.	Oil	CO _x ^a	C ₁ -C ₅
DECS-6	CH ₃ OH	1.89	88.3	10.9	39.1	32.5	2.6	3.3
DECS-6	THF	2.00	87.7	8.3	35.6	37.0	3.1	3.7
DECS-6	Pyridine	2.75	91.6	7.9	35.4	42.1	1.8	4.4
DECS-1	CH ₃ OH	1.82	79.2	20.5	18.6	27.5	7.0	5.6
DECS-1	Pyridine	2.13	75.3	6.3	19.7	38.7	5.0	5.6
DECS-1	TBAH ^b	1.97	78.0	8.6	28.8	25.0	9.6	6.0

^a Corrected for the CO content of CPMC

^b Hydrocarbon content of yield corrected using the gas analysis from TBAH, obtained by hydrogenating TBAH at the liquefaction conditions in the absence of coal.

of CO_x gases.

Characterization of selected products.

To begin an investigation of the effects of catalyst addition and solvent treatment on modifying the structure of the liquefaction products, selected products were subjected to ¹³C solids NMR spectroscopy (THF-insoluble residues), to FTIR spectroscopy (residues, asphaltenes and preasphaltenes), and to GC and GC/MS analysis (saturated fractions of hexane-solubles).

Tables XI and XII compare f_a values of the residues calculated from ¹³C NMR spectra. It is noteworthy that there is a significant increase in f_a of the residue from non-catalytic reactions relative to the unreacted coal, even though these reactions attained only 50% conversion and consumed relatively little hydrogen. Further increase in f_a , accompanying an increase in conversion to 90% and a quadrupling of hydrogen consumption, is relatively small. These results suggest that the early stage of reaction, in which half (or perhaps even less) of the coal is converted to soluble products, leaves a highly aromatic material as residue; further hydrogenation, facilitated by addition of a catalyst, swelling solvent, or both, essentially "nibbles away" molecular fragments of the residue and converts them to soluble products. From our present experiments we cannot say whether the highly aromatic residue at approximately equal to 50% conversion represents the less-reactive aromatic material originally present in the coals, or is a result of retrogressive crosslinking reactions inadvertently accompanying the early stages of liquefaction.

Figure 8 illustrates the FTIR spectra of THF-insolubles obtained from the Big Brown subbituminous coal. The aliphatic C-H stretching bands between 2700 and 3000 cm⁻¹ are less intense in the residue than in the unreacted coal. With higher conversion, the contribution of the organic phase of the lignite to the spectrum decreases, and the absorbance bands from minerals become more noticeable. Similarly, the intensities of aliphatic C-H stretching bands in the spectra of residues from Blind Canyon is always less than those in the original coal (Figure 9).

Selected asphaltene and preasphaltene fractions were also examined by FTIR. Generally, slight differences can be seen in the region between 1150 cm⁻¹ and 1300 cm⁻¹. The unresolved absorption bands in this region can be attributed to aryl C-O (stretching) aromatic ethers and phenols and to C-O-H deformation bands.³⁸⁻⁴⁰ The peak at 1035 cm⁻¹ may be due to C-O vibrations of aryl-alkyl ether⁴¹. Figure 10 illustrates the spectra of asphaltenes obtained from Big Brown subbituminous coal. The spectrum of asphaltenes produced in the non-catalytic reaction exhibits two maxima in the region representing C-O groups, at 1267 and 1225 cm⁻¹, and a shoulder at 1700 cm⁻¹ assigned to C=O stretching. The spectrum of asphaltenes produced in catalytic reactions spectrum did not differ from that of the non-catalytic experiment. For the pyridine-treated subbituminous coal, the intensity of the 1267-1225 cm⁻¹

Table XI. f_2 Values of THF-Insoluble Residues of Blind Canyon Coal (DECS-6)

Solvent	—	None	None	pyridine
Catalyst	—	No	ATTM	ATTM
f_2	0.598*	0.891	0.850	0.871

* Parent coal

Table XII. f_2 Values of THF-Insoluble Residues of Big Brown Subbituminous Coal (DECS-1)

Solvent	—	None	None	Pyridine	TBAH
Catalyst	—	No	ATTM	ATTM	ATTM
f_2	0.438*	0.850	0.850	0.881	0.896

* Parent coal

Figure 8. Comparison of FTIR spectra of Big Brown subbituminous coal (DECS-1) and THF-insoluble liquefaction residues.
1) Unreacted coal, 2) residue from non-catalytic reaction, 3) residue from reaction with ATTM, 4) residue from reaction of pyridine-treated coal with ATTM, 5) residue from reaction of TBAH-treated coal with ATTM.

Figure 9. Comparison of FTIR spectra of Blind Canyon (DECS-6) bituminous coal and THF-insoluble liquefaction residues. 1) Unreacted coal, 2) residue from non-catalytic reaction, 3) residue from reaction with ATTm, 4) residue from reaction of pyridine-treated coal with ATTm.

Figure 10. Comparison of FTIR spectra of asphaltenes from liquefaction of Big Brown subbituminous coal (DECS-1). 1) Asphaltenes from non-catalytic reaction, 2) asphaltenes from reaction with ATTM. 3) asphaltenes from reaction of pyridine-treated coal with ATTM, 4) asphaltenes from reaction of TBAH-treated coal with ATTM.

region decreased slightly. The most notable distinction was in the spectrum of asphaltenes from the catalytic reaction of TBAH-treated coal. The maximum at 1225 cm^{-1} disappeared and the relative intensity of the band at 1267 cm^{-1} was lowered. A decrease in O-H stretching at 3400 cm^{-1} was observed (although there is a contribution from water to this region). In addition, the distribution of aliphatic hydrogens is different from that of other asphaltenes obtained from this coal, owing to a higher proportion of methyl groups absorbing at 2956 cm^{-1} , and similarly for methylene groups (2925 cm^{-1}). The proportion of bands between 700 and 900 cm^{-1} (aromatic C-H out-of-plane bending modes) also differed from those of other asphaltene. That the proportion of the bands at 748 (4 neighboring H) and 812 cm^{-1} (2 neighboring H) increased relative to the absorption band at 850 cm^{-1} (isolated H band) suggests that the asphaltene sample from the TBAH-treated Big Brown is less substituted and contains less condensed aromatic species. (It should be noted that, not only are there apparent chemical differences in the asphaltenes from TBAH-treated Big Brown *vis-a-vis* the other asphaltenes from this coal, but also TBAH treatment - with or without added catalyst - invariably led to the highest yields of asphaltenes.) For asphaltenes from Blind Canyon, no difference in the C-H stretching region was observed, nor was there any exhibit remarkable difference among samples in the absorbance range between 1150 - 1300 cm^{-1} . The use of catalyst did not affect the intensity of the C=O and C-O group bands. However, after pyridine treatment the carbonyl peak intensity was weakened.

FTIR spectra of preasphaltenes obtained from Big Brown subbituminous coal show no differences in the aliphatic C-H stretching region, regardless of the use of catalyst or preswelling (Figure 11). The intensity of the peaks at 1230 and 1190 cm^{-1} is less for the preasphaltene obtained from the catalytic experiment. Pyridine treatment resulted in a decrease in the maxima at 1230 , 1190 and 1267 cm^{-1} . The spectrum of the preasphaltene sample obtained from TBAH-treated coal does not show peaks at 1230 and 1190 cm^{-1} . Use of a catalyst seems not to affect the the carbonyl peak (1700 cm^{-1}), but solvent treatment caused a significant decrease. In the case of preasphaltenes from Blind Canyon coal, the band at 3400 cm^{-1} is more intense when catalyst is used, regardless of whether the coal had also been treated with a swelling solvent (Figure 12). Since in the presence of catalyst the absorbance peak at 1184 cm^{-1} decreased, and with pyridine treatment the maxima at 1184 and 1225 cm^{-1} disappeared, it is likely that the increase of the 3400 cm^{-1} peak is due to water. The oxygen contents of the asphaltenes and preasphaltenes, shown in Table XIII, are consistent with FTIR results. The nitrogen contents of samples obtained from TBAH- and pyridine-treated coals are higher than that of untreated coal. This is attributed to contribution of nitrogen-containing compounds to asphaltenes and preasphaltenes. In view of all the FTIR results and elemental analyses of asphaltenes and preasphaltenes, it can be understood that nitrogen-containing solvents which are capable of swelling coal interact with oxygen functional groups so as to lower their concentration in liquefaction products.

Comparative gas chromatograms of the saturated fractions of oils from Big Brown and Blind Canyon coals are illustrated in Figures 13 and 14,

Figure 11. Comparison of FTIR spectra of preasphaltenes from liquefaction of Big Brown subbituminous coal (DECS-1).
1) Preasphaltenes from non-catalytic reaction,
2) preasphaltenes from reaction with ATTM. 3) preasphaltenes from reaction of pyridine-treated coal with ATTM,
4) preasphaltenes from reaction of TBAH-treated coal.

Figure 12. Comparison of FTIR spectra of preasphaltenes from liquefaction of Blind Canyon coal (DECS-6). 1) Preasphaltenes from non-catalytic reaction, 2) preasphaltenes from reaction with ATTM. 3) preasphaltenes from reaction of pyridine-treated coal with ATTM.

Table XIII. Elemental Analyses of Preasphaltenes and Asphaltenes.

Sample ^a	Solvent	Catalyst	Element (wt%, daf)			
			C	H	N	O+S
6-AS	—	—	78.8	5.7	1.5	14.0
6-AS	Water	ATTM	83.1	6.1	1.9	8.9
6-AS	Pyridine	ATTM	85.2	6.1	1.9	6.8
6-PAS	—	—	82.5	5.4	2.1	10.0
6-PAS	Water	ATTM	83.6	5.3	2.1	9.0
6-PAS	Pyridine	ATTM	84.4	4.9	2.6	8.1
1-AS	—	—	77.7	5.4	1.7	15.2
1-AS	Water	ATTM	81.1	5.7	2.0	11.2
1-AS	Pyridine	ATTM	82.2	6.1	1.9	9.8
1-AS	TBAH	ATTM	82.3	6.1	2.9	8.7
1-PAS	—	—	80.6	4.9	2.1	12.4
1-PAS	Water	ATTM	81.3	5.0	2.1	11.6
1-PAS	Pyridine	ATTM	81.1	5.0	3.3	10.6
1-PAS	TBAH	ATTM	82.0	5.2	3.0	9.8

^a 6= DECS-6; 1=DECS-1; AS=Asphaltene; PAS=Preasphaltene.

Table XIV. Percentage of Saturated Fraction of Oil Yields from Big Brown (DECS-1) and Blind Canyon (DECS-6) Coals and Pristane-Phytane Ratios in Each Related Saturate Fraction.

Coal	Catalyst	Solvent	Pri./Phyt.	Sat.% (daf)
DECS-6	None	None	7.1	2.7
DECS-6	ATTM	Water	5.2	3.4
DECS-6	ATTM	Pyridine	6.1	4.0
DECS-1	None	None	5.4	2.5
DECS-1	ATTM	Water	5.4	4.1
DECS-1	ATTM	Pyridine	5.3	4.4
DECS-1	ATTM	TBAH	5.4	4.2

Figure 13. Comparison of gas chromatograms of saturated fractions from liquefaction of Big Brown subbituminous coal (DECS-1). 1) Saturates from non-catalytic reaction, 2) saturates from reaction with ATTM, 3) saturates from reaction of pyridine-treated coal with ATTM, 4) saturates from reaction of TBAH-treated coal with ATTM. Pr – pristane, Phy – phytane, IS – internal standard.

Figure 14. Comparison of gas chromatograms of saturated fractions from liquefaction of Blind Canyon coal (DECS-6). 1) Saturates from non-catalytic reaction, 2) saturates from reaction with ATTM, 3) saturates from reaction of pyridine-treated coal with ATTM, 4) saturates from reaction of TBAH-treated coal with ATTM. Pr – pristane, Phy – phytane, IS – internal standard.

respectively. Smooth distributions of n-alkanes were obtained. The distributions of n-alkanes are more homogeneous for the subbituminous than for the bituminous coal following the non-catalytic reactions. In the non-catalytic reactions, n-alkanes from the subbituminous coal have a maximum at C_{27} , whereas those from the bituminous coal have a maximum at C_{25} . The concentration of saturates was found to be 2.5% (daf) for the subbituminous and 2.7% (daf) for the bituminous coal (Table XIII) when no catalyst was used.

When ATTM was used, higher concentrations of bicyclic terpenes and monoaromatic hydrocarbons contributed to the chromatograms. For the Blind Canyon coal, the maximum in the distribution of n-alkanes shifted to C_{27} for reaction in the presence of the catalyst. With pyridine swelling pretreatment, the concentration of n-alkanes increased slightly and the alkanes exhibit two maxima, at C_{27} and C_{15} . For Big Brown subbituminous coal, with pyridine treatment n-alkanes exhibit maxima at C_{13} - C_{15} and C_{27} . TBAH treatment yielded maxima at C_{15} and C_{27} . The concentration of saturates increased upon catalyst addition for both coals. Solvent treatments increased the concentration of saturates only slightly for Blind Canyon bituminous coal, and there was no difference in the case of the Big Brown subbituminous coal.

Various ideas have been offered to account for the origin of alkanes in coal liquefaction products. It has been proposed that alkanes are absorbed physically in the coal matrix^{42,43}; that alkanes derived from hydrocarbons present in the pore structure or from the decomposition of alkyl chains bonded to the coal matrix;^{44,45} or that at least part of the n-alkanes derive from hydrogenation of occluded esters, alcohols, or acids.⁴⁶⁻⁴⁹ The most noticeable effect of the added catalyst is a substantial increase in the concentration of pristane and phytane. The pristane-to-phytane ratio in products from Big Brown subbituminous coal was 5.4 regardless of the use of catalyst during liquefaction or of preswelling. For Blind Canyon bituminous coal, this ratio was more variable, being 7.1 in products from reaction without catalyst, 5.2 for catalytic reactions, and 6.1 in products from pyridine-treated coal. These results raise the possibility that, at least in part, isoprenoids are bonded to the coal matrix.

Pristane is thought to be formed from the oxidation and decarboxylation of pristol; phytane is formed by the hydrogenation and dehydration of phytol.⁴⁹ The source of phytol may be the side chain of chlorophyll. Dihydropythyl- and phytyl-containing components (vitamin E and vitamin K1, for example) might be possible alternative precursors.⁴⁸ On the basis of extraction and hydrogenation of Wandoan (Australian) coal, Dong *et al.*⁴⁸ proposed that part of the n-alkane content in the fractions was produced by the reduction of methyl and ethyl esters of straight-chain carboxylic acids. Isoprenoids (e.g., pristane, and phytane) linked by ether bonds to the coal matrix are the possible precursors, and they may be derived from pristol or phytol skeletons. Both our and Dong's findings support the idea that pristane and phytane are bound, at least in part, to the coal matrix.

Summary and Conclusions

The experimental findings are summarized in Figure 15, which is a plot of the conversions and oil yields from *all* of the experiments described in this paper. Although there is certainly some scatter in the data, we consider the linearity remarkable, considering that the Figure incorporates 51 sets of data derived from liquefaction of two coals of different rank, two gas atmospheres, seven catalyst precursors, and four swelling solvents. Clearly the key to high conversion, and high oil yield, is to increase hydrogen utilization.

For Blind Canyon bituminous coal, high conversions (*i.e.*, in the 85–91% range) are attained by impregnating the coal with a molybdenum-based catalyst precursor. If the precursor is already sulfided, *e.g.* ATTM, a hydrogen atmosphere is adequate; if, however, the precursor is not sulfided, then liquefaction in a $\text{H}_2\text{S}:\text{H}_2$ atmosphere is desirable. Although solvent pretreatment does not provide dramatic increases in conversion relative to untreated samples, it is sufficient to gain an extra 5% in conversion, especially when using pyridine as the treatment solvent. This "extra" 5% conversion is, however, enough to raise conversion from 85% to 90%. The highest conversion observed for this coal, 91.6%, was obtained by a combination of pyridine pretreatment, impregnation with CPMC, and liquefaction in $\text{H}_2\text{S}:\text{H}_2$. For Big Brown subbituminous coal the highest conversions (89%) were obtained with ATTM impregnation and solvent pretreatment with pyridine or TBAH. Pretreatment of the subbituminous coal enhances conversions by 10% relative to otherwise similar experiments but without solvent pretreatment, and the nitrogen-containing solvents seem effective at suppressing formation of CO_x gases. In contrast to Blind Canyon bituminous coal, the organometallic molybdenum-containing precursors gave very good conversions (84–86%) without using H_2S . The marked difference in behavior of these precursors with subbituminous and bituminous coals merits further investigation.

The slopes of the curves plotted in Figure 15 are not parallel; the oil yield increases less rapidly with increased hydrogen consumption than does conversion. The results suggest that if it were possible to attain 100% conversion, the oil yield would be about 45%. Consequently, if one were to envision a process designed around the reaction conditions reported here, some down-stream hydrotreating of preasphaltenes and asphaltenes would be necessary if the goal were to obtain very high oil yields.

For Blind Canyon bituminous coal, the conditions favoring high oil yields are essentially those that also favor high conversions: molybdenum-based precursors, either already sulfided or reacted in $\text{H}_2\text{S}:\text{H}_2$; and solvent pretreatment. The use of organic solvent can enhance oil yields by up to 10% relative to reaction at the same conditions without solvent. The highest oil yields, 42–43%, were obtained with pyridine pretreatment and ATTM in H_2 or CPMC in $\text{H}_2\text{S}:\text{H}_2$. Little or no benefit is observed for oil yields by solvent pretreatment of the subbituminous coal. Sulfided molybdenum catalysts are generally best at providing high oil yields. However, it is noteworthy that

Figure 15. Dependence of conversion and oil yield on hydrogen consumption, combining all data reported in this paper, for 51 temperature-staged liquefaction reactions involving two coals, two gas atmospheres, seven catalyst precursors, and four swelling solvents.

ion-exchanged iron, with reaction in $\text{H}_2\text{S}:\text{H}_2$, gave an oil yield from the subbituminous coal quite comparable to those obtained with molybdenum catalyst precursors, although the total conversion was not quite so high. Ion-exchange impregnation of catalyst precursors into low-rank coals also merits further investigation.

Finally, it should be understood that throughout the course of this work the temperatures, reaction times, and vehicle were not varied, nor was the overall reaction strategy (*i.e.* comparison with single-stage reaction or temperature-programmed reactions). All of these factors are well known to affect the course of liquefaction reactions. Although we have demonstrated approaches to achieve 90% conversions with 40% oil yields, further experimentation that involves changing one or more of these factors could offer potential improvements in reduction of reaction severity, increase of yields of specific desired products, or both.

Acknowledgment.

The authors are grateful for the financial support for this work provided by the U.S. Department of Energy, and for useful discussions with Drs. Malvina Farcasiu and Udaya Rao of the Pittsburgh Energy Technology Center. The authors are pleased to acknowledge many fruitful discussions with Dr. Chunshan Song. We also thank Dr. Jacqueline Bortiantynski and Ms. Maria Sobkowiak for their kind assistance in acquisition of the spectra.

- 1 Derbyshire, F.J .; Davis, A.; Epstein, M.; Stansberry, P. G. *Fuel*, 1986, 65, 1233.
- 2 Derbyshire, F. J.; Davis, A.; Lin, R.; Stansberry, P. G.; Terrer, M. T. *Fuel Proc. Technol.*, 1986, 12, 127.
- 3 Burgess, C.E.; Schobert, H.H. *Fuel*, 1991, 70, 372.
- 4 Solomon, P. R.; Serio, M. A.; Deshpande, G. V.; Kroo, E.; Schobert, H. H.; Burgess, C.E. In *Coal Science II*; Schobert, H.H.; Bartle, K.D.; Lynch, L.J., Eds.; American Chemical Society: Washington, 1991; Chapter 15.
- 5 Baldwin, R. M.; Kennar, D. R; Nguanprasert, O.; Miller, R. L. *Fuel*, 1991, 70, 429.
- 6 Rincon, J. M.; Cruz, S. *Fuel*, 1988, 67, 1162.
- 7 Joseph, J. T. *Fuel*, 1991, 70, 139.
- 8 Artok, L.; Schobert, H. H.; Mitchell; G. D.; Davis, A. *Amer. Chem. Soc. Div. Fuel Chem. Prepr.*, 1991, 36 (1), 36.
- 9 Artok, L.; Davis, A.; Mitchell, G. D.; Schobert, H. H. *Fuel*, (In press, 1992).
- 10 Weller, S. W.; Pelipetz, M. G. *Ind. Eng. Chem.*, 1951, 43, 1243.
- 11 Terrer, M. T.; Derbyshire, F.J . *U.S. Dept. of Energy Report*, 1986, No. DOE-PC-60811-F1.
- 12 Stansberry, P. G.; Derbyshire, F.J . *U.S. Dept. of Energy Report*, 1988, No. DOE-PC-60811-F3
- 13 Garcia, A. B.; Schobert, H. H. *Fuel*, 1989, 68, 1613.

- 14 Hawk, C. O.; Hiteshue, R. W. U.S. Bureau Mines Bulletin, 1965, No.622.
- 15 Suzuki, T.; Yamada, O.; Then, J. H.; Ando, T. *Proc. Internat. Conf. Coal Sci.*, 1985, 205.
- 16 Watanabe, Y.; Yamada, O.; Fujita, K.; Takegami, Y.; Suzuki, T. *Fuel*, 1984, 63, 752.
- 17 Anderson, R. R.; Bockrath, B. C. *Fuel*, 1984, 63, 329.
- 18 Suzuki, T.; Yamada, O.; Fujita, K.; Takegami, Y.; Watanabe, Y. *Fuel*, 1984, 63, 1707.
- 19 Cugini, A. V.; Utz, B.R.; Krastman, D.; Hickey, R. F. *Amer. Chem. Soc. Div. Fuel Chem. Prepr.*, 1991, 36 (1), 91
- 20 Hirschon, A. S.; Wilson, R. B. Jr. In *Coal Science II* ; Schobert, H.H.; Bartle, K.D.; Lynch, L.J., Eds.; American Chemical Society: Washington, 1991; Chapter 21.
- 21 Yamada, O.; Suzuki, T.; Then, J. H.; Ando, T.; Watanabe, Y. *Fuel Proc. Technol.* 1985, 11, 297.
- 22 Joseph, J. T. *Fuel*, 1991, 70, 459.
- 23 Warzinski, R. P., Holder, G. D., *Amer. Chem. Soc. Div. Fuel Chem. Prepr.*, 1991, 36 (1), 44.
- 24 Leclercq, L., Provost, M., Grimblot, J., Hardy, A.M., Gengenbre, L. *J.Catal.*, 1989, 117, 371.
- 25 Song, C.; Hanaoka, K.; Nomura, M. *Fuel*, 1989, 68, 287.
- 26 Baldwin, R. M.; Vinciguerra, S. *Fuel*, 1983, 62, 498.
- 27 Willson, W.G.; Riskedahl, D.; Stenberg, V. I. *Fuel*, 1985, 64, 128.
- 28 Murakami, K.; Yokono, T.; Sanada, Y. *Fuel*, 1986, 65, 1079.
- 29 Artok, L.; Schobert, H. H.; Davis, A. *Fuel Proc. Technol.* (Accepted, 1992).
- 30 Utz, B. R.; Cugini, A. V.; Frommell, E. A. *Amer. Chem. Soc. Div. Fuel Chem. Prepr.* 1989, 34 (4), 1423.
- 31 Suzuki, T.; Yamada, H.; Sears, P. L.; Watanabe, Y. *Energy & Fuels*, 1989, 3, 707.
- 32 Yamamoto, A. *Organotransition Metal Chemistry*; Wiley: New York, 1986; Chapter 4.
- 33 Ohtsuka, Y.; Asami, K. *Ind. Eng. Chem. Res.*, 1991, 30, 1921.
- 34 Anderson, K. B.; Winans, R. E. *Amer. Chem. Soc. Div. Fuel Chem. Prepr.*, 1991, 36 (2), 765.
- 35 Kazimi, F.; Chen, W.Y.; Whitney, R. R.; Zimny, B. *Amer. Chem. Soc. Div. Fuel Chem. Prepr.*, 1985, 30 (4), 402.
- 36 Tagaya, H.; Sugayi, J.; Onuki, M.; Chiba, K. *Energy Fuels*, 1987, 1, 397.
- 37 Miller, R. L.; Baldwin, R. M.; Kennar, D. R. *Amer. Chem. Soc. Div. Fuel Chem. Prepr.*, 1990, 35(1), 9.
- 38 Painter, P.C.; Coleman, M. M. *Fuel*, 1979, 58, 301.
- 39 Painter, P.C.; Snyder, R. W.; Starsinic, M.; Coleman, M. M.; Kuehn, D. H.; Davis, A. *Appl. Spectroscopy*, 1981, 35, 475
- 40 Bellamy, L. J. *The Infra-red Spectra of Complex Molecules* ; Chapman and Hall: London, 1975; Part 2.
- 41 Briggs, L. H.; Colebrook, L. D.; Fales, H. M.; Widmann, W. C. *Anal. Chem.* 1957, 29, 904.
- 42 Bartle, K. D.; Martin, T. G.; Williams, D.F. *Fuel*, 1975, 54, 226.
- 43 Bartle, K. D.; Jones, D. W.; Pakdel, H.; Snape, C. E.; Calimli, A.;

- Olçay, A. and Tugrul, T. *Nature*, 1979, 277, 284.
- 44 Snape, C. E.; Stokes, B. J.; Bartle, K. D. *Fuel*, 1981, 60, 903.
- 45 Mashima, K.; Miya, K.; Sato, S.; Tsuchiya, H.; Ainai, J. *Fuel*, 1984, 63, 1417.
- 46 Mudamburi, Z.; Given, P. H. *Org. Geochem.*, 1985, 8, 221.
- 47 Dong, J. Z.; Katoh, T.; Itoh, H.; Ouchi, K. *Fuel* 1986, 65, 1073.
- 48 Dong, J. Z.; Katoh, T.; Itoh, H.; Ouchi, K. *Fuel* 1987, 66, 1336.
- 49 Philp, R.P. *Fossil Fuel Biomarkers: Applications and Spectra* ;
Elsevier: Amsterdam, 1985; Chapter 2.

END

**DATE
FILMED**

9 / 9 / 92