DOE/MC/26039--12

DE92 017581

METHANE OXIDATION OVER DUAL REDOX CATALYSTS

Quarterly Technical Progress Report
October-December 1991

Kamil Klier, Richard G. Herman, and Juana Isabel Di Cosimo

Zettlemoyer Center for Surface Studies
and
Department of Chemistry
Lehigh University
Bethlehem, PA 18015

February 1992

Prepared for

U.S. Department of Energy
Morgantown Energy Technology Center

Under Contract No. DE-FG21-89MC26039

7/28/92
DEN
MASTER
OK

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

METHANE OXIDATION OVER DUAL REDOX CATALYSTS

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States DOE, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

METHANE OXIDATION OVER DUAL REDOX CATALYSTS

SUMMARY OF PROGRESS

The effect of doping lanthana-based catalysts with antimony and bismuth on the catalytic behavior toward the selective oxidation of methane has been studied. New catalytic results have been obtained upon doping the $\text{Sr/La}_2\text{O}_3$ catalyst, obtained from AMOCO Oil Co., with the acidic Sb and Fe dopants. Both activity and selectivity of the original $\text{Sr/La}_2\text{O}_3$ catalyst can be modified by introducing small amounts of either dopant. Iron doping lowered selectivity to C_2 products whereas antimony increased the selectivity while decreasing the reaction temperature by 100°C .

TECHNICAL PROGRESS

1. INTRODUCTION

Since methane is the major constituent of natural gas, routes involving the indirect conversion of methane to CO and then to oxygenates or higher hydrocarbons have been developed. However, the steam reforming process is endothermic, and it is desirable to explore other routes with more favorable thermodynamic driving force. One possible alternative is the direct catalytic oxidative coupling of methane to C_2 products, which can in turn be converted to gasoline or used as chemical feedstocks.

Lanthanum-based oxides are well-known recently developed catalysts for the oxidative coupling of methane toward C_2 products (1-3). The oxidative coupling of methane is a well-studied process over many different types of catalysts, and several reviews have been written on the homogeneous and heterogeneous oxidative coupling of methane (4-7). For the heterogeneous catalytic process, a great variety of catalytic materials have been reported, with the alkali and alkaline earth metals (8,9), as well as the rare earth oxides (10), being the most promising and widely studied catalysts.

In this context, lanthana and strontia-lanthana based catalysts are considered among the most active and selective catalysts for the oxidative coupling of methane. DeBoy and Hicks (2,3,11) reported selectivities to C_2 products of up to 64% and a methane conversion of 20.9% at 750°C for the Sr-promoted La_2O_3 catalyst. They also showed that the unpromoted La_2O_3 was less selective at those conditions. Despite the wide range of experimental conditions employed by the different research groups, which makes the comparison of results difficult, the undoped La_2O_3 oxide was always found to be less active and selective than the Sr/ La_2O_3 catalyst, confirming the promoting effect of Sr.

On the other hand, several research groups have studied the catalytic

properties of metal oxide catalysts such as Fe_2O_3 , Sb_2O_5 , SnO_2 , PbO , and Bi_2O_3 and found that these oxides had low activity for the synthesis of C_2 hydrocarbons, either alone or supported on other oxides (4-6). However, relatively good selectivities were obtained with those redox oxide systems under cyclic (12,13) or cofeed (14-18) operations at 700-850°C.

In this report, we report on the results obtained by promoting the $\text{Sr/La}_2\text{O}_3$ catalyst with small, e.g. 0.5 wt%, amounts of Sb or Fe. Both the activity and selectivity toward C_2 products of the base catalyst were dramatically affected by the promoters, whereas Fe was found to decrease the overall selectivity, the Sb-doped catalyst exhibited higher activity and selectivities toward C_2 hydrocarbons.

2. EXPERIMENTAL

A 1 wt% $\text{Sr/La}_2\text{O}_3$ catalyst prepared as described in (3) was obtained from AMOCO Oil Co. Samples containing Sb or Fe were prepared by aqueous impregnation of the $\text{Sr/La}_2\text{O}_3$ sample with SbCl_3 or $\text{Fe}(\text{NO}_3)_3 \cdot 9 \text{H}_2\text{O}$, respectively. After drying, samples were calcined in air at 600°C for 20 h. Before the catalytic test, samples were activated in a He flow at 700°C for 3 h in order to remove any traces of water and to decompose $\text{La}(\text{OH})_3$ and surface carbonate phases that might be formed upon impregnation and calcination in air. The catalytic testing was performed at ambient pressure in the temperature range of 500-850°C in a continuous flow microreactor. The reactants consisted of a CH_4 and air mixture with $\text{CH}_4/\text{air} = 1$ molar ratio and with gas hourly space velocity (GHSV) of 70,000 l/kg cat/h.

3. RESULTS AND DISCUSSION

Catalytic results obtained with the unpromoted and the Fe- or Sb-promoted $\text{Sr/La}_2\text{O}_3$ as a function of temperature are presented in Figure 1. The comparative performance of the catalysts at 600°C is shown in Table 1.

TABLE 1.

ACTIVITY AND SELECTIVITY OF LANTHANA-BASED OXIDES FOR METHANE OXIDATION^a

CATALYST	METHANE CONVERSION (%)	SELECTIVITIES (carbon at. %)				YIELD (%) C ₂ 's	PRODUCT RATIO	
		C ₂ = ^b	C ₂ ^b	CO	CO ₂		C ₂ =/C ₂	CO ₂ /CO
Sr/La ₂ O ₃	8.8	5.3	25.3	23.9	45.4	2.7	0.2	1.9
Fe/Sr/La ₂ O ₃	13.5	7.6	26.6	4.1	58.6	4.6	0.3	14.3
Sb/Sr/La ₂ O ₃	23.5	25.2	32.3	5.0	34.0	13.5	0.8	6.8

^aReaction conditions: T = 600°C; CH₄/air = 1; GHSV = 70,000 l/kg cat/h^bC₂=, ethene; C₂, ethane FIGURE 1. Effect of temperature on the yield of total C₂ products for the unpromoted and Lewis acid promoted Sr/La₂O₃ catalysts.

Comparison between the Fe-promoted and the unpromoted Sr/La₂O₃ catalysts indicates that Fe/Sr/La₂O₃ was slightly more active and selective to C₂ hydrocarbons than the unpromoted oxide at temperatures lower than 650°C. The consequent increase in the C₂ yield upon Fe promotion is shown in Figure 1. The ethylene/ethane ratio (C₂=/C₂) was also higher on the Fe-promoted catalyst at those low temperatures as shown in Table 1. However, the CO₂/CO ratio calculated at this temperature was one order of magnitude higher than that of the unpromoted catalyst, suggesting that the Fe-doped catalyst favors production of deep oxidation products at low temperatures. Results obtained at temperatures higher than 600°C showed that the Fe-doped catalyst was less active than the undoped catalyst in terms of methane conversion and produced more CO_x than the unpromoted Sr/La₂O₃, which led to a decrease in the total selectivity to C₂ products compared to the undoped oxide. This effect is shown in Figure 1 as a lower C₂ yield compare to the Sr/La₂O₃. Similar results have been obtained by other workers with CoO (19) or FeO (20) doped in Li/MgO catalysts.

Although a sharp increase of the methane conversion in the temperature range of 550–600°C was observed for all the samples, the unpromoted Sr/La₂O₃ reached the highest conversion level at about 650°C, whereas the Sb-promoted catalyst showed complete oxygen depletion at 550°C, indicating that the Sb dopant significantly lowered the reaction temperature. The antimony-doped sample showed the highest activity of this series of catalysts. As shown in Table 1, high selectivities toward C₂ products were obtained with the Sb-doped catalyst, with the C₂=/C₂ molar ratio being four times higher than that of the undoped catalyst. Clearly, Sb enhances selectivity to C₂ products at low temperatures by depleting production of CO and CO₂. At temperatures higher than 700°C, the Sb-doped catalyst lost antimony by volatilization and showed an increasing selectivity to CO₂. A striking feature of the performance of this sample was that the

volatilization process led to methane conversions and selectivities toward C_2 products lower than those of the unpromoted Sr/La_2O_3 at those temperatures, suggesting that in that process the deactivation of the active sites responsible for the generation of methyl radicals was also involved, and was probable caused by the spreading of a melt film of Sb on the surface of the Sr/La_2O_3 base catalyst.

For all three catalysts, a linear increase in the $C_2= / C_2$ ratio was observed with increasing temperature, although the Sb-doped catalyst showed the highest ratio at temperatures up to $750^\circ C$, reaching a value of 1.01 at that temperature, compared to 0.87 obtained with the unpromoted Sr/La_2O_3 .

Thus, as shown, the performance of the Sr/La_2O_3 catalyst in the partial oxidation of CH_4 to C_2 products can be selectively modified by doping this catalyst with 0.5 wt% Sb or 0.5 wt% Fe. The contrast observed at temperatures lower than $650^\circ C$ between the performance of both dopants indicates that the promoter- Sr/La_2O_3 surface interaction is specific and selective. Although both Fe and Sb increased CH_4 conversion, their effect on the selectivity to ($C_2= + C_2$) were dramatically opposite (Table 1), i.e. Fe decreased and Sb increased selectivity.

Iron thus behaves as a non-selective oxidation component, similar to FeO_x (21). No selectivity switch to oxygenates due to the presence of Fe was observed in the present system as contrary to the Fe-doping of ZnO (22). The latter could be due to (i) much higher activity of the present base Sr/La_2O_3 catalyst for C_2 coupling and (ii) different dispersion and thereby chemical state of the Fe dopant on the surface of Sr/La_2O_3 , e.g. vs the lattice structure controlling surface siting and geometry of the Fe dopant in ZnO (23).

Because Sb significantly increased both activity and selectivity, we consider this dopant to be an important improvement of the Sr/La_2O_3 catalyst.

By ESCA analysis (24), the Sb surface concentration was 37%, implying all of the dopant was dispersed on the surface, not in the bulk. The $4d_{3/2}$ XPS photoemission peaks are asymmetric, indicating coexistent of Sb^{III} and Sb^V . Two properties of SbO_x have to be considered to explain the promotion effect: (i) Sb^{III}/Sb^V is a redox system and a similar class of redox promoters (SbO_x , SnO_x) was found to be effective for promotion of the Li/MgO catalyst (19), and in the Sn system, kinetic analysis (25) indicated enhancement of oxygen chemisorption, and (ii) SbO_x materials are also acidic oxides, and are used here to dope a strongly basic Sr/La₂O₃ system. The acid-base interaction is expected to be strong and responsible for the spreading of the Sb. It could also neutralize chemical species that poison the Sr/La₂O₃ oxide such as CO_3^{2-} , OH^- , or HCO_3^- , rendering the active sites operational. The nature of these active sites is still uncertain and subject to further investigations. Preliminary results with Sn, Bi, Pb, and P indicate that the Sb-effects are general for that class of dopants.

4. REFERENCES

1. C.H. Lin, K.D. Campbell, J.X. Wang and J.H. Lunsford, J. Phys. Chem., **90**, 534 (1986).
2. J.M. DeBoy and R.F. Hicks, J. Catal., **113**, 517 (1988).
3. J.M. DeBoy and R.F. Hicks, Ind. Eng. Chem. Res., **27**, 1577 (1988).
4. G.J. Hutchings, M.S. Scurrall and J.R. Woodhouse, Chem. Soc. Rev., **18**, 251 (1989).
5. Y. Amenomiya, V.I. Birss, M. Golezdzinowski, J. Galuszka and A. Sanger, Catal. Rev.-Sci. Eng., **32**(3), 163 (1990).
6. J.S. Lee and S.T. Oyama, Catal. Rev.-Sci. Eng., **30**(2), 249 (1987).
7. R. Pitchai and K. Klier, Catal. Rev.-Sci. Eng., **28**(1), 13 (1986).
8. T. Ito, J. Wang, C. Lin and J.H. Lunsford, J. Am. Chem. Soc., **107**, 5062 (1985).

9. C. Lin, J. Wang and J.H. Lunsford, J. Catal., **111**, 302 (1988).
10. K. Otsuka, K. Jinno and A. Morikawa, J. Catal., **100**, 353 (1986).
11. J.M. DeBoy and R.F. Hicks, J. Chem. Soc., Chem. Commun., 982 (1988).
12. J.A. Sofranko, J.J. Leonard and C.A. Jones, J. Catal., **103**, 302 (1987).
13. G.E. Keller and M.M. Bhasin, J. Catal., **73**, 9 (1982).
14. I.T.A. Emesh and Y. Amenomiya, J. Phys. Chem., **90**, 4785 (1986).
15. M.Y. Lo, S.K. Agarwal, L.G. Galya and G. Marcelin, Catal. Today, **3**, 137 (1988).
16. K. Otsuka, K. Jinno and A. Morikawa, Chem. Lett., 499 (1985).
17. K. Asami, S. Hashimoto, T. Shikada, K. Fujimoto and H. Tominaga, Ind. Eng. Chem. Res., **26**, 1485 (1987).
18. W. Hinnen, W. Bytyn and M. Baerns, Proc. 8th Intern. Congr. Catal., **3**, 581 (1984).
19. S.J. Korf, J.A. Roos, L.J. Veltman, J.G. van Ommen and J.H. Ross, Appl. Catal., **56**, 119 (1989).
20. S. Bartsch and H. Hofman, Catal. Today, **6**, 527 (1990).
21. M. Hatano and K. Otsuka, Inorg. Chim. Acta, **146**, 243 (1988).
22. Z. Sojka, R.G. Herman and K. Klier, J. Chem. Soc., Chem. Comm., 185 (1991).
23. Z. Sojka and K. Klier, J. Elect. Spect. Rel. Phenom., (1992); in press.
24. J.I. Di Cosimo, R.G. Herman and K. Klier, to be published.
25. S.J. Korf, J.A. Ross, J.A. Vreeman, J.W.H.C. Derksen, J.G. van Ommen and J.R.H. Ross, Catal. Today, **6**, 417 (1990).

END

**DATE
FILMED
9/01/92**