PROGRESS REPORT

DE92 017388

for

DOE contract #DE-FG02-87ER45298
AMENDMENT # A004

"Synthesis and Properties of Novel Cluster Phases"

Principal Investigator: Prof. Frank DiSalvo
Department of Chemistry
Cornell University

DATE: May 15, 1992

This report covers the second year of funding (ending June 30, 1992) under this grant.

A summary of our accomplishments in this last year follows. All the research is in the area of cluster compounds, those solid state compounds that contain metal clusters. Major goals of the research were to examine the solution chemistry of clusters and the materials that could be prepared from these solutions, to synthesize new cluster phases, and to examine the properties of the materials so produced. We continue to make meet these goals, uncovering new compounds and understanding their properties at a deeper level.

This was a particularly gratifying year in that our discoveries were honored by my election to the American Academy of Arts and Sciences. This followed election to the National Academy of Sciences and the American Physical Society International Prize for New Materials in 1991.

Solution Chemistry of Clusters

Our work on the solution chemistry of LiMo_3Se_3 continues with gratifying results. We have prepared a number of solutions containing the inorganic polymeric chains of $(\text{Mo}_3\text{Se}_3)_\infty$ in polar

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

solvents, from which solid films have been cast or from which films of organic polymer blends have also been produced. We are studying the properties of these systems in order to understand the range of behavior of single Mo_3Se_3 chains all the way to the bulk organic-inorganic polymer blends. We have started a collaboration with scientists at Kodak to examine the blends for potential uses as antistatic coatings, etc.

When we make dilute solutions, single Mo_3Se_3 chains may be isolated by putting a drop of the solution on a STEM grid and pushing the grid into the high vacuum of the STEM column. The solvent evaporates quickly, precipitating the chains. The precipitation process brings the chains together in small bundles containing as many as a few hundred chains all the way down to one individual chain. Each of these bundles can be examined in the STEM to look at the structure and the electronic excitation spectrum. We are collaborating with Prof. J. Silcox in Applied Physics, who has the current state of the art STEM in his laboratory. This apparatus will not only resolve atomic spacings below $2\text{\AA}$ but also has an energy loss spectrometer attached, allowing us to study composition and electronic excitations in the bundles as a function of their diameter.

Figure 1 shows a typical bundle on aoley carbon substrate. This image covers an area of 3×3 microns. The "wire" shown is 17 nm wide. This is a dark field image formed by recording the intensity of electrons which are scattered by large angles (greater than 20 mrad) as a function of beam position. The large scattering power of the molybdenum relative to the carbon substrate gives this method very good contrast for the material. Figure 2 shows a $5,000,000$ magnification of this same wire, clearly resolving the $6\text{\AA}$ diameter Mo_3Se_3 individual chains. At $10,000,000$ magnification (figure 3) this same region clearly shows bands at $2.3\text{\AA}$, the expected distance between the triangular Mo_3Se_3 units that stack up to make the long chains (see inset for Mo_3Se_3 structure). In fact, wires of single $6\text{\AA}$ fibers are easily visible in the STEM but

unfortunately they decompose quickly (20 sec. or so) under the electron beam. We are currently working on reducing the beam damage by lowering the beam voltage so these single fibers can be imaged and studied at high resolution.

Larger diameter wires (3 nm and greater) are stable indefinitely at high voltages ($>100\text{keV}$) and we have successfully measured electron energy loss spectra for these wires. We have discovered that a known absorption in the LiMo_3Se_3 solutions at 2.5 eV is thickness dependent, becoming stronger as the wire thickness decreases. This absorption may therefore be a surface or waveguide type mode in the wire. We have also discovered a plasmon resonance at 23 eV and preliminary results indicate that this resonance may have a linear dispersion relation. These studies both prove that we can prepare the world's thinnest wires and begin to give us some idea of their electronic properties.

The study of the inorganic - organic polymer composites is proceeding at a good pace. We have prepared films at ratios of organic to inorganic polymer ranging from 10:1 to 1:1 and studied their electrical properties. All are quite conducting at room temperature but the conductivity decreases at low temperatures, indicating activated behavior. This activation could be due to either an intra or inter-chain barrier for electron conductivity. Intrachain activation could be due to a Peierl's distortion or other localizing interactions while interchain activation would be due to tunnelling through the organic polymer from chain to chain. We are gathering more resistivity data in order to determine which effects dominate as a function of the concentration of the organic polymer. We will study the mechanical properties and glass transition of the films in the near future.

The solution chemistry of Nb_6I_{11} and the solution synthesis of Mo_6S_8 like clusters has proved to be very difficult. I have only one student left on that project and if the next few experiments don't work we will drop that line of attack on cluster containing solids.

So far as I know a few other scientists have tried this approach and have found the experiments equally frustrating.

New Solid State Cluster Compounds

In this area we continue to be particularly successful. Last year we reported that we discovered several new families of compounds that are characterized by condensed sheets of metal atoms. We have synthesized other classes of these materials and examined more closely the structure and properties of some of these phases. One of the new compounds discovered is Nb_3SiTe_6 . It has a sheet structure as shown in figure 4.

Research in the Next Year

We will follow the plan outlined in the renewal proposal submitted in 1990. The solution behavior of clusters, the polymer blends, and the synthesis of new metal-metal bonded phases will all be pursued with vigor. The physical properties of the materials will be examined to guide future synthesis to compounds with even more exciting properties.

PUBLICATIONS since last report (DOE support is preceded with a *)

- *195. "New Layered Ternary Niobium Tellurides: Synthesis, Structure and Properties of NbMTe_2 ($M = \text{Fe or Co}$)" J. Li, M. E. Badding and F. J. DiSalvo, Inorganic Chemistry, 31, 1050 (1992)
- 196. "Structure of Lithium Niobium Nitride" D. A. Vennos and F. J. DiSalvo, accepted Acta Cryst. C
- 197. "Synthesis and Characterization of a New Ternary Nitride, Ca_3VN_3 ," D. A. Vennos and F. J. DiSalvo, accepted J. Solid State Chemistry
- 198. " LiMoN_2 : The First Metallic Layered Nitride" S. H. Elder, L. H. Doerrler and F. J. DiSalvo, submitted to Chem. of Materials
- *199. "Characterization of $\text{TaFe}_{1.2}\text{Te}_2$, a New Layered Telluride with an Unusual Metal Network Structure" M. E. Badding, W. Zhou, P. P. Edwards, J. Li, and F. J. DiSalvo, accepted, J. Solid State Chemistry

- *200. "Synthesis, Structure and Properties of the New Cluster Phase: $\text{Ba}_6\text{Co}_{25}\text{S}_{27}$ " J. Snyder, M. E. Badding and F. J. DiSalvo, accepted Inorg. Chemistry
- *201. "Synthesis and Structure of Nb_3SiTe_6 , a New Layered Chalcogenide Compound" J. Li, M. E. Badding and F. J. DiSalvo, accepted J. of Alloys and Compounds

Figure Captions

Figure 1. The bright line in the photograph is an LiMo_3Se_3 bundle about 70 nm wide. The diameter of the bundle is thus about 30 individual chains wide.

Figure 2. A magnified view (5,000,000) of the edge of the bundle shown in figure 1 resolves individual 6Å wires.

Figure 3. At 10,000,000 times magnification the spacing between the Mo_3Se_3 flat "monomer" units is resolved at 2.3Å. The inset shows the structure of Mo_3Se_3 wire, with Mo atoms on the inside and Se atoms wrapped around the outside.

Figure 4. Perspective views of the layered Nb_3SiTe_6 structure. (a) view along the c-axis, (b) view along the b-axis. The hatched circles are the Nb atoms, partially hatched circles Si atoms, and the dotted circles Te atoms.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Pix: th1feb92a.bdfpix
range: 46.00000 235.0000 7-May-92 12:45:20
Nx, Ny = 256 256, a,b= 0.9922179 0.9961546

fig 1

Pix: th1feb92z.bdfpix
range: 1000.000 2252.000 7-May-92 13:53:20
Nx, Ny = 256 256, a,b= 0.9922179 0.9961546

Fig 2

Pix: th1feb92a2.dfpix

range: 4000.000 6411.000 7-May-92 14:17:43

Nx, Ny = 256 256, a,b= 0.9922179 0.9961546

fig 4

END

**DATE
FILMED**

9/04/92