1st Quarter
1991

DRAFT QUARTERLY TECHNICAL PROGRESS REPORT

Technology Development for Iron Fischer-Tropsch Catalysis - Period ending March 31, 1991

Contract No.: DE-AC22-91PC90056

DOE/PC/90056--T5

Contractor: University of Kentucky Research Foundation
Kinkead Hall
Lexington, KY 40506-0057

DE92 017645

Starting Date: December 18, 1990

Ending Date: December 17, 1993

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

JMS

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

INTRODUCTION

Pretreatment has a great impact on the compounds present in iron catalysts and on the Fischer-Tropsch (FT) synthesis activity and selectivity. For a catalyst pretreated in hydrogen at 300°C or above, iron may initially be present in the metallic state. However, it converts rapidly to carbidic phases or oxides when exposed to syngas under reaction conditions.¹⁻⁶ An oxidic catalysts that is pretreated in CO or directly exposed to syngas may be converted from Fe_2O_3 to low valent oxides or carbides.^{5,7,8} In these cases, the composition of the iron phases changes with pretreatment and reaction time.⁹⁻¹¹ It has been reported that pretreatment in CO results in a better catalyst than one pretreated in hydrogen.^{5,10,11} Many studies have aimed at defining active iron phase by correlation of the structure of the catalyst to FT synthesis activity.^{1,2,5,6,9,21-24} However, there is no clear consensus as to which phase provides the superior activity.^{10,11}

Recently, the advantages of slurry phase FT synthesis in handling the large heat of reaction, the ability to use low H_2/CO ratios and the low capital and operation costs have attracted much attention.¹⁰ In a slurry phase reactor, the presence of solvent may render the effect of pretreatment on iron catalyst structure and on the FT synthesis activity and selectivity quite different from those reported in earlier studies using plug flow reactors. A better understanding the relationships between pretreatment and the FT activity should lead to improvements in process technology.

The present study focuses on the effect of pretreatment on the structure, catalytic activity and selectivity of a high surface area Fe_2O_3 catalysts in a continuously stirred tank reactor (CSTR). Catalyst samples were withdrawn periodically from the

reactor and characterized by X-ray diffraction (XRD) and transmission electron microscopy (TEM). The results of catalyst characterization is correlated with the FT synthesis activity and selectivity.

EXPERIMENTAL

Catalyst activation and syngas reaction

A process scheme employing 300 ml continuously stirred tank reactor (CSTR) was used for the present study (Figure 1). A slurry of 2.2g of Fe_2O_3 (United Technologies, surface area $270 \text{ m}^2/\text{g}$) in 180 cc of tetralin (Fisher, 99%) was charged into the CSTR. Pretreatment gas (i.e. CO or H_2) or syngas ($\text{H}_2/\text{CO}=1.03$) was introduced and the reactor was pressurized to 105 psig (8 atm absolute). The temperature of the reactor was then increased from the ambient to 260°C at a rate of $1.5^\circ\text{C}/\text{min}$ with a gas flow rate of 2.57 L/g-Fe/hr (or 5.57 L/g-Fe/hr for a $\text{H}_2/\text{CO} = 1.03$ mixture; and a stirring rate of 1200 rpm. The reactor was then held at 260°C for 24 hrs. After activation, syngas ($\text{H}_2/\text{CO}= 1.03$) was introduced to the reactor at a flow rate of 5.57 L/g-Fe/hr . CO and H_2 conversions and gas products selectivity were obtained by analysis of the exit gas using a Carle gas analyzer. During the activation process and the syngas reaction period, a small amount of catalyst was withdrawn from the reactor at several designated times for X-ray diffraction and electron microscopy studies.

Catalyst Characterization

X-ray Diffraction (XRD): Powder X-ray diffraction patterns were obtained using a Phillips APD X-ray diffraction spectrometer equipped with a Cu anode and Ni filter operated at 40 kV and 20 mA (Cu K = $1.5418 \text{ \AA}$). A catalyst slurry sample (ca. 6 ml)

was discharged from the reactor into a beaker containing 100 ml acetone. After the catalyst particles settled to the bottom, most of the solvent was removed by decanting. The catalyst was washed with two 20 ml portions of acetone. After drying at room temperature under vacuum, the catalyst was transferred to a sample holder for XRD study. Identification of iron phases in the catalyst was accomplished by comparing the XRD pattern of the catalyst sample with those in the standard powder X-ray diffraction file compiled by the joint committee on powder diffraction standards published by the International Center for Diffraction Data.

Transmission Electron Microscopy (TEM): TEM picture and data were obtained using a Hitachi model H800NA electron microscopy operating at a voltage of 200 kV. The sample were prepared by suspending the catalyst particles withdrawn from the reactor in acetone. An optimum ratio of acetone to catalyst slurry was determined so that the catalyst particles formed a slightly turbid suspension (ca. 2 mL of catalyst slurry in 400 ml acetone). This suspension was constantly agitated in an ultrasonic bath. A drop of the suspension (ca. 7 μ l) was placed with a syringe onto a carbon film coated copper grid. After the acetone evaporated, the grid was loaded into the microscope for analysis.

RESULTS

Activation in CO

Figure 2 shows the XRD patterns of the Fe_2O_3 catalyst activated in CO for 2, 10 and 24 hr. The untreated Fe_2O_3 is amorphous to XRD. According to the manufacture specification, the Fe_2O_3 structure determined by electron diffraction is hematite. After 2 hrs of reaction in CO at 260 $^{\circ}\text{C}$, the catalyst shows XRD peaks at $2\theta = 30.1, 35.4,$

43.1, 56.9 and 62.5° that are characteristic of Fe_3O_4 magnetite (Fig 1a). Furthermore, weak doublet peaks can also be observed above $2\theta = 60^\circ$ (e.g. peaks at ca. $2\theta = 90^\circ$), indicating the presence of Fe_2O_3 magnetite can also be observed. Two additional peaks at $2\theta = 38.0$ and 45.0 , which are not due to the magnetites, were also observed; these can be attributed to the two most intense peaks of Fe_3C cementite ($2\theta = 37.8$ and 45.1°). The peak at 45.0° is also coincident with the most intense XRD peak of $\alpha\text{-Fe}$. With further conversion in CO, several changes in the XRD pattern of the catalyst can be noted by comparing Figure 2b (10 hr in CO) and 2c (24 h in CO) with 2a:

1. The XRD peaks at $2\theta = 30, 35, 43$ and 62.5° become broad; indicating the formation of new iron phases;
2. A new, weak peak at 31° was observed that, together with the observation in (1) above, suggests that maghemite Fe_2O_3 is the new phase since maghemite shows XRD peaks near $31, 35, 43$ and 62° ;
3. The peak at 56.9° decreases with reaction time; this peak can be used as an indication of the presence of Fe_3O_4 magnetite; therefore, the decrease in intensity of the 56.9 peak suggests the disappearance of magnetite phase in the catalyst with reaction time;
4. The XRD intensity of the peaks at $2\theta = 38, 43, 45.0$ and 73.0° grow with increasing reaction time.

The increase in the intensity of the 38.0 and 45.0 peaks indicate that the Fe_3C and Fe phases increase with reaction time. The increase in the peak intensity at 43° indicates the possible formation of another phase. As mentioned above, magnetite

decreased with run time. Therefore, if the XRD peak at 62.5° is solely due to magnetite, it should decrease with run time. Instead, the 62.5° peak increases with run time; this indicates the presence of an iron phase having an XRD peak near 62.5° . This, and the observation of an increase in intensity of the 73° peak with run time, strongly suggests the formation of a new phase, FeO wustite, which increases with run time.

Figure 3 shows the XRD pattern of the CO activated catalyst following 2, 10 and 48 hrs. in syngas. After 2 hrs of syngas conversion, the XRD pattern (Fig. 3a) shows that magnetite Fe_3O_4 is the major phase; weak lines at $2\theta=38.0$ and 45.0 still can be seen. However, the intensity was weaker than that before the introduction of syngas (Fig 2c). This indicates that a portion of Fe_3C and/or $\alpha\text{-Fe}$, produced by reaction of Fe_2O_3 with CO, has been oxidized to Fe_3O_4 magnetite. Moreover, by comparing Fig. 2c with Fig. 3a, the XRD characteristic of FeO has disappeared completely after 2 hrs. in syngas. Apparently, the presence of syngas caused transformation of FeO to Fe_3O_4 magnetite. Prolonged reaction in the syngas environment also caused the XRD peaks characteristic of Fe_3C and $\alpha\text{-Fe}$ to disappear completely (Fig. 3b and 3c). Based on the Fe_3O_4 (311) peak ($2\theta=35.3^\circ$), using the Scherrer equation ($d=\lambda /w_{1/2}\cos\theta$) a mean particle size of 230 Å was estimated for the catalyst after 10 hr syngas reaction. A particle of this size corresponds to a surface area of about $50 \text{ m}^2/\text{g}$ (calculated by $A=6V/d$)

Figure 4 shows a typical TEM picture for the catalyst activated in CO followed by 10 hr of syngas reaction. The particle size distribution based on TEM pictures of the sample is presented in Figure 5. A normal distribution of particle sizes can be

seen. An average particle size of about 290 Å (calculated by $((\sum d_i^3)/n)^{1/3}$) was obtained. Thus the mean particle size of the catalyst obtained from TEM study shows good agreement with the one estimated from XRD line broadening (230 Å).

Figure 6 shows the evolution of CO₂ as a function of the duration of pretreatment of the Fe₂O₃ catalyst in CO. The fraction of CO₂ in the exited gas decreases from 2.5 % after 2 hr to 0.5% after 24 hr in CO. This indicates that the reaction of CO with Fe₂O₃ readily occurs at 260 °C; this observation agrees with the XRD results which show the presence of Fe₃O₄, Fe₃C and Fe in the sample activated in CO for 2hrs (Fig 2a). The detection of CO₂ in the exited gas after 24 hrs of CO exposure suggests that the conversion of iron oxides to iron carbides is incomplete; this is consistent with the detection of Fe₃O₄ and FeO by XRD in the sample after 24 hrs of activation in CO (Fig 2c).

The results of syngas conversion for the catalyst activated in CO are presented in Table 1. Plots of % hydrogen (filled circles) and CO conversions (filled circles) as a function of reaction time are shown in Figure 7a and 7b, respectively. Clearly, the H₂ conversion decreases whereas the CO conversion increases with reaction time. Both CO and H₂ conversion, however, level off at 40% and 22%, respectively, after 10 hr of reaction time. Consequently, the H₂/CO usage ratio, indicated in table 1 column 4, decreases with time to attain a constant value after 10 hrs of synthesis.

Figure 8a and 8b show CO₂ (filled circles) and CH₄ (filled circles) selectivities, as a function of run time. Both selectivities decrease with run time and level off after 10 hr. From column 9 of Table 1, the C2 olefin/paraffin (o/p) ratio does not change significantly (ca. 10%) with reaction time. The C3 o/p ratio (column 10) decreases with

run time and remains constant after 10 h on stream. Comparing column 9 and 10 with column 4 of Table 1, it appears that C2 o/p ratio is not affected significantly by a change in the H₂/CO usage ratio; however, the other four selectivities and the C3 o/p ratio follow the same trend as that of H₂/CO usage.

Activation in H₂

The XRD patterns for the Fe₂O₃ catalyst after 2, 10 and 24 hr in H₂ (260 °C, 8 atm) show mainly Fe₃O₄ magnetite phase. An additional weak peak indicating the presence of metallic Fe was also observed for the catalyst pretreated in hydrogen for 24 h. After reduction, the introduction of syngas does not alter the XRD patterns of the catalyst. This suggests that reduction in H₂ of Fe₂O₃ and the following syngas conversion under 8 atm at 260 °C results mainly in Fe₃O₄.

Table 2 summarizes the results of syngas conversion with the Fe₂O₃ catalyst that was activated in H₂. Plots of H₂ and CO conversion (open circles) versus run time are shown in Figure 7a and 7b, respectively. The H₂ conversion increases slightly with run time and levels off at about 18% after 10 h on stream. The CO conversion increases slightly from 2 to 24 h and then decreases. Consequently, as shown in column 4 of Table 2, the H₂/CO usage ratio increases with run time.

Figure 8a and 8b also show the selectivity for CH₄ (open circles), and CO₂ (open circles) as a function of run time, respectively. Clearly both selectivities increase with run time.

Indicated in column 9 and 10 of Table 2, the o/p ratio for C2 remains constant during the 48 hr period and the o/p ratio for C3 increases slightly with time.

Catalyst activation during synthesis

Figure 9 shows the XRD patterns for the catalyst activated in syngas for 2 (A), 10 (B), 24 (C) and 48 hr(D). It can be seen that after only 2h in syngas, Fe_3O_4 is the major phase. The weak peaks appearing as a shoulder at $2\theta=35.3, 43$ and 63° , indicate the presence of FeO. The FeO phase increases with run time up to 24 hr (Fig 9 b and c) and then has disappeared completely after 48 h (Figure 9 d). $\alpha\text{-Fe}$ and/or Fe_3C , indicated by the peaks at 38° and 45° can also be seen for the material after 2 hrs. in syngas. Similar to the trend observed for FeO, $\alpha\text{-Fe}$ and/or Fe_3C phases increase with run time to 24 hr then disappear after 48 h on stream.

Table 3 shows the results of CO hydrogenation for the catalyst activated in syngas only. CO (filled squares) and hydrogen (filled squares) conversions are plotted as a function of run time in Figure 7a and 7b respectively. The CO and hydrogen conversions increase with run time and level off after 72 h on stream. Thus, from column 4 of Table 3, the H_2/CO usage ratio decreases with run time and levels off after 10 hr.

Figure 8a and 8b show respectively the CH_4 (filled squares), and CO_2 (filled squares) selectivities as a function of synthesis time. Both selectivities decrease with run time, and then level off after 24 h.

From column 9 and 10 of Table 3, one can see that the o/p ratios for C2 and C3 compounds remain constant for the 96 hr period.

DISCUSSION

Effect of activation gas on catalyst structure

The present study shows that Fe_2O_3 can be partially reduced in CO, in hydrogen or in CO/ H_2 mixture. After 10 hr of activation, Fe_2O_3 was completely transformed to Fe_3O_4 and other phases. The ease of reduction of Fe_2O_3 to Fe_3O_4 has been well documented,^{13,14} and is expected on the basis of the exothermic nature of the reaction.¹³

XRD studies conducted in the present work clearly indicate that CO is a better reducing agent, as well as a carburization agent, than H_2 or the H_2/CO mixture. These results are consistent with a static TG/DTA study which showed that CO is better than H_2 for the reduction of $\alpha\text{-Fe}_2\text{O}_3$.¹³ The incomplete transformation of Fe_2O_3 to iron carbide after 24 hrs. of activation in CO (Fig 2c) is also consistent with a Mössbauer spectroscopic study that showed the presence of magnetite Fe_3O_4 and Fe_5C_2 in an amorphous $\alpha\text{-Fe}_2\text{O}_3$ after 24 hrs of activation in CO at 270 °C.¹⁴ However, Zaroachak and McDonald have reported a complete transformation of Fe in a Fe-K-Cu (65:0.29:0.6) catalyst to carbidic iron at 280 °C and under 200 psig CO during 24 h in a slurry phase autoclave.¹⁰ The presence of K, which has been reported to accelerate carburization,^{16,17} as well as the higher temperature (280 vs 260°C) and pressure (200 vs 105 psig) they used, may explain the difference between their and our results.

The observation of only a small fraction of metallic iron after 24 h activation in H_2 at 260 °C is surprising, but this has also been reported.¹⁴ It is possible that the condenser in the reactor set-up (Figure 1) which was used to trap tetralin vapor may

also condense water vapor during the course of reaction; this water may reoxidize metallic Fe to Fe_3O_4 .

Effect of syngas reaction on the catalyst structure

After 10 h of syngas conversion, the catalysts activated in hydrogen and CO showed only the Fe_3O_4 phase by XRD. The catalyst without preactivation also showed by XRD only the Fe_3O_4 after 48 hr on stream. The observation of only Fe_3O_4 phase for iron catalysts after syngas conversion has been reported for catalysts which showed mainly iron carbide or α -Fe phase after activation.^{10,15} This has been attributed to the presence of water vapor, particularly at high conversion. As mentioned in the previous version, the condenser set-up can accumulate relatively large amount of water. High water vapor pressure in the reactor is thus expected. This may be one of the reason for the detection only Fe_3O_4 phase by XRD in the catalysts after prolonged syngas conversion.

Earlier study of Fe catalysts often observed carbidic phase in the spent catalysts.^{5,8} However, the catalysts in those studies are low surface area material or contain alkali promoters. An outer layer of large particles of catalysts may retard oxidation of carbidic or metallic phase. The alkali promoter which has been reported to accelerate carburization is also expected to stabilize the carbidic phases. Thus in the present study, the use of higher surface area Fe_2O_3 and the lack of alkali promoter in the catalyst, may also be the reasons for the observation of only Fe_3O_4 by XRD in the catalysts after 10 or more hours of syngas conversion.

The average particle size of Fe_3O_4 was 230, 250 and 310 Å for catalyst activated in CO and in H_2 followed by 10 h syngas conversion, and direct activation in syngas

for 48 h, respectively. Therefore, the activation does not significantly impact on the particle size of the catalysts following syngas conversion.

Effect of pretreatment on CO hydrogenation selectivity and activity

From Figure 8, it appears that in the earlier stage of syngas conversion, the CO₂ and methane selectivities for the catalysts activated in CO or without preactivation were similar and higher than that of the H₂-activated catalyst. However, the two selectivities merge after only 10 h of syngas conversion so that the catalysts prepared by the three activation procedures become the same. Thus the gas(es) used for activation appear to affect the product selectivity primarily in the earlier stage of syngas reaction. The time dependant trend and magnitude of CH₄ and CO₂ for the catalyst activated in CO (Fig 8, filled circles) and without preactivation (Fig 8, filled square) indicate that they have similar active phases. Furthermore, independent of pretreatment, both CH₄ and CO₂ selectivities merged after 10 h in syngas. This implies that the active sites in the catalysts are similar after 10 h of syngas conversion. As shown in Figure 7, the catalysts activated in hydrogen and without preactivation have comparable CO and hydrogen conversion after 24 h on stream. The catalyst activated in CO or without preactivation showed an induction period; however, no induction period was observed for the hydrogen pretreated catalyst. The CO conversion was similar for the catalyst activated in H₂ or that was not pretreated; however, the CO pretreated catalyst has a CO conversion ca. 3 times that of the sample activated in syngas or hydrogen. Thus, the present study clearly shows that, for a high surface area Fe₂O₃ in a CSTR using tetralin as solvent, activation in CO produced the most active catalyst for subsequent CO hydrogenation. The results are

consistent with the studies of the effect of activation procedure on FT activity for promoted K-Cu-Fe₂O₃ catalysts^{10,11} and for a FeMn catalyst.⁷ The catalyst activated in H₂ has a CO conversion comparable to that of a catalyst without preactivation and is in agreement with the results obtained by Dictor and Bell.⁸

The XRD patterns show that only Fe₃O₄ is detected for the catalyst at the point of maximum activity, and this does not depend upon the activation gases. This implies that Fe₃O₄ is the active phase, or that the active phase can not be detected by XRD. However, the fact that, after 2 h in syngas, Fe₂O₃ already has been completely transformed into Fe₃O₄ and that this material only shows minimum activity while a Fe₃O₄ phase that was observed for the catalyst activated in H₂ for 24 h showed a much higher activity, indicates that bulk Fe₃O₄ is not likely to be the active phase for CO hydrogenation. Furthermore, at maximum activity, the particle size of Fe₃O₄ for the catalyst activated in CO was 74% of that for the catalyst activated in hydrogen. The CO conversion for the CO activated catalyst however, was 3 times that of the catalyst activated in hydrogen. Therefore, the presence of an active surface or bulk phase supported on the surface of Fe₃O₄ is likely.

The attainment of a similar selectivity independent of the initial pretreatment in the present study suggests the same, or at least similar active phase(s). It has been proposed that a number of compounds coexists on the surface of an iron catalyst : iron oxides, iron carbides and metallic iron co-exist.¹² Iron carbides has been proposed to be the active phase,^{2,9,22} and the fraction of iron carbides on the catalyst surface determines the activity.⁹ Others, however, have proposed that metallic iron^{23,24}, or iron oxides¹⁸⁻²⁰ are the active phases. In the present study, the nature of

the active sites was not determined. Nevertheless, the present study suggests that a common active phase can be obtained after a period of syngas conversion.

We speculate that pretreated in H_2 results in the following transformation:

Pretreatment in CO or syngas results in the following transformations:

The difference among the activities of catalysts appears to depend upon the concentration of active sites on the surface. Apparently, Fe_2O_3 activated in CO produced the highest concentration of active sites, and therefore results in the highest activity.

CONCLUSION

The present study has shown that activation of a high surface area Fe_2O_3 catalyst in CO in a CSTR using tetralin as solvent results in an activity that is three times of material that is activated in H_2 or directly in the syngas.

Independent of the catalyst activation, similar methane and CO_2 selectivities are obtained. This suggests that the active catalytic phase is the same. Since particle size estimated by XRD only shows a variation within 30%, the difference among the activities of the differently activated catalysts can be attributed to differences in the concentration of active sites on the catalyst surface.

ACKNOWLEDGEMENT

The authors acknowledge the financial support of this work by the Department of Energy contract No. xxxxx and by the Commonwealth of Kentucky.

REFERENCES

1. J. A. Amelse, L. H. Schwartz and J. B. Butt, *J. Catal.*, **72**, 95 (1981).
2. G. B. Raupp and W. N. Delgass, *J. Catal.*, **58**, 348 (1979).
3. W. M. Shen, J. A. Dumesic and C. G. Hill, *Rev. Sci. Instrum.*, **52**, 858 (1981).
4. M. E. Dry, "Catalysis-Sci and Tech.", (J. R. Anderson and M. Boudart, Eds.), Vol 1, 160-255 (1981).
5. R. B. Anderson in "Catalysis" edited by P. H. Emmett, Van Nostrand-Reinhold, New York, 1956, Vol IV, pp 29-255.
6. C. N. Satterfield, R. T. Hanlon, S. E. Tung, Z. Zou and G. C. Papaefthymiou, *Ind. Eng. Chem. Prod. Res. Dev.*, **25**, 401-414 (1986).
7. H. W. Pennline, M. F. Zarochak, J. M. Stencel and J. R. Diehl, *Ind. Eng. Chem. Res.*, **26**, 595-601 (1987).
8. R. A. Dictor and A. T. Bell, *J. Catal.*, **97**, 121-136 (1986).
9. J. W. Niemantsverdriet and A. M. Van Der Kraan, *J. Catal.*, **72**, 385-388 (1981).
10. M. F. Zarochak and M. A. McDonald, Proceed. Indirect Liquefaction Contractor Meeting, Dec 1986, Pittsburgh, pp 58-82.
11. D. B. Bukur, X. Lang, J. A. Rossin, W. H. Zimmerman, M. P. Rosynek, E. B. Yeh and C. Li, *Ind. Eng. Chem. Res.*, **28**, 1130-1140 (1989).
12. J. W. Niemantsverdriet, C. F. J. Flipse, A. M. Van Der Kraan and J. J. Van Loef, *Appl. Surf. Sci.*, **10**, 302-313 (1982).
13. M. A. Richard, S. L. Soled, R. A. Fiato and B. A Derites, *Mat. Res. Bull.*, **18**, pp 829-833 (1983).

14. F. J. Berry and M. R. Smith, *J. Chem. Soc. Faraday Trans. I*, **85** (2), 467-477 (1989).
15. M. H. Jellinek and I. Frankuchen in "Advance in Catalysis", Vol 1, Academic Press, 279 (1948).
16. H. Pichler and H. Merkel, US Bureau of Mines Tech. Paper 718 (1949).
17. G. L. Vogler, X.-Z. Jiang, J. A. Dumesic and R. J. Madon, *J. Catal.*, **89** 116 (1984).
18. J. P. Reymond, P. Meriadeau and S. J. Teichner, *J. Catal.*, **75**, 39-48 (1982).
19. F. B. Blanchard, J. P. Raymond, B. Pommier, and S. J. Teichner, *J. Mol. Catal.*, **17**, 171-181 (1982).
20. L. J. E. Hofer; in "Catalysis" edited by P. H. Emmett, Van Nostrand-Reinhold, New York, 1956, Vol IV, pp 373-441.
21. H. Matsumoto and C. O. Bennett, *J. Catal.*, **52**, 331 (1978).
22. D. J. Dwyer and J. H. Hardenbergh, *J. Catal.*, **87**, 66-76 (1984).
23. D. J. Dwyer and G. A. Somorjai, *J. Catal.*, **52**, 291 (1978).
24. H. J. Kerbs, H. P. Bonzel and G. Gafner, *Surf. Sci.*, **88**, 269 (1979).

CSTR Reactor System Unit B

Fig. 1

Fig 2

Fig 3

45 nm

Fig 6

Fig 7

Fig 8

Fig 9

END

**DATE
FILMED**

9104192