AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 1

DOE/ER/45328--8

Surface Phases, Surface Defects and the Initial Stages of Oxidation

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Progress Report

DOE Grant DE-FG02-87ER45328

Jack Blakely
Materials Science & Eng.
Cornell University

March 1994

Tel. 607-255-5149
SS# 023-34-0099
e-mail: blakely@msc.cornell.edu
Fax: 607-255-2365

MASTER

Summary of work during past year

Data, from electron diffraction and spectroscopy, on the 2-dimensional binary alloy system, S+O on Ni(111) has now been analysed and published recently in the surface science literature. Since the average density of 2-dimensional adsorbed systems can be varied over very wide ranges a large number of constant coverage phase diagram sections can be studied. This allows comparison with the predictions of model dependent simulations so that interaction parameters can be better established. However in real metal-gas systems the energies of adsorption are usually sufficiently high (of order eV per atom adsorbed) that there are really only a few 'saturation' structures which will dominate in the low pressure range. In the Ni(111) system that we have studied these correspond to $1/4$ monolayer ($p(2 \times 2)$) and $1/3$ monolayer ($\sqrt{3} \times \sqrt{3}$) coverages of the S+O binary. Our data now allows us to give suggested binary diagrams for these specific coverages on Ni(111). A miscibility gap at lower temperatures ($< \sim 100^\circ\text{C}$) indicates a preference for clustering of S even at low atomic fractions so that a surface oxidizing under in a S containing environment is likely to develop adsorbed patches rich in S; these may well have a strong influence on the subsequent adhesion of the oxide to the underlying metal.

The studies of the influence of adsorbed S on the oxidation kinetics can be correlated with the equilibrium adsorbed structures. Although it is surely true that monolayer amounts of adsorbates have little influence on the long term thickness of oxide scales, it should be remembered that the adhesion of the oxide to the underlying metal depends primarily on local bonding at the interface. Our work indicates that S, which initially bonds strongly to Ni (..and to other transition metal surfaces), remains concentrated at the interface even after many monolayers of oxide have grown.

During the current grant period we have carried out studies of the break-up of Fe oxide layers ($\sim 100\text{nm}$ thick) under S exposure in an Environmental Scanning Electron Microscope. The oxide layers were grown on a (100) surface of an $\text{Fe}_{40}\text{-Ni}_{60}$ alloy and characterised in UHV by LEED and Auger spectroscopy before transferring to the SEM. The layers were epitaxial single crystals with some mosaic spread in orientation. At low temperatures S (from H_2S) had no observed effect on the oxide layer, but on raising the temperature to $\sim 500^\circ\text{C}$,while observing the surface in the ESEM, a

dramatic breakup of the oxide layer is observed. Figures 1a and 1b show the changing morphology of the oxide layer at 500°C as observed in the ESEM. These experiments will be repeated in the near future with emphasis on identifying the sites at which the oxide breakup is nucleated. We have also carried out preliminary atomic force microscopy studied of the S exposed surface after removal from the ESEM. Figure 2 below shows an example of the highly stepped or faceted morphology of the final sulfide covered surface as seen by an AFM. This type of study will be pursued during the next year.

One of the goals of this work is to understand the effect of the underlying metal structure on the initiation and growth of oxide particles. We believe that atomic steps are important both in the initiation of oxide nuclei and in the bonding of the metal-oxide interface. To study this aspect of the oxidation problem we have proposed to use 'patterned' metal substrates with a predictable atomic step structure. These atomic step arrays can be characterized by X-ray and electron diffraction (as we have demonstrated for Ni surfaces in our previous DOE work) and by scanning tunneling microscopy. Our STM experience with 'patterned' surfaces (1- and 2-dimensional gratings) has so far been limited to Si. We have developed both the lithography and the STM methods so that we can observe these substrates with atomic resolution. We have just begun to work on the lithographic methods for metal surfaces and will be pursuing this aspect during the coming grant period.

We have also focussed on two 'theoretical' aspects of the work during the current grant period. These are (i) the simulation of 2-phase formation in S+O adsorbed layers using Monte Carlo and other methods and (ii) the possible existence of charged layers in the oxide in contact with the metal. Both of these topics will be worked on during the coming year.

Figure 1: Environmental SEM images of the break-up of an initially continuous single crystal Fe oxide layer on the (100) surface of a NiFe alloy during exposure to 1.2mm of H₂S at 500°C. (a) after ~9min, (b) after 12 min. This work has not yet been published.

Figure 2: Atomic force microscope (AFM) images of regions of the same surface shown in figure 1 after long exposure to H_2S . At this stage the surface is covered by an Fe sulfide layer. The images show the faceted morphology that the sulfide layer develops. This work has not yet been published.

PUBLICATIONS DURING 1993-94 GRANT PERIOD

Publications with DOE support during past year of current project.

"Effect of Sulfur on Oxygen Adsorption and Oxidation of the Ni(111) Surface", Jun Liu, J.P. Lu, P.W. Chu, and J.M. Blakely, J Vac. Sci. Technol., A10, 2355, (1993).

"Effect of Sulfur on Initial Stages of Oxide Growth on Ni(111)", J Liu and J. M. Blakely, Applied Surface Science, 74,43,(1994).

"Surface Phases for Sulfur and Oxygen Coadsorption on Ni(111)", J. Liu and J.M. Blakely, Surf. Sci, 302,171,(1994).

() "Pairing of Curved Atomic Steps at the Extrema of periodic Gratings on Si(001)", C.C. Umbach, M.E.Keeffe and J.M. Blakely, J. Vac. Sci. Tech., A11, 1830, (1993).*

(*) This related work on Si surfaces involved development of STM and Synchrotron X-ray methods, techniques used in the central DOE project.

DATE

FILMED

9 / 1 / 94

END