"MULLED COAL - A BENEFICIATED COAL FORM
FOR USE AS A FUEL OR FUEL INTERMEDIATE"

Contract No. DE-AC22-90PC90167

Phase II: System Demonstration

Prepared By:

Energy International Corporation
135 William Pitt Way
Pittsburgh, PA 15238

May, 1992

Prepared For:

PETC Project Manager: Anthony E. Mayne
Pittsburgh Energy Technology Center
U.S. Department of Energy
P. O. Box 10940
Pittsburgh, PA 15236

TABLE OF CONTENTS

	<u>Page No.</u>
LIST OF TABLES	i
LIST OF FIGURES	ii
1.0 EXECUTIVE SUMMARY	1
2.0 INTRODUCTION	2
3.0 PHASE I SUMMARY	3
4.0 PHASE II ACTIVITIES	4
4.1 Component Testing	7
4.2 Bulk Flow Properties	7
4.3 Storage Studies	15
4.4 Full System Test	23
4.4.1 Continuous CWF Production	25
4.4.2 CWF Atomization Facilities and Procedures	25
4.4.3 Mulled Coal Feed Facilities and Procedures	27
4.4.4 Results of Atomization Testing	27
5.0 CONCLUSIONS	36
6.0 APPENDICES	37
Appendix 6.1 - H. Colijn & Associates Flowability Tests on Fresh Mulled Coal	38
Appendix 6.2 - H. Colijn & Associates Flowability Tests on Aged Mulled Coal	62
Appendix 6.3 - Spray Testing by UNDEERC	84

LIST OF TABLES

<u>Table No.</u>		<u>Page No.</u>
I	Test Runs in Teledyne Two-Inch Continuous Processor	9
II	Samples of Mulled Coal Submitted for Flowability Testing	11
III	Bulk Flow Properties of Mulled Coal	12
IV	Mulled Coal Aging Studies	16
V	Test Results of Outdoor Aging Studies of Mulled Coal	18
VI	Samples of Aged Mulled Coal Submitted for Flowability Testing	23
VII	Bulk Flow Properties of Aged Mulled Coal Samples	24
VIII	Conversion of Mulled Coal to Coal-Water Slurries	26
IX	Atomization of CWF Prepared from Mulled Coal with 1% Surfactant	30
X	Atomization of CWF Prepared from Mulled Coal with 2% Surfactant	31
XI	Atomization of CWF Prepared from Mulled Coal with 0.6% Surfactant	32
XII	Moisture Levels and Particle Size Distribution of CWF Obtained from Mulled Coal	33
XIII	Atomization Tests of Granular Mulled Coal	35

LIST OF FIGURES

<u>Figure No.</u>		<u>Page No.</u>
1	Conceptual Flow Scheme for Converting Wet Filter Cake to Mulled Coal	5
2	Conceptual Flow Scheme for Converting Mulled Coal to Liquid Slurry Fuel	6
3	Continuous Processing System for Making Mulled Coal and/or Coal-Water-Slurry	8
4	Critical Arching Diameters as a Function of Moisture Content and Mulling Agent Level	13
5	Stable Rathole Diameters as a Function of Moisture Content and Mulling Agent Level	14
6	Mulled Coal Aging Study	17
7	Effect of Outdoor Aging on the Bulk Densities of Mulled Coal	20
8	Moisture Content of Mulled Coal Versus Outdoor Storage Time	21
9	Critical Arching Diameter as a Function of Moisture Content and Aging (74 Days)	22
10	Mulled Coal Test Loop	28
11	Mulled Coal Feed System	29
12	Particle Size of Sprayed Coal-Water Fuel as a Function of the Air/Fuel Ratio	34

1.0 EXECUTIVE SUMMARY

Energy International was awarded a contract by DOE-PETC (DE-AC22-90PC90167) to evaluate a new concept for utilization of the fine coal wetcake produced by many of the physical beneficiation processes now under development.

Energy International is developing a technology that will create a staged formulation with the first coal form (Mulled Coal) that can be stored, transported, and pumped. Just prior to combustion, the Mulled Coal (MC) is modified to provide the properties needed for proper atomization. This concept is an alternative to the expensive and energy intensive thermal drying processing of fine coal wetcakes. The material is suitable for both direct feed use in conventional and fluid bed combustors as well as on-site conversion to combustible slurries. By maintaining the coal form relatively close to the feed wetcake, only minor processing with low additive levels and low energy blending is needed at the point of production. Its conversion to slurry or other use-feed form is made near the time of use and thus the requirements for stability, climatic control, and other storage, transport, and handling requirements are much less severe.

The project was divided into two Phases:

Phase I provided the technology base and established the technical feasibility of the concept. The information developed during Phase I provided a basis for design and implementation of a full scale test (Phase II).

Phase II activities were to determine if the Mulled Coal would indeed improve the ability to store and transport fine coal as a stabilized wetcake. The Phase II results have confirmed the findings of Phase I, i.e.,

- The granular Mulled Coal has handling characteristics compatible with existing solids handling equipment.
- Open storage does not materially affect handling properties.
- Aged samples will lose surface moisture and will not rewet upon subsequent exposure to rain.
- Mulled Coal can be pneumatically transported and injected into the boiler with heated air without agglomeration.
- Mulled Coal can be converted into CWF with an in-line processor.
- CWF prepared from Mulled Coal in an in-line processor can be readily pumped and atomized.

2.0 INTRODUCTION

Under the auspices of the Department of Energy and private industry, considerable progress has been made in:

- a. preparation of coal-water fuels,
- b. combustion of low-ash coal-based fuel forms,
- c. processes to provide deeply-cleaned coal.

These technology advances are compatible with national objectives to increase the environmentally responsive use of readily available and abundant coal resources, and to reduce oil and gas fuel consumption.

As these technical developments move toward commercial application, the needs for coordinated efforts and integrated requirements have become increasingly apparent. Systems are vitally needed to integrate energy delivery systems from the raw resource through processing to application and use. Problems have been encountered in the preparation of conventional coal-water fuels that mutually satisfy the requirements for storage stability, handling, preparation, atomization, combustion, and economics. Experience has been slow in evolving generic technologies or products and coal-specific requirements and specifications continue to dominate the development. Thus, prospects for commercialization remain highly specific to the coal, the processor, and the end use.

Developments in advanced beneficiation of coal to meet stringent requirements for low ash and low sulfur can be anticipated to further complicate the problem area. This is attributable to the beneficiated coal being produced in very fine particles with high surface areas, modified surface characteristics, reduced particle size distribution range, and high inherent moisture. Experience in the storage, handling, and transport of highly beneficiated coal has been limited. This is understandable, as quantities of such product are only now becoming available in meaningful quantities.

Much of the existing work and experience with advanced coal-based fuels such as CWF has been built on the premise that the fuel should and will be capable of compatibility with use in the existing storage, handling, and transport equipment as a "one-to-one" replacement for conventional oil fuels. Additives, additional processing, equipment, and system modifications will be needed to provide effective and versatile fuel delivery systems. This will be even more significant for highly beneficiated coal fuels with small particles (<30 microns).

Energy International was awarded a contract by DOE-PETC (DE-AC22-90PC90167) to evaluate a new concept for utilization of the fine coal wetcake produced by many of the physical beneficiation processes now under development. The process would produce a stabilized wetcake (Mulled Coal) that can be stored, transported, and handled in conventional systems. Just prior to combustion, the Mulled Coal (MC) would be modified to provide the properties needed for proper combustion.

Energy International is developing a technology that will convert wet coal fines (<28 mesh, 15-50% moisture) from a "wetcake" to a granular solid (Mulled Coal). The basic concept is one of "Water Management". The granular solid retains the moisture in such a fashion that the material has handling characteristics similar to damp sand. In the wetcake, the water acts as an adhesive holding the coal particles together in large lumps. The adhesive action of the water is limited to the extent that much smaller lumps (granules) are formed. When a liquid fuel is required, the water is modified to act as a mobile phase allowing the individual coal particles to flow past each other. Mulled Coal should readily lose the moisture during storage or processing through a dryer with the material retaining the granular form rather than returning to dust. The dried material will not "rewet" when exposed to water and should resist oxidation as compared to untreated coal. The material should be suitable for direct feed use in conventional and fluid bed combustors as well as on-site conversion to combustible slurries.

By maintaining the coal form relatively close to the feed wetcake, only minor processing with low additive levels and low energy blending is needed at the point of production. Its conversion to slurry or other use-feed form is made near the time of use and thus the requirements for stability, climatic control, and other storage, transport, and handling requirements are much less severe.

The project was divided into two phases.

Phase I provided the technology base and established the technical feasibility of the concept. The information developed during Phase I provided a basis for design and implementation of a full scale test. (Phase II).

Phase II demonstrated the ability to utilize the Mulled Coal to improve the ability to store and move fine coal products as a stable "wetcake" and to convert the wetcake into a Coal Water Fuel. This report covers the Phase II activities.

3.0 PHASE I SUMMARY

Phase I results included:

- Identification of additives that would produce a stabilized wetcake. Stabilized wetcakes were produced in varying types ranging from highly thixotropic gels to free-flowing/granular powders. All stabilized wetcakes retained the original moisture levels (20 to 50%) of the wetcake.
- Selection of the granular form of the Mulled Coal as the preferred form.
- Preparation of granular mulls from a wide range of bituminous coals with particle sizes from 10 microns to >100 microns.

- Indications that the granular mulls will lose moisture on standing or heating with little change in handling characteristics or appearance.
- Indication that the granular mulls would resist rewetting.
- Indications that freeze-thaw cycles or high ambient temperatures (<120 degrees F) had little effect on handling properties.
- Indications that the granular mull could be readily converted into a Coal Water Fuel with conventional CWF additives.

The granular mull is the preferred form for the following reasons:

1. Consistency of handling characteristics over a range of moisture levels, coal particle sizes, and coals.
2. Lower reagent costs.
3. Potentially simpler storage, handling, and transportation system.

Also based on the results of Phase I activities, conceptual schemes for the handling, transportation and use of the granular mull were prepared and are shown in Figures 1 and 2. It can be seen that the schemes presented are quite straightforward and should be able to use equipment and technology readily available.

4.0 PHASE II ACTIVITIES

The Phase II activities were to determine if the granular form of the mull would improve the ability to store and transport fine wet coal in barrel quantities and subsequently be used to prepare a usable fuel for combustion. They included:

1. Testing and evaluation of mixing and feeding equipment for the preparation of the mull and subsequent conversion of the mull into CWF.
2. Determination of the bulk flow properties of the mulls as a function of additive level, particle size, and moisture content on freshly prepared and samples stored under different conditions.
3. A "full system" test in which barrel quantities of mull were prepared from a wetcake from an advanced physical fine coal cleaning process in a continuous process.
4. Transporting the mull to a second site where it was converted into CWF in a continuous processor and tested in an atomization chamber.

Figure 1

CONCEPTUAL FLOW SCHEME FOR CONVERTING WET FILTER CAKE TO MULLED COAL

Figure 2
 CONCEPTUAL FLOW SCHEME FOR CONVERTING
 MULLED COAL TO LIQUID SLURRY FUEL

Energy International Corp.

4.1 Component Testing

Several manufacturers of mixing equipment were contacted. As a result of these contacts and discussions with them of our needs it was decided to conduct tests using three different pieces of equipment:

- ribbon blender
- sigma blade mixer
- concentric continuous processor

Several gallons of dry micronized deep cleaned (1.9% ash) Upper Elkhorn #3 coal having a mean volume diameter of 13 microns (Mv by Micro-Trac analysis) were taken to each manufacturer for testing. The ribbon blender evaluated was unsatisfactory because of its design. In this particular blender there was a cavity above the ribbons that allowed the wet filter cake to bypass mixing with the mulling additive. Both the sigma blade and the continuous processor made satisfactory mulls. The AccuRate volumetric screw feeder was also tested with the continuous processor and was found to satisfactorily feed the wetcake for preparation of the mull and the mull for preparation of the slurries. Both the sigma blade mixer and the continuous processor were leased. The continuous processor was used to prepare large scale quantities of the mull and also to convert the mull to slurry in the full system test. The sigma blade mixer was used to prepare batch samples of the mulls for outdoor aging and for bulk flow property determinations. The AccuRate Model 602 open screw feeder with a capacity range of one to 20 cu. ft./hr. was also leased for the full system test.

The configuration for testing the feeder, continuous processor and reagent feed system is shown schematically in Figure 3. In order to establish the best parameters for the use of this equipment a series of tests were carried out in which both the mull and the slurry was prepared. The run conditions and the results are given in Table I. The coal used in these experiments was again a deep cleaned (1.9% ash) micronized (Mx = 20 microns) Upper Elkhorn #3 coal, i.e., the Taggart Seam coal from Westmoreland Coal Company's Wentz Mine near Big Gap, Virginia.

The results of these experiments showed that with the 2" continuous processor a satisfactory mull can be prepared from a wetcake containing 35% moisture at a rate of 30 lbs/hr. It was further demonstrated that a satisfactory coal water slurry can be produced at mull feed rates of 100 lbs/hr. Therefore, it was felt that this equipment would be satisfactory for the full system test and completion of the contract. This work also indicated that, for commercial scale production, almost any low shear mixer (pug mills, ribbon blenders, muller mills, etc.) should be able to produce satisfactory mulls and slurries.

4.2 Bulk Flow Properties

Measurement of flow properties of solids is critical to the proper design of storage and transportation systems. These properties are determined by measurement of internal friction and friction against different

Figure 3

**CONTINUOUS PROCESSING SYSTEM FOR
MAKING MULLED COAL AND/OR COAL-WATER-SLURRY**

Table I

TESTS RUN IN TELEPHONE TWO-INCH CONTINUOUS PROCESSOR

Test No.	Solids Charge			Agent		Water In.	Motor RPM	Comments
	Feed	Rate Lb/Hr	Set	Feed	Rate Lb/Hr			
ICP-1	Coal (1)	50	150	H ₂ O	25.2	1.0	150	Watcaks not too good - chunky
ICP-1A	Coal (1)	50	150	H ₂ O	25.2	1.0	100	Watcaks OK - 35% H ₂ O
ICP-2	Watcaks	50	225	H ₂ O (2)	0.99	3/4	310	Hull OK - fairly lumpy - 3% H ₂ O
ICP-3	Watcaks	25.9	170	H ₂ O	0.50	3/4	310	Hull better - smaller lumps - 3% H ₂ O
ICP-4	Hull (3)	52.3	200	Disper. (4)	0.33	3/4	310	Good slurry
ICP-5	Hull	102.2	350	Disper.	0.66	3/4	310	Good slurry
ICP-6	Hull	102.2	350	Disper.	0.66	3/4	160	Good slurry
ICP-7	Coal	53.7	150	H ₂ O	25.6	1.0	100	Watcaks OK - lots of small lumps
ICP-8	Watcaks	30.25	165	H ₂ O	0.60	1/2	310	Hull OK - 3% H ₂ O
ICP-9	Watcaks	30.25	165	H ₂ O	0.42	3/4	310	Hull marginal - 2% H ₂ O
ICP-10	Watcaks	30.25	165	H ₂ O	0.22	3/4	310	Hull no good - 1% H ₂ O
ICP-11	Watcaks	30.25	165	H ₂ O	0.60	3/4	310	Hake mull for beard oil - 3% H ₂ O
ICP-12	Hull	52.3	200	Disper. - 1% H ₂ O	0.33	3/4	310	Good C-H-S Viscosity 218 cp @ 100 Particle Size 18.15 μ m HV 281 cp @ 200 1:200 PLF
ICP-13	Watcaks	31.3	164	H ₂ O	0.22	3/4	310	Hull wet and chunky - 1% H ₂ O
ICP-14	Hull	50	200	Disper. 0.5% H ₂ O	0.16	3/4	310	Good C-H-S 515 cp @ 200 μ -1 357 cp @ 100 μ -1 PLF - 1.344
ICP-15	Hull	50	200	Disper. 1.0% H ₂ O	0.33	3/4	310	Good C-H-S 269 cp @ 200 μ -1 235 cp @ 100 μ -1 1.039 PLF

Table I (Continued)

TESTS RUN IN TELETYPE TWO-INCH CONTINUOUS PROCESSOR

Test No.	Solids Charge			Agent			Water RPH	Comments
	Feed	Rate Lb/Hr	Set	Feed	Rate Lb/Hr	Set		
ICP-16	Coal	50	150	H ₂ O	25.2	8.2	100	Wetcake OK - same as ICP-1A
ICP-17A	Wetcake	40	160	HFA	0.80	2.7	310	Mull chunky - marginal - 3% HFA
ICP-17B	Wetcake	40	160	HFA	0.80	2.7	310	Water opening showed no effect
ICP-18	Wetcake	50	200	HFA	1.01	3.0	310	Mull chunky and feels wet. It flows but not a very good mull at 3% HFA.

(1) Deep-cleaned Upper Elkhorn No. 3 coal ground to 20 μ m IV, dried to 1% moisture.

(2) Non-polar additive - weight % of dry coal.

(3) Wetcake product from run ICP-3.

(4) Dispersing agent - weight % of dry coal, 25% in water solution.

materials of construction. The measurements are used to calculate design parameters such as:

- critical arching diameter - minimum outlet size below which the material will not flow fresh, and under compaction.
- stable rathole - diameter which will form a funnel flow (fresh and under compaction).
- slope angles - minimum hopper slope angles for different materials of construction.
- hopper and chute angles for self cleaning for different materials of construction.

The above properties of the granular mulls of different composition were measured by H. Colijn & Associates in Monroeville, PA. They are experts in transportation and material handling systems. By measuring the internal friction and friction against different surfaces of solids before and after compaction they are able to recommend the proper configuration and materials of construction to insure the free flow of material from storage or transportation hoppers.

To prepare samples for testing, sufficient quantities of the deep-cleaned (1.9% ash) Upper Elkhorn #3 coal were ground to 12, 20 and 70 micron mean volume diameters. Ten samples with varying amounts of dried coal, water and mulling agent were prepared in the sigma blade mixer. The composition of the Mulled Coal samples prepared and submitted for evaluation are given in Table II and the results of the measurements are shown in Table III. Plots of the critical arching dimensions and stable rathole diameters as a function of the moisture content and the mulling agent concentration are shown in Figures 4 and 5. The complete report from H. Colijn & Associates is given in Appendix 6.1.

Table II

SAMPLES OF MULLED COAL
SUBMITTED FOR FLOWABILITY TESTING

<u>Sample No.</u>	<u>Mean Volume Diameter</u> <u>Microns</u>	<u>Moisture</u> <u>Wt. %</u>	<u>Mulling Agent</u> <u>Wt. % of Coal</u>
005-87A	20	20	0.5
005-88A	20	20	1.0
005-89A	20	30	1.0
005-90A	20	30	2.0
005-91A	20	30	3.0
005-92A	20	40	1.0
005-93A	20	40	3.0
005-114-1	20	30	0.0
005-1145-A	12	30	2.0
005-114-3	70	30	2.0

The conclusions of the flowability studies are that systems can be designed for handling and storage of any of the mulls using conventional technology.

Multiflow Properties of Hulled Coal

-12-

FIGURE 5

Stable Rathole Diameters
As a Function of Moisture Content
and Mulling Agent Level

4.3 Storage Studies

Mulls were prepared and stored outside under various conditions for 74 days. Thirty-six three-gallon samples of Mulled Coal were prepared using the deep-cleaned Upper Elkhorn #3 coal which had been ground to a mean volume diameter (Mv) of 20 microns and having a moisture content of 30%. Two different mulling agents were used. The samples prepared, their designations and the storage configuration for each sample is shown in Table IV and Figure 6. The storage conditions examined were:

1. Open bin storage.
2. Closed bin storage.
3. Inerted bin storage.
4. Exposed shallow tray storage.

The "bins" in each case were five-gallon plastic buckets which had been painted black in order to accelerate thermal effects of the sun. The inert "bins" had tight fitting lids and the contents were continuously purged with nitrogen. The closed "bins" had tight fitting lids which allowed little or no circulation of air. The open "bins" had no lids and drain holes punched in the bottom which were covered with a fine mesh screen and elevated above the ground to insure good drainage of rainwater. The shallow trays used were as shown in Figure 6. Three sides were protected with clear plexiglass walls and the fourth side with a sheet of polyethylene film taped to the lid. This gave the coal pile protection from wind erosion and allowed air circulation around the pile. At each sampling period the entire sample was riffled until an approximate one-quart sample of each was taken. This gave enough sample for testing and evaluation purposes.

The samples were exposed for 74 days (8-6-91 through 10-16-91) and representative samples taken about every two weeks for the determination of the bulk density and moisture content. The results of the measurements are given in Table V. Some of the results are shown graphically in Figures 7 and 8. The only significant changes were in moisture levels with all samples losing moisture at different rates consistent with the manner of storage. The data also showed the samples resistance to rewetting with a continuing moisture loss in spite of exposure to rainfall.

Select samples were taken and submitted for bulk flow measurements. The samples submitted are given in Table VI and the results of the flowability tests in Table VII. As stated above the change in any of the flow characteristics was due primarily to moisture loss. This is illustrated in Figure 9 which shows the critical arching diameter for fresh and aged mulls contained 2% mulling additive. This shows a direct relationship to the moisture content and that storage conditions had little or no effect on the bulk flow properties of the mull. The complete report from H. Colijn & Associates of measurements made on the exposed samples is given in Appendix 6.2.

Table IV
MULLED COAL AGING STUDIES
(8-G-91)

MULL ADDITIVE PRODUCT	ADDITIVE (% wt.)	OPEN BIN STORAGE	CLOSED BIN STORAGE	INERTED BIN STORAGE	EXPOSED		CUMULATIVE VOLUME (Gals.)	CUMULATIVE VOLUME (Lbs.)
					TRAY TEST (Skin Effect)			
NPA2	2%	A1			A2		6	46
NPA1	1%	B1	B2	B3			16	112.6
	2%	B4	B5	B6	B7		27	202.6
	3%	B8	B9	B10			36	270

NOTES:

1. All samples will be +/- 3gal. (22.6 lb.)
2. Samples will have a +/- 20 micron particle size and +/- 30% moisture content.
3. Samples will be aged 76 days and monitored for moisture content, oxidation levels and flowability tests.
4. Representative samples will be subjected to freeze/thaw cycles before and after the aging process. The samples will be checked for effects on mull integrity.

Inerted Bin Storage

Exposed Tray

Exposed Tray

Closed Bin Storage

Open Bin Storage

Figure 6
Milled Coal Aging Studies

1. All samples +/- 3 gal
2. All samples +/- 20 mu
- Particle Size and +/- 30% Moisture Content

MA1 - Mulling Agent #1
MA2 - Mulling Agent #2

Table V

Test Results from Outdoor Aging Studies
of Milled Coal

	Storage Time, days				
	0	30	44	58	70
<hr/>					
Sample A1					
<hr/>					
Open Bin Storage					
2% Mulling Agent					
Bulk Density, lbs/cuft.	29.34	27.40	26.45	25.05	26.71
Moisture, Wt. %	30.64	27.84	16.80	17.20	20.00
Sample A2					
<hr/>					
Exposed Shallow Tray					
2% Mulling Agent					
Bulk Density, lbs/cuft.	28.90	23.33	21.87	21.51	24.13
Moisture, Wt. %	30.89	24.58	1.00	1.00	0.79
Sample B1					
<hr/>					
Open Bin Storage					
1% Mulling Agent	31.44	30.29	27.51	26.00	26.11
Bulk Density, lbs/cuft.	31.77	23.50	17.30	2.80	14.40
Moisture, Wt. %	1.03	N/A	N/A	2.30	1.50
Sample B2					
<hr/>					
Closed Bin Storage					
1% Mulling Agent					
Bulk Density, lbs/cuft.	30.15	28.84	28.36	28.67	28.63
Moisture, Wt. %	29.91	27.84	28.90	28.70	25.70
Sample B3					
<hr/>					
Inerted Bin Storage					
1% Mulling Agent					
Bulk Density, lbs/cuft.	31.64	28.04	26.34	26.61	27.11
Moisture, Wt. %	30.03	20.56	22.22	15.70	17.50
Sample B4					
<hr/>					
Open Bin Storage					
2% Mulling Agent					
Bulk Density, lbs/cuft.	27.24	25.53	24.02	25.05	23.81
Moisture, Wt. %	30.89	25.40	43.10	18.40	19.20

Table V (cont.)

Sample B5	Storage Time, days				
	0	30	44	58	70
Closed Bin Storage					
2% Mulling Agent					
Bulk Density, lbs/cuft.	28.13	27.19	26.62	26.50	25.34
Moisture, Wt. %	30.17	26.86	23.5	27.20	28.00
Sample B6					
Inerted Bin Storage					
2% Mulling Agent					
Bulk Density, lbs/cuft.	27.87	26.79	24.74	26.52	25.98
Moisture, Wt. %	28.93	28.89	27.00	26.10	26.70
Sample B7					
Exposed Shallow Tray Storage					
2% Mulling Agent					
Bulk Density, lbs/cuft.	28.33	21.15	20.57	20.62	21.99
Moisture, Wt. %	30.64	3.40	2.00	1.10	1.20
Sample B8					
Open Bin Storage					
3% Mulling Agent					
Bulk Density, lbs/cuft.	24.84	23.06	20.97	22.19	21.14
Moisture, Wt. %	30.62	24.58	20.40	17.90	18.40
Sample B9					
Closed Bin Storage					
3% Mulling Agent					
Bulk Density, lbs/cuft.	25.64	25.43	24.52	25.65	25.18
Moisture, Wt. %	32.81	29.48	31.20	27.60	30.30
Sample B10					
Inerted Bin Storage					
3% Mulling Agent					
Bulk Density, lbs/cuft.	26.98	24.54	23.52	24.28	23.76
Moisture, Wt. %	29.95	22.22	22.10	18.90	17.00

FIGURE 7

Effect of Outdoor Aging on
The Bulk Densities of Mulled Coal

FIGURE 8
Moisture Content of Mulled Coal
Versus Outdoor Storage Time

FIGURE 9
Critical Arching Diameter
As a Function of Moisture Content
and Aging (74 days)

Table VI

SAMPLES OF AGED MULLED COAL
SUBMITTED FOR FLOWABILITY TESTING

<u>Sample No.</u>	<u>Storage Container</u>	<u>Moisture Content</u>	<u>Mull Agent</u>
		<u>Wt. %</u>	<u>Wt. % of Coal</u>
B-1	Open bin	14.0	1.0
B-4	Open bin	20.6	2.0
B-5	Closed bin	28.5	2.0
B-6	Nitrogen inerted bin	26.8	2.0
B-7	Shallow exposed tray	2.5	2.0

4.4 Full System Test

The full system test consisted of:

1. Preparation of a centrifuge wetcake of 1.65% ash Upper Elkhorn coal ground to 20 micron mean particle size with an average moisture level of 50%. The wetcake was prepared at Virginia Tech, drummed and shipped to the Energy International facility at Pittsburgh.
2. Conversion of the wetcake into mull in two steps. The wetcake had formed a hard pack in the drums creating large chunks of material causing feed problems into the processor. The wetcake was pretreated by batch blending it with mulling agent in a mortar mixer to make it suitable for being fed into the small processor. The rough mull was then fed through the processor with additional mulling agent.
3. 1400 pounds of Mulled Coal were sealed in barrels and sent to Grand Forks, North Dakota for atomization testing. Upon arrival, the drums were opened and inspected. The mull was still a granular, free flowing material with some free moisture condensed on the plastic liner.
4. Shipping the 2" processor to UNDEERC and setting up to generate CWF for atomization testing. The CWF was generated with the in-line processor and injected in the spray chamber. CWF samples were taken and rheological measurements made.
5. The as-received and air dried mull samples were injected into the solids fuel system to measure particle sizes of the mull under varied conditions of air transport.

TABLE VII
Bulk Flow Properties of Aged
Mull coal Samples

Sample No.	B1	B4	B5	B6	B7
Moisture, Wt.%	14.0	20.6	28.5	26.8	2.5
Mulling Additive, Wt.%	1.0	2.0	2.0	2.0	2.0
Critical Arching Dimension					
For Mass Flow:					
Steady Flow:					
round outlet diameter	0.7'	0.8'	1.6'	1.5'	0.7'
slot outlet diameter	0.35'x1.0'	0.4'x1.2'	0.8'x2.4'	0.7'x2.1'	0.35'x1.1
Time Consolidation:					
round outlet diameter	2.1'	2.0'	2.8'	2.5'	1.1'
slot outlet diameter	1'x3'	1'x3'	1.3'x3.9'	1.2'x3.6'	0.5'x1.5
Stable Rathole Diameters					
Steady Flow:					
Time Consolidation:	1.5'	1.4'	2.5'	2.2'	1.25'
	3.1'	3.0'	5.5'	4.8'	2.2'
Minimum Hopper Slope Angles					
For Mass Flow, (deg.)					
Cone:					
UHMP (Polyethylene)	90	90	90	90	90
304-25 stainless steel	90	90	90	85	90
Wedge:					
UHMP (Polyethylene)	90	90	89	80	79
304-25 stainless steel	90	90	83	76	79
Self Cleaning Hopper and Chute					
Angle, (deg.)					
UHMP (Polyethylene)	77	70	70	65	60
304-25 stainless steel	78	78	70	60	60
rusted carbon steel	75	75	80	77	70

4.4.1 Continuous CWF Production

The specifications for the CWF will vary depending on the combustion system. However, general specifications will include:

Particle Size: Provided in feed coal

Solids Loading: 65-70% for industrial size
60-65% for residential/commercial
45-50% for heat engines

Viscosity: To be determined but will generally be required to have a power law factor <1.1 with viscosity $<1000 \text{ cp @ } 100 \text{ sec}^{-1}$.

Stability: CWF will be prepared at the point and time of usage with no storage. The system will be purged at shutdown.

For this study, the CWF specs were chosen to match those for heat engine fuels. This choice was dictated largely by the high moisture level of the wetcake (50%) and particle size (20 microns).

To establish the preferred conditions for the preparation of the CWF for the trials at UNDEERC a series of experiments were carried out using the two-inch continuous processor and varying the surfactant concentration. The rheological properties of the resulting slurries were then measured. The experiments carried out and the results are shown in Table VIII. It can be seen that acceptable slurries were prepared at surfactant concentrations ranging from 0.7 to 2.0% based on the weight of the coal. This was the range of surfactant concentrations used to determine its effect on spray properties in the tests at UNDEERC.

4.4.2 CWF Atomization Facilities and Procedures

The slurry atomization tests were conducted using EERC's existing spray chamber and coal water fuel (CWF) feeding system. The tests utilized EI-supplied equipment to convert the Milled Coal into a CWF. The CWF was fed to the inlet of a Moyno pump to deliver the CWF to the atomizer chamber. The process variables that were examined included atomizing air-to-fuel ratio, fuel and atomizing air temperatures, slurry and rheology and additive concentrations for their effect on droplet size distributions and spray angle. The system and details of the operation are described in Appendix 6.3.

An existing pressure vessel was modified to include observation ports to perform atomization studies under typical turbine operating pressures and air flows. The system is described in Appendix 6.3, Section 3.1. This apparatus was used to conduct atomization tests on Energy International's coal-water fuel derived from their Milled Coal.

Table VIII

CONVERSION OF MULLED COAL PRODUCT TO COAL-WATER-SLURRY IN THE
2-INCH CONTINUOUS PROCESSOR AT VARIOUS DISPERSANT CONCENTRATIONS

Test No.	Mull Rate lb/hr	Dispersant Rate (1)		Viscosity		PLF	Slurry Product	
		cc/min.	conc. %	% of coal	100 sec ⁻¹	200 sec ⁻¹	% Solids	% Coal
006-TCP-1	52	7.6	25	1.0	276	449	61.7	57.4
006-TCP-2	52	15.2	25	2.0	122	149	59.5	54.2
006-TCP-3	52	15.2	18.75	1.5	112	146	58	53.2
006-TCP-4	52	15.2	12.5	1.0	111	149	58	53.7
006-TCP-5 (3)	52	15.2	6.25	0.5	-	-	-	-
006-TCP-6	52	15.2	8.33	0.67	129	195	57	53.0

(1) 25 wt. % in water solution

(2) Includes agent added to coal (6 wt. % of dry coal) plus dispersant

(3) Did not make slurry

4.4.3 Mulled Coal Feed Facilities and Procedures

The objectives of the solid Mulled Coal testing was to determine how well the Mulled Coal can be fed in a manner similar to a pulverized coal and to look for a significant particle size decrease as the solid fuel is fed through a screw feeder and pneumatically conveyed through a piping system which simulates a primary air coal feed line on a boiler. The effects of air temperature, particle residence time, and the starting Mulled Coal moisture levels on the particle size distribution of the solid fuel leaving the piping system was examined. The solid form of the Mulled Coal was dispersed or "atomized" utilizing the pilot-scale combustion facility feed system. The fuel was dispersed through a piping system and then into the back end of the ash-fouling furnace where it was collected.

A test loop was constructed at the EERC for the purpose of feeding the Mulled Coal and evaluating particle degradation over time at two temperature set points. The loop, shown in Figure 10, was constructed of 1-inch Schedule 40 type 304 stainless steel pipe. The test loop utilized flanged junctions at intervals of approximately 104 inches to allow measurement of particle size at different residence times. The test loop was attached to the EERC's combustion test facility (CTF, described in Appendix 6.3, Section 3.1) to obtain the air required to convey the Mulled Coal through the test loop. The test loop was connected to a CTF forced draft fan through the existing primary air line and plumbed to a particle collection cyclone and the induced draft fan at the CTF exit.

The CTF has an air preheater to provide heated combustion air to the system. The heaters are adjustable and were used in conjunction with an air heater bypass line to control air temperatures for the Mulled Coal test series. An AccuRate screw feed system, shipped with the slurry mixer and the Mulled Coal, was used to convey the mull to a Venturi feeder located at the top of the test loop. The feeder was mounted on a scale above the test loop to verify feed rates and can be seen in Figure 11. The mull was metered into the throat of the Venturi feed system by the AccuRate feeder where it was picked up by the preheated air and conveyed through the test loop past the Malvern particle sizer to the cyclone separator where it was removed from the gas stream prior to entering the induced-draft fan.

4.4.4 Results of Atomization Testing

4.4.4.1 CWF Atomization Test Results

Atomization testing was performed on the slurried Mulled Coal at three different additive concentrations under the subcontract between Energy International Corporation and UNDEERC. Tables IX through XI summarize the data collected for the atomization tests using the three CWF formulations. Table XII shows properties of the three coal-water fuel formulations atomized for this project. Results from the atomization testing are shown in Figure 12. These CWFs were atomized both at room temperature and were preheated to approximately 130°F. As can be seen from the figure, all three CWFs atomized very well, especially at higher atomizer pressure ratios (i.e., higher atomizing air-to-fuel ratios). This figure indicates that preheating the CWF/atomizing air improved the atomization of the 1% and 2% additive concentration CWF, especially at lower atomizer pressure ratios (i.e., lower atomizing air-to-fuel ratios). This is expected atomization be-

Figure 10
MULLED COAL TEST LOOP

Figure 11

MULLED COAL FEED SYSTEM

Table IX

ATOMIZATION OF CWF PREPARED FROM MULLED COAL WITH 1% SURFACTANT

Test No.	Atom. Air Press. psia	Fuel Deliv. Press. psia	Spray Cham. Air Press. psia	Test Fuel Flow Rate lb/hr	Atom. Test Fuel Temp. °F	Atom. Air Temp. °F	Total Air Flow Rate scfm	Atom. Air Flow Rate lb/hr	Atom. Air-to-Fuel Ratio	Atom. Press. Ratio	Corr. SMD μ m	Corr. VMD μ m
1	151.9	107.4	101.7	142.5	86	72	301	249	1.74	1.43	34.0	119.3
2	151.5	104.9	100.3	125.6	86	72	296	249	1.99	1.45	46.7	138.9
3	128.5	108.3	99.8	125.2	87	66	299	189	1.51	1.25	96.2	141.9
4	117.3	109.6	99.8	125.2	85	64	299	151	1.21	1.15	122.3	183.9
5	111.6	113.8	100.2	125.0	84	67	299	125	1.00	1.10	201.3	275.4
6	150.8	99.1	100.4	126.3	118	130	300	244	1.93	1.44	56.3	95.1
7	127.6	99.9	99.9	126.5	122	151	298	184	1.45	1.24	70.8	113.0
8	119.0	100.3	100.8	126.4	133	168	299	155	1.22	1.16	78.2	122.9
9	108.5	99.6	99.4	126.4	128	189	301	122	0.97	1.08	89.6	124.5

Table X

ATOMIZATION OF CWF PREPARED FROM MULLED COAL WITH 2% SURFACTANT

Test No.	Atom. Air Press. psig	Fuel Deliv. Press. psig	Spray Cham. Air Press. psig	Test Fuel Flow Rate lb/hr	Atom. Test Fuel Temp. °F	Atom. Air Temp. °F	Total Air Flow Rate scfm	Atom. Air Flow Rate lb/hr	Atom. Air-to-Fuel Ratio	Atom. Press. Ratio	Corr. SMD μ m	Corr. VMD μ m
1	146.4	108.2	99.9	125.9	81	69	301	242	1.92	1.41	61.2	101.5
2	126.9	109.7	100.8	126.0	81	64	299	187	1.49	1.23	75.6	117.3
3	116.8	109.0	99.8	125.8	81	61	301	156	1.24	1.15	143.4	243.6
4	110.7	110.4	100.3	125.7	81	65	300	126	1.00	1.09	235.7	311.6
5	150.4	99.3	99.7	126.0	136	169	300	238	1.88	1.44	60.9	102.9
6	150.7	98.6	101.3	126.5	143	165	300	239	1.89	1.43	63.6	105.3
7	129.8	100.8	100.2	127.0	132	176	301	189	1.49	1.26	85.5	174.3
8	117.9	101.7	100.4	126.8	132	192	300	153	1.20	1.15	95.5	198.3
9	111.5	102.3	100.5	127.5	143	212	300	120	0.94	1.10	171.4	256.6

Table XI

ATOMIZATION OF CWF PREPARED FROM MULLED COAL WITH 0.6% SURFACTANT

Test No.	Atom. Air Press. psig	Fuel Deliv. Press. psig	Spray Cham. Air Press. psig	Test Fuel Flow Rate lb/hr	Atom. Test Fuel Temp. °F	Atom. Air Temp. °F	Total Air Flow Rate scfm	Atom. Air Flow Rate lb/hr	Atom. Air-to-Fuel Ratio	Atom. Press. Ratio	Corr. SMD μ m	Corr. VMD μ m
1	128.2	103.5	99.7	127.8	146	173	300	181	1.42	1.25	108.3	250.4
2	119.6	104.1	99.9	127.9	144	183	300	154	1.20	1.17	137.9	285.4
3	110.2	104.5	99.8	127.6	145	193	300	123	0.96	1.09	228.7	330.2
4	103.3	104.2	98.8	127.6	147	204	301	93	0.73	1.04	443.5	422.2
5	144.1	100.3	100.3	116.9	76	64	299	224	1.92	1.38	47.0	78.7
6	140.2	104.6	99.8	128.8	79	67	299	223	1.73	1.35	69.0	115.1
7	123.9	109.1	98.3	128.3	76	66	301	183	1.42	1.23	96.6	185.7
8	118.4	112.0	99.5	128.6	76	64	301	160	1.25	1.17	99.8	176.4
9	109.4	114.0	100.2	128.9	76	65	300	122	0.95	1.08	91.5	112.7
10	105.4	114.6	99.9	129.5	75	64	299	98	0.76	1.05	149.6	216.5
11	146.7	97.8	99.5	128.6	134	151	301	227	1.76	1.41	72.9	96.1
12	148.9	100.2	99.8	128.3	123	152	300	232	1.81	1.43	77.7	100.7

havior because preheating the CWF should lower the viscosity of the fuel. However, preheating the 0.6% additive CWF appears to have significantly decreased atomization performance.

Table XII

MOISTURE LEVELS AND PARTICLE SIZE DISTRIBUTION
OF CWF OBTAINED FROM MULLED COAL

	<u>Mulled Feed Coal</u>	<u>CWF with 1% Additive</u>	<u>CWF with 2% Additive</u>	<u>CWF with 0.6% Additive</u>
Solids Loading of CWF	59.6	57.4	57.9	56.4
Particle Size, mean μm^*	23.3	11.2	10.8	11.3
Top Size, (100%), μm	162.0	57.7	42.9	89.9

* Obtained using Malvern and PS14 and PS23 recirculating flow-through cell in water.

4.4.4.2 Mulled Coal Dry Feed Test Results

Dry feed tests using the Energy International Mulled Coal were completed for the test program. Initial shakedown dry feed tests using pulverized coal in a recently built Venturi-type coal feeder showed that dusting of the lenses in the sight port was going to be a problem; however, when the lenses were removed, and air was allowed to pass through the lens openings, subsequent tests were successful. This coal feeder provides a significantly better vacuum to pull the coal particles into the preheated primary air stream for the UNDEERC 600,000 Btu/hr ash-fouling combustion furnace. However, this Venturi coal feeder has smaller passages than the original coal feeder, and significant plugging problems were experienced with the Mulled Coal. Insertion of a 1/2" square mesh into the feeder funnel appeared to break up the mull dropping from the AccuRate screw feeder, but still did not prevent the feeder from plugging. An older coal feeder was installed in the system, but did not provide sufficient vacuum with the sight port lenses removed to pull the mull into the piping system. In order to obtain a vacuum at the feeder, plexiglass piping was made which fit snugly around the Malvern 2600 enough to provide a vacuum at the coal feeder so that the Mulled Coal would feed. This piping also allowed the Malvern lenses to be recessed back from the sight port openings to prevent the Malvern lenses from being coated with coal particles.

Table XIII summarizes the test results from the Mulled Coal dry powder feed tests. The air-dried mull contained approximately 30.0 wt. % moisture, while the as-received mull was approximately 40.3 wt. % moisture. One temperature range was selected to be below the boiling point of water, while the other was selected to be above the boiling point of water. It appears that higher temperatures help reduce the particle size of the as-received mull fed to the system. Temperature did not appear to significantly affect the particle size of the air-dried mull, presumably because there is less loosely bound moisture to be evaporated from the mull.

Figure 12
Particle Size of Sprayed Coal-Water Fuel
As a Function of the Air/Fuel Ratio

Table XIII

ATOMIZATION TESTS OF GRANULAR MULLED COAL

Fuel Type	Coal Feed Rate lb/hr	Prim. Air Flow Rate scfm	Feed. Inlet Air Temp °F	Sight Port Air Temp °F	Sight Port Diff. Temp °F	Dist. to Sight Port in.	Avg. Gas Vel. ft/s	Part. Resid. Time sec.	Corr. SMD um	Corr. VMD um
Air-Dried Mull	36.5	13.5	215	100	ND	316	49.1	0.54	55.0	109.1
Air-Dried Mull	19.2	14.4	170	118	21	316	51.2	0.51	29.4	55.6
Air-Dried Mull	16.4	14.3	180	109	24	316	50.8	0.52	43.9	74.1
Air-Dried Mull	21.0	14.3	336	168	19	316	59.7	0.44	24.0	30.6
Air-Dried Mull	19.2	14.2	346	172	13	316	60.1	0.44	30.0	38.8
Air-Dried Mull	22.2	15.1	340	238	76	108	66.3	0.14	17.6	30.1
Air-Dried Mull	17.5	15.0	365	122	2	732	62.1	0.98	24.3 _f	29.8
Wet Mull	22.5	14.6	191	114	17	316	52.4	0.50	67.4	137.8
Wet Mull	22.5	14.5	195	117	21	316	52.6	0.50	74.2	144.6
Wet Mull	22.7	14.7	361	172	42	316	62.8	0.42	36.7	65.0
Wet Mull	24	14.7	371	182	47	316	63.4	0.42	38.0	63.0
Wet Mull	27.9	14.7	364	229	100	108	65.1	0.14	50.6	138.1
Wet Mull	36	14.8	377	125	6	732	61.9	0.99	34.9	54.7

5.0 CONCLUSIONS

The Phase II results have confirmed the findings of Phase I, i.e.,

- The granular Mulled Coal has handling characteristics compatible with existing solids handling equipment.
- Open storage does not materially affect handling properties.
- Aged samples will lose surface moisture and will not rewet upon subsequent exposure to rain.
- Mulled Coal can be pneumatically transported and injected into the boiler with heated air without agglomeration.
- Mulled Coal can be converted into CWF with an in-line processor.
- CWF prepared from Mulled Coal in an in-line processor can be readily pumped and atomized.

6.0 APPENDICES

Appendix 6.1

H. COLIJN & ASSOCIATES
FLOWABILITY TESTS ON FRESH MULLED COAL

H. COLIJN & ASSOCIATES
CONSULTING ENGINEERS
TRANSPORTATION & MATERIAL HANDLING SYSTEMS
423 FRANKLIN HTS. DRIVE
MONROEVILLE, PA. 15146

August 26, 1991.

Mr. Bill Gall
Energy International Corp.
135 William Pitt Way, Bldg. A 5
Pittsburgh, PA. 15238.

Flowability Testing of
Mulled Coal
(P.O. # EI-174-2024).

Dear Bill,

In accordance with your purchase order, we tested seven samples of a mulled coal, identified as follows:

	<u>Moisture %</u>	<u>% Mulling Agent</u>
1. No. 005-87A	20	1/2
2. No. 005-88A	20	1
3. No. 005-89A	30	1
4. No. 005-90A	30	2
5. No. 005-91A	30	3
6. No. 005-92A	40	1
7. No. 005-93A	40	3

Our figures 1 through 14 show these test results. Based on these measured flow properties, we determined the basic hopper design criteria as shown in Tables I, II, and III.

We plotted in figures 15 and 16 the critical arching diameters of a conical hopper and stable rathole diameters versus moisture content.

We measured the moisture content on an infra-red CENCO moisture balance. All samples are close to the designated moistures, as determined at your lab.

The term "instantaneous" reflects the strength of the material under "steady flow" conditions. The term "3 days consolidation" reflects the strength after the material has been subjected to 3 days of static pressure.

We did not find much difference among the first two tests at 20% moisture. The higher mulling agent addition of 1% exhibited somewhat greater strength than the 1/2%.

At the higher moistures, however, the mulling agent additions are lowering the strength, and making the mix more flowable.

In case slot openings are contemplated in the final design, care must be taken to taper the slot (from tail to front) at least at 10% along each side.

A stable rathole may form only for a funnel flow type of hopper. During mass-flow, stable ratholes will not form, as the material slides along the steep hopper walls. Our figure 17 shows the typical flow pattern in hoppers.

If you have any further questions, please call us.

Sincerely yours,

A handwritten signature in dark ink, appearing to read 'H. Colijn'. The signature is written in a cursive style with a large initial 'H' and a horizontal line at the end.

H. Colijn.

Table 1.

**H. Colijn and Assoc.
Basic Hopper Design Criteria**

Company: ENERGY INTERNATIONAL CORP.

Material: Mullied Coal

Moisture	18.8%	19.4%
Mulling Agent	0.5%	1.0%

	005-87A	005-88A
Critical Arching Dimension for mass-flow: Steady flow: round outlet diameter slot outlet dimension Time Consolidation: round outlet diameter slot outlet dimension	0.3' 0.15'x0.5' 0.8' 0.4'x1.2'	0.7' 0.35'x1.1' 2.1' 1'x3'
Stable rathole diameters: Steady flow Time Consolidation	0.6' 1.8'	1.6' 3.5'
Minimum hopper slope angles (with horizontal) for mass flow (deg): Cone: UHMP 304-2B stainless steel Wedge: UHMP 304-2B stainless steel	90 90 80 90	90 90 80 90
Self-cleaning hopper and chute angle (with horizontal) (deg): UHMP 304-2B stainless steel Rusted carbon steel	60 73 73	60 76 76

Table II

**H. Colijn and Assoc.
Basic Hopper Design Criteria**

Company: ENERGY INTERNATIONAL CORP.

Material: Milled Coal

Moisture: 29.3% 29.6% 29.7%

Mulling Agent 1.0% 2.0% 3.0%

	005-89A	005-90A	005-91A
Critical Arching Dimension for mass-flow:			
Steady flow:			
round outlet diameter	2.2'	1.3'	0.7'
slot outlet dimension	1'x3'	0.6'x1.8'	0.35'x1.1'
Time Consolidation:			
round outlet diameter	4.7'	3.4'	2.5'
slot outlet dimension	2.2'x6.6'	1.6'x4.8'	1.1'x3.3'
Stable rathole diameters:			
Steady flow	5.5'	2.8'	1.6'
Time Consolidation	11'	7.0'	4.1'
Minimum hopper slope angles (with horizontal) for mass flow (deg):			
Cone:			
UHMP	85	85	85
304-2B stainless steel	85	83	80
Wedge:			
UHMP	75	75	75
304-2B stainless steel	75	73	70
Self-cleaning hopper and chute angle (with horizontal) (deg):			
UHMP	72	72	72
304-2B stainless steel	68	68	68
Rusted carbon steel	84	84	84

Table III

**H. Colijn and Assoc.
Basic Hopper Design Criteria**

Company: ENERGY INTERNATIONAL CORP.

Material: Milled Coal

Moisture	40.3%	39.9%
Mulling Agent	1.0%	3.0%

	005-92A	005-93A
Critical Arching Dimension for mass-flow: Steady flow: round outlet diameter slot outlet dimension Time Consolidation: round outlet diameter slot outlet dimension	5.9' 2.8"x8.4' 16.7' 8'x24'	2.2' 1'x3' 6.4" 3'x9'
Stable rathole diameters: Steady flow Time Consolidation	16.5' *	6.4' 10'
Minimum hopper slope angles (with horizontal) for mass flow (deg): Cone: UHMP 304-2B stainless steel Wedge: UHMP 304-2B stainless steel	85 85 75 75	90 90 85 85
Self-cleaning hopper and chute angle (with horizontal) (deg): UHMP 304-2B stainless steel Rusted carbon steel	67 67 80	70 67 80

FLOW PROPERTIES:

DATE *AUG. 6, 1991*

MATERIAL: *MULLED COAL* SAMPLE NO. *005-87A*
MOISTURE: *18.6%* - *1/2%* Mulling Agent
COMPANY: *ENERGY INTERNATIONAL*

H. COLIJN

CONSULTING ENGINEER

TRANSPORTATION & MATERIAL HANDLING SYSTEMS

423 FRANKLIN HHS. DRIVE

MONROEVILLE, PA. 15146

WALL YIELD LOCI:

DATE: 8/10/91

MATERIAL: MILLED COAL Sample No. 005-87A
MOISTURE: 18.6% - 1/2% Mulling Agent
COMPANY: ENERGY INTERNATIONAL

WALL SHEAR (PSF)
200
100
0

TYPE 304-2B STAINLESS STEEL

WALL SHEAR (PSF)
200
100
0

SOLIDUR 10-100 UHMW POLYETHYLENE

WALL SHEAR (PSF)
200
100
0

RUSTED STEEL

0

100

200

300

400

500

CONSOLIDATION PRESSURE (PSF)

DATE 8/10/91

MATERIAL: MULLED COAL SAMPLE NO. 005-88A

MOISTURE: 19.4% — 1% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

WALL YIELD LOC:

DATE: 8/10/91

MATERIAL: MULLED COAL SAMPLE NO. 105-88

MOISTURE: 19.4% - 1% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

FLOW PROPERTIES:

DATE AUG. 3, 1991

MATERIAL: MULLED COAL SAMPLE NO. 005-89
 MOISTURE: 29.3 % - 1% Mulling Agent
 COMPANY: ENERGY INTERNATIONAL

K&E 10 X 10 TO 1 INCH NEUTRAL & ESSIP 1.0

WALL YIELD LOC.

DATE: 8/10/91

MATERIAL: MILLED COAL SAMPLE NO. 005-87A

MOISTURE: 29.3% - 1% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

FLOW PROPERTIES:

DATE: AUG. 20, 1991

MATERIAL: MILLED COAL SAMPLE NO. 005-90A
 MOISTURE: 29.6% — 2% Mulling AREA
 COMPANY: ENERGY INTERNATIONAL

K&E 10 X 10 TO 1/2 INCH 7.5 X 7.5 INCHES
 KEUFFEL & ESSER CO. 440 N. 10th St.

WALL YIELD LOGS

DATE: AUG 25, 1991

MATERIAL: MILLED COAL SAMPLE NO. 005-90A

MOISTURE: 29.6% - 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

FLOW PROPERTIES:

DATE: AUG. 21, 1971

MATERIAL: MILLED COAL SAMPLE NO. 005-71A

MOISTURE: 29.7% 3% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

H. COLIJN

CONSULTING ENGINEER

TRANSPORTATION & MATERIAL HANDLING SYSTEMS

423 FRANKLIN HTS. DRIVE

MONROEVILLE, PA. 15146

WALL YIELD LOC.

DATE AUG. 24, 1991

MATERIAL: MILLED COAL SAMPLE NO. 005-91A

MOISTURE: 29.7% - 3% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

FLOW PROPERTIES:

DATE AUG 22, 1997

MATERIAL MULLED COAL SAMPLE NO. 005-92A

MOISTURE 40.3% - 1% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

H. COLIJN

CONSULTING ENGINEER

TRANSPORTATION & MATERIAL HANDLING SYSTEMS

423 FRANKLIN HTS. DRIVE

MONROEVILLE, PA. 15146

WALL YIELD LOC:

DATE: AUG - 24, 1991

MATERIAL: MULLED COAL SAMPLE NO. 005-92A

MOISTURE: 40.3% - 1% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

FLOW PROPERTIES:

DATE AUG. 23, 1991

MATERIAL MULLED COAL SAMPLE NO. 005-934

MOISTURE 39.9% = 3% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

K&E 10 X 10 IN. TO 1 INCH
MINIMUM A REGR.

H. COLIJN

CONSULTING ENGINEER

TRANSPORTATION & MATERIAL HANDLING SYSTEMS

423 FRANKLIN HTS. DRIVE

MONROEVILLE, PA. 15146

WALL YIELD LOC.

DATE: AUG. 24, 1971

MATERIAL: MULLED COAL SAMPLE NO. 005-93A

MOISTURE: 39.9% - 3% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

200
100
0

WALL SHEAR (PSF)

TYPE 304-2B STAINLESS STEEL

200
100
0

WALL SHEAR (PSF)

SOLIDUR 10-100 UHMW POLYETHYLENE

200
100
0

WALL SHEAR (PSF)

RUSTED STEEL

200
100
0

WALL SHEAR (PSF)

CONSOLIDATION PRESSURE (PSF)

SUBJECT: Mulled Coal Mixture

DATE: 8/25/91

FIGURE 17

FLOW PATTERNS

Appendix 6.2

H. COLIJN & ASSOCIATES
FLOWABILITY TESTS ON AGED MULLED COAL

H. COLIJN & ASSOCIATES
CONSULTING ENGINEERS
TRANSPORTATION & MATERIAL HANDLING SYSTEMS
423 FRANKLIN HTS. DRIVE
MONROEVILLE, PA. 15146

November 3, 1991.

Mr. Bill Gall
Energy International Corp.
135 William Pitt Way, Bldg. A5
Pittsburgh, PA. 15238.

Flowability Testing of
Mulled Coal

(P.O. # EI-174-2024-
release 3 & 4)

Dear Bill,

In accordance with your instructions, we tested 8 samples
as indicated below:

<u>Sample No.</u>	<u>Moisture %</u>	<u>Mulling Agent</u>	<u>Size (µm)</u>	<u>Stored for 74 days</u>
005-114-1	30.3	0	20	- - - - -
005-114-A	28.0	2	12	- - - - -
005-114-B	29.6	2	70	- - - - -
-B1	14.0	1	20	in open bin
-B4	20.6	2	20	in open bin
-B5	28.5	2	20	in closed bin
-B6	26.8	2	20	in inerted bin
-B7	2.5	2	20	in exposed tray

Note: The stored material had initially about 30% moisture.

The test results are shown in our figures 1 through 16. Based on these measured flow properties, we established the basic hopper design criteria, as shown in Tables 1, 2, and 3.

The following general conclusions can be reached from these and earlier tests.

1. Mulling agent additions lower the cohesive strength of the wet fine coal.
2. The finer the grind, the stronger the cohesive strength.
3. Open storage dries out the mulled coal mix. The greater the exposed area, the greater the evaporation.
4. The compressive strength for a specific final moisture level is about the same whether the material was previously stored or not. The final moisture content is the determining factor. We did not notice any appreciable oxidation-effect.

If you have any further questions, please let us know.

Sincerely yours,

A handwritten signature in dark ink, appearing to read 'H. Colijn', with a stylized, cursive script.

H. Colijn.

Table 1.

H. Colijn and Assoc.
Basic Hopper Design Criteria

Company: ENERGY INTERNATIONAL CORP.
Material: Wet Coal Fines and Mulled Coal
Moisture 30.3% 28.0% 29.6%
Mulling Agent 0.0% 2.0% 2.0%

Sample No.	005-114-1	005-114-A	005-114-B
Critical Arching Dimension for mass-flow: Steady flow: round outlet diameter slot outlet dimension Time Consolidation: round outlet diameter slot outlet dimension	5.1' 2.5'x7.5' 18' 8'x24'	2.0' 1'x3' 3.8' 1.8'x5.4'	0.9' 0.5'x1.5' 2.6' 1.2'x3.6'
Stable rathole diameters: Steady flow Time Consolidation	25' *	3.9' 8.0'	1.8' 4.8'
Minimum hopper slope angles (with horizontal) for mass flow (deg): Cone: UHMP 304-2B stainless steel Wedge: UHMP 304-2B stainless steel	90 90 80 90	90 90 80 90	90 90 80 86
Self-cleaning hopper and chute angle (with horizontal) (deg): UHMP 304-2B stainless steel Rusted carbon steel	70 83 80	65 73 70	65 68 70

* too large to compute

Table 2.

H. Colijn and Assoc.
Basic Hopper Design Criteria

Company: ENERGY INTERNATIONAL CORP.

Material: Milled Coal : After 74 days of storage

Moisture 14.0% 20.6% 28.5%

Mulling Agent 1.0% 2.0% 2.0%

Sample No.	B 1	B 4	B 5
Critical Arching Dimension for mass-flow:			
Steady flow:			
round outlet diameter	0.7'	0.8'	1.6'
slot outlet dimension	0.35'x1.0'	0.4'x1.2'	0.8'x2.4'
Time Consolidation:			
round outlet diameter	2.1'	2.0'	2.8'
slot outlet dimension	1'x3'	1'x3'	1.3'x3.9'
Stable rathole diameters:			
Steady flow	1.5'	1.4'	2.5'
Time Consolidation	3.1'	3.0'	5.5'
Minimum hopper slope angles (with horizontal) for mass flow (deg):			
Cone:			
UHMP	90	90	90
304-2B stainless steel	90	90	90
Wedge:			
UHMP	90	90	89
304-2B stainless steel	90	90	83
Self-cleaning hopper and chute angle (with horizontal) (deg):			
UHMP	77	70	70
304-2B stainless steel	78	78	70
Rusted carbon steel	75	75	80

Table 3.

**H. Colijn and Assoc.
Basic Hopper Design Criteria**

Company: ENERGY INTERNATIONAL CORP.

Material: Mulled Coal After 74 days of storage

Moisture 26.8% 2.5%

Mulling Agent 2.0% 2.0%

Sample No.	B 6	B 7
Critical Arching Dimension for mass-flow: Steady flow: round outlet diameter slot outlet dimension Time Consolidation: round outlet diameter slot outlet dimension	1.5' 0.7'x2.1' 2.5' 1.2'x3.6'	0.7' 0.35'x1.0' 1.1' 0.5'x1.5'
Stable rathole diameters: Steady flow Time Consolidation	2.2' 4.8'	1.25' 2.2'
Minimum hopper slope angles (with horizontal) for mass flow (deg): Cone: UHMP 304-2B stainless steel Wedge: UHMP 304-2B stainless steel	90 85 80 76	90 90 79 79
Self-cleaning hopper and chute angle (with horizontal) (deg): UHMP 304-2B stainless steel Rusted carbon steel	65 60 77	60 60 70

DATE: OCT. 6, 1991

MATERIAL: MULLED COAL SAMPLE 005-114-1
MOISTURE: 30.3% No additive 20μ
COMPANY: ENERGY INTERNATIONAL

WALL YIELD LOC:

DATE: Oct 1, 1991

MATERIAL: MULLED COAL SAMPLE NO. 005-14

MOISTURE: 30.3% No additive

COMPANY: ENERGY INTERNATIONAL

H. COLIJN

CONSULTING ENGINEER

TRANSPORTATION & MATERIAL HANDLING SYSTEMS

423 FRANKLIN HTS. DRIVE

MONROEVILLE, PA. 15146

FLOW PROPERTIES:

DATE: OCT. 4, 1991

MATERIAL: MULLED COAL SAMPLE NO. 005-14A

MOISTURE: 28.0% 2% Mulling Agent 12/11

COMPANY: ENERGY INTERNATIONAL

WALL YIELD LOC.

DATE: OCT. 6, 199

MATERIAL: MULLED COAL SAMPLE NO. 005-114-A

MOISTURE: 28.0% 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

DATE: OCT. 3, 1991

MATERIAL: MULLED COAL (SAMPLE NO. 005-143)
MOISTURE: 29.6% 2% Mulling Agent 70%
COMPANY: ENERGY INTERNATIONAL

WALL YIELD LOC.

DATE: Oct 6, 1991

MATERIAL: MILLED COAL SAMPLE NO. 705-114-B

MOISTURE: 29.6% 2% Mulling 75/100
Agent

COMPANY: ENERGY INTERNATIONAL

DATE: OCT. 24, 1991

MATERIAL: MULLED COAL (SAMPLE B1)

MOISTURE: 14.0% $\pm$ 1% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

DATE: OCT. 26, 1991

MATERIAL: MULLED COAL (SAMPLE B4)

MOISTURE: 20.6% + 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

WALL YIELD LOG

DATE: OCT 30, 1974

MATERIAL: MILLED COAL (SAMPLE B-4)

MOISTURE: 20.6% & 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

K&E 10 X 10 TO 1/2 INCH
KEUFFEL & ESSER CO. MADE IN U.S.A.

DATE: OCT. 31, 1991

MATERIAL: MULLED GOAL (SAMPLE B-5)

MOISTURE: 28.5% ± 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

MATERIAL: MILLED COAL (SAMPLE B-5)

MOISTURE: 28.5% & 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

H. COLIJN

CONSULTING ENGINEER

TRANSPORTATION & MATERIAL HANDLING SYSTEMS

423 FRANKLIN HTS. DRIVE

MONROEVILLE, PA. 15146

FLOW PROPERTIES:

DATE: OCT. 28, 1991

MATERIAL: MULLED COAL (SAMPLE B-6)

MOISTURE: 26.8% $\pm$ 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

WALL YIELD LOC.

DATE: OCT. 30, 1991

MATERIAL: MILLED COAL (SAMPLE B-6)

MOISTURE: 26.8% & 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

K&E
X 10 1/2 INCH
KEUFFEL & ESSER CO. MADE IN U.S.A.

H. COLIJN

CONSULTING ENGINEER

TRANSPORTATION & MATERIAL HANDLING SYSTEMS

423 FRANKLIN HTS. DRIVE

MONROEVILLE, PA. 15146

FLOW PROPERTIES:

DATE: OCT 31 1991

MATERIAL: MULLED COAL (SAMPLE B-7)

MOISTURE: 2.5% & 2% Mulling Agent

COMPANY: ENERGY INTERNATIONAL

WALL YIELD LOG

DATE: OCT 30, 1991

MATERIAL: MILLED COAL (SAMPLE B-7)

MOISTURE: 2.5% ~~2%~~ Mulling Agent

COMPANY: ENERGY INTERNATIONAL

[Faint, illegible handwritten text]

Appendix 6.3

SPRAY TESTING BY UNDEERC

Energy &
Environmental
Research
Center

Fuels & Process Chemistry Research Institute
ND Mining & Mineral Resources Research Institute
Combustion & Environmental System Research Institute

15 North 23rd Street - Box 8213, University Station / Grand Forks, ND 58202-8213 / Phone: (701) 777-5000 FAX: 777-5181

January 15, 1992

Mr. Burl E. Davis
Executive Vice President
Energy International Corporation
135 William Pitt Way
Pittsburgh, PA 15238

Dear Mr. Davis:

Enclosed is a copy of the final report on the "Mulled" Coal Atomization Testing conducted at the University of North Dakota Energy and Environmental Research Center with Energy International.

If you should have any questions, please feel free to call me at (701) 777-5239.

Sincerely,

Mike L. Swanson
Research Engineer
Combustion Systems

MLS/yjq-f

Enclosure

ENERGY INTERNATIONAL "MULLED" COAL ATOMIZATION SUBCONTRACT

Final Report

by

Michael L. Swanson, Research Engineer
Jay R. Gunderson, Research Engineer
Chris M. Anderson, Research Engineer

Energy and Environmental Research Center
University of North Dakota
Box 8213, University Station
Grand Forks, North Dakota 58202

for

Mr. Burl E. Davis
Executive Vice President
Energy International Corporation
135 William Pitt Way
Pittsburgh, Pennsylvania 15238

January 15, 1992

(subcontract with the University of North Dakota Energy and Environmental
Research Center [UNDEERC] under the DOE Prime Contract No.
DE-AC22-90PC90167 entitled "Development of Mulled Coal")

TABLE OF CONTENTS

	<u>Page</u>
LIST OF FIGURES	ii
LIST OF TABLES	iv
1.0 OBJECTIVES	1
2.0 BACKGROUND	1
2.1 Types of Atomizers	2
2.2 Types of Measurement Techniques	2
2.3 Forward Laser Diffraction Sizing Theory	2
2.4 Definition of VMD and SMD	5
2.5 Definition of Rheological Properties/Data Analysis	5
3.0 PROJECT DESCRIPTION	10
3.1 High-Pressure Atomization Spray Chamber	10
3.2 High-Shear Viscometer	11
3.3 Dry Powder Feed Facilities and Procedures	11
4.0 RESULTS	17
4.1 CWF Atomization and Rheology	17
4.1.1 CWF Atomization	17
4.1.2 CWF Rheology	21
4.2 Milled Coal Dry Feed Test Results	29
5.0 CONCLUSIONS	34
6.0 NOMENCLATURE FOR HIGH-SHEAR RHEOLOGY	34
7.0 REFERENCES	35

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1 Properties of scattered light from particles	4
2 Schematic of pressurized spray chamber	12
3 Photograph of pressurized spray chamber	13
4 High-shear viscometer	14
5 Mulled coal test loop	15
6 Schematic of combustion test facility	16
7 Mulled coal feed system	16
8 Plot of corrected SMD for three CWF formulations versus atomizer pressure ratio	20
9 Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 2.0	22
10 Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 1.5	22
11 Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 1.25	23
12 Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 1.0	23
13 Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 0.75	24
14 Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 2.0	24
15 Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 1.5	25
16 Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 1.25	25
17 Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 1.0	26
18 Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 0.75	26

LIST OF FIGURES (Continued)

<u>Figure</u>	<u>Page</u>
19 Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 2.0	27
20 Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 1.5	27
21 Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 1.25	28
22 Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 1.0	28
23 Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 0.75	29
24 Plot of apparent viscosity for CWF with 12.5% additive versus shear rate	30
25 Plot of apparent viscosity for CWF with 25.0% additive versus shear rate	30
26 Plot of apparent viscosity for CWF with 8.33% additive versus shear rate	31
27 Plot of air temperature versus corrected particle size for air-dried and as-received mull coal	32
28 Plot of particle residence time versus corrected particle size for air-dried and as-received mull coal	33

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1 Size Ranges and Lens Cutoff (Vignetting) Distances for Various Range Lenses	5
2 Energy International Mulled Coal-Water Fuel with 12.5% Additive Solution Using Parker Hannifan M2 Nozzle	17
3 Energy International Mulled Coal-Water Fuel with 25.0% Additive Solution Using Parker Hannifan M2 Nozzle	18
4 Energy International Mulled Coal-Water Fuel with 8.3% Additive Solution Using Parker Hannifan M2 Nozzle	18
5 Water Atomization Tests Using Parker Hannifan M2 Nozzle	19
6 Moisture Levels and Particle-Size Distribution of Energy International's CWF Obtained from Mulled Coal	19
7 Energy International Mulled Coal Dry Powder Feed Test Results . . .	32

ENERGY INTERNATIONAL "MULLED" COAL ATOMIZATION SUBCONTRACT

1.0 OBJECTIVES

The objective of Energy International's (EI's) mulled coal atomization subcontract with the University of North Dakota Energy and Environmental Research Center (UNDEERC) is to conduct atomization testing of both the solid and slurry forms of mulled coal. This research is being performed under DOE prime contract No. DE-AC22-90PC90167 entitled "Development of Mulled Coal." The slurry atomization tests are to be conducted using EERC's existing spray chamber and coal-water fuel (CWF) feeding system. These tests will utilize a EI-supplied apparatus for rapidly converting the "mulled" coal to a coal-water fuel. This CWF will be fed to the Moyno pump intake on the EERC CWF feeding system, which will deliver the CWF to the atomization chamber. The CWF drop-let size from the atomizer will be measured using a Malvern 2600 particle-size analyzer with a 300-mm lens capable of measuring droplet sizes up to 564 μm in diameter. The process variables to be examined include atomizing air-to-fuel ratio, fuel and atomizing air temperatures, slurry rheology (both low and high shear) and additive concentrations for their effect on droplet size distribution and spray angle. Either a Parker Hannifan M2 or M6 external mix nozzle will be used, as this atomizer is similar to atomizers used by other CWF researchers. The M6 nozzle was designed for operation under pressure, while the M2 nozzle is designed for atmospheric pressure applications. The deliverables will include a final report describing the results of a statistical analysis of the droplet sizes measured by the Malvern 2600.

The objectives of the solid mulled coal testing are to determine how well the mulled coal can be fed in a manner similar to a pulverized coal and to look for a significant particle size decrease as the solid fuel is fed through a screw feeder and pneumatically conveyed through a piping system which simulates a primary air coal feed line on a boiler. The effects of air temperature, particle residence time, and the starting mulled coal moisture levels on the particle-size distribution of the solid fuel leaving the piping system will be examined. The solid form of the mulled coal will be dispersed or "atomized" utilizing the pilot-scale combustion facility feed system. The fuel will be dispersed through a piping system and then into the back end of the ash-fouling furnace where it will be collected. The system piping and sight port will have to be modified for this testing. The deliverables will include a report which will detail a statistical analysis of these variables on the "mulled" coal particle-size distribution and a determination of whether further particle-size reduction is required to achieve a typical pulverized coal distribution.

2.0 BACKGROUND

Achieving a high level of atomization is a key requirement for attaining high combustion efficiencies in CWF-fired combustors. Superior atomization should improve flame stability, combustor turndown, and carbon burnout by limiting the agglomeration of the coal particles in a droplet as the carrier fluid is evaporated. The principal aim of fuel atomization is to achieve a high ratio of fuel surface area to mass, which produces very high evaporation rates and keeps the number of coal particles per droplet to a minimum. A good review of atomization technology is given in the book by Lefebvre (1).

Several researchers have shown that carbon conversion decreases and the mass mean ash particle diameter increases with increasing mass mean droplet diameter (2,3). Atomization performance can be sensitive to small changes in water content and to the chemical and physical effects of additives. Atomized slurry droplet size has been found to decrease with increasing air-to-fuel ratio (4). Atomization performance is also affected significantly by the atomizer design itself. Other researchers have reported that atomization appears to be strongly affected by rheology (5,6) and that measured SMD decreases with increasing spray chamber pressure (6). It has also been reported that SMD decreases by preheating the atomizing air (7). At distances greater than 2 to 4 inches downstream from the atomizer, SMDs were shown to increase and obscuration decrease with increasing distance downstream from the atomizer (8).

2.1 Types of Atomizers

The goal of the atomization process is to convert the flow of liquid fuel into a controlled spray of small fuel droplets. The best atomization performance is achieved when sprays of a high surface-to-volume ratio are obtained, since the high surface-to-volume ratios result in higher fuel evaporation rates. The major types of atomizers that have been used for the atomization of conventional liquid fuels are 1) pressure atomization, 2) pressure-swirl atomization, 3) air assist atomization, and 4) airblast atomization (1). Pressure and pressure-swirl atomization use high liquid fuel pressure to atomize the fuel through a small orifice. A second approach, which includes air-assist and airblast atomizers, uses a high velocity air stream to shear the relatively low velocity liquid fuel, thereby forming a liquid droplet spray. The air-assist atomizers can consist of external mix atomizers (air and fuel mixed external to the atomizer) or internal mix atomizers (air and fuel mixed inside the atomizer and then passing through a common orifice).

2.2 Types of Measurement Techniques

Measurement techniques for determining spray droplet size consist of imaging and nonimaging techniques. Imaging techniques include high-speed cinematography, strobe photography, and holography. Nonimaging techniques include forward light-scattering techniques, such as the commercially available Malvern particle-size analyzer, and laser-Doppler techniques, such as the Aerometrics Phase Doppler particle sizer. The forward light-scattering technique is an ensemble or multiparticle scattering method which measures the aggregate effect of multiple droplets present in the laser beam line of sight. The laser Doppler technique is a single particle counter that collects scattered light from individual particles as they traverse a small illuminated sample volume.

2.3 Forward Laser Diffraction Sizing Theory

The principle of the forward light-scattering technique used in this research is based on Fraunhofer diffraction theory for a spherical particle with a diameter d significantly greater than the wavelength, as given in Equation 1.

$$I(\theta) = I_{inc}(\alpha^4 \lambda^2 / 16\pi^2) (2J_1(\alpha\theta) / \alpha\theta)^2 \quad [\text{Eq. 1}]$$

where: I_{inc} = intensity incident on the particles (assumed constant)
 $\alpha = \pi D/\lambda$ the size parameter
 J_1 = first-order Bessel function of first kind
 λ = light wavelength, and
 θ = scattering angle measured from incident beam propagation direction

The diffraction signature of a polydisperse spray is given by Equation 2.

$$I(\theta) = \int_0^\infty n(\alpha) I_{inc} (\alpha^4 \lambda^2 / 16 \pi^2) (2J_1(\alpha \theta) / \alpha \theta)^2 d\alpha \quad [\text{Eq. 2}]$$

where $n(\alpha) d\alpha$ is the number of droplets with sizes between $\alpha + d\alpha$.

The Malvern 2600 particle-size analyzer uses a 2-mW HeNe laser whose 633-nm wavelength beam is spatially filtered, expanded, and collimated to a 9-mm diameter (9). The beam is aligned on a central detector to measure beam power and to set the system baseline. A fuel spray is passed directly through the beam where the light scattered by the particles and the unscattered remainder pass through the receiver lens. The receiver lens acts to Fourier transform the diffraction pattern of the scattered light at its focal plane. This transformed scattered light impacts a custom-designed detector, in the form of 31 concentric annular rings, which gathers the scattered light over a range of solid angles of scatter. The detector provides an electronic signal proportional to the light energy measured over the 31 separate solid angles of collection. When a particle scatters light, it produces a unique light intensity as a function of the angle of observation. The scattered light is related to the diameter of the particle. Large particles scatter light at small angles of scatter, while small particles scatter light at large angles, as shown in Figure 1.

In practice, many particles are simultaneously present in the analyzer beam, and the scattered light measured on the detector is the sum of all individual patterns overlain on the central axis. Thus the system inherently measures the integral scattering from all particles present in the beam. To avoid the possibilities of inadequate statistical significance and unrepresentative sampling of the spray, time-averaged measurements of the light scattering are collected while the spray is passing through the beam. These time-averaged measurements are obtained by having the computer make many detector readings (sweeps) and averaging these sweeps to create an average light scattering based on millions of droplets. This measured light-scattering signal can then be analyzed independently of any model or can be fit to different types of models such as Rosin-Rammler, normal, or log-normal (9). If models are used, caution must be utilized to ensure that the data actually fit the model selected. It has been reported that it is best to perform the tests using the model-independent mode (10).

Potential errors in the Malvern measurements can result from lens cutoff (vignetting), multiple scattering, and beam steering. Vignetting is the result of the sample being too far away from the range lens, which causes some of the scattered light to fall outside the range lens and not be transformed onto the detector rings. The lens cutoff distances for the different range

Figure 1. Properties of scattered light from particles (9).

lenses are given in Table 1. In order to ensure that no vignetting occurs, the point where the beam first intersects the droplets should be within the cutoff distances listed below.

Multiple scattering results when there are so many particles in the beam path that a significant quantity of the light is being diffracted more than once. The Malvern analysis assumes that scattered light is collected independently of other particles. It has been reported that at obscurations greater than 0.5, a significant amount of light is either rescattered outside the detector area and lost, or is rescattered to smaller angles than the angle originally diffracted (10). Multiple scattering has been shown to result in a smaller droplet size distribution than those measured at lower obscurations. One technique to reduce multiple scattering is to perform the drop size measurements further downstream from the atomizer, thereby reducing the fraction of the spray which is passing through the beam at any given time. Another technique is to utilize a sight pipe which protrudes partway into the spray to reduce the total length of the spray that the light must pass through. This technique has also been used to prevent vignetting problems. Various researchers have also determined corrections which can be applied to Malvern data when the obscuration values are above 0.5 (11-13).

Beam steering is caused by the suspending fluid having an unstable refractive index under the conditions of measurement. These refractive index variations could be caused by temperature gradients around hot gas streams, turbulent structure within the fluid, etc. These types of errors result in light scattering at low angles, thus appearing to result from very large droplets. In general, these low-angle scattering contributions will be present when the suspending fluid only is measured, providing some indication that there is a refractive index instability problem. Potential solutions to the refractive index problem are to eliminate the instability (i.e., eliminate the thermal gradient or turbulent structure in the suspending fluid) or to make measurements in the presence of such fluctuations by limiting the dynamic range of the analyzer. However, the ability to measure particle sizes that scatter at the same low angles will be lost.

TABLE 1
Size Ranges and Lens Cutoff (Vignetting)
Distances for Various Range Lenses

<u>Range Lens</u>	<u>Size Range (μm)</u>	<u>Cutoff Distance (mm)</u>
63	1.2 - 118	55
100	1.9 - 188	133
300	5.8 - 564	400
600	11.6 - 1128	780
800	15.5 - 1503	1050
1000	19.4 - 1880	1300

2.4 Definition of VMD and SMD

The fundamental measurement from the Malvern 2600 is volume of the particles. All other outputs from the Malvern are calculated results from the volume measurements assuming spherical particles are being measured. Mass-related outputs are derived assuming a uniform density for the measured drop-let volumes. The average drop size of a spray is usually reported as the volume median diameter (VMD), the mass mean diameter (MMD), or the Sauter mean diameter (SMD). In mathematical terms, the VMD is expressed in Equation 3.

$$\text{VMD} = (\sum nD^3 / \sum n)^{1/3} \quad [\text{Eq. 3}]$$

The SMD is defined as the diameter of a drop having a surface-to-volume ratio equal to that of the spray. SMD can be calculated by Equation 4.

$$\text{SMD} = \sum nD^3 / \sum nD^2 \quad [\text{Eq. 4}]$$

Since the purpose of atomization is to obtain high evaporation rates by achieving high surface-to-volume ratios, the SMD is the preferred format for reporting fuel sprays.

2.5 Definition of Rheological Properties/Data Analysis

Rheological studies of CWF are needed to aid the formulation and utilization of CWF suitable for boiler and heat engine applications. Efficient operation of boilers and advanced heat engine combustion systems depends on high CWF carbon burnout. Previous studies have shown atomization quality to be a critical parameter influencing combustibility of CWF in turbine and diesel engine applications. The apparent viscosity of CWFs at the high-shear rates present during atomization was found to have a dominant effect on atomization quality as measured by the size distribution of atomized droplets (14).

Coal-water rheology is complex and composition-dependent. Variables, such as particle-size distribution, solids concentration, and additive

package, influence flow properties (15). In general, CWFs can be classified as non-Newtonian and typically exhibit shear-dependent flow behavior which can be either pseudoplastic or dilatant.

The objective of this study is to determine the flow behavior of the CWFs at the high-shear rate region characteristic of the point of atomization. The relationship between high-shear and low-shear flow behavior and apparent viscosity, as well as variables such as additive concentration, will be studied. Additionally, a correlation between high-shear flow behavior and apparent viscosity with droplet size distribution during atomization may be established. Yu and others (14) considered that atomization quality predictions can be made using effective viscosity measurements at a shear rate range of 10,000-100,000 sec^{-1} , calculated to arise at atomization. They reported linear relationships between mean droplet size and apparent viscosity at this shear region.

To determine flow behavior, viscometers measure the deformation that occurs when a force or a shearing action is applied to a given fluid. Shear stress is defined as the ratio of this force to the area on which it is applied. The apparent viscosity is defined as the ratio of wall shear stress to the rate of shear applied to the fluid.

Previous studies at UNDEERC found various CWFs exhibited pseudoplastic flow behavior at the low-shear rate region of up to 450 sec^{-1} (15). Apparent viscosity of various CWFs appeared to be a function of the solids concentration. Use of a dispersant additive (nonionic surfactant type) was found very effective in decreasing apparent viscosity at low-shear rates (100 sec^{-1}) by almost one order of magnitude (15). However, flow behavior was found to be adversely affected by the use of a dispersant, which induced shear-thickening behavior. Mannheimer also reported shear-thickening behavior of a low solids content micronized CWF with dispersant additive at shear rates of up to 10,000 sec^{-1} (16).

Measurement of flow properties at high-shear rates with rotational viscometers, such as the HAAKE concentric cylinder viscometer, becomes very cumbersome as the frictional heat buildup becomes significant. Capillary tube viscometers, such as extrusion rheometers, avoid this problem by once-through flow of the fluid which carries out the built-up heat. Extrusion rheometers use a pressurized vessel to force the fluid through a long, smooth cylindrical capillary tube of known dimensions. The frictional pressure drop associated with the laminar flow of the fluid and the corresponding flow rate is measured. For determination of the flow curve, several measurements are necessary at different pressures and length-to-diameter ratios of the capillary.

For a fluid in steady laminar flow within a tube of radius R and length L , with a pressure difference between the ends of the capillary tube, ΔP , a viscous force tending to retard flow will be exactly balanced by a force resulting from the ΔP . Therefore, the shear stress at any point in the capillary is directly proportional to the distance from the center of the tube and to the pressure gradient.

$$\tau = (\Delta P \cdot r) / 2L \quad [\text{Eq. 5}]$$

Shear stress at the center of the capillary is zero and becomes maximum at the wall. This linear relationship of shear stress with tube radius is valid regardless of the nature of the fluid. At the wall, the shear stress is proportional to the radius R .

$$\tau_w = (\Delta P_r \cdot R)/2L \quad [\text{Eq. 6}]$$

The rate of shear also varies with the radius and is dependent on the nature of the fluid. For a Newtonian fluid, shear rate decreases linearly with the radius.

$$\gamma = (-dV/dr) = 8V/D = (32Q/\pi D^3) \quad [\text{Eq. 7}]$$

However, for a non-Newtonian fluid, the relationship is more complex. The shear rate at the wall is determined by applying the Rabinowitsch correction to the average rate of shear calculated from the volumetric flow rate.

$$\gamma_w = (8V/D)(3n'+1)/4n' \quad [\text{Eq. 8}]$$

where

$$n' = (d \ln \tau / d \ln \gamma) \quad [\text{Eq. 9}]$$

For the laminar tube flow of any time-independent fluid, $\tau(8V/D)$ is some unique function of τ_w only. This may be expressed as

$$\tau_w = K'(8V/D)^{n'} \quad [\text{Eq. 10}]$$

where, in the most general case, K' and n' are not constants, but vary with $8V/D$. Equation 10 is the equation of the tangent to the curve at a given value of $8V/D$, n' being the slope of this tangent and K' its intercept on the ordinate at $8V/D$ equal to unity.

For non-Newtonian fluids, shear rate and shear stress are related by the coefficient of proportionality known as the apparent viscosity. Unlike Newtonian viscosity, this apparent viscosity is not a constant and is a function of the shear rate.

$$\mu_a = \tau/\gamma \quad [\text{Eq. 11}]$$

Apparent viscosity is determined from measurement of the pressure drop in the capillary tube and the associated flow rate. Shear rate and shear stress are calculated at the same point in the capillary (i.e., the wall) so that:

$$\mu_a = \tau_w / \gamma_w = [(\pi \cdot \Delta P_r \cdot D^3) / (128 L \cdot Q)] (3n' + 1) / 4n' \quad [\text{Eq. 12}]$$

A power law model, where the shear stress is proportional to the power of the shear rate, describes flow behavior of many non-Newtonian fluids and has been successfully applied to CWF. When the shear rate increases more than in proportion to the shearing stress, the fluid is called pseudoplastic or shear-thinning. For the case of a dilatant or shear-thickening fluid, the shear rate increases less than in proportion to the shearing stress.

$$\tau = k \cdot \gamma^n = k(-dV/dr)^n \quad [\text{Eq. 13}]$$

At the wall, the relationship is thus expressed as

$$\tau_w = k \Gamma_w^n \quad [\text{Eq. 14}]$$

Comparing this relation with Equation 10, it can be shown that over the range of shear rates for which the power law applies with constant values of k and n , n' and n are identical. Under these conditions, a plot of $\log \tau_w$ versus $\log \Gamma$ is linear; that is, n' is constant over this range.

The volumetric rate of flow is determined from this relationship by integrating the velocity distribution over the cross section of the tube.

$$Q = \pi (\Delta P_r / 2k \cdot L)^{1/n} [n / (3n + 1)] R^{(3n+1)/n} \quad [\text{Eq. 15}]$$

For $n=1$ (Newtonian fluid), this equation reduces to the Hagen-Poiseuille relation, given by Equation 16.

$$Q = \pi R^4 \cdot \Delta P / 8\mu \cdot L \quad [\text{Eq. 16}]$$

Three general correction terms must be added to obtain the frictional pressure drop from the applied pressure on the fluid (P_1) and the pressure of the liquid exiting from the capillary tube (P_2). These correction terms account for the head of fluid above the tube exit, kinetic energy effects due to the velocity head of the exiting liquid and entrance effects due to sudden contraction.

$$\Delta P_r = P_1 - P_2 + (L + L') d \cdot g / g_c - (d \cdot V^2 / g_c) (1/2\alpha + k_c/2) \quad [\text{Eq. 17}]$$

The values of α and k_e are not firmly established for non-Newtonian fluids. Combined corrections for kinetic energy and entrance effects may be taken to be the same as for a Newtonian material (17).

$$\Delta P_r = P_1 - P_2 + (L + L')d \cdot g / g_c - 1.12(d \cdot V^2 / g_c) \quad [\text{Eq. 18}]$$

Combined correction factors may also be obtained as a function of flow index as given by Bogue (18). Uncertainties regarding the correction term may be minimized by making the L/D ratio for the capillary tube as great as possible. L/D ratios on the order of 200 to 1000 have been used by some investigators.

Alternatively, Bagley's empirical method may be used to eliminate entrance effects from the obtained pressure drop. Entrance losses are expressed in terms of effective capillary length ($L + N_r$), such that measured pressure drop is equal to pressure drop over the effective capillary length for fully developed flow.

$$\tau_w = \Delta P \cdot R / 2(L + N_r \cdot R) \quad [\text{Eq. 19}]$$

$$L/R = -N_r + \Delta P / 2\tau_w \quad [\text{Eq. 20}]$$

For non-Newtonian fluids, τ is a unique function of apparent shear rate at the wall ($4Q/\pi R^3$). A series of measurements of pressure drop on capillary tubes of different L/D ratios at constant values of apparent shear rate is required. A plot of L/R versus ΔP will be linear and intercept the L/R ordinate at ΔP equal to zero. N_r is defined as the slope of this line. From a set of data at different values of $4Q/\pi R^3$, a plot of N_r versus $4Q/\pi R^3$ can be obtained. Shear stress at the wall can then be calculated using the effective capillary length to exclude the entrance effect.

Data Analysis

From experimental measurement of superincumbent pressure P_1 , exit pressure P_2 , and the mass flow rate W , the frictional pressure drop ΔP_r is calculated using the appropriate form of Equation 13.

$$\Delta P_r = P_1 - P_2 - 1.265[(d/g_c)(0.2V_e^2 + 0.39V_e^2 + V_r^2)] \quad [\text{Eq. 21}]$$

The experimental setup was standardized with standard oil N100 having a viscosity of 201.5 centipoise at 25°C. Pressure losses due to sudden contraction and expansion at the entrance and exit of the capillary tube and also kinetic energy at the exit are accounted for and subtracted from the pressure difference at the entrance and exit. Pressure losses due to end effects determined experimentally for the standard oil could be correlated to calculated pressure losses by a factor of 1.265. The HAAKE RV100 viscometer with MV-IIP sensor system used to determine CWF flow behavior at shear rates to 440

sec⁻¹ was also standardized with the same oil. Results show that the frictional pressure drop obtained from experimental measurement using Equation 17 agrees closely with the calculated frictional drop.

For each experimental run, shear stress at the wall is calculated using Equation 6, while the average shear rate is calculated using Equation 7. Linear regression analysis of the log of the wall shear stress with the log of the average shear rate yields a value of n' and, thus, n , assuming the power law relationship to be valid over the entire experimental run.

The power law parameters k and n can also be determined by regression analysis. Equation 13 can be written in the form of a straight-line formula, as indicated by the equation:

$$\log Q = \log[(1/2k)^{1/n} \pi n / (3n+1) R^{(3n+1)/n}] + (1/n) \log(\Delta P_r/L) \quad [\text{Eq. 22}]$$

Apparent viscosity at the experimental shear rate can then be calculated using the respective k and n values. Using a set of shear stress and shear rate data at different shear rates, the power law parameters can also be estimated by regression.

3.0 PROJECT DESCRIPTION

3.1 High-Pressure Atomization Spray Chamber

An existing pressure vessel was modified to include observation ports to perform atomization studies under typical turbine operating pressures and air flows. The main objective for constructing this spray chamber was to determine if differences in atomization quality accounted for the differences in carbon burnout experienced with the LRC fuels in UNDEERC's 1-MMBtu/hr gas turbine simulator. This apparatus was used to conduct atomization tests on the Energy International's coal-water fuel derived from their milled coal. The design of the spray chamber involves an existing 11.25-inch ID pressure vessel which was modified to provide optical access perpendicular to the direction of the atomized spray. The optical access consists of two diametrically opposite 3" sight ports for the use of high-speed photography. In addition, a 2" sight port opposite a 1" NPT port through which a sight pipe can be inserted was also added. The use of a sight pipe reduces the length of the spray through which the Malvern 2600's laser beam must pass and eliminates the potential for vignetting, which could occur if the beam were to pass through the complete spray cone. A honeycomb catalyst support is used as a flow straightener to provide a laminar flow of air around the atomizing nozzle. The height of the atomizer in relationship to the optical ports is adjustable from outside the pressure vessel, thus allowing the atomizer position to be easily changed. A Moyno progressive cavity pump is used to pump the coal-water slurry fuels into the spray chamber, while a Micro-motion mass flowmeter is used to measure the flow rate of the slurry fuels. A rotary control valve is used to control the flow of high-pressure air entering the spray chamber. The spray chamber is designed to operate at pressures up to 250 psig by passing the air through a rotary control valve used to back pressure the spray chamber. The air and fuel temperatures are measured with

standard stainless steel sheathed type K thermocouples. Spray chamber, total air, fuel, and atomizing air pressures are all monitored with pressure transducers. Process data and control are accomplished using an Analog Devices data acquisition and control system. This system consists of three RTI-820 cards inserted in a Sperry 286 AT personal computer. These boards are interfaced with six STB-TC type K thermocouple boards providing 75 thermocouple inputs and three 5802 backplanes which provide a 48-channel multi-I/O capability. The data acquisition system is run under a Genesis Control Series software package available from Iconics.

Figure 2 shows the internal details of the pressurized spray chamber. Figure 3 is a photograph of the pressurized spray chamber. The atomized slurry is collected in a funnel at the bottom of the spray chamber where it is drained off to a pressurized separation vessel. Pneumatic control valves are used to control the air flow rate and to back pressure the spray chamber. High-speed photography is accomplished using a Sage Instruments Superstrobe Model 550 high-speed strobe and a mylar diffuser to backlight the slurry droplets during atomization. A T-90 Canon 35-mm camera with a programmable back and a 100-mm macro lens is used to obtain the high-speed pictures. Best results were obtained using Kodacolor 100 film with 1/60th second exposure time and an F11 aperture. The use of high-speed photography allows droplet sizes larger than 564 microns (the top size for a Malvern particle-size analyzer with a 300-mm lens) to be detected and also provides information about the spray angle obtained under a given set of operating conditions.

3.2 High-Shear Viscometer

The bench-scale unit consists of an insulated autoclave vessel fitted with a threaded capillary tube attachment, an actuated 1/16" valve, and various flow, pressure, and temperature instrumentation, as depicted in Figure 4. Rheology tests consist of first charging the slurry to the autoclave vessel, adjusting the operating temperature, and back pressuring the system with nitrogen up to 1400 psi. The CWF is forced through the capillary tube, at which time the flow through the capillary is measured with a Micro-Motion mass flowmeter. Two pressure transducers are used to collect pressure data. The first one, fitted to the autoclave head, measures the superincumbent pressure on the fluid P1. The second transducer, fitted just before the flowmeter, measures the exit pressure P2. Data from pressure transducers, the temperature probe, and the flowmeter are acquired in real-time with a PC-based data acquisition program. The system enables recording of instantaneous pressure and flow data at a scan interval of one-third of a second. The high-shear data is correlated with low-shear data obtained using a HAAKE RV100 viscometer to extend the validity of the yield power law curve fit for the flow behavior of non-Newtonian CWFs.

3.3 Dry Powder Feed Facilities and Procedures

A test loop was constructed at the EERC for the purpose of feeding the milled coal and evaluating particle degradation over time at two temperature set points. The loop, shown in Figure 5, was constructed of 1-inch Schedule 40 type 304 stainless steel pipe. The test loop utilized flanged junctions at intervals of approximately 104 inches to allow measurement of particle size at different residence times. The test loop was attached to the EERC's combustion test facility (CTF, shown in Figure 6) to obtain the air required to

Figure 2. Schematic of pressurized spray chamber.

Figure 3. Photograph of pressurized spray chamber.

Figure 4. High-shear viscometer.

convey the mulled coal through the test loop. The CTF is designed for combustion testing of pulverized coals and coal-water fuels and uses a balanced draft to provide combustion air and maintain furnace operating pressure under a slight vacuum. Pulverized fuels are fired at approximately 600,000 Btu/hr, depending upon the fuel type and the operating conditions specified. The test loop was sized to accommodate feed rates in this range to ensure adequate fan capacity to convey the mulled coal at velocities typically found in full-scale pulverized-coal-fired boiler systems (between 35 and 50 ft/sec). Between 10% and 15% of the total air required for combustion of the mulled coal (approximately 13.6 acfm) will transport the fuel at a minimum of 35 ft/sec through the test loop. The test loop was connected to the CTF forced draft fan through the existing primary air line and plumbed to a particle collection cyclone and the induced draft fan at the CTF exit.

The CTF has an air preheater to provide heated combustion air to the system. The heaters are adjustable and were used in conjunction with an air heater bypass line to control air temperatures for the mulled coal test series. An Accurate screw feed system, shipped with the slurry mixer and the mulled coal, was used to convey the mull to a venturi feeder located at the top of the test loop. The feeder was mounted on a scale above the test loop to verify feed rates and can be seen in Figure 7. The mull was metered into the throat of the venturi feed system by the Accurate feeder where it was picked up by the preheated air and conveyed through the test loop past the Malvern particle sizer to the cyclone separator where it was removed from the gas stream prior to entering the induced-draft fan.

Figure 5. Mullied coal test loop.

Figure 6. Schematic of combustion test facility.

Figure 7. Mulled coal feed system.

4.0 RESULTS

4.1 CWF Atomization and Rheology

4.1.1 CWF Atomization

Atomization testing was performed on the slurried mulled coal at three different additive concentrations under the subcontract between Energy International Corporation and UNDEERC. Initial atomization testing using the Parker Hannifan M6 nozzle gave confusing results until it was discovered that, at low atomizing air-to-fuel ratios, the spray would have a flat spray angle. This particular atomizer had the same operating problem even while atomizing water. Once it was determined that this was an operating characteristic of this particular nozzle, it was decided to switch to the Parker Hannifan M2, which had been designed for operation at atmospheric pressure. This resulted in lower atomizer pressure ratios than originally desired, but a better developed spray cone was achieved. Tables 2 through 5 summarize the data collected for the atomization tests using the three CWF formulations requested by Energy International. Table 6 shows the initial CWF properties of the three coal-water fuel formulations atomized for this project. Results from the atomization testing using the M2 nozzle are shown in Figure 8. This figure plots the SMD corrected for high obscuration using the method of Gölnder (11) against the atomizer pressure ratio for coal-water fuels (CWF) made from Energy International's "mulled" coal at three different additive loadings. These CWFs were atomized both at room temperature and were preheated to approximately 130°F. Also shown are the results from water atomized under similar operating conditions. As can be seen from the figure, all three CWFs atomized very well, especially at higher atomizer pressure ratios (i.e., higher atomizing air-to-fuel ratios). SMDs were approximately 50 to 70 μm for all three CWF mixtures versus approximately 40 to 50 μm for water. This figure indicates that preheating the CWF/atomizing air improved the atomization of the 12.5% and 25% additive concentration CWF, especially at lower

TABLE 2

Energy International Mulled Coal-Water Fuel with 12.5% Additive
Solution Using Parker Hannifan M2 Nozzle

Test No.	Atom. Air Press. psig	Fuel Deliv. Press. psig	Spray Cham. Air Press. psig	Test Fuel Flow Rate lb/hr	Atom. Test Fuel Temp. °F	Atom. Air Temp. °F	Total Air Flow Rate scfm	Atom. Air Flow Rate lb/hr	Atom. Air-to-Fuel Ratio	Atom. Press. Ratio	Corr. SMD μm	Corr. VMD μm
1	151.9	107.4	101.7	142.5	86	72	301	249	1.74	1.43	34.0	119.3
2	151.5	104.9	100.3	125.6	86	72	296	249	1.99	1.46	46.7	138.9
3	128.5	108.3	99.8	125.2	87	66	299	189	1.51	1.25	96.2	141.9
4	117.3	109.6	99.8	125.2	85	64	299	151	1.21	1.15	122.3	183.9
5	111.6	113.6	100.2	125.0	84	67	299	125	1.00	1.10	201.3	275.4
6	150.8	99.1	100.4	126.3	118	130	300	244	1.93	1.44	56.3	95.1
7	127.6	99.9	99.9	126.5	122	151	298	184	1.45	1.24	70.8	113.0
8	119.0	100.3	100.8	126.4	133	166	296	155	1.22	1.16	78.2	122.9
9	108.9	99.6	99.4	126.4	128	189	301	122	0.97	1.08	89.6	124.5

TABLE 3

Energy International Mulled Coal-Water Fuel with 25.0% Additive
Solution Using Parker Hannifan M2 Nozzle

Test No.	Atom. Air Press. psig	Fuel Deliv. Press. psig	Spray Chm. Air Press. psig	Test Fuel Flow Rate lb/hr	Atom. Test Fuel Temp. °F	Atom. Air Temp. °F	Total Air Flow Rate scfm	Atom. Air Flow Rate lb/hr	Atom. Air-to-Fuel Ratio	Atom. Press. Ratio	Corr. SMD μ m	Corr. VMD μ m
1	146.4	108.2	99.9	125.9	81	69	301	242	1.92	1.41	61.2	101.5
2	126.9	109.7	100.8	126.0	81	64	299	187	1.49	1.23	75.6	117.3
3	116.8	109.0	99.8	125.8	81	61	301	156	1.24	1.15	143.4	243.6
4	110.7	110.4	100.3	125.7	81	65	300	126	1.00	1.09	235.7	311.6
5	150.4	99.3	99.7	126.0	138	169	300	238	1.88	1.44	60.9	102.9
6	150.7	98.6	101.3	126.5	143	165	300	239	1.89	1.43	63.6	105.3
7	129.8	100.8	100.2	127.0	132	176	301	189	1.49	1.26	85.5	174.3
8	117.9	101.7	100.4	126.8	132	192	300	153	1.20	1.15	95.5	198.3
9	111.5	102.3	100.5	127.5	143	212	300	120	0.94	1.10	171.4	256.6

TABLE 4

Energy International Mulled Coal-Water Fuel with 8.3% Additive
Solution Using Parker Hannifan M2 Nozzle

Test No.	Atom. Air Press. psig	Fuel Deliv. Press. psig	Spray Chm. Air Press. psig	Test Fuel Flow Rate lb/hr	Atom. Test Fuel Temp. °F	Atom. Air Temp. °F	Total Air Flow Rate scfm	Atom. Air Flow Rate lb/hr	Atom. Air-to-Fuel Ratio	Atom. Press. Ratio	Corr. SMD μ m	Corr. VMD μ m
1	128.2	103.5	99.7	127.8	146	173	300	181	1.42	1.25	108.3	250.4
2	119.6	104.1	99.9	127.9	144	183	300	154	1.20	1.17	137.9	285.4
3	110.2	104.5	99.8	127.6	145	193	300	123	0.96	1.09	228.7	330.2
4	103.3	104.2	99.8	127.6	147	204	301	93	0.73	1.04	443.5	422.2
5	144.1	100.3	100.3	116.9	76	64	299	224	1.92	1.38	47.0	78.7
6	140.2	104.6	99.8	128.6	79	67	299	223	1.73	1.35	69.0	115.1
7	123.9	109.1	98.3	128.3	76	66	301	183	1.42	1.23	96.6	185.7
8	118.4	112.0	99.5	128.6	76	64	301	160	1.25	1.17	99.8	176.4
9	109.4	114.0	100.2	128.9	76	65	300	122	0.95	1.08	91.5	112.7
10	105.4	114.6	99.9	129.5	75	64	299	98	0.76	1.05	149.6	216.5
11	146.7	97.8	99.5	128.6	134	181	301	227	1.76	1.41	72.9	96.1
12	148.9	100.2	99.8	128.3	123	182	300	232	1.81	1.43	77.7	100.7

TABLE 5

Water Atomization Tests Using Parker Hannifan M2 Nozzle

Test No.	Atom. Air Press. psig	Fuel Deliv. Press. psig	Spray Cham. Air Press. psig	Test Fuel Flow Rate lb/hr	Atom. Test Fuel Temp. °F	Atom. Air Temp. °F	Total Air Flow Rate scfm	Atom. Air Flow Rate lb/hr	Atom. Air-to-Fuel Ratio	Atom. Press. Ratio	Corr. SMD μm	Corr. VMD μm
1	193.2	148.6	149.0	166.5	78	64	304	253	1.52	1.27	56.9	88.3
2	191.8	149.4	150.0	124.6	78	64	299	245	1.96	1.25	53.7	82.3
3	181.6	151.1	150.7	168.1	78	61	301	214	1.27	1.19	64.3	96.4
4	174.5	149.7	149.6	124.7	78	62	297	191	1.53	1.15	63.8	96.2
5	170.0	151.4	150.4	166.7	77	62	299	167	1.00	1.12	71.6	106.5
6	167.7	151.6	150.8	124.8	79	64	300	156	1.25	1.10	80.3	116.4
7	159.6	150.9	149.6	124.8	79	65	300	127	1.02	1.06	89.1	128.6
8	159.1	151.3	150.1	167.7	78	65	299	123	0.73	1.05	92.7	133.0
9	154.1	151.2	150.2	125.0	78	68	299	96	0.77	1.02	211.5	303.3
10	205.6	151.0	151.0	167.2	126	165	298	261	1.56	1.33	42.4	71.3
11	201.3	148.9	149.3	124.9	128	148	301	255	2.04	1.32	39.6	68.0
12	185.6	151.2	150.6	167.2	122	178	298	209	1.25	1.21	83.0	116.6
13	178.3	149.7	149.2	126.3	128	172	302	190	1.50	1.18	84.5	121.3
14	173.2	151.4	150.5	166.8	114	171	298	169	1.02	1.14	89.3	126.3
15	169.4	150.8	150.1	126.5	126	174	301	157	1.24	1.12	93.2	132.0
16	160.1	151.0	149.8	167.8	114	187	300	124	0.74	1.06	111.2	158.3
17	160.2	150.5	149.8	125.8	126	190	301	124	0.99	1.06	111.8	157.9
18	153.2	150.8	149.6	125.6	128	202	300	93	0.74	1.02	143.9	264.9
19	199.3	150.4	150.8	125.8	127	148	300	252	2.00	1.29	57.4	86.3
20	196.3	149.1	149.5	167.7	111	137	302	249	1.48	1.29	62.7	91.1
21	150.4	98.0	101.6	126.8	83	60	299	243	1.92	1.42	46.8	71.0
22	157.3	95.9	100.0	125.6	142	170	300	244	1.94	1.50	43.7	67.1

TABLE 6

Moisture Levels and Particle-Size Distribution of Energy International's CWF Obtained from Milled Coal

	EI Milled Feed Coal	EI CWF w/ 12.5% Additive	EI CWF w/ 25.0% Additive	EI CWF w/ 8.33% Additive
Solids Loading of CWF	59.6	57.4	57.9	56.4
Particle Size, mean μm^*	23.3	11.2	10.8	11.3
Top size, (100%<), μm	162.0	57.7	42.9	89.9

* Obtained using Malvern and PS14 and PS23 recirculating flow-through cell in water.

Figure 8. Plot of corrected SMD for three CWF formulations versus atomizer pressure ratio.

atomizer pressure ratios (i.e., lower atomizing air-to-fuel ratios). This is expected atomization behavior, because preheating the CWF should decrease the lower viscosity of fuel. However, preheating the 8.3% additive CWF appears to have significantly decreased atomization performance. The reasons for this decrease are not immediately obvious, but it appears that the solids loading of the CWFs was higher during the latter atomization tests, possibly due to the mull air-drying slightly during handling and storage.

Atomization tests at Allison Gas Turbine Division using an external mix atomizer similar to that used in these tests and an Otis Industries-produced micronized CWF indicated that smaller SMDs were achieved, but at much higher atomizer pressure ratios (7,19). Other tests comparing the Allison CWF nozzle to the Parker Hannifan indicated that the Allison nozzle appeared to perform better than the Parker Hannifan nozzle, which could account for some of the better performance. In general, due to the difference in atomizers; CWF rheology; and other parameters, such as the condition and position of the Malvern measurement in the spray downstream from the atomizer; fuel and air flow rates; and multiple scattering effects, it is very difficult to make absolute comparisons between results from different groups (10).

A statistical analysis of the atomization data was performed using Statistical Analysis System (SAS) software for personal computers. This statistical analysis was first run on just the CWF data, with the three additive levels being different fuel types, but no fuel-type effect could be statistically verified at the 5% confidence level. This means that, statistically, all three fuels atomized the same. Only atomizer pressure ratio and fuel temperature/atomizer pressure ratio interactions were statistically significant. This interaction is apparent in Figure 8, because at high

atomizer pressure ratios, fuel temperature does not have a significant effect, but at low atomizer pressure ratios, fuel temperature does appear to affect the measured SMD of the spray. A second statistical analysis was run comparing the water atomization data and the CWF atomization data. Since the previous analysis showed that there was no statistical difference between different CWF additive levels, the fuel-type difference was CWF versus water only. From this analysis, the statistically significant parameters were atomizer pressure ratio and a fuel type/fuel temperature interaction. Again, the atomizer pressure ratio effect is obvious from Figure 8; however, the fuel-type interaction is less obvious. Closer examination of the data indicates that, for water, there is very little effect from preheating the fuel, while preheating can have a significant effect on atomization performance for the CWF.

High-speed still photographs were taken of the three different CWF formulations under room temperature operating conditions. These photographs were taken at varying atomizing air-to-fuel ratios ranging from 2.0 to 0.75. In these photographs, the scale is approximately 1000 μm equals 0.04 inches. The photographic series shown in Figures 9 through 13 shows the increasing droplet size with decreasing atomizing air-to-fuel ratio for the 12.5% additive CWF formulation. Figures 14 through 18 show the spray droplets for the 25% additive formulation and Figures 19 through 23 display the droplet sizes for the 8.3% additive CWF formulation. These photographic series again show that droplet size increases with decreasing atomizing air-to-fuel ratio (i.e., decreasing atomizer pressure ratio), which is consistent with the Malvern data reported earlier. At the low atomizing air-to-fuel ratios, it can be seen that some droplets greater than 1000 microns in diameter are present in the spray.

4.1.2 CWF Rheology

Different rotors were used with the HAAKE viscometer to compare apparent viscosities at various shear rates and to extend the atmospheric viscosity curves to approximately 1000 sec^{-1} . The two rotors that were used with the HAAKE viscometer were the MV-IIP rotor which covers a shear rate range up to 440 sec^{-1} and the MV-I rotor that ranges up to 1100 sec^{-1} . Profiles indicated that the various additive levels produced slurries with viscosities that increased from 100 to 250 cp with decreasing additive levels. The results indicated a distinct transition point in flow behavior at shear rates of 400 to 800 sec^{-1} for the different slurries. Additive concentrations seemed to be a critical parameter in the definition of the transition point. The test matrix was then expanded to include duplicate additive slurries with similar solids concentrations. The results from duplicate tests yielded similar transitional flow behavior occurring at 400 to 800 sec^{-1} . Data up to 400 sec^{-1} indicates that the slurries were dilatant or shear thickening, with flow factors ranging from 1.1 to 1.2. At the transition point, the rheological behavior switched to more pseudoplastic or shear-thinning behavior.

The slurries were then analyzed using the EERC extrusion viscometer. The results from the high-shear tests supported the results of the atmospheric viscometer: that above 1000 sec^{-1} each of the fuels showed shear-thinning flow behavior. All of the initial high-shear tests were conducted using a 1/16" capillary tube with a L/D ratio equal to 100. The results of rheological tests on the CWF with different additive concentrations at both low- and

Figure 9. Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 2.0.

Figure 10. Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 1.5.

Figure 11. Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 1.25.

Figure 12. Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 1.0.

Figure 13. Photograph of spray droplets from CWF with 12.5% additive concentration at an atomizing air-to-fuel ratio of 0.75.

Figure 14. Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 2.0.

Figure 15. Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 1.5.

Figure 16. Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 1.25.

Figure 17. Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 1.0.

Figure 18. Photograph of spray droplets from CWF with 25% additive concentration at an atomizing air-to-fuel ratio of 0.75.

Figure 19. Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 2.0.

Figure 20. Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 1.5.

Figure 21. Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 1.25.

Figure 22. Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 1.0.

Figure 23. Photograph of spray droplets from CWF with 8.33% additive concentration at an atomizing air-to-fuel ratio of 0.75.

high-shear rates are summarized by plotting apparent viscosity versus wall shear rate, as indicated in Figures 24 through 26. The different curves indicate the viscosity determination using the different rotors and the high-shear assembly. Notice the difference in the location and extent of various flow behavior transition points.

Two similar slurry samples were used for the different tests: one for atmospheric and the other for extrusion rheology testing. Atmospheric testing was first performed on the MV-IIP, and then the same sample was tested with the MV-I rotor system. The reported differences in viscosity for the respective slurries when comparing MV-IIP data to MV-I data at a given shear rate is due to the sensitivity of the coal slurry to the shearing forces encountered during MV-IIP testing. Duplicate testing using the same sample for the MV-IIP rotor also indicated a slight decrease in viscosity for the latter sample.

4.2 Milled Coal Dry Feed Test Results

Dry feed tests using the Energy International milled coal were completed for the test program. Initial shakedown dry feed tests using pulverized coal in a recently built venturi-type coal feeder showed that dusting of the lenses in the sight port was going to be a problem; however, when the lenses were removed, and air was allowed to pass through the lens openings, subsequent tests were successful. This coal feeder provides a significantly better vacuum to pull the coal particles into the preheated primary air stream for the UNDEERC 600,000-Btu/hr ash-fouling combustion furnace. However, this venturi coal feeder has smaller passages than the original coal feeder, and

Figure 24. Plot of apparent viscosity for CWF with 12.5% additive versus shear rate.

Figure 25. Plot of apparent viscosity for CWF with 25.0% additive versus shear rate.

Figure 26. Plot of apparent viscosity for CWF with 8.33% additive versus shear rate.

significant plugging problems were experienced with the mulled coal. Insertion of a 1/2" square mesh into the feeder tunnel appeared to break up the mull dropping from the Accurate screw-feeder, but still did not prevent the feeder from plugging. An older coal feeder was installed in the system, but did not provide sufficient vacuum with the sight port lenses removed to pull the mull into the piping system. In order to obtain a vacuum at the feeder, plexiglass piping was made which fit snugly around the Malvern 2600 lenses and the sight port. The plexiglass piping sealed the sight port well enough to provide a vacuum at the coal feeder so that the mulled coal would feed. This piping also allowed the Malvern lenses to be recessed back from the sight port openings to prevent the Malvern lenses from being coated with coal particles.

Table 7 summarizes the test results from the Energy International mulled coal dry powder feed tests. Results from dry feed testing are shown in Figures 27 and 28. Figure 27 plots the corrected particle size (both SMD and VMD are shown) as measured at position 3 for both an air-dried and an as-received mull at two different temperature ranges. The air-dried mull contained approximately 30.0 wt% moisture, while the as-received mull was approximately 40.3 wt% moisture. One temperature range was selected to be below the boiling point of water, while the other was selected to be above the boiling point of water. From Figure 27, it appears that higher temperatures help reduce the particle size of the as-received mull fed to the system. Temperature did not appear to significantly affect the particle size of the air-dried mull, presumably because there is less loosely bound moisture to be evaporated from the mull. Figure 28 plots the particle size for both the as-received mull and air-dried mull as a function of the particle residence time.

TABLE 7

Energy International Mulled Coal Dry Powder Feed Test Results

Fuel Type	Coal Feed Rate lb/hr	Prim. Air Flow Rate scfm	Feed. Inlet Air Temp °F	Sight Port Air Temp °F	Sight Port Diff. Temp °F	Dist. to Sight Port in.	Avg. Gas Vel. ft/s	Part. Resid. Time sec.	Corr. SMD µm	Corr. VMD µm
Air-Dried Mull	36.5	13.5	215	100	ND	316	49.1	0.54	55.0	109.1
Air-Dried Mull	19.2	14.4	170	118	21	316	51.2	0.51	29.4	55.6
Air-Dried Mull	16.4	14.3	180	109	24	316	50.8	0.52	43.9	74.1
Air-Dried Mull	21.0	14.3	336	168	19	316	59.7	0.44	24.0	30.6
Air-Dried Mull	19.2	14.2	346	172	13	316	60.1	0.44	30.0	38.8
Air-Dried Mull	22.2	15.1	340	238	76	108	66.3	0.14	17.6	30.1
Air-Dried Mull	17.5	15.0	365	122	2	732	62.1	0.98	24.3	29.8
Wet Mull	22.5	14.6	191	114	17	316	52.4	0.50	67.4	137.8
Wet Mull	22.5	14.5	195	117	21	316	52.6	0.50	74.2	144.6
Wet Mull	22.7	14.7	361	172	42	316	62.8	0.42	36.7	65.0
Wet Mull	24	14.7	371	182	47	316	63.4	0.42	38.0	63.0
Wet Mull	27.9	14.7	364	229	100	108	65.1	0.14	50.6	138.1
Wet Mull	36	14.8	377	125	6	732	61.9	0.99	34.9	54.7

ND Not determined.

Figure 27. Plot of air temperature versus corrected particle size for air-dried and as-received mulled coal.

Figure 28. Plot of particle residence time versus corrected particle size for air-dried and as-received mull coal.

These tests were all performed at air temperatures of approximately 350°F, and residence times were varied by changing the position of the sight port in the system piping. For the as-received mull, the residence time seemed to have a significant effect on the particle size up to a particle residence time of approximately 0.4 seconds, but did not change significantly after that time. The particle size of the air-dried mull was not affected by particle residence time, again presumably because there is much less loosely bound moisture which can evaporate during those short residence times. At the end of the dry powdered tests, some tests were tried in which the raw mull was scattered through Malvern 2600's laser beam in an effort to characterize the mull's starting particle size. Results indicate that the mull's initial particle size was very large, with approximately half of the normal distribution being larger than the 564-μm top size of the Malvern's 300-mm lens. This is consistent with the 28-mesh size reported by EI personnel for mull coal agglomerates and indicates that there was a substantial particle-size reduction as the mull coal was fed into the preheated air.

A statistical analysis of the operating parameters indicates that, at the 5% level of significance, there is a fuel-type effect (i.e., wet mull versus air-dried mull), an air temperature effect, and a second-order effect between fuel type and particle residence time. The fuel type and air temperature effects can be seen in Figures 27 and 28. In each case, the air-dried mull is reduced to a smaller size than the wet mull, under the same conditions. The fuel-type/residence time interaction can be seen in Figure 28. From this figure, it can be seen that residence time has no apparent effect on the air-dried fuel, but has a significant effect on the as-received fuel. It should

be remembered that this statistical analysis is only based on thirteen tests that were not performed according to a statistically designed test matrix. The residence time effects should also have been examined at the low air temperature setting to give a uniform test matrix.

5.0 CONCLUSIONS

The atomization performance of the CWFs made with the three different additive formulations was very good, with no significant difference between the three CWFs. At high atomizing air-to-fuel ratios, droplet SMDs were approximately 20 to 30 μm larger than similar atomization tests using water, and this difference became greater at lower atomizing air-to-fuel ratios. The CWF rheology, as determined by both low- and high-shear viscometers, indicated that the CWF's peak apparent viscosity did decrease with increasing additive loading. All three formulations showed slightly dilatant behavior at low-shear rates up to approximately 400 to 800 sec^{-1} , but at high-shear rates all three fuels exhibited pseudoplastic behavior with very similar apparent viscosities. In conclusion, all three formulations performed very well as potential CWFs for boiler or heat engine applications.

Dry feed testing showed that increasing air temperatures and particle residence times decreased the measured particle size of the mulled coal. Reasonable particle sizes can be obtained from the mulled coal either by reducing the level of moisture in the mull prior to feeding or by feeding the mull into an air stream preheated to approximately 350°F for residence times of approximately 0.4 seconds.

6.0 NOMENCLATURE FOR HIGH-SHEAR RHEOLOGY

τ	shear stress, lb_f/ft^2
τ_w	shear stress at the wall, lb_f/ft^2
ΔP	pressure difference between two capillary ends, lb_f/ft^2
ΔP_f	frictional pressure loss between capillary ends, lb_f/ft^2
$\dot{\gamma}$	shear rate, sec^{-1}
$\dot{\gamma}_w$	shear rate at the wall, sec^{-1}
μ	coefficient of viscosity, $\text{lb}_f\text{-sec}/\text{ft}^2$
μ_a	apparent viscosity, $\text{lb}_f\text{-sec}/\text{ft}^2$
α	kinetic energy correction factor
D	diameter of the capillary tube, ft
R	radius of the capillary tube, ft
P1	pressure above the liquid level, lb_f/ft^2
P2	pressure at the exit of the capillary tube, lb_f/ft^2
r	distance from the center of the tube, ft
L	length of capillary tube, ft
L'	height of liquid above the capillary tube, ft
V	velocity in the axial direction, ft/sec
Q	volumetric flow rate, ft^3/sec
d	density, lb_m/ft^3
k	flow index
k_c	coefficient of sudden contraction
n	power law flow coefficient
n'	Rabinowitsch-Mooney coefficient

- N, length equivalent for frictional pressure loss equal to entrance losses, ft
 g, acceleration due to gravity, ft/sec²
 g_c, conversion factor, 32.174 lb_m-ft/lb_m-sec²

7.0 REFERENCES

1. Lefebvre, A.H. *Atomization and Sprays*; Hemisphere Publishing Corp.: New York, 1989, 421 p.
2. Winters, P.J.; Bailey, R.T.; Olen, K.R. "The Effect of Fuel Formulation on the Atomization Characteristics of Coal-Water Mixtures," In *Proceedings of the Seventh International Symposium on Coal Slurry Fuels Preparation and Utilization*; New Orleans, LA, May 21-24, 1985, pp 430-439.
3. Cook, D.A.; Kearns, J.D.; Smith, D.A.; Rini, M.J.; LaFlesh, R.C. "C-E Canada CWM Nozzle Development and Firing Experience," In *Proceedings of the Sixth International Symposium on Coal Slurry Combustion and Technology*; Orlando, FL, June 25-27, 1984, pp 993-1011.
4. Allen, J.W.; Rennie, A.G.; Welbourne, M.C. "Atomization of Coal-Water Mixtures," In *Proceedings of the Seventh International Symposium on Coal Slurry Fuels Preparation and Utilization*; New Orleans, LA, May 21-24, 1985, pp 392-401.
5. Lefebvre, A.H.; Sojka, P.E.; Smith, C.F. "Investigation of Spray Characteristics of Coal-Water Slurry Fuels," In *Proceedings of the First Annual Heat Engine Contractors' Meeting*; Morgantown, WV, November 1984, pp 206-213.
6. Smith, C.F.; Sojka, P.E.; Thames J.M. "The Influence of Fluid Physical Properties on Coal-Water Slurry Atomization," *Journal of Engineering for Gas Turbines and Power* 1990, 112, 15-20.
7. Smith, C.F.; Williams, M.C. "Methods to Improve Atomization Performance in a CWS-Fired Gas Turbine Combustor," In *Proceedings of the Sixth Annual International Pittsburgh Coal Conference*; Sept. 1989, pp 1068-1077.
8. Meyer, P.L.; Chigier, N. "Photographic and Malvern Analysis of Coal-Water Slurry Atomization," In *Proceedings of the Seventh International Symposium on Coal Slurry Fuel Preparation and Utilization*; New Orleans, LA, May 1985, pp 402-429.
9. Malvern Instruments Particle Sizer 2600 Series User Manual, Version 6.0, October 15, 1987.
10. Meyer, P.L.; Chigier, N. "Dropsize Measurements Using a Malvern 2200 Particle Sizer," *Atomization and Spray Technology* 1986, 2, 261-298.
11. Gölnder, Ö.L. "Multiple Scattering Effects in Dense Spray Sizing by Laser Diffraction," *Aerosol Science and Technology* 1990, 12, 570-577.

12. Dodge, L.G. "Change of Calibration of Diffraction-Based Particle Sizers in Dense Sprays," *Optical Eng.* 1984, 23 (5), 626-630.
13. Cao, J.; Brown, D.J.; Rennie, A.G. "Laser-Diffraction Particle Sizing in Dense Suspensions and Sprays, with Correction for Multiple Scattering," *J. of the Institute of Energy* 1991, 64, 26-30.
14. Yu, T.U.; et al. "Atomization Quality and High-Shear Rate Viscosity of Coal-Water Fuels," Massachusetts Institute of Technology, 12th International Conference on Slurry Technology, New Orleans, LA, March 1987.
15. Potas, T.A.; Anderson, C.M. "Rheology of Low-Ash, Hot-Water-Dried Coal-Water Fuels," 13th International Conference on Coal and Slurry Technology, Denver, CO, April 1988.
16. Mannheimer, R.J. "Shear and Extensional Flow Properties of a Micronized Coal-Water Fuel," Southwest Research Institute, 14th International Conference on Coal and Slurry Technology, Clearwater, FL, April 1989.
17. Skelland, A.H.P. *Non-Newtonian Flow and Heat Transfer*; Wiley: New York, 1967, p 34.
18. Van Wazer, J.R.; Lyons, J.W.; Kim, K.Y.; Colwell, R.E. *Viscosity and Flow Measurement-A Laboratory Handbook*; Interscience, 1973.
19. Rothrock, J.W.; Bourke, R.C.; Caraker, K.W.; Williams, M.C. "Low-Cost Fuels for Coal-Fired Turbines," *In Proceedings of the Seventh Annual Coal-Fueled Heat Engines and Gas Stream Cleanup Systems Contractors' Review Meeting*; March 1990, pp 241-250.

END

**DATE
FILMED**

9 / 14 / 92