DOE/ER/13189-5
JUN 9 1992

Institute of Paper Science and Technology

DOE/ER/13189--5

DOE-ER-13189-5

DE92 015288

RAMAN MICROPROBE INVESTIGATION OF MOLECULAR STRUCTURE AND
ORGANIZATION IN THE NATIVE STATE OF WOODY TISSUE

Progress Report

for Period April 1, 1987-July 31, 1989

R. H. Atalla *

The Institute of Paper Science and Technology
575 14th Street, NW
Atlanta, GA 30318

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

RAMAN MICROPROBE INVESTIGATION OF MOLECULAR STRUCTURE AND
ORGANIZATION IN THE NATIVE STATE OF WOODY TISSUE

Progress Report

for Period April 1, 1987-July 31, 1989

R. H. Atalla *

The Institute of Paper Science and Technology
575 14th Street, NW
Atlanta, GA 30318

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately owned rights.

August, 1989

Prepared for

The U.S. DEPARTMENT OF ENERGY

MASTER

* Present Address: USDA Forest Products Laboratory
One Gifford Pinchot Drive
Madison, WI 53705-2398

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

RAMAN MICROPROBE INVESTIGATION OF MOLECULAR STRUCTURE AND
ORGANIZATION IN THE NATIVE STATE OF WOODY TISSUE

Progress Report
for Period April 1, 1987-July 31, 1989

R. H. Atalla*

The Institute of Paper Science and Technology
575 14th Street, NW
Atlanta, GA 30318

August, 1989

Prepared for

THE U.S. DEPARTMENT OF ENERGY

* Present address: USDA, Forest Products Laboratory
One Gifford Pinchot Drive
Madison, Wisconsin 53705-2398

MOLECULAR ORGANIZATION IN THE NATIVE STATE OF WOODY TISSUE:
STUDIES OF TERTIARY STRUCTURE USING THE RAMAN MICROPROBE
SOLID STATE ^{13}C NMR AND BIOMIMETIC TERTIARY AGGREGATES

Progress Report
for the period April 1, 1987 to July 31, 1989

Grant No. DE-FG02-84ER13189

R. H. Atalla

USDA Forest Products Laboratory
Madison, Wisconsin 53705-2398

THIS REPORT IS BASED ON WORK CARRIED OUT AT
THE INSTITUTE OF PAPER CHEMISTRY

IT IS SUBMITTED FOR REVIEW PURPOSES ONLY

A formal report will be issued after
administrative review at
The Institute of Paper Chemistry

SUMMARY

Although the primary emphasis of our program has remained with the application of Raman spectroscopy to the study of native tissue, the scope of the work has been expanded to include a number of complementary approaches. These have included Solid State ^{13}C NMR, autoradiography of radiolabelled woody tissue sections, and the generation of biomimetic tertiary aggregates which simulate states of aggregation characteristic of cell walls. During this project period we have found it useful to clarify the levels of structure we are addressing by emphasizing the distinctions between primary secondary and tertiary structures, and noting that, except when dealing with issues involving chemical transformations, we are focusing on the interplay between secondary and tertiary structures. The tertiary structures represent the first level of intermolecular aggregation of the constituents of biological tissue. We note that in biological systems this level of aggregation is not likely to be adequately described in terms of the conceptual framework usually applicable to mixtures of constituents; the latter framework usually relies on assumptions of randomness and homogeneity which are not applicable to a biological system.

Our Raman spectroscopic studies have resulted in progress in the areas of interpretation of the spectral features, and confirmation of the variability of the patterns of orientation of lignin reported earlier. We have assembled and made operational our new microprobe and spectrometer systems acquired under the DOE-URIP program. We have also demonstrated that, operating with gated detection and pulsed laser excitation, we can discriminate against the laser-excited fluorescence characteristic of most woody tissue. Our studies of celluloses, which combine Raman spectroscopy and ^{13}C NMR have shown that all native celluloses are composites of two forms which have the same secondary structure but different tertiary structures. Furthermore, there appears to be a correlation between the proportion of the two forms in a

The PI chose relocation to the USDA Foerst Products Laboratory (FPL) in Madison, together with an affiliation with the faculty of the Chemical Engineering Department of the University of Wisconsin at Madison, (UW-M). An agreement to transfer the current grant and the equipment of the Raman spectroscopy laboratory has been concluded and is currently being implemented. The senior staff associate, graduate students, and postdoctoral fellow affiliated with the programs in our laboratory have also relocated to FPL.

Though this report is being issued as an IPC document, the remainder of the work under the current grant period will be completed at FPL. We expect the Raman systems to be disassembled for transfer in late August. The Raman microprobe and the high resolution Raman spectrometer should be operational again by late September or early October. The ultrafast laser system should be operational soon thereafter.

OVERVIEW OF PROGRESS

Categories of Structure

In the "Discussion" section of our paper in Planta (Attachment 1), reporting our findings that lignin within the cell walls appears to be highly organized, we raised the question whether the categories of order common in traditional methodologies of chemistry and polymer science will be adequate for description of states of aggregation or molecular organization in the native state. In particular, it was noted that the categories of crystalline and amorphous, which are the usual categories of tertiary structure, were very limited because they implied a range of variation from the translational symmetries of crystallography, at one end of the range, to the homogeneous disorder associated

with amorphous structures at the other end. The states of aggregation in the cell wall are not within this range at all, for though they appear to be highly ordered, the patterns cannot be described in terms of lattice geometries. Nor can they be regarded as homogeneous or disordered even though traditional diffractometric methods do not detect the coherence in their order. In our search for a conceptual framework to organize our analyses of our observations we have found it useful to introduce the notion of a Biomimetic Tertiary Aggregate, that being the state in which two or more constituents are aggregated in a manner that simulates the states of organization in the cell walls.

To clarify the terminology in use in our work, we describe the levels of structure that we consider. The primary structure is the pattern of covalent bonds in a particular molecule, which will concern us only in the case of chemical transformations. The secondary structure is the conformation of an individual molecule, usually defined by the values of the internal coordinates. In a biological macromolecule the internal coordinates of most interest are those defining the linkages between its component units. The tertiary structure then is the first level of intermolecular aggregation to form the substance of biological tissue. The pattern of aggregation is defined by the intermolecular interactions between adjacent molecules. And because the deposition of constituents in biological tissue is not random, the conceptual frameworks available from the classical theories of mixed systems are not valid. Thus, our definition of Biomimetic Tertiary Aggregates as a category of organization. It will no doubt need further refinement and redefinition.

Though the need for a new conceptual framework was recognized as we contemplated the results of our first Raman microprobe studies of organization of lignin, we have adopted this perspective in all of our studies of native tissues, whether they be celluloses which are nearly pure in their native state, or celluloses with other

cell wall polysaccharides, as in tissues from algae and other primitive plant forms, or lignocellulosic tissues with the full complement of the constituents of a wood. Our presentation of the results of the different programs of investigation is predicated on this perspective.

Raman Spectroscopic Studies

Our effort in Raman spectroscopy has continued to combine methods development with the exploration of tertiary structure that is our ultimate goal. Our first comprehensive report on our studies of orientation in lignin was published in Planta (Attachment 1), with a preliminary report in Science (1) and a complementary report in the Journal of Raman spectroscopy (2). A broader discussion of the methodology is presented in the preliminary preprint of a chapter entitled "Raman Spectroscopy of Lignin" which we have been asked to contribute to the book on Methods in Lignin Chemistry, C. Dence and S. Lin, Eds, (Attachment 2).

In summary, the studies of the Raman spectra continue to combine considerations of primary structures, which are necessary for identifying the spectral features, with further explorations of questions of tertiary structure and the methodologies they require. As noted in greater detail in Att. 2, we have recognized that the intensity of the 1595 cm^{-1} ring stretching band of aromatic centers is enhanced by conjugation and pre-resonance Raman phenomena. We are actively pursuing a program to identify the primary contributors to this effect.

An even more interesting observation is the transience of some of the intensity enhancement effects when the specimens are exposed to the 5145 Å excitation while immersed in water. These transient effects were not observable until the new multichannel detection systems were installed, because most of the changes occur during the first few minutes of exposure, and thus escaped detection with

the scanning spectrometer system. We have in progress a program to identify the species involved in this effect and the mechanisms involved.

Because of these effects we deemed it necessary to carry out additional experiments to ascertain that our earlier conclusions about lignin orientation were not based on artifacts associated with transients. We found additional evidence of orientation in spectra excited with the red line of a krypton laser, which are entirely free of transients, and in spectra of adjacent domains acquired with the green line of the argon laser.

In addition to the work directed at spectral interpretation and at explorations of tertiary structure we devoted some effort to developing the use of the ultrafast laser with gated detection. We demonstrated that it is possible to discriminate against the fluorescence of the samples by proper timing of the gating relative to the exciting laser pulse. We were able to discriminate in samples of cellulose which has fluorescence underlying the Raman spectra, in samples of ethylene glycol that had fluorescein dissolved in them, and in samples of ground wood. We expect to couple the ultrafast laser and the gated detection system to the microprobe sometime before the end of the current grant period.

Reports are currently in preparation on the studies of the transient components in the 1595 cm^{-1} band, on the discrimination against fluorescence using the ultrafast system, and on the preliminary mapping studies using the new microprobe system.

Tertiary Structures in Celluloses

Our studies of tertiary structure in celluloses has combined the use of Raman spectroscopy with x-ray diffractometry and Solid State (CP/MAS) ^{13}C NMR. Two recent publications are attached.

One is from the proceedings of the 10th Cellulose Conference (Attachment 3), the other from the proceedings of the Cellucon 88 Conference (Attachment 4). The latter is the publication in which we introduced the conceptual framework which we have adopted into our discussions of the structures of cellulose. The former, Attachment 3, provides a more complete presentation of the evidence in support of our interpretations.

In terms of our framework, the key findings are that native celluloses from plants are composites of two forms of cellulose that have the same secondary structure but subtly different tertiary structures, which we have identified as I_{α} and I_{β} . The Raman spectra, which are more sensitive to secondary than tertiary structure show that the skeletal conformations are the same but that the hydrogen bonding patterns between the chains are different. The Solid State ^{13}C NMR spectra, which are sensitive to both secondary and tertiary structures, show that two intimately blended tertiary structures occur in all the native celluloses, and that the balance between the two forms is dependent on the source of native cellulose. The bacterial and algal celluloses have the I_{α} form dominant, while the celluloses from the higher plants have the I_{β} form dominant.

Another significant observation was the finding that a correlation seems to exist between the type of terminal complexes synthesizing the celluloses and the balance between the two tertiary structures. The celluloses that have the I_{β} form dominant all appear to be produced by plants that have rosette like arrays of complexes at the cell membrane. Thus, a tertiary structure defined by the processes of deposition is clearly indicated. We note in this connection that Chanzy and coworkers have found the animal cellulose tunicin to be of the pure I_{β} form (3).

Biomimetic Tertiary Aggregates

Our reports on biomimetic tertiary aggregates are currently in preparation. In the accompanying proposal we have defined two classes of biomimetic aggregates, the first prepared to explore the effects of other cell wall constituents on the patterns of aggregation of cellulose, the second seeking to duplicate the patterns which may emerge when lignin precursors are polymerized in ordered polysaccharide matrices. Our own program has focussed on the first of these classes.

Our program on the manner in which constituents which mimic the cell wall environment affect the aggregation of cellulose was concerned with two groups of constituents. They were added to the media of Acetobacter xylinum cultures, and the celluloses harvested from these cultures were characterized with respect to states of aggregation using X-ray diffractometry, Raman spectroscopy, and in selected cases, Solid State ^{13}C NMR. The groups of constituents were some selected polysaccharides similar to those occurring in the cell wall and a group of lignin precursors known to occur within the cell walls of differentiating woody tissue, and some related model compounds. In the studies carried out so far these two groups have been evaluated separately.

The polysaccharides investigated included low molecular weight mannans, some xylans, and a tamarind seed derived xyloglucan. They were found to influence the states of aggregation of cellulose to varying degrees. The effects will be described in detail in a future report, but one key finding is relevant here. This finding is that in every instance application of procedures routinely used in the isolation of cellulose from plant tissue resulted in changes in the state of aggregation. The changes were in the direction of producing a more crystalline aggregate than that originally formed. Thus, although in most cases the aggregates formed initially were different from those of the

controls, after they had been subjected to the extraction procedures usually used to remove other cell wall constituents they were in essence indistinguishable from the controls.

The lignin precursors investigated included coniferyl alcohol, coniferin, and syringin. In all cases the cellulose aggregates were less crystalline than the controls, but with the group it was only necessary to apply vigorous washing to bring about aggregation similar to that in the controls. This effect is not unlike reported by Haigler and Brown and their coworkers (4-7) when they washed with distilled water bacterial celluloses the structure of which had been perturbed by optical brighteners.

The findings in these studies raise a very important question about models of celluloses in cell walls of higher plants. It is generally assumed that the cellulose is formed as fibrils which are embedded in the polysaccharides and lignin matrices that surround them as encrustants. Our results suggest that this may be an unjustified extrapolation of the observations on more primitive plants or on selected higher plants wherein the cellulose is produced in near pure form. We believe it important to consider the possibility that the fibrillar celluloses that are isolated from higher plants using, classical preparative procedures, may have a morphology that is more reflective of the isolation procedure than the native states of aggregation.

Autoradiographic Localization of Hemicelluloses in Cell Walls

This work was undertaken in our laboratory in collaboration with Dr. N. S. Thompson in relation to a mutual interest in the relationship of hemicelluloses to cellulose. Dr. Thompson had used autoradiography in some previous studies of hardwoods; we were able to contribute some refinements of the methodology. Although the initial motivation was the localization of the hemicelluloses, as reported in a preliminary manuscript appended

as Attachment 5, the variability in the content of the hemicelluloses monitored suggested different degrees of moderation of the states of aggregation of cellulose. Furthermore, the implication is clear from the resulting distributions of hemicelluloses that they are deposited simultaneously with the celluloses. Even more direct evidence was seen in the autoradiographs of less mature tissue not included in the present study.

These results, when taken together with the expectation that the the hemicelluloses and cellulose are thermodynamically compatible, provide further support for our view that, particularly in the higher plants, the traditional model of pure cellulose fibrils surrounded by encrustants is seriously flawed. In search of alternatives we have considered the possibility that the hemicelluloses and lignin precursors are more intimately blended with the cellulose than is generally assumed. On the basis of the studies of biomimetic aggregates derived from the cultures of *Acetobacter xylinum*, we believe that the hemicelluloses are the primary moderators of the states of aggregation of the cellulose, and that the lignin precursors are involved in a secondary role not yet clearly defined.

REFERENCES

1. Atalla, R.H. and Agarwal, U.P., 1985. *Science* 227, 636.
2. Atalla, R.H. and Agarwal, U.P., 1986. *J. Raman Spec.* 17, 229.
3. Belton, P.S., Tanner, S.F., Cartier, N. and Chanzy, H., 1989. *Macromolecules* 22, 1615.
4. Haigler, C. H., Brown, R. H., Jr., and Benziman, M., 1980. *Science*, 210, 903.

5. Brown, M. R., Jr., Haigler, C. H.. and Cooper, K., 1982.
Science, 218, 1141.
6. Haigler, C. H. and Chanzy, H., 1988. J. Ultrastructure and
Molecular Structure Research, 98, 299.
7. Haigler, C. H., White, A. R., Brown, M. R., Jr., and
Cooper, K. M., 1982. J. Cell Biology, 94, 64.

**DATE
FILMED**

8/27/92