DOE/PC/89881--T8

DE92 019005

Microbial Recovery of Metals from Spent Catalysts

Quarterly Report, July - September, 1990

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Penny L. Sperl and George T. Sperl
Geo-Microbial Technologies, Inc.

P.O. Box 132
Ochelata, OK 74051
Phone 918-535-2281

Contract No. DEAC2289PC89881

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Abstract/Summary

The fourth quarter of this project (July through September 1990) was one of significant progress in the study of the microbiological reclamation of Mo and Ni from spent coal liquefaction catalysts. We confirmed that *T. ferrooxidans* was very sensitive to molybdate and extremely sensitive to tungstate, but showed relatively little sensitivity for the related compounds, chromate and vanadate, and for the catalyst associated metals, Ni^{++} and Al. There appears to be no negative synergistic effects between Ni^{++} and molybdate for growth, which bodes well for processes to reclaim both of these metals from spent coal liquefaction catalysts. We have shown that *T. ferrooxidans* is indeed capable of leaching Mo and Ni^{++} from spent catalysts if the catalyst is washed initially with an organic solvent such as tetrahydrofuran to remove the oily contaminants and an aqueous acidic medium to remove readily solubilized Ni^{++} and Mo. The stage is now set for the development of a molybdate tolerant strain to be used for actual microbial leaching of the spent catalyst. These studies should provide both a good handle on the practical aspects of recovering metals from the spent catalyst, and should also provide conditions necessary for the selection of naturally-occurring molybdate resistant strains of *T. ferrooxidans*.

Introduction.

This project was initiated on October 1, 1989, for the purpose of recovering metals from spent coal liquefaction catalysts. Two catalyst types are the subject of the contract. The first is a Ni-Mo catalyst supported on alumina (Shell 324) as is used in a pilot scale coal liquefaction facility at Wilsonville, Alabama. This plant is run and operated by Southern Clean Fuels. A large sample of spent catalyst from this facility has been obtained. The second material is an unsupported ammonium molybdate catalyst used in a pilot process by the Department of Energy at the Pittsburgh Energy Technology Center. This material was obtained in late February 1990 but has not been pursued since the Mo content of this particular sample is too low for the current studies. The object of the contract is to treat these spent catalysts with microorganisms, especially *Thiobacillus ferrooxidans*, but also other *Thiobacillus* sp. and possibly *Sulfolobus*, to leach and remove the metals (Ni and Mo) from the spent catalysts into a form which can be readily recovered by conventional techniques.

Cultures.

Cultures of *T. ferrooxidans* and *T. denitrificans* and related organisms were obtained from INEL, the American Type Culture Collection, and isolated from natural sources. The INEL medium for the cultivation of *T. ferrooxidans* was used with an initial pH of 2.0; this pH was later changed to 2.5 when better and more reproducible results were obtained at that pH. *Thiobacillus denitrificans* was cultured in the ATCC medium of choice (usually medium 450). Growth of *T. ferrooxidans* is visible in 3-5 days with an active inoculum, and *T. denitrificans* in about 48 hrs.

Catalyst Treatment.

The spent catalyst from Wilsonville was treated initially by extensively washing the material with tetrahydrofuran in a soxhlet extractor and evaporating the THF from the residual catalyst and the oil/THF-containing liquid. The dried catalyst was then crushed in a ball mill, producing fractions from 10 to smaller than 100 mesh. Minus 100 mesh material was initially used to assay metal release. This has since been replaced by 10 mesh or uncrushed material since microbial leaching appears to proceed just as well without crushing.

Molybdate Tolerance.

Thiobacillus ferrooxidans strains from the American Type Culture Collection (Numbers 14119 and 21834) were tested and found to have similar Ni^{++} and molybdate toxicities as do the strains obtained from INEL. The bottom line is that all *T. ferrooxidans* strains so far tested show maximum tolerance levels for molybdate of less than 100 μM . It has now become obvious that a Mo tolerant strain will be necessary for economic success of the project and that little or no pre treatment of the spent catalyst may be necessary for application of *T. ferrooxidans* to the leaching of both Ni and Mo from spent coal liquefaction catalyst. The possibility of oil toxicity appears now to be very real but relatively easy to circumvent. We are still undecided as to whether organisms other than *T. ferrooxidans* might be useful metal leaching microorganisms. It is clear that they must be strong acid producers in order to adequately leach metals from the spent catalyst. Three strains of *T. ferrooxidans* (DT-3, DT-5, F221) were selected for their general higher tolerance of molybdate and then grown in the presence of the above related elements as well as Vanadium. In general we found that Cr is tolerated at very high levels relative to Mo. This was quite surprising since Cr is usually considered quite toxic to microorganisms, probably because of its high reactivity. Since the INEL broth at pH 2.5 was used, there certainly was some conversion of the Sodium Chromate (about 50%) supplied in the medium to Dichromate and indeed there was visible ferrous iron

oxidation at high chromate concentrations. Nevertheless, visible and considerable growth of *T. ferrooxidans* was seen with much higher levels of Chromate than can be seen with Molybdate. Vanadate also was tolerated at very high levels and, as with Chromate, there was some chemical oxidation of the ferrous iron at high Vanadate concentrations. The addition of Sodium Tungstate to INEL broth at pH 2.5 revealed that *T. ferrooxidans* is extremely sensitive to Tungstate. Tungstate is tolerated at only 10% the levels Molybdate is tolerated (i.e. 10 μ M for Tungstate vs. ~100 μ M for Molybdate). These results are summarized in Tables 1-3 below.

Related Metal Tolerance Studies.

Table 1

Vanadate Tolerances of *T. ferrooxidans* Strains

		Growth				
		Vanadate Concentrations				
Strain	0 μ M	5 μ M	10 μ M	50 μ M	100 μ M	500 μ M
DT-3	+	+	+	+	+	+
DT-5	+	+	+	+	+	+
F221	+	+	+	+	+	+

Table 2

Chromate Tolerances of *T. ferrooxidans* Strains

		Growth				
		Chromate Concentrations				
Strain	0 μ M	5 μ M	10 μ M	50 μ M	100 μ M	500 μ M
DT-3	+	+	+	+	++	++
DT-5	+	+	+	+	++	++
F221	+	+	+	++	++	++

* - Although there was visible oxidation of ferrous iron in these cultures before growth was initiated, significant growth with the production of typical cell densities still occurred in these cultures. Of course the Chromate concentration was lowered because of the chemical oxidation, but the Cr still remained in some form in the culture vessel.

Table 3
Tungstate Tolerances of *T. ferrooxidans* Strains
Growth

Tungstate Concentrations						
Strain	0 μ M	5 μ M	10 μ M	50 μ M	100 μ M	500 μ M
DT-3	+	+	***	-	-	-
DT-5	+	+	***	-	-	-
F221	+	+	+	-	-	-

** - These cultures took extremely long to grow, 21 days vs 5-7 days for the other cultures which were positive for growth.

Microbial Leaching Experiments.

During this quarter of the contract we were successful in completely leaching both Ni and Mo from the catalyst samples from Wilsonville. These studies were done in a shake flask with initial amounts of the catalyst at a concentration of 1g catalyst per 100 ml of the acidic INEL medium. These studies were carried out by removing the liquid portion of the shake flask contents and replacing this liquid with fresh medium and microorganisms on, typically, a weekly basis. The liquid was analyzed for Ni and Mo content using atomic absorption. In addition, the fine microparticulate material which is formed during growth of the microorganisms was collected by centrifugation and dissolved in 4 N HCl at 65 C. This was also analyzed for Ni and Mo. The results are graphically shown in the figures below and can be summarized as follows. Raw Shell 324 catalyst is readily leached by *T. ferrooxidans* and all of the Ni and Mo can be reasonably accounted for within a short period of leaching time. When the catalyst is complicated by sulfiding (the "Presulfided" samples) which has transformed the raw Shell 324 into a form where the metals are in the sulfide form and the catalyst is contaminated with a light oil, *T. ferrooxidans* is able to release the metals from these catalyst samples whether or not the oil is first removed. In this case, as opposed to the case of the spent catalyst, the oil has no toxicity for *T. ferrooxidans*. The next level of complication of the catalyst is THF-extracted spent catalyst. Again, *T. ferrooxidans* is capable of removing the metals from these catalyst samples, although the kinetics are such that it takes considerably longer for the complete removal. When the most complex catalyst samples are subjected to leaching, the metals are eventually completely solubilized and removed from the catalyst matrix, although the time frame for these samples is considerably longer and the total volume of leaching solution is

greater (see Figures 1-16). These leaching results are summarized in Table 4 below.

Table 4
Percentages of Leached Metals

Catalyst Sample	% Mo Leached	% Ni Leached*
Oily Wilsonville INEL Pre Wash	45	91
Oily Wilsonville H ₂ SO ₄ Pre Wash	49	81
10 Mesh-THF Extracted INEL Pre Wash	141	93
10 Mesh-THF Extracted H ₂ SO ₄	122	100
Presulfided Shell 324 INEL Pre Wash	116	63
Presulfided Shell 324 ** H ₂ SO ₄	84	62
Shell 324 ** INEL Pre Wash	111	58
Shell 324 ** H ₂ SO ₄	77	99

* - In all cultures, Ni appears to be completely removed

** - These cultures show no more metal release and had been previously discontinued.

Figure 1

Figure 2

Figure 3

Figure 4

Figure 5

Figure 6

Figure 7

Figure 8

Figure 9

Figure 10

Figure 11

Figure 12

Figure 13

Figure 14

Figure 15

Figure 16

END

**DATE
FILMED
9/23/92**