**ADVANCED
FUEL
RESEARCH**

P.O. Box 18343
East Hartford, Connecticut 06118
Telephone (203) 528-9806

DOE PC/79901-78

DOE/PC/79901--T8

DE92 041113

RADIATIVE PROPERTIES OF ASH AND SLAG

Sixth Quarterly Report

#523050-18

For the Period

November 1, 1988 to January 31, 1989

PETER R. SOLOMON

and

JAMES R. MARKHAM

Work Performed Under Contract #DE-AC22-87PC79901

for

U.S. DOE - PITTSBURGH ENERGY TECHNOLOGY CENTER

by

ADVANCED FUEL RESEARCH, INC.

**87 Church Street
East Hartford, CT 06108
203/528-9806**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or it presents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PATENT STATUS

"U.S. DOE Patent Clearance is **not** required prior to the publication of this document".

ABSTRACT

Thermal radiation plays a key role in the operation and efficiency of combustion systems, accounting for over 90% of the heat transfer. The analysis of radiative heat transfer in coal-fired boilers, combustion chambers and other energy systems requires accounting for the effects of inorganic deposits on bounding surfaces and of entrained particulates, such as pulverized coal, char and fly-ash. These effects can be predicted; however, the accuracy in predicting the radiative properties of entrained particles (ash) and deposit layers (slag) is limited by inaccurate knowledge of the physical/chemical properties of the materials over a range of material temperatures and radiative wavelengths that is representative of conditions in practical combustion systems. The objective of this project is to make laboratory measurements of the radiative properties of extracted ash deposit samples. During this quarter, technique validation measurements were performed on several test samples. Technique validation has been achieved for infrared opaque and semi-transparent materials that exhibit a high degree of specular reflection (i.e. having a negligible diffuse reflectance component). Validation has not been achieved for non-specular reflecting surfaces, but work is progressing on modifying the present system to accommodate these materials.

RADIATIVE PROPERTIES OF ASH AND SLAG

TABLE OF CONTENTS

<u>Section</u>	<u>Title</u>	<u>Page</u>
	Disclaimer	i
	Abstract	ii
I.	INTRODUCTION	1
II.	PROGRESS SUMMARY	2

I. INTRODUCTION

Thermal radiation plays a key role in the operation and efficiency of combustion systems accounting for over 90% of the heat transfer. The radiative heat transfer in coal-fired boilers, combustion chambers and other energy systems is dominated by the properties of inorganic deposits on bounding surfaces and of particulates, such as pulverized coal, char, soot, and fly-ash which are present in the system. The properties governing the emission, absorption and attenuation of the radiative energy by deposits and entrained particulates are a key element in accurately predicting the radiative heat transfer. The radiative properties of materials are characterized by the extinction efficiency, absorption efficiency (or emissivity) and scattering efficiency. These efficiencies depend on the complex refractive index, the particle size or layer thickness and the material's porosity.

This project will determine the radiative properties of ash and slag from combustion devices using state-of-the-art experimental techniques. Improved measurements of radiative properties of minerals at high temperature will be made by a technique employing a flow reactor coupled to a Fourier Transform Infrared (FT-IR) Spectrometer to measure emission, transmission, and reflection on the same sample. The complex index of refraction required to calculate emissivities will be determined by transmission techniques employing fine particles suspended in a KBr matrix.

We applied our transmission/reflection technique to obtain the spectral emissivity of specular and non-specular reflecting surfaces at room and elevated temperatures. Closure of

$$\rho_{\nu} + \alpha_{\nu} + \tau_{\nu} = 1 \quad (1)$$

where ρ is the fraction of radiation reflected, α is the fraction absorbed (and is equal to the emissivity, ϵ), τ is the fraction transmitted, and where the subscript ν indicates a spectral quantity, has been achieved for specular reflecting materials. Data for polished silicon nitride, fused quartz, and synthetic sapphire are presented in Task 2.

Closure has not been achieved at present for non-specular reflecting surfaces due to anisotropies in the sample (i.e. the angular dependence of the reflectance varies with the rotation of the sample). Data for rough silicon nitride and alumina has been analyzed and work is progressing on modifying the present system to accommodate these materials.

The spectral emittance from radiance measurements of the above samples has been determined. Good agreement has been reached between these measurements and the emittance obtained from the transmission/reflection technique.

PROGRESS SUMMARY

Task 1 - Project Implementation Plan

Completed in the third quarter and approved in the fourth quarter.

Task 2 - Measurement Technique Validation

The spectral emittance at room temperature has been measured for polished surfaces of silicon nitride and fused quartz by the transmission/reflection technique. The work on silicon nitride was performed under a separate program but is reported here as good validation data for the technique. Both of these materials were determined to be good specular reflectors (i.e., negligible diffuse reflectance component) of infrared radiation. The infrared opaque ($\tau = 0$) silicon nitride required only reflectance measurements, whereas the quartz required the determination of reflected and transmitted radiation.

Figure 1a shows the total integrated hemispherical reflected radiation from polished silicon nitride. Figure 1b is of each integrated angular component of the hemispherical sum. The optical and sample geometry is arranged such that the 15° designation (angle between the center of the incident IR beam to the center of the reflected IR beam) is the specular geometry; and the optics and the computational routine developed to obtain the radiation integrated over a hemisphere allows for measurements to be taken at $+5^\circ$ intervals from specular. Figure 1b indicates that negligible radiation was reflected from the polished Si_3N_4 out of the specular geometry. At a 25° setting, no radiation was detected.

Figure 1c is of the spectral emittance calculated from Eq. 1. If there is no transmittivity, the emittance must be equal to unity where the reflectance of the material is zero. The shape of our room temperature emittance curve follows trends reported by Johnson et al. (1) typical of Si_3N_4 , who observed a maximum at $8\text{ }\mu\text{m}$ followed by a sharp decline and then increase to $14\text{ }\mu\text{m}$. These data (Fig. 1d) were taken at 1700 K.

Data for optical grade fused quartz are presented in Fig. 2. Figure 2a is of the total hemispherical reflected radiation and as with the polished Si_3N_4 , negligible radiation was detected out of the specular geometry. Figure 2b is of the transmittivity of the quartz. The decline at 3000 cm^{-1} ($3.3\text{ }\mu\text{m}$) matches specifications for IR grade fused quartz. The features at 3650 cm^{-1} ($2.7\text{ }\mu\text{m}$) and 4500 cm^{-1} ($2.2\text{ }\mu\text{m}$) are characteristic absorption bands of hydroxyl ion impurities in the quartz. Figure 2c is the spectral emittance calculated from Eq. 1. Notable is that again where the reflectance and transmittance is zero, emittance is equal to unity. Figure 2d is data of Myers et al. (2) for fused quartz at 1273 K. Our sample was supplied by the same company that supplied Myers' sample, and corresponds to the 320 mm thick sample. Good agreement in shape is achieved given the differences in sample temperature.

Figure 3a-3c shows spectral emittance calculated from Eq. 1 for polished silicon nitride, fused quartz, and synthetic sapphire that were brought to elevated temperatures by surrounding the sample with a hydrogen flame. All three materials exhibited negligible reflection from non-specular angles; and all three materials exhibited a unique characteristic spectral region where both the transmittivity and the reflectivity is zero. Overlaid on Fig. 3b is the data of Myers et al. Agreement is excellent below 3000 cm^{-1} , in the non-transparent region of the quartz. Differences in the hydroxyl absorption regions is most likely due to concentration differences. Not understood is the discrepancy with our non-zero emissivity above 5000 cm^{-1} .

Figure 1. a) Total Integrated Spectral Reflectivity for Polished Silicon Nitride at Room Temperature, b) 15° Specular and 20° Non-specular Components, c) Spectral Emittance Calculated from 1-Reflectance, and d) Data of Johnson, et.al. (1) for Several Si_3N_4 Samples at 1700k.

Figure 2. a) Total Integrated Spectral Reflectivity for Optical Grade Fused Quartz at Room Temperature, b) Transmittance Through the Sample, c) Spectral Emittance Calculated from 1-Reflectance - Transmittance, and d) Data of Myers et.al. (2) at 1273k.

Figure 3. Spectral Emittance Calculated from 1-Reflectance - Transmittance for a) Polished Silicon Nitride at $\sim 925\text{K}$, b) Optical-grade Fused Quartz at 900K , and c) Synthetic Sapphire at $\sim 1100\text{K}$. The Darkened Circled in b) are from the Data of Myers et.al. in Fig. 2b for Quartz at 1273K . -5-

The results for specular reflecting materials appear good. Closure of Eq. 1 is evident and comparison with literature values is good.

Closure has not been achieved for surfaces with diffuse reflectance components. Two problems have been identified that are contributing to this: 1) Anisotropic reflection due to surface ridge patterns originating in the manufacturing process (cutting or press patterns), and 2) a multiple scattering effect which will allow radiation that passes into the material to emerge again from the same surface, but effectively enlarging the outgoing infrared spot size with respect to the incident spot size. Work is progressing on accounting for these effects and achieving closure of Eq. 1 for diffuse reflecting materials.

The spectral emittance for all of the samples mentioned above have been measured from radiance measurements at elevated temperature.

Figure 4a-4c show the measured radiance for the specular surfaces, corrected for instrument response, overlaid with the theoretical black-body radiance that corresponds to the sample temperature. The black-body temperature was determined by matching the observed radiance to the theoretical black-body radiance at the spectral region where the reflectance and transmittance are both zero, thereby establishing the emittance to be unity at that region. Thermocouple measurements of the sample surfaces typically indicated temperatures $\sim 150^\circ\text{C}$ hotter due to effects of the substantially hotter surrounding H_2 flame. The thickness of these test samples did not allow for placement of a thermocouple in a blind hole to accurately indicate sample temperature.

Figure 4a, for quartz was taken at 0.5 cm^{-1} resolution so that a continuum quartz spectrum could be determined at the baseline of the H_2O line spectrum caused by H_2 combustion. The time necessary to collect this high resolution spectrum was ~ 10 minutes. Figures 4b and 4c show spectra taken in 15 seconds for sapphire and silicon nitride at 16 cm^{-1} resolution. For these samples the H_2 flame was shut off and a quick argon purge was used to remove residual hot water vapor from the beam path. The 15 second measurement is therefore an average radiance measurement as the sample cools. Measurements with the H_2 flame on indicated $\sim 125\text{ K}$ hotter sample temperature but the broad H_2O emission bands could not be quantitatively removed in the rapid measurement.

Figures 5a-5c compare the emittance determined from the radiance measurements with those determined from the reflectance measurement. Very good agreement is observed.

Task 3.a - Deposit Sample Acquisition

Babcock & Wilcox Company will be supplying AFR with a minimum of six ash deposit samples. These samples will have been produced under DOE Contract No. DE-AC22-87PC79902 and be those for which in-situ optical measurements made by Babcock & Wilcox are available.

Task 3.b. - Sample Characterization

Work will be scheduled when Task 3a is completed.

Task 4 - Measurement of Radiative Properties of Ash Deposit Samples

No work was scheduled for this quarter.

Figure 4. Radiance Measurements for a) Fused Quartz in the Hydrogen Flame at 0.5 cm⁻¹ Resolution, b) Polished Silicon Nitride (H₂ Flame Off) at 16 cm⁻¹ Resolution. Each are Overlaid with a Theoretical Black-Body Radiance Calculation Corresponding to the Sample Temperature.

Figure 5. Spectral Emittance Determined by Radiance Measurement Compared to Spectral Emittance Determined by 1-Reflectance - Transmittance for a) Fused Quartz, b) Polished Silicon Nitride, and c) Synthetic Sapphire.

Overall Plans and Objectives for Next Quarter

1) Work on achieving technique validation for transmission/reflection measurements of non-specular materials; 2) elevate samples to higher temperatures; 3) initiate work on ash deposit samples.

References

1. Johnson, P.E., DeWitt, D.P., and Taylor, R.E., AIAA Journal, **19**, 113, (1981).
2. Myers, V.H., Ono, A., and DeWitt, D.P., AIAA Journal, **24**, (2) 321, (1986).

END

**DATE
FILMED**

11 / 10 / 92