DOE/PC/88856--T12

DE93 000892

SURFACE MAGNETIC ENHANCEMENT
FOR COAL CLEANING

FINAL REPORT

Submitted to:

U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Contract Number: DE-AC22-88PC88856

Technical Program Officer: McMahan L. Gray

Prepared by:

Project Manager and Principal Investigator:
J. Y. Hwang
Program Manager - Minerals

Institute of Materials Processing
Michigan Technological University
Houghton, Michigan 49931

MASTER

ABSTRACT

A coal cleaning research by means of surface magnetic enhancement through the use of magnetic reagent has been conducted by the Institute of Materials Processing at Michigan Technological University. This research has been funded by the Department of Energy under Contract No. DE-AC22-88PC88856, entitled "Surface Magnetic Enhancement for Coal Cleaning." The program consisted of a fundamental study to define the chemistry for the interactions between magnetic reagent and mineral and coal particles, a laboratory study to determine the applicability of this technology on coal cleaning, and a parameter study to evaluate the technical and economical feasibility of this technology for desulfurization and de-ashing under various processing schemes.

Surface magnetic enhancement using magnetic reagent is a new technology developed at the Institute. This technology can be applied to separate pyrite and other minerals particles from coal with a magnetic separation after adsorbing magnetic reagent on the surface of pyrite and other minerals particles. Particles which have absorbed magnetic reagent are rendered magnetic. The adsorption can be controlled to yield selectivity. Thus, the separation of traditionally nonmagnetic materials with a magnetic separator can be achieved.

Experiments have been performed to demonstrate the theoretical fundamentals and the applications of the technology. Adsorbability, adsorption mechanisms, and adsorption selectivity are included in the fundamental study. The effects of particle size, magnetic reagent dosage, solid contents, magnetic matrix, applied magnetic field strengths, retention times, and feed loading capacities are included in the application studies.

Three coals, including Illinois No. 6, Lower Kittanning and Pocahontas seams, have been investigated. More than 90% pyritic sulfur and ash reductions have been achieved. Technical and economic feasibilities of this technology have been demonstrated in this study. Both are competitive to that of the froth flotation approach for coal cleaning.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	i.
LIST OF FIGURES	iv.
LIST OF TABLES	x.
CHAPTER 1 - INTRODUCTION	1
1.1 Program Background	1
1.2 Objectives	3
1.3 Program Rationale and Outlines	3
CHAPTER 2 - MAGNETIC REAGENT AND ITS PREPARATION	5
2.1 What is a Magnetic Reagent	5
2.2 Preparation of Magnetic Reagent	6
CHAPTER 3 - ADSORPTION MECHANISMS OF MAGNETIC REAGENTS	9
3.1 Experimental Procedures	9
3.2 Anionic Magnetic Reagents	11
3.3 Cationic Magnetic Reagents	14
3.4 Nonionic Magnetic Reagents	14
3.5 Activators and Depressants	15
3.6 Adsorptions on Coal	17
3.7 Adsorption Mechanisms	18
CHAPTER 4 - MAGNETIC REAGENT APPLICATION PARAMETERS	20
4.1 Reagent Dosage	20
4.2 Shelf Life	22
4.3 Magnetite Particle Size and Surfactant Consumption	23
4.4 Collection of Magnetic Enhanced Minerals	24
CHAPTER 5 - COAL PREPARATION AND CHARACTERIZATION	27
5.1 Coal Preparation	27
5.2 Characterization	29
5.2.1 Coal Analysis	29
5.2.2 Grinding	29
5.2.3 Washability	29
5.2.4 Mineralogy	30
CHAPTER 6 - COAL CLEANING WITH MAGNETIC REAGENTS	32
6.1 Chemistry for Coal Cleaning with Magnetic Reagents	32
6.2 Coal Cleaning at -48 Mesh	
-6.2.1 Application to ROM coal	33
6.2.2 Application to Flotation Concentrate	35

TABLE OF CONTENTS (continued)

	<u>Page</u>
6.3 Fine Coal Cleaning	37
6.3.1 Illinois No. 6 Fine Coal Cleaning	37
6.3.2 Lower Kittanning Fine Coal Cleaning	39
6.3.3 Pocahontas Fine Coal Cleaning	40
CHAPTER 7 - OPTIMIZATION OF MAGNETIC REAGENT SEPARATIONS	42
7.1 Magnetic Separator	42
7.2 Particle Size and Magnetic Matrix	42
7.3 Magnetic Reagent Dosage	44
7.3.1 Illinois No. 6	44
7.3.2 Lower Kittanning	46
7.3.3 Pocahontas	47
7.4 Applied Magnetic Field Strength	48
7.5 Solids Content	51
7.6 Loading Capacity	52
CHAPTER 8 - TECHNOLOGY COMPARISON AND DISCUSSION	55
8.1 Comparison of Washability, Flotation, and Magnetic Reagent Separation	55
8.2 Technical Discussion	58
CHAPTER 9 - ECONOMIC ANALYSIS	62
9.1 General Consideration	62
9.2 Capital Costs	63
9.3 Operating and Maintenance Costs	66
9.4 Combination of Economic Parameters	68
CHAPTER 10 - CONCLUSIONS AND RECOMMENDATIONS	70
ACKNOWLEDGEMENT	73
APPENDIX I - FIGURES	75
APPENDIX II - TABLES	160

LIST OF FIGURES

<u>Figure</u>		<u>Page</u>
1	The structure of a magnetic reagent.	76
2	The adsorption of MR-30 (sodium oleate) on various minerals.	77
3	The adsorption of MR-31 (sodium lauryl sulfate) on various minerals.	78
4	The adsorptions of various anionic magnetic reagents on calcite.	79
5	The adsorptions of various anionic magnetic reagents on quartz.	80
6	The adsorptions of various anionic magnetic reagents on kaolinite.	81
7	The adsorption of MR-30 on pyrite under various conditions.	82
8	The adsorption of MR-31 on pyrite under various conditions.	83
9	The adsorption of MR-1 (primary amine) on various minerals.	84
10	The adsorption of MR-1 on pyrite under various conditions.	85
11	The adsorption of MR-45 (polyoxyethylene-4 lauryl ether) on various minerals.	86
12	The adsorption of MR-45 on pyrite under various conditions.	87
13	The effects of activators and depressants for the adsorption of MR-30 on calcite.	88
14	The effects of activators and depressants for the adsorption of MR-30 on quartz.	89
15	The effects of surface modifiers on the adsorption of cationic magnetic reagent (MR-3) on calcite.	90
16	The adsorption of anionic, cationic, and nonionic magnetic reagents on coal.	91

LIST OF FIGURES (continued)

		<u>Page</u>
17	The effects of salts on the adsorption of anionic MR-30 on coal.	92
18	The effects of salts on the adsorption of cationic MR-1 on coal.	93
19	The effects of salts on the adsorption of nonionic MR-45 on coal.	94
20	Magnetic enhancement of minerals by MR-1 at various dosages.	95
21	Magnetic enhancement of minerals by MR-45 at various dosages.	96
22	Magnetic enhancement of calcite by MR-30 at various dosages.	97
23	Sample preparation flowsheet for Illinois No. 6 coal.	98
24	Sample preparation flowsheet for Lower Kittanning coal.	99
25	Sample preparation flowsheet for Pocahontas coal.	100
26	Concentration flowsheet for Illinois No. 6 coal.	101
27	Concentration flowsheet for Lower Kittanning coal.	102
28	Concentration flowsheet for Pocahontas coal.	103
29	Size distribution of Illinois No. 6 coal at various grinding times.	104
30	Size distribution of Lower Kittanning coal at various grinding times.	105
31	Size distribution of Pocahontas coal at various grinding times.	106
32	Washability of coals at -48 mesh.	107
33	Washability of coals at 90% passing 100 mesh.	108

LIST OF FIGURES (continued)

		<u>Page</u>
34	Washability of coals at 90% passing 200 mesh.	109
35	Washability of coals at 90% passing 325 mesh.	110
36	Washability of coals at 90% passing 500 mesh.	111
37	X-ray diffraction pattern and mineral interpretation of Illinois No. 6 coal.	112
38	X-ray diffraction pattern and mineral interpretation of Lower Kittanning coal.	113
39	X-ray diffraction pattern and mineral interpretation of Pocahontas coal.	114
40	Pyrite grain size frequency of Illinois No. 6 coal.	115
41	Pyrite grain size frequency of Lower Kittanning coal.	116
42	Pyrite grain size frequency of Pocahontas coal.	117
43	Coal cleaning with magnetic enhancement at -48 mesh.	118
44	Comparison of flotation and magnetic enhanced separation at -48 mesh for Illinois No. 6 coal.	119
45	Comparison of flotation and magnetic enhanced separation for Lower Kittanning coal.	120
46	Comparison of flotation and magnetic enhanced separation for Pocahontas coal.	121
47	Ash contents of Illinois No. 6 coal at various particle size using magnetic reagent cleaning method.	122
48	Pyritic sulfur rejection results for Illinois No. 6.	123
49	Ash content of Lower Kittanning coal after magnetic reagent cleaning.	124

LIST OF FIGURES (continued)

		<u>Page</u>
50	Pyritic sulfur rejection of magnetic reagent processed Lower Kittanning coal.	125
51	Ash content of Pocahontas coal after magnetic reagent cleaning.	126
52	Pyritic sulfur rejection of Pocahontas coal with magnetic reagent cleaning.	127
53	Separation of -48 mesh Illinois No. 6 coal with various magnetic matrix.	128
54	Separation of Illinois No. 6 coal at 90% passing 200 mesh with various magnetic matrix.	129
55	Magnetic reagent dosage for the separation of -48 mesh Illinois No. 6 coal.	130
56	Magnetic reagent dosage for the separation of -200 mesh Illinois No. 6 coal.	131
57	Magnetic reagent dosage for the separation of Lower Kittanning coal at -48 mesh.	132
58	Magnetic reagent dosage for the separation of Lower Kittanning coal at 90% passing 200 mesh.	133
59	Magnetic reagent dosage for the separation of Pocahontas coal at -48 mesh.	134
60	Magnetic reagent dosage for the separation of Pocahontas coal at 90% passing 200 mesh.	135
61	Magnetic field strength effects for the separation of Illinois No. 6 at -48 mesh.	136
62	Magnetic field strength effects for the separation of Illinois No. 6 at 90% passing 200 mesh.	137
63	Magnetic field strength effects for the separation of Lower Kittanning at -48 mesh.	138
64	Magnetic field strength effects for the separation of Lower Kittanning at 90% passing 200 mesh.	139

LIST OF FIGURES (continued)

		<u>Page</u>
65	Magnetic field strength effects for the separation of Pocahontas at -48 mesh.	140
66	Magnetic field strength effects for the separation of Pocahontas at 90% passing 200 mesh.	141
67	Solids content effects for the separation of Illinois No. 6 at -48 mesh.	142
68	Solids content effects for the separation of Lower Kittanning at -48 mesh.	143
69	Solids content effects for the separation of Pocahontas at -48 mesh.	144
70	Solids content effects for the separation of Illinois No. 6 at 90% passing 200 mesh.	145
71	Solids content effects for the separation of Lower Kittanning at 90% passing 200 mesh.	146
72	Solids content effects for the separation of Pocahontas at 90% passing 200 mesh.	147
73	Loading capacity for the separation of Illinois No. 6 at -48 mesh.	148
74	Loading capacity for the separation of Lower Kittanning at -48 mesh.	149
75	Loading capacity for the separation of Pocahontas at -48 mesh.	150
76	Loading capacity for the separation of Illinois No. 6 at 90% passing 200 mesh.	151
77	Loading capacity for the separation of Lower Kittanning at 90% passing 200 mesh.	152
78	Loading capacity for the separation of Pocahontas at 90% passing 200 mesh.	153
79	Total sulfur separation results of Lower Kittanning coal at -48 mesh by washability, flotation, and magnetic reagent methods.	154

LIST OF FIGURES (continued)

		<u>Page</u>
80	Ash content separation results of Lower Kittanning coal at -48 mesh by washability, flotation, and magnetic reagent method.	155
81	Total sulfur separation results of Lower Kittanning coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent method.	156
82	Ash content separation results of Lower Kittanning coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent method.	157
83	Total sulfur separation results of Illinois No. 6 coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent method.	158
84	Ash content separation results of Illinois No. 6 coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent method.	159

LIST OF TABLES

<u>Table</u>		<u>Page</u>
1	Magnetic enhancement of minerals and coals by cationic magnetic reagents at pH 7.	161
2	Enhanced magnetic susceptibility of calcite by fresh and aged magnetizing reagent.	162
3	Magnetic Particle Size and Corresponding Surfactant Consumption.	163
4	Magnetite Particle Size Effect on Magnetic Separation of Calcite Using MR-01 for Magnetic Enhancement.	164
5	Magnetite Particle Size Effect on Magnetic Separation of Calcite Using MR-30 for Magnetic Enhancement.	165
6	Head analyses of the test coals.	166
7	Maceral distributions.	167
8	Particle size distributions of pyrite in volume percent.	168
9	Economic parameters for coal cleaning with the magnetic reagent approach.	169

CHAPTER 1

INTRODUCTION

1.1 Program Background

Coal is probably the most important energy resource of the foreseeable future. To be efficiently and acceptably utilized, most coals require cleaning to remove inorganic impurities. Common current practices employ heavy media separation, tabling and flotation to beneficiate and clean coal. However, such coal cleaning methods are becoming inadequate as SO_x emissions standards are made more stringent.

Many advanced physical separation technologies have been investigated. Magnetic separation is one of them. However, even high gradient magnetic separation technology has obtained only limited success [1]. Coal is a diamagnetic material. The minerals associated with coal, such as quartz, clays, calcite and pyrite, are also diamagnetic to very weak paramagnetic. Thus, the magnetic properties of most minerals associated with coal are too low to allow a clean separation using the existing magnetic separators. To increase the magnetic property of the minerals selectively while not changing the coal is the scientific goal of this study.

Traditional selective magnetic enhancement is approached through phase transformation. Roasting or microwave heating of pyrite under an inert or reducing environment to yield magnetic pyrrhotite are examples [2]. Reaction with toxic iron carbonyl

gases at high temperature is another example [3]. Because this approach cannot magnetize other minerals, such as quartz, clays, and calcite, the ash reduction capability of this approach is limited.

In the early 1980's, a selective magnetic enhancement approach utilizing the "piggy-back" concept developed by Hwang was reported [4]. Selective flocculations of the desired minerals with magnetite is the initial method. Successful applications to the beneficiation of ultrafine aluminum ores have been demonstrated [5]. The advancement of this technology in recent years is the development of "magnetic reagents" at Michigan Technological University [7].

Magnetic reagents are magnetic materials containing various functional groups. These functional groups can be tailored for an individual magnetic reagent to result in selective adsorption on desired nonmagnetic minerals [8]. This system is similar to the flotation approach, although the separation means is changed. Flotation combines the technologies of surface chemistry and gravitational separation, where air bubbles are utilized to "piggy-back" the desired minerals. Magnetic reagent technology conceptually replaces air bubbles with magnetic reagent. Technologies of surface chemistry and magnetics are combined to facilitate this technology.

This research was conducted to investigate the applications of this method on coal cleaning. The project was sponsored by the Department of Energy under the Contract Number DE-AC22-88PC88856.

The project was initiated on January 24, 1988, and took 3 years to complete.

1.2 Objectives

This research was formulated to enhance the magnetic properties of minerals in coal selectively. The enhancement was proceeded through the adsorption of a magnetic reagent on the surface of minerals, which was known in our previous investigations. The goal of this study was to find out how this technology could be applied to coal cleaning. Specific objectives included:

- To define the optimal conditions for the selective adsorption of magnetic reagents and their effects on magnetic enhancement.
- To determine the effects of magnetic enhancement on the efficiency of coal cleaning.
- To evaluate the adaptation of this method into existing coal processing circuits.

1.3 Program Rationale and Outlines

Three phases of work were involved in this study. The Phase I study (presented in Chapters 2 through 4) investigated the fundamentals for the adsorption of magnetic reagents on coal associated minerals and applied the fundamentals to develop the criteria for selective adsorption. Chapter 2 of this report describes what magnetic reagents are and how they are prepared. Chapter 3 discusses the mechanisms involved in the adsorption of

magnetic reagents on minerals and coal. Chapter 4 details some parameters of the magnetic reagents, such as dosage, shelf life and magnetite size, and their effects on magnetic reagent applications. Thus, the appropriate magnetic reagent for this study could be selected.

The Phase II study (discussed in Chapters 5 & 6) investigated the feasibility of applying the Phase I results to the cleaning of three coals. The Illinois No. 6, Lower Kittanning, and Pocahontas seams were selected. Chapter 5 describes the preparation and characterization of these coals, while Chapter 6 examines the cleaning of these coals under various processing conditions. Thus, the feasibility and the processing schemes could be determined.

The optimization of processing conditions, as described in Chapter 7, is a major part of the Phase III study. The results are compared with that of other technologies such as froth flotation, direct magnetic separation, and washability in Chapter 8. Technical discussion of the magnetic reagent technology is also included in this chapter. An economic analysis for the process developed in this study is provided in Chapter 9. Finally, Chapter 10 concludes the results of this study and recommends the work for future research.

CHAPTER 2

MAGNETIC REAGENT AND ITS PREPARATION

2.1 What is a Magnetic Reagent

A magnetic reagent is a composite of magnetic materials and surface active agents. The surface active agents contain functional groups which can react with magnetic materials and other materials. Under appropriate conditions, the agents can serve as a bridge to couple magnetic materials and other materials. Thus, the composite of magnetic materials and surface active agents with the capabilities to couple other materials is a magnetic reagent.

The magnetic reagents for this study have been developed by J.Y. Hwang in U.S. Patent Nos. 4,834,898 (1989) and 4,906,382 (1990). The reagent basically includes a particulate nucleus of a magnetic material and two layers of surfactants. Magnetite was the magnetic material utilized in this study. Other magnetic materials may include ferrites, maghemite, pyrrhotite, and metals, alloys, or compounds of iron, nickel, cobalt, etc. Magnetite was utilized because of its low cost.

Two layers of surfactants are built on magnetite as shown in Figure 1. The surfactants are water soluble or miscible organic compounds and have a heteropolar molecule including a functional group (or hydrophilic end) and a hydrocarbon chain (hydrophobic end). Figure 1 is an ideal representation of a magnetic reagent in water, in which the surfactant forming the inner layer is adsorbed on the magnetic nucleus with the functional group oriented toward

the magnetic nucleus and the hydrophobic end pointing radially outward. The surfactant forming the outer layer is adsorbed in the opposite direction with the functional group oriented toward the water. In actual practice, the hydrophobic ends of the two surfactants may mesh rather than meeting end to end as illustrated in the drawing.

The surfactants used for the inner and outer layers can be various anionic, cationic, or nonionic surfactants. The inner layer surfactant should have a functional group which has a strong affinity for the magnetic nucleus. The outer layer surfactant should be designed to have strong adsorbability on the interested minerals. Thus the two layers of surfactants can function as a bridge to couple the magnetic nucleus and the interested minerals.

2.2 Preparation of Magnetic Reagent

Magnetite can be obtained from various sources. One obvious way is to concentrate magnetite from ores, followed by grinding to produce materials with the desired particle sizes. However, this study utilized a wet method to generate colloidal magnetite with particle sizes of around 100 angstroms. The colloidal magnetite provides a large number of magnetic nucleus, which is beneficial to the reaction between the magnetic reagent and the minerals.

The wet method produces magnetite by reacting solutions of ferrous and ferric salts with the alkalies to precipitate gels of ferrous and ferric hydroxides. The gels are subsequently dehydrated by heating to form magnetite, if the amounts of ferrous and ferric molecules are in the appropriate ratio.

In an experiment, 3.4 grams $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ and 4.8 grams $\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$ were dissolved in 10 ml of water. Adding 10 ml of concentrated ammonia solution (56%) with rapid mixing, causes hydroxides to be precipitated. Because the reaction is exothermic, the solution is heated and some magnetite may form spontaneously. Heating the solution to above 60°C results in the complete conversion of the hydroxides to magnetite. Approximately 2.2 grams of magnetite can be produced with this procedure.

The two layers of surfactants can be built on the magnetite sequentially or simultaneously. For example, an aqueous suspension containing 2.2 grams of colloidal magnetite in 10 ml water first conditioned with 0.8 grams lauric acid to facilitate the adsorption of the first layer surfactant. Sodium hydroxide and heating (80°C) can improve the adsorption of lauric acid on magnetite. Excess lauric acid can be removed by water washing the lauric acid coated magnetite, which is usually in the form of oily agglomerates. Then the second layer surfactant can be established by adding it to the agglomerates. For example, adding 0.5 grams sodium dioctyl sulfonsuccinate (Aerosol OT) to the agglomerates will yield a peptized product possessing the desired double layer surfactant structure.

The lauric acid and sodium sulfonsuccinate can be added simultaneously to produce the double layer product as well. Because lauric acid has a stronger affinity to magnetite, this surfactant will be preferentially adsorbed on magnetite to form the inner

layer. Of course, some molecules of the two surfactants will be misplaced with this approach.

To obtain various functional groups for magnetic reagents, appropriate surfactants with the desired functional groups were selected for this study. The preparation of these magnetic reagents basically followed the same procedures as discussed above.

CHAPTER 3

ADSORPTION MECHANISMS OF MAGNETIC REAGENTS

To increase the magnetic properties of minerals with the magnetic reagent technology, it is necessary to understand the fundamental adsorption mechanisms of magnetic reagents on the minerals and organics in coal. The most common minerals associated with coal are quartz, kaolinite, calcite, and pyrite. These minerals and low ash coal fragments were utilized in this study. Factors affecting the adsorption of magnetic reagents were believed to be similar to those affecting the adsorption of surfactants. To verify this assumption, parameters affecting the adsorption of surfactants, which include pH, types and dosages of reagent, activators and depressants, were investigated in this study.

3.1 Experimental Procedures

Research grade mineral samples of pyrite, kaolinite, calcite, and quartz were acquired and prepared for experiments in this study. Since minerals usually occur in coal as disseminants or banded, loosely bound sediments at sizes of -325 mesh for the individual mineral grains, each mineral sample was prepared by grinding to -325 mesh. The grinding was carried out with a ceramic puck mill to avoid magnetic contamination, except kaolinite which was prepared with a blender. To eliminate oxidation problems, pyrite samples were washed with dilute hydrochloric acid and dried before grinding. The grinding product was stored under a nitrogen atmosphere.

A bituminous coal of the Ohio Lower Kittanning seam with a low ash content (about 6%) was utilized to compare with the minerals on the interactions with the magnetizing reagents. The coal was ground to the same size as the minerals.

The magnetic susceptibility of each mineral and coal sample was measured with a Johnson & Matthey magnetic susceptibility balance at 2 kilogauss. The results were: 0.44×10^{-6} cgs/g for quartz, 4.84×10^{-6} cgs/g for kaolinite, 3.94×10^{-6} cgs/g for calcite, 1.46×10^{-6} cgs/g for pyrite, and 1.31×10^{-6} cgs/g for coal.

The adsorption study was carried out with standard procedures for each test. In each test, a gram of a mineral powder was slurried in 30 ml of water. Sodium hydroxide and hydrochloric acid were utilized to adjust pH. The salinity of the water was maintained at 2×10^{-3} molar of sodium chloride. A magnetic reagent was added at a dosage equivalent to $0.002 \text{ g}^{\text{magnetic}}$ per gram of mineral. After three minutes of stirring to condition the mineral and magnetic reagent, the mineral particles were filtered, dried, and measured for magnetic susceptibility. The degree of adsorption for the magnetic reagent on a mineral was determined by the amount of magnetic susceptibility increase.

The use of mineral activators and depressants to aid the adsorption of the magnetic reagents was investigated by using inorganic surface modifying agents. Two cationic salts, ferrous sulfate and calcium chloride, and two anionic salts, sodium silicate and sodium tripolyphosphate (STPP), were selected. The

dosage of salt was maintained at 300 ppm in solution for each test. These surface modifying chemicals were added to the mineral slurry at various pH levels before the addition of the magnetic reagent. Two minutes were allowed for the conditioning of the minerals with the surface modifying chemicals.

3.2 Anionic Magnetic Reagents

The adsorption of anionic magnetic reagents on minerals at various pH level was investigated first. The pH was singled out as a major parameter because pH has a strong effect on the adsorption of surfactants. The surface charge and surface species are affected by pH, as are the solubility and stability of the surfactants. The dissolved species in water modify the mineral surface and surfactants at various pH levels as well.

The anionic magnetic reagents for this study included the use of various surfactants for the outer layer. Each outer layer surfactant was regarded as the one responsible for coupling minerals. The reagents included MR-30 (sodium oleate), MR-31 (sodium lauryl sulfate), MR-33 (organic phosphate ester), MR-35 (sodium dioctyl sulfonsuccinate), MR-37 (sodium methyl oleyl taurate), and MR-83 (potassium butyl ricinoleate xanthate). The chemical name indicated above for each magnetic reagent was the outer layer surfactant.

The adsorptions of MR-30 (sodium oleate) on the four minerals are shown in Figure 2. Apparently, calcite and kaolinite have a strong adsorption of this magnetic reagent. Quartz and pyrite have

very little adsorption of this reagent, except at pH 3. The other exception is the small amount of adsorption for quartz at pH 11.

The adsorptions of MR-31 (sodium lauryl sulfate) on the four minerals are shown in Figure 3. Strong adsorptions on calcite and kaolinite were observed again. Weak adsorptions of MR-31 on quartz and pyrite, including at pH 3, were also observed. A small peak at pH 11 for the adsorption on quartz indicated an unexpected trend.

Figure 4 illustrates the adsorption of various anionic magnetic reagents on calcite. The magnetic susceptibility of calcite was consistently increased from 3.94×10^{-6} cgs/g to approximately 40×10^{-6} cgs/g by the tested reagents. This phenomenon agrees with the common knowledge for the adsorption of an anionic surfactant on calcite.

Figure 5 explains the adsorption of various anionic magnetic reagents on quartz. It is known that quartz does not adsorb anionic surfactants. The results of our study showed that quartz generally does not adsorb anionic magnetic reagents, either, however, adsorption at pH 3 and 11 may occur.

Figure 6 demonstrates the adsorption of anionic magnetic reagents on kaolinite. The adsorption of surfactants on kaolinite has rarely been studied, although it is usually suggested that anionic surfactants have difficulties floating kaolinite. This study showed that the anionic magnetic reagents were strongly adsorbed on kaolinite. A possible explanation is that kaolinite adsorbs anionic surfactants but does not become hydrophobic enough to float because of its high surface area.

The adsorption of anionic magnetic reagents on pyrite is complex because pyrite may have various surface properties depending on oxidation. Figure 7 shows the adsorption of MR-30 (sodium oleate) on pyrite under three conditions. One utilized fine (-325 mesh) pyrite without hydrochloric acid washing. The second condition involved the washing of pyrite with hydrochloric acid then using the mineral particles immediately after. The third condition included washing pyrite with hydrochloric acid then drying the pyrite in an oven before use. The first condition yielded strong adsorption of MR-30. The second conditions caused very weak adsorption, while the third condition favored the adsorption only at pH 7 or below.

A possible explanation for this is that unwashed pyrite has ferrous sulfate formed on its surface due to oxidation. When ferrous sulfate is dissolved in water, it acts as an activator for the adsorption of MR-30. Acid washed pyrite may have a layer of elemental sulfur on its surface, which makes the adsorption of anionic magnetic reagents very difficult. Oven drying the pyrite may have evaporated the elemental sulfur and changed the pyrite surface to iron oxides. Iron oxides have a positive surface charge at low pH levels and, thus, can adsorb MR-30.

Figure 8 shows the adsorption of MR-31 (sodium lauryl sulfate) on pyrite under the three conditions. Very similar results were obtained. Other anionic magnetic reagents examined in this study also showed a consistent trend. Detailed data were shown in the Phase I report.

3.3 Cationic Magnetic Reagents

Cationic surfactants include various functional groups such as primary, secondary, tertiary, and quaternary amines and their derivatives such as diamines, diquaternary amines, and ethoxylated amines. The adsorption of amines on minerals usually has poor selectivity.

The adsorption of MR-1 (primary amine) on minerals is illustrated in Figure 9. It is obvious that all the minerals investigated adsorbed this magnetic reagent very well. Replacing MR-1 with MR-3 (quaternary amine), MR-4 (diamine), MR-19 (diquaternary amine), MR-20 (ethoxylated quaternary amine), and MR-81 (tertiary amine), showed that the magnetic susceptibility of each mineral was still strongly enhanced. A summary of the results is shown in Table 1, which lists the magnetic susceptibility increase of minerals by various cationic magnetic reagents at pH 7.

Unlike the anionic magnetic reagents, cationic magnetic reagents show less sensitivity to the oxidation of pyrite. As demonstrated in Figure 10, washing pyrite with hydrochloric acid then drying caused only limited fluctuations in the adsorption of MR-1 (primary amine) on pyrite. Removing oxidized products, such as ferrous sulfate, by hydrochloric acid, however, does have some positive effect on the adsorption.

3.4 Nonionic Magnetic Reagents

The adsorption of MR-45 (polyoxyethylene-4 lauryl ether) on various minerals is shown in Figure 11. Calcite and kaolinite adsorbed MR-45 very well. Quartz and pyrite, however, could only

adsorb MR-45 at pH of 5 or below. Generally, the adsorption of MR-45 was very similar to that of the anionic magnetic reagents. The difference occurred at pH 5. At this pH, quartz and pyrite could still adsorb nonionic magnetic reagents but not the anionic magnetic reagents. An explanation is that the nonionic surfactant may form hydrogen bonds with these minerals.

The oxidation state of pyrite again showed a strong impact on the adsorption of MR-45. As shown in Figure 12, pyrite washed with hydrochloric acid adsorbed MR-45 at a pH of 5 or below. After drying the washed pyrite in an oven, strong adsorption was observed even at pH 7. Without washing, adsorption of MR-45 occurred at all pH levels.

3.5 Activators and Depressants

The modifications in the surface charge and surface species of minerals in water by inorganic salts are well known. The adsorption of multivalent cations will increase the positive charge of minerals. On the other hand, the adsorption of multivalent anions will increase the negative charge of minerals. The surface charge can influence the adsorption of surfactants through the electrokinetic interactions. In addition, the adsorption of modifiers may be pH dependent. The species formed on the surface of the minerals may also vary with pH. The chemical force affecting the adsorption is species dependent.

Two cationic salts, ferrous sulfate and calcium chloride, and two anionic salts, sodium silicate and sodium tripolyphosphate (STPP), were studied for their effects on the adsorption of

magnetic reagents. The relationship between the anionic MR-30 (sodium oleate) and calcite is shown in Figure 13. When calcite was first conditioned with ferrous sulfate and calcium chloride, strong enhancement of magnetic susceptibility through the adsorption of MR-30 was observed. The effect of calcium was even stronger than the iron effect. On the other hand, anionic salts show depressing effects on anionic MR-30. Sodium tripolyphosphate, for example, almost completely depressed the adsorption of MR-30 on calcite at pH 9 and 11. Sodium silicate is known to have no adsorption on calcite. Our results also show that sodium silicate had very little effect on the adsorption of MR-30 on calcite.

The adsorption of MR-30 on quartz in the presence of surface modifiers is shown in Figure 14. Quartz would not adsorb MR-30 without surface modifiers. Sodium silicate and sodium tripolyphosphate had no effects either, however, the presence of ferrous sulfate and calcium chloride caused strong adsorption of MR-30 on quartz. The activation effect of the multivalent cation on the adsorption of the anionic magnetic reagent was obvious.

The interaction of cationic magnetic reagents and minerals is illustrated in Figure 15. In this example, calcite adsorbed MR-3 (quarternary amine) very well without the presence of any surface modifiers. When ferrous sulfate was added, the adsorption of MR-3 was depressed by the cations. However, calcium ions did not cause any depressing. Anionic salts, such as sodium silicate and sodium tripolyphosphate, were predicted as activators for this adsorption due to electrokinetic interactions. The results show that they did

cause a small amount of activations for the adsorption of MR-3 on calcite.

The reactions between MR-45 (polyoxyethylene 4 lauryl ether) and calcite in the presence of surface modifiers are utilized to discuss the cases of nonionic magnetic reagents. This reagent adsorbed well on calcite originally. When ferrous sulfate and calcium chloride were present, strong activation occurred. On the other hand, sodium silicate and sodium tripolyphosphate caused strong depressing effects, especially at high pH levels. At high pH levels, these anionic inorganic salts dissociate strongly.

3.6 Adsorptions on Coal

The adsorption of anionic, cationic, and nonionic magnetic reagents on coal is shown in Figure 16. MR-30 (sodium oleate), MR-1 (primary amine), and MR-45 (ethoxylated lauric ether) are utilized as the examples. Strong adsorption could be obtained in all cases.

Inorganic salts also showed strong effects for the adsorption of magnetic reagents on coal. Figure 17 illustrates the adsorption of MR-30 (sodium oleate) on coal in the presence of various salts. Ferrous sulfate and calcium chloride showed strong activation effects. Sodium silicate and sodium tripolyphosphate, on the other hand, showed strong depressing effects. Based on these results, coal was activated and depressed following the same principles that were applicable to the minerals.

The interactions of the cationic MR-1 (primary amine acetate) with coal under the influence of inorganic salts are shown in Figure 18. Strong adsorption occurred in almost every case. Ferrous

sulfate and calcium chloride had no depressing effect at all, sodium silicate did not activate the adsorption, either; on the contrary, a depressing effect was observed at pH 11. Sodium tripolyphosphate showed strong depressing effects, as well. Probably these anionic salts destabilized the cationic magnetic reagent.

The nonionic MR-45 (ethoxylated lauric ether), again, behaved similarly to the anionic magnetic reagents in the presence of inorganic surface modifiers. As shown in Figure 19, ferrous sulfate and calcium chloride had some activation effects. Sodium silicate and sodium tripolyphosphate had depressing effects, especially at high pH levels.

3.7 Adsorption Mechanisms

The fundamental chemistry of adsorption involves four adsorption mechanisms. They are: a) covalent bonding force, b) electrostatic bonding force, c) hydrogen bonding force, and d) van der Waals force. The results of this study demonstrated that these mechanisms are responsible for the adsorption of magnetic reagents as well.

The adsorption of MR-30 on calcite is a clear example of the covalent bonding force. MR-30 has sodium oleate as the outer layer surfactant. It is well known that carboxylic acid forms covalent bonding with calcite to result in a chemisorption. The strong adsorption of MR-30 on calcite obviously demonstrated the affinity.

The interaction between MR-30 and quartz is a typical example of the electrostatic mechanism. Quartz has no chemical bonding with

the carboxylic acids, but the surface charge on quartz may affect the interactions. The isoelectric point of quartz is usually at a pH of between 2 and 3. At a pH below the isoelectric point, quartz carries a positive charge. At pH above the isoelectric point, quartz has negative charges. Thus, quartz could hardly adsorb any anionic MR-30 at high pH levels. Adsorption was observed at pH 3, which is close to the isoelectric point of quartz.

The hydrogen bonding mechanism is demonstrated by the adsorptions of MR-45 on quartz. MR-45 has ethoxylated lauric ether as the outer layer surfactant. Ethoxylated compounds are known to have an affinity with quartz by forming hydrogen bonding through their hydroxyl groups. The adsorption of MR-45 at pH up to 7 agreed very well with this affinity.

The strong adsorption of various magnetic reagents on kaolinite was probably achieved through the van der Waals force. Kaolin characteristically has a high surface area. The magnetic reagents are a composite of a magnetic nucleus with two layers of surfactants, which can be considered a macromolecule. Thus, the van der Waals force may be strong enough to result in a large amount of physical adsorption when the electrokinetic force is not strongly repulsive.

CHAPTER 4

MAGNETIC REAGENT APPLICATION PARAMETERS

There are a few parameters of the magnetic reagents which will affect the magnetic enhancement of minerals. In this chapter, some of the parameters are studied. The first parameter is the dosage of the magnetic reagent. It is known that the amount of adsorption is related to the concentration of surfactants. The applicability of this kind of relationship between minerals and magnetic reagents was explored. The second parameter is the shelf life of magnetic reagents. It is important to know if the property of the magnetic reagents will change with long term storage. The third parameter is the optimization of the magnetic reagent. Magnetic reagents are composites of a magnetic nucleus and surfactants. It is necessary to know if the magnetic nucleus has an optimal particle size and what is the relation between the magnetic nucleus particle size and the surfactant quantities. Magnetic separation performance of enhanced mineral particles was evaluated to determine the appropriate formulation of magnetic reagents for this application.

4.1 Reagent Dosage

Experiments were carried out to investigate the relationship between magnetic reagent dosage and magnetic enhancement of minerals. Three reagents, MR-1 (primary amine acetate), MR-30 (sodium oleate) and MR-45 (polyoxyethylene 4 lauryl ether), were examined. Each reagent was conditioned with minerals of -325 mesh particle size at various dosages in water. After 3 minutes of

stirring for conditioning, the minerals particles were filtered, dried, and measured for their magnetic susceptibilities. The detailed procedure for this type of standard mineral-reagent tests was described in Chapter 3.

Figure 20 shows the effects of MR-1 dosage on the magnetic enhancement of calcite, quartz, kaolinite, and pyrite. Generally, the magnetic susceptibility of each mineral increased with the increase in reagent dosage. At dosages up to 0.002 grams reagent (on the basis of magnetite content) per gram of mineral, the adsorbability was about the same for all of these minerals. Magnetic susceptibility was increased from $0.44\text{--}4.84 \times 10^{-6}$ cgsemu/g to approximately 50×10^{-6} cgsemu/g. At higher dosages, the differences in adsorbability gradually became significant. Quartz had the strongest adsorbability. Kaolinite also maintained strong adsorbability throughout the range of testing, which had a maximum dosage of 0.01 grams magnetic reagent per gram of mineral. The adsorption on calcite got slower at dosages above 0.005 grams per gram of mineral. For pyrite, the adsorption was obviously saturated at dosages above the 0.005 grams level.

The interactions of MR-45 with minerals at various magnetic reagent dosages are shown in Figure 21. Kaolinite had the strongest adsorbability with this reagent and showed a linear relationship throughout the range of study. The other three minerals reached saturation at dosages above 0.005 grams of reagent per gram of mineral. Among the three minerals, the adsorbability had the sequence of calcite > pyrite > quartz. However, it should be noted

that the pyrite was not washed with hydrochloric acid immediately before the testing and ferrous sulfate was believed to be present which resulted in activation effects.

Only calcite was tested for the MR-30 dosage study. Previous results had shown that quartz and pyrite did not adsorb this magnetic reagent. The range of dosage for this study was extended up to 0.02 grams of reagent per gram of mineral. As shown in Figure 22, a linear, strong adsorption relationship was observed. At 0.02 grams reagent dosage, the magnetic susceptibility of calcite was increased from 3.94×10^{-6} cgsemu/g to 430×10^{-6} cgsemu/g. The chemisorption mechanism was believed to be responsible for this strong adsorption.

4.2 Shelf Life

Three magnetic reagents, the cationic MR-1, anionic MR-30, and nonionic MR-45, were examined for their activities at various shelf ages. The activities were determined by the amount of magnetic enhancement on calcite after conditioning with the magnetic reagent. The conditioning procedures and magnetic susceptibility measurements remained the same as those described earlier. The test matrix included variations in pH to assure the validity of the interpretations.

Three shelf ages were investigated: fresh, 7 months, and 10 months. The results are shown in Table 2. The extent of the magnetic enhancement was generally consistent at various ages. Although we cannot rule out small variations due to experimental error, there seems to be a tendency for a slight increase in

magnetic enhancement with aging. The oxidation of magnetite with aging in the magnetic reagent which results in a better stoichiometric ferrous and ferric ratio in magnetite may be an explanation. Nevertheless, this study shows that magnetic reagents are basically stable for long term storage.

4.3 Magnetite Particle Size and Surfactant Consumption

One of the major concerns for studying appropriate magnetite particle size in magnetic reagents is to reduce the surfactant consumption. With an increase in magnetite particle size, it is possible to decrease the surface area to mass ratio. If the amount of surfactant built up on the magnetite to yield a magnetic reagent is proportional to the surface area, the amount of surfactant consumption can then be reduced. Since the surfactant cost may constitute a major portion of the magnetic reagent cost, there is a strong economic incentive to increase the magnetite particle size. However, the increase in magnetite particle size may reduce the number of magnetite particles in a magnetic reagent at the same weight of magnetite. Subsequently, the collision rate between the magnetic reagent and the mineral particles may be reduced. Inhomogeneous adsorption of the magnetic reagent on mineral particles may result, which can make magnetic collection incomplete.

MR-1 and MR-30 were studied for the effects of magnetite particle size. For each reagent, eight varieties with different magnetite particle size were made. Each variety was designated with a number such as MR-1-11, where 11 corresponds to a particular

particle size as shown in Table 3. The particle sizes of magnetite estimated under a transmission electron microscope, ranged from approximately 50 to 250 angstroms.

Table 3 also shows the amounts of surfactant required to produce the magnetic reagents at various magnetite particle sizes. The amount of surfactant varied with the kind of magnetic reagent and the magnetite particle sizes. Using 100 angstrom magnetite as the reference for each magnetic reagent, the amount of surfactant required for MR-1 and MR-30 was 0.591 and 0.569 grams, respectively. The variations were related to the molecular weight, structure, hydrophobicity, and adsorption density of the surfactant. With the increase of magnetite particle size, the amount of surfactant required for each magnetic reagent gradually decreased. For MR-1, the minimum surfactant consumption was 0.295 grams, occurring at approximately 200 angstrom magnetite particle size. The minimum surfactant consumption for MR-30 was 0.262 grams, also occurring at about 200 angstrom magnetite particle size. Thus, a significant cost reduction in magnetic reagent production can be obtained with the increase of magnetite size.

4.4 Collection of Magnetic Enhanced Minerals

To determine whether the magnetite size would change the magnetic separation performance, a series of magnetic separation tests was conducted. In each test, ten grams of calcite were conditioned with a magnetizing reagent at pH 7 for two minutes. Then the slurry was fed through a magnetic separator with a ball matrix. The speed valve control was fully open to allow the maximum

flow speed (near free falling). The magnetic and nonmagnetic fractions were then collected, filtered, dried, and weighed to determine the weight percentage of calcite reporting to the magnetic fraction.

The magnetic field strengths for the separation tests were selected at 3.5 and 5 kilogauss. The two types of magnetizing reagents (MR-1 and MR-30) with eight different magnetite sizes for each type were evaluated. The reagent dosage varied from 2 to 12 pounds of magnetite per ton of calcite. The results are shown in Tables 4 and 5 for each type of magnetizing reagent. As the magnetizing reagent dosage increased, the magnetic collection efficiency also increased, at the same magnetic field strengths. The minimum dosage for satisfactory magnetic recovery varied with the type of reagent, ranging from 4 to 8 pounds per ton. However, all of the reagents showed that magnetic recovery decreases with the increase in magnetite size at the same dosage of magnetite and magnetic field strength. There are two possibilities to explain this phenomena. One is an inhomogeneous adsorption of the magnetizing reagent due to the decrease in the number of magnetite particles. The other is the decrease of the adsorption efficiency for large magnetite particles. There is no direct evidence at this stage to determine which one is the major cause.

The cost of this approach is obviously associated with the magnetic field strength and the reagent consumption. Although the increase in magnetite size can reduce the surfactant consumption, the magnetic field strength and the total magnetite dosage may have

to be increased to achieve a satisfactory magnetic recovery at large magnetite sizes. The economics are thus complicated and rely on the individual systems. Since the reference magnetic reagent, which utilized 100 angstrom magnetite, showed the best separation efficiency, the rest of the study was based on this magnetite particle size.

CHAPTER 5

COAL PREPARATION AND CHARACTERIZATION

5.1 Coal Preparation

Three coals were selected to examine the application of magnetic reagent technology for coal cleaning. They were Illinois No. 6, Ohio Lower Kittanning, and West Virginia Pocahontas seams. Each 400 pound sample was cut from freshly mined 4" x 10" coal and shipped in sealed containers.

The preparation procedures and weight splits for each coal can be found in Figure 23 through Figure 25. The as received sample was blended three times, then coned and quartered to produce a reserve sample and a sample which was crushed to 3/4-inch. The minus 3/4-inch sample was riffled to yield a fraction for reduction to minus 48 mesh and a second fraction for screening at 6 mesh and 48 mesh. The crushed minus 48 mesh material was then split into a reserve sample, a head sample, and a testing sample (300 grams per charge). The other minus 3/4-inch fraction was screened as indicated above to make a 3/4-inch by 6 mesh fraction for heavy media testing, a 6 mesh by 48 mesh fraction for tabling and a 48 mesh by 0 fraction for flotation. All samples were stored in plastic bags which were filled and sealed in an argon atmosphere. In addition, the plastic bags were stored in either 55-gallon drums or 5-gallon plastic pails which were evacuated then filled with argon. To insure low levels of oxygen in the storage containers, each was evacuated to 15-ins. of Hg and filled with argon four times.

Flowsheets for the heavy media, tabling, and flotation tests on the three coals are shown in Figures 26 through 28, respectively. The heavy media concentration was done in an Erickson 10-inch cone using magnetite media at gravities of 1.3 and 2.0. Concentration of the 6 mesh by 48 mesh was done on a Deister No. 15S laboratory concentrating table with a coarse deck. All of the flotation work was done in a Wemco laboratory flotation machine at 12% solids. A combination of 1/3 Dowfroth 250 and 2/3 No. 2 fuel oil by weight was utilized as the frother/collector.

The data on weight splits, assays of the products, and a comparison of calculated and assayed head analysis are also shown in Figure 26 through Figure 28. The heavy media concentration tests reduced the ash contents of the Illinois No. 6, Lower Kittanning and Pocahontas coals from 19.17%, 4.13% and 43.03% to 4.79%, 2.16% and 3.32%, respectively, at 1.3 specific gravity. The sink fractions of the three coals at 2.0 specific gravity contained 62 to 90% ash. The middlings, which had specific gravities between 1.3 and 2.0, had ash contents of 22.17%, 14.61% and 21.63%, respectively, for the three coals.

The tabling process reduced the ash content of the three coals from 19.39%, 7.89%, and 16.27% to 6.69%, 2.33%, and 4.11%, respectively. The tabling rejects of the three coals had ash contents in the range of 25% to 50%. Flotation concentrates had the ash contents of 10.61%, 9.97%, and 5.58%, respectively, for the three coals. The flotation tailings contained ash in the range of 63% to 78%.

Pyritic sulfur was reduced to below 0.5% by the heavy media and tabling processes. Flotation was not as efficient as these processes in pyritic sulfur removal.

5.2 Characterization

5.2.1 Coal Analysis

The head samples of each coal were analyzed for moisture, volatile matter, fixed carbon, ash, total sulfur, sulfate sulfur, pyritic sulfur, and heat of combustion. Table 6 shows the data for the three coals.

5.2.2 Grinding

The grindability of each coal was established with a standard procedure. The test was conducted using a laboratory stainless steel rod mill (7" I.D. x 9" long). About 300 grams of minus 48 mesh coal at 25% solids content was ground in each test. Soda ash (2 lb/ton) and sodium tripolyphosphate (1 lb/ton) was added for dispersion. The pH was set at 9 by NaOH or HCl. Grinding times were 20, 40, 60, and 80 minutes and the size distributions were determined with a Microtrac. The results are shown in Figure 29 through Figure 31.

5.2.3 Washability

The washability was carried out with the heavy liquid tests. Commercially available CENTRIGRAV (American Minechem Corp.) heavy liquids were utilized. A high speed centrifuge was employed to enhance the separation of sink and float products at specific gravities ranging from 1.3 to 1.9. An ultrasonic bath was applied to aid the dispersion. Surfactants were also added to insure the

wetting and dispersion of particles. The samples were first dispersed utilizing the ultrasonic bath for 45 minutes, centrifuged for 15 minutes at 1500 rpm, then bathed with ultrasonics again for 40 minutes, and finally centrifuged for 15 minutes at 4500 rpm. The results of the -48, -100, -200, -325, and -500 mesh samples are plotted on Figures 32, 33, 34, 35, and 36, respectively.

5.2.4 Mineralogy

The mineralogy was performed using x-ray diffraction methods. The sink material at 1.9 density from the -48 mesh sample was utilized. The diffraction patterns of the three coals are shown in Figures 37 through 39. The minerals corresponding to the diffraction peaks were identified and are listed on these figures. The major minerals in the Illinois No. 6 seam were quartz, clays, pyrite and calcite. Clays included kaolinite, chlorite and muscovite. The major minerals in the Lower Kittanning seam were quartz, pyrite, feldspar, hematite, and chlorite. The Pocahontas seam had the major minerals of quartz, muscovite, chlorite, kaolinite, feldspar, calcite, with a little siderite and gypsum (anhydrite). Pyrite was rare.

A petrographic examination was performed under optical and scanning electron microscopes. Polished mounts of each coal at -48 mesh were prepared and examined to identify macerals and pyrite and to determine their distributions.

The results of maceral distributions are shown in Table 7. All of the three coals were very high in vitrinite content (about 92%). Inertinite and exinite contents were all lower than 4%. Therefore,

it was not anticipated that macerals would have a significant influence on the separation in this study.

The occurrence frequencies of pyrite at various grain sizes are shown in Figure 40 through Figure 42. Calculated volume (equivalent to weight) distributions of pyrite at various sizes are demonstrated in Table 8. Illinois No. 6 contained large amounts of fine pyrite, about 25% were smaller than 5 microns, making pyritic sulfur removal difficult. Lower Kittanning had about 15% pyrite in sizes smaller than 5 microns. Pocahontas is a low sulfur coal and its pyrite grains were mostly in larger particle sizes. These two coals have better pyrite rejectability than the Illinois No. 6.

CHAPTER 6

COAL CLEANING WITH MAGNETIC REAGENTS

6.1 Chemistry for Coal Cleaning with Magnetic Reagents

A fundamental study for the adsorption of magnetic reagents on minerals and coals showed that only the cationic magnetic reagents can magnetize all the mineral matters in coal. Magnetic reagents of anionic and nonionic properties were not effective in magnetizing all minerals at the same time, unless multivalent cations such as calcium and iron were present to activate the minerals. However, these cations activate coal as well. Therefore, the use of anionic and nonionic magnetic reagents can provide only limited magnetic enhancement.

Cationic magnetic reagents can be adsorbed on coal as well as on minerals. To aid in the selectivity, coal will have to be depressed. The use of anionic depressants is usually ineffective because the negative charge generated by anionic depressants on coal will result in a strong electrokinetic reaction with the cationic magnetic reagent. Cationic depressants are usually inapplicable because they may depress both coal and minerals at the same time. Nonionic depressants appear to be a logical choice because they may have stronger affinity to coals than to minerals through the hydrophobic interaction, although excess nonionic surfactant may still depress some minerals through the hydrogen bonding mechanism.

Experiments were carried out to investigate the possibility of using nonionic surfactants for coal depressing and cationic magnetic reagents for mineral enhancement. The nonionic surfactant used in this study was Brij 700. This surfactant is a polyoxyethylene (100) stearyl ether. The stearyl side is the hydrophobic part responsible for the adsorption on coal. A hundred units of oxyethylene makes a long hydrophilic chain to encapsulate coal from interaction with other reagents. The HLB (hydrophile-lipophile balance) value of this surfactant is 18.8. The magnetic reagent for mineral enhancement was MR-217, which utilizes diamine as the bridging surfactant. Diamine has the strongest cationic properties of various amines. This reagent combination was found effective for selective magnetic enhancement of minerals from coal and was utilized for the coal cleaning study.

6.2 Coal Cleaning at -48 Mesh

6.2.1 Application to ROM coal

The application of the magnetic reagent approach on coal cleaning was first examined at -48 mesh particle size. About 20 grams of run-of-mine (ROM) coal were utilized for each test. After slurring the coal in 200 ml tap water, reagent at the desired dosages were added. Conditioning time was two to three minutes for each reagent. Then the slurry was transferred to the magnetic separation device. The separation was conducted by two runs on a grooved plate filter at 18 kilogauss and 18 cm/sec slurry velocity (about 1 second retention time for each run) and three runs on a screen filter at 5 kilogauss and 5.7 cm/sec slurry

velocity (about 3 seconds retention time per run). The repeated separation was necessary to understand the retention time requirements. The screen filter was composed of a pack of screens with the screen plane parallel to the flow direction. Each screen had wires of 0.64 mm diameter with square mesh openings of 6 mm width. The selection of optimum separator and reagent conditions will be discussed in the next chapter.

Figure 43 shows the results of coal cleaning with magnetic enhancement at -48 mesh. The ash content of Illinois No. 6 at -48 mesh was reduced from 21.24% to 6.50% (82.45% ash reduction) at 57.36% yield of coal (68.10% coal recovery, which is usually very close to BTU recovery). For the Ohio Lower Kittanning coal, the ash content was reduced from 6.33% to 2.26% (72.12% ash reduction) at 78.10% coal yield (81.49% coal recovery). Pocahontas ROM coal contained very high ash, 30.94%. The magnetic reagent approach brought the ash content down to 4.93% (92.12% ash reduction) at 49.03% yield (67.50% coal recovery). The increase of coal recovery was inevitably accompanied by the increase of ash content, as shown in the Figure.

Pyritic sulfur was also effectively reduced with the magnetizing reagent approach. The pyritic sulfur results are included in Figure 43. The pyritic sulfur content in the concentrate of Illinois No. 6 was 0.79%, which is a 71% reduction from the original 1.56% pyritic sulfur. Ohio Lower Kittanning coal had 0.27% pyritic sulfur content in the concentrate, or about an 85% reduction from the original 1.39% pyritic sulfur. The

Pocahontas coal contained 0.15% pyritic sulfur in the concentrate, equivalent to an 83% reduction from the original 0.43% pyritic sulfur.

Optical examination of the separation products showed that some very coarse pyrite (larger than 150 μm) and very fine clays (a few microns in size) were misplaced in the coal concentrate. Although these misplaced particles were magnetic, they were difficult to collect on the screen type magnetic filter (designed for medium size particles). The use of a gravitational method to remove coarse pyrite prior to magnetic separation or pumping slurry upward through the separator may help in reducing the coarse pyrite problem. Mechanical entrapment of nonmagnetic coal in the magnetic fraction was also common, this reduces the coal recovery. Improvement of coal recovery is possible with better magnetic separator design.

6.2.2 Application to Flotation Concentrate

Coal concentrate obtained from the froth flotation circuit was conditioned with fuel oil and MIBC. It was shown that the magnetic reagent approach can also be applied to the flotation concentrate to enhance the magnetic susceptibility of minerals. The reagent conditioning and magnetic separation for this approach followed the same procedures as described for the ROM coal cleaning study.

The results of separation for froth flotation concentrates (after rougher and two cleaners) are shown in Figure 44 through Figure 46 for the three coal samples. The results of flotation with repeated cleaning flotation stages were also included in these

Figures for comparison. The magnetic reagent obviously performs better than, or, as well as the froth flotation approach on the cleaning of flotation concentrate at -48 mesh. The flotation concentrate feed at -48 mesh contained few liberated minerals. Without further grinding, the cleaning had to rely on the ability of the magnetic separation to remove the unliberated minerals. Both approaches are fundamentally controlled by the surface of particles. However, froth flotation is controlled by the surface of coal whereas the magnetic reagent is controlled by the surface of the associated minerals. The results indicate that the magnetic reagent approach may have an advantage on cleaning unliberated minerals.

Pyritic sulfur contents for products from the two approaches are also included in Figure 44 through Figure 46. The magnetic reagent approach apparently showed a better pyrite cleaning ability than the flotation approach for all three coals. For example, more than 12% additional yield of coal was obtained for Illinois No. 6 with the magnetic reagent when the concentrate pyritic sulfur content was about 0.65% for both approaches.

The magnetic reagent selected for this study was a cationic diamine type reagent. It did not show strong affinity to calcite, but it was undoubtedly favorable to the adsorption on pyrite and silicates. The separation results agreed with this strong adsorption tendency. Illinois No. 6 coal contained a large amount of unliberated pyrite, as shown in the characterization study. Therefore, the magnetizing reagent approach was most successful.

More ash at the same pyrite content was probably due to the large amount of calcite in this coal, as suggested in characterization results. Calcite is a good sulfur adsorber during combustion and, therefore, will be advantageous. Pocahontas coal contained very little pyrite and a very small fraction of unliberated minerals, also shown in the characterization study. For this sample, both approaches were equally successful on ash reduction although the magnetic reagent approach was still better on pyrite cleaning.

6.3 Fine Coal Cleaning

6.3.1 Illinois No. 6 Fine Coal Cleaning

The ROM Illinois No. 6 coal was wet ground to various sizes with tap water. Four sizes were included in the tests. They were 90% passing 500, 325, 200, and 100 mesh, respectively. Each ground coal was conditioned with Brij 700 hydrophillic modifier and diamine magnetic reagent. Magnetic separation was conducted at 20 kilogauss with coarse steel wool utilized as the matrix. Slurry was gravitationally fed through the separator without velocity control (near free falling velocity). Repeated separations were utilized to obtain various retention times of separation. The retention time for each run was about 1 second.

Figure 47 illustrates the separation results. Ash content was reduced from about 22% to 3.3% at 90% passing 500 mesh, which is equivalent to about 91% ash removal. Coal yield was about 57%, or about 70% BTU recovery. At 90% passing 325 mesh, ash was reduced to 3.6% with 52% yield (63% BTU recovery). For the coal ground to 90%

passing 200 mesh, the ash content was reduced to 4.2% with 59% yield (69% BTU recovery). Tests on the 90% passing 100 mesh coal showed that the ash content was reduced to 4.2% as well with only 39% yield (47% BTU recovery).

The ash reduction results show that the separation efficiency generally increased with the finer grinding. The improvement of liberation with grinding was the major reason. However, the mechanical entrapment of coal particles at -100 mesh by the coarse wool matrix of the magnetic separator may be significant in causing the extraordinarily low recovery.

A critical evaluation of the magnetic reagent approach should also rely on the capability for removing pyritic sulfur. Figure 48 demonstrates the pyritic sulfur rejection results at various particle sizes. At 90% passing 500 mesh, pyritic sulfur was reduced from 2.2% to 0.28%, about 93.28% pyritic sulfur was removed. For total sulfur, the reduction was from 3.38% to 1.70% (73.62% rejection). The separation efficiency (BTU recovery - (100-pyritic sulfur rejection)) was 61.7%.

The results at 90% passing 325 mesh show that pyritic sulfur was reduced to 0.34% with a total sulfur content of 1.97%. The separation efficiency was 55.09%. At 90% passing 200 mesh, pyritic sulfur content was reduced to 0.51% with a total sulfur content of 2.23%. Separation efficiency was 60.63%. The lack of liberation or the mechanical entrapment at -100 mesh caused significant problems. Although pyritic sulfur was still reduced to 0.69% with 2.29% total sulfur, the separation efficiency was only 41.90%.

6.3.2 Lower Kittanning Fine Coal Cleaning

The Lower Kittanning ROM coal was processed following the same procedures for the cleaning of Illinois No. 6 coal. Figure 49 shows the results of the magnetic reagent approach for ash cleaning at various particle sizes. Figure 50 illustrates the pyritic sulfur rejection results. At 90% passing 500 mesh, the ash content was reduced from 6.71% to 1.56%, the pyritic sulfur was reduced from 1.76% to 0.48%, and the total sulfur content was reduced from 2.27% to 1.02%. Coal yield was 80.26% and BTU recovery was 85.03%. The separation efficiency was 63.10%, while the ash, pyritic sulfur, and total sulfur rejections were 81.33%, 78.07%, and 63.97%, respectively.

At 90% passing 325 mesh, ash content was reduced to 1.92%, pyritic sulfur was reduced to 0.41%, with a total sulfur content of 1.12%. Coal yield was 80.05% with a BTU recovery of 84.93%. The rejection rates of ash, pyritic sulfur, and total sulfur were 77.22%, 80.85%, and 62.70%, respectively. Coal separation efficiency was 65.77%.

Processing at 90% passing 200 mesh resulted in an ash content reduced to 1.93%. Pyritic sulfur was reduced to 0.39%, while total sulfur was reduced to 1.16%. Coal yield was 79.28% with a BTU recovery of 84.07%. The rejection rates of ash, pyritic sulfur and total sulfur were 77.57%, 80.40%, and 65.91%, respectively. The separation efficiency was 64.47%.

Tests at 90% passing 100 mesh resulted in the reduction of ash content to 2.29%, while pyritic sulfur was reduced to 0.37%. Total

sulfur was reduced to 1.16%. Coal yield was 78.44% with BTU recovery at 81.63%. The rejection rates of ash, pyritic sulfur, and total sulfur were 69.78%, 79.29%, and 58.93%, respectively. Coal separation efficiency was 60.93%.

6.3.3 Pocahontas Fine Coal Cleaning

The same procedures for the cleaning of Illinois No. 6 and Lower Kittanning coals were applied for the cleaning of Pocahontas coal. Figure 51 shows the results of ash content reduction with the magnetic reagent method. Figure 52 demonstrates the results of pyritic sulfur rejection. At 90% passing 500 mesh, ash content was reduced from 32.40% to 2.57%. Pyritic sulfur was reduced from 0.41% to 0.08%, while total sulfur was reduced from 0.70% to 0.69%. Coal yield was 33.07% at a BTU recovery of 47.33%. Separation efficiency was 40.84%. The rejection rates of ash, pyritic sulfur, and total sulfur were 97.38%, 93.51%, and 67.24%, respectively. The high ash content of this coal seemed to have significant impacts on the coal recovery. Since minerals are attracted to the magnetic matrix in this process, large amounts of coal particles can be mechanical entrapped with the magnetic mineral particles. This will inevitably result in a low coal recovery. Comparing with the results of Illinois No. 6 and Lower Kittanning coals, the trend became obvious. Lower Kittanning coal contained the lowest ash content in the feed, but the cleaning of this coal with the magnetic reagent resulted in the highest coal recovery. Unless a new magnetic separator can be designed to repel coal particles from mechanical entrapment, the processing of high ash coal with the magnetic

reagent approach will continue to be a problem. One magnetic separator which has the potential to eliminate this problem is the Magfloat separator recently designed by Hydro Processing & Mining Ltd. This is a new patented separator, which was not yet available for this study.

At 90% passing 325 mesh, ash content was reduced to 2.58%. Pyritic sulfur was reduced to 0.07% with total sulfur at 0.69%. Coal yield is 38.01% with 57.84% BTU recovery. Separation efficiency was improved to 51.24%. The rejection rates of ash, pyritic sulfur, and total sulfur were 96.92%, 93.39%, and 63.61%, respectively.

Cleaning at 90% passing 200 mesh resulted in an ash content reduction to 4.27%. Pyritic sulfur was reduced to 0.07%, while total sulfur was reduced to 0.64%. Coal yield was 39.59% with a BTU recovery of 57.41%. The rejection rates of ash, pyritic sulfur, and total sulfur were 94.55%, 90.82%, and 64.39%, respectively. Separation efficiency was 48.23%.

Processing at 90% passing 100 mesh was again involved with the mechanical entrapment of coarse particles by the steel wools. The ash content was reduced to 4.74%. Pyritic sulfur was reduced to 0.07% and the total sulfur content was reduced to 0.68%. Coal yield was 32.43% with 41.60% BTU recovery. Separation efficiency was 34.02%. Ash, pyritic sulfur, and total sulfur rejection rates were 95.00%, 92.42%, and 70.90%, respectively.

CHAPTER 7

OPTIMIZATION OF MAGNETIC REAGENT SEPARATIONS

The optimization of the magnetic reagent method for coal cleaning was conducted with assistance provided by Eriez Magnetics. The optimization study included the selection of a magnetic separator, identification of the coal particle sizes for investigation, determination of the magnetic matrix for separation at various particle sizes, investigation of the appropriate reagent dosages, determination of the magnetic field strengths necessary for operation, examination of the effects of slurry solid content, and investigation into the capacity of the magnetic separator.

7.1 Magnetic Separator

Laboratory test results obtained earlier were discussed with the technical staff of Eriez Magnetics, led by Dan Norrgran, Technical Manager. A wet high intensity magnetic separator was determined to be the appropriate magnetic separator for this approach, based on both technical and economic concerns. The Eriez Model L-4-20 separator was then selected to conduct all optimization experiments.

7.2 Particle Size and Magnetic Matrix

Two coal particle sizes were selected for this study: -48 mesh and 90% passing 200 mesh. The -48 mesh coal was obtained directly from the conventional coal preparation plant. Since grinding was not required, the cost of processing was thus greatly reduced. The study of the 90% passing 200 mesh coal provided the fine coal

cleanability data. Earlier results showed that there was no significant difference for coals processed in the range of 90% passing 200 mesh to 90% passing 500 mesh. Coarser grinding obviously would provide a cost advantage.

Based on the experience of Eriez Magnetics, potential magnetic matrices for the wet high intensity magnetic separator at the two particle sizes included expanded metal (EXM), coarse screen (CS), chicken wire (CW), and 1/4" stainless steel balls (Ball). The stainless steel wool matrix utilized for earlier studies was generally applied for minus 270 mesh materials as coarser materials are easily entrapped in the matrix causing low recovery of nonmagnetics. Our magnetic reagent approach may further intensify this problem because large amounts of minerals are strongly magnetized. The relatively low coal recovery obtained in earlier tests demonstrated this problem.

Selection of a magnetic matrix for various particle sizes was conducted experimentally. Figure 53 shows the effects of the magnetic matrix on coal cleaning at -48 mesh particle size. Experiments were carried out by feeding a slurry of Illinois No. 6 coal through a canister containing an 18 cm length of the desired magnetic matrix, magnetized at 10 kilogauss applied magnetic field strength. Three periods of retention time were involved for each matrix testing, these were 1, 2, and 3 seconds. Longer retention time provided a higher extent of ash reduction. The retention time was controlled by passing the slurry repeatedly through the canister. Each pass had a retention time of approximately one

second. The slurry was fed through the canister gravitationally with a velocity of about 18 cm/sec.

As shown in Figure 53, the matrix had strong effects on the separation results. Expanded metal showed the lowest magnetic collection capacity, while the coarse screen removed the largest amount of mineral matter. From the standpoint of separation efficiency, the ball matrix undoubtedly performed the best. Much higher coal recovery was obtained with this matrix. Therefore, the ball matrix was selected for the -48 mesh coal processing in this study.

The experiments to determine the effects of the magnetic matrix on the 90% passing 200 mesh coal were conducted using the same experimental procedures. The results are demonstrated in Figure 54. Expanded metal and chicken wire matrices were less efficient than the ball and coarse screen matrices. Comparing the ball matrix and the coarse screen matrix, the ball matrix was slightly better with respect to coal recovery and separation efficiency. However, the coarse screen matrix produced much better ash reduction. One second retention time with the coarse screen matrix was equivalent to approximately three seconds retention time with the ball matrix. Therefore, a coarse screen matrix was utilized for the processing of 90% passing 200 mesh coal in this study.

7.3 Magnetic Reagent Dosage

7.3.1 Illinois No. 6

Four dosages of magnetic reagents were studied for Illinois No. 6 coal at the -48 mesh particle size. These dosages were 0, 3, 5, and 10 pounds of magnetite per ton of coal. The diamine dosage was equivalent to one third of the magnetite dosage. Thus, the magnetic reagent dosages on the basis of diamines were 0, 1, $5/3$, and $10/3$ pounds of diamines per ton of coal. The ratio between magnetite and diamine was consistent throughout this study. Magnetite dosage was utilized as the basis for magnetic reagent dosages in this report.

Magnetic separation was carried out with a ball matrix at 10 kilogauss magnetic field strength. Separation results are shown in Figure 55. Without the magnetic reagent, only a small amount of ash was removed. The best separation was obtained at 3 lbs/ton magnetic reagent dosage. Further increase in magnetic reagent dosage resulted in serious loss of coal recovery, although the extent of ash reduction was improved.

The effects of magnetic reagent dosage for Illinois No. 6 coal at 90% passing 200 mesh particle size were studied at five dosage levels: 0, 4, 6, 8, and 10 pounds per ton of coal. Experiments were carried out with a coarse screen matrix at 10 kilogauss applied magnetic field strength for 1, 2, and 3 seconds of retention time.

Figure 56 shows the results of the magnetic reagent dosage effects. Without the magnetic reagent, poor separation with very little ash reduction was obtained. With the addition of the magnetic reagent, selective separation with much higher efficiency was obtained. The results at various dosages generally formed a

continuous grade-recovery curve. The increase of magnetic reagent dosage corresponded to an increase in ash removal. Optimum dosage can be selected along the curve after determining the retention time for the separation.

7.3.2 Lower Kittanning

Four magnetic reagent dosages were investigated for Lower Kittanning coal at -48 mesh, these were 0, 3, 5, and 10 pounds of magnetite per ton of coal. Magnetic separations were carried out using a ball matrix at 10 kilogauss with up to 3 seconds of retention time. Figure 57 shows the results. Without the magnetic reagent, very small amounts of ash were removed. The addition of magnetic reagent results in the removal of most of the ash. Ash content was reduced from 6.40% to 2.28% with 89% coal recovery. Variations of magnetic reagent dosage from 3 to 10 pounds did not have much effect on the separation. For example, a dosage increase from 3 lbs to 5 lbs improved the ash content reduction by about 0.6%. A further increase of dosage to 10 lbs corresponded to an increase in coal recovery of only 2%. Thus, the process can use an optimum dosage in the range of 3 to 10 lbs per ton. Economic reasons favor the use of a low reagent dosage, which was 3 lbs per ton. This dosage is the same as that for the Illinois No. 6 at -48 mesh.

For Lower Kittanning coal at 90% passing 200 mesh, the reagent dosages were investigated at 0, 4, 6, and 10 lbs magnetite per ton of coal. Magnetic separations were carried out with a coarse screen matrix at 10 kilogauss with 1, 2, and 3 seconds of retention time.

The separation results are shown in Figure 58. Without the magnetic reagent, the separation was poor, with only about 33% ash rejection. Better recovery and ash removal were obtained after the addition of magnetic reagent. Again, the variation of magnetic reagent dosage from 4 to 10 lbs per ton of coal resulted in approximately equal coal cleaning. Ash content could be reduced to 2.27% with 91.19% coal recovery. The optimum dosage should be the lowest reagent dosage, which was 4 lbs or lower in these tests.

7.3.3 Pocahontas

The magnetic reagent dosage for Pocahontas coal at -48 mesh was studied at the same levels as before, i.e., at 0, 3, 5, and 10 lbs of magnetite per ton of coal. Magnetic separations were carried out using the same procedures with the ball matrix. Figure 59 shows the separation results. The difference between the addition and no addition of magnetic reagent was obvious. Without addition, ash content was reduced to 15.54%. When the magnetic reagent was added, ash content was reduced to 5.36%. The increase of magnetic reagent dosage from 3 to 10 lbs correlated to the increase in the extent of ash reduction. The grade-recovery results of all tests at various dosages and separation conditions formed a continuous curve. Selection of the optimum dosage can be obtained from any point on the curve when the extent of ash reduction is decided. The dosage of 3 lbs is still favored because significant ash reduction with high coal recovery can be obtained at this level.

The nature of the Pocahontas coal is different from the Illinois No. 6 and Lower Kittanning coals. Pocahontas contains more than 30% mineral matter, mostly clays. These clays are fine particles and thus, require more magnetic reagent than the other two coals at -48 mesh.

Dosages for Lower Kittanning coal at 90% passing 200 mesh were studied at five levels, which were 0, 4, 6, 8, and 10 lbs magnetite per ton of coal. The separation results are shown in Figure 60. Very small amounts of ash reduction were observed without the addition of magnetic reagent, i.e., processing reduced ash content from 30% to only 20.61%. With the addition of the magnetic reagent, reduction of ash content to 3.71% was obtained. A continuous grade-recovery curve was again formed when all data points were plotted. On this curve, it was apparent that very little gain on ash reduction can be obtained when the reagent dosage exceeds 8 lbs magnetite per ton of coal. At this dosage, 90.39% of the ash was removed with about 80% coal recovery.

7.4 Applied Magnetic Field Strength

A major cost of magnetic separation is the energy consumed to generate the applied magnetic field strength. For the conventional high intensity magnetic separator, a maximum of 20 kilogauss can be obtained. However, the energy consumed above 10 kilogauss is exponential to the increase of magnetic field strength. This high energy consumption has prevented the use of magnetic separation for many applications.

In a high intensity magnetic separator, the magnetic force of a particle is proportional to the magnetization of the matrix material and the magnetization of particles. The magnetization of the matrix materials is usually proportional to the applied magnetic field strength to approximately 6 kilogauss (varies with materials). At 6 kilogauss, the magnetization is nearly saturated. There is little gain in magnetization of the matrix above 6 kilogauss. The magnetization of particles depends on the magnetic property of the particles. For paramagnetic particles, the magnetization is proportional to the applied magnetic field strength. The increase of magnetic field strength is then above to improved magnetic separation continuously. When a magnetic reagent is added, the magnetic properties of particles will be dictated by the magnetite adsorbed on the particle. Magnetite is a ferromagnetic material, with saturation of the magnetization occurring at approximately 2 kilogauss. Further increase in applied magnetic field strength will not increase the magnetization of magnetite. Thus, magnetic separation of magnetic reagent treated particles will have little gains at above 6 kilogauss unless the paramagnetic properties of the original particles are significant in the particle/magnetite composites.

In this study, the effects of magnetic field strength were investigated in a range of up to 10 kilogauss. The Illinois No. 6 coal at -48 mesh was processed at four different magnetic field strengths: 2, 5, 7, and 10 kilogauss. Each test was carried out with a reagent dosage of 3 lbs magnetite per ton of coal and

retention time that varied from 1 to 3 seconds. The results are shown in Figure 61. All of the data points fall along a line on the grade-recovery curve. Separations at 5, 7, and 10 kilogauss showed very little difference. Actually, the separation results at 7 and 10 kilogauss were almost identical. These results showed that saturation of magnetization for both matrix and particles occurred at approximately 6 kilogauss.

Figure 62 shows the results for processing Illinois No. 6 at 90% passing 200 mesh under various magnetic strengths. The applied magnetic field strengths included 2, 4, 6, 8, and 10 kilogauss. Improvements of separation were observed from 2 to 6 kilogauss. From 6 to 10 kilogauss, the separation results were again nearly identical.

Lower Kittanning coal at -48 mesh was investigated at magnetic field strengths varying from 2 to 10 kilogauss. As shown in Figure 63, there was little difference in the separation results at magnetic field strengths ranging from 4 to 10 kilogauss. Figure 64 shows the results of separation for Lower Kittanning at 90% passing 200 mesh. Magnetic field strengths were 2, 6, 8, and 10 kilogauss. From 6 to 10 kilogauss, separation results were all consistent.

Pocahontas coal was studied with the same procedures. Figure 65 shows the results of processing at -48 mesh. Magnetic field strengths tested included 2, 4, 6, 8, and 10 kilogauss. The increase of ash reduction was significant from 2 to 4 kilogauss. At higher magnetic field strengths, there was not much increase of ash reduction. Figure 66 illustrates the results for the separation of

Pocahontas at 90% passing 200 mesh. Variations of magnetic field strength at 2, 4, 6, 8, and 10 kilogauss were included. Improvements of magnetic separation from 2 to 6 kilogauss were very significant. Above 6 kilogauss, nearly identical separation results were again observed.

The magnetic field strength for separating coal using the magnetic reagent method was thus determined to have an optimum at 6 kilogauss.

7.5 Solids Content

The solids content of a slurry passing through a magnetic separator can affect the efficiency of separation. Experiments were conducted to determine the effects.

For coals processed at -48 mesh, four solids contents were investigated: 5%, 10%, 20%, and 30% solids. Figure 67 shows the results of Illinois No. 6 coal. At 5% solids content, the separation was relatively poor. With the increase of solids content, from 5% to 20%, the separation was improved. From 20% to 30% solids content, there was no further improvement on separation performance. Figure 68 shows the results of Lower Kittanning coal. The separation at 5% solids content still produced lower recovery. From 10% to 20% solids content, the separation results were generally consistent. The results of -48 mesh Pocahontas coal processed at various solid contents are shown in Figure 69. Significant effects of solids content were not observed. But the trend of separation performance improvement with the increase of

solids content still existed. The best separation was achieved at 30% solids content.

The optimum solids content for the processing of -48 mesh coal using ball matrix may have a relation to the ash content of the feed. Lower Kittanning, Illinois No. 6, and Pocahontas coals have 6%, 22%, and 30% ash content in the feed, respectively. Their optimum solids contents were roughly >10%, >20%, and 30%, respectively. In general, a 20% to 30% solids content would be the choice for operations.

At 90% passing 200 mesh particle size, three solid contents were investigated: 5%, 10%, and 20% solids. Higher solid contents were not studied because the slurry viscosity became high. Magnetic separations at this particle size were carried out with a coarse screen matrix at 6 kilogauss. Figure 70 shows the results of Illinois No. 6 coal. The separations at 5% and 10% solids fell on the same curve. At 20% solids content, the grade-recovery curve was improved. Figure 71 shows the results of Lower Kittanning coal. The separations at 10% and 20% solids were on the same grade-recovery curve. This curve had better performance than that of the 5% solids. The results for Pocahontas coal at 90% passing 200 mesh is shown in Figure 72. Again, the separations at 10% and 20% solids had the same grade-recovery curve and were better than that at 5% solids. In general practice, a 20% solids content would probably be the choice.

7.6 Loading Capacity

The loading capacity of a magnetic separator is important for the efficient utilization of the separator. To investigate this factor, various amounts of materials were fed through a magnetic separator. For the study of -48 mesh coals, five loading levels were tested. Figure 73 shows the separation results for Illinois No. 6 coal at 20, 40, 60, 80, and 100 grams loading for each canister. Apparently, loading capacity at 20 and 40 grams per batch formed a lower grade-recovery curve. At a loading capacity in the range of 40 to 100 grams per batch, the grade-recovery curve was quite consistent. Figure 74 shows the separation results for Lower Kittanning coal. The curve formed by the data points from 20 to 80 grams per batch had better grade-recovery results than that at 100 grams per batch. For the results of Pocahontas coal, which is shown in Figure 75, the loading capacity was favored in the range of 40 to 100 grams per batch. Combining the results of the three coals, it was concluded that a loading capacity of about 80 grams per canister is probably an appropriate choice.

The loading capacity for coals at 90% passing 200 mesh particle size was also studied. The study included four levels of loading capacity: 20, 40, 60, and 80 grams coal per canister. Figure 76 shows the results for the separation of Illinois No. 6 coal at various loading capacities. The separation grade-recovery curve was improved with increased loading capacity. The optimum loading capacity was in the range of 60 to 80 grams per canister. Figure 77 shows the results of separation for Lower Kittanning coal at various loading capacities. The separation at 20 grams per

canister had lower efficiency, with the optimum capacity in the range of 40 to 80 grams per canister. Figure 78 shows the results of separation for Pocahontas coal. The separations at 20 to 40 grams per canister are less efficient. The optimum loading capacity was in the range of 60 to 80 grams per canister for this coal. Combining the results of the three coals, a loading capacity of about 80 grams per canister would be appropriate for the 90% -200 mesh coal.

CHAPTER 8

TECHNOLOGY COMPARISON AND DISCUSSION

8.1 Comparison of Washability, Flotation, and Magnetic Reagent Separation

A washability analysis is a standard laboratory test to determine the theoretical limit a physical separation can achieve. Flotation is a conventional physical separation which is commercially available for fine coal cleaning. The separation results of washability, flotation, and magnetic reagent separation methods were compared to evaluate the technical performance of the magnetic reagent method.

Figure 79 shows the total sulfur separation results of Lower Kittanning coal at -48 mesh obtained by washability, flotation, and magnetic reagent methods. Washability results provided the best grade-recovery curve. Flotation and the magnetic reagent method agreed very well on their grade-recovery curves. However, when deep sulfur removal was required, the magnetic reagent method was better than flotation. At about 1% total sulfur content, the magnetic reagent method yielded approximately 88% coal recovery. An additional 5% gain on coal recovery was obtained with the magnetic reagent method.

Figure 80 shows the ash separation results obtained on Lower Kittanning coal at -48 mesh by the three methods. The three methods were nearly identical regarding their capabilities of ash

reduction. The differences were within 2% of coal recovery in most cases.

At 90% passing 200 mesh, the reductions of total sulfur for Lower Kittanning coal by the three methods had similar relationships as that at -48 mesh. Washability provided the best separation. Flotation and the magnetic reagent method had nearly identical sulfur reduction capabilities, as shown in Figure 81. At about 1% total sulfur (reduced from 2.3%), 95% coal recovery was obtained. Direct magnetic separation without utilizing the magnetic reagent was also evaluated. The results, as shown in the figure, demonstrate that the effect of magnetic reagents on separation improvements was very significant.

Ash reductions obtained for the Lower Kittanning coal at 90% passing 200 mesh by the three methods were also compared. As shown in Figure 82, washability and flotation had very close grade-recovery curves. The magnetic reagent method was slightly off, by approximately 3%, in coal recovery. Compared with the results of direct magnetic separation with no magnetic reagent, the improvement on separation was again obvious.

The processing of Illinois No. 6 at 90% passing 200 mesh is another example. Figure 83 shows the total sulfur separation results using washability, flotation, magnetic reagent separation methods, and direct magnetic separation without the magnetic reagent. The washability method apparently had the best separation efficiency, while magnetic separation with no magnetic reagent was the worst. The comparison between the flotation and magnetic

reagent methods was difficult. As shown in the figure, the total sulfur contents were quite different in the feeds to the two sets of tests. The samples for the final magnetic reagent tests had been stored in argon for a year after the flotation and washability tests were conducted. The total sulfur content in the stored sample was approximately 0.8% higher. However, the magnetic reagent method still cleaned the coal with better efficiency than flotation when deep sulfur cleaning was required. The high ash content of this coal (22%) caused significant mechanical entrapment of coal particles in the high intensity magnetic separator, as discussed earlier. This corresponded to a lower coal recovery at the initial stage of coal cleaning. After most mineral particles were removed in a magnetic separator, the mechanical entrapment problem was insignificant. At that stage, further magnetic separation (by increasing retention time) efficiently removed pyrite without significant loss of coal. The better performance of the magnetic reagent method on sulfur reduction then became apparent. This result was consistent with that of magnetic reagent separation after flotation at -48 mesh, which was demonstrated in Figure 44.

Mechanical entrapment of coal particles at high ash contents was also clear after evaluating the ash content reduction results for the Illinois No. 6 at 90% passing 200 mesh. As shown in Figure 84, the magnetic reagent method resulted in a lower coal recovery than flotation at the initial stage of separation. But the grade-recovery curves of the two methods were approaching each other at later stages of cleaning.

The hydrophobicity of coals may vary. Lower Kittanning and Illinois No. 6 coals have shown strong flotabilities. However, the floatability of Pocahontas coal may not be as strong. Figure 85 shows the ash content reduction results by washability, flotation, magnetic reagent, and without magnetic reagent methods for Pocahontas coal at 90% passing 200 mesh. The washability and without magnetic reagent methods provided the results of the best and the worst scenarios. Comparing the flotation and magnetic reagent results, it was apparent that the magnetic reagent method produced a much better separation than flotation. An improvement of about 15% coal recovery at 5% ash (reduced from 31% ash) was obtained.

8.2 Technical Discussion

Coal cleaning with magnetic reagents is an innovative approach which may bring magnetic separation to a new arena. Traditionally, magnetic separation has been limited to the separation of natural magnetic minerals in the mining industry. With the development of the magnetic reagent method, it becomes possible to magnetize nonmagnetic minerals at will. Magnetic separation of naturally nonmagnetic minerals can now be achieved.

The physical forces for separation are generally limited to gravitational (including centrifugal), electrostatic, and magnetic forces. There are only a few applications in which minerals are separated purely on the basis of these forces. The development of froth flotation brought numerous applications for gravitational separation to the mining industry. This method utilizes the

apparent density concept by coupling mineral particles with air bubbles to result in a composite which has an apparent density lower than water. The gravitational force can then bring the composite to the top of water to yield a separation. Surface chemistry is utilized to control the coupling of air bubbles and mineral particles.

The magnetic reagent method is conceptually comparable with the froth flotation method. When the air bubbles in a composite are replaced by magnetic particles, magnetic separation can be utilized as a substitute for the gravitational separation of froth flotation. Surface chemistry is also utilized to control the coupling of magnetic particles with the mineral particles, although the route of coupling is different between the two approaches.

In froth flotation, mineral particles are rendered hydrophobic through the use of collectors such as surfactants, to facilitate the coupling of air bubbles and mineral particles. In the magnetic reagent approach, magnetic particles are treated with surfactants or the like to result in reactivity for the magnetic particles. Through tailored reactivity, coupling (or adsorption) of magnetic particles on the desired mineral particles can be controlled at will.

This study investigated the preparation of magnetic reagents, the adsorption mechanisms of magnetic reagents on minerals, the applications of magnetic reagent technology on coal cleaning, and the optimization of separation conditions. Success was obtained from both the theoretical and the applied sides.

The double surfactant layer structure was proven effective for the preparation of various magnetic reagents. The adsorption of magnetic reagents on minerals through electrokinetic, covalent, van der Waals, and hydrogen bonding mechanisms were clarified. Methods to control these adsorption mechanisms were determined. The theoretical background of the magnetic reagent technology was well established.

The application of magnetic reagent technology to coal cleaning was established on the basis of the fundamental studies. Reagents able to make mineral matters selectively magnetic were identified. Experiments on coal cleaning were very successful. The cleaning was carried out in two approaches. One was to process the coal directly with the magnetic reagent technology, the other one was to process a flotation concentrate with the magnetic reagent.

In the particle size ranges investigated in this study, i.e. from -48 mesh to -500 mesh, the magnetic reagent technology was proven effective. Selective magnetic enhancement of minerals was consistently achieved in these particle size ranges. More than 90% of the ash and pyritic sulfur contents were removed.

Comparing with conventional flotation, the magnetic reagent technology proved to be competitive. For coals with high floatability, such as Lower Kittanning coal, the magnetic reagent technology was better in total sulfur reduction. With respect to coals with low floatability, such as Pocahontas coal, much higher coal recovery was obtained with the magnetic reagent technology. As for coals with poor liberation, such as Illinois No. 6, magnetic

reagent technology was applied to clean the flotation concentrate to yield an improved separation.

CHAPTER 9

ECONOMIC ANALYSIS

9.1 General Consideration

The economic analysis of the magnetic reagent process was investigated following the guidelines described in the Bureau of Mines Cost Estimating System Handbook [9], after reviewing several cost estimation publications [10, 11]. The handbook was published in 1987 with the objective of assisting in the preparation of prefeasibility type estimates for capital and operating (including maintenance) costs of beneficiation of various types of mineral occurrences using current technology. It provided a convenient costing procedure based on the summation of the costs for the unit processes required in any particular mineral processing operation. The accuracy is expected to be within 25% of the actual cost.

The scope of the economic analysis in this study included the capital and operating (including maintenance) costs involved in the magnetic reagent processing circuit. This circuit is primarily a wet high intensity magnetic separation in conjunction with a reagent preconditioning step. Since wet high intensity magnetic separation is a well established mineral processing method, the Bureau of Mines handbook utilized data from existing operations as the basis of its study. Those results were applied directly in this work for magnetic separation cost estimation. The magnetic reagent in our process required only mild stirring for conditioning. Additional capital investment for this step was very little

compared to the magnetic separation. Therefore, we added 5% to the capital and operating costs of wet high intensity magnetic separation to compensate for the involvement of magnetic reagents. The cost of magnetic reagents and coal modifying chemicals was added to the operating costs under the category reagent costs.

Operations which are common for all coal cleaning processes were not included in this economic analysis. Mining, crushing, grinding, filtration, wastewater treatment, and transportation are examples of the operations which were not considered. With this approach, our estimates could be directly compared with those of other advanced coal cleaning technologies.

The estimation of the costs in the Bureau of Mines handbook was based on the dollar as of January, 1984. To adjust to the cost as of January, 1991, an inflation rate of 5% per year was assumed. Thus, the costs estimated in this study reflect a compounded 41% increase of the costs calculated from the handbook.

9.2 Capital Costs

The capital cost estimate developed by the Bureau of Mines for industrial mineral processing unit process is composed of the construction labor cost, the construction materials cost, the purchased equipment cost, and the cost of equipment transportation. A 5% to 10% contingency was included in each cost section to cover incidental items not specifically addressed in their estimates.

The construction labor costs were estimated from worker-hour requirements for each unit operation. Average labor costs were determined from local wage rates for a variety of job

classifications common to mineral industry construction. The labor burden and fringe benefits at 21% of the base wage rates were included in the labor costs.

The estimates for construction materials included support steel, steel reinforcing bars, concrete, sand and gravel, timber, etc. Also included were small hand tools, welding rods, and other miscellaneous equipment. The freight cost associated with these materials was not included by assuming that these materials were readily available at the construction site.

The purchased equipment referred to the major process equipment directly associated with each mineral processing unit operation. For the wet high intensity magnetic separation operation, the magnetic separator and the necessary materials handling equipment were included. The costs associated with the acquisition and installation of the oversize particle removal screens, feed pumps, feed distributors, tailing collection, middling collection and final product collection constituted a major part of the materials handling equipment cost.

The transportation cost was the freight cost associated with the equipment shipment. Average transportation rates were applied in the calculations.

The total capital cost for a wet high intensity magnetic separation is given by a formula:

$$Y = 515.411 (X)^{0.970}$$

where X is the feed rate, in metric tons dry feed to the magnetic separation circuit per day. This formula is based on a three-shift-

per-day operation with an availability of 95%. It is valid for operations between 2,100 and 47,000 metric ton per day.

For coal processing using the magnetic reagent technology, an operation of 100 ton per hour at three shifts per day, eight hours per shift, is equivalent to 2,400 tons per day, or 2,182 metric tons per day. This scale of operation is valid for the application of the Bureau of Mines formula. By substituting X in the formula with 2,182 metric tons per day, a capital cost of \$892,982 before necessary adjustments was obtained.

Several adjustments were used to derive a meaningful capital cost for the magnetic reagent coal cleaning operation. The first adjustment factor was for inflation. As discussed earlier, an increase of 41% was required to account for the inflation from January 1984 to January 1991. The second factor was the recleaning of coal concentrates with repeated magnetic separations to obtain the retention time requirements in our study. Laboratory tests showed that three seconds of retention time were typical for magnetic enhanced separation. In practice, this was achieved by repeating the magnetic separation twice. Therefore, two recleanings are probably necessary for plant operation. The Bureau of Mines handbook shows that a factor of 24% increase is necessary for a recleaning stage. Based on this factor, we assumed that a total of 48% increase would be necessary for two recleanings. Finally, adjustments to handle the magnetic reagent conditioning may be required. An increase of 5% on capital cost was proposed, as discussed earlier.

The capital cost for coal cleaning using the magnetic reagent method at 100 tons per hour on the basis of the 1991 dollar was then calculated as:

$$Y = \$892,982 \times 1.41 \times 1.48 \times 1.05 = \$1,956,649$$

In other words, approximately two million dollars of capital cost were estimated. The breakdown of the capital cost included 2.3% construction labor cost, 1.5% construction supply cost, 95.7% purchased equipment cost, and 0.5% transportation cost, as shown in the Bureau of Mines handbook.

9.3 Operating and Maintenance Costs

The operating and maintenance (O&M) costs are classified into four portions: the labor cost, the supplies, the equipment operation cost, and the reagent cost. Adjustment factors include inflation (41%) and the addition of two recleaning stages.

The labor costs included both direct operating labor and maintenance labor cost. The average wage for labor was \$21.67 per worker-hour (including burden and average shift differential). Control room operator, mill operator, mill helper, and mill laborer were included in consideration. Direct labor cost was 86% of the total labor cost. The maintenance labor was 14% in the breakdown. The total daily labor cost was calculated by the formula (including adjustments):

$$L = 0.512 (X)^{0.785} (1.41)$$

where X is the metric tons of dry feed to the magnetic separation circuit per day. At a rate of 100 tons per hour (2,182 metric tons per day), the labor cost equals \$301.64 per day.

The supplies portion of the operating cost is usually comprised of electrical power, natural gas, reagents, and other consumables. For wet high intensity magnetic separation, electric power cost was the dominant portion of the supplies. Reagent cost for the magnetic reagent method was calculated separately. The electric power cost was assumed at \$0.05 per KWH in the Bureau of Mines handbook. Current power rate is approximately \$0.06 per KWH. Thus, an inflation factor of 20% applied. In addition, the two recleaning stages added another 44% supply cost. The formula for the daily supply cost was then modified to:

$$S = 0.038 (X)^{1.020} (1.20) (1.44)$$

At the feed rate of 100 tons per hour, the daily supplies cost equaled \$167.09.

Equipment operation costs are considered to include fuel, lubrication, repair parts and materials for all process equipment related to the unit processes. A standard sales tax of 4% was included on all nonfuel items. Adjustments for the equipment operation costs included 41% inflation and 28% for recleanings. The formula modified for the equipment operation costs then became:

$$E = 0.042 (X)^{0.935} (1.41) (1.28)$$

A daily equipment operation cost of \$100.35 was obtained for the 100 tph feed rate.

The reagent costs included the coal surface modifier and the magnetic reagent. The cost of coal surface modifier (Brij 700) was \$1.30 per pound. The cost of magnetic reagent was \$1.36 per pound (on the basis of magnetite weight). Laboratory tests showed that 8

pounds of modifier and 3 pounds of magnetic reagent were typically required to process a ton of coal. Until a low cost coal surface modifier can be identified for the magnetic reagent approach, the high reagent cost will continue to exist. At a processing rate of 2400 tons per day, the daily reagent cost was \$34,752.

The total daily operation and maintenance cost is the summation of labor cost, supplies, equipment operation cost, and reagent cost, which equaled \$35,321. The reagent cost amounted to 98.39% of the total cost. The other costs equaled only \$0.24 per ton.

9.4 Combination of Economic Parameters

The total capital cost estimate was \$1,956,649. Assuming an economic model with 100% debt financing at 11% annual debt interest rate for a plant life of 20 years, the annual capital cost would be \$242,356. For a plant operating 300 days per year, the daily capital cost was \$808. This is equivalent to \$0.34 per ton of coal. As shown earlier, the O&M costs were \$14.72 per ton of coal.

The Lower Kittanning coal at 90% passing 200 mesh was processed with the magnetic reagent method to yield 87.72% coal concentrate with 92.88% BTU recovery after three stages of magnetic separation. The total sulfur content was reduced from 2.43% to 0.96%. This is equivalent to 58.80 pounds of SO_2 removal per ton of coal. To remove a ton of SO_2 , requires processing of 34.01 tons of coal. Thus, the total cost to remove a ton of SO_2 is \$512.

The BTU value of the concentrate of Lower Kittanning coal was 14,702 BTU/lb. To obtain a million BTU, a cost of \$0.58 is

required. The cost to yield a ton of coal concentrate at 2.12% ash content and 0.96% total sulfur content can also be calculated as \$17.17 per ton.

The processing cost for Illinois No. 6 coal at 90% passing 200 mesh was calculated following the same rules. Test results showed that a 63.37% yield of coal concentrate with 79.72% BTU recovery was obtained. The BTU value of the concentrate was 13,651 BTU/lb. The total sulfur content was reduced from 4.84% to 2.55% and the ash content was reduced from 22.25% to 6.95%. The cost of SO₂ removal was calculated as \$329 per ton of SO₂ removed. The cost to obtain a ton of coal concentrate is \$23.77. This is equivalent to a cost of \$0.87 per million BTU.

The results of the economic analysis are summarized in Table 9.

CHAPTER 10

CONCLUSIONS AND RECOMMENDATIONS

The overall objectives of this study were to define the fundamental properties of magnetic reagents and to determine the technical and economic feasibilities of the magnetic reagent technology for coal cleaning applications. Specific objectives included the determination of i) the conditions for selective magnetic enhancement of mineral matters from coal, ii) the effectiveness of the method on coal cleaning, and iii) the adaptation of this method into existing coal processing circuits.

Based on the results of this study, we were able to draw the following conclusions:

1) Magnetic reagents were proven to be effective on enhancing the magnetic property of mineral particles. The enhancement was achieved through adsorption mechanisms and obtained through the selection of the magnetic reagent and the water chemistry conditions which were related to the adsorption mechanisms.

2) The conditions most favorable for the selective magnetic enhancement of mineral matters from coal required the use of a nonionic surfactant and a cationic magnetic reagent. This combination can be applied in a wide pH range, although pH 7 was utilized for various tests in this study. Nonionic surfactants are effective to wet coal and to eliminate the surface charge effect of coal for magnetic reagent adsorption. Brij 700 is a typical nonionic surfactant. Cationic magnetic reagents are generally

effective to enhance the magnetic property of all minerals in coal. The cationic reagent utilized for coal cleaning had the diamine functional group, which provided strong cationic properties.

3) Coal cleaning using the magnetic reagent method to separate pyrite and ash forming minerals magnetically from coal after the magnetic enhancement treatment was successfully demonstrated in this study. Sulfur reduction obtained by this method was similar or better than that produced by conventional froth flotation for the same coal recovery in many cases. Direct magnetic separation without magnetic reagent treatment was not able to remove significant amounts of pyrite and ash forming minerals.

4) The magnetic reagent method can be applied over a wide range of particle sizes. Tests of sizes ranging from -48 mesh to -500 mesh were all successful. Thus, the magnetic reagent method can be adapted to existing coal processing circuits as a direct cleaning method or as a recleaning method. As a recleaning method, it can be applied to process the heavy media, tabling, and froth flotation concentrates. The coating of oils on coal particles after froth flotation does not cause deleterious effects on the magnetic reagent method.

5) The economic feasibility of the magnetic reagent method for coal cleaning was shown to be competitive to the flotation method. Based on an economic analysis, the total capital, operating and maintenance cost to remove a ton of SO_2 at 90% passing 200 mesh was \$329 for Illinois No. '6 coal and \$550 for Lower Kittanning coal.

From the results of this study, the following recommendations for continued work were formulated:

1) The development of a magnetic separator capable of handling a relatively large amount ($>5\%$) of magnetic materials at approximately 6 kilogauss can be very beneficial to the magnetic reagent method. Current design of the wet high intensity magnetic separator frequently causes mechanical entrapment of nonmagnetic particles in the magnetic concentrate. This is particularly serious when the fraction of magnetic concentrate is high. In this application, coal recovery can be further increased if an appropriate magnetic separator for the magnetic reagent method was available.

2) It is important to develop a new, low cost coal surface modifier. This study demonstrated that a nonionic surface modifier effectively depressed coal from adsorbing the magnetic reagent. Brij 700 (polyoxyethylene stearyl ether) was the chemical utilized for that purpose in this study. This chemical was picked off the shelf and may not be the optimal one, especially from the cost standpoint. This chemical was actually designed for high value applications such as pharmaceuticals, and was available commercially at a price of \$1.30 per pound. More than 50% of the total cost for coal cleaning with the magnetic reagent method was spent on Brij 700 for coal depressing. To develop a low cost substitute for Brij 700 from cheap raw materials will make this method economically very attractive.

ACKNOWLEDGEMENT

The Institute of Materials Processing at Michigan Technological University wishes to acknowledge the following persons and organizations.

Mr. MacMahan Gray, Dr. Richard Hucko, Dr. Richard Killmeyer, and Dr. George Wen, of the Department of Energy Pittsburgh Energy Technology Center, for their continued stimulation and constructive discussions.

Jack Keck, Junbiao Liu, Ruth Kramer, Tom Hozeska, Rodney Lizak, and Allison Hein, of Michigan Technological University, for their technical support during this study.

Mr. Dan Norrgran and Mr. Richard Merwin, Eriez Magnetics, for their helpful discussions on magnetic separator selections. Also Eriez Magnetics for kindly providing a part of the testing facilities.

REFERENCES

- [1] Y.A. Liu, "High Gradient Magnetic Separation for Coal Desulfurization," Physical Cleaning of Coal, Y.A. Liu ed., Marcel Dekker, Inc., 1982.
- [2] D.D. Bluhm, G.E. Fanslow and S.R. Beck-Montgomery, "Selective Magnetic Enhancement of Pyrite in Coal by Dielectric Heating," Report No. IS-4766, Ames Laboratory, Iowa State University, 1982.
- [3] J.K. Kindig, "The Magnex Process: Review and Current Status," Proceedings of the Conference on Industrial Applications of Magnetic Separation, IEEE Publication No. 78, CH1447-2MAG, 1978.
- [4] J.Y. Hwang, G. Kullerud, M. Takayasu, F.J. Friedlaender, and P.C. Wankat, "Selective Seeding for Magnetic Separation," IEEE Transactions on Magnetics, Vol. MAG-18, pp. 1689-1691, 1982.
- [5] J.Y. Hwang, G. Kullerud, F.J. Friedlaender, and M. Takayasu, "Ultrafine Particle Processing: A Method for Alunite Beneficiation," Society of Mining Engineers of AIME, Transactions Vol. 280, pp. 1961-1964, 1986.
- [6] J.Y. Hwang, U.S. Patent 4,834,898, 1989.
- [7] J.Y. Hwang, U.S. Patent 4,906,382, 1990.
- [8] J.Y. Hwang, "Fine Coal Cleaning with Advanced Magnetic Enhancement Technology," Proceedings of the Sixth Annual Coal Preparation, Utilization, and Environmental Control Contractors' Conference, pp. 290-297, 1990.
- [9] Staff of the U.S. Bureau of Mines, "Bureau of Mines Cost Estimating System Handbook," U.S.B.M. IC-9143, 1987.
- [10] F.A. Holland, F.A. Watson, J.K. Wilkinson, "Process Economics," Perry's Chemical Engineering Handbook, Section 25, 6th Edition, 1984.
- [11] F.A. Peters, "Economic Evaluation Methodology," U.S. Bureau of Mines IC-9147, 1987.

APPENDIX I**FIGURES**

Figure 1.

The Structure of Magnetic Reagent

Figure 2. The adsorption of MR-30 (Na Oleate) on Various Minerals

Figure 3 The adsorption of MR-31 (Na lauryl sulfate) on various minerals

Figure 4 The adsorption of various anionic reagents on calcite

Figure 5 The adsorption of various anionic reagents on quartz

Figure 6 The adsorption of various anionic reagents on kaolinite

Figure 7 The adsorption of MR-30 on pyrite under various conditions

Figure 8 The adsorption of MR-31 on pyrite under various conditions

Figure 9 The adsorption of MR-1 (primary amine) on various minerals

Figure 10 The adsorption of MR-1 on pyrite under various conditions

**Figure 11 The adsorption of MR-45
(polyoxyethylene-4 lauryl ether)
on various minerals**

Figure 12 The adsorption of MR-45 on pyrite under various conditions

Figure 13 The effects of activators and depressants for the adsorption of MR-30 on calcite

Figure 14 The effects of activators and depressants for the adsorption of MR-30 on quartz

**Figure 15 The effects of surface modifiers
for the adsorption of cationic reagent (MR-3)
on calcite**

Figure 16 The adsorption of anionic, cationic, and nonionic magnetic reagents on coal

Figure 17 The effects of salts on the adsorption of anionic reagent (MR-30) on coal

Figure 18 The effects of salts on the adsorption of anionic reagent (MR-1) on coal

Figure 19 The effects of salts on the adsorption of anionic reagent (MR-45) on coal

Figure 20 Magnetic Enhancement of Minerals by MR-1 at Various Dosages

Figure 21 Magnetic Enhancement of Minerals by MR-45 at Various Dosages

Figure 22 Magnetic Enhancement of Calcite
by MR-30 at Various Dosages

SAMPLE PREPARATION FLOWSHEET

ILLINOIS #6 COAL SAMPLE

HEAD ANALYSIS

HEAT OF COMB 6823.2 CAL/G
 TOTAL SULFUR 3.94%
 PYRITIC SULFUR 1.56%
 SULFATE 0.04%
 ORGANIC SULFUR 2.34%
 ASH 22.44%
 FIXED CARBON 45.97%
 VOLATILES 31.82%
 MOISTURE 0.57%

SAMPLE PREPARATION FLOWSHEET

LOWER KITTANING SAMPLE

HEAD ANALYSIS

HEAT OF COMB 7708 CAL/G
 TOTAL SULFUR 2.43%
 PYRITIC SULFUR 1.39%
 SULFATE 0.07%
 ORGANIC SULFUR 1.03%
 ASH 6.37%
 FIXED CARBON 53.01%
 VOLATILES 39.29%
 MOISTURE 1.33%

SAMPLE PREPARATION FLOWSHEET

POCAHONTAS #3 COAL SAMPLE

HEAD ANALYSIS

HEAT OF COMB 6166 CAL/G
 TOTAL SULFUR 0.75%
 PYRITIC SULFUR 0.43%
 SULFATE 0.87%
 ORGANIC SULFUR 0.25%
 ASH 27.55%
 FIXED CARBON 58.49%
 VOLATILES 13.59%
 MOISTURE 0.37%

CONCENTRATION FLOWSHEET

ILLINOIS #6 COAL SAMPLE

ASSAY HEAD

100% WEIGHT
22.44% ASH
3.94% TOT SULFUR
1.56% PYR SULFUR

CALCULATED HEAD

100% WEIGHT
20.37% ASH
3.96% TOT SULFUR
2.06% PYR SULFUR

CONCENTRATION FLOWSHEET

LOWER KITTANNING COAL SAMPLE

ASSAY HEAD

6.37% ASH
2.43% TOT SULFUR
1.39% PYR SULFUR

CALCULATED HEAD

100% WEIGHT
5.78% ASH
2.27% TOT SULFUR
1.13% PYR SULFUR

CONCENTRATION FLOWSHEET

POCAHONTAS #3 COAL SAMPLE

ASSAY HEAD

100% WEIGHT
27.55% ASH
0.75% TOT SULFUR
0.43% PYR SULFUR

CALCULATED HEAD

100% WEIGHT
30.96% ASH
0.67% TOT SULFUR
0.28% PYR SULFUR

Figure 29. Size distribution of Illinois No.6 coal
at various grinding times.

Figure 30. Size distribution of Lower Kittanning coal
at various grinding times

Figure 31. Size distribution of Pocahontas coal
at various grinding times

Figure 32. Washability of Coal at -48 Mesh

**Figure 33. Washability of Coal at 90% Passing
100 Mesh**

Figure 34. Washability of Coal at 90% Passing
200 Mesh

Figure 35. Washability of Coal at 90% Passing
325 Mesh

Illinois No.6 Lower Kittanning Pocahontas

Figure 36. Washability of Coal at 90% Passing
500 Mesh

Figure 37. X-ray diffraction pattern and mineral interpretation of Illinois No. 6 coal.

Figure 38. X-ray diffraction pattern and mineral interpretation of Lower Kittanning coal.

Figure 39. X-ray diffraction pattern and mineral interpretation of Pocahontas coal.

Figure 40. Grain size frequency of Illinois No. 6 pyrite.

Figure 41. Grain size frequency of Lower Kittanning pyrite.

Figure 43. Coal cleaning with magnetic enhancement
at -48 mesh

Figure 44. Comparison of flotation and magnetic enhanced separation
 at -48 mesh for Illinois No.6 coal

Figure 45. Comparison of flotation and magnetic enhanced separation at -48 mesh for Lower Kittanning coal

Figure 46. Comparison of flotation and magnetic enhanced separation at -48 mesh for Pocahontas coal

Figure 47. Ash contents of Illinois N.6 coal at various particle size
using magnetic reagent cleaning method

Figure 48. Pyritic sulfur rejection of Illinois No.6 coal with magnetic reagent cleaning

Figure 49. Ash contents of low. Kittanning coal at various particle size
using magnetic reagent cleaning method

Figure 50. Pyritic sulfur rejection of Lower Kittanning coal with magnetic reagent cleaning

Figure 51. Ash contents of Pocahontas coal at various particle size
using magnetic reagent cleaning method

Figure 52. Pyritic sulfur rejection of Pocahontas coal with magnetic reagent cleaning

Matrix Selection

ILL. No.6 -48 mesh

Figure 53. Separation of -48 mesh Illinois No.6 coal
with various magnetic matrix

Figure 54. Separation of Illinois No.6 coal at 90% passing 200 mesh
with various magnetic matrix

Reagent Dosage Effect

ILL. No.6 -48 mesh

Figure 55. Magnetic reagent dosage for the separation of -48 mesh
Illinois No.6 coal

Figure 56 Magnetic reagent dosage for the separation of -200 mesh
Illinois No.6 coal

Reagent Dosage Effect

Low. Kittanning -48 mesh

Figure 57. Magnetic reagent dosage for the separation of -48 mesh

Lower Kittanning coal

Figure 58. Magnetic reagent dosage for the separation of -200 mesh
Lower Kittanning coal

Reagent Dosage Effect Pocanhontas -48 mesh

Figure 59. Magnetic reagent dosage for the separation of -48 mesh
Pocanhontas coal

Figure 60. Magnetic reagent dosage for the separation of -200 mesh
Pocahontas coal

Field Strength Effect
ILL.No.6 -48 mesh

Figure 61. Magnetic field strength effects for the separation of Illinois No. 6 at -48 mesh.

Figure 62. Magnetic field strength effects for the separation of Illinois No. 6 at 90% passing 200 mesh.

Field Strength Effect
Low. Kittanning -48 mesh

Figure 63. Magnetic field strength effects for the separation of Lower Kittanning at -48 mesh.

Field Strength Effect Low. Kittanning -200 mesh (90%)

Figure 64. Magnetic field strength effects for the separation of Lower Kittanning at 90% passing 200 mesh.

Figure 65. Magnetic field strength effects for the separation of Pocahontas at -48 mesh.

Figure 66. Magnetic field strength effects for the separation of Pocahontas at 90% passing 200 mesh.

Figure 67. Solids content effects for the separation of Illinois No. 6 at -48 mesh.

Figure 68. Solids content effects for the separation of Lower Kittanning at -48 mesh.

Figure 69. Solids content effects for the separation of Pocahontas at -48 mesh.

IL-200 Mesh (90%) Solid Content Effect

Figure 70. Solids content effects for the separation of Illinois No. 6 at 90% passing 200 mesh.

Figure 71. Solids content effects for the separation of Lower Kittanning at 90% passing 200 mesh.

Figure 72. Solids content effects for the separation of Pocahontas at 90% passing mesh.

Figure 73. Loading capacity for the separation of Illinois No. 6 at -48 mesh.

Figure 74. Loading capacity for the separation of Lower Kittanning at -48 mesh.

Figure 75. Loading capacity for the separation of Pocahontas at -48 mesh.

IL-200 Mesh (90%) Loading Capacity Effect

Figure 76. Loading capacity for the separation of Illinois No. 6 at 90% passing 200 mesh.

Figure 77. Loading capacity for the separation of Lower Kittanning at 90% passing 200 mesh.

Figure 78. Loading capacity for the separation of Pocahontas at 90% passing 200 mesh.

LK-48 Mesh

Figure 79. Total sulfur separation results of Lower Kittanning coal at -48 mesh by washability, flotation, and magnetic reagent methods.

Figure 80. Ash content separation results of Lower Kittanning coal at -48 mesh by washability, flotation and magnetic reagent methods.

Figure 81. Total sulfur separation results of Lower Kittanning coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent methods.

Figure 82. Ash content separation results of Lower Kittanning coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent methods.

IL-200 Mesh (90%)

Figure 83. Total sulfur separation results of Illinois No. 6 coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent methods.

IL-200 Mesh (90%)

Figure 84. Ash content separation results of Illinois No. 6 coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent methods.

Figure 85. Ash content separation results of Pocahontas coal at 90% passing 200 mesh by washability, flotation, and magnetic reagent methods.

APPENDIX II
TABLES

Coals by
Pyrite
1.5
48.5
52.3
38.6
24.4
24.1
37.1

Enhanced magnetic susceptibility of calcite
fresh and aged magnetizing reagent.

pH	Fresh	7 Months	10 Months
5	61.3	73.9	64.2
7	50.9	57.9	54.4
9	55.6	57.6	54.7
11	51.2	52.9	53.2
5	49.9	73.6	61.8
7	47.4	54.0	54.6
9	49.6	52.2	54.7
11	49.0	53.3	55.8
5	38.0	59.3	43.6
7	35.4	44.4	38.8
9	36.7	41.7	41.5
11	35.3	42.4	43.8
5	56.4	63.5	65.5
7	47.4	49.4	55.3
9	45.9	51.4	57.9
11	46.0	50.8	56.8
5	65.5	59.2	53.6
7	60.6	45.1	50.5
9	66.1	45.8	57.8
11	59.8	42.0	47.9

Page 161 and 162: this is the only
copy available

Table 3. Magnetic Particle Size and Corresponding Surfactant Consumption.		
	Surfactant (g/g Mt)	Calculated Magnetite Size (Å)
01-11	0.591	100 (reference)
01-12	0.473	160
01-13	0.473	190
01-14	0.473	250
01-21	0.443	140
01-22	0.369	170
01-23	0.295	190
01-24	0.295	210
30-11	0.569	100 (reference)
30-12	0.365	160
30-13	0.306	190
30-14	0.569	250
30-21	0.379	140
30-22	0.292	170
30-23	0.262	190
30-24	0.262	210

Table 4. Magnetite Particle Size Effect on
Magnetic Separation of Calcite Using MR-01
for Magnetic Enhancement.

	Magnetite Size Effect on Calcite Recovery at Different Dosage (Field Strength 5000 Gauss)				Magnetite Size Effect on Calcite Recovery at Different Dosage (Field Strength 3500 Gauss)			
Dosage (lb/ton)	01-11	01-12	01-13	01-14	01-11	01-12	01-13	01-14
2.0	44.03	30.87	12.39	8.46	33.19	22.51	16.46	9.91
4.0	78.83	55.83	38.64	18.55	65.37	51.75	27.93	18.75
8.0	95.51	90.89	82.28	41.33	92.05	84.41	63.54	36.23
12.0	99.24	95.31	83.79	57.99	97.67	92.68	76.99	50.00
Dosage (lb/ton)	01-21	01-22	01-23	01-24	01-21	01-22	01-23	01-24
2.0	34.27	21.09	6.05	10.35	22.17	16.39	6.41	8.70
4.0	42.37	36.02	23.72	17.90	41.98	31.44	20.25	12.63
8.0	68.54	59.25	40.30	23.85	65.93	52.98	44.01	24.90
12.0	91.74	68.79	49.08	28.27	86.92	59.88	45.77	35.41

Table 3. Magnetite Particle Size Effect on
Magnetic Separation of Calcite Using MR-30
for Magnetic Enhancement.

Dosage (lb/ton)	Magnetite Size Effect on Calcite Recovery at Different Dosage (Field Strength 5000 Gauss)				Magnetite Size Effect on Calcite Recovery at Different Dosage (Field Strength 3500 Gauss)			
	30-11	30-12	30-13	30-14	30-11	30-12	30-13	30-14
2.0	53.42	60.33	53.21	26.88	34.18	40.21	44.91	28.45
4.0	84.22	82.10	78.60	60.79	68.73	78.34	67.34	46.98
8.0	98.53	98.77	96.68	88.57	92.57	95.82	95.61	89.83
12.0	100.00	100.00	100.00	96.41	97.74	97.17	98.04	88.39
Dosage (lb/ton)	30-21	30-22	30-23	30-24	30-21	30-22	30-23	30-24
2.0	65.85	59.59	47.65	55.32	45.62	48.53	44.80	44.89
4.0	84.09	82.10	80.86	79.63	81.63	81.31	74.90	74.95
8.0	98.98	98.36	95.13	95.05	96.91	95.81	95.37	96.18
12.0	100.00	99.16	99.38	98.93	98.41	98.40	97.68	96.55

Table 6. Head analyses of the test coals.

	Illinois No. 6	Ohio Lower Kittanning	W. Virginia Pocahontas
Moisture %	0.57	1.33	0.37
Volatiles %	31.02	39.29	13.59
Fixed Carbon %	45.97	53.01	58.49
Ash %	22.44	6.37	27.55
BTU/lb	10,851	13,886	11,108
Total S%	3.94	2.43	0.75
Sulfate S%	0.04	0.07	0.07
Pyritic S%	1.56	1.39	0.43

Table 7. Maceral distributions.			
Seam	Vitrinite	Inertinite	Exinite
Illinois No. 6	95.96	1.87	2.17
Lower Kittanning	94.43	1.96	3.61
Pocahontas	96.70	3.23	0.07

Table 8. Particle size distributions of
pyrite in volume percent.

Size (μm)	Illinois No. 6	Lower Kittanning	Pocahontas
>250	12.05	8.9	24.07
100-250			25.60
50-100			24.85
25-50	16.87	25.1	17.63
10-25	16.34	29.3	7.10
5-10	29.69	22.1	0.75
1-5	22.75	12.3	
<1	2.31	2.3	

Table 9. Economic parameters for coal cleaning with the magnetic reagent approach.			
DESCRIPTION OF PARAMETER	UNIT	LOWER KITTANNING	ILLINOIS NO. 6
PLANT FEED RATE	TPH	100	100
COAL YIELD	%	87.72	63.37
BTU RECOVERY	%	92.88	79.72
PARTICLE SIZE	Mesh	90% -200	90% -200
FEED ASH CONTENT	%	6.37	22.25
PRODUCT ASH CONTENT	%	2.12	6.95
FEED TOTAL SULFUR	%	2.43	4.84
PRODUCT TOTAL SULFUR	%	0.96	2.55
RETENTION TIME	SECOND	3	3
APPLIED MAGNETIC FIELD	kilogauss	6	6
MAGNETIC MATRIX	TYPE	COARSE SCREEN	COARSE SCREEN
OPERATING HOURS	PER YEAR	7,200	7,200
CLEAN COAL	TON/YR	631,584	456,214
TOTAL CAPITAL COST	\$	1,956,649	1,956,649
PLANT LIFE	YEARS	20	20
DEBT INTEREST	%	11	11
DEBT FINANCING	%	100	100
CAPITAL COST/YEAR	\$/YR	242,356	242,356
CAPITAL COST/TON	\$/TON	0.34	0.34
O&M COST/TON	\$/TON	14.72	14.72
TOTAL COST/TON	\$/TON	15.06	15.06
CLEAN COAL COST/TON	\$/TON	17.17	23.77
CLEAN COAL COST/MBTU	\$/MBTU	0.58	0.87
\$/TON OF SO ₂ REMOVED	\$/TON	512	329

END

**DATE
FILMED**

5 / 26 / 93