RECEIVED
DOE/PC/89757

20 FEB 12 AM 11:13

DOE/PC/89757

DOE/PC/89757--1

DE92 040023

DE-AC22-

SURFACE STRUCTURE AND THERMODYNAMICS OF COALS

Quarterly Report for the Period
October 1, 1989 to December 31, 1989

Patrick C. Wernett and John W. Larsen

Department of Chemistry
Lehigh University
Bethlehem, Pa. 18015

RECEIVED BY 1031

AUG 2 1992

PREPARED FOR THE UNITED STATES DEPARTMENT OF ENERGY
Under Contract DE-AC22-89PC89757

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

OBJECTIVES AND SCOPE OF WORK

Objectives:

The objectives of this work are to investigate the surface structure and surface interaction thermodynamics of a variety of coals and treated coals in order to develop an understanding of the coal surface and how it changes.

Scope:

- (1) The deposition of NMR relaxation agents will provide spectra of atoms near the coal surface which will yield direct information about the structure of the surface groups.
- (2) Pore size distributions and the surface polarity of coals will be determined using ^{129}Xe NMR.
- (3) The steep dependence of surface area on adsorbate size will be mapped out for a variety of coals using BET gas adsorption techniques and a series of adsorbate gases varying in size and shape.
- (4) Full desorption isotherms of coals will be obtained by inverse gas chromatographic techniques.
- (5) A thermodynamic data base of coal surface-adsorbate interactions will be generated using classical calorimetric techniques.

Present Work:

Our present work this quarter has been the determination of the average micropore diameter of an Argonne Illinois No. 6 coal and a spherocarb sample by ^{129}Xe NMR. ^{129}Xe NMR spectroscopy has been used to determine pore sizes and surface characteristics in zeolites.¹⁻⁴ The chemical shift of ^{129}Xe was measured as a function of pressure and the average micropore diameter was calculated using established techniques.^{1,5} For the spherocarb, the calculated pore diameter of 15.4 Å agrees well with the manufacturer's reported value of 15 Å. The Illinois No. 6 coal gave two ^{129}Xe peaks. Extrapolation of the pressure dependent peak gave a micropore diameter of 5.2 Å. The other peak was not pressure dependent and is tentatively assigned to Xe dissolved in the coal.

The NMR chemical shift of ^{129}Xe is a useful probe of micropore (<20 Å diameter) size and surface characteristics. This application was developed principally by Fraissard and co-workers to determine pore size distributions and the degree of crystallinity in zeolites.^{1,5-7} The observed ^{129}Xe NMR chemical shift can be attributed to 4 factors: 1) the number of Xe-Xe collisions; 2) the electric field established by neighboring ions in the solid sample, found to be negligible for monovalent cations in zeolites; 3) the number of Xe-wall collisions; and 4) the nature of the interaction of Xe with the pore wall.²⁻⁴ The chemical shift due to Xe-wall collisions can be determined by extrapolation of ^{129}Xe NMR resonances to 0 Xe pressure. The ^{129}Xe

NMR chemical shift due to Xe-wall collisions is directly related to the mean free path of the Xe atom in the pore. From the diameter of the Xe atom ($4.4 \text{ \AA}$) and its mean free path in the pore, the dimensions of the pore can be calculated if the pore shape is assumed.^{1,5}

To test this NMR technique on a carbonaceous substance, a standard $15 \text{ \AA}$ diameter molecular sieve (spherocarb, Analabs Inc.) was studied. Xenon gas (99.995% , Air Products Co.) was used in all experiments. Sample tubes were loaded in a N_2 filled glovebox and degassed for no less than 6 hrs. at 10^{-5} torr on a glass vacuum line equipped with a diffusion pump and a Barocel pressure sensor to measure Xe gas pressures. All spectra were obtained on a Bruker AM 500 MHz spectrometer operating at 138.3 MHz. The chemical shifts are expressed relative to the free ^{129}Xe gas peak and are always positive.

The ^{129}Xe NMR chemical shift dependence on Xe gas pressure is presented in Figure 1 for a spherocarb sample. Demarquay and Fraissard have developed a semi-empirical relationship between the ^{129}Xe NMR chemical shift at 0 pressure (δ_0) and the mean free path ($\bar{l}$) of Xe adsorbed in some model zeolites.^{1,5} Assuming the pore shape of the spherocarb to be spherical, a pore diameter of $15.4 \text{ \AA}$ is obtained by this NMR method. This value agrees remarkably well with the pore diameter of $15 \text{ \AA}$ reported by Analabs. We were encouraged to proceed with coals.

The ^{129}Xe NMR spectra in descending Xe gas pressures on an Illinois No.6 coal are shown in Figure 2. The furthest upfield

peak is due to free Xe gas and is assigned a chemical shift value of 0 ppm. ^{129}Xe in the Illinois No. 6 coal gives rise to two distinct resonances. The peak furthest downfield (peak A) shows a chemical shift dependence on Xe pressure and extrapolates to 179 ppm at 0 Xe pressure. This is what is expected of Xe in a pore. The width of the peak is assumed to be due to the distribution of micropore sizes in the coal sample. Using the peak center, a mean free path for Xe of $0.4 \text{ \AA}$ was calculated. Assuming spherical pores, an average pore diameter of $5.2 \text{ \AA}$ for the Illinois No. 6 coal is obtained. Data verifying this pore diameter were not found. Experimental techniques such as SANS^{8,9} and SAXS^{10,11} cannot resolve micropore diameters of coals less than $10 \text{ \AA}$.

The chemical shift of peak B is independent of Xe gas pressure. One possibility for Peak B is that its resonance is due to micropores that can only accommodate one Xe atom. This is implausible because the ^{129}Xe NMR chemical shift increases as pore size decreases,⁵ and peak A has a greater ^{129}Xe NMR chemical shift than peak B. Peak B is tentatively assigned to Xe dissolved in the coal. Reucroft and Patel have shown by dilatometric studies that Xe is slightly soluble in 3 Kentucky coals ranging from 65.8 to 83.8% C daf.¹² This would explain the insensitivity of the ^{129}Xe NMR chemical shift of resonance B to varying Xe gas pressure.

We are currently extending the ^{129}Xe NMR work to the full series of Argonne coals. We are also developing a computer modeling program which will provide a pore size distribution based

on the total area under the ^{129}Xe NMR resonance peak, as the peak shape would appear at 0 Xe concentration. The preliminary results presented here show that this technique is a promising, convenient method for determining the micropore sizes in coals, requiring only a vacuum line with a good pressure measuring device, high purity Xe gas, and an NMR spectrometer.

REFERENCES

1. Fraissard, J. ; Ito, T. *Zeolites* 1988, 8, 350-361.
2. Ito, T. ; Fraissard, J. *J. Chem. Phys.* 1982, 76 (11), 5225-5229.
3. Ito, T. ; De Menorval, L. C. ; Guerrer, E. ; Fraissard, J. P. *Chem. Phys. Lett.* 1984, 111 (3), 271-274.
4. Johnson, D. W. ; Griffiths, L. *Zeolites* 1987, 7, 484-487.
5. Demarquay, J. ; Fraissard, J. *Chem. Phys. Lett.* 1987, 136 (3,4), 314-318.
6. Benslama, R. ; Fraissard, J. ; Albizane, A. ; Fajula, F. ; Figueras, F. *Zeolites* 1988, 8, 196-198.
7. Springuel-Huet, M. A. ; Ito, T. ; Fraissard, J. *Structure and Reactivity of Modified Zeolites* Elsevier Science Publishers B. V. : Amsterdam, 1984.
8. Gethner, J. S. *J. Appl. Phys.* 1986, 59 (4), 1068-1085.
9. Tricker, M. J. ; Grint, A. ; Audley, G. J. ; Church, S. M. ; Rainey, V. S. ; Wright, C. J. *Fuel*, 1983, 62, 1092-1096.
10. Schmidt, P. W. ; Kwak, C. Y. ; Kalliat, M. *Prepr. Pap. - Am. Chem. Soc., Div. Fuel Chem.* 1983, 28 (4), 75-80.
11. Lin, J. S. ; Hendricks, R. W. ; Harris, L. A. ; Yust, C. S. *J. Appl. Cryst.* 1978, 11, 621-625.
12. Reucroft, P. J. ; Patel, H. *Fuel* 1986, 65, 816-820.

Figure 1. ^{129}Xe NMR chemical shift pressure dependence on 15 Å spherocarbs. (●) Xe adsorption (■) Xe desorption

Figure 2. NMR spectra of ^{129}Xe in Argonne Illinois No. 6 coal at various Xe gas pressures.

$$\delta_{o(A)} = 179 \text{ ppm}$$

where: $\delta_{o(A)}$ is the ^{129}Xe NMR chemical shift at zero $\text{Xe}_{(g)}$ pressure based on the center of peak A.

END

DATE
FILMED

10 / 20 / 92