RECEIVED
JUL 26 1993
OSTI

Progress Report
Covering

**The ANL Electric Vehicle Battery
R&D Program
for
DOE-EHP**

Electrochemical Technology
Program
Electrochemical Technology
Program
Electrochemical Technology
Program

for the Period

January - March 1993

Prepared for the

**DOE Office of Propulsion Systems
Electric and Hybrid Propulsion Division**

Argonne National Laboratory, Argonne, Illinois 60439
operated by The University of Chicago
for the United States Department of Energy

Chemical Technology
Division
Chemical Technology
Division
Chemical Technology
Division
Chemical Technology
Division

June 15, 1993

REPRODUCTION OF THIS DOCUMENT IS UNLIMITED

Argonne National Laboratory, with facilities in the states of Illinois and Idaho, is owned by the United States government, and operated by The University of Chicago under the provisions of a contract with the Department of Energy.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Progress Report

Covering

The ANL Electrochemical Program

for

DOE on Electric Vehicle R&D

for the period

January - March 1993

Prepared for the

***DOE Office of Propulsion Systems
Electric and Hybrid Propulsion Division***

June 15, 1993

MASTER

CHLORINE AND BROMINE OXIDES AND HYDROGEN PEROXIDE

rb

TABLE OF CONTENTS

	<u>Page</u>
Section I. PROJECT HIGHLIGHTS	1
Section II. INTRODUCTION	2
Section III. TECHNICAL PROGRESS AND STATUS	3
TASK AREA 1.0 PROJECT MANAGEMENT	3
TASK AREA 2.0 SODIUM/METAL CHLORIDE R&D	3
TASK AREA 3.0 MICROREFERENCE ELECTRODES FOR LITHIUM/POLYMER BATTERIES	5

Section I

PROJECT HIGHLIGHTS

TASK 1.0 PROJECT MANAGEMENT

- The DOE contract with SAFT America to develop Li/FeS batteries remains in effect. However, no new funding has been provided and SAFT's efforts were limited to the preparation of a draft copy of the final executive summary report. This report was delivered to ANL and reviewed. ANL is currently discussing the issuance of this report with DOE/EHP.
- In the area of DOE's ad hoc EV Battery Working Group activities, efforts of the Shipping SubWorking Group led to the issuance of a general shipping exemption for "hot" sodium-beta batteries by the U.S. Department of Transportation. As sponsor of the application, Ford was granted the exemption (DOT-E-10917) and four sodium-beta battery developers applied for party status.

TASK 2.0 ADVANCED SODIUM/BETA BATTERIES

- The first full-scale sealed cell fabricated by the Hughes Aircraft Company with the ANL nickel chloride electrode technology failed on start up because of a cracked β -alumina tube.
- Experiments on the performance of the sintered nickel chloride electrode as a function of thickness have now been completed for three thicknesses; 0.2-0.3 cm, 0.4-0.5, and 0.7-0.8 cm.
- Experiments have been initiated with unsintered nickel chloride electrodes to evaluate the effect of the ANL-92 electrode additives on the performance of the sodium/nickel chloride cells using the AEG cell design.

TASK 3.0 MICROREFERENCE ELECTRODES FOR LITHIUM/POLYMER BATTERIES

- Ultra-thin tin films (50-1000Å) were deposited (physical vapor deposition; PVD or ion-beam assisted deposition; IBAD techniques) onto a substrate and fabricated into an electrochemical cell. The films were investigated as a possible reference electrode material. These tin film electrodes were galvanostatically loaded *in-situ* with lithium in a polymer-electrolyte cell. The resulting phases, possibly two-phase regions, give stable, reversible and reproducible open circuit cell voltages.

Section II

INTRODUCTION

The Electrochemical Technology Program at Argonne National Laboratory (ANL) provides technical and programmatic support to DOE's Electric and Hybrid Propulsion Division (DOE-EHP). The goal of DOE-EHP is to advance promising electric-vehicle (EV) propulsion technologies to levels where industry will continue their commercial development and thereby significantly reduce air pollution and petroleum consumption due to the transportation sector of the economy. In support of this goal, ANL provides research, development, testing/evaluation, post-test analysis, modeling, and project management on advanced battery technologies for DOE-EHP.

This report summarizes the battery-related activities undertaken during the period of January 1, 1993 through March 31, 1993. In this report, the objective, background, technical progress, and status are described for each task. The work is organized into the following task areas:

- 1.0 Project Management
- 2.0 Sodium/Metal Chloride R&D
- 3.0 Microreference Electrodes for Lithium/Polymer Batteries

Section III

TECHNICAL PROGRESS AND STATUS

TASK 1.0 PROJECT MANAGEMENT

The DOE contract with SAFT America to develop Li/FeS batteries remains in effect. However, no new funding has been provided and SAFT's efforts were limited to the preparation of a draft copy of the final executive summary report. This report was delivered to ANL and reviewed. ANL is currently discussing the issuance of this report with DOE/EHP.

In the area of DOE's ad hoc EV Battery Working Group activities, efforts of the Shipping SubWorking Group led to the issuance of a general shipping exemption for "hot" sodium-beta batteries by the U.S. Department of Transportation. As sponsor of the application, Ford was granted the exemption (DOT-E-10917) and four sodium-beta battery developers applied for party status.

TASK 2.0 ADVANCED SODIUM/METAL CHLORIDE BATTERIES

Objectives and Background

This task area seeks to develop improved positive electrodes and electrolytes for use in batteries based on sodium electrodes and sodium-ion conducting solid electrolytes. The overall objective is to stimulate commercialization of low-cost advanced batteries with performance and reliability levels that meet the established goals for electric vehicle propulsion. To achieve these goals, the sodium/nickel chloride task focuses on developing cells with high electrode/electrolyte surface area and nickel chloride electrodes with improved utilization and reduced impedance.

Sodium/nickel chloride (Na/NiCl_2) batteries offer many attractive properties: high cell voltage, high theoretical specific energy, broad range in operating temperature, and high reliability due to a failure mode that results in a hard short-circuit within the failed cell. The specific power and specific energy of present state-of-the-art (SOA) batteries, however, is modest because of the performance-limiting characteristics of the nickel-chloride electrode.

The main objective of this task is the development of an advanced Na/NiCl_2 battery technology that meets the established USABC goals for EV battery applications. The strategies of our development approach are to (1) fully understand and improve the chemistry and morphology of the nickel chloride electrode in order to enhance performance, (2) continue studies to investigate the viability of nickel metal as a current collector and cell case assembly for the Na/NiCl_2 battery, (3) measure the dynamic-performance (DST) of Na/NiCl_2 research cells, (4) project performance (W/kg and Wh/kg) of full-size batteries for static and dynamic load conditions, (5) optimize cell and battery designs, and (6) verify the projected performance in sealed cells. ANL also seeks to identify industrial partners with the interest and capabilities to incorporate ANL-developed technology into a viable commercial product. The emphasis of our efforts during the past three months has been focused on the development of full-scale sealed cells and the characterization of Ni/NiCl_2 electrodes that would be used in such cells.

Technical Progress and Status

In the reporting period, our research has progressed along two avenues: (1) design and testing of sealed Na/NiCl₂ cells and (2) experimentation with small-scale engineering research cells to improve our understanding of the chemistry and performance controlling parameters of the nickel chloride electrode.

Sealed 30-Ah Na/NiCl₂ cells were designed and fabricated in collaboration with Hughes Aircraft Co., Torrance, CA. The cell design and electrode preparation methods were based on the previously reported ANL-92 electrode technology. The cell has an outside nickel electrode and incorporates the ANL-92 electrode chemical additives. The goal of this effort, in addition to verifying the performance of the ANL-92 electrode in full-size sealed cells, is to develop the technical know-how for the new sodium/nickel chloride technology and establish performance parameters of this new cell.

Several technology related problems were solved during the fabrication of the first cell. For example, problems associated with pressing and sintering of the large donut-shaped nickel electrode and proper use of the performers for electrode fabrication have been addressed. Safe procedures for cell fabrication, activation, and testing have been established.

The first cell (sent to ANL on March 8, 1993), however, failed as a result of short circuit during the initial heat-up producing as low as a 50 mohm internal resistance before it was possible to initiate the electrochemical performance evaluation. The cell failure did not cause any safety related problem. Thermographic short-circuit location detection and x-ray techniques identified a crack in the β -alumina tube. The crack presumably developed during fabrication and propagated during the heat-up providing free passage for the liquid sodium to the nickel electrode. This cell failure demonstrates again the technical and human safety features of the Na/NiCl₂ system. New cells are being built and will be tested in the next quarter.

In addition, we have continued our research to further improve the nickel chloride electrode and measure performance parameters of various electrode designs. Power and energy performance as function of electrode thickness and electrode/liquid electrolyte volume ratios were investigated in 1- to 2-Ah capacity engineering research cells under a wide variety of conditions including the newly developed power dynamic conditions that simulate electric vehicle driving loads.

The experiments to determine the thickness effect on the performance of the Ni/NiCl₂ electrode have now been finished on the thick (0.7-0.8 cm), the mid-thickness (0.4-0.5 cm), and the thin (0.2-0.3 cm) electrodes. Analyses of the digitally stored data of these measurements is being continued. New electrodes are being prepared for the performance characterization of very thick (1.25-1.30 cm) Ni/NiCl₂ electrodes. Our measurements have shown that both the electrode thickness and electrolyte volume fraction are important design factors because these parameters significantly influence cell performance.

We have initiated experiments with the unsintered Ni/NiCl₂ electrodes to evaluate the effect of the ANL-92 electrode additives on the performance of Na/NiCl₂ cells using the AEG cell design. These characterization studies are important since AEG may consider using the ANL-92 electrode additives in their battery cells that utilize unsintered Ni/NiCl₂ electrodes.

TASK 3.0 MICROREFERENCE ELECTRODES FOR LITHIUM/POLYMER BATTERIES

Objective and Background

The objective of this program is to develop reference electrodes and their application methodology for advanced Li/polymer electrolyte (LIPE) cells.

Reference electrodes are valuable tools for battery R&D. They provide a means for performance analysis of electrodes in working cells and batteries, thereby suggesting effective ways to improve the overall performance of the battery system. To obtain reliable information with reference electrodes, however, a measuring procedure must be established and strictly followed. Details of the measuring procedure depend on the cell system under investigation and must be in agreement with the intended end use of the cell or battery.

In this research program, microreference electrodes will be developed for LIPE cell systems. The basic determinant for the selection of the reference electrode is the chemistry of the LIPE cell itself. Chemical compatibility between the reference electrode and the LIPE cell, as well as the electrochemical stability of the reference electrode must be established to assure long-term functioning. Special thin-film preparation techniques will be used to make the configuration of the reference electrode compatible with the predominant feature, the thinness, of the LIPE cell.

The small dimensions of the reference electrode, the ultra-thin cell components, and the special configurations of the LIPE battery require investigations of the placement of the reference electrode to ensure that it is functioning properly for the electrode and cell performance evaluation. The techniques developed in other advanced battery R&D programs will be adapted and refined so that precise electrode impedance, current distribution, energy, and power data can be measured. The acquired data set will be directly applicable for evaluation and improvement of cell chemistry, geometry, and performance as well as for use in design studies to project the performance of full-size cells/batteries.

Technical Progress and Status

During this last reporting period, work continued on developing a lithium-polymer cell reference electrode based on the binary metallic lithium-tin (Li_xSn) alloy. We have advanced our study of this material from an initial electrochemical examination of bulk (thick) tin foil samples to new tin thin-film specimens. The specimens were prepared as ultra-thin tin layers (50-1000 Å) *ex-situ* using vacuum evaporation-deposition techniques onto sputter-cleaned stainless steel foil substrates (10 mil or 254 µm thick). Adhesion appears good and passes a rudimentary Scotch tape touch test. Two electrode cells containing the tin thin-films with a polymer-electrolyte film ($\text{PEO}_{10}\text{-LiCF}_3\text{SO}_3$; 5 mil or 120-130 µm thick) and lithium foil (12 mil or 300 µm thick) were fabricated. These cell component layers were stacked together and then vacuum-sealed at 100-110°C to provide a good interfacial contact.

The various sample types and thin-film techniques used are summarized in Table 1. The "X"'s in the table indicate the specimens prepared and the "F"'s show which specimens were further fabricated into a polymer cell. Typical exposed area for electrochemical testing was approximately 4 to 6.5 cm² and was dependent on the cell configuration. Dr. Bob Erck of ANL-MCT kindly provided his expertise and equipment in the vacuum evaporation-deposition steps.

Table 1. Summary of Tin Thin-film Specimens.

Thickness ^a (Å)	Sample Type ^{b,c,d}		
	PVD	IBAD (Ar ⁺)	IBAD (Ar ⁺ /O ₂)
1000	X,F	X,F	X
500	X,F	X,F	--
50	X	X	X

- a. true tin thickness is 90% of nominal thickness
- b. PVD = Physical Vapor Deposition; IBAD = Ion-Beam Assisted Deposition
- c. sample substrate for all specimens is 2 mil thick stainless steel foil; l x w = 3"x1.5"
- d. prior to deposition, all specimens were sputter-cleaned by ion bombardment (500 eV) for five minutes

After the cells were brought to operating temperature (95-100°C), the tin layers were loaded with lithium by a constant current galvanostatic technique. The lithium-tin alloy (Li_xSn) was made electrochemically by reducing Li^+ at the Sn thin-film electrode. Current was applied to the $\text{Li(s)}/\text{PEO}_{10}\text{-LiCF}_3\text{SO}_3/\text{Li}_x\text{Sn(s)}$ cell in a square wave pattern, in which current was passed for ten minutes, then interrupted for ten minutes to allow for cell relaxation. In this manner the open-circuit voltage could be followed over time. The composition of the alloy was varied by coulometrically loading within a fairly large range of x , beginning with $x = 0$.

Figure 1 shows the cell voltage response of the 500Å (PVD) specimen over the course of the first 67 hours of coulometric loading. Steady-state conditions were established after approximately 0.24 Coulombs of current had passed. This condition gives a stable voltage range under open circuit conditions at 0.728 to 0.740 V (Phase I). The first voltage plateau (Phase I) matches that found in the earlier bulk tin foil experiments which had shown excellent open circuit voltage stability at an average cell voltage of 0.732 V (+/- 0.17 mV) vs. lithium foil. Since the total amount of tin contained in a nominally 500Å layer (Area = 6.413 cm²) is quite small, being approximately 1.76 micromoles, then only a small amount of loading is necessary to produce a stable binary phase. Furthermore, the volume or density change induced within the tin thin-film during lithium loading is negligible to the overall cell and this allows for precise electrochemical data measurement and control. The capacity experimentally found is calculated to a stoichiometric ratio of $\text{Li}_{1.4}\text{Sn}$. This voltage plateau is maintained during additional charging at the same rate. After approximately 0.072 Coulombs of additional charge had been passed then the voltage began decreasing into a second region of steady-state stability at a range of open circuit voltage values from 0.630 to 0.645 V (Phase II). The experiment was terminated at the 67th hour. The stoichiometric range of the first voltage plateau (Phase I) at approximately 0.734 V is therefore calculated as $\text{Li}_{1.4}\text{Sn}$ to $\text{Li}_{1.82}\text{Sn}$.

Fig. 1. Voltage of the $\text{Li}/\text{PEO}_{10}\text{-CF}_3\text{SO}_3/\text{Sn}$ cell during square-wave current profile to reduce Li at the Sn electrode at ca. 97°C . The tin layer is a thin-film ($500\text{\AA}$ - PVD) on stainless steel foil. Note the presence of two stable phases I and II.

Figure 2 shows a continuation of experiments with this specimen. Reversing the current to unload the Li^+ from the tin (same parameters as load) causes the voltage to increase from the lower voltage plateau (Phase II) back up to Phase I voltage, thus exhibiting reversibility. While the emf of this returned phase remains constant over an additional discharge of 0.04 Coulombs, this returned capacity falls short when compared to its initial loading value. The cell voltage increases abruptly at approximately the 4th hour, but can be brought back by reloading the tin until the voltage had returned to the Phase I level. Under open circuit conditions however, this voltage does not remain with that phase, but instead settles to a higher level at approximately 1.31 V. This voltage increase was also seen with a $1000\text{\AA}$ (PVD) tin thin-film on the stainless steel foil substrate.

The slow open circuit potential increase for PVD samples to 1.31 V and higher suggests a loss of the Li_xSn material from the substrate sample. Thus the tin thin-film may be losing its adhesion to the underlying substrate and then eventually dissolve or become suspended in the polymer-electrolyte matrix as particulate matter. A similar voltage increase was experienced with thin-films of aluminum (Al) on nickel substrate.

There are various techniques which may be used when depositing thin-films of materials. For instance, with the deposition of main group elements (i.e. C, Al, Sn, Pb, Si, etc.), the adhesion to the underlying substrate is greatly enhanced when an Ion-Beam Assisted Deposition (IBAD) process is employed versus conventional Physical Vapor Deposition (PVD). Physisorption appears stronger with these types of specimens due to an increase in atomic layer mixing at the interface. Impinging low energy argon gas ions provide the energy necessary to mix the tin vapor with surface metallic atoms on the substrate. The kinetic energy of the ion gas is transferred to the specimen surface by a recoil process.

Fig. 2. Cell voltage profile following experimentation in Fig. 1. The current was reversed to reduce Li at the Li electrode (negative electrode). After approximately five hours the current is switched to reduce Li at the Sn electrode (positive electrode). The potential increases after the 8th hour due to thin-layer instability.

Thus, to complement our study, identical experiments were conducted using a 1000Å IBAD tin thin-film sample. Figure 3 shows the cell voltage profile during a loading experiment. Current was delivered following a square wave profile at ca. $1.0 \mu\text{A}/\text{cm}^2$ current density. Table 2 summarizes the voltage plateaus and capacity ratios. This figure shows three steady-state voltage plateaus, suggesting three two-phase regions. The open circuit voltage of plateau III was monitored during the two weeks after the initial 60 hours and displayed good stability within a few millivolts of 0.520 V.

According to the Li-Sn binary phase diagram, the next phase of composition Li_7Sn_3 should begin at ca. the 45th hour of the experiment (see Fig. 3). At this point the voltage might have been expected to drop as lithium activity increases in the tin thin-film. However, voltage was maintained at open circuit conditions which suggests that Li-rich phases are not well-defined in this system in a temperature range of 95-100°C.

Further experiments, shown in Figure 4, demonstrate that the lithium from the tin thin film can be unloaded by reversing the current ($j = -3.8 \mu\text{A}/\text{cm}^2$). This suggests that the IBAD tin thin film is quite stable and electrochemically reversible, both necessary requirements for a good reference electrode.

In summary, the IBAD sample's voltage has not increased under open circuit conditions, unlike the PVD specimens. This implies that the tin thin-film layer deposited using ion-beam assisted deposition does indeed form a strong physisorbed bond to the substrate. Strong bonding or adhesion to the substrate is an important criteria to cover in searching for a thin-film microreference electrode. These tin films can be readily alloyed with lithium during *in-situ* electrochemical loading in a polymer-electrolyte cell. The resulting phases which may be two-phase regions appear to give stable, reversible and reproducible open-circuit cell voltages.

Fig. 3. Voltage of $\text{Li}/\text{PEO}_{10}\text{-LiCF}_3\text{SO}_3/\text{Li}_x\text{Sn}$ cell during square-wave current profile ($j = 1.0 \mu\text{A}/\text{cm}^2$) to reduce Li at the Sn thin-film electrode at 97°C . The tin layer is a thin film ($1000 \text{ \AA}$ -IBAD) on stainless steel foil. Plateaus I, II, and III represent distinct phases of the Li_xSn layer.

Table 2. Summary of Partial Coulometric Titration of $1000 \text{ \AA}$ IBAD Tin Sample

Loading Plateau #	Nominal Composition of Phases Present	Stoichiometric Ratio Range Li/Sn	Approximate Voltage E vs. E_{Li} Volts (100°C)
I	$\text{Li}_2\text{Sn}_5 + \text{Sn}$	≤ 0.4	0.733
II	$\text{Li}_2\text{Sn}_5 + \text{LiSn}$	0.4 - 1.0	0.632
III	$\text{LiSn} + \text{Li}_{1+x}\text{Sn}$	> 1.0	0.535

Quantitative phase determination and additional coulometric titrations are currently being carried out. We also plan to analyze the kinetics of lithium diffusion within these phases in the polymer cells. This data should help to determine what phase (voltage plateau) the Li_xSn reference electrode should reside in to maximize its voltage sensing capabilities and sensitivity. The material's continued long-term (> 2 months) voltage stability and chemical compatibility within the solid polymer-electrolyte will be examined.

Fig. 4. Voltage of $\text{Li}/\text{PEO}_{10}\text{-LiCF}_3\text{SO}_3/\text{Li}_x\text{Sn}$ cell during square-wave current profile to reversibly oxidize and reduce Li at the Li_xSn electrode of Figure 3. The applied current density was $\pm 3.8 \mu\text{A}/\text{cm}^2$ during this experiment. Note once again the presence of three voltage plateaus (I, II, and III), at approximately 0.535, 0.632, and 0.733 volts vs. Li were observed.

END

**DATE
FILMED**

9/2/93