RADIATIVE PROPERTIES OF ASH AND SLAG

Ninth Quarterly Report

#523050-27

For the Period

October 1, 1989 to December 31, 1989

PETER R. SOLOMON

and

JAMES R. MARKHAM

Work Performed Under Contract No. DE-AC22-87PC79901

for

U.S. DOE - PITTSBURGH ENERGY TECHNOLOGY CENTER

by

ADVANCED FUEL RESEARCH, INC.

87 Church Street
East Hartford, CT 06108
(203) 528-9806

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Research, analytical services and consulting for the development of new and improved clean fuels

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States Government nor the United States Department of Energy, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned right. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The view and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PATENT STATUS

"U.S. DOE Patent Clearance is not required prior to the publication of this document".

ABSTRACT

Thermal radiation plays a key role in the operation and efficiency of combustion systems, accounting for over 90% of the heat transfer. The analysis of radiative heat transfer in coal-fired boilers, combustion chambers and other energy systems requires accounting for the effects of inorganic deposits on bounding surfaces and of entrained particulates, such as pulverized coal, char, and fly-ash. These effects can be predicted; however, the accuracy in predicting the radiative properties of entrained pyrolysis (ash) and deposit layers (slag) is limited by inaccurate knowledge of the physical/chemical properties of the materials over a range of material temperatures and radiative wavelengths that is representative of conditions in practical combustion systems. The objective of this project is to make laboratory measurements of the radiative properties of extracted ash and slag deposit samples.

RADIATIVE PROPERTIES OF ASH AND SLAG

TABLE OF CONTENTS

Disclaimer	i
Abstract	ii
I. INTRODUCTION	1
II. PROGRESS SUMMARY	2
II.1. Task 1 - Project Implementation Plan	2
II.2. Task 2 - Measurement Technique Validation	2
II.3.a Task 3.a - Deposit Sample Acquisition	2
II.3.b Task 3.b - Deposit Sample Characterization	2
II.4. Task 4 - Measurement of Radiative Properties of Ash Deposit Samples	2

I. INTRODUCTION

Thermal radiation plays a key role in the operation and efficiency of combustion systems, accounting for over 90% of the heat transfer. The radiative heat transfer in coal-fired boilers is dominated by the properties of inorganic deposits and bounding surfaces, and of particulates, which are present in the system. The properties governing the emission, absorption, and attenuation of the radiative energy by deposits and entrained particulates are a key element in accurately predicting the radiative heat transfer. They are also necessary for in-situ determination of current deposit condition (composition, temperature) from optical measurements. The radiative properties of particles are characterized by the extinction efficiency, absorption efficiency (or emissivity) and scattering efficiency. That of deposits by the reflectance, transmittance, and absorptivity. These characteristics depend on the complex refractive index, the particle size or layer thickness and the material's morphology (porosity, inhomogeneities, grain boundaries, etc.).

This project will determine the radiative properties of deposits extracted from combustion devices. Measurements of radiative properties of materials at high temperatures are made by a technique employing a sample heating device that is coupled to a Fourier Transform Infrared (FT-IR) spectrometer to measure emission, hemispherical-directional transmission, and hemispherical-directional reflection of a sample. By this technique, the temperature at the measurement point and the spectral emittance (emissivity) of the surface can both be obtained. The complex index of refraction that is required to calculate emissivities is determined by a transmission spectroscopic technique that employs fine sample particulates suspended in KBr and CsI matrices.

During this quarter, the program was temporarily discontinued by PETC administrators. The work that was accomplished in the limited time further demonstrates the effects of deposit surface texture on observed radiative properties.

II. PROGRESS SUMMARY

II.1. Task 1 - Project Implementation Plan

Completed in the third quarter and approved in the fourth quarter.

II.2. Task 2 - Measurement Technique Validation

Completed in the seventh quarter and discussed in detail in the seventh quarterly report.

II.3.a. Task 3.a - Deposit Sample Acquisition

Completed in the seventh quarter.

II.3.b. Task 3.b - Deposit Sample Characterization

No work was performed during this quarter due to the temporary discontinuance of the project by PETC administrators.

II.4. Task 4 - Measurement of Radiative Properties of Ash Deposit Samples

Work in this task during this quarter was abbreviated by the temporary discontinuance of the project by PETC administrators.

This program has demonstrated that the physical characteristics of the deposits greatly influence the spectral emittance. Figure 4.1 reviews the differences observed in spectral emittance between fused, sintered, and powdery deposits for samples #1 and #7. For these opaque samples, the emittance, and hence, the reflectance of the material is clearly influenced by the texture of the sample.

To further substantiate the effect of texture on radiative property measurements, reflectance and transmittance measurements were performed on pressed pellets of KBr, which has a low absorption coefficient in the IR and is transparent when it is in homogeneous pellet form (i.e., the form of a KBr optical window). The data are presented in Fig. 4.2. Under 10 tons of pressure, the reflectance is about 7%, while the transmittance is 90%. The KBr pellet can retain internal cracks and surfaces if the pressure applied is insufficient to fuse the material. At one-half ton pressure, the reflectance is as high as 50% and the transmittance reduced to 30%. At only 170 lbs of pressure, the reflectance is as high as 70% with the transmittance near zero. In principal, the reflectance and transmittance should add to 100% for this non-absorbing material; but because of the pellet's diffuse scattering, the reflected or transmitted radiation can emerge from the surface so far from the entrance point that it is not recovered by our collection optics which are directed at the entrance point. The influence of sample texture is, however, clearly demonstrated.

Plans and Objectives for Next Quarter

Upon continuance of the program, work will concentrate on identifying the parameters necessary as input for model predictions as discussed in the Eighth Quarterly report.

Figure 4.1. Measured Spectral Emittance for a) Sintered Slag Deposit (sample #1) Compared to the Material After Grinding and Pressing into a Wafer; and After Thermally Fusing the Material and b) Powderly Ash (sample #7) Compared to the Emittance After Thermally Fusing the Material.

Figure 4.2. Pressure Influence on a) Reflectance and b) Transmittance for Pressed Wafers (1 mm thick) of KBr Powder at 25°C.

END

**DATE
FILMED**

11 / 12 / 92